

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
23 July 2009 (23.07.2009)

PCT

(10) International Publication Number
WO 2009/090208 A1(51) International Patent Classification:
B29C 55/18 (2006.01)

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(21) International Application Number:
PCT/EP2009/050412

(22) International Filing Date: 15 January 2009 (15.01.2009)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0800828.6 17 January 2008 (17.01.2008) GB
0814308.3 5 August 2008 (05.08.2008) GB

(71) Applicant and

(72) Inventor: RASMUSSEN, Ole-Bendt [DK/CH]; Sagenstrasse 12, CH-6318 Walchwil (CH).

(72) Inventor; and

(75) Inventor/Applicant (for US only): RASMUSSEN, Nikolai Wettergren [CH/CH]; Sagenstrasse 12, CH-6318 Walchwil (CH).

(74) Agent: JONES, Helen Marjorie Meredith; Broadgate House, 7 Eldon Street, London EC2M 7LH (GB).


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(54) Title: FILM MATERIAL EXHIBITING TEXTILE PROPERTIES AND METHOD AND APPARATUS FOR ITS MANUFACTURE

Fig. 2a



predominant original orientation, at least one of the grooved rollers having crests with sharp edges to form the division between regions A and webs B and to stretch the material to form webs B while stretching the material less or not at all to form regions A. Preferably at least one of the grooved rollers has crests with a waved surface shape.

(57) Abstract: A film material formed of thermoplastic polymer material is processed so as to have linearly extending regions (A) linked together by linearly extending webs (B), regions (A) and webs (B) each being oriented, the dominant direction of orientation in regions (A) forming an angle (V) to the direction on which (A) extends and webs (B) comprising arrays of linear furrows of thinner material or splits forming angles (U) higher than (V) to the direction in which (A) extends. The method of producing the new film involves passing an orientated film through a pair of intermeshing grooved rollers to cold-stretch the film in a direction at an angle to the

1

FILM MATERIAL EXHIBITING TEXTILE PROPERTIES, AND METHOD AND
APPARATUS FOR ITS MANUFACTURE.

The object of the invention appears from the title. By textile properties
5 there is primarily meant a soft and warm handle. In particular the invention
concerns very low weight film materials, and embodiments of the invention are
directed to film material which additionally exhibits through-going porosity and/or
high strength such as tear propagation resistance, tensile strength and puncture
strength.

10 During the last 40-50 years there have been presented a number of
proposals and a few industrial processes for manufacture of film materials
formed of thermoplastic polymer material exhibiting textile properties, but due to
complications in the manufacturing process and/or relatively high machine costs,
these technologies have in general not been competitive with non-woven
15 technologies based on spun filaments. In particular this has been a difficulty for
materials with low weight per area. The object of the present invention can be
further specified as aiming at relatively low machine costs, and simplicity in the
carrying out of the process.

WO 06/072604 and WO 06/120238, both concerning inventions which
20 have been developed in the laboratory of the inventors, disclose stretching of
monoaxially oriented film in a direction transverse to the original orientation, by
passage between intermeshing grooved rollers on which the crests are generally
flat and have sharp edges. There is hereby formed a fine pattern of thicker linear
“bosses” and intervening thinner “webs”, and due to the sharp edges on the
25 crests of the grooved rollers there is a distinct separation between the two
regions in the pattern.

In both inventions this stretching is a step in the manufacture of
crosslaminates. In the first mentioned patent the produced pattern of thickness
differences serves to form an internal micro-channel system in the
30 crosslamine, channels which in connection with mutually displaced
perforations in the two films form an advantageous type of through-going
porosity.

In the second mentioned invention the purpose of the introduction of the fine pattern of "webs" which have become biaxially oriented, is to improve the tear propagation resistance.

As it appears from both of the above-mentioned WO publications, the stretching between the intermeshing grooved rollers with crests having sharp edges is carried out in such a way that the original direction of orientation is parallel or practically parallel with the grooves. However, in trials preceding the present invention the inventors used their grooved-roller machine, designed for the abovementioned two inventions, in a different way, namely to stretch a 20 micron thick coextruded uniaxially melt-oriented HDPE film under an angle of about 45° to the melt orientation and with an engagement between the crests of the grooved rollers which was deeper than tried before. This produced a film of unique structure, namely the structure which appears from the microphoto Figure 1. This structure gave the film a surprising soft and warm feel. It became clear that such film in itself, or in form of an assembly of several films, is very suited for several textile applications. As it will appear from the following, this film structure and an assembly of such films can be manufactured by an uncomplicated process and using relatively inexpensive and safely working machinery, the key machinery being the grooved rollers with sharp-edged crests and industrially well established, uncomplicated machinery designed to make a uniaxial orientation extend under an acute angle to the continuous direction of a film web.

The product according to the present invention is a film or an assembly of films, the or each film being formed of thermoplastic polymer material and comprising an array of parallel bandformed, linearly extending regions (A) and distinct therefrom as this expression is specified below linearly extending webs (B) which integrally connect said regions (A), each web (B) being at each location of its linear extension thinner than the adjacent portions of regions (A), and in which film or assembly of films both (A) and (B) are oriented having at each location a dominating direction of orientation, The product is characterised in that in said film or in each film of the assembly the dominating direction of orientation in the regions (A) forms angles (ν) higher than zero but no higher than 80° with the direction in which (A) extends, and the said webs (B) comprise arrays of linear furrows (C) which either are necking-down zones or

are splits, said furrows forming angles (u) higher than (v) to the direction in which (A) extends.

The method of the invention is a method of producing this product by stretching, and starts with a film or an assembly of films each having a predominant direction of orientation. The stretching is carried out by means of a pair of mutually intermeshing first grooved rollers and takes place in a direction which is different, but at the highest 80° different from the predominant original direction of orientation in the said single film or in each of the said assembled films. The method is characterized in that at least one of the grooved rollers in the pair has crests with edges which are sufficiently sharp to form a distinct division as this expression is specified below between parallel, linearly extending webs (B) of film material, which has been coldstretched between the crests of the two first grooved rollers and intervening linearly extending band-shaped regions (A), which have laid on the sharp edged crests and have not been stretched or have been stretched to a smaller extent between the said grooved rollers.

The word coldstretching as used in this specification is meant to comprise any stretching carried out significantly below the melting point of the film, but preferably temperatures below about 60°C are chosen.

The division between each pair of regions(s) (A) and webs (B) is considered sufficiently distinct, if more than 50% of the thickness change takes place within a zone which is no wider than 15% of the width of the region (A). However, preferably it should be no wider than 10% and more preferably no wider than 5% of this width. This can be examined by microscope.

The thickness change is not necessarily a steady decrease from the higher values in region (A) to the lower values in region (B). Due to the forces concentrated on the material which is in contact with the sharp edges, this change in thickness may be a steady decrease which is followed by a steady increase.

The term "necking-down" is normally used in connection with stretching of polymer films at temperatures essentially below their melting range. It indicates that the stretching process takes place abruptly, such that a section of the film looks like a neck on the shoulders. In the present invention the minimum

thickness within the “necking-down” zones should preferably be no higher than 50% of the thickness of the surrounding web (B) material.

It is the combination of the three structural elements, namely the described bandformed regions (A), the traversing furrows (C), and the rest of the 5 interconnecting web (B), which provides the product with a combination of strength properties and textile feel, which is unique for a film product. The furrows (C) which are either ultra-thin regions or regular splits, have particular importance for the flexibility.

Very suitable raw materials for the invention are films which in amounts of 10 at least 50% consist of HDPE or isotactic or syndiotactic PP, preferably of HMWHDPE, but other thermoplastic polymer materials are also applicable, including biodegradable polymers.

The grooves on each first grooved roller may be circular or may be helical under an angle no smaller than 85° to the axis of the roller to make the regions 15 (A) and webs (B) extend parallel with the machine direction or under a small angle with the latter. Variations of the circular shape are waved surface forms which shall be described below.

The average gauge of each web (B) is preferably at the highest 70% of 20 the average gauge of the two adjacent regions (A). This can also be examined in microscope. In this connection the demarcation between a region (A) and an adjacent web (B) is considered to be the location where the thickness is the average between the thickest part of said region (A) and the thinnest part of said web (B).

As mentioned in claim 1 it is a precondition that the dominating direction 25 of orientation in the regions (A) forms an angle no higher than 80° with the direction in which (A) extends. It is not possible to indicate a general quantitative lower limit of this angle, since this depends on the polymer material, the orientation in the starting material, the thickness of the film and other parameters. Normally this angle should not be lower than 10°, and normally 30 angles no lower than 20° are preferable, but in some cases good results have been achieved with angles around 5°. However, the choice will be easy for a person skilled in the art after simple experimentation.

The statement that the crests on the first grooved rollers are generally flat implies that they may be slightly curved in section perpendicular to the grooves

(i.e. be convex) as long as they are able to produce a distinct separation as specified above, or they may have slightly protruding edge portions, i.e. be slightly concave as shown in Figure 6 of WO 06/072604 and in Figure 8 of WO 06/120238. Such protrusions can serve to make the separation between (A) and 5 (B) particularly distinct.

When the regions (A) and webs (B) are made to become parallel or practically parallel with the machine direction, it means that the original film or films, which become coldstretched between the intermeshing grooved rollers, must have a predominant direction of orientation forming an angle to the 10 machine direction. This can be achieved by forming the starting film for the method by helical cutting of a tubular film which is oriented mainly in its longitudinal direction. That may be solely by orientation in molten or semi-molten state, or the starting film may additionally have been machine-direction oriented by coldstretching.

15 The helical cutting can e.g. be carried out as disclosed in U.S. 5,248,366. This well established method is simple, safe and practical. However, if only melt orientation is wanted in the starting film a tubular film can be supplied with a helically extending melt orientation during the haul-off from the extrusion die by rotating the latter relative to the haul-off means. Such method of making biased 20 orientation is also well known.

As mentioned in the introduction, a major purpose of the invention is to provide a film with textile soft and warm handle. To this end the average gauge of the film or of each film in the assembly preferably is no more than 20 g m^{-2} , and still more preferably no more than 15 g m^{-2} or even no more than 10 g m^{-2} . 25 In this connection it should be mentioned that in practice it will normally not be difficult to separate the films in an assembly and weigh them individually. This shall be further explained below.

Further with a view to the above mentioned primary purpose of the invention, namely achieving a soft and warm handle, it is advantageous that the 30 width of each region (A) is at the highest 2mm, preferably at the highest 1mm, and still more preferable at the highest 0.5mm, while advantageously the division of the array of regions (A) is at the highest 4mm, preferably at the highest 2mm, and still more preferably at the highest 1mm.

For the sake of good order it should be mentioned that GB 1,526,722 and US 5,028,289 disclose processes for manufacture of a crosslaminate, in which tubular films of thermoplastic polymer material, having a predominant longitudinal melt orientation, are helically cut to make the melt orientation extend 5 on bias, then assembled with the melt orientations crossing each other and are transversely stretched together between grooved rollers. However, these grooved rollers are not adapted to produce a distinct separation between zones exhibiting different degrees or directions of orientation. On the contrary, there is aimed at making a relatively smooth crosslaminate, and preferably the 10 transverse stretching between grooved rollers takes place in several steps.

A very important embodiment of the invention is characterised in that the regions (A) are waved, each wave extending over the width of such region, such that each section along the regions (A) extend in a generally sinuous manner, and the webs being shorter than adjacent parts of the regions (A) to stabilize the 15 waving. Figure 7 shows a preferable minimum height (h) of the waving. The waving acts as a kind of nap to provide a warm feel by means of its heat isolating effect. It also gives the material an aesthetic textile appearance. If micro-flake shaped pigment is dispersed in the polymer material, e.g. made from mineral graphite or on the basis of mica, the material will get a diamond like 20 gloss. A similar effect can be achieved by vacuum coating of the surface of the product, e.g. with aluminium.

This waving occurs spontaneously when the film or assembly of films leaves the intermeshing grooved rollers with the generally flat crests. The reason is that the stretching of the webs introduces a tension which also has a 25 component in the machine direction, thus the webs contract, also along the machine direction, when the tension is released. It is hereby noted that any uniaxial stretching of a thermo-plastic film will introduce a tendency to contraction perpendicular to the direction of stretching. It was found that a pre-existing angle of orientation as in the invention enhances such contraction. The 30 regions (A) are practically not subjected to stretching forces since such forces are taken up by the sharp edges and therefore have practically no tendency to contraction after the grooved roller process, but form pleats when the webs contract.

In some applications in which such "nap" effect is not desirable, the waving can be eliminated by stretching in the machine direction at an elevated temperature.

However, the "nap" effect can also be enhanced. For this purpose the 5 degree of the described coldstretching between mutually intermeshing first grooved rollers may be sequentially varied by giving the crests of at least one roller in the pair of grooved rollers a waved surface shape. This is explained in further detail in connection with the drawings.

"Sequential orientation" or "sequential stretching" are well known terms, 10 indicating that the degree of orientation or stretching varies repetitively. This includes the possibility that the orientation or stretching repetitively is zero.

When this "nap" effect is made particularly pronounced by using a relatively deep waving on the surface of one or both intermeshing grooved rollers, the film material in contact with the crests of the waved grooved rollers 15 may locally loose its distinct separation between in the transverse direction practically unstretched regions (A) and more strongly stretched and optionally fibrillated regions (B). Thus, an advantageous product according to the invention, being in the form of a single film or an assembly of films, is characterised in that the linear extending regions (A) form interrupted lines, the 20 regions of interruptions (D) formed of webs thinner than (A) being generally similar to the webs (B) and without any distinct border between the said two web regions, whereby each interrupted linear region (A) including its thinner interruptions (D) is waved, the webs (D) forming the crests of this waving.

As already mentioned, the establishment of the predominant direction of 25 orientation of the starting film can be limited to take place in molten or semi-molten state carried out in the machine direction or helically in connection with the extrusion or it can comprise a coldstretching process in the machine direction. Such coldstretching preceding the helical cutting and preceding the 30 grooved roller stretching can with advantage be a sequential longitudinal stretching preferably between second grooved rollers which have teeth extending parallel to the axis. Preferably the thickness and degree of orientation within each region (A) is thereby brought to vary in sequences no longer than 10mm, more preferably no longer than 5mm.

It is known to carry out sequential m.d. stretching between such types of grooved rollers. Since the teeth exert a pressure on the film perpendicularly to the surfaces of the film, it will normally be the film portions which contact the teeth of one or both rollers which receive the highest orientation.

5 There are several reasons for using such sequential stretching. One reason concerns the tear propagation strength and puncture strength of the product. These properties are normally best when the degree of orientation is low, but on the other hand some coldstretching before the helical cutting may be needed in order to sufficiently bring down the square meter weight.

10 Coldstretching ratios in the range about 1.5 – 2.0 will often be preferable. However, any attempt to carry out the coldstretching in such low ratios and in continuous manner will normally give a very irregular result with more stretched and less stretched or even unstretched areas randomly between each other, while the sequential stretching in the ratios as mentioned brings order in the

15 variations. The differently stretched portions of the film will thereby form transverse bands.

Additionally, there is a surprising effect by using the sequential stretching, namely an important influence on the creation of waves in the regions (A). When the sequentially stretched tubular film relaxes after the sequential stretching, the

20 bands which have been stretched the most will perform some transverse contraction. This makes the less stretched bands form slacks, which during the step of coldstretching between grooves with sharp-edged crests enhance the formation of waves in region (A). Furthermore, the waving of the regions (A) becomes particularly stable in the spots which are thicker than the rest of the

25 film.

It is well known to make protruding bosses in a film by means of embossment, however by the known embossment these bosses generally become thinner than the surrounding material, and therefore easily lose their protruding shape under a mild pressure. The product according to claim 3 and

30 especially according to claims 4, 5, 20 and/or 28 is better in this respect since the protruding “bosses” here form the thicker portions of the film material, while most of the material which surrounds a “boss” is thinner and provides the desired flexibility of the product.

The film or assembly of films leaving the grooved rollers with sharp-edged crests will be deeply pleated parallel with the regions (A) and the webs (B) and must normally be transversely extended to remove these pleats. This can take place by means of banana rollers or similar simple means. The material may be 5 heat stabilized in this extended form, and a slight tentering may be carried out, preferably while allowing it some contraction in the continuous direction of the regions (A) and webs (B). The tentering devices may be very simple pairs of belts since the forces involved normally are low. The mentioned contraction can e.g. be obtained by giving the film or assembly of films pleats extending 10 perpendicularly to the regions (A) and the webs (B) before it is fed into the tentering devices.

In a second particularly important embodiment of the invention the product is a crosslaminate, as this is more precisely stated in claim 6. Such product normally exhibits, in addition to the textile feel, particularly good tensile 15 properties, tear propagation resistance and puncture strength. The above mentioned advantages of a waved shape of the regions (A) will normally also apply to this embodiment of the invention.

The individual films may become joined in a separate process after the coldstretching of each film between the grooved rollers with sharp-edged crests. 20 Preferably the bulk of each film should be preserved by carrying out the joining as an extrusion lamination process with molten filaments as binder, while keeping a small distance between the laminating rollers.

A simpler method, which generally provides higher tensile strength but less bulk, integrates the laminating with the coldstretching between the sharp-edged crests, by feeding the assembly of films into the stretching nip with their 25 original directions of predominant orientation being in criss-crossing arrangement. After passage of the films through this nip the regions (A) in the different crosslaminated films will exactly cover each other along their full length, and the webs (B) will similarly cover each other. In the crosslaminate 30 manufactured through these steps, the elongation at break is preferably no less than 100% and the ultimate tensile strength no less than 10 MPa, preferably no less than 15 MPa, referring to tensile testing of 2.5cm wide samples at a velocity corresponding to 500% of the length per minute.

During this coldstretching there may be established a bonding or blocking between the films, localized to the regions (A) and (D) or to boundaries between the webs (B) and the regions (A) or (D), normally under use of films which by coextrusion have been supplied with a suitable lamination layer. Any process for 5 bonding or blocking the films together is preferably limited such that most of each web (B) remains unbonded and unblocked. (The term "blocking" is normally used for a bonding which is so weak that it can be eliminated by peeling without distorting the films).

It is noted that the tendency to blocking is very pronounced at the 10 boundaries between regions (A) and webs (B), i.e. in the film portions which are drawn against the sharp edges, and when using lamination layers which become slightly sticky at about 60°C, a coldstretching at room temperature between the sharp-edged crests can in many cases provide a blocking which is sufficient for the practical application of the laminate. However, for some applications there 15 will be need for stronger bonding, but still leaving the webs (B) unbonded and maintaining the waving of the regions (A) and (D). This can be established by localized heating of zones within the regions (A) and (D), carried out before or after the stretching between the grooved rollers with sharp-edged crests. Such heating may be carried out with another set of grooved rollers, which are 20 adjusted to be in register with the sharp-edged crests, as this is further explained in connection with Figure 5.

A special crosslaminate, aiming at particularly good puncture properties, is constructed as stated in claim 10. This arrangement is further described in connection with Figure 8.

25 In a third particularly important aspect of the invention the webs (B) are in fibrillated or through-going micro-voided state, the fibrillation substantially following the local dominating direction of orientation, while the regions (A) are less fibrillated, preferably essentially unfibrillated and with less (preferably much less) through-going micro-voids. To achieve this structure, the choice of starting 30 film material and the parameters of the coldstretching between the sharp-edged crests may be adapted to produce fibrillation or through-going micro-voiding of the webs while maintaining their coherence and their integral connection with (A), such fibrillation being substantially parallel with the local dominating

direction of orientation. Thus the starting material may comprise an additive suitable for producing such fibrillation or through-going micro-voiding.

One embodiment of this method is stated in claim 32, another embodiment in claim 33. Both are further explained below. However, the 5 structure according to the third aspect of the invention can also be established by carrying the stretching between the grooved rollers under conditions which form the webs in a continuous structure but with the furrows (C) in form of parallel "necking-down" zones (see fig. 1 and description of this). Subsequent to the stretching, but preferably in line herewith, the "necking-down" zones are then 10 disrupted to form real splits. Such disruption can be carried out in different ways, but preferably by passing the product while tentered over a stream of hot air and adapting the conditions of the treatment (air temperature, air velocity, velocity of the film) so that the disruption in general becomes confined to the "necking-down" zones. One advantage of this method of forming splits is that 15 the polymer portions which were broken by heating, have lost the orientation, and thereby help to avoid further splitting.

For the understanding of the methods according to claims 32 and 33, reference is made to GB Patent No. 1,148,382 (Rasmussen). This patent deals with the manufacture of extremely fine fibre networks by fibrillation of an oriented 20 film made from a polymer blend. Such fibre networks are made (quoting from the patent) "by colloidally mixing while molten a crystallizable high molecular weight polymeric material A with a polymeric material B, which is chemically different from A and has a lower melting point and a higher melt index than A, extruding the melt mixture as a sheet and phase orientating the sheet by 25 strongly stretching the sheet in the direction of extrusion while the sheet is still molten, cooling the stretched sheet first to make the polymeric material A crystallize and agglomerate while keeping the polymeric material B in fluid state, swelling or partially leaching out the polymeric material B and splitting the sheet material thus formed by stretching it in a direction transverse to the direction of 30 orientation".

(The use of the symbols A and B are of course different from the use of the same symbols in the present claims).

The said patent explains that under such conditions the polymer called B will tend to form thin membranes around "crystal needles" of the polymer called

12

A, although there still will be direct connections between adjacent crystal formations. The patent also mentions polyoxyethylene as a suitable "B" polymer.

In connection with the present invention it is not economically feasible to 5 leach out or swell a component, but the structure described in the old patent, i.e. needle formed crystal formations partly separated by fine membranes, is very suitable for the fibrillation. This is the background for claims 32 and 33.

As regards claim 32 it is noted that, although the mentioned two polyethylenes chemically seen are almost identical, the big differences in their 10 molecular weights cause the HMWHDPE to form the described "crystal needles" and the other HDPE to form more fragile "membranes" between these needles. This promotes the splitability while still maintaining a suitably high strength in the product.

The method of claim 33 is in particular meant for manufacture of diapers, 15 namely for the web in direct contact with the skin. The urine will partly dissolve the water-soluble polymer, which by the splitting has become exposed at the split surfaces. Thereby it will act lubricating on the skin. There may be added an aseptic agent to this water-soluble polymer.

For most but not all applications, this third aspect of the invention, i.e. the 20 fibrillation or the formation of through-going voids, is preferably carried out in conjunction with the first embodiment, i.e. the waving of regions (A) (and (C) when present), and/or with the second embodiment, i.e. the crosslamination.

The film or film assembly made according to the invention can be very 25 suitable for manufacture of bags with special properties and in the manufacture of several types of sanitary products. As an example, the film or assembly of films in essentially non-fibrillated form and without through-going voids is very suitable for garbage bags.

As described above, the coldstretching by use of a relatively deep waving 30 on one or both intermeshing grooved rollers may make the regions (A) interrupted lines instead of continuous lines. In order to achieve a particularly high bulk and/or degree of fibrillation or though-going porosity, but to some extent at the expense of strength properties, this effect may be taken so far that the regions (A) lose the character of being linear and become a multitude of "dots" arranged in linear arrays.

The invention also comprises any new apparatus which is suitable for carrying out the described method steps.

The invention shall now be described in further detail with reference to the drawings.

5 Figure 1 is a microphoto showing a single film according to the invention. It is the film produced as described in Example 1.

Figure 2 a, b and c are sketches of a crosslaminate according to the invention but disregarding the furrows (C). The pleating of regions (A) is considered stretched out. Figure 2a shows one ply of the laminate, 2b the other 10 ply, the two sides being shown mutually displaced along the direction of the regions (A) and the webs (B). The hatching on Figures 2a and b all over indicates the dominating directions of orientation.

Figure 2c shows a cross-section of the laminate, indicating that the webs (B) are drawn thin and are unbonded, while the regions (A) are mutually bonded 15 together at least in spots or lines or along the boundaries between (A) and (B). Note that in Figure 2c the thicknesses are shown on a scale which is 10 times the scale on which the widths of the regions (A) and webs (B) are shown.

Figure 3 shows an axial section of the surface parts of two grooved rollers having circular crests with sharp edges, which intermesh and stretch a film or an 20 assembly of films.

Figure 4 is two flow sheets representing two lines which together produce a crosslaminate according to the invention. The two steps "Lamination and bonding in linear stripes" and "T.d. stretching between sharp-edged grooved rollers in register with stripes" are carried out by the apparatus shown in Figure 25 5.

Figure 5 shows in axial sections the surface parts of a stack of grooved rollers which first bond two or more films together in stripes and then transversely stretch unbonded stripes of the assembly, all grooved rollers being in exact registration with each other at the respective operating temperatures.

30 Figure 6 is a flow-sheet showing a simplified process for manufacture of a crosslaminate, all in line.

Figure 7 is a sketch serving as basis for a description regarding the depth of the pleating of the regions (A).

Figure 8 is a sketch demonstrating angles in a specialty product, between the extension of regions (A) – direction (1) - and the predominant directions of orientation in these regions – directions (2) and (3) - of two cross-laminated films.

5 Figs 9a and b are cross-sections representing modifications of the surface shape of the crests of the grooved rollers described in connection with Figure 3.

Figs 10a and b are sketches illustrating two different patterns of waving, which can be obtained with the roller shapes shown in Figures 9a and b.

10 Figure 11 is a flow-sheet showing particularly practical combination of manufacturing steps.

Figure 12 which is a microphoto which like Figure 1, shows a single film according to the invention. In this case the film is produced as described in Example 3 using the roller shown in Figure 9a.

15 Figure 13 is a sketch which illustrates a process of developing the furrows (C) from being “necking-down zones” to become open splits. The sketch is drawn parallel with the machine direction.

Figure 14 is a schematic representation of the film structure according to the invention, corresponding to the realistic representation in the microphoto figure 1. The meaning of the reference letters (A), (B) and (C) appears from the description of Figure 1.

Figures 2 a, b and c, Figure 4 and Figure 6 require no further explanation. The microphoto Figure 1 shows the single film made as explained in Example 1 and demonstrates the linearly extending regions (A), which are waved with each 25 wave extending over the width of such region, and the webs (B), which have been drawn thinner between sharp-edged crests on the intermeshing grooved roller shown in Figure 3. The webs (B) comprises the ultra thin “necking-down” zones (C). As the photo demonstrates there is a distinct separation between (A) and (B). It is noted that the polymer material has been pigmented white and the 30 background is black.

To emphasize the waving, the photo is taken with a beam of light projected on the sample almost parallel with the direction in which (A) and (B) extends. Measurements on microphotos of samples from the same film material but taken under other angles show that the ratio (l/h) between a half wave

15

length (l) and the height (h) of a single wave generally is about 4:1. The sketch Figure 7 is drawn in order to avoid any misunderstanding of what half wavelength (l) and waveheight (h) here mean. For comparison, the ratio (l /h) in Figure 7 is 3:1. It is considered that a ratio as high as about 8:1 also will provide

5 a thin film according to the invention with a warm feel.

While the predominant direction of orientation in the regions (A) form an angle of 45° with the extension of these regions – this appears from the manufacturing process described in Example 1 – the black biased lines in the microphoto show how the stretching between the sharp-edged crests has turned

10 this angle larger in the webs (B). These lines appear as being splits, but attempts to transmit air through gave negative result, showing that they are extremely thin film portions, or in other words “necking-down” zones. They contribute especially to the flexibility of the film, and they also occur when two films are stretched together to form a crosslaminate according to the invention.

15 On the other hand, these split-like lines also show that it will be easy, by modifications of the raw material composition and/or of the parameters of the process conditions, and/or by a subsequent disruptive process to form real splits and/or through-going micro-voids. This can e.g. be established by basing the composition on polymer grades which are less split-resistant than the

20 HMWHDPE used in Example 1, and/or by admixture of split-inducing particles. In this connection, the concentration of such particles can be and ought to be much lower than normally used when producing through-going micro-voids during stretching.

In the foregoing general description there are mentioned preferable limits

25 for the average gauge of each web (B), expressed as a percentage of the average gauge of the adjacent regions (A). If the webs (B) have been supplied with splits, the split micro-areas must hereby be included in the calculation of average, contributing with gauge zero.

As mentioned above the microphoto shows a single film made as

30 described in Example 1. This Example also describes a trial production of a 2-ply crosslaminate on basis of the same starting film. Microphotos of this crosslaminate looks the same as Figure 1, except that the pictures of the webs (B) show criss-crossing lines appearing like splits, but in reality being ultra thin stretching lines in the two films.

Figures 2 a, b and c show how two films in a crosslaminate according to the invention can have regions (A) which entirely cover each other, and thinner webs (B) which also entirely cover each other. It has already been mentioned that the furrows (C) are disregarded in these drawings. As shown in Figure 2c 5 the webs (B) are not bonded or blocked together, while the regions (A) at least are blocked together. This is normally established through lamination layers (not shown in the sketch). As mentioned in the general description the tendency to blocking is high at the boundaries between (A) and (B). This is because the two 10 films are strongly pulled together on the sharp edges of the crests of the grooved rollers. However, preferably the main portions of the regions (A) should be regularly bonded together, as this is described in connection with Figure 5.

As the hatching of Figures 2a and 2b indicate, the directions of orientation criss-cross all over. The angles which the orientation of the two films within the regions (A) form with the direction in which these regions extend (that 15 is normally but not always the machine direction) is here shown as plus and minus 45°, but in practice it can be any angle from about +/- 5° to +/- 80°.

However, there needs not be symmetry as here shown, and the orientations in the two films may even be one-sided, seen in relation to the direction in which the regions (A) and the webs (B) extend. This is shown in 20 Figure 8, where (1) is the direction in which (A) and (B) extend, (2) is the predominant direction of orientation of one film in the crosslaminate, and (3) the predominant direction of orientation in the other ply. In both cases these orientations refer the regions (A). In claim 10 this arrangement of orientation is expressed more exact. The purpose of this very asymmetric arrangement is to 25 give the crosslaminate particular good puncture resistance, however at the expense of some other strength properties.

With reference to Figure 3, the mutually intermeshing grooved rollers (112) and (113) which effect the segmental transverse stretching of webs (B) have flat crests (114) on their circular teeth with sharp edges (115). (Flat seen in 30 axial section, in section perpendicular to the axis they are circular). This causes the stretching to be limited to these webs, here numbered (111). The portions of the film material which lay on the flat crest (114) form the practically unstretched regions (A). In order to fully avoid stretching of these regions the grooved rollers are preferably kept at a low temperature, e.g. 15 to 20°C, while the rest of the

film may be treated with warm air e.g. of temperature about 40°C. The requirements for precision in the manufacture of the roller surfaces are high, and it is highly advisable to make the outer part of rollers from short segments.

As mentioned in the general description, on one of the rollers 112 or 113 5 the crests may have rounded edges or may be rounded all over, so that the transverse stretching and the formation of the thin "necking-down" zones or of splits also take place on these crests. This means that the webs (B) will become wider than the regions (A). Certain strength values may hereby become enhanced, while the textile appearance becomes somewhat less pronounced.

10 When the crest on one roller (112) or (113) are rounded or have rounded crests, that roller should preferably be heated, e.g. to a temperature between about 15-20°C. The process may conveniently take place in an ambience of about 40°C air temperature. The film is first preheated by this ambience, then it enters the relatively cold roller to cool the regions (A), and finally the film is 15 transversely stretched in the nip between the two rollers. This stretching comprises the warm film portions.

The process steps, which in one of the flow-sheets in Figure 4 are called "lamination and bonding in linear stripes" and "T.d. (transverse direction) stretching between sharp-edged grooved rollers in register with stripes" are 20 carried out with the machine shown in Figure 5. The first mentioned step is carried out with rollers (118) and (119) which have axes (118a) and (119a). These rollers are heated, e.g. to about 90°C to establish bonding between lamination layers on the films. To achieve even temperature in the different linear stripes to be laminated, there may be a third grooved heating roller 25 upstream of roller (118) but this is not shown. The bonding is established in the nip between the slightly intermeshing grooved rollers (118) and (119). The crests (120) on these rollers are rounded. There must be some intermeshing between the grooved rollers to achieve bonding, but preferably this intermeshing is minimized in order to minimize any stretching at this step.

30 The stretching which produce the webs (B) takes place between the rollers (112) and (113) with axes (112a) and (113a). These rollers are constructed like (112) and (113) in Figure 3, having crests with sharp edges (115). They are preferably kept at about room temperature by circulating water.

To avoid bonding between the two films within the webs (B), all grooved rollers in this stack must be in exact register as indicated by the dot-and-dash lines (121). This registration refers to the operating conditions at which the rollers have different temperatures. The pitch of the grooves, when they are 5 manufactured, must be accordingly calculated. (A 1m long steel roller expands about 0.11mm with 10°C increase in temperature).

It is possible to reverse the route which the film is taken through this stack of rollers, such that the stretching between the sharp-edged crests takes place prior to the lamination on hot rounded grooved rollers. When such route is used, 10 there must be a deep intermeshing between the rounded crests on the rollers (118) and (119).

Furthermore, still referring to the reversed route, roller (118) may be substituted by a nip roller, coated with soft rubber and preferably heated. In this case, only every other region (A) will become bonded in the nip. If one of the 15 preceding grooved rollers has a waved surface shape as shown on figure 9a or 9b, while the matching grooved roller is truly circular, it must be the latter which forms the nip together with the rubber roller. This nip also produces a slight U-shape of the A-regions which pass the nips, thereby improving the stiffness in one direction.

20 Figure 7 has already been described in connection with the description of Figure 1.

Figure 8 has already been described in connection with the description of Figures 2a and b.

Figure 9a shows the surface waving of one of the sharp-edged grooved 25 rollers used in Example 3. The sharp-edged grooved roller with which it intermeshes has a circular surface without any waving. As shown in the sketch the shape of the waving is generally sinusoidal, but with a radius of curvature greatest where the distance from the roller axis is largest (in fact the radius of curvature used in example 3 is 68 mm, equal to the roller radius) and smallest 30 (0.5 mm) where this distance is shortest. Depending on the desired film structure, it can also be the other way, or the two mentioned radii may be equal. In this system the stretching/embossing between the grooved rollers will form elongated "pockets" which mainly protrude from one surface of the film or assembly of films.

Alternatively, both grooved rollers may be supplied with a sinusoidal surface shape and assembled such that the regions (200) of biggest diameter on one roller match with the regions of biggest diameters on the other roller. In this case each "pocket" which protrude from one surface will have two neighbours 5 protruding from the opposite surface. In order to avoid overstretching of the film, the waving roller surfaces in this system should generally be shallower than the waving which is preferable in the system described above.

The making of "pockets" on both surfaces can also be effected with a pair of rollers each shaped as shown in Figure 9b. The two rollers must be mutually 10 adjusted so that the positions (200) of greatest distance from the roller axis on one roller corresponds with the middle (201) between neighbours of similar positions (200) on the other roller.

The type of roller illustrated in figure 9b can also work together with a roller 15 having circular surface without any waving. In this way there can be produced relatively short bosses in the film. Right on the "tip" of each wave on the roller, the edges may be rounded (see below) to promote fibrillation of the tips on the bosses of the film. These tips may even be completely perforated.

In Figure 10a and b one of the grooved rollers has had waved surfaces, the other one cylindrical surface, like in Figure 9a. The peaks of the linear 20 regions (A) formed by the waved surfaces are marked (202). In Figure 10a each peak in one region (A) is directly adjacent to a peak in each of the two adjacent regions (A), formed by the roller with waved surfaces. This makes the product look as if it were woven and enhances the softness.

In Figure 10b it is opposite. Each peak in one region (A) lays midway 25 between the two closest peaks in each of the two adjacent regions (A) formed by the roller with waved surfaces. This serves to provide some stiffness to the structure, which in some cases is preferable, e.g. for films used to make bags.

In all cases the grooves in the rollers may be formed by turning, while the waved surfaces and the sharp edges best are produced by spark erosion. To 30 make the sharp edges abrasion resistant, a steel with high content of carbon is preferably chosen. This will become particularly hard by the spark erosion process.

If it is desired for the tips on the waved crests to be rounded, this can be done after the spark erosion by means of electrolytic polishing.

For a correct understanding of Figure 11, reference is made to US 5,248,366 (Rasmussen) Figures 1, 2 and 3 and related descriptions. These drawings show helical cutting of a tube, which before the illustrated processes has been supplied in lay-flat form with a main direction of orientation parallel with its longitudinal direction. In Figure 1 of US 5.248,366, the unwinding reel (9), take-off rollers (11) and conveyor belts (17), are assembled in a frame (5) and (6) which performs a "tumbling" movement, i.e. the axes of reel (9), or rollers (11) and of the rollers supporting and driving the conveyor belts (17), are rotated around the axis (23). This is perpendicular to the above-mentioned roller axes and generally goes through the middle of the advancing lay-flat film (10). The latter is inflated and carried over a fixed mandrel (14) in a screwing movement, the inflation being helped by air, introduced by fan (13) to blow through the mandrel (14). The screwing movement is controlled by the circumferential velocity of rollers (11) and the revolutions of the "tumbling". While the inflated film (10) passes over the mandrel (14), it is lubricated by the air stream and remains in stable tubular form until it is helically cut by means of a fixed knife (18) and taken up by a winding system (20), (21), (22).

Now with reference to Figure 11 of the present specification, the new feature of the "tumbling" arrangement is that the take-off rollers (11) are substituted by or supplemented with a pair or series of machine direction (m.d.) stretching rollers. This may simply be a set of gear rollers as described above. After helical cutting on the mandrel, the biased oriented film may go directly to the t.d. stretching/embossing between the sharp-edged grooved rollers, or it may first or simultaneously be "sandwiched" with a similarly and simultaneously made, biased oriented film, especially so that the orientations of the two films cross each other.

Reverting to US 5,248,366, Figures 2 and 3 show a modification of the method and apparatus of Figure 1 of that specification. In this modification, the axis of the unwinding reel (9) coincides with the axis (23) around which the "tumbling" takes place. There are guiding means (28), (29) and (30) (see Figure 3) arranged such that the advancement of film 11, which at zone (31) starts perpendicular to the axis of "tumbling" (23), is turned by folding to become parallel with this axis (23). This way of carrying out the "tumbling" unwinding can also be applied as the first step shown in Figure 10 of the present specification.

The addition of m.d. stretching rollers in a "tumbling" unwinding apparatus for the tubular film, followed by helical cutting while the tube passes over a mandrel in a screwing movement, is considered an invention in itself, independent of its use for manufacture of the textile like film products, which is 5 the primary objective of this specification. In this connection the m.d. stretching method is not limited to the use of gear rollers, but can in principle be any m.d. stretching method carried out by rollers. Furthermore, the change of film form from the lay-flat to tube does not necessarily require inflation by air (13) and conveyor belts (17). These features are preferable, but alternatives can be 10 chosen.

With reference to the sketch figure 13, it should be understood that the film (203) while entering the device for heat treatment has the structure which appears from the microphoto figure 1. As mentioned in the description of this microphoto, the black lines which transverse the webs (B) under an acute angle 15 with the linear regions (A) and which look like splits, are not really splits, but are extremely thin "necking-down" zones. The purpose of the heat treatment shown in figure 13 is to disrupt these highly stretched, extremely thin "lines" so that at least a part of these "lines" become transformed into real splits by melting or semi-melting, but without disrupting the webs (B) so seriously that the 20 connections between the linear regions (A) become ruined.

The film (203) is dragged over a slot extending perpendicularly to the plane of viewing, the slot being formed by the metal walls (204) while hot gas, normally air, is blown through the slot as indicated by the arrow (205). At the inlet to the slot there is a system of channels (not shown) to distribute the hot 25 gas evenly over the length of the slot, and a perfect equalization of gas velocity and gas temperatures is further achieved by a packing of ceramic pebbles (206).

The film (203) passes over the slot in tentered state and in contact with the walls (204). The latter are cooled by a cooling fluid which is circulated through the channels (207). Insulating plates (208) prevent cooling of the 30 stream of gas.

During the process, the velocity of the film (203) is kept constant and the temperature and velocity of the gas is very exactly adjusted by experimentation so as to achieve the desired disruption of the "lines" without undesirable further disruptions.

To the knowledge of the inventor it is new to form small holes or small splits in an oriented or unoriented film, by first making the small areas in the film thin by stretching, and then disrupting these small areas by use of hot gas, while the contact time, velocity and temperature of the gas are adjusted to each other.

5 This method is in itself considered an invention independent of its use in connection with the structure which is defined in claim 1.

Example 1

A tubular film of average gauge 18.6 micron (measured as 17.9 g/ m²) is coextruded having the following composition:

10 - Middle layer, 65% of total: all HMWHDPE except for additives and white masterbatch.

- Outer surface layer, 15% of total: 70% LLDPE of m.f.i. = 1.0 + 30% metallocene PE melting between 50-60°C.

- Inner surface layer, 100% LLDPE

15 The blow up ratio is 2.7 : 1 and the gap of the circular die orifice is 1.0mm. This means that the tubular film, while getting its thickness reduced by a factor of about 50, gets a strong predominantly longitudinal melt orientation.

This tubular film is helically cut to form a web with 45° orientation. Two such webs are assembled on a 40°C warm roller with their directions of 20 orientation crossing each other. In line herewith the assembly is transversely stretched between the grooved rollers shown in Figure 3. The roller temperature is maintained at 20°C by means of circulating water. The width of each flat crest is 0.4mm and the pitch of the grooves on each roller is 1.2mm. This leaves a 0.2mm space between each set of intermeshing crests. The depth of 25 intermeshing is 1.00mm, which is the deepest that can be obtained with the available grooved rollers. The average t.d. stretching ratio after a spontaneous shrinkage becomes 1.65:1.

The film is examined for bonding, and it turns out that there is a strong blocking between the two films at the boundaries between the transversely 30 stretched and unstretched portions of the films.

Some of the helically cut film is similarly t.d. stretched as single film. The structure obtained hereby – and similar for each of the films in the crosslaminate – is described in connection with the microphoto Figure 1.

The produced crosslaminate is tested as it is described after Example 2.

Example 2

There is used the same extruded film, the same helical cutting under 45°, and the same crosslamination and transverse stretching / laminating process as in Example 1, but before helical cutting the lay-flat tubular film is m.d. stretched 5 in sequential manner between grooved rollers which have teeth extending parallel to the axis. The crests of these teeth are semicircular with diameter 1.9mm, and the pitch of the grooves on each roller is 5.0mm. By the applied inlet and outlet tension in the film and the intermeshing between the rollers the average stretching ratio is adapted to be 1.4:1. The stretching takes place on the 10 rounded teeth on one of the grooved rollers and between the teeth, while film on the teeth of the other roller remains unstretched.

The testing of the produced crosslaminate is recorded below.

Comparative testing of Example 1 and Example 2 film.

The two crosslamines and the extruded tubular film are tensile tested 15 and tested for puncture strength against penetration of a "horn" of diameter 10mm having semi spherical tip.

The tensile testing is carried out on 25mm wide specimens cut at 45° or in m.d. or t.d. using a velocity corresponding to 500% elongation per minute. Yield force, ultimate tensile strength and elongation at break are determined 20 from strain/stress diagrams. The aim has been to produce a film which in all direction exhibits high ultimate tensile tension in combination with a high elongation at break.

The puncture resistance test is carried out by tightly buckling the film material between two rings, each having in their middle a circular opening of 25 diameter 35mm. The "horn" is centred in relation to this opening and is penetrated into the film material with a velocity of 5mm per second till the film breaks. There is aimed at a high force at break as well as a deep penetration. The force at break is converted from Newton to MPa by dividing with an area which is the thickness multiplied with the circumference of the horn, both in mm.

30 The results of the comparative testing appear from the following tables.

a) Horn Puncture Tests

Extruded film, no further treatments, gauge 17.9 g/m²

24

| | | Ultimate puncture strength | |
|---------|------------------|----------------------------|-------|
| Test | Penetration (mm) | N | MPa |
| Test 1 | 26 | 16.00 | 26.79 |
| Test 2 | 33 | 19.00 | 31.82 |
| Test 3 | 28 | 15.40 | 25.79 |
| Test 4 | 33 | 20.40 | 34.16 |
| Test 5 | 33 | 20.00 | 33.49 |
| Average | 30.6 | 18.16 | 30.41 |

Example 1, gauge 22 g/m²

| | | Ultimate puncture strength | |
|---------|------------------|----------------------------|-------|
| Test | Penetration (mm) | N | MPa |
| Test 1 | 26 | 28.50 | 38.69 |
| Test 2 | 25 | 24.50 | 33.26 |
| Test 3 | 23 | 27.00 | 36.66 |
| Test 4 | 26 | 24.50 | 33.26 |
| Test 5 | 24 | 28.00 | 38.01 |
| Average | 24.8 | 26.5 | 35.98 |

5 Example 2, gauge 19 g/m²

| | | Ultimate puncture strength | |
|---------|------------------|----------------------------|-------|
| Test | Penetration (mm) | N | MPa |
| Test 1 | 20 | 26.75 | 42.11 |
| Test 2 | 23 | 32.50 | 51.16 |
| Test 3 | 24 | 33.75 | 53.13 |
| Test 4 | 23 | 32.00 | 50.37 |
| Test 5 | 22 | 34.00 | 53.52 |
| Average | 22.4 | 31.8 | 50.06 |

b) Tensile Tests

25
Extruded film, no further treatments, gauge 17.9 g/m²

| Test No. | Elongation at break (%) | Ultimate tensile strength | | Yield tension | |
|--------------|-------------------------|---------------------------|-------|---------------|-------|
| | | N | MPa | N | MPa |
| m.d. Test 1 | 392.00 | 34.00 | 71.58 | 12.00 | 25.26 |
| m.d. Test 2 | 199.49 | 19.00 | 40.00 | 11.00 | 23.16 |
| m.d. Test 3 | 371.01 | 33.00 | 69.47 | 12.20 | 25.68 |
| m.d. Test 4 | 340.00 | 27.00 | 56.84 | 11.50 | 24.21 |
| m.d. Test 5 | 364.00 | 32.00 | 67.37 | 12.50 | 26.32 |
| Average m.d. | 333.3 | 29.00 | 61.05 | 11.84 | 24.93 |
| t.d. Test 1 | 168.86 | 6.30 | 13.26 | 8.50 | 17.89 |
| t.d. Test 2 | 510.00 | 8.20 | 17.26 | 8.40 | 17.68 |
| t.d. Test 3 | 365.87 | 7.20 | 15.16 | 8.20 | 17.26 |
| t.d. Test 4 | 579.37 | 6.40 | 13.47 | 6.60 | 13.89 |
| t.d. Test 5 | 577.44 | 6.00 | 12.63 | 6.50 | 13.68 |
| Average t.d. | 440.31 | 6.82 | 14.36 | 7.64 | 16.08 |
| 45° Test 1 | 368.33 | 9.80 | 20.63 | 7.5 | 15.79 |
| 45° Test 2 | 330.55 | 6.90 | 14.53 | 4.3 | 9.05 |
| 45° Test 3 | 618.00 | 10.50 | 22.11 | 8 | 16.84 |
| 45° Test 4 | 414.30 | 9.40 | 19.79 | 6.2 | 13.05 |
| 45° Test 5 | 386.19 | 9.10 | 19.16 | 8 | 16.84 |
| Average 45° | 423.47 | 9.14 | 19.24 | 6.80 | 14.32 |

Example 1, gauge 22 g/m²

| Test No. | Elongation at break (%) | Ultimate tensile strength | | Yield tension | |
|--------------|-------------------------|---------------------------|-------|---------------|-------|
| | | N | MPa | N | MPa |
| m.d. Test 1 | 488.14 | 21.00 | 35.84 | 8.80 | 15.02 |
| m.d. Test 2 | 558.39 | 25.50 | 43.52 | 6.70 | 11.44 |
| m.d. Test 3 | 528.75 | 23.00 | 39.26 | 7.50 | 12.80 |
| m.d. Test 4 | 566.65 | 26.50 | 45.23 | 9.00 | 15.36 |
| m.d. Test 5 | 480.00 | 21.50 | 36.70 | 7.00 | 11.95 |
| Average m.d. | 524.39 | 23.50 | 40.11 | 7.80 | 13.31 |
| t.d. Test 1 | 127.23 | 23.50 | 40.11 | 23.50 | 40.11 |
| t.d. Test 2 | 109.01 | 24.50 | 41.82 | 24.50 | 41.82 |
| t.d. Test 3 | 116.70 | 23.00 | 39.26 | 23.00 | 39.26 |
| t.d. Test 4 | 120.15 | 25.50 | 43.52 | 25.50 | 43.52 |
| t.d. Test 5 | 199.37 | 19.20 | 32.77 | 22.00 | 37.55 |
| Average t.d. | 134.49 | 23.14 | 39.49 | 23.70 | 40.45 |
| 45° Test 1 | 156.71 | 17.50 | 29.87 | 13.2 | 22.53 |
| 45° Test 2 | 69.30 | 14.00 | 23.89 | 14 | 23.89 |
| 45° Test 3 | 137.54 | 20.00 | 34.14 | 16 | 27.31 |
| 45° Test 4 | 142.94 | 21.00 | 35.84 | 16.5 | 28.16 |
| 45° Test 5 | 122.20 | 18.50 | 31.58 | 15.3 | 26.11 |
| Average 45° | 125.74 | 18.2 | 31.06 | 15.00 | 25.60 |

Example 2, gauge 19 g/m²

| Test No. | Elongation at break (%) | Ultimate tensile strength | | Yield tension | |
|--------------|-------------------------|---------------------------|-------|---------------|-------|
| | | N | MPa | N | MPa |
| m.d. Test 1 | 440.89 | 8.10 | 16.03 | 4.70 | 9.30 |
| m.d. Test 2 | 440.10 | 7.90 | 15.63 | 3.90 | 7.72 |
| m.d. Test 3 | 421.48 | 6.90 | 13.65 | 3.60 | 7.12 |
| m.d. Test 4 | 493.78 | 9.50 | 18.80 | 5.20 | 10.29 |
| m.d. Test 5 | 357.16 | 6.20 | 12.27 | 3.40 | 6.73 |
| Average m.d. | 430.68 | 7.72 | 15.28 | 4.16 | 8.23 |
| t.d. Test 1 | 133.00 | 7.10 | 14.05 | 12.40 | 24.54 |
| t.d. Test 2 | 226.29 | 10.00 | 19.79 | 14.50 | 28.69 |
| t.d. Test 3 | 176.00 | 10.50 | 20.78 | 12.20 | 24.14 |
| t.d. Test 4 | 168.55 | 11.10 | 21.97 | 12.00 | 23.75 |
| t.d. Test 5 | 188.04 | 12.10 | 23.95 | 14.40 | 28.50 |
| Average t.d. | 178.37 | 10.16 | 20.11 | 13.10 | 25.92 |
| 45° Test 1 | 91.00 | 16.50 | 32.65 | 16.5 | 32.65 |
| 45° Test 2 | 82.05 | 14.50 | 28.69 | 14.5 | 28.69 |
| 45° Test 3 | 71.79 | 12.20 | 24.14 | 12.2 | 24.14 |
| 45° Test 4 | 77.03 | 13.20 | 26.12 | 13.2 | 26.12 |
| 45° Test 5 | 85.55 | 15.00 | 29.68 | 15 | 29.68 |
| Average 45° | 81.48 | 14.28 | 28.26 | 14.28 | 28.26 |

Example 3

There is used the same extruded films as in Example 1, and the same sequential m.d. stretching as in Example 2. Helical cutting is carried out under 30° to the original m.d. The film with 30° orientation is transversely stretched/embossed, in part as a single film, and in part cross webbed with itself between sharp-edged grooved rollers. The grooved rollers and the grooved roller process deviate from what is described in Example 1 only on the following 5 points:

10

- 1) The grooves are made slightly deeper to allow a deeper intermeshing, and this is set at 1.2 mm.
- 2) One of the two grooved rollers with sharp-edged crests has a waved surface, exactly as shown in Figure 9a. The intermeshing by 1.2 mm refers to 5 the top sections of the waving.
- 3) The process is carried out at ambient temperature 25°C.

The produced single ply has gauge 9.5 g/m², and the produced crosslaminate is 19 g/m². A microphoto of the single ply film is shown as figure 12. The structure of the two products, when observed in microscope, looks 10 generally similar to the structure shown in Figure 1, but with the following differences:

- 1) The wavelength of the “ribbon-like regions” (A), which in Figure 1 is about 0.6-1.2 mm and is irregular, now is even and corresponds to the wavelength of the roller shown in Figure 9a, i.e. 2.5 mm.
- 15 2) The thinner “webs” (B) which in Figure 1 are narrower than (A) now are slightly wider than (A), giving improved flexibility.
- 3) The “amplitude” of the waving, i.e. average vertical distance between each high region on one side and adjacent high regions on other side, now is about 0.5-0.6 mm, giving the film a particularly warm feel.

20 This high “amplitude” is remarkable, since the “amplitude” of the waving on one of the grooved, sharp-edged rollers is no more than 0.25 mm. It is a consequence of the variable degree of orientation within each region (A), produced by the gear roller stretching.

CLAIMS

1. A film or assembly of films, the or each film being formed of thermoplastic polymer material and comprising an array of parallel band-shaped, linearly extending regions (A) and distinct there from as this expression is 5 specified in the description linearly extending webs (B) which integrally connect said regions (A), each web (B) being at each location of its linear extension thinner than the adjacent portions of regions (A), and in which film or assembly of films both (A) and (B) are oriented having at each location a dominating direction of orientation, characterised in that in said film or in each film of the 10 assembly the dominating direction of orientation in the regions (A) forms angles (v) higher than zero but no higher than 80° with the direction in which (A) extends, and the said webs (B) comprise arrays of linear furrows (C) which either are necking-down zones or are splits, said furrows forming angles (u) higher than (v) to the directions in which (A) extends.
- 15 2. A product according to claim 1, characterised in that in said film or in each film of the assembly the dominating direction of orientation at each location forms an angle of no less than 10° , preferably no less than 20° , with the direction in which (A) extends.
- 20 3. A product according to claim 1 or 2, characterised in that the regions (A) are waved, each wave extending over the width of such region and the webs being shorter than adjacent parts of the regions (A) so as to stabilize the waving.
- 25 4. A product according to claim 3, characterised in that the linear extending regions (A) form interrupted lines, the regions of interruptions (D) formed of webs thinner than (A) being generally similar to the webs (B) and without any distinct border between the said two web regions, whereby each interrupted linear region (A) including its thinner interruptions (D) is waved, the webs (D) forming the crests of this waving.
- 30 5. A product according to any of claims 1-4, characterised in that the degree of orientation within each region (A) varies in sequences no longer than 10 mm, and preferably no longer than 5 mm.
6. A product according to any of claims 1-5, characterised in that it is an assembly of films in the form of a crosslaminate, whereby the dominating directions of orientation at each location of the laminate cross each other, the

30

assembled films being joined in spots or lines or both by bonding or blocking or both.

7. A crosslaminate according to claim 6, characterised in that the regions (A) in the different crosslaminated films cover each other along their full 5 length, and the webs (B) similarly cover each other.

8. A crosslaminate according to claim 7, characterised in that the bonding or blocking is limited so as to leave most of each web (B) unbonded and unblocked.

9. A crosslaminate according to any of claims 6-8, characterised in 10 that the bonding or blocking is established through surface layers selected to aid the laminating.

10. A crosslaminate according to claim 7 or claim 8, characterised in 15 that in the regions (A) the angle between the dominating directions of orientation of any two laminated films is smaller than the sum of the angles which each of these directions form with the direction in which the regions (A) extends.

11. A product according to any of claims 1-10, characterised in that the webs (B) and regions of interruptions (D) if the linear extending lines (A) are interrupted, are in through going micro-voided state, the fibrillation substantially following the local dominating direction of orientation, while the rest of the 20 regions (A) are with less or no through going micro-voids.

12. A product according to any of claims 1-11, characterised in that at least 50% of said film or each of the films in the assembly consists of HDPE or isotactic or syndiotactic PP, preferably of HMWHDPE.

13. A product according to any of claims 1-12, characterised in that 25 the gauge of said film or of each film in the assembly is no more than 15 grams per sq.m, preferably no more than 10 grams per sq.m.

14. A product according to any preceding claim, characterised in that the average gauge of each web (B), is at the highest 70% of the average gauge of the two adjacent regions (A).

30 15. A crosslaminate according to claim 7, characterised in that in all directions the elongation at break is no less than 100% and the ultimate tensile strength no less than 10 MPa, referring to tensile testing of 2.5 cm wide ribbons at a velocity corresponding to 500% elongation per minute.

16. A product according to any preceding claim, characterised in that the width of each region (A) is at the highest 2 mm, preferably at the highest 1 mm, and still more preferably at the highest 0.5 mm.

17. A product according to claim 16, characterised in that the division 5 of the array of regions (A) is at the highest 4 mm, preferably at the highest 2 mm, and still more preferably at the highest 1 mm.

18. A product according to any preceding claim, characterised in that the product is continuous and the extension of regions (A) is substantially parallel with the continuous extension of the product.

10 19. A method of producing the product according to claim 1, by stretching starting with a film or an assembly of films each having a predominant direction of orientation, the stretching being carried out by means of a pair of mutually intermeshing first grooved rollers and taking place in a direction which is different, but at the highest 80° different from the predominant original 15 direction of orientation in the said single film or in each of the said assembled films, characterised in that at least one of the grooved rollers in the pair has crests with edges which are sufficiently sharp to form a distinct division as this expression is specified in the description between parallel, linear extending webs (B) of film material, which have been coldstretched between the crests of the two 20 first grooved rollers and intervening linearly extending band-shaped regions (A), which have laid on the sharp edged crests and have not been stretched or have been stretched to a smaller extent between the said grooved rollers.

20. A method according to claim 19, characterised in that the degree of stretching in said coldstretching procedure is sequentially varied by giving the 25 crests of at least one roller in the pair of grooved rollers a waved surface shape.

21. A method according to claim 19 or 20, in which said film material consists of an assembly of two or more such films, characterised in that the predominant directions of orientation in the different films cross each other at each location.

30 22. A method according to claim 21, characterised in that during said coldstretching there is established a bonding or blocking between two or more films, localised to the regions (A) or to boundaries between the webs (B) and the regions (A) or both, for example under use of films which by coextrusion have been supplied with a suitable lamination layer.

23. A method according to any of claims 19-22, characterised in that starting material comprises an additive suitable for producing fibrillation or through-going micro-voiding of the furrows (C) in the webs (B) while maintaining the coherence of webs (B) and their integral connection with (A).

5 24. A method according to any of claims 19-23 characterised in that each of the grooved rollers has crests with edges which are sufficiently sharp to form such distinct division.

10 25. A method according to any of claims 19-24, characterised in that the grooves on each first grooved roller are circular or are helical under an angle no smaller than 85° to the axis of the roller to make the regions (A) extend parallel with the machine direction or under a small angle to the latter.

15 26. A method according to any of claims 19-25, characterised in that the orientation in the starting film or films is limited to the orientation which has taken place in molten or semi-molten state in connection with the extrusion.

20 27. A method according to any of claims 19-25, characterised in that the orientation in the starting film or films comprises a preceding coldstretching process.

28. A method according to claim 27, characterised in that said preceding coldstretching is a sequential stretching preferably between second grooved rollers which have axially extending teeth.

25 29. A method according to any of claims 19-28, characterised in that in order to enhance a transverse waving of the regions (A) and stabilize this waving by contractions within the webs (B) the film or assembly of films coldstretched between the first grooved roller is slightly tentered in the direction in which the stretching took place, preferably while allowing a contraction of the film or film assembly in a direction transverse hereof, and preferably at an elevated temperature.

30 30. A method according to claim 22, characterised in that prior or subsequent to the coldstretching between said pair of first grooved rollers, the assembly of films is heated for bonding, said heating being generally localized to areas within the regions (A) and carried out by means of one or more second grooved rollers which are adjusted to be in register with the first grooved rollers.

31. A method according to claim 26, for manufacture of a 2-ply crosslaminate, characterised by being carried out in line with the extrusion and

melt orientation of a tubular film, whereby the extrusion die rotates relative to the take-off means to produce a helically extending predominant direction of orientation, and the tubular film is laid flat with the predominant directions of orientation on the two sides crossing each other.

5 32. A method according to claim 23, the polymer material is a bimodal combination of i) HMWHDPE and ii) HDPE of a much higher melt flow index than the HDPE, e.g. 20 times so high or higher, with an addition of split-promoting micro-grains, preferably consisting of chalk or talc.

10 33. A method according to claim 23, characterized in that the polymer material is a blend of HDPE, preferably HMWHDPE, and minor amounts of an extrudable water-soluble polymer of a lower melting point, e.g. polyoxyethylene.

15 34. A method according to any of claims 19-22, characterized in that the choice of starting material and the parameters of the coldstretching process are adapted to produce a pattern of thin film portions in the webs (B) in form of parallel stretching lines and subsequent to the stretching these film portions are disrupted by passage of the product over a stream of hot air, the conditions of this treatment being controlled to avoid a general disruption of the product.

20 35. A method according to any of claims 19-23, characterized in that one of the grooved rollers or some part(s) of one of the grooved rollers have rounded crests or crests with rounded edges, while the corresponding part of the grooved roller which matches herewith has crests with edges which are sufficiently sharp to form the distinct division.

36. Use of the film or film assembly according to claim 1, for manufacture of bags.

25 37. The use according to claim 36, for manufacture of garbage bags, the film or the assembly of films being essentially in non-fibrillated form and without through-going voids.

38. Use of the crosslaminate according to claim 1, for sanitary purposes, e.g. in diapers or similar products.

30 39. Apparatus for trans-direction stretching of thermoplastic polymer film comprising a pair of intermeshing grooved stretching rollers having generally cylindrical grooves and teeth, characterised in that the teeth of at least one roller have sharp-edged crests and have a waved surface shape.

34

40. Apparatus according to claim 39, in which the other roller of the pair of grooved stretching rollers has cylindrical teeth with substantially no surface waving.

41. Apparatus according to claim 39 or 40, which is for stretching of 5 an assembly of at least two thermoplastic polymer films which comprises a pair of laminating rollers, at least one of which has generally cylindrical grooves and teeth in register with the teeth of the stretching rollers, at least one of the laminating rollers being heated, so that passage of the assembly of films between the laminating rollers effects bonding of the films in strips.

10 42. Apparatus according to claim 41, in which the crests of the teeth of the grooved laminating roller are rounded.

43. Apparatus according to any of claims 39 to 42, in which the waves 15 of the surface shape of a stretching roller have a radius of curvature which is largest at the greatest distance from the axis of the roller and smallest at the smallest distance from this axis.

Fig. 1




Fig. 2a




Fig. 2b

Fig. 2c




Fig. 3






Fig. 4

Fig. 5








Fig. 7**Fig. 8**



Fig.9a**Fig.9b**

Fig.10b




Fig. 10a




Fig. 11




Figure 12






Fig.13

Fig.14



INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2009/050412

A. CLASSIFICATION OF SUBJECT MATTER
INV. B29C55/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category* | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|-----------|--|-----------------------|
| A | WO 91/12125 A (CLOPAY CORP [US]) 22 August 1991 (1991-08-22) claims 1,10; figures ----- | 1-43 |
| A | EP 0 810 078 A (PROCTER & GAMBLE [US]) 3 December 1997 (1997-12-03) figure 2 ----- | 39-43 |
| A | WO 2006/072604 A (RASMUSSEN OLE-BENDT [CH]) 13 July 2006 (2006-07-13) cited in the application figure 6 ----- | 39-43 |

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

| | |
|--|--|
| Date of the actual completion of the international search | Date of mailing of the international search report |
| 29 April 2009 | 11/05/2009 |
| Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016 | Authorized officer Attalla, Giancarlo |

INTERNATIONAL SEARCH REPORT
Information on patent family members
International application No
PCT/EP2009/050412

| Patent document cited in search report | Publication date | | Patent family member(s) | Publication date |
|--|------------------|--|--|--|
| WO 9112125 | A 22-08-1991 | | AR 246533 A1 AT 106314 T AU 642981 B2 AU 7304691 A BR 9106035 A CA 2075940 A1 DE 69102267 D1 DE 69102267 T2 DK 515501 T3 EP 0515501 A1 ES 2055593 T3 IE 910448 A1 JP 7045174 B | 31-08-1994 15-06-1994 04-11-1993 03-09-1991 02-02-1993 13-08-1991 07-07-1994 15-09-1994 10-10-1994 02-12-1992 16-08-1994 14-08-1991 17-05-1995 |
| EP 0810078 | A 03-12-1997 | | AU 3064997 A CA 2256474 A1 JP 2000500712 T KR 20000016103 A WO 9745254 A1 ZA 9704382 A | 05-01-1998 04-12-1997 25-01-2000 25-03-2000 04-12-1997 23-12-1997 |
| WO 2006072604 | A 13-07-2006 | | AU 2006204518 A1 CA 2594263 A1 EP 1843897 A2 JP 2008526556 T KR 20070091644 A | 13-07-2006 13-07-2006 17-10-2007 24-07-2008 11-09-2007 |