



(51) International Patent Classification:

D04H 1/413 (2012.01) *D04H 1/488* (2012.01)
D04H 1/4209 (2012.01) *D04H 1/64* (2012.01)
D04H 1/46 (2012.01) *F01N 3/28* (2006.01)

(21) International Application Number:

PCT/US2016/050493

(22) International Filing Date:

7 September 2016 (07.09.2016)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

15184316.6 8 September 2015 (08.09.2015) EP

(71) Applicant: **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(72) Inventors: **KUNZE, Ulrich**; Carl-Schurz-Strasse 1, 41453 Neuss (DE). **ROSEN, Kerstin**; Carl-Schurz-Strasse 1, 41453 Neuss (DE).

(74) Agents: **KNECHT, Harold, C., III** et al.; 3M Center, Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: MOUNTING MEMBER FOR WRAPPING AND MOUNTING A POLLUTION CONTROL ELEMENT




Fig. 2

(57) Abstract: The invention relates to a mounting member for wrapping and mounting a pollution control element in a casing of a pollution control device, the mounting member comprising: inorganic fiber material; and inorganic particles, wherein the inorganic particles are distributed throughout most of the mat and comprise an average diameter of 800 nm to 15000 nm (DV 50), preferably of 1000 nm to 15000 nm (DV 50) measured according to DIN ISO 13320.

MOUNTING MEMBER FOR WRAPPING AND MOUNTING A POLLUTION CONTROL ELEMENT

Field of the Invention

5 The invention relates to a mounting member for wrapping and mounting a pollution control element in a casing of a pollution control device, with the mounting member comprising inorganic fiber material and inorganic particles. The invention also relates to a method of manufacturing a mounting member for wrapping and mounting a pollution control element in a casing of a pollution control device.

Background

10 Exhaust gas cleaning systems using a ceramic catalytic converter are known as means for removing carbon monoxide (CO), hydrocarbons (HC), and nitrogen oxides (NOx) and the like that are included in exhaust gas from automobile engines. Basically, the ceramic catalytic converter generally stores a ceramic catalyst carrier with a honeycomb shape or the like in a metal casing. Other exhaust gas cleaning systems contain ceramic particulate filters for removing particulates from the exhaust gas of diesel or gasoline engines.

20 There are various types of ceramic catalytic converters, but a general form provides a catalyst carrier or a filter, a casing that stores the catalyst carrier or the filter, and a thermal insulation member that fills the gap between the outer surface of the catalyst carrier or the filter and the inner surface of the casing. The thermal insulation member mounts the catalyst carrier or the filter and prevents mechanical shock due to impact and vibration and the like from being inadvertently applied to the catalyst carrier or the filter. Thereby, moving and breaking of the catalyst carrier or the filter can be sufficiently suppressed, and thus the desired effect can be provided over a long period of time. This type of thermal insulation member is also commonly called a mounting member because the member has a function of mounting a pollution control element such as a catalyst carrier or a filter in a metal shell or the like.

30 JP 2002 206 421 A2 discloses a holding and sealing material for a catalytic converter, that can sufficiently maintain the function of retaining the pollution control element in a pollution control device at high temperatures. The holding and mounting material comprises ceramic fibers. The fibers comprise an uneven structure consisting of inorganic particles added to the fibers by sintering.

WO 2012/106295 A1 discloses a mounting member that can sufficiently suppress scattering of inorganic fiber material when a pollution control element is assembled in a casing, and that can maintain sufficiently high contact pressure between the inner surface of the casing and the pollution control element. The mounting member provides a mat
5 made from inorganic fiber material and an aggregated substance containing an organic binder and inorganic fine particles that is impregnated throughout most of the mat.

US 8,071,040 B2 discloses a mounting mat for an exhaust gas treatment device including high temperature resistant ceramic fibers containing alumina and/or high temperature resistant biosoluble inorganic fibers, organic binder which at least partially
10 liquefies at elevated temperature prior to binder burnout, colloidal inorganic oxide and optionally intumescent material. The mounting mat can be easily installed and can function across a wide range of inlet gas temperatures without a significant loss in mat thickness and corresponding shear strength and holding pressure performance.

15 Summary of the Invention

The above cited documents deal with improved behavior of mounting members during its use in a pollution control device especially with improved holding or contact pressure of the mounting member and with reducing fiber scattering. None of the documents deals with the problem of reducing the elongation of a mounting member
20 during the assembly of a pollution control device. Elongation of a mounting member is the length difference between the mat width after assembly in a pollution control device and the width of the virgin mat.

This behavior may lead to a lower than expected mounted density of the mounting member and thus to lower contact pressure of the mounting member (mat) during the use
25 of the pollution control device. A potential compensation of this effect by using a mounting member with a higher area weight adds cost to the system.

The width of a mounting member for a pollution control element is typically adopted to cover the length of the ceramic element of the pollution control device either completely or a significant portion of it. The elongation of a mounting member needs to
30 be taken into account to avoid that the mounting member extends over the edge of the ceramic element after assembly. A lower elongation allows the use of wider mounting members leading to higher holding force of the ceramic element in the metallic shell.

In view of the above it is an object of the invention to provide a mounting member that on the one side can sufficiently maintain the function of retaining the pollution

control element in a pollution control device during its use across wide temperature ranges and that on the other side has an improved behaviour during the assembly of the pollution control device, e.g. provides a reduced elongation during canning. The reduction of the elongation helps to reduce the amount of the relative expensive inorganic fiber material and on the other hand to ensure a high enough mount density.

It has been found that a mounting member for wrapping and mounting a pollution control element in a casing of a pollution control device, in accordance with the present invention, can provide excellent performance during the use of the pollution control device and has a reduced elongation during canning. Such a mounting member can have the following features:

- inorganic fiber material; and
- inorganic particles, wherein the inorganic particles are distributed throughout most of the mounting member and comprise an average diameter of DV 50 of 800 nm to 15000 nm measured according to DIN ISO 13320, preferably 1000 nm to 15000 nm.

The particle size is defined as DV 50, which is the median particle diameter on a volumetric basis, i.e. 50% by volume of the particles are smaller than this diameter and 50% are larger. The diameters are measured according to DIN ISO 13320.

It has been found a mounting member for wrapping and mounting a pollution control element in a casing of a pollution control device with inorganic particles being distributed throughout most of the mounting member, wherein the size of the particles is in the claimed range provides an improved elongation during mounting the pollution control device while still showing sufficient retaining forces of the pollution control element in a pollution control device during its use across wide temperature ranges. The positive effect in elongation may also reduce the waste during production and may therefore provide a cost benefit.

According to one embodiment, the inorganic fiber material of the mounting member may comprise fibers selected from the group of glass fibers, ceramic fibers, carbon fibers, silicon carbide fibers or boron fibers or a combination thereof. Other fibers are possible as well as long as they withstand the high temperatures occurring in a pollution control device and the required holding forces during use of the pollution control device.

According to another embodiment of the invention, the inorganic fiber material may be needle punched. Other ways of compressing the inorganic fiber material may be

used as well such as for example stitch-bonding, resin bonding, applying pressure and/or combinations thereof.

According to another embodiment of the invention, the inorganic particles are selected from the group consisting of metal oxides, metal hydroxides, metal oxide
5 hydroxides, silicates, clays, nitrides, carbides, sulphides, carbonates and combinations thereof. They may for example be selected from Dispal™ particles from Sasol Corporation, USA. With Dispal™ 23N4-80 and Dispal™ 18N4-80 particles from Sasol Corporation, USA very good results have been achieved as will be explained in the example section of this patent application.

10 According to one embodiment the mount member may contain organic binder up to 3 wt. %. It is also possible to achieve good results without any binder, as shown in the examples. But the use of binder may under certain conditions lead to better results of the elongation. The amount of binder used needs to be optimized regarding the ability to sufficiently hold the pollution control element within the pollution control device during
15 use.

According to another embodiment, the inorganic particles may get impregnated through the mat by using a water base slurry containing the inorganic particles. An easy way of distributing the particles throughout the mat is to prepare a slurry, for example a water based slurry and apply the slurry onto the mat. The slurry needs to be of a
20 concentration that allows the particles to migrate throughout most of the mat. If the slurry is too concentrated, which means if the concentration of particles within the slurry is too high, the risk exists, that the particles stay on the surface of the mounting member and do not migrate into the mounting member. It is also possible to distribute the particles within the mounting member during the fiber laying process by mixing the particles with the
25 fibers before laying them to a mat.

The slurry may contain at least 80 wt. %, preferably 90 wt. % and more preferably 95 wt. % of water. The slurry may also contain an organic binder.

The organic binder may comprise at least one of polymers or copolymers of acrylate, methacrylate, styrene, butadiene, vinyl pyridine, acrylonitrile, vinyl chloride,
30 vinyl acetate, vinyl alcohol or ethylene, polyurethane, polyamides, silicones, polyesters, epoxy resins, or combinations thereof.

Furthermore the concentration of the inorganic particles within the mounting member may be between 0.5 and 5 wt. %, preferred between 1.0 and 2.5 wt. %.

According to yet another embodiment, the maximum reduction of mount density of a mounting member according to the invention may be 3 % caused by an elongation of the mounting member during stuffing at a calculated mount density of 0.4 g/cm³. The calculated mount density of the mounting member in the pollution control device (assuming no mat elongation) is calculated by dividing the weight per area 2 times by the difference between metal shell inner diameter minus the pollution control element outer diameter. The following formula illustrates the calculation:

MD_c – calculated mount density

W/A_m – weight per area or area weight of mounting member (mat)

ID_{ms} – metal shell inner diameter

OD_{pce} – pollution control element outer diameter

Wt_m – weight of (mat)

L_m – length of mat

W_m – width of mat (= length of pollution control element)

$$MD_c = \frac{W/A \times 2}{ID_{ms} - OD_{pce}}$$

whereby W/A is calculated as follows:

$$W/A = \frac{Wt_m}{L_m \times W_m}$$

Calculation of the mount density reduction: After canning the mounting member may extend over the pollution control element due to its elongation during the canning process. This portion of the mat is cut off and weighed. This cut off weight is subtracted from the original mat weight and the reduced weight per area of the mat after canning is calculated based on its original dimension. The mount density after canning is calculated using the weight per area after canning. The mount density difference is calculated in percent of the calculated mount density. The following formula illustrates the calculation:

MD_{red} – mount density reduction

MD_{ac} – mount density after canning

Wt_{em} – weight of mat extended over the edge of the pollution control element after canning

$$W/A_{ac} = \frac{Wt_m - Wt_{em}}{L_m \times W_m}$$

$$MD_{ac} = \frac{W/A_{ac} \times 2}{ID_{ms} - OD_{pce}}$$

$$MD_{red} = \frac{MD_c - MD_{ac}}{MD_c} \times 100\%$$

5 The mounting member may comprise intumescent material disposed in the mat member. As used herein, "intumescent material" means a material that expands, foams, or swells when exposed to a sufficient amount of thermal energy. Useful intumescent materials for use in making an intumescent mounting member may include, but are not limited to, unexpanded vermiculite ore, treated unexpanded vermiculite ore, partially
10 dehydrated vermiculite ore, expandable graphite, mixtures of expandable graphite with treated or untreated unexpanded vermiculite ore, processed expandable sodium silicate, for example EXPANTROL™ insoluble sodium silicate, commercially available from 3M Company, St. Paul, Minn., and mixtures thereof. Another example of a desirable commercially available expandable graphite material is GRAFOIL™ Grade 338-50
15 expandable graphite flake, from UCAR Carbon Co., Inc., Cleveland, Ohio.

The invention also relates to a method of manufacturing a mounting member for wrapping and mounting a pollution control element in a casing of a pollution control device comprising the following steps:

- preparing a water based slurry containing fine inorganic particles with an average
20 diameter DV 50 of 800 nm to 15000 nm measured according to DIN ISO 13320, preferably DV 50 of 1000 nm to 15000 nm measured according to DIN ISO 13320; and
- impregnating a mat containing inorganic fiber material with the slurry.

25 The method according to the invention may also comprise a drying step after the impregnating step. The drying may be done by room temperature or by elevated temperatures, such as for example temperatures between 100°C and 180°C. The drying may also be done by using an air stream.

The slurry used for the method according to the invention may contain an organic binder.

And finally the invention relates to the use of inorganic particles for producing a mounting member for wrapping and mounting a pollution control element in a casing of a pollution control device, wherein the average diameter of the fine particles ranges from DV 50 of 800 nm to 15000 nm measured according to DIN ISO 13320, preferably from DV 50 of 1000 nm to 15000 nm according to DIN ISO 13320.

Brief Description of the Drawings

The invention will now be described in more detail with reference to the following Figures exemplifying particular embodiments of the invention:

Fig. 1 is a perspective view illustrating the retaining material according to an embodiment of the present invention;

Fig. 2 is a cross-sectional view schematically illustrating the pollution control device according to an embodiment of the present invention.

Detailed Description of Embodiments of the Invention

Herein below various embodiments of the present invention are described and shown in the drawings wherein like elements are provided with the same reference numbers.

Fig. 1 is a perspective view illustrating an example of the mounting member of the present invention. The mounting member 10 illustrated in this figure may be wrapped around a pollution control element 30 having for example a round cylindrical or elliptical cylindrical outer shape, in order to retain the element in a casing 20 (refer to Fig. 2). All other shapes of the pollution control element 30 are possible as well. The mounting member 10 has a length that is in accordance with the length of the outer circumference of the pollution control element 30. The mounting member 10 has a convex part 10a and a concave part 10b on another end, for example, and has a shape such that the convex part 10a and the concave part 10b mutually engage when the mounting member 10 is wrapped around the pollution control element 30, but the shape for the mating is not restricted in particular, and any shape that can effectively prevent leaking of the exhaust gas in the mating region is acceptable, and other shapes such as an L shape are also possible. The mounting member 10 has also a width that is in accordance with the length of the pollution control element 30. As already pointed out above the width of the mounting

member 10 needs to take into account an elongation of the mounting member 10 that might occur, when the mounting member 10 being wrapped around the pollution control element 30 gets stuffed into the casing 20, to avoid that the mounting member 10 after stuffing extends over the edge of the pollution control element 30.

5 Fig. 2 shows the mounting member 10 that is used to retain the pollution control element 30 in a pollution control device 50. A specific example of the pollution control element 30 is a catalyst carrier or a filter element or the like that is used for cleaning the exhaust gas from an engine. Specific examples of the pollution control device 50 include catalytic converters and exhaust cleaning devices (for example, a particulate filter device).

10 The pollution control device 50 illustrated in Fig. 2 has a casing 20, a pollution control element 30 provided in the casing 20, and a mounting member 10 provided between the inner surface of the casing 20 and the outer surface of the pollution control element 30. The pollution control device 50 also has a gas intake port 21 where the exhaust gases are introduced to the pollution control element 30, and a gas discharge port
15 22 where the exhaust gas that has passed through the pollution control element 30 is discharged.

The width of the gap between the inner surface of the casing 20 and the outer surface of the pollution control element 30 may be between 1.5 to 15 mm, preferably 3 to 10 mm. The mounting member 10 is preferably in an appropriately compressed condition
20 to achieve a suitable bulk density between the casing 20 and the pollution control element 30. By using the mounting member 10 according to the invention to retain the pollution control element 30, a sufficiently high surface pressure can be maintained between the inner surface of the casing 20 and the pollution control element 30. Furthermore, the elongation during the mounting of the pollution control element into the pollution control
25 device can be reduced as compared to conventional mounting members, and therefore the usage amount of the relative expensive inorganic fiber material can be reduced.

EXAMPLES

The present invention is described while referencing examples. Note that the
30 present invention is in no way restricted by these examples.

All examples are based on alumina-silica fiber blankets from Mitsubishi Plastics Inc. (Maftec MLS2). The mats are spray impregnated with a slurry of inorganic particles. In some examples an additional an organic latex binder was added to the slurry in addition to the inorganic particles. The impregnated mats were dried and then tested. The tests

include multi-cycle compression testing at elevated temperatures and hard stuffing tests to determine the mat elongation.

Components Examples:

- 5 Inorganic particles: Dispal™ 23N4-80, Dispal™ 18N4-80 both from Sasol Corporation, 12120 Wickchester Lane, Houston TX 77079, USA
- Organic binder: Acronal™ A273S from BASF SE, Ludwigshafen, Germany.

Components Comparative Examples:

- 10 Inorganic particles: Snowtex™ OS; Nissan Chemical Industries, Japan; Colloidal Alumina; Nissan Chemical Industries, Japan
- Organic binder: Nipol™ LX 874; Nippon Zeon Co., Japan

Slurry Preparation:

- 15 The slurries for impregnation were prepared by adding the inorganic particles to water in an amount according to the below table and stirring with a laboratory mixer for 5 minutes. In some samples (see also below table) additional organic binder was added afterwards and was stirred for 1 additional minute.

Example No.	Inorganic Particle or Slurry	Organic Binder Emulsion	Inorganic Particle or slurry	Organic Binder Emulsion	Water
			wt. %	wt. %	wt. %
1	Dispal 23N4-80	None	0.74	-	99.3
2	Dispal 23N4-80	Acronal A273S	0.74	0.18	99.1
3	Dispal 18N4-80	None	0.74	-	99.3
4	Dispal 18N4-80	Acronal A273S	0.74	0.18	99.1
Comp. Ex. 1	no particles	no binder	-	-	
Comp. Ex. 2	Snowtex OS	Nipol LX874	4.6	0.13	95.3
Comp. Ex. 3	Colloidal Alumina	Nipol LX874	6.7	0.13	93.2
Comp. Ex. 4	Snowtex OS	Nipol LX874	4.6	0.13	95.3
Surface Coating Comp. Ex. 2 and 3	Snowtex OS	Nipol LX874	48.5	1.5	50.0

Example 1:

A sheet of the MLS 2 blanket was cut into pieces and impregnated by spraying the above described slurry containing the Dispal™ 23N4-80 particles, particle size 1.87 nm

(DV 50) measured according to DIN ISO 13320, onto the blanket. After the liquid was impregnated into the blanket in this manner, drying was performed in a forced air dryer for 15 minutes at 150°C air temperature. The impregnated and dried mounting member contained about 1.5 % by weight of the particles.

5

Example 2:

A sheet of the MLS 2 blanket was cut into pieces and impregnated by spraying the above described slurry containing the Dispal™ 23N4-80 particles, particle size 1.87 nm (DV 50) measured according to DIN ISO 13320, and the organic binder Acronal™ A273S, onto the blanket. After the liquid was impregnated into the blanket in this manner, drying was performed in a forced air dryer for 15 minutes at 150°C air temperature. The impregnated and dried mounting member contained about 1.5% by weight of the inorganic particles and 0.8% by weight organic binder.

10

15

Example 3:

A sheet of the MLS 2 blanket was cut into pieces and impregnated by spraying the above described slurry containing the Dispal™ 18N4-80 particles, particle size 3.51 nm (DV 50) measured according to DIN ISO 13320, onto the blanket. After the liquid was impregnated into the blanket in this manner, drying was performed in a forced air dryer for 15 minutes at 150°C air temperature. The impregnated and dried mounting member contained about 1.5% by weight of the particles.

20

Example 4:

A sheet of the MLS 2 blanket was cut into pieces and impregnated by spraying the above described slurry containing the Dispal™ 18N4-80 particles, particle size 3.51 nm (DV 50) measured according to DIN ISO 13320, and the organic binder Acronal™ A273S, onto the blanket. After the liquid was impregnated into the blanket in this manner, drying was performed in a forced air dryer for 15 minutes at 150°C air temperature. The impregnated and dried mounting member contained about 1.5% by weight of the particles and 0.8% by weight of the organic binder.

25

30

Comparative Example 1a:

MLS 2 blanket without any treatment was cut into pieces and used as comparative example 1a. For the stuffing and multi-cycle tests, the mounting density was adapted to the mounting density of examples 1 and 2.

5

Comparative Example 1b:

MLS 2 blanket without any treatment was cut into pieces and used as comparative example 1b. For the stuffing and multi-cycle tests, the mounting density was adapted to the mounting density of examples 3 and 4.

10

Comparative Example 2:

A comparative sample was prepared by adding inorganic colloid particles (Snowtex™ OS, produced by Nissan Chemical Industries, Ltd.) 68.55 g and 2.0 g organic binder (Nipol™ LX874, produced by Nippon Zeon Co., Ltd.) to 1429.50g Water and stirring for 5 minutes. The inorganic colloidal particles had a particle size of 16.9 nm (DV 50) measured according to DIN ISO 13320. A needle punched alumina fiber blanket (produced by Mitsubishi Plastics, Inc.) was impregnated by spraying the above described slurry onto the blanket. After the liquid was impregnated into the blanket in this manner, drying was performed for 15 minutes using a forced air dryer with the temperature set to 150°C.

20

A second liquid containing inorganic colloid particles and organic binder was prepared by adding 63g of colloidal silica (Snowtex™ OS) and 10g Nipol™ LX874 to 65g of water and stirring for 1 minute. The second liquid was coated to both an upper and lower surface of the blanket that had been impregnated before with the first liquid. In total the amount of 7g/m² of colloid silica was sprayed onto both surfaces and the total amount of organic binder was 0.8%. The impregnated material was dried for 5 minutes in a forced air dryer with temperature set to 150°C.

25

Comparative Example 3:

A first liquid containing colloidal particles and organic binder was prepared by adding 201g of colloidal alumina (alumina sol, produced by Nissan Chemical Industries, Ltd.) and 3.99g organic binder (Nipol™ LX874, produced by Nippon Zeon Co., Ltd.) to 2790g Water and stirring for 5 minutes. The inorganic colloidal particles had a particle size of 0.76 nm (DV 50) measured according to DIN ISO 13320. A needle punched

30

alumina fiber blanket (produced by Mitsubishi Plastics, Inc.) was impregnated by spraying the above described slurry onto the blanket. After the liquid was impregnated into the blanket in this manner, drying was performed for 15 minutes using a forced air dryer with the temperature set to 150°C.

5 A second liquid containing inorganic colloid particles and organic binder was prepared by adding 63g of colloidal silica (Snowtex™ OS) and 10g Nipol™ LX874 to 65g of water and stirring for 1 minute. The second liquid was coated to both an upper and lower surface of the blanket that had been impregnated before with the first liquid. In total the amount of 7g/m² of colloid silica was sprayed onto both surfaces and the total amount
10 of organic binder was 0.8%. The impregnated material was dried for 5 minutes in a forced air dryer with temperature set to 150°C.

Comparative Example 4:

15 A further comparative sample was prepared by adding inorganic colloid particles (Snowtex™ OS, produced by Nissan Chemical Industries, Ltd.) 68.55g and 2.0g organic binder (Nipol™ LX874, produced by Nippon Zeon Co., Ltd.) to 1429.50g Water and stirring for 5 minutes. The inorganic colloidal particles had a particle size of 16.9 nm (DV 50) measured according to DIN ISO 13320. A needle punched alumina fiber blanket (produced by Mitsubishi Plastics, Inc.) was impregnated by spraying the above described
20 slurry onto the blanket. After the liquid was impregnated into the blanket in this manner, drying was performed for 15 minutes using a forced air dryer with the temperature set to 150°C.

Evaluation Tests

25 **Measurement of particle size**

 The particle size is determined with laser diffraction according to DIN ISO 13320: 2009(E). The particle size is defined as DV50, which is the median particle diameter on a volumetric basis, i.e. 50% by volume of the particles are smaller than this diameter and 50% are larger.

30

Measurement of multi cycle compression

 The multi-cycle compression test is frequently used to design applications. The Examples were tested at a temperature of 650°C, the gap was cycled 1000 times between a closed gap and an open gap density. The open gap pressure after cycling is recorded.

For the tests in these examples a material test machine from Zwick/Roell Model Z010 from Zwick GmbH & Co KG, Ulm, Germany was utilized. The test machine was equipped with a lower fixed heatable stainless steel block and a load cell capable of measuring forces up to 10 kN and an upper heatable stainless steel block mounted to the movable crosshead of the test machine. For the tests a sample of each example and comparative example with 50.8 mm diameter was cut out of the mounting member and placed on the lower heatable stainless steel block. The crosshead was moved downwards to compress the mounting member to a defined closed gap, which corresponds to a density of the mounting member of 0.366 g/cm³. The temperature of the heatable stainless steel blocks was raised to 650°C while keeping the gap constant. After reaching the temperature of 650°C, the gap was cycled between the closed gap position corresponding to a density of the mounting member of 0.366 g/cm³ and an open gap position corresponding to a density of the mounting member of 0.329 g/cm³. After 1000 cycles the test was stopped and the open gap pressure after 1000 cycles was recorded.

Measurement of elongation

Hard stuffing experiments were conducted to determine the elongation of the mounting members. The area weight of the mounting members, the metal shell inner diameter, and the pollution control element outer diameter were chosen to achieve a desired calculated mount density. The metal shell was calibrated using a shrinking machine from the company Wecotech, Gähwil, Switzerland. The transition angle between the inner shell diameter at the entrance side and the calibrated inner diameter was kept between 14° and 16°, in order to ensure consistent conditions for each example.

The mounting members were cut so that they covered the complete length of the pollution control element. The mounting members were wrapped around the corresponding pollution control element and the stuffing was performed using a stuffing funnel with a contraction of 1.6°. A compression test machine MTS Alliance RT/30 from MTS, Eden Prairie, MN, USA was utilized to push the pollution control element together with the mounting member into the metal shell at a defined speed of 500 mm/min.

After stuffing the mat extended over the pollution control element due to the elongation during the stuffing process. This portion of the mat was cut and weighed to determine the effective mount density of the mat in the pollution control device.

In the following table the particle diameters of all examples and comparative examples are shown as well as the measured elongation and the results of the multi-cycle compression test:

			Elongation				Multi-Cycle-Compression		
	Par- ticle dia. (DV 50)	Mat weight	Calcul. mount density*	Weight of material extend. over the edge	Eff. mount density	Mount density reduc- tion**	Closed cap density	Open gap density	Open gap press. after 1000 cycles
	nm	(g)	(g/cm ³)	(g)	(g/cm ³)	%	(g/cm ³)	(g/cm ³)	(kPA)
Example 1	1.87	124.9	0.391	2.02	0.385	1.5	0.366	0.329	84
Example 2	1.87	125.1	0.392	2.843	0.383	2.3	0.366	0.329	75
Comp. Ex. 1a	-	123.5	0.391	4.25	0.378	3.3	0.366	0.329	70
Example 3	3.51	126.3	0.401	2.965	0.392	2.2	0.366	0.329	68
Example 4	3.51	128.8	0.402	3.696	0.390	3.0	0.366	0.329	55
Comp. Ex. 1b	-	127.6	0.398	4.815	0.393	3.8	See Comp. Ex. 1a		
Comp. Ex. 2	16.9	Does not work in canning process – the mat does not slide into the can and is destroyed during the stuffing process							
Comparative Example 3	0.76	Does not work in canning process – the mat does not slide into the can and is destroyed during the stuffing process							
Comparative Example 4	16.9	Does not work in canning process - the mat does not slide into the can and is destroyed during the stuffing process							

5

*Calculated mount density: is the calculated mount density of the mounting member in the pollution control device (assuming no mat elongation). It is calculated by dividing the weight per area 2 times by the difference between metal shell inner diameter minus pollution control element outer diameter.

10

MD_c – calculated mount density

W/A_m – weight per area or area weight of mounting member (mat)

ID_{ms} – metal shell inner diameter

OD_{pce} – pollution control element outer diameter

W_{t_m} – weight of (mat)

15

L_m – length of mat

W_m – width of mat (= length of pollution control element)

$$MD_c = \frac{W/A \times 2}{ID_{ms} - OD_{pce}}$$

$$W/A = \frac{W_{t_m}}{L_m \times W_m}$$

20

**Mount density reduction: (Uli kannst Du bitte noch angeben, wie die berechnet wird?)

After canning the mat extends over the pollution control element due to its elongation

during the canning process. This portion of the mat is cut off and weighed. This cut off weight is subtracted from the original mat weight and the reduced weight per area of the mat after canning is calculated based on its original dimension. The mount density after canning is calculated using the weight per area after canning. The mount density

5 difference is calculated in percent of the calculated mount density.

MD_{red} – mount density reduction

MD_{ac} – mount density after canning

10 W_{tem} – weight of mat extended over the edge of the pollution control element after canning

$$W/A_{ac} = \frac{Wt_m - Wt_{em}}{L_m \times W_m}$$

$$MD_{ac} = \frac{W/A_{ac} \times 2}{ID_{ms} - OD_{pce}}$$

$$MD_{red} = \frac{MD_c - MD_{ac}}{MD_c} \times 100\%$$

15 The results show:

It can be seen from the table above, that the examples 1 to 4 with the inorganic particles distributed through the mat show less elongation than the comparative example 1a and 1b. Comparative examples 2, 3 and 4 failed completely during the canning, the mats did not slide into the can and were destroyed. For these mounting members no
20 elongation could be measured.

The results show also that the examples 1 and 2, with 1.5% Dispal™ 23N4-80 show the higher results in the multi-cycle compression test. The open gap pressure after 1000 cycles for Examples 3 and 4 is lower than the one for comparative example 1a or 1b but they are still acceptable.

25

CLAIMS

1. A mounting member for wrapping and mounting a pollution control element in a casing of a pollution control device, the mounting member comprising:

- 5 - inorganic fiber material; and
- inorganic particles, wherein the inorganic particles are distributed throughout most of the mounting member and comprise an average diameter of 800 nm to 15000 nm (DV 50) measured according to DIN ISO 13320, preferably of 1000 nm to 15000 nm (DV 50) measured according to DIN ISO 13320.

10

2. The mounting member according to claim 1 wherein the inorganic fiber material comprises fibers selected from the group of glass fibers, ceramic fibers, carbon fibers, silicon carbide fibers or boron fibers or a combination thereof.

15 3. The mounting member according to claim 1 or 2, wherein the inorganic fiber material of the mounting member is needle-punched.

4. The mounting member according to any of the preceding claims, wherein the inorganic particles are selected from the group consisting of metal oxides, metal
20 hydroxides, metal oxide hydroxides, silicates, clays, nitrides, carbides, sulphides, carbonates and combinations thereof.

5. The mounting mat according to any of the preceding claims, wherein the inorganic particles are selected from Dispal™ particles from Sasol Corporation, USA.

25

6. The mounting member according to any of the preceding claims, wherein the mounting member contains organic binder up to 3 wt. %.

7. The mounting member according to any of the preceding claims, wherein the
30 inorganic particles get impregnated through the mat by using a water based slurry containing the inorganic particles.

8. The mounting member according to claim 7, wherein the slurry contains at least 80 wt. % water, preferably 90 wt. % water and more preferably 95 wt. % water.

9. The mounting member according to claim 7 or claim 8, wherein the slurry contains an organic binder.

10. The mounting member according to claim 9, wherein the organic binder comprises at least one of polymers or copolymers of acrylate, methacrylate, styrene, butadiene, vinyl pyridine, acrylonitrile, vinyl chloride, vinyl acetate, vinyl alcohol or ethylene, polyurethane, polyamides, silicones, polyesters, epoxy resins, or combinations thereof.

11. The mounting member according to any of the preceding claims, wherein the concentration of the inorganic particles within the mounting member is between 0.5 and 5 wt. %, preferred between 1.0 and 2.5 wt. %.

12. A mounting member according to any of the preceding claims, having a maximum reduction of the mount density of 3% caused by elongation of the mounting member during stuffing at a calculated mount density of 0.4 g/cm³).

13. The mounting member according to any of the preceding claims, wherein the mounting member comprises intumescent material disposed in the mounting member.

14. Method of manufacturing a mounting member for wrapping and mounting a pollution control element in a casing of a pollution control device, comprising the following steps:

preparing a water based slurry containing fine inorganic particles with an average diameter of 800 nm to 15000 nm (DV 50) measured according to DIN ISO 13320, preferably of 1000 nm to 15000 nm (DV 50) measured according to DIN ISO 13320;

impregnating a mat containing inorganic fiber material with the slurry.

15. The method according to claim 14, wherein the method comprises a drying step after the impregnating step.

16. The method according to claim 14 or claim 15, wherein the slurry contains an organic binder.

- 5 17. Use of inorganic particles for producing a mounting member for wrapping and mounting a pollution control element in a casing of a pollution control device, wherein the average diameter of the fine particles ranges from of 800 nm to 15000 nm (DV 50) measured according to DIN ISO 13320, preferably from of 1000 nm to 15000 nm (DV 50) according to DIN ISO 13320.




Fig. 1




Fig. 2

INTERNATIONAL SEARCH REPORT

International application No

PCT/US2016/050493

A. CLASSIFICATION OF SUBJECT MATTER		
INV.	D04H1/413	D04H1/4209
	F01N3/28	
ADD.	D04H1/46	D04H1/488
		D04H1/64
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
D04H F01N		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
EPO-Internal, WPI Data		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 00/17121 A1 (ROCKWOOL INT [DK]; DYRBOEL SUSANNE [DK]; HANSEN ERLING LENNART [DK]; F) 30 March 2000 (2000-03-30) page 14, line 29 - page 15, line 2; claims 1-3, 21-24	1,2,5, 7-9,14, 15,17
X	US 2011/247839 A1 (LALOUCHE LAHOUSSEINE [FR] ET AL) 13 October 2011 (2011-10-13) paragraphs [0059], [0026] - [0029]; claims 1,5,3,6	1-13
A	WO 2012/106295 A1 (3M INNOVATIVE PROPERTIES CO [US]; SAKO KENJI [JP]) 9 August 2012 (2012-08-09) cited in the application page 8, line 27 - page 9, line 5; claims 1-5	1-17
	-/--	
☒ Further documents are listed in the continuation of Box C. ☒ See patent family annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier application or patent but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
2 December 2016		12/12/2016
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016		Authorized officer Elsässer, Ralf

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2016/050493

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CH 653 288 A5 (MICA FIL AG) 31 December 1985 (1985-12-31) page 3, left column, last two lines; claims	1-17
X	----- WO 2014/160665 A1 (3M INNOVATIVE PROPERTIES CO [US]) 2 October 2014 (2014-10-02) paragraphs [0060] - [0062], [0043]; claims 1,2,4,17 -----	1,14,16, 17

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2016/050493

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 0017121	A1	30-03-2000	AT 258537 T 15-02-2004
		AU 6087499 A 10-04-2000	
		AU 6196399 A 10-04-2000	
		DE 69914501 D1 04-03-2004	
		DE 69914501 T2 04-11-2004	
		DK 1127032 T3 07-06-2004	
		EP 1115674 A1 18-07-2001	
		EP 1127032 A1 29-08-2001	
		ES 2215403 T3 01-10-2004	
		HU 0103850 A2 28-02-2002	
		HU 0104152 A2 28-11-2002	
		WO 0017120 A1 30-03-2000	
		WO 0017121 A1 30-03-2000	
US 2011247839	A1	13-10-2011	CA 2796039 A1 20-10-2011
			CN 102869822 A 09-01-2013
			EP 2561129 A2 27-02-2013
			KR 20130056868 A 30-05-2013
			TW 201142101 A 01-12-2011
			US 2011247839 A1 13-10-2011
			US 2014345882 A1 27-11-2014
			WO 2011130056 A2 20-10-2011
WO 2012106295	A1	09-08-2012	CN 103429865 A 04-12-2013
			EP 2670960 A1 11-12-2013
			JP 5971894 B2 17-08-2016
			JP 2012157809 A 23-08-2012
			KR 20140005275 A 14-01-2014
			US 2013305697 A1 21-11-2013
			WO 2012106295 A1 09-08-2012
CH 653288	A5	31-12-1985	NONE
WO 2014160665	A1	02-10-2014	CN 105074072 A 18-11-2015
			EP 2978886 A1 03-02-2016
			JP 2016517920 A 20-06-2016
			KR 20150137086 A 08-12-2015
			US 2016084140 A1 24-03-2016
			WO 2014160665 A1 02-10-2014