



(11)

EP 4 038 149 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:

25.01.2023 Bulletin 2023/04

(21) Application number: **21798821.1**

(22) Date of filing: **20.10.2021**

(51) International Patent Classification (IPC):
C09D 5/16 (2006.01)

(52) Cooperative Patent Classification (CPC):
C09D 5/16

(86) International application number:
PCT/SE2021/051046

(87) International publication number:
WO 2022/086416 (28.04.2022 Gazette 2022/17)

(54) **ANTIFOULING COMPOUNDS**

ANTIFOULING-VERBINDUNGEN

COMPOSÉS ANTISALISSURE

(84) Designated Contracting States:

**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

(30) Priority: **21.10.2020 SE 2051222**

(43) Date of publication of application:
10.08.2022 Bulletin 2022/32

(60) Divisional application:
22215139.1

(73) Proprietor: **I-Tech AB
431 83 Mölndal (SE)**

(72) Inventors:

- **ISAKSSON, Dan
431 47 Mölndal (SE)**
- **HOFFMANN, Markus
08198 Sant Cugat (ES)**

(74) Representative: **Barker Brettell Sweden AB
Östermalmsgatan 87B
114 59 Stockholm (SE)**

(56) References cited:

**EP-A1- 2 551 309 EP-A1- 3 339 387
EP-A1- 3 480 267 EP-A1- 3 480 268
EP-A1- 3 540 022 WO-A1-2006/096129**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 4 038 149 B1

Description

TECHNICAL FIELD

- 5 **[0001]** The present embodiments generally relate to antifouling compounds, methods for producing such antifouling compounds and the use thereof in surface coatings.

BACKGROUND

- 10 **[0002]** Biofouling presents several issues for underwater structures and, thus, there is a general need to prevent and reduce biofouling on such structures. There are numerous antifouling approaches currently employed, including the use of specific coatings that deter biofouling, the use of toxins or biocides having antifouling activity as additives in coatings or paints for surfaces, and the use of mechanical cleaning of surfaces. The toxins or biocides can cause a physiological disruption or disturbance of the organism, or result in killing the organism. The toxic or biocidal effects may occur prior to, during or after adhesion of the organism, with the final outcome that the organism falls off the coated surface. A number of different substances are employed for this purpose depending on the organism to deter from fouling surfaces. Certain coatings present surfaces that physically deter organisms so that they cannot easily adhere to the surface. These types of coatings are generally hydrophobic, smooth, slippery and have low friction, such as elastomers, including silicone rubbers. Self-polishing coatings (SPCs) slowly degrade over time so that the attached organisms will be shed or fall off the coated surface. The degradation is often caused by a slow, controlled hydrolysis of a component in the coating, usually a binder component and dissolution of water soluble pigments.

[0003] There are both economic and environmental benefits of reducing biofouling on marine and freshwater installations. For example, biofouling reduces fuel efficiency for ships, reduces profitable operation time of ships during the biofouling cleaning procedures and decreases cooling power of cooling water equipment, to mention a few.

- 25 **[0004]** US 7,531,581 discloses a method and use of an antifouling paint that specifically and efficiently impede settlement of, for example, barnacles on aquatic structures, by the formation of an ionic pair between an imidazole containing compound, such as medetomidine, and a sulfonated, acid sulphate ester, phosphonic acid, carboxylic acid or acid phosphate ester modified polymer backbone, such as polystyrene or acrylate polymers.

- 30 **[0005]** US 10,239,898 discloses compounds based on adducts with isocyanates and a method for preparation thereof comprising reacting 3-isocyanatopropyltrimethoxysilane with medetomidine, compositions comprising these compounds and also use thereof as, or for producing, coatings.

- 35 **[0006]** CZ 30 799 discloses a hydrophobic antimicrobial polymer system consisting of a reactive polymer or a reactive polymerizable monomer with at least one covalently bound antimicrobial substance having acidic hydrogen atoms in its structure and at least one main hydrophobizing component. The main hydrophobizing component is 2,2,3,3-tetrafluoro-1-propanol or 2,2,3,3,4,4,5,5-octafluoro-1-pentanol, or a combination thereof. The hydrophobic antimicrobial polymer system comprises at least one excipient, which is a catalyst or a pH stabilizer.

- 40 **[0007]** EP 3 540 022 discloses an antifouling coating composition capable of forming an antifouling coating film that exhibits antifouling performance, has excellent slime resistance, and is prevented from cracking. The antifouling coating composition contains a polyorganosiloxane block-containing hydrolyzable copolymer (A) and medetomidine (B), wherein the polyorganosiloxane block-containing hydrolyzable copolymer (A) contains (i) a constituent unit derived from a hydrolyzable group-containing monomer (a1) and (ii) a constituent unit derived from a polyorganosiloxane block-containing monomer (a2).

- 45 **[0008]** EP 3 480 267 discloses an antifouling coating composition capable of forming an antifouling coating film that retains a high antifouling performance for a prolonged period of time and has an excellent damage resistance. Another object of the present invention is to provide an antifouling coating film formed with the antifouling coating composition, a substrate with an antifouling coating film and a method for producing the same, and an antifouling method using the antifouling coating film. The antifouling coating composition of the present invention contains a hydrolyzable polymer (A) containing a metal ester group, zinc oxide (B), and medetomidine (C), and has a content of the zinc oxide (B) in a solid content of the antifouling composition of 27 to 60% by mass.

- 50 **[0009]** EP 3 480 268 discloses an antifouling coating composition capable of forming an antifouling coating film that continuously has antifouling performance against aquatic organisms even in the case where the antifouling coating film is exposed to a high-speed water flow for a prolonged period of time. The antifouling coating composition contains a hydrolyzable polymer (A) containing a metal ester group, cuprous oxide (B), a copper pyrithione (C), and medetomidine (D).

- 55 **[0010]** EP 2 551 309 discloses antifouling coating composition capable of forming an antifouling coating film, which has stable coating film consumption degree and which exhibits antifouling property over a long term. The antifouling coating composition includes a hydrolyzable copolymer (A) and an antifouling agent (B), wherein the hydrolyzable copolymer (A) is a metal salt bond-containing copolymer having a component unit derived from a monomer (a21)

represented by the general formula: $\text{CH}_2=\text{C}(\text{R}_2)\text{-COO-M-O-CO-C}(\text{R}_2)=\text{CH}_2$, wherein M is zinc or copper, and R_2 is a hydrogen atom or a methyl group, and a component unit derived from other unsaturated monomer (a22) co-polymerizable with the monomer (a21), and wherein the antifouling agent (B) includes at least medetomidine.

[0011] There is, however, still a need for antifouling compounds that, in addition to antifouling capability, have desired and improved properties for usage in coatings and materials used on underwater or submersible installations and equipment.

SUMMARY

[0012] It is a general objective to provide antifouling polymers acting as polymeric carriers of antifouling agents, and monomers that can be polymerized into such antifouling polymers.

[0013] It is a particular objective to provide antifouling polymers and monomers that can be used in surface coatings in underwater or submersible installations and equipment.

[0014] These and other objectives are met by embodiments as disclosed herein.

[0015] The present invention is defined by the independent claims. Further embodiments of the invention are defined by the dependent claims.

[0016] An aspect of the invention relates to an antifouling polymer comprising a plurality of repeating units. At least a portion of the plurality of repeating units comprises medetomidine, or an enantiomer, base or salt thereof, covalently bound to the repeating unit through a hydrolysable bond.

[0017] A further aspect of the invention relates to a method of producing a medetomidine monomer. The method comprises reacting a polymerizable monomer comprising an electrophilic site with medetomidine, or an enantiomer, base or salt thereof, to covalently bind medetomidine, or the enantiomer, base or salt thereof, to the monomer through a hydrolysable bond formed between the electrophilic site and a nitrogen on the imidazole ring of medetomidine, or the enantiomer, base or salt thereof.

[0018] Yet another aspect of the invention relates to a method of producing an antifouling polymer. The method comprises polymerizing monomers comprising medetomidine, or an enantiomer, base or salt thereof, covalently bound to the monomer through a hydrolysable bond and optionally monomers lacking medetomidine, or an enantiomer, base or salt thereof, to form an antifouling polymer comprising a plurality of repeating units derived from monomers. At least a portion of the plurality of repeating units comprises medetomidine, or the enantiomer, base or salt thereof, covalently bound to the repeating unit through a hydrolysable bond.

[0019] A further aspect of the invention relates to a method of producing an antifouling polymer. The method comprises covalently binding medetomidine, or an enantiomer, base or salt thereof, to a polymer comprising a plurality of repeating units so that at least a portion of the plurality of repeating units comprises medetomidine, or the enantiomer, base or salt thereof, covalently bound to the repeating unit through a hydrolysable bond.

[0020] The antifouling compounds of the present invention, i.e., antifouling polymers and polymerizable monomers, have several advantages as compared to using free medetomidine in antifouling coatings. The antifouling compounds improve the lifetime of the antifouling coating by evenly distributing the antifouling agent, i.e., medetomidine, throughout the antifouling coating and control the release rate of medetomidine from the antifouling compounds in the antifouling coating. As a consequence, less medetomidine can be used in the antifouling coating as compared to antifouling coating comprising free medetomidine and still achieving corresponding antifouling effects. The antifouling compounds also enable formulation of antifouling coatings without the need for inorganic carriers, such as metal oxide particles, and thereby make it possible to formulate metal free coatings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0021] The embodiments, together with further objects and advantages thereof, may best be understood by making reference to the following description taken together with the accompanying drawings, in which:

Fig. 1 illustrates a reaction scheme for the production of 1-{4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazol-1-yl}-2-methylprop-2-en-1-one (**M1**), 4-[1-(2,3-dimethylphenyl)ethyl]-1-(prop-2-ene-1-sulfonyl)-1*H*-imidazole (**M2**) and 4-[1-(2,3-dimethylphenyl)ethyl]-1-(methanesulfonyl)-1*H*-imidazole (**M0**) according to an embodiment.

Fig. 2 illustrates a reaction scheme for the production of prop-2-en-1-yl 4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carboxylate (**M3**), 4-[1-(2,3-dimethylphenyl)ethyl]-*N*-(prop-2-en-1-yl)-1*H*-imidazole-1-carboxamide (**M4**) and 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate (**M5**) according to an embodiment.

Fig. 3 illustrates a reaction scheme for the production of 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbo-

nyl}amino)ethyl 2-methylprop-2-enoate (**M6**) and polystyrene medetomidine (**PSB**) according to an embodiment.

Fig. 4 illustrates structures of methyl methacrylate (MMA), ethylene glycol dimethacrylate (EGDMA) and azobisisobutyronitrile (AIBN) used to produce co-polymers according to various embodiments.

Fig. 5 is a diagram illustrating time dependent release of medetomidine from polystyrene medetomidine (**PSB**).

Fig. 6 illustrates the concentration of medetomidine (nM) in the incubation medium (0.05 M phosphate buffer pH 8.0 with 3% NaCl) plotted against incubation time for the three evaluated incubation temperatures: (A): +5°C, (B): room temperature (RT) and (C): +50°C.

Fig. 7 illustrates the amount of released medetomidine (pmol) plotted vs the incubation period from day 1 (24 h) until day 21 (504 h), considered as the constant period of compound release. The slopes were calculated and represent pmol released medetomidine per hour. (A): +5°C, (B): room temperature (RT) and (C): +50°C.

Fig. 8 schematically illustrates a medetomidine containing polymer and its hydrolysis to release free medetomidine. A: polymer, copolymer (binder or polymeric particle) with medetomidine covalently bound to the polymer; B: water soluble polymer; C: free medetomidine ready to act as antifoulant; D: In contact with water hydrolysis takes place and free medetomidine is released. The same process is making the polymer residue more water soluble, which in turn helps the surface to polish and refresh.

Fig. 9 shows epoxy control PMMA panels following 13 weeks of immersion.

Fig. 10 shows free medetomidine formulation PMMA panels 13 weeks of immersion.

Fig. 11 shows formulation # 2 PMMA panels 13 weeks of immersion.

Fig. 12 shows formulation # 3 PMMA panels 13 weeks of immersion.

Fig. 13 shows formulation # 4 PMMA panels 13 weeks of immersion.

Fig. 14 shows formulation # 5 PMMA panels 13 weeks of immersion.

Fig. 15 shows formulation # 6 PMMA panels 13 weeks of immersion.

DETAILED DESCRIPTION

[0022] The foregoing and other aspects of the embodiments will now be described in more detail with respect to the description and methodologies provided herein. It should be appreciated that the invention may be embodied in different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to one of ordinary skill in the art.

[0023] The one of ordinary skill in the art will understand that terminology used in the description herein is for the purpose of describing particular embodiments only and is not intended to be limiting of the invention. Unless otherwise defined, all terms, including technical and scientific terms used in the description, have the same meaning as commonly understood by one of ordinary skill in the art to which this invention belongs.

[0024] As used in the description of the embodiments, the singular forms "a," "an" and "the" are intended to include the plural forms as well, unless the context clearly indicates otherwise. Thus, such references may be replaced with a reference to "one or more", e.g., one, of the relevant component or integer. As used herein, all references to "one or more" of a particular component or integer will be understood to refer to from one to a plurality, e.g., two, three or four, of such components or integers. It will be understood that references to "one or more" of a particular component or integer will include a particular reference to one such integer. Also, as used herein, "and/or" refers to and encompasses any and all possible combinations of one or more of the associated listed items. Furthermore, the term "about," as used herein when referring to a measurable value, such as an amount of a compound, dose, time, temperature, and the like, refers to variations of 20 %, 10 %, 5 %, 1 %, 0.5 %, or even 0.1 % of the specified amount. When a range is employed, e.g., a range from x to y, it is meant that the measurable value is a range from about x to about y, or any range or value therein including x and y. It will be further understood that the terms "comprises" and/or "comprising," when used in this specification, specify the presence of stated features, integers, steps, operations, elements, components and/or


groups, but do not preclude the presence or addition of one or more other features, integers, steps, operations, elements, components, and/or groups thereof.

[0025] "Effective amount" as used herein refers to an amount of a compound, composition and/or formulation that is sufficient to produce a desired effect.

[0026] All patents, patent applications and publications referred to herein are incorporated by reference in their entirety. In the event of conflicting terminology, the present specification is controlling.

[0027] The present embodiments generally relate to antifouling compounds, methods for producing such antifouling compounds and the use thereof in surface coatings.

[0028] Medetomidine, also referred to as $(\pm)$ -4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole, see formula I, is a highly selective α 2-adrenoreceptor agonist. There are two tautomers of the imidazole group of medetomidine resulting in 4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole as shown in formula I or its tautomer 5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole.



(I)

[0029] Medetomidine is a highly efficient inhibitor of barnacles and impede larval settlement already at low concentrations, 1-10 nM. Medetomidine interacts with octopamine receptors in the barnacle cyprid larva, causing the legs of the larva to kick and thereby prevents the larva from settling onto medetomidine containing or releasing surface. Medetomidine has also shown effect on other hard fouling, such as tube worms.

[0030] Medetomidine is a racemic mixture of the two optical enantiomers, the levo- and dextro-rotary optical isomers (Journal of pharmacology and experimental therapeutics, 259: 848-854, 1991; European Journal of Pharmacology, 195: 193-199, 1991) with generic names levomedetomidine and dexmedetomidine, respectively. A process for the preparation of the racemic mixture of medetomidine and related intermediates is disclosed in WO 2011/070069. Many of the previous medetomidine syntheses used expensive 4-substituted imidazole derivatives as starting material. However, the synthesis presented in WO 2011/070069 is made from affordable commercially available starting materials, where the imidazole ring is instead formed during the synthesis. WO 2013/014428 describes a novel process of preparing medetomidine, including novel intermediates thereof, avoiding potentially disadvantageous use of imidazole derivatives as starting material. WO 2016/120635 relates to new processes for preparation of intermediates, such as 3-arylbutanals, useful in the synthesis of medetomidine.

[0031] The terms medetomidine, dexmedetomidine, and levomedetomidine as used herein include salts, bases and solvates thereof unless specifically stated otherwise. Acceptable salts of medetomidine, dexmedetomidine, and levomedetomidine include acid addition salts and base addition salts. Such salts may be formed by conventional means, for example by reaction of a free acid or a free base form of medetomidine, dexmedetomidine, and levomedetomidine with one or more equivalents of an appropriate acid or base, optionally in a solvent, or in a medium in which the salt is insoluble, followed by removal of the solvent, or the medium, using standard techniques, e.g., in vacuum or by freeze-drying. Salts may also be prepared by exchanging a counter-ion of medetomidine, dexmedetomidine, and levomedetomidine in the form of a salt with another counter-ion, for example using a suitable ion exchange resin. An illustrative, but non-limiting, example of a salt of medetomidine is medetomidine hydrochloride. For the avoidance of doubt, other acceptable derivatives of medetomidine, dexmedetomidine, and levomedetomidine are included within the scope of the invention, e.g., solvates, etc.

[0032] The enantiomers of medetomidine may be isolated and separated from each other by separation of racemic or other mixtures of the enantiomers using chiral resolution or chiral column chromatography known in the art. Alternatively the desired enantiomer may be prepared by enantio-selective synthesis, also called chiral synthesis or asymmetric synthesis, which is defined as a chemical reaction, or reaction sequence, in which one or more new elements of chirality are formed in a substrate molecule and which produces the stereoisomeric products in unequal amounts.

[0033] The base form of medetomidine is distributed by the company I-Tech AB under the product name SELEKTOPE®.

[0034] Medetomidine has been suggested to be used in free form, i.e., as free medetomidine molecules, in antifouling compositions thereby allowing medetomidine molecules to diffuse through an antifouling coating when coating a surface with the antifouling composition. This may cause the antifouling coating to be depleted of medetomidine too fast and

reduce the lifetime of the antifouling coating. Hence, medetomidine attached to carriers have been suggested to reduce this risk and help to control the leaching rate. So far, carriers in the form of metal oxide particles, in particular zinc oxide (ZnO) or copper(I) oxide (Cu₂O) or copper (II) oxide (CuO) particles, have been used in antifouling composition (US 2006/0201379). Such metal oxide particles, however, limit the applications of the antifouling compositions since there

may be a desire to have zinc or copper free antifouling compositions.

[0035] The present invention is based on using polymerizable monomers as carrier for medetomidine and where these polymerizable monomers can be further polymerized into polymers acting as polymeric carriers of the antifouling agent medetomidine. Such medetomidine monomers and polymers solve the problem of free medetomidine leaking too fast from antifouling coatings and thereby improve the lifetime of the antifouling coatings. Furthermore, this improved control of the leaching rate of medetomidine is achieved without the need for using metal oxide particles.

[0036] In some antifouling compositions, it may not be possible to add medetomidine directly due to incompatibility issues. For instance, a solvent for medetomidine may not be compatible with other ingredients of the antifouling composition and/or any metal oxide particles used as medetomidine carriers may limit the usage of additional ingredients due to incompatible issues. A related issue is that some binder systems used in antifouling compositions are sensitive to the addition of additives, including organic biocides, such as free medetomidine, which may trigger gelation of the antifouling composition. This problem may be eliminated or at least reduced by attaching medetomidine to a monomer or polymer carrier according to the invention.

[0037] In the following, various aspects and embodiments of the present invention are described in further detail with reference to medetomidine. These aspects and embodiments also encompass an enantiomer of medetomidine, such as dexmedetomidine or levomedetomidine, a salt of medetomidine, a salt of dexmedetomidine, or a salt of levomedetomidine, or a base of medetomidine, a base of dexmedetomidine, or a base of levomedetomidine collectively denoted medetomidine, or an enantiomer, base or salt thereof herein. Thus, reference to medetomidine herein should be regarded as relating to medetomidine, a salt of medetomidine, a base of medetomidine, dexmedetomidine, a salt of dexmedetomidine, a base of dexmedetomidine, levomedetomidine, a salt of levomedetomidine, and/or a base of levomedetomidine unless indicated otherwise.

[0038] An aspect of the invention relates to an antifouling polymer comprising a plurality of repeating units. According to the invention, at least a portion of the plurality of repeating units comprises medetomidine, or an enantiomer, base or salt thereof, covalently bound to the repeating unit through a hydrolysable bond.

[0039] The antifouling polymer of the invention comprises a plurality of monomers, also referred to as repeating unit or repeat unit in the art, of which at least a portion thereof is carriers of medetomidine, i.e., comprises medetomidine attached to the repeating unit through a hydrolysable covalent bond. The antifouling polymer therefore comprises a plurality of repeating units derived from monomers. The covalent bond between medetomidine and at least a portion of the repeating units in the antifouling polymer means that these repeating units and thereby the antifouling polymer act or acts a carrier of medetomidine. The covalent bond is, however, hydrolysable. This means medetomidine can be released from the repeating units in the antifouling polymer through hydrolysis when in contact with water, see Fig. 8. Such a hydrolysis of the covalent bond enables a controlled release and leaching of free medetomidine from an antifouling coating made from and comprising the antifouling polymer of the invention.

[0040] An additional advantage of covalently bonding medetomidine to monomers or repeating units derived from such monomers through a hydrolysable bond is that the antifouling polymer becomes more hydrophilic and water soluble as medetomidine is hydrolyzed from its repeating units. A surface of an antifouling coating comprising the antifouling polymers will thereby become polished and refreshed due to the hydrolysis. Hence, such polishing and refreshing action caused by the hydrolysis of the covalent bond between medetomidine and repeating units in the antifouling polymer will even further contribute to the antifouling capability of the antifouling coating comprising the antifouling polymers of the present invention.

[0041] The antifouling polymer of the present invention could be a homopolymer, i.e., a polymer containing only a single type of repeating units, i.e., monomers, comprising medetomidine. Hence, in such an embodiment, the antifouling polymer is a homopolymer of repeating units comprising medetomidine, or the enantiomer, base or salt thereof.

[0042] Illustrative, but non-limiting, examples of such homopolymer are homopolymers made of repeating units or monomers selected from the group consisting of a medetomidine methacrylate, such as 1-{4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazol-1-yl}-2-methylprop-2-en-1-one (**M1**) or 1-{5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazol-1-yl}-2-methylprop-2-en-1-one, 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl 2-methylprop-2-enoate (**M6**) or 2-({5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl 2-methylprop-2-enoate; an allylsulfonyl medetomidine, such as 4-[1-(2,3-dimethylphenyl)ethyl]-1-(prop-2-ene-1-sulfonyl)-1*H*-imidazole (**M2**) or 5-[1-(2,3-dimethylphenyl)ethyl]-1-(prop-2-ene-1-sulfonyl)-1*H*-imidazole; an allyl medetomidine, such as prop-2-en-1-yl 4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carboxylate (**M3**) or prop-2-en-1-yl 5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carboxylate, 4-[1-(2,3-dimethylphenyl)ethyl]-*N*-(prop-2-en-1-yl)-1*H*-imidazole-1-carboxamide (**M4**) or 5-[1-(2,3-dimethylphenyl)ethyl]-*N*-(prop-2-en-1-yl)-1*H*-imidazole-1-carboxamide; a medetomidine acrylate, such as 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate (**M5**) or 2-({5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate.

phenyl)ethyl]-1*H*-imidazole-1-carbonyl)amino)ethyl prop-2-enoate; and a silyl medetomidine, such as 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl)amino)ethyl prop-2-enoate (**M10**) or 2-({5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl)amino)ethyl prop-2-enoate, 3-(4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-dimethylsilyl)propyl 2-methylprop-2-enoate (**M11**) or 3-(5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-dimethylsilyl)propyl 2-methylprop-2-enoate.

[0043] In an embodiment, the homopolymer is selected from the group consisting of a poly(medetomidine methacrylate), a poly(allylsulfonyl medetomidine), a poly(allyl medetomidine), a poly(medetomidine acrylate) and a poly(silyl medetomidine).

[0044] The present invention is, however, not limited to antifouling polymers in the form of homopolymers. Hence, the antifouling polymer may alternatively be in the form of a co-polymer, i.e., a polymer containing two or more types of repeating units, i.e., monomers. Hence, in an embodiment, the antifouling polymer is a co-polymer comprising a first type of repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, and the first type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof. Hence, in this co-polymer the same type of repeating unit is used in the polymerization to form the antifouling polymer. However, some of these repeating units comprise medetomidine, or the enantiomer, base or salt thereof, covalently bound to the repeating unit through a hydrolysable bond whereas remaining repeating units in the co-polymer do not comprise any medetomidine.

[0045] Alternatively, the antifouling polymer could be a co-polymer of different types of repeating units. In an embodiment, the antifouling polymer is a co-polymer comprising a first type of repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, a second, different type of repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, and optionally the first type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof, and/or optionally the second, different type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof. In this embodiment, both first and second repeating units comprise medetomidine covalently bound thereto using a hydrolysable bond. In another embodiment, the antifouling polymer is a co-polymer comprising a first type of repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, a second, different type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof, and optionally the first type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof. In this embodiment, medetomidine is only covalently bound to first type of repeating units, whereas the second type of repeating units does not comprise any covalently attached medetomidine.

[0046] The invention also encompasses a co-polymer comprising more than two types of repeating units. In such an embodiment, all of the different types of repeating units may comprise medetomidine covalently attached thereto through a hydrolysable bond or only one or a portion of the different types of repeating units is used as medetomidine carrier.

[0047] Illustrative, but non-limiting, examples of monomers or repeating units lacking medetomidine covalently attached thereto can be selected among the above described monomers or repeating units and may, also include, methyl methacrylate (MMA), methylacrylate, butyl methacrylate (BMA), butyl acrylate, 2-methoxyethyl acrylate (MEA), tri-isopropylsilyl methacrylate, and/or tri-isopropylsilyl acrylate (TIPSA).

[0048] Illustrative, but non-limiting, examples of co-polymers include a co-polymer between any of monomer **M0** to **M11** and at least one other monomer lacking medetomidine as mentioned above, i.e., MMA, BMA, butyl acrylate, MEA, tri-isopropylsilyl methacrylate, and/or TIPSA. As illustrative examples, the co-polymer could be a co-polymer between **M6** and MMA, such as co-polymer CP6R1 or CP6R2 as disclosed herein; a co-polymer between **M5** and MMA, such as co-polymer CP5R1 as disclosed herein, a co-polymer between **M6**, MMA and TIPSA, a co-polymer between **M5**, MMA and TIPSA, a co-polymer between **M6**, MMA, TIPSA and MEA; a co-polymer between **M6**, MMA, TIPSA and BMA; a co-polymer between **M5**, MMA, TIPSA and MEA; or a co-polymer between **M5**, MMA, TIPSA and BMA.


[0049] A polymerizable monomer comprises medetomidine, or an enantiomer, base or salt thereof, covalently bound to the polymerizable monomer through a hydrolysable bond.

[0050] In an embodiment, medetomidine, or the enantiomer, base or salt thereof, is covalently bound to the monomer through the hydrolysable bond between a nitrogen on the imidazole ring of medetomidine, or the enantiomer, base or salt thereof, and the monomer.


[0051] The imidazole ring of medetomidine comprises two nitrogen atoms at position 1 and 3, of which the nitrogen with an attached hydrogen is at position 1. In an embodiment, medetomidine, or the enantiomer, base or salt thereof, is covalently bound to the monomer through the hydrolysable bond between a nitrogen at position 1 on the imidazole ring of medetomidine, or the enantiomer, base or salt thereof, and the monomer.

[0052] In a particular embodiment, medetomidine, or the enantiomer, base or salt thereof, is covalently bound to the monomer through the hydrolysable bond between a nitrogen on the imidazole ring of medetomidine, or the enantiomer, base or salt thereof, and a carbon, silicon or sulfur on the monomer. Hence, in this particular embodiment, the hydrolysable bond is an N-C, N-Si or a N-S bond.

[0053] In an embodiment, the monomer comprising medetomidine, or the enantiomer, base or salt thereof, has a general formula II or III:




(II)




(III)


[0054] In an embodiment, R¹ is selected from the group consisting of carbonyl, sulphonyl, and dimethylsilyl. Hence, in a particular embodiment R¹ is selected from the group consisting of formula IV to VI:



(IV)




(V)




(VI)

[0055] In an embodiment, R² is selected from the group consisting of oxygen and amine. Hence, in a particular embodiment R² is selected from the group consisting of formula VII and VIII:




(VII)




(VIII)

[0056] In an embodiment, n is 0 or 1.


[0057] In an embodiment, R^3 is selected from the group consisting of formula IX to XIV:




(IX)




(X)




(XI)



(XII)



(XIII)



(XIV)

[0058] In an embodiment, R is independently H or alkyl, preferably a C1 to C6 alkyl, and more preferably a C1 to C4 alkyl. In a particular embodiment, R is independently H, methyl or ethyl, preferably H or methyl. In an embodiment, R⁴, R⁵ and R⁶ are independently alkoxy, preferably a C1 to C6 alkoxy, and more preferably a C1 to C4 alkoxy. In a particular embodiment, R⁴, R⁵ and R⁶ are independently methoxy, ethoxy or propoxy. In an embodiment, m is 0, 1, 2 or 3

[0059] In an embodiment, the monomer comprising medetomidine, or the enantiomer, base or salt thereof, is selected from the group consisting of a medetomidine methacrylate, such as 1-{4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazol-1-yl}-2-methylprop-2-en-1-one (**M1**) or 1-{5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazol-1-yl}-2-methylprop-2-en-1-one, 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl 2-methylprop-2-enoate (**M6**) or 2-({5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl 2-methylprop-2-enoate; an allylsulfonyl medetomidine, such as 4-[1-(2,3-dimethylphenyl)ethyl]-1-(prop-2-ene-1-sulfonyl)-1*H*-imidazole (**M2**) or 5-[1-(2,3-dimethylphenyl)ethyl]-1-(prop-2-ene-1-sulfonyl)-1*H*-imidazole; an allyl medetomidine, such as prop-2-en-1-yl 4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carboxylate (**M3**) or prop-2-en-1-yl 5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carboxylate, 4-[1-(2,3-dimethylphenyl)ethyl]-*N*-(prop-2-en-1-yl)-1*H*-imidazole-1-carboxamide (**M4**) or 5-[1-(2,3-dimethylphenyl)ethyl]-*N*-(prop-2-en-1-yl)-1*H*-imidazole-1-carboxamide; a medetomidine acrylate, such as 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate (**M5**) or 2-({5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate; and a silyl medetomidine, such as 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate (**M10**) or 2-({5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate, 3-(4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-dimethylsilyl)propyl 2-methylprop-2-enoate (**M11**) or 3-(5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-dimethylsilyl)propyl 2-methylprop-2-enoate.

[0060] The present invention also relates to an antifouling composition comprising a polymer according to the embodiments and/or a monomer according to the embodiments and a solvent.

[0061] In an embodiment, the antifouling composition comprises the antifouling polymer comprising a plurality of repeating units, of which at least a portion comprises medetomidine, or the enantiomer, base or salt thereof, covalently bound to the repeating unit through a hydrolysable bond and the solvent.

[0062] In another embodiment, the antifouling composition may comprise, in addition to the antifouling polymer and the solvent, also monomers of which at least a portion thereof comprises medetomidine, or the enantiomer, base or salt thereof, covalently bound to the monomer through a hydrolysable bond. Hence, in this embodiment, the antifouling composition also comprises non-polymerized monomers that may carry medetomidine.

[0063] In an embodiment, the antifouling composition may also comprise free medetomidine, or the enantiomer, base or salt thereof, not covalently bound to any monomer or repeating unit.

[0064] In an embodiment, the solvent is selected from the group consisting of xylene, toluene, 1-methoxy-2-propanol, 1-methoxy-2-propanoyl acetate, methyl isobutyl ketone, solvent naphtha and a mixture thereof.

[0065] The antifouling composition may optionally comprise other ingredients including, but not limited to, one or more pigments, such as Cu₂O, ZnO, TiO₂ and/or an iron oxide (Fe_xO_y), one or more fillers or extenders, such as talc, CaCO₃, BaSO₄ and/or mica (phyllosilicates), one or more rheology modifiers, such as fumed silica, silica and/or clay, and/or one or more biocides.

[0066] In an embodiment, at least one other biocide other than medetomidine is included in the antifouling composition. This at least one other biocide could be an antifouling agent, an algicide, a fungicide, a herbicide or a combination thereof.

[0067] Non-limiting, but illustrative examples of such biocides other than medetomidine that can be used according to the embodiments are listed in WO 2012/175469 on page 11, line 16 to page 12, line 10 and in WO 2013/182641 on page 10, line 22 to page 13, line 2, the teaching of which is hereby incorporated by reference with regard to biocides that can be used according to the embodiments.

[0068] Other non-limiting biocides that can be used according to the embodiments include, but are not limited to, chlorothalonil (2,4,5,6-tetrachlorobenzene-1,3-dicarbonitrile), dichlofluanid (N-{[dichloro(fluoro)methyl]sulfanyl}-N',N'-dimethyl-N-phenylsulfuric diamide), DCOIT (4,5-dichloro-2-n-octyl-4-isothiazolin-3-one), cybutryne (2-N-tert-butyl-4-N-cyclopropyl-6-methylsulfanyl-1,3,5-triazine-2,4-diamine), DCMU (3-(3,4-dichlorophenyl)-1,1-dimethylurea), tolylfluanid (N-[dichloro(fluoro)methyl]sulfanyl-N-(dimethylsulfamoyl)-4-methylaniline), zinc pyriothione (bis(2-pyridylthio)zinc 1,1'-dioxide), copper pyriothione (bis(2-pyridylthio)copper 1,1'-dioxide), cybutryne (2-N-tert-butyl-4-N-cyclopropyl-6-methylsulfanyl-1,3,5-triazine-2,4-diamine), zinc ethane-1,2-diylbis(dithiocarbamate), zinc bis(dimethylthiocarbamates), manganese ethylene-1,2-bis(dithiocarbamate) polymer, 4-bromo-2-(4-chlorophenyl)-5-(trifluoromethyl)-1*H*-pyrrole-3-carbonitrile (tralopyril), and a mixture thereof.

[0069] Medetomidine has specific actions against hard fouling, in particular barnacle cyprids, but typically no effect on algal growth. Accordingly, at least one other biocide, such as an algicide, could be used to prevent algal growth as well.

[0070] The antifouling composition, polymer and monomers according to the invention can be included in a surface coating, such as an antifouling coating, an antifouling film or an antifouling paint, of an article, such as an underwater or submersible device or structure. The antifouling composition could then be regarded as an antifouling coating composition or formulation, an antifouling film composition or formulation, or an antifouling paint composition or formulation. Hence, the article comprises a surface coating with a polymer according to the invention, a monomer according to the invention

and/or an antifouling composition according to the invention on at least a portion of a surface of the article designed or configured to be submersed in water to inhibit marine biofouling of the surface.

[0071] For instance, the antifouling composition or polymer could be applied as a coating, film or paint on the underwater or submersible device or structure, such as in the form of a spray coating, film or paint.

[0072] The article could be a propeller tunnel, a guide vane, a fender, mooring equipment, underwater rope, underwater wire, underwater net, ship or boat hull etc. as illustrative but non-limiting examples.

[0073] When the surface coating of the article is submersed and come in contact with water the covalent bond between medetomidine and repeating units in the polymer and/or between medetomidine and free monomer units in the surface coating is hydrolyzed to thereby release medetomidine from the surface coating, see Fig. 8. The free medetomidine can then act as an antifouling agent and inhibit marine biofouling on the submersed surface of the article.

[0074] The release rate of medetomidine can be controlled in various ways including the concentration of the antifouling polymer in the surface coating. A higher concentration of the antifouling polymer generally leads to a higher release rate of medetomidine and a prolonged medetomidine release. Furthermore, the proportion of medetomidine carrying repeating units in the antifouling polymer affects the release rate of medetomidine from the surface coating. Hence, a higher percentage of medetomidine carrying repeating units in the antifouling polymer generally leads to a higher release rate of medetomidine and a prolonged medetomidine release. Furthermore, by using different types of medetomidine carrying repeating units in the antifouling polymer, the release rate of medetomidine from the surface coating can be controlled and tailored to meet a target release rate. In addition, the release of medetomidine from the antifouling polymer depends on the hydrophilicity or hydrophobicity of the antifouling polymer and of a paint film comprising the antifouling polymer.

[0075] A free medetomidine molecule will diffuse freely through a surface coating interacting with other coating constituents depending on the formula. This may cause the surface coating to be depleted of medetomidine too fast and reduce the antifouling lifetime of the surface coating. Attaching medetomidine to a polymeric or monomeric carrier will reduce this risk and, in addition, enables control of the release or leaching rate. Furthermore, covalently attaching medetomidine to repeating units in the antifouling polymer will more evenly disperse medetomidine in the antifouling composition during the formulation phase.

[0076] In certain antifouling compositions, it may not be possible to add medetomidine directly due to incompatibility. For instance, a solvent for medetomidine may not be compatible with at least some of the other ingredients in the antifouling composition.

[0077] Furthermore, by attaching medetomidine to repeating units in a polymer, the polymer can act as a carrier of the antifouling agent. The polymer can then either be used as the binder, such as alone or in combination with other polymers, in the antifouling composition or as a carrier particle immobilizing medetomidine in the surface coating until needed. Furthermore, when the surface coating is in contact with water, the water will penetrate into the surface coating and trigger hydrolysis to release medetomidine. At the same time, the polymers are made more water soluble, which in turn polishes and refreshes the surface coating.

[0078] The antifouling polymers of the invention can act as metal free carriers of medetomidine thereby preventing the release of zinc and copper to water as compared to previously used metal oxide based carriers. Hence, the antifouling composition of the invention can be in the form of a zinc and copper free composition.

[0079] Attaching medetomidine to repeating units of an antifouling polymer furthermore inhibits the problems associated of certain binder systems, such as silyl acrylates, being sensitive to free medetomidine molecules causing undesired gelation.

[0080] A further aspect of the invention relates to a method of producing a medetomidine monomer. The method comprises reacting a polymerizable monomer comprising an electrophilic site with medetomidine, or an enantiomer, base or salt thereof, to covalently bind medetomidine, or the enantiomer, base or salt thereof, to the monomer through a hydrolysable bond formed between the electrophilic site and a nitrogen on the imidazole ring of medetomidine, or the enantiomer, base or salt thereof.

[0081] In an embodiment, the method further comprises dissolving medetomidine, or the enantiomer, base or salt thereof, in a solvent to form a medetomidine solution and adding the polymerizable monomer to the medetomidine solution.

[0082] In a particular embodiment, medetomidine, or the enantiomer, base or salt thereof, and diisopropylethylamine are dissolved in dichloromethane to form the medetomidine solution. In this particular embodiment, allyl chloroformate is added as polymerizable monomer to the medetomidine solution.

[0083] In another particular embodiment, medetomidine, or the enantiomer, base or salt thereof, and optionally pyridine are dissolved in dichloromethane to form the medetomidine solution. In this particular embodiment, allyl isocyanate is added as polymerizable monomer to the medetomidine solution.

[0084] In a further particular embodiment, medetomidine, or the enantiomer, base or salt thereof, and trimethylamine are dissolved in dichloromethane to form the medetomidine solution. In this particular embodiment, 2-propenylsulfonyl chloride is added as polymerizable monomer to the medetomidine solution.

[0085] In another particular embodiment, medetomidine, or the enantiomer, base or salt thereof, and *N,N*-dimethyl-

4-aminopyridine are dissolved in dichloromethane to form the medetomidine solution. In this particular embodiment, methacrylic anhydride or methacryloyl chloride is added as polymerizable monomer to the medetomidine solution.

[0086] In a further particular embodiment, medetomidine, or the enantiomer, base or salt thereof, is dissolved in dichloromethane to form the medetomidine solution. In an optional embodiment, pyridine may be added as catalyst to the medetomidine solution. In this particular embodiment, isocyantoethyl methacrylate is added as polymerizable monomer to the medetomidine solution.

[0087] In yet another particular embodiment, medetomidine, or the enantiomer, base or salt thereof, is dissolved in dichloromethane to form the medetomidine solution. In an optional embodiment, pyridine may be added as catalyst to the medetomidine solution. In this particular embodiment, isocyantoethyl acrylate is added as polymerizable monomer to the medetomidine solution.

[0088] In the above described particular, any of dichloromethane, pyridine and xylene, if any, could be used as solvent.

[0089] Yet another aspect of the invention relates to a method of producing an antifouling polymer. The method comprises polymerizing monomers comprising medetomidine, or an enantiomer, base or salt thereof, covalently bound to the monomer through a hydrolysable bond and optionally monomers lacking medetomidine, or an enantiomer, base or salt thereof, to form an antifouling polymer comprising a plurality of repeating units derived from monomers, wherein at least a portion of the plurality of repeating units comprises medetomidine, or the enantiomer, base or salt thereof, covalently bound to the repeating unit through a hydrolysable bond.

[0090] A further aspect of the invention relates to a method of producing an antifouling polymer. The method comprises covalently binding medetomidine, or an enantiomer, base or salt thereof, to a polymer comprising a plurality of repeating units so that at least a portion of the plurality of repeating units comprises medetomidine, or the enantiomer, base or salt thereof, covalently bound to the repeating unit through a hydrolysable bond.

EXAMPLES

EXAMPLE 1

[0091] A set of monomers were designed based on couplings of a polymerizable part to the imidazole of medetomidine. The hydrolysable connection between the medetomidine and the polymerizable part of the molecule is made up from one of following bonds/functional groups: amide bonds, sulfonamide, urea or carbamate. In the beginning pyridine, DMAP and/or Et₃N was used as catalyst in the reactions but it was discovered that a catalyst was often not needed.

Preparation of 1-{4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazol-1-yl}-2-methylprop-2-en-1-one (M1)

[0092] Compound **M1** was prepared from acylation of the imidazole and a range of acylating agents and reaction were investigated. Both methacrylic anhydride and methacryloyl chloride afforded **M1** as shown in Fig. 1.

[0093] Methacrylic anhydride or methacryloyl chloride (1.12 mL, 7.5 mmol, 1.5 equiv.) was added dropwise to a solution of medetomidine (**I**) (1 g, 5.0 mmol, 1.0 equiv.) and *N,N*-dimethyl-4-aminopyridine (DMAP; 0.061 g, 0.5 mmol, 10 mol %) in anhydrous dichloromethane (DCM; 10 mL) and the reaction mixture was stirred at room temperature for 24 h. The resulting mixture was washed twice with saturated sodium bicarbonate and then subjected to flash column chromatography on silica gel using petroleum ether:acetone (8:2) as eluent to afford the acylated medetomidine **M1** as a colorless liquid. ¹H NMR (500 MHz, Chloroform-*d*): δ 8.00 (d, *J* = 1.4 Hz, 1H), 7.27 (s, 1H), 7.13 - 7.10 (m, 1H), 7.10 - 7.02 (m, 3H), 5.83 (d, *J* = 1.6 Hz, 1H), 5.64 (d, *J* = 1.4 Hz, 1H), 4.39 (q, *J* = 8.1, 7.2 Hz, 1H), 2.30 (s, 3H), 2.27 (s, 3H), 2.11 (s, 3H), 1.60 (d, *J* = 7.1 Hz, 3H). ¹³C NMR (126 MHz, Chloroform-*d*): δ 166.75, 149.61, 142.24, 138.37, 137.49, 136.90, 134.20, 128.15, 125.58, 125.38, 124.37, 113.07, 35.12, 21.06, 20.42, 19.47, 14.96. The yield with metacryloyl chloride was 69 %, whereas the yield using methacrylic anhydride was lower.

[0094] The syntheses as shown in Fig. 1 were also repeated using *N,N'*-dicyclohexylcarbodiimide (DCC) as coupling reagent instead of DMAP resulting in substantially the same yield of **M1**.

Preparation of 4-[1-(2,3-dimethylphenyl)ethyl]-1-(prop-2-ene-1-sulfonyl)-1*H*-imidazole (M2)

[0095] Medetomidine (200 mg, 1 mmol) and triethylamine (202 mg, 2 mmol) were dissolved in dichloromethane (10 ml) at -78°C. After 30 min at -78°C, 2-propenylsulfonyl chloride was added and the reaction was stirred 4 hours at -78°C. Hydrogen chloride (1 M) and diethyl ether were added. The organic layer was dried (Na₂SO₄), filtered through celite and solvent was evaporated. Crude amount 259 mg. NMR showed presence of two regioisomers and other impurities. This indicates production of two polymerizable monomers comprising medetomidine bound to the propenylsulfonyl via either of the two imidazole nitrogens. Fig. 1 illustrates the reaction scheme for producing one of the present polymerizable monomers comprising medetomidine.

Preparation of prop-2-en-1-yl 4-[1-(2,3-dimethylphenyl)ethyl]-1H-imidazole-1-carboxylate (M3)

[0096] Medetomidine (200 mg, 1 mmol) and diisopropylethylamine (194 mg, 1.5 mmol) were dissolved in dichloromethane (10 ml) at -78°C. Allyl chloroformate was added and the solution was stirred 3 h at -78°C. Water and diethylether were added. The organic layer was dried (Na₂SO₄), filtered through celite and solvent was evaporated. Crude amount 240 mg, yield 85 %. ¹H-NMR (CDCl₃): 1.59 (d, 3H), 2.25 (s, 3H), 2.30 (s, 3H), 4.37 (q, 1H), 4.84 (d, 2H), 5.36 (dd, 1H), 5.43 (dd, 1H), 5.99 (m, 1H), 6.99 (d, 1H), 7.02-7.09 (b, 3H), 8.08 (d, 1H). Fig. 2 illustrates the reaction scheme for producing the present polymerizable monomer comprising medetomidine.

Preparation of 4-[1-(2,3-dimethylphenyl)ethyl]-N-(prop-2-en-1-yl)-1H-imidazole-1-carboxamide (M4) - synthesis I

[0097] Medetomidine (200 mg, 1 mmol) and allyl isocyanate (88 ml, 1 mmol) were added to dichloromethane at room temperature (20-25°C). The reaction was stirred 3 hours. Water and diethylether were added. The organic layer was dried (Na₂SO₄), filtered through celite and solvent was evaporated. Crude amount 280 mg, yield 99 %. ¹H-NMR (CDCl₃): 1.50 (d, 3H), 2.14 (s, 3H), 2.25 (s, 3H), 3.75 (m, 2H), 4.26 (q, 1H), 5.08 (d, 1H), 5.14 (d, 1H), 5.75 (m, 1H), 6.89-7.01 (m, 3H), 7.14 (b, 1H), 8.05 (b, 1H). Fig. 2 illustrates the reaction scheme for producing the present polymerizable monomer comprising medetomidine.

Preparation of 4-[1-(2,3-dimethylphenyl)ethyl]-N-(prop-2-en-1-yl)-1H-imidazole-1-carboxamide (M4) - synthesis II

[0098] Allyl medetomidine **M4** was prepared from **I** and allyl isocyanate according to the reaction scheme illustrated in Fig. 2.

[0099] Allyl isocyanate (1.91 mL, 21.6 mmol, 2.94 equiv.) was added in three portions to a solution of **I** (1.47 g, 7.36 mmol, 1.0 equiv.) and pyridine (1.8 mL, 22.3 mmol, 3.04 equiv.) in anhydrous dichloromethane (7.5 mL). The reaction mixture was stirred at room temperature for 24 h. The solvent was removed by rotary evaporation at reduced pressure. The crude was re-dissolved in toluene and the solvent was once more removed at reduced pressure. The crude was dissolved in ethyl acetate and subjected to flash column chromatography on silica gel using ethyl acetate/heptane (1:1) to ethyl acetate as eluent to afford pure (determined via LC-MS and TLC analysis) allyl medetomidine **M4**. Following solvent removal, the purified **M4** was dissolved in acetonitrile/H₂O (1:1) and lyophilized to yield 1.96 g (94%) of pure crystalline **M4**.

Preparation of 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1H-imidazole-1-carbonyl}amino)ethyl prop-2-enoate (M5) and 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1H-imidazole-1-carbonyl}amino)ethyl 2-methylprop-2-enoate (M6)

[0100] Several reactions/preparations were done and they will be referred to with a R followed by a number as indicator following the corresponding monomer M5 or M6. In an initial synthesis, pyridine was used as a catalyst to aid in the conjugation reaction of an isocyanate with medetomidine. Isocyanatoethyl methacrylate (IEM) or isocyanatoethyl acrylate (IEA) was combined with medetomidine at 5 % molar excess, see Figs. 2 and 3. In the initial synthesis, pyridine was added at threefold the molar quantity of medetomidine. In subsequent syntheses, pyridine was reduced to an equimolar ratio with medetomidine or eliminated. This reduction or elimination of pyridine simplifies subsequent purification.

[0101] Table 1 provides a summary of molar ratios and reaction times for the various syntheses.

Table 1 - Summary of molar ratios and reaction times

	Medetomidine	Pyridine	IEM or IEA*	DCM (g : mL)	Reaction time (h)
M6R1	1	3	1.05	5	4.5
M6R2	1	3	1.05	5	4.5
M6R3	1	0	1.05	5	72
M6R4	1	3	1.05	5	4.5
M6R5	1	1	1.05	5	24
M6R6	1	0	1.05	5	44
M5R1	1	0	1.05	6	24
*IEM was used as isocyanate in M6R1-M6R6 and IEA was used as isocyanate in M5R1					

Synthesis protocol for M6R1, M6R2 and M6R4

[0102] A 100 mL 3-necked round bottom flask was immersed in a temperature regulated oil bath. On its leftmost neck, nitrogen gas was flown in. In its middle neck, a glass stopper was placed where it could be removed and replaced in order to take samples of the reaction at different times. On its rightmost neck, a condenser with cold running water as coolant was placed to prevent runoff of the dichloromethane (DCM) solvent.

[0103] Medetomidine (M6R1: 5.0781 g; M6R2: 5.3057 g; M6R4: 5.03225 g) was first dissolved in 25 mL DCM. 6.03 mL pyridine, acting as catalyst, was then introduced into the medetomidine solution. 3.71 mL IEM was next added dropwise, with an exothermic reaction being noticeable from the increase in the thermocouple sensor going above the set temperature. The reaction was run for 4.5 h as the isocyanate peak has been found to be greatly reduced from a Fourier-transform infrared spectroscopy (FTIR) reading at 4 h.

Purification

[0104] In the second preparation of **M4** above, the medetomidine conjugated allyl isocyanate was purified by dissolving the crude mixture in toluene and co-evaporating the pyridine from the mixture in a rotary evaporator in room temperature. This procedure was followed for M6R1, M6R2, M6R4.

[0105] The next step was to use a flash chromatography column to separate the unreacted medetomidine and isocyanate from the adduct. The original protocol used a gradient of ethyl acetate and heptane, first dissolving the product in a 50:50 blend. M6R1 immediately precipitated and formed a solid chunk where it was previously a sticky liquid mixture with some toluene. M6R2 and M6R4 were stored without flash chromatography purification.

[0106] M6R2 and M6R4 were stored and used in chemical characterization and release studies without further purification to prevent unwanted precipitation/crosslinking of unreacted isocyanate chains.

M6R5 synthesis

[0107] Medetomidine (5.03830 g) was added in 25 mL DCM for dissolution in a 100 mL 3-neck round bottom flask. Pyridine (2.01 mL) was added. The starting temperature in the oil bath was 31.7°C. IEM (3.71 mL) was added by 200 µL stages. The synthesis was run for 24 hours. The following day, the reaction mixture was used directly for CP6R1 polymerization.

M6R3 and M6R6 synthesis

[0108] From HPLC analysis of M6R4, the reaction was determined to have a 90±2% efficiency. In order to reduce time spent on the removal of pyridine, synthesis of M6R3, M6R6, and M10R1 were attempted without pyridine.

[0109] Medetomidine (M6R3: 1.0013 g; M6R6: 4.02450 g) was first dissolved in the DCM solvent (M6R3: 5 mL; M6R6: 20.53 mL) within the reaction flask. IEM was then added dropwise and the flask was sealed. Samples were taken at different time intervals to monitor the extent of reaction. The synthesis was run for much longer (see Table 6) in order to allow sufficient time for the addition reaction to take place.

M5R1 synthesis

[0110] Medetomidine (5.03104 g) was added in 30 mL DCM for dissolution in a 100 mL 3-neck round bottom flask. The starting temperature in the oil bath was 31.7°C. IEA (3.36 mL) was added by 200 µL stages.

[0111] M5R1 was precipitated in heptane. Previous observations of M6 showed that keeping the monomer in room temperature to thaw for use renders it insoluble to acetone and solvents, in which it was previously soluble. However this was not the case with M5R1. The monomer/heptane slurry was placed in a fume hood to evaporate out the remaining organic solvent for two days. Acetone was added to resolubilize and the M5R1 monomer was successfully re-dissolved.

Preparation of 4-[1-(2,3-dimethylphenyl)ethyl]-1-(methanesulfonyl)-1H-imidazole (M0)

[0112] Medetomidine (200 mg, 1 mmol) and triethylamine (152 mg, 1.5 mmol) were added to dichloromethane (10 mL) at -78°C. After 30 min methane sulfonyl chloride was added at -78°C. The reaction mixture was stirred 3 hours at -78°C. Diethyl ether and water were added. The organic layer was dried (Na₂SO₄), filtered through celite and solvent was evaporated. Amount 270 mg, yield 97 %. NMR showed two regioisomers in a ratio of 1:1. This indicates production of two polymerizable monomers comprising medetomidine bound to the propenylsulfonyl via either of the two imidazole nitrogens. Fig. 1 illustrates the reaction scheme for producing this medetomidine containing sulfonamide compound **M0**.

EXAMPLE 2

[0113] The stability/hydrolysis rate of the monomer were tested in two setups described below

5 Setup 1

[0114] The stability of the carbamate- (**M3**), urea- (**M4**) and sulfonyl derivative of medetomidine (**M2** and **M0**) were studied in ethanol and phosphate-buffered saline (PBS) buffer. Thin-layer chromatography (TLC) was used to follow the decomposition of the derivatives to free medetomidine. It took approximately two weeks until most of the derivatives stored at room temperature to decompose. If the storage temperature was +6°C no decomposition was observed.

Materials and Methods

[0115] Nine vials were prepared. Vial 1 contained reference compound medetomidine dissolved in ethanol (1 ml). Substance **M2** (25 mg) was added to vial 2 and 3. Substance **M3** (25 mg) was added to vial 4 and 5. Substance **M4** (25 mg) was added to vial 6 and 7 and substance **M0** was added to vial 8 and 9. The solid material in vials 2 to 9 were dissolved in ethanol (1 ml) and PBS buffer pH 7.4 (1 ml) to mimic sea water containing different salts and having a pH slightly basic. Ethanol was chosen as solvent to increase the solubility of the substances. During the study vial 1, 3, 5, 7 and 9 were stored at room temperature, whereas vial 2, 4, 6 and 8 were stored in a refrigerator at +6°C. Stability of the compounds was studied after 0, 1, 2, 5, 6, 9, 13 and 15 days using TLC and dichloromethane - methanol (95-5) as eluent.

Results

[0116] Sample **M2** had a Rf value of ≈ 0.6 , sample **M3** had a Rf value of ≈ 0.8 , sample **M4** had a Rf value of 0.55-0.60 and sample **M0** had a Rf value of 0.7. Medetomidine had a Rf value of 0.1. After day 2, only the starting materials (monomers comprising medetomidine) were visible in all vials indicating that no decomposition had taken place. After one week, decomposition of the derivatives was more visible, mainly in the vials stored at room temperature. After two weeks, sample **M2** showed only medetomidine from the vial stored at room temperature, while the vial stored in the refrigerator showed a mixture of medetomidine and the starting material. Sample **M3** showed only medetomidine from the vial stored in room temperature, while the other vial stored in the refrigerator showed a mixture of medetomidine and the starting material. Samples **M2** and **M3** seemed to be very similar in stability. Sample **M4** was stable when stored in the refrigerator after two weeks, but the vial stored at room temperature showed decomposition to medetomidine as well as non-hydrolyzed **M4**. Sample **M0** was stable in room temperature and in the refrigerator after two weeks. The results from the stability experiment indicated that the urea derivative was the most stable and the carbamate derivative was the least stable. The stability of the sulfonamide derivatives was very dependent on the size of the alkyl group.

Setup 2

Materials and methods

[0117] The stability of **M1** and **M4** was evaluated via quantification of the release of **I** into artificial seawater (3 % NaCl, pH 8.0). For the experiments, compound **M1** (0.023 g) was suspended in 5 mL artificial seawater, while **M4** (0.044 g) were suspended in 10 mL artificial seawater. The solutions were stirred (300 rpm) at ambient temperatures and samples were collected at 10, 15, 20 and 25 days. The samples were stored in freezer 2-2.5 months prior to LC-MS analysis.

LC-MS analysis

[0118] Samples from the release studies were analyzed using LC-MS. The LC-MS system was composed of an Acquity I-class UPLC with a Waters Xevo G2-S Qtof. The chromatographic separation was obtained on a C18 column with gradient elution (Eluent A, 0.1 % NH₄ in MQ-water and Eluent B, 100 % acetonitrile). The samples (from freezer) were extracted with hexane and the organic extracts were analyzed by LC-MS. Three external calibration curves for **I**, **M1** and **M4** were prepared the same way as the samples and used for quantification.

[0119] Both the stability of the monomers in artificial seawater and the potential release of **I** were studied and quantified employing LC-MS as summarized in Table 2.

Table 2 - Concentration of I (ng/mL) released from **M1** and **M4**

Compound	Incubation time (days)			
	10	15	20	25
M1	9330.0	9905.8	9748.8	9820.4
M4	5028.9	5592.2	5078.0	-*
* No result due to technical problem during analysis.				

[0120] All samples from the stability studies of compounds **M1** and **M4** yielded a near constant amount of **I**. This suggest either a rapid hydrolysis taking place prior to the first data point at day 10 or a contamination of **I** present in the monomer preparation. The concentration was ~9 µg/mL for **M1** and ~5 µg/mL for **M4**. A complete hydrolysis of the two monomers would yield a concentration of 3.3 mg/mL for **I**, which may be indicative of a low residual contamination of unreacted **I** from the synthesis of **M1** and **M4**. Being present at a concentration of between 0.16-0.27 % in the monomer samples, such a small contamination would not be readily detectable with either NMR or LC-MS and it is possible that the **I** detected from the monomer stability studies indeed is a contamination. A low degree of hydrolysis during sample storage (freezer) cannot be ruled out either.

EXAMPLE 3

[0121] Polymerization of monomers both as homopolymers and as co-polymers was done followed by characterization as described below.

[0122] Polymers from **M1** and **M4** were prepared using radical polymerization initiated by UV-irradiation according to Analytica Chimica Acta 2001, 435: 19-24 and the general method for polymerization is as follows.

Homopolymerization of **M1** and **M4**

[0123] Homopolymers of **M1** and **M4** was further prepared to evaluate the reactivity of the individual monomers. For the preparation of homopolymers, **M1** and **M4** (0.26 g) were dissolved in CHCl₃ (2 mL) and azobis isobutyronitrile (AIBN) (0.026 g) was added. The solution was purged with N₂ (g) for 5 min and placed in the UV-cabinet where it was cured for initial 24 h. Inspection after 24 h indicated a low degree of polymerization (clear, non-viscous solution) and polymerization was therefore continued for an additional 24 h. The experiment was terminated after 48 h and the resultant viscous solution was left to dry at ambient temperature to remove the solvent.

Co-polymerization of **M1** and **M4** together with MMA and EGDMA

[0124] Co-polymers of **M1** and **M4** were prepared with methyl methacrylate (MMA) and the crosslinker ethylene glycol dimethacrylate (EGDMA) employing AIBN as free radical polymerization initiator as illustrated in Fig. 4.

[0125] 1.32 mL (7 mmol) and 745 µL MMA (7 mmol) were dissolved in CHCl₃ (5 mL) in a 20 mL glass scintillation vial. 89 mg of **M4** and AIBN (24 mg, 0.15 mmol) were added to the solution, which was subsequently purged with N₂ (g) for 5 min to remove oxygen from the reaction vessel. The vessel was sealed and placed in a UV-cabinet at room temperature for 24 h to cure at 365 nm, which yielded a solid white polymer monolith inside the vial.

[0126] Following the polymerization, the solid polymer monolith was washed with acetone (10 mL, discarded), crushed with a mortar and pestle (in an acetone slurry) and passed through a sieve (60 µm) to generate a homogenous polymer particle distribution for the release studies. The polymer particles were sedimented from acetone (discarded) and dried at room temperature prior to further studies.

[0127] Polymers prepared with only MMA as co-polymers did not form solid polymers but instead transparent gels due to the lack of a crosslinking monomer. These polymers were also washed with acetone prior to analysis.

[0128] A range of polymers with ranging compositions of EGDMA and MMA and with compounds **I**, **M1** and **M4** (only incorporated one at a time and not in combination) incorporated were prepared according to Table 3.

Table 3 - Polymer composition ratios

	EGDMA:MMA 1:0 (molar ratio)			EGDMA:MMA 0.5:0.5 (molar ratio)			EGDMA:MMA 0:1 (molar ratio)		
	Amount (mmol)	Mass (g)	Volume (μ L)	Amount (mmol)	Mass (g)	Volume (μ L)	Amount (mmol)	Mass (g)	Volume (μ L)
EGDMA	10.5	2.076	1977	7.0	1.388	1321	0	0	0
MMA	0	0	0	7.0	0.701	745	21.0	2.098	2231
AIBN	0.15	0.024		0.15	0.024		0.15	0.024	
CHCl ₃ (mL)			5000			5000			5000
I	0.3	0.062		0.3	0.063		0.3	0.063	
M1	0.3	0.084		0.3	0.084		0.3	0.084	
M4	0.3	0.089		0.3	0.089		0.4	0.089	

[0129] Polymers incorporating ~0.3 % of the monomers **M1** and **M4** were also prepared according to the ratios summarized in Table 1. In addition, polymers incorporating 10 % of **M4** were also prepared using the composition for the neat EGDMA polymers.

Polymer characterization

[0130] The prepared polymers were characterized with FTIR in an attempt to quantify the covalent incorporation of **M1** and **M4** in the copolymers. The reference spectra of the monomers and **I** were compared to the IR-spectra of the ground and washed polymers. Polymers prepared with 10 % **M4** were also analyzed using FTIR.

[0131] Monomers **M1** and **M4** were incorporated at molar ratios ranging between 0.3-10 % in different copolymer systems together with EGDMA and MMA. Visually the polymerization reactions appeared successful as shown and the material was used for release studies. In parallel, the polymers were evaluated using FTIR. Both **M1** and **M4** also displayed strong carbonyl signals at ~1750 cm⁻¹, which unfortunately overlapped with the carbonyl signals of both EGDMA and MMA making the use of that signal ambiguous for assessment of monomer incorporation.

[0132] Attempts to increase the ratio of **M4** were performed by incorporating it at a higher molar ratio. However, the results suggest that the degree of polymer integration is the same for the "3 %" and the "10 %" polymers.

Ninhydrin testing

[0133] The staining of primary and secondary amines by the use of ninhydrin was also employed on the prepared polymers in an attempt to evaluate the presence of covalently incorporated medetomidine monomers. Ninhydrin solution was prepared by dissolving 100 mg ninhydrin in 5 mL acetone (2 % w/v). Polymer samples (5-10 mg) suspended in 0.5 mL of acetone was mixed with 0.5 mL ninhydrin solution in 1 mL clear high-performance liquid chromatography (HPLC) vials. The samples were heated to 90°C for five minutes before the samples were assessed for colorimetric changes indicative of the presence of amines in the polymer. In addition, seawater from "day 30" from the polymer stability study (Example 4) was also analyzed for the presence of released **I** via the potential detection of amines in the seawater.

[0134] Some of the polymer samples generated a weak positive response in comparison with the positive controls **I** and **M4** implying the presence of amines inside the polymer matrix. None of the water samples from the polymer release studies investigated suggested the presence of **I** in the water.

Gel permeation chromatography (GPC)

[0135] To investigate the ability of the monomers (**M1** and **M4**) to generate linear homopolymers gel permeation chromatography (refractive index detection) was performed on polymer samples dissolved in tetrahydrofuran (THF) employing a Styragel HR (Waters) column and isocratic elution with THF at 1 mL/min. Polystyrene standards (M_w : 480, 1050 and 2200 g/mol) were employed to establish the approximate molecular weight of the prepared polymers.

[0136] The results showed that the prepared material eluted with retention times near that of the 500 g/mol standard indicating that polymerization conditions could be further optimized to enhance the yield of polymers.

Co-polymerization of M5 or M6 together with MMA**CP6R1 co-polymer synthesis (M6 and MMA)**

[0137] CP6R1 was synthesized from M6R5 without any purification of the M6R5 monomer. Azobisisobutyronitrile (AIBN) (0.82118 g) dissolved in 5 mL dimethylformamide (DMF), methyl methacrylate (MMA) (26.6 mL), and an additional 35 mL DMF were added to the M6R5 reaction product. This mixture was purged with argon gas before being sealed. The reaction was run for 5 hours.

[0138] The crude mixture was precipitated in 400 mL Tris buffer solution, then washed with pure water, before being washed with acetonitrile. This acetonitrile/polymer slurry was left to dry and a hard white polymer was obtained as the final product.

CP6R2 co-polymer synthesis (M6 and MMA)

[0139] CP6R2 was synthesized from M6R6 without any purification of the M6R6 monomer. AIBN (1.65376 g) dissolved in 5 mL DMF, MMA (8.54 mL), and an additional 78 mL DMF were added to the M6R6 reaction product. This mixture was purged with argon gas before being sealed. The reaction was run for 4 hours.

[0140] CP6R1 had an AIBN:MMA:M6 ratio of 0.5:10:1, whereas CP6R2 had an AIBN:MMA:M6 ratio of 1:8:2. The resulting co-polymer CP6R2 was soluble in acetone and could be precipitated in water.

CP5R1 co-polymer synthesis (M5 and MMA)

[0141] CP5R1 was synthesized from M5R1 following a purification of the M5R1 monomer. The sticky M5R1 (4.0090 g) was dissolved in 45 mL DMF. AIBN (0.96481 g) and MMA (5.010 mL) were then added and this mixture was purged with argon gas. The reaction was run for 4.5 hours.

Co-polymerization of M5 or M6 together with more than one other monomer

[0142] It turned out that co-polymerizing of M5 and M6 together with other monomers was best performed using freshly prepared monomer and continue the polymerization in the same pot. Therefore both the monomer synthesis and polymer synthesis are described in the examples below

[0143] Table 4 show all the synthesized polymers divided into groups (PoC, CP5, CP6 and MS) where the same method was used within each group. The only difference between syntheses within the group was the ratios used of the reagents and monomers. Therefore only one detailed example from each group is given below. The reaction temperature was 65°C for all polymers except PoC_R2 and PoC_R3, which had a reaction temperature of 70°C.

[0144] The PoC-group contained M5 or M6, tri-isopropyl silyl acrylate (TIPSA), and MMA.

[0145] The CP5- and CP6-groups have M5 or M6, TIPSA and MMA and may contain either 2-methoxyethyl acrylate (MEA) or butyl methacrylate (BMA) to give it increased hydrophilicity or hydrophobicity.

[0146] The MS-group is the non-RAFT synthesis based on the corresponding polymers made with similar CP6 monomer ratios. The exception to this is MS_R13a, MS_R13b, and MS_R13c. MS-synthesis was made in smaller scale in scintillation vials. Four monomers were used, M6, TIPSA, MMA and MEA or BMA

Table 4 - Summary of polymer synthesis amounts (mass or volume)

Polymer name	AIBN [g]	DSDA [g]	I [g]	IEA [μ l]	IEM [μ l]	MMA [ml]	BMA [ml]	TIPSA [ml]	2-MEA [ml]	Solvent	v [ml]	t [h]
PoC_R1	0.058	0	0.359	228	0	1.85	0	2.97	0	Butanone	45	5
PoC_R2	0.145	0	1.071	0	750	2.81	0	6.08	0	Butanone	45	5.5
PoC_R3	0.162	0	1.244	0	880	4.91	0	3.54	0	Butanone	45	5.5
PoC_R4	0.163	0	1.245	0	880	4.91	0	3.54	0	Butanone	40	6
CP5_R2	0.152	0.196	0.685	440	0	2.82	0	6.14	0.69	Xylene	40	6
CP6_R3	0.151	0.195	0.691	0	490	2.81	0	6.11	0.68	Butanone	40	6
CP6_R4	0.152	0.196	0.681	0	480	2.81	0	6.11	0.68	Xylene	40	6.5
CP6_R5	0.170	0.219	0.794	0	560	4.9	0	3.56	0.8	Xylene	40	6
CP6_R6	0.138	0.177	0.597	0	420	1.23	0	8.03	0.6	Xylene	40	6
CP6_R7	0.153	0.197	0.689	0	490	2.68	0	5.83	1.04	Xylene	40	6
CP6_R8	0.151	0.194	0.675	0	480	2.93	0	6.38	0.34	Xylene	40	6
CP6_R9	0.151	0.194	0.676	0	480	2.79	0.84	6.07	0	Xylene	40	6
CP6_R10	0.152	0.195	0.682	0	480	2.81	0	6.11	0.68	Xylene	40	6
CP6_R11	0.153	0.198	0.689	0	490	2.68	0	5.83	1.04	Xylene	40	6
CP6_R12	0.488	0.635	0.682	0	480	2.81	0	6.11	0.68	Butanone	40	6
MS_R1	0.062	0	0.275	0	192	1.12	0	2.44	0.27	Butanone	6	5
MS_R2	0.068	0	0.316	0	220	2.07	0.17	1.5	0	Butanone	6	5
MS_R3	0.068	0	0.317	0	220	2.08	0	1.51	0.14	Butanone	6	5
MS_R4	0.068	0	0.318	0	220	1.96	0	1.42	0.32	Butanone	6	5
MS_R5	0.068	0	0.318	0	220	1.86	0	1.35	0.48	Butanone	6	5
MS_R6	0.068	0	0.314	0	220	1.95	0.39	1.41	0	Butanone	6	5
MS_R7	0.068	0	0.318	0	220	1.96	0	1.42	0.32	Butanone	6	5
MS_R8	0.068	0	0.318	0	220	1.86	0	1.35	0.48	Butanone	6	5
MS_R9	0.068	0	0.315	0	220	1.95	0.39	1.41	0	Butanone	6	5
MS_R10	0.062	0	0.272	0	192	1.95	0	2.44	0.27	Butanone	6	5

(continued)

Polymer name	AIBN [g]	DSDA [g]	I [g]	IEA [μ l]	IEM [μ l]	MMA [ml]	BMA [ml]	TIPSA [ml]	2-MEA [ml]	Solvent	v [ml]	t [h]
MS_R11	0.058	0	0.258	0	181	0.85	0	2.78	0.26	Butanone	6	5
MS_R12	0.069	0	0.317	0	220	1.96	0	1.42	0.32	Butanone	6	5
MS_R13a	0.061	0.013	0.273	0	192	1.12	0	2.48	0.24	Butanone	6	5
MS_R13b	0.062	0.012	0.273	0	192	1.12	0	2.40	0.24	Butanone	6	5
MS_R13c	0.061	0	0.273	0	192	1.12	0	2.42	0.24	Butanone	6	5
MS_R13d	0.061	0.012	0.272	0	192	1.12	0	2.42	0.24	Butanone	6	5

[0147] AIBN: azobis isobutyronitrile; DSDA: tetraethyl thiuram disulfide; I: medetomidine IEA: isocyanatoethyl acrylate; IEM: isocyanatoethyl methacrylate; MMA: methyl methacrylate; BMA: butyl methacrylate; TIPSA: tri-isopropyl silyl acrylate; 2-MEA: 2-methoxyethyl acrylate; V: solvent volume; t: reaction time

PoC_R2 (M6 10 mol%, TIPSA 45 mol% and MMA 45 mol%)

[0148] In a 100 mL 3-neck round bottom flask, medetomidine I (1.07068 g) was dissolved in 10 ml DCM with a magnetic stirring, set in room temperature. IEM (750 μ l) was added dropwise. After three hours, MMA (2.81 mL) and TIPSA (6.08 mL) were added. AIBN (0.14472 g) and butanone (40 mL) were added and the mixture was homogenized and sealed with rubber stoppers and parafilm under argon atmosphere. The reaction was left with stirring at 70°C for 5.5 h. The reaction was terminated by removing the flask from the oil bath and opening it and letting oxygen terminate the radicals.

CP6_R4 (M6 6 mol%, TIPSA 21.15 mol%, MMA 63.45 mol% and 9.4 mol% MEA)

[0149] In a 3-neck round bottom flask, medetomidine I (0.6808 g) was dissolved with 10 ml DCM by stirring with a magnet. IEM (480 μ l) was then added dropwise with the flask left unsealed to eventually let the DCM evaporate overnight. MMA (2.81 mL), TIPSA (6.11 mL), and MEA (0.68 mL). Xylene (20 mL) were added to the flask and mixed to homogenize.

[0150] AIBN (0.15206 g) and DSDA (0.19585 g) were added to individual scintillation vials. In the scintillation vial containing AIBN, butanone (1 ml) was added to dissolve the AIBN. Once it had dissolved, xylene (9 ml) was added. This AIBN solution was then added to the reaction flask. In the scintillation vial containing DSDA, xylene (10 mL) was added to dissolve it. This DSDA solution was then added to the reaction flask. The reaction flask was purged with argon and sealed with rubber stopper and parafilm. The reaction was started by lowering the reaction flask down into a 65°C oil bath. The reaction was left in the bath for 6.5 hours and was then terminated by taking it out of the bath, opening the flask and letting oxygen terminate the radicals.

MS_R12 (M6 6 mol%, TIPSA 21.15 mol%, MMA 63.45 mol% and 9.4 mol% MEA)

[0151] In a scintillation vial, medetomidine I (0.31741 g) was dissolved with 4 ml DCM by stirring with a magnet. IEM (220 μ L) was then added dropwise with the vial left unsealed to eventually evaporate the DCM overnight.

[0152] AIBN (0.06865 g), MMA (1.96 mL), TIPSA (1.42 mL), and MEA (0.32 mL) were added to the vial. The vial was sealed with a rubber stopper and wrapped with parafilm. Using a glass syringe, 6 mL of butanone was introduced. The content of the vial was mixed at room temperature. The vial was purged with argon for 20 minutes and was then lowered into the oil bath to start the polymerization reaction and was left at 65°C for 5 hours. The reaction was terminated by bringing the vial out of the bath, opening the vessel and letting oxygen terminate the radicals.

EXAMPLE 4

Release of medetomidine from M4 co-polymers in artificial sea water

[0153] Release of I from selected polymers was also established in artificial seawater in accordance with the monomer release studies. For the studies, 0.5 g polymer (the three polymer systems from Table 3 incorporating M4 as medetomidine monomer) was added to 20 mL artificial seawater, which was stirred (300 rpm) at ambient temperature. 1 mL samples were collected after 2, 10, and 15 days. These samples were filtered through a 0.22 μ m syringe-driven filter to remove any solid residue before being analyzed using LC-MS. The samples were stored in freezer prior (~2 months) to analysis.

[0154] The polymeric PSB displayed a time dependent low linear release of 1 as graphically illustrated in Fig. 5.

[0155] A selection of prepared polymers (Table 3) was also incubated in seawater and the release of I from the material was analyzed. No release of I was detected from any of the polymer samples in the LC-MS analysis. No release would indicate either a low or no incorporation of the monomers into the polymers or no hydrolysis of the incorporated monomers under the experimental conditions employed. Previous results (monomer release and FT-IR studies) suggest that both events are likely and it is impossible to distinguish between their potential individual contributions to the results here. Potential residual free I from the polymer synthesis would have been washed away during the work-up and would not produce a "constant" release as that observed for the monomer release studies.

EXAMPLE 5

[0156] Medetomidine was also linked to isocyanate functionalized polystyrene beads (from Biotage) to function as a model polymer system (shown in Fig. 3) to study the release of medetomidine from a polymer.

Preparation of medetomidine loaded polystyrene beads (PSB)

[0157] The polystyrene immobilized medetomidine (**PSB**) was generated by reacting **I** with polystyrene methylisocyanate employing the same coupling conditions used to produce **M4**, see Fig. 3.

[0158] The synthesis of **PSB** was performed in syringes (20 mL) fitted with filters to retain the polystyrene beads. 1 g of polystyrene methylisocyanate beads (Biotage 800261 batch 04446, capacity 1.48 mmol/g) was added to the syringe followed by the addition of **I** (446 mg, 2.23 mmol, 1.5 equiv.) and pyridine (0.36 mL, 4.46 mmol, 3 equiv.) dissolved in anhydrous dichloromethane (10 mL). The syringe was agitated overnight at room temperature. After 24 h the syringe was drained and the beads were three times washed with dichloromethane before the material was freeze dried. 5 mg of **PSB** was removed and exposed to 1 mL of TFA/dichloromethane (1:1) under sonication. Liquid chromatography-mass spectrometry (LC-MS) analysis revealed a release of **I** indicating cleavage of the urea bond to the polystyrene bead. In total 2 g of **PSB** was prepared in two batches.

[0159] The washed and dried beads were studied using Fourier-transform infrared spectroscopy (FTIR) and comparison of **PSB** with the unreacted polystyrene methylisocyanate revealed a complete loss of the isocyanate peak at 2259 cm⁻¹ and an appearance of a weak carbonyl signal at 1720 cm⁻¹, which could be linked to the urea bond carbonyl in **PSB**.

EXAMPLE 6**Incubation of medetomidine-loaded polymer in sea water mimic buffer**

[0160] Three weightings of 5 mg each of the medetomidine loaded polystyrene beads (**PSB**) from Example 5 was added to three 50 mL glass bottles with screw caps. 20 mL of sea water mimic buffer, 0.05 M phosphate buffer at pH 8 with 3% NaCl, was added, with the polymer lying on the surface of the solutions. The three bottles were incubated in the dark at +5°C (cold room), room temperature (RT) and at +50°C (water bath) with gentle stirring, keeping the polymer still lying on the surface. The solutions at +5°C and RT were gently stirred by magnetic stirrer and the bottle in the +50°C water bath was gently shaken.

[0161] Aliquots were removed from the incubations after 1 and 4 hours and after 1, 4, 7, 11, 14, 18 and 21 days. The concentration of medetomidine in the samples was quantified using a calibration curve. In more detail, a sampling volume (100 µL) was added directly into LC vials of glass with inserts and the solutions were injected as such. At later time points the samples from the incubation at +50°C was diluted 1:10 (10 µL + 90 µL buffer) respectively 1:20 (10 µL + 190 µL buffer) before injection.

[0162] A series of six working standard solutions of medetomidine was prepared in water/ethanol (75/25, v/v), with hundred times the final concentrations in sea water mimic buffer (see Table 5). Initially a 10 mM stock solution of medetomidine in EtOH was diluted 1:100 by adding 5 µL to 495 µL water/ethanol (75/25, v/v) giving a concentration of 100 µM:

S1 60 µL of 100 µM) was added to 540 µL water/ethanol (75/25, v/v)
 S2 300 µL of S1 was added to 700 µL water/ethanol (75/25, v/v)
 S3 300 µL of S2 was added to 600 µL water/ethanol (75/25, v/v)
 S4 300 µL of S3 was added to 700 µL water/ethanol (75/25, v/v)
 S5 300 µL of S4 was added to 600 µL water/ethanol (75/25, v/v)
 S6 300 µL of S5 was added to 700 µL water/ethanol (75/25, v/v)

[0163] A volume of 10 µL of the working standard solutions was spiked individually into 990 µL of sea water mimic buffer pH 8 with 3% NaCl. The dilutions were made directly into LC vials of glass. A blank sample was prepared by adding 10 µL water/ethanol (75/25, v/v) into 990 µL sea water mimic buffer.

Table 5 - Concentrations (nM) in the working standard solutions and the final concentrations in the calibration samples in sea water mimic buffer

Calibration samples	Concentration (nM)	
	Working std solutions in water/ethanol	Sea water mimic buffer
S1	10000	100
S2	3000	30
S3	1000	10

(continued)

Calibration samples	Concentration (nM)	
	Working std solutions in water/ ethanol	Sea water mimic buffer
S4	300	3
S5	100	1
S6	30	0.3
Blank	0	0

[0164] A few injections were made up front to assure that the instrumentation was equilibrated. A calibration curve was injected in the beginning and in the end of the analytical sequence, bracketing the unknown samples.

[0165] All samples were analyzed within 24 h after sampling, together with a three-point calibration curve, to be able to follow the changes in concentrations. The samples were then stored dark at RT in the LC vials until the last sampling occasion, when all samples were analyzed/reanalyzed and quantified vs a freshly prepared calibration curve. The re-analyzed samples showed good agreement with the initial analysis, with a difference of less than 10% for most samples and with >20% for two samples out of the twenty-seven samples. All calculations are based on data from the final analysis occasion.

[0166] The order of the injected samples in the final analytical sequence was as follows; Blank, Calibration samples S1 to S6, Blank, 1 h (+5°C, RT, +50°C), 4 h (+5°C, RT, +50°C), 24 h (+5°C, RT, +50°C), 96 h (+5°C, RT, +50°C 1:10), 168 h (+5°C, RT, +50°C 1:10), 264 h (+5°C, RT, +50°C 1:20), 336 h (+5°C, RT, +50°C 1:20), 432 h (+5°C, RT, +50°C 1:20), 504 h (+5°C, RT, +50°C 1:20), Blank, Calibration samples S1 to S6, Blank.

[0167] The data indicates a faster release of medetomidine during the initial phase, up to approximately 24 hours, potentially corresponding to a wash-out phase of unbound medetomidine from the polymer. Subsequently, another release phase follows characterized by a slower constant rate during the last twenty days of the three weeks of incubation. This was experienced for all three evaluated temperatures (+5°C, RT and +50°C), see Figs. 6A to 6C. However, the rate of release of medetomidine was different between the three evaluated temperatures. The total amount of released medetomidine was calculated in picomol (pmol) and was plotted against time during the period of constant compound release (day 1 to day 21), see Figs. 7A to 7C, and the rate of release was calculated as pmol/h/mg polymer. Assuming a linear relationship, the release rate of medetomidine at +5°C was about 0.007 pmol/h/mg polymer, at RT about 0.18 pmol/h/mg polymer and about 4.6 pmol/h/mg polymer for the incubation at +50°C.

[0168] Table 6 summaries the results plotted in Figs. 6 and 7.

Table 6 - Measured concentrations of medetomidine (nM) and the calculated released amounts of medetomidine (pmol) over time

Time (h)	+5°C		RT		+50°C	
	Concentration (nM)	Released amount (pmol)	Concentration (nM)	Released amount (pmol)	Concentration (nM)	Released amount (pmol)
1	1.01	20.2	2.67	53.4	9.67	193
4	1.06	21.2	3.43	68.5	25.5	508
24	1.39	27.6	7.04	139	75.3	1487
96	1.76	35.0	12.2	242	183	3616
168	1.92	38.2	14.4	285	257	5067
264	2.03	40.3	19.4	382	396	7777
336	2.10	41.7	24.3	477	480	9407
432	2.23	44.2	27.8	545	566	11067
504	2.37	46.9	28.9	566	638	12450

EXAMPLE 7

Leaching rate of medetomidine (I) from copolymers

[0169] The crude polymer product from MS_R7 and MS_R13a were precipitated in methanol and the methanol/monomer/reaction residues mixture was decanted off. The "wet polymer" contained some butanone and methanol. The wet polymer was immediately re-dissolved back into butanone before it was used for the leach rate study.

[0170] In a weighed scintillation vial, 200-500 μ l of polymer solution was cast onto the base of the vial (inner diameter of this vial was 25 mm) and left to dry for two days. The vial was weighed again to determine the mass of the polymer.

[0171] Artificial seawater (1.5 ml) was added to the vial and closed off with a cap. After one month, all the seawater in the vial was removed, and fresh artificial seawater was introduced. This was repeated for three months. The concentration of medetomidine in the artificial seawater was determined with HPLC after each month

Table 7 - release of medetomidine (I) over time and area from polymers in sea water

	MS_R7			MS_R13A		
Time [months]	1	2	3	1	2	3
I released [μ g]	495.8	178.2	66.5	1380	85.7	56.7
I cumulative release [μ g]	495.8	674	740.5	1380	1465	1522
I released per area [μ g/mm ²]	1.01	1.37	1.51	2.81	2.98	3.10

[0172] After an initial burst, there was a slow release of medetomidine over time. The results show that the polymers were hydrolyzing and medetomidine was released over time.

EXAMPLE 8

Paint formulation and performance of medetomidine containing copolymers in marine paint formulations on panels in the sea

Paint Formulations and application to test panels

[0173] In Table 8, the content of medetomidine, Cu-Pt and Cu₂O of the formulation 1-6 are presented. A general description for preparation of control formulation is as follows. 8 g of hydrogenated Rosin ((2E)-3-Phenylprop-2-en-1-yl β -D-glucopyranoside) was dissolved in 28 ml xylene at 3000 rpm for 2 minutes using a speed mixer (Synergy Devices Ltd, UK). This was followed by addition of 0,5 g of soy lecithin, 9 g of acrylic resin at 5 + 4 g aliquots, 2 g of plasticizer, 8 g of iron oxide, 2 g of GARAMITE[®] clay, 0,5 g mica, 10 g of barium sulphate at 5 + 5 g aliquots, 9 g of talc in 5 + 4 g aliquots and 10 g Cu₂O. After each addition step, there was a mixing step at 3000 rpm for 2-5 minutes depending on dispersion of components (visual inspection). After these steps, viscosity was adjusted by addition of 3-16 ml of xylene and mixing continued until the temperature reached 40°C, indicating good dispersion of the paint components. During preparation of formulation #2 Cu-Pt (1 g) and medetomidine (0.1 g) were added before the talc addition step. In formulation # 3-6, the polymer conjugated with medetomidine was added first before dissolving the rosin. Around 1.5 g of this polymer was added, either as crude (dissolved in butanone) or as precipitate (following a MeOH wash), resulting in a final concentration of bound medetomidine in the range of 0.10 - 0.18 weight% (Table 8). The acrylic resin was reduced to 8 g to compensate for the addition of medetomidine containing binder.

Table 8 - Paint formulations

Formulation #	Medetomidine [wt%]	Cu-Pt [wt%]	Cu ₂ O [wt%]	Note
#1	-	-	11.6	Control
#2	0.10	1.1	10.0	Reference, Free medetomidine
#3	0.12	1.1	10.3	Medetomidine polymer bound, MS_R12
#4	0.18	1.1	10.6	Medetomidine polymer bound, MS_R12
#5	0.10	1.1	10.5	Medetomidine polymer bound, MS_R13a
#6	0.10	1.0	9.7	Medetomidine polymer bound, MS_R13b

[0174] 3 PMMA panels (25 × 15 cm) were first coated with an epoxy primer. Two layers of formulation # 1-6 were then applied by the use of a roller resulting in dry weight of around 5 g of coating/panel. Drying of the paint was performed at ambient humidity and temperature.

Field study

[0175] A field study was carried out at Kristineberg centre on the west coast of Sweden (58°25'01.0"N 11°44'45.3"E, Baltic Sea transition zone). Coated PMMA panels (25 × 15 cm) were deployed by hanging them with a tie strap on an aluminium frames (190 × 91 cm) using pre-drilled holes on the corners of the panels. The panels were randomly distributed on the frame both achieving a random vertical and lateral distribution. Uncoated panels (epoxy primer) as well as control coating without any medetomidine (formulation #1) were used as negative controls. A coating with free medetomidine (formulation #2) was used as positive control. Water depth ranged from 25 cm to 205 cm. The field study was initiated in June (23 June 2021) when the fouling pressure is known to be highest and inspected visually and photographed monthly during summer season with last inspection at 9 September 2021. The degree of fouling and species was assessed based on visual inspection and photographs.

Results

[0176] Both the epoxy control and control formulation (formulation #1) showed high degree of fouling accumulation after 13 weeks of immersion (Figs. 9 and 10). Fouling species on epoxy control included, for example, barnacles, mussel, bryozoa, tunicate, green algae, filamentous algae and tubeworm (Fig. 9). On control formulation (formulation #1), the biofouling was mainly barnacles (Fig. 10). A few tunicates were visible, but in principle the control formulation was selective for barnacle accumulation and, thus, relevant to use for studying the effect upon addition of medetomidine, both free or as polymer bound. By adding medetomidine dispersed (free) at 0.1% in the coating (formulation #2) no accumulation of barnacles was observed showing the potential of medetomidine in preventing barnacle settling (Fig. 11). Comparable results were observed when investigating the settling of barnacles on formulations (formulation #3-6) containing medetomidine bound to an eroding polymer binder. Formulation #3 showed some barnacle settling along the periphery of the panels but in principle the formulation worked acceptable. Formulation #3 contained non-purified polymer (crude from synthesis was used directly in the formulation) at 0.1% (Fig. 12). Interestingly, adding this polymer at slightly higher concentration (0.18%) as in formulation #4 improved the performance (Fig. 13) and no barnacle settling was observed on this formulation. In formulation #5 (Fig. 14) and formulation #6 (Fig. 15), the molar composition in the polymer was changed by decreasing the MMA and increasing the TIPSA molar concentration in the feed during polymerization. In formulation #5, a polymer synthesized by radical polymerization was used and in formulation #6 a polymer synthesized by RAFT polymerization was used. As can be seen in Figs. 14 and 15, both these formulations performed comparable with formulation #2 (free medetomidine) showing no barnacle settling. However, on formulation #6 some tunicates and filamentous algae were observed (Fig. 15). In conclusion, formulations containing polymer bound medetomidine, depending on hydrolysis for the release, can perform comparable with formulations having medetomidine dispersed (free).

Table 9 - Area covered by various fouling organism on each test panel

Formulation_ panel replicate no.	Barnacles (%)	Bryozoa (%)	Sea anemones (%)	Blue mussel (%)	Tube worm (%)	Green algae and filamentous algae (%)	Tunicate (%)	Total biofouling coverage (%)
Epoxy rep 1	2	25	5	2	2	15	0	51
Epoxy rep 2	8	50	0	25	1	10	0	94
Epoxy rep 3	2	20	2	40	1	30	0	95
#1_rep 1	30	0	1*	0	0	0	1*	32
#1_rep 2	25	0	2	0	0	0	1*	28
#1_rep 3	25	0	0	1	0	3	0	29
#2_rep 1	1**	0	0	1*	0	0	0	2
#2_rep 2	1**	0	0	1*	0	0	0	2
#2_rep 3	0	0	0	0	0	0	0	0
#3_rep 1	2	0	0	0	0	0	0	2
#3_rep 2	4	0	0	0	0	1	0	5
#3_rep 3	1	0	0	0	0	0	0	1
#4_rep 1	0	0	0	0	0	0	0	0
#4_rep 2	0	0	0	0	0	0	0	0
#4_rep 3	0	0	0	0	0	0	0	0
#5_rep 1	0	0	0	0	0	0	0	0
#5_rep 2	0	0	0	0	0	0	0	0
#5_rep 3	0	0	0	0	0	0	0	0

5
10
15
20
25
30
35
40
45
50
55


(continued)


Formulation_ panel replicate no.	Barnacles (%)	Bryozoa (%)	Sea anemones (%)	Blue mussel (%)	Tube worm (%)	Green algae and filamentous algae (%)	Tunicate (%)	Total biofouling coverage (%)
#6_rep 1	0	0	4	2	0	0	0	6
#6_rep 2	0	0	3	0	0	2	0	5
#6_rep 3	0	0	3	0	0	2	0	5
* one individual ** a few individuals								

[0177] The embodiments described above are to be understood as a few illustrative examples of the present invention. It will be understood by those skilled in the art that various modifications, combinations and changes may be made to the embodiments without departing from the scope of the present invention. In particular, different part solutions in the different embodiments can be combined in other configurations, where technically possible. The scope of the present invention is, however, defined by the appended claims.

Claims

1. An antifouling polymer comprising a plurality of repeating units, wherein at least a portion of the plurality of repeating units comprises medetomidine, or an enantiomer, base or salt thereof, covalently bound to the repeating unit through a hydrolysable bond.
2. The polymer according to claim 1, wherein the polymer is:
 - a co-polymer comprising a first type of repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, and the first type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof;
 - a co-polymer comprising a first type of repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, a second, different type of repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, and optionally the first type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof, and/or optionally the second, different type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof; or
 - a co-polymer comprising a first type of repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, a second, different type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof, and optionally the first type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof.
3. The polymer according to claim 2, wherein the polymer is a co-polymer comprising the first type of repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, and the first type of repeating unit lacking medetomidine, or the enantiomer, base or salt thereof.
4. The polymer according to claim 1, wherein the polymer is a homopolymer of repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, preferably the homopolymer is selected from the group consisting of a poly(medetomidine methacrylate), a poly(allylsulfonyl medetomidone), a poly(allyl medetomidine), a poly(medetomidine acrylate) and a poly(silyl medetomidine).
5. The polymer according to any of the claims 1 to 4, wherein medetomidine, or the enantiomer, base or salt thereof, is covalently bound to the repeating unit through the hydrolysable bond between a nitrogen on the imidazole ring of medetomidine, or the enantiomer, base or salt thereof, and the monomer.
6. The polymer according to any of the claims 1 to 5, wherein the repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, has a general formula II or III:







(III)

wherein


R^1 is selected from the group consisting of formula IV to VI:



(IV)




(V)




(VI)

R^2 is selected from the group consisting of formula VII and VIII:




(VII)




(VIII)

n is 0 or 1;


R^3 is selected from the group consisting of formula IX to XIV:



(IX)




(X)




(XI)


m is 0, 1, 2 or 3;



(XII)



(XIII)



(XIV)

R is independently H or alkyl, wherein alkyl is preferably a C1 to C6 alkyl, and more preferably a C1 to C4 alkyl, such as methyl or ethyl, preferably methyl; and

R⁴, R⁵ and R⁶ is independently alkoxy, preferably a C1 to C6 alkoxy, and more preferably a C1 to C4 alkoxy, such as methoxy, ethoxy or propoxy.

7. The polymer according to any of the claims 1 to 6, wherein the repeating unit comprising medetomidine, or the enantiomer, base or salt thereof, is selected from the group consisting of 1-{4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazol-1-yl}-2-methylprop-2-en-1-one, 1-{5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazol-1-yl}-2-methylprop-2-en-1-one, 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl 2-methylprop-2-enoate, 2-({5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl 2-methylprop-2-enoate, 4-[1-(2,3-dimethylphenyl)ethyl]-1-(prop-2-ene-1-sulfonyl)-1*H*-imidazole, 5-[1-(2,3-dimethylphenyl)ethyl]-1-(prop-2-ene-1-sulfonyl)-1*H*-imidazole, prop-2-en-1-yl 4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carboxylate, prop-2-en-1-yl 5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carboxylate, 4-[1-(2,3-dimethylphenyl)ethyl]-*N*-(prop-2-en-1-yl)-1*H*-imidazole-1-carboxamide, 5-[1-(2,3-dimethylphenyl)ethyl]-*N*-(prop-2-en-1-yl)-1*H*-imidazole-1-carboxamide, 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate, 2-({5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate, 2-({4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate, 2-({5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-carbonyl}amino)ethyl prop-2-enoate, 3-(4-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-dimethylsilyl)propyl 2-methylprop-2-enoate and 3-(5-[1-(2,3-dimethylphenyl)ethyl]-1*H*-imidazole-1-dimethylsilyl)propyl 2-methylprop-2-enoate.

8. An antifouling composition comprising a polymer according to any of the claims 1 to 7 and a solvent.

9. The composition according to claim 8, further comprising free medetomidine or an enantiomer, base or salt thereof, not covalently bound to any repeating unit or monomer.

10. An article comprising a surface coating comprising a polymer according to any of the claims 1 to 7 and/or an antifouling composition according to claim 8 or 9 on at least a portion of a surface of the article designed to be submersed in water to inhibit marine biofouling of the surface.

11. A method of producing a medetomidine monomer, the method comprises reacting a polymerizable monomer comprising an electrophilic site with medetomidine, or an enantiomer, base or salt thereof, to covalently bind medetomidine, or the enantiomer, base or salt thereof, to the monomer through a hydrolysable bond formed between the electrophilic site and a nitrogen on the imidazole ring of medetomidine, or the enantiomer, base or salt thereof.

12. The method according to claim 11, further comprising:

dissolving medetomidine, or the enantiomer, base or salt thereof, in a solvent to form a medetomidine solution; and
adding the polymerizable monomer to the medetomidine solution.

13. The method according to claim 12, wherein

dissolving medetomidine, or the enantiomer, base or salt thereof, comprises dissolving medetomidine, or the enantiomer, base or salt thereof, and diisopropylethylamine in dichloromethane to form the medetomidine solution; and

adding the polymerizable monomer comprises adding allyl chloroformate to the medetomidine solution; or

dissolving medetomidine, or the enantiomer, base or salt thereof, comprises dissolving medetomidine, or the enantiomer, base or salt thereof, and optionally pyridine in dichloromethane to form the medetomidine solution; and

adding the polymerizable monomer comprises adding allyl isocyanate to the medetomidine solution; or

dissolving medetomidine, or the enantiomer, base or salt thereof, comprises dissolving medetomidine, or the enantiomer, base or salt thereof, and trimethylamine in dichloromethane to form the medetomidine solution; and
adding the polymerizable monomer comprises adding 2-propenylsulfonyl chloride to the medetomidine solution; or

dissolving medetomidine, or the enantiomer, base or salt thereof, comprises dissolving medetomidine, or the enantiomer, base or salt thereof, and *N,N*-dimethyl-4-aminopyridine in dichloromethane to form the medetomidine solution; and

adding the polymerizable monomer comprises adding methacrylic anhydride or methacryloyl chloride to the medetomidine solution; or


dissolving medetomidine, or the enantiomer, base or salt thereof, comprises dissolving medetomidine, or the

enantiomer, base or salt thereof, in dichloromethane to form the medetomidine solution; and
 adding the polymerizable monomer comprises adding isocyanatoethyl methacrylate to the medetomidine so-
 lution; or
 dissolving medetomidine, or the enantiomer, base or salt thereof, comprises dissolving medetomidine, or the
 enantiomer, base or salt thereof, in dichloromethane to form the medetomidine solution; and
 adding the polymerizable monomer comprises adding isocyanatoethyl acrylate to the medetomidine solution.


14. A method of producing an antifouling polymer, the method comprises polymerizing monomers comprising medeto-
 midine, or an enantiomer, base or salt thereof, covalently bound to the monomer through a hydrolysable bond and
 optionally monomers lacking medetomidine, or an enantiomer, base or salt thereof, to form an antifouling polymer
 comprising a plurality of repeating units derived from the monomers, wherein at least a portion of the plurality of
 repeating units comprises medetomidine, or the enantiomer, base or salt thereof, covalently bound to the repeating
 units through a hydrolysable bond.
15. A method of producing an antifouling polymer, the method comprises covalently binding medetomidine, or an enan-
 tiomer, base or salt thereof, to a polymer comprising a plurality of repeating units so that at least a portion of the
 plurality of repeating units comprises medetomidine, or the enantiomer, base or salt thereof, covalently bound to
 the repeating units through a hydrolysable bond.

Patentansprüche

1. Antifouling-Polymer, das eine Vielzahl von Wiederholungseinheiten umfasst, wobei mindestens ein Teil der Vielzahl
 von Wiederholungseinheiten Medetomidin oder ein Enantiomer, eine Base oder ein Salz davon umfasst, das/die
 über eine hydrolysierbare Bindung kovalent an die Wiederholungseinheit gebunden ist.
2. Polymer nach Anspruch 1, wobei das Polymer Folgendes ist:
- ein Copolymer umfassend eine erste Art von Wiederholungseinheit umfassend Medetomidin oder das Enanti-
 omer, die Base oder das Salz davon und die erste Art von Wiederholungseinheit, der Medetomidin oder das
 Enantiomer, die Base oder das Salz davon fehlt;
 ein Copolymer umfassend eine erste Art von Wiederholungseinheit umfassend Medetomidin oder das Enanti-
 omer, die Base oder das Salz davon, eine zweite, andere Art von Wiederholungseinheit umfassend Medetomidin
 oder das Enantiomer, die Base oder das Salz davon und optional die erste Art von Wiederholungseinheit, der
 Medetomidin oder das Enantiomer, die Base oder das Salz davon fehlt, und/oder optional die zweite, andere
 Art von Wiederholungseinheit, der Medetomidin oder das Enantiomer, die Base oder das Salz davon fehlt; oder
 ein Copolymer umfassend eine erste Art von Wiederholungseinheit umfassend Medetomidin oder das Enanti-
 omer, die Base oder das Salz davon, eine zweite, andere Art von Wiederholungseinheit, der Medetomidin oder
 das Enantiomer, die Base oder das Salz davon fehlt, und optional die erste Art von Wiederholungseinheit, der
 Medetomidin oder das Enantiomer, die Base oder das Salz davon fehlt.
3. Polymer nach Anspruch 2, wobei das Polymer ein Copolymer umfassend die erste Art von Wiederholungseinheit
 umfassend Medetomidin oder das Enantiomer, die Base oder das Salz davon und die erste Art von Wiederholungs-
 einheit, der Medetomidin oder das Enantiomer, die Base oder das Salz davon fehlt, ist.
4. Polymer nach Anspruch 1, wobei das Polymer ein Homopolymer mit Wiederholungseinheit ist, die Medetomidin
 oder das Enantiomer, die Base oder das Salz davon umfasst, vorzugsweise wobei das Homopolymer ausgewählt
 ist aus der Gruppe bestehend aus einem Poly(medetomidinmethacrylat), einem Poly(allylsulfonylmedetomidon),
 einem Poly(allylmedetomidin), einem Poly(medetomidinacrylat) und einem Poly(silylmedetomidin).
5. Polymer nach einem der Ansprüche 1 bis 4, wobei Medetomidin oder das Enantiomer, die Base oder das Salz
 davon über die hydrolysierbare Bindung zwischen einem Stickstoff am Imidazolring von Medetomidin oder dem
 Enantiomer, der Base oder dem Salz davon und dem Monomer kovalent an die Wiederholungseinheit gebunden ist.
6. Polymer nach einem der Ansprüche 1 bis 5, wobei die Wiederholungseinheit umfassend Medetomidin oder das
 Enantiomer, die Base oder das Salz davon eine allgemeine Formel II oder III aufweist:




(II)




(III)

wobei


R¹ ausgewählt ist aus der Gruppe bestehend aus Formel IV bis VI:



(IV)




(V)




(VI)

R² ausgewählt ist aus der Gruppe bestehend aus Formel VII und VIII:




(VII)




(VIII)

n 0 oder 1 ist;


R³ ausgewählt ist aus der Gruppe bestehend aus Formel IX bis XIV:



(IX)




(X)



(XI)

m 0, 1, 2 oder 3 ist;



R unabhängig voneinander H oder Alkyl ist, wobei Alkyl vorzugsweise ein C1- bis C6-Alkyl und besonders bevorzugt ein C1- bis C4-Alkyl, wie Methyl oder Ethyl, bevorzugt Methyl, ist; und
 R⁴, R⁵ und R⁶ unabhängig voneinander Alkoxy, bevorzugt ein C1- bis C6-Alkoxy und besonders bevorzugt ein C1- bis C4-Alkoxy, wie Methoxy, Ethoxy oder Propoxy, sind.

7. Polymer nach einem der Ansprüche 1 bis 6, wobei die Wiederholungseinheit umfassend Medetomidin oder das Enantiomer, die Base oder das Salz davon ausgewählt ist aus der Gruppe bestehend aus 1-{4-[1-(2,3-Dimethylphenyl)ethyl]-1H-imidazol-1-yl}-2-methylprop-2-en-1-on, 1-{5-[1-(2,3-Dimethylphenyl)ethyl]-1H-imidazol-1-yl}-2-methylprop-2-en-1-on, 2-({4-[1-(2,3-Dimethylphenyl)ethyl]-1H-imidazol-1-carbonyl}amino)ethyl-2-methylprop-2-enoat, 2-({5-[1-(2,3-Dimethylphenyl)ethyl]-1H-imidazol-1-carbonyl}amino)ethyl-2-methylprop-2-enoat, 4-[1-(2,3-Dimethylphenyl)ethyl]-1-(prop-2-en-1-sulfonyl)-1H-imidazol, 5-[1-(2,3-Dimethylphenyl)ethyl]-1-(prop-2-en-1-sulfonyl)-1H-imidazol, Prop-2-en-1-yl-4-[1-(2,3-dimethylphenyl)ethyl]-1H-imidazol-1-carboxylat, Prop-2-en-1-yl-5-[1-(2,3-dimethylphenyl)ethyl]-1H-imidazol-1-carboxylat, 4-[1-(2,3-Dimethylphenyl)ethyl]-N-(prop-2-en-1-yl)-1H-imidazol-1-carboxamid, 5-[1-(2,3-Dimethylphenyl)ethyl]-N-(prop-2-en-1-yl)-1H-imidazol-1-carboxamid, 2-({4-[1-(2,3-Dimethylphenyl)ethyl]-1H-imidazol-1-carbonyl}amino)ethylpropen-2-enoat, 2-({5-[1-(2,3-Dimethylphenyl)ethyl]-1H-imidazol-1-carbonyl}amino)ethylpropen-2-enoat, 2-({4-[1-(2,3-Dimethylphenyl)ethyl]-1H-imidazol-1-carbonyl}amino)ethylpropen-2-enoat, 2-({5-[1-(2,3-Dimethylphenyl)ethyl]-1H-imidazol-1-carbonyl}amino)ethylpropen-2-enoat, 3-(4-[1-(2,3-Dimethylphenyl)ethyl]-1H-imidazol-1-dimethylsilyl)propyl-2-methylprop-2-enoat und 3-(5-[1-(2,3-Dimethylphenyl)ethyl]-1H-imidazol-1-dimethylsilyl)propyl-2-methylprop-2-enoat.

8. Antifouling-Zusammensetzung, umfassend ein Polymer nach einem der Ansprüche 1 bis 7 und ein Lösungsmittel.

9. Zusammensetzung nach Anspruch 8, ferner umfassend freies Medetomidin oder ein Enantiomer, eine Base oder ein Salz davon, das/die nicht kovalent an eine Wiederholungseinheit oder ein Monomer gebunden ist.

10. Gegenstand umfassend eine Oberflächenbeschichtung, die ein Polymer nach einem der Ansprüche 1 bis 7 und/oder eine Antifouling-Zusammensetzung nach Anspruch 8 oder 9 auf mindestens einem Teil einer Oberfläche des Gegenstands umfasst, der dazu ausgelegt ist, in Wasser eingetaucht zu werden, um marines Biofouling der Oberfläche zu hemmen.

11. Verfahren zum Herstellen eines Medetomidinmonomers, wobei das Verfahren die Umsetzung eines polymerisierbaren Monomers, das eine elektrophile Stelle umfasst, mit Medetomidin oder einem Enantiomer, einer Base oder einem Salz davon umfasst, um Medetomidin oder das Enantiomer, die Base oder das Salz davon kovalent über eine hydrolysierbare Bindung an das Monomer zu binden, die zwischen der elektrophilen Stelle und einem Stickstoff am Imidazolring von Medetomidin oder dem Enantiomer, der Base oder dem Salz davon gebildet ist.

12. Verfahren nach Anspruch 11, ferner Folgendes umfassend:

Auflösen von Medetomidin oder des Enantiomers, der Base oder des Salzes davon in einem Lösungsmittel, um eine Medetomidinlösung zu bilden; und
 Zugabe des polymerisierbaren Monomers zur Medetomidinlösung.

13. Verfahren nach Anspruch 12, wobei

das Auflösen von Medetomidin oder des Enantiomers, der Base oder des Salzes davon das Auflösen von Medetomidin oder des Enantiomers, der Base oder des Salzes davon und von Diisopropylethylamin in Dichlor-

methan zur Bildung der Medetomidinlösung umfasst; und
das Zugabe des polymerisierbaren Monomers das Zugabe von Chlorameisensäureallylester zu der Medetomidinlösung umfasst; oder
das Auflösen von Medetomidin oder des Enantiomers, der Base oder des Salzes davon das Auflösen von
5 Medetomidin oder des Enantiomers, der Base oder des Salzes davon und optional von Pyridin in Dichlormethan zur Bildung der Medetomidinlösung umfasst; und
das Zugabe des polymerisierbaren Monomers das Zugabe von Allylisocyanat zu der Medetomidinlösung umfasst; oder
das Auflösen von Medetomidin oder des Enantiomers, der Base oder des Salzes davon das Auflösen von
10 Medetomidin oder des Enantiomers, der Base oder des Salzes davon und von Trimethylamin in Dichlormethan zur Bildung der Medetomidinlösung umfasst; und
das Zugabe des polymerisierbaren Monomers das Zugabe von 2-Propylsulfonylchlorid zu der Medetomidinlösung umfasst; oder
das Auflösen von Medetomidin oder des Enantiomers, der Base oder des Salzes davon das Auflösen von
15 Medetomidin oder des Enantiomers, der Base oder des Salzes davon und von *N,N*-Dimethyl-4-aminopyridin in Dichlormethan zur Bildung der Medetomidinlösung umfasst; und
das Zugabe des polymerisierbaren Monomers das Zugabe von Methacrylsäureanhydrid oder Methacryloylchlorid zu der Medetomidinlösung umfasst; oder
das Auflösen von Medetomidin oder des Enantiomers, der Base oder des Salzes davon das Auflösen von
20 Medetomidin oder des Enantiomers, der Base oder des Salzes davon in Dichlormethan zur Bildung der Medetomidinlösung umfasst; und
das Zugabe des polymerisierbaren Monomers das Zugabe von Isocyanatoethylmethacrylat zu der Medetomidinlösung umfasst; oder
das Auflösen von Medetomidin oder des Enantiomers, der Base oder des Salzes davon das Auflösen von
25 Medetomidin oder des Enantiomers, der Base oder des Salzes davon in Dichlormethan zur Bildung der Medetomidinlösung umfasst; und
das Zugabe des polymerisierbaren Monomers das Zugabe von Isocyanatoethylacrylat zu der Medetomidinlösung umfasst.

14. Verfahren zum Herstellen eines Antifouling-Polymers, wobei das Verfahren das Polymerisieren von Monomeren, die Medetomidin oder ein Enantiomer, eine Base oder ein Salz davon umfassen, das/die über eine hydrolysierbare Bindung kovalent an das Monomer gebunden ist, und gegebenenfalls von Monomeren, denen Medetomidin oder ein Enantiomer, eine Base oder ein Salz davon fehlt, umfasst, um ein Antifouling-Polymer zu bilden, das eine Vielzahl von Wiederholungseinheiten umfasst, die von den Monomeren abgeleitet ist, wobei mindestens ein Teil der Vielzahl von Wiederholungseinheiten Medetomidin oder das Enantiomer, die Base oder das Salz davon umfasst, das/die über eine hydrolysierbare Bindung kovalent an die Wiederholungseinheiten gebunden ist.

15. Verfahren zum Herstellen eines Antifouling-Polymers, wobei das Verfahren die kovalente Bindung von Medetomidin oder eines Enantiomers, einer Base oder eines Salzes davon an ein Polymer umfasst, das eine Vielzahl von Wiederholungseinheiten umfasst, sodass mindestens ein Teil der Vielzahl von Wiederholungseinheiten Medetomidin oder das Enantiomer, die Base oder das Salz davon umfasst, das/die über eine hydrolysierbare Bindung kovalent an die Wiederholungseinheiten gebunden ist.

Revendications

1. Polymère antisalissure comprenant une pluralité de motifs répétés, dans lequel au moins une partie de la pluralité de motifs répétés comprend la médétomidine, ou un énantiomère, une base ou un sel de celle-ci, lié(e) de manière covalente au motif répété par une liaison hydrolysable.


2. Polymère selon la revendication 1, dans lequel le polymère est :

un copolymère comprenant un premier type de motif répété comprenant la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, et le premier type de motif répété dépourvu de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci ;


un copolymère comprenant un premier type de motif répété comprenant la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, un second type différent de motif répété comprenant la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, et éventuellement le premier type de motif répété dépourvu de médétomidine, ou

de l'énantiomère, de la base ou du sel de celle-ci, et/ou éventuellement le second type différent de motif répété dépourvu de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci ; ou un copolymère comprenant un premier type de motif répété comprenant la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, un second type différent de motif répété dépourvu de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, et éventuellement le premier type de motif répété dépourvu de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci.

3. Polymère selon la revendication 2, dans lequel le polymère est un copolymère comprenant le premier type de motif répété comprenant la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, et le premier type de motif répété dépourvu de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci .
4. Polymère selon la revendication 1, dans lequel le polymère est un homopolymère de motif répété comprenant la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, de préférence l'homopolymère est choisi dans le groupe constitué d'un poly(méthacrylate de médétomidine), d'une poly(allylsulfonylmédétomidine), d'une poly(allylmédétomidine), d'un poly(acrylate de médétomidine) et d'une poly(silylmédétomidine).
5. Polymère selon l'une quelconque des revendications 1 à 4, dans lequel la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, est lié(e) de manière covalente au motif répété par la liaison hydrolysable entre un azote sur le cycle imidazole de la médétomidine, ou de l'énantiomère, de la base ou d'un sel de celle-ci, et le monomère.
6. Polymère selon l'une quelconque des revendications 1 à 5, dans lequel le motif répété comprenant la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, a une formule générale II ou III :




(II)



(III)

dans laquelle


R¹ est choisi dans le groupe constitué des formules IV à VI :



(IV)




(V)




(VI)

R² est choisi dans le groupe constitué des formules VII et VIII :




(VII)




(VIII)

n vaut 0 ou 1 ;


R^3 est choisi dans le groupe constitué des formules IX à XIV :



(IX)




(X)




(XI)


m vaut 0, 1, 2 ou 3 ;



(XII)



(XIII)



(XIV)

R est indépendamment H ou un alkyle, l'alkyle étant de préférence un alkyle en C1 à C6, et plus préférablement un alkyle en C1 à C4, tel qu'un méthyle ou un éthyle, de préférence un méthyle ; et

R^4 , R^5 et R^6 sont indépendamment un alcoxy, de préférence un alcoxy en C1 à C6, et plus préférablement un alcoxy en C1 à C4, tel qu'un méthoxy, un éthoxy ou un propoxy.

7. Polymère selon l'une quelconque des revendications 1 à 6, dans lequel le motif répété comprenant la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, est choisi dans le groupe constitué de la 1-{4-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazol-1-yl]-2-méthylprop-2-én-1-one, de la 1-{5-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazol-1-yl]-2-méthylprop-2-én-1-one, du 2-méthylprop-2-énoate de 2-({4-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazole-1-carbonyl}amino)éthyle, du 2-méthylprop-2-énoate de 2-({5-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazole-1-carbonyl}amino)éthyle, du 4-[1-(2,3-diméthylphényl)éthyl]-1-(prop-2-ène-1-sulfonyl)-1*H*-imidazole, du 5-[1-(2,3-diméthylphényl)éthyl]-1-(prop-2-ène-1-sulfonyl)-1*H*-imidazole, du 4-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazole-1-carboxylate de prop-2-én-1-yle, du 5-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazole-1-carboxylate de prop-2-én-1-yle, du 4-[1-(2,3-diméthylphényl)éthyl]-*N*-(prop-2-én-1-yl)-1*H*-imidazole-1-carboxamide, du 5-[1-(2,3-diméthylphényl)éthyl]-*N*-(prop-2-én-1-yl)-1*H*-imidazole-1-carboxamide, du prop-2-énoate de 2-({4-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazole-1-carbonyl}amino)éthyle, du prop-2-énoate de 2-({5-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazole-1-carbonyl}amino)éthyle, du prop-2-énoate de 2-({4-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazole-1-carbonyl}amino)éthyle, du prop-2-énoate de 2-({5-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazole-1-carbonyl}amino)éthyle, du 2-méthylprop-2-énoate de 3-(4-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazole-1-diméthylsilyl)propyle et du 2-méthylprop-2-énoate de 3-(5-[1-(2,3-diméthylphényl)éthyl]-1*H*-imidazole-1-diméthylsilyl)propyle.

8. Composition antisalissure comprenant un polymère selon l'une quelconque des revendications 1 à 7 et un solvant.

9. Composition selon la revendication 8, comprenant en outre de la médétomidine libre ou un énantiomère, une base ou un sel de celle-ci, lié(e) de manière non covalente à un quelconque motif répété ou un monomère.

10. Article comprenant un revêtement de surface comprenant un polymère selon l'une quelconque des revendications 1 à 7 et/ou une composition antisalissure selon la revendication 8 ou 9 sur au moins une partie d'une surface de l'article conçu pour être immergé dans l'eau pour inhiber la bio-salissure marine de la surface.

11. Procédé de production d'un monomère de médétomidine, le procédé comprenant le fait de faire réagir un monomère polymérisable comprenant un site électrophile avec la médétomidine, ou un énantiomère, une base ou un sel de celle-ci, pour lier de manière covalente la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, au monomère par une liaison hydrolysable formée entre le site électrophile et un azote sur le cycle imidazole de la médétomidine, ou d l'énantiomère, de la base ou du sel de celle-ci.

12. Procédé selon la revendication 11, comprenant en outre :

la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, dans un solvant pour former une solution de médétomidine ; et

l'ajout du monomère polymérisable à la solution de médétomidine.

13. Procédé selon la revendication 12, dans lequel

la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, comprend la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, et de diisopropyléthylamine dans du dichlorométhane pour former la solution de médétomidine ; et

l'ajout du monomère polymérisable comprend l'ajout de chloroformiate d'allyle à la solution de médétomidine ; ou la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, comprend la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, et éventuellement de pyridine dans du dichlorométhane pour former la solution de médétomidine ; et

l'ajout du monomère polymérisable comprend l'ajout d'isocyanate d'allyle à la solution de médétomidine ; ou la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, comprend la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, et de triméthylamine dans du dichlorométhane pour former la solution de médétomidine ; et

l'ajout du monomère polymérisable comprend l'ajout de chlorure de 2-propénylsulfonyl à la solution de médétomidine ; ou

la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, comprend la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, et de *N,N*-diméthyl-4-aminopyridine dans du dichlorométhane pour former la solution de médétomidine ; et

l'ajout du monomère polymérisable comprend l'ajout d'anhydride méthacrylique ou de chlorure de méthacryloyle à la solution de médétomidine ; ou

la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, comprend la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, dans du dichlorométhane pour former la solution de médétomidine ; et

l'ajout du monomère polymérisable comprend l'ajout de méthacrylate d'isocyanato-éthyle à la solution de médétomidine ; ou

la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, comprend la dissolution de médétomidine, ou de l'énantiomère, de la base ou du sel de celle-ci, dans du dichlorométhane pour former la solution de médétomidine ; et

l'ajout du monomère polymérisable comprend l'ajout d'acrylate d'isocyanato-éthyle à la solution de médétomidine.

14. Procédé de production d'un polymère antisalissure, le procédé comprenant la polymérisation de monomères comprenant la médétomidine, ou un énantiomère, une base ou un sel de celle-ci, lié(e) de manière covalente au monomère par une liaison hydrolysable et éventuellement de monomères dépourvus de médétomidine, ou d'un énantiomère, d'une base ou d'un sel de celle-ci, pour former un polymère antisalissure comprenant une pluralité de motifs répétés dérivés des monomères, dans lequel au moins une partie de la pluralité de motifs répétés comprend la médétomidine, ou l'énantiomère, la base ou le sel de celle-ci, lié(e) de manière covalente aux motifs répétés par une liaison hydrolysable.

15. Procédé de production d'un polymère antisalissure, le procédé comprend la liaison covalente de médétomidine, ou d'un énantiomère, d'une base ou d'un sel de celle-ci, à un polymère comprenant une pluralité de motifs répétés de sorte qu'au moins une partie de la pluralité de motifs répétés comprenne la médétomidine, ou l'énantiomère, la

base ou le sel de celle-ci, lié(e) de manière covalente aux motifs répétés par une liaison hydrolysable.

5

10

15

20

25

30

35

40

45

50

55




Fig. 1




Fig. 2






Fig. 3






Fig. 6A




Fig. 6B




Fig. 6C




Fig. 7A




Fig. 7B




Fig. 7C




Fig. 8






Fig. 9






Fig. 10






Fig. 11






Fig. 12






Fig. 13






Fig. 14






Fig. 15

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 7531581 B [0004]
- US 10239898 B [0005]
- CZ 30799 [0006]
- EP 3540022 A [0007]
- EP 3480267 A [0008]
- EP 3480268 A [0009]
- EP 2551309 A [0010]
- WO 2011070069 A [0030]
- WO 2013014428 A [0030]
- WO 2016120635 A [0030]
- US 20060201379 A [0034]
- WO 2012175469 A [0067]
- WO 2013182641 A [0067]

Non-patent literature cited in the description

- *Journal of pharmacology and experimental therapeutics*, 1991, vol. 259, 848-854 [0030]
- *European Journal of Pharmacology*, 1991, vol. 195, 193-199 [0030]
- *Analytica Chimica Acta*, 2001, vol. 435, 19-24 [0122]