




(86) Date de dépôt PCT/PCT Filing Date: 2015/03/12
(87) Date publication PCT/PCT Publication Date: 2015/09/17
(85) Entrée phase nationale/National Entry: 2016/09/12
(86) N° demande PCT/PCT Application No.: US 2015/020246
(87) N° publication PCT/PCT Publication No.: 2015/138771
(30) Priorité/Priority: 2014/03/12 (US61/951,930)

(51) Cl.Int./Int.Cl. *B01D 53/22* (2006.01),
B01D 69/12 (2006.01)
(71) Demandeur/Applicant:
LOCKHEED MARTIN CORPORATION, US
(72) Inventeurs/Inventors:
SINTON, STEVEN W., US;
BEDWORTH, PETER V., US;
MOLONEY, PADRAIG, US
(74) Agent: DEETH WILLIAMS WALL LLP

(54) Titre : MEMBRANES DE SEPARATION FORMEES A PARTIR DE GRAPHENE PERFORE
(54) Title: SEPARATION MEMBRANES FORMED FROM PERFORATED GRAPHENE



(57) **Abrégé/Abstract:**

Perforated graphene sheets can be used in forming separation membranes. Separation membranes of the present disclosure, which can be used in gas separation processes in some embodiments, can include one or more polymer layers and one or more layers of perforated graphene. Methods for separating a gas mixture can include contacting a gas mixture with the separation membranes, and transiting one or more of the gases through the perforated graphene so as to affect separation.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



WIPO | PCT



(10) International Publication Number

WO 2015/138771 A1

(43) International Publication Date
17 September 2015 (17.09.2015)

(51) International Patent Classification:

B01D 53/00 (2006.01) *B01D 69/00* (2006.01)
B01D 53/22 (2006.01)

(21) International Application Number:

PCT/US2015/020246

(22) International Filing Date:

12 March 2015 (12.03.2015)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/951,930 12 March 2014 (12.03.2014) US

(71) Applicant: **LOCKHEED MARTIN CORPORATION**
[US/US]; 6801 Rockledge Drive, Bethesda, Maryland
20817 (US).

(72) Inventors: **SINTON, Steven W.**; 21 Somerset Place, Palo
Alto, California 94301 (US). **BEDWORTH, Peter V.**;
17724 Comanche Trail, Los Gatos, California 95033 (US).
MOLONEY, Pdraig; 30 Union Park Street, Unit 305,
Boston, Massachusetts 02118 (US).


(74) Agents: **JONAS, Tamala R.** et al.; Lathrop & Gage LLP,
4845 Pearl East Circle, Suite 201, Boulder, Colorado
80301 (US).

(81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG,
MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM,
PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC,
SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, KM, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: SEPARATION MEMBRANES FORMED FROM PERFORATED GRAPHENE



(57) Abstract: Perforated graphene sheets can be used in forming separation membranes. Separation membranes of the present disclosure, which can be used in gas separation processes in some embodiments, can include one or more polymer layers and one or more layers of perforated graphene. Methods for separating a gas mixture can include contacting a gas mixture with the separation membranes, and transiting one or more of the gases through the perforated graphene so as to affect separation.

WO 2015/138771 A1

Published:

— *with international search report (Art. 21(3))*

SEPARATION MEMBRANES FORMED FROM PERFORATED GRAPHENE

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the benefit of priority under 35 U.S.C. § 119 of United States Provisional Application 61/951,930, filed March 12, 2014, which is hereby incorporated by reference in its entirety.

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

[0002] Not applicable.

10 **FIELD**

[0003] The present disclosure generally relates to separation processes, and, more specifically, to separation membranes containing graphene or other two dimensional materials and methods for use and fabrication thereof.

BACKGROUND

15 **[0004]** Gas species separation from mixtures represents an important industrial and economic process. In the natural gas production industry, for example, almost all raw (as-produced) natural gas is processed to remove various contaminants and non-valued gases before downstream utilization, such as introducing it as a product into a pipeline transportation system. For example, co-produced gases such as carbon dioxide and hydrogen sulfide, especially in combination with water, can heavily impact the value of as-produced
20 natural gas. Production of unconventional gas sources such as shale plays and coal beds is increasing and driving a need for more efficient and affordable processing systems at more remote sites and with higher contaminant gas level processing capabilities. Contaminants in other types of gases can also be problematic and can impact their valuation, as well as the applicability of various industrial processes. For example, CO₂ and contaminant capture
25 from industrial flue gas, hydrogen purification and recovery processes, syngas production, and fuel cells represent non-limiting areas that can benefit from gas separation technology.

[0005] Separation membranes are commonly used for gas separation processes in a

variety of industrial settings, including speciation of natural gas. Gas separation membranes are attractive for use in gas phase separation processes because they generally possess no or few moving parts, require low maintenance, exhibit low energy consumption, and possess exceptional reliability. However, many conventional membranes are not highly efficient, can be chemically unstable in certain instances, and do not compete well with bulk separation processes (non-membrane). For example, illustrative bulk carbon dioxide separation technologies can include cryogenic separation, pressure-temperature adsorption cycles, CO₂ capture with amines, and the like. CO₂ separation membranes, in contrast, can operate well at high CO₂ concentrations, but can be less effective at modest H₂S concentrations.

Nevertheless, with proper process design, membrane-based gas separation processes can be used to simplify overall process design and be more convenient for deployment in remote field locations.

[0006] Specialized polymer membranes have been developed for use in specific gas separation applications. Examples include cellulose acetate membranes for CO₂ separations in "sour gas" conditions, polyimide membranes, and polyamide membranes. Many different polymers are used in this regard, as different polymers have utility and affinity for use with different gas species, allowing certain gases to transit the membrane in preference to others. The transit mechanism can depend on specific interactions between gas and polymer molecules that affect gas dissolution and diffusion through the polymer. The polymer is generally chosen to enhance these interactions for the target gases and enhance the permeation rate of a desired gas over the permeation rate of an undesired gas. Generally, a membrane is considered to give an adequate separation of two gases from one another if the permeation ratio of the two gases is about 10:1 or above, although other permeation ratios can also be adequate depending on the intended application in which the gas will be used.

Although widely used, existing polymer membranes can display inadequate performance for certain gas mixtures or not be applicable to certain types of process conditions. For example, chemical stability of the polymer membrane under certain process conditions can represent a concern.

[0007] In view of the foregoing, improved techniques for gas separation, particularly using membrane technology, would be of considerable benefit in the art. The present disclosure satisfies this need and provides related advantages as well.

SUMMARY

[0008] The present disclosure describes separation membranes containing at least one layer of a polymer and at least one layer of a perforated two-dimensional material, particularly perforated graphene. Methods for preparing the separation membranes can include stacking one or more layers of polymer and one or more layers of the two-dimensional material upon one another. The two-dimensional material can be perforated before or after being stacked with the polymer layers. In specific embodiments, the two-dimensional material is a graphene-based material such as a graphene-based sheet. In an embodiment, the at least one layer of polymer exhibits a selected permeability for a first elected gas with respect to one or more other gases. In specific embodiments, the at least one layer of polymer is non-porous or dense. In specific embodiments, the at least one layer of polymer exhibits permeance to one or more gases via one or more solution diffusion processes.

[0009] Separation processes using the separation membranes described herein can be accomplished by contacting a gas mixture with the separation membrane. In an embodiment, the gas mixture comprises a first and a second gas. By perforating the two-dimensional material, such as graphene, with perforations or apertures that are of a sufficient size to allow increased transit of a desired gas through the membrane over that of one or more undesired gases, or vice versa, separation of the gas mixture can take place. Separation of two or more species in a mixture includes at least a change in the ratio(s) (weight or molar ratio) of the two or more species in the gas mixture after passage of the mixture through a perforated two-dimensional material or through the composite separation membranes herein. It will be appreciated that separation of a desired gas component from an undesired component can be achieved by retarding passage of the undesired species with respect to the desired species or by retarding passage of the desired species with respect to the undesired species. Separation processes herein may include multiple passages of a given gas mixture through a given separation membrane or passage of a gas mixture through multiple separation membranes.

[0010] In an aspect, the invention provides separation membranes comprising at least one dense polymeric membrane and at least one layer of a perforated two dimensional material. The dense polymer membrane can operate normally by solution-diffusion processes, giving some initial separation of gas species. The filter of perforated two

dimensional material (*i.e.*, perforated graphene layers) can block or limit passage of molecules larger than the holes in the two dimensional material, while at the same time permitting passage of smaller molecules. Thus, the composite membrane can separate gas species by two complementary mechanisms: solution-diffusion at the polymer (*i.e.*,
 5 molecule-polymer interaction) and molecule size sieving. In this regard, the two-dimensional sieve barrier can provide very high permeability contrast at a threshold molecular size, allowing high separation ratios based upon size to be realized (*e.g.*, CO₂ compared to methane). If the hole-size density in the graphene layer is sufficiently high, the graphene layer can convey very little added resistance to permeation of small molecules.
 10 Accordingly, the higher selectivity provided by the graphene layer can allow for a much thinner polymer membrane to be used, compared to solely polymer-containing membranes.

[0011] The disclosure provides a composite membrane for separation of a first gas from a second gas; said separation membrane comprising: at least one dense polymeric membrane permeable to said first gas and at least one layer of a perforated two-dimensional
 15 material wherein said composite membrane is arranged to provide preferential transport of said first gas relative to said second gas through said at least one dense polymer membrane and said at least one layer of said perforated two-dimensional material. In embodiments, at least one of or each of the dense polymeric membranes is independently characterized by a permeability to said first gas greater or equal to than 1 Barrer ($7.5 \times 10^{-11} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$),
 20 10 Barrer ($7.5 \times 10^{-10} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$) or 100 Barrer ($7.5 \times 10^{-9} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$). In embodiments, at least one of or each of the dense polymeric membranes is independently characterized by a permeability for said first gas is independent from 1 Barrer to 100,000 Barrer, from 10 Barrer to 100,000 Barrer or from 100 Barrer to 100,000 Barrer. In embodiments, the composite membrane is characterized by a net or overall permeability to said first gas greater
 25 or equal to than 1 Barrer ($7.5 \times 10^{-11} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$), 10 Barrer ($7.5 \times 10^{-10} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$) or 100 Barrer ($7.5 \times 10^{-9} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$). In embodiments, the net permeability of the composite membrane to said first gas is from 1 Barrer to 100,000 Barrer, from 10 Barrer to 100,000 Barrer or from 100 Barrer to 100,000 Barrer.

[0012] The separation selectivity or efficiency of the composite membrane may be
 30 taken as the ratio of the net permeability of the composite membrane to the first gas to the net permeability of the composite membrane to the second gas. In embodiments, the net separation selectivity of the composite membrane is greater than 10, greater than 2, greater

than 50 or greater than 100.

[0013] In an aspect, the disclosure provides a composite membrane comprising at least one dense polymeric membrane and at least one layer of said perforated two-dimensional material, wherein the at least one dense polymeric membrane and at least one layer of said perforated two-dimensional material are provided in physical contact with each other or separated by one or more intermediate structures provided in physical contact with said at least one dense polymeric membrane and said at least one layer of said perforated two-dimensional material. In an embodiment, said at least one dense polymeric membrane and said at least one layer of said perforated two-dimensional material are provided in a stacked multilayer geometry. In embodiments, said stacked multilayer geometry comprises 1 to 100 layers of dense polymeric membrane and 1 to 100 layers of said perforated two-dimensional material, 1 to 50 layers of said dense polymeric membrane and 1 to 50 layers of said perforated two-dimensional material, 1 to 25 layers of said dense polymeric membrane and 1 to 25 layers of said perforated two-dimensional material, 1 to 10 layers of said dense polymeric membrane and 1 to 10 layers of said perforated two-dimensional material or 1 to 5 layers of dense polymeric membrane and 1 to 5 layers of said perforated two-dimensional material. In an embodiment, said stacked multilayer geometry comprises at least one dense polymeric membrane positioned on an external surface of said composite membrane in physical contact with said first gas and said second gas. In an embodiment, each of said layers of said perforated two-dimensional material provided in said stacked multilayer geometry is independently positioned between first and second adjacent dense polymeric membranes. In an embodiment, said stacked multilayer geometry comprises a first dense polymeric membrane in physical contact with a first layer of said perforated two-dimensional material. In an embodiment, said stacked multilayer geometry further comprises a second dense polymeric membrane wherein said first layer of said perforated two-dimensional material is provided between, and in physical contact with, said first and second dense polymeric membranes. In an embodiment, said stacked multilayer geometry comprises a plurality of said dense polymeric membranes, wherein at least a portion of said dense polymeric membranes have a different chemical compositions, thicknesses or both. In an embodiment, said stacked multilayer geometry comprises a plurality of said layers of said perforated two-dimensional material, wherein at least a portion of said layers of said perforated two-dimensional material have a different chemical compositions, hole cross sectional dimensions, hole densities or any combination of these.

[0014] In an embodiment, each of said layers of a perforated two dimensional material independently provides separation of said first and second gases via a molecular sieving process. In an embodiment, each of said layers of perforated two-dimensional material is independently characterized by a ratio of a permeance for said first gas to a permeance for said second gas greater than or equal to 1000. In an embodiment, each of said layers of perforated two-dimensional material is independently characterized by a thickness selected from the range of 0.3 to 5 nm. In an embodiment, each of said layers of perforated two-dimensional material is independently characterized by a tensile strength greater than or equal to 50 MPa. In an embodiment, each of said layers of perforated two-dimensional material is independently characterized by a plurality of holes independently having cross sectional dimensions less than or equal to 15 angstroms, less than or equal to 10 angstroms, or less than or equal to 5 angstroms. In an embodiment, said plurality of holes independently have cross sectional dimensions selected over the range of 3 to 5 angstroms, 3 to 10 angstroms or 3 to 15 angstroms.

[0015] In an embodiment each of said layers of perforated two dimensional material independently comprises graphene, a graphene-based material, a transition metal dichalcogenide, molybdenum sulfide, α -boron nitride, silicene, germanene, or a combination thereof. In an embodiment, each of said layers of perforated two-dimensional material independently comprises a perforated graphene-based material. In an embodiment, said perforated graphene-based material comprises single-layer graphene or multi-layer graphene. In an embodiment, the perforated graphene-based material comprises 2 to 20 layers of graphene. In an embodiment, said perforated graphene-based material comprises at least 70% graphene. In an embodiment, said perforated graphene-based has a thickness selected from the range of 0.34 to 5 nm.

[0016] In an embodiment, the dense polymeric membrane is selected to provide a higher flux, permeance or permeability for one component of a feedstock mixture over another. In an embodiment, each of said dense polymeric membranes independently provides separation of said first gas and second gas via one or more solution diffusion processes. In an embodiment, each of said dense polymeric membranes is independently characterized by a ratio of the permeability for said first gas to the permeability for said second gas greater than or equal to 10. In an embodiment, each of the dense polymeric membranes is independently characterized by a porosity less than or equal to 1%.

[0017] In an embodiment, the dense polymeric membrane contacts the layer of two-dimensional material so that the primary gas transport occurs through the dense polymeric material and layer of two-dimensional material (rather than leakage from the membrane assembly at the interface between the layers). In an embodiment, the dense polymeric membrane is a homogeneous membrane. In embodiments, the thickness of each of the dense polymeric membranes is from less than or equal to 50 μ m, from 0.1 μ m to 50 μ m, from 0.1 μ m to 20 μ m, 1.0 μ m to 15 μ m, 0.25 μ m to 5 μ m, or 5 μ m to 10 μ m.

[0018] Dense polymeric membranes for gas permeation include, but are not limited to, In an embodiment, said each of said dense polymeric membranes independently comprises a fluorocarbon, hydrocarbon, polysilicone, polyimide (PI), cellulose acetate (CA), polysulfone (PSf), polyethersulfone (PES), and polycarbonate (PC) or any combination of these. Polysilicone may also be referred to as silicone rubber. In embodiment, the dense polymeric membrane is selected from the group consisting of polyimide or cellulose acetate. In an embodiment, each of said dense polymeric membranes independently comprises a material selected from the group consisting of Teflon[®] AF, Sylgard[®] and any combination of these.

[0019] In an embodiment, each of said dense polymeric membranes is capable of exposure to a pressure of 50 psi, 100 psi, 500 psi, 1000 psi or 1500 psi or 2000 psi without undergoing mechanical failure. In an embodiment, each of said dense polymeric membranes is independently characterized by a tensile strength greater than or equal to 20 MPa. In embodiments, each of said dense polymeric membranes is capable of exposure to temperatures up to 300 K, 400 K, 500 K or 600 K without undergoing chemical or physical degradation. In embodiment, each said each of said dense polymeric membranes is independently characterized by a glass transition temperature greater than or equal to 300 K, 400 K, 500 K or 600 K. In an embodiment, each of said dense polymeric membranes is resistant to chemical reaction with H₂O, CO₂, H₂S, a hydrocarbon having from 1 to 9 carbon atoms or any combination of these. The hydrocarbon may be an alkane, an alkene, or an alkyne. In an embodiment, the hydrocarbon has the formula C_nH_{2n+2}, C_nH_{2n}, or C_nH_{2n-2} where n is an integer from 1 to 9.

[0020] In an aspect, the disclosure provides a method for separating a first gas from a second gas; said method comprising the steps of:

providing a composite membrane comprising: at least one dense polymeric membrane permeable to said first gas and at least one layer of a perforated two-dimensional material; and

contacting an external surface of said composite membrane with said first gas and said second gas; wherein said composite membrane provides preferential transport of said first gas relative to said second gas through said at least one dense polymer membrane and said at least one layer of perforated two-dimensional material, thereby separating said first gas from said second gas

In embodiments, at least one of or each of the dense polymeric membranes is characterized by a permeability to said first gas greater or equal to than 1 Barrer ($7.5 \times 10^{-11} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$), 10 Barrer ($7.5 \times 10^{-10} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$) or 100 Barrer ($7.5 \times 10^{-9} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$). In embodiments, the permeability of at least one of or each of the dense polymeric membranes to said first gas is from 1 Barrer to 100,000 Barrer, from 10 Barrer to 100,000 Barrer or from 100 Barrer to 100,000 Barrer. In embodiments, the composite membrane is characterized by a net or overall permeability to said first gas greater or equal to than 1 Barrer ($7.5 \times 10^{-11} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$), 10 Barrer ($7.5 \times 10^{-10} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$) or 100 Barrer ($7.5 \times 10^{-9} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$). In embodiments, the net permeability of the composite membrane to said first gas is from 1 Barrer to 100,000 Barrer, from 10 Barrer to 100,000 Barrer or from 100 Barrer to 100,000 Barrer.

[0021] In an embodiment, the disclosure provides a method of processing a feedstock gas, an exhaust gas, a revitalization gas or a commercial chemical product. In embodiments, the method is a method of processing a product or a byproduct produced in chemical refining or bioenergy production, a method of N_2 purification or CO_2 purification, a method of capture or sequestering of CO_2 or a method of revitalizing air. In an embodiment, said method is carried out a pressure at said external surface selected over the range of 15 PSI to 2000 PSI. In an embodiment, said method is carried out a temperature at said external surface selected over the range of 200 K to 600 K.

[0022] In a further embodiment, a method of processing natural gas by separation of methane from non-methane components is provided. In an embodiment, methane is separated from CO_2 , H_2O , H_2S or any combination of these. In an embodiment, methane is said second gas and said first gas is selected from the group consisting of CO_2 , H_2O , H_2S or

any combination of these. In an embodiment, said processing is carried out at the source of said natural gas. In an embodiment, said natural gas is from a high-CO₂ gas field

[0023] The foregoing has outlined rather broadly the features of the present disclosure in order that the detailed description that follows can be better understood. Additional features and advantages of the disclosure will be described hereinafter. These and other advantages and features will become more apparent from the following description.

BRIEF DESCRIPTION OF THE DRAWINGS

[0024] For a more complete understanding of the present disclosure, and the advantages thereof, reference is now made to the following descriptions to be taken in conjunction with the accompanying drawings describing specific embodiments of the disclosure, wherein:

[0025] FIGURE 1 shows a schematic of an illustrative graphene-based gas separation membrane of the present disclosure and an exemplary method for its fabrication.

DETAILED DESCRIPTION

[0026] A variety of two-dimensional materials useful in the present invention are known in the art. In various embodiments, the two-dimensional material comprises graphene, molybdenum sulfide, or boron nitride. In an embodiment, the two-dimensional material is a graphene-based material. In more particular embodiments, the two-dimensional material is graphene. Graphene according to the embodiments of the present disclosure can include single-layer graphene, multi-layer graphene, or any combination thereof. Other nanomaterials having an extended two-dimensional molecular structure can also constitute the two-dimensional material in the various embodiments of the present disclosure. For example, molybdenum sulfide is a representative chalcogenide having a two-dimensional molecular structure, and other various chalcogenides can constitute the two-dimensional material in the embodiments of the present disclosure. Choice of a suitable two-dimensional material for a particular application can be determined by a number of factors, including the chemical and physical environment into which the graphene or other two-dimensional material is to be terminally deployed.

[0027] In an embodiment, the two dimensional material useful in membranes herein

is a sheet of graphene-based material. Graphene-based materials include, but are not limited to, single layer graphene, multilayer graphene or interconnected single or multilayer graphene domains and combinations thereof. In an embodiment, graphene-based materials also include materials which have been formed by stacking single or multilayer graphene sheets. In

5 embodiments, multilayer graphene includes 2 to 20 layers, 2 to 10 layers or 2 to 5 layers. In embodiments, graphene is the dominant material in a graphene-based material. For example, a graphene-based material comprises at least 30% graphene, or at least 40% graphene, or at least 50% graphene, or at least 60% graphene, or at least 70% graphene, or at least 80% graphene, or at least 90% graphene, or at least 95% graphene. In embodiments, a graphene-

10 based material comprises a range of graphene selected from 30% to 95%, or from 40% to 80% from 50% to 70%, from 60% to 95% or from 75% to 100%.

[0028] As used herein, a “domain” refers to a region of a material where atoms are uniformly ordered into a crystal lattice. A domain is uniform within its boundaries, but

15 different from a neighboring region. For example, a single crystalline material has a single domain of ordered atoms. In an embodiment, at least some of the graphene domains are nanocrystals, having a domain size from 1 to 100 nm or 10-100 nm. In an embodiment, at least some of the graphene domains have a domain size greater than 100 nm to 1 micron, or from 200 nm to 800 nm, or from 300 nm to 500 nm. “Grain boundaries” formed by

20 crystallographic defects at edges of each domain differentiate between neighboring crystal lattices. In some embodiments, a first crystal lattice may be rotated relative to a second crystal lattice, by rotation about an axis perpendicular to the plane of a sheet, such that the two lattices differ in “crystal lattice orientation”.

25 **[0029]** In an embodiment, the sheet of graphene-based material comprises a sheet of single or multilayer graphene or a combination thereof. In an embodiment, the sheet of graphene-based material is a sheet of single or multilayer graphene or a combination thereof. In another embodiment, the sheet of graphene-based material is a sheet comprising a plurality of interconnected single or multilayer graphene domains. In an embodiment, the

30 interconnected domains are covalently bonded together to form the sheet. When the domains in a sheet differ in crystal lattice orientation, the sheet is polycrystalline.

[0030] In embodiments, the thickness of the sheet of graphene-based material is from

0.34 to 10 nm, from 0.34 to 5 nm, or from 0.34 to 3 nm. In an embodiment, a sheet of graphene-based material comprises intrinsic defects. Intrinsic defects are those resulting from preparation of the graphene-based material in contrast to perforations which are selectively introduced into a sheet of graphene-based material or a sheet of graphene. Such
 5 intrinsic defects include, but are not limited to, lattice anomalies, pores, tears, cracks or wrinkles. Lattice anomalies can include, but are not limited to, carbon rings with other than 6 members (e.g. 5, 7 or 9 membered rings), vacancies, interstitial defects (including incorporation of non-carbon atoms in the lattice), and grain boundaries.

10 **[0031]** In an embodiment, membrane comprising the sheet of graphene-based material further comprises non-graphenic carbon-based material located on the surface of the sheet of graphene-based material. In an embodiment, the non-graphenic carbon-based material does not possess long range order and may be classified as amorphous. In
 15 embodiments, the non-graphenic carbon-based material further comprises elements other than carbon and/or hydrocarbons. Non-carbon elements which may be incorporated in the non-graphenic carbon include, but are not limited to, hydrogen, oxygen, silicon, copper and iron. In embodiments, the non-graphenic carbon-based material comprises hydrocarbons. In
 20 embodiments, carbon is the dominant material in non-graphenic carbon-based material. For example, a non-graphenic carbon-based material comprises at least 30% carbon, or at least 40% carbon, or at least 50% carbon, or at least 60% carbon, or at least 70% carbon, or at least 80% carbon, or at least 90% carbon, or at least 95% carbon. In embodiments, a non-graphenic carbon-based material comprises a range of carbon selected from 30% to 95%, or from 40% to 80%, or from 50% to 70%.

[0032] Two-dimensional materials in which pores are intentionally created are
 25 referred to herein as "perforated", such as "perforated graphene-based materials", "perforated two-dimensional materials" or "perforated graphene." Two-dimensional materials are, most generally, those which have atomically thin thickness from single-layer sub-nanometer thickness to a few nanometers and which generally have a high surface area. Two-dimensional materials include metal chalcogenides (e.g., transition metal dichalcogenides),
 30 transition metal oxides, hexagonal boron nitride, graphene, silicone and germanene (see: Xu et al. (2013) "Graphene-like Two-Dimensional Materials) Chemical Reviews 113:3766-3798).

[0033] Two-dimensional materials include graphene, a graphene-based material, a transition metal dichalcogenide, molybdenum sulfide, α -boron nitride, silicene, germanene, or a combination thereof. Other nanomaterials having an extended two-dimensional, planar molecular structure can also constitute the two-dimensional material in the various

5 embodiments of the present disclosure. For example, molybdenum sulfide is a representative chalcogenide having a two-dimensional molecular structure, and other various chalcogenides can constitute the two-dimensional material in embodiments of the present disclosure. In another example, two-dimensional boron nitride can constitute the two-dimensional material in an embodiment of the invention. Choice of a suitable two-dimensional material for a

10 particular application can be determined by a number of factors, including the chemical and physical environment into which the graphene, graphene-based or other two-dimensional material is to be deployed.

[0034] The technique used for forming the two-dimensional material, graphene or

15 graphene-based material in the embodiments described herein is not believed to be particularly limited. For example, in some embodiments CVD graphene or graphene-based material can be used. In various embodiments, the CVD graphene or graphene-based material can be liberated from its growth substrate (e.g., Cu) and transferred to a polymer backing. Likewise, the techniques for introducing perforations to the graphene or graphene-

20 based material are also not believed to be particularly limited, other than being chosen to produce perforations within a desired size range. Perforations are sized to provide desired selective permeability of a species (atom or molecule) for a given gas separation application. Selective permeability relates to the propensity of a porous material or a perforated two-dimensional material to allow passage (or transport) of one or more species more readily or

25 faster than other species. Selective permeability allows separation of species which exhibit different passage or transport rates. In two-dimensional materials selective permeability correlates to the dimension or size (e.g., diameter) of apertures and the relative effective size of the species. Selective permeability of the perforations in two-dimensional materials such as graphene-based materials can also depend on functionalization of perforations (if any) and

30 the specific species that are to be separated. Selective permeability of gases can also depend upon adsorption of a gas species on the filtration material, e.g., graphene. Adsorption at least in part can increase the local concentration of the gas species at the surface of the filtration material enhancing the rate of passage through the apertures. Separation of two or more

species in a mixture includes a change in the ratio(s) (weight or molar ratio) of the two or more species in the mixture after passage of the mixture through a perforated two-dimensional material.

5 **[0035]** For example in applications for separation of gases, permeance is correlated with the size of a gas atom or molecule, for example as in kinetic diameters [see Marreucci et al. (2006) “Transport of gases and Vapors in Glass and Rubbery Polymers” in Materials Science of Membranes for Gas and Vapor Separation. (Eds. Yu et al.) John Wiley & Sons (New York).

10

[0036] The present disclosure is also directed, in part, to perforated graphene, perforated graphene-based materials and other perforated two-dimensional materials containing a plurality of apertures (or holes) ranging from about 3 to 15 angstroms in size. In a further embodiment, the hole size ranges from 3 to 10 angstroms or from 3 to 6
15 angstroms in size. The present disclosure is further directed, in part, to perforated graphene, perforated graphene-based materials and other perforated two-dimensional materials containing a plurality of holes ranging from about 3 to 15 angstrom in size and having a narrow size distribution, including but not limited to a 1-10% deviation in size or a 1-20% deviation in size. In an embodiment, the characteristic dimension of the holes is from about 3
20 to 15 angstroms in size. For circular holes, the characteristic dimension is the diameter of the hole. In embodiments relevant to non-circular pores, the characteristic dimension can be taken as the largest distance spanning the hole, the smallest distance spanning the hole, the average of the largest and smallest distance spanning the hole, or an equivalent diameter based on the in-plane area of the pore. As used herein, perforated graphene-based materials
25 include materials in which non-carbon atoms have been incorporated at the edges of the pores.

[0037] The present disclosure is directed, in part, to methods for conducting gas separation using perforated graphene or another two dimensional material. The present
30 disclosure is also directed, in part, to separation membranes formed from graphene or another two dimensional material. The present disclosure is also directed, in part, to methods for fabricating a separation membrane containing graphene or another two dimensional material.

[0038] Graphene has garnered widespread interest for use in a number of applications due to its favorable mechanical, thermal and electronic properties. Graphene represents an atomically thin layer of carbon in which the carbon atoms reside as closely spaced atoms at regular lattice positions. The regular lattice positions can have a plurality of defects present therein, which can occur natively or be intentionally introduced to the graphene basal plane. Such defects will also be equivalently referred to herein as "apertures," "perforations," or "holes." The term "perforated graphene" will be used herein to denote a graphene sheet with defects in its basal plane, regardless of whether the defects are natively present or intentionally produced. Aside from such apertures, graphene and other two-dimensional materials can represent an impermeable layer to many substances. Therefore, if they can be sized properly, the apertures in the impermeable layer can be useful for only allowing substances meeting certain size criteria through the impermeable layer.

[0039] In an embodiment, a dense polymeric membrane is substantially nonporous. In an embodiment, gas transport through a nonporous membrane occurs at least in part through a solution-diffusion mechanism. The present inventors recognized that the performance of polymer membranes could be improved by inserting a molecular sieve barrier into the polymer, specifically a molecular sieve barrier formed from graphene or a like two-dimensional material. In particular, the inventors recognized that perforated graphene could be used in a gas separation membrane to provide improved gas separation properties. Perforated graphene can be produced by any suitable technique, such as disclosed in commonly owned United States Patent Application Publication 2012/0048804, which is incorporated herein by reference in its entirety. In this regard, the extreme thinness of graphene reflects that molecular transport across the membrane can involve the least possible driving energy, and there are not believed to be distinct "dissolution" and "evaporation" steps involved during transport across its atomic lattice.

[0040] The use of graphene in gas separation processes can allow very selective separation processes to take place with various gases. For example, use of graphene in separating a mixture of CO₂ and methane can result in a selectivity ratio of about 10,000:1. By carefully choosing the perforation size within the graphene basal plane, graphene can allow complex gas mixtures to be separated that are not able to be efficiently handled using existing processes.

[0041] In addition to the foregoing benefits, permeation rates across the graphene can be "tuned" via specialized chemical functionalization of the graphene, such as along its edges, thereby providing an additional means of designing membranes for specific separation applications. Moreover, because the membranes described herein represent a layered
5 structure with atomically thin layers of graphene embedded therein, the mass and footprint of the present membranes are not significantly different than existing polymeric membranes, while still achieving improved gas separation performance.

[0042] Further to the above, graphene-containing gas separation membranes can further offer reduced pressure sensitivity requirements, improved chemical inertness, and the
10 opportunity to functionalize the surface of the graphene. Functionalization, in particular, can be used to tailor the graphene's performance during various separation operations.

[0043] In various embodiments, the gas separation membranes described herein can include one or more layers of a polymer and one or more layers of perforated graphene. Polymers suitable for use in the gas separation membranes can include those that are used in
15 conventional gas separation membranes. The perforated graphene can be produced by any technique, known or presently unknown, used for introducing a plurality of holes in graphene. Suitable techniques can include plasma treatment, ion or other particle beams, chemical modifications, and the like. The holes in the graphene can be sized such that they render the graphene impermeable to gases that are larger than the hole size. In various
20 embodiments, the perforations can range between about 0.2 nm to about 15 nm in size, from 3 to 15 angstroms in size, from 3 to 10 angstroms in size or from 3 to 6 angstroms in size.

[0044] Benefits that can be conveyed by the polymer in the gas separation membranes can include support of the graphene and conveyance of some gas separation properties in their own right. In illustrative embodiments, the polymer can include a fluorocarbon
25 polymer, such as polytetrafluoroethylene, or a silicone polymer. In addition, the polymer can provide good tensile strength and good tensile elongation properties. Moreover, some polymers can be flexible as thin layers and exhibit high glass transition temperatures. All of these properties can be complementary to the graphene and its properties and support its combination therewith in forming a gas separation membrane.

[0045] Benefits that can be conveyed by the graphene in the gas separation
30 membranes can include extreme molecular separation capabilities at high permeability. The

extreme thinness of graphene (*e.g.*, 0.3-3 nm) can enhance these features. Moreover, graphene exhibits high tensile strength (~ 106 GPa), excellent chemical stability, and thermal stability above 400°C . Again, the graphene properties can well complement those of the polymer in forming a gas separation membrane.

5 [0046] Several parameters are known in the art to characterize transport through membranes. As used herein, the flux (J_i) refers to the number of moles, volume or mass of a specified component i passing per unit time through a unit of membrane surface area normal to the thickness direction (SI Units: $\text{m}^3 \text{ m}^{-2} \text{ s}^{-1}$). As used herein, the permeance or pressure normalized flux refers to the transport flux per unit transmembrane driving force (SI Units: $\text{m}^3 \text{ m}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$). As used herein, the permeability refers to the transport flux per unit transmembrane driving force per unit membrane thickness ($P_i = J_i / \text{transmembrane driving force of component } i$ SI Units: $\text{m}^3 \text{ m m}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$). Other units for permeability include the Barrer, defined as $1 \text{ Barrer} = 10^{-10} \text{ cm}^3 \text{ cm cm}^{-2} \text{ s}^{-1} \text{ cmHg}^{-1}$, which is equal to $7.5 \times 10^{-11} \text{ cm}^3 \text{ cm cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$. Techniques for measuring these parameters for conventional membranes are known to those skilled in the art.

[0047] FIGURE 1 shows a schematic of an illustrative graphene-based gas separation membrane of the present disclosure and an exemplary method for its fabrication. As shown, the graphene layer (10) is made on a layer of copper (50). A polymer layer (20) is then spun on the graphene layer (10) and annealed. A stamp (60) is applied to the polymer layer before the copper is removed through etching. The graphene layer is perforated and then transferred to a substrate (80). The stamp is then removed, producing the polymer and graphene layered upon one another on a substrate. Although FIGURE 1 shows perforation of the graphene with Xe ions, other perforation processes can be used. Moreover, the graphene can be perforated before or after being layered with the polymer.

25 [0048] Referring still to FIGURE 1, a simple molding process can be used to embed large areas of graphene into polymer matrices, such as an exemplary siloxane (PDMS) rubber matrix. The rubber matrix can mechanically support and protect the graphene, while the graphene layer lends new separation capabilities to the composite membrane, as described above. Substantially impermeable membranes are also possible by embedding un-perforated graphene layers in a polymer stack.

[0049] The bulk polymer membrane can operate normally by solution-diffusion

processes, giving some separation of gas species. The embedded graphene sieve filter (*i.e.*, perforated graphene layers) can block or inhibit diffusion of molecules larger than the holes in the graphene, while at the same time permitting diffusion of smaller molecules. Thus, the composite membrane can separate gas species by two complementary mechanisms: solution-diffusion at the polymer (*i.e.*, molecule–polymer interaction) and molecule size sieving. In this regard, the two-dimensional sieve barrier can provide very high permeability contrast at a threshold molecular size, allowing high separation ratios based upon size to be realized (*e.g.*, CO₂ compared to methane). If the hole-size density in the graphene layer is sufficiently high, the graphene layer can convey very little added resistance to permeation of small molecules. Accordingly, the higher selectivity provided by the graphene layer can allow for a much thinner polymer membrane to be used, compared to solely polymer-containing membranes.

[0050] Due to the complementary solution-diffusion separation provided by the polymer, enhanced separation capabilities can be further realized. For example, when separating H₂S from methane, H₂S separation can take place in a silicone-rubber polymer (silicone-rubber has high affinity for separating H₂S) even if the graphene layer doesn't separate these species efficiently. With a proper selection of polymer type, polymer thickness, graphene hole size, graphene hole density, and graphene hole functionalization, composite membranes of this type can be designed that are capable of high selectivity across a wide range of molecular types while preserving or even enhancing overall separation efficiency (in terms of flux of separating species passing therethrough).

[0051] A membrane that can simultaneously handle both high CO₂ and H₂S gas concentrations would extend the range of applications for membrane separations in natural gas processing. If such a membrane could simultaneously remove these gases from natural gas in a single process step, it would eliminate the need for separate cleaning processes for these contaminants, thereby reducing overall process costs and complexity. In this regard, various gas separation membranes described herein can be used in separating natural gas from various contaminant gases therein. The methods can include contacting as-produced or partially purified natural gas with the described separation membranes. Other gas mixtures can be purified in a like manner by appropriately sizing the holes in the graphene layer.

[0052] Other new functionalities are also possible by the foregoing composite membrane approach. For example, graphene is electrically conductive and can be built into a multi-layer composite stack with graphene layers separated by dielectric layers and

electrically connected to a voltage source to enable capacitive charging between layers. Such an arrangement can be used to electrophoretically or dielectrophoretically control the movement of charged or polar particles between charged graphene electrode layers. If the graphene layers are perforated, the motion of molecules entering thorough graphene pores
5 can be controlled between graphene layers by application of an appropriate voltage waveform to the graphene layers. Thus, molecular transport between graphene layers can be controllably retarded or enhanced in accordance with these embodiments. Such an arrangement can effectively represent a switchable membrane "gate" through which transport can be reduced or enhanced at will. Other versions are also possible for the case of
10 uncharged or non-polar particles or very small particles (molecules). For example, electrical heating of embedded graphene layers can be used to force interlayer material phase changes (for example from a glassy state to liquid or back), thereby providing further control options over molecular transport between layers.

[0053] In addition to the foregoing uses in gas separation described hereinabove, it is
15 to be recognized that the membranes described herein can also be used in a variety of other applications. Illustrative processes can include, for example, reverse osmosis filters, integrated circuits, flat panel displays, electrodes, flexible solar cells, desalination, and other molecular filtration processes, both in the gas and liquid phases.

[0054] Although the disclosure has been described with reference to the disclosed
20 embodiments, one having ordinary skill in the art will readily appreciate that these are only illustrative of the disclosure. It should be understood that various modifications can be made without departing from the spirit of the disclosure. The disclosure can be modified to incorporate any number of variations, alterations, substitutions or equivalent arrangements not heretofore described, but which are commensurate with the spirit and scope of the disclosure.
25 Additionally, while various embodiments of the disclosure have been described, it is to be understood that aspects of the disclosure may include only some of the described embodiments. Accordingly, the disclosure is not to be seen as limited by the foregoing description.

[0055] Every formulation or combination of components described or exemplified
can be used to practice the invention, unless otherwise stated. Specific names of compounds
30 are intended to be exemplary, as it is known that one of ordinary skill in the art can name the same compounds differently. When a compound is described herein such that a particular

isomer or enantiomer of the compound is not specified, for example, in a formula or in a chemical name, that description is intended to include each isomers and enantiomer of the compound described individual or in any combination. One of ordinary skill in the art will appreciate that methods, device elements, starting materials and synthetic methods other than those specifically exemplified can be employed in the practice of the invention without resort to undue experimentation. All art-known functional equivalents, of any such methods, device elements, starting materials and synthetic methods are intended to be included in this invention. Whenever a range is given in the specification, for example, a temperature range, a time range, or a composition range, all intermediate ranges and subranges, as well as all individual values included in the ranges given are intended to be included in the disclosure. When a Markush group or other grouping is used herein, all individual members of the group and all combinations and subcombinations possible of the group are intended to be individually included in the disclosure.

[0056] As used herein, “comprising” is synonymous with "including," "containing," or "characterized by," and is inclusive or open-ended and does not exclude additional, unrecited elements or method steps. As used herein, "consisting of" excludes any element, step, or ingredient not specified in the claim element. As used herein, "consisting essentially of" does not exclude materials or steps that do not materially affect the basic and novel characteristics of the claim. Any recitation herein of the term “comprising”, particularly in a description of components of a composition or in a description of elements of a device, is understood to encompass those compositions and methods consisting essentially of and consisting of the recited components or elements. The invention illustratively described herein suitably may be practiced in the absence of any element or elements, limitation or limitations which is not specifically disclosed herein.

[0057] The terms and expressions which have been employed are used as terms of description and not of limitation, and there is no intention in the use of such terms and expressions of excluding any equivalents of the features shown and described or portions thereof, but it is recognized that various modifications are possible within the scope of the invention claimed. Thus, it should be understood that although the present invention has been specifically disclosed by preferred embodiments and optional features, modification and variation of the concepts herein disclosed may be resorted to by those skilled in the art, and that such modifications and variations are considered to be within the scope of this invention

as defined by the appended claims.

[0058] In general the terms and phrases used herein have their art-recognized meaning, which can be found by reference to standard texts, journal references and contexts known to those skilled in the art. The preceding definitions are provided to clarify their
5 specific use in the context of the invention.

[0059] All references throughout this application, for example patent documents including issued or granted patents or equivalents; patent application publications; and non-patent literature documents or other source material; are hereby incorporated by reference herein in their entireties, as though individually incorporated by reference, to the extent each
10 reference is at least partially not inconsistent with the disclosure in this application (for example, a reference that is partially inconsistent is incorporated by reference except for the partially inconsistent portion of the reference).

[0060] All patents and publications mentioned in the specification are indicative of the levels of skill of those skilled in the art to which the invention pertains. References cited
15 herein are incorporated by reference herein in their entirety to indicate the state of the art, in some cases as of their filing date, and it is intended that this information can be employed herein, if needed, to exclude (for example, to disclaim) specific embodiments that are in the prior art. For example, when a compound is claimed, it should be understood that compounds known in the prior art, including certain compounds disclosed in the references
20 disclosed herein (particularly in referenced patent documents), are not intended to be included in the claim.

CLAIMS

We claim:

1. A composite membrane for separation of a first gas from a second gas; said separation membrane comprising:
 - 5 at least one dense polymeric membrane characterized by a permeability for said first gas greater or equal to than $7.5 \times 10^{-11} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$ and
 - at least one layer of a perforated two-dimensional material;

wherein said composite membrane is arranged to provide preferential transport of said first gas relative to said second gas through said at least one dense polymer membrane and said at least one layer of said perforated two-dimensional material.
- 10 2. The composite membrane of claim 1 providing a net permeability of said first gas greater than or equal to $7.5 \times 10^{-10} \text{ m}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$.
3. The composite membrane of any one of claims 1-2 providing a net gas separation selectivity for said first gas relative to said second gas greater than or equal to 100.
- 15 4. The composite membrane of any one of claims 1-3, wherein each of said dense polymeric membranes independently provides separation of said first gas and second gas via one or more solution diffusion processes.
5. The composite membrane of any one of claims 1-4, wherein each of said dense polymeric membranes is independently characterized by a permeability for said first gas selected over the range of $7.5 \times 10^{-10} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$ to $7.5 \times 10^{-6} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$.

20
6. The composite membrane of any one of claims 1-5, wherein each of said dense polymeric membranes is independently characterized by a ratio of a permeability for said first gas to a permeability for said second gas greater than or equal to 10.
- 25 7. The composite membrane of any one of claims 1-6, wherein each of said dense polymeric membranes is independently characterized by a porosity less than or equal to 1%.

8. The composite membrane of any one of claims 1-7, wherein each of said dense polymeric membranes is independently characterized by a tensile strength greater than or equal to 20 MPa.
9. The composite membrane of any one of claims 1-8, wherein each of said dense polymeric membranes is capable of exposure to a pressure of 500 psi without undergoing mechanical failure.
10. The composite membrane of any one of claims 1-9, wherein each of said dense polymeric membranes is capable of exposure to temperatures up to 300 K without undergoing chemical or physical degradation.
11. The composite membrane of any one of claims 1-10, wherein said each of said dense polymeric membranes is independently characterized by a glass transition temperature greater than or equal to 300 K.
12. The composite membrane of any one of claims 1-11, wherein said each of said dense polymeric membranes is resistant to chemical reaction with H₂O, CO₂, H₂S, a hydrocarbon having from 1 to 9 carbon atoms, or any combination of these.
13. The composite membrane of any one of claims 1-12, wherein said each of said dense polymeric membranes independently has a thickness less than or equal to 50 microns.
14. The composite membrane of any one of claims 1-13, wherein said each of said dense polymeric membranes independently has a thickness selected over the range of 0.1 to 50 microns.
15. The composite membrane of any one of claims 1-14, wherein said each of said dense polymeric membranes independently comprises a fluorocarbon, hydrocarbon, polysilicone, polyimide, cellulose acetate, polysulfone, polyethersulfone, and polycarbonate or any combination of these.
16. The composite membrane of any one of claims 1-15, wherein said each of said dense polymeric membranes independently comprises a material selected from the group consisting of Teflon ® AF, Sylgard ® and any combination of these.
17. The composite membrane of any one of claims 1-16, wherein each of said layers of

perforated two dimensional material independently provides separation of said first and second gases via a molecular sieving process.

18. The composite membrane of any one of claims 1-17, wherein each of said layers of perforated two-dimensional material is independently characterized by a ratio of a permeability for said first gas to a permeability for said second gas greater than or equal to 1000.
19. The composite membrane of any one of claims 1-18, wherein each of said layers of perforated two-dimensional material is independently characterized by a thickness selected from the range of 0.3 to 5 nm.
20. The composite membrane of any one of claims 1-19, wherein each of said layers of perforated two-dimensional material is independently characterized by a tensile strength greater than or equal to 50 MPa.
21. The composite membrane of any one of claims 1-20, wherein each of said layers of perforated two-dimensional material is independently characterized by a plurality of holes independently having cross sectional dimensions less than or equal to 10 angstroms.
22. The composite membrane of claim 21, wherein said plurality of holes independently have cross sectional dimensions selected over the range of 3 to 5 angstroms.
23. The composite membrane of any one of claims 1-22, wherein each of said layers of perforated two-dimensional material independently comprises graphene, a graphene-based material, a transition metal dichalcogenide, molybdenum sulfide, α -boron nitride, silicene, germanene, or a combination thereof .
24. The composite membrane of any one of claims 1-23, wherein each of said layers of perforated two-dimensional material independently comprises a perforated graphene-based material.
25. The composite membrane of any one of claims 1- 24, wherein said perforated graphene-based material comprises single-layer graphene or multi-layer graphene.
26. The composite membrane of any one of claims 1-25, wherein said perforated

graphene-based material comprises 2 to 20 layers of graphene.

27. The composite membrane of any one of claims 1-26, wherein said perforated graphene-based material comprises at least 70% graphene.
28. The composite membrane of any one of claims 1-27, wherein said perforated
5 graphene-based has a thickness selected from the range of 0.34 to 5 nm.
29. The composite membrane of any one of claims 1-28, wherein at least one dense polymeric membrane and at least one layer of said perforated two-dimensional material are provided in physical contact with each other or separated by one or more intermediate structures provided in physical contact with said at least one dense
10 polymeric membrane and said at least one layer of said perforated two-dimensional material.
30. The composite membrane of any one of claims 1-29, wherein said at least one dense polymeric membrane and said at least one layer of said perforated two-dimensional material are provided in in a stacked multilayer geometry.
- 15 31. The composite membrane of any one of claims 1- 30, wherein said stacked multilayer geometry comprises 1 to 100 layers of said dense polymeric membrane and 1 to 100 layers of said perforated two-dimensional material.
32. The composite membrane of any one of claims 1-31, wherein said stacked multilayer geometry comprises at least one dense polymeric membrane positioned on an external
20 surface of said composite membrane in physical contact with said first gas and said second gas.
33. The composite membrane of any one of claims 1-32, wherein said each of said layers of said perforated two-dimensional material provided in said stacked multilayer geometry is independently positioned between first and second adjacent dense
25 polymeric membranes.
34. The composite membrane of any one of claims 1-33, wherein said stacked multilayer geometry comprises a first dense polymeric membrane in physical contact with a first layer of said perforated two-dimensional material.

35. The composite membrane of any one of claims 1-34, wherein said stacked multilayer geometry further comprises a second dense polymeric membrane wherein said first layer of said perforated two-dimensional material is provided between, and in physical contact with, said first and second dense polymeric membranes.
- 5 36. The composite membrane of any one of claims 1-35, wherein said stacked multilayer geometry comprises a plurality of said dense polymeric membranes, wherein at least a portion of said dense polymeric membranes have a different chemical compositions, thicknesses or both.
- 10 37. The composite membrane of any one of claims 1-36, wherein said stacked multilayer geometry comprises a plurality of said layers of said perforated two-dimensional material, wherein at least portion of said layers of said perforated two-dimensional material have a different chemical compositions, hole cross sectional dimensions, hole densities or any combination of these.
- 15 38. A method for separating a first gas from a second gas; said method comprising the steps of:
- providing a composite membrane comprising:
- at least one dense polymeric membrane characterize by a permeability for said first gas greater or equal to than $7.5 \times 10^{-11} \text{ cm}^3 \text{ cm}^{-2} \text{ s}^{-1} \text{ kPa}^{-1}$ and
- at least one layer of a perforated two-dimensional material;
- 20 contacting an external surface of said composite membrane with said first gas and said second gas; wherein said composite membrane provides preferential transport of said first gas relative to said second gas through said at least one dense polymer membrane and said at least one layer of perforated two-dimensional material, thereby separating said first gas from said second gas.
- 25 39. The method of claim 38, providing a method of processing a feedstock gas, an exhaust gas, a revitalization gas or a commercial chemical product.
40. The method of claim 38, providing a method of processing natural gas by separation of methane from non-methane components.

41. The method of claim 40, wherein methane is separated from CO₂, H₂O, H₂S or any combination of these.
42. The method of claim 40, wherein methane is said second gas and said first gas is selected from the group consisting of CO₂, H₂O, H₂S or any combination of these.
- 5 43. The method of any one of claims 40-42, wherein said processing is carried out at the source of said natural gas.
44. The method of any one of claims 40-43, wherein said natural gas is from a high-CO₂ gas field.
45. The method of claim 38, providing a method of processing a product or a byproduct
10 produced in chemical refining or bioenergy production.
46. The method of claim 38, providing a method of N₂ purification or CO₂ purification.
47. The method of claim 38, providing a method of capture or sequestering of CO₂.
48. The method of claim 38, providing a method of revitalizing air.
49. The method of any one of claims 38-48, wherein said method is carried out a pressure
15 at said external surface selected over the range of 15 PSI to 2000 PSI.
50. The method of any one of claims 38-49, wherein said method is carried out a temperature at said external surface selected over the range of 200 K to 600 K.

1/1

