



(11) (21) (C) **2,015,051**
(22) 1990/04/20
(43) 1990/10/21
(45) 2000/03/14

(72) Colombo, Edilberto, IT

(73) PRESIDENZA DEL CONSIGLIO DEI MINISTRI UFFICIO DEL
MINISTRO PER IL COORDINAMENTO DELLE INIZIATIVE PER
LA RICERCA SCIENTIFICA E TECNOLOGICA, IT

(51) Int.Cl.⁵ C10M 137/10

(30) 1989/04/21 (20 255 A/89) IT

(54) **LUBRIFIANTS RENFERMANT DES DITHIOPHOSPHATES
NON METALLIQUES**

(54) **LUBRICANT COMPOSITIONS CONTAINING NON-METALLIC
DITHIOPHOSPHATES**

(57) This invention relates to lubricant compositions containing both zinc 0,0'-dialkyldithiophosphates and ashless 0,0'-diaryldithiophosphates obtained by reacting an 0,0'-diaryldithiophosphoric acid with a diolefin. These lubricant compositions give improved anti-wear performance.



"LUBRICANT COMPOSITIONS CONTAINING NON-METALLIC
DITHIOPHOSPHATES"

Abstract

This invention relates to lubricant compositions containing both zinc 0,0'-dialkyldithiophosphates and ashless 0,0'-diaryldithiophosphates obtained by reacting
5 an 0,0'-diaryldithiophosphoric acid with a diolefin. These lubricant compositions give improved anti-wear performance.

LUBRICANT COMPOSITIONS CONTAINING NON-METALLIC
DITHIOPHOSPHATES

This invention relates to lubricant compositions
5 containing both zinc 0,0'-dialkyldithiophosphates and
ashless 0,0'-diaryldithiophosphates of high thermal
stability. These additives result in lubricant
compositions with very high anti-wear activity.

Zinc dialkyldithiophosphates are the most well know
10 anti-wear additives and are used universally not only
because of their activity but also because of their
flexibility. In this respect they are able to behave
simultaneously both as antioxidants and anticorrosives.

For some time there has however been a tendency to use
15 fluid lubricants in such a manner as to reduce fuel
consumption, eventhough a reduction in the thickness of
the oil film results.

Under severe lubrication conditions this thickness
reduction leads to an increase in the probability of
20 rupture of the protective oil film and consequently an
increase in wear. To ensure proper operation of the
lubricant system there is therefore a requirement for
additives with high anti-wear characteristics, a
requirement which the metallic dithio phosphates
25 generally used in an engine oil do not seem able to
satisfy, probably because of their relatively low
thermal stability.

This problem cannot be solved by increasing the amount of additive, and in fact this must be avoided because it would lead to interaction with the detergent system and would increase the ash content, resulting in undesirable
5 pre-ignition.

It has now been found that lubricant compositions containing both zinc 0,0'-dialkyldithiophosphates and ashless 0,0'-diaryldithiophosphates of high thermal stability provide the higher anti-wear performance
10 required from these types of more fluid lubricant.

The present invention therefore provides lubricant compositions containing from 0.5 to 1.5% of a zinc 0,0'-dialkyldithiophosphate and from 0.3 to 1% of an ashless 0,0'-diaryldithiophosphate obtained in a two-step
15 process consisting of:

A. reacting with P_2S_5 a phenol of formula $ArOH$, where Ar is a mono or polyalkylsubstituted phenyl in which the alkyl substituents contain from 4 to 24 carbon atoms and can be linear or branched, to give the
20 corresponding 0,0'-diaryldithiophosphoric acid
(ArO)₂PSSH;

B. adding the 0,0'-diaryldithiophosphoric acid obtained from the preceding step to a diene chosen from norbornadiene, cyclopentadiene and bicyclopentadiene.

25 The phenol used in the first step is preferably chosen from p-dodecylphenol and p-nonylphenol.

Step A consists of heating at least 4 moles of the phenol ArOH to a temperature of between 55 and 150°C and then adding 1 mole of P₂S₅ in small portions.

When the addition is complete the reaction mixture is
5 maintained at the same temperature until hydrogen sulphide evolution ceases, generally within one hour.

In step B the diaryldithiophosphoric acid obtained is reacted with a diene chosen from cyclopentadiene, bicyclopentadiene and norbornadiene. Specifically, the
10 reaction is conducted with equimolecular quantities if the diene is bicyclopentadiene and it is required to obtain the products deriving from adding the 0,0'-diaryldithiophosphoric acid to only one of the two double bonds present in the molecule. If the diene is
15 chosen from norbornadiene, cyclopentadiene and bicyclopentadiene and it is required to obtain the products deriving from adding the 0,0'-diaryldithiophosphoric acid to both the double bonds present in the molecule the molar quantity of 0,0'-
20 diaryldithiophosphoric acid used is at least double that of the diene.

The reaction can be conducted without solvent or in the presence of a solvent such as hexane, heptane, cyclohexane or toluene.

25 The chosen diene compound is added to the diaryldithiophosphoric acid in small portions to control the exothermic effect of the reaction in such a manner

as to maintain the temperature between 25 and 140°C according to the type of diene.

On termination of the addition the reaction can be completed, if necessary, by heating further for about 1
5 hour.

Specifically, the present invention provides lubricant formulations having the following composition:

- 1) from 55.0 to 65.0% of a mineral oil
- 2) from 8.0 to 12.0% of a polyolefin
- 10 3) from 8.0 to 12.0% of a carbonic or carboxyl ester
- 4) from 5.5 to 6.5% of an ethylene-propylene copolymer
- 5) from 5.5 to 6.5% of a polymethacrylate
- 6) from 3.5 to 4.5% of a polyisobutenylsuccinimide borate
- 15 7) from 2.0 to 3.0% of a neutral calcium and/or magnesium sulphonate
- 8) from 1.0 to 2.0% of a superbasic calcium and/or magnesium sulphonate
- 9) from 1.0 to 1.5% of a zinc dithiophosphate
- 20 10) from 0.2 to 0.4% of an aromatic amine
- 11) from 0.2 to 0.4% of a sterically hindered phenol
- 12) from 0.3 to 1.0% of an ashless diaryldithiophosphate obtained by reacting $(ArO)_2PSSH$ with a diene chosen from norbornadiene, cyclopentadiene and
25 bicyclopentadiene, under the conditions described heretofore.

These formulations were subjected to engine tests to evaluate their anti-wear properties in comparison with the results obtainable from the same mixture but without the additive. The OM616-KOMBITEST, M102E and HKL engine tests were used.

The first of these evaluates the wear at the cam-rocker arm and cylinder-piston contact surfaces. The CCMC specification defines the following values for this test:

10 average wear = 1.5 $\mu\text{m}/1000 \text{ km}$
max wear = 3.0 $\mu\text{m}/1000 \text{ km}$

where these values are measured on the cam.

The second test evaluates lubricant performance with regard both to controlling sludge formation and to evaluating the wear expressed as deformation of the cam profile.

The third test, the HKL test, evaluates the wear of the transmission contact surface under conditions which simulate engine operation under idling conditions. The wear is measured on the cam and rocker arm.

Specifically, the tests were implemented on a formulation containing 0.5% of an ashless diaryldithiophosphate obtained by reacting p-dodecylphenol with P_2S_5 and then reacting the 0,0'-di(p-dodecylphenyl)-dithiophosphoric acid thus obtained with norbornadiene. This formulation was compared with the

same formulation but without the addition of the ashless dithiophosphate.

The results obtained in the first test are as follows:

	reference formulation	formulation with (II) added
5 average wear $\mu\text{m}/1000 \text{ km}$	1.8	0.4
maximum wear $\mu\text{m}/1000 \text{ km}$	3.5	0.9

The following results were obtained in the second test:

	reference formulation	formulation with (II) added
10 sludge score	9	9.2
average wear μm	65	20
maximum wear μm	80	30

In the third test, the HKL, the extent of wear expressed
15 in $\mu\text{m}/100 \text{ hours}$ was as follows:

	reference formulation	formulation with (II) added
cam wear	29	22
rocker arm wear	4	2

20 All these tests prove the greater anti-wear efficiency of the lubricant compositions according to the present invention containing both zinc 0,0'-dialkyldithiophosphates and ashless 0,0'-diaryldithiophosphates.

25 EXAMPLE 1

88 g (0.4 moles) of p-nonylphenol are fed into a 4-neck flask and heated to about 120°C . 22.2 g (0.1 mole) of

P₂S₅ are then added in small portions over 3 hours. The mixture is then heated for a further one hour until the reaction is complete. 6.0 g of cyclopentadiene deriving from the thermal cracking of bicyclopentadiene at 140°C are then added to 100 g of the obtained acid (P = 5.3% total acid number TAN = 100 mg KOH/g) in such a manner as to control the exothermic effect of the reaction. On termination of the addition the reaction mixture is kept stirring for 1 hour at 50-70°C until the reaction is complete.

The product obtained (P = 5.0%) has a copper compatibility evaluated by the ASTM D130 test (3 hours, 121°C) of 1b and a thermal stability (by PDSC) of 318°C.

EXAMPLE 2

104.8 g of p-dodecylphenol are reacted with 22.2 g of P₂S₅ at 150°C for 3 hours. 100 g of the 0,0'-didodecylphenyl-dithio-phosphoric acid obtained (P = 5.0%, TAN = 74 mg KOH/g) are dissolved in 100 ml of toluene and treated with 6 g of 2,5-norbornadiene. The reaction is complete in 2 hours. The solvent is removed by distillation and the recrystallized product (P = 4.8%) has a copper compatibility evaluated by the ASTM D130 test (3 hours, 121°C) of 1b and a thermal stability (by PDSC) of 320°C.

CLAIMS

1. A lubricant composition with anti-wear activity containing from 0.5 to 1.5% of a zinc 0,0'-dialkyldithiophosphate and from 0.3 to 1.0% of an ashless 0,0'-diaryldithiophosphate obtained by a two-step process consisting of: A) reacting with P_2S_5 a phenol of formula $ArOH$, where Ar is a mono or polyalkylsubstituted phenyl in which the alkyl substituents contain from 4 to 24 carbon atoms and can be linear or branched, to give the corresponding 0,0'-diaryldithiophosphoric acid $(ArO)_2PSSH$, B) adding the 0,0'-diaryldithiophosphoric acid obtained from the preceding step to a diene chosen from norbornadiene, cyclopentadiene and bicyclopentadiene.
2. A lubricant composition as claimed in claim 1, containing:
- a) from 55.0 to 65.0% of mineral oil
 - b) from 8.0 to 12.0% of polyolefin
 - c) from 8.0 to 12.0% of carbonic or carboxyl ester
 - d) from 5.5 to 6.5% of ethylene-propylene copolymer
 - e) from 5.5 to 6.5% of polymethacrylate
 - f) from 3.5 to 4.5% of polyisobutenylsuccinimide borate
 - g) from 2.0 to 3.0% of neutral calcium and/or magnesium sulphonate
 - h) from 1.0 to 2.0% of superbasic calcium and/or magnesium sulphonate
 - i) from 1.0 to 1.5% of zinc dithiophosphate

- i) from 1.0 to 1.5% of zinc dithiophosphate
 - l) from 0.2 to 0.4% of aromatic amine
 - m) from 0.2 to 0.4% of sterically hindered phenol
 - n) from 0.3 to 1.0% of an ashless diaryldithiophosphate
- 5 obtained by a two-step process consisting of: A) reacting with P_2S_5 a phenol of formula $ArOH$, where Ar is a mono or polyalkylsubstituted phenyl in which the alkyl substituents contain from 4 to 24 carbon atoms and can be linear or branched, to give the
- 10 corresponding O,O' -diaryldithiophosphoric acid $(ArO)_2PSSH$, B) adding the O,O' -diaryldithiophosphoric acid obtained from the preceding step to a diene chosen from norbornadiene, cyclopentadiene and bicyclopentadiene.
- 15 3. A lubricant composition as claimed in claim 1, wherein in step A the molar ratio of phenol to P_2S_5 is at least 4 and in step B the molar ratio of O,O' -diaryldithiophosphoric acid to diene is at least stoichiometric.
- 20 4. A lubricant composition as claimed in claim 1, wherein the phenol of formula $ArOH$ used in step A is preferably p-nonylphenol or p-dodecylphenol.
5. A lubricant composition as claimed in claim 1, wherein the ashless dithiophosphate is obtained by
- 25 reacting p-dodecylphenol with P_2S_5 and then reacting the O,O' -di(p-dodecylphenyl)-dithiophosphoric acid obtained with norbornadiene.

6. A lubricant composition as claimed in claim 5, wherein the concentration of the ashless diaryldithiophosphate is 0.5%.