

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(10) International Publication Number

WO 2017/187233 A1

(43) International Publication Date
02 November 2017 (02.11.2017)

(51) International Patent Classification:

F16L 11/12 (2006.01)

(21) International Application Number:

PCT/IB2016/052435

(22) International Filing Date:

29 April 2016 (29.04.2016)

(25) Filing Language:

English

(26) Publication Language:

English

(71) Applicant: FITT S.P.A. [IT/IT]; Via Piave, 8, 36066 Sandrigo (IT).

(72) Inventors: MEZZALIRA, Alessandro; Via Guarriere, 24, 36066 Sandrigo (VI) (IT). VIGOLO, Valentino; Via Molinetto, 56, 36030 Caldognو (VI) (IT). BATTAGLIA, Luca; Via Romagna, 1, 36061 Bassano del Grappa (VI) (IT). PETRONILLI, Andrea; Via Zanella, 10, 35010 Carmignano di Brenta (PD) (IT). BUCCI, Marco; Via Terralba 3/f, 35030 Baone (PD) (IT). CEGALIN, Alessandro; Via Cimone 12, 36100 Vicenza (VI) (IT).

(74) Agent: AUTUORI, Angelo et al.; c/o Eureka IP Consulting, Via Monte Cengio, 32, 36100 Vicenza (VI) (IT).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN,

MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: ENLARGEABLE FLEXIBLE HOSE




FIG. 3

(57) Abstract: A flexible hose for transporting fluid, particularly a flexible garden hose for transporting water. The hose comprises: at least one inner layer (10) made of a first elastic polymeric material; at least one outer layer (20) made of a second elastic polymeric material; at least one textile reinforcement layer (30) interposed between said at least one inner layer (10) and at least one outer layer (20). The at least one inner layer (10) and the at least one outer layer (20) are reciprocally coupled to form a unitary tubular member (50) internally to which the at least one textile reinforcement layer (30) is embedded. The unitary tubular member (50) has an elasticity such to automatically enlarge upon the working pressure given by the liquid flowing therethrough to increase its original diameter and such to automatically recovery once the working pressure stops for assuming again the original diameter. The at least one textile reinforcement layer (30) is susceptible to move from a rest configuration that has when the working pressure stops to a working configuration that has when said unitary tubular member (50) enlarges upon the working pressure and vice-versa.

WO 2017/187233 A1

ENLARGEABLE FLEXIBLE HOSE**DESCRIPTION**Field of the invention

The present invention is generally applicable to the technical field of flexible hoses,

5 and particularly relates to a flexible hose, preferably an irrigation hose or garden hose for transporting water, which is enlargeable, i. e. susceptible to automatically enlarge upon the passage of the fluid inside it and to automatically retract when the pressure of the liquid stops.

Definitions

10 As used herein, with the expression "textile reinforcement layer" or derivative thereof is meant a layer consisting of at least one textile yarn arranged on a layer that supports it. The "textile reinforcement layer" is disposed on the supporting layer so as to leave free portions thereof, generally square-, rectangular- or rhomboid- shaped.

15 As used herein, with the expression "textile yarn" or derivative thereof includes an elongated thread-like member of any shape and made of any material, provided that the magnitude of the length is significantly prevailing over the other. For example, the textile yarn may be a polymer yarn, which may have a unitary structure or may in turn consist of the union of several elementary threads, or a textile band having rectangular section.

20 As used herein, with the expression "textile knitted layer" or "knitting" or derivative thereof is meant a layer consisting of at least two yarns or groups of yarns laying on the supporting layer and connected to each other to form a plurality of chain-like stitches or knit.

25 As used herein, with the expression "textile woven layer" or "weaving" or derivative thereof is meant a layer consisting of at least two yarns or groups of yarns laying on a supporting layer with opposite inclinations and connected to one another alternately to form a weave. In a weaving a yarn is interlaced with another yarn once above and then below the latter. Depending on the inclination, the weaving is also known as fabric.

30 As used herein, with the expression "textile knotted layer" or "knotting" or derivative thereof is meant a layer consisting of at least two yarns or groups of yarns laying on the supporting layer with opposite inclinations and interconnected to each other by means of one or more knots. In a knotting a yarn cannot slide with respect to another due to the

constraint imposed by the knots.

As used herein, with the expression "compatible materials" or derivative thereof materials are meant having chemical and/or physical compatibility to each other, that is materials which once coupled give rise to a junction adapted to support the transfer of tensile or shear stresses through the contact surface. Therefore, identical materials or in any case materials having the matrix with the same base have the maximum compatibility.

As used herein, with the expression "matrix" of a polymer or derivative thereof is meant a polymeric material capable of providing the molecular structure of the finished product.

As used herein, with the expression "providing" or derivative thereof is meant the preparation of an element of interest to a process step of interest, thus including any preventive treatment act for the optimum exploiting of the same step of interest, from the simple withdrawal and possible storage to pre-heat and/or chemical and/or physical treatments and the like.

As used herein, with the expression "film" or derivative thereof is meant a layer of polymeric material whose thickness is less than 0,5 mm.

State of the art

Hoses are known, especially fire hoses, which includes an outer jacket and an inner flexible tube.

The outer jacket is generally made of synthetic textile fibers and has a predetermined inner diameter, whereas the inner tube is made of rubber and is designed to enlarges upon working pressure imparted by the water flowing therethrough up to an outer diameter coinciding with the inner diameter of the jacket.

As a result, the latter defines the inner diameter of the whole hose when in use. On the other hand, when not in use, i.e. when no water flows through the hose, the inner tube collapse and became flat, so that the whole hose has a relatively low bulkiness so that it can be stored on a reel.

This kind of hose is difficult and cumbersome to manufacture, since the jacket and the inner tube have to be manufactured separately and subsequently assembled.

Moreover, this kind of hoses are to be used by specialized operators, and is heavy, bulky and difficult to handle.

Summary of the invention

Object of the present invention is to overcome at least partially the above drawbacks, by providing an enlargeable flexible hose of remarkable efficiency and relative cheapness.

Another object of the invention is to provide an enlargeable flexible hose which can 5 be manufactured in a simple and fast manner.

Another object of the invention is to provide an enlargeable flexible hose which can be manufactured automatically in line.

Another object of the invention is to provide an enlargeable flexible hose which is wieldy to use.

10 Another object of the invention is to provide an enlargeable flexible hose which has a relatively high burst pressure.

Another object of the invention is to provide an enlargeable flexible hose that has minimum bulkiness.

15 Another object of the invention is to provide an enlargeable flexible hose which is simple and practical to be stored.

Another object of the invention is to provide an enlargeable flexible hose that can be repaired in case of breakage.

Another object of the invention is to provide an enlargeable flexible hose that can be customized in length.

20 This and other objects are achieved by a flexible hose for transporting liquids, particularly an enlargeable irrigation hose or garden hose for the transport of water and by a hose assembly which includes such hose, according to which is herein described, shown and/or claimed.

25 The hose has a non-corrugated, non-coiled tubular structure, typical of the irrigation hoses or garden hoses. The polymeric layers may be tubular shaped.

An example of a corrugated hose is known from document US3028290, whereas an example of a coiled hose is known from document US4009734.

30 The flexible hose may comprise at least one inner layer of a first polymeric elastic material, at least an outer layer of a second polymeric elastic material and at least one textile reinforcement layer interposed therebetween.

The at least one inner layer and at least one outer layer may be joined together to

form a unitary tubular member that integrates, that is embed, the at least one textile layer.

To do this, the at least one outer layer and the at least one inner layer may be reciprocally joined in correspondence of the areas of the outer surface of the at least one inner layer not covered by the at least one textile reinforcement layer. In other words, the at 5 least one outer layer and the at least one inner layer may be reciprocally joined except at the regions occupied by the textile yarns of the at least one textile layer.

Suitably, the unitary tubular member may have an elasticity such as to automatically enlarge and possibly elongate under the pressure imparted by the working fluid that flows therethrough to increase its original diameter and possibly its original length and such as to 10 retract automatically once the working pressure stops to return to the original diameter possibly to the original length.

The enlargement is apparent and appreciable at sight, whereas the elongation is less apparent and eventually not appreciable at sight. In other word, the elongation may occur or not, and in case of elongation is remarkably less apparent with respect to the enlargement.

15 To do this, the first and the second polymeric elastic material forming the unitary tubular member are to be suitably chosen.

The first and the second polymeric materials may be elastomers or thermoplastic elastomers (TPE).

Suitable TPEs may be TPE-S, such as PP/SEBS or PP/EPDM, or TPE-O, such as 20 Ethylene-Octene copolymer.

Suitable elastomers may be natural rubber or latex.

Suitably, the unitary tubular member may have a Shore A hardness measured according to ASTM D2240 (3") of 30 ShA to 50 ShA.

The textile yarns of the at least one textile layer may be polyester, nylon 6,6, 25 polyvinyl alcohol, para-aramid fibers, meta-aramid fibers, Rayon®.

Advantageously, the textile yarns of the at least one textile layer may have an elongation at break measured according to BISFA (Chap 7) less than 30%, and preferably less than 25%.

Advantageously, the textile yarns of the at least one textile layer may have a 30 toughness as measured according to BISFA (Chap 7) of at least 50 cN / tex.

In a *per se* known manner, the automatic enlargement and possibly elongation is

promoted by one or more restrictions or flow restrictors inserted in the hose or connected therewith, as taught by the documents EP2520840 and/or EP2778491, which are referred to for proper consultation. Suitably, one of the ends of the hose may be connected to means for supplying the liquid to be transported, for example a faucet.

5 As known, a textile reinforcement layer in a flexible hose if stressed tends to elongate axially and/or to enlarge radially, depending on the type.

Suitably, the unitary tubular member and the at least one textile reinforcement layer may cooperate each other so that under a working pressure of 2 bar the hose enlarges its outer diameter of at least 1,3 times with respect to its original outer diameter, preferably of 10 at least 1,4 times with respect to its original diameter, more preferably at least 1,45 times with respect to its original diameter and still more preferably at least 1,5 times with respect to its original diameter.

On the other hand, the unitary tubular member and said at least one textile reinforcement layer may cooperate each other so that under a working pressure of 5 bar the 15 elongation in length of said unitary tubular member is less than 20% with respect to the original length when in the unitary tubular member does not flow the liquid, and preferably less than 15% with respect to the original length when in the unitary tubular member does not flow the liquid.

Advantageously, the at least one textile reinforcement layer of the enlargeable hose 20 of the present invention may be susceptible to move between a rest configuration that has at rest, i.e. when the liquid does not flow through the unitary tubular member, and a working configuration that has when the unitary tubular member is actuated by the working pressure of the liquid flowing therethrough.

In the working configuration the at least one textile reinforcement layer expands 25 radially and possibly extends axially to accompany the enlargement and possibly the elongation of the unitary tubular member.

Depending on whether the yarns of the textile reinforcement layer are elastic or rigid and on the type of the textile reinforcement layer, such enlargement and possible elongation is more or less apparent.

30 However, the yarns of the textile reinforcement layer may preferably be rigid, so as to effectively act on the unitary tubular member upon the enlargement thereof.

Preferably, the at least one textile reinforcement layer and the unitary tubular member may be mutually configured so that the former intercepts the latter upon its enlargement and possible elongation in order to determine the maximum diameter and possibly the maximum length.

5 In other words, for a given inner hose pressure the maximum radial enlargement and possibly the maximum axial elongation of the at least one textile reinforcement layer is lower than the maximum radial enlargement and possibly the maximum axial elongation of the unitary tubular member, so that the maximum radial enlargement and possibly the maximum axial elongation of the at least one textile reinforcement layer determines the 10 maximum radial enlargement and possibly the maximum axial elongation of the whole hose.

Suitably, the automatic retraction of the unitary tubular member allows the at least one textile reinforcement layer to return to the rest configuration once the pressure inside the hose stops.

15 This automatic retraction of the unitary tubular member can only be accomplished by its elasticity, without any other help. In particular, the hose of the invention may be free of coil springs or similar automatic retraction means.

Thanks to one or more of the above features, it is possible to obtain a flexible enlargeable hose wieldy and practical to use.

20 The flexible hose according to the present invention allows to combine all the advantages of an enlargeable hose with those of a "classic" flexible hose, without all the drawbacks of the enlargeable hoses of the prior art.

In fact, the flexible hose according to the present invention has a relatively high burst pressure, absolutely comparable to that of the "classical" flexible hoses.

25 In fact, the at least one textile reinforcement layer ensures high burst pressure, and therefore greater durability of the hose.

Moreover, thanks to the fact that the at least one outer layer is of polymeric material, the flexible hose is simple and quick to clean from any residual dirt and/or mud due to dragging on wet soils.

30 Further, the overall bulkiness of the flexible hose according to the present invention is minimal. This allows for example to store it in a very small space. It is moreover easily storable on a classic hose reel.

In addition, the flexible hose according to the present invention in case of breakage or damage can be restored as a "classic" hose. It is also possible to replace the original fittings, if any, using the classic fittings for flexible hoses on the market, for example in case to rupture of one thereof.

5 It is however understood that in the hose of the present invention fittings or any element for connecting the ends are not needed to connect each other the various layers. In fact, in the hose of the present invention all the elements are integrated, and in particular the at least one textile reinforcement layer is integrated through the unitary tubular member.

10 It is further possible to cut the hose of the present invention to any size while maintaining the features of the whole structure. This makes further possible the customized per meter commercialization thereof.

15 Preferably, the reinforcing textile layer of the enlargeable hose according to the present invention may be a textile knotted layer or a textile knitted layer. Preferably, the stitches of the latter may be a of the tricot-type, radial-type or diamond-type, or may be interlocked or interweaved.

The at least one first textile layer and the unitary tubular member may be mutually configured so that the former intercepts the latter upon its enlargement in order to determine the maximum diameter.

Advantageous embodiments of the invention are described in the dependent claims.

20 Brief description of the drawings

Further features and advantages of the invention will be apparent upon reading the detailed description of a preferred, non-exclusive embodiment of an enlargeable flexible hose **1**, which are described as non limiting examples with the help of the annexed drawings, in which:

25 **FIGs. 1 and 2** are schematic view of an embodiment of the hose **1** during use;

FIG. 3 is a schematic side view of an embodiment of the hose **1** at rest;

FIG. 4 is a schematic side view of the embodiment of the hose **1** of FIG. 4 under pressure;

30 **FIG. 5** shows an example of a knitted textile reinforcement layer of the diamond-stitches type;

FIG. 6 shows an example of hose **1** including a knitted textile reinforcement layer of

the interlocked type;

FIG. 7 shows an example of hose **1** including a knitted textile reinforcement layer of the interweaved type;

FIGs. 8 and 9 show two examples of woven textile reinforcement layer;

5 **FIG. 10** shows an example of a knotted textile reinforcement layer.

Detailed description of some preferred embodiment

With reference to the above figures, the enlargeable hose **1** is advantageously used for the transport of liquids. In particular, the flexible hose **1** may be a irrigation hose or garden hose for the transport of water.

10 As particularly shown in FIGs. 3 and 4, the enlargeable hose **1** may include an inner polymer layer **10** and an outer polymer layer **20**.

The enlargeable flexible hose **1** may further include a knitted textile layer **30** with a tricot-type chain stitches.

15 It is understood that although in the follow there is described a flexible hose **1** with the above structure, the hose according to the invention may include other layers, according to what is defined by the appended claims.

For example, a double textile reinforcement layer may be provided, or one or more further polymeric layers internally or externally to the above layers.

20 It is further understood that although in the follow a flexible hose **1** with the above structure is described, the technical features here described are applicable to a hose which includes at least three layers, according to what is defined by the appended claims.

It is further understood that although hereinafter reference is made to a garden hose for the transport of water, the enlargeable flexible hose **1** can have any destination and can transport any liquid, according to what is defined by the appended claims.

25 In a preferred but not exclusive embodiment, inner layer **10** and outer layer **20** may be made of a styrene-based thermoplastic elastomer (TPE-S) having a matrix based on polypropylene (PP), for example the Nilflex® SH (Taro Plast SpA), having a Shore A hardness measured according to ASTM D2240 (3") of 40. Such a material has a tensile strength measured according to ASTM D412/C of about 6,5 MPa and an elongation at break measured according to ASTM D412/C of approximately 880%.

30 Indicatively, the inner layer **10** may have a thickness of 1,5 mm to 2,5 mm, preferably

1,6 mm – 2 mm.

In a preferred but not exclusive embodiment, the textile reinforcement layer **30** may be made of polyester (PET)-based yarns, for example the Brilen GLE® (Brilen Tech SA) having a linear density of 550 dtex. Such yarns have an ultimate tensile strength, measured 5 according to BISFA (Chap 7) of 42,7 +/- 4,2 N, an elongation at break measured according to BISFA (Chap 7) of 12,5 +/- 2,5% and toughness measured according BISFA (Chap 7) of 75,5 +/- 7 cN / tex.

The first textile reinforcement layer **30** may be placed on the outer surface **12** of the inner layer **10** so as to leave thereon a plurality of open areas **13**, which are directly facing to 10 the corresponding portions **13'** of the inner surface **21** of the outer layer **20**.

Suitably, the inner layer **10** and the outer layer **20** may be reciprocally bonded in correspondence with the respective uncovered areas **13, 13'**.

The bond between the inner layer **10** and the outer layer **20** may be assured by the use of materials compatible with each other or by a layer of adhesive material interposed 15 between them.

To effect such a coupling, the inner layer **10** and the outer layer **20** form a unitary tubular member **50**, inside of which the reinforcing textile layer **30** may be integrated or embedded.

The possible choice of the same material for all the polymeric layers of the hose 20 makes homogeneous the mechanical behavior of the unitary tubular member **50**, and ensures maximum compatibility between the materials.

As particularly shown in FIGs. 1 and 2, at the ends **51, 52** of the hose **1** appropriate mutual union elements may be provided.

For example, respective couplers **60, 61** may be provided.

In a preferred but not exclusive embodiment, the coupler **60** may be e.g. a female 25 coupler, and may be adapted to connect the hose **1** to a point of use, for example a tap **R**. On the other hand, the coupler **61** may be a male coupler, and may be adapted to connect the hose **1** to one or more sprinkler accessories **D**, for example a lance or a sprinkler.

In another embodiment, the end **52** of the hose **1** may be fixedly coupled to the 30 sprinkler accessory **D**, for example a lance or a sprinkler. In this case, the hose **1** does not include the coupler **61**, and cannot be coupled to more sprinkler accessories. At the other

end 51 the coupler 60 may be provided for connecting the hose 1 to a point of use, for example a tap R.

Thanks to the above features, the enlargeable hose 1 may be susceptible to be automatically enlarged and possibly elongated by the working pressure imparted by the 5 water that flows internally it, thus increasing its original diameter and possibly its original length.

To do this, in a *per se* known manner, at least one restriction inside the hose or connected therewith may be provided.

In a preferred but not exclusively embodiment, in *per se* known manner, the at least 10 one restriction may be defined by a flow restrictor located inside the coupler 61.

On the other hand, the hose 1 may internally include one or more restrictions, such as thickened portions or the like.

The at least one restriction may also be provided in the sprinkler accessory D, for example a lance or a sprinkler.

15 The at least one restriction may create a pressure drop such that the pressure upstream thereof acts internally to the hose 1, thus radially enlarging it perpendicularly to the axis X and possibly axially elongating it along the same axis X.

In practice, once connected to the hose 1 to a point of use, for example to a tap R, upon the opening of the tap the water that passes through the hose 1 promotes the radial 20 enlarging and possibly the axial elongation thereof, as shown in FIGs. 1 and 2. In any event, the elongation will be very low, and sensibly lower than the enlargement.

In other words, the water flow promotes the passage of the hose 1 from an original diameter D0 (FIG. 3), that the same hose 1 has when no water passes through it, to a working diameter D1 (FIG. 4).

25 The transition from the original diameter D0 to the working diameter D1 may occur gradually.

By contrast, upon the closing of the tap R the hose 1 automatically retracts, thus recovering to its original diameter and possibly to the original length.

In order to achieve the above, the unitary tubular member 50 and the textile layer 30 30 can cooperate with each other.

More precisely, the unitary tubular member 50 may have an elasticity such as to

automatically radially enlarge under the working pressure imparted by the water and such as to retract automatically once the working pressure stops.

On the other hand, the enlargement of the unitary tubular member **50** promotes the passage of the textile reinforcement layer **30** from a rest configuration, shown in FIG. 3, 5 which has when no water flows through the hose to a working configuration, shown in FIG. 4, which has under the working pressure.

Conversely, when the working pressure stops the automatic retraction of the unitary tubular member **50** returns the textile reinforcement layer **30** in their rest configuration.

Under the working pressure, in addition to the increase in the diameter and possibly 10 in the length of the hose, a thinning of the whole thickness thereof further occurs. With the configuration and the materials shown above, the wall thickness under pressure decreases by about half.

Suitably, the textile reinforcement layer **30** may be configured so as to intercept the unitary tubular member **50** upon its enlargement so as to determine the maximum 15 diameter.

To do this, the yarn of the textile reinforcement layer **30** and the materials of the unitary tubular member **50** may be suitably selected, for example as described above.

The knitted textile reinforcement layer **30** may be of the chain-like tricot type, as shown in the FIGs. 3 and 4, or made according to the teachings of EP0623776 in the name of 20 the same Applicant.

Alternatively, the knitted textile reinforcement layer **30** may be of the diamond-stitches type, as shown in FIGs. 5, or of the radial type, as taught by the European Patent application EP0527512 in the name of the same Applicant.

In another embodiment, the knitted textile reinforcement layer **30** may be of the 25 interlocked type, as shown in FIGs. 6, or of the interweaved type, as shown in FIGs. 7.

Alternatively to the knitted configuration, the first textile reinforcement layer **30** may be a weaving or knotting. FIGs. 8 and 9 show two examples of textile reinforcement woven layer, different each other for the orientation, the number and configuration of the yarns. FIG. 10 shows an example of a textile reinforcement knotted layer.

30 Suitably, the unitary tubular member and the at least one textile reinforcement layer may cooperate each other so that under a working pressure of 2 bar the hose enlarges its

outer diameter of at least 1,3 times with respect to its original outer diameter, preferably of at least 1,4 times with respect to its original diameter, more preferably at least 1,45 times with respect to its original diameter and still more preferably at least 1,5 times with respect to its original diameter.

5 For example, with a hose having the structure described above and manufactured in the above materials, with an inner diameter at rest of 9 mm, outer diameter at rest of 14,5 mm and weight of 80 g/mt, the enlargements at different Internal working pressures are provided in table 1 below.

10

Table 1

Working pressure (bar)	Outer diameter [mm]	$\varnothing_{\text{out under press}} / \varnothing_{\text{out at rest}}$
0	14,5	1
0,5	20,5	1,41
1	23,1	1,59
1,5	23,3	1,61
2	23,5	1,62
2,5	23,8	1,64
3	24,1	1,66
3,5	24,4	1,68
4	24,7	1,70
4,5	25	1,72
5	25,3	1,74
5,5	25,4	1,75
6	25,5	1,76

It is understood that these data may change depending on the materials and/or the features of the hose, such as the inner or outer diameter or the weight/mt thereof.

15 Suitably, the unitary tubular member **50** and the textile reinforcement layer **30** may cooperate each other so that under a working pressure of 5 bar the elongation in length of said unitary tubular member **50** is less than 20% with respect to the original length, and preferably less than 15% with respect to the original length.

This film **20** has the purpose of protecting the underlying layers, in particular the

textile layers, and to give the appearance to the hose. It is also important for the resistance to external agents and the sliding of the hose on the ground. In fact, it minimizes fouling of the hose as a result of the use on muddy grounds or in a garden.

From the above description, it is apparent that the invention fulfils the intended
5 objects.

The invention is susceptible of numerous modifications and variations, all falling within the inventive concept expressed in the attached claims. All the details may be replaced with other technically equivalent elements, and the materials may be different according to requirements, without departing from the scope of the invention.

10 Although the invention has been described with particular reference to the attached figures, reference numbers used in the description and in the claims are used to improve the intelligence of the invention and do not constitute any limitation of the claimed scope.

CLAIMS

1. A hose assembly for transporting liquids, particularly water, comprising:
 - an enlargeable flexible hose; and
 - at least one restriction or at least one flow restrictor (61) to create within the hose

5 a working pressure susceptible to promote the enlargement thereof, said at least one restriction or at least one flow restrictor (61) being internal to the hose or connected therewith;

wherein the enlargeable flexible hose includes:

- at least one inner layer (10) made of a first elastic polymeric material;
- at least one outer layer (20) made of a second elastic polymeric material;
- at least one textile reinforcement layer (30) interposed between said at least one inner layer (10) and at least one outer layer (20);

10 wherein said at least one inner layer (10) and at least one outer layer (20) are reciprocally coupled to form a unitary tubular member (50), said at least one textile reinforcement layer (30) being embedded therein (50);

15 wherein said unitary tubular member (50) has an elasticity such to automatically enlarge upon the working pressure given by the liquid flowing therethrough to increase its original outer diameter and such to automatically recovery once the working pressure stops for assuming again said original outer diameter;

20 wherein said at least one textile reinforcement layer (30) is susceptible to move between a rest configuration that has when no liquid flows through the unitary tubular member (50) and a working configuration that has when said unitary tubular member (50) enlarges upon the working pressure;

25 wherein said unitary tubular member (50) and said at least one textile reinforcement layer (30) cooperate each other so that under a working pressure of 2 bar the hose enlarges its outer diameter of at least 1,3 times with respect to its original outer diameter.

30 2. Hose assembly according to claim 1, wherein the automatic enlargement of said unitary tubular member (50) promotes the moving of said at least one textile layer (30) from the rest configuration to the working configuration, the automatic recovery of said unitary tubular member (50) promoting the moving back of said at least one textile layer (30) from the working configuration to the rest configuration.

3. Hose assembly according to claim 1 or 2, wherein said at least one textile reinforcement layer (30) and said unitary tubular member (50) are reciprocally configured so that the former (30) captures the latter (50) upon its enlargement so as to define the maximum outer diameter thereof.

5 4. Hose assembly according to claim 1, 2 or 3, wherein said at least one textile reinforcement layer (30) lays on the outer surface (12) of said at least one inner layer (10) so as to leave thereon a plurality of uncovered areas (13), said at least one outer layer (20) and at least one inner layer (10) being reciprocally coupled in correspondence of said uncovered areas (13).

10 5. Hose assembly according to any one of the preceding claims, wherein said unitary tubular member (50) has the original outer diameter when said at least one textile reinforcement layer (30) is in the rest configuration, said unitary tubular member (50) being enlarged when said at least one textile reinforcement layer (30) is in the working configuration.

15 6. Hose assembly according to any one of the preceding claims, wherein said at least one first textile reinforcement layer (30) is selected among the group consisting of knitting, weaving or knotting.

20 7. Hose assembly according to the preceding claim, wherein said at least one first textile reinforcement knitted layer (30) is of the chain-like tricot type or of the diamond-stitches type or of the radial type or of the interlocked type or of the interweaved type.

25 8. Hose assembly according to any one of the preceding claims, wherein said unitary tubular member (50) and said at least one textile reinforcement layer (30) cooperate each other so that under a working pressure of 2 bar the hose increases its outer diameter of at least 1,4 times with respect to its original diameter, preferably at least 1,45 time with respect to its original diameter and more preferably at least 1,5 times with respect to its original diameter.

9. Hose assembly according to any one of the preceding claims, wherein said unitary tubular member (50) once enlarged by the working pressure recovers back to its original outer diameter exclusively thanks to its elasticity, without any other biasing means.

30 10. Hose assembly according to any one of the preceding claims, wherein the hose is a garden hose for the transport of water.

11. Hose assembly according to any one of the preceding claims, wherein the hose is a not corrugated and not coiled hose.

12. Hose assembly according to any one of the preceding claims, wherein said first and said second elastic polymeric materials are elastomers or a thermoplastic elastomers.

5 13. Hose assembly according to any one of the preceding claims, wherein said unitary tubular member (50) has a Shore A hardness measured according to ASTM D2240 (3") of 30 ShA to 50 ShA.



14. Hose assembly according to any one of the preceding claims, wherein said at least one textile reinforcement layer (30) consists of non-elastic rigid yarns.



10 15. Hose assembly according to the preceding claim, wherein said rigid yarns have an elongation at break measured according to BISFA (Chap 7) less than 30%, and preferably less than 25%.

16. Hose assembly according to claim 15, wherein said rigid yarns have a toughness as measured according to BISFA (Chap 7) of at least 50 cN / tex.

15 17. Hose assembly according to any one of the preceding claims, wherein said unitary tubular member (50) and said at least one textile reinforcement layer (30) cooperate each other so that under a working pressure of 5 bar the elongation in length of said unitary tubular member (50) is less than 20% with respect to the original length when in said unitary tubular member (50) does not flow the liquid, and preferably less than 15% with respect to 20 the original length when in said unitary tubular member (50) does not flow the liquid.

18. An enlargeable flexible hose as defined in one or more of the preceding claims.













FIG. 6





INTERNATIONAL SEARCH REPORT

International application No

PCT/IB2016/052435

A. CLASSIFICATION OF SUBJECT MATTER
INV. F16L11/12
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
F16L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	WO 2016/098063 A1 (FITT SPA [IT]) 23 June 2016 (2016-06-23) page 10, lines 15-20 page 15, lines 5-15 -----	1-17
A	US 2015/354731 A1 (RAGNER GARY DEAN [US]) 10 December 2015 (2015-12-10) figures 3, 3A -----	1-17
A	US 2013/213514 A1 (BERARDI MICHAEL [US]) 22 August 2013 (2013-08-22) claim 1; figure 7 -----	1-17
A	US 3 682 202 A (BUHRMANN WAYNE H ET AL) 8 August 1972 (1972-08-08) figure 2 ----- -/-	1-17

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance
"E" earlier application or patent but published on or after the international filing date
"L" document which may throw doubts on priority, claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
"O" document referring to an oral disclosure, use, exhibition or other means
"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search	Date of mailing of the international search report
10 January 2017	25/01/2017
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Dauvergne, Bertrand

INTERNATIONAL SEARCH REPORT

International application No PCT/IB2016/052435

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 091 026 A (SHIZUO YOKOHORI [JP] ET AL) 25 February 1992 (1992-02-25) claim 1 -----	1-17

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/IB2016/052435

Patent document cited in search report	Publication date	Patent family member(s)			Publication date
WO 2016098063	A1	23-06-2016	EP 3052847 A1		10-08-2016
			WO 2016098063 A1		23-06-2016
US 2015354731	A1	10-12-2015	NONE		
US 2013213514	A1	22-08-2013	US 2013213514 A1		22-08-2013
			US 2014345734 A1		27-11-2014
			US 2016178092 A1		23-06-2016
US 3682202	A	08-08-1972	DE 2063641 A1		29-07-1971
			FR 2075485 A5		08-10-1971
			GB 1306589 A		14-02-1973
			NL 7100457 A		26-07-1971
			US 3682202 A		08-08-1972
			ZA 7008428 B		29-09-1971
US 5091026	A	25-02-1992	DE 3838008 A1		18-05-1989
			US 4957792 A		18-09-1990
			US 5091026 A		25-02-1992