

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
31 March 2011 (31.03.2011)

(10) International Publication Number
WO 2011/036016 A1

PCT

(51) International Patent Classification:
C08L 23/12 (2006.01) *C08F 297/08* (2006.01)

(21) International Application Number:
PCT/EP2010/062401

(22) International Filing Date:
25 August 2010 (25.08.2010)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09170990.7 22 September 2009 (22.09.2009) EP
61/277,734 29 September 2009 (29.09.2009) US

(71) Applicant (for all designated States except US):
BASELL POLIOLEFINE ITALIA S.R.L. [IT/IT]; Intellectual Property, Via Pergolesi, 25, I-20124 Milano (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MASSARI, Paola** [IT/IT]; Via E. Farolfi, 3, I-44100 Ferrara (IT). **CIARAFONI, Marco** [IT/IT]; Via Risorgimento, 84, I-44100 Ferrara (IT). **BIONDINI, Gisella** [IT/IT]; Via dei Gigli, 16, I-44015 Portomaggiore (IT). **CAPUTO, Tiziana** [IT/IT]; via Carlo Mayr, 52, I-44100 Ferrara (IT).

(74) Agent: **SACCO, Marco**; Basell Poliolefine Italia s.r.l., Intellectual property, P. le Donegani, 12, I-44100 Ferrara (IT).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: PROPYLENE POLYMER COMPOSITIONS

(57) Abstract: A propylene composition comprising (percent by weight): A) 70%-95%, of a propylene homopolymer having a Polydispersity Index (P.I.) value of from 4.6 to 10, a fraction insoluble in xylene at 25°C, higher than 90 %, and MFR L (Melt Flow Rate according to ISO 1133, condition L, i.e. 230°C and 2.16 kg load) from 100 to 250 g/10 min; B) 5%-30%, of a copolymer of propylene containing from 36% to 44% of ethylene derived units; the composition having an intrinsic viscosity of the fraction soluble in xylene at 25°C comprised between 3 and 5 dl/g.



WO 2011/036016 A1

Title:**Propylene polymer compositions**

The present invention relates to a propylene polymer composition having an optimum balance of properties in particular an improved flexural modulus.

As is known, the isotactic polypropylene is endowed with an exceptional combination of excellent properties which render it suitable for a very great number of uses. In order to improve said properties into the propylene stereoregular homopolymerization process have been introduced one or more copolymerization steps or one or more monomer have been introduced in the homopolymer matrix.

WO 05/014713 relates to a heterophasic polyolefin composition comprising (percent by weight):

1) 65-95% of a crystalline propylene polymer selected from propylene homopolymer and random polymer of propylene with 0.1-10% of an α -olefin selected from ethylene, a C_4 - C_{10} α -olefin and a mixture thereof, the said polymer being insoluble in xylene at ambient temperature in an amount over 85% and having a polydispersity index ranging from 4 to 13, preferably 4.5 to 12, more preferably 5 to 9, and an intrinsic viscosity value over 2.2 dl/g, preferably 2.2 to 4.5 dl/g; and

2) 5-35% of an elastomeric olefin polymer of ethylene with a C_3 - C_{10} α -olefin and optionally a diene, having an ethylene content ranging from 15 to 85% and an intrinsic viscosity value of at least 1.4 dl/g, preferably from 2.5 to 5 dl/g.

WO 2006/037705 relates to an olefin polymer composition comprising (by weight, unless otherwise specified):

A) 60-85%, preferably 65-80%, more preferably 65-75%, of a crystalline propylene homopolymer or a crystalline copolymer of propylene containing 3% or less of ethylene or C_4 - C_{10} α -olefin(s) or of combinations thereof, said homopolymer or copolymer having a Polydispersity Index (P.I.) value of from 4.5-6, preferably 4.5-5.5, and a content of isotactic pentads (mmmm), measured by ^{13}C NMR on the fraction insoluble in xylene at 25 °C, higher than 96%, preferably higher than 98%;

B) 15-40%, preferably 20-35%, more preferably 25-35%, of a partially amorphous copolymer of ethylene containing from 35% to 70%, preferably from 40 to 55%, of propylene or C_4 - C_{10} α -olefin(s) or of combinations thereof, and optionally minor proportions of a diene.

The olefin polymer composition according to the present invention exhibits a value of elongation at break ranging from 150 to 600%, preferably 200-500%, according to ISO method 527.

These two documents relates to a very broad class of polypropylene compositions. The applicant found that it is possible to achieve improved properties especially in term of flexural modulus by using a particular class of propylene composition.

The object of the present invention is a propylene composition comprising (percent by weight):

A) 70%-95%, preferably 75%-90%, more preferably 80%-88%, of a propylene homopolymer having a Polydispersity Index (P.I.) value of from 4.6 to 10, preferably from 5.1 to 8; a fraction insoluble in xylene at 25 °C, higher than 90%, preferably higher than 95% more preferably higher than 97%; and a MFR L (Melt Flow Rate according to ISO 1133, condition L, i.e. 230°C and 2.16 kg load) from 100 to 250 g/10 min, in particular from 120 to 220 g/10 min; preferably from 150 to 200 g/10 min;

B) 5%-30%, preferably 10%-25%, more preferably 12%-19% of a copolymer of propylene with from 36% to 44%, preferably from 39% to 43%; even more preferably from 39% to 41% of ethylene derived units;

the composition having an intrinsic viscosity of the fraction soluble in xylene at 25 °C comprised between 3.0 and 5.0 dl/g; preferably between 3.5 and 5.0 dl/g more preferably between 3.8 and 4.5 dl/g.

From the above definitions it is evident that the term "copolymer" includes polymers containing only two kinds of monomers.

Other preferred features for the compositions of the present invention are:

- MFR L (Melt Flow Rate according to ISO 1133, condition L, i.e. 230°C and 2.16 kg load) from 30 to 90 g/10 min, in particular from 40 to 80 g/10 min.; more preferably from 50 to 70 g/10 min.

Moreover, the compositions of the present invention preferably are endowed with:

- a Flexural Modulus is comprised between 1580 MPa and 2000 MPa, preferably comprised between 1600 and 1800 MPa, even more preferably comprised between 1650 and 1750MPa;

With the composition of the present invention it is possible to achieve an optimum balance of properties, in particular the value of the flexural modulus is particularly high.


The propylene polymer compositions of the present invention can be prepared by sequential polymerization in at least two stages, with each subsequent polymerization stage being conducted in the presence of the polymeric material formed in the immediately preceding polymerization

reaction, wherein the copolymer (A) is normally prepared in at least one first polymerization stage and the copolymer (B) is normally prepared in at least one second polymerization stage.

Preferably, each polymerization stage is carried out in presence of a highly stereospecific heterogeneous Ziegler-Natta catalyst. The Ziegler-Natta catalysts suitable for producing the propylene polymer compositions of the invention comprise a solid catalyst component comprising at least one titanium compound having at least one titanium-halogen bond and at least an electron-donor compound (internal donor), both supported on magnesium chloride. The Ziegler-Natta catalysts systems further comprise an organo-aluminum compound as essential co-catalyst and optionally an external electron-donor compound.

Suitable catalysts systems are described in the European patents EP45977, EP361494, EP728769, EP 1272533 and in the international patent application W000163261.

Preferably, the solid catalyst component comprises Mg, Ti, halogen and an electron donor selected from succinates of formula (I):



wherein the radicals R^1 and R^2 , equal to or different from each other, are a C_1 - C_{20} linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, optionally containing heteroatoms belonging to groups 15-17 of the periodic table; the radicals R^3 to R^6 equal to or different from each other, are hydrogen or a C_1 - C_2 linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, optionally containing heteroatoms, and the radicals R^3 to R^6 which are joined to the same carbon atom can be linked together to form a cycle.

R^1 and R^2 are preferably C_1 - C_8 alkyl, cycloalkyl, aryl, arylalkyl and alkylaryl groups.

Particularly preferred are the compounds in which R^1 and R^2 are selected from primary alkyls and in particular branched primary alkyls. Examples of suitable R^1 and R^2 groups are methyl, ethyl, n-propyl, n-butyl, isobutyl, neopentyl, 2-ethylhexyl. Particularly preferred are ethyl, isobutyl, and neopentyl.

One of the preferred groups of compounds described by the formula (I) is that in which R^3 to R^5 are hydrogen and R^6 is a branched alkyl, cycloalkyl, aryl, arylalkyl and alkylaryl radical having from 3 to 10 carbon atoms. Another preferred group of compounds within those of formula (I) is that in which at least two radicals from R^3 to R^6 are different from hydrogen and are selected from C_1 - C_{20} linear or branched alkyl, alkenyl, cycloalkyl, aryl, arylalkyl or alkylaryl group, optionally containing heteroatoms belonging to groups.

Particularly preferred are the compounds in which the two radicals different from hydrogen are linked to the same carbon atom. Furthermore, also the compounds in which at least two radicals different from hydrogen are linked to different carbon atoms, that is R^3 and R^5 or R^4 and R^6 are particularly preferred.

According to a preferred method, the solid catalyst component can be prepared by reacting a titanium compound of formula $Ti(OR)_{n-y}X_y$ where n is the valence of titanium and y is a number between 1 and n , preferably $TiCl_4$, with a magnesium chloride deriving from an adduct of formula $MgCl_2 \cdot pROH$, where p is a number between 0.1 and 6, preferably from 2 to 3.5, and R is a hydrocarbon radical having 1-18 carbon atoms. The adduct can be suitably prepared in spherical form by mixing alcohol and magnesium chloride in the presence of an inert hydrocarbon immiscible with the adduct, operating under stirring conditions at the melting temperature of the adduct (100-130 °C). Then, the emulsion is quickly quenched, thereby causing the solidification of the adduct in form of spherical particles. Examples of spherical adducts prepared according to this procedure are described in US 4,399,054 and US 4,469,648. The so obtained adduct can be directly reacted with the Ti compound or it can be previously subjected to thermal controlled dealcoholation (80-130 °C) so as to obtain an adduct in which the number of moles of alcohol is generally lower than 3, preferably between 0.1 and 2.5. The reaction with the Ti compound can be carried out by suspending the adduct (dealcoholated or as such) in cold $TiCl_4$ (generally 0 °C); the mixture is heated up to 80-130 °C and kept at this temperature for 0.5-2 hours. The treatment with $TiCl_4$ can be carried out one or more times. The internal donor can be added during the treatment with $TiCl_4$ and the treatment with the electron donor compound can be repeated one or more times. Generally, the succinate of formula (I) is used in molar ratio with respect to the $MgCl_2$ of from 0.01 to 1 preferably from 0.05 to 0.5. The preparation of catalyst components in spherical form is described for example in European patent application EP-A-395083 and in the International patent application W098144001. The solid catalyst components obtained according

to the above method show a surface area (by B.E.T. method) generally between 20 and 500 m²/g and preferably between 50 and 400 m²/g, and a total porosity (by B.E.T. method) higher than 0.2 cm³/g preferably between 0.2 and 0.6 cm³/g. The porosity (Hg method) due to pores with radius up to 10.000 Å generally ranges from 0.3 to 1.5 cm³/g, preferably from 0.45 to 1 cm³/g.

The organo-aluminum compound is preferably an alkyl-Al selected from the trialkyl aluminum compounds such as for example triethylaluminum, triisobutylaluminum, tri-n-butylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum. It is also possible to use mixtures of trialkylaluminum's with alkylaluminum halides, alkylaluminum hydrides or alkylaluminum sesquichlorides such as AlEt₂Cl and Al₂Et₃Cl₃.

Preferred external electron-donor compounds include silicon compounds, ethers, esters such as ethyl 4-ethoxybenzoate, amines, heterocyclic compounds and particularly 2,2,6,6-tetramethyl piperidine, ketones and the 1,3-diethers. Another class of preferred external donor compounds is that of silicon compounds of formula R_a⁵R_b⁶Si(OR⁷)_c where a and b are integer from 0 to 2, c is an integer from 1 to 3 and the sum (a+b+c) is 4; R⁵, R⁶, and R⁷, are alkyl, cycloalkyl or aryl radicals with 1-18 carbon atoms optionally containing heteroatoms. Particularly preferred are methylcyclohexyldimethoxysilane, diphenyldimethoxysilane, methyl-t-butyldimethoxysilane, dicyclopentyldimethoxysilane, 2-ethylpiperidinyl-2-t-butyldimethoxysilane and 1,1,1-trifluoropropyl-2-ethylpiperidinyl-dimethoxysilane and 1,1,1-trifluoropropyl-metildimethoxysilane. The external electron donor compound is used in such an amount to give a molar ratio between the organo-aluminum compound and said electron donor compound of from 0.1 to 500.

The polymerization process can be carried out in gas phase and/or in liquid phase, in continuous or batch reactors, such as fluidized bed or slurry reactors. For example, it is possible to carry out the polymerization of the propylene polymer (A) in liquid phase, using liquid propylene as diluent, while the copolymerization stage to obtain the propylene copolymer fraction (B) is carried out in gas phase, without intermediate stages except for the partial degassing of the monomers. Alternatively, all the sequential polymerization stages can be carried out in gas phase. The reaction time, temperature and pressure of the polymerization steps are not critical, however the temperature for the preparation of fraction (A) and (B), that can be the same or different, is usually from 50°C to 120°C. The polymerization pressure preferably ranges from 0.5 to 12 MPa if the polymerization is carried out in gas-phase. The catalytic system can be pre-contacted (pre-

polymerized) with small amounts of olefins. The molecular weight of the propylene polymer composition is regulated by using known regulators, such as hydrogen.

According to a preferred embodiment, the propylene polymer (A) is produced by a gas-phase polymerization process carried out in at least two interconnected polymerization zones. Said polymerization process is described in the European patent EP 782587.

The process is carried out in a first and in a second interconnected polymerization zone to which propylene and ethylene or propylene and alpha-olefins are fed in the presence of a catalyst system and from which the polymer produced is discharged. The growing polymer particles flow through the first of said polymerization zones (riser) under fast fluidization conditions, leave said first polymerization zone and enter the second of said polymerization zones (downcomer) through which they flow in a densified form under the action of gravity, leave said second polymerization zone and are reintroduced into said first polymerization zone, thus establishing a circulation of polymer between the two polymerization zones. Generally, the conditions of fast fluidization in the first polymerization zone is established by feeding the monomers gas mixture below the point of reintroduction of the growing polymer into said first polymerization zone. The velocity of the transport gas into the first polymerization zone is higher than the transport velocity under the operating conditions and is normally between 2 and 15 m/s. In the second polymerization zone, where the polymer flows in densified form under the action of gravity, high values of density of the solid are reached which approach the bulk density of the polymer; a positive gain in pressure can thus be obtained along the direction of flow, so that it becomes possible to reintroduce the polymer into the first reaction zone without the help of mechanical means. In this way, a "loop" circulation is set up, which is defined by the balance of pressures between the two polymerization zones and by the head loss introduced into the system. Optionally, one or more inert gases, such as nitrogen or an aliphatic hydrocarbon, are maintained in the polymerization zones, in such quantities that the sum of the partial pressures of the inert gases is preferably between 5 and 80% of the total pressure of the gases. The operating parameters such as, for example, the temperature are those that are usual in gas-phase olefin polymerization processes, for example between 50°C and 120°C. The process can be carried out under operating pressure of between 0,5 and 10 MPa, preferably between 1.5 and 6 MPa. Preferably, the various catalyst components are fed to the first polymerization zone, at any point of said first polymerization zone. However, they can also be

fed at any point of the second polymerization zone. Molecular weight regulators known in the art, particularly hydrogen, can be used to regulate the molecular weight of the growing polymer.

In the second stage of the particularly preferred polymerization process, the propylene/ethylene copolymer (B) is produced in a conventional fluidized-bed gas-phase reactor in the presence of the polymeric material and the catalyst system coming from the preceding polymerization step. The polymerization mixture is discharged from the downcomer to a gas-solid separator, and subsequently fed to the fluidized-bed gas-phase reactor operating under conventional conditions of temperature and pressure.

The propylene polymer compositions of the present invention can also be obtained by separately preparing the said copolymers (A) and (B), operating with the same catalysts and substantially under the same polymerization conditions as previously illustrated and subsequently mechanically blending said copolymers in the molten state using conventional mixing apparatuses, like twin-screw extruders.

The propylene polymer compositions of the present invention may further comprise additives commonly employed in the polyolefin field, such as antioxidants, light stabilizers, nucleating agents, antiacids, colorants and fillers.

The main application of the propylene polymer compositions of the invention is the production of molded articles, particularly injection-molded items. The injection-molded articles comprising the propylene polymer compositions of the invention have good flexibility and good impact properties and are also endowed with good transparency.

The following examples are given to illustrate and not to limit the present invention.

Examples

The data of the propylene polymer materials were obtained according to the following methods:

Xylene-soluble fraction (XS)

2.5 g of polymer and 250 mL of o-xylene are introduced in a glass flask equipped with a refrigerator and a magnetical stirrer. The temperature is raised in 30 minutes up to the boiling point of the solvent. The so obtained solution is then kept under reflux and stirring for further 30 minutes. The closed flask is then kept for 30 minutes in a bath of ice and water and in thermostatic water bath at 25°C for 30 minutes as well. The solid thus obtained is filtered on quick filtering paper and the filtered liquid is divided into two 100 mL aliquots. One 100 mL aliquots of the filtered liquid is poured in a previously weighed aluminum container, which is

heated on a heating plate under nitrogen flow, to remove the solvent by evaporation. The container is then kept on an oven at 80°C under vacuum until constant weight is obtained. The residue is weighed to determine the percentage of xylene-soluble polymer.

Ethylene (C₂) content

By IR spectroscopy.

The comonomer content of the Component B is determined on the precipitated "amorphous" fraction of the polymer. The precipitated "amorphous" fraction is obtained as follows: to one 100 ml aliquot of the filtered liquid obtained as described above (procedure for the Xylene-soluble fraction) 200 ml of acetone are added under vigorous stirring. Precipitation must be complete as evidenced by a clear solid-solution separation. The solid thus obtained is filtered on a tared metallic screen and dried in a vacuum oven at 70°C until a constant weight is reached.

Molar ratio of feed gasses

Determined by gas-chromatography

Melt flow rate (MFR)

Determined according to ISO 1133 (230°C, 2.16 Kg)

Intrinsic viscosity

Determined in tetrahydronaphthalene at 135°C

Flexural modulus

Determined according to ISO 178

Stress at yield and at break

Determined according to ISO 527

Elongation at yield and break

Determined according to ISO 527

IZOD Impact Strength

Determined according to ISO 18011A

Melting temperature, melting enthalpy and crystallization temperature

Determined by DSC with a temperature variation of 20°C per minute.

The melting and crystallization temperatures were measured by Differential Scanning Calorimetry (DSC) on a Perkin Elmer DSC-1 calorimeter equipped with the Pyris 1 software performing scans in a flowing N₂ atmosphere. The DSC apparatus was previously calibrated at indium and zinc melting points with particular attention in determining the baseline with required accuracy. The

preparation of the samples, for calorimetric investigations, was performed by cutting them into small pieces by using a cutter. The weight of the samples in every DSC crucible was kept at 6.0 ± 0.5 mg.

In order to obtain the melting and crystallization temperatures of the copolymers, the weighted sample was sealed into aluminium pans and heated to 180°C at 20°C/minute. The sample was kept at 180°C for 5 minutes to allow a complete melting of all the crystallites, and then cooled down to -20°C at 20°C/minute. After standing 2 minutes at -20°C, the sample was heated for the second time to 180°C at 20°C/min.

Polydispersity Index (PI): measurement of molecular weight distribution of the polymer. To determine the PI value, the modulus separation at low modulus value, e.g. 500 Pa, is determined at a temperature of 200 °C by using a RMS-800 parallel plates rheometer model marketed by Rheometrics (USA), operating at an oscillation frequency which increases from 0.01 rad/second to 100 rad/second. From the modulus separation value, the PI can be derived using the following equation:

$$PI = 54.6 \times (\text{modulus separation})^{-1.76}$$

wherein the modulus separation (MS) is defined as:

$$MS = (\text{frequency at } G' = 500 \text{ Pa}) / (\text{frequency at } G'' = 500 \text{ Pa})$$

wherein G' is the storage modulus and G'' is the loss modulus.

Examples 1 and comparative examples 1-2

The Ziegler-Natta catalyst was prepared according to the Example 5, lines 48-55 of the European Patent EP 728 769. Triethylaluminium (TEAL) was used as co-catalyst and dicyclopentylmethoxysilane as external donor.

The propylene polymer compositions of the examples were prepared in a two-step polymerization process, wherein the copolymer (A) was prepared in the first polymerization step by feeding the monomers and the catalyst system to a gas-phase polymerization reactor comprising two interconnected polymerization zones, a riser and a downcomer (MZCR reactor), as described in the European Patent EP 782 587. The polymerization mixture was discharged from said reactor, conveyed to a gas-solid separator and the polymerized material was sent into a conventional gas-phase fluidized-bed reactor where the propylene/ethylene copolymer (B) was produced. The operative conditions are indicated in Table 1.

The polymer particles exiting from the second polymerization step were subjected to a steam treatment to remove the unreacted monomers and dried.

The propylene polymer compositions were added with the following additives Calcium stearate 500ppm, GMS90 500ppm, Irganox B215 1500ppm, Millad 3988 1800 ppm- and extruded in a twin-screw extruder Berstorff (L/D=33) under the following operating conditions:

Temperature of the feeding section: 190-210°C

Melt temperature: 240°C

Temperature of the die section: 230°C

Flow rate: 16 Kg/h

Rotational speed: 250 rpm

Table 1

Example		1	Comp 1	Comp 2
Component A)				
TEAL/external donor	wt/wt	3.5	3.8	7.5
TEAL/catalyst	wt/wt	5.4	4.5	11
Temperature	°C	80	80	80
Pressure	bar-g	28	28	30
Split holdup riser	wt%	33	42	35
downcomer	wt%	67	58	65
C ₃ ⁻ riser	mole%	75	82	76
H ₂ /C ₃ ⁻ riser	mol/mol	0.13	0.045	0.07
C ₂ ⁻ /(C ₂ ⁻ +C ₃ ⁻)	mol/mol	-	-	-
MFR	g/10 min	184	54	45.5
XS	wt%	2.5	2.3	2.3
Tm	°C	160.1	162.1	162
Component B (fluidized bed reactor)				
Temperature	°C	80	80	80
Pressure	MPa	19	19	19

Split *	%	14	16	13
$C_2^-/C_2^-+C_3^-$	mol/mol	0.22	0.22	0.31
H_2/C_2^-	mol/mol	0.022	0.012	0.04

Tabella da riempire

*Amount of component B with respect to A+B

C_2^- = ethylene C_3^- = propylene

The properties of the material obtained according to example 1 and comparative example 1 are reported in table 2

Table 2

Example		1	Comp ex 1	Comp ex 2
MFR of the component A)	g/10'	188	54	46
Polydispersity		6.7	6.1	5.5
XS	%	2.5	2.3	1.6
%copolymer component B)	wt%	14	16	13
% C_2^- component B)	wt%	40	35	45
MFR of the composition	g/10'	64	23	29
XSIV	dl/g	4.1	4.1	2.82
Flexural Modulus	MPa	1654	1555	1550
GLOSS °60		78	82	n.m.

C_2^- = ethylene

n.m. not measured

XS xylene solubles

XSIV intrinsic viscosity of the xylene soluble fraction

By comparing example 1 of the present invention and comparative examples 1-2 it is clear that the flexural modulus is improved considerably

Claims

1. A propylene composition comprising (percent by weight):
 - A) 70%-95%, of a propylene homopolymer having a Polydispersity Index (P.I.) value of from 4.6 to 10, a fraction insoluble in xylene at 25 °C, higher than 90 %, and MFR L (Melt Flow Rate according to ISO 1133, condition L, i.e. 230°C and 2.16 kg load) from 100 to 250 g/10 min;
 - B) 5%-30%, of a copolymer of propylene containing from 36% to 44% of ethylene derived units;
the composition having an intrinsic viscosity of the fraction soluble in xylene at 25°C comprised between 3 and 5 dl/g.
2. The composition according to claim 1 wherein component A) has a polydispersity Index (P.I.) value of from 5.1 to 8.
3. The composition according to claims 1 or 2 wherein component A) has a MFR L (Melt Flow Rate according to ISO 1133, condition L, i.e. 230°C and 2.16 kg load) ranging from 120 to 220 g/10 min.
4. The composition according to anyone of claims 1-3 wherein component B) has from 39% to 43% by weight of ethylene derived units.
5. The composition according to anyone of claims 1-4 having an intrinsic viscosity of the fraction soluble in xylene at 25 °C comprised between 3.5 and 5.0 dl/g.
6. The composition according to anyone of claims 1-5 having a Flexural Modulus is comprised between 1500 MPa and 2000 MPa.
7. The composition according to anyone of claims 1-6 having the MFR L (Melt Flow Rate according to ISO 1133, condition L, i.e. 230°C and 2.16 kg load) from 30 to 90 g/10 min.

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2010/062401

A. CLASSIFICATION OF SUBJECT MATTER

INV. C08L23/12 C08F297/08
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C08L C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPQ-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2007/060114 A1 (BASELL POLIOLEFINE SRL [IT]; MASSARI PAOLA [IT]; NEWS JEAN [IT]; CIARA) 31 May 2007 (2007-05-31) claims 1-5; example 1; table 2 -----	1-4,7
A	WO 03/076511 A1 (BASELL POLIOLEFINE SPA [IT]; PELLICONI ANTEO [IT]; GARAGNANI ENEA [IT]) 18 September 2003 (2003-09-18) polymers III, IV -----	1-7

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

3 November 2010

Date of mailing of the international search report

11/11/2010

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Knutzen-Mies, Karen

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2010/062401

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2007060114 A1	31-05-2007	AU 2006316534 A1	31-05-2007
		CA 2630679 A1	31-05-2007
		EP 1951806 A1	06-08-2008
		JP 2009516767 T	23-04-2009
		KR 20080078677 A	27-08-2008
WO 03076511 A1	18-09-2003	AR 038923 A1	02-02-2005
		AU 2003208706 A1	22-09-2003
		BR 0303383 A	30-03-2004
		CA 2478513 A1	18-09-2003
		CN 1639251 A	13-07-2005
		EP 1483327 A1	08-12-2004
		JP 4365685 B2	18-11-2009
		JP 2005521759 T	21-07-2005
		RU 2304598 C2	20-08-2007