



Office de la Propriété

Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2586684 C 2014/04/15

(11)(21) **2 586 684**

(12) **BREVET CANADIEN**
CANADIAN PATENT

(13) **C**

(86) Date de dépôt PCT/PCT Filing Date: 2005/11/09
(87) Date publication PCT/PCT Publication Date: 2006/05/18
(45) Date de délivrance/Issue Date: 2014/04/15
(85) Entrée phase nationale/National Entry: 2007/05/07
(86) N° demande PCT/PCT Application No.: EP 2005/011954
(87) N° publication PCT/PCT Publication No.: 2006/050917
(30) Priorités/Priorities: 2004/11/10 (US10/985,652);
2005/04/04 (DE10 2005 015 573.1);
2005/04/04 (DE10 2005 015 575.8);
2005/04/04 (DE10 2005 015 576.6)

(51) Cl.Int./Int.Cl. *C23C 22/34* (2006.01),
C09D 5/12 (2006.01), *C23C 22/36* (2006.01)

(72) Inventeurs/Inventors:
KOLBERG, THOMAS, DE;
WALTER, MANFRED, DE;
SCHUBACH, PETER, DE

(73) Propriétaire/Owner:
CHEMETALL GMBH, DE

(74) Agent: ROBIC

(54) Titre : METHODE DE REVETEMENT DE SURFACES METALLIQUES AVEC UNE COMPOSITION AQUEUSE
COMPORTANT DES SILANES, DES SILANOLS, DES SILOXANES OU DES POLYSILOXANES ET LADITE
COMPOSITION
(54) Title: METHOD FOR THE COATING OF METALLIC SURFACES WITH AN AQUEOUS COMPOSITION
COMPRISING SILANES, SILANOLS, SILOXANES OR POLYSILOXANES, AND SAID COMPOSITION

(57) Abrégé/Abstract:

The invention relates to a method for coating metallic surfaces with a silane/silanol/siloxane/polysiloxane-containing composition, whereby the composition essentially comprises: a) at least one compound selected from the silanes, silanols, siloxanes and polysiloxanes, b) at least two compounds selected from titanium-, hafnium-, zirconium-, aluminium- or/and boron-containing compounds, optionally c) at least one type of cation selected from cations of metals of the 1st to 3rd and 5th to 8th sub-groups including the lanthanides and the 2nd main group of the periodic table of the elements or/and at least one corresponding compound, d) at least one organic compound selected from monomers, oligomers, polymers, copolymers and block copolymers or/and e) at least one substance affecting the pH value and furthermore, f) water and g) optionally at least one organic solvent. The invention further relates to corresponding aqueous compositions.

(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG

(19) Weltorganisation für geistiges Eigentum
Internationales Büro(43) Internationales Veröffentlichungsdatum
18. Mai 2006 (18.05.2006)

PCT

(10) Internationale Veröffentlichungsnummer
WO 2006/050917 A3

(51) Internationale Patentklassifikation:

C23C 22/34 (2006.01) C09D 5/12 (2006.01)
C23C 22/36 (2006.01)

(74) Anwalt: HÜBNER, Günter; Patente, Marken & Lizenzen, c/o Chemetall GmbH, Trakehner Str. 3, 60487 Frankfurt am Main (DE).

(21) Internationales Aktenzeichen: PCT/EP2005/011954

(81) Bestimmungsstaaten (soweit nicht anders angegeben, für jede verfügbare nationale Schutzrechtsart): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) Internationales Anmeldedatum:

9. November 2005 (09.11.2005)

(84) Bestimmungsstaaten (soweit nicht anders angegeben, für jede verfügbare regionale Schutzrechtsart): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), eurasisches (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), europäisches (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(25) Einreichungssprache:

Deutsch

(26) Veröffentlichungssprache:

Deutsch

(30) Angaben zur Priorität:

10/985,652 10. November 2004 (10.11.2004) US
10 2005 015 573.1 4. April 2005 (04.04.2005) DE
10 2005 015 576.6 4. April 2005 (04.04.2005) DE
10 2005 015 575.8 4. April 2005 (04.04.2005) DE

Veröffentlicht:

— mit internationalem Recherchenbericht

(88) Veröffentlichungsdatum des internationalen
Recherchenberichts: 27. Juli 2006

[Fortsetzung auf der nächsten Seite]

(54) Title: METHOD FOR THE COATING OF METALLIC SURFACES WITH AN AQUEOUS COMPOSITION COMPRISING SILANES SILANOLS SILOXANES AND POLYSILOXANES AND SAID COMPOSITION

(54) Bezeichnung: VERFAHREN ZUR BESCHICHTUNG VON METALLISCHEN OBERFLÄCHEN MIT EINER WÄSSRIGEN SILAN/SILANOL/SILOXAN/ POLYSILOXAN ENTHALTENDEN ZUSAMMENSETZUNG UND DIESE ZUSAMMENSETZUNG

(57) Abstract: The invention relates to a method for coating metallic surfaces with a silane/silanol/siloxane/polysiloxane-containing composition, whereby the composition essentially comprises: a) at least one compound selected from the silanes, silanols, siloxanes and polysiloxanes, b) at least two compounds selected from titanium-, hafnium-, zirconium-, aluminium- or/and boron-containing compounds, optionally c) at least one type of cation selected from cations of metals of the 1st to 3rd and 5th to 8th sub-groups including the lanthanides and the 2nd main group of the periodic table of the elements or/and at least one corresponding compound, d) at least one organic compound selected from monomers, oligomers, polymers, copolymers and block copolymers or/and e) at least one substance affecting the pH value and furthermore, f) water and g) optionally at least one organic solvent. The invention further relates to corresponding aqueous compositions.

(57) Zusammenfassung: Die Erfindung betrifft ein Verfahren zur Beschichtung von metallischen Oberflächen mit einer Silan/Silanol/Siloxan/Polysiloxan enthaltenden Zusammensetzung, wobei die Zusammensetzung im wesentlichen besteht aus: a) mindestens einer Verbindung ausgewählt aus Silanen, Silanolen, Siloxanen und Polysiloxanen und b) mindestens zwei Verbindungen ausgewählt aus Titan-, Hafnium-, Zirkonium-, Aluminium- oder/und Bor-haltigen Verbindungen sowie gegebenenfalls c) aus mindestens einer Art Kationen ausgewählt aus Kationen von Metallen der 1. bis 3. und 5. bis 8. Nebengruppe einschließlich Lanthaniden sowie der 2. Hauptgruppe des Periodensystems der Elemente oder/und aus mindestens einer entsprechenden Verbindung, d) aus mindestens einer organischen Verbindung ausgewählt aus Monomeren, Oligomeren, Polymeren, Copolymeren und Blockcopolymeren oder/und e) aus mindestens einer den pH-Wert beeinflussenden Substanz sowie außerdem aus f) Wasser und g) gegebenenfalls aus mindestens einem organischen Lösemittel. Die Erfindung betrifft außerdem auch entsprechende wässrige Zusammensetzungen.

WO 2006/050917 A3

WO 2006/050917 A3



Zur Erklärung der Zweibuchstaben-Codes und der anderen Abkürzungen wird auf die Erklärungen ("Guidance Notes on Codes and Abbreviations") am Anfang jeder regulären Ausgabe der PCT-Gazette verwiesen.

**METHOD FOR THE COATING OF METALLIC SURFACES WITH AN AQUEOUS
COMPOSITION COMPRISING SILANES, SILANOLS, SILOXANES OR
POLYSILOXANES, AND SAID COMPOSITION**


The invention relates to a process for coating metallic surfaces with an aqueous composition containing at least one silane and/or related compound and at least one other component. The invention further relates to corresponding aqueous compositions and to the use of the substrates coated by the process according to the invention.

The processes most commonly employed hitherto for the treatment of metallic surfaces, especially parts, coil or coil portions made of at least one metallic material, or for the pretreatment of metallic surfaces prior to lacquering are frequently based on the one hand on the use of chromium(VI) compounds, optionally together with diverse additives, or on the other hand on phosphates, e.g. zinc/manganese/nickel phosphates, optionally together with diverse additives.

Because of the toxicological and ecological risks associated especially with processes using chromate or nickel, alternatives to these processes in all the areas of surface technology for metallic substrates have been sought for many years, but it has repeatedly been found

1a

that, in many applications, completely chromate-free or nickel-free processes do not satisfy 100% of the performance spectrum or do not offer the desired safety. Attempts are therefore being made to minimize the chromate contents or nickel contents and to replace Cr⁶⁺ with Cr³⁺ as far as possible. High-quality phosphatizing processes are used especially in the automobile industry, e.g. for the pretreatment of car bodies prior



to lacquering, which have maintained the quality of automobile corrosion protection at a high level. Zinc/manganese/nickel phosphatizing processes are conventionally employed for this purpose. Despite many 5 years of research and development, attempts to phosphatize nickel-free without pronounced quality limitations have proved unsuccessful for multelmetall applications such as those often involved in car bodies, where, in Europe, metallic surfaces of steel, galvanized 10 steel and aluminium or aluminium alloys are typically pretreated in the same bath. However, since nickel contents, even if comparatively small, are now classified as being of greater toxicological concern for the foreseeable future, the question arises as to 15 whether an equivalent corrosion protection can be achieved with other chemical processes.

The use e.g. of silanes/silanols in aqueous compositions for the production of siloxane/polysiloxane-rich 20 anticorrosive coatings is known in principle. For the sake of simplicity, silane/silanol/siloxane/polysiloxane will hereafter often be referred to only as silane. These coatings have proved themselves, but some processes for coating with an aqueous composition 25 containing predominantly silane, in addition to solvent(s), are difficult to apply. These coatings are not always formed with outstanding properties. Moreover, adequate characterization, with the naked eye or optical aids, of the very thin, transparent silane 30 coatings on the metallic substrate, and their defects, can be problematic. The corrosion protection and the lacquer adhesion of the siloxane- and/or polysiloxane-rich coatings formed are often high, but not always; in some cases, even with appropriate application, they are

insufficiently high for particular uses. There is a need for other processes, using at least one silane, which offer a high process safety and a high quality of the coatings produced, especially in respect of corrosion resistance and lacquer adhesion.

10 In the formulation of silane-containing aqueous compositions, it has also proved beneficial to add a small or large amount of at least one component selected from the group comprising organic monomers, oligomers and polymers. The type and amount of silane added to such compositions is in some cases of decisive importance for the outcome. Conventionally, however, the amounts of silane added are comparatively small - usually only up to 5 wt.% of the total solids content - and they then function as a coupling agent, where the adhesion-promoting action should prevail especially between metallic substrate and lacquer and optionally between pigment and organic lacquer constituents, but a slight crosslinking action can also occur in some cases as a secondary effect. Chiefly, very small amounts of silane are added to thermosetting resin systems.

20

The other two patent applications on a similar subject matter submitted to the same patent office on the same date, namely WO 2006/050915 A2 and WO 2006/050916 A2 describe the aqueous compositions, the additions to the aqueous compositions, the steps before, during and after coating, the bath behaviour, the layer formation, the layer properties and the effects determined, particularly in the Examples and Comparative Examples.

It is known from EP 1 017 880 B1 to use an aqueous composition containing a partially hydrolysed aminosilane and a fluorine-containing acid in a mixing ratio of 1:2 to 2:1. This acid is preferably 5 fluorotitanic acid. The coatings produced therewith are good but do not satisfy the prerequisites for high-quality corrosion-resistant coatings in the same way as the extremely high-quality phosphate coatings based on zinc/manganese/nickel phosphate used in automobile 10 construction, especially for multimetal applications. The publication gives no indication that a combination of several acids can be advantageous.

The object was therefore to propose aqueous compositions 15 whose coatings have an environmentally friendly chemical composition and assure a high corrosion resistance, and which are also suitable in multimetal applications in which e.g. steel and zinc-rich metallic surfaces, and optionally also aluminium-rich metallic surfaces, are 20 treated or pretreated in the same bath. The object was also to propose aqueous compositions that are suitable for coating car bodies in automobile construction.

It has now been found that a combination of at least two 25 complex fluorides, especially fluorotitanic acid and fluorozirconic acid, affords an exceptional increase in quality of the coating.

It has now been found not only that it is possible to 30 rinse freshly applied silane-based coatings that have not yet dried thoroughly and hence not yet condensed more substantially, but also that this process sequence is even advantageous, because the coatings produced and rinsed in this way even have better corrosion protection

and better lacquer adhesion, to some extent independently of the chemical composition of the aqueous bath. This contradicts earlier experiences where the rinsing of a freshly applied silane-based coating that 5 has not yet dried more substantially easily and frequently leads to an impairment of the quality of the layer, or even to the removal of part or, occasionally, all of the coating.

10 It has now also been found that it is possible and advantageous to apply a lacquer, a lacquer-like coating, a primer or an adhesive to freshly applied silane-based coatings that have not yet dried thoroughly and hence not yet condensed more substantially, which may also 15 have been rinsed in this state. The application of such compositions to silane-based wet films is advantageous because the coatings produced and rinsed in this way even have better corrosion protection and better lacquer adhesion, to some extent independently of the chemical 20 composition of the aqueous bath.

The object is achieved by a process for coating metallic surfaces with a composition containing silane/silanol/siloxane/polysiloxane, the composition consisting 25 essentially of

- a) at least one compound selected from silanes, silanols, siloxanes and polysiloxanes,
- b) at least two compounds selected from compounds containing titanium, hafnium, zirconium, aluminium and/or boron, and optionally
- c) at least one type of cation selected from cations of metals of subgroups 1 to 3 and 5 to 8, including lanthanides, and of main group 2 of the

periodic table of the elements, and/or at least one corresponding compound,

d) at least one organic compound selected from monomers, oligomers, polymers, copolymers and block copolymers, and/or

e) at least one substance that influences the pH, as well as

f) water, and

g) optionally at least one organic solvent.

10

The object is also achieved with an aqueous composition for coating metallic surfaces which consists essentially of

a) at least one compound selected from silanes, silanols, siloxanes and polysiloxanes, and

b) at least two compounds containing titanium, hafnium, zirconium, aluminium and/or boron, and optionally

c) at least one type of cation selected from cations of metals of subgroups 1 to 3 and 5 to 8, including lanthanides, and of main group 2 of the periodic table of the elements, and/or at least one corresponding compound,

d) at least one organic compound selected from monomers, oligomers, polymers, copolymers and block copolymers, and/or

e) at least one substance that influences the pH, as well as

f) water, and

g) optionally at least one organic solvent.

20

The invention also concerns an aqueous composition containing a silane, silanol, siloxane or polysiloxane for coating a metal surface. The composition comprises:

- a) at least one compound a) selected from silanes, silanols, siloxanes and polysiloxanes, the content of the silane, silanol, siloxane or polysiloxane in the composition ranging from 0.02 to 1 g/l, calculated on the basis of the corresponding silanols;
- b) at least two compounds b) containing a metal selected from the group consisting of titanium, hafnium, zirconium, aluminium and boron, the content of compounds b) in the composition ranging from 0.01 to 15 g/l, calculated as the sum of the corresponding metal, the compounds b) being optionally in a form of a fluoride complex;
- c) at least one cation selected from the group consisting of cations of metals of subgroups 1 to 3 and 5 to 8, including lanthanides, and of main group 2 of the periodic table of the elements, and/or a corresponding compound containing said cation, said at least one cation and/or corresponding compound including manganese and being present in the composition in a range of from 0.01 to 6 g/l;
- d) optionally at least one organic compound selected from the group consisting of monomers, oligomers, polymers, copolymers and block copolymers, with a weight ratio of compounds a) based on silane, silanols, siloxane or polysiloxane, calculated on the basis of the corresponding silanols, to organic compounds d), calculated as added solids, in the composition ranging of from 1:0.05 to 1:12;
- e) optionally at least one substance that influences the pH;
- f) water; and
- g) optionally at least one organic solvent;

with the proviso that the aqueous composition is free of polymeric epoxy compounds.

The invention further concerns a process for coating a metal substrate comprising the step of coating the metal substrate with an aqueous composition as defined above.

The invention also concerns the use of the above defined aqueous composition for coating a metal substrate.

The word "silane" is used here for silanes, silanols, siloxanes, polysiloxanes and their reaction products or derivatives, which often are also "silane" mixtures. In 10 terms of the present patent application, the word "condensation" denotes all forms of crosslinking, further crosslinking and further chemical reactions of the silanes/silanols/siloxanes/polysiloxanes. In terms of the present patent application, the word "coating" refers to the coating formed with the aqueous composition, including the wet film, the dried-on film, the thoroughly dried film, the film dried at elevated temperature and the film optionally crosslinked further by heating and/or irradiation.

20 In terms of the present patent application, the expression "consists essentially of ..." is understood as meaning that the aqueous composition according to the invention can optionally comprise up to 15 wt.%, based on the content of solids and active ingredients of substances a) to d) and f), of other substances that can help to improve the very wide variety of properties of the aqueous composition and/or the coating, and/or to

adapt them to requirements. These substances can include especially additives such as biocide(s) and/or defoamers and/or at least one substance selected from silicon-free compounds having at least one amino, urea and/or ureido group, hydroxide(s), carboxylate(s), nitrate(s) and phosphorus-containing and oxygen-containing compounds, e.g. phosphate(s). This expression preferably comprises, within the up to 15 wt.% of the content of solids and active ingredients of substances a) to d) and f), other substances that essentially are only hydroxide(s), acetate(s) and nitrate(s). Particularly preferably, the content of the other substances is up to 12, up to 10, up to 8, up to 6, up to 4 or up to 2 wt.% of the content of solids and active ingredients of substances a) to d) and f).

The aqueous composition is an aqueous solution, an aqueous dispersion and/or an emulsion. The pH of the aqueous composition is preferably greater than 1.5 and less than 9, particularly preferably in the range from 2 to 7, very particularly preferably in the range from 2.5 to 6.5 and especially in the range from 3 to 6.

Particularly preferably, at least one silane and/or at least one corresponding compound having at least one amino group, urea group and/or ureido group (imino group) is added to the aqueous composition because the coatings produced therewith often exhibit a greater lacquer adhesion and/or a higher affinity for the subsequent lacquer layer. In particular, when using at least one silane and/or at least one corresponding compound having at least one such group, it should be pointed out that condensation may proceed very rapidly at pH values below 2. The proportion of aminosilanes,

ureidosilanes and/or silanes having at least one ureido group, and/or of corresponding silanols, siloxanes and polysiloxanes, relative to the sum of all types of compounds selected from silanes, silanols, siloxanes and polysiloxanes, can preferably be high, particularly preferably above 20, above 30 or above 40 wt.%, calculated as the corresponding silanols, very particularly preferably above 50, above 60, above 70 or above 80 wt.% and possibly even up to 90, up to 95 or up to 100 wt.%.

Preferably, the aqueous composition has a content of silane/silanol/siloxane/polysiloxane a) ranging from 0.005 to 80 g/l, calculated on the basis of the corresponding silanols. This content is particularly preferably in the range from 0.01 to 30 g/l, very particularly preferably in the range from 0.02 to 12 g/l, to 8 g/l or to 5 g/l and especially in the range from 0.05 to 3 g/l or in the range from 0.08 to 2 g/l or to 1 g/l. These ranges of contents refer particularly to bath compositions.

However, if a concentrate is used to prepare a corresponding bath composition, especially by dilution with water and optionally by the addition of at least one other substance, it is advisable, for example, to keep a concentrate A containing silane/silanol/siloxane/polysiloxane a) separate from a concentrate B containing all or almost all of the remaining constituents, and only to bring these components together in the bath. This optionally also makes it possible for at least one silane, silanol, siloxane and/or polysiloxane to be partially or completely in the solid state, to be added in the solid state and/or to be added as a dispersion or

solution. The content of silane/silanol/siloxane/polysiloxane a) in concentrate A preferably ranges from 0.01 to 1000 g/l, calculated on the basis of the corresponding silanols. This content ranges 5 particularly preferably from 0.02 to 200 g/l, very particularly preferably from 0.05 to 120 g/l and especially from 0.1 to 60 g/l. However, the main emphases of the contents in the concentration ranges of concentrate A or the bath can vary with the application.

10

Particularly preferably, the composition contains at least one silane, silanol, siloxane and/or polysiloxane a) having in each case at least one group selected from acrylate groups, alkylaminoalkyl groups, alkylamino 15 groups, amino groups, aminoalkyl groups, succinic anhydride groups, carboxyl groups, epoxy groups, glycidoxy groups, hydroxyl groups, urea groups, isocyanato groups, methacrylate groups and/or ureido groups (imino groups).

20

The silanes, silanols, siloxanes and/or polysiloxanes in the aqueous composition, or at least their compounds added to the aqueous composition, or at least some of these, are preferably water-soluble. In terms of the 25 present patent application, the silanes are regarded as water-soluble if together they have a solubility in water of at least 0.05 g/l, preferably of at least 0.1 g/l and particularly preferably of at least 0.2 g/l or at least 0.3 g/l at room temperature in the 30 composition containing silane/silanol/siloxane/polysiloxane. This does not mean that each individual silane must have this minimum solubility, but that these minimum values are achieved on average.

The aqueous composition preferably contains at least one silane/silanol/siloxane/polysiloxane selected from fluorine-free silanes and the corresponding silanols/siloxanes/polysiloxanes, consisting respectively of at 5 least one acyloxysilane, alkoxy silane, silane having at least one amino group, such as an aminoalkylsilane, silane having at least one succinic acid group and/or succinic anhydride group, bis(silyl)silane, silane having at least one epoxy group, such as a glycidoxysilane, (meth)acrylatosilane, poly(silyl)silane, ureidosilane or vinylsilane, and/or at least one silanol and/or at least one siloxane or polysiloxane whose 10 chemical composition corresponds to that of the silanes mentioned above. It contains at least one silane and/or 15 (in each case) at least one monomeric, dimeric, oligomeric and/or polymeric silanol and/or (in each case) at least one monomeric, dimeric, oligomeric and/or polymeric siloxane, oligomers being understood hereafter to include dimers and trimers. Particularly preferably, 20 the at least one silane or the corresponding silanol/siloxane/polysiloxane has in each case at least one amino group, urea group and/or ureido group.

In particular, this composition contains at least one 25 silane and/or at least one corresponding silanol/siloxane/ polysiloxane selected from the following group or based thereon:

- (3,4-epoxyalkyl)trialkoxysilane,
- 30 (3,4-epoxycycloalkyl)alkyltrialkoxysilane,
- 3-acryloxyalkyltrialkoxysilane,
- 3-glycidoxylalkyltrialkoxysilane,
- 3-methacryloxyalkyltrialkoxysilane,
- 3- (trialkoxysilyl)alkylsuccinosilane,

4-aminodialkylalkyltrialkoxysilane,
4-aminodialkylalkylalkyldialkoxysilane,
aminoalkylaminoalkyltrialkoxysilane,
aminoalkylaminoalkylalkyldialkoxysilane,
5 aminoalkyltrialkoxysilane,
bis(trialkoxysilylalkyl)amine,
bis(trialkoxysilyl)ethane,
gamma-acryloxyalkyltrialkoxysilane,
gamma-aminoalkyltrialkoxysilane,
10 gamma-methacryloxyalkyltrialkoxysilane,
(gamma-trialkoxysilylalkyl)dialkylenetriamine,
gamma-ureidoalkyltrialkoxysilane,
N-2-aminoalkyl-3-aminopropyltrialkoxysilane,
N-(3-trialkoxysilylalkyl)alkylenediamine,
15 N-alkylaminoisoalkyltrialkoxysilane,
N-(aminoalkyl)aminoalkylalkyldialkoxysilane,
N-beta-(aminoalkyl)-gamma-aminoalkyltrialkoxysilane,
N-(gamma-trialkoxysilylalkyl)dialkylenetriamine,
N-phenylaminoalkyltrialkoxysilane,
20 poly(aminoalkyl)alkyldialkoxysilane,
tris(3-trialkoxysilyl)alkylisocyanurate,
ureidoalkyltrialkoxysilane and
vinylacetoxysilane.

25 Particularly preferably, this composition contains at least one silane and/or at least one corresponding silanol/ siloxane/polysiloxane selected from the following group or based thereon:

30 (3,4-epoxybutyl)triethoxysilane,
(3,4-epoxybutyl)trimethoxysilane,
(3,4-epoxycyclohexyl)propyltriethoxysilane,
(3,4-epoxycyclohexyl)propyltrimethoxysilane,
3-acryloxypropyltriethoxysilane,

3-acryloxypropyltrimethoxysilane,
3-aminopropylsilanetriol,
3-glycidoxypolypropyltriethoxysilane,
3-glycidoxypolypropyltrimethoxysilane,
5 3-methacryloxypropyltriethoxysilane,
3-methacryloxypropyltrimethoxysilane,
3-(triethoxysilyl)propylsuccinosilane,
aminoethylaminopropylmethyldiethoxysilane,
aminoethylaminopropylmethyldimethoxysilane,
10 aminopropyltrialkoxysilane,
beta-(3,4-epoxycyclohexyl)ethyltriethoxysilane,
beta-(3,4-epoxycyclohexyl)ethyltrimethoxysilane,
beta-(3,4-epoxycyclohexyl)methyltriethoxysilane,
beta-(3,4-epoxycyclohexyl)methyltrimethoxysilane,
15 bis-1,2-(triethoxysilyl)ethane,
bis-1,2-(trimethoxysilyl)ethane,
bis(trimethoxysilylpropyl)amine,
bis(trimethoxysilylpropyl)amine,
gamma-(3,4-epoxycyclohexyl)propyltriethoxysilane,
20 gamma-(3,4-epoxycyclohexyl)propyltrimethoxysilane,
gamma-acryloxypropyltriethoxysilane,
gamma-acryloxypropyltrimethoxysilane,
gamma-aminopropyltriethoxysilane,
gamma-aminopropyltrimethoxysilane,
25 gamma-methacryloxypropyltriethoxysilane,
gamma-methacryloxypropyltrimethoxysilane,
gamma-ureidopropyltrialkoxysilane,
N-2-aminoethyl-3-aminopropyltriethoxysilane,
N-2-aminoethyl-3-aminopropyltrimethoxysilane,
30 N-2-aminomethyl-3-aminopropyltriethoxysilane,
N-2-aminomethyl-3-aminopropyltrimethoxysilane,
N-(3-(trimethoxysilyl)propyl)ethylenediamine,
N-beta-(aminoethyl)-gamma-aminopropyltriethoxysilane,
N-beta-(aminoethyl)-gamma-aminopropyltrimethoxysilane,

N- (gamma-triethoxysilylpropyl)diethylenetriamine,
N- (gamma-trimethoxysilylpropyl)diethylenetriamine,
N- (gamma-triethoxysilylpropyl)dimethylenetriamine,
N- (gamma-trimethoxysilylpropyl)dimethylenetriamine,
5 poly(aminoalkyl)ethyldialkoxysilane,
poly(aminoalkyl)methyldialkoxysilane,
tris(3- (triethoxysilyl)propyl) isocyanurate,
tris(3- (trimethoxysilyl)propyl) isocyanurate,
ureidopropyltrialkoxysilane and
10 vinyltriacetoxy silane.

Optionally, in specific embodiments, the aqueous composition contains at least one silane/silanol/siloxane/ polysiloxane having a fluorine-containing group. By choosing the silane compound(s) it is also possible to adjust the hydrophilicity/hydrophobicity according to the desired objective.

Preferably, in some embodiments of the aqueous composition, at least one at least partially hydrolysed and/or at least partially condensed silane/silanol/siloxane/polysiloxane is added. In particular, when mixing the aqueous composition, it is optionally possible to add at least one already prehydrolysed, 25 precondensed silane/silanol/siloxane/ polysiloxane. Such an addition is particularly preferred.

In some embodiments, at least one at least extensively and/or completely hydrolysed and/or at least extensively and/or completely condensed silane/silanol/siloxane/polysiloxane can be added to the aqueous composition. In many embodiments, a non-hydrolysed silane bonds to the metallic surface less well than an at least partially hydrolysed silane/silanol. In many

embodiments, an extensively hydrolysed and uncondensed or only slightly condensed silane/silanol/siloxane bonds to the metallic surface markedly better than an at least partially hydrolysed and extensively condensed 5 silane/silanol/ siloxane/polysiloxane. In many embodiments, a completely hydrolysed and extensively condensed silanol/siloxane/ polysiloxane exhibits only a slight tendency to become chemically bonded to the metallic surface.

10

In some embodiments, at least one siloxane and/or polysiloxane containing little or no silanes/silanols - e.g. less than 20 or less than 40 wt.% of the sum of silane/silanol/siloxane/polysiloxane - can be added to 15 the aqueous composition in addition and/or as an alternative to silane(s)/silanol(s). The siloxane or polysiloxane is preferably short-chain and is preferably applied by means of a rollcoater treatment. This then optionally affects the coating by strengthening the 20 hydrophobicity and increasing the blank corrosion protection.

Preferably, the aqueous composition contains at least two or even at least three titanium, hafnium, zirconium, 25 aluminium and boron compounds, it being possible for these compounds to differ in their cations and/or anions. The aqueous composition, especially the bath composition, preferably contains at least one complex fluoride b) and particularly preferably at least two 30 complex fluorides selected from complex fluorides of titanium, hafnium, zirconium, aluminium and boron. Preferably, their difference lies not only in the type of complex. The aqueous composition, especially the bath composition, preferably has a content of compounds

b), selected from titanium, hafnium, zirconium, aluminium and boron compounds, ranging from 0.01 to 50 g/l, calculated as the sum of the corresponding metals. This content ranges particularly preferably from 0.1 to 30 g/l, very particularly preferably from 0.3 to 15 g/l and especially from 0.5 to 5 g/l. On the other hand, the content of titanium, hafnium, zirconium, aluminium and boron compounds in the concentrate, for example in concentrate B free of silane/silanol/siloxane/polysiloxane, can preferably range from 1 to 300 g/l, calculated as the sum of the corresponding metals. This content ranges particularly preferably from 2 to 250 g/l, very particularly preferably from 3 to 200 g/l and especially from 5 to 150 g/l. The composition preferably contains no aluminium phosphate, no titanium sulfate, no zirconium nitrate and/or no zirconium chloride.

Preferably, the composition contains at least one complex fluoride, the content of complex fluoride(s) ranging especially from 0.01 to 100 g/l, calculated as the sum of the corresponding metal complex fluorides as MeF_6 . This content ranges preferably from 0.03 to 70 g/l, particularly preferably from 0.06 to 40 g/l and very particularly preferably from 1 to 10 g/l. The complex fluoride can be present especially as MeF_4 and/or MeF_6 , but also in other states or intermediate states. Advantageously, at least one titanium complex fluoride and at least one zirconium complex fluoride are simultaneously present in many embodiments. It can be advantageous in many cases here to have at least one MeF_4 complex and at least one MeF_6 complex present in the composition simultaneously, especially a TiF_6 complex and a ZrF_4 complex. It can be advantageous here to adjust

these proportions of complex fluorides in the concentrate and transfer them to the bath in this way. On the other hand, the content of these compounds in the concentrate, for example in concentrate B free of 5 silane/silanol/siloxane/polysiloxane, can preferably range from 0.05 to 500 g/l, calculated as the sum of MeF_6 . This content ranges particularly preferably from 0.05 to 300 g/l, very particularly preferably from 0.05 to 150 g/l and especially from 0.05 to 50 g/l.

10

Surprisingly, the individual complex fluorides do not adversely affect one another when combined, but exhibit an unexpected positive reinforcing effect. These 15 additions based on complex fluoride obviously act in a similar or identical manner. Surprisingly, if a combination of complex fluorides based on titanium and zirconium is used rather than a complex fluoride based only on titanium or only on zirconium, the results obtained are always noticeably better than in the case 20 of only one of these additions. A complex fluoride based on titanium or zirconium probably deposits on the surface as oxide and/or hydroxide.

It has now been established, surprisingly, that a good 25 multometal treatment with a single aqueous composition is only possible if a complex fluoride has been used, and that a very good multometal treatment with a single aqueous composition is only possible if at least two different complex fluorides are used, e.g. those based 30 on titanium and zirconium. In a very wide variety of experiments, the complex fluorides used individually never gave results equivalent to those for the combination of these two complex fluorides, independently of what other additions were made.

As an alternative or in addition to at least one complex fluoride, it is also possible to add another type of titanium, hafnium, zirconium, aluminium and/or boron compound, for example at least one hydroxycarbonate 5 and/or at least one other water-soluble or sparingly water-soluble compound, e.g. at least one nitrate and/or at least one carboxylate.

It has now been shown, however, that an addition of 10 silicon hexafluoride as the only complex fluoride added to an aqueous composition has a different and sometimes markedly poorer effect than the additions of other complex fluorides.

15 Preferably, only types of cation, or corresponding compounds, from the group comprising magnesium, calcium, yttrium, lanthanum, cerium, vanadium, niobium, tantalum, molybdenum, tungsten, manganese, iron, cobalt, nickel, copper, silver and zinc, and particularly preferably 20 from the group comprising magnesium, calcium, yttrium, lanthanum, cerium, vanadium, molybdenum, tungsten, manganese, iron, cobalt, copper and zinc, are selected as cations and/or corresponding compounds c), trace contents being excepted.

25 On the other hand, it has been shown, surprisingly, that iron and zinc cations, and therefore also the presence in the bath of corresponding compounds which can make an increased contribution, in the particular case of acidic 30 compositions, to dissolving such ions out of the metallic surface, do not have an adverse effect, over wide ranges of contents, on the bath behaviour, the layer formation or the layer properties.

Preferably, the aqueous composition, especially the bath composition, has a content of cations and/or corresponding compounds c) ranging from 0.01 to 20 g/l, calculated as the sum of the metals. This content

5 ranges particularly preferably from 0.03 to 15 g/l, very particularly preferably from 0.06 to 10 g/l and especially from 0.1 to 6 g/l. On the other hand, the content of these compounds in the concentrate, for example in concentrate B free of silane/silanol/

10 siloxane/polysiloxane, can preferably range from 1 to 240 g/l, calculated as the sum of the metals. This content ranges particularly preferably from 2 to 180 g/l, very particularly preferably from 3 to 140 g/l and especially from 5 to 100 g/l.

15

The composition preferably contains at least one type of cation selected from cations of cerium, chromium, iron, calcium, cobalt, copper, magnesium, manganese, molybdenum, nickel, niobium, tantalum, yttrium, zinc, tin and other lanthanides, and/or at least one corresponding compound. Preferably, not all the cations present in the aqueous composition have been not only dissolved out of the metallic surface by the aqueous composition, but also at least partially or even extensively added to the aqueous composition. A freshly prepared bath can therefore be free of certain cations or compounds which are only freed or formed from reactions with metallic materials or from reactions in the bath.

25

Surprisingly, the addition of manganese ions or at least one manganese compound has been shown to be particularly advantageous. Although apparently no manganese compound or almost no manganese compound is deposited on the

metallic surface, this addition clearly promotes the deposition of silane/silanol/siloxane/polysiloxane, thereby significantly improving the properties of the coating. Unexpectedly, an addition of magnesium ions or 5 at least one magnesium compound has also been shown to be advantageous, since this addition promotes the deposition of titanium and/or zirconium compounds, probably as oxide and/or hydroxide, on the metallic surface and thus markedly improves the properties of the 10 coating. A combined addition of magnesium and manganese improves the coatings still further in some cases. By contrast, an addition of only 0.02 g/l of copper ions has not yet been shown to have a significant influence. If the calcium ion content is increased, care should be 15 taken to ensure that a complex fluoride is not destabilized by the formation of calcium fluoride.

Preferably, the composition has a content of at least one type of cation and/or corresponding compounds, 20 selected from alkaline earth metal ions, ranging from 0.01 to 50 g/l, calculated as corresponding compounds, particularly preferably from 0.03 to 35 g/l, very particularly preferably from 0.06 to 20 g/l and especially from 0.1 to 8 g/l. The alkaline earth metal 25 ions or corresponding compounds can help to reinforce the deposition of compounds based on titanium and/or zirconium, which is often advantageous especially for increasing the corrosion resistance. On the other hand, the content of these compounds in the concentrate, for 30 example in concentrate B free of silane/silanol/siloxane/polysiloxane, can range preferably from 0.1 to 100 g/l, calculated as the sum of the corresponding compounds, particularly preferably from 0.3 to 80 g/l,

very particularly preferably from 0.6 to 60 g/l and especially from 0.5 to 30 g/l.

Preferably, the composition has a content of at least 5 one type of cation, selected from cations of iron, cobalt, magnesium, manganese, nickel, yttrium, zinc and lanthanides, and/or of at least one corresponding compound c), ranging especially from 0.01 to 20 g/l, calculated as the sum of the metals. This content 10 ranges particularly preferably from 0.03 to 15 g/l, very particularly preferably from 0.06 to 10 g/l and especially from 0.1 to 6 g/l. On the other hand, the content of these compounds in the concentrate, for example in concentrate B free of silane/silanol/siloxane/polysiloxane, can preferably range from 1 to 15 240 g/l, calculated as the sum of the metals. This content ranges particularly preferably from 2 to 180 g/l, very particularly preferably from 3 to 140 g/l and especially from 5 to 100 g/l.

20 Preferably, the composition contains at least one organic compound d) selected from monomers, oligomers, polymers, copolymers and block copolymers, especially at least one compound based on acrylic, epoxide and/or 25 urethane. At least one organic compound having at least one silyl group can also be used here, in addition or as an alternative. It is preferred in some embodiments to use such organic compounds having a content or a higher content of OH groups, amine groups, carboxylate groups, 30 isocyanate groups and/or isocyanurate groups.

Preferably, the composition has a content of at least one organic compound d), selected from monomers, oligomers, polymers, copolymers and block copolymers,

ranging from 0.01 to 200 g/l, calculated as added solids. This content ranges particularly preferably from 0.03 to 120 g/l, very particularly preferably from 0.06 to 60 g/l and especially from 0.1 to 20 g/l. In 5 some embodiments, such organic compounds can help to homogenize the formation of the coating. These compounds can contribute to the formation of a more compact, denser, more chemically resistant and/or more water-resistant coating, compared with coatings based on 10 silane/silanol/siloxane/polysiloxane etc. without these compounds. The hydrophilicity/hydrophobicity can also be adjusted according to the desired objective by the choice of organic compound(s). However, a strongly hydrophobic coating is problematic in some applications 15 because of the required bonding of especially water-based lacquers, although a stronger hydrophobicity can be established in the case of powder coatings in particular. When using an addition of at least one organic compound, a combination with compounds having a 20 certain functionality can prove particularly advantageous, examples being compounds based on amines/diamines/polyamines/urea/imines/diimines/polyimines or derivatives thereof, compounds based in particular on capped isocyanate/isocyanurate/melamine 25 compounds, and compounds with carboxyl and/or hydroxyl groups, e.g. carboxylates, longer-chain sugar-like compounds, e.g. (synthetic) starch, cellulose, saccharides, long-chain alcohols and/or derivatives thereof. The long-chain alcohols added are especially 30 those having 4 to 20 C atoms, such as a butanediol, a butyl glycol, a butyl diglycol, an ethylene glycol ether such as ethylene glycol monobutyl ether, ethylene glycol monoethyl ether, ethylene glycol monomethyl ether, ethyl glycol propyl ether, ethylene glycol hexyl ether,

diethylene glycol methyl ether, diethylene glycol ethyl ether, diethylene glycol butyl ether, diethylene glycol hexyl ether, or a propylene glycol ether such as propylene glycol monomethyl ether, dipropylene glycol monomethyl ether, tripropylene glycol monomethyl ether, propylene glycol monobutyl ether, dipropylene glycol monobutyl ether, tripropylene glycol monobutyl ether, propylene glycol monopropyl ether, dipropylene glycol monopropyl ether, tripropylene glycol monopropyl ether or propylene glycol phenyl ether, trimethylpentanediol diisobutyrate, a polytetrahydrofuran, a polyetherpolyol and/or a polyesterpolyol.

The weight ratio of compounds based on silane/silanol/siloxane/polysiloxane, calculated on the basis of the corresponding silanols, to compounds based on organic polymers, calculated as added solids, in the composition, ranges preferably from 1:0.05 to 1:3, particularly preferably from 1:0.1 to 1:2 and very particularly preferably from 1:0.2 to 1:1. In some embodiments, this ratio ranges preferably from 1:0.05 to 1:30, particularly preferably from 1:0.1 to 1:2, very particularly preferably from 1:0.2 to 1:20 and especially from 1:0.25 to 1:12, from 1:0.3 to 1:8 or from 1:0.35 to 1:5.

It has now been found, surprisingly, that an addition of organic polymer and/or copolymer, in particular, markedly improves the corrosion resistance, especially on iron and steel, and is of particular advantage for a higher process safety and constantly good coating properties.

Acetic acid, for example, can be added as a catalyst for the hydrolysis of a silane. The pH of the bath can be raised e.g. with ammonia/ammonium hydroxide, an alkali-metal hydroxide and/or a compound based on amine, such 5 as monoethanolamine, while the pH of the bath is preferably lowered with acetic acid, hydroxyacetic acid and/or nitric acid. Such additions belong to the substances that influence the pH.

10 The composition optionally has a content of silicon-free compounds having at least one amino, urea and/or ureido group, especially amine/diamine/polyamine/urea/imine/diimine/polyimine compounds and derivatives thereof, ranging preferably from 0.01 to 10 g/l, calculated as 15 the sum of the corresponding compounds. This content ranges particularly preferably from 0.03 to 7 g/l, very particularly preferably from 0.06 to 4 g/l and especially from 0.1 to 1 g/l. It is preferable to add at least one compound such as aminoguanidine,

20 monoethanolamine, triethanolamine and/or a branched urea derivative with an alkyl radical. An addition of aminoguanidine, for example, markedly improves the properties of the coatings according to the invention.

25 On the other hand, the composition can also contain nitroguanidine. It has now been found, surprisingly, that an addition of nitroguanidine, in particular, to the aqueous composition makes the appearance of the 30 coatings according to the invention very homogeneous and perceptibly increases the coating quality. This has a very positive effect especially on "sensitive" metallic surfaces such as sand-blasted iron or steel surfaces. An addition of nitroguanidine noticeably improves the properties of the coatings according to the invention.

A content of nitrite can markedly reduce the rusting tendency particularly of steel surfaces. It has now been found, unexpectedly, that an addition of hydrogen peroxide to the aqueous composition according to the 5 invention improves the optical quality of the coated substrates.

Optionally, the composition also contains phosphorus-containing compounds, especially as oxyanions and/or 10 corresponding compounds, but preferably no aluminium phosphate. This content ranges particularly preferably from 0.05 to 8 g/l, very particularly preferably from 0.1 to 5 g/l and especially from 0.2 to 2 g/l. These compounds can be at least one orthophosphate, at least 15 one oligomeric and/or polymeric phosphate and/or at least one phosphonate. The at least one orthophosphate and/or salts thereof and/or esters thereof can be e.g. at least one alkali-metal phosphate, at least one orthophosphate containing iron, manganese and/or zinc, 20 and/or at least one of their salts and/or esters.

Instead or in addition, it is also possible to add in each case at least one metaphosphate, polyphosphate, pyrophosphate, triphosphate and/or salts thereof and/or esters thereof. As phosphonate it is possible to add 25 e.g. at least one phosphonic acid, such as at least one alkyldiphosphonic acid, and/or salts thereof and/or esters thereof. It has now been found, surprisingly, that an addition of orthophosphate to the aqueous composition according to the invention markedly improves 30 the quality of the coatings, especially on electro-galvanized substrates. The phosphorus-containing compounds of this group of substances are not surfactants.

Optionally, the aqueous composition contains at least one type of anion selected from carboxylates, e.g. acetate, butyrate, citrate, formate, fumarate, glycolate, hydroxyacetate, lactate, laurate, maleate, 5 malonate, oxalate, propionate, stearate and tartrate, and/or at least one corresponding undissociated and/or only partially dissociated compound.

Preferably, the composition has a content of carboxylate 10 anions and/or carboxylate compounds ranging from 0.01 to 3 g/l, calculated as the sum of the corresponding compounds. This content ranges particularly preferably from 0.05 to 1.5 g/l, very particularly preferably from 0.1 to 0.8 g/l and especially from 0.15 to 0.6 g/l.

15 Particularly preferably, in each case at least one citrate, lactate, oxalate and/or tartrate can be added as carboxylate. The addition of at least one carboxylate can help to complex a cation and keep it in solution more easily, thereby making it possible to 20 increase the stability and controllability of the bath. Surprisingly, it has been found that the bonding of a silane to the metallic surface can in some cases be facilitated and improved by a carboxylate content.

25 Optionally, the composition also contains nitrate. The nitrate content preferably ranges from 0.01 to 2 g/l, calculated as the sum of the corresponding compounds. This content ranges particularly preferably from 0.03 to 1.2 g/l, very particularly preferably from 0.06 to 30 0.8 g/l and especially from 0.1 to 0.5 g/l. Nitrate can help to homogenize the formation of the coating, especially on steel. Nitrite may be converted to nitrate, usually only partially. Nitrate can be added especially as an alkali-metal nitrate, ammonium nitrate,

a heavy metal nitrate, nitric acid and/or a corresponding organic compound. The nitrate can markedly reduce the rusting tendency, especially on steel and iron surfaces. The nitrate can optionally 5 contribute to the formation of a defect-free coating and/or an exceptionally even coating that may be free of optically recognizable marks.

Optionally, the composition contains at least one type 10 of cation selected from alkali-metal ions, ammonium ions and corresponding compounds, especially potassium and/or sodium ions, or at least one corresponding compound.

Optionally, the composition has a free fluoride content 15 ranging from 0.001 to 3 g/l, calculated as F^- . This content ranges preferably from 0.01 to 1 g/l, particularly preferably from 0.02 to 0.5 g/l and very particularly preferably up to 0.1 g/l. It has been determined that it is advantageous in many embodiments 20 to have a low free fluoride content in the bath because the bath can then be stabilized in many embodiments. An excessively high free fluoride content can sometimes adversely affect the deposition rate of cations. In addition, undissociated and/or uncomplexed fluoride can 25 also occur in many cases, especially in the range from 0.001 to 0.3 g/l. On the other hand, the content of these compounds in the concentrate, for example in concentrate B free of silane/silanol/siloxane/polysiloxane, can preferably range from 0.05 to 5 g/l, 30 calculated as the sum of MeF_6 . This content ranges particularly preferably from 0.02 to 3 g/l, very particularly preferably from 0.01 to 2 g/l and especially from 0.005 to 1 g/l. Such an addition is

preferably made in the form of hydrofluoric acid and/or its salts.

Optionally, the composition has a content of at least 5 one fluoride-containing compound and/or fluoride anions, calculated as F^- and without including complex fluorides, especially at least one fluoride from alkali metal fluoride(s), ammonium fluoride and/or hydrofluoric acid, ranging particularly preferably from 0.001 to 12 g/l, 10 very particularly preferably from 0.005 to 8 g/l and especially from 0.01 to 3 g/l. The fluoride ions or corresponding compounds can help to control the deposition of the metal ions on the metallic surface so that, for example, the deposition of the at least one 15 zirconium compound can be increased or decreased as required. On the other hand, the content of these compounds in the concentrate, for example in concentrate B free of silane/silanol/siloxane/polysiloxane, can preferably range from 0.1 to 100 g/l, calculated as the 20 sum of the corresponding compounds. This content ranges particularly preferably from 0.3 to 80 g/l, very particularly preferably from 0.6 to 60 g/l and especially from 1 to 30 g/l. The weight ratio of the sum of the complex fluorides, calculated as the sum of 25 the associated metals, to the sum of the free fluorides, calculated as F^- , is preferably greater than 1:1, particularly preferably greater than 3:1, very particularly preferably greater than 5:1 and especially greater than 10:1.

30

In the process according to the invention, the aqueous composition can optionally contain at least one compound selected from alkoxides, carbonates, chelates,

surfactants and additives, e.g. biocides and/or defoamers.

The aforementioned additions normally have a beneficial
5 effect in the aqueous compositions according to the invention in that they help to further improve the good properties of the aqueous base composition according to the invention consisting of components a), b) and solvent(s). These additions normally act in the same
10 way if only one titanium compound or only one zirconium compound, or a combination thereof, is used. However, it has been shown, surprisingly, that the combination of at least one titanium compound and at least one zirconium compound, especially as complex fluorides,
15 significantly improves the properties particularly of the coatings produced therewith. Surprisingly, the different additives thus function as in a modular system and make a substantial contribution to optimization of the particular coating. In the specific case where a
20 so-called multimetal mix is used, as often occurs in the pretreatment of car bodies and in the treatment or pretreatment of different hardware or assembly parts, the aqueous composition according to the invention has proved very suitable since the composition containing
25 the various additives can be specifically optimized to the particular multimetal mix and its peculiarities and requirements.

With the process according to the invention, a mix of
30 different metallic materials, e.g. as in the case of car bodies or different hardware, can be coated with the aqueous coating in the same bath. Here, for example, any desired mix of substrates with metallic surfaces, selected from cast iron, steel, aluminium, aluminium

alloys, magnesium alloys, zinc and zinc alloys, can be coated simultaneously and/or successively according to the invention, it being possible for the substrates to be at least partially coated with metal and/or to 5 consist at least partially of at least one metallic material.

Provided at least one other component and/or traces of other substances are not present, the remainder to 10 1000 g/l consists of water or of water and at least one organic solvent such as ethanol, methanol, isopropanol or dimethylformamide (DMF). Preferably, in most embodiments, the organic solvent content is particularly low or zero. Because of the hydrolysis of the at least 15 one silane present, a content especially of ethanol and/or methanol can appear. It is particularly preferable not to add any organic solvent.

The composition is preferably free or substantially free 20 of all types of particles, or particles with a mean diameter greater than 0.02 μm , which might be added e.g. in the form of oxides such as SiO_2 .

The composition is preferably poor in, substantially 25 free of or free of larger contents or contents exceeding 1 g/l of water hardeners such as calcium. The aqueous composition is preferably free of or poor in lead, cadmium, chromate, cobalt, nickel and/or other toxic heavy metals. Preferably, such substances are not 30 deliberately added, although at least one heavy metal, dissolved out of a metallic surface, can be entrained e.g. from another bath and/or can occur as an impurity. The composition is preferably poor in, substantially free of or totally free of bromide, chloride and iodide,

since these can contribute to corrosion under certain circumstances.

The layer thickness of the coatings produced according
5 to the invention ranges preferably from 0.005 to 0.3 μm , particularly preferably from 0.01 to 0.25 μm and very particularly preferably from 0.02 to 0.2 μm , and is frequently about 0.04 μm , about 0.06 μm , about 0.08 μm , about 0.1 μm , about 0.12 μm , about 0.14 μm , about 10 0.16 μm or about 0.18 μm . The coatings containing organic monomer, oligomer, polymer, copolymer and/or block copolymer are often somewhat thicker than those that are free or almost free thereof.

15 Preferably, the composition forms a coating with a layer weight which, based only on the titanium and/or zirconium content, ranges from 1 to 200 mg/m^2 , calculated as elemental titanium. This layer weight ranges particularly preferably from 5 to 150 mg/m^2 and very 20 particularly preferably from 8 to 120 mg/m^2 and, in particular, is about 10, about 20, about 30, about 40, about 50, about 60, about 70, about 80, about 90, about 100 or about 110 mg/m^2 .

25 Preferably, the composition forms a coating with a layer weight which, based only on siloxanes/polysiloxanes, ranges from 0.2 to 1000 mg/m^2 , calculated as the corresponding extensively condensed polysiloxane. This layer weight ranges particularly preferably from 2 to 30 200 mg/m^2 and very particularly preferably from 5 to 150 mg/m^2 and, in particular, is about 10, about 20, about 30, about 40, about 50, about 60, about 70, about

80, about 90, about 100, about 110, about 120, about 130 or about 140 mg/m².

If necessary, the coating produced with the aqueous
5 composition according to the invention can then be coated with at least one primer, lacquer or adhesive and/or with a lacquer-like organic composition, optionally at least one of these other coatings being cured by heating and/or irradiation.

10

The metallic substrates coated by the process according to the invention can be used in the automobile industry, for railway vehicles, in the aerospace industry, in apparatus engineering, in mechanical engineering, in the
15 building industry, in the furniture industry, for the manufacture of crash barriers, lamps, profiles, sheathing or hardware, for the manufacture of car bodies or body parts, individual components or preassembled/connected elements, preferably in the automobile or
20 aeronautical industry, or for the manufacture of appliances or installations, especially household appliances, control devices, testing devices or structural elements.

25 An addition of manganese has surprisingly proved particularly advantageous: Although apparently no or almost no manganese compound is deposited on the metallic surface, the addition greatly promotes the deposition of silane/ silanol/siloxane/polysiloxane on
30 the metallic surface. When adding nitroguanidine, it was found, surprisingly, that the optical characteristics of the coated metallic sheets are very uniform, especially on sensitive surfaces such as sand-blasted iron or steel surfaces. Unexpectedly, an

addition of nitrite markedly reduced the rusting tendency of steel substrates. It was found, surprisingly, that every addition mentioned in the present patent application as having a significantly 5 positive effect has an additive effect on improving the coating according to the invention: Choosing several additions, in a similar manner to a modular system, enables the different properties, especially of a multimetal system, to be further optimized.

10

It has now been found, surprisingly, that a good multimetal treatment with a single aqueous composition is only possible if a complex fluoride has been used, and that a very good multimetal treatment with a single 15 aqueous composition is only possible if at least two different complex fluorides are used, e.g. those based on titanium and zirconium. In a very wide variety of experiments, the results obtained for complex fluorides used individually were never as good as those obtained 20 for the combination of these two complex fluorides, independently of what other additions were made.

The possibility of such a large increase in quality of aqueous compositions containing silane/silanol/siloxane/polysiloxane could not be anticipated. Surprisingly, 25 however, a marked increase in the level of quality in all tests was also found when using aqueous compositions based on a silane and only one titanium-based or zirconium-based complex fluoride (cf. Comparative 30 Examples CE 3 and CE 4).

It was further surprising that, when testing the lacquer adhesion, stone chip resistance scores of 1 or 2 were obtained, even on steel: Steel has proved to be the most

problematic material for aqueous compositions based on a silane and only one titanium-based or zirconium-based complex fluoride, especially in terms of the corrosion resistance (cf., for example, E 2).

5

In the case of aluminium and aluminium alloys, experience shows that the CASS test is problematic, but this also turned out markedly better than expected with the compositions according to the invention.

10

Examples and Comparative Examples:

15 The Examples according to the invention (E) and Comparative Examples (CE) described below are intended to illustrate the subject matter of the invention in greater detail.

20 The aqueous bath compositions are prepared as mixtures according to Table 1 using already prehydrolysed silanes. They each contain predominantly one silane and optionally also have small contents of at least one other similar silane, where here again the word silane is used rather than silane/silanol/siloxane/polysiloxane by way of simplification, and where normally these 25 various compounds, sometimes in a larger number of similar compounds, also pass through into the formation of the coating, so there are often several similar compounds present in the coating as well. Depending on the silane, the prehydrolysis step can also take several 30 days at room temperature, with vigorous stirring, if the silanes to be used are not already present in prehydrolysed form. The prehydrolysis of the silane is carried out by placing the silane in excess water and optionally catalysing with acetic acid. Acetic acid was

added in only a few embodiments for the sole purpose of adjusting the pH. In some embodiments, acetic acid is already present as a hydrolysis catalyst. Ethanol is formed in the hydrolysis, but is not added. The 5 finished mixture is used fresh.

Then, for each test, at least 3 sheets of cold-rolled steel (CRS), aluminium alloy Al 6016, steel hot-dip galvanized or electrogalvanized on both sides, or 10 Galvaneal® (ZnFe layer on steel), previously cleaned with an aqueous alkaline cleaner and rinsed with industrial water and then with demineralized water, are brought into contact on both sides with the appropriate pretreatment liquid in Table 1 at 25°C by spraying, 15 dipping or rollcoater treatment. The sheets treated in this way were then dried at 90°C PMT and subsequently lacquered with a cathodic automobile dip lacquer (CDL). These sheets were then provided with a complete 20 commercial automotive lacquer system (filler, covering lacquer, transparent lacquer; overall thickness of stacked layers, including CDL, approx. 105 µm) and tested for their corrosion protection and lacquer adhesion. The compositions and properties of the treatment baths and the properties of the coatings are 25 collated in Table 1.

The organofunctional silane A is an amino-functional trialkoxysilane and has one amino group per molecule. Like all the silanes used here, it is in extensively or 30 almost completely hydrolysed form in the aqueous solution. The organofunctional silane B has one terminal amino group and one ureido group per molecule. The non-functional silane C is a bis-trialkoxysilane;

the corresponding hydrolysed molecule has up to 6 OH groups on two silicon atoms. The polysiloxane D has a relatively short-chain molecule with a terminal OH group. It renders the coating hydrophobic.

5

The complex fluorides of aluminium, silicon, titanium or zirconium are used extensively in the form of an MeF_6 complex, but the complex fluorides of boron are used extensively in the form of an MeF_4 complex. Manganese is 10 added to the particular complex fluoride solution as metallic manganese and dissolved therein. This solution is mixed with the aqueous composition. If no complex fluoride is used, manganese nitrate is added. Copper is added as copper(II) nitrate and magnesium as magnesium 15 nitrate. Iron and zinc are mixed in as the nitrates. Nitrate on its own is preferably added as sodium nitrate or nitric acid. Epoxy polymer A contains OH^- and isocyanate groups and can therefore subsequently be chemically crosslinked at temperatures above 100°C. 20 Epoxy polymer B also contains OH^- and isocyanate groups and likewise can therefore subsequently be chemically crosslinked at temperatures above 100°C. Polymer B is more stable than polymer A in the bath when using the chosen compositions according to the invention. 25 Silylated epoxy polymer C has a small content of OH^- and isocyanate groups and can therefore also subsequently be chemically crosslinked at temperatures above 100°C.

The silanes present in the aqueous composition – 30 concentrate and/or bath – are monomers, oligomers, polymers, copolymers and/or reaction products with other components due to hydrolysis reactions, condensation reactions and/or other reactions. The reactions take place especially in the solution, during drying or

optionally also during curing of the coating, especially at temperatures above 70°C. All the concentrates and baths proved to be stable for one week without undergoing changes or precipitations. No ethanol was added. Ethanol contents in the compositions originated only from chemical reactions.


10 In the majority of Examples and Comparative Examples, the pH is adjusted with ammonia if at least one complex fluoride is present and with an acid in other cases. All the baths have a good solution quality and almost always a good stability. There are no precipitations in the baths. After the coating step with the silane-containing solution, the coating is firstly rinsed briefly once with demineralized water. The coated sheets are then dried at 120°C in an oven for 5 minutes. Because of the interference colours, only the coatings on steel can be significantly examined visually, allowing an assessment of the homogeneity of the coating. The coatings without any complex fluoride content are very inhomogeneous. Surprisingly, a coating with titanium complex fluoride and zirconium complex fluoride proved to be markedly more homogeneous than when only one of these complex fluorides had been applied. An addition of nitroguanidine, nitrate or nitrite likewise improves the homogeneity of the

20

37a

coating. In some cases the layer thickness increases with the concentration of these substances.

Table 1: Bath compositions in g/l, based on solids contents or, in the case of silanes, on the weight of the hydrolysed silanes; residual content: water and usually a very small amount of ethanol; process data and properties of the coatings.



Example / CE	CE 1	CE 2	CE 3	CE 4	CE 5	E 1	E 2	E 3	E 4	E 5	E 6	E 7	E 8	E 9	E 10	E 11	E 12	E 13	E 14	E 15	CE 5
Organofunct. silane A	0.2	-	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.1	0.3	0.2	0.1	-	-	0.2	
Organofunct. silane B	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	0.1	-	
Non-funct. silane C	-	0.2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	0.1	-	
H ₂ TiF ₆ as Ti	-	-	0.2	-	0.1	0.1	0.5	0.5	0.3	0.2	0.3	0.2	0.3	0.2	0.4	0.2	0.2	0.2	0.2	0.2	
H ₂ ZrF ₆ as Zr	-	-	0.2	0.1	0.5	0.1	0.5	0.3	0.2	0.2	0.4	0.3	0.3	0.2	0.2	0.2	0.2	0.2	0.2	-	
Mn	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	0.3	
Acetic acid	-	0.02	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	0.01	-	
pH	10.5	5	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4.5	
BMW cross-cut test: score																					
Steel	4	3	5	3	2	0	1-2	1	1-2	2	2	1	1	1	2	1	1	1	1	2-3	
E-zinc on steel	3	4	4	4	2	2	0	0	0	1	1-2	1	0	1-2	0	2	1	2	1	2	3
Hot-dip zinc on steel	2	5	4	4	1-2	1	0	0	0	1	0	0	0	1	0	1	0	1	0	3	
Al 6016	2	3	2	2	1-2	0	1	0	1	1	0-1	1	1	0	1	1	1	1	0	2	
Galvaneal®	1	2	1	2	1	0	0	0	0	1	0	0	1	0	0	1	0	0-1	0	1	

Example / CE	CE 1	CE 2	CE 3	CE 4	E 1	E 2	E 3	E 4	E 5	E 6	E 7	E 8	E 9	E 10	E 11	E 12	E 13	E 14	E 15	CE 5
10 VDA cycles, mm disbonding																				
Steel	8	7	7	4	2	1.5	2.5	1.5	3	3	1.5	2	1.5	2.5	2	2.5	1.8	3	7	
E-zinc on steel	5	5	3	4	1.5	2	1	1	2	1.5	1.5	2	1.5	2.5	1.5	2	1	2.5	5	
Hot-dip zinc on steel	4	5	2.5	3.5	<1	<1	<1	<1	<1	<1	<1	<1	<1	<1	<1	1	<1	1	2	4
Galvaneal®	2	3	2	1.5	<1	<1	<1	<1	<1	<1	<1	<1	<1	<1	<1	1	1	0	0	3
Stone chip resistance after VDA stress: score																				
Steel	5	5	4	4	2-3	1	3	1	1	2-3	2	1-2	2	1	2	1	2	1-2	3	5
E-zinc on steel	5	5	3	4	2	2-3	1	1	1-2	2	1	1-2	1	1	2	1	2	1	2	4
Hot-dip zinc on steel	5	5	3	4	2	2	1	1	1	1	1	0-1	1	0	1	1	1	1	1	4
Galvaneal®	4	4	2	3	2	1	1	0	0	1-2	1	0	0	1	0	1	1	1	1	4
Salt spray test, 1008 h																				
Steel	7	8	4	3.5	3	2	2.5	2	1.8	2	2.5	2	2	2.5	3	2	2	1.5	2.5	7

Example / CE	CE 1	CE 2	CE 3	CE 4	E 1	E 2	E 3	E 4	E 5	E 6	E 7	E 8	E 9	E 10	E 11	E 12	E 13	E 14	E 15	CE 5
CASS test, mm disbonding																				
Al 6016	6	5	3.5	3.5	3	3	2.5	2.5	2	2.5	3	2.5	2	2	2.5	3	2	2.5	2	

Example / CE	E 16	E 17	E 18	E 19	E 20	E 21	CE 6	E 22	E 23	CE 7	E 24	E 25	E 26	E 27	E 28
Organofunct. silane A	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2
Non-funct. silane C	-	-	0.2	-	-	-	-	-	-	-	-	-	-	-	-
H ₂ TiF ₆ as Ti	0.2	0.2	0.2	0.2	0.2	-	0.2	0.2	-	0.2	0.2	0.2	0.2	0.2	0.2
H ₂ ZrF ₆ as Zr	0.2	0.2	0.2	0.2	0.2	-	0.2	0.2	-	0.2	0.2	0.2	0.2	0.2	0.2
Mn	0.1	0.3	0.5	0.5	-	0.3	-	-	0.3	-	-	0.3	-	0.3	0.2
Cu	-	-	-	-	0.02	0.02	-	-	-	-	-	-	-	-	-
Mg	-	-	-	-	-	-	-	-	-	0.3	-	0.3	0.3	-	-
Epoxy polymer A	-	-	-	-	-	-	-	-	-	1	1	1	1	1	-
Silylated epoxy polymer C	-	-	-	-	-	-	-	-	-	-	-	-	-	-	1
Acetic acid	-	-	-	-	-	-	-	-	-	0.3	-	-	-	-	-
pH	4	4	4	4	4	9	4	4	5	4	4	4	4	4	4
BMW cross-cut test: score															
Steel	2	1	1	3	1	1	3	1	0	3	1	0	2	1	0
E-zinc on steel	2	1	1	2	1	1	3	0	0	3	0	0	2	1	0
Hot-dip zinc on steel	1	0	0	0	0	0	4	0	0	3	0	0	1	0	0
Al 6016	1	1	0	1	1	2	1	1	3	1	1	1	0	0	0
Galvaneal®	1	1	0	0	1	1	2	0	0	2	0	0	1	0	0

Example / CE	E 16	E 17	E 18	E 19	E 20	E 21	CE 6	E 22	E 23	CE 7	E 24	E 25	E 26	E 27	E 28
10 VDA cycles, mm disbonding															
Steel	2	2	1.5	1.5	2	2	4	2.5	1.5	5	2	2	2.5	1.5	1.5
E-zinc on steel	1	1	1	1.5	1.5	1	4	1	1	4	1	< 1	2	1	< 1
Hot-dip zinc on steel	1	< 1	< 1	< 1	< 1	< 1	4	< 1	< 1	4	< 1	< 1	1.5	< 1	< 1
Galvaneal®	< 1	< 1	< 1	0	< 1	3	< 1	< 1	4	< 1	< 1	1	< 1	< 1	< 1
Stone chip resistance after VDA stress: score															
Steel	2	1	1	1	1	4	1	1	1	4	1	1- 2	1- 2	2- 3	2
E-zinc on steel	1- 2	1	1	2	1	4	1	1	4	1	1- 2	1	2	1- 2	1
Hot-dip zinc on steel	1	1	0- 1	1	0	1	4	0	1	5	1	1	1	1	1
Galvaneal®	1	1	1	2	0	1	3	0	1	3	1	1	1	1	1
Salt spray test, 1008 h															
Steel	2	1.5	1	2.5	2.5	1.5	3.5	1	0.5	5	1.5	1.5	2.5	2	1.5
CASS test, mm disbonding															
Al 6016	2	1.5	1.5	1	2.8	2	5	1.5	1.5	6	1.5	1.5	2.5	2	1

Example / CE	E 29	E 30	E 31	E 32	E 33	E 34	E 35	E 36	E 37	E 38	E 39	E 40	E 41	CE 8	E 42	E 43
Organofunct. silane A	0.2	0.2	0.2	0.2	0.1	-	0.2	0.1	0.1	0.6	0.6	0.1	-	-	0.1	-
Organofunct. silane B	-	-	-	-	0.2	0.2	-	-	-	-	-	0.2	0.2	-	-	-
Non-funct. silane C	-	-	-	0.1	-	-	-	-	-	-	-	-	-	-	-	-
Polysiloxane D	-	-	-	-	-	-	-	-	-	-	-	-	-	-	0.1	0.2
H ₂ TiF ₆ as Ti	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.2	0.3	0.3	0.1	0.1	0.2	0.2	0.2	0.2
H ₂ ZrF ₆ as Zr	0.2	0.2	0.2	0.2	0.2	0.2	0.2	-	0.3	0.3	0.1	0.1	0.2	0.2	0.2	0.2
Zr carbonate	-	-	-	-	-	-	-	0.2	-	-	-	-	-	-	-	-
Mn	0.2	0.2	0.2	0.2	0.2	0.2	0.2	-	0.2	-	0.2	0.3	0.3	-	0.3	0.3
Polymer B	0.1	0.5	2.5	-	-	-	-	-	-	-	-	-	-	-	-	-
Acetic acid	-	-	-	0.01	-	-	-	-	-	-	-	-	-	-	-	-
pH	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4	4
BMW cross-cut test: score																
Steel	-	-	-	1	1	-	2	-	-	-	0 - 1	0 - 1	-	-	-	-
E-zinc on steel	-	-	-	-	1	1	-	-	-	-	1	1	-	-	-	-
Hot-dip zinc on steel	-	-	-	-	0 - 1	0 - 1	-	1	-	-	0	0	-	-	-	-
Al 6016	-	-	-	-	1 - 2	1 - 2	-	1	-	-	1	1	-	-	-	-
Galvaneal®	-	-	-	-	1	1	-	0	-	-	1	1	-	-	-	-

44

Example / CE	E 29	E 30	E 31	E 32	E 33	E 34	E 35	E 36	E 37	E 38	E 39	E 40	E 41	CE 8	E 42	E 43
10 VDA cycles, mm disbonding																
Steel	-	-	-	-	2	2	-	1.5	-	-	-	1.5	1.5	-	-	-
E-zinc on steel	-	-	-	-	1.5	1.5	-	1	-	-	-	1	1	-	-	-
Hot-dip zinc on steel	-	-	-	-	1	1	-	<1	-	-	-	1	1	-	-	-
Galvaneal®	-	-	-	-	1	1	-	<1	-	-	-	<1	<1	-	-	-
Stone chip resistance after VDA stress: score																
Steel	-	-	-	-	1	1	-	1-2	-	-	-	0-1	0-1	-	-	-
E-zinc on steel	-	-	-	-	1-2	1-2	-	1-2	-	-	-	1	1	-	-	-
Hot-dip zinc on steel	-	-	-	-	1-2	1-2	-	1	-	-	-	1	1	-	-	-
Galvaneal®	-	-	-	-	1-2	1-2	-	0-1	-	-	-	1	1	-	-	-
Salt spray test, 1008 h																
Steel	-	-	-	-	1.5	1.5	-	2	-	-	-	1	1	-	-	-
CASS test, mm disbonding																
Al 6016	-	-	-	-	2	2	-	2	-	-	-	1.5	1.5	-	-	-

Over the short period of use, all the bath compositions are found to be stable and satisfactory to apply. There are no precipitations and no colour changes. There are no differences in behaviour, visual impression or test results between the different Examples and Comparative Examples which can be attributed to the treatment conditions, e.g. application by spraying, dipping or rollcoater treatment. The films formed are transparent and almost all are extensively homogeneous. They do not colour the coating. The structure, gloss and colour of the metallic surface appear to be only slightly changed by the coating. If a titanium and/or zirconium complex fluoride is present, iridescent layers are formed, especially on steel surfaces. Combining several silanes has not so far brought about a significant improvement in the corrosion protection, but this cannot be ruled out. Furthermore, a content of H_3AlF_6 was found on aluminium-rich metallic surfaces due to corresponding reactions in the aqueous composition. Surprisingly, however, combining two or three complex fluorides in the aqueous composition has proved extremely beneficial.

The layer thickness of the coatings produced in this way – also dependent on the type of application, which was initially varied in specific experiments – ranged from 0.01 to 0.16 μm and usually from 0.02 to 0.12 μm and was often up to 0.08 μm , being markedly greater when organic polymer was added.

The corrosion protection scores in the cross-cut test according to DIN EN ISO 2409, after storage for 40 hours in 5% NaCl solution according to BMW specification GS 90011, range from 0 to 5, 0 representing the best

values. In the salt spray/condensation water alternation test over 10 cycles according to VDA test sheet 621-415 with alternating corrosion stress between salt spray test, perspiration water test and drying 5 interval, the disbonding is measured on one side from the scratch outwards and reported in mm, the disbonding ideally being as small as possible. In the stone chip resistance test according to DIN 55996-1, the coated metallic sheets are bombarded with scrap steel after the 10 aforementioned VDA alternation test over 10 cycles: The damage picture is characterized by scores from 0 to 5, 0 representing the best results. In the salt spray test according to DIN 50021 SS, the coated sheets are exposed for up to 1008 hours to an atomized corrosive sodium 15 chloride solution; the disbonding is then measured in mm from the scratch outwards, the scratch being made with a standard gouge down to the metallic surface, and the disbonding ideally being as small as possible. In the CASS test according to DIN 50021 CASS, the coated sheets 20 made of an aluminium alloy are exposed for 504 hours to an atomized special corrosive atmosphere; the disbonding is then measured in mm from the scratch outwards and ideally is as small as possible.

25 Given that the development of the zinc/manganese/nickel phosphatizing of car bodies has spanned several decades, the phosphate layers of this type produced today are of extremely high quality. Nevertheless, contrary to expectation, it was possible to achieve the same high- 30 quality properties with silane-containing coatings by means of aqueous silane-containing compositions that have only been in use for a few years, even though a greater effort was required.

Other experiments on car body elements have shown that the electrochemical conditions of the CDL bath may be very slightly adaptable to the different kind of coating, but otherwise that the outstanding properties 5 obtained in laboratory experiments can be reproduced on car body elements.

WHAT IS CLAIMED IS:

1. An aqueous composition containing a silane, silanol, siloxane or polysiloxane for coating a metal surface, said composition comprising:
 - a) at least one compound a) selected from silanes, silanols, siloxanes and polysiloxanes, the content of the silane, silanol, siloxane or polysiloxane in the composition ranging from 0.02 to 1 g/l, calculated on the basis of the corresponding silanols;
 - b) at least two compounds b) containing a metal selected from the group consisting of titanium, hafnium, zirconium, aluminium and boron, the content of compounds b) in the composition ranging from 0.01 to 15 g/l, calculated as the sum of the corresponding metal, said compounds b) being optionally in a form of a fluoride complex;
 - c) at least one cation selected from the group consisting of cations of metals of subgroups 1 to 3 and 5 to 8, including lanthanides, and of main group 2 of the periodic table of the elements, and/or a corresponding compound containing said cation, said at least one cation and/or corresponding compound including manganese and being present in the composition in a range of from 0.01 to 6 g/l;
 - d) optionally at least one organic compound selected from the group consisting of monomers, oligomers, polymers, copolymers and block copolymers, with a weight ratio of compounds a) based on silane, silanols, siloxane or polysiloxane, calculated on the basis of the corresponding silanols, to organic compounds d), calculated as added solids, in the composition ranging of from 1:0.05 to 1:12;
 - e) optionally at least one substance that influences the pH;
 - f) water; and
 - g) optionally at least one organic solvent;

with the proviso that said aqueous composition is free of polymeric epoxy compounds.

2. The composition of claim 1, wherein said aqueous composition has a pH greater than 1.5 and less than 9.
3. The composition of claim 1 or 2, wherein said at least one silane, silanol, siloxane, polysiloxane has at least one amino group, urea group and/or ureido group in each case.
4. The composition of any one of claims 1 to 3, wherein compounds b) are fluorides complex of titanium and zirconium.
5. The composition of any one of claims 1 to 4, wherein said at least one compound c) is selected from the group consisting of chromium, iron, calcium, cobalt, copper, magnesium, manganese, molybdenum, nickel, niobium, tantalum, yttrium, zinc, tin and lanthanides.
10
6. The composition of claim 5, wherein said at least one compound c) is cerium.
7. The composition of any one of claims 1 to 6, wherein the composition further comprises at least one phosphorus-containing and oxygen-containing compound.
8. The composition of any one of claims 1 to 7, wherein the composition further comprises at least one anion selected from carboxylates.
9. The composition of any one of claims 1 to 8, wherein the composition further comprises nitrate and/or nitrite.
10. The composition of any one of claims 1 to 9, wherein the composition further comprises at least one cation selected from alkali metal ions, ammonium ions, at
20 least one compound containing said alkali metal ions or ammonium ions, and mixture thereof.

11. The composition of any one of claims 1 to 10, wherein the composition further comprises free fluorides with a content ranging from 0.001 to 3 g/l, calculated as F⁻.
12. The composition of any one of claims 1 to 11, wherein the composition contains at least one fluoride-containing compound and/or fluoride anions.
13. A process for coating a metal surface comprising the step of coating said metal surface with an aqueous composition as defined in any one of claims 1 to 12.
14. The process of claim 13, wherein a mix of different metallic materials is coated with the aqueous composition in a same bath.
15. The process of claim 13 or 14, wherein the aqueous composition forms a coating with a layer weight which, based only on titanium and/or zirconium contents, ranges from 1 to 200 mg/m², calculated as titanium.
16. The process of claim 13 or 14, wherein the composition forms a coating with a layer weight which, based only on siloxanes/polysiloxanes, ranges from 0.2 to 1000 mg/m², calculated as the corresponding condensed polysiloxane.
17. The process of any one of claims 13 to 16, wherein the coating produced with the aqueous composition is then coated with at least one other coating selected from primer, lacquer, adhesive, an organic composition having lacquer properties and mixture thereof, optionally at least one of these other coatings being cured by heating and/or irradiation.
- 20 18. Use of an aqueous composition as defined in any one of claims 1 to 12 for coating a metal substrate.

19. Use of claim 18, wherein the coated metal substrate is used in the automobile industry, for railway vehicles, in the aerospace industry, in apparatus engineering, in mechanical engineering, in the building industry, in the furniture industry.
20. Use of claim 19, wherein the coated metal substrate is used in the automobile or aeronautical industry.
21. Use of any one of claims 18 to 20, wherein the coated metal substrate is used for the manufacture of crash barriers, lamps, profiles, sheathing, hardware, car bodies or body parts, individual components, preassembled/connected elements, or for the manufacture of appliances or installations.

10 22. Use of claim 21, wherein said appliances or installations are household appliances, control devices, testing devices or structural elements.