

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
19 August 2004 (19.08.2004)

PCT

(10) International Publication Number
WO 2004/069886 A1

(51) International Patent Classification⁷: C08F 220/00

(utility model), DE, DK (utility model), DK, DM, DZ, EC, EE (utility model), EE, EG, ES, FI (utility model), FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK (utility model), SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number:
PCT/US2003/040170

(22) International Filing Date:
17 December 2003 (17.12.2003)

(25) Filing Language: English

(84) **Designated States (regional):** ARIPO patent (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(26) Publication Language: English

(30) Priority Data:
60/444,200 30 January 2003 (30.01.2003) US
10/626,341 24 July 2003 (24.07.2003) US

(71) **Applicant:** 3M INNOVATIVE PROPERTIES COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations
- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for all designations
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

(72) **Inventors:** ALI, Mahfuza, B.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). MITRA, Sumita, B.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). OXMAN, Joel, D.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US).

Published:

- with international search report

(74) **Agents:** EDMAN, Sean, J. et al.; Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(81) **Designated States (national):** AE, AG, AL, AM, AT (utility model), AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ (utility model), CZ, DE

WO 2004/069886 A1

(54) **Title:** AMIDE-FUNCTIONAL POLYMERS, COMPOSITIONS, AND METHODS

(57) **Abstract:** Amide-functional polymers, and compositions including such polymers, are disclosed. The compositions, which optionally may be hardenable, are useful for treating a surface.

AMIDE-FUNCTIONAL POLYMERS, COMPOSITIONS, AND METHODS

5

BACKGROUND

Thermally reversible gel compositions including a thermally responsive viscosity modifier are useful for applications in environments where the temperature is generally higher than the ambient or pre-treatment temperature of the composition. Such compositions can be of low viscosity at ambient 10 temperature, but substantially increase in viscosity or thicken to a thickened, semi-solid, or gel-like composition in the higher temperature environment (e.g., an oral environment). Known thermally reversible compositions include, for example, a poly(oxyalkylene) as a thermally responsive viscosity modifier.

What is needed are non-poly(oxyalkylene)-based polymers that may 15 preferably be useful as thermally responsive viscosity modifiers in thermally responsive compositions.

SUMMARY

In one aspect, the present invention provides a reactive polymer 20 including a non-terminal monomeric unit including a pendant ethylenically unsaturated group and monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide). Preferably the pendant ethylenically unsaturated group includes a (meth)acrylate group.

In another aspect, the present invention provides a reactive polymer 25 including a polymeric backbone having at least three ethylenically unsaturated pendant groups and a plurality of pendant groups of the formula -C(O)NHCH(CH₃)₂ attached to the backbone. Preferably the pendant ethylenically unsaturated group includes a (meth)acrylate group.

In another aspect, the present invention provides a method of preparing a 30 reactive polymer. The method includes: copolymerizing monomers including N-isopropylacrylamide and a hydroxy-functional (meth)acrylate monomer to form

a hydroxy-functional polymer; and reacting the hydroxy-functional polymer with a hydroxy-reactive material selected from the group consisting of a (meth)acrylate-functional isocyanate, a (meth)acrylate-functional epoxide, a vinyl azlactone, and combinations thereof. Optionally, the monomers further

5 include acrylamide.

In another aspect, the present invention provides a method of preparing a reactive polymer. The method includes: copolymerizing monomers including N-isopropylacrylamide and vinyl azlactone to form an azlactone-functional polymer; and reacting the azlactone-functional polymer with a hydroxy-functional (meth)acrylate.

10

In another aspect, the present invention provides a dental composition suitable for use in the oral environment. The dental composition includes: a polymer including monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide); and a dental additive.

15 Preferably the dental composition is in the form of a dispersion, suspension, emulsion, or solution. Preferably the dental composition is an aqueous composition. Preferably the dental composition is thermally responsive. Optionally the dental composition further includes a polymerizable component.

In another aspect, the present invention provides a composition

20 including: a reactive polymer including a non-terminal monomeric unit including a pendant ethylenically unsaturated group and monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide); and water. Preferably the composition is thermally responsive.

25 In another aspect, the present invention provides a method of treating an oral surface. The method includes: applying a thermally responsive composition in a low viscosity state at a pre-treatment temperature to the oral surface, the composition including water and a polymer including monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide); and allowing the composition to warm to a treatment temperature and exhibit a thermal response. Optionally, applying the composition includes delivering the composition through an orifice, preferably

30

the orifice of a syringe. Optionally, applying the composition includes painting the composition, brushing the composition, syringing the composition, misting the composition, spraying the composition, applying a substrate having the composition thereon, or combinations thereof.

5 In another aspect, the present invention provides a method of hardening a composition on a surface. The method includes: applying a thermally responsive composition in a low viscosity state at a pre-treatment temperature to the surface, the composition including water and a reactive thermally responsive viscosity modifier including a polymer including a non-terminal monomeric unit including
10 a pendant ethylenically unsaturated group and monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide); allowing the composition to warm to a treatment temperature and exhibit a thermal response; and inducing the reactive thermally responsive viscosity modifier to react.

15 In another aspect, the present invention provides a thermally responsive composition including: a polymer including monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide); a polymerizable component different than the polymer; and water.

20 In another aspect, the present invention provides a method of preparing a hardened composition on a surface. The method includes: applying a thermally responsive composition in a low viscosity state at a pre-treatment temperature to the surface, allowing the composition to warm to a treatment temperature; and inducing the polymerizable component to polymerize. The thermally responsive
25 composition includes: a polymer including monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide); a polymerizable component different than the polymer; and water.

30 In some embodiments of the present invention, the compositions and methods of the present invention provide hardenable compositions (e.g., hardenable gels). Hardenable compositions can offer advantages over unhardenable compositions (e.g., thermally reversible compositions).

Advantages after hardening may include, for example, dimensional stability, thermal stability, improved stability to liquids, improved adhesion, and the potential for sustained release of incorporated additives (e.g., dental additives).

5 *Definitions*

As used herein, "thermally responsive" refers to the occurrence of a change in a physical property in response to a change in temperature.

As used herein, "thermally responsive viscosity modifier" means a material that may be incorporated into a composition to provide the composition 10 the capability of substantially changing in viscosity (including a phase change, e.g., a single liquid phase to separate into separate liquid-liquid phases or liquid-solid phases) in response to a change in temperature.

As used herein, a "reactive" thermally responsive viscosity modifier is a thermally responsive viscosity modifier that includes a reactive group.

15 As used herein, a "reactive" group is a group that can react under selected conditions (e.g., in the presence of free radicals or under condensation reaction conditions) with another reactive group or another component (e.g., a crosslinker or a compound with condensation reaction sites). For example, in a polymer that includes a reactive group, the reactive group can react with another reactive 20 group and/or another component to form crosslinks through dimerization, oligomerization, and/or polymerization reactions.

As used herein, "monomeric unit" refers to a unit in a polymer that is derived from an ethylenically unsaturated monomer. For example, polypropylene includes $-\text{CH}_2\text{CH}(\text{CH}_3)-$ monomeric units that are derived from 25 the ethylenically unsaturated monomer propylene, $\text{CH}_2=\text{CH}(\text{CH}_3)$.

As used herein, the term "polymer" is used to encompass homopolymers (e.g., polymers derived from a single monomer) and copolymers (e.g., polymers derived from two or more different monomers).

30 As used herein, "pendant" refers to groups that are attached to the polymer backbone.

As used herein, "hardenable" refers to a material that can be "hardened." As used herein, "harden" is meant to encompass processes including, for

example, crosslinking, dimerization, oligomerization, and/or polymerization reactions.

As used herein, "(meth)acryl" is an abbreviation intended to refer collectively to "acryl" and/or "methacryl."

5 As used herein, "a," "at least one," and "one or more" are used interchangeably.

As used herein, the recitations of numerical ranges by endpoints include all numbers subsumed within that range (e.g., 1 to 5 includes, for example, 1, 1.5, 2, 2.75, 3, 3.80, 4, 5, etc.).

10 The above summary of the present invention is not intended to describe each disclosed embodiment or every implementation of the present invention. The description that follows more particularly exemplifies illustrative embodiments.

15 DETAILED DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

In one aspect of the present invention, a dental composition suitable for use in the oral environment is provided. The dental composition includes a polymer including monomeric units derived from N-isopropylacrylamide (e.g., 20 polymerized or copolymerized N-isopropylacrylamide, as described in detail herein below) and a dental additive. The dental composition optionally includes a polymerizable component. Optionally, the composition is thermally responsive. Preferably the composition is in the form of a dispersion, suspension, emulsion, or solution. Preferably the composition is an aqueous 25 composition.

In another aspect of the present invention, a reactive polymer is provided. In one embodiment, the reactive polymer includes a pendant ethylenically unsaturated group and monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide). In another 30 embodiment, the reactive polymer includes a polymeric backbone having at least three ethylenically unsaturated pendant groups and a plurality of pendant groups of the formula -C(O)NHCH(CH₃)₂ attached to the backbone. In preferred

embodiments, the reactive polymers in combination with water form thermally responsive compositions. Preferably, the thermally responsive compositions are dental compositions suitable for use in the oral environment.

A thermally responsive composition is generally provided in a low viscosity state at a pre-treatment temperature prior to application onto a target site (e.g., a surface of a body), but typically becomes highly viscous (e.g., thick, and controllable) or forms a film or coating (e.g., flexible or rigid) at the target site. Once properly applied to the target site, the composition may optionally be hardened to provide a semi-permanent or permanent composition. These compositions are generally easily dispensed, applied, and manipulated when handled by the user, and are generally easily controlled upon application to the target site. Because the composition typically has a low viscosity (e.g., a free-flowing fluid state) initially at a pre-treatment temperature, it generally requires, for example, lower syringe extrusion forces to deliver the composition to the intended site. In addition, the low viscosity compositions can provide the ability to spray a fine mist or aerosol to a relatively large surface area (e.g., an oral cavity), typically allowing subsequent long term retention upon gellation or phase separation on the warm target site. This can allow the user the freedom to select a dispenser or applicator from an array of systems that are incapable of delivering high viscosity materials. In addition, production of low viscosity compositions may allow for easier processing and greater uniformity and consistency.

Thermally responsive compositions are generally suitable for use in or on living tissues where a composition having a pre-treatment temperature at or lower than ambient (e.g., room temperature) is applied to hard and/or soft tissue that is near or at oral temperature (e.g., 30°C to 39°C).

The ability to optionally harden (e.g., with light) a thermally responsive composition *in vivo* can provide materials that exhibit enhanced physical properties and the advantage of not reverting to a fluid state upon cooling or simple aqueous dilution. Moreover, many of the problems of formulation, handling, delivery, and application of viscous compositions may be overcome,

since the compositions of the present invention may be free-flowing liquids prior to treatment.

In a preferred embodiment of the invention, the initial viscosity of the unhardened composition at the pretreatment temperature may be low enough 5 such that the composition is in a liquid state. Subsequently, upon exposure to treatment temperature (e.g., a temperature at or near oral temperature), the viscosity can increase to thicken the composition. A viscosity increase in the range of 5-fold, 10-fold, or even 100-fold or more can be experienced when the initial viscosity is such that the composition is a liquid. Thus, for example, a 10 composition in a liquid state may have a viscosity of 0-7000 poise. In response to an increase in temperature, the viscosity of the composition can increase to at least 10,000 poise. Upon lowering the temperature, the unhardened composition preferably has the ability to reverse its viscosity and return to the flow properties of a liquid. Alternatively, upon increasing the temperature from the pretreatment 15 temperature to the treatment temperature, the thermally responsive composition may separate into phases, resulting, for example, in the formation of a precipitate or a film.

The pre-treatment temperature is the temperature at which the composition is subjected to prior to application or treatment. The pretreatment 20 temperature is preferably at least 5°C and more preferably at least 20°C. The pretreatment temperature is preferably at most 29°C and more preferably at most 25°C. However, there may be certain instances where the temperature may be outside this range. A pre-treatment temperature of at least 20°C allows the composition to be easily stored at ambient or room temperature. A pre-treatment 25 temperature of at most 25°C allows the composition to be easily stored at ambient or room temperature. However, the compositions of the invention can also be stored at lower, refrigerated pre-treatment temperatures of 5°C to 10°C to provide improved stability and shelf life. Preferably a refrigerated pretreatment temperature is at least 5°C. Preferably a refrigerated pretreatment temperature is 30 at most 10°C. The treatment temperature is the temperature at which the composition is exposed to during application. The treatment temperature can be

at or near body temperature. Preferably the treatment temperature is at least 30°C. Preferably the treatment temperature is at most 39°C.

Compositions of the present invention optionally include a reactive polymer. The reactive polymer includes a non-terminal monomeric unit

5 including a pendant ethylenically unsaturated group and monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide). Compositions of the present invention preferably include at least 1% by weight of the reactive polymer and more preferably at least 10% by weight of the reactive polymer, based on the total weight of the composition.

10 Compositions of the present invention preferably include at most 99% by weight of the reactive polymer and more preferably at most 90% by weight of the reactive polymer, based on the total weight of the composition.

In some embodiments, compositions of the present invention preferably include at least 30% by weight of water, and more preferably at least 40% by

15 weight of water, based on the total weight of the composition. In some embodiments, compositions of the present invention preferably include at most 90% by weight of water, and more preferably at most 80% by weight of water, based on the total weight of the composition. Water is preferably purified by methods including, for example, distillation, filtration, and ion-exchange

20 processes. In addition to water, compositions of the present invention may optionally include a solvent. Useful solvents include, for example, polyols (e.g., propylene glycol, poly(ethylene glycol), and glycerin). Preferably the solvent is a water miscible solvent.

Compositions of the present invention may be prepared as a single part

25 liquid or gel by combining the above components. For example, the polymer and any additional components may be mixed at the desired temperature (e.g., room temperature). Alternatively, compositions of the present invention may be prepared as multiple part liquids and/or gels that are mixed prior to delivery to the tissue. Such multiple part systems may provide shelf stability that may not

30 exist in single part compositions including, for example, compositions including an initiator system based on two-component redox chemistry, and compositions

including an additive that is incompatible with other materials in the composition.

POLY(N-ISOPROPYLACRYLAMIDE) POLYMERS

5 Polymers that include monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide) can be prepared by any suitable method known to one of skill in the art. Such methods include, for example, those disclosed in the Examples. In brief, polymers that include monomeric units derived from N-isopropylacrylamide can be prepared by homopolymerizing or copolymerizing 10 N-isopropylacrylamide.

15 Polymers that include monomeric units derived from N-isopropylacrylamide preferably include at least 1 mole %, more preferably at least 50 mole %, and most preferably at least 70 mole % of monomeric units derived from N-isopropylacrylamide, based on the total moles of monomeric units.

20 Suitable monomers to copolymerize with N-isopropylacrylamide may be selected by one skilled in the art to provide useful polymers. Exemplary monomers that may be used in copolymerizations include, for example, acrylic acid, methacrylic acid, itaconic acid, N-vinyl pyrrolidone, n-butyl acrylate, isobutyl acrylate, lauryl acrylate, octadecyl acrylate, 3-(trimethoxysilyl)propyl methacrylate, macromers (e.g., silicone macromers, fluorocarbon macromers, hydrocarbon macromers), trimethylammoniummethyl methacrylate 25 tetrafluoroborate, dimethylhexadecylammoniummethyl methacrylate bromide, 2-(methyl(nonafluorobutyl)sulfonyl)aminoethyl acrylate, 2-(methyl(nonafluorobutyl)sulfonyl)aminoethyl methacrylate, dimethylaminoethyl methacrylate, 2-isocyanatoethyl methacrylate, 2-hydroxyethyl methacrylate, vinyl azlactones (e.g., 4,4-dimethyl-2-vinyl-2-oxazolin-5-one), polyethyleneglycol dimethacrylate, and combinations thereof.

30

REACTIVE POLYMERS

In one embodiment, the present invention provides a reactive polymer including a non-terminal monomeric unit including a pendant ethylenically unsaturated group and monomeric units derived from N-isopropylacrylamide (e.g., polymerized or copolymerized N-isopropylacrylamide). In another 5 embodiment, the present invention provides a polymer including a polymeric backbone having at least three ethylenically unsaturated pendant groups and a plurality of pendant groups of the formula -C(O)NHCH(CH₃)₂ attached to the backbone. Reactive polymers including an ethylenically unsaturated group can react, for example, in the presence of free radicals to form crosslinks through 10 dimerization, oligomerization, and/or polymerization reactions.

The non-terminal monomeric unit including a pendant ethylenically unsaturated group and/or the plurality of pendant groups of the formula -C(O)NHCH(CH₃)₂ attached to the backbone may be derived, for example, from (meth)acrylate monomers.

15 In one illustrative method, the reactive polymer can be prepared by copolymerizing monomers including N-isopropylacrylamide and a hydroxy-functional (meth)acrylate monomer to form a hydroxy-functional copolymer. Methods for copolymerizing such monomers are well known to one of skill in the art. Illustrative conditions for copolymerizing N-isopropylacrylamide are 20 disclosed in the Examples.

The hydroxy-functional copolymer can further be reacted with hydroxy-reactive materials including, for example, (meth)acrylate-functional isocyanates, (meth)acrylate-functional epoxides, vinyl azlactones, and combinations thereof, to provide a (meth)acrylate-functional polymer. For the reaction, preferably, at 25 least 0.01 equivalents of hydroxy-reactive material, more preferably at least 0.1 equivalents of hydroxy-reactive material, and most preferably at least 0.2 equivalents of hydroxy-reactive material, per one equivalent of hydroxy in the hydroxy-functional polymer, is mixed with the hydroxy-functional polymer. For the reaction, preferably, at most 2 equivalents of hydroxy-reactive material, more 30 preferably at most 1 equivalent of hydroxy-reactive material, and most preferably at most 0.8 equivalents of hydroxy-reactive material, per one

equivalent of hydroxy in the hydroxy-functional polymer, is mixed with the hydroxy-functional polymer.

Preferred (meth)acrylate-functional isocyanates include, for example, 2-isocyanatoethyl methacrylate. Methods for reacting such compounds are well known to one of skill in the art. Illustrative conditions for reacting a (meth)acrylate-functional isocyanate with a hydroxy-functional polymer are disclosed in the Examples.

Preferred (meth)acrylate-functional epoxides include, for example, glycidyl methacrylate. Methods for reacting such compounds are well known to one of skill in the art.

Preferred vinyl azlactones include, for example, 4,4-dimethyl-2-vinyl-2-oxazolin-5-one. Methods for reacting such compounds are well known to one of skill in the art. Illustrative conditions for reacting a vinyl azlactone with a hydroxy-functional polymer are disclosed in the Examples.

15 In another illustrative method, the reactive polymer can be prepared by copolymerizing monomers including N-isopropylacrylamide and a vinyl azlactone to form an azlactone-functional polymer. Methods for copolymerizing such monomers are well known to one of skill in the art. Illustrative conditions for copolymerizing the monomers are described in the Examples.

20 The azlactone-functional polymer can further be reacted with a hydroxy-functional (meth)acrylate to provide a (meth)acrylate-functional polymer. For the reaction, preferably, at least 0.01 equivalents of hydroxy-functional (meth)acrylate, more preferably at least 0.1 equivalents of hydroxy-functional (meth)acrylate, and most preferably at least 0.2 equivalents of hydroxy-functional (meth)acrylate, 25 per one equivalent of azlactone in the azlactone-functional polymer. For the reaction, preferably, at most 2 equivalents of hydroxy-functional (meth)acrylate, more preferably at most 1 equivalent of hydroxy-functional (meth)acrylate, and most preferably at most 0.8 equivalents of hydroxy-functional (meth)acrylate, 30 per one equivalent of azlactone in the azlactone-functional polymer, is mixed with the azlactone-functional polymer.

Preferred hydroxy-functional (meth)acrylates include, for example, 2-hydroxyethyl methacrylate. Methods for reacting such compounds are well known to one of skill in the art. Illustrative conditions for reacting a hydroxy-functional (meth)acrylate with an azlactone-functional polymer are disclosed in 5 the Examples.

Reactive polymers preferably include at least 1 mole %, more preferably at least 50 mole %, and most preferably at least 70 mole % of monomeric units derived from N-isopropylacrylamide, based on the total moles of monomeric units. Reactive polymers preferably include at most 99 mole %, more preferably 10 at most 95 mole %, and most preferably at most 90 mole % of monomeric units derived from N-isopropylacrylamide, based on the total moles of monomeric units.

Reactive polymers preferably include at least 1 mole %, more preferably at least 5 mole %, and most preferably at least 10 mole % of non-terminal 15 monomeric units comprising a pendant ethylenically unsaturated group, based on the total moles of monomeric units. Reactive polymers preferably include at most 90 mole %, more preferably at most 50 mole %, and most preferably at most 30 mole % of non-terminal monomeric units comprising a pendant ethylenically unsaturated group, based on the total moles of monomeric units.

20 Other monomers that may be used in the copolymerization include, for example, those disclosed in the Examples.

INITIATOR SYSTEM

Compositions of the present invention that include a reactive polymer 25 and/or a polymerizable component preferably also include an initiator system (e.g., one or more initiators) or catalyst that enables the composition to be hardened. For example, visible and/or near-infrared photoinitiator systems may be used to initiate photopolymerization in compositions including free-radically polymerizable components. For example, a monomer can be combined with a 30 three component or ternary photoinitiator system including a sensitizer, an electron donor, and an iodonium salt as disclosed, for example, in U.S. Pat. No. 5,545,676 (Palazzotto et al.). Alternatively, the composition may include a

binary initiator system including a sensitizer (e.g., camphorquinone) and an electron donor (e.g., a secondary or a tertiary alkyl amine compound as disclosed, for example, in U.S. Pat. No. 4,071,424 (Dart et al.)).

Another class of useful photoinitiators includes acylphosphine oxides, as 5 disclosed in European Pat. Publ. No. 173,567 (Ying). Such acylphosphine oxides are of the general formula $(R)_2 P(=O)C(=O) — R^1$, wherein each R individually can be a hydrocarbyl group (e.g., alkyl, cycloalkyl, aryl, and aralkyl), which may be substituted with a halo-, alkyl- or alkoxy-group, or the two R groups may be joined to form a ring along with the phosphorous atom, 10 and wherein R^1 is a hydrocarbyl group, an S-, O-, or N-containing five- or six-membered heterocyclic group, or a $-Z-C(=O)-P(=O)-(R)_2$ group, wherein Z represents a divalent hydrocarbyl group (e.g., alkylene or phenylene) having from 2 to 6 carbon atoms.

Preferred acylphosphine oxides useful in the invention are those in which 15 the R and R^1 groups are phenyl or lower alkyl- or lower alkoxy-substituted phenyl. By "lower alkyl" and "lower alkoxy" is meant such groups having from 1 to 4 carbon atoms. Most preferably, the acylphosphine oxide is bis(2,4,6-trimethylbenzoyl)phenyl phosphine oxide available under the trade designation IRGACURE 819 from Ciba Specialty Chemicals (Tarrytown, NY).

20 The use of redox catalysts including oxidants and reductants for inducing free radical polymerization in multi-component systems is also useful for generating hardened gels. A preferred mode of initiating the polymerization reaction uses oxidizing and reducing agents as a redox catalyst system. Various redox systems optionally including microencapsulated reducing and/or oxidizing 25 agents are disclosed in U.S. Pat. No. 5,154,762 (Mitra et al.).

Preferably, the oxidizing agent reacts with or otherwise cooperates with the reducing agent to produce free radicals. The free radicals are capable of initiating polymerization of the ethylenically unsaturated moiety. The oxidizing and reducing agents preferably are sufficiently soluble and are present in an 30 amount sufficient to permit an adequate free radical reaction rate as disclosed in U.S. Pat. No. 6,136,885 (Rusin et al.).

A preferred class of oxidizing agents includes persulfates (e.g., sodium, potassium, ammonium, and alkyl ammonium persulfates). Another preferred class of oxidizing agents includes peroxides or peroxide salts (e.g., hydrogen peroxide, benzoyl peroxide, and hydroperoxides including, for example cumene hydroperoxide, tert-butyl hydroperoxide, tert-amyl hydroperoxide, and 2,5-dihydroperoxy-2,5-dimethylhexane). Other preferred oxidizing agents include salts of cobalt (III) and iron (III), perboric acid and its salts, and salts of a permanganate anion. Combinations of any of the above mentioned oxidizing agents can also be used.

Preferred reducing agents include, for example, amines (e.g., aromatic amines), ascorbic acid, metal complexed ascorbic acid, cobalt (II) chloride, ferrous chloride, ferrous sulfate, hydrazine, hydroxylamine, oxalic acid, thiourea, and salts of dithionite, thiosulfate, benzene sulfinate, or sulfite anions.

If initiators are included in compositions of the present invention, the compositions preferably include at least 0.01% by weight of the initiator and more preferably at least 0.1% by weight of the initiator, based on the total weight of the composition. If initiators are included in compositions of the present invention, the compositions preferably include at most 10% by weight of the initiator and more preferably at most 5% by weight of the initiator, based on the total weight of the composition.

SECONDARY POLYMERIZABLE COMPONENT

Compositions of the present invention may optionally include a polymerizable component different than the reactive polymer (e.g., a secondary polymerizable component). If a polymerizable component different than the reactive polymer is included, the composition preferably includes at least 1% by weight of the polymerizable component and more preferably at least 5% by weight of the polymerizable component, based on the total weight of the composition. If a polymerizable component different than the reactive polymer is included, the composition preferably includes at most 90% by weight of the polymerizable component and more preferably at most 80% by weight of the polymerizable component, based on the total weight of the composition.

In certain embodiments, the compositions are photopolymerizable, i.e., the compositions include a polymerizable component and a photoinitiator (i.e., a photoinitiator system) that upon irradiation with actinic radiation initiates the polymerization (or hardening) of the composition. Such photopolymerizable 5 compositions are preferably free radically polymerizable.

In certain embodiments, the compositions are chemically polymerizable, i.e., the compositions contain a chemical initiator system that can polymerize, 10 cure, or otherwise harden the composition without dependence on irradiation with actinic radiation. Such chemically polymerizable compositions are sometimes referred to as "self-cure" compositions and may include, for example, glass ionomer cements (e.g., conventional and resin-modified glass ionomer cements), redox cure systems, silane moieties capable of undergoing a condensation reaction (as described, for example, in U.S. Pat. Nos. 5,607,663 (Rozzi et al.), 5,662,887 (Rozzi et al.), 5,866,630 (Mitra et al.), 5,876,208 (Mitra 15 et al.), 5,888,491 (Mitra et al.), and 6,312,668 (Mitra et al.)), and combinations thereof.

Ethylenically Unsaturated Compounds. Ethylenically unsaturated compounds include, for example, polymerizable monomers, polymerizable oligomers, polymerizable polymers, and combinations thereof. Preferably, the 20 polymerizable component is free radically polymerizable. Preferred monomers, oligomers, and polymers are those which are partially or fully water miscible.

Suitable polymerizable monomers and oligomers include, for example, poly(ethyleneglycol) dimethacrylate (PEGDMA), tetrahydrofurfural methacrylate, as well as hydroxylic functional monomers including, for example, 25 2-hydroxyethyl methacrylate (HEMA), glycidyl dimethacrylate (GDMA), and glycidyl monomethacrylate (GMMA). Hydrophobic monomers and oligomers including, for example, bis(glycidyl methacrylate) (bis-GMA), tri(ethyleneglycol) dimethacrylate (TEGDMA), and urethane dimethacrylate may also be utilized.

30 Suitable polymerizable polymers include, for example, partially or fully acrylate- or methacrylate-functionalized polymers including, for example, functionalized poly(acrylic acid) polymers, cellulosics, poly(vinylalcohol)

polymers, poly(oxyethylene)-poly(oxypropylene) block copolymers, poly(ethyleneglycol) polymers, and the like.

Chemically Polymerizable Compositions. Chemically polymerizable compositions may include glass ionomer cements such as conventional glass ionomer cements that typically employ as their main ingredients a homopolymer or copolymer of an ethylenically unsaturated carboxylic acid (e.g., poly acrylic acid, copoly (acrylic, itaconic acid), and the like), a fluoroaluminosilicate ("FAS") glass, water, and a chelating agent such as tartaric acid. Conventional glass ionomers (i.e., glass ionomer cements) typically are supplied in powder/liquid formulations that are mixed just before use. The mixture will undergo self-hardening in the dark due to an ionic reaction between the acidic repeating units of the polycarboxylic acid and cations leached from the glass. The glass ionomer cements may also include resin-modified glass ionomer ("RMGI") cements. Exemplary chemically polymerizable compositions are described, for example, in Applicants' Assignees' copending Application Serial No. 10/327,411, filed December 20, 2002.

The chemically polymerizable compositions may include redox cure systems that include a polymerizable component (e.g., an ethylenically unsaturated polymerizable component) and redox agents. The redox agents may include an oxidizing agent and a reducing agent. Suitable polymerizable components, redox agents, optional acid-functional components, and optional fillers that are useful in the present invention are described Applicants' Assignees' copending Application Serial Nos. 10/121,326 and 10/121,329, both filed April 12, 2002. Alternatively, the redox agents may include a free-radical initiator system containing enzymes as disclosed in Applicants' Assignees' copending Application Serial No. 10/327,202, filed December 20, 2002.

The reducing and oxidizing agents should react with or otherwise cooperate with one another to produce free-radicals capable of initiating polymerization of the resin system (e.g., the ethylenically unsaturated component). This type of cure is a dark reaction, that is, it is not dependent on the presence of light and can proceed in the absence of light. The reducing and oxidizing agents are preferably sufficiently shelf-stable and free of undesirable

colorization to permit their storage and use under typical dental conditions. They should be sufficiently compatible with the composition (and preferably water-miscible) to permit ready dissolution in (and discourage separation from) the other components of the polymerizable composition.

5 Useful reducing agents include ascorbic acid, ascorbic acid derivatives, and metal complexed ascorbic acid compounds as described in U.S. Pat. No. 5,501,727 (Wang et al.); amines, especially tertiary amines, such as 4-tert-butyl dimethylaniline; aromatic sulfinic salts, such as p-toluenesulfinic salts and benzenesulfinic salts; thioureas, such as 1-ethyl-2-thiourea, tetraethyl thiourea, 10 tetramethyl thiourea, 1,1-dibutyl thiourea, and 1,3-dibutyl thiourea; and mixtures thereof. Other secondary reducing agents may include cobalt (II) chloride, ferrous chloride, ferrous sulfate, hydrazine, hydroxylamine (depending on the choice of oxidizing agent), salts of a dithionite or sulfite anion, and mixtures thereof. Preferably, the reducing agent is an amine.

15 Suitable oxidizing agents will also be familiar to those skilled in the art, and include but are not limited to persulfuric acid and salts thereof, such as sodium, potassium, ammonium, cesium, and alkyl ammonium salts. Additional oxidizing agents include peroxides such as benzoyl peroxides, hydroperoxides such as cumyl hydroperoxide, t-butyl hydroperoxide, and amyl hydroperoxide, 20 as well as salts of transition metals such as cobalt (III) chloride and ferric chloride, cerium (IV) sulfate, perboric acid and salts thereof, permanganic acid and salts thereof, perphosphoric acid and salts thereof, and mixtures thereof.

25 It may be desirable to use more than one oxidizing agent or more than one reducing agent. Small quantities of transition metal compounds may also be added to accelerate the rate of redox cure. In some embodiments it may be preferred to include a secondary ionic salt to enhance the stability of the polymerizable composition as described in Applicants' Assignees' copending Application Serial No. 10/121,329, filed April 12, 2002.

30 The reducing and oxidizing agents are present in amounts sufficient to permit an adequate free-radical reaction rate. This can be evaluated by combining all of the ingredients of the polymerizable composition except for any optional filler, and observing whether or not a hardened mass is obtained.

The reducing or oxidizing agents can be microencapsulated as described in U.S. Pat. No. 5,154,762 (Mitra et al.). This will generally enhance shelf stability of the polymerizable composition, and if necessary permit packaging the reducing and oxidizing agents together. For example, through appropriate 5 selection of an encapsulant, the oxidizing and reducing agents can be combined with an acid-functional component and optional filler and kept in a storage-stable state. Likewise, through appropriate selection of a water-immiscible encapsulant, the reducing and oxidizing agents can be combined with an FAS glass and water and maintained in a storage-stable state.

10 A redox cure system can be combined with other cure systems, e.g., with a glass ionomer cement and with a photopolymerizable composition such as described U.S. Pat. No. 5,154,762 (Mitra et al.).

The hardenable compositions that utilize a redox cure system can be supplied in a variety of forms including two-part powder/liquid, paste/liquid, and 15 paste/paste systems. Other forms employing multi-part combinations (i.e., combinations of two or more parts), each of which is in the form of a powder, liquid, gel, or paste are also possible. In a multi-part system, one part typically contains the reducing agent(s) and another part typically contains the oxidizing agent(s). Therefore, if the reducing agent is present in one part of the system, 20 then the oxidizing agent is typically present in another part of the system. However, the reducing agent and oxidizing agent can be combined in the same part of the system through the use of the microencapsulation technique.

ADDITIVES

25 In some embodiments, compositions of the present invention include, or may optionally include, additives (e.g., medical additives for medical compositions that are suitable for use in or on the body, dental additives for dental compositions that are suitable for use in the oral environment).

Exemplary additives include, for example, fluoride sources, whitening agents, 30 anticaries agents (e.g., xylitol), remineralizing agents (e.g., calcium phosphate compounds), enzymes, breath fresheners, anesthetics, clotting agents, acid neutralizers, chemotherapeutic agents, immune response modifiers,

medicaments, indicators, dyes, pigments, wetting agents, surfactants, buffering agents, viscosity modifiers, thixotropes, fillers, polyols, antimicrobial agents, antifungal agents, stabilizers, agents for treating xerostomia, desensitizers, and combinations thereof. Preferably the additives are dental additives suitable for

5 use in the oral environment.

Useful additives may be selected for specific applications as desired. For example, dental whitening compositions generally include a whitening agent. The whitening agent used in the present invention may be any material that has the effect of whitening teeth. Useful whitening agents include, for example,

10 hypochlorites (e.g., sodium hypochlorite), peroxides, hydroperoxides, hydrogen peroxide, peracids (also known as peroxyacids), carbamide peroxide (i.e., the urea complex of hydrogen peroxide, $\text{CO}(\text{NH}_2)_2\text{H}_2\text{O}_2$, also known as urea hydrogen peroxide, hydrogen peroxide carbamide, or perhydrol-urea), and combinations thereof. The concentration of a whitening agent in the

15 composition can vary depending upon its activity. Compositions of the present invention may be adjusted as desired to include the amount of additive as desired for the specific application.

Compositions of the present invention may also include non-polymerizable polymers. Preferably, the non-polymerizable polymers are

20 partially or fully miscible in an aqueous environment and include, for example, poly(acrylic acid) polymers, cellulosics, poly(vinylalcohol) polymers, poly(oxyethylene)-poly(oxypropylene) block copolymers, poly(ethyleneglycol) polymers, and combinations thereof.

25 *METHODS*

Methods of the present invention provide for the treatment of a surface. In one embodiment, the treated surface is the surface (e.g., soft or hard tissue) of a body (e.g., animal or human). Hard tissues include, for example, bone, teeth, and the component parts of teeth (e.g., enamel, dentin, and cementum). Soft tissues include, for example, mucosa (e.g., tongue, gingiva, and throat).

30 Alternatively, the treated surface may be, for example, a substrate (e.g., a flexible film). Preferably the surface-treated substrate may be shaped or

deformed. More preferably, the surface-treated substrate may be shaped or deformed by pressure from the surface of a body (e.g., a hand, a foot, a tooth). If only one surface of the substrate is treated, the pressure may be applied from either side of the substrate.

5 Compositions of the present invention may be delivered to the desired site by any method as desired. For example, the composition may be delivered directly onto the target site from a container or dispenser. Suitable containers or dispensers include, for example, bottles, vials, syringes, and tubes. The ability to delivery the composition as a bulk liquid from a needle tip or as a fine mist from 10 an aerosol provides versatility in application. Alternatively, the composition can be delivered by using a brush, sponge, applicator, or swab to paint or coat the composition onto the target site. For some applications it may be desirable to apply the composition to larger areas. For those particular applications, the compositions may be delivered via spray or aerosol dispensers or by simply 15 rinsing the entire target area (e.g., the oral cavity) with the liquid. Another alternative mode of delivery includes the use of a tray type dispenser.

Alternatively, the composition can be applied to a substrate, and the substrate having the composition thereon can be applied to the desired surface. Suitable substrates include, for example, polymeric films, paper, and woven and 20 non-woven sheets. The composition can also be applied to a brush, spatula, medical/dental instrument, or an applicator prior to application to the desired surface.

When the thermally responsive compositions of the present invention include two or more parts, the two or more parts are preferably mixed just prior 25 to or during the application process. Suitable mixing devices include, for example, static mixing devices.

The composition is preferably allowed to stand on the surface of the target site long enough to provide the desired effect. The standing time will vary depending on the particular composition employed, the type of target site (e.g., 30 tissue), the intended use, and the time available for carrying out the procedure. For many applications, the composition may be allowed to remain on the target site for an extended period of time.

Prior to hardening, thermally reversible compositions of the present invention can be readily removed from the target site by cooling the material below the liquid to semi-solid transition temperature, thus reversing the thickening effect. This can be accomplished with cool water or other

5 physiologically compatible liquids. Alternatively, the concentrations of the components in the composition may be adjusted and diluted by adding water or other liquids. By adjusting the concentrations of the components, the transition temperature is correspondingly adjusted, and thus provides the user the ability to remove the composition even with warm solutions. Water or other liquids may

10 be administered through a rinsing cup, squirt bottle, a liquid dispensing dental tool, or any other liquid dispensing device that can provide a liquid to the oral environment. Preferably, administering cool or cold water provides a significant decrease in viscosity. Alternatively, the composition may be brushed, wiped, or blown off.

15 Compositions of the present invention that include a reactive polymer may be hardened by inducing the reactive polymer to react. If the composition includes an optional polymerizable component different than the reactive polymer, hardening of the composition may also include polymerization of the polymerizable component. For example, when the reactive polymer or the

20 polymerizable component includes an ethylenically unsaturated group, polymerization may be induced by the application of actinic radiation. Preferably the composition is irradiated with radiation having a wavelength of 400 to 1200 nanometers, and more preferably with visible radiation. Visible light sources include, for example, the sun, lasers, metal vapor (e.g., sodium and

25 mercury) lamps, incandescent lamps, halogen lamps, mercury arc lamps, fluorescent room light, flashlights, light emitting diodes, tungsten halogen lamps, and xenon flash lamps.

Alternatively, when the reactive polymer or the polymerizable component includes an ethylenically unsaturated group, the composition may

30 include two or more parts, with one part including an oxidizing agent, and another part including a reducing agent.

Upon exposure to treatment temperature (e.g., a temperature at or near oral temperature) and hardening, the viscosity of the composition can increase to thicken the composition. A viscosity increase in the range of 10-fold, 50-fold, or even 100-fold or more can be experienced when the initial viscosity is such that

5 the composition is a liquid. Alternatively, exposure to treatment temperature (e.g., a temperature at or near oral temperature) and hardening, the thermally responsive composition may separate into phases, resulting, for example, in the formation of a precipitate or a film. Typically, the film or precipitate is insoluble.

10 Once a composition of the present invention has been hardened, the composition is rendered thermally irreversible and is generally not readily removed by reducing temperature or diluting with water. However, the hardened composition can generally be removed by mechanical or chemical methods including, for example, brushing, wiping, scraping, and use of solvents (e.g.,

15 alcohols).

For some embodiments of the present invention, the substantial moisture content of the composition provides the ability to easily deliver or apply, for example, a gel-on-contact aqueous material that provides substantial hydration of tissues that are subject to dehydration. Compositions of the present invention

20 may also be useful for applications including, for example, tissue adhesives and sealants for surgical and medical applications; treatment of periodontal disease; caries reduction gels; oral coatings (with/without local anesthetics) for hard and soft tissues; and dermal and sub-dermal delivery of drugs.

25 Objects and advantages of this invention are further illustrated by the following examples, but the particular materials and amounts thereof recited in these examples, as well as other conditions and details, should not be construed to unduly limit this invention. Unless otherwise indicated, all parts and

30 percentages are on a weight basis, all water is deionized water, and all molecular weights are weight average molecular weight.

EXAMPLES

Abbreviations/Definitions

NIPAAM	N-Isopropyl acrylamide (Sigma-Aldrich, St. Louis, MO)
IEM	2-Isocyanatoethyl methacrylate (Sigma-Aldrich)
AA	Acrylic acid (Sigma-Aldrich)
MAA	Methacrylic acid (Sigma-Aldrich)
ITA	Itaconic acid (Sigma-Aldrich)
NVP	N-Vinyl Pyrrolidone (Sigma-Aldrich)
LA	Lauryl acrylate (Sigma-Aldrich)
ODA	Octadecyl acrylate (Sigma-Aldrich)
A-174	3-(Trimethoxysilyl)propyl methacrylate (Sigma-Aldrich)
SiMac	Silicone macromer of MW approximately 10,000 (prepared as described for making "monomer C 3b" at column 16 of U.S. Pat. No. 4,693,935 (Mazurek))
TMA-BF ₄	Trimethylammoniummethyl methacrylate tetrafluoroborate (Prepared as described for SM-1)
DMA-C ₁₆ Br	Dimethylhexadecylammoniummethyl methacrylate bromide (Prepared as described for SM-2)
MeFBSEA	2-(Methyl(nonafluorobutyl)sulfonyl)amino)ethyl acrylate (Prepared as described in Example 2 of International Publication No. WO 01/30873 (Savu et al.))
MeFBSEMA	2-(Methyl(nonafluorobutyl)sulfonyl)amino)ethyl methacrylate (Prepared as described in Example 2 of International Publication No. WO 01/30873 (Savu et al.))
DMAEMA	Dimethylaminoethyl methacrylate (Sigma-Aldrich)
HEMA	2-Hydroxyethyl methacrylate (Sigma-Aldrich)
AAM	Acrylamide (Sigma-Aldrich)
IBMA	Isobutyl methacrylate (Sigma-Aldrich)
VDMA	Vinyl dimethyl azlactone (4,4-dimethyl-2-vinyl-2-oxazolin-5-one; Group SNPE, Strasbourg, France)

PEGDMA 400	Polyethyleneglycol dimethacrylate (Sartomer, Exton, PA)
VAZO-67	2,2'-Azobis(2-methylbutanenitrile) (Dupont, Wilmington, DE)
V-50	2,2'-Azobis(2-amidinopropane) dihydrochloride (WAKO, Richmond, VA)
DBTDL	Dibutyltin dilaurate (Sigma-Aldrich)
DBU	1,8-Diazabicyclo(5.4.0)undec-7-ene (Sigma-Aldrich)
CPQ	Camphorquinone (Sigma-Aldrich)
EDMAB	Ethyl 4-(N,N-dimethylamino)benzoate (Sigma-Aldrich)
DPIHFP	Diphenyliodonium hexafluorophosphate (Johnson Matthey, Alpha Aesar Division, Ward Hill, NJ)
BHT	2,6-Di- <i>tert</i> -butyl-4-methylphenol (Sigma-Aldrich)
THF	Tetrahydrofuran (Sigma-Aldrich)
DMF	Dimethyl formamide (Sigma-Aldrich)

PREPARATION OF STARTING MATERIALS

Polymer A: Preparation of Poly(NIPAAM(76)/HEMA(16)/AAM(8))

5 NIPAAM (10 parts), HEMA (1.0 parts), AAM (1.0 parts), VAZO-67 (0.22 parts), and THF (25 parts) were combined in a reaction bottle and the resulting mixture purged with nitrogen for 2 minutes. The bottle was sealed and maintained at 60°C in a constant temperature rotating device for 17 hours. The resulting viscous polymer solution was poured into a large excess

10 (approximately 5 times volume of reaction mixture) of cyclohexane and the precipitated solid collected by filtration and dried in a 30°C vacuum oven. The dried powdery solid was designated Polymer A and identified as the polymer of NIPAAM (76), HEMA (16), and AAM (8) with weight ratios indicated in parentheses.

15

Polymers B - E: Preparation of NIPAAM-Derived Polymers

Polymers B – E were prepared as described for Polymer A and are listed as follows with monomeric units and weight ratios indicated:

Polymer B: NIPAAM(93.3)/AAM(6.5)
Polymer C: NIPAAM(76.9)/AAM(7.7)/VDMA(15.4)
Polymer D: NIPAAM(83.3)/HEMA(16.7)
Polymer E: NIPAAM(76.9)/VDMA(23.1)

5

Polymers F and G: Preparation of NIPAAM-Derived Polymers

Polymers F and G were prepared as described for Polymer A, except that 3-mercaptopropionic acid (Sigma-Aldrich) was used as a chain transfer agent (0.62 parts), *tert*-butanol was used as a solvent, and the polymer was precipitated 10 in hexane. Polymers F and G and are listed as follows with monomeric units and weight ratios indicated:

Polymer F: HO₂CCH₂CH₂CH₂S-(NIPAAM(71.5)/HEMA(28.5))

Polymer G: HO₂CCH₂CH₂CH₂S-(NIPAAM(76.9)/HEMA(15.5)/AAM (7.6))

15 *Starting Material 1 (SM-1): Synthesis of Trimethylammoniummethyl Methacrylate Tetrafluoroborate (TMA-BF₄)*

A three-necked flask fitted with a mechanical stirrer, a dropping funnel and a condenser was charged with 80 parts of sodium tetrafluoroborate (Alfa Aesar Inorganics, Ward Hill, MA) and 130 parts of DI water. The mixture was 20 stirred for 15 minutes and a clear solution was obtained. From the dropping funnel a solution of 202.4 parts of dimethylaminoethyl methacrylate-methyl chloride (trimethylammoniummethyl methacrylate chloride; CPS Company, Ciba, Crystal Lake, IL) and 80 parts of DI water was added slowly. A solid product immediately began to precipitate out. After the addition was complete, the 25 mixture was stirred for 30 minutes and the solid isolated by filtration, washed with 30 parts of DI water, and dried under vacuum at 40°C. An NMR analysis of the solid product revealed the structure to be pure trimethylammoniummethyl methacrylate tetrafluoroborate.

30

Starting Material 2 (SM-2): Synthesis of Dimethylhexadecylammoniummethyl Methacrylate Bromide (DMA-C₁₆Br)

A 500-ml round-bottom flask was charged with 42.2 parts of DMAEMA, 154.7 parts of acetone, 93.2 parts of 1-bromohexadecane (Sigma-Aldrich), and 5 0.34 parts of BHT. The mixture was stirred for 16 hours at 35°C and then allowed to cool to room temperature. The resulting white solid precipitate was isolated by filtration, washed with cold ethyl acetate, and dried under vacuum at 40°C. An NMR analysis of the solid product revealed the structure to be pure dimethylhexadecylammoniummethyl methacrylate bromide.

10

EXAMPLE 1

Derivatization of Polymer C (NIPAAM/AAM/VDMA) with HEMA

A three-neck reaction flask fitted with a mechanical stirrer, condenser, dropping funnel, and thermometer was charged with 76 parts of a 34.2% THF solution of Polymer C followed by 0.22 parts of 1,8-diazabicyclo(5.4.0)undec-7-ene (Sigma-Aldrich). A solution of HEMA (3.74 parts) in THF (13 parts) was slowly added from the dropping funnel and the resulting solution heated at 40°C for 30 minutes. The resulting polymer solution was poured into a large excess of cyclohexane (approximately 5 times volume of reaction mixture) and the 15 precipitated solid collected by filtration and dried in a 30°C vacuum oven. The dried white solid was designated Example 1 and identified as the polymer of NIPAAM/AAM/VDMA with a plurality of the dimethyl azlactone monomeric units derivatized with HEMA to provide monomeric units of the following 20 structure (Me = CH₃):

25 CH₂=C(Me)CO₂CH₂CH₂OC(O)C(Me)₂NHC(O)-Polymer backbone.

EXAMPLE 2

Derivatization of Polymer D (NIPAAM/HEMA) with IEM

A three-neck reaction flask fitted with a mechanical stirrer, condenser, 30 dropping funnel, and thermometer was charged with 76 parts of a 32.4% THF solution of Polymer D followed by (0.25 parts) of dibutyltin dilaurate (Sigma-Aldrich) and 0.01 parts of BHT. A solution of IEM (4.77 parts) in THF (10

parts) was slowly added from the dropping funnel and the resulting solution heated at 40°C for 30 minutes. The resulting polymer solution was cooled to room temperature, poured into a large excess of cyclohexane (approximately 5 times volume of reaction mixture), and the precipitated solid collected by 5 filtration and dried in a 30°C vacuum oven. The dried white solid was designated Example 2 and identified as the polymer of NIPAAM/HEMA with a plurality of the HEMA monomeric units derivatized with IEM to provide monomeric units of the following structure (Me = CH₃):

CH₂=C(Me)CO₂CH₂CH₂NHC(O)OCH₂CH₂OC(O)-Polymer backbone.

10

EXAMPLE 3

Derivatization of Polymer E (NIPAAM/VDMA) with HEMA

A three-neck reaction flask fitted with a mechanical stirrer, condenser, dropping funnel, and thermometer was charged with 76 parts of a 34.2% THF solution of Polymer E followed by 0.22 parts of 1,8-diazabicyclo(5.4.0)undec-7-ene and 0.01 parts of BHT. A solution of HEMA (5.61 parts) in THF (5 parts) 15 was slowly added from the dropping funnel and the resulting solution heated at 40°C for 30 minutes. The resulting polymer solution was cooled to room temperature, poured into a large excess of cyclohexane (approximately 5 times volume of reaction mixture), and the precipitated solid collected by filtration and dried in a 30°C vacuum oven. The dried white solid was designated Example 3 20 and identified as the polymer of NIPAAM/VDMA with a plurality of the dimethyl azlactone monomeric units derivatized with HEMA to provide monomeric units of the following structure (Me = CH₃):

CH₂=C(Me)CO₂CH₂CH₂OC(O)C(Me)₂NHC(O)-Polymer backbone.

EXAMPLE 4

Derivatization of Polymer F: [MPA-(NIPAAM(71.5)/HEMA(28.5))] with VDMA(MPA = HO₂CCH₂CH₂CH₂S)

30 Polymer F (2.5 parts) was dissolved in THF (5 parts) in a reaction vessel to form a clear solution to which was added DBU (0.04 parts) and then VDMA (0.44 parts). The vessel was sealed and maintained at 40°C for 1 hour. The

resulting polymer solution was poured into a large excess of cyclohexane (approximately 5 times volume of reaction mixture) and the precipitated solid collected by filtration and dried in a 30°C vacuum oven. The dried solid was designated Example 4 and identified as the Polymer of MPA-(NIPAAM/HEMA)

5 with a plurality of the HEMA monomeric units and the MPA moiety derivatized with VDMA.

EXAMPLE 5

Derivatization of Polymer G:

10 [MPA-(NIPAAM (76.9)/HEMA (15.5)/AAM (7.6))] with VDMA

Polymer G (5 parts) was dissolved in THF (10 parts) in a reaction vessel to form a clear solution to which was added DBU (0.04 parts) and then VDMA (0.44 parts). The resulting reaction mixture was stirred and heated at 40°C for 1 hour. The resulting polymer solution was poured into a large excess of

15 cyclohexane (approximately 5 times volume of reaction mixture) and the precipitated solid collected by filtration and dried in a 30°C vacuum oven. The dried solid was designated Example 5 and identified as the Polymer of MPA-(NIPAAM/HEMA/AAM) with a plurality of the HEMA monomeric units and the MPA moiety derivatized with VDMA.

20

EXAMPLE 6

Thermal Polymerization (Cross-Linking) of Examples 4 and 5

In two separate vials, the polymers of Examples 4 and 5 (10 parts in each vial) were combined with water (30 parts) and V-50 (0.01 parts) and the

25 resulting mixtures purged with nitrogen for 1 minute. The vials were sealed and heated in a hot-water bath for 10 minutes. A solid lump of material separated out in both vials. The solids were isolated by filtration, dried and found in both cases to be insoluble in water.

EXAMPLE 7

Evaluation of Polymer Thermoreversibility Properties

Examples 1-3 in individual vials (5 parts each) were combined with chilled (5°C) water (20 parts) and thoroughly mixed at 5°C until either a clear 5 solution or a homogeneous dispersion was obtained. The resulting compositions were designated Samples 7a, 7b, and 7c, respectively.

Two-gram aliquots of Samples 7a, 7b, and 7c were transferred to 2-dram glass vials and sealed with a screw cap. The Samples were examined visually at 5°C and 22°C for fluidity and homogeneity by observing whether the 10 compositions readily flowed upon inversion of the vial. The vials were then heated to 37°C in a water bath for 1 minute and the compositions again observed for fluidity and or phase separation. Observation results are reported in Table 1.

Table 1			
Composition	5°C	22°C	37°C
Example 1 (Sample 7a) p(NIPAAm/AAM/VDMA)~HEMA	White Dispersion	White Dispersion	Precipitated Particles
Example 2 (Sample 7b) p(NIPAAm/HEMA)~IEM	White Dispersion	White Dispersion	Gellation (Solid Gel)
Example 3 (Sample 7c) p(NIPAAm/VDMA)~HEMA	Clear Solution	Clear Solution	Precipitated Particles (Phase Separation)

15 All samples were flowable compositions at 5°C and 22°C and all produced either a solid cohesive gel or precipitation of substantial amounts of solid particulates upon heating to 37°C. In each case, cooling the compositions back to 5°C or 22°C resulted in the regeneration of a fluid flowable solution. These compositions were therefore found to exhibit thermoreversible behavior.

EXAMPLE 8

Photopolymerization (Cross-Linking) of Example 2

To Example 2 (0.40 parts) dispersed in 1.60 parts of 5°C water in a 2-dram vial was added the ternary initiator system comprised of CPQ (0.01 parts), 5 EDMAB (0.01 parts), and DPIHFP (0.01 parts) and the resulting dispersion mixed thoroughly. This composition was designated Sample 8a and, like Sample 7b above, was a fluid and flowable white dispersion at 5°C and 22°C and a cohesive solid gel when heated for 30 seconds at 37°C. The composition could be reversibly converted to a liquid dispersion or to a cohesive solid gel upon 10 cooling or heating, respectively.

Sample 8a in gel form at 37°C in a glass vial was irradiated for 60 seconds with a FX 3000 dental curing light (3M ESPE, St. Paul, MN) by placing the tip of the light guide in direct contact with the vial and rotating the vial throughout the duration of the light exposure. The gelled sample was then cooled 15 to 5°C for 5 minutes and observed to be a rubbery solid. The sample was no longer thermoreversible and the experiment demonstrated that an irreversible cross-linked hydrogel could be obtained by photopolymerization.

An identical Sample 8a in fluid form at 22°C was irradiated in the same manner. Following irradiation, the sample remained as a fluid flowable 20 dispersion at 5°C and 22°C.

EXAMPLE 9

Photopolymerization (Cross-Linking) of Example 2 + PEGDMA 400

To Example 2 (0.36 parts) dispersed in water (1.44 parts) in a 2-dram 25 glass vial was added PEGDMA 400 (0.20 parts) and the ternary initiator system comprised of CPQ (0.01 parts), EDMAB (0.01 parts), and DPIHFP (0.01 parts) and the resulting dispersion mixed thoroughly. This composition was designated Sample 9a and, like Samples 7b and 8a above, was a white dispersion that readily flowed upon inversion of the vial at 5°C and 22°C. However, when 30 heated for 60 seconds at 37°C, substantial phase separation was observed in the form of a clear liquid component and a white cohesive gel. Subsequent cooling of the phase separated composition to 5°C or 22°C resulted in the regeneration of

a fluid flowable dispersion and thus the composition demonstrated thermoreversible behavior.

Sample 9a was irradiated at 37°C in a glass vial by the procedure described in Example 8. Another vial of Sample 9a was irradiated in the same 5 manner at 22°C. Following irradiation at both temperatures, the compositions transformed into rubbery solids that did not exhibit a significant change in appearance when cooled or heated between 5°C and 22°C. The compositions remained as rubbery solids and did not exhibit thermoreversible behavior.

10

EXAMPLE 10

Preparation of Poly(AA(40)/ITA(20)/NIPAAM(20)/TMA-BF₄(20)) in THF
AA (40 parts), ITA (20 parts), NIPAAM (20 parts), TMA-BF₄ (20 parts), VAZO-67 (1.0 part), and THF (300 parts) were combined in a reaction vessel and the resulting mixture purged with nitrogen for 2 minutes. The vessel was 15 sealed and maintained at 65°C in a constant temperature rotating device for 18 hours during which time a white solid precipitate formed. After cooling to room temperature, water (300 parts) was added to the mixture with agitation until the solid was dissolved. The resulting polymer solution was designated Example 10 and identified as the polymer of AA (40), ITA (20), NIPAAM (20), and TMA- 20 BF₄ (20) with weight ratios indicated in parentheses. The polymer solution was determined to have 18.4% solids.

EXAMPLES 11-17

Preparation of NIPAAM-Containing Polymers in THF

25 Polymer solutions designated Examples 11-17 were prepared as described for Example 10 and are listed as follows with monomeric units, weight ratios, and % Solids indicated:

Example 11: AA(40)/ITA(20)/NIPAAM(20)/TMA-BF₄(18)/LA(2); 21.7%
Solids
30 Example 12: AA(40)/ITA(20)/NIPAAM(20)/TMA-BF₄(18)/SiMac(2); 19.2%
Solids

Example 13: AA(40)/ITA(20)/NIPAAM(20)/TMA-BF₄(18)/ODA(2); 18.8%
Solids

Example 14: AA(40)/ITA(20)/NIPAAM(20)/TMA-BF₄(19)/SiMac(1); 25.7%
Solids

5 Example 15*: AA(40)/ITA(17)/NIPAAM(20)/TMA-BF₄(18)/ODA(2)/
A-174(3); 20.0% Solids

Example 16: AA(40)/ITA(20)/MeFBSEA(1)/NIPAAM(20)/TMA-BF₄(19);
15.3% Solids

Example 17: AA(40)/ITA(20)/MeFBSEA(1)/NIPAAM(20)/TMA-BF₄(19);
10 13.3% Solids

*Example 15 polymer solution was made in a 1:1 THF-Ethanol solvent and no
water was added after polymerization.

EXAMPLE 18

15 *Preparation of Poly(AA(40)/ITA(20)/NIPAAM(20)/TMA-BF₄(18)/SiMac(2))
in Water*

AA (40 parts), ITA (20 parts), NIPAAM (20 parts), TMA-BF₄ (18 parts),
SiMac (2 parts), V-50 (1 part), and DI water (300 parts) were combined in a
reaction vessel and the resulting mixture purged with nitrogen for 5 minutes. The
20 vessel was sealed and maintained at 60°C in a constant temperature rotating
device for 30 hours. Upon cooling to room temperature a viscous polymer
solution was obtained that was designated Example 9 and identified as the
polymer of AA (40), ITA (20), NIPAAM (20), TMA-BF₄(18), and SiMac (2
parts) with weight ratios indicated in parentheses. The polymer solution was
25 determined to have 20.0% solids.

EXAMPLES 19-21

Preparation of NIPAAM-Containing Polymers in Water

Polymer solutions designated Examples 19-21 were prepared as
30 described for Example 18 and are listed as follows with monomeric units, weight
ratios, and % Solids indicated:

Example 19: AA(40)/ITA(20)/NIPAAM(20)/TMA-BF₄(14)/DMA-C₁₆Br(4)/SiMac(2); 19.7% Solids

Example 20: AA(10)/ITA(10)/NIPAAM(60)/TMA-BF₄(20); 15.2% Solids

Example 21: AA(20)/ITA(20)/NIPAAM(20)/NVP(20)/TMA-BF₄(20);

5 17.0% Solids

EXAMPLES 22-24

Polymers Derivatized with IEM

AA (40 parts), ITA (20 parts), NIPAAM (20 parts), TMA-BF₄ (18 parts),
10 ODA (2 parts), VAZO-65 (1 part), and THF (300 parts) were combined in a reaction vessel and the resulting mixture purged with nitrogen for 2 minutes. The vessel was sealed and maintained at 65°C in a constant temperature rotating device for 18 hours during which time a white solid precipitate formed. After cooling to room temperature, DMF (30 parts) was added to the mixture to
15 dissolve the solid and to the resulting solution was added IEM (1.1 parts), DBTDL (0.04 parts), and BHT (0.001 parts). After heating at 40°C for 1 hour, the resulting polymer solution was poured into a large excess of ethyl acetate and the precipitated solid collected by filtration. The solid was washed two times with ethyl acetate, dried, and dissolved in DI water to make a 22.5% solids
20 solution that was designated Example 22 and identified as the polymer of AA (40), ITA (20), NIPAAM (20), TMA-BF₄ (18), and ODA (2) with weight ratios indicated in parentheses and with a plurality (approximately ten mole percent) of the carboxy acid units derivatized with IEM to provide monomeric units of the following structure (Me = CH₃):
25 CH₂=C(Me)CO₂CH₂CH₂NHC(O)-Polymer backbone.

Examples 23 and 24 were prepared in a similar manner and are listed below.

Example 23: AA(40)/ITA(20)/NIPAAM(20)/MeFBSEMA(1)TMA-BF₄(19)/~IEM; 2.8% Solids
30

Example 24: AA(40)/ITA(20)/NIPAAM(20)/MeFBSEMA(5)TMA-BF₄(15)/~IEM; 21.8% Solids

EXAMPLES 25-32

Preparation of Poly(NIPAAAM(55)/AA(20)/IBMA(20)/LA(5)) in Isopropanol

NIPAAAM (55 parts), AA (20 parts), IBMA (20 parts), LA (5 parts),

5 VAZO-67 (1.0 part), and isopropanol (200 parts) were combined in a reaction vessel and the resulting mixture purged with nitrogen for 2 minutes. The vessel was sealed and maintained at 65°C in a constant temperature rotating device for 18 hours during which time a clear viscous polymer solution formed. A second charge of VAZO-67 (0.20 parts) was added to the reaction vessel and the
10 solution heated at 65°C for an additional 8 hours. After cooling to room temperature, the resulting polymer solution was poured into a large excess of ethyl acetate and the precipitated solid polymer collected by filtration. The solid was washed two times with ethyl acetate and dried in a vacuum oven at 40°C. The dried solid was designated Example 25 and identified as the polymer of
15 NIPAAAM (55), AA (20), IBMA (20), and LA (5) with weight ratios indicated in parentheses.

Dried polymers designated Examples 26-32 were prepared as described for Example 25 and are listed as follows with monomeric units and weight ratios indicated:

20 Example 26: NIPAAAM(45), AA(20), ITA(10), IBMA(20), LA(5)
Example 27: NIPAAAM(45), AA(30), IBMA(20), SiMac(5)
Example 28: NIPAAAM(35), AA(30), ITA(10), IBMA(25)
Example 29: NIPAAAM(55), AA(20), IBMA(20), SiMac(5)
Example 30: NIPAAAM(20), AA(50), IBMA(25), SiMac(5)
25 Example 31: NIPAAAM(60), AA(20), IBMA(20)
Example 32: NIPAAAM(55), AA(20), IBMA(20), LA(5)

EVALUATIONS

Evaluation of Polymer Retention Times on Tooth Surfaces

30 To the polymer solutions designated Examples 11-14 and 29 was added 0.014% by weight of a red pigment (D&C Red 30 Talc Lake Sensient code: K7094, Sensient Technologies, St. Louis, MO) to provide Samples A-D listed in

Table 2. Similarly, the red pigment was added to the product available under the trade designation SIMPLY WHITE (Colgate, New York, NY) to provide Control Sample A (CR-A). These Samples were then evaluated for retention on teeth by using the following procedure.

5 Five extracted bovine teeth were removed from their storage container filled with water, and briefly patted with a paper towel. Samples A-D and CR-A were then individually brushed on each tooth and after 1 minute, the coated teeth were immersed in a water bath that was maintained at 37°C and continuously agitated. The teeth were visually monitored over 1 hour for changes in the
10 intensity and continuity of the red color on the tooth. The period of time that the red-colored polymer coating remained on a tooth was reported as the “Retention Time”. After 1 hour, the coated teeth were removed from the water bath and probed gently to gauge the integrity of the tooth coatings. Results are provided in Table 2. Overall, based on direct observations of color intensity and continuity,
15 Samples A-D all appeared to maintain a retentive film for greater than 1 hour, whereas Sample CR-A lost substantially all of the red coating color within 5 minutes.

Table 2

Sample	Composition	Retention Time	Observations
A	Ex. 11 + red pigment	>1 hour	Coating was retained but fragile to the touch (loss of red color and coating fragmented when probed)
B	Ex. 12 + red pigment	>1 hour	Coating less fragile than Samples B and D (more difficult to remove red color and coating with probe)
C	Ex. 13 + red pigment	>1 hour	Coating was retained but fragile to the touch (loss of red color and coating fragmented when probed)
D	Ex. 14 + red pigment	>1 hour	Least fragile coating (most difficult coating to remove red color and fragment coating with probe)
E	Ex. 29	> 1 hour	Coating was retained
CR-A	“SIMPLY WHITE” + red pigment	< 5 minutes	Color loss began immediately when coated tooth placed in water bath.

Evaluation of Polymers/Whitening Agent on Tooth Surfaces

5 To the polymer solutions designated Examples 11-14 was added 18% by carbamide peroxide (Sigma-Aldrich) to provide Samples E-H listed in Table 3. These Samples were then evaluated for whitening of teeth by using the following procedure.

10 Eight extracted bovine teeth were removed from their storage container filled with water and stained by soaking in a solution of Classic Coke and coffee for 24 hours at 38°C. An initial determination of tooth shade was determined for each tooth by comparing the shade with a VITA Shade Guide (Vident, Brea, CA). Samples E-H were then individually painted on the surface of each tooth

with a brush and air dried for 30 seconds. Two teeth were identically coated with each polymer solution sample. The coated teeth were immersed in a water bath that was maintained at 37°C and continuously agitated. After 30-45 minutes, the coated teeth were removed from the water bath and coated again with the 5 samples in a similar manner. This procedure was repeated until the teeth had been coated a total of 10 times. The teeth were then removed from the water bath and a final determination of tooth shade was determined for each tooth by comparing the shade with the VITA Shade Guide. The differences between the initial and the final stain values were calculated with a larger difference being 10 indicative of increased tooth whitening. Results as an average of the two replicates per sample are provided in Table 3. All samples showed an increase in teeth whitening when evaluated under the conditions of this test method.

Table 3		
Sample	Composition	Change in Stain Value (Increase in Whitening)
E	Ex. 11 + carbamide peroxide	3.5
F	Ex. 12 + carbamide peroxide	2.5
G	Ex. 13 + carbamide peroxide	4.0
H	Ex. 14 + carbamide peroxide	3.5

Various modifications and alterations to this invention will become apparent to those skilled in the art without departing from the scope and spirit of this invention. It should be understood that this invention is not intended to be unduly limited by the illustrative embodiments and examples set forth herein and that such examples and embodiments are presented by way of example only with the scope of the invention intended to be limited only by the claims set forth herein as follows.

5

WHAT IS CLAIMED IS:

1. A reactive polymer comprising a non-terminal monomeric unit comprising a pendant ethylenically unsaturated group and copolymerized N-isopropylacrylamide.
2. The reactive polymer of claim 1 wherein the pendant ethylenically unsaturated group comprises a (meth)acrylate group.
3. A reactive polymer comprising:
1% by weight to 90% by weight of non-terminal monomeric units comprising a pendant ethylenically unsaturated group, based on the total weight of monomeric units; and
1% by weight to 99% by weight of copolymerized N-isopropylacrylamide, based on the total weight of monomeric units.
4. The reactive polymer of claim 3 comprising:
5% by weight to 50% by weight of non-terminal monomeric units comprising a pendant ethylenically unsaturated group, based on the total weight of monomeric units; and
50% by weight to 95% by weight of copolymerized N-isopropylacrylamide, based on the total weight of monomeric units.
5. The reactive polymer of claim 4 comprising:
10% by weight to 30% by weight of non-terminal monomeric units comprising a pendant ethylenically unsaturated group, based on the total weight of monomeric units; and
70% by weight to 90% by weight of copolymerized N-isopropylacrylamide, based on the total weight of monomeric units.

6. A reactive polymer comprising a polymeric backbone having at least three ethylenically unsaturated pendant groups and a plurality of pendant groups of the formula -C(O)NHCH(CH₃)₂ attached to the backbone.
7. The reactive polymer of claim 6 wherein the ethylenically unsaturated pendant groups comprise (meth)acrylate groups.
8. A method of preparing a reactive polymer comprising:
copolymerizing monomers comprising N-isopropylacrylamide and a hydroxy-functional (meth)acrylate monomer to form a hydroxy-functional polymer; and
reacting the hydroxy-functional polymer with a hydroxy-reactive material selected from the group consisting of a (meth)acrylate-functional isocyanate, a (meth)acrylate-functional epoxide, a vinyl azlactone, and combinations thereof.
9. The method of claim 8 wherein the hydroxy-reactive material is selected from the group consisting of 2-isocyanatoethyl methacrylate, 4,4-dimethyl-2-vinyl-2-oxazolin-5-one, and combinations thereof.
10. The method of claim 8 wherein the monomers further comprise acrylamide.
11. A method of preparing a reactive polymer comprising:
copolymerizing monomers comprising N-isopropylacrylamide and vinyl azlactone to form an azlactone-functional polymer; and
reacting the azlactone-functional polymer with a hydroxy-functional (meth)acrylate.
12. The method of claim 11 wherein the azlactone is 4,4-dimethyl-2-vinyl-2-oxazolin-5-one.

13. The method of claim 11 wherein the hydroxy-functional (meth)acrylate is 2-hydroxyethyl methacrylate.

14. The method of claim 11 wherein the monomers further comprise acrylamide.

15. A dental composition suitable for use in the oral environment comprising:

a polymer comprising polymerized N-isopropylacrylamide; and
a dental additive.

16. The dental composition of claim 15 wherein the dental additive is selected from the group consisting of fluoride sources, whitening agents, anticaries agents (e.g., xylitol), remineralizing agents (e.g., calcium phosphate compounds), enzymes, breath fresheners, anesthetics, clotting agents, acid neutralizers, chemotherapeutic agents, immune response modifiers, medicaments, indicators, dyes, pigments, wetting agents, surfactants, buffering agents, viscosity modifiers, thixotropes, fillers, polyols, antimicrobial agents, antifungal agents, stabilizers, agents for treating xerostomia, desensitizers, and combinations thereof.

17. The dental composition of claim 15 wherein the dental additive is a tooth whitening agent selected from the group consisting of hypochlorites, peroxides, hydroperoxides, hydrogen peroxide, peracids, carbamide peroxides, and combinations thereof.

18. The dental composition of claim 15 wherein the dental composition is in a form selected from the group consisting of a dispersion, a suspension, an emulsion, a solution, and combinations thereof.

19. The dental composition of claim 15 wherein the composition is an aqueous composition.

20. The dental composition of claim 19 wherein the composition is thermally responsive.
21. The dental composition of claim 15 further comprising a polymerizable component.
22. The dental composition of claim 21 wherein the polymerizable component is selected from the group consisting of an ethylenically unsaturated compound, a glass ionomer cement, and combinations thereof.
23. The dental composition of claim 21 wherein the polymerizable component is a free radically polymerizable compound.
24. A composition comprising:
a reactive polymer comprising a non-terminal monomeric unit comprising a pendant ethylenically unsaturated group and copolymerized N-isopropylacrylamide; and
water.
25. The composition of claim 24 wherein the composition is thermally responsive.
26. The composition of claim 24 wherein the composition is suitable for use in the oral environment.
27. The composition of claim 24 wherein the pendant ethylenically unsaturated group comprises a (meth)acrylate group.
28. The composition of claim 24 further comprising an initiator.
29. The composition of claim 28 wherein the initiator is a photoinitiator.

30. The composition of claim 28 wherein the initiator is a free radical initiator.
31. The composition of claim 24 further comprising an oxidizing agent and a reducing agent.
32. The composition of claim 24 further comprising a polymerizable component different than the reactive polymer.
33. A composition comprising:
1% by weight to 99% by weight of a reactive polymer comprising a non-terminal monomeric unit comprising a pendant ethylenically unsaturated group and copolymerized N-isopropylacrylamide, based on the total weight of the dental composition; and
water.
34. A method of treating an oral surface comprising:
applying a thermally responsive composition in a low viscosity state at a pre-treatment temperature to the oral surface, the composition comprising water and a polymer comprising polymerized N-isopropylacrylamide; and
allowing the composition to warm to a treatment temperature and exhibit a thermal response.
35. The method of claim 34 wherein the thermal response is selected from the group consisting of gellation, phase separation, and combinations thereof.
36. The method of claim 34 wherein the composition further comprises a dental additive.
37. The method of claim 36 wherein the dental additive is selected from the group consisting of fluoride sources, whitening agents, anticaries agents (e.g.,

xylitol), remineralizing agents (e.g., calcium phosphate compounds), enzymes, breath fresheners, anesthetics, clotting agents, acid neutralizers, chemotherapeutic agents, immune response modifiers, medicaments, indicators, dyes, pigments, wetting agents, surfactants, buffering agents, viscosity modifiers, thixotropes, fillers, polyols, antimicrobial agents, antifungal agents, stabilizers, agents for treating xerostomia, desensitizers, and combinations thereof.

38. The method of claim 36 wherein the dental additive is a tooth whitening agent selected from the group consisting of hypochlorites, peroxides, hydroperoxides, hydrogen peroxide, peracids, carbamide peroxides, and combinations thereof.

39. The method of claim 34 wherein applying the composition comprises delivering the composition through an orifice.

40. The method of claim 39 wherein the orifice is the orifice of a syringe.

41. The method of claim 34 wherein applying the composition is selected from the group consisting of painting the composition, brushing the composition, syringing the composition, misting the composition, spraying the composition, applying a substrate having the composition thereon, and combinations thereof.

42. The method of claim 34 wherein the pre-treatment temperature is at most room temperature.

43. The method of claim 34 wherein the treatment temperature is body temperature.

44. A method of hardening a composition on a surface comprising:
applying a thermally responsive composition in a low viscosity state at a pre-treatment temperature to the surface, the composition comprising water and

a reactive thermally responsive viscosity modifier comprising a polymer comprising a non-terminal monomeric unit comprising a pendant ethylenically unsaturated group and copolymerized N-isopropylacrylamide;

allowing the composition to warm to a treatment temperature and exhibit a thermal response; and

inducing the reactive thermally responsive viscosity modifier to react.

45. The method of claim 44 wherein the composition further comprises an initiator.

46. The method of claim 45 wherein the initiator is a photoinitiator.

47. The method of claim 45 wherein the initiator is a free radical initiator.

48. The method of claim 44 wherein the composition further comprises an oxidizing agent and a reducing agent.

49. The method of claim 44 wherein inducing reaction comprises irradiating the composition.

50. The method of claim 49 wherein irradiating comprises irradiating the composition with visible or ultraviolet light.

51. The method of claim 44 wherein inducing reaction comprises introducing one or more additional components.

52. The method of claim 44 wherein the thermally responsive composition comprises two or more parts, and wherein applying the composition comprises combining the two or more parts.

53. The method of claim 52 wherein combining comprises using a static mixing device.

54. The method of claim 44 wherein the surface is a surface of a body.
55. The method of claim 54 wherein the surface of the body is an oral surface.
56. The method of claim 55 wherein the oral surface is selected from the group consisting of bone, tooth, tongue, gingiva, throat, and combinations thereof.
57. A thermally responsive composition comprising:
 - a polymer comprising polymerized N-isopropylacrylamide;
 - a polymerizable component different than the polymer; and
 - water.
58. A method of preparing a hardened composition on a surface comprising:
 - applying a thermally responsive composition in a low viscosity state at a pre-treatment temperature to the surface, the composition comprising:
 - a polymer comprising polymerized N-isopropylacrylamide;
 - a polymerizable component different than the polymer; and
 - water;
 - allowing the composition to warm to a treatment temperature; and
 - inducing the polymerizable component to polymerize.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 03/40170

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08F220/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, CHEM ABS Data, BIOSIS, BEILSTEIN Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 6 497 729 B1 (BURGESS DIANE ET AL) 24 December 2002 (2002-12-24) the whole document -----	1-56
A	EP 1 266 570 A (MORI YUICHI ; KUBOTA SUNAO (JP)) 18 December 2002 (2002-12-18) the whole document -----	1-56

Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search 27 April 2004	Date of mailing of the international search report 13/05/2004
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Rouault, Y

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 03/40170

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. Claims Nos.: because they relate to subject matter not required to be searched by this Authority, namely:

2. Claims Nos.: 57, 58 because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210

3. Claims Nos.: because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.

2. As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.

3. As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:

4. No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

The additional search fees were accompanied by the applicant's protest.

No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

Claims Nos.: 57,58

Present claims 57 and 58 relate to an extremely large number of possible products. Support within the meaning of Article 6 PCT and/or disclosure within the meaning of Article 5 PCT is to be found, however, for only a very small proportion of the products claimed. In the present case, the claims so lack support, and the application so lacks disclosure, that a meaningful search over the whole of the claimed scope is impossible. Indeed, the presence of non-terminal pendant ethylenically unsaturated group is an essential feature and mandatory.

Claims 57 and 58 ignore this essential feature and claim a polymer comprising polymerized N-isopropylacrylamide without any other technical feature for the polymer i.e. even an homopolymer of isopropylacrylamide could be understood.

Consequently, the search has been carried out for those parts of the claims which appear to be supported and disclosed, namely those parts relating to the product containing the features of claim 1.

The applicant's attention is drawn to the fact that claims relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure. If the application proceeds into the regional phase before the EPO, the applicant is reminded that a search may be carried out during examination before the EPO (see EPO Guideline C-VI, 8.5), should the problems which led to the Article 17(2) declaration be overcome.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 03/40170

Patent document cited in search report	Publication date	Patent family member(s)			Publication date
US 6497729	B1 24-12-2002	US	2003099682	A1	29-05-2003
		CA	2351734	A1	02-06-2000
		CA	2354060	A1	02-06-2000
		EP	1131114	A1	12-09-2001
		EP	1130996	A1	12-09-2001
		WO	0030698	A1	02-06-2000
		WO	0030532	A1	02-06-2000
		US	6366794	B1	02-04-2002
EP 1266570	A 18-12-2002	AU	4455301	A	03-10-2001
		EP	1266570	A1	18-12-2002
		WO	0170022	A1	27-09-2001
		US	2003104347	A1	05-06-2003