

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property

Organization

International Bureau

(43) International Publication Date

06 December 2018 (06.12.2018)



(10) International Publication Number

WO 2018/219762 A1

(51) International Patent Classification:

C09J 151/06 (2006.01) F16L 13/02 (2006.01)
F16L 9/12 (2006.01) B32B 27/30 (2006.01)

Published:

— with international search report (Art. 21(3))

(21) International Application Number:

PCT/EP2018/063599

(22) International Filing Date:

24 May 2018 (24.05.2018)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

17173681.2 31 May 2017 (31.05.2017) EP

(71) Applicant: BOREALIS AG [AT/AT]; Wagramer Strasse
17-19, 1220 Vienna (AT).

(72) Inventors: SUNDHOLM, Tua; Roviovuorenkatu 12,
06100 Porvoo (FI). HARTIKAINEN, Juha; Kerkkoontie
294, 06530 Kerkkoo (FI). PURMONEN, Jouni; Eestin-
mäentie 7 D 31, 06450 Porvoo (FI). TUPE, Ravindra;
Borealis Polymers Oy, PO Box 330, 06101 Porvoo (FI).
KUOSA, Juha; Hämeentie 36 A122, 00530 Helsinki (FI).
NIKIFOROVA, Liubov; Haarikkokuja 5 B 18, 01350
Vantaa (FI).

(74) Agent: KADOR & PARTNER PARTG MBB; Cor-
neliusstr. 15, 80469 München (DE).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,
CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO,
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,
HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP,
KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME,
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,
SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
KM, ML, MR, NE, SN, TD, TG).

(54) Title: IMPROVED ADHESIVE POLYMER COMPOSITION

(57) Abstract: An adhesive polymer composition comprising a non-elastomeric copolymer of ethylene and one or more comonomers having 3 to 10 carbon atoms, and an elastomer is disclosed herein. The non-elastomeric copolymer is present in an amount of 60 to 95 % by weight, based on the adhesive polymer composition, has a weight average molecular weight Mw of from 50 000 to 80 000 g/mol, molecular weight distribution Mw/Mn of 2.0 to 5.5, density of from 0.925 to 0.945 g/cm³, and at most 0.1 vinyl groups/ 1000 carbon atoms. The non-elastomeric copolymer or the non-elastomeric copolymer and the elastomer have been grafted with an acid grafting agent.

WO 2018/219762 A1

IMPROVED ADHESIVE POLYMER COMPOSITION

Field of the invention

5 The present invention relates to an adhesive polymer composition comprising an acid grafted polyethylene and an elastomer, to an article comprising a layer of the adhesive polymer composition, in particular a multilayer pipe such as a coated metal pipe, and to the use of the adhesive polymer composition for the production of an adhesive layer, in particular an adhesive layer of a multilayer structure of a pipe such as a coated metal pipe.

10

Problem to be solved

Multilayer structures comprising two, three, four, five or more layers are known for many applications such as the protective coating of pipes. In these multilayer structures different layers most often consist of different materials which accordingly have different physical and chemical properties. This results in the problem that adjacent layers do not or only to an insufficient extent adhere to each other. Therefore, it is commonly known to build up multilayer structure with intermediate adhesive layers for improving the adhesion of adjacent layers consisting of different materials and thus avoid delamination.

20

For example, in the coating of metal pipes commonly a three-layer polymer structure is used. It consists of an epoxy layer which is designed to firmly adhere to the outer surface of the metal wall of the pipe, an intermediate adhesive layer and an outer polyolefin protective layer which commonly is a polyethylene or polypropylene. The three-layer structure shows improved properties compared to formerly known single-layer coatings. On the one hand, the epoxy layer shows an improved bonding to the metal wall, avoids cathodic disbondment and provides less oxygen penetration whereas on the other hand the outer polyolefin-based layer provides good mechanical protection, and less water penetration. However, to avoid delamination of the polyolefin layer and the epoxy layer which would result in damage of the multilayer coating an adhesive layer between both layers is necessary.

30

Adhesive layers and materials for the production of such layers are for example known from WO99/37730 A1 which discloses an adhesive composition comprising an ethylene copolymer component and from 2 to 35 wt% of a grafted metallocene polyethylene.

JP 8208915 A describes an adhesive polyethylene composition comprising a grafted ethylene/alpha-olefin copolymer as cover for e.g. cables and steel pipes.

- 5 EP 0896044 A1 relates to an adhesive resin composition, in particular used for laminates. The resin contains an alpha-olefin/aromatic vinyl compound random copolymer which is partially or wholly graft-modified.

- EP 0791628 B1 provides an adhesive composition comprising a grafted long-chain
10 branched ethylene- α -olefin copolymer with a tackifier or an ethylene-vinyl acetate copolymer for use as film layers in adhesion to e.g. metals.

- EP 1316598 B1 discloses an adhesive polymer composition comprising an acid grafted polyethylene which has been produced using a single-site catalyst in an amount of at least
15 40 wt% of the composition.

- WO 2009/103516 A2 discloses an adhesive polymer composition comprising an acid grafted polyethylene, which has a M_w/M_n from 6 to 30, a density from 0.93 to 0.955 g/cm³, M_w from 20 000 to 500 000 g/mol, from 0.01 to 20 CH₃/1000 carbon atoms and at least 0.6 vinyl
20 groups/1000 carbon atoms, in an amount of at least 50 wt% of the composition.

In spite of the prior art there still remains a need for adhesive polymer composition for use in the production of adhesive layers for multilayer structures with improved adhesion properties.

25 **Summary of the invention**

The present invention provides an adhesive polymer composition comprising

- a) a non-elastomeric copolymer of ethylene and one or more comonomers having 3
to 10 carbon atoms, which non-elastomeric copolymer is present in an amount of
30 60 to 95 % by weight, based on the adhesive polymer composition, has a weight average molecular weight M_w of from 50 000 to 80 000 g/mol, molecular weight distribution M_w/M_n of 2.0 to 5.5, density of from 0.925 to 0.945 g/cm³, and at most 0.1 vinyl groups/ 1000 carbon atoms, and
b) an elastomer,

wherein the non-elastomeric copolymer or the non-elastomeric copolymer and the elastomer have been grafted with an acid grafting agent.

5 The present invention also provides an article, in particular a multilayer pipe, comprising an adhesive layer which comprises the adhesive polymer composition.

The present invention also provides a use of the adhesive polymer composition for the production of an adhesive layer, preferably an adhesive layer of a pipe.

10 Detailed description

The inventive adhesive polymer composition shows improved adhesion properties, in particular when used as an adhesive layer. For example, the adhesive polymer composition when coextruded as an adhesive layer in the three-layer structure for coating of metal pipes
15 shows improved peel strength values at 23 °C.

The non-elastomeric copolymer of the inventive adhesive polymer composition is a non-elastomeric copolymer of ethylene and one or more α -unsaturated olefinic comonomer(s). Preferably the α -olefin comonomer(s) comprise(s) from 3 to 20 carbon atoms, more
20 preferably from 2 to 12 carbon atoms and most preferably from 3 to 8 carbon atoms.

Examples of the α -olefin comonomers include propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 1-octene, 1-decene, and mixtures thereof. Particularly preferred comonomers are 1-butene, 1-hexene and 1-octene.

25 Typically, the amount of comonomer within the non-elastomeric copolymer is from 1 to 30 % by weight and more preferably is from 1 to 5 % by weight.

The non-elastomeric copolymer is present in an amount of 60 to 95 % by weight based on
30 the adhesive polymer composition. In a further preferred embodiment the non-elastomeric copolymer is present in an amount of 70 to 90 % by weight based on the adhesive polymer composition.

The non-elastomeric copolymer has a weight average molecular weight M_w of from 40 000 to 90 000 g/mol, more preferably from 50 000 to 80 000 g/mol.

5 The non-elastomeric copolymer has a molecular weight distribution M_w/M_n of 2.0 to 5.5, more preferably 2.5 to 5.0.

The non-elastomeric copolymer has a density of from 0.920 to 0.950 g/cm³, more preferably from 0.925 to 0.945 g/cm³, and even more preferably from 0.930 to 0.942 g/cm³.

10 The non-elastomeric copolymer has from 0 to 0.1 vinyl groups/1000 carbon atoms, more preferably from 0.01 to 0.07 vinyl groups/1000 carbon atoms.

The non-elastomeric copolymer can be free of long chain branches or have long chain branches. Typically, the amount of long chain branches depends on the catalyst and on the process conditions employed. The term 'long chain branches' refers to branches produced by polymerisation conditions but not to branches introduced by polymerisable comonomer species.

15

The non-elastomeric copolymer can be produced in a process comprising any catalyst known in the art, more preferably any single-site catalyst known in the art.

20

It is also possible that the non-elastomeric copolymer is produced in a process comprising a mixture of a single-site catalyst and another catalyst of the same or different nature. In the case of a mixture of a single-site catalyst and a catalyst of a different nature, it is preferred that at least 90 % of the non-elastomeric copolymer of the adhesive polymer composition is produced by a single-site catalyst.

25

Preferably, the non-elastomeric copolymer is produced in a process comprising a metallocene catalyst. Further preferred, the catalyst comprises a metallocene component on a support and an alumoxane component.

30

Any known process may be used, e.g. slurry, gas phase or solution process or a combination of the above mentioned processes for preparation of the non-elastomeric copolymer.

Further typically, the non-elastomeric copolymer may be produced in a slurry process, for example as disclosed in US 3248179 A.

The polymerisation steps may be preceded by a prepolymerisation step. The
5 prepolymerisation step may be conducted in a loop reactor. The prepolymerisation is then preferably conducted in an inert diluent, typically a hydrocarbon diluent such as methane, ethane, propane, n-butane, isobutane, pentanes, hexanes, heptanes, octanes etc., or their mixtures. Preferably the diluent is a low-boiling hydrocarbon having from 1 to 4 carbon atoms or a mixture of such hydrocarbons. The temperature in the prepolymerisation step is typically
10 from 0 to 90 °C, preferably from 20 to 80 °C and more preferably from 50 to 75 °C. The pressure is not critical and is typically from 1 to 150 bar, preferably from 40 to 80 bar. The amount of ethylene fed during prepolymerisation step is typically from 100 to 6000 g/h, preferably from 2000 to 4000 g/h. 1-Butene is added as comonomer and the amount of comonomer fed during prepolymerisation step is from 10 g/h to 400 g/h, preferably from 50
15 g/h to 200 g/h. Hydrogen amount during prepolymerisation is varied from 0 to 2 g/h, preferably from 0 to 0.4 g/h.

The polymerisation stage is preferably conducted as a slurry polymerisation. The polymerisation step may be conducted in a loop reactor. The slurry polymerisation usually
20 takes place in an inert diluent, typically a hydrocarbon diluent such as methane, ethane, propane, n-butane, isobutane, pentanes, hexanes, heptanes, octanes etc., or their mixtures. Preferably the diluent is a low-boiling hydrocarbon having from 1 to 4 carbon atoms or a mixture of such hydrocarbons. An especially preferred diluent is propane, possibly containing minor amount of methane, ethane and/or butane. The ethylene content in the fluid phase of
25 the slurry may be from 1 to about 50 % by mole, preferably from about 2 to about 20 % by mole and in particular from about 2 to about 10 % by mole. The temperature in the polymerisation stage is typically from 60 to 100 °C, preferably from 70 to 90 °C. The pressure is from 1 to 150 bar, preferably from 40 to 80 bar. The amount of hydrogen needed to reach the desired MFR depends on the catalyst used and the polymerisation conditions. Hydrogen
30 to ethylene molar ratio during polymerisation is typically from 0 to 4 g/h, preferably from 0 to 1 g/h. The amount of comonomer needed to reach the desired density depends on the comonomer type, the catalyst used and the polymerisation conditions.

In the inventive adhesive polymer composition the elastomer is an elastomeric ethylene copolymer. The elastomer may be ethylene propylene rubber (EPR), ethylene α -olefin elastomer or plastomer or ethylene propylene diene monomer rubber (EPDM). Preferably the elastomer comprises an elastomeric copolymer of ethylene with one or more polar
5 monomer(s). Preferred examples of such elastomers are ethylene-alkylacrylates and ethylene-alkylacetates. Further preferred, the comonomer has a polar moiety of the formula –O(CO)C₁-C₆-alkyl or –C(O)-OC₁-C₆-alkyl. Particularly preferred elastomers are ethylenevinylacetate (EVA), ethylenemethylacrylate (EMA), ethylenemethylmethacrylate (EMMA), ethylenepropylacrylate and ethylenebutylacrylate (EBA), in particular EBA.

10 The elastomer may be made by any process known in the art also including processes comprising a single-site catalyst. Acrylate copolymers are produced in a free-radical process.

As acid grafting agent, any such agent can be used which is known to be suitable for this
15 purpose by the person skilled in the art.

Preferably, the acid grafting agent is an unsaturated carboxylic acid or a derivative thereof such as anhydrides, esters and salts (both metallic and non-metallic). Preferably, the unsaturated group is in conjugation with the carboxylic group. Examples of such grafting
20 agents include acrylic acid, methacrylic acid, fumaric acid, maleic acid, nadic acid, citraconic acid, itaconic acid, crotonic acid, and their anhydrides, metal salts, esters amides or imides. The preferred grafting agents are maleic acid, its derivatives such as maleic anhydride, and in particular maleic anhydride.

25 Grafting can be carried out by any process known in the art such as grafting in a melt without a solvent or in solution or dispersion or in a fluidised bed. Typically, grafting is performed in a heated extruder or mixer as e.g. described in US 3236917 A, US 4639495 A, US 4950541 A or US 5194509 A. The contents of these documents are herein included by reference.

Typically, grafting is carried out in a twin screw extruder such as described in US 4950541 A.

30 Grafting may be carried out in the presence or absence of a radical initiator but is preferably carried out in the presence of a radical initiator such as an organic peroxide, organic perester or organic hydroperoxide.

The amount of said acid grafting agent added to the adhesive polymer composition before grafting is preferably from 0.01 to 3.0 parts by weight, more preferably from 0.03 to 1.5 parts by weight based on the adhesive polymer composition.

- 5 Grafting may be applied either to the non-elastomeric copolymer or to the blend of non-elastomeric copolymer and elastomer. Preferably, grafting is applied to the blend of non-elastomeric copolymer and elastomer.

10 Preferably the non-elastomeric copolymer before grafting has a melt flow rate MFR_2 of from 1 to 20 g/min, more preferably of from 1 to 10 g/min.

The non-elastomeric copolymer can be a unimodal or a multimodal polyethylene. Preferably the non-elastomeric copolymer is a unimodal polyethylene.

- 15 The expression 'modality of a polymer' refers to the form of its molecular weight distribution (MWD) curve, i.e. the appearance of the graph of the polymer weight fraction as a function of its molecular weight. If the polymer is produced in one reactor or several reactors having similar conditions all over the reactor (s), only one type of polymer is produced with a single-site catalyst. In that case, the produced polymer is unimodal.

20

In a preferred embodiment the adhesive polymer composition has an MFR_2 value (after grafting) of from 0.1 to 10 g/min, more preferably from 1.0 to 6.0 g/min.

- 25 The adhesive polymer composition has a density of from 0.925 to 0.945 g/cm³, more preferably from 0.930 to 0.940 g/cm³.

- 30 The adhesive polymer composition comprises the non-elastomeric copolymer and the elastomer as described above. In addition to these components, conventional additives may also be present in the adhesive polymer composition in small amounts, preferably up to at most 4 % by weight. For example, an antioxidant may be present in the adhesive polymer composition in an amount of at most 10 000 ppm, more preferably at most 5 000 ppm and most preferably at most 3 000 ppm.

It is preferred that the adhesive polymer composition apart from the conventional additives consists of the non-elastomeric copolymer and the elastomer, i.e. that no further polymer components before or after grafting are added. Conventional additives may be added before or after grafting.

5

The adhesive polymer composition of this invention is most useful as co-extrudable adhesive, but other applications are not excluded.

10

The present invention also relates to an article which comprises an adhesive layer comprising the adhesive polymer composition as described above. Such articles e.g. comprise pipes, cables, films, articles made by extrusion coating and articles used in engineering applications. In the latter, the adhesive polymer composition may also be used to provide compatibility between various layers or parts.

15

In a preferred embodiment, the adhesive layer in the article is adjacent to a polyolefin layer. The present invention in particular relates to a multilayer pipe, i.e. a pipe comprising a multilayer coating with two, three, four, five or more layers, which comprises a polyolefin layer and an adhesive layer adjacent to the polyolefin layer which comprises the inventive adhesive polymer composition as described above.

20

In a preferred embodiment, the present invention also relates to a coated metal pipe, comprising a polyolefin layer and a layer of a polar polymer, in particular an epoxy layer, wherein between the layers an adhesive layer is present which comprises the adhesive polymer composition according to any of the above described embodiments. In particular, the present invention also relates to a metal pipe with an three-layer protective coating consisting of an inner epoxy layer, an intermediate adhesive layer comprising the inventive adhesive polymer composition and an outer polyolefin layer such as a polyethylene or polypropylene layer.

25
30

Furthermore, the present invention relates to the use of the adhesive polymer composition as described above for the production of an adhesive layer. Preferably, the present invention further relates to the use of the adhesive polymer composition for the production of an adhesive layer in an article as e.g. a pipe, a cable, a film, an article made by extrusion coating and articles used in engineering applications. In these latter articles, the adhesive

polymer composition may also be used to provide compatibility between various layers or parts.

In a preferred embodiment, the present invention also relates to the use of the adhesive polymer composition for the production of an adhesive layer of a pipe. In particular, the present invention also relates to the use of the adhesive polymer composition for the production of an adhesive layer of the coating of a metal pipe with a three-layer protective coating as described above.

In the production of coated metal pipes having a three-layer coating preferably the epoxy layer is produced first by spraying epoxy in powder or liquid form, in one or two component form, onto the heated outer surface of the metal wall. Thereby, the epoxy forms a thin layer which firmly adheres to the metal surface. Subsequently, the adhesive and the outer polyolefin layer which preferably is a polyethylene or polypropylene layer are co-extruded onto the epoxy layer. The adhesive can also be applied by spraying the adhesive in a powder form onto the epoxy layer.

Methods

Melt index

The melt flow rate (MFR) is determined under a load of 2.16 kg at 190 °C according to ISO 1133-1 method B and is indicated in g/10 min.

Density

Density of the polymer is measured according to ISO 1183 -1 Method A using compression moulded samples.

Quantification of microstructure by NMR spectroscopy: ethylene-butene and ethylene-hexene comonomers

Quantitative nuclear-magnetic resonance (NMR) spectroscopy was used to quantify the comonomer content of the polymers.

Quantitative $^{13}\text{C}\{^1\text{H}\}$ NMR spectra recorded in the molten-state using a Bruker Avance III 500 NMR spectrometer operating at 500.13 and 125.76 MHz for ^1H and ^{13}C respectively. All spectra were recorded using a ^{13}C optimised 7 mm magic-angle spinning (MAS) probehead at 150°C using nitrogen gas for all pneumatics. Approximately 200 mg of material was

5 packed into a 7 mm outer diameter zirconia MAS rotor and spun at 4 kHz. This setup was chosen primarily for the high sensitivity needed for rapid identification and accurate quantification (Klimke, K., Parkinson, M., Piel, C., Kaminsky, W., Spiess, H.W., Wilhelm, M., Macromol. Chem. Phys. 2006;207:382., Parkinson, M., Klimke, K., Spiess, H.W., Wilhelm, M., Macromol. Chem. Phys. 2007;208:2128., Castignolles, P., Graf, R., Parkinson, M.,

10 Wilhelm, M., Gaborieau, M., Polymer 50 (2009) 2373). Standard single-pulse excitation was employed utilising the transient NOE at short recycle delays of 3s (Pollard, M., Klimke, K., Graf, R., Spiess, H.W., Wilhelm, M., Sperber, O., Piel, C., Kaminsky, W., Macromolecules 2004;37:813., Klimke, K., Parkinson, M., Piel, C., Kaminsky, W., Spiess, H.W., Wilhelm, M., Macromol. Chem. Phys. 2006;207:382.) and the RS-HEPT decoupling scheme (Filip, X.,

15 Tripon, C., Filip, C., J. Mag. Resn. 2005, 176, 239, Griffin, J.M., Tripon, C., Samoson, A., Filip, C., and Brown, S.P., Mag. Res. in Chem. 2007 45, S1, S198). A total of 1024 (1k) transients were acquired per spectrum. This setup was chosen due its high sensitivity towards low comonomer contents.

Quantitative $^{13}\text{C}\{^1\text{H}\}$ NMR spectra were processed, integrated and quantitative properties

20 determined using custom spectral analysis automation programs. All chemical shifts are internally referenced to the bulk methylene signal (δ^+) at 30.00 ppm (J. Randall, Macromol. Sci., Rev. Macromol. Chem. Phys. 1989, C29, 201).

Comonomer content quantification in ethylene-butene copolymers:

Characteristic signals corresponding to the incorporation of 1-butene were observed (J.

25 Randall, Macromol. Sci., Rev. Macromol. Chem. Phys. 1989, C29, 201.) and all contents calculated with respect to all other monomers present in the polymer.

Characteristic signals resulting from isolated 1-butene incorporation i.e. EEBEE comonomer sequences, were observed. Isolated 1-butene incorporation was quantified using the integral of the signal at 39.84 ppm assigned to the αB2 sites, accounting for the number of reporting

30 sites per comonomer:

$$B = I_{\alpha\text{B2}}$$

When characteristic signals resulting from consecutive 1-butene incorporation i.e. EBBE comonomer sequences were observed, such consecutive 1-butene incorporation was

quantified using the integral of the signal at 39.4 ppm assigned to the $\alpha\alpha$ B2B2 sites accounting for the number of reporting sites per comonomer:

$$BB = 2 * I_{\alpha\alpha B2B2}$$

When characteristic signals resulting from non consecutive 1-butene incorporation i.e.

- 5 EBEBE comonomer sequences were also observed, such non-consecutive 1-butene incorporation was quantified using the integral of the signal at 24.7 ppm assigned to the $\beta\beta$ B2B2 sites accounting for the number of reporting sites per comonomer:

$$BEB = 2 * I_{\beta\beta B2B2}$$

- 10 Due to the overlap of the α B2 and β B2B2 sites of isolated (EEBEE) and non-consecutively incorporated (EBEBE) 1-butene respectively the total amount of isolated 1-butene incorporation is corrected based on the amount of non-consecutive 1-butene present:

$$B = I_{\alpha B2} - 2 * I_{\beta\beta B2B2}$$

- 15 With no other signals indicative of other comonomer sequences, i.e. butene chain initiation, observed the total 1-butene comonomer content was calculated based solely on the amount of isolated (EEBEE), consecutive (EBBE) and non-consecutive (EBEBE) 1-butene comonomer sequences:

$$B_{total} = B + BB + BEB$$

- 20 Characteristic signals resulting from saturated end-groups were observed. The content of such saturated end-groups was quantified using the average of the integral of the signals at 22.84 and 32.23 ppm assigned to the 2s and 3s sites respectively:

$$S = (1/2) * (I_{2s} + I_{3s})$$

The relative content of ethylene was quantified using the integral of the bulk methylene (δ +) signals at 30.00 ppm:

$$E = (1/2) * I_{\delta+}$$

- 25 The total ethylene comonomer content was calculated based the bulk methylene signals and accounting for ethylene units present in other observed comonomer sequences or end-groups:

$$E_{total} = E + (5/2) * B + (7/2) * BB + (9/2) * BEB + (3/2) * S$$

The total mole fraction of 1-butene in the polymer was then calculated as:

- 30 $fB = (B_{total} / (E_{total} + B_{total}))$

The total comonomer incorporation of 1-butene in mole percent was calculated from the mole fraction in the usual manner:

$$B [\text{mol}\%] = 100 * fB$$

The total comonomer incorporation of 1-butene in weight percent was calculated from the mole fraction in the standard manner:

$$B [\text{wt}\%] = 100 * (f_B * 56.11) / ((f_B * 56.11) + ((1 - f_B) * 28.05))$$

Comonomer content quantification in ethylene-hexene copolymers:

- 5 Characteristic signals corresponding to the incorporation of 1-hexene were observed (J. Randall, Macromol. Sci., Rev. Macromol. Chem. Phys. 1989, C29, 201.) and all contents calculated with respect to all other monomers present in the polymer.

Characteristic signals resulting from isolated 1-hexene incorporation i.e. EEHEE comonomer sequences, were observed. Isolated 1-hexene incorporation was quantified using the integral of the signal at 38.29 ppm assigned to the α B4 sites, accounting for the number of reporting sites per comonomer:

$$H = I_{\alpha B4}$$

- When characteristic signals resulting from consecutive 1-hexene incorporation, i.e. EHHE comonomer sequences were observed, such consecutive 1-hexene incorporation was quantified using the integral of the signal at 40.46 ppm assigned to the $\alpha\alpha$ B4B4 sites accounting for the number of reporting sites per comonomer:

$$HH = 2 * I_{\alpha\alpha B4B4}$$

- When characteristic signals resulting from non consecutive 1-hexene incorporation, i.e. EHEHE comonomer sequences were observed, such non-consecutive 1-hexene incorporation was quantified using the integral of the signal at 24.7 ppm assigned to the $\beta\beta$ B4B4 sites accounting for the number of reporting sites per comonomer:

$$HEH = 2 * I_{\beta\beta B4B4}$$

- Due to the overlap of the signals from the α B4 and β B4B4 sites from isolated (EEHEE) and non-consecutively incorporated (EHEHE) 1-hexene respectively the total amount of isolated 1-hexene incorporation is corrected based on the amount of non-consecutive 1-hexene present:

$$H = I_{\alpha B4} - 2 * I_{\beta\beta B4B4}$$

- With no other signals indicative of other comonomer sequences, i.e. 1-hexene chain initiation, observed the total 1-hexene comonomer content was calculated based solely on the amount of isolated (EEHEE), consecutive (EHHE) and non-consecutive (EHEHE) 1-hexene comonomer containing sequences:

$$H_{\text{total}} = H + HH + HEH$$

Characteristic signals resulting from saturated end-groups were observed. The content of such saturated end-groups was quantified using the average of the integral of the signals at 22.84 and 32.23 ppm assigned to the 2s and 3s sites respectively:

$$S = (1/2) * (I_{2s} + I_{3s})$$

- 5 The relative content of ethylene was quantified using the integral of the bulk methylene ($\delta+$) signals at 30.00 ppm:

$$E = (1/2) * I_{\delta+}$$

The total ethylene comonomer content was calculated based the bulk methylene signals and accounting for ethylene units present in other observed comonomer sequences or end-

10 groups:

$$E_{total} = E + (5/2) * H + (7/2) * HH + (9/2) * HEH + (3/2) * S$$

The total mole fraction of 1-hexene in the polymer was then calculated as:

$$fH = (H_{total} / (E_{total} + H_{total}))$$

The total comonomer incorporation of 1-hexene in mole percent was calculated from the

15 mole fraction in the usual manner:

$$H [mol\%] = 100 * fH$$

The total comonomer incorporation of 1-hexene in weight percent was calculated from the mole fraction in the standard manner:

$$H [wt\%] = 100 * (fH * 84.16) / ((fH * 84.16) + ((1-fH) * 28.05))$$

20

Molecular weight averages, molecular weight distribution (M_n , M_w , M_z , MWD)

- 25 Molecular weight averages (M_z , M_w and M_n), Molecular weight distribution (MWD) and its broadness, described by polydispersity index, $PDI = M_w/M_n$ (wherein M_n is the number average molecular weight and M_w is the weight average molecular weight) were determined by Gel Permeation Chromatography (GPC) according to ISO 16014-1:2003, ISO 16014-2:2003, ISO 16014-4:2003 and ASTM D 6474-12 using the following formulas:

$$M_n = \frac{\sum_{i=1}^N A_i}{\sum_{i=1}^N (A_i/M_i)} \quad (1)$$

30

$$M_w = \frac{\sum_{i=1}^N (A_i * M_i)}{\sum_{i=1}^N A_i} \quad (2)$$

$$M_z = \frac{\sum_{i=1}^N (A_i * M_i^2)}{\sum_{i=1}^N (A_i * M_i)} \quad (3)$$

For a constant elution volume interval ΔV_i , where A_i and M_i are the chromatographic peak slice area and polyolefin molecular weight (M_w), respectively associated with the elution volume, V_i , where N is equal to the number of data points obtained from the chromatogram between the integration limits. Peak Integration was performed according to ISO 16017-

5 1:2003, which means that oil and antioxidant peaks below 1000 g/mol are not included into the calculation of the MWD.

A high temperature GPC instrument, equipped with an infrared (IR) detector (IR5) from PolymerChar (Valencia, Spain), equipped with 3 x Agilent-PLgel Olexis and 1x Agilent-PLgel Olexis Guard columns was used. As the solvent and mobile phase 1,2,4-trichlorobenzene
10 (TCB) stabilized with 250 mg/L 2,6-Di tert butyl-4-methyl-phenol) was used. The chromatographic system was operated at 160 °C and at a constant flow rate of 1 mL/min. 200 µL of sample solution was injected per analysis. Data collection was performed using PolymerChar GPCone software.

The column set was calibrated using universal calibration (according to ISO 16014-2:2003)
15 with 19 narrow MWD polystyrene (PS) standards in the range of 0.5 kg/mol to 11 500 kg/mol. The PS standards were dissolved at 160°C for 15 min. The conversion of the polystyrene peak molecular weight to polyolefin molecular weights is accomplished by using the Mark Houwink equation and the following Mark Houwink constants:

$$\begin{aligned} K_{PS} &= 19 \times 10^{-3} \text{ mL/g}, & \alpha_{PS} &= 0.655 \\ 20 \quad K_{PE} &= 39 \times 10^{-3} \text{ mL/g}, & \alpha_{PE} &= 0.725 \\ K_{PP} &= 19 \times 10^{-3} \text{ mL/g}, & \alpha_{PP} &= 0.725 \end{aligned}$$

A third order polynomial fit was used to fit the calibration data.

All samples were prepared in the concentration range of 0.5 -1 mg/ml and dissolved at 160 °C for 3 hours under continuous gentle shaking.

25

Peel strength

Peel strength designates the relative strength of the bonding between epoxy layer and adhesive layer. The peel strength of the coating compositions was measured at 23 °C
30 according to ISO21809-1:2011 using a Zwick Roell tensile testing machine, with the following alterations to the method: The peel strength was recorded for three minutes, after which the mean value of the peel strength recorded over these three minutes was calculated. The mean value corresponds to the reported peel strength of the composition.

Unsaturation

Quantitative nuclear-magnetic resonance (NMR) spectroscopy was used to quantify the content of unsaturated groups present in the polymers.

- 5 Quantitative ^1H NMR spectra recorded in the solution-state using a Bruker Avance III 400 NMR spectrometer operating at 400.15 MHz. All spectra were recorded using a ^{13}C optimised 10 mm selective excitation probehead at 125°C using nitrogen gas for all pneumatics. Approximately 250 mg of material was dissolved in 1,2-tetrachloroethane- d_2 (TCE- d_2) using approximately 3 mg of Hostanox 03 (CAS 32509-66-3) as stabiliser. Standard
- 10 single-pulse excitation was employed utilising a 30 degree pulse, a relaxation delay of 10 s and 10 Hz sample rotation. A total of 128 transients were acquired per spectra using 4 dummy scans. This setup was chosen primarily for the high resolution needed for unsaturation quantification and stability of the vinylidene groups. (He, Y., Qiu, X, and Zhou, Z., Mag. Res. Chem. 2010, 48, 537-542., Busico, V. et. al. Macromolecules, 2005, 38 (16),
- 15 6988-6996) All chemical shifts were indirectly referenced to TMS at 0.00 ppm using the signal resulting from the residual protonated solvent at 5.95 ppm.

Characteristic signals corresponding to the presence of terminal aliphatic vinyl groups ($\text{R}-\text{CH}=\text{CH}_2$) were observed and the amount quantified using the integral of the two coupled

20 inequivalent terminal CH_2 protons (Va and Vb) at 4.95, 4.98 and 5.00 and 5.05 ppm accounting for the number of reporting sites per functional group:

$$N_{\text{vinyl}} = IV_{\text{ab}} / 2$$

Characteristic signals corresponding to the presence of internal vinylidene groups ($\text{RR}'\text{C}=\text{CH}_2$) were observed and the amount quantified using the integral of the two CH_2

25 protons (D) at 4.74 ppm accounting for the number of reporting sites per functional group:

$$N_{\text{vinylidene}} = ID / 2$$

When characteristic signals corresponding to the presence of internal cis-vinylene groups ($\text{E}-\text{RCH}=\text{CHR}'$), or related structure, were observed, then the amount quantified using the integral of the two CH protons (C) at 5.39 ppm accounting for the number of reporting sites

30 per functional group:

$$N_{\text{cis}} = IC / 2$$

When characteristic signals corresponding to the presence of internal cis-vinylene groups ($\text{E}-\text{RCH}=\text{CHR}'$), or related structure, were not visually observed, then these groups were not counted and the parameter N_{cis} was not used.

Characteristic signals corresponding to the presence of internal trans-vinylene groups (Z-RCH=CHR') were observed and the amount quantified using the integral of the two CH protons (T) at 5.45 ppm accounting for the number of reporting sites per functional group:

$$N_{trans} = IT / 2$$

- 5 Characteristic signals corresponding to the presence of internal trisubstituted-vinylene groups (RCH=CR'R''), or related structure, were observed and the amount quantified using the integral of the CH proton (Tris) at 5.14 ppm accounting for the number of reporting sites per functional group:

$$N_{tris} = I_{Tris}$$

- 10 The Hostanox 03 stabiliser was quantified using the integral of multiplet from the aromatic protons (A) at 6.92, 6.91, 6.69 and at 6.89 ppm and accounting for the number of reporting sites per molecule:

$$H = IA / 4$$

- As is typical for unsaturation quantification in polyolefins the amount of unsaturation was determined with respect to total carbon atoms, even though quantified by 1H NMR spectroscopy. This allows direct comparison to other microstructure quantities derived directly from ^{13}C NMR spectroscopy.

- The total amount of carbon atoms was calculated from integral of the bulk aliphatic signal between 2.85 and -1.00 ppm with compensation for the methyl signals from the stabiliser and carbon atoms relating to unsaturated functionality not included by this region:

$$NC_{total} = (I_{bulk} - 42 \cdot H) / 2 + 2 \cdot N_{vinyl} + 2 \cdot N_{vinylidene} + 2 \cdot N_{cis} + 2 \cdot N_{trans} + 2 \cdot N_{tris}$$

The content of unsaturated groups (Ux) was calculated as the number of unsaturated groups in the polymer per thousand total carbons (kCHn):

$$U_x = 1000 \cdot N_x / NC_{total}$$

- 25 In particular, the content of vinyl groups U_{vinyl} was calculated as the number of vinyl groups in the polymer per thousand carbons (kCHn):

$$U_{vinyl} = 1000 \cdot N_{vinyl} / NC_{total}$$

Examples

30

Polyethylene A (inventive)

A medium density polyethylene was produced using a single-site catalyst. As catalyst was used alumoxane containing, supported catalyst containing metallocene bis(1-methyl-3-n-

butylcyclopentadienyl) zirconium (IV) chloride and with enhanced ActivCat® activator technology from Albemarle Corporation.

- 5 A prepolymerisation was carried out in a first slurry loop reactor followed with a polymerisation in a second slurry loop reactor. Polymerisation conditions can be found in Table 1.

Table 1

Prepolymerisation Reactor	
Temperature (°C)	50.0
Pressure (bar)	57.1
Ethylene feed (kg/h)	2.0
1-Butene Feed (g/h)	201.0
Loop Reactor	
Temperature (°C)	85.0
Pressure (bar)	55.0
Ethylene Concentration (mol-%)	4.7
1-Butene/Ethylene ratio (mol/kmol)	98.0
Propane feed (kg/h)	92.3
Density by balance, plaque (g/cm ³)	0.938
MFR2 (g/10 min)	5.3
Pellet	
MFR2 (g/10 min)	5.4
Density (g/cm ³)	0.939

10 Polyethylene B (comparative)

A medium density polyethylene was produced using a single-site catalyst prepared according to example 1 of WO 95/12622 A1. The polymerisation was carried out according to Example 1 of EP 1316598 B1.

15

Polyethylene C (comparative)

- A medium density polyethylene was produced using a mixed iron catalyst and a single-site catalyst. The catalysts were prepared and polymerisation carried out according to Example 4 of WO 2009/103516 A2.
- 20

Properties of inventive and comparative polyethylenes are summarised in Table 2.

Table 2

	Polyethylene A (inventive)	Polyethylene B (comparative)	Polyethylene C (comparative)
Density (g/cm ³)	0.939	0.934	0.936
MFR ₂ (g/10 min)	5.4	6.0	2.5
Mn (g/mol)	14 750		
Mw (g/mol)	67 550		95 693
Mz (g/mol)	134 000		280 975
Mw/Mn	2.8		8.9
Comonomer (wt%)	C ₄ 1.5		C ₆ 5.6
Vinyl/kCH _n	0.04		1.08

5

Compositions 1 and 2 (inventive)

The adhesive blend compositions were grafted in Werner & Pfleiderer ZSK 30 mm co-rotating twin-screw extruder. Polyethylene A was used for compositions 1 and 2. The adhesive blend compositions are shown in Table 3.

10

The ethylene butyl acrylate elastomer, which has a density of 0.926 g/cm³, MFR₂ of 4.5 g/10 min and butyl acrylate content of 27 wt%, was added to improve flexibility. The graft was achieved by adding various amounts of maleic anhydride. The peroxide initiator (Perkadox 14S-fl, Akzo Nobel) was fed as a 10% isododecane solution. The temperature in the extruder was varied between 170 and 210 °C and the screw speed was set at 200 rpm.

15

Composition 3 (comparative)

Composition 3 was prepared according to Example 2, Composition 2 of EP 1316598 B1.

20

Composition 4 (comparative)

Polyethylene C was used for composition 4. Composition 4 was prepared according to Example 6 of WO 2009/103516 A2.

25

Table 3.

	Composition 1 (inventive)	Composition 2 (inventive)	Composition 3 (comparative)	Composition 4 (comparative)
Polyethylene (wt%)	77.1	73.1	69.2	55.0 + 14.9 (grafted)
Ethylene butyl acrylate elastomer (wt%)	22.0	26.0	29.7	30.0
Maleic Anhydride (wt%)	0.40	0.40	0.50	0.08
Peroxide solution (wt%)	0.5	0.5	0.5	
Antioxidant (wt%)	none	None	0.1	

Processing of compositions 1-2

5

Table 4 shows properties of the grafted adhesive blend compositions and adhesion properties of co-extrudable adhesives coated on steel pipes.

10 Epoxy powder was sprayed on as corrosion protection, where the temperature of the rotating steel pipeline (8m/min) was 200-220 °C. The adhesive blend composition and the conventional high-density polyethylene outer layer were co-extruded onto the epoxy layer. The co-extrusion was performed with KrausMaffei 45 mm and Barmag 45 mm single screw extruders. The temperature of the adhesive blend composition and the high-density polyethylene at the respective dies was ca 220 °C. Both the adhesive blend composition and

15 high-density polyethylene layer are rolled tightly onto the coating surface with a silicone pressure roller. Thickness value for the epoxy layer was 145 µm, the adhesive blend composition 430 µm, and the polyethylene outer layer 4.0 mm. The cooled three layer composition was evaluated by measuring its peel strength with a Zwick Roell tensile testing machine.

20

Processing of composition 3

Processing of composition 3 was done according to Example 3 of EP 1316598 B1.

Processing of composition 4

Coating of a steel plate and measuring of peel strength were done according to examples of WO 2009/103516 A2.

5

Table 4.

	Composition 1 (inventive)	Composition 2 (inventive)	Composition 3 (comparative)	Composition 4 (comparative)
MFR ₂ (g/10 min)	1.2	1.1	1.2	1.9
Density (g/cm ³)	(Not measured)	0.935	0.934	0.931
Peel strength at 23 °C (N/cm)	568	580	468	540

The peel strength at 23 °C of the grafted blend compositions 1 and 2 are better compared to the compositions of the comparative examples.

15

20

25

Claims

1. An adhesive polymer composition comprising

- 5 a) a non-elastomeric copolymer of ethylene and one or more comonomers having 3 to 10 carbon atoms, which non-elastomeric copolymer is present in an amount of 60 to 95 % by weight, based on the adhesive polymer composition, has a weight average molecular weight M_w of from 50 000 to 80 000 g/mol, molecular weight distribution M_w/M_n of 2.0 to 5.5, density of
10 from 0.925 to 0.945 g/cm³, and at most 0.1 vinyl groups/ 1000 carbon atoms, and
 b) an elastomer,

wherein the non-elastomeric copolymer or the non-elastomeric copolymer and the elastomer have been grafted with an acid grafting agent.

15

2. The adhesive polymer composition according to claim 1, wherein the non-elastomeric copolymer is present in an amount of 70 to 90 % by weight based on the adhesive polymer composition.

20

3. The adhesive polymer composition according to claims 1 and 2, wherein the non-elastomeric copolymer has an MFR_2 of from 1 to 20 g/10 min, more preferably from 1 to 10 g/10 min.

25

4. The adhesive polymer composition according to any one of the preceding claims wherein said component a) has a density of from 0.930 to 0.942 g/cm³.

5. The adhesive polymer composition according to any one of the preceding claims, wherein the non-elastomeric copolymer is a polyethylene with unimodal molecular weight distribution.

30

6. The adhesive polymer composition according to any one of the preceding claims, wherein the non-elastomeric copolymer has been produced in a process using a single-site catalyst.

7. The adhesive polymer composition according to any one of the preceding claims, wherein the single-site catalyst comprises a metallocene component on a support and an alumoxane component.
- 5 8. The adhesive polymer composition according to any one of the preceding claims, wherein the adhesive polymer composition has an MFR₂ value of from 0.1 to 10 g/ 10 min, preferably from 1.0 to 6.0 g/min.
9. The adhesive polymer composition according to any one of the preceding claims, wherein
10 the adhesive polymer composition has a density of from 0.925 to 0.945 g/cm³, more preferably from 0.930 to 0.940 g/cm³.
10. The adhesive polymer composition according to any one of the preceding claims, wherein the acid grafting agent is an unsaturated carboxylic acid or a derivative thereof,
15 more preferably maleic acid or a derivative thereof, in particular maleic anhydride.
11. The adhesive polymer composition according to any one of the preceding claims, wherein the acid grafting agent is present in an amount of from 0.01 to 3.0 parts by weight, more preferably from 0.03 to 1.5 parts by weight based on the adhesive polymer
20 composition.
12. The adhesive polymer composition according to any one of the preceding claims, wherein the elastomer comprises an elastomeric ethylene copolymer.
- 25 13. The adhesive polymer composition according to any one of the preceding claims, wherein the elastomer comprises an elastomeric ethylene copolymer with polar comonomer groups.
14. An article, in particular a multilayer pipe, comprising an adhesive layer which comprises
30 the adhesive polymer composition according to any of the preceding claims.
15. Use of the adhesive polymer composition according to any one of claims 1 to 13 for the production of an adhesive layer, preferably an adhesive layer of a pipe.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2018/063599

A. CLASSIFICATION OF SUBJECT MATTER
INV. C09J151/06 F16L9/12 F16L13/02 B32B27/30
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C09J F16L C08L B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 2009/103516 A2 (BASELL POLYOLEFINE GMBH [DE]; VOGT HEINZ [DE]; MIHAN SHAHRAM [DE]; MAN) 27 August 2009 (2009-08-27) cited in the application example 6	1-15
A	----- EP 1 316 598 A1 (BOREALIS TECH OY [FI]) 4 June 2003 (2003-06-04) cited in the application paragraphs [0051] - [0057]; examples 1-3	1-15
A	----- WO 95/12622 A1 (BOREALIS HOLDING AS [DK]; KALLIO KALLE [FI]; ANDELL OVE [FI]; KNUUTTIL) 11 May 1995 (1995-05-11) cited in the application example 1	1-15
	----- -/-	



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

24 July 2018

Date of mailing of the international search report

02/08/2018

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Iraegui Retolaza, E

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2018/063599

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2013/085221 A1 (BOTROS MAGED G [US] ET AL) 4 April 2013 (2013-04-04) claims; examples -----	1-15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2018/063599

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2009103516	A2	27-08-2009	AT 531776 T 15-11-2011
		BR PI0908249 A2 21-07-2015	
		CA 2713892 A1 27-08-2009	
		CN 102037090 A 27-04-2011	
		EP 2134801 A2 23-12-2009	
		EP 2236577 A2 06-10-2010	
		MY 152524 A 15-10-2014	
		RU 2010138562 A 27-03-2012	
		US 2011045295 A1 24-02-2011	
		WO 2009103516 A2 27-08-2009	
EP 1316598	A1	04-06-2003	AT 468377 T 15-06-2010
		AU 2002365503 A1 10-06-2003	
		BR 0214465 A 03-11-2004	
		CN 1592776 A 09-03-2005	
		EA 200400747 A1 30-12-2004	
		EP 1316598 A1 04-06-2003	
		ES 2341605 T3 23-06-2010	
		KR 20040083057 A 30-09-2004	
		WO 03046101 A1 05-06-2003	
WO 9512622	A1	11-05-1995	AT 195325 T 15-08-2000
		AU 685870 B2 29-01-1998	
		BR 9407968 A 03-12-1996	
		CA 2175702 A1 11-05-1995	
		CN 1134160 A 23-10-1996	
		CZ 9601305 A3 17-07-1996	
		DE 69425485 D1 14-09-2000	
		DE 69425485 T2 11-01-2001	
		EP 0678103 A1 25-10-1995	
		ES 2149950 T3 16-11-2000	
		FI 934917 A 06-05-1995	
		HU 216545 B 28-07-1999	
		IL 111532 A 29-02-2000	
		JP 2990299 B2 13-12-1999	
		JP H09504567 A 06-05-1997	
		KR 100262245 B1 15-07-2000	
		MY 131681 A 30-08-2007	
		SK 56096 A3 09-04-1997	
		TW 341578 B 01-10-1998	
		US 6291611 B1 18-09-2001	
		WO 9512622 A1 11-05-1995	
US 2013085221	A1	04-04-2013	CN 103946330 A 23-07-2014
		EP 2760958 A1 06-08-2014	
		US 2013085221 A1 04-04-2013	
		US 2016222257 A1 04-08-2016	
		WO 2013049786 A1 04-04-2013	