



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶ : A61K 7/11	A1	(11) International Publication Number: WO 99/38478 (43) International Publication Date: 5 August 1999 (05.08.99)
(21) International Application Number: PCT/US99/00718 (22) International Filing Date: 13 January 1999 (13.01.99) (30) Priority Data: 09/014,464 28 January 1998 (28.01.98) US (71) Applicant: ISP INVESTMENTS INC. [US/US]; 818 Washington Street, Wilmington, DE 19801 (US). (72) Inventor: LIU, Kou-Chang; 11 Drayton Place, Wayne, NJ 07470 (US). (74) Agents: MAUE, Marilyn, J. et al.; International Specialty Products, Legal Dept., Building 10, 1361 Alps Road, Wayne, NJ 07470 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: PERSONAL CARE COMPOSITION CONTAINING A HOMOGENEOUS TERPOLYMER OF AN N-VINYL LACTAM AND A POLYSILOXANE		
(57) Abstract A homogeneous terpolymer of random monomer distribution containing from 30 to 90 % of a N-vinyl lactam, from 0,5 to 20 % of a mono- or di- functional polysiloxane and from 5 to 50 % of quaternized or non-quaternized dimethylaminoalkyl- acrylate, methacrylate, acrylamide or methacrylamide combined to form a 100 % terpolymer composition for use in a personal care applications, particularly as a hair fixative and conditioning where colorless and clear film forming properties of the terpolymer provides a superior silky, lustrous appearance to the hair.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakistan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PERSONAL CARE COMPOSITION CONTAINING A
HOMOGENEOUS TERPOLYMER OF AN
N-VINYL LACTAM AND A POLYSILOXANE

BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to homogeneous terpolymers of an N-vinyl lactam, and at least one vinyl polysiloxane in predetermined concentrations and in random monomer distribution in the terpolymer structure to more uniformly diffuse the individual properties of each monomer.

Description of the Prior Art

Several non-volatile polysiloxane polymers e.g. polyethylene oxide or polypropylene oxide modified types, (Dow Corning DC-1248) have been proposed as hair shampoo additives. Such polysiloxanes can be employed as encapsulating agents for active components as described in U.S. Patent 5,156,914. However, the use of most polysiloxanes in formulations is somewhat limited by their high water insolubility.

Many synthetic polymers containing vinyl lactams are employed in hair and skin care applications of the prior art. Representative of this art are U.S. Patents 3,914,403; 3,954,960; 4,039,734, 4,057,533; 4,210,161; 4,223,009, 4,586,518; 4,764,363; 4,834,968; 4,842,850;

4,902,499; 4,906,459; 4,923,694; 4,963,348; 4,983,77;
5,011,895; 5,015,708; 5,126,124; 5,158,762; 5,275,809;
5,502,136; WO 91/15186; WO 91/15185; EPO 412704A2; EPO
0412707A1 and JP 57126409.

Several U.S. patents disclose the use of a N-vinyl lactam, an alkylaminoalkyl (meth)acrylate or (meth)acrylamide as a polymer suitable for use in the pharmaceutical and cosmetic arts, particularly for use in hair spray compositions. These patents are 3,910,862; 4,923,694; 5,045,617; 5,321,110; 5,492,988 and 5,637,296 and of these, only U.S. 5,492,988; 5,684,105; 5,609,865 and 5,626,836 disclose a homogeneous polymer structure. However, the homogeneous polymers of the prior art lack the essential third monomer unit of the present invention which provides superior shine and soft, silky appearance to the hair without sacrificing body building and durable film forming properties. Several patents describe the use of insoluble silicones with surfactants in shampoo formulations for removal of excess oils. These patents are PCT 760,132; U.S. 4,704,272; 4,741,855; 4,36,837 and 4,788,006. U.S. Patent 5,156,914 describes the encapsulation of silicone oils and gums with surfactant in a polymer matrix for use in a shampoo formulation. However the discrete silicone droplets encapsulated in the polymer are not distributed throughout the polymer and diffusion of monomeric properties as in homogeneous polymers is not achieved. The PCT 760,132 graft polymers fails to obtain uniformity in the beneficial properties of homogeneous polymers.

The homogeneous polymer structure is achieved only by the processes disclosed in U.S. patents 5,609,865; 5,626,836; 5,492,988 and 5,684,105 whose teachings are incorporated herein by reference. The homogeneous polymerization process generally comprises monitoring the feed rate of the more active monomer species with the rate of consumption of the less active monomer species.

Accordingly, it is an object of this invention to provide a new and colorless terpolymer of homogeneous structure having additional benefits for cosmetic and personal care formulations.

Another object is to provide a polymer having superior hair luster and tone without sacrifice to body building and durable film forming properties for use in a hair fixative composition which terpolymer is quick drying and provides a soft natural appearance.

Another object centers on the ability to adjust the degree of hair hold and conditioning by the choice of certain polyfunctional monomers in the homogeneous terpolymer system.

Still another object is to provide a terpolymer having random distribution of monomer units in the polymer so as to substantially and uniformly distribute the properties of the individual monomers throughout the polymer.

These and other benefits and uses of the present invention will become apparent from the following description and disclosure.

DEFINITIONS

For the purposes of this invention, the term "polymer" is intended to describe the polymer containing three distinct monomer unit species as more particularly defined hereinafter. The terms "acrylamide" and "acrylate" as used alone or in combined form, are intended to include the methacrylamide, methacrylate and visa versa. For example, "dimethylamino ethylmethacrylate" (DMAEMA) is intended to include dimethylamino ethylacrylate, alone or both in admixture unless otherwise indicated. Similarly, "dimethylamino propylmethacrylamide" (DMPMA), includes dimethylamino propyl acrylamide, alone or both in admixture unless otherwise indicated.

A personal care concentrate of the present invention as used for example in a hair spray, hair styling mousse or gel, is the present homogeneous terpolymer in an aqueous, aqueous-alcoholic or alcohol solvent wherein the concentration of the polymer is between about 0.1 and about 10 wt.%, preferably between about 0.5 and about 2 wt.%.

A 50-60% VOC (volatile organic compounds) pump hair spray composition is a solution or suspension of the present homogeneous terpolymer containing from about 1 to about 10% solids, preferably from about 2 to about 5.5% solids, in 60% or less solvent, such as an alcohol, e.g. ethanol, the remainder being water and excipients at the

option of the formulator but preferably contains a corrosion inhibitor.

A 50-60% VOC aerosol hair spray of this invention contains between about 1 and about 10% solids, preferably between about 2 and about 4% solids, in a microsuspension of the homogeneous terpolymer, 20% or less alcohol, preferably ethanol, and 35% or less propellant, e.g. dimethyl ether. Generally the composition also contains a neutralizer and other excipients as well as a corrosion inhibitor, e.g. ethoxylated butynediol, a thioester, etc.

SUMMARY OF THE INVENTION

In accordance with this invention there is provided a homogeneous terpolymer of (a) from about 30 to about 90 wt.% of a N-vinyl lactam, (b) from about 5 to about 50 wt.% of dimethylaminoalkyl acrylate or acrylamide and (c) from about 0.5 to about 20 wt.% of a mono- or poly-functional polysiloxane monomer


The N-vinyl pyrrolidone and/or N-vinyl caprolactam components may optionally contain one or two C₁ to C₄ alkyl groups substituted on their respective heterocyclic rings.

The terpolymers of this invention have a weight average molecular weight of from about 10,000 to about 5,000,000 and a Hack turbidity preferably less than 5.

DETAILED DESCRIPTION OF THE INVENTION

Within the broad definition of the present polymer, the preferred homogeneous polymer of this invention contains, as the first component, from about 40 to about 85 wt.% of the N-vinyl lactam moiety, most preferably from 60 to 80 wt.%. The N-vinyl lactam component comprises from 0 to 100% VP, from 0 to 100% VCL or mixtures of these monomers; these monomers being most preferably unsubstituted. When a mixture of VP and VCL is employed, a mole ratio of between about 5:1 and about 1:5 is preferred.

The second quaternized or non-quaternized amino component of the polymer is preferably present at a concentration of from about 10 to about 30 wt.% and is an acrylate or acrylamide defined by the formula:




wherein R₁ is hydrogen or methyl; R₂ is C₂ to C₂₀ alkylene;

X is oxygen or $\begin{array}{c} \text{R}_6 \\ | \\ -\text{N}- \end{array}$; R₆, R₃ and R₄ are each independently hydrogen or C₁ to C₄ alkyl; R₅ is C₁ to C₅ alkyl and A is any anion including a halide, sulfate, sulfonate, phosphate, tosylate etc. As the second (b) component, mixtures of quaternized and non-quaternized compounds are included as well as mixtures of compounds designated by X


such as mixtures of aminoalkyl acrylate and aminoalkylacrylamide in a quaternized or non-quaternized state. Particularly preferred species of (b) are the quaternized and non-quaternized dimethylamino propyl methacrylate, dimethylamino propylacrylate, dimethylamino ethylacrylate, 3-methyl acrylamidopropyl trimethyl ammonium chloride (MAPTAC), 3-methylacrylamido propyl dimethylethyl tosylate and dimethylamino propyl methacrylamide (DMAPMA).

The polysiloxane component (c) is preferably employed at a concentration of from 1 to 20 wt.% for the monofunctional polysiloxane (MVPS) and from about 0.5 to about 10 wt.% for the difunctional polysiloxane (DVPS). Most preferably a concentration of from 2 to 10% monofunctional or 1 to 5% difunctional polysiloxane is employed. The siloxane monomer is broadly described by the formula:




wherein n has a value of from 1 to 100;

W is vinyl dimethyl silyl,



methacryloxyalkyl dimethyl silyl,



wherein q has a value of from 1 to 50, preferably 2 to 10, Y = W or Y is phenyl or $\text{CH}_3(\text{CH}_2)_p$ where p has a value from 0 to 6 and Z is methylene or C_2 to C_4 alkylene oxide. Examples of the silyl monomers include mono- or di-methacryloxy propyl terminated polydimethyl siloxane, mono- or di- acryloxy propyl terminated polydimethyl-siloxane and di- vinyl terminated polydimethylsiloxane. Mixtures of vinyl polysiloxane monomers are also included in this invention as the third component of the terpolymer. The preferred species of the vinyl polysiloxanes are those wherein alkyl is methyl or ethyl and include vnyl poly(dimethylsiloxane); divinyl poly(dimethylsiloxane; vinyl poly(dimethylsiloxane/methyl vinylsiloxane); vnyl poly(dimethylsiloxane/methylphenyl-siloxane); polyalkylene oxide modified siloxanes are also suitable for monomers of the present invention as well as mixed aliphatic/aromatic types supplied by General Electric (VISCASIL series) and Dow Corning (200 series) having Brookfield viscosities between about 5-600,000 cps preferably 300-1,000 cps. Other suitable polysiloxanes are polymerizable species disclosed in U.S. Patents 4,788,006; 4,741,855; 4,704,272 and 4,364,837.

The polysiloxane moiety in the present homogeneous terpolymer reinforces body building and luster to hair while increasing combability. The polyfunctional siloxane introduces a degree of crosslinking in the terpolymer which further promotes hair body building properties and produces a firmer hold.

In the present invention, the high water insolubility of the polysiloxane component is overcome by the homogeneous structure of the terpolymer where monomer moieties are randomly distributed as opposed to blocks of polysiloxane moieties which concentrate hydrophobicity.

A further benefit of the siloxane moiety in the present homogeneous terpolymer is that the silky texture imparted to the hair is not accompanied with the commonly associated attraction of static electricity which is responsible for "fly away", unmanageable hair. Incorporation of the siloxane moiety in the homogeneous polymer reinforces body building and luster and soft feel to hair while increasing combability. The polyfunctional siloxane introduces a degree of crosslinking in the polymer which further promotes hair body building properties and produces a firmer stronger hold.

The present terpolymer is generally prepared according to the homogeneous polymerization process disclosed in U.S. patents 5,492,988; 5,609,865; 5,684,105 and 5,626,836; the teachings of which is incorporated herein by reference. In summary, the process involves precharging the monomer having the lowest reactivity and initiator prior to the charge of major amounts of the remaining monomers having higher reactivity and

controlling the gradual feed rate of the more reactive monomer species so that the relative concentrations of all monomer species remain constant throughout the polymerization reaction and the product at completion of the polymerization contains less than 0.1% unreacted VP and/or less than 1% unreacted VCL.

Suitable initiators for the homogeneous polymerization reaction are the conventional free radical types which include organic and inorganic compounds such as hydrogen peroxide, lauryl peroxide, t-butylperoxy pivalate (LUPERSOL® 11); t-amylperoxy pivalate (LUPERSOL® 554); dimethyl 2,5-di(t-butylperoxy) hexane (LUPERSOL® 101); azobis(butyronitrile); azobis(methylnitrile); azobis(diisobutyronitrile); azobis(isovaleronitrile); azobis(cyclohexanecarbonitrile) etc.

The solution polymerization is carried out at a temperature of between about 50° and about 90°C, preferably between about 60° and about 80°C for a period of from about 4 to about 100 hours, more conveniently from about 6 to about 30 hours or until the polymerization is completed by indication of the above trace amounts of residual monomer.

To obtain the present polymer having a homogeneous structure it is critical that part or all of the least reactive monomer be precharged into a reactor and that at least a major portion of the more reactive remaining monomers, be then introduced incrementally or continuously into the pre-charged reactor at such rates that allow the ratio of the relative concentrations of all monomers to remain constant throughout the reaction

so that all monomers can react to form a substantially homogeneous polymer in a desired compositional ratio. Consequently, the substantially homogeneous polymer of this invention is obtained whose composition approaches the nominal monomer ratio of the desired polymer composition and whose structure has at least three individual monomeric unit groups of the polymer distributed substantially uniformly in a homogeneous chain along the backbone of the polymer.

The precharge in the process of the invention may include some of the more active component monomers, generally in an amount of up to about 30% of the total amount of second and third monomers required for a predetermined terpolymer composition without affecting the homogeneous polymerization process.

The schedule of addition to accomplish the desired matched rate of reaction is described in following Examples.

EXAMPLE 1

Preparation of a Homogeneous Terpolymer of 74% VP, 20% DMAPMA and 6% Witico Y-14225

Initially, vinylpyrrolidone (VP), dimethylaminopropylmethacrylamide (DMAPMA) and Witico Y-14225, an acrylated siloxane polyalkylene oxide copolymer, and ethanol were charged into a two liter resin pot equipped with a gas inlet, a liquid inlet, a thermometer, a condenser and a mechanical stirrer. The solution was gradually heated to 78°C and a stream of

nitrogen introduced which bubbled through the solution during the reaction to remove oxygen from the system. The remaining amounts of the monomers were then added to the solution according to the time shown in Table I, so that the relative concentrations of the component monomers remained practically constant throughout the reaction.

An ethanol solution of 2,2'-azobis(2-methylbutane-nitrile) (Vazo-67) initiator was added to the reaction pot as soon as the scheduled monomer feedings started. A total of 4.4 g of the initiator solution was added in portion over 5.5 hours. The solution was held for an additional 10 hours at 78°C to yield an ethanol solution of compositionally homogeneous copolymer of VP/DMAPMA/Y-14225.

TABLE I

Time (min)	VP (g)	DMAPMA (ml)	Y-14225 Si (ml)	EtOH (ml)	Total (g)
0	444	12.77	3.5	1000.13	1244.71
0-30		23.98	6.57	30.55	1298
30-60		23.43	6.42	29.85	1350.07
60-90		19.2	5.26	24.46	1392.74
90-120		15.08	4.13	19.21	1426.25
120-150		11.03	3.02	14.05	1450.76
150-180		7.98	2.19	10.17	1468.5
180-210		5.67	1.55	7.22	1481.09
210-240		3.95	1.08	5.03	1489.86
240-270		2.71	0.74	3.45	1495.88
270-300		1.86	0.51	2.38	1500.02
Total (g)	444	120	36	900	1500

EXAMPLE 2Preparation of a Homogeneous Terpolymer of
83% VP, 15% MAPTAC and 2% Huls PS-441

Initially, vinylpyrrolidone (VP), 3-trimethylammonium propylmethacrylamide chloride (MAPTAC), Huls PS-441, a vinyl dimethyl terminated polydimethylsiloxane (viscosity = 100 cps), and methanol are charged into a two liter resin pot equipped with a gas inlet, a liquid inlet, a thermometer, a condenser and a mechanical stirrer. The solution is gradually heated to 75°C and a stream of nitrogen introduced which bubbled through the solution during the reaction to remove oxygen from the system. The remaining amounts of the monomers are then added to the solution according to the time shown in Table II, so that the relative concentrations of the component monomers remained practically constant throughout the reaction.

A methanol solution of 2,2'-azobis(2-methylbutanenitrile) (Vazo-67) initiator is added to the reaction pot as soon as the scheduled monomer feedings started. A total of 4.4 g of the initiator solution is added in portion over 5.5 hours. The solution is held for an additional 12 hours at 75°C to yield a methanol solution of compositionally homogeneous copolymer of VP/MAPTAC/PS-441.

TABLE II

<u>Time (min)</u>	<u>VP (g)</u>	<u>MAPTAC (ml)</u>	<u>PS-441 Si (ml)</u>	<u>MeOH (ml)</u>	<u>Total (g)</u>
0	581	9.97	14	750.56	1356.06
0-30		39.55			1397.71
30-60		38.64			1438.4
60-90		31.66			1471.74
90-120		24.87			1497.93
120-150		18.19			1517.08
150-180		13.16			1530.94
180-210		9.35			1540.79
210-240		6.51			1547.65
240-270		4.47			1552.36
270-300		3.08			1555.6
Total (g)	581	210	14	750.56	1555.56

MAPTAC is 50% aqueous

EXAMPLE 3

Preparation of a Homogeneous Terpolymer of
65% VCL, 30% DMAPMA-50% DES quat and 5% Huls PS-583

Initially, vinylpyrrolidone (VP), 50% diethylsulfate quaternized dimethylaminopropylmethacrylamide (DMAPMA-50% DES quat) and Huls PS-583, a polydimethyl siloxane methacryloxypropyl terminated, and ethanol are charged into a two liter resin pot equipped with a gas inlet, a liquid inlet, a thermometer, a condenser and a mechanical stirrer. The solution is gradually heated to 78°C and a stream of nitrogen introduced which bubbled through the solution during the reaction to remove oxygen from the system. The remaining amounts of the monomers are then added to the solution according to the time shown in Table III, so that the relative concentrations of the component monomers remained practically constant throughout the reaction.

An ethanol solution of 2,2'-azobis(2-methylbutane-nitrile) (Vazo-67) initiator is added to the reaction pot as soon as the scheduled monomer feedings started. A total of 4.4 g of the initiator solution is added in portion over 5.5 hours. The solution is held for an additional 10 hours at 78°C to yield an ethanol solution of compositionally homogeneous copolymer of VP/DMAPMA-50% DES quat/PS-583.

TABLE III

Time (min)	VCL (g)	DMAPMA (ml)	PS-583 Si (ml)	EtOH (ml)	Total (g)
0	341.25	7.9	1.31	1051.43	1175.81
0-30		31.32	5.21	39.78	1243.47
30-60		30.6	5.09	38.87	1309.58
60-90		25.08	4.17	31.85	1363.76
90-120		19.7	3.27	25.02	1406.31
120-150		14.41	2.39	18.3	1437.43
150-180		10.42	1.73	13.24	1459.94
180-210		7.4	1.23	9.4	1475.93
210-240		5.16	0.86	6.55	1487.08
240-270		3.54	0.59	4.5	1494.73
270-300		2.43	0.4	3.09	1499.98
Total (g)	341.25	157.5	26.25	975	1500

EXAMPLE 4

Preparation of a Homogeneous Terpolymer of
35% VP, 45% VCL, 15% DMAEMA and 5% Huls PS-442

Initially, vinylpyrrolidone (VP), vinyl caprolactam (VCL), DMAEMA (2-dimethylaminoethyl methacrylate), and Huls PS-442, a vinyl dimethyl terminated polydimethylsiloxane (viscosity = 500 cps), and ethanol are charged into a two liter resin pot equipped with a gas inlet, a liquid inlet, a thermometer, a condenser and a mechanical stirrer. The solution is gradually heated to 75°C and a

stream of nitrogen introduced which bubbled through the solution during the reaction to remove oxygen from the system. The remaining amounts of the monomers are then added to the solution according to the time shown in Table IV, so that the relative concentrations of the component monomers remained practically constant throughout the reaction.

Luperson-11 initiator (t-butylperoxypivalate) is added to the reaction pot as soon as the scheduled monomer feedings started. A total of 1.0 g of the initiator solution is added in portion over 6 hours. The solution is held for an additional 10 hours at 75°C to yield an ethanol solution of compositionally homogeneous copolymer of VP/VCL/DMAEMA/PS-442.

TABLE IV

Time (min)	VCL (g)	VP (ml)	DMAEMA (ml)	PS442 Si (g)	EtOH (ml)	Total (g)
0	202.5	76.17	3.62	22.5	1193.59	1244.56
0-30		43.94	14.35		58.29	1349.4
30-60		20.1	14.01		34.11	1410.15
60-90		8.13	11.48		19.61	1444.71
90-120		3.1	9.02		12.12	1465.86
120-150			6.6		6.6	1477.2
150-180			4.77		4.77	1485.39
180-210			3.39		3.39	1491.21
210-240			2.36		2.36	1495.26
240-270			1.62		1.62	1498.04
270-300			1.11		1.11	1499.95
Total (g)	202.5	157.5	67.5	22.5	1050	1500

EXAMPLE 5Preparation of a Homogeneous Terpolymer of
70% VP, 20% DMAPMA and 10% Huls PS-560

Initially, vinylpyrrolidone (VP), dimethylamino-propylmethacrylamide (DMAPMA) and Huls PS-560, a polydimethyl siloxane monomethacryloxypropyl terminated, and ethanol are charged into a two liter resin pot equipped with a gas inlet, a liquid inlet, a thermometer, a condenser and a mechanical stirrer. The solution is gradually heated to 78°C and a stream of nitrogen introduced which bubbled through the solution during the reaction to remove oxygen from the system. The remaining amounts of the monomers are then added to the solution according to the time shown in Table V, so that the relative concentrations of the component monomers remained practically constant throughout the reaction.

An ethanol solution of 2,2'-azobis(2-methylbutane-nitrile) (Vazo-67) initiator is added to the reaction pot as soon as the scheduled monomer feedings started. A total of 4.4 g of the initiator solution is added in portion over 5.5 hours. The solution is held for an additional 10 hours at 78°C to yield an ethanol solution of compositionally homogeneous copolymer of VP/DMAPMA/PS-560.

TABLE V

Time (min)	VP (g)	DMAPMA (ml)	PS-560 Si (ml)	EtOH (ml)	Total (g)
0	420	6.38	3	968.22	1189.05
0-30		25.31	11.9	37.21	1253.95
30-60		24.73	11.62	36.36	1317.36
60-90		20.27	9.53	29.79	1369.33
90-120		15.92	7.48	23.4	1410.14
120-150		11.64	5.47	17.12	1439.99
150-180		8.42	3.96	12.38	1461.58
180-210		5.98	2.81	8.79	1476.91
210-240		4.17	1.96	6.13	1487.6
240-270		2.86	1.35	4.21	1494.94
270-300		1.97	0.92	2.89	1499.98
Total (g)	420	120	60	900	1500

Representative applications of the present polymer are the following:

HAIR CARE COMPOSITIONS

In a water-based, hair styling and conditioning composition, the homogeneous polymer of the invention comprises about 0.2-20%, preferably 1-10%, and, most preferably, about 2-8%, by weight of the hair care product, the rest being water, and, optionally including an organic solvent such as ethanol, and/or other acceptable excipient components such as corrosion inhibitors, surface active agents, viscosity modifiers, dyes, chelating agents, distributing aids, pearlescent aids, opacifiers, perfumes, fatty alcohols, pH adjusting agents, and the like.

The homogeneous polymer of the invention also finds particular utility in multifunctional hair care products such as water-based, rinse-off hair styling and conditioning products, and in leave-on hair care products such as a mousse, and may be included as a concentrate,

or as a gel, and applied as a self-actuated pump hair spray, or in an aerosol product with a propellant. Various actuator and packaging devices known in the art may be used therewith.

PROCEDURE FOR PREPARING HAIR SPRAY

COMPOSITIONS OF INVENTION

A. Pump Spray

The pump hair spray compositions of the invention were prepared by first dissolving the homogeneous polymer resin in ethanol and adding the requisite amount of water. The composition then was packaged into a high density polyethylene bottle fitted with a suitable pump actuator, e.g. a pump sprayer (160 ml) with 0.018 x 0.010 inch deep actuator (SEAQUIST EUROMIST II).

B. Aerosol Spray

The aerosol hair spray resin compositions of the invention were prepared from 65% by weight of the hair spray concentrate, a vapor phase inhibitor, a liquid phase inhibitor, adjuvants where needed, and 35% by weight of a propellant, e.g. dimethyl ether.

EXAMPLES 6-9

The following hair spray compositions of the invention were prepared in a stainless steel mixing vessel and mixed at ambient temperature for 20 minutes with a turbine agitator.

TABLE VI
HAIR SPRAY COMPOSITIONS

<u>Example No.</u>	<u>6</u>	<u>7</u>	<u>8</u>	<u>9</u>
<u>Component</u>	<u>Weight %</u>			
Homogeneous polymer of Ex. 1 (45% active in ethanol)	8.90	6.67	8.90	6.67
Water	41.00	42.00	40.50	41.50
Excipients			0.50	0.50
Propellant			35.00	35.00
Ethanol	50.10	51.33	15.10	16.33
	100.00	100.00	100.00	100.00

COMPARATIVE EXAMPLE 10

The following comparative hair spray composition was prepared in the manner set forth above.

TABLE VII

<u>Component</u>	<u>Weight %</u>
Non-Homogeneous polymer of Ex. 1 (45% active in ethanol)	8.90
Water	41.00
Ethanol	50.10

HAIR SPRAY PROPERTIESINVENTION VS. COMPARATIVE EXAMPLE


	<u>Homogeneous Composition (Ex. 6)</u>	<u>Non-Homogeneous Composition (Ex. 10)</u>
Turbidity (HACH)	0.6	40.1
HHCR (90 min)	88.6	84.2
(4 hr.)	76.6	75.3
Particle size, DAV [V, 0.5]	85.3	95.3
Stiffness	8.3	6.7
Curl snap	9.0	6.7
Curl memory	7.7	4.0

While the invention has been described with particular reference to certain embodiments thereof, it will be understood that many changes and modifications within the scope of the foregoing disclosure may be made which are within the skill of the art. Accordingly, it is intended to be bound only by the following claims, in which:

WHAT IS CLAIMED IS:


1. A homogeneous polymer of random monomer distribution containing (a) from about 30 to about 90 wt.% of a N-vinyl lactam, (b) from about 5 to about 50 wt.% of a quaternized and/or non-quaternized dialkylaminoalkyl acrylate and/or -acrylamide, and (c) from 0.5 to about 20 wt.% of a mono- or di-functional polysiloxane; all monomers combined in 100% composition.
2. The homogeneous polymer of claim 1 containing from about 40 to about 85 wt.% of (a), from about 10 to about 30 wt.% of (b) and from about 1 to about 20 wt.% of monofunctional polysiloxane.
3. The homogeneous polymer of claim 2 containing from about 2 to about 10 wt.% of monofunctional polysiloxane.
4. The homogeneous polymer of claim 1 containing from about 40 to about 85 wt.% of (a), from about 10 to about 30 wt.% of (b) and from about 0.5 to about 10 wt.% of difunctional polysiloxane.
5. The homogeneous polymer of claim 4 containing from about 1 to about 5 wt.% of difunctional polysiloxane.

6. The homogeneous polymer of claim 1 wherein said polysiloxane has the formula:




wherein n has a value of from 1 to 100;

W is vinyl dimethyl silyl,



methacryloxyalkyl dimethyl silyl,



wherein q has a value of from 1 to 50, preferably 2 to 10, $Y = W$ or Y is phenyl or $\text{CH}_3(\text{CH}_2)_p$ where p has a value from 0 to 6 and Z is methylene or C_2 to C_4 alkylene oxide.

7. A concentrate of the homogeneous polymer of claim 1 in an aqueous and/or alcoholic medium wherein the concentration of the polymer is between about 10 and about 70 wt. %.

8. The concentrate of claim 7 wherein the concentration of the polymer is between about 30 and about 55 wt.%.

9. A 50-60% VOC pump hair spray fixative composition containing from about 1 to about 10% homogeneous polymer of any one of claims 1, 2, 3 and 4 in less than 65% C₁ to C₄ alkanol and from about 25 to about 95 wt.% water.

10. A 50-60% VOC aerosol spray composition comprising from about 1 to about 10 wt.% homogeneous polymer of any one of claims 1, 2, 3 and 4 in 20% or less alcohol and 35% or less propellant.

11. The aerosol spray of claim 10 wherein said polymer concentration is between about 2 and about 4 wt.%, the alcohol is ethanol and the propellant is dimethyl ether.

12. A hair mousse or styling gel containing between about 0.1 and about 10 wt.% of the polymer of claim 1.

13. A hair mousse or styling gel containing between about 0.1 and about 10 wt.% of the polymer of claim 2.

14. A hair mousse or styling gel containing between about 0.1 and about 10 wt.% of the polymer of claim 4.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US99/00718

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) :A61K 7/11
US CL :424/70.12, 70.15

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/70.12, 70.15

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5,658,557 A (BOLICH, JR. et al.) 19 August 1997, see claims.	1-14
Y	US 5,480,634 A (HAYAMA et al.) 02 January 1996, see claims.	1-14
Y	US 5,609,865 A (LUI et al.) 11 March 1997, see claims.	1-14

Further documents are listed in the continuation of Box C. See patent family annex.

<p>* Special categories of cited documents:</p> <p>*A* document defining the general state of the art which is not considered to be of particular relevance</p> <p>*E* earlier document published on or after the international filing date</p> <p>*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>*O* document referring to an oral disclosure, use, exhibition or other means</p> <p>*P* document published prior to the international filing date but later than the priority date claimed</p>	<p>*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>* & * document member of the same patent family</p>
--	---

Date of the actual completion of the international search

10 MARCH 1999

Date of mailing of the international search report

23 APR 1999

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

Peter Kulkosky
PETER KULKOSKY aco For

Telephone No. (703) 308-1235