



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2579232 C 2015/05/26

(11)(21) **2 579 232**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(86) **Date de dépôt PCT/PCT Filing Date:** 2005/10/18
(87) **Date publication PCT/PCT Publication Date:** 2006/04/27
(45) **Date de délivrance/Issue Date:** 2015/05/26
(85) **Entrée phase nationale/National Entry:** 2007/03/02
(86) **N° demande PCT/PCT Application No.:** US 2005/037750
(87) **N° publication PCT/PCT Publication No.:** 2006/045017
(30) **Priorité/Priority:** 2004/10/20 (US60/620,639)

(51) **Cl.Int./Int.Cl. C09D 151/08** (2006.01),
B65D 17/00 (2006.01)

(72) **Inventeurs/Inventors:**
O'BRIEN, ROBERT M., US;
RARDON, DANIEL E., US;
SPYNDA, RACHAEL ANN, US;
BARTLEY, GEORGE K., III, US;
EVANS, RICHARD H., US

(73) **Propriétaire/Owner:**
VALSPAR SOURCING, INC., US

(74) **Agent:** SMART & BIGGAR

(54) **Titre : COMPOSITIONS DE REVETEMENT POUR CANETTES ET PROCEDES DE REVETEMENT**
(54) **Title: COATING COMPOSITIONS FOR CANS AND METHODS OF COATING**

(57) **Abrégé/Abstract:**

A coating composition for a food or beverage can that includes an emulsion polymerized latex polymer formed by combining an ethylenically unsaturated monomer component with an aqueous dispersion of a salt of an acid-or anhydride-functional polymer and an amine, preferably, a tertiary amine.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
27 April 2006 (27.04.2006)

PCT

(10) International Publication Number
WO 2006/045017 A1

(51) International Patent Classification:

C09D 151/08 (2006.01) **B65D 17/00** (2006.01)

(21) International Application Number:

PCT/US2005/037750

(22) International Filing Date: 18 October 2005 (18.10.2005)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

60/620,639 20 October 2004 (20.10.2004) US

(71) Applicant (for all designated States except US):

VALSPAR SOURCING, INC. [US/US]; 1101 South Third Street, Minneapolis, MN 55415 (US).

(72) Inventors; and

(75) **Inventors/Applicants (for US only): O'BRIEN, Robert, M.** [US/US]; 163 Ridge Road, Monongahela, PA 15063 (US). **RARDON, Daniel, E.** [US/US]; 5972 Alder Street, Pittsburgh, PA 15232 (US). **SPYNDA, Rachael, Ann** [US/US]; 135 Weller Drive, Wexford, PA 15090 (US). **BARTLEY, George, K., III** [US/US]; 168 Raymond Street, Burgettstown, PA 15021 (US). **EVANS, Richard, H.** [US/US]; 1801 St. James Place, Wexford, PA 15090 (US).

(74) **Agent: MUETING, Ann, M.**; Mueting, Raasch, Gebhardt, P.A., P.O. Box 581415, Minneapolis, MN 55458-1415 (US).

(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) **Title:** COATING COMPOSITIONS FOR CANS AND METHODS OF COATING

(57) **Abstract:** A coating composition for a food or beverage can that includes an emulsion polymerized latex polymer formed by combining an ethylenically unsaturated monomer component with an aqueous dispersion of a salt of an acid-or anhydride-functional polymer and an amine, preferably, a tertiary amine.

WO 2006/045017 A1

79713-5

5

COATING COMPOSITIONS FOR CANS AND METHODS OF COATING

10

BACKGROUND

15 A wide variety of coatings have been used to coat the surfaces of packaging articles (e.g., food and beverage cans). For example, metal cans are sometimes coated using "coil coating" or "sheet coating" operations, i.e., a planar coil or sheet of a suitable substrate (e.g., steel or aluminum metal) is coated with a suitable composition and hardened (e.g., cured). The coated substrate then is formed into the can end or body. Alternatively, liquid coating compositions may be applied (e.g., by
20 spraying, dipping, rolling, etc.) to the formed article and then hardened (e.g., cured).

Packaging coatings should preferably be capable of high-speed application to the substrate and provide the necessary properties when hardened to perform in this demanding end use. For example, the coating should be safe for food contact, have excellent adhesion to the substrate, and resist degradation over long periods of time,
25 even when exposed to harsh environments.

Many current packaging coatings contain mobile or bound bisphenol A ("BPA") or aromatic glycidyl ether compounds or PVC compounds. Although the balance of scientific evidence available to date indicates that the small trace amounts of these compounds that might be released from existing coatings does not pose any
30 health risks to humans, these compounds are nevertheless perceived by some people as being potentially harmful to human health. Consequently, there is a strong desire to eliminate these compounds from food contact coatings.

From the foregoing, it will be appreciated that what is needed in the art is a packaging container (e.g., a food or beverage can) that is coated with a composition that does not contain extractable quantities of such compounds.

5

SUMMARY

This invention provides a coating composition for a food or beverage can that includes an emulsion polymerized latex polymer. This polymer is formed by combining an ethylenically unsaturated monomer component with an aqueous dispersion of a salt of an acid- or anhydride-functional polymer (i.e., an acid group-
10 or anhydride group-containing polymer) and an amine, preferably, a tertiary amine, and then polymerizing the monomer component.

The ethylenically unsaturated monomer component is preferably a mixture of monomers. At least one of the monomers in the mixture is preferably an alpha, beta-unsaturated monomer, and at least one monomer is preferably an oxirane functional
15 monomer. More preferably, at least one of the monomers in the mixture is an oxirane group-containing alpha, beta-ethylenically unsaturated monomer.

In one embodiment, a method of preparing a food or beverage can is provided. The method includes: forming a composition that includes an emulsion polymerized latex polymer, including: forming a salt of an acid- or anhydride-
20 functional polymer and an amine in a carrier comprising water (and an optional organic solvent) to form an aqueous dispersion; combining an ethylenically unsaturated monomer component with the aqueous dispersion; and polymerizing the ethylenically unsaturated monomer component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer; and applying the
25 composition including the emulsion polymerized latex polymer to a metal substrate prior to or after forming the metal substrate into a food or beverage can or portion thereof.

In another embodiment, the method includes: forming a composition including an emulsion polymerized latex polymer, including: forming a salt of an
30 acid- or anhydride-functional polymer and a tertiary amine in a carrier comprising water (and an optional organic solvent) to form an aqueous dispersion; combining an ethylenically unsaturated monomer component comprising 0.1 wt-% to 30 wt-% of

an oxirane-functional alpha, beta-ethylenically unsaturated monomer with the aqueous dispersion, based on the weight of the monomer component; and polymerizing the ethylenically unsaturated monomer component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer; and
5 applying the composition comprising the emulsion polymerized latex polymer to a metal substrate prior to or after forming the metal substrate into a food or beverage can or portion thereof.

In certain embodiments, the composition can include an organic solvent in the aqueous dispersion. In certain embodiments, the method can include removing
10 at least a portion of the organic solvent, if present, from the aqueous dispersion.

In certain embodiments, applying the composition to a metal substrate includes applying the composition to the metal substrate in the form of a planar coil or sheet, hardening the emulsion polymerized latex polymer, and forming the substrate into a food or beverage can or portions thereof. In certain embodiments,
15 applying the composition to a metal substrate comprises applying the composition to the metal substrate after the metal substrate is formed into a can or portion thereof.

In certain embodiments, forming the substrate into a can or portion thereof includes forming the substrate into a can end or a can body. In certain embodiments, the can is a 2-piece drawn food can, 3-piece food can, food can end, drawn and
20 ironed food or beverage can, beverage can end, and the like. The metal substrate can be steel or aluminum.

In certain embodiments, combining an ethylenically unsaturated monomer component with the aqueous dispersion includes adding the ethylenically unsaturated monomer component to the aqueous dispersion. Preferably, the
25 ethylenically unsaturated monomer component is added incrementally to the aqueous dispersion.

In certain embodiments, the ethylenically unsaturated monomer component includes a mixture of monomers. Preferably, the mixture of monomers includes at least one oxirane functional group-containing monomer, and more preferably, at
30 least one oxirane functional group-containing alpha, beta-ethylenically unsaturated monomer. In certain embodiments, the oxirane functional group-containing monomer is present in the ethylenically unsaturated monomer component in an

amount of at least 0.1 wt-%, based on the weight of the monomer mixture. In certain embodiments, the oxirane functional group-containing monomer is present in the ethylenically unsaturated monomer component in an amount of no greater than 30 wt-%, based on the weight of the monomer mixture.

5 In certain embodiments, the methods of the present invention further include combining the emulsion polymerized latex polymer with one or more crosslinkers, fillers, catalysts, dyes, pigments, toners, extenders, lubricants, anticorrosion agents, flow control agents, thixotropic agents, dispersing agents, antioxidants, adhesion promoters, light stabilizers, organic solvents, surfactants or combinations thereof in
10 the coating composition.

In certain embodiments, the acid-functional polymer has a number average molecular weight of 1500 to 50,000.

In certain embodiments, the composition is substantially free of mobile BPA and aromatic glycidyl ether compounds. Preferably, the composition is substantially
15 free of bound BPA and aromatic glycidyl ether compounds.

In certain embodiments, the acid- or anhydride-functional polymer includes an acid- or anhydride-functional acrylic polymer, acid- or anhydride-functional alkyd resin, acid- or anhydride-functional polyester resin, acid- or anhydride-functional polyurethane, or combinations thereof. Preferably, the acid- or
20 anhydride-functional polymer includes an acid-functional acrylic polymer.

In certain embodiments, the amine is a tertiary amine. Preferably, the tertiary amine is selected from the group consisting of trimethyl amine, dimethylethanol amine (also known as dimethylamino ethanol), methyldiethanol amine, triethanol amine, ethyl methyl ethanol amine, dimethyl ethyl amine, dimethyl
25 propyl amine, dimethyl 3-hydroxy-1-propyl amine, dimethylbenzyl amine, dimethyl 2-hydroxy-1-propyl amine, diethyl methyl amine, dimethyl 1-hydroxy-2-propyl amine, triethyl amine, tributyl amine, N-methyl morpholine, and mixtures thereof. Preferably, the acid- or anhydride-functional polymer is at least 25% neutralized with the amine in water.

30 In certain embodiments, the ethylenically unsaturated monomer component is polymerized in the presence of the aqueous dispersion with a water-soluble free radical initiator at a temperature of 0°C to 100°C. In certain embodiments, the free

79713-5

radical initiator includes a peroxide initiator. Preferably, the free radical initiator includes hydrogen peroxide and benzoin. Alternatively, in certain embodiments the free radical initiator includes a redox initiator system.

5 The present invention also provides food cans and beverage cans prepared by a method described herein.

In one embodiment, the present invention provides a food or beverage can that includes: a body portion or an end portion including a metal substrate; and a coating composition disposed thereon, wherein the coating composition includes an emulsion polymerized latex polymer, wherein the emulsion polymerized latex polymer is prepared from
10 a salt of an acid- or anhydride-functional polymer and an amine, an ethylenically unsaturated monomer component, and water.

In yet another embodiment, the present invention provides a composition for use in coating a food or beverage can, wherein the composition includes an emulsion polymerized latex polymer, wherein the emulsion polymerized latex polymer is prepared from
15 a salt of an acid- or anhydride-functional polymer and an amine, an ethylenically unsaturated monomer component, and water.

According to another aspect of the present invention, there is provided an article comprising: a body portion or an end portion of a food or beverage can comprising a metal substrate; and a coating composition disposed on an inside surface thereof, wherein the
20 coating composition includes an emulsion polymerized latex polymer, and wherein the emulsion polymerized latex polymer: (i) comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a polymer salt, wherein the ethylenically unsaturated monomer component includes at least one oxirane functional group-containing monomer and wherein the ethylenically unsaturated
25 monomer component comprises a vinyl aromatic compound; and (ii) is substantially free of bound bisphenol A and aromatic glycidyl ether compounds.

According to still another aspect of the present invention, there is provided an article comprising: a body portion or an end portion of a food or beverage can comprising a

79713-5

metal substrate; and a coating composition disposed on an inside surface thereof, wherein the coating composition includes an emulsion polymerized latex polymer, and wherein the emulsion polymerized latex polymer: (i) comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a salt of an acid or anhydride-functional polymer and a tertiary amine, wherein the ethylenically unsaturated monomer component comprises 0.1 wt-% to 30 wt-% of an oxirane-functional alpha, beta-ethylenically unsaturated monomer, based on the weight of the monomer component and wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic compound; and (ii) is substantially free of bound bisphenol A and aromatic glycidyl ether compounds.

According to yet another aspect of the present invention, there is provided a method, comprising: providing a coating composition including an emulsion polymerized latex polymer, wherein the emulsion polymerized latex polymer: (i) comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a polymer, wherein the ethylenically unsaturated monomer component includes at least one oxirane functional-group containing monomer and wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic compound, and (ii) is substantially free of bound bisphenol A and aromatic glycidyl ether compounds; and applying the coating composition to a surface of a metal substrate prior to or after forming the metal substrate into a food or beverage can or portion thereof, wherein the surface of the metal substrate coated by the coating composition is an inside surface.

According to a further aspect of the present invention, there is provided a method of coating an inside surface of a food or beverage can, the method comprising: forming a composition comprising an emulsion polymerized latex polymer, comprising: forming a salt of an acid- or anhydride-functional polymer and an amine in a carrier comprising water to form an aqueous dispersion; combining an ethylenically unsaturated monomer component with the aqueous dispersion; wherein the ethylenically unsaturated monomer component includes at least one oxirane functional group containing monomer and wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic compound; and polymerizing the ethylenically unsaturated monomer component in the

79713-5

presence of the aqueous dispersion to form an emulsion polymerized latex polymer that is substantially free of bound bisphenol A and aromatic glycidyl ether compounds; and applying the composition comprising the emulsion polymerized latex polymer to a metal substrate on an inside surface side prior to or after forming the metal substrate into a food or beverage can
5 or portion thereof.

According to yet a further aspect of the present invention, there is provided a method of coating an inside surface of a food or beverage can, the method comprising: forming a composition comprising an emulsion polymerized latex polymer, comprising: forming a salt of an acid- or anhydride-functional polymer and a tertiary amine in a carrier
10 comprising water to form an aqueous dispersion; combining an ethylenically unsaturated monomer component comprising 0.1 wt-% to 30 wt-% of an oxirane-functional alpha, beta-ethylenically unsaturated monomer with the aqueous dispersion, based on the weight of the monomer component, wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic compound; and polymerizing the ethylenically unsaturated monomer
15 component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer; and applying the composition comprising the emulsion polymerized latex polymer to a metal substrate on an inside surface side prior to or after forming the metal substrate into a food or beverage can or portion thereof.

According to still a further aspect of the present invention, there is provided a
20 method of coating an inside surface of a food or beverage can, the method comprising: receiving a composition formulated for inside spraying comprising the output of a process, the process comprising forming a composition comprising an emulsion polymerized latex polymer by: forming a salt of an acid- or anhydride-functional polymer and an amine in a carrier comprising water to form an aqueous dispersion; combining an ethylenically
25 unsaturated monomer component with the aqueous dispersion; wherein the ethylenically unsaturated monomer component includes at least one oxirane functional group containing monomer and wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic compound; and polymerizing the ethylenically unsaturated monomer component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer that is
30 substantially free of bound bisphenol A and aromatic glycidyl ether compounds; and spray

79713-5

applying the composition comprising the emulsion polymerized latex polymer to a metal substrate on an inside surface side prior to or after forming the metal substrate into a food or beverage can or portion thereof.

According to another aspect of the present invention, there is provided a
5 method of coating an inside surface of a food or beverage can, the method comprising:
receiving a composition formulated for inside spraying comprising the output of a process, the
process comprising forming a composition comprising an emulsion polymerized latex
polymer by: forming a salt of an acid- or anhydride-functional polymer and an amine in a
carrier comprising water to form an aqueous dispersion; combining an ethylenically
10 unsaturated monomer component with the aqueous dispersion; wherein the ethylenically
unsaturated monomer component comprises butyl acrylate; and wherein the ethylenically
unsaturated monomer component further comprises a vinyl aromatic compound; and
polymerizing the ethylenically unsaturated monomer component in the presence of the
aqueous dispersion to form an emulsion polymerized latex polymer that is substantially free of
15 bound bisphenol A and aromatic glycidyl ether compounds; and spray applying the
composition comprising the emulsion polymerized latex polymer to a metal substrate on an
inside surface side prior to or after forming the metal substrate into a food or beverage can or
portion thereof.

According to yet another aspect of the present invention, there is provided a
20 method, comprising the steps of: receiving a coating composition that includes an emulsion
polymerized latex polymer that comprises a reaction product of an ethylenically unsaturated
monomer component polymerized in the presence of an aqueous dispersion of a salt of an
acid- or anhydride-functional polymer, wherein the ethylenically unsaturated monomer
component includes an oxirane group-containing monomer, and wherein the coating
25 composition is made without using PVC compounds, BPA, or aromatic glycidyl ether
compounds; and spray applying the coating composition onto an interior surface of an
aluminum beverage can including a body portion and a bottom end portion.

According to yet another aspect of the present invention, there is provided a
method, comprising the steps of: receiving a coating composition that includes an emulsion

79713-5

polymerized latex polymer that comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a salt of an acid- or anhydride-functional acrylic polymer and an amine, wherein the ethylenically unsaturated monomer component includes an oxirane group-containing monomer, and
5 wherein the coating composition is made without using PVC compounds, BPA, or aromatic glycidyl ether compounds; and spray applying the coating composition onto an interior surface of an aluminum beverage can including a body portion and a bottom end portion.

According to yet another aspect of the present invention, there is provided a coated article comprising: an aluminum beverage can including a body portion and a bottom
10 end portion; and a cured coating on an interior surface of the aluminum beverage can, wherein the coating is formed from a coating composition that includes an emulsion polymerized latex polymer that comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a salt of an acid- or anhydride-functional polymer, wherein the ethylenically unsaturated monomer component
15 includes an oxirane group-containing monomer, and wherein the coating composition is made without using PVC compounds, BPA, or aromatic glycidyl ether compounds.

According to yet another aspect of the present invention, there is provided a method, comprising the steps of: (a) providing a latex-based coating composition that includes one or more polymers, wherein the one or more polymers are formed by
20 polymerizing one or more ethylenically unsaturated monomers, wherein the ethylenically unsaturated monomers include (i) one or more oxirane functional group-containing monomers, (ii) one or more acid-functional monomers and (iii) one or more additional ethylenically unsaturated monomers selected from butyl (meth)acrylate or styrene, wherein the one or more oxirane functional-group containing monomers are polymerized into the one
25 or more polymers using an emulsion polymerization, and wherein the coating composition is not made using PVC compounds and is substantially free of bound BPA and aromatic glycidyl ether compounds; and (b) spray applying the coating composition to an interior surface of a food or beverage can or a portion thereof.

79713-5

According to yet another aspect of the present invention, there is provided a method, comprising the steps of: (a) providing an aqueous coating composition that includes a latex polymer that is substantially free of bound BPA and aromatic glycidyl ether compounds and is made without using PVC compounds, wherein the latex polymer is formed
5 by emulsion polymerizing a mixture of ethylenically unsaturated monomers comprising 0.1 to 30 weight percent oxirane functional group-containing monomer, based on the weight of the mixture, in the presence of an acid- or anhydride-functional polymer; and (b) spray applying the coating composition to an interior surface of a food or beverage can or a portion thereof.

According to yet another aspect of the present invention, there is provided a
10 method, comprising the steps of: (a) providing an aqueous coating composition that includes a latex polymer that is substantially free of bound BPA and aromatic glycidyl ether compounds, wherein the latex polymer is formed by emulsion polymerizing a mixture of ethylenically unsaturated monomers comprising butyl acrylate, styrene, and 0.1 to 30 weight
15 percent of oxirane functional group-containing monomer, based on the weight of the mixture, in the presence of an acid- or anhydride-functional acrylic polymer having an acid number of at least 40 milligrams KOH per gram resin; and (b) spray applying the coating composition to an interior surface of a food or beverage can or a portion thereof.

According to yet another aspect of the present invention, there is provided an article comprising: a body portion or an end portion of a food or beverage can comprising a
20 metal substrate; and a coating composition disposed on an inside surface thereon, wherein the coating composition includes an emulsion polymerized latex polymer, and wherein the emulsion polymerized latex polymer comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a polyurethane resin.

25 According to yet another aspect of the present invention, there is provided a method of coating a food or beverage can, the method comprising: forming a composition comprising an emulsion polymerized latex polymer and being substantially free of bound bisphenol A and aromatic glycidyl ether compounds, comprising: forming a salt of an acid- or anhydride-functional polymer and an amine in a carrier comprising water to form an

79713-5

aqueous dispersion; combining an ethylenically unsaturated monomer component with the aqueous dispersion; and polymerizing the ethylenically unsaturated monomer component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer, wherein the ethylenically saturated monomer component comprises a mixture of monomers comprising at least one oxirane functional group-containing monomer, wherein at least 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates; and applying the composition comprising the emulsion polymerized latex polymer to a metal substrate prior to or after forming the metal substrate into a food or beverage can or portion thereof.

10 According to yet another aspect of the present invention, there is provided a food or beverage can comprising: a body portion or an end portion comprising a metal substrate; and a coating composition disposed thereon, wherein the coating composition comprises an emulsion polymerized latex polymer and is substantially free of bound bisphenol A and aromatic glycidyl ether compounds, wherein the emulsion polymerized latex polymer is prepared from a salt of an acid- or anhydride-functional polymer and an amine, an ethylenically unsaturated, monomer component, and water, wherein the ethylenically saturated monomer component comprises a mixture of monomers comprising at least one oxirane functional group-containing monomer, wherein at least 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates.

20 According to yet another aspect of the present invention, there is provided a composition for use in coating a food or beverage can, the composition comprising an emulsion polymerized latex polymer, wherein the emulsion polymerized latex polymer is prepared from a salt or an acid- or anhydride-functional polymer and a tertiary amine, an ethylenically unsaturated monomer component including a mixture of monomers including at least one oxirane functional group-containing alpha, beta-ethylenically unsaturated monomer in an amount of at least 0.1 wt-% and no greater than 30 wt-%, based on the weight of the monomer mixture, and water, wherein at least 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates.

79713-5

According to yet another aspect of the present invention, there is provided a method of coating an inside surface of a food or beverage can, the method comprising: forming a composition comprising an emulsion polymerized latex polymer and being substantially free of bound bisphenol A and aromatic glycidyl ether compounds, comprising:

5 forming a salt of an acid- or anhydride-functional polymer and an amine in a carrier comprising water to form an aqueous dispersion; combining an ethylenically unsaturated monomer component with the aqueous dispersion; and polymerizing the ethylenically unsaturated monomer component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer, wherein the ethylenically saturated monomer

10 component comprises a mixture of monomers comprising at least one oxirane functional group-containing monomer, wherein at least 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates; and applying the composition comprising the emulsion polymerized latex polymer to a metal substrate on an inside surface side prior to or after forming the metal substrate into a food or beverage can or

15 portion thereof.

According to yet another aspect of the present invention, there is provided a food or beverage can comprising: a body portion or an end portion comprising a metal substrate; and a coating composition disposed on an inside surface side, wherein the coating composition comprises an emulsion polymerized latex polymer and is substantially free of

20 bound bisphenol A and aromatic glycidyl ether compounds, wherein the emulsion polymerized latex polymer is prepared from a salt of an acid- or anhydride-functional polymer and an amine, an ethylenically unsaturated, monomer component, and water, wherein the ethylenically saturated monomer component comprises a mixture of monomers comprising at least one oxirane functional group-containing monomer, wherein at least

25 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates.

According to yet another aspect of the present invention, there is provided a composition for use in coating an inside surface side of a food or beverage can, the composition comprising an emulsion polymerized latex polymer, wherein the emulsion

30 polymerized latex polymer is prepared from a salt or an acid- or anhydride-functional

79713-5

polymer and a tertiary amine, an ethylenically unsaturated monomer component including a mixture of monomers including at least one oxirane functional group-containing alpha, beta-ethylenically unsaturated monomer in an amount of at least 0.1 wt-% and no greater than 30 wt-%, based on the weight of the monomer mixture, and water, wherein at least 40 wt-%
5 of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates.

DEFINITIONS

The term "substantially free" of a particular mobile compound means that the compositions of the present invention contain less than 1000 parts per million (ppm) of the
10 recited mobile compound. The term "essentially free" of a particular mobile compound means that the compositions of the present invention contain less than 100 parts per million (ppm) of the recited mobile compound. The term "essentially completely free" of a particular mobile compound means that the compositions of the present invention contain less than 5 parts per million (ppm) of the recited mobile compound. The term "completely
15 free" of a particular mobile compound means that the compositions of the present invention contain less than 20 parts per billion (ppb) of the recited mobile compound.

The term "mobile" means that the compound can be extracted from the cured coating when a coating (typically, approximate film weight of 1 mg/cm²) is exposed to a test medium for some defined set of conditions, depending on the end use. An example of these
20 testing conditions is exposure of the cured coating to 10 weight

percent ethanol solution for two hours at 121°C followed by exposure for 10 days in the solution at 49°C.

If the aforementioned phrases are used without the term "mobile" (e.g., "substantially free of XYZ compound") then the compositions of the present invention contain less than the aforementioned amount of the compound whether the compound is mobile in the coating or bound to a constituent of the coating.

As used herein, the term "organic group" means a hydrocarbon group (with optional elements other than carbon and hydrogen, such as oxygen, nitrogen, sulfur, and silicon) that is classified as an aliphatic group, cyclic group, or combination of aliphatic and cyclic groups (e.g., alkaryl and aralkyl groups). The term "aliphatic group" means a saturated or unsaturated linear or branched hydrocarbon group. This term is used to encompass alkyl, alkenyl, and alkynyl groups, for example. The term "alkyl group" means a saturated linear or branched hydrocarbon group including, for example, methyl, ethyl, isopropyl, t-butyl, heptyl, dodecyl, octadecyl, amyl, 2-ethylhexyl, and the like. The term "alkenyl group" means an unsaturated, linear or branched hydrocarbon group with one or more carbon-carbon double bonds, such as a vinyl group. The term "alkynyl group" means an unsaturated, linear or branched hydrocarbon group with one or more carbon-carbon triple bonds. The term "cyclic group" means a closed ring hydrocarbon group that is classified as an alicyclic group or an aromatic group, both of which can include heteroatoms. The term "alicyclic group" means a cyclic hydrocarbon group having properties resembling those of aliphatic groups.

The term "Ar" refers to a divalent aryl group (i.e., an arylene group), which refers to a closed aromatic ring or ring system such as phenylene, naphthylene, biphenylene, fluorenylene, and indenyl, as well as heteroarylene groups (i.e., a closed ring hydrocarbon in which one or more of the atoms in the ring is an element other than carbon (e.g., nitrogen, oxygen, sulfur, etc.)). Suitable heteroaryl groups include furyl, thienyl, pyridyl, quinolinyl, isoquinolinyl, indolyl, isoindolyl, triazolyl, pyrrolyl, tetrazolyl, imidazolyl, pyrazolyl, oxazolyl, thiazolyl, benzofuranyl, benzothiophenyl, carbazolyl, benzoxazolyl, pyrimidinyl, benzimidazolyl, quinoxalinyl, benzothiazolyl, naphthyridinyl, isoxazolyl, isothiazolyl, purinyl, quinazolinyl, pyrazinyl, 1-oxidopyridyl, pyridazinyl, triazinyl,

tetrazinyl, oxadiazolyl, thiadiazolyl, and so on. When such groups are divalent, they are typically referred to as "heteroarylene" groups (e.g., furylene, pyridylene, etc.)

A group that may be the same or different is referred to as being "independently" something.

5 Substitution is anticipated on the organic groups of the compounds of the present invention. As a means of simplifying the discussion and recitation of certain terminology used throughout this application, the terms "group" and "moiety" are used to differentiate between chemical species that allow for substitution or that may be substituted and those that do not allow or may not be so substituted. Thus, when
10 the term "group" is used to describe a chemical substituent, the described chemical material includes the unsubstituted group and that group with O, N, Si, or S atoms, for example, in the chain (as in an alkoxy group) as well as carbonyl groups or other conventional substitution. Where the term "moiety" is used to describe a chemical compound or substituent, only an unsubstituted chemical material is intended to be
15 included. For example, the phrase "alkyl group" is intended to include not only pure open chain saturated hydrocarbon alkyl substituents, such as methyl, ethyl, propyl, t-butyl, and the like, but also alkyl substituents bearing further substituents known in the art, such as hydroxy, alkoxy, alkylsulfonyl, halogen atoms, cyano, nitro, amino, carboxyl, etc. Thus, "alkyl group" includes ether groups, haloalkyls, nitroalkyls,
20 carboxyalkyls, hydroxyalkyls, sulfoalkyls, etc. On the other hand, the phrase "alkyl moiety" is limited to the inclusion of only pure open chain saturated hydrocarbon alkyl substituents, such as methyl, ethyl, propyl, t-butyl, and the like.

The terms "comprises" and variations thereof do not have a limiting meaning where these terms appear in the description and claims.

25 The terms "preferred" and "preferably" refer to embodiments of the invention that may afford certain benefits, under certain circumstances. However, other embodiments may also be preferred, under the same or other circumstances. Furthermore, the recitation of one or more preferred embodiments does not imply that other embodiments are not useful, and is not intended to exclude other
30 embodiments from the scope of the invention.

As used herein, "a," "an," "the," "at least one," and "one or more" are used interchangeably. Thus, for example, a coating composition that comprises "a"

polymer can be interpreted to mean that the coating composition includes "one or more" polymers.

Also herein, the recitations of numerical ranges by endpoints include all numbers subsumed within that range (e.g., 1 to 5 includes 1, 1.5, 2, 2.75, 3, 3.80, 4, 5, etc.).

The above summary of the present invention is not intended to describe each disclosed embodiment or every implementation of the present invention. The description that follows more particularly exemplifies illustrative embodiments. In several places throughout the application, guidance is provided through lists of examples, which examples can be used in various combinations. In each instance, the recited list serves only as a representative group and should not be interpreted as an exclusive list.

DETAILED DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

This invention provides a coating composition for use on food and beverage cans that includes a latex polymer. The polymer is prepared in an emulsion polymerization process, preferably a free radical initiated polymerization process.

5 The latex polymer can be applied to a metal substrate either before or after the substrate is formed into a food or beverage can (e.g., two-piece cans, three-piece cans) or portions thereof, whether it be a can end or can body. The latex polymers of the present invention are suitable for use in food contact situations and may be used on the inside of such cans. They are particularly useful on the interior of two-
10 piece drawn and ironed beverage cans and on beverage can ends.

The latex polymer is prepared by polymerizing an ethylenically unsaturated monomer component in an aqueous medium in the presence of the salt of an acid group- or anhydride group-containing polymer and an amine, preferably, a tertiary amine. The ethylenically unsaturated monomer component is preferably a mixture of
15 monomers. Preferably, at least one of the monomers in the mixture is an alpha, beta-ethylenically unsaturated monomer, and preferably at least one of the monomers contains an oxirane groups. More preferably, at least one of the monomers is an oxirane group-containing alpha, beta-ethylenically unsaturated monomer.

20 The composition may optionally include crosslinkers, fillers, catalysts, dyes, pigments, toners, extenders, lubricants, anticorrosion agents, flow control agents, thixotropic agents, dispersing agents, antioxidants, adhesion promoters, light stabilizers, surfactants, organic solvents, and mixtures thereof as required to provide the desired film properties.

25 In one embodiment, the coating composition is prepared by: forming a salt of an acid-functional or anhydride-functional polymer and an amine; dispersing the salt in a carrier that includes water and an optional organic solvent to form an aqueous dispersion; optionally removing the organic solvent, if present, from the aqueous dispersion; combining an ethylenically unsaturated monomer component
30 with the aqueous dispersion (preferably, the ethylenically unsaturated monomer component is added to the aqueous dispersion); and polymerizing the ethylenically

unsaturated monomer component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer.

Preferred compositions are substantially free of mobile bisphenol A (BPA) and aromatic glycidyl ether compounds (e.g., BADGE, BFDGE, and epoxy novalacs), more preferably essentially free of these compounds, even more preferably essentially completely free of these compounds, and most preferably completely free of these compounds. The coating composition is also preferably substantially free of bound BPA and aromatic glycidyl ether compounds, more preferably essentially free of these compounds, most preferably essentially completely free of these compounds, and optimally completely free of these compounds.

The ethylenically unsaturated monomer component is preferably a mixture of monomers that is capable of free radical initiated polymerization in aqueous medium. The monomer mixture preferably contains at least one oxirane functional monomer, and more preferably, at least one oxirane group-containing alpha, beta-ethylenically unsaturated monomer.

The monomer mixture preferably contains at least 0.1 percent by weight (wt-%), more preferably at least 1 wt-%, of an oxirane group-containing monomer, based on the weight of the monomer mixture. Typically, at least 0.1 wt-% of the oxirane group-containing monomer contributes to the stability of the latex. Although not intended to be limited by theory, it is believed that this is because of the reduction in the amount of quaternary salt formation between the oxirane species, acid group-containing polymer, and amine, which can cause coagulation of the latex. In addition, at least 0.1 wt-% of the oxirane group-containing monomer contributes to crosslinking in the dispersed particles and during cure, resulting in better properties of coating compositions formulated with the polymeric latices.

The monomer mixture preferably contains no greater than 30 wt-%, more preferably no greater than 20 wt-%, even more preferably no greater than 10 wt-%, and optimally no greater than 9 wt-%, of the oxirane group-containing monomer, based on the weight of the monomer mixture. Typically, greater than 30 wt-% of the oxirane group-containing monomer in the monomer mixture can contribute to diminished film properties. Although not intended to be limited by theory, it is

believed that this is due to embrittlement caused by an overabundance of crosslinking.

Suitable oxirane-functional monomers include monomers having a reactive carbon-carbon double bond and an oxirane (i.e., a glycidyl) group. Typically, the monomer is a glycidyl ester of an alpha, beta-unsaturated acid, or anhydride thereof (i.e., an oxirane group-containing alpha, beta-ethylenically unsaturated monomer). Suitable alpha, beta-unsaturated acids include monocarboxylic acids or dicarboxylic acids. Examples of such carboxylic acids include, but are not limited to, acrylic acid, methacrylic acid, alpha-chloroacrylic acid, alpha-cyanoacrylic acid, beta-methylacrylic acid (crotonic acid), alpha-phenylacrylic acid, beta-acryloxypropionic acid, sorbic acid, alpha-chlorosorbic acid, angelic acid, cinnamic acid, p-chlorocinnamic acid, beta-stearylacrylic acid, itaconic acid, citraconic acid, mesaconic acid, glutaconic acid, aconitic acid, maleic acid, fumaric acid, tricarboxyethylene, maleic anhydride, and mixtures thereof.

Specific examples of suitable monomers containing a glycidyl group are glycidyl (meth)acrylate (i.e., glycidyl methacrylate and glycidyl acrylate), mono- and di-glycidyl itaconate, mono- and di-glycidyl maleate, and mono- and di-glycidyl formate. It also is envisioned that allyl glycidyl ether and vinyl glycidyl ether can be used as the oxirane-functional monomer. A preferred monomer is glycidyl methacrylate ("GMA").

The oxirane-functional monomer is preferably reacted with suitable other monomers within the monomer mixture. These can be ethylenically unsaturated monomer and hydroxy-functional monomers. Suitable ethylenically unsaturated monomers include alkyl (meth)acrylates, vinyl monomers, alkyl esters of maleic or fumaric acid, and the like.

Suitable alkyl (meth)acrylates include those having the structure: $\text{CH}_2=\text{C}(\text{R}^1)-\text{CO}-\text{OR}^2$ wherein R^1 is hydrogen or methyl, and R^2 is an alkyl group preferably containing one to sixteen carbon atoms. The R^2 group can be substituted with one or more, and typically one to three, moieties such as hydroxy, halo, phenyl, and alkoxy, for example. Suitable alkyl (meth)acrylates therefore encompass hydroxy alkyl (meth)acrylates. The alkyl (meth)acrylate typically is an ester of acrylic or methacrylic acid. Preferably, R^1 is hydrogen or methyl and R^2 is an alkyl

group having two to eight carbon atoms. Most preferably, R¹ is hydrogen or methyl and R² is an alkyl group having two to four carbon atoms.

Examples of suitable alkyl (meth)acrylates include, but are not limited to, methyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate, isopropyl (meth)acrylate, butyl (meth)acrylate, isobutyl (meth)acrylate, pentyl (meth)acrylate, isoamyl (meth)acrylate, hexyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, cyclohexyl (meth)acrylate, decyl (meth)acrylate, isodecyl (meth)acrylate, benzyl (meth)acrylate, lauryl (meth)acrylate, isobornyl (meth)acrylate, octyl (meth)acrylate, nonyl (meth)acrylate, hydroxyethyl acrylate (HEA), hydroxyethyl methacrylate (HEMA), hydroxypropyl (meth)acrylate (HPMA).

Difunctional (meth)acrylate monomers may be used in the monomer mixture as well. Examples include ethylene glycol di(meth)acrylate, 1,6-hexanediol di(meth)acrylate, allyl methacrylate, and the like.

Suitable vinyl monomers include styrene, methyl styrene, halostyrene, isoprene, diallylphthalate, divinylbenzene, conjugated butadiene, alpha-methylstyrene, vinyl toluene, vinyl naphthalene, and mixtures thereof. The vinyl aromatic monomers described below in connection with the acid- or anhydride-functional polymer are also suitable for use in the ethylenically unsaturated monomer component used to make the latex polymer. Styrene is a presently preferred vinyl monomer, in part due to its relatively low cost.

Other suitable polymerizable vinyl monomers for use in the ethylenically unsaturated monomer component include acrylonitrile, acrylamide, methacrylamide, methacrylonitrile, vinyl acetate, vinyl propionate, vinyl butyrate, vinyl stearate, N-isobutoxymethyl acrylamide, N-butoxymethyl acrylamide, and the like.

The oxirane group-containing monomer preferably constitutes 0.1 wt-% to 30 wt-%, and more preferably 1 wt-% to 20 wt-%, of the ethylenically unsaturated monomer component. The other monomer or monomers in the mixture constitute the remainder of the monomer component, that is, 70 wt-% to 99.9 wt-%, preferably 80 wt-% to 99 wt-%, based on total weight of the monomer mixture.

Preferably, at least 40 wt-% of the ethylenically unsaturated monomer component, more preferably at least 50 wt-%, will be selected from alkyl acrylates

and methacrylates. Preferably, at least 20 wt-%, more preferably at least 30 wt-%, will be selected from vinyl aromatic compounds.

Preferably, at least 5 wt-%, more preferably at least 25 wt-%, even more preferably at least 50 wt-%, and even more preferably at least 60 wt-%, of the ethylenically unsaturated monomer component is used in making the latex polymer. Preferably, no greater than 95 wt-%, more preferably no greater than 90 wt-%, and even more preferably no greater than 85 wt-%, of the ethylenically unsaturated monomer component is used in making the latex polymer. Such percentages are based on total weight of ethylenically unsaturated monomer component and salt of the acid group-containing or anhydride group-containing polymer (i.e., acid-functional or anhydride-functional polymer).

Among the acid functional polymers that can be employed in preparing the latex polymer of the present invention are virtually any acid-containing or anhydride-containing polymers that can be neutralized or partially neutralized with an appropriate amine to form a salt that can be dissolved or stably dispersed in the aqueous medium. The choice of the acid-containing or anhydride-containing monomer(s) is dictated by the intended end use of the coating composition and is practically unlimited.

The acid-containing polymer (i.e., acid-functional polymer) preferably has an acid number of at least 40, and more preferably at least 100, milligrams (mg) KOH per gram resin. The acid-containing polymer preferably has an acid number of no greater than 400, and more preferably no greater than 300, mg KOH per gram resin. The anhydride-containing polymer, when in water, preferably has similar acid number ranges.

Low molecular weight polymers are preferred for certain applications of the present invention. Preferably, the molecular weight of the acid- or anhydride-functional polymer is no greater than 50,000 on a number average molecular weight basis, and preferably no greater than 20,000. Preferably, the molecular weight of the acid- or anhydride-functional polymer is at least 1500 on a number average molecular weight basis, and more preferably at least 2000.

Preferred acid- or anhydride-functional polymers that may be employed include acid-functional or anhydride-functional acrylic polymers, alkyd resins,

polyester polymers, and polyurethanes. Combinations of such polymers can be used if desired. Herein, the term polymer includes both homopolymers and copolymers (i.e., polymers of two or more different monomers).

Preferred acid- or anhydride-functional polymers utilized in this invention include those prepared by conventional free radical polymerization techniques. Suitable examples include those prepared from unsaturated acid- or anhydride-functional monomers, or salts thereof, and other unsaturated monomers. Of these, preferred examples include those prepared from at least 15 wt-%, more preferably at least 20 wt-%, unsaturated acid- or anhydride-functional monomer, or salts thereof, and the balance other polymerizable unsaturated monomer. Examples of co-monomers described previously apply here as well.

A variety of acid- or anhydride-functional monomers, or salts thereof, can be used; their selection is dependent on the desired final polymer properties. Preferably, such monomers are ethylenically unsaturated, more preferably, alpha, beta-ethylenically unsaturated. Suitable ethylenically unsaturated acid- or anhydride-functional monomers for the present invention include monomers having a reactive carbon-carbon double bond and an acidic or anhydride group, or salts thereof. Preferred such monomers have from 3 to 20 carbons, at least 1 site of unsaturation, and at least 1 acid or anhydride group, or salt thereof.

Suitable acid-functional monomers include ethylenically unsaturated acids (mono-protic or diprotic), anhydrides or monoesters of a dibasic acid, which are copolymerizable with the optional other monomer(s) used to prepare the polymer. Illustrative monobasic acids are those represented by the structure $\text{CH}_2=\text{C}(\text{R}^3)\text{COOH}$, where R^3 is hydrogen or an alkyl radical of 1 to 6 carbon atoms. Suitable dibasic acids are those represented by the formulas $\text{R}^4(\text{COOH})\text{C}=\text{C}(\text{COOH})\text{R}^5$ and $\text{R}^4(\text{R}^5)\text{C}=\text{C}(\text{COOH})\text{R}^6\text{COOH}$, where R^4 and R^5 are hydrogen, an alkyl radical of 1-8 carbon atoms, halogen, cycloalkyl of 3 to 7 carbon atoms or phenyl, and R^6 is an alkylene radical of 1 to 6 carbon atoms. Half-esters of these acids with alkanols of 1 to 8 carbon atoms are also suitable.

Non-limiting examples of useful ethylenically unsaturated acid-functional monomers include acids such as, for example, acrylic acid, methacrylic acid, alpha-chloroacrylic acid, alpha-cyanoacrylic acid, crotonic acid, alpha-phenylacrylic acid,

79713-5

beta-acryloxypropionic acid, fumaric acid, maleic acid, sorbic acid, alpha-chlorosorbic acid, angelic acid, cinnamic acid, p-chlorocinnamic acid, beta-stearylacrylic acid, citraconic acid, mesaconic acid, glutaconic acid, aconitic acid, tricarboxyethylene, 2-methyl maleic acid, itaconic acid, 2-methyl itaconic acid, methyleneglutaric acid, and the like, or mixtures thereof. Preferred unsaturated acid-functional monomers include acrylic acid, methacrylic acid, crotonic acid, fumaric acid, maleic acid, 2-methyl maleic acid, itaconic acid, 2-methyl itaconic acid and mixtures thereof. More preferred unsaturated acid-functional monomers include acrylic acid, methacrylic acid, crotonic acid, fumaric acid, maleic acid, itaconic acid, and mixtures thereof. Most preferred unsaturated acid-functional monomers include acrylic acid, methacrylic acid, maleic acid, crotonic acid, and mixtures thereof.


Nonlimiting examples of suitable ethylenically unsaturated anhydride monomers include compounds derived from the above acids (e.g., as pure anhydride or mixtures of such). Preferred anhydrides include acrylic anhydride, methacrylic anhydride, and maleic anhydride. If desired, aqueous salts of the above acids may also be employed.

Polymerization of the monomers to form an acid- or anhydride-functional polymer is usually conducted by organic solution polymerization techniques in the presence of a free radical initiator as is well known in the art. Although the preparation of the acid-functional or anhydride-functional polymer is conveniently carried out in solution, neat processes may be used if desired.

Besides the acid- or anhydride-functional acrylic polymers, acid- or anhydride-functional alkyd, polyester, polyurethane resins, or combinations thereof, can also be used in the practice of the invention. Such polymers are described in U.S. Pat. Nos. 4,692,491; 3,479,310; and 4,147,679. Preferably, the acid- or anhydride-functional polymers are acid-functional acrylic polymers.

In another preferred embodiment, the acid- or anhydride-functional polymers are polyester polymers. Examples of such polyester polymers are disclosed in U.S. Pat. No. 7,910,170 B2 entitled COATING COMPOSITIONS

FOR CONTAINERS AND METHODS OF COATING. Briefly, the polymers described therein have one or more segments of Formula I:




wherein each Ar is independently a divalent aryl group (i.e., an arylene group) or heteroarylene group; R^1 is a divalent organic group; each R is independently a divalent organic group; and n is 0 or 1. Any one polymer can have a variety of such segments, which may be the same or different.

Preferably, R^1 provides hydrolytic stability to at least one of the adjacent ester linkages ($-C(O)-O-$ and $-O-C(O)-$), and preferably to both of them. In this context, "hydrolytic stability" means that R^1 decreases the reactivity (preferably, by at least half) of the adjacent ester linkage with water compared to a $-CH_2-CH_2-$ moiety under the same conditions. This can be accomplished by selection of R^1 that includes a sterically bulky group in proximity (preferably within two atoms distance) to the oxygen of the ester. The polymer preferably includes more than 70%, more preferably more than 80%, and even more preferably more than 90%, hydrolytically stable ester linkages (based on the total number of ester linkages).

In the segments of Formula I, R^1 is a divalent organic group, preferably, having at least 3 carbon atoms, more preferably, at least 4 carbon atoms, even more preferably, at least 5 carbon atoms, and even more preferably, at least 8 carbon atoms. It is envisioned that R^1 can be as large as desired for the particular application, which one of skill in the art can readily determine.

In certain preferred embodiments of Formula I, R^1 is of the formula



wherein each R^2 is independently hydrogen or an organic group (e.g., an alicyclic group or a branched or unbranched alkyl group), Y is a divalent organic group, and t is 0 or 1 (preferably 1). In certain embodiments, each R^2 is independently hydrogen.

In certain embodiments, Y can optionally include one or more ether or ester linkages. In certain embodiments, Y is a divalent saturated aliphatic group (i.e., a branched or unbranched alkylene group), a divalent alicyclic group, or a divalent aromatic group (i.e., an arylene group), or combinations thereof.

In certain embodiments, Y is a divalent alkyl group (i.e., an alkylene group), which can be branched or unbranched, preferably having at least 1 carbon atom,

more preferably having at least 2 carbon atoms, even more preferably having at least 3 carbon atoms, and even more preferably having at least 6 carbon atoms. In certain embodiments, Y is a divalent alicyclic group, preferably cyclohexylene. It is envisioned that Y can be as large as desired for the particular application, which one
 5 of skill in the art can readily determine.

Preferably, Y provides hydrolytic stability to at least one of the ester linkages adjacent R^1 in Formula I. This can be accomplished by selection of Y that includes a sterically bulky group that is in proximity (preferably within two atoms) of at least one of the ester oxygen atoms in Formula I.

10 In certain embodiments, R^1 has the formula $-(C(R^2)_2)_s-$ wherein s is at least 2, and preferably, s is at least 3, wherein each R^2 is as defined above. Examples of such R^1 groups include, for example, neopentylene, butylethylpropylene, and $-\text{CH}_2-\text{CH}(\text{CH}_3)-\text{CH}_2-$.

In certain embodiments, Y has the formula

15
$$-[Z_w-\text{C}(\text{R}^2)_2-\text{O}-\text{C}(\text{O})-\text{R}^3-\text{C}(\text{O})-\text{O}-\text{C}(\text{R}^2)_2-]_v Z_w-$$

wherein w is 0 or 1, v is 1 to 10, each R^2 is as defined above, each R^3 is independently a divalent organic group, and each Z is independently a divalent organic group.

20 In certain embodiments, R^3 is a divalent saturated aliphatic group (i.e., branched or unbranched alkylene group), a divalent alicyclic group, an arylene group, or combinations thereof. In certain embodiments, R^3 is a (C3-C20)alkylene (branched or unbranched) group or a phenylene group.

25 In certain embodiments, Z is a divalent saturated aliphatic group (i.e., branched or unbranched alkylene group), a divalent alicyclic group, a divalent aromatic group (i.e., an arylene group), or combinations thereof.


Preferably, Z provides hydrolytic stability to at least one of the ester linkages adjacent R^1 in Formula I and/or to an adjacent ester linkage contained within Y. This can be accomplished by selection of Z that includes a sterically bulky group that is in proximity (preferably within two atoms distance) of at least one of the ester
 30 oxygen atoms.

In the segments of Formula I, n is preferably 0 (i.e., R is not present). If n is 1 and R is present, however, it is preferably a (C1-C4)alkylene group, and more preferably a (C1-C4)alkylene moiety.

5 In the segments of Formula I, preferably each Ar has less than 20 carbon atoms, more preferably less than 11 carbon atoms, and even more preferably less than 8 carbon atoms. Preferably, Ar has at least 4 carbon atoms, more preferably at least 5 carbon atoms, and even more preferably, at least 6 carbon atoms.

In certain embodiments, each Ar is a phenylene group. In certain embodiments, each Ar is a phenylene group of the formula $-C_6(R^4)_4-$, wherein each 10 R^4 is independently hydrogen, a halogen, or an organic group, and wherein two R^4 groups can join to form a ring optionally containing one or more heteroatoms. In certain embodiments, R^4 is hydrogen or an organic group, wherein two R^4 groups can join to form a 6-membered ring. Preferably, R^4 is hydrogen.

15 Polyester polymers such as these can be made by a variety of methods from compounds of Formula II:



wherein Ar, R, R^1 , and n are as defined above. Such compounds can be made, for example, by the esterification reaction of one mole of a diol (e.g., $HO-R^1-OH$ such as, for example, 1,4-cyclohexane dimethanol, neopentyl glycol, 2-butyl-2-ethyl-1,3- 20 propane diol, or 2-methyl-1,3-propane diol) with two moles of an acid (e.g., 4-hydroxy benzoic acid). Alternatively, such compounds can be made, for example, by the transesterification reaction of one mole of a diol (e.g., 1,4-cyclohexane dimethanol, neopentyl glycol, 2-butyl-2-ethyl-1,3-propane diol, or 2-methyl-1,3-propane diol) with two moles of an ester (e.g., 4-hydroxy methyl benzoate, 4- 25 hydroxy ethyl benzoate, or 4-hydroxy butyl benzoate).

Polymers of Formula I can be prepared by methods that involve advancing the molecular weight of compounds of Formula II. In certain embodiments, compounds of Formula II (e.g., dihydric phenols) can be reacted with a diepoxide to advance the molecular weight. For example, compounds of Formula II (e.g., dihydric 30 phenols) can be reacted with non-BPA and non-BPF based diepoxides much in the same manner that Bisphenol A or Bisphenol F do, to create polymers that can be formulated with crosslinkers and additives for coatings for rigid packaging. For

79713-5

example, compounds of Formula II can be reacted with a diepoxide to form a polymer that includes $-\text{CH}_2-\text{CH}(\text{OH})-\text{CH}_2-$ segments. Alternatively, compounds of Formula II can be reacted with epichlorohydrin to form a diepoxide analog of compounds of Formula II, which can then be reacted with other compounds of Formula II to form a polymer that includes $-\text{CH}_2-\text{CH}(\text{OH})-\text{CH}_2-$ segments.

The diepoxide analogs of compounds of Formula II (e.g., glycidyl polyethers of the dihydric phenols) can be prepared by reacting the required proportions of a compound of Formula II (e.g., dihydric phenol) and epichlorohydrin in an alkaline medium. The desired alkalinity is obtained by adding basic substances, such as sodium or potassium hydroxide, preferably in stoichiometric excess to the epichlorohydrin. The reaction is preferably accomplished at temperatures of 50°C to 150°C . The heating is continued for several hours to effect the reaction and the product is then washed free of salt and base. Procedures for such reactions are generally well known and disclosed, for example, in U.S. Pat. No. 2,633,458.

As used in the present invention, suitable diepoxides (other than the diepoxide analogs of compounds of Formula II) are BPA- or BPF-free diepoxides, preferably with one or more ether linkages. Suitable diepoxides may be prepared by a variety of processes, for example, by the condensation of a dihydroxy compound and epichlorohydrin. Examples of suitable diepoxides (other than the diepoxide analogs of compounds of Formula II) include, for example, 1,4-cyclohexanedimethanol diglycidyl ether (CHDMDGE), resorcinol diglycidyl ether, neopentyl glycol diglycidyl ether, and 2-methyl-1,3-propandiol diglycidyl ether.

The resultant polymers of Formula I may be epoxy terminated or phenoxy terminated, for example. They may be made in a variety of molecular weights, such as the molecular weights of commercially available BPA-based epoxy materials (e.g., those available under trade designations such as EPONTM 828, 1001, 1007, 1009 from Resolution Performance Products, Houston, Texas). Preferred polymers of the present invention have a number average molecular weight (M_n) of at least 2,000, more preferably at least 3,000, and even more preferably at least 4,000. The molecular weight of the polymer may be as high as is needed for the desired application.

Advancement of the molecular weight of the polymer may be enhanced by the use of a catalyst in the reaction of a diepoxide (whether it be a diepoxide analog of Formula II or another diepoxide) with a compound of Formula (II). Typical catalysts usable in the advancement of the molecular weight of the epoxy material of the present invention include amines, hydroxides (e.g., potassium hydroxide),
5 phosphonium salts, and the like. A presently preferred catalyst is a phosphonium catalyst. The phosphonium catalyst useful in the present invention is preferably present in an amount sufficient to facilitate the desired condensation reaction.

Alternatively, the epoxy terminated polymers of Formula I may be reacted
10 with fatty acids to form polymers having unsaturated (e.g., air oxidizable) reactive groups, or with acrylic acid or methacrylic acid to form free radically curable polymers.

Advancement of the molecular weight of the polymer may also be enhanced by the reaction of an epoxy terminated polymer of Formula I with a suitable diacid
15 (such as adipic acid).

A salt (which can be a full salt or partial salt) of the acid- or anhydride-functional polymer is formed by neutralizing or partially neutralizing the acid groups (whether present initially in the acid-functional polymer or formed upon addition of the anhydride-functional polymer to water) of the polymer with a suitable amine,
20 preferably a tertiary amine. The degree of neutralization required to form the desired polymer salt may vary considerably depending upon the amount of acid included in the polymer, and the degree of solubility or dispersibility of the salt which is desired. Ordinarily in making the polymer water-dispersible, the acidity of the polymer is at least 25% neutralized, preferably at least 30% neutralized, and more preferably at
25 least 35% neutralized, with the amine in water.

Some examples of suitable tertiary amines are trimethyl amine, dimethylethanol amine (also known as dimethylamino ethanol), methyldiethanol amine, triethanol amine, ethyl methyl ethanol amine, dimethyl ethyl amine, dimethyl propyl amine, dimethyl 3-hydroxy-1-propyl amine, dimethylbenzyl amine, dimethyl
30 2-hydroxy-1-propyl amine, diethyl methyl amine, dimethyl 1-hydroxy-2-propyl amine, triethyl amine, tributyl amine, N-methyl morpholine, and mixtures thereof.

Most preferably triethyl amine or dimethyl ethanol amine is used as the tertiary amine.

The amount of the salt of the acid-functional or anhydride-functional polymer that is used in the polymerization is preferably at least 5 wt-%, more preferably at least 10 wt-%, and even more preferably at least 15 wt-%. The amount of the salt of the acid-functional or anhydride-functional polymer that is used in the polymerization is preferably no greater than 95 wt-%, preferably no greater than 50 wt-%, and even more preferably no greater than 40 wt-%. These percentages are based on total weight of polymerizable ethylenically unsaturated monomer component and the salt of the acid group-containing polymer.

The reaction of tertiary amines with materials containing oxirane groups, when carried out in the presence of water, can afford a product that contains both a hydroxyl group and a quaternary ammonium hydroxide. Under preferred conditions an acid group, an oxirane group, and an amine form a quaternary salt. This linkage is favored, as it not only links the polymers but promotes water dispersibility of the joined polymer. It should be noted that an acid group and an oxirane group may also form an ester. Some of this reaction is possible, though this linkage is less desirable when water dispersibility is sought.

While the exact mode of reaction is not fully understood, it is believed that a competition between the two reactions exist; however, this is not intended to be limiting. In preferred embodiments, one reaction involves the tertiary amine neutralized acid-functional polymer reacting with an oxirane-functional monomer or polymer to form a quaternary ammonium salt. A second reaction involves esterification of the oxirane-functional monomer or polymer with a carboxylic acid or salt. In the current invention it is believed the presence of water and level of amine favor formation of quaternary ammonium salts over ester linkages. A high level of quaternization improves water dispersability while a high level of esterification gives higher viscosity and possibly gel-like material.

With regard to the conditions of the emulsion polymerization, the ethylenically unsaturated monomer component is preferably polymerized in aqueous medium with a water-soluble free radical initiator in the presence of the salt of the acid- or anhydride-functional polymer.

The temperature of polymerization is typically from 0°C to 100°C, preferably from 50°C to 90°C, more preferably from 70°C to 90°C, and even more preferably from 80°C to 85°C. The pH of the aqueous medium is usually maintained at a pH of 5 to 12.

5 The free radical initiator can be selected from one or more water-soluble peroxides which are known to act as free radical initiators. Examples include hydrogen peroxide and t-butyl hydroperoxide. Redox initiator systems well known in the art (e.g., t-butyl hydroperoxide, erythorbic acid, and ferrous complexes) can also be employed. It is especially preferred to use a mixture of benzoin and
10 hydrogen peroxide. Persulfate initiators such as ammonium persulfate or potassium persulfate are not preferred, as they lead to poor water resistance properties of the cured coating.

 The polymerization reaction of the ethylenically unsaturated monomer component in the presence of the aqueous dispersion of the polymer salt may be
15 conducted as a batch, intermittent, or continuous operation. While all of the polymerization ingredients may be charged initially to the polymerization vessel, better results normally are obtained with proportioning techniques.

 Typically, the reactor is charged with an appropriate amount of water, polymer salt, and free radical initiator. The reactor is then heated to the free radical
20 initiation temperature and then charged with the ethylenically unsaturated monomer component. Preferably only water, initiator, polymer salt, and some portion of the ethylenically unsaturated monomer component are initially charged to the vessel. There may also be some water miscible solvent present. After this initial charge is allowed to react for a period of time at polymerization temperature, the remaining
25 ethylenically unsaturated monomer component is added incrementally with the rate of addition being varied depending on the polymerization temperature, the particular initiator being employed, and the type and amount of monomers being polymerized. After all the monomer component has been charged, a final heating is carried out to complete the polymerization. The reactor is then cooled and the latex recovered.

30 It has been discovered that coating compositions using the aforementioned latices may be formulated using one or more optional curing agents (i.e., crosslinking resins, sometimes referred to as "crosslinkers"). The choice of

79713-5

particular crosslinker typically depends on the particular product being formulated. For example, some coating compositions are highly colored (e.g., gold-colored coatings). These coatings may typically be formulated using crosslinkers that themselves tend to have a yellowish color. In contrast, white coatings are generally formulated using non-yellowing crosslinkers, or only a small amount of a yellowing crosslinker. Preferred curing agents are substantially free of mobile BPA and aromatic glycidyl ether compounds (e.g., BADGE, BFDGE and epoxy novalacs).

Any of the well known hydroxyl-reactive curing resins can be used. For example, phenoplast, and aminoplast curing agents may be used.

Phenoplast resins include the condensation products of aldehydes with phenols. Formaldehyde and acetaldehyde are preferred aldehydes. Various phenols can be employed such as phenol, cresol, p-phenylphenol, p-tert-butylphenol, p-tert-amylphenol, and cyclopentylphenol.

Aminoplast resins are the condensation products of aldehydes such as formaldehyde, acetaldehyde, crotonaldehyde, and benzaldehyde with amino or amido group-containing substances such as urea, melamine, and benzoguanamine.

Examples of suitable crosslinking resins include, without limitation, benzoguanamine-formaldehyde resins, melamine-formaldehyde resins, esterified melamine-formaldehyde, and urea-formaldehyde resins. Preferably, the crosslinker employed when practicing this invention includes a melamine-formaldehyde resin. One specific example of a particularly useful crosslinker is the fully alkylated melamine-formaldehyde resin commercially available from Cytec Industries, Inc. under the trade name of CYMELTM 303.

As examples of other generally suitable curing agents are the blocked or non-blocked aliphatic, cycloaliphatic or aromatic di-, tri-, or poly-valent isocyanates, such as hexamethylene diisocyanate, cyclohexyl-1,4-diisocyanate, and the like.

The level of curing agent (i.e., crosslinker) required will depend on the type of curing agent, the time and temperature of the bake, and the molecular weight of the polymer. If used, the crosslinker is typically present in an amount of up to 50 wt-%, preferably up to 30 wt-%, and more preferably up to 15 wt-%. These weight percentages are based upon the total weight of the resin solids in the coating composition.

A coating composition of the present invention may also include other optional polymers that do not adversely affect the coating composition or a cured coating composition resulting therefrom. Such optional polymers are typically included in a coating composition as a filler material, although they can be included
5 as a crosslinking material, or to provide desirable properties. One or more optional polymers (e.g., filler polymers) can be included in a sufficient amount to serve an intended purpose, but not in such an amount to adversely affect a coating composition or a cured coating composition resulting therefrom.

Such additional polymeric materials can be nonreactive, and hence, simply
10 function as fillers. Such optional nonreactive filler polymers include, for example, polyesters, acrylics, polyamides, polyethers, and novalacs. Alternatively, such additional polymeric materials or monomers can be reactive with other components of the composition (e.g., the acid-functional polymer). If desired, reactive polymers can be incorporated into the compositions of the present invention, to provide
15 additional functionality for various purposes, including crosslinking. Examples of such reactive polymers include, for example, functionalized polyesters, acrylics, polyamides, and polyethers. Preferred optional polymers are substantially free of mobile BPA and aromatic glycidyl ether compounds (e.g., BADGE, BFDGE and epoxy novalacs)

20 A coating composition of the present invention may also include other optional ingredients that do not adversely affect the coating composition or a cured coating composition resulting therefrom. Such optional ingredients are typically included in a coating composition to enhance composition esthetics, to facilitate manufacturing, processing, handling, and application of the composition, and to
25 further improve a particular functional property of a coating composition or a cured coating composition resulting therefrom.

Such optional ingredients include, for example, catalysts, dyes, pigments, toners, extenders, fillers, lubricants, anticorrosion agents, flow control agents, thixotropic agents, dispersing agents, antioxidants, adhesion promoters, light
30 stabilizers, surfactants, and mixtures thereof. Each optional ingredient is included in a sufficient amount to serve its intended purpose, but not in such an amount to

79713-5

adversely affect a coating composition or a cured coating composition resulting therefrom.

One preferred optional ingredient is a catalyst to increase the rate of cure. Examples of catalysts, include, but are not limited to, strong acids (e.g., dodecylbenzene sulphonic acid (DDBSA, available as CYCATTM 600 from Cytec), methane sulfonic acid (MSA), p-toluene sulfonic acid (pTSA), dinonylnaphthalene disulfonic acid (DNNDSA), and triflic acid), quaternary ammonium compounds, phosphorous compounds, and tin and zinc compounds. Specific examples include, but are not limited to, a tetraalkyl ammonium halide, a tetraalkyl or tetraaryl phosphonium iodide or acetate, tin octoate, zinc octoate, triphenylphosphine, and similar catalysts known to persons skilled in the art. If used, a catalyst is preferably present in an amount of at least 0.01 wt-%, and more preferably at least 0.1 wt-%, based on the weight of nonvolatile material. If used, a catalyst is preferably present in an amount of no greater than 3 wt-%, and more preferably no greater than 1 wt-%, based on the weight of nonvolatile material.

Another useful optional ingredient is a lubricant (e.g., a wax), which facilitates manufacture of metal closures by imparting lubricity to sheets of coated metal substrate. Preferred lubricants include, for example, Carnauba wax and polyethylene type lubricants. If used, a lubricant is preferably present in the coating composition in an amount of at least 0.1 wt-%, and preferably no greater than 2 wt-%, and more preferably no greater than 1 wt-%, based on the weight of nonvolatile material.

Another useful optional ingredient is a pigment, such as titanium dioxide. If used, a pigment is present in the coating composition in an amount of no greater than 70 wt-%, more preferably no greater than 50 wt-%, and even more preferably no greater than 40 wt-%, based on the total weight of solids in the coating composition.

Surfactants can be optionally added to the coating composition to aid in flow and wetting of the substrate. Examples of surfactants, include, but are not limited to, nonylphenol polyethers and salts and similar surfactants known to persons skilled in the art. If used, a surfactant is preferably present in an amount of at least 0.01 wt-%, and more preferably at least 0.1 wt-%, based on the weight of resin solids. If used, a

surfactant is preferably present in an amount no greater than 10 wt-%, and more preferably no greater than 5 wt-%, based on the weight of resin solids.

As described above, the coating compositions of the present invention are particularly well adapted for use on food and beverage cans (e.g., two-piece cans, three-piece cans, etc.). Two-piece cans are manufactured by joining a can body (typically a drawn metal body) with a can end (typically a drawn metal end). The coatings of the present invention are suitable for use in food or beverage contact situations and may be used on the inside of such cans. They are particularly suitable for spray applied, liquid coatings for the interior of two-piece drawn and ironed beverage cans and coil coatings for beverage can ends. The present invention also offers utility in other applications. These additional applications include, but are not limited to, wash coating, sheet coating, and side seam coatings (e.g., food can side seam coatings).

Spray coating includes the introduction of the coated composition into the inside of a preformed packaging container. Typical preformed packaging containers suitable for spray coating include food cans, beer and beverage containers, and the like. The spray preferably utilizes a spray nozzle capable of uniformly coating the inside of the preformed packaging container. The sprayed preformed container is then subjected to heat to remove the residual solvents and harden the coating.

A coil coating is described as the coating of a continuous coil composed of a metal (e.g., steel or aluminum). Once coated, the coating coil is subjected to a short thermal, ultraviolet, and/or electromagnetic curing cycle, for hardening (e.g., drying and curing) of the coating. Coil coatings provide coated metal (e.g., steel and/or aluminum) substrates that can be fabricated into formed articles, such as 2-piece drawn food cans, 3-piece food cans, food can ends, drawn and ironed cans, beverage can ends, and the like.

A wash coating is commercially described as the coating of the exterior of two-piece drawn and ironed ("D&I") cans with a thin layer of protectant coating. The exterior of these D&I cans are "wash-coated" by passing pre-formed two-piece D&I cans under a curtain of a coating composition. The cans are inverted, that is, the open end of the can is in the "down" position when passing through the curtain. This curtain of coating composition takes on a "waterfall-like" appearance. Once these

cans pass under this curtain of coating composition, the liquid coating material effectively coats the exterior of each can. Excess coating is removed through the use of an "air knife." Once the desired amount of coating is applied to the exterior of each can, each can is passed through a thermal, ultraviolet, and/or electromagnetic curing oven to harden (e.g., dry and cure) the coating. The residence time of the coated can within the confines of the curing oven is typically from 1 minute to 5 minutes. The curing temperature within this oven will typically range from 150°C to 220°C.

A sheet coating is described as the coating of separate pieces of a variety of materials (e.g., steel or aluminum) that have been pre-cut into square or rectangular "sheets." Typical dimensions of these sheets are approximately one square meter. Once coated, each sheet is cured. Once hardened (e.g., dried and cured), the sheets of the coated substrate are collected and prepared for subsequent fabrication. Sheet coatings provide coated metal (e.g., steel or aluminum) substrate that can be successfully fabricated into formed articles, such as 2-piece drawn food cans, 3-piece food cans, food can ends, drawn and ironed cans, beverage can ends, and the like.

A side seam coating is described as the spray application of a liquid coating over the welded area of formed three-piece food cans. When three-piece food cans are being prepared, a rectangular piece of coated substrate is formed into a cylinder. The formation of the cylinder is rendered permanent due to the welding of each side of the rectangle via thermal welding. Once welded, each can typically requires a layer of liquid coating, which protects the exposed "weld" from subsequent corrosion or other effects to the contained foodstuff. The liquid coatings that function in this role are termed "side seam stripes." Typical side seam stripes are spray applied and cured quickly via residual heat from the welding operation in addition to a small thermal, ultraviolet, and/or electromagnetic oven.

Other commercial coating application and curing methods are also envisioned, for example, electrocoating, extrusion coating, laminating, powder coating, and the like.

Preferred coatings of the present invention display one or more of the properties described in the Examples Section. More preferred coatings of the

present invention display one or more of the following properties: metal exposure value of less than 3 mA; metal exposure value after drop damage of less than 3.5 mA; global extraction results of less than 50 ppm; adhesion rating of 10; blush rating of at least 7; slight or no crazing in a reverse impact test; no craze (rating of 10) in a dome impact test; feathering below 0.2 inch; COF range of 0.055 to 0.095; and after
5 pasteurization or retort, a continuity of less than 20 mA.

EXAMPLES

The following examples are offered to aid in understanding of the present invention and are not to be construed as limiting the scope thereof. Unless otherwise
10 indicated, all parts and percentages are by weight.

Curing Conditions

For beverage inside spray bakes, the curing conditions involve maintaining the temperature measured at the can dome at 188°C to 199°C for 30 seconds.
15

For beverage end coil bakes, the curing conditions involve the use of a temperature sufficient to provide a peak metal temperature within the specified time (e.g., 10 seconds at 204°C means 10 seconds, in the oven, for example, and a peak metal temperature achieved of 204°C).

20 The constructions cited were evaluated by tests as follows:

Initial Metal Exposure

This test method determines the amount the inside surface of the can that has not been effectively coated by the sprayed coating. This determination is made thorough the use of an electrically conductive solution (1% NaCl in deionized
25 water). The coated can is filled with this conductive solution, and an electrical probe is attached in contact to the outside of the can (uncoated, electrically conducting). A second probe is immersed in the salt solution in the middle of the inside of the can. If any uncoated metal is present on the inside of the can, a current is passed between these two probes and registers as a value on an LED display. The
30 LED displays the conveyed currents in milliamps (mA). The current that is passed is directly proportional to the amount of metal that has not been effectively covered

with coating. The goal is to achieve 100% coating coverage on the inside of the can, which would result in an LED reading of 0.0 mA. Preferred coatings give metal exposure values of less than 3 mA, more preferred values of less than 2 mA, and even more preferred values of less than 1 mA. Commercially acceptable metal exposure values are typically less than 2.0 mA on average.

Metal Exposure After Drop Damage

Drop damage resistance measures the ability of the coated container to resist cracks after being conditions simulating dropping of a filled can. The presence of cracks is measured by passing electrical current via an electrolyte solution, as previously described in the Metal Exposure section. A coated container is filled with the electrolyte solution and the initial metal exposure is recorded. The can is then filled with water and dropped through a tube from a specified height onto an inclined plane, causing a dent in the chime area. The can is then turned 180 degrees, and the process is repeated. Water is then removed from the can and metal exposure is again measured as described above. If there is no damage, no change in current (mA) will be observed. Typically, an average of 6 or 12 container runs is recorded. Both metal exposures results before and after the drop are reported. The lower the milliamp value, the better the resistance of the coating to drop damage. Preferred coatings give metal exposure values after drop damage of less than 3.5 mA, more preferred valued of less than 2.5 mA, and even more preferred values of less than 1.5 mA.

Solvent Resistance

The extent of "cure" or crosslinking of a coating is measured as a resistance to solvents, such as methyl ethyl ketone (MEK, available from Exxon, Newark, NJ) or isopropyl alcohol (IPA). This test is performed as described in ASTM D 5402 – 93. The number of double-rubs (i.e., one back-and forth motion) is reported.

Global Extractions

The global extraction test is designed to estimate the total amount of mobile material that can potentially migrate out of a coating and into food packed in a

coated can. Typically coated substrate is subjected to water or solvent blends under a variety of conditions to simulate a given end-use. Acceptable extraction conditions and media can be found in 21CFR 175.300 paragraphs (d) and (e). The allowable global extraction limit as defined by the FDA regulation is 50 parts per million (ppm).

The extraction procedure used in the current invention is described in 21CFR 175.300 paragraph (e) (4) (xv) with the following modifications to ensure worst-case scenario performance: 1) the alcohol content was increased to 10% by weight and 2) the filled containers were held for a 10-day equilibrium period at 100°F. These conditions are per the FDA publication "Guidelines for Industry" for preparation of Food Contact Notifications. The coated beverage can was filled with 10 weight percent aqueous ethanol and subjected to pasteurization conditions (150°F) for 2 hours, followed by a 10-day equilibrium period at 100°F. Determination of the amount of extractives was determined as described in 21CFR 175.300 paragraph (e) (5), and ppm values were calculated based on surface area of the can (no end) of 44 square inches with a volume of 355 ml. Preferred coatings give global extraction results of less than 50 ppm, more preferred results of less than 10 ppm, even more preferred results of less than 1 ppm. Most preferably, the global extraction results are optimally non-detectable.

Adhesion

Adhesion testing is performed to assess whether the coating adheres to the coated substrate. The adhesion test was performed according to ASTM D 3359 – Test Method B, using SCOTCH 610 tape, available from 3M Company of Saint Paul, Minnesota. Adhesion is generally rated on a scale of 0-10 where a rating of "10" indicates no adhesion failure, a rating of "9" indicates 90% of the coating remains adhered, a rating of "8" indicates 80% of the coating remains adhered, and so on. Adhesion ratings of 10 are typically desired for commercially viable coatings.

Blush Resistance

Blush resistance measures the ability of a coating to resist attack by various solutions. Typically, blush is measured by the amount of water absorbed into a coated film. When the film absorbs water, it generally becomes cloudy or looks
5 white. Blush is generally measured visually using a scale of 0-10 where a rating of "10" indicates no blush and a rating of "0" indicates complete whitening of the film. Blush ratings of at least 7 are typically desired for commercially viable coatings and optimally 9 or above.

10 Process or Retort Resistance

This is a measure of the coating integrity of the coated substrate after exposure to heat and pressure with a liquid such as water. Retort performance is not necessarily required for all food and beverage coatings, but is desirable for some product types that are packed under retort conditions. The procedure is similar to
15 the Sterilization or Pasteurization test. Testing is accomplished by subjecting the substrate to heat ranging from 105-130°C and pressure ranging from 0.7 to 1.05 kg/cm² for a period of 15 to 90 minutes. For the present evaluation, the coated substrate was immersed in deionized water and subjected to heat of 121°C (250°F) and pressure of 1.05 kg/cm² for a period of 90 minutes. The coated substrate was
20 then tested for adhesion and blush as described above. In food or beverage applications requiring retort performance, adhesion ratings of 10 and blush ratings of at least 7 are typically desired for commercially viable coatings.

Crazing - Reverse Impact Resistance

25 The reverse impact measures the coated substrate's ability to withstand the deformation encountered when impacted by a steel punch with a hemispherical head. For the present evaluation, coated substrate was subjected to 12 in-lbs (1.36 N m) of force using BYK-Gardner "overall" Bend and Impact Tester and rated visually for micro-cracking or micro-fracturing – commonly referred to as crazing. Test
30 pieces were impacted on the uncoated or reverse side. A rating of 10 indicates no craze and suggests sufficient flexibility and cure. A rating of 0 indicates complete

failure. Commercially viable coatings preferably show slight or no crazing on a reverse impact test.

Impact on Dome

5 Dome impact was evaluated by subjecting the dome apex of a 12 oz. beverage can to a reverse impact as described in the previous section. Craze was evaluated after impact. A rating of 10 indicates no craze and suggests sufficient flexibility and cure. A rating of 0 indicates complete failure. Coatings for beverage can interiors preferably show no craze (rating of 10) on a dome impact.

10

Joy Detergent Test

A 1% solution of JOY Detergent (available from Procter & Gamble) in deionized water is prepared and heated to 82°C (180°F). Coated panels are immersed in the heated solution for 10 minutes and are then removed, rinsed, and
15 dried. Samples are then evaluated for adhesion and blush, as previously described. Commercially viable beverage interior coatings preferably give adhesion ratings of 10 and blush ratings of at least 7, optimally at least 9, in the detergent test.

Feathering

20 Feathering is a term used to describe the adhesion loss of a coating on the tab of a beverage can end. When a beverage can is opened, a portion of free film may be present across the opening of the can if the coating loses adhesion on the tab. This is feathering.

To test feathering, a "tab" is scored on the backside of a coated panel, with
25 the coated side of the panel facing downward. The test piece is then pasteurized as described under the Pasteurization section below.

After pasteurization, pliers are used to bend the cut "tab" to a 90 degree angle away from the coated side of the substrate. The test piece is then placed on a flat surface, coated side down. The cut "tab" is gripped using pliers and the "tab" is
30 pulled from the test panel at an angle of 180 degrees until it is completely removed. After removing the "tab," any coating that extends into the opening on the test panel is measured. The distance of the greatest penetration (feathering) is reported in

inches. Coatings for beverage ends preferably show feathering below 0.2 inch (0.508 cm), more preferably below 0.1 inch (0.254 cm), most preferably below 0.05 inch (0.127 cm), and optimally below 0.02 inch (0.051 cm).

5 Dowfax Detergent Test

The "Dowfax" test is designed to measure the resistance of a coating to a boiling detergent solution. This is a general test run for beverage end coatings and is mainly used to evaluate adhesion. Historically, this test was used to indicate problems with the interaction of coating to substrate pretreatment. The solution is prepared by mixing 5 ml of Dowfax 2A1 (product of Dow Chemical) into 3000 ml of deionized water. Typically, coated substrate strips are immersed into the boiling Dowfax solution for 15 minutes. The strips are then rinsed and cooled in deionized water, dried, and then tested and rated for blush and adhesion as described previously. Preferred beverage end coatings provide adhesion ratings of 10 and blush ratings of at least 4, more preferably 6 or above in the Dowfax detergent test.

Sterilization or Pasteurization

The sterilization or pasteurization test determines how a coating withstands the processing conditions for different types of food products packaged in a container. Typically, a coated substrate is immersed in a water bath and heated for 5-60 minutes at temperatures ranging from 65°C to 100°C. For the present evaluation, the coated substrate was immersed in a deionized water bath for 45 minutes at 85°C. The coated substrate was then removed from the water bath and tested for coating adhesion and blush as described above. Commercially viable coatings preferably provide adequate pasteurization resistance with perfect adhesion (rating of 10) and blush ratings of at least 5, optimally at least 9.

Coefficient of Friction

Coefficient of friction (COF) is a measurement of lubricity of a coating and is used to give an indication of how a cured coating will perform on commercial fabrication equipment and presses. Typically, lubricants are added to coatings requiring aggressive post application fabrication to give the appropriate lubricity.

For the present evaluation, an Altek Mobility / Lubricity Tester Model 9505AE with a chart recorder was used to measure the COF of cure beverage end coatings on aluminum substrates. The instrument works by pulling a sled with steel balls attached to a loadbar across the surface of the coated substrate, and the COF is
5 charted out as resistance on 0-10 scale chart paper. Each unit equals 0.25 COF units. Coatings of the present invention are formulated to give a preferred COF range of 0.055 to 0.095.

Fabrication or End Continuity

10 This test measures the ability of a coated substrate to retain its integrity as it undergoes the formation process necessary to produce a beverage can end. It is a measure of the presence or absence of cracks or fractures in the formed end. The end is typically placed on a cup filled with an electrolyte solution. The cup is inverted to expose the surface of the end to the electrolyte solution. The amount of
15 electrical current that passes through the end is then measured. If the coating remains intact (no cracks or fractures) after fabrication, minimal current will pass through the end.

For the present evaluation, fully converted 202 standard opening beverage ends were exposed for a period of 4 seconds to an electrolyte solution comprised of
20 1% NaCl by weight in deionized water. Metal exposure was measured using a WACO Enamel Rater II, available from the Wilkens-Anderson Company, Chicago, IL, with an output voltage of 6.3 volts. The measured electrical current, in milliamps, is reported. End continuities are typically tested initially and then after the ends are subjected to pasteurization or retort.

25 Preferred coatings of the present invention initially pass less than 10 milliamps (mA) when tested as described above, more preferably less than 5 mA, most preferably less than 2 mA, and optimally less than 1 mA. After pasteurization or retort, preferred coatings give continuities of less than 20 mA, more preferably less than 10 mA, even more preferably less than 5 mA, and even more preferably
30 less than 2 mA.

79713-5

List of Raw Materials and Ingredients

The following table lists some of the raw materials and ingredients used in the following examples. Alternative materials or suppliers may be substituted as is appreciated to one skilled in the art

5

Chemical Name	Trade Name	Supplier	Location
Glacial Methacrylic Acid		Rohm & Haas	Philadelphia, PA
Butyl Acrylate		Rohm & Haas	Philadelphia, PA
Styrene		Rohm & Haas	Philadelphia, PA
Benzoyl Peroxide		Norac Company	Helena, AR
Butanol		Dow	Midland, MI
Ethylene Glycol Butyl ether	Butyl Cellosolve™/Dowanol™ EB	Dow	Midland, MI
Butyl Methacrylate		Rohm & Haas	Philadelphia, PA
t-Butyl peroxoate		Arkema	Philadelphia, PA
Ethyl acrylate		Rohm & Haas	Philadelphia, PA
Acrylic Acid		Rohm & Haas	Philadelphia, PA
Hydroxypropylmethacrylate	ROCRYL™ 410	Rohm & Haas	Philadelphia, PA
Hydroxyethyl methacrylate	ROCRYL™ 400	Rohm & Haas	Philadelphia, PA
Dimethylethanol amine		Huntsman Chemical	Dallas, TX
Glycidyl methacrylate	SR 379	Sartomer, Inc	Warrington, PA
Hydrogen peroxide		Ashland Chemical	Pittsburgh, PA
Benzoin		Estron	Calvert City, KY
N- Isobutoxymethacrylamide	CYLINK™ IBMA monomer	Cytec Ind.	West Patterson, NJ
Amyl alcohol		Dow	Midland, MI
Propylene glycol butyl ether	DOWANOL™ PNB	Dow	Midland, MI
Secondary alcohol ethoxylate	TERGITOL™ 15-S-7	Dow	Midland, MI
sec-butanol		Dow	Midland, MI
Polyethylene wax	Slipayd™ 404	Elementis	Staines, UK
Thermoset Phenol Based Phenolic	SD-912B	Valspar	Minneapolis, MN
Carnuba wax emulsion	Michemlube™ 160 PFE	Michelman	Cincinnati, OH
Isooctyl alcohol		Aldrich Chemical	Milwaukee, WI

79713-5

Polyethylene wax	Lanco Glidd™ 5118	Lubrizol	Wickliffe, OH
Dipropylene glycol		Aldrich Chemical	Milwaukee, WI
Isophthalic acid		BP Amoco	Chicago, IL
Dibutyl tin oxide	Fastcat™ 4201	Arkema	Philadelphia, PA
Xylene		Exxon	Newark, NJ
Trimellitic anhydride		BP Amoco	Chicago, IL
Iron Complex	Hamp-OL™ 4.5% Iron	Traylor Chemical	Orlando, FL
Erythorbic acid		Aldrich Chemical	Milwaukee, WI
T-Butylhydroperoxide	Trigonox™ A-W70	Akzo	Philadelphia, PA
Ethylene glycol		Ashland Chemical	Pittsburgh, PA
Sebacic acid		Ivanhoe Industries	Tampa, FL
1,4-cyclohexane dimethanol 90% in water	CHDM-90	Eastman	Kingsport, TN
Buty Stannoic acid	Fastcat™ 4100	Arkema	Philadelphia, PA
4-Hydroxybenzoic acid		Acros Organics through Fisher Scientific	Houston, TX
1,4-Cyclohexane dimethanol diglycidyl ether	Erisys™ GE-22	CVC Specialty Chemicals	Maple Shade, NJ
Ethyltriphenyl phosphonium iodide	Catalyst™ 1201	Deepwater Chemicals	Woodward, OK
Succinic anhydride		JLM Marketing	Tampa, FL
Bisphenol A		Dow	Midland, MI
Bisphenol A diglycidyl ether	Epon™ 828	Resolution Performance Products	Houston, TX
Methylisobutyl ketone		Dow	Midland, MI
Dibasic ester		Dupont	Wilmington, DE
Propylene glycol methyl ether	Dowanol™ PM	Dow	Midland, MI

Example 1: Run 1. Preparation of Acid-Functional Acrylic

A premix of 512.6 parts glacial methacrylic acid (MAA), 512.6 parts butyl acrylate (BA), 114.0 parts styrene, and 73.2 parts benzoyl peroxide (70% water wet) was prepared in a separate vessel. A 3-liter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Ten percent of the premix was added to the flask along with 405.9 parts butanol and 30.6 parts deionized water. To the remaining premix were added 496.1 parts butanol and 38.3 parts deionized water. With the nitrogen blanket flowing in the flask, the contents were heated to 93°C. At 93°C, external heating was stopped and the material was allowed to increase in temperature for fifteen minutes. After fifteen minutes, the batch was at 97°C, and the remaining premix was added uniformly over two hours maintaining 97°C to 100°C. When the premix addition was complete, the premix vessel was rinse with 5 parts butanol. The batch was held at temperature for two and a half hours. The heating was discontinued and 317.7 parts butyl cellosolve was added. The resulting acrylic prepolymer was 44.3% solids (NV), with an acid number of 313 and a Brookfield viscosity (as determined by ASTM D-2196) of 4,990 centipoise (cps).

Example 1: Run 2. Preparation of Acid-Functional Acrylic

A premix of 677.7 parts glacial methacrylic acid, 677.7 parts butyl methacrylate (BMA), 150.8 parts styrene, and 96.9 parts benzoyl peroxide (70% water wet) was prepared in a separate vessel. A 5-liter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Ten percent of the premix was added to the flask along with 536.9 parts butanol and 40.7 parts deionized water. To the remaining premix were added 758.1 parts butanol and 50.6 parts deionized water. With the nitrogen blanket flowing in the flask, the contents were heated to 93°C. At 93°C, external heating was stopped, and the material was allowed to increase in temperature for ten minutes. After ten minutes, the batch was at 98°C, and the remaining premix was added uniformly over two hours maintaining 97°C to 100°C. The batch was held at temperature for three hours.

The heating was discontinued and the batch cooled. The resulting acrylic prepolymer was 49.9% NV, with an acid number of 304 and a Brookfield viscosity of 101,000 centipoise.

5 Example 1: Run 3. Preparation of Acid-Functional Acrylic

A premix of 802.6 parts glacial methacrylic acid, 807 parts butyl methacrylate, 178.5 parts styrene, 80.3 parts t-butyl peroctoate, 838.5 parts butanol, and 59.9 parts deionized water was prepared in a separate vessel. A 5-liter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and
10 nitrogen blanket. Added to the 5 liter flask were 635.8 parts butanol and 48.1 parts deionized water. The flask was heated to 94°C. At 94°C 12.5 parts t-butyl peroctoate were added. The batch was held for five minutes after which the premix was added over two and a half hours. A second premix containing 59.2 parts butanol and 16.1 parts t-butyl peroctoate was prepared. When the addition of the first
15 premix was complete the second premix was added over 30 minutes. Once complete, the batch was held for 30 minutes. A chase of 3.4 parts t-butyl peroctoate was added and the batch held for two hours. After the two-hour hold time, the heat was discontinued and the batch cooled. The resulting acrylic prepolymer was 50.1% NV, with an acid number of 292 and a Brookfield viscosity of 150,000 centipoise.

20

 Example 1: Run 4. Preparation of Acid-Functional Acrylic

A premix of 802.6 parts glacial methacrylic acid, 445.9 parts ethyl acrylate, 535.1 parts styrene, 108.6 parts t-butyl peroctoate, 838.5 parts butanol, and 59.9 parts deionized water was prepared in a separate vessel. A 5-liter flask was
25 equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Added to the 5-liter flask was 635.8 parts butanol and 48.1 parts deionized water. The flask was heated to 94 °C. At 94 °C 16.6 parts t-butyl peroctoate was added. The batch was held for five minutes after which the premix was added over two and a half hours. A second premix containing 59.2 parts butanol and 21.2 parts t-butyl peroctoate was prepared. When the addition of the first premix
30 was complete the second premix was added over 30 minutes. Once complete, the batch was held for 30 minutes. A chase of 4.6 parts t-butyl peroctoate was added and

the batch held for two hours. After the two hour hold the heat discontinued and the batch cooled. The resulting acrylic prepolymer was 49.8% NV, with an acid number of 303 and a Brookfield viscosity of 21,650 centipoise.

5

Example 1: Runs 5-11

Using techniques from Example 1: Run 4, the systems shown in Table 1 were prepared.

Table 1: Acid-Functional Acrylics

Ex. 1:	Run 4	Run 5	Run 6	Run 7	Run 8	Run 9	Run 10	Run 11
MAA	45	30	45	0	30	45	25	45
EA	25	50	45	23	0	15	30	0
Styrene	30	5	10	10	25	0	25	10
BMA	0	15	0	31	0	40	0	45
AA ¹	0	0	0	36	0	0	0	0
BA	0	0	0	0	45	0	0	0
HPMA ²	0	0	0	0	0	0	20	0
Solids	49.8%	62.8%	49.4%	51.4%	55.4%	49.6%	50.5%	49.7%
Acid No.	303	198	295	246	192	293	155	292
Brookfield Visc. (cps)	21,650	50,000	8,730	1,100	6,660	27,800	3,532	106,000

10

¹ Glacial acrylic acid

² Hydroxypropyl methacrylate

Example 1: Run 12. Preparation of Acid-Functional Acrylic

A premix of 803.4 parts glacial methacrylic acid, 446.3 parts ethyl acrylate (EA), 535.5 parts styrene, 153 parts benzoyl peroxide (70% water wet), 839.2 parts butanol, and 60 parts deionized water was prepared in a separate vessel. A 5-liter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle and nitrogen blanket. To the flask, 636.3 parts butanol and 48.2 parts deionized water were added and heated to 97°C to 100°C with a nitrogen blanket flowing in the flask. The premix was added uniformly over two and a half hours maintaining 97°C to 100°C. When the premix was in, the premix vessel was rinsed with 59.2 parts

20

butanol and added to the flask. The batch was held at temperature for two hours. The heating was discontinued and the batch cooled. The resulting acrylic prepolymer was 50.2% NV, with an acid number of 301 and a Brookfield viscosity of 25,400 centipoise.

5

Example 1: Runs 13-15

Using techniques from Example 1: Run 12 the systems shown in Table 2 were prepared.

10 Table 2: Acid-Functional Acrylics

Example No. 1:	Run 12	Run 13	Run 14	Run 15
MAA	45	25	35	25
EA	25	25	25	33
Styrene	30	30	30	22
HPMA	0	20	10	20
Solids	51.2%	50.2%	50.0%	50.3%
Acid Number	301	171	234	169
Brookfield Viscosity (cps)	25,400	2,820	6,020	2,220

Example 2: Run 1. Preparation of Salt of Acid-Functional Acrylic

15 A 3-liter flask was equipped with a stirrer, reflux condenser, Dean Stark
Tube, thermocouple, heating mantle, and nitrogen blanket. Into the flask was added
711.5 parts of Example 1: Run 1 acrylic, 762.9 parts deionized water, and 56.9 parts
dimethyl ethanol amine (DMEA). The contents were heated to reflux and 553 parts
were distilled from the flask. After distillation was complete, 598 parts of deionized
water were added. The batch was cooled giving an acrylic solution at 20.3% solids
20 and 307 acid number.

Example 2: Run 2. Preparation of Salt of Acid-Functional Acrylic

A 5-liter flask was equipped with a stirrer, reflux condenser, Dean Stark Tube, thermocouple, heating mantle, and nitrogen blanket. Into the flask was added 1853 parts of Example 1: Run 2 acrylic, 2220.4 parts deionized water, and 163.3 parts dimethyl ethanol amine. The contents were heated to reflux and 1587 parts were distilled from the flask. After distillation was complete, 1718 parts of deionized water were added. The batch was cooled giving an acrylic solution at 22.2% solids, 294 acid number, pH of 6.0, and a viscosity of 13 seconds (Number 4 Ford cup viscosity as determined by ASTM D-1200).

Example 2: Run 3. Preparation of Salt of Acid-Functional Acrylic

A 5-liter flask was equipped with a stirrer, reflux condenser, Dean Stark Tube, thermocouple, heating mantle, and nitrogen blanket. Into the flask was added 1852.3 parts of Example 1: Run 3 acrylic, 2219 parts deionized water, and 163 parts dimethyl ethanol amine. The contents were heated to reflux and 1463 parts were distilled from the flask. After distillation was complete, 1581 parts of deionized water were added. The batch was cooled giving an acrylic solution at 21.6% solids, 284 acid number, pH of 6.23 and a viscosity of 13 seconds (Number 4 Ford cup).

Example 2: Run 4. Preparation of Salt of Acid Functional Acrylic

A 5-liter flask was equipped with a stirrer, reflux condenser, Dean Stark Tube, thermocouple, heating mantle, and nitrogen blanket. Into the flask was added 1799.2 parts of Example 1: Run 4 acrylic, 2155.9 parts deionized water, and 158.6 parts dimethyl ethanol amine. The contents were heated to reflux and 1541 parts were distilled from the flask. After distillation was complete, 1615 parts of deionized water were added. The batch was cooled giving an acrylic solution at 22.1% solids, 302 acid number, pH of 6.55 and a Brookfield viscosity of 2060 centipoise.

Example 2: Runs 5-15

Using techniques from Example 2: Run 4 the systems shown in Table 3 were prepared. Each run of Example 2 used the correspondingly numbered run from

Example 1. That is, Example 2: Run 5 used the acrylic prepolymer from Example 1: Run 5, etc.

Table 3: Acid-Functional Acrylic Salts

Ex 2:	Run 4	Run 5	Run 6	Run 7	Run 8	Run 9
Solids	22.1%	21.4%	21.6%	22.0%	21.7%	21.3%
Acid No.	302	198	291	248	193	291
PH	6.55	6.49	5.96	5.95	7.30	6.26
Viscosity ¹	2,060 cps	1,050 cps	1,770 cps	----	----	20 sec
Ex. 2:	Run 10	Run 11	Run 12	Run 13	Run 14	Run 15
Solids	21.7%	21.7%	22.0%	21.3%	21.7%	22.2%
Acid No.	153	300	291	169	231	271
pH	7.29	6.54	6.37	6.72	----	6.67
Viscosity ¹	881 cps	15 sec	167 cps	304 cps	248 cps	1900 cps

5 ¹ Brookfield viscosity values in cps and Number 4 Ford cup viscosity values in sec.

Example 3: Run 1. Emulsion

A 1-liter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Into the flask were added 313.9 parts of Example 2: Run 3 salt and 267.3 parts deionized water. The contents of the flask were heated to 75°C at 280 revolutions per minute (RPM). In a separate vessel, a premix of 71.4 parts styrene, 116.3 parts butyl methacrylate, and 16.3 parts glycidyl methacrylate (GMA) was prepared. Once the flask was at 75°C, 10% of the premix was added followed by 2.04 parts benzoin and 20 parts deionized water. The flask was heated further to 79°C. At 79°C, 2.04 parts of 35% hydrogen peroxide was added and held for five minutes. After five minutes the temperature control was set at 81°C and the remaining premix was added over a period of one hour. When the addition was complete, 20 parts deionized water were used to rinse the residual premix into the flask. The batch was held for ten minutes and then 0.35 part benzoin, 20 parts deionized water, and 0.35 part 35% hydrogen peroxide were added. After two hours the heat was removed and the batch cooled. This gave an emulsion at 31.9% solids, 63.3 acid number, pH of 6.48, and a Brookfield viscosity of 203 centipoise.

Example 3: Run 2. Emulsion

A 0.5-liter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Into the flask was added 155.6 parts of
5 Example 2: Run 4 salt and 120.6 parts deionized water. The contents of the flask were heated to 75°C at 240 RPM. In a separate vessel, a premix of 66.3 parts styrene, 19.6 parts ethyl acrylate, and 7.5 parts glycidyl methacrylate was prepared. Once the flask was at 75°C, 10% of the premix was added followed by 0.91 part benzoin and 9.4 parts deionized water. The flask was heated further to 79°C. At
10 79°C, 0.91 part of 35% hydrogen peroxide was added and held for five minutes. After five minutes the temperature control was set at 81°C and the remaining premix was added over one hour. When the addition was complete, 9.4 parts deionized water were used to rinse the residual premix into the flask. The batch was held for ten minutes and then 0.16 part benzoin, 9.4 parts deionized water, and 0.16 part 35%
15 hydrogen peroxide were added. After two hours the heat was removed and the batch cooled. This gave an emulsion at 30.9% solids, 83.8 acid number, pH of 6.70, and a viscosity of 40 seconds (Number 4 Ford cup).

Example 3: Run 3. Emulsion

20 A 1-liter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Into the flask was added 311.2 parts of Example 2: Run 4 salt and 241.2 parts deionized water. The contents of the flask were heated to 75°C at 270 RPM. In a separate vessel, a premix of 112.1 parts styrene, 59.8 parts ethyl acrylate, and 14.9 parts glycidyl methacrylate was prepared.
25 Once the flask was at 75°C, 10% of the premix was added followed by 1.87 parts benzoin and 18.8 parts deionized water. The flask was heated further to 79°C. At 79°C, 1.87 parts of 35% hydrogen peroxide were added and held for five minutes. After five minutes, the temperature control was set at 81°C and the remaining premix was added over one hour. When the addition was complete, 18.8 parts
30 deionized water were used to rinse the residual premix into the flask. The batch was held for ten minutes and then 0.32 part benzoin, 18.8 parts deionized water, and 0.32 part 35% hydrogen peroxide were added. After two hours, the heat was removed and

the batch cooled. This gave an emulsion at 31.8% solids, 76.7 acid number, pH of 6.67, and a viscosity of 28 seconds (Number 4 Ford cup).

Example 3: Run 4. Emulsion

5 A 5-liter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Into the flask was added 1525.0 parts of Example 2: Run 4 salt and 1219.1 parts deionized water. The contents of the flask were heated to 70°C at 250 RPM. In a separate vessel a premix of 380.4 parts styrene, 278.3 parts butyl acrylate (BA), 194.9 parts butyl methacrylate, and 74.2
10 parts glycidyl methacrylate was prepared. Once the flask was at 70°C, 10% of the premix was added followed by 9.29 parts benzoin and 92.9 parts deionized water. The flask was heated further to 79°C. At 79°C, 9.29 parts of 35% hydrogen peroxide were added and held for five minutes. After five minutes the temperature control was set at 81°C and the remaining premix was added over one hour. When the
15 addition was complete, 92.9 parts deionized water were used to rinse the residual premix into the flask. The batch was held for ten minutes and then 1.59 parts benzoin, 92.9 parts deionized water, and 1.59 parts 35% hydrogen peroxide were added. The batch was held for 45 minutes and then 0.52 part benzoin and 0.52 part 35% hydrogen peroxide were added. After two hours the heat was removed and the
20 batch cooled. This gave an emulsion at 31.4% solids, 64.1 acid number, pH of 6.95, and a viscosity of 22 seconds (Number 4 Ford cup).

Example 3: Run 5. Emulsion

 A 12-liter flask was equipped with a stirrer, reflux condenser, thermocouple,
25 heating mantle, and nitrogen blanket. Into the flask was added 3886.5 parts of Example 2: Run 4 salt and 3022.5 parts deionized water. The contents of the flask were heated to 70°C at 235 RPM. In a separate vessel, a premix of 771.25 parts styrene, 933.75 parts butyl acrylate, 537.5 parts butyl methacrylate, and 93.75 parts glycidyl methacrylate was prepared. Once the flask was at 70°C, 23.38 parts benzoin
30 and 116.25 parts deionized water followed by 10% of the premix were added. The flask was heated further to 79°C. At 79 °C, 23.38 parts of 35% hydrogen peroxide and 116.25 parts deionized water were added and held for five minutes. After five

minutes the temperature control was set at 81°C and the remaining premix was added over one hour. When the addition was complete, 232.5 parts deionized water were used to rinse the residual premix into the flask. The batch was held for ten minutes and then 4.0 parts benzoin, 232.5 parts deionized water, and 4.0 parts 35% hydrogen peroxide were added. The batch was held for 45 minutes and then 1.25 parts benzoin and 1.25 parts 35% hydrogen peroxide were added. After two hours the heat was removed and the batch cooled. This gave an emulsion at 31.4% solids, 72.4 acid number, pH of 7.05, and a viscosity of 32 seconds (Number 4 Ford cup).

10

Example 3: Runs 6-10

Using the process outlined in Example 3: Run 4 the Emulsions shown in Table 4 were prepared.

Table 4: Emulsions

Example 3:	Run 4	Run 6	Run 7	Run 8	Run 9	Run 10
Acrylic salt	Ex. 2: Run 4	Ex. 2: Run 4	Ex. 2: Run 4	Ex. 2: Run 4	Ex. 2: Run 4	Ex. 2: Run 4
Monomers						
Styrene	41.0	39.0	42.0	43.5	43.5	45.0
BA	30.0	53.0	54.0	54.5	54.5	55.0
BMA	21.0	0.0	0.0	0.0	0.0	0.0
GMA	8.0	8.0	4.0	2.0	2.0	0.0
Emulsion Comments	Good Appearance	Good Appearance	Good Appearance	White-High Viscosity	White-Low Conversion	Emulsion Separated
Solids	31.4%	31.3%	31.5%	31.7%	28.6%	31.2%
Viscosity (No. 4 Ford Cup)	22 sec	51 sec	103 sec	----	22 sec	----
Brookfield Viscosity	----	230 cps	610 cps	25,000cps	----	----
pH	6.95	7.05	6.88	----	6.65	----

15

This resin series showed that as the GMA level decreased, acceptable emulsions became more difficult to produce.

Example 3: Runs 11-18

A design experiment using Example 2: Run 9 as the acid functional acrylic salt and the process outlined above was prepared and is depicted in Table 5.

5

Table 5: Emulsion Design Experiment

Example 3:	Run 11	Run 12	Run 13	Run 14	Run 15	Run 16	Run 17	Run 18
Acrylic/Monomer Ratio	73 / 27				65 / 35			
	Monomer Composition 1		Monomer Composition 2		Monomer Composition 1		Monomer Composition 2	
GMA Level	Low	High	Low	High	Low	High	Low	High
Monomers								
Styrene	42	39	33	33	43	41	33	33
BA	54	53	40	41	54	53	40	40
BMA	0	0	23	18	0	0	24	21
GMA	4	8	4	8	3	6	3	6
Solids	32.0%	31.3%	31.6%	31.9%	31.6%	32.0%	31.7%	32.0%
Viscosity (No. 4 Ford Cup)	---	63 sec	---	---	35 sec	210 sec	42 sec	---
Brookfield Viscosity (cps)	10,000	---	10,000	695	---	---	---	1,384
Acid Number	74.7	72.9	74.9	70.2	101	96.1	101	96.5

The latices from Table 5 were tested without further modification or formulation, and the results are shown in Table 6. Each composition was drawn down onto Alcoa ALX aluminum at a film weight of 7-8 milligrams per square inch (msi) (1.1-1.25 milligrams per square centimeter (mg/cm²)) and cured for 10 seconds to achieve a 420°F (215°C) peak metal temperature in a gas fired coil oven.

Table 6: Beverage End Film Performance

	Waterbased	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run
	Control ¹	11	12	13	14	15	16	17	18	
Craze	None	None	None	None	None	None	Slight	None	None	
MEK Resistance	19	5	6	3	7	5	6	4	8	
Feathering ⁴	0.343	0.013	0.020	0.071	0.003	0.020	0.013	0.030	0.013	
Water Retort ²										
Blush	9.5	10	9.5	9.5	9.5	9	10	8	10	
Adhesion	10	10	10	10	10	10	10	10	10	
Pasteurization ³										
Blush	10	10	10	10	10	10	10	10	10	
Adhesion	10	10	10	10	10	10	10	10	10	
End Continuity										
Initial	0	0.22	25.3	11.5	57.8	17.7	133.5	27.5	132.2	
After Retort ²	8.4	31.8	Not Tested	31.7	Not Tested	Not Tested	Not Tested	34.3	Not Tested	

¹ Commercially available beverage end coating from Valspar coded 13Q80AG.² 90 minutes at 121°C (250°F).³ 30 minutes at 85°C (185°F).⁴ Performed after a 45 minutes at 85°C (185°F) pasteurization. Measured in centimeters.

Example 3: Runs 5b and 19-25

A design experiment using Example 2: Run 4 as the acid functional acrylic salt and the process outlined above was prepared and is depicted in Table 7.

Example 3: Run 5b was included as one of the variables and was a repeat of Run 5.

5

Table 7: Emulsion Design Experiment

Example 3:	Run 19	Run 20	Run 5b	Run 21	Run 22	Run 23	Run 24	Run 25
Acrylic/Monomer Ratio	73 / 27				65 / 35			
	Monomer Composition 1		Monomer Composition 2		Monomer Composition 1		Monomer Composition 2	
GMA Level	Low	High	Low	High	Low	High	Low	High
Monomers								
Styrene	42	39	33	33	43	41	33	33
BA	54	53	40	41	54	53	40	40
BMA	0	0	23	18	0	0	24	21
GMA	4	8	4	8	3	6	3	6
Solids	31.5%	31.6%	31.6%	31.4%	31.3%	31.6%	31.5%	31.7%
Viscosity (No. 4 Ford Cup)	55 sec	60 sec	50 sec	56 sec	106 sec	---	70 sec	---
Brookfield Viscosity (cps)	---	---	---	---	---	2,624	---	3,000
Acid Number	71.9	73.0	69.0	68.3	95.4	92.5	94.7	98.0

The lattices from Table 7 were tested without further modification or formulation, and the results are shown in Table 8. Each composition was drawn down onto Alcoa ALX aluminum at a film weight of 7-8 msi (1.1-1.25 mg/cm²) and cured for 10 seconds to achieve a 420°F (215°C) peak metal temperature in a gas fired coil oven.

10

Table 8: Beverage End Film Performance

	Waterbased Control ¹	Ex. 3: Run 19	Ex. 3: Run 20	Ex. 3: Run 5b	Ex. 3: Run 21	Ex. 3: Run 22	Ex. 3: Run 23	Ex. 3: Run 24	Ex. 3: Run 25
Craze	None	None	None	None	None	None	Slight	None	Yes
MEK	19	4	7	4	10	6	11	4	6
Feathering ⁴	0.343	0.064	0.051	0.038	0.033	0.056	0.013	0.046	0.013
Water Retort ²									
Blush	9.5	9.5	9.5	10	10	9.5	10	7	9.5
Adhesion	10	10	10	10	10	10	10	10	10
Pasteurization ³									
Blush	10	10	10	10	10	10	10	10	10
Adhesion	10	10	10	10	10	10	10	10	10
End Continuity									
Initial	0	5.5	2.6	6.0	12.3	20.2	61.2	1.9	93.6
After Retort ²	8.4	23.5	143	23.4	134.0	78.8	Not Tested	52.5	Not Tested

¹ Commercially available beverage end coating from Valspar coded 13Q80AG.² 90 minutes at 121°C (250°F).³ 30 minutes at 85°C (185°F).⁴ Performed after a 45 minutes at 85°C (185°F) pasteurization. Measured in centimeters.

Example 3: Runs 26-33

A design experiment using Example 2: Run 11 as the acid functional acrylic salt and the process outlined above was prepared and is depicted in Table 9.

5

Table 9: Emulsion Design Experiment

Example 3:	Run 26	Run 27	Run 28	Run 29	Run 30	Run 31	Run 32	Run 33
Acrylic/Monomer Ratio	73 / 27				65 / 35			
	Monomer Composition 1		Monomer Composition 2		Monomer Composition 1		Monomer Composition 2	
GMA Level	Low	High	Low	High	Low	High	Low	High
Monomers								
Styrene	42	39	33	33	43	41	33	33
BA	54	53	40	41	54	53	40	40
BMA	0	0	23	18	0	0	24	21
GMA	4	8	4	8	3	6	3	6
Solids	31.0%	31.8%	31.5%	31.4%	30.9%	31.3%	31.4%	31.6%
Viscosity (No. 4 Ford Cup)	40 sec	48 sec	---	17 sec	14 sec	16 sec	14 sec	16 sec
Brookfield Viscosity (cps)	---	---	17,000	---	---	---	---	---
Acid Number	73.5	68.7	71.2	68.6	97.0	93.9	99.3	93.9

The latices from Table 9 were tested without further modification or formulation, and the results are shown in Table 10. Each composition was drawn down onto Alcoa ALX aluminum at a film weight of 7-8 msi (1.1-1.25 mg/cm²) and cured for 10 seconds to achieve a 420°F (215°C) peak metal temperature in a gas fired coil oven.

10

Table 10: Beverage End Film Performance of Emulsion DOE C

	Waterbased	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run	Ex. 3: Run
	Control ¹	26	27	28	29	30	31	32	33
Craze	None	Slight	None	None	Yes	Yes	Yes	Yes	Yes
MEK	19	7	8	3	12	3	5	7	6
Feathering ⁴	0.343	0.046	0.043	0.013	0.025	0.013	0.013	0.020	0.013
Water Retort ²									
Blush	9.5	9.5	10.0	9.5	10	2	10	3	9.5
Adhesion	10	10	10	10	10	10	10	10	10
Pasteurization ³									
Blush	10	10	10	10	10	10	10	10	10
Adhesion	10	10	10	10	10	10	10	10	10
End Continuity									
Initial	0	82.4	107.4	12.2	215.6	178.9	315.9	161.5	336.9
After Retort ²	8.4	Not Tested	Not Tested	Not Tested	Not Tested	Not Tested	Not Tested	Not Tested	Not Tested

¹ Commercially available beverage end coating from Valspar coded 13Q80AG.

² 90 minutes at 121°C (250°F).

³ 30 minutes at 85°C (185°F).

⁴ Performed after a 45 minutes at 85°C (185°F) pasteurization. Measured in centimeters.

The following are some of the conclusions drawn from results of the emulsion DOEs shown in Tables 5 through 10. The non styrene-containing acrylic stabilizer polymer from Example 2: Run 9 produced higher viscosity emulsions, which are less desirable for some end uses. The composition from Example 2: Run 4 gave better overall film performance. In general, a higher acrylic polymer/monomer ratio tended to give poorer film integrity (continuities). Higher GMA levels in the emulsion monomer mix tended to give higher emulsion viscosities and greater increases in film continuity mAs after retort. Little difference was noticed between the various co-monomer compositions, so there is latitude to vary the overall emulsion monomer composition.

Example 3: Runs 34-35

A series of emulsions, shown in Table 11 were prepared using a monomer to acid functional acrylic ratio of 73/27 solids/solids. These systems were prepared using the process outlined in Example 3: Run 5 using Example 2: Run 4 as the acid functional acrylic salt.

Table 11: Emulsion GMA Level Study

Example 3:	Run 5b	Run 34	Run 35
GMA Level	4%	12%	20%
Monomers			
Styrene	33	33	33
BA	40	42	44
BMA	23	13	3
GMA	4	12	20
Solids	31.6%	31.8%	32.0%
Viscosity (No. 4 Ford cup)	50 sec	---	---
Brookfield Visc. (cps)	---	1,070	33,950
Acid Number	69.0	59.5	44.9

It can be seen that as the glycidyl methacrylate level was increased, the resulting acid number decreased, indicating the GMA consumed some of the acid groups on the acrylic polymer stabilizer.

5

Example 3: Runs 36-42

A series of emulsions, shown in Table 12, were prepared using a monomer to acid functional acrylic ratio of 73/27 solids/solids. These systems were prepared using the process outlined in Example 3: Run 5b using Example 2: Run 10 as the acid functional acrylic salt. This acrylic contains hydroxyl functionality that may theoretically co-react with the IBMA during cure.

10

Table 12: Effect of IBMA in Emulsions

Example 3:	Run 36	Run 37	Run 38	Run 39	Run 40	Run 41	Run 42
IBMA Level	0%	4%	5%	6%	7%	8%	12%
Monomers							
Styrene	33	26	26	26	26	26	26
BA	40	45	46	46	46	47	48
BMA	23	21	19	18	17	15	10
GMA	4	4	4	4	4	4	4
IBMA ¹	0	4	5	6	7	8	12
Solids %	31.4%	31.6%	30.9%	30.4%	30.4%	30.0%	29.8%
Viscosity (No. 4 Ford Cup)	22 sec	17 sec	18 sec	16 sec	16 sec	16 sec	17 sec
Acid Number	38.1	40.1	40.9	39.5	40.5	41.0	40.4

¹ N-Isobutoxymethyl acrylamide

15

The latices from Table 12 were tested without further modification or formulation, and the results are shown in Table 13. Each composition was drawn down onto Alcoa ALX aluminum at a film weight of 7-8 msi (1.1-1.25 mg/cm²) and cured for 10 seconds to achieve a 420°F (215°C) peak metal temperature in a gas fired coil oven.

20

Table 13: Beverage End Continuities (IBMA Level)

Example 3:	Run 36	Run 37	Run 38	Run 39	Run 40	Run 41	Run 42
IBMA Level	0%	4%	5%	6%	7%	8%	12%
End Continuity							
Initial	3	1.5	1.1	1.0	0.4	0.9	0.7
After Retort ¹	19	12	4.3	6.5	6.6	9.3	31

¹ 90 minutes at 250°F (121°C).

Results from Table 13 indicate the optimum level of IBMA in the emulsion monomer composition is around 5%, when used in conjunction with hydroxyl functionality in the acrylic polymer stabilizer.

Example 4: Runs 1-2. Spray Application

The water-based emulsion of Example 3: Run 4 was successfully formulated into a spray applied coating for the interior of beer/beverage aluminum cans. The product was formulated with or without additional surfactant, as described in Table 14.

Table 14: Beverage Inside Spray Coating Compositions

Example 4:	Run 1	Run 2
Composition (parts)		
Example 3: Run 4	62	65
Butanol	6	5
Butyl Cellosolve	3	0
Amyl Alcohol	1	0
Dowanol PNB ¹	0	5
TERGITOL 15-S-7 ²	0	1
Deionized Water	28	24
Formulation Solids, %	20	21
Viscosity, No. 4 Ford cup	20 sec	30 sec
VOC, kg/l – H ₂ O	0.358	0.358

¹ Commercially available from Dow Chemical.

² Commercially available surfactant from Dow Chemical.

- 5 These formulations were sprayed at typical laboratory conditions at 120 milligram per can (mg/can) to 130 mg/can coating weight for the application of interior beverage coatings, and cured at 188°C to 199°C (measured at the can dome) for 30 seconds through a gas oven conveyor at typical heat schedules for this application. The film properties shown in Table 15 were achieved.

Table 15: Inside Spray Film Properties

Example 4:	Run 1	Run 2
Metal Exposures		
Initial	2 mA	3 mA
After drop damage	2 mA	7 mA
MEK resistance	< 2	< 2
Water retort ¹		
Blush	None	None
Adhesion	Excellent	Excellent
Global extraction ²	0.25 ppm	3.8 ppm

¹ 90 minutes at 250°F (121°C).

² 2 hours at 150°F in 90% aqueous ethanol.

5 The cured films displayed excellent resistance properties and low global extractions despite the fact that their solvent resistance as determined by MEK rubs is low. The higher global extraction result for Example 4: Run 2 was determined to be due to the surfactant present.

10 Example 4: Runs 3-4. Spray Application

The water-based emulsion of Example 3: Run 4 and Example 3: Run 7 were successfully formulated into spray applied coatings for the interior of beer/beverage aluminum cans. Coating compositions are shown in Table 16.

15

Table 16: Inside Spray Coating Compositions

Example 4:	Run 3	Run 4
Composition (Parts)		
Example 3 Run 4	62.8	0
Example 3 Run 7	0	62.8
Deionized water	22.1	22.1
Butanol	5.9	5.3
Butyl Cellosolve	2.9	2.9
Amyl alcohol	1.3	1.3
Secondary butanol	0	0.5
Deionized water	5.0	5.1
Dimethyl ethanolamine	As Needed	As Needed
Formulation solids	20.7%	20.4%
Viscosity (No. 4 Ford cup)	20 sec	16 sec

These formulations were sprayed at typical laboratory conditions at 120 mg/can to 130 mg/can (12-ounce) coating weight for the application of interior beverage coatings, and cured at 188°C to 199°C (measured at the can dome) for 30 seconds through a gas oven conveyor at typical heat schedules for this application. The film properties shown in Table 17 were achieved, using a commercial epoxy-acrylate coating as a control.

Table 17: Inside Spray Film Properties

	Waterbased Control ¹	Example 4: Run 3	Example 4: Run 4
Coating weight, mg/can	124	123	121
Metal Exposures			
Initial	0.9 mA	2.2 mA	0.5 mA
After drop damage	1.3 mA	2.9 mA	1.2 mA
MEK Resistance	20 – 50	2 - 5	<1
Impact on Dome	10	10	10
Isopropanol Resistance	>100	>100	5 – 10
Water retort ²			
Blush	7	10	10
Adhesion	10	10	10
Joy Detergent Test			
Blush	7	10	10
Adhesion	10	10	10
Global extractions ³	<0.1 ppm ⁴	<0.1 ppm ⁴	<0.1 ppm ⁴

¹ Commercially available inside beverage can coating from Valspar coded 10Q45AF.

² 90 minutes at 250°F (121°C).

³ 2 hours at 150°F in 90% aqueous ethanol.

⁴ Below the current detection limit.

As can be seen in Table 17, the coatings of the present invention compare favorably to the commercial epoxy-acrylate coating, and there is a substantial benefit for retort resistance.

Example 5: Run 1. Beverage End Coil Coating

In a jar with an agitator, 483.25 parts of Example 3: Run 5 emulsion was stirred with 16.75 parts SLIPAYD 404 wax. The mixture was stirred for 10 minutes to make it uniform. The mixture was then filtered. The mixture was approximately 31% solids. The mixture was applied at 7-8 milligrams per square inch (msi) (1.1-1.25 mg/cm²) on ALX Alcoa aluminum and baked for 10 seconds (sec) to achieve a 400°F (204°C) peak metal temperature in a coil oven. It was also applied at 7-8 msi (1.1 – 1.25 mg/cm²) on ALX Alcoa aluminum and baked for 10 seconds to achieve a

435°F (224°C) peak metal temperature in a coil oven. Film properties are shown in Table 18.

Table 18: Beverage End Film Properties

	Waterbased Control ¹				Example 5 Run 1			
	10 sec to achieve 400°F (204°C)		10 sec to achieve 435°F (224°C)		10 sec to achieve 400°F (204°C)		10 sec to achieve 435°F (224°C)	
Bake								
MEK Res.	23		35		4		4	
Feathering ²	0.500		0.193		0.018		0.010	
Dowfax ³								
Blush	4		9		4		9	
Adhesion	10		10		10		10	
Pasteurization ⁴								
Blush	6		9		5		10	
Adhesion	10		10		10		10	
Water Retort ⁵								
Blush	6.5		10		5.5		10	
Adhesion	10		10		10		10	
End Continuities	Initial	After	Initial	After	Initial	After	Initial	After
Pasteurization ⁴	0.13	0.33	0.06	0.28	2.76	21.35	1.5	17.9
Water Retort ⁵	0.016	2.22	0.06	0.52	4.16	22.9	1.4	17.55

¹ Commercially available beverage end coating from Valspar coded 13Q80AG.

² Performed after a 45 minutes at 85°C (185°F) pasteurization. Measured in centimeters.

³ 15 minutes at 100°C (212°F).

⁴ 30 minutes at 85°C (185°F).

⁵ 90 minutes at 121°C (250°F).

10

Example 5: Runs 2-4 Beverage End Coatings

Using the process of Example 5: Run 1, the formulations shown in Table 19 were prepared to investigate the effect of GMA level on end continuities. Each formula was applied at 7-8 milligrams per square inch (msi) (1.1 – 1.25 mg/cm²) on ALX Alcoa aluminum and baked for 10 seconds to achieve a 420°F (215°C) peak metal temperature in a coil oven. End continuities are shown in Table 20.

15

Table 19: Effect of GMA Level

Example 5:	Run 2	Run 3	Run 4
Example 3 Run 5	95.7	0	0
Example 3 Run 34	0	95.7	0
Example 3 Run 35	0	0	95.7
Phenolic ¹	2.3	2.3	2.3
SLIPAYD 404	1.5	1.5	1.5
Michem Lube 160 PFE ²	0.5	0.5	0.5
Water/Solvent ³	To 23% Solids	To 23% Solids	--
Deionized Water	--	--	To 23% Solids

¹ A phenol-formaldehyde phenolic at 50% in water, prepared by reacting 2.3 moles of formaldehyde with 1 mole of phenol.

² Commercially available lubricant from Michelman Inc.

5 ³ 1:1 Blend of deionized water and isopropyl alcohol.

Table 20: Effect of GMA Level on Beverage End Performance

Example 5:	Run 2	Run 3	Run 4
GMA Level	4%	12%	20%
End Continuities			
Initial	2	49	149
After Retort ¹	21	193	304

¹ 90 minutes at 121°C (250°F).

10 As can be seen by the data in Table 20, lower GMA levels appear to provide better film integrity on fabricated ends, especially after a retort.

Example 5: Run 5 Beverage End Coating

15 Using the process of Example 5: Run 1, the formulation shown in Table 21 was prepared. The formula was applied at 7-8 milligrams per square inch (msi) (1.1-1.25 mg/cm²) on ALX Alcoa aluminum and baked for 10 seconds to achieve 400°F (204°C) and 420°F (215°C) peak metal temperatures in a coil oven. Film and end performance properties are shown in Table 22. This material contains 4% GMA

and 5% IBMA in the emulsion monomer mix and an acrylic composition with hydroxyl functionality.

Table 21: Beverage End Formulation

	Example 5 Run 5
Composition	
Example 3, Run 38	90.80
Dowanol PNP ¹	2.425
Dowanol DPNB ¹	2.425
Isooctyl Alcohol	1.54
Michem Lube 160 PFE	0.57
Lanco Glidd 5118 ²	2.24
Solids (%)	27.5 – 29.5
Viscosity (No. 4 Ford Cup)	20 sec – 30 sec

5 ¹ Commercially available from Dow Chemical

² Commercially available lubricant from Lubrizol Corp.

Table 22: Film Performance of Beverage End Formulation

	Water Base Control ¹				Example 5 Run 5			
Bake	10 sec to achieve 400°F (204°C)		10 sec to achieve 420°F (215°C)		10 sec to achieve 400°F (204°C)		10 sec to achieve 420°F (215°C)	
MEK Res.	34		40		10		8	
Feathering ⁴	0.178		0.094		0.074		0.038	
Pencil Hardness	3H – 4H		3H		HB		HB	
COF	0.068		0.076		0.068		0.075	
Pasteurization ²								
Blush	10		10		9		10	
Adhesion	10		10		10		10	
Water Retort ³								
Blush	9		10		8		9	
Adhesion	10		10		10		10	
End Continuities	Initial	After	Initial	After	Initial	After	Initial	After
Pasteurization ²	0.0	0.1	1.1	17.6	0.5	0.7	0.5	4.3
Water Retort ³	0.05	0.15	1.4	11.2	0.15	0.35	0.78	10.5

¹ Commercially available beverage end coating from Valspar coded 13Q80AG.

² 30 minutes at 85°C (185°F).

³ 90 minutes at 121°C (250°F).

5 ⁴ Performed after 45 minutes at 85°C (185°F) pasteurization. Measured in centimeters.

Results from Table 22 show that a beverage end formulation of the present invention can give similar performance to a commercial epoxy-based waterborne beverage end coating even with lower solvent resistance as measured by MEK double rubs. There is also an added benefit of improved feathering resistance.

Example 6: Latex with Polyester Stabilizer

Example 6 is designed to illustrate the use of a different acid-functional polymer salt as the stabilizer for an emulsion of the present invention.

Stage A

A 2-liter flask was equipped with a stirrer, packed column, Dean Stark trap, reflux condenser, thermocouple, heating mantle and nitrogen blanket. To the flask 700.1 parts dipropylene glycol and 700.1 parts isophthalic acid were added. Under a
5 nitrogen blanket, the contents were heated to 125°C. At 125°C, 1.05 parts FASCAT 4201 was added. The temperature was increased to remove water. At 210°C, water was beginning to collect. After an acid number of 5.2 was obtained, 37 parts of xylene was added to aid in the removal of water. An acid number of 0.9 was obtained, and a portion of the product was used in Stage B.

10

Stage B

The material from Stage A (599.8 parts) was placed in a 2-liter flask. The temperature was set at 112°C and 82 parts trimellitic anhydride was added. The material was heated to 232°C, and water was removed. After an acid number of 48.4
15 was obtained, a portion of the material was used in Stage C.

Stage C

The material from Stage B (198.8 parts) was added to a 2-liter flask, and 40 parts of DOWANOL PNP were added. The material was adjusted to 74°C, and slow
20 addition of deionized water (200 parts) was initiated. After about 30 parts of water were added, 7.6 parts dimethyl ethanolamine were introduced. When about 150 parts of the deionized water were in, heating was halted (the temperature was at 80°C) and 2.4 parts dimethyl ethanolamine were added. After the entire charge of deionized water was complete, the viscosity was visually high and 200 additional parts
25 deionized water was added. The material was allowed to slowly cool while additional dimethyl ethanolamine was added incrementally to increase the pH to 6.6. The resulting product was 29.7% solids with an acid number of 53.9.

Stage D

30 A 500-milliliter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Into the flask was added 93.2 parts of the Stage C material and 179 parts deionized water. While the contents of the flask were being heated to 50°C at 240 RPM, 2 drops of HAMP-OL 4.5% Iron

and 1.11 parts erythorbic acid were added. In a separate vessel a premix of 28.8 parts styrene, 50.9 BA, 21.0 parts BMA, 5.6 parts IBMA, 4.5 parts GMA and 1.11 parts TRIGONOX A-W70 were premixed. Once the flask was at 52°C, 10% of the premix was added and held for five minutes. After five minutes, the temperature control was set for 50°C and the remaining premix was added over one hour. When the addition was complete, 15.0 parts deionized water was used to rinse the residual premix into the flask. The batch was then held for two hours at temperature, and the batch was cooled. This yielded an emulsion at 34.0% solids, 14.5 acid number, pH of 5.45, and a viscosity 11.5 sec (Number 4 Ford Cup).

Stage E

To 50 parts of the emulsion from Stage D, 3.125 parts of a 50/50 blend of ethylene glycol and butyl cellosolve was added. This material was applied to chrome treated aluminum panels and baked for 10 seconds to achieve a 420°F (217°C) peak metal temperature. Results from beverage end testing of this example versus a commercial control formula are shown in Table 23.

Table 23:

	Waterbased Control ¹	Example 6
MEK Resistance	22	11
Feathering ⁴	0.102	0.013
Pasteurization ²		
Blush	10	9.5
Adhesion	10	10
Water Retort ³		
Blush	10	10
Adhesion	10	10
End Continuity		
Initial	1.35	0.25
Pasteurization ²	2.38	1.35

¹ Commercially available beverage end coating from Valspar coded 13Q80AG.

² 30 minutes at 85°C (185°F).

³ 90 minutes at 121°C (250°F).

⁴ Performed after 45 minutes at 85°C (185°F) pasteurization. Measured in centimeters.

Example 7: Emulsion for Inside Spray

5 A 3-liter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Into the flask was added 392.2 parts of Example 1: Run 4 Acid Functional Acrylic, 86.4 parts deionized water, 34.6 parts DMEA, and 1120.8 parts deionized water. The contents of the flask were heated to 70°C. In a separate vessel a premix of 215.8 parts styrene, 302.7 parts butyl acrylate, 10 and 42.0 parts glycidyl methacrylate was prepared. Once the flask was at 70°C, 5.5 parts benzoin and 27.8 parts deionized water was added, followed by 10% of the premix. The flask was heated further to 79°C and when this temperature was reached 5.5 parts of 35% hydrogen peroxide and 27.8 parts deionized water were added and held for five minutes. The flask was stirred at 210 rpm. After five minutes the 15 temperature control was set at 81°C and the remaining premix was added over one hour. When the addition was complete, 55.9 parts deionized water were used to rinse the residual premix into the flask. The batch was held for ten minutes and then 0.96 parts benzoin, 55.9 parts deionized water, and 0.95 parts 35% hydrogen peroxide were added. The batch was held for 45 minutes and then 0.31 parts benzoin and 0.31 20 part 35% hydrogen peroxide were added. After two hours the batch was cooled to 45°C. Once at 45°C, 0.46 part of HAMP-OL 4.5% Iron 2.98 parts TRIGONOX A-W70, and a premix of 2.1 parts erythorbic acid, 0.91 parts DMEA, and 18.0 parts deionized water, were added. The batch was held at 45°C for one hour. The material was then cooled to give an emulsion at 31.6% solids, 67.7 acid number, pH of 7.04, 25 and a viscosity of 84 seconds (Number 4 Ford cup).

Example 8: Spray Application

 The water-based emulsion of Example 7 was successfully formulated into a spray applied coating for the interior of beer/beverage aluminum cans. The product 30 was formulated as described in Table 24.

Table 24	
Beverage Inside Spray Coating Composition	
Composition (parts)	Example 8
Example 7 material	62.8
Deionized Water	25.3
Butyl Cellosolve	5.1
Amyl Alcohol	3.1
Butanol	0.7
Deionized Water	3.0
Additional Deionized Water to 18.5% Solids	
Formulation Solids, %	18.5%
Viscosity, No. 4 Ford cup	46 Seconds

5 This formulation was sprayed at typical laboratory conditions at 120 milligram per can (mg/can) to 130 mg/can coating weight for the application of interior beverage coatings, and cured at 188°C to 199°C (measured at the can dome) for 30 seconds through a gas oven conveyor at typical heat schedules for this application. The film properties shown in Table 25 were achieved.

Table 25		
Inside Spray Film Properties		
	Water-based Control ¹	Example 8
Metal Exposures		
Initial	2 mA	1 mA
After drop damage	2 mA	5 mA
Water retort ²		
Blush	None	None
Adhesion	Excellent	Excellent

¹ Commercially available inside beverage can coating from Valspar coded 10Q45AF.

² 90 minutes at 250°F (121°C)

10

As can be seen in Table 25, the coatings of the present invention compare favorably to the commercial epoxy-acrylate coating

Example 9: Latex with Polyester-Polyether Stabilizer

Example 9 illustrates the use of a different acid-functional polymer salt as the stabilizer for an emulsion of the present invention.

5 Stage A

A flask was equipped with a stirrer, packed column, Dean Stark trap, reflux condenser, thermocouple, heating mantle and nitrogen blanket. To the flask, 809.8 parts sebacic acid and 1283.0 parts CHDM-90 (90% 1,4-cyclohexane dimethanol in water) were added. Under a nitrogen blanket, the contents were heated to distill the
10 water from the CHDM-90. While the contents were heated at 165°C, 1.96 parts FASCAT 4100 was added. The temperature was increased to 220°C to remove water. A sample of the batch was tested and found to have an acid number of 0.5. The remainder of the batch was weighed, and to 1711.7 parts of this material were added 1040.2 parts of para-hydroxy benzoic acid. The batch was heated to 230°C to
15 remove water. To aid in the removal of water xylene was added incrementally. After two days of water removal, 1.04 parts FASCAT 4100 was added to aid in the reaction. The reaction was held an additional 5 hours and then considered complete. A portion of the product was used in Stage B.

20 Stage B

The material from Stage A (1915.2 parts) was placed in a flask along with 823.8 parts ERISYS GE-22 (cyclohexanedimethanol diglycidyl ether, , 84.8 parts methyl isobutyl ketone (, and 2.63 parts Catalyst 1201 (ethyltriphenyl phosphonium iodide,). The temperature was set at 170°C and the contents heated. After three
25 hours at temperature, the epoxy value of the material was 0.003. The batch was adjusted to have 2684.2 parts of this material in the flask. Added to the flask were 145.0 parts methyl isobutyl ketone and 294.7 parts succinic anhydride. The temperature was maintained at 120-135°C for two hours. After the two-hour hold, 124.8 parts deionized water and a premix of 214.2 parts DMEA with 265.8 parts
30 deionized water were added. Then 6325.8 parts deionized water was added. The material was cooled resulting in a product with 26.4% solids, an acid number of 71.9, a pH of 7.7, and a Number 4 Ford viscosity of 15 seconds. This material was used in Stage C.

Stage C

A 5-liter flask was equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Into the flask was added 1183.4 parts of the Stage B material and 779.6 parts deionized water. A premix of 7.25 parts erythorbic acid, 6.5 parts DMEA, and 76.7 parts deionized water was prepared. This initial premix and 0.18 parts HAMP-OL 4.5% Iron were added to the flask. The contents of the flask were heated to 30°C. In a separate vessel a monomer premix of 249.0 parts styrene, 113.8 BA, 106.7 parts BMA, 177.8 parts Hydroxy Ethyl Methacrylate (HEMA), 35.6 parts IBMA, and 28.5 parts GMA was prepared. A third premix of 7.25 parts TRIGONOX A-W70 and 82.2 parts deionized water were made. Once all the premixes were prepared and the flask at 30°C, the stirrer was set at 240 rpm and all of the monomer premix was added. The monomer premix vessel was rinsed with 81.6 parts deionized water, which was also added to the flask. The contents of the flask were stirred for 10 minutes, after which 10% of the third premix was added within one minute. Once the 10% of the third premix was in, the temperature was increased to 37°C and the batch was held for five minutes. After five minutes, the remaining amount of the third premix was added over 45 minutes. The temperature was allowed to increase with no external heat applied. During the addition the maximum temperature was 57°C. After the addition was complete the temperature was 51°C. Temperature control was set for 52°C. The third premix was rinsed with 108.4 parts deionized water and added to the batch. The batch was held for 1.5 hours and then cooled. This yielded an emulsion at 33.1% solids, 27.1 acid number, pH of 7.9, and a viscosity 12 sec (Number 4 Ford Cup).

Stage D

To 1473.75 parts of the emulsion from Stage C, 26.25 parts DMEOA were added to increase the pH to 8.6. Using 1330.18 parts of this increased pH material, 89.51 parts ethylene glycol, 16.65 parts dibasic ester, 16.67 parts DOWANOL PM, 5.17 parts xylene, 17.5 parts of a 50% solids solution of a phenol-formaldehyde phenolic, and 24.57 parts MICHEM 160 PFE were added. This formulation was determined to be 30.1% solids, 12 seconds Number 4 Ford viscosity and 8.75 pounds per gallon (1.05 kg/l).

The Stage D composition was applied to non-chrome aluminum panels and baked for 10 seconds to achieve a 420°F (215°C) peak metal temperature. A second set was baked for 10 seconds to achieve a 440°F (227°C) peak metal temperature. Results from beverage end testing of this example versus a commercial water base and solvent base control formulas are shown in Tables 26 and 27.

Table 26						
Comparative Testing of Example 9 Stage D Cured at 420°F (215°C)						
	Water-based Control ¹		Solvent-based Control ²		Example 9 Stage D	
MEK	44		34		38	
Feathering ³	0.0457		0.0457		0.000	
COF	0.061		0.066		0.063	
Pasteurization ⁴						
Blush	10		10		8 to 9 ⁶	
Adhesion	10		10		10	
Water Retort ⁵						
Blush	10		10		4 to 10 ⁶	
Adhesion	10		10			
End Continuity	Initial	After	Initial	After	Initial	After
Pasteurization	0.08	0.12	0.0	0.30	0.0	0.5
Water Retort	0.10	0.4	0.02	0.72	0.27	1.2

¹ Commercially available beverage end coating from Valspar coded 13Q80AG.

² Commercially available beverage end coating from Valspar coded 92X205S.

³ Performed after 45 minutes at 85°C (185°F) pasteurization. Measured in centimeters (cm).

⁴ 30 minutes at 85°C (185°F).

⁵ 90 minutes at 121°C (250°F).

⁶ Initial Blush seen which improves within 5 minutes.

Table 27						
Comparative Testing of Example 9 Stage D Cured at 440°F (227°C)						
	Water-based Control ¹		Solvent-based Control ²		Example 9 Stage D	
MEK	52		37		40	
Feathering ³	0.0559		0.0356		0.000	
COF	0.059		0.065		0.063	
Pasteurization ⁴						
Blush	10		10		8 to 10 ⁶	
Adhesion	10		10		10	
Water Retort ⁵						
Blush	10		10		6 to 10 ⁶	
Adhesion	10		10			
End Continuity	Initial	After	Initial	After	Initial	After
Pasteurization	0.0	0.48	0.07	0.23	0.1	0.8
Water Retort	0.05	0.4	0.25	1.5	0.35	0.8

¹ Commercially available beverage end coating from Valspar coded 13Q80AG.

² Commercially available beverage end coating from Valspar coded 92X205S.

³ Performed after 45 minutes at 85°C (185°F) pasteurization. Measured in cm.

⁴ 30 minutes at 85°C (185°F).

⁵ 90 minutes at 121°C (250°F).

⁶ Initial Blush seen which improves within 5 minutes.

Example 10

Example 10 illustrates the use of a different acid-functional polymer salt as the stabilizer for an emulsion of the present invention.

Stage 1

Approximately 1055 parts BPA is placed in a flask along with approximately 1684 parts of liquid epoxy resin (EPON 828), 85 parts methyl isobutyl ketone, and 2 to 3 parts Catalyst 1201. The temperature is set at 160°C and the contents are then heated for approximately three hours to achieve an epoxy value of the material of approximately 0.003. The batch is then adjusted to have 2684.2 parts of this material in the flask. Added to the flask is 145.0 parts methyl isobutyl ketone and 294.7 parts succinic anhydride. The temperature is maintained at 120-135°C for two

hours. After the two-hour hold, 124.8 parts deionized water and a premix of 214.2 parts DMEA with 265.8 parts deionized water is added. Then 6325.8 parts deionized water is added. The material is cooled, and should result in a product with target values of 26% to 27% solids, an acid number of approximately 72, a pH of approximately 7 to 9, and a Number 4 Ford viscosity of 15 Seconds. This material is used in Stage 2.

Stage 2

A 5-liter flask is equipped with a stirrer, reflux condenser, thermocouple, heating mantle, and nitrogen blanket. Into the flask is added approximately 1183 parts of the Stage 1 material and 780 parts deionized water. A premix of 7.25 parts erythorbic acid, 6.5 parts DMEA, and 77 parts deionized water is prepared. This initial premix and 0.18 parts HAMP-OL 4.5% Iron are added to the flask. The contents of the flask are heated to 30°C. In a separate vessel a monomer premix of 249 parts styrene, 114 BA, 107 parts BMA, 178 parts HEMA, 36 parts IBMA, and 28 parts GMA is prepared. A third premix of 7.25 parts TRIGONOX A-W70 and 82.2 parts deionized water is made. Once all the premixes are prepared and the flask is at 30°C, the stirrer is set at 240 rpm and all of the monomer premix is added. The monomer premix vessel is rinsed with 82 parts deionized water, which is also added to the flask. The contents of the flask are stirred for 10 minutes, after which 10% of the third premix is added within one minute. Once the 10% is in the temperature is increased to 37°C. The batch is held for five minutes. After five minutes, the remaining amount of the third premix is added over 45 minutes. The temperature is allowed to increase with no external heat applied. During the addition the maximum temperature is 57 °C. After the addition is complete the temperature is set for 52 °C. The third premix is rinsed with 109 parts deionized water and added to the batch. The batch is held for 1.5 hours and cooled. This process should yield an emulsion with a target of approximately 33 % solids, 27 acid number, pH of 8, and a viscosity of 12 sec (Number 4 Ford Cup).

30

79713-5

Stage 3

To 1474 parts of the emulsion from Stage 2, 26.25 parts DMEOA is added to increase the pH to 8.6. Using 1330.18 parts of this increased pH material, 89.51 parts ethylene glycol, 16.65 parts dibasic ester, 16.67 parts Dowanol PM, 5.17 parts xylene, 17.5 parts of a 50% solids solution of a phenol-formaldehyde phenolic, and 24.57 parts Michem 160 PFE is added. This formulation should yield a composition having approximately 30% solids.

The Stage 3 composition may be applied to non-chrome aluminum panels and baked for 10 seconds to achieve a 217°C peak metal temperature.

10

Various modifications and alterations to this invention will become apparent to those skilled in the art without departing from the scope of this invention. It should be understood that this invention is not intended to be unduly limited by the illustrative embodiments and examples set forth herein and that such examples and embodiments are presented by way of example only with the scope of the invention intended to be limited only by the claims set forth herein as follows.

20

79713-5

CLAIMS:

1. An article comprising: a body portion or an end portion of a food or beverage can comprising a metal substrate; and

a coating composition disposed on an inside surface thereof, wherein the
5 coating composition includes an emulsion polymerized latex polymer, and wherein the emulsion polymerized latex polymer:

(i) comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a polymer salt, wherein the ethylenically unsaturated monomer component includes at least one oxirane functional
10 group-containing monomer and wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic compound; and

(ii) is substantially free of bound bisphenol A and aromatic glycidyl ether compounds.

2. The article of claim 1, wherein the coating composition comprises a cured
15 coating composition.

3. The article of claim 1, wherein the ethylenically unsaturated monomer component comprises a mixture of monomers that includes at least one oxirane functional group-containing alpha, beta-ethylenically unsaturated monomer in an amount of 0.1 wt-% to 30 wt-%, based on the weight of the monomer mixture.

20 4. The article of claim 1, wherein the polymer salt comprises an acrylic polymer, a polyurethane polymer, a polyester resin, an alkyd resin, or a combination thereof.

5. The article of claim 1, wherein the polymer salt comprises a salt of an acid- or anhydride-functional acrylic polymer.


6. The article of claim 1, wherein the polymer salt comprises a salt of an acid- or
25 anhydride-functional polymer and an amine.

79713-5

7. The article of claim 1, wherein the polymer salt comprises a salt of an acid- or anhydride-functional acrylic polymer, acid- or anhydride-functional polyurethane polymer, acid- or anhydride-functional polyester resin, acid- or anhydride-functional alkyd resin, or a combination thereof.

5 8. The article of claim 1, wherein the polymer salt comprises a salt of an amine and an acid- or anhydride-functional acrylic polymer, acid- or anhydride-functional polyurethane polymer, acid- or anhydride-functional polyester resin, acid- or anhydride-functional alkyd resin, or a combination thereof.

9. The article of claim 1, wherein the polymer salt comprises a polyester resin
10 having one or more segments of Formula I:



wherein:

each Ar is independently a divalent aryl group or heteroarylene group;

each R is independently a divalent organic group;

15 R^1 is a divalent organic group; and

each n is 0 or 1.

10. The article of claim 1, wherein the polymer salt has a number average molecular weight of 1,500 to 50,000.

11. The article of claim 1, wherein the polymer salt is present in an amount
20 comprising at least 5% by weight, based on the total weight of the ethylenically unsaturated monomer component and the polymer salt.

12. The article of claim 1, wherein the ethylenically unsaturated monomer component is polymerized in the presence of the aqueous dispersion with a water-soluble free radical initiator at a temperature of 0°C. to 100°C.

79713-5

13. The article of claim 1, wherein the ethylenically unsaturated component comprises at least about 25 weight percent of the emulsion polymerized latex polymer, based on the total weight of the ethylenically unsaturated monomer component and the polymer salt.

14. The article of claim 1, wherein the coating composition is substantially free of
5 bound bisphenol A and aromatic glycidyl ether compounds.

15. The article of claim 1, wherein the coating composition, when present on a beverage can end at a dry film thickness of 7 milligrams per square inch, passes less than 10 milliamps of current after being exposed for 4 seconds to a room-temperature electrolyte solution containing 1% by weight of NaCl dissolved in water.

10 16. The article of claim 1, wherein the emulsion polymerized latex polymer consists essentially of the reaction product of the ethylenically unsaturated monomer component polymerized in the presence of the aqueous dispersion of the polymer salt, and wherein the polymer salt comprises a salt of an amine and an acid- or anhydride-functional polymer.

15 17. An article comprising:

a body portion or an end portion of a food or beverage can comprising a metal substrate; and

a coating composition disposed on an inside surface thereof, wherein the coating composition includes an emulsion polymerized latex polymer, and wherein the
20 emulsion polymerized latex polymer:

(i) comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a salt of an acid or anhydride-functional polymer and a tertiary amine, wherein the ethylenically unsaturated monomer component comprises 0.1 wt-% to 30 wt-% of an oxirane-functional alpha, beta-
25 ethylenically unsaturated monomer, based on the weight of the monomer component and wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic compound; and

79713-5

(ii) is substantially free of bound bisphenol A and aromatic glycidyl ether compounds.

18. A method, comprising:

providing a coating composition including an emulsion polymerized latex
5 polymer, wherein the emulsion polymerized latex polymer:

(i) comprises a reaction product of an ethylenically unsaturated monomer
component polymerized in the presence of an aqueous dispersion of a polymer, wherein the
ethylenically unsaturated monomer component includes at least one oxirane functional-group
containing monomer and wherein the ethylenically unsaturated monomer component
10 comprises a vinyl aromatic compound, and

(ii) is substantially free of bound bisphenol A and aromatic glycidyl ether
compounds; and applying the coating composition to a surface of a metal substrate prior to or
after forming the metal substrate into a food or beverage can or portion thereof, wherein the
surface of the metal substrate coated by the coating composition is an inside surface.

15 19. The method of claim 18, wherein:

the water-dispersible polymer comprises a salt of an acid- or anhydride-
functional polymer and a tertiary amine; and

the ethylenically unsaturated monomer component comprises 0.1 wt-% to
30 wt-% of an oxirane-functional alpha, beta-ethylenically unsaturated monomer, based on the
20 weight of the monomer component.

20. The article of claim 1, wherein the ethylenically unsaturated monomer
component comprises a vinyl aromatic component that is at least 20-wt% of the ethylenically
unsaturated monomer component, and wherein the vinyl aromatic component comprises one
or more vinyl aromatic compounds.

25 21. The method of claim 18, wherein the ethylenically unsaturated monomer
component comprises a vinyl aromatic component that is at least 20-wt% of the ethylenically

79713-5

unsaturated monomer component, and wherein the vinyl aromatic component comprises one or more vinyl aromatic compounds.

22. The article of claim 1, wherein the ethylenically unsaturated monomer component comprises a mixture of monomers that includes at least one oxirane functional group-containing monomer in an amount of 0.1 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

23. The article of claim 22, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

24. The article of claim 23, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 9 wt-%, based on the weight of the ethylenically unsaturated monomer component.

25. The article of claim 24, wherein the at least one oxirane functional group-containing monomer is present in an amount of at least 6 wt-% but less than 8 wt-%, based on the weight of the ethylenically unsaturated monomer component.

26. The method of claim 18, wherein the ethylenically unsaturated monomer component comprises a mixture of monomers that includes at least one oxirane functional group-containing monomer in an amount of 0.1 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

27. The method of claim 26, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

28. The method of claim 27, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 9 wt-%, based on the weight of the ethylenically unsaturated monomer component.

79713-5

29. The method of claim 28, wherein the at least one oxirane functional group-containing monomer is present in an amount of at least 6 wt-% but less than 8 wt-%, based on the weight of the ethylenically unsaturated monomer component.

30. The article of claim 20, wherein the ethylenically unsaturated monomer component comprises a mixture of monomers that includes at least one oxirane functional group-containing monomer in an amount of 0.1 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

31. The article of claim 30, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

32. The article of claim 31, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 9 wt-%, based on the weight of the ethylenically unsaturated monomer component.

33. The article of claim 32, wherein the at least one oxirane functional group-containing monomer is present in an amount of at least 6 wt-% but less than 8 wt-%, based on the weight of the ethylenically unsaturated monomer component.

34. The method of claim 21, wherein the ethylenically unsaturated monomer component comprises a mixture of monomers that includes at least one oxirane functional group-containing monomer in an amount of 0.1 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

35. The method of claim 34, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

36. The method of claim 35, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 9 wt-%, based on the weight of the ethylenically unsaturated monomer component.

79713-5

37. The method of claim 36, wherein the at least one oxirane functional group-containing monomer is present in an amount of at least 6 wt-% but less than 8 wt-%, based on the weight of the ethylenically unsaturated monomer component.

38. The article of claim 1, wherein the at least one oxirane functional group-
5 containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

39. The method of claim 18, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

10 40. The article of claim 20, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

41. The method of claim 21, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl
15 methacrylate and glycidyl acrylate.

42. The article of claim 22, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

43. The article of claim 23, wherein the at least one oxirane functional group-
20 containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

44. The article of claim 24, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

79713-5

45. The article of claim 25, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

46. The method of claim 26, wherein the at least one oxirane functional group-
5 containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

47. The method of claim 27, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

10 48. The method of claim 28, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

49. The method of claim 29, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl
15 methacrylate and glycidyl acrylate.

50. The article of claim 30, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

51. The article of claim 31, wherein the at least one oxirane functional group-
20 containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

52. The article of claim 32, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

79713-5

53. The article of claim 33, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

54. The method of claim 34, wherein the at least one oxirane functional group-
5 containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

55. The method of claim 35, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

10 56. The method of claim 36, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

57. The method of claim 37, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl
15 methacrylate and glycidyl acrylate.

58. The article of claim 20, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

59. The method of claim 21, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

20 60. The article of claim 30, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

61. The article of claim 31, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

62. The article of claim 32, wherein the ethylenically unsaturated monomer
25 component comprises at least 20 wt-% styrene.

79713-5

63. The article of claim 33, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

64. The method of claim 34, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

5 65. The method of claim 35, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

66. The method of claim 36, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

10 67. The method of claim 37, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

68. The article of claim 40, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

69. The method of claim 41, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

15 70. The article of claim 50, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

71. The article of claim 51, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

20 72. The article of claim 52, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

73. The article of claim 53, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

74. The method of claim 54, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

79713-5

75. The method of claim 55, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

76. The method of claim 56, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

5 77. The method of claim 57, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

78. The article of claim 6, wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic component that is at least 20 wt-% of the ethylenically unsaturated monomer component, and wherein the vinyl aromatic component comprises one
10 or more vinyl aromatic compounds.

79. The article of claim 6, wherein the ethylenically unsaturated monomer component comprises a mixture of monomers that includes at least one oxirane functional group-containing monomer in an amount of 0.1 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

15 80. The article of claim 79, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

81. The article of claim 80, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 9 wt-%, based on the
20 weight of the ethylenically unsaturated monomer component.

82. The article of claim 81, wherein the at least one oxirane functional group-containing monomer is present in an amount of at least 6 wt-% but less than 8 wt-%, based on the weight of the ethylenically unsaturated monomer component.

83. The article of claim 78, wherein the ethylenically unsaturated monomer
25 component comprises a mixture of monomers that includes at least one oxirane functional

79713-5

group-containing monomer in an amount of 0.1 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

84. The article of claim 83, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 30 wt-%, based on the
5 weight of the ethylenically unsaturated monomer component.

85. The article of claim 84, wherein the at least one oxirane functional group-containing monomer is present in an amount of more than 5 wt-% to 9 wt-%, based on the weight of the ethylenically unsaturated monomer component.

86. The article of claim 85, wherein the at least one oxirane functional group-
10 containing monomer is present in an amount of at least 6 wt-% but less than 8 wt-%, based on the weight of the ethylenically unsaturated monomer component.

87. The article of claim 78, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

88. The article of claim 83, wherein the ethylenically unsaturated monomer
15 component comprises at least 20 wt-% styrene.

89. The article of claim 84, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

90. The article of claim 85, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

20 91. The article of claim 86, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene.

92. The article of claim 85, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

79713-5

93. The article of claim 89, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

94. The article of claim 86, wherein the at least one oxirane functional group-
5 containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

95. The article of claim 87, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

10 96. The article of claim 78, wherein the amine is a tertiary amine.

97. The article of claim 83, wherein the amine is a tertiary amine.

98. The article of claim 84, wherein the amine is a tertiary amine.

99. The article of claim 85, wherein the amine is a tertiary amine.

100. The article of claim 86, wherein the amine is a tertiary amine.

15 101. The article of claim 93, wherein the amine is a tertiary amine.

102. The article of claim 96, wherein the at least one oxirane functional group-containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

103. The article of claim 20, wherein the polymer salt comprises an acrylic polymer.

20 104. The article of claim 20, wherein the polymer salt comprises a polyurethane polymer, a polyester resin, an alkyd resin, or a combination thereof.

105. The method of claim 21, wherein the polymer comprises an acrylic polymer.

79713-5

106. The method of claim 21, wherein the polymer comprises a polyurethane polymer, a polyester resin, an alkyd resin, or a combination thereof.

107. The article of claim 6, wherein the polymer salt comprises an acrylic polymer.

108. The article of claim 6, wherein the polymer salt comprises a polyurethane
5 polymer, a polyester resin, an alkyd resin, or a combination thereof.

109. The article of claim 78, wherein the polymer salt comprises an acrylic polymer.

110. The article of claim 78, wherein the polymer salt comprises a polyurethane polymer, a polyester resin, an alkyd resin, or a combination thereof.

111. A method of coating an inside surface of a food or beverage can, the method
10 comprising:

forming a composition comprising an emulsion polymerized latex polymer,
comprising:

forming a salt of an acid- or anhydride-functional polymer and an amine in a
carrier comprising water to form an aqueous dispersion;

15 combining an ethylenically unsaturated monomer component with the aqueous
dispersion; wherein the ethylenically unsaturated monomer component includes at least one
oxirane functional group containing monomer and wherein the ethylenically unsaturated
monomer component comprises a vinyl aromatic compound; and

polymerizing the ethylenically unsaturated monomer component in the
20 presence of the aqueous dispersion to form an emulsion polymerized latex polymer that is
substantially free of bound bisphenol A and aromatic glycidyl ether compounds; and

applying the composition comprising the emulsion polymerized latex polymer
to a metal substrate on an inside surface side prior to or after forming the metal substrate into
a food or beverage can or portion thereof.

79713-5

112. The method of claim 111 wherein applying the composition to a metal substrate comprises applying the composition to the metal substrate in the form of a planar coil or sheet, hardening the emulsion polymerized latex polymer, and forming the substrate into a food or beverage can or portion thereof.

5 113. The method of claim 112 wherein forming the substrate into a can or portion thereof comprises forming the substrate into a can end or a can body.

114. The method of claim 112 wherein the can is a 2-piece drawn food can, 3-piece food can, food can end, drawn and ironed can, or beverage can end.

115. The method of claim 111 wherein the metal substrate comprises steel or
10 aluminum.

116. The method of claim 111 wherein applying the composition to a metal substrate comprises applying the composition to the metal substrate after the metal substrate is formed into a can or portion thereof.

117. The method of claim 111 wherein combining an ethylenically unsaturated
15 monomer component with the aqueous dispersion comprises adding the ethylenically unsaturated monomer component to the aqueous dispersion.

118. The method of claim 117 wherein the ethylenically unsaturated monomer component is added incrementally to the aqueous dispersion.

119. The method of claim 111 wherein the at least one oxirane functional group
20 containing monomer is present in an amount of more than 5 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

120. The method of claim 119 wherein the at least one oxirane functional group containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

25 121. The method of claim 120 wherein the mixture of monomers comprises at least one oxirane functional group-containing alpha, beta-ethylenically unsaturated monomer.

79713-5

122. The method of claim 120 wherein the oxirane functional group-containing monomer is present in the ethylenically unsaturated monomer component in an amount of at least 0.1 wt-%, based on the weight of the monomer mixture.

123. The method of claim 120 wherein the oxirane functional group-containing
5 monomer is present in the ethylenically unsaturated monomer component in an amount of no greater than 30 wt-%, based on the weight of the monomer mixture.

124. The method of claim 111 further comprising combining the emulsion
polymerized latex polymer with one or more crosslinkers, fillers, catalysts, dyes, pigments,
toners, extenders, lubricants, anticorrosion agents, flow control agents, thixotropic agents,
10 dispersing agents, antioxidants, adhesion promoters, light stabilizers, organic solvents,
surfactants, or combinations thereof in the coating composition.

125. The method of claim 111 wherein the acid- or anhydride-functional polymer has a number average molecular weight of 1500 to 50,000.

126. The method of claim 111 wherein the composition is substantially free of
15 mobile bisphenol A and aromatic glycidyl ether compounds.

127. The method of claim 126 wherein the composition is substantially free of bound bisphenol A and aromatic glycidyl ether compounds.


128. The method of claim 111 wherein the acid- or anhydride-functional polymer comprises an acid- or anhydride-functional acrylic polymer, acid- or anhydride-functional
20 alkyd resin, acid- or anhydride-functional polyester resin, acid- or anhydride-functional polyurethane, or combinations thereof.

129. The method of claim 128 wherein the acid- or anhydride-functional polymer comprises an acid-functional acrylic polymer.

130. The method of claim 128 wherein the acid- or anhydride-functional polymer
25 comprises a polyester polymer.

79713-5

131. The method of claim 130 wherein the polyester polymer comprises one or more segments of Formula I:



wherein: each Ar is independently a divalent aryl group or heteroarylene

5 group;

each R is independently a divalent organic group;

R¹ is a divalent organic group; and

each n is 0 or 1.

132. The method of claim 111 wherein the amine is a tertiary amine.

10 133. The method of claim 132 wherein the tertiary amine is selected from the group consisting of trimethyl amine, dimethylethanol amine, methyldiethanol amine, triethanol amine, ethyl methyl ethanol amine, dimethyl ethyl amine, dimethyl propyl amine, dimethyl 3-hydroxy-1-propyl amine, dimethylbenzyl amine, dimethyl 2-hydroxy-1-propyl amine, diethyl methyl amine, dimethyl 1-hydroxy-2-propyl amine, triethyl amine, tributyl amine,
15 N-methyl morpholine, and mixtures thereof.

134. The method of claim 111 wherein the acid- or anhydride-functional polymer is at least 25% neutralized with the amine in water.

135. The method of claim 111 wherein the ethylenically unsaturated monomer component is polymerized in the presence of the aqueous dispersion with a water-soluble free
20 radical initiator at a temperature of 0° C. to 100° C.

136. The method of claim 135 wherein the free radical initiator comprises a peroxide initiator.

137. The method of claim 135 wherein the free radical initiator comprises hydrogen peroxide and benzoin.

79713-5

138. The method of claim 135 wherein the free radical initiator comprises a redox initiator system.

139. The method of claim 111 wherein the aqueous dispersion further comprises an organic solvent.

5 140. The method of claim 139 further comprising removing at least a portion of the organic solvent prior to forming the emulsion polymerized latex polymer.

141. The method of claim 111, wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic component that is at least 20 wt-% of the ethylenically unsaturated monomer component, and wherein the vinyl aromatic component comprises one
10 or more vinyl aromatic compounds.

142. A method of coating an inside surface of a food or beverage can, the method comprising:

forming a composition comprising an emulsion polymerized latex polymer,
comprising:

15 forming a salt of an acid- or anhydride-functional polymer and a tertiary amine in a carrier comprising water to form an aqueous dispersion;

combining an ethylenically unsaturated monomer component comprising
0.1 wt-% to 30 wt-% of an oxirane-functional alpha, beta-ethylenically unsaturated monomer
with the aqueous dispersion, based on the weight of the monomer component, wherein the
20 ethylenically unsaturated monomer component comprises a vinyl aromatic compound; and

polymerizing the ethylenically unsaturated monomer component in the
presence of the aqueous dispersion to form an emulsion polymerized latex polymer; and

applying the composition comprising the emulsion polymerized latex polymer
to a metal substrate on an inside surface side prior to or after forming the metal substrate into
25 a food or beverage can or portion thereof.

79713-5

143. The method of claim 142, wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic component that is at least 20 wt-% of the ethylenically unsaturated monomer component, and wherein the vinyl aromatic component comprises one or more vinyl aromatic compounds.

5 144. The method of claim 143, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene, based on the weight of the ethylenically unsaturated monomer component.

145. The method of claim 142, wherein the oxirane-functional alpha, beta-ethylenically unsaturated monomer is present in an amount of more than 5 wt-%, based on the
10 weight of the ethylenically unsaturated monomer component.

146. The method of claim 145, wherein the oxirane-functional alpha, beta-ethylenically unsaturated monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

147. The method of claim 142, wherein the acid- or anhydride-functional polymer
15 comprises at least 15% methacrylic acid, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional polymer.

148. The method of claim 142, wherein the acid- or anhydride-functional polymer comprises styrene.

149. The method of claim 141, wherein the ethylenically unsaturated monomer
20 component comprises at least 20 wt-% styrene, based on the weight of the ethylenically unsaturated monomer component.

150. The method of claim 111, wherein the acid- or anhydride-functional polymer comprises at least 15% methacrylic acid, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional polymer.

25 151. The method of claim 111, wherein the acid- or anhydride-functional polymer comprises styrene.

79713-5

152. A method of coating an inside surface of a food or beverage can, the method comprising:

receiving a composition formulated for inside spraying comprising the output of a process, the process comprising forming a composition comprising an emulsion

5 polymerized latex polymer by:

forming a salt of an acid- or anhydride-functional polymer and an amine in a carrier comprising water to form an aqueous dispersion;

combining an ethylenically unsaturated monomer component with the aqueous dispersion; wherein the ethylenically unsaturated monomer component includes at least one

10 oxirane functional group containing monomer and wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic compound; and

polymerizing the ethylenically unsaturated monomer component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer that is substantially free of bound bisphenol A and aromatic glycidyl ether compounds; and

15 spray applying the composition comprising the emulsion polymerized latex polymer to a metal substrate on an inside surface side prior to or after forming the metal substrate into a food or beverage can or portion thereof.

153. The method of claim 152, wherein the ethylenically unsaturated monomer component comprises a vinyl aromatic component that is at least 20 wt-% of the ethylenically
20 unsaturated monomer component, and wherein the vinyl aromatic component comprises one or more vinyl aromatic compounds.

154. The method of claim 153, wherein the ethylenically unsaturated monomer component comprises at least 20 wt-% styrene, based on the weight of the ethylenically unsaturated monomer component.

79713-5

155. The method of claim 152, wherein at least one oxirane functional group containing monomer is present in an amount of more than 5 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

156. The method of claim 155, wherein the at least one oxirane functional group
5 containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.

157. The method of claim 152, wherein the acid- or anhydride-functional polymer comprises at least 15% methacrylic acid, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional polymer.

10 158. The method of claim 152, wherein the acid- or anhydride-functional polymer comprises styrene.

159. A method of coating an inside surface of a food or beverage can, the method comprising:

receiving a composition formulated for inside spraying comprising the output
15 of a process, the process comprising forming a composition comprising an emulsion polymerized latex polymer by:

forming a salt of an acid- or anhydride-functional polymer and an amine in a carrier comprising water to form an aqueous dispersion;

combining an ethylenically unsaturated monomer component with the aqueous
20 dispersion; wherein the ethylenically unsaturated monomer component comprises butyl acrylate; and

wherein the ethylenically unsaturated monomer component further comprises a vinyl aromatic compound; and

polymerizing the ethylenically unsaturated monomer component in the
25 presence of the aqueous dispersion to form an emulsion polymerized latex polymer that is substantially free of bound bisphenol A and aromatic glycidyl ether compounds; and

79713-5

spray applying the composition comprising the emulsion polymerized latex polymer to a metal substrate on an inside surface side prior to or after forming the metal substrate into a food or beverage can or portion thereof.

160. The method of claim 159, wherein the ethylenically unsaturated monomer
5 component comprises a vinyl aromatic component that is at least 20 wt-% of the ethylenically unsaturated monomer component, and wherein the vinyl aromatic component comprises one or more vinyl aromatic compounds.
161. The method of claim 160, wherein the ethylenically unsaturated monomer
10 component comprises at least 20 wt-% styrene, based on the weight of the ethylenically unsaturated monomer component.
162. The method of claim 159, wherein the ethylenically unsaturated monomer component comprises at least one oxirane functional group containing monomer present in an amount of more than 5 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.
- 15 163. The method of claim 162, wherein the at least one oxirane functional group containing monomer is glycidyl methacrylate, glycidyl acrylate or a mixture of glycidyl methacrylate and glycidyl acrylate.
164. The method of claim 159, wherein the acid- or anhydride-functional polymer
20 comprises at least 15 wt-% methacrylic acid, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional polymer.
165. The method of claim 159, wherein the acid- or anhydride-functional polymer comprises styrene.
166. The method of claim 111, wherein the acid- or anhydride-functional polymer
25 comprises more than 30 wt-% acid- or anhydride functional monomers, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional polymer.

79713-5

167. The method of claim 142, wherein the acid- or anhydride-functional polymer comprises more than 30 wt-% acid- or anhydride functional monomers, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional polymer.

5 168. The method of claim 152, wherein the acid- or anhydride-functional polymer comprises more than 30 wt-% acid- or anhydride functional monomers, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional polymer.

169. The method of claim 159, wherein the acid- or anhydride-functional polymer
10 comprises more than 30 wt-% acid- or anhydride functional monomers, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional polymer.

170. A method, comprising the steps of:

receiving a coating composition that includes an emulsion polymerized latex
15 polymer that comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a salt of an acid- or anhydride-functional polymer, wherein the ethylenically unsaturated monomer component includes an oxirane group-containing monomer, and wherein the coating composition is made without using PVC compounds, BPA, or aromatic glycidyl ether compounds; and

20 spray applying the coating composition onto an interior surface of an aluminum beverage can including a body portion and a bottom end portion.

171. The method of claim 170, wherein the salt of an acid- or anhydride-functional polymer comprises a salt of an acid- or anhydride-functional acrylic polymer.

172. The method of claim 171, further comprising curing the coating composition to
25 form a cured coating.

79713-5

173. The method of claim 172, wherein the cured coating exhibits a metal exposure of less than 2 mA on average when the can is filled with 1% NaCl in deionized water and tested pursuant to the Initial Metal Exposure test method disclosed herein.

174. The method of claim 172, wherein the cured coating exhibits a metal exposure
5 of less than 1 mA on average when the can is filled with 1% NaCl in deionized water and tested pursuant to the Initial Metal Exposure test method disclosed herein.

175. The method of claim 172, wherein the cured coating exhibits a global extraction result of less than 50 ppm.

176. The method of claim 172, wherein the cured coating exhibits a global
10 extraction result of less than 10 ppm.

177. The method of claim 172, wherein the cured coating exhibits a global extraction result of less than 1 ppm.

178. The method of claim 172, wherein the beverage can or a portion thereof includes a dome apex and the cured coating shows no craze after the outside of the dome apex
15 is subjected to a 12 in-lbs reverse impact.

179. The method of claim 172, wherein the cured coating exhibits no adhesion failure when tested pursuant to ASTM D-3359-Test method B after retort in deionized water for 90 minutes at a heat of 121°C and a corresponding pressure.

180. The method of claim 170, wherein the oxirane-group containing monomer is
20 present in an amount of 0.1 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

181. The method of claim 180, wherein the oxirane-group containing monomer is present in an amount of more than 5 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

79713-5

182. The method of claim 180, wherein the oxirane-group containing monomer is present in an amount of more than 5 wt-% to 9 wt-%, based on the weight of the ethylenically unsaturated monomer component.

183. The method of claim 170, wherein the oxirane group-containing monomer
5 comprises glycidyl methacrylate, glycidyl acrylate, or a mixture of glycidyl methacrylate and glycidyl acrylate.

184. The method of claim 181, wherein the oxirane group-containing monomer comprises glycidyl methacrylate, glycidyl acrylate, or a mixture of glycidyl methacrylate and glycidyl acrylate.

10 185. The method of claim 170, wherein the ethylenically unsaturated monomer component includes at least 20 wt-% of a vinyl aromatic compound.

186. The method of claim 170, wherein the ethylenically unsaturated monomer component includes at least 20 wt-% of styrene.

187. The method of claim 170, wherein the ethylenically unsaturated monomer
15 component includes butyl acrylate.

188. The method of claim 185, wherein the ethylenically unsaturated monomer component includes butyl acrylate.

189. The method of claim 186, wherein the ethylenically unsaturated monomer component includes butyl acrylate.

20 190. The method of claim 187, wherein the ethylenically unsaturated monomer component includes from about 30 wt-% to about 55 wt-% of butyl acrylate.

191. The method of claim 188, wherein the ethylenically unsaturated monomer component includes from about 30 wt-% to about 55 wt-% of butyl acrylate.

192. The method of claim 189, wherein the ethylenically unsaturated monomer
25 component includes from about 30 wt-% to about 55 wt-% of butyl acrylate.

79713-5

193. The method of claim 170, wherein the ethylenically unsaturated monomer component includes ethyl acrylate.

194. The method of claim 185, wherein the ethylenically unsaturated monomer component includes ethyl acrylate.

5 195. The method of claim 186, wherein the ethylenically unsaturated monomer component includes ethyl acrylate.

196. The method of claim 170, wherein the ethylenically unsaturated monomer component does not include acrylamide, methacrylamide, N-isobutoxymethyl acrylamide, or N-butoxymethyl acrylamide.

10 197. The method of claim 196, wherein the ethylenically unsaturated monomer component does not include any vinyl acrylamide monomers.

198. The method of claim 170, wherein at least 50 wt-% of the ethylenically unsaturated monomer component is used in making the latex polymer, based on the total weight of ethylenically unsaturated monomer component and salt of the acid- or anhydride-
15 functional polymer.

199. The method of claim 170, wherein the salt of an acid- or anhydride-functional polymer comprises a salt of an acid- or anhydride-functional polymer and a tertiary amine.

200. The method of claim 170, wherein the acid- or anhydride-functional polymer comprises an organic-solution polymerized acid- or anhydride-functional polymer.

20 201. The method of claim 199, wherein the acid- or anhydride-functional polymer comprises an organic-solution polymerized acid- or anhydride-functional polymer.

202. The method of claim 170, wherein the salt of an acid- or anhydride-functional polymer comprises a salt of an acid- or anhydride-functional alkyd resin, a salt of an acid- or anhydride-functional polyester resin, or a salt of an acid- or anhydride-functional
25 polyurethane resin.

79713-5

203. The method of claim 171, wherein the acid- or anhydride-functional acrylic polymer comprises more than 15 wt-% acid- or anhydride-functional monomers, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional acrylic polymer.

5 204. The method of claim 171, wherein the acid- or anhydride-functional acrylic polymer comprises more than 30 wt-% acid- or anhydride-functional monomers, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional acrylic polymer.

205. The method of claim 171, wherein the polymerizable unsaturated monomers
10 used to generate the acid- or anhydride-functional acrylic polymer includes methacrylic acid and does not include acrylic acid.

206. The method of claim 171, wherein the acid- or anhydride-functional monomers included in the polymerizable unsaturated monomers used to generate the acid-or anhydride-functional acrylic polymer consists of methacrylic acid.

15 207. The method of claim 170, wherein the coating composition does not include a crosslinker.

208. The method of claim 179, wherein the coating composition does not include a crosslinker.

209. The method of claim 170, wherein the coating composition does not include a
20 phenoplast crosslinker, an aminoplast crosslinker, or a blocked or non-blocked isocyanate crosslinker.

210. The method of claim 170, wherein the coating composition is completely free of bound BPA and aromatic glycidyl ethers.

211. The method of claim 170, further comprising filling the coated beverage can
25 with a beverage product.

212. A method, comprising the steps of:

79713-5

receiving a coating composition that includes an emulsion polymerized latex polymer that comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a salt of an acid- or anhydride-functional acrylic polymer and an amine, wherein the ethylenically unsaturated monomer component includes an oxirane group-containing monomer, and wherein the coating composition is made without using PVC compounds, BPA, or aromatic glycidyl ether compounds; and

spray applying the coating composition onto an interior surface of an aluminum beverage can including a body portion and a bottom end portion.

213. The method of claim 212, further comprising curing the coating composition to form a cured coating.

214. The method of claim 173, wherein the cured coating exhibits a metal exposure of less than 2 mA on average when the can is filled with 1% NaCl in deionized water and tested pursuant to the Initial Metal Exposure test method disclosed herein.

215. The method of claim 213, wherein the cured coating exhibits a metal exposure of less than 1 mA on average when the can is filled with 1% NaCl in deionized water and tested pursuant to the Initial Metal Exposure test method disclosed herein.

216. The method of claim 213, wherein the cured coating exhibits a global extraction result of less than 50 ppm.

217. The method of claim 213, wherein the cured coating exhibits a global extraction result of less than 10 ppm.

218. The method of claim 213, wherein the cured coating exhibits a global extraction result of less than 1 ppm.

219. The method of claim 213, wherein the beverage can or a portion thereof includes a dome apex and the cured coating shows no craze after the outside of the dome apex is subjected to a 12 in-lbs reverse impact.

79713-5

220. The method of claim 213, wherein the cured coating exhibits no adhesion failure when tested pursuant to ASTM D-3359-Test method B after retort in deionized water for 90 minutes at a heat of 121°C and a corresponding pressure.

221. The method of claim 212, wherein the oxirane-group containing monomer is present in an amount of 0.1 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

222. The method of claim 221, wherein the oxirane-group containing monomer is present in an amount of more than 5 wt-% to 30 wt-%, based on the weight of the ethylenically unsaturated monomer component.

223. The method of claim 221, wherein the oxirane-group containing monomer is present in an amount of more than 5 wt-% to 9 wt-%, based on the weight of the ethylenically unsaturated monomer component.

224. The method of claim 212, wherein the oxirane group-containing monomer comprises glycidyl methacrylate, glycidyl acrylate, or a mixture of glycidyl methacrylate and glycidyl acrylate.

225. The method of claim 222, wherein the oxirane group-containing monomer comprises glycidyl methacrylate, glycidyl acrylate, or a mixture of glycidyl methacrylate and glycidyl acrylate.

226. The method of claim 212, wherein the ethylenically unsaturated monomer component includes at least 20 wt-% of a vinyl aromatic compound.

227. The method of claim 212, wherein the ethylenically unsaturated monomer component includes at least 20 wt-% of styrene.

228. The method of claim 212, wherein the ethylenically unsaturated monomer component includes butyl acrylate.

229. The method of claim 226, wherein the ethylenically unsaturated monomer component includes butyl acrylate.

79713-5

230. The method of claim 227, wherein the ethylenically unsaturated monomer component includes butyl acrylate.

231. The method of claim 228, wherein the ethylenically unsaturated monomer component includes from about 30 wt-% to about 55 wt-% of butyl acrylate.

5 232. The method of claim 229, wherein the ethylenically unsaturated monomer component includes from about 30 wt-% to about 55 wt-% of butyl acrylate.

233. The method of claim 212, wherein the ethylenically unsaturated monomer component includes ethyl acrylate.

10 234. The method of claim 226, wherein the ethylenically unsaturated monomer component includes ethyl acrylate.

235. The method of claim 227, wherein the ethylenically unsaturated monomer component includes ethyl acrylate.

15 236. The method of claim 213, wherein the ethylenically unsaturated monomer component does not include acrylamide, methacrylamide, N-isobutoxymethyl acrylamide, or N-butoxymethyl acrylamide.

237. The method of claim 236, wherein the ethylenically unsaturated monomer component does not include any vinyl acrylamide monomers.

20 238. The method of claim 212, wherein at least 50 wt-% of the ethylenically unsaturated monomer component is used in making the latex polymer, based on the total weight of ethylenically unsaturated monomer component and the salt of the acid- or anhydride-functional acrylic polymer and an amine.

239. The method of claim 212, wherein the acid- or anhydride-functional acrylic polymer comprises an organic-solution polymerized acid- or anhydride-functional acrylic polymer.

79713-5

240. The method of claim 212, wherein the acid- or anhydride-functional acrylic polymer comprises more than 30 wt-% acid- or anhydride-functional monomers, based on the weight of polymerizable unsaturated monomer used to generate the acid- or anhydride-functional acrylic polymer.

5 241. The method of claim 240, wherein the polymerizable unsaturated monomers used to generate the acid- or anhydride-functional acrylic polymer includes methacrylic acid and does not include acrylic acid.

242. The method of claim 212, wherein the amine comprises a tertiary amine.

243. The method of claim 239, wherein the amine comprises a tertiary amine.

10 244. The method of claim 212, wherein the coating composition does not include a crosslinker.

245. The method of claim 220, wherein the coating composition does not include a crosslinker.

15 246. The method of claim 212, wherein the coating composition does not include a phenoplast crosslinker, an aminoplast crosslinker, or a blocked or a blocked or non-blocked isocyanate crosslinker.

247. The method of claim 213, further comprising filling the coated beverage can with a beverage product.

20 248. The method of claim 214, wherein the coating composition is completely free of bound BPA and aromatic glycidyl ethers.

249. A coated article comprising:

an aluminum beverage can including a body portion and a bottom end portion;

and

79713-5

a cured coating on an interior surface of the aluminum beverage can, wherein the coating is formed from a coating composition that includes an emulsion polymerized latex polymer that comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a salt of an acid- or anhydride-functional polymer, wherein the ethylenically unsaturated monomer component includes an oxirane group-containing monomer, and wherein the coating composition is made without using PVC compounds, BPA, or aromatic glycidyl ether compounds.

250. The coated article of claim 249, wherein the salt of the acid- or anhydride-functional polymer comprises a salt of an acid- or anhydride-functional acrylic polymer and an amine, and wherein the coating is formed from a spray applied coating composition.

251. The coated article of claim 280, wherein the beverage can contains a beverage product.

252. A method, comprising the steps of:

(a) providing a latex-based coating composition that includes one or more polymers, wherein the one or more polymers are formed by polymerizing one or more ethylenically unsaturated monomers, wherein the ethylenically unsaturated monomers include (i) one or more oxirane functional group-containing monomers, (ii) one or more acid-functional monomers and (iii) one or more additional ethylenically unsaturated monomers selected from butyl (meth)acrylate or styrene, wherein the one or more oxirane functional-group containing monomers are polymerized into the one or more polymers using an emulsion polymerization, and wherein the coating composition is not made using PVC compounds and is substantially free of bound BPA and aromatic glycidyl ether compounds; and

(b) spray applying the coating composition to an interior surface of a food or beverage can or a portion thereof.

253. The method of claim 252, wherein the one or more oxirane functional group-containing monomers comprises a glycidyl ester of an alpha, beta-unsaturated acid or anhydride thereof.

79713-5

254. The method of claim 252, wherein the one or more oxirane functional group-containing monomers comprises glycidyl (meth)acrylate.
255. The method of claim 252, wherein the ethylenically unsaturated monomers include glycidyl (meth)acrylate, butyl acrylate, and styrene.
- 5 256. The method of claim 252, wherein the ethylenically unsaturated monomers including methacrylic acid.
257. The method of claim 252, wherein the ethylenically unsaturated monomers include one or more hydroxyl alkyl (meth)acrylate.
258. The method of claim 252, wherein the coating composition is spray applied
10 onto at least a portion of an interior surface of an aluminum beverage can or a portion thereof.
259. The method of claim 252, wherein the coating composition includes a strong acid.
260. The method of claim 259, wherein the strong acid comprises dodecylbenzene sulphonic acid.
- 15 261. The method of claim 259, wherein the strong acid is present in an amount of from at least 0.01 % by weight to no greater than 3 % by weight, based on the weight of nonvolatile material.
262. The method of claim 252, wherein the coating composition includes a tertiary amine.
- 20 263. The method of claim 252, wherein the coating composition comprises a quaternary salt linkage.
264. The method of claim 252, wherein one or more of the one or more polymers has an acid number of at least 40 milligrams KOH per gram resin.

79713-5

265. The method of claim 252, wherein one or more of the one or more polymers is an acid- or anhydride-functional acrylic polymer having an acid number of at least 40 milligrams KOH per gram resin

266. The method of claim 252, wherein the coating composition includes a
5 surfactant.

267. A method, comprising the steps of:

(a) providing an aqueous coating composition that includes a latex polymer that is substantially free of bound BPA and aromatic glycidyl ether compounds and is made without using PVC compounds, wherein the latex polymer is formed by emulsion
10 polymerizing a mixture of ethylenically unsaturated monomers comprising 0.1 to 30 weight percent oxirane functional group-containing monomer, based on the weight of the mixture, in the presence of an acid- or anhydride-functional polymer; and

(b) spray applying the coating composition to an interior surface of a food or beverage can or a portion thereof.

15 268. The method of claim 267, wherein the oxirane functional group-containing monomer comprises a glycidyl ester of an alpha, beta-unsaturated acid or anhydride thereof.

269. The method of claim 267, wherein oxirane functional group-containing monomer comprises glycidyl (meth)acrylate.

270. The method of claim 267, wherein the mixture of ethylenically unsaturated
20 monomer includes at least one additional ethylenically unsaturated monomer selected from butyl (meth)acrylate or styrene

271. The method of claim 267, wherein the mixture of ethylenically unsaturated monomers includes glycidyl (meth)acrylate and styrene.

272. The method of claim 271, wherein the mixture of ethylenically unsaturated
25 monomers includes at least 20 weight percent of styrene.

79713-5

273. The method of claim 267, wherein the mixture of ethylenically unsaturated monomers includes glycidyl (meth)acrylate, butyl acrylate, and styrene.
274. The method of claim 267, wherein the mixture of ethylenically unsaturated monomers comprises at least 20 weight percent of vinyl aromatic compounds.
- 5 275. The method of claim 267, wherein the mixture of ethylenically unsaturated monomers comprises at least 40 weight percent of alkyl (meth)acrylates.
276. The method of claim 267, wherein the mixture of ethylenically unsaturated monomers comprises at least 40 weight percent of alkyl (meth)acrylates and at least 20 weight percent of vinyl aromatic compounds.
- 10 277. The method of claim 267, wherein the acid- or anhydride-functional polymer comprises an acrylic polymer.
278. The method of claim 277, wherein the acrylic polymer is formed from ethylenically unsaturated monomers including methacrylic acid.
279. The method of claim 277, wherein the acrylic polymer has an acid number of
15 at least 40 milligrams KOH per gram resin.
280. The method of claim 267, wherein the coating composition includes a strong acid.
281. The method of claim 267, wherein the coating composition includes dodecylbenzene sulphonic acid.
- 20 282. The method of claim 267, wherein the coating composition includes a surfactant.
283. The method of claim 267, wherein the coating composition includes a tertiary amine.

79713-5

284. The method of claim 267, wherein the coating composition comprises a quaternary salt linkage.

285. The method of claim 267, wherein the coating composition is substantially free of mobile and bound BPA and aromatic glycidyl ether compounds.

5 286. A method, comprising the steps of:

(a) providing an aqueous coating composition that includes a latex polymer that is substantially free of bound BPA and aromatic glycidyl ether compounds, wherein the latex polymer is formed by emulsion polymerizing a mixture of ethylenically unsaturated monomers comprising butyl acrylate, styrene, and 0.1 to 30 weight percent of oxirane functional group-containing monomer, based on the weight of the mixture, in the presence of an acid- or anhydride-functional acrylic polymer having an acid number of at least 40 milligrams KOH per gram resin; and

10

(b) spray applying the coating composition to an interior surface of a food or beverage can or a portion thereof.

15 287. An article comprising:

a body portion or an end portion of a food or beverage can comprising a metal substrate; and

a coating composition disposed on an inside surface thereon, wherein the coating composition includes an emulsion polymerized latex polymer, and wherein the emulsion polymerized latex polymer comprises a reaction product of an ethylenically unsaturated monomer component polymerized in the presence of an aqueous dispersion of a polyurethane resin.

20

288. The article of claim 287, wherein the article comprises a 2-piece drawn food can body, a 3-piece food can body, a food can end, a drawn and ironed can body, a beverage can body, or a beverage can end.

25

79713-5

289. The article of claim 287, wherein the polyurethane resin comprises a salt of an acid- or anhydride-functional polyurethane resin.

290. The article of claim 287, wherein the polyurethane resin comprises a salt of an acid- or anhydride-functional polyurethane resin and an amine.

5 291. The article of claim 287, wherein the polyurethane resin has a number average molecular weight of 1,500 to 50,000.

292. The article of claim 287, wherein the polyurethane resin is present in an amount comprising at least 5 wt-%, based on the total weight of the ethylenically unsaturated monomer component and the polyurethane resin.

10 293. The article of claim 287, wherein the ethylenically unsaturated component comprises at least about 25 wt-% of the emulsion polymerized latex polymer, based on the total weight of the ethylenically unsaturated monomer component and the polyurethane resin.

294. The article of claim 287, wherein the ethylenically unsaturated monomer component is polymerized in the presence of the aqueous dispersion with a water-soluble free
15 radical initiator at a temperature of 0 °C to 100 °C.

295. The article of claim 294, wherein the free radical initiator comprises a redox initiator system.

296. The article of claim 287, wherein the emulsion polymerized latex polymer is substantially free of bound bisphenol A and aromatic glycidyl ether compounds.

20 297. The article of claim 287, wherein the coating composition, when present on a beverage can end at a dry film thickness of 7 milligrams per square inch, passes less than 10 milliamps of current after being exposed for 4 seconds to a room-temperature electrolyte solution containing 1% by weight of NaCl dissolved in water.

25 298. The article of claim 287, wherein the coating composition is substantially free of bound bisphenol A and aromatic glycidyl ether compounds.

79713-5

299. The article of claim 287, wherein the article comprises a beverage can end having the coating composition disposed on the inside surface of the beverage can end.

300. The article of claim 287, wherein the emulsion polymerized latex polymer consists essentially of the polyurethane resin and the polymerized ethylenically unsaturated
5 monomer component.

301. The article of claim 287, wherein the ethylenically unsaturated monomer component comprises a mixture of monomers that includes at least one oxirane functional-group containing monomer.

302. The article of claim 301, wherein the ethylenically unsaturated monomer
10 component includes at least one oxirane functional group-containing alpha, beta-ethylenically unsaturated monomer.

303. The article of claim 302, wherein at least one oxirane functional group-containing alpha, beta-ethylenically unsaturated monomer is present in the ethylenically unsaturated monomer component in an amount of at least 0.1 wt-% to no greater than
15 30 wt-%, based on the weight of the monomer mixture.

304. The article of claim 302, wherein the at least one oxirane functional group-containing alpha, beta-ethylenically unsaturated monomer comprises glycidyl methacrylate.

305. A method of coating a food or beverage can, the method comprising:
forming a composition comprising an emulsion polymerized latex polymer and
20 being substantially free of bound bisphenol A and aromatic glycidyl ether compounds, comprising:

forming a salt of an acid- or anhydride-functional polymer and an amine in a carrier comprising water to form an aqueous dispersion;

combining an ethylenically unsaturated monomer component with the aqueous
25 dispersion; and

79713-5

polymerizing the ethylenically unsaturated monomer component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer, wherein the ethylenically saturated monomer component comprises a mixture of monomers comprising at least one oxirane functional group-containing monomer, wherein at least
 5 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates; and

applying the composition comprising the emulsion polymerized latex polymer to a metal substrate prior to or after forming the metal substrate into a food or beverage can or portion thereof.

10 306. The method of claim 305 wherein applying the composition to a metal substrate comprises applying the composition to the metal substrate in the form of a planar coil or sheet, hardening the emulsion polymerized latex polymer, and forming the substrate into a food or beverage can or portion thereof.

307. The method of claim 305 wherein the metal substrate comprises steel or
 15 aluminium.

308. The method of claim 305 wherein the acid-functional polymer has a number average molecular weight of 1,500 to 50,000.

309. The method of claim 305 wherein the composition is substantially free of mobile BPA and aromatic glycidyl ether compounds.

20 310. The method of claim 305 wherein the acid- or anhydride-functional polymer comprises an acid- or anhydride-functional acrylic polymer, acid- or anhydride-functional alkyd resin, acid- or anhydride-functional polyester resin, acid- or anhydride-functional polyurethane, or combinations thereof.

311. The method of claim 310 wherein the acid- or anhydride-functional polymer
 25 comprises an acid-functional acrylic polymer.

79713-5

312. The method of claim 310 wherein the acid- or anhydride-functional polymer comprises a polyester polymer.

313. The method of claim 312 wherein the polyester polymer comprises one or more segments of Formula 1



wherein:

each Ar is independently a divalent aryl group or heteroarylene group;

each R is independently a divalent organic group;

R¹ is a divalent organic group; and

10 each n is 0 or 1.

314. The method of claim 305 wherein the amine is a tertiary amine.

315. The method of claim 305 wherein the acid- or anhydride-functional polymer is at least 25% neutralized with the amine in water.

15 316. The method of claim 305 wherein the ethylenically unsaturated monomer component is polymerized in the presence of the aqueous dispersion with a water-soluble free radical initiator at a temperature of 0°C to 100°C.

317. A method of coating a food or beverage can, the method comprising:

forming a composition comprising an emulsion polymerized latex polymer, comprising:

20 forming a salt of an acid- or anhydride-functional polymer and a tertiary amine in a carrier comprising water to form an aqueous dispersion;

combining an ethylenically unsaturated monomer component comprising 0.1 wt-% to 30 wt-% of an oxirane-functional alpha; beta-ethylenically unsaturated

79713-5

monomer with the aqueous dispersion, based on the weight of the monomer component wherein at least 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates, and

polymerizing the ethylenically unsaturated monomer component in the
5 presence of the aqueous dispersion to form an emulsion polymerized latex polymer, and

applying the composition comprising the emulsion polymerized latex polymer to a metal substrate prior to or after forming the metal substrate into a food or beverage can or portion thereof.

318. A food or beverage can prepared by the method of claim 305 or 317.

10 319. A food or beverage can comprising:

a body portion or an end portion comprising a metal substrate; and

a coating composition disposed thereon, wherein the coating composition comprises an emulsion polymerized latex polymer and is substantially free of bound bisphenol A and aromatic glycidyl ether compounds, wherein the emulsion polymerized
15 latex polymer is prepared from a salt of an acid- or anhydride-functional polymer and an amine, an ethylenically unsaturated, monomer component, and water, wherein the ethylenically saturated monomer component comprises a mixture of monomers comprising at least one oxirane functional group-containing monomer, wherein at least 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and
20 methacrylates.

320. The can of claim 319 wherein the ethylenically unsaturated monomer component comprises a mixture of monomers comprising at least one oxirane functional group-containing monomer.

321. The can of claim 318 wherein the acid- or anhydride-functional polymer
25 comprises an acid- or anhydride-functional acrylic polymer, acid- or anhydride-functional

79713-5

alkyd resin, acid- or anhydride-functional polyester resin, acid- or anhydride-functional polyurethane, or combinations thereof.

322. The can of claim 318 wherein the amine is a tertiary amine.

323. A composition for use in coating a food or beverage can, the composition
 5 comprising an emulsion polymerized latex polymer, wherein the emulsion polymerized latex polymer is prepared from a salt or an acid- or anhydride-functional polymer and a tertiary amine, an ethylenically unsaturated monomer component including a mixture of monomers including at least one oxirane functional group-containing alpha, beta-
 10 ethylenically unsaturated monomer in an amount of at least 0.1 wt-% and no greater than 30 wt-%, based on the weight of the monomer mixture, and water, wherein at least 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates.

324. A method of coating an inside surface of a food or beverage can, the method comprising:

15 forming a composition comprising an emulsion polymerized latex polymer and being substantially free of bound bisphenol A and aromatic glycidyl ether compounds, comprising:

forming a salt of an acid- or anhydride-functional polymer and an amine in a carrier comprising water to form an aqueous dispersion;


20 combining an ethylenically unsaturated monomer component with the aqueous dispersion; and

polymerizing the ethylenically unsaturated monomer component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer, wherein the ethylenically saturated monomer component comprises a mixture of monomers
 25 comprising at least one oxirane functional group-containing monomer, wherein at least 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates; and

79713-5

applying the composition comprising the emulsion polymerized latex polymer to a metal substrate on an inside surface side prior to or after forming the metal substrate into a food or beverage can or portion thereof.

325. The method of claim 324 wherein applying the composition to a metal
5 substrate comprises applying the composition to the metal substrate in the form of a planar coil or sheet, hardening the emulsion polymerized latex polymer, and forming the substrate into a food or beverage can or portion thereof.
326. The method of claim 324 wherein the metal substrate comprises steel or aluminium.
- 10 327. The method of claim 324 wherein the acid-functional polymer has a number average molecular weight of 1,500 to 50,000.
328. The method of claim 324 wherein the composition is substantially free of mobile BPA and aromatic glycidyl ether compounds.
329. The method of claim 324 wherein the acid- or anhydride-functional polymer
15 comprises an acid- or anhydride-functional acrylic polymer, acid- or anhydride-functional alkyd resin, acid- or anhydride-functional polyester resin, acid- or anhydride-functional polyurethane, or combinations thereof.
330. The method of claim 329 wherein the acid- or anhydride-functional polymer comprises an acid-functional acrylic polymer.
- 20 331. The method of claim 329 wherein the acid- or anhydride-functional polymer comprises a polyester polymer.
332. The method of claim 331 wherein the polyester polymer comprises one or more segments of Formula 1



25 wherein:

79713-5

each Ar is independently a divalent aryl group or heteroarylene group;

each R is independently a divalent organic group;

R¹ is a divalent organic group; and

each n is 0 or 1.

5 333. The method of claim 324 wherein the amine is a tertiary amine.

334. The method of claim 324 wherein the acid- or anhydride-functional polymer is at least 25% neutralized with the amine in water.

335. The method of claim 324 wherein the ethylenically unsaturated monomer component is polymerized in the presence of the aqueous dispersion with a water-soluble
10 free radical initiator at a temperature of 0°C to 100°C.

336. A method of coating an inside surface of a food or beverage can, the method comprising:

forming a composition comprising an emulsion polymerized latex polymer,
comprising:

15 forming a salt of an acid- or anhydride-functional polymer and a tertiary amine in a carrier comprising water to form an aqueous dispersion;

combining an ethylenically unsaturated monomer component comprising 0.1 wt-% to 30 wt-% of an oxirane-functional alpha; beta-ethylenically unsaturated monomer with the aqueous dispersion, based on the weight of the monomer component
20 wherein at least 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates, and

polymerizing the ethylenically unsaturated monomer component in the presence of the aqueous dispersion to form an emulsion polymerized latex polymer, and

79713-5

applying the composition comprising the emulsion polymerized latex polymer to a metal substrate on an inside surface side prior to or after forming the metal substrate into a food or beverage can or portion thereof.

337. A food or beverage can prepared by the method of claim 324 or 336.

5 338. A food or beverage can comprising:

a body portion or an end portion comprising a metal substrate; and

a coating composition disposed on an inside surface side, wherein the coating composition comprises an emulsion polymerized latex polymer and is substantially free of bound bisphenol A and aromatic glycidyl ether compounds, wherein the emulsion
10 polymerized latex polymer is prepared from a salt of an acid- or anhydride-functional polymer and an amine, an ethylenically unsaturated, monomer component, and water, wherein the ethylenically saturated monomer component comprises a mixture of monomers comprising at least one oxirane functional group-containing monomer, wherein at least
40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl
15 acrylates and methacrylates.

339. The can of claim 338 wherein the ethylenically unsaturated monomer component comprises a mixture of monomers comprising at least one oxirane functional group-containing monomer.

340. The can of claim 337 wherein the acid- or anhydride-functional polymer
20 comprises an acid- or anhydride-functional acrylic polymer, acid- or anhydride-functional alkyd resin, acid- or anhydride-functional polyester resin, acid- or anhydride-functional polyurethane, or combinations thereof.

341. The can of claim 337 wherein the amine is a tertiary amine.

342. A composition for use in coating an inside surface side of a food or beverage
25 can, the composition comprising an emulsion polymerized latex polymer, wherein the emulsion polymerized latex polymer is prepared from a salt or an acid- or anhydride-

79713-5

- functional polymer and a tertiary amine, an ethylenically unsaturated monomer component including a mixture of monomers including at least one oxirane functional group-containing alpha, beta-ethylenically unsaturated monomer in an amount of at least 0.1 wt-% and no greater than 30 wt-%, based on the weight of the monomer mixture, and water, wherein at
- 5 least 40 wt-% of the ethylenically unsaturated monomer component are selected from alkyl acrylates and methacrylates.