

United States Patent [19]

Ohmi et al.

[11] Patent Number: 4,640,699

[45] Date of Patent: * Feb. 3, 1987

[54] PROCESS FOR PRODUCING GLASS PRODUCT HAVING GRADIENT OF REFRACTIVE INDEX

[75] Inventors: Shigeaki Ohmi, Tokorozawa; Seiichi Shingaki; Hiroyuki Sakai, both of Akishima; Yoshiyuki Asahara, Higashiyamato, all of Japan

[73] Assignee: Hoya Corporation, Tokyo, Japan

[*] Notice: The portion of the term of this patent subsequent to Jun. 25, 2002 has been disclaimed.

[21] Appl. No.: 719,569

[22] Filed: Apr. 3, 1985

Related U.S. Application Data

[63] Continuation of Ser. No. 488,809, Apr. 26, 1983, Pat. No. 4,525,189.

[30] Foreign Application Priority Data

May 14, 1982 [JP] Japan 57-80124

[51] Int. Cl.⁴ C03B 25/02

[52] U.S. Cl. 65/3.15; 65/31

[58] Field of Search 65/3.15, 31; 501/12

[56] References Cited

U.S. PATENT DOCUMENTS

4,225,330 9/1980 Kakuzen et al. 65/31
4,389,233 6/1983 Kurosaki et al. 65/3.15
4,525,189 6/1985 Ohmi et al. 65/3.15
4,528,010 7/1985 Edahiro et al. 65/3.15

Primary Examiner—S. Leon Bashore

Assistant Examiner—Michael K. Boyer

Attorney, Agent, or Firm—Oblon, Fisher, Spivak, McClelland & Maier

[57] ABSTRACT

A process for producing a glass product having Δn , the difference between the central and peripheral portions of the glass, greater than 0.04. This process utilizes a porous glass body which is produced via a phase separation technique. A dopant selected from the group consisting of (1) TiNO_3 , (2) TiNO_3 and an alkali metal compound and (3) TiNO_3 , $\text{Pb}(\text{NO}_3)_2$ and an alkali metal compound is then permeated into the micropores of the porous glass product. A concentration gradient of the dopant is then formed by leaching out a portion of the dopant from the micropores. After the dopant is solidified in the micropores, the porous glass product is dried. A heat-treatment step then serves to collapse the micropores. A glass product having a gradient of refractive indices is thereby obtained.

9 Claims, No Drawings

PROCESS FOR PRODUCING GLASS PRODUCT HAVING GRADIENT OF REFRACTIVE INDEX

This is a continuation, of application Ser. No. 488,809, filed Apr. 26, 1983, now U.S. Pat. No. 4,525,189.

FIELD OF THE INVENTION

The present invention relates to a process for producing a glass product having a gradient of refractive indices which can be used as a material (preform) for optical transmission fibers or as a material for rod lenses.

BACKGROUND OF THE INVENTION

A molecular stuffing method is known as a process for producing a glass product having a gradient of refractive indices, in which a porous glass is used and its pores are filled with dopants (refractive index correction components).

Japanese Patent Application (OPI) No. 126207/76 (the term "OPI" as used herein refers to a "published unexamined Japanese patent application"), laid opened on Nov. 1, 1976, describes a process for producing a glass product having a gradient of refractive indices by the molecular stuffing method, as well as a process for producing a porous glass. According to the process, a borosilicate glass is subjected to a heat treatment at a prescribed condition to separate it into an SiO_2 -rich phase and an alkali metal oxide and B_2O_3 -rich phase (phase separation). The glass is then treated with an aqueous solution containing an acid such as hydrochloric acid, sulfuric acid, or nitric acid, to leach the alkali metal oxide and B_2O_3 -rich acid-soluble phase, thereby forming a porous glass having continuous micropores which has the SiO_2 -rich phase as a skeleton. After allowing a solution of dopants to permeate into the micropores present in the porous glass thus prepared (stuffing), a part of the dopants is leached out from the outside of the glass product (unstuffing) to form a gradient of dopant concentration. The dopants are then solidified in the pores and the glass product is dried and subjected to a heat treatment to collapse the micropores, thereby obtaining a glass product having a gradient of refractive indices. Oxides, nitrates, carbonates, acetates, phosphates, borates, arsenates and silicates of alkali metals, alkaline earth metals, boron, aluminum, lead, phosphorus, and the like are described as examples of dopant.

A transparent glass product having a gradient of refraction is used as rod microlenses for microlens arrays, pickup lenses for optical video or audio disks, and the like. Rod microlenses used for rod microlens arrays of copying machines must have a Δn (difference of refractive index between central and peripheral portions of the lens) of only from about 0.007 to about 0.008. Therefore, the glass product obtained by the molecular stuffing method can sufficiently meet the requirement. However, lens arrays for facsimile and lens arrays for LED printers which are required to have a large numerical aperture and which are bright must have a Δn value exceeding 0.04 to 0.03, respectively. Therefore, a glass product satisfying this requirement cannot be obtained by merely utilizing the molecular stuffing method.

In order to increase the Δn by the molecular stuffing method, the concentration of dopants in the stuffing solution must be increased or a dopant having a high refractive index must be used. However, the concentra-

tion of dopants in the stuffing solution cannot be increased infinitely due to the limit of their solubility. For example, CsNO_3 , which is often used as a dopant, has a solubility at 100°C . of at most 200 g/100 ml H_2O . Accordingly, even if a saturated solution of CsNO_3 is used as a stuffing solution, no significant effect can be expected to increase the Δn . In fact, Japanese Patent Application (OPI) No. 126207/76 shows examples which produce a glass product having a gradient of refractive indices by stuffing a CsNO_3 aqueous solution containing 120 g of CsNO_3 per 100 ml of water at a temperature of 95°C . wherein the maximum value for Δn is merely 0.031. A glass product having such a Δn value cannot be used in lens arrays for facsimile machines.

Regarding the use of dopants having a high refractive index, viz., dopants other than alkali metal compounds, even if those can be used for stuffing into the pores in a porous glass product, such dopants tend to react with the glass during heat treatment of the porous glass product, thereby making the glass product unstable. For example, $\text{Pb}(\text{NO}_3)_2$ is known as a dopant to increase the refractive index and has a solubility of about 130 g/100 ml H_2O at 100°C . Even if this is used for the stuffing of a porous glass, the porous glass becomes unstable during the heat treatment and a transparent glass product is hardly obtained. Accordingly, when a dopant having a high refractive index is used, the amount used thereof must be limited to the range where a transparent glass product can be obtained. In the case of $\text{Pb}(\text{NO}_3)_2$, the concentration of the stuffing solution is at most about 40 g/100 ml H_2O and even if the stuffing is conducted with such a concentration, the refractive index at the central portion of the resulting glass product is at best 1.465, as is described in Japanese Patent Application (OPI) No. 126207/76.

SUMMARY OF THE INVENTION

It has been found that a glass product having a large gradient of refractive indices can be obtained by using thallium nitrate (TlNO_3) as a dopant in the molecular stuffing method due to its high solubility in water.

It has also been found that the production of a white turbid, opaque glass product due to the use of thallium can be effectively prevented by the use of an alkali metal compound in combination with TlNO_3 even if a large amount of a thallium component is present in a glass product.

It has been further found that TlNO_3 can be used together with $\text{Pb}(\text{NO}_3)_2$ which is conventionally known as a dopant for increasing a refractive index.

Accordingly, an object of the present invention is to provide a method of producing a glass product having a gradient of refractive indices which comprises the steps of:

stuffing a solution of a dopant selected from the group consisting of (1) TlNO_3 , (2) TlNO_3 and an alkali metal compound, and (3) TlNO_3 , $\text{Pb}(\text{NO}_3)_2$ and an alkali metal compound into micropores of a porous glass product;

unstuffing a part of the dopant in the micropores with or without solidifying the dopant in the micropores to form a prescribed gradient of refractive indices in the porous glass product;

solidifying the dopant in the micropores;

drying the porous glass product; and

heat treating the porous glass product to collapse the micropores.

DETAILED DESCRIPTION OF THE INVENTION

TiNO₃ has an extremely high solubility in water. As a result, where TiNO₃ is used as a dopant, TiNO₃ can be stuffed in a porous glass product in a high concentration. However, where TiNO₃ is used alone as a dopant, if the solution having a high concentration of more than 80 g/100 ml H₂O is stuffed, the glass becomes white turbid during the heat treatment and a transparent product cannot be obtained. Therefore, when TiNO₃ is used alone as a dopant, the amount (concentration) of TiNO₃ is 80 g/100 ml H₂O or less, preferably 60 to 80 g/100 ml H₂O.

On the other hand, where TiNO₃ is used together with an alkali metal compound such as CsNO₃ as a dopant, even if TiNO₃ is stuffed in a high concentration, it is possible to effectively prevent the glass product from becoming white turbid and opaque and a transparent glass product can be obtained. When TiNO₃ is used together with an alkali metal compound, the amount of TiNO₃ is preferably 100 to 400 g/100 ml H₂O, and the amount of the alkali metal compound is 20 g/100 ml H₂O or more, preferably 100 to 200 g/100 ml H₂O.

Further, where TiNO₃ is used together with Pb(NO₃)₂ and an alkali metal compound such as CsNO₃ as a dopant, it is also possible to effectively prevent the glass product from becoming white turbid and opaque, and a transparent glass product can be obtained. When TiNO₃ is used together with Pb(NO₃)₂ and the alkali metal compound, the amount of TiNO₃ is preferably 100 to 400 g/100 ml H₂O, the amount of Pb(NO₃)₂ is 20

thereto. Unless otherwise indicated, all percents are by weight.

EXAMPLES

A glass composed of 54.50% SiO₂, 34.30% B₂O₃, 5.20% Na₂O and 6.00% K₂O was melted at 1,450° C. for 3 hours while stirring it about 1 hour during melting. The molten glass was casted into a mold, maintained at 580° C. for 1 hour, and gradually cooled in a furnace to give a glass block. A glass rod having a diameter of 3 mm and a length of 60 mm was produced by cutting the block and was subjected to a heat treatment at a temperature of 540° C. for 120 hours to cause a phase separation. The resulting phase-separated rod was treated in 1.5N H₂SO₄ aqueous solution at 100° C. for 12 to 24 hours to give a porous glass rod.

The porous glass rod was immersed in an aqueous solution containing 120 g of CsNO₃ and 200 g of TiNO₃ per 100 ml of water at 100° C. for 24 hours to effect stuffing, and then immersed in an ethanol aqueous solution (40% by volume) at 70° C. for 20 minutes to effect unstuffing. The thus treated rod was immersed in a methanol solution at 0° C. for 2 hours to solidify the dopant in the micropores and dried in a desiccator for 2 hours. Thereafter, the rod was maintained at 920° C. for 6 hours and the micropores were collapsed to obtain a transparent glass product.

The above procedures were followed except that the type and amount of the dopant were changed as shown in the table below to obtain glass rods. The refractive index of each glass rod was measured.

The results obtained are shown in the table below.

TABLE

Example Nos.	Amount of Dopant (in 100 ml of H ₂ O)			Refractive Index		Appearance
	CsNO ₃ (g)	Pb(NO ₃) ₂ (g)	TiNO ₃ (g)	Central Portion	Peripheral Portion	
Example 1	120	—	200	1.530	1.463	Transparent
Example 2	—	—	80	1.496	1.463	"
Example 3	—	—	100	1.500	1.463	White turbid
Example 4	120	—	100	1.512	1.463	Transparent
Example 5	120	100	100	1.536	1.463	"
Example 6	200	—	100	1.524	1.463	"
Example 7	120	—	300	1.548	1.463	"
Example 8	200	—	400	1.569	1.463	"
Comparative Example 1	190	—	—	1.486	1.464	Transparent
Comparative Example 2	—	70	—	—	—	White turbid
Comparative Example 3	—	40	—	1.465	—	Transparent

g/100 ml H₂O or more, preferably 80 to 120 g/100 ml H₂O, and the amount of the alkali metal compound is 20 g/100 ml H₂O or more, preferably 100 to 200 g/100 ml H₂O.

Further, examples of the alkali metal compound which can be used in combination with TiNO₃ in the present invention include, for example, nitrates, and carbonates, of Na, and K.

Examples of the solvent which dissolves the dopant according to the invention include water, an organic solvent such as methanol or ethanol, or a mixture of the organic solvent and water.

Any solvent which can be used as the solvent for the dopant can be used for the unstuffing.

The present invention is described in greater detail by reference to the following examples although the present invention is not to be construed as being limited

While the invention has been described in detail and with reference to specific embodiments thereof, it will be apparent to one skilled in the art that various changes and modifications can be made therein without departing from the spirit and scope thereof.

What is claimed as new and desired to be secured by Letters Patent of the United States is:

1. A process for producing a glass product having a gradient of refractive indices and transparent without turbidity which comprises:

(a) producing a porous glass body by:

(1) heating a glass body to effectuate a phase separation;

(2) leaching out the acid-soluble phase from said glass body; and then

(3) recovering therefrom the porous glass body;

- (b) premeating a solution of dopant into the micropores of said porous glass product wherein said dopant is selected from the group consistin of (1) TiNO_3 , the concentration of TiNO_3 in the dopant solution being about 80 g/100 ml of H_2O or less, (2) TiNO_3 and an alkali metal compound, the concentration of TiNO_3 in the dopant solution being about 100 to 400 g/100 ml of H_2O , and (3) TiNO_3 , $\text{Pb}(\text{NO}_3)_2$ and an alkali metal compound, the concentration of TiNO_3 in the dopant solution being about 100 to 400 g/100 ml of H_2O ,
- (c) leaching out a portion of the dopant from the micropores with or without solidifying the dopant in the micropores to form a concentration gradient of the dopant in said porous glass product;
- (d) solidifying the dopant in the micropores,
- (e) drying the porous glass product,
- (f) heat treating said porous glass product to collapse the micropores, and
- (g) recovering a glass having Δn greater than 0.04 wherein Δn is the difference between the central and peripheral portions of the glass.
2. The process of claim 1, wherein the alkali metal compound is CsNO_3 .
3. The process of claim 1, wherein a solvent for the dopant is selected from the group consisting of water,

an organic solvent, and a mixture of water and organic solvent.

4. The process of claim 3, wherein when the dopant is (1) TiNO_3 , the concentration of TiNO_3 in the dopant solution is about 80 g/100 ml of H_2O or less.

5. The process of claim 1, wherein the concentration of TiNO_3 in the dopant solution is about 60 to 80 g/100 ml of H_2O .

6. The process of claim 3, wherein when the dopant is (2) TiNO_3 and an alkali metal compound, the concentration of TiNO_3 in the dopant solution is about 100 to 400 g/100 ml of H_2O and the concentration of said alkali metal compound is about 20 g/100 ml of H_2O or greater.

7. The process of claim 6, wherein the concentration of said alkali metal compound is about 100 to 200 g/100 ml of H_2O .

8. The process of claim 3, wherein when the dopant is (3) TiNO_3 , $\text{Pb}(\text{NO}_3)_2$ and an alkali metal compound, the concentration of TiNO_3 in the dopant solution is about 100 to 400 g/100 ml of H_2O , the concentration of said $\text{Pb}(\text{NO}_3)_2$ is about 20 g/100 ml of H_2O or greater, and the concentration of said alkali metal compound is about 20 g/100 ml of H_2O or greater.

9. The process of claim 8, wherein the concentration of said $\text{Pb}(\text{NO}_3)_2$ is about 80 to 120 g/100 ml of H_2O , and the concentration of said alkali metal compound is about 100 to 200 g/100 ml of H_2O .

* * * * *

30

35

40

45

50

55

60

65