




(86) Date de dépôt PCT/PCT Filing Date: 2010/12/17
(87) Date publication PCT/PCT Publication Date: 2011/06/23
(45) Date de délivrance/Issue Date: 2019/12/24
(85) Entrée phase nationale/National Entry: 2012/06/12
(86) N° demande PCT/PCT Application No.: IE 2010/000075
(87) N° publication PCT/PCT Publication No.: 2011/073969
(30) Priorités/Priorities: 2009/12/18 (US61/287,838);
2010/11/03 (US61/409,741)

(51) Cl.Int./Int.Cl. *A61M 25/00* (2006.01),
A61M 39/24 (2006.01)
(72) Inventeur/Inventor:
BEHAN, NIAL, IE
(73) Propriétaire/Owner:
COLOPLAST A/S, DK
(74) Agent: RIDOUT & MAYBEE LLP

(54) Titre : DISPOSITIF UROLOGIQUE
(54) Title: A UROLOGICAL DEVICE



(57) **Abrégé/Abstract:**

A urological device comprises a urological valve having a plurality of valve leaflets with a region of co-action between the valve leaflets. The valve has a normally closed configuration in which the valve leaflets are engaged at the region of co-action and an open configuration in which the leaflets are separated at the co-action region for fluid flow through the valve. The valve is automatically movable from the closed configuration to the open configuration in response to applied urological pressure.

ABSTRACT

A urological device comprises a urological valve having a plurality of valve leaflets with a region of co-action between the valve leaflets. The valve has a normally closed configuration in which the valve leaflets are engaged at the region of co-action and an open configuration in which the leaflets are separated at the co-action region for fluid flow through the valve. The valve is automatically movable from the closed configuration to the open configuration in response to applied urological pressure.

“A UROLOGICAL DEVICE”

Introduction

5 Prostate Cancer is the most common male malignancy in the Western world. In the U.S. there are approximately 180,000 new diagnoses annually. Each year, 40,000 men with established disease die from prostate cancer.

The main cause of stress urinary incontinence (SUI) in males is radical prostatectomy for cancer.

10 Catalona WJ, Carvalhal GF, Mager DE, Smith DS. Potency, continence and complication rates in 1,870 consecutive radical retropubic prostatectomies. J Urol. 1999 Aug;162(2):433-8 report that the incidence of SUI 1 yr post radical prostatectomy is 20%.

Lee WR, Schultheiss TE, Hanlon AL, Hanks GE. Urinary incontinence following external-beam
15 radiotherapy for clinically localized prostate cancer Urology. 1996 Jul;48(1):95-9 report that adjuvant radiotherapy of prostate cancer can also affect treatment of SUI.

There is a need for a urology device that will improve patient quality of life by effectively providing a patient controlled device that removes the need for a urine bag and also facilitates
20 normal social functioning.

Statements of Invention

According to the invention there is provided a urological device comprising a urological valve,
25 the valve comprising a plurality of valve leaflets, the valve having a region of co-aption between the valve leaflets, the valve having a normally closed configuration in which the valve leaflets are engaged at the region of co-aption and an open configuration in which the leaflets are separated at the co-aption region for fluid flow through the valve, the valve being automatically movable from the closed configuration to the open configuration in response to applied
30 urological pressure.

In one embodiment the valve is of a viscoelastic polymeric foam material.

In one case the valve leaflets evert on movement between the closed and the open configuration in response to applied urological pressure.

The valve may be adapted to open in response to a preset pressure applied over a preset time.

- 5 The valve may be adapted to open in response a pressure of at least 750mm H₂O applied for at least 5 seconds.

- In one embodiment the valve is adapted to remain closed in response to a spike pressure applied for a short time as would be generated by a user coughing. The spike pressure may be 900mm
10 H₂O applied for a period of less than 0.5 seconds.

- In one embodiment the valve remains open as fluid flows therethrough without a requirement for a user to apply urological pressure. The valve may return to the closed configuration when flow through the valve has substantially stopped.
15

In one case the valve everts on movement from the closed to open configuration. The valve may revert on return from the open to the closed configuration.

- In one embodiment the valve comprises at least three valve leaflets. There may for example be
20 six valve leaflets.

The valve may comprise a main body having a region which defines a hinge about which portion of the valve main body is movable between the closed and open configurations.

- 25 In one embodiment the valve comprises stiffening means. The hinge region may be at least partially defined adjacent to the stiffening means.

- In one embodiment the urological device comprises a support for the valve. The support may be generally cylindrical. In one case the support is of the same material as that of the valve. In one
30 embodiment the valve and support are integrally moulded.

The urological device may comprise a first retainer for locating the device in the bladder. The first retainer may comprise a flare extending radially outwardly of the support. The first retainer may be of the same material as that of the support.

In one case the first retainer, the support and the valve are integrally moulded.

The urological device may comprise stiffening means for the first retainer. The retainer
5 stiffening means may be of a shape memory material such as Nitinol.

In one embodiment the urological device comprises a second retainer to prevent proximal migration of the device. The second retainer may comprise a meatal tab. The second retainer may comprise a bulbous region of compressive material.

10

In one embodiment the urological device comprises an antimicrobial coating.

In one case the device comprises a support to which the valve is mounted. The support may be adapted for mounting in a urinary tract. The support may comprise a generally tubular member.

15 The tubular member may comprise a catheter.

In one embodiment the urological device comprises an anchor for anchoring the support and valve in situ.

20 In some cases the device comprises a housing for the valve, the housing having an inlet on one side of the valve and an outlet on the opposite side of the valve. The inlet may be adapted for mounting to a catheter such as a Foley catheter. The outlet may be adapted for mounting to a drainage bag.

25 In one case the urological device comprises a collar to support the valve in the housing. The valve may comprise a valve body and the collar is arranged to engage the valve body to control the pressure at which the valve moves from the open to the closed configuration and/or from the closed to the open configuration.

30 The invention also provides a drainage catheter system comprising a valve, the valve having:-

a normally closed configuration in which the valve is closed; and

an open configuration in which the valve is opened for flow through the valve;

the valve being automatically movable from the closed to the open configuration for flushing of the catheter.

- 5 The valve may be a one-way valve. The valve may be movable from the closed to the open position in response to a predefined yield pressure. The valve may be of a biocompatible viscoelastic foam material.

In one case the catheter comprises a urological catheter.

10

According to the invention there is provided a urological device comprising a urological valve having:-

a normally closed configuration in which the valve is closed; and

15

an open configuration in which the valve is opened for flow through the valve;

the valve being movable from the closed to the open configuration in response to applied urological pressure.

20

In one embodiment the device comprises a support to which the valve is mounted.

In one case the support is adapted for mounting in a urinary tract.

- 25 The support may comprise a generally tubular member. The tubular member may comprise a catheter.

In one embodiment the device comprises an anchor for anchoring the support and valve in situ.

- 30 In one aspect the valve everts on movement between the closed and the open configuration in response to applied urological pressure. On reduction of urological pressure to a preset pressure the valve returns from the open to the closed configuration.

In another aspect the device comprises a housing for the valve, the housing having an inlet on one side of the valve and an outlet on the opposite side of the valve. The inlet may be adapted for mounting to a catheter such as a Foley catheter. The outlet may be adapted for mounting to a drainage bag.

5

In one embodiment the device comprises a collar to support the valve in the housing. The valve may comprise a valve body and the collar is arranged to engage the valve body to control the pressure at which the valve moves from the open to the closed configuration and/or from the closed to the open configuration.

10

In one embodiment the valve is adapted to open in response to a preset pressure applied over a preset time. The valve may be adapted to remain closed in response to a spike pressure applied for a short time such as would be generated by a user coughing.

15 The invention also provides a drainage catheter system comprising a valve, the valve having:-

a normally closed configuration in which the valve is closed; and

an open configuration in which the valve is opened for flow through the valve;

20

the valve being automatically movable from the closed to the open configuration for flushing of the catheter.

In one embodiment the valve is a one-way valve. The valve may be movable from the closed to
25 the open position in response to a predefined yield pressure. The valve may be of a biocompatible viscoelastic foam material.

In one embodiment the valve comprises a polymeric valve body having an outer support rim, at least three valve leaflets, and a main body region extending between the support rim and the
30 valve leaflets.

The invention also provided a luminal valve for placing in a body lumen comprising at least four valve leaflets, the valve having a normally closed configuration in which the leaflets are engaged

and an open configuration in which the leaflets are open. There may be at least five valve leaflets. There may be six valve leaflets.

The valve may comprise a valve body of polymeric material. The valve may comprise an outer support region. The valve may also have a main body region extending between the support region and the valve leaflets.

In one case the main body region is generally concave between the outer support rim and a region of co-aptation of the valve leaflets.

10

In one case the valve leaflets have a region of co-aptation and the valve body is reinforced at the region of co-aptation. The valve body may be thickened at the region of co-aptation.

The region of co-aptation may extend for an axial length of at least 1mm. The region of co-aptation may extend for a depth of from 1mm to 5mm.

15

In one embodiment the support rim of the valve body is reinforced. The support rim of the valve may be thickened. In one embodiment the valve comprises three valve leaflets. In another embodiment the valve comprises six valve leaflets.

20

In one embodiment the polymeric material is stable to gastric fluid for at least 3 months, for at least 4 months, for at least 5 months, for at least 6 months, for at least 7 months, for at least 8 months, for at least 9 months, for at least 10 months, for at least 11 months, or for at least one year.

25

In one case the polymeric material takes up less than about 5%, less than about 10%, less than about 15%, less than about 20%, less than about 25%, or less than about 30% by weight of water at equilibrium.

In one case the polymeric material of the valve body has a % elongation of from 50% to 3000% or 200% to 1200%.

30

In one case the polymeric material of the valve body has a tensile strength of from 0.01 to 5 MPa or about 0.1 to 1.0 MPa, or about 0.25 to 0.5 MPa.

In one embodiment the polymeric material has a Young's Modulus of about 0.01 to 0.6 MPa, or about 0.1 to about 0.5 MPa.

In one embodiment the polymeric material of the valve body has a density of from 0.1 g/cm³ to 1.5 g/cm³, or 0.3 to 1.2g/cm³, or 0.8 to 0.9g/cm³, or 0.5 to 0.6g/cm³.

In one embodiment the distance between the proximal end of the support region of the valve body and the distal end of the valve leaflets is less than 50mm, or less than 40mm, or less than 30mm, or less than 25mm, or less than 20mm, or less than 15mm.

10

In one case the polymeric material of the valve body is of an elastic material.

In another case the polymeric material of the valve body is of a viscoelastic material.

15 In one embodiment the polymeric material of the valve body comprises a foam. The polymeric material of the valve body may comprise an open cell foam.

In one embodiment the polymeric material of the valve body comprises a polyurethane foam.

20 In one embodiment the length of the valve from the proximal end of the support region to the distal end of the valve leaflets is less than 50 mm, less than 40 mm, less than 30 mm. The length of the valve may be approximately the same as the outer diameter of the support region of the valve. The length of the valve may be approximately 23 mm.

25 Brief Description of the Drawings

The invention will be more clearly understood from the following description thereof given by way of example only, in which:-

30 Fig. 1 is an isometric view (from above) of a urological valve according to the invention;

Fig. 2 is an isometric view (from below) of the valve of Fig. 1;

Fig. 3 is an underneath plan view of the valve;

Fig. 4 is a top plan view of the valve;

Figs. 5 and 6 are isometric, partially cut-away sectional, views of the valve;

5 Figs. 7 and 8 are cross sectional views of the valve;

Fig. 9 is a cross sectional view of the valve in a normally closed configuration with a force F_1 applied;

10 Fig. 10 is a cross sectional view of the valve in an open configuration in response to the force F_1 ;

Fig. 11 is a cross sectional view of the valve returned to the closed configuration after opening to flow;

15

Fig. 12 is a cross sectional view of the valve in a normally closed configuration with a force F_2 applied;

20

Fig. 13 is a cross sectional view of the valve in an open configuration in response to the force F_2 ;

Fig. 14 is a cross sectional view of the valve returned to the closed configuration after opening;

25

Fig. 15 is an isometric view (from above) of the valve in a normally closed configuration;

Fig. 16 is an isometric view of the valve moving towards an open configuration in response to the force F_1 ;

30

Fig. 17 is an isometric view of the valve in a fully open configuration permitting flow;

Fig. 18 is an isometric view (from below) of the valve in a normally closed configuration;

Fig. 19 is an isometric view of the valve in a partially open configuration in response to the force F2;

5 Fig. 20 is an isometric view of the valve in a fully open configuration in response to force F2;

Fig. 21 is an isometric view of another valve according to the invention;

10 Fig. 22 is a cross sectional view of the valve in a closed configuration;

Fig. 23 is a cross sectional view with the valve in the open configuration in response to a urological pressure F1;

15 Fig. 24 is an elevational view of the valve of Fig. 21;

Fig. 25 is a plan view of the device of Figs. 21 with the valve in a closed configuration;

Fig. 26 is a plan view similar to Fig. 25 with the valve in an open configuration;

20 Fig. 27 is an isometric view of an external urological valve device according to the invention;

Fig. 28 is another isometric view of the device of Fig. 27;

25 Fig. 29 is an isometric, partially cut-away view of the device of Figs. 27 and 28 with a valve omitted;

Fig. 30 is an exploded view of the device of Figs. 27 and 28;

30 Figs. 31 to 33 are elevational, partially cross sectional views illustrating the device of Figs. 27 to 30 in use with the valve in different configurations;

Fig. 34 is a graph of pressure over time illustrating the pressure applied when the valve is in the configurations of Figs. 31 to 33;

Figs. 35 and 36 are cross sectional views of the device of Figs. 29 to 34 illustrating eversion of the valve and fluid flow;

5 Figs. 37 to 39 are elevational, partially cross sectional views of the device of Figs. 29 to 33 and 35 to 36 in use illustrating the functioning of the valve in use when exposed to a rapid pressure spike;

10 Fig. 40 is a graph of pressure over time illustrating the pressure applied when the valve is in the configuration of Figs. 37 to 39;

Fig. 41 is a cross sectional view illustrating a valve mounting arrangement;

Fig. 42 is an isometric view of a collar used for mounting the valve;

15 Fig. 43 is a cross sectional view of the collar of Fig. 42;

Fig. 44 is an isometric view of the device of Figs. 27 to 33 mounted to a catheter;

20 Fig. 45 is a cross sectional view illustrating a male version device and catheter in use;

Fig. 46 is an enlarged view of a detail of Fig. 45;

Fig. 47 is a cross sectional view of a female version of the device and catheter in use;

25 Fig. 48 is an enlarged view of a detail of Fig. 47;

Fig. 49 is a cross sectional view illustrating a modified male version of the device and catheter in use;

30 Fig. 50 is an enlarged view of a detailed of Fig. 49;

Fig. 51 is a cross sectional view illustrating a modified female version of the device and catheter in use;

Fig. 52 is an enlarged view of a detail of the device of Fig. 51;

Fig. 53 is a view of a prior art drainage catheter;

5 Fig. 54 is an enlarged cross sectional view of detail A of Fig. 53;

Fig. 55 is an enlarged cross sectional view of detail B of Fig. 53;

10 Fig. 56 is a view of a drainage catheter according to the invention in situ, the catheter having a valve in a closed configuration;

Fig. 57 is a cross sectional view of detail B of Fig. 56;

15 Fig. 58 is a view of the catheter and valve of Fig. 56 with the valve in an open configuration;

Fig. 59 is an enlarged cross sectional view of detail A of Fig. 58;

20 Fig. 60 is an enlarged cross sectional view of detail B of Fig. 58;

Fig. 61 is a graph of time taken for devices to encrust using an accelerated bacterial culture test;

25 Fig. 62 is a cross sectional view illustrating another female version of the device;

Fig. 63 is an enlarged view of a detail of the device of Fig. 62;

Fig. 64 is a cross sectional view of an internal urological valve device in use;

30 Fig. 65 is an enlarged view of a detail of Fig. 64;

Fig. 66 is a cross sectional view of another internal urological valve device in use;

Fig. 67 is an enlarged view of a detail of Fig. 66;

Fig. 68 is a perspective view of another valve device according to the invention;

Fig. 69 is a cross sectional view of the valve device of Fig. 68;

5 Fig. 70 is a cross sectional view of the valve device of Figs. 68 and 69 in situ in a bladder neck;

Figs. 71 to 73 are diagrams illustrating the delivery and deployment of a valve device according to the invention;

10

Fig. 74 is a cross sectional view of another valve device of the invention deployed in a bladder neck;

15 Fig. 75 is a cross sectional view illustrating the opening of a valve at the proximal end of the device of Fig. 74 opening in response to pressure;

Fig. 76 is a perspective view of another valve device according to the invention;

Fig. 77 is a cross sectional view of the device of Fig. 76;

20

Fig. 78 is a perspective view of another valve device according to the invention;

Fig. 79 is a cross sectional view of the device of Fig. 78;

25 Fig. 80 is a cross sectional view of the device of Figs. 78 and 79 anchored in a bladder neck;

Fig. 81 is a perspective view of another valve device according to the invention;

30 Fig. 82 is a cross sectional view of the device of Fig. 81;

Fig. 83 is a cross sectional view of the device of Figs. 81 and 82 in use;

Fig. 84 is a cross sectional view of another valve device according to the invention, in use;

Fig. 85 is a perspective view of another urological device according to the invention;

5

Fig. 86 is a cut-away view of the device of Fig. 85;

Fig. 87 is a cross sectional view of the device of Figs. 85 and 86;

10

Fig. 88 is an enlarged view of a detail of Fig. 87;

Fig. 89 is a perspective view of a further urological device according to the invention;

Fig. 90 is a perspective view of a further urological device according to the invention;

15

Fig. 91 is a cut-away view of the device of Fig. 90;

Fig. 92 is a cross sectional view of the device of Fig. 91;

20

Fig. 93 is an enlarged view of a detail of Fig. 92;

Fig. 94 is a graph illustrating the flow characteristics through a urological device of the invention;

25

Fig. 95 is a graph of the pressure profile of a urological device of the invention during accelerated bladder filling simulation;

Fig. 96 is a graph of differential pressure control using a urological device of the invention;

30

Fig. 97 is an illustration of prior art polymers with urea and urethane linkages interspersed between homopolymer soft segments;

Fig. 98 is an illustration of a polyurethane/urea foam according to the invention with urea and urethane linkages interspersed between triblock copolymer soft segments;

5 Fig. 99 is an illustration of a siloxane and polypropylene oxide based triblock copolymer in different forms;

Fig. 100 is a graph of comparative mechanical properties of homo (VF130309) and triblock copolymer (VF230209A) soft segments;

10 Fig. 101 is a graph of comparative mechanical properties of homo (VF190309) and triblock copolymer (VF090309) soft segments;

15 Fig. 102 is a graph illustrating the mechanical performance of triblock copolymer soft segments versus homopolymer soft segment during accelerated aging in simulated gastric fluid;

Fig. 103 depicts a gastric yield pressure test apparatus as utilized in Example 10;

20 Fig. 104 and Fig. 105 depict results of accelerated stability of a valve prepared from a viscoelastic foam of the present invention;

Detailed Description

Referring to the drawings and initially to Figs. 1 to 20 thereof there is illustrated a urological
25 valve 1 which can open automatically in response to applied urological pressure.

The valve 1 comprises a polymeric valve body having an outer support region with a rim 2, at least three valve leaflets 3, 4, 5, and a main body region 6 extending between the support rim 2 and the valve leaflets 3, 4, 5. The valve leaflets 3, 4, 5 extend inwardly and terminate at end
30 faces 7, 8, 9 respectively. The leaflets each 3, 4, 5 have legs a, b which extend at an included angle of 120° to each other. The adjacent pairs of legs 3a; 4a; 4b; 5b; 5a; 3b; co - apt to close the gap between the valve leaflets when the valve is in the normally closed configuration.

The valve 1 has three configurations. The first configuration is a normally closed configuration in which the valve leaflets 3, 4, 5 co-apt to close the valve. The second configuration is an open configuration to allow fluid flow in which the valve leaflets 3, 4, 5 are opened such that the leaflet leg pairs 3a; 4a; 4b; 5b; 5a; 3b are opened and spaced-apart in response to a force F1 to allow flow through the valve. The third configuration is a second open configuration in response to a force F2.

The various configurations of the valve 1 are illustrated in Figs. 11 to 20. In the first or normally closed configuration (Figs 9, 15) the valve leaflets 3, 4, 5 co-apt.

10

When a urological pressure force F1 is applied to the valve body. This force initially pushes the valve leaflets 3, 4, 5 against one another and if the pressure is greater than a set value, the valve body will invert. The start of inversion is illustrated in Fig. 16. When the valve is fully opened in response to force F1 the valve main body (and the leaflets 3, 4, 5) extend downwardly as illustrated in Figs. 10 and 17. This allows flow to pass through the valve. When the flow is stopped the valve main body will return to the original configuration by everting in response to the biasing of the polymeric material to return to the normally closed configuration with the valve leaflets extending as illustrated in Figs. 11 and 15.

20 When force F2 is applied to the valve leaflets 3, 4, 5 the leaflet legs pairs 3a; 4a; 4b; 5b; and 5a; 3b open to allow an object to pass (Figs. 13, 20). Fig. 19 illustrates a partially open configuration in response to a force F2. When the force F2 is removed the leaflets 3, 4, 5 return to the closed position under the inherent biasing of the polymeric material of the valve body (Fig. 13).

25 The valve leaflets 3, 4, 5 are reinforced in the region of co – aption. In this case, this is achieved by a local thickening of the polymeric material in this region. Similarly the support rim 2 is reinforced by a local thickening of the polymeric material.

The region of co-aption of the valve leaflets 3, 4, 5 has an axial extent which is typically from 1 to 5mm. This ensures positive co-aption of the leaflets across a significant interfacial area when the valve is in the normally closed configuration. The thickness of the leaflets at the region of co-aption is typically between 0.1mm and 10mm.

30

The valve 1 is a two-way valve. Different forces are required to open the valve from the opposite directions. The valve 1 requires different forces to open in the different directions. By varying the properties (such as density) of the material of the valve the valve can be tailored to accommodate varying yield pressures. The valve accomplishes this by controllably inverting
 5 when placed under pressure.

The valve 1 of the invention returns to its original working position after being fully opened. This is accomplished without damaging the working valve.

10 When the valve is opened by an applied urological pressure and fluid flow the leaflets open. The outer face of the valve has a greater resistance to change in shape and thus the force required to open main body in this direction is higher.

The important characteristics influencing the functioning of the valve are the leaflet legs that
 15 impinge on one another. By varying the geometry and length of the leaflets 3, 4, 5 the valve 1 can be made to open in one direction at different pressures. Opening in the opposite direction is somewhat less dependant on the geometry of the leaflets and more dependant on the elasticity and density of the material the device is made from. Additionally, the overall diameter and the diameter to which the leaflets open influence the opening force in both directions.

20

The valve may be of any suitable biocompatible polymeric material. It may be of a biocompatible polymeric material having properties which allow the valve to function as described.

25 The materials used for the production of this valve have a % elongation between 50% and 3000%. The material also has a tensile strength of between 0.01 and 5 MPa. Additionally the material could have an antimicrobial action to prevent colonisation when in-vivo. Additionally the material can be elastic or viscoelastic and can optionally be an open cell foam. The density of the material should be between 0.1 g/cm³ to 1.5 g/cm³.

30

The valve may have any desired number of leaflets, for example the valve 30 illustrated in Figs. 21 to 26 has six valve leaflets 251. These leaflets 251 are oriented perpendicular to direction of flow to additionally allow greater distensibility of the valve aperture.

The valve 30 is similar to the valve described above and comprises a polymeric valve body having a proximal outer support region with a rim 32, six valve leaflets 33, and a main body region 36 extending between the support rim 32 and the valve leaflets 33. The valve leaflets 33 extend terminate at distal end faces 33. The leaflets each have legs which extend at an included
 5 angle of 60° to each other. The adjacent pairs of legs co - apt to close the gap between the valve leaflets 33 when the valve is in the normally closed configuration.

The valve 30 has three configurations. The first configuration is a normally closed configuration in which the valve leaflets 33 co-apt to close the valve. The second configuration is an open
 10 configuration to allow fluid flow in which the valve leaflets 33 are opened such that the leaflet leg pairs are opened and spaced-apart in response to a force F1 to allow flow through the valve 30. The third configuration is a second open configuration in response to a force F2 which is substantially larger than the antegrade force F2.

15 The various configurations of the valve 30 are illustrated in Figs. 21 to 26. In the first or normally closed configuration (Fig. 21) the valve leaflets 33 co-apt.

When a urological pressure force F1 is applied to the valve body. This force initially pushes the valve leaflets 33 against one another (Fig. 22) and if the pressure is greater than a set value, the
 20 valve body will invert as illustrated in Fig. 23. When the valve is fully opened in response to force F₁ the valve main body (and the leaflets 33) extend downwardly as illustrated in Fig. 23. This allows flow to pass through the valve. When the flow is stopped the valve main body will return to the original configuration by everting in response to the biasing of the polymeric material to return to the normally closed configuration with the valve leaflets extending as
 25 illustrated in Fig. 21.

When force F2 is applied to the valve leaflets 33 the leaflet legs pairs open to allow an object to pass (Fig. 26). When the force F2 is removed the leaflets 33 return to the closed position under the inherent biasing of the polymeric material of the valve body

30

The valve leaflets 33 are reinforced in the region of co - aption. In this case, this is achieved by a local thickening of the polymeric material in this region. Similarly the support rim 32 is reinforced by a local thickening of the polymeric material.

The region of co-action of the valve leaflets 33 has an axial extent which is typically from 1 to 5mm. This ensures positive co-action of the leaflets across a significant interfacial area when the valve is in the normally closed configuration. The thickness of the leaflets at the region of co-action is typically between 0.1mm and 10mm.

5

The valve 30 is a two-way valve. Different forces are required to open the valve from the opposite directions. The valve 30 requires different forces to open in the different directions. By varying the properties (such as density) of the material of the valve the valve can be tailored to accommodate varying yield pressures. The valve 30 accomplishes this by controllably inverting
10 when placed under pressure.

The valve 30 of the invention returns to its original working position after being fully opened. This is accomplished without damaging the working valve.

15 When the valve 30 is opened by user applied urological pressure.

One important characteristic influencing the functioning of the valve 30 is the leaflet legs that impinge on one another. By varying the geometry and length of the leaflets 33 the valve 30 can be made to open in one direction at different pressures. Opening in the opposite direction is
20 somewhat less dependant on the geometry of the leaflets and more dependant on the elasticity and density of the material the device is made from. Additionally, the overall diameter and the diameter to which the leaflets open influence the opening force in both directions.

The valve may be of any suitable biocompatible polymeric material. It may be of a
25 biocompatible polymeric material having properties which allow the valve to function as described.

The materials used for the production of this valve have a % elongation between 50% and 3000%. The material also has a tensile strength of between 0.01 and 5 MPa. Additionally the
30 material could have an antimicrobial action to prevent colonisation when in-vivo. Additionally the material can be elastic or viscoelastic and can optionally be an open cell foam. The density of the material should be between 0.1 g/cm³ to 1.5 g/cm³.

Referring to Figs. 27 to 58 of the drawings there are illustrated various urological valve devices according to the invention. The devices comprise a valve 600 which may be of the type described above. The valve has a normally closed configuration in which the valve is closed and an open configuration in which the valve is opened for flow through the valve. The valve is

5 movable from the closed to the open configuration in response to applied urological pressure. In some cases the valve 600 everts on movement between the closed and open configuration in response to applied urological pressure. On reduction of urological pressure to a present pressure the valve 600 returns from the open to the closed configuration. The device may be adapted for use in the male or female anatomy. In some cases the valve is mounted to a support. The support

10 may be adapted for mounting in the urinary tract in which case there may be an anchor for anchoring the valve in situ. The valve may be external of the body and may be mounted in a housing having an inlet and an outlet. The inlet may be adapted for mounting to a catheter such as a Foley catheter. The outlet may be adapted for mounting to a drainage means such as a bag or the like.

15

The invention provides a urological valve device that may be used to treat patients with stress urinary incontinence, for example as a result of a radical prostatectomy. The valve will open based on the pressure applied by the patient through the muscles of the bladder.

20 In one embodiment the device is for connection to a catheter such as a Foley catheter. The device in this configuration is not intended to be in direct contact with the urethra.

The continence mechanism of the device is a one-way valve that maintains a leak-free system until a pre-defined hydraulic pressure is applied. Once the 'break-pressure' has been reached the

25 lumen of the catheter is open to drain freely. The lumen will remain open until fluid flow has stopped after which the valve will reset itself (this may takes approx 15 sec after cessation of micturition).

The valve is designed to open when a preset pressure applied to it. The valve is capable of

30 remaining closed at higher pressures if they are not sustained for a prolonged period of time. For example, the valve can be opened by applying a pressure of 750mmH₂O for 5 sec but should remain closed during an pressure of 900 mmH₂O over a short time. The valve in this way is insulated from coughing/straining related pressure spikes.

Figs. 27 and 28 illustrate an external urological valve assembly housing with a fitting 602 for connecting to a Foley catheter at proximal end and a fitting 601 for connecting to a drainage bag at distal end. The housing comprises a proximal section 604 and a distal section 603, which are separable for insertion of a valve 600.

5

Fig. 29 is a cutaway view of the valve housing without a valve in place. The proximal and distal caps 603, 604 can be seen. An area 609 for seating the valve 600 is illustrated. There is an extended collar 610, which protrudes into the proximal lumen of the valve.

- 10 Fig. 30 is an exploded view of valve housing and valve 600, illustrating how the extended collar 610 on the distal cap 602 locates into the lumen of the valve 600.

Figs. 31 to 33 illustrates the functioning of the valve 600 under the influence of hydrostatic pressure. Referring to Fig. 31 as the urethral fluid pressure begins to rise the valve 600 starts to
 15 deform slightly. At a predetermined pressure the valve 600 will completely evert thus providing a conducting path for fluid to pass. (Fig. 32) After a predetermined period of time the everted valve 600 will reorient itself to its original position. (Fig. 33) This is graphically illustrated in Fig. 34.

- 20 Figs. 35 and 36 illustrate valve eversion and fluid flow.

Figs. 37 to 39 illustrate the functioning of the valve 600 when the valve 600 is exposed to a rapid pressure spike. (Fig. 38) due to a cough or a sneeze may deform momentarily but unless the pressure is maintained will revert to its original configuration. (Fig. 39) In this situation the valve
 25 600 would require a predetermined prolonged time at high pressure to open the valve 600. This is graphically illustrated in Fig. 40.

Referring to Figs. 41 to 43 the mounting of the valve 600 may be controlled using a separate collar component 650 having a projecting part 651 which extends into the rim of the valve body
 30 to control the pressure at which the valve 600 moves from the open to the closed configuration and/or from the closed to the open configuration. This can be varied by adjusting the length X of the projection 651. For example, a short length may allow the valve to freely move whereas longer lengths would control the movement of the valve between the closed and open

configurations. In this way a single valve may be used for a number of different applications by adjusting the projection 651 length appropriately.

Figs. 44 to 48 illustrate embodiments of the use of the urology valve attached to a urinary
5 catheter, such as a Foley catheter 620.

Figs. 49 to 52 are views similar to Figs. 44 to 48 illustrating an alternative arrangement in which the valve device is incorporated into the proximal housing of the urinary catheter.

- 10 The urological valve devices of the invention are in certain embodiments made from a polymeric viscoelastic material. The use of this material addresses a number of problems associated with conventional devices. In the prior art, urological devices have been made from metals and materials that are relatively stiff. These prior art devices, when placed in contact with soft tissues can lead to tissue remodelling, whereby the tissue can become eroded or fibrotic and hardened.
- 15 In addition, the use of hard materials in contact with soft tissues can result in irritation and subsequently discomfort for the patient.

The urological devices of the invention have features which function using polymeric
20 viscoelastic materials. The viscoelastic polymeric materials form valves, which are normally closed but which can evert on exposure to pressure. The mechanism by which the valves evert is associated with the ability of the material to deform under pressure. The deformation of viscoelastic materials under pressure can also be influenced by the duration over which the pressure is applied.

25

The material used for may be as described below. The material may also be as described in our application entitled "A biomaterial" Ref: VYSE12 filed on the same date as this application.

30

The various urological valves described herein may be manufactured from a suitable polymeric viscoelastic material such as described below in example 5 of the material section.

Valves of the type illustrated in Figs. 28 / 29 above manufactured from this material were tested for opening pressure and flowrate. The following results were obtained.

Valve Number	Polymer Density (g/ml)	Leakage (mls)	Opening pressure (mmH ₂ O)	Flowrate (ml/min)
1	1.02	0	817	877
2	0.95	0	703	894
3	1.01	0	877	875
4	1.01	0	803	941
5	1.02	0	877	892
6	0.96	0	820	928
7	1.07	0	945	1010

5

The results in the table above illustrate that a number of valves made with a density between 0.95 – 1.07 g/ml have opening pressures within the required specification but with no leakage when the valve is closed. The flowrate through the valve is also noteworthy as this enables bladder emptying within a reasonable timeframe.

10

This invention also relates to improvements in devices such as catheters that present a conduit through which bacteria can enter the internal anatomy. In particular, the invention relates to urological drainage catheters. However, the technology described below may also be relevant to long and short term drainage devices such as supra pubic catheters, Percutaneous Endoscopic
15 Gastrostomy (PEG) tubes and other devices that might present a conduit through which bacteria could enter the internal anatomy.

Bacteria external to the body are known to travel rapidly up the urethra leading to urinary tract infections and biofilm formation in the case of indwelling catheters and devices.

20

The proliferation of *Proteus Miribellis* within urological devices results in the precipitation of salts and minerals from urine resulting in the ultimate encrustation of the device lumen leading to blockage. Although many attempts have been made to use antimicrobial coating to prevent this effect, no long term solution has been found and urinary catheters will become blocked within a
25 3-4 week period.

The Foley urinary catheter has remained unchanged for the past 60 years. It is widely accepted that 100% of indwelling Foley catheters will become encrusted and block within a 4 week timeframe. A great deal of commercial effort has focused on increasing the longevity of these devices because long term users require specialist nurses to change the devices frequently, which is costly.

There are very large number of disclosures in the prior art teaching the use of a variety of antimicrobial coatings and inserts for use in drainage catheters. US4603152 describes antimicrobial coatings for catheters canulea and the like. US7601361 describes durable antimicrobial coatings. US4932948 describes antimicrobial insert for a male urinary catheter. US5782808 describes an antimicrobial tubing connector.

One problem with the existing technology is that most of the antimicrobial agents are only minimally effective at preventing the proliferation of bacteria and the subsequent encrustation of drainage devices by those bacteria. In addition many of the antimicrobial agents in use can lead to the development of resistance by the bacteria to the agent in use.

Much work has been carried out to coat indwelling catheters with antimicrobial coatings in an effort to prevent biofilm formation. These coatings have either been ineffective or of insufficient durability to sustain the antimicrobial effect.

Referring to Figs. 53 to 55 there is illustrated a conventional urinary drainage catheter 500 for draining urine from a bladder 501. The catheter comprises a tube 502 having an inlet 503 and an outlet 504 through which urine is drained. The catheter 500 has a bulbous head 505 for retaining the catheter in situ in the bladder. A conventional catheter of this type is generally referred to as a Foley catheter. In use, urine drips from the catheter outlet 504 into a collection bag. Such a catheter suffers from the considerable disadvantage that bacterial colonisation and encrustation adjacent to the inlet 503 and in the catheter lumen can occur, as illustrated in Figs. 54 and 55 respectively.

In the invention, a drainage catheter 550 has a valve 551 to control flow through the catheter. Figs. 56 and 57 illustrate the catheter 550 when the valve 551 is in a closed configuration. The valve 551 allows the bladder to fill above the level of the catheter inlet 503. While the valve 551

is closed a build up of urine in the catheter lumen may start the process of bacterial biofilm formation and encrustation as illustrated in Fig. 57.

Referring to Figs. 58 to 60 when the valve 551 is opened voluntarily a pressurised flow of urine
5 through the catheter is generated until the level of urine in the bladder 501 drops below the level of the catheter inlet 503. Regular application of such pressurised flow generates sufficient force to prevent accumulation of bacterial biofilm at the catheter inlet and in the catheter lumen as illustrated in Figs. 59 and Fig. 60 respectively.

10 In the invention a one way valve is incorporated into a catheter, especially a urinary catheter. The valve is designed not to leak but to open at a predefined yield pressure and return to its closed position following bladder emptying. The predefined yield pressure may correspond to an abdominal force generated by the patient through conscious straining or due to normal movement. The force of standing or sitting alone is known to generate significant abdominal
15 pressures. The valve in this case is designed to be placed in line between the catheter and a urine collection bag. The valve facilitates the cyclic filling and emptying of the bladder and thus regular flushing of the catheter lumen. The emptying of the bladder may be conscious or unconscious due to movement.

20 This invention teaches a completely different approach to that conventionally used to achieve an antimicrobial effect. In the invention a physical and mechanical means is used to achieve an antimicrobial effect, thus avoiding the need for potentially cytotoxic coatings. In addition this approach represents a durable and sustained effect rather than the transient effect seen with antimicrobial compounds.

25

Accelerated microbial tests (Fig. 61) have demonstrated that incorporation of a tricuspid valve of a biocompatible foam material as described herein into a Foley catheter prolongs the 'time to encrustation' by a factor of almost 4 compared to an open Foley catheter. The valve of the invention also performs very significantly better than a catheter fitted with a ball valve which is
30 manually movable between an open and close configuration. One search prio-art valve is available under the tradename FlipFlow.

The invention provides a valve for control of urinary incontinence. The valve opens at a specific bladder pressure, in one case when the bladder is full (or at a required volume), without any

manual manipulation. The bladder will then empty into an attached drainage bag and the valve will return to the closed position. This has the benefit of being easy to use. The use of a valve to offer intermittent rather than continual drainage has been shown to potentially reduce catheter blockage. Those users most likely to suffer from catheter blockages are those that have other co-
5 morbidities, a number of which result in dexterity or mobility.

The valve aids patients who are unable to use a conventional catheter valve but who would still benefit greatly in maintaining 'normal' bladder function by intermittent drainage as opposed to continuous drainage.

10

In vitro studies in a laboratory model of the catheterised bladder were undertaken to investigate the time to blockage of the valve of the invention in comparison to the 'Flip-flo' (Trade Mark of Bard Inc) valve and continuous drainage model. The bladder model is described by Striker et al in Stickler, D.J., Morris, N.S. and Winters, C. (1999). Simple physical model to study formation
15 and physiology of biofilms on urethral catheters. Methods in Enzymology, 310:494.

The valve of the invention demonstrated a significantly increased length of time to blockage versus a continuous drainage model (110.4 vs. 22.9 hours, p-value 0.001). There was no significant difference between a normally draining 'Flip-flo' valve and a 'Flip-flo' valve assisted
20 by the automated syringe pump (40.0 vs. 45.1 hours, p-value- 0.425). The mean time to blockage was 110.4 hours for the valve of the invention compared to 45.1 hours for the automated Flip-flo: This result was highly significant (p- value 0.004).

The bladder model consists of a glass chamber (the bladder) maintained at 37°C by a water
25 jacket. Each model was sterilised by autoclaving and then a size 14ch Romed catheter, latex based was inserted into the bladder chamber through a section of silicon tubing (the urethra) at the base of the model. Catheters were secured in place at the outlet of the bladder by inflation of their balloons with 10 ml of deionised water. Where appropriate, the end of the catheters were then attached to either a valve of the invention, Flip-flo valve or left open for continuous
30 drainage. The Flip-flo valve and the continuous drainage models were then subsequently connected to drainage bags in the normal way but the valve of the invention and automated Flip-flo valve were left to drain into a covered plastic beaker (to allow for an open system due to the pressures applied from the syringe pump). Sterile urine was pumped into the chambers so that residual volumes collected below the catheter eye-holes before flowing through the drainage

tube to the collection bags/ beaker.

Flip-flo valves were attached to normal Foley catheters with and without an automated syringe pump and intermittently opened every four hours over a 12 hour period and then both switched
5 to continuous drainage overnight, until blockage occurred. In normal use, a Flip-flo valve would be used for intermittent drainage during the daytime and continuous drainage at night. This regime was used in the tests to reproduce normal use as much as possible.

Valved catheters according to the invention provide the patient with a number of advantages:
10 firstly unsightly drainage bags do not have to be continually worn throughout the day, and secondly it also helps retain some bladder tone because the bladder fills and empties periodically, as is the case in a 'normal' bladder. Additionally the periodic flushing of urine through the catheter displaces some of the developing biofilm, which ultimately causes catheter blockage, and hence increases the life-span of the catheter. The Vysera valve offers additional benefits,
15 such as increasing the number of potential users to include those with dexterity or mobility difficulties and increase the life-span of the catheter by permitting intermittent drainage to occur overnight as well as during the day.+

Figs. 62 to 65 illustrate a urology valve in an indwelling valve device 600 to be retained using a
20 balloon 630 or other anchor in the bladder. The valve 600 may be mounted to a tubular support 635. There may be a pending tether 631 for recovery of the valve 600 externally.

Figs. 66 and 67 illustrate a urology valve 600 in a self retaining structure 635 placed in the urethra. This could be held in placed with an adhesive or through anchoring or suturing
25 technology.

Referring to Figs. 68 to 70 there is illustrated another valve device 800 according to the invention. The device 800 comprises a hollow stem 801 and a head part 802 having slits 803 therein forming valve leaflets. When the slits 803 open in response to applied pressure, urine
30 flows through the head part 802 and into a flow channel 804 extending through the stem 801. The stem 801 also has a bulbous part 805 to assist in locating and retaining the device in situ within a bladder neck 806.

Figs. 71 to 73 illustrate the delivery and deployment of a valve device 810 having a head part 811 with a valve 812 and a stem part 813. The delivery system comprises a catheter 820 which is advanced into the neck of the bladder. The valve device 810 is retained within the catheter 820 in a retracted configuration (Fig. 71). The device 810 is deployed from the distal end 821 of the catheter (Fig. 72). During deployment the valve device 810 expands to a deployed configuration and the catheter 820 is withdrawn to deploy the proximal end of the device (Fig. 73).

Figs. 74 and 75 illustrate the functioning of the valve device 810 deployed in the bladder neck. The valve 812 at the proximal end opens in response to applied pressure.

10

Figs. 76 and 77 illustrate a valve device 830 which is similar to the device of Figs. 71 to 75. In this case there is a tab 831 at the distal tip of the device to ensure that the device is firmly located in situ. The tab 831 typically anchors at the meatus to prevent proximal migration into the bladder.

15

Referring to Figs. 78 to 80 there is illustrated another valve device 850 according to the invention which in this case has anchoring tabs 851 for anchoring the device in the bladder neck. In this case a valve part 852 is located in the urethra.

20 Referring to Figs. 81 to 83 there is illustrated another valve device 860 according to the invention. The device 860 comprises a valve part 861, a head part 862, and a stem part 863. The stem part 863 has a soft compressible foam structure 864 that anchors in the membranous urethra.

25 Referring to Fig. 84 there is illustrated another valve device 870 according to the invention. The valve device 870 has a stem part 871 with a deformable foam bulb 872. The bulb 872 acts as a valve and has a normally closed configuration. Application of a predefined pressure causes the valve to open.

30 Referring to Fig. 85 to 86 there is illustrated another urological device 500 according to the invention. In this case the device is for use in a male. The device 900 comprises a valve 901 at one end of a tubular stem 902. The device has a bladder retainer comprising a flared region 903 which is typically of 40mm diameter for a valve diameter of 9mm. The device also has a second

retainer in this case provided by a bulbous region 904 for maintaining the position of the device in the urethra.

The valve 901 is in this case of a polymeric viscoelastic foam material and is of the type
5 described above with reference to Figs. 1 to 20.

In this case the leaflets are at the top of the device and the valve has a stiffening means provided by vertical reinforcement features 905 which define a fulcrum or hinge region about which the valve leaflets are movable from a normally closed configuration as illustrated in Figs. 85 to 88 to
10 an open position. The valve has a region of co-action between the valve leaflets and has a normally closed configuration in which the valve leaflets are engaged at the region of co-action and an open configuration in which the leaflets are separated at the co-action region for fluid flow through the valve. The valve is movable automatically from the closed to the open configuration in response to applied urological pressure. In this case the leaflets evert on
15 movement between the closed and the open configuration in response to user patient applied urological pressure. The valve is adapted to open in response to a preset pressure applied over a preset time. For example, the valve may be adapted to open in response to a pressure of at least 750mm H₂O applied for at least 5 seconds. However, the valve remains closed in response to a strike pressure applied for a short time such as would be generated by a user coughing. The valve
20 remains open as fluid flows therethrough without a requirement for a user to continue to apply urological pressure. The flow through the valve is sufficient to keep the valve open. The valve returns to the closed configuration when flow through the valve has substantially stopped. The valve in this case everts on movement from the closed to the open configuration and reverts on movement from the open to the closed configuration.

25

In this case the valve and the other elements of the device are all of a polymeric viscoelastic foam material. For example, for optimised manufacturing and cost the device may be integrally moulded.

30 The various urological devices of the invention may comprise a suitable anti-microbial agent such as an anti-microbial coating.

Referring to Fig. 89 there is illustrated another urological device 910 which is similar to the device of Figs. 85 to 88 and like parts are assigned the same reference numerals. In this case the

retaining flare 903 is reinforced, for example by a mesh 911 which may, for example be of a shape memory material such as Nitinol.

Referring to Figs. 90 to 93 there is illustrated another urological device 920 according to the invention which is similar to the device of Figs. 85 to 88 and like parts are assigned the same reference numerals. In this case the device is for female use and the retaining means comprises a meatal tab 921 for prevention of proximal migration.

Test Results

- 10 Various tests were carried out using the urological devices of the invention. The following relates in particular to a female urological device as illustrated in Fig. 90 and described above. The device was manufactured from a polymeric foam material as described in Example 5 below. The valve was a 9mm valve
- 15 Referring to Fig. 94 the flow characteristics through a urological device of the invention is illustrated. It can be seen that flow through the valve is maintained even when the pressure is very low. This feature ensures that emptying of the bladder can be completed without maintaining constant urological or abdominal pressure.
- 20 Referring to Fig. 95 the pressure profile of a urological device of the invention is illustrated during simulated bladder pressure ramp. It can be seen that until a certain pressure is exerted on the valve the valve does not open. Further the pressure continues to drop even after the initial depressurization of the valve due to opening. This in turn illustrates a similar point to Fig. 94 in that constant application of elevated pressure is not required to keep the valve open.
- 25 Referring to Fig. 96 differential pressure control using a urological device of the invention is illustrated. In this illustration the first peak shows the normal opening of the valve due to application of elevated pressure. The magnitude of pressure required to trigger the valve in this case is indicative of a prolonged application or ramping of pressure or valsalva maneuver. The second set of peaks illustrates the application of high pressure spikes to the valve to simulate coughing. In the case of coughing the valve does not open.
- 30

The following section describes one group of biomaterials that are suitable for manufacturing devices and valves of the invention.


The material may also be as described in our application entitled "A biomaterial" Ref: VYSE12 filed on the same date as this application.

5

Use of polyethers as soft segments in polyurethane foams is known to result in soft elastic and viscoelastic materials due to the dynamic reinforcing effect of hydrogen bonding. Conversely, use of non-hydrogen bonding hydrophobic soft segments results in harder, less elastic material. Blending of such hydrophobic and hydrophilic homopolymer soft segments as shown in Figure 10 85 via urethane/urea linkages is known in the art to achieve mechanical properties appropriate to specific applications.

Acid catalysed hydrolytic degradation occurs at urethane linkages within polyurethane materials. These urethane/urea linkages are therefore the 'weak-links' of the polyurethane material. It 15 follows that the intrinsic hydrophilicity of the polyurethane material will affect the rate of hydrolysis through modulation of water uptake. Thus, such materials are incompatible with use in a gastric environment (i.e., a highly acidic aqueous environment).

Thus, in some embodiments, the present invention provides a multiblock copolymer that is 20 biomimetic and hydrolytically stable in a gastric environment. Such multiblock copolymers are of formula I:



25 wherein:

- each ζ represents a point of attachment to a urethane or urea linkage;
- each of X and Y is independently a polymer or co-polymer chain formed from one or more of a polyether, a polyester, a polycarbonate, or a fluoropolymer;
- each of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently selected from one or more of R, OR, $-\text{CO}_2\text{R}$, a 30 fluorinated hydrocarbon, a polyether, a polyester or a fluoropolymer;
- each R is independently hydrogen, an optionally substituted C_{1-20} aliphatic group, or an optionally substituted group selected from phenyl, 8-10 membered bicyclic aryl, a 4-8 membered

monocyclic saturated or partially unsaturated heterocyclic ring having 1-2 heteroatoms independently selected from nitrogen, oxygen, or sulphur, or 5-6 membered monocyclic or 8-10 membered bicyclic heteroaryl group having 1-4 heteroatoms independently selected from nitrogen, oxygen, or sulfur;

- 5 each of m, n and p is independently 2 to 100; and
 each of L¹ and L² is independently a bivalent C₁₋₂₀ hydrocarbon chain wherein 1-4 methylene units of the hydrocarbon chain are optionally and independently replaced by -O-, -S-, -N(R)-, -C(O)-, -C(O)N(R)-, -N(R)C(O)-, -SO₂-, -SO₂N(R)-, -N(R)SO₂-, -OC(O)-, -C(O)O-, or a bivalent cycloalkylene, arylene, heterocyclene, or heteroarylene, provided that neither of L¹ nor L²
 10 comprises a urea or urethane moiety.

2. Definitions:

Compounds of this invention include those described generally above, and are further illustrated by the classes, subclasses, and species disclosed herein. As used herein, the following
 15 definitions shall apply unless otherwise indicated. For purposes of this invention, the chemical elements are identified in accordance with the Periodic Table of the Elements, CAS version, Handbook of Chemistry and Physics, 75th Ed. Additionally, general principles of organic chemistry are described in "Organic Chemistry", Thomas Sorrell, University Science Books, Sausalito: 1999, and "March's Advanced Organic Chemistry", 5th Ed., Ed.: Smith, M.B. and
 20 March, J., John Wiley & Sons, New York: 2001.

As described herein, compounds of the invention may optionally be substituted with one or more substituents, such as are illustrated generally above, or as exemplified by particular classes,
 25 subclasses, and species of the invention. It will be appreciated that the phrase "optionally substituted" is used interchangeably with the phrase "substituted or unsubstituted." In general, the term "substituted", whether preceded by the term "optionally" or not, refers to the replacement of hydrogen radicals in a given structure with the radical of a specified substituent. Unless otherwise indicated, an optionally substituted group may have a substituent at each
 30 substitutable position of the group, and when more than one position in any given structure may be substituted with more than one substituent selected from a specified group, the substituent may be either the same or different at every position. Combinations of substituents envisioned by this invention are preferably those that result in the formation of stable or chemically feasible compounds. The term "stable", as used herein, refers to compounds that are not substantially

altered when subjected to conditions to allow for their production, detection, and preferably their recovery, purification, and use for one or more of the purposes disclosed herein. In some embodiments, a stable compound or chemically feasible compound is one that is not substantially altered when kept at a temperature of 40°C or less, in the absence of moisture or
5 other chemically reactive conditions, for at least a week.

The term “aliphatic” or “aliphatic group”, as used herein, denotes a hydrocarbon moiety that may be straight-chain (i.e., unbranched), branched, or cyclic (including fused, bridging, and spiro-fused polycyclic) and may be completely saturated or may contain one or more units of
10 unsaturation, but which is not aromatic. Unless otherwise specified, aliphatic groups contain 1–20 carbon atoms. In some embodiments, aliphatic groups contain 1–10 carbon atoms. In other embodiments, aliphatic groups contain 1–8 carbon atoms. In still other embodiments, aliphatic groups contain 1–6 carbon atoms, and in yet other embodiments aliphatic groups contain 1–4 carbon atoms. Suitable aliphatic groups include, but are not limited to, linear or branched, alkyl,
15 alkenyl, and alkynyl groups, and hybrids thereof such as (cycloalkyl)alkyl, (cycloalkenyl)alkyl or (cycloalkyl)alkenyl.

The term “lower alkyl” refers to a C₁₋₄ straight or branched alkyl group. Exemplary lower alkyl groups are methyl, ethyl, propyl, isopropyl, butyl, isobutyl, and tert-butyl.
20

The term “lower haloalkyl” refers to a C₁₋₄ straight or branched alkyl group that is substituted with one or more halogen atoms.

The term “heteroatom” means one or more of oxygen, sulfur, nitrogen, phosphorus, or silicon
25 (including, any oxidized form of nitrogen, sulfur, phosphorus, or silicon; the quaternized form of any basic nitrogen or; a substitutable nitrogen of a heterocyclic ring, for example N (as in 3,4-dihydro-2*H*-pyrrolyl), NH (as in pyrrolidiny) or NR⁺ (as in N-substituted pyrrolidiny)).

The term “unsaturated”, as used herein, means that a moiety has one or more units of
30 unsaturation.

As used herein, the term “bivalent C₁₋₈ [or C₁₋₆] saturated or unsaturated, straight or branched, hydrocarbon chain”, refers to bivalent alkylene, alkenylene, and alkynylene chains that are straight or branched as defined herein.

The term “alkylene” refers to a bivalent alkyl group. An “alkylene chain” is a polymethylene group, i.e., $-(CH_2)_n-$, wherein n is a positive integer, preferably from 1 to 6, from 1 to 4, from 1 to 3, from 1 to 2, or from 2 to 3. A substituted alkylene chain is a polymethylene group in which
5 one or more methylene hydrogen atoms are replaced with a substituent. Suitable substituents include those described below for a substituted aliphatic group.

The term “alkenylene” refers to a bivalent alkenyl group. A substituted alkenylene chain is a polymethylene group containing at least one double bond in which one or more hydrogen atoms
10 are replaced with a substituent. Suitable substituents include those described below for a substituted aliphatic group.

The term “halogen” means F, Cl, Br, or I.

15 The term “aryl” used alone or as part of a larger moiety as in “aralkyl”, “aralkoxy”, or “aryloxyalkyl”, refers to monocyclic or bicyclic ring systems having a total of five to fourteen ring members, wherein at least one ring in the system is aromatic and wherein each ring in the system contains 3 to 7 ring members. The term “aryl” may be used interchangeably with the term “aryl ring”.

20

As described herein, compounds of the invention may contain “optionally substituted” moieties. In general, the term “substituted”, whether preceded by the term “optionally” or not, means that one or more hydrogens of the designated moiety are replaced with a suitable substituent. Unless otherwise indicated, an “optionally substituted” group may have a suitable substituent at each
25 substitutable position of the group, and when more than one position in any given structure may be substituted with more than one substituent selected from a specified group, the substituent may be either the same or different at every position. Combinations of substituents envisioned by this invention are preferably those that result in the formation of stable or chemically feasible compounds. The term “stable”, as used herein, refers to compounds that are not substantially
30 altered when subjected to conditions to allow for their production, detection, and, in certain embodiments, their recovery, purification, and use for one or more of the purposes disclosed herein.

Suitable monovalent substituents on a substitutable carbon atom of an “optionally substituted” group are independently halogen; $-(CH_2)_{0-4}R^\circ$; $-(CH_2)_{0-4}OR^\circ$; $-O-(CH_2)_{0-4}C(O)OR^\circ$; $-(CH_2)_{0-4}CH(OR^\circ)_2$; $-(CH_2)_{0-4}SR^\circ$; $-(CH_2)_{0-4}Ph$, which may be substituted with R° ; $-(CH_2)_{0-4}O(CH_2)_{0-1}Ph$ which may be substituted with R° ; $-CH=CHPh$, which may be substituted with R° ; $-NO_2$;
5 $-CN$; $-N_3$; $-(CH_2)_{0-4}N(R^\circ)_2$; $-(CH_2)_{0-4}N(R^\circ)C(O)R^\circ$; $-N(R^\circ)C(S)R^\circ$; $-(CH_2)_{0-4}N(R^\circ)C(O)NR^\circ_2$; $-N(R^\circ)C(S)NR^\circ_2$; $-(CH_2)_{0-4}N(R^\circ)C(O)OR^\circ$; $-N(R^\circ)N(R^\circ)C(O)R^\circ$; $-N(R^\circ)N(R^\circ)C(O)NR^\circ_2$; $-N(R^\circ)N(R^\circ)C(O)OR^\circ$; $-(CH_2)_{0-4}C(O)R^\circ$; $-C(S)R^\circ$; $-(CH_2)_{0-4}C(O)OR^\circ$; $-(CH_2)_{0-4}C(O)SR^\circ$; $-(CH_2)_{0-4}C(O)OSiR^\circ_3$; $-(CH_2)_{0-4}OC(O)R^\circ$; $-OC(O)(CH_2)_{0-4}SR^\circ$; $SC(S)SR^\circ$; $-(CH_2)_{0-4}SC(O)R^\circ$; $-(CH_2)_{0-4}C(O)NR^\circ_2$; $-C(S)NR^\circ_2$; $-C(S)SR^\circ$; $-SC(S)SR^\circ$; $-(CH_2)_{0-4}OC(O)NR^\circ_2$; $-C(O)N(OR^\circ)R^\circ$;
10 $-C(O)C(O)R^\circ$; $-C(O)CH_2C(O)R^\circ$; $-C(NOR^\circ)R^\circ$; $-(CH_2)_{0-4}SSR^\circ$; $-(CH_2)_{0-4}S(O)_2R^\circ$; $-(CH_2)_{0-4}S(O)_2OR^\circ$; $-(CH_2)_{0-4}OS(O)_2R^\circ$; $-S(O)_2NR^\circ_2$; $-(CH_2)_{0-4}S(O)R^\circ$; $-N(R^\circ)S(O)_2NR^\circ_2$; $-N(R^\circ)S(O)_2R^\circ$; $-N(OR^\circ)R^\circ$; $-C(NH)NR^\circ_2$; $-P(O)_2R^\circ$; $-P(O)R^\circ_2$; $-OP(O)R^\circ_2$; $-OP(O)(OR^\circ)_2$; SiR°_3 ; $-(C_{1-4}$ straight or branched alkylene) $O-N(R^\circ)_2$; or $-(C_{1-4}$ straight or branched alkylene) $C(O)O-N(R^\circ)_2$, wherein each R° may be substituted as defined below and is
15 independently hydrogen, C_{1-6} aliphatic, $-CH_2Ph$, $-O(CH_2)_{0-1}Ph$, or a 5–6-membered saturated, partially unsaturated, or aryl ring having 0–4 heteroatoms independently selected from nitrogen, oxygen, or sulfur, or, notwithstanding the definition above, two independent occurrences of R° , taken together with their intervening atom(s), form a 3–12-membered saturated, partially unsaturated, or aryl mono- or bicyclic ring having 0–4 heteroatoms independently selected from
20 nitrogen, oxygen, or sulfur, which may be substituted as defined below.

Suitable monovalent substituents on R° (or the ring formed by taking two independent occurrences of R° together with their intervening atoms), are independently halogen, $-(CH_2)_{0-2}R^\bullet$, $-(haloR^\bullet)$, $-(CH_2)_{0-2}OH$, $-(CH_2)_{0-2}OR^\bullet$, $-(CH_2)_{0-2}CH(OR^\bullet)_2$; $-O(haloR^\bullet)$, $-CN$, $-N_3$, $-(CH_2)_{0-2}C(O)R^\bullet$, $-(CH_2)_{0-2}C(O)OH$, $-(CH_2)_{0-2}C(O)OR^\bullet$, $-(CH_2)_{0-2}SR^\bullet$, $-(CH_2)_{0-2}SH$, $-(CH_2)_{0-2}NH_2$,
25 $-(CH_2)_{0-2}NHR^\bullet$, $-(CH_2)_{0-2}NR^\bullet_2$, $-NO_2$, $-SiR^\bullet_3$, $-OSiR^\bullet_3$, $-C(O)SR^\bullet$, $-(C_{1-4}$ straight or branched alkylene) $C(O)OR^\bullet$, or $-SSR^\bullet$ wherein each $R^\bullet$ is unsubstituted or where preceded by “halo” is substituted only with one or more halogens, and is independently selected from C_{1-4} aliphatic, $-CH_2Ph$, $-O(CH_2)_{0-1}Ph$, or a 5–6-membered saturated, partially unsaturated, or aryl ring having 0–
30 4 heteroatoms independently selected from nitrogen, oxygen, or sulfur. Suitable divalent substituents on a saturated carbon atom of R° include $=O$ and $=S$.

Suitable divalent substituents on a saturated carbon atom of an “optionally substituted” group include the following: =O, =S, =NNR^{*}₂, =NNHC(O)R^{*}, =NNHC(O)OR^{*}, =NNHS(O)₂R^{*}, =NR^{*}, =NOR^{*}, -O(C(R^{*})₂)₂₋₃O-, or -S(C(R^{*})₂)₂₋₃S-, wherein each independent occurrence of R^{*} is selected from hydrogen, C₁₋₆ aliphatic which may be substituted as defined below, or an
 5 unsubstituted 5-6-membered saturated, partially unsaturated, or aryl ring having 0-4 heteroatoms independently selected from nitrogen, oxygen, or sulfur. Suitable divalent substituents that are bound to vicinal substitutable carbons of an “optionally substituted” group include: -O(CR^{*})₂₋₃O-, wherein each independent occurrence of R^{*} is selected from hydrogen, C₁₋₆ aliphatic which may be substituted as defined below, or an unsubstituted 5-6-membered
 10 saturated, partially unsaturated, or aryl ring having 0-4 heteroatoms independently selected from nitrogen, oxygen, or sulfur.

Suitable substituents on the aliphatic group of R^{*} include halogen, -R[•], -(haloR[•]), -OH, -OR[•], -O(haloR[•]), -CN, -C(O)OH, -C(O)OR[•], -NH₂, -NHR[•], -NR[•]₂, or -NO₂, wherein each R[•] is
 15 unsubstituted or where preceded by “halo” is substituted only with one or more halogens, and is independently C₁₋₄ aliphatic, -CH₂Ph, -O(CH₂)₀₋₁Ph, or a 5-6-membered saturated, partially unsaturated, or aryl ring having 0-4 heteroatoms independently selected from nitrogen, oxygen, or sulfur.

20 Suitable substituents on a substitutable nitrogen of an “optionally substituted” group include -R[†], -NR[†]₂, -C(O)R[†], -C(O)OR[†], -C(O)C(O)R[†], -C(O)CH₂C(O)R[†], -S(O)₂R[†], -S(O)₂NR[†]₂, -C(S)NR[†]₂, -C(NH)NR[†]₂, or -N(R[†])S(O)₂R[†]; wherein each R[†] is independently hydrogen, C₁₋₆ aliphatic which may be substituted as defined below, unsubstituted -OPh, or an unsubstituted 5-6-membered saturated, partially unsaturated, or aryl ring having 0-4 heteroatoms independently
 25 selected from nitrogen, oxygen, or sulfur, or, notwithstanding the definition above, two independent occurrences of R[†], taken together with their intervening atom(s) form an unsubstituted 3-12-membered saturated, partially unsaturated, or aryl mono- or bicyclic ring having 0-4 heteroatoms independently selected from nitrogen, oxygen, or sulfur.


30 Suitable substituents on the aliphatic group of R[†] are independently halogen, -R[•], -(haloR[•]), -OH, -OR[•], -O(haloR[•]), -CN, -C(O)OH, -C(O)OR[•], -NH₂, -NHR[•], -NR[•]₂, or -NO₂, wherein each R[•] is unsubstituted or where preceded by “halo” is substituted only with one or more halogens, and is independently C₁₋₄ aliphatic, -CH₂Ph, -O(CH₂)₀₋₁Ph, or a 5-6-membered

saturated, partially unsaturated, or aryl ring having 0–4 heteroatoms independently selected from nitrogen, oxygen, or sulfur.

3. Description of Exemplary Embodiments:

5 A. Multiblock Copolymers

As described generally above, one embodiment of the present invention provides a triblock copolymer of formula I:



10 wherein the copolymers are chemically interspersed (bound) between urethane and/or urea linkages (i.e., at the bond designated with ζ) and wherein each of X, Y, m, n, p, L¹, L², R¹, R², R³, R⁴, R⁵, and R⁶ is as defined and described herein.

As defined generally above, the each of X and Y groups of formula I is independently a polymer
15 or co-polymer chain formed from one or more of a polyether, a polyester, a polycarbonate, and a fluoropolymer.

Examples of polymer or co-polymer chains represented by X and/or Y include:
poly(ethylene oxide), poly(difluoromethyl ethylene oxide), poly(trifluoromethyl ethylene oxide),
20 poly(propylene oxide), poly(difluoromethyl propylene oxide), poly(propylene oxide),
poly(trifluoromethyl propylene oxide), poly(butylene oxide), poly(tetramethylene ether glycol),
poly(tetrahydrofuran), poly(oxymethylene), poly(ether ketone), poly(etherether ketone) and
copolymers thereof, poly(dimethylsiloxane), poly(diethylsiloxane) and higher alkyl siloxanes,
poly(methyl phenyl siloxane), poly(diphenyl siloxane), poly(methyl di-fluoroethyl siloxane),
25 poly(methyl tri-fluoroethyl siloxane), poly(phenyl di-fluoroethyl siloxane), poly(phenyl tri-
fluoroethyl siloxane) and copolymers thereof, poly(ethylene terephthalate) (PET), poly(ethylene
terephthalate ionomer) (PETI), poly(ethylene naphthalate) (PEN), poly(methylene naphthalate)
(PTN), poly(butylene teraphalate) (PBT), poly(butylene naphthalate) (PBN), polycarbonate.

30 In certain embodiments, the present invention provides a pre-formed soft segment for a polyurethane / urea foam.

In some embodiments X is a polyether and Y is a polyether. More specifically in one case X and Y are both poly(propylene oxide).

In certain embodiments, m and p are each independently between 2 and 50 and n is between 2 and 20. In some embodiments, m and p are each independently between 2 and 30 and n is between 2 and 20.

As defined generally above, each of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently selected from one or more of R, OR, $-CO_2R$, a fluorinated hydrocarbon, a polyether, a polyester or a fluoropolymer. In some embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is $-CO_2R$. In some embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is $-CO_2R$ wherein each R is independently an optionally substituted C_{1-6} aliphatic group. In certain embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is $-CO_2R$ wherein each R is independently an unsubstituted C_{1-6} alkyl group. Exemplary such groups include methanoic or ethanoic acid as well as methacrylic acid and other acrylic acids.

In certain embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently R. In some embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is an optionally substituted C_{1-6} aliphatic group. In certain embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is an optionally substituted C_{1-6} alkyl. In other embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is an optionally substituted group selected from phenyl, 8-10 membered bicyclic aryl, a 4-8 membered monocyclic saturated or partially unsaturated heterocyclic ring having 1-2 heteroatoms independently selected from nitrogen, oxygen, or sulphur, or 5-6 membered monocyclic or 8-10 membered bicyclic heteroaryl group having 1-4 heteroatoms independently selected from nitrogen, oxygen, or sulphur. Exemplary such R^1 , R^2 , R^3 , R^4 , R^5 and R^6 groups include methyl, ethyl, propyl, isopropyl, cyclopropyl, butyl, isobutyl, cyclobutyl, phenyl, pyridyl, morpholinyl, pyrrolidinyl, imidazolyl, and cyclohexyl.

In certain embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently -OR. In some embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is -OR wherein R is an optionally substituted C_{1-6} aliphatic group. In certain embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is -OR wherein R is C_{1-6} alkyl. In other embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is -OR wherein R is an optionally substituted group selected from phenyl, 8-10 membered bicyclic aryl, a 4-8 membered monocyclic saturated or partially unsaturated heterocyclic ring

having 1-2 heteroatoms independently selected from nitrogen, oxygen, or sulphur, or 5-6 membered monocyclic or 8-10 membered bicyclic heteroaryl group having 1-4 heteroatoms independently selected from nitrogen, oxygen, or sulphur. Exemplary such R^1 , R^2 , R^3 , R^4 , R^5 and R^6 groups include -Omethyl, -Oethyl, -Opropyl, -Oisopropyl, -Ocyclopropyl, -Obutyl, -Oisobutyl, -Ocyclobutyl, -Ophenyl, -Opyridyl, -Omorpholinyl, -Opyrrolidinyl, -Oimidazolyl, and -Ocyclohexyl.

In certain embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently R wherein each R is a C_{1-6} aliphatic group substituted with one or more halogens. In some embodiments, each R is C_{1-6} aliphatic substituted with one, two, or three halogens. In other embodiments, each R is a perfluorinated C_{1-6} aliphatic group. Examples of fluorinated hydrocarbons represented by R^1 , R^2 , R^3 , R^4 , R^5 and R^6 include mono-, di-, tri-, or perfluorinated methyl, ethyl, propyl, butyl, or phenyl. In some embodiments, each of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is trifluoromethyl, trifluoroethyl, or trifluoropropyl.

15

In certain embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently a polyether. Examples of polyethers represented by R^1 , R^2 , R^3 , R^4 , R^5 and R^6 include poly(ethylene oxide), poly(difluoromethyl ethylene oxide), poly(trifluoromethyl ethylene oxide), poly(propylene oxide), poly(difluoromethyl propylene oxide), poly(propylene oxide), poly(trifluoromethyl propylene oxide), poly(butylene oxide), poly(tetramethylene ether glycol), poly(tetrahydrofuran), poly(oxymethylene), poly(ether ketone), poly(etherether ketone) and copolymers thereof.

In certain embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently a polyester. Examples of polyesters represented by R^1 , R^2 , R^3 , R^4 , R^5 and R^6 include poly(ethylene terephthalate) (PET), poly(ethylene terephthalate ionomer) (PETI), poly(ethylene naphthalate) (PEN), poly(methylene naphthalate) (PTN), poly(butylene terephthalate) (PBT), poly(butylene naphthalate) (PBN), polycarbonate.

In certain embodiments, one or more of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently a fluoropolymer. Examples of fluoropolymers represented by R^1 , R^2 , R^3 , R^4 , R^5 and R^6 include poly(tetrafluoroethylene), poly(methyl di-fluoroethyl siloxane), poly(methyl tri-fluoroethyl siloxane), poly(phenyl di-fluoroethyl siloxane).

In some embodiments, R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently hydrogen, hydroxyl, carboxylic acids such as methanoic or ethanoic acid as well as methacrylic acid and other acrylic acids. Alkyl or aryl hydrocarbons such as methyl, ethyl, propyl, butyl, phenyl and ethers thereof. Fluorinated hydrocarbons such as mono-, di-, tri-, or perfluorinated methyl, ethyl, propyl, butyl, phenyl. Polyether such as Poly(ethylene oxide), poly(difluoromethyl ethylene oxide), poly(trifluoromethyl ethylene oxide), poly(propylene oxide), poly(difluoromethyl propylene oxide), poly(propylene oxide), poly(trifluoromethyl propylene oxide), poly(butylene oxide), poly(tetramethylene ether glycol), poly(tetrahydrofuran), poly(oxymethylene), poly(ether ketone), poly(etherether ketone) and copolymers thereof. Polyesters such as Poly(ethylene terephthalate) (PET), poly(ethylene terephthalate ionomer) (PETI), poly(ethylene naphthalate) (PEN), poly(methylene naphthalate) (PTN), Poly(Butylene Teraphalate) (PBT), poly(butylene naphthalate) (PBN), polycarbonate and fluoropolymer such as Poly(tetrafluoroethylene), poly(methyl di-fluoroethyl siloxane), poly(methyl tri-fluoroethyl siloxane), poly(phenyl di-fluoroethyl siloxane).

15

In some embodiments, m and p are between 2 and 50 and n is between 2 and 20. In certain embodiments, m and o are between 2 and 30 and n is between 2 and 20.

As defined generally above, each of L^1 and L^2 is independently a bivalent C_{1-20} hydrocarbon chain wherein 1-4 methylene units of the hydrocarbon chain are optionally and independently replaced by $-O-$, $-S-$, $-N(R)-$, $-C(O)-$, $-C(O)N(R)-$, $-N(R)C(O)-$, $-SO_2-$, $-SO_2N(R)-$, $-N(R)SO_2-$, $-OC(O)-$, $-C(O)O-$, or a bivalent cycloalkylene, arylene, heterocyclene, or heteroarylene, provided that neither of L^1 nor L^2 comprises a urea or urethane moiety. In some embodiments, each of L^1 and L^2 is independently a bivalent C_{1-20} alkylene chain. In certain embodiments, each of L^1 and L^2 is independently a bivalent C_{1-10} alkylene chain. In certain embodiments, each of L^1 and L^2 is independently a bivalent C_{1-6} alkylene chain. In certain embodiments, each of L^1 and L^2 is independently a bivalent C_{1-4} alkylene chain. Exemplary such L^1 and L^2 groups include methylene, ethylene, propylene, butylene or higher bivalent alkanes.


30 In some embodiments, each of L^1 and L^2 is independently a bivalent C_{1-20} alkylene chain wherein one methylene unit of the chain is replaced by $-O-$. In some embodiments, each of L^1 and L^2 is independently a bivalent C_{1-10} alkylene chain wherein one methylene unit of the chain is replaced by $-O-$. In some embodiments, each of L^1 and L^2 is independently a bivalent C_{1-6} alkylene chain wherein one methylene unit of the chain is replaced by $-O-$. In some

embodiments, each of L^1 and L^2 is independently a bivalent C_{1-4} alkylene chain wherein one methylene unit of the chain is replaced by $-O-$. Exemplary such L^1 and L^2 groups include $-OCH_2-$, $-OCH_2CH_2-$, $-OCH_2CH_2CH_2-$, $-OCH_2CH_2CH_2CH_2-$, or higher bivalent alkylene ethers.


- 5 In some embodiments, each of L^1 and L^2 is independently a bivalent C_{1-20} alkylene chain wherein at least one methylene unit of the chain is replaced by $-O-$ and at least one methylene unit of the chain is replaced by a bivalent arylene. In some embodiments, each of L^1 and L^2 is independently a bivalent C_{1-10} alkylene chain wherein at least one methylene unit of the chain is replaced by $-O-$ and at least one methylene unit of the chain is replaced by a bivalent arylene. In
- 10 some embodiments, each of L^1 and L^2 is independently a bivalent C_{1-6} alkylene chain wherein at least one methylene unit of the chain is replaced by $-O-$ and at least one methylene unit of the chain is replaced by a bivalent arylene. In some embodiments, each of L^1 and L^2 is independently a bivalent C_{1-4} alkylene chain wherein at least one methylene unit of the chain is replaced by $-O-$ and at least one methylene unit of the chain is replaced by a bivalent arylene.
- 15 Exemplary such L^1 and L^2 groups include $-OCH_2$ -phenylene-, $-OCH_2CH_2$ -phenylene-, $-OCH_2CH_2$ -phenylene- CH_2- , $-OCH_2CH_2CH_2CH_2$ -phenylene-, and the like.

One of ordinary skill in the art would understand that a polyurethane results from the reaction of a diisocyanate and a hydroxyl group. Similarly, a polyurea results from the reaction of a

20 diisocyanate and an amine. Each of these reactions is depicted below.



Thus, it is readily apparent that provided compounds of formula I can be functionalized with end groups suitable for forming urethane and/or urea linkages. In certain embodiments, the present invention provides a compound of formula II:



25

II

wherein:

each of R^x and R^y is independently $-OH$, $-NH_2$, a protected hydroxyl or a protected amine;

each of X and Y is independently a polymer or co-polymer chain formed from one or more of a polyether, a polyester, a polycarbonate, and a fluoropolymer;

each of R^1 , R^2 , R^3 , R^4 , R^5 and R^6 is independently selected from one or more of R, OR, $-CO_2R$, a fluorinated hydrocarbon, a polyether, a polyester or a fluoropolymer;

5 each R is independently hydrogen, an optionally substituted C_{1-20} aliphatic group, or an optionally substituted group selected from phenyl, 8-10 membered bicyclic aryl, a 4-8 membered monocyclic saturated or partially unsaturated heterocyclic ring having 1-2 heteroatoms independently selected from nitrogen, oxygen, or sulphur, or 5-6 membered monocyclic or 8-10 membered bicyclic heteroaryl group having 1-4 heteroatoms independently selected from
10 nitrogen, oxygen, or sulfur;

each of m, n and p is independently 2 to 100; and

each of L^1 and L^2 is independently a bivalent C_{1-20} hydrocarbon chain wherein 1-4 methylene units of the hydrocarbon chain are optionally and independently replaced by $-O-$, $-S-$, $-N(R)-$, $-C(O)-$, $-C(O)N(R)-$, $-N(R)C(O)-$, $-SO_2-$, $-SO_2N(R)-$, $-N(R)SO_2-$, $-OC(O)-$, $-C(O)O-$, or a bivalent
15 cycloalkylene, arylene, heterocyclene, or heteroarylene, provided that neither of L^1 nor L^2 comprises a urea or urethane moiety.

In some embodiments, each of X, Y, m, n, p, L^1 , L^2 , R^1 , R^2 , R^3 , R^4 , R^5 , and R^6 is as defined and described herein.

20

As defined generally above, each of R^x and R^y is independently $-OH$, $-NH_2$, a protected hydroxyl or a protected amine. In some embodiments, both of R^x and R^y are $-OH$. In other embodiments, both of R^x and R^y are $-NH_2$. In some embodiments one of R^x and R^y is $-OH$ and the other is $-NH_2$.

25

In some embodiments, each of R^x and R^y is independently a protected hydroxyl or a protected amine. Such protected hydroxyl and protected amine groups are well known to one of skill in the art and include those described in detail in *Protecting Groups in Organic Synthesis*, T. W. Greene and P. G. M. Wuts, 3rd edition, John Wiley & Sons, 1999, the entirety of which is
30 incorporated herein by reference. Exemplary protected amines include methyl carbamate, ethyl carbamate, 9-fluorenylmethyl carbamate (Fmoc), 9-(2-sulfo)fluorenylmethyl carbamate, 9-(2,7-dibromo)fluorenylmethyl carbamate, 2,7-di-*t*-butyl-[9-(10,10-dioxo-10,10,10,10-tetrahydrothioxanthyl)]methyl carbamate (DBD-Tmoc), 4-methoxyphenacyl carbamate (Phenoc), 2,2,2-trichloroethyl carbamate (Troc), 2-trimethylsilylethyl carbamate (Teoc), 2-

phenylethyl carbamate (hZ), 1-(1-adamantyl)-1-methylethyl carbamate (Adpoc), 1,1-dimethyl-2-haloethyl carbamate, 1,1-dimethyl-2,2-dibromoethyl carbamate (DB-t-BOC), 1,1-dimethyl-2,2,2-trichloroethyl carbamate (TCBOC), 1-methyl-1-(4-biphenyl)ethyl carbamate (Bpoc), 1-(3,5-di-t-butylphenyl)-1-methylethyl carbamate (t-Bumeoc), 2-(2'- and 4'-pyridyl)ethyl

5 carbamate (Pyoc), 2-(N,N-dicyclohexylcarboxamido)ethyl carbamate, t-butyl carbamate (BOC), 1-adamantyl carbamate (Adoc), vinyl carbamate (Voc), allyl carbamate (Alloc), 1-isopropylallyl carbamate (Ipaoc), cinnamyl carbamate (Coc), 4-nitrocinnamyl carbamate (Noc), 8-quinolyl carbamate, N-hydroxypiperidiny carbamate, alkylidithio carbamate, benzyl carbamate (Cbz), p-methoxybenzyl carbamate (Moz), p-nitobenzyl carbamate, p-bromobenzyl

10 carbamate, p-chlorobenzyl carbamate, 2,4-dichlorobenzyl carbamate, 4-methylsulfinylbenzyl carbamate (MsZ), 9-anthrylmethyl carbamate, diphenylmethyl carbamate, 2-methylthioethyl carbamate, 2-methylsulfonyl ethyl carbamate, 2-(p-toluenesulfonyl)ethyl carbamate, [2-(1,3-dithianyl)]methyl carbamate (Dmoc), 4-methylthiophenyl carbamate (Mtpc), 2,4-dimethylthiophenyl carbamate (Bmpc), 2-phosphonioethyl carbamate (Peoc), 2-

15 triphenylphosphonioisopropyl carbamate (Ppoc), 1,1-dimethyl-2-cyanoethyl carbamate, m-chloro-p-acyloxybenzyl carbamate, p-(dihydroxyboryl)benzyl carbamate, 5-benzisoxazolylmethyl carbamate, 2-(trifluoromethyl)-6-chromonylmethyl carbamate (Tcroc), m-nitrophenyl carbamate, 3,5-dimethoxybenzyl carbamate, o-nitrobenzyl carbamate, 3,4-dimethoxy-6-nitrobenzyl carbamate, phenyl(o-nitrophenyl)methyl carbamate, phenothiazinyl-

20 (10)-carbonyl derivative, N'-p-toluenesulfonylaminocarbonyl derivative, N'-phenylaminothiocarbonyl derivative, t-amyl carbamate, S-benzyl thiocarbamate, p-cyanobenzyl carbamate, cyclobutyl carbamate, cyclohexyl carbamate, cyclopentyl carbamate, cyclopropylmethyl carbamate, p-decyloxybenzyl carbamate, 2,2-dimethoxycarbonylvinyl carbamate, o-(N,N-dimethylcarboxamido)benzyl carbamate, 1,1-dimethyl-3-(N,N-

25 dimethylcarboxamido)propyl carbamate, 1,1-dimethylpropynyl carbamate, di(2-pyridyl)methyl carbamate, 2-furanylmethyl carbamate, 2-iodoethyl carbamate, isoborynl carbamate, isobutyl carbamate, isonicotinyl carbamate, p-(p'-methoxyphenylazo)benzyl carbamate, 1-methylcyclobutyl carbamate, 1-methylcyclohexyl carbamate, 1-methyl-1-cyclopropylmethyl carbamate, 1-methyl-1-(3,5-dimethoxyphenyl)ethyl carbamate, 1-methyl-1-(p-

30 phenylazophenyl)ethyl carbamate, 1-methyl-1-phenylethyl carbamate, 1-methyl-1-(4-pyridyl)ethyl carbamate, phenyl carbamate, p-(phenylazo)benzyl carbamate, 2,4,6-tri-t-butylphenyl carbamate, 4-(trimethylammonium)benzyl carbamate, 2,4,6-trimethylbenzyl carbamate, formamide, acetamide, chloroacetamide, trichloroacetamide, trifluoroacetamide, phenylacetamide, 3-phenylpropanamide, picolinamide, 3-pyridylcarboxamide, N-

benzoylphenylalanyl derivative, benzamide, p-phenylbenzamide, o-nitrophenylacetamide, o-nitrophenoxyacetamide, acetoacetamide, (N'-dithiobenzylloxycarbonylamino)acetamide, 3-(p-hydroxyphenyl)propanamide, 3-(o-nitrophenyl)propanamide, 2-methyl-2-(o-nitrophenoxy)propanamide, 2-methyl-2-(o-phenylazophenoxy)propanamide, 4-chlorobutanamide, 3-methyl-3-nitrobutanamide, o-nitrocinnamide, N-acetylmethionine derivative, o-nitrobenzamide, o-(benzoyloxymethyl)benzamide, 4,5-diphenyl-3-oxazolin-2-one, N-phthalimide, N-dithiasuccinimide (Dts), N-2,3-diphenylmaleimide, N-2,5-dimethylpyrrole, N-1,1,4,4-tetramethyldisilylazacyclopentane adduct (STABASE), 5-substituted 1,3-dimethyl-1,3,5-triazacyclohexan-2-one, 5-substituted 1,3-dibenzyl-1,3,5-triazacyclohexan-2-one, 1-substituted 3,5-dinitro-4-pyridone, N-methylamine, N-allylamine, N-[2-(trimethylsilyl)ethoxy]methylamine (SEM), N-3-acetoxypropylamine, N-(1-isopropyl-4-nitro-2-oxo-3-pyrroline-3-yl)amine, quaternary ammonium salts, N-benzylamine, N-di(4-methoxyphenyl)methylamine, N-5-dibenzosuberylamine, N-triphenylmethylamine (Tr), N-[(4-methoxyphenyl)diphenylmethyl]amine (MMTr), N-9-phenylfluorenylamine (PhF), N-2,7-dichloro-9-fluorenylmethyleneamine, N-ferrocenylmethylamino (Fcm), N-2-picolylamino N'-oxide, N-1,1-dimethylthiomethyleneamine, N-benzylideneamine, N-p-methoxybenzylideneamine, N-diphenylmethyleneamine, N-[(2-pyridyl)mesityl]methyleneamine, N-(N',N'-dimethylaminomethylene)amine, N,N'-isopropylidenediamine, N-p-nitrobenzylideneamine, N-salicylideneamine, N-5-chlorosalicylideneamine, N-(5-chloro-2-hydroxyphenyl)phenylmethyleneamine, N-cyclohexylideneamine, N-(5,5-dimethyl-3-oxo-1-cyclohexenyl)amine, N-borane derivative, N-diphenylborinic acid derivative, N-[phenyl(pentacarbonylchromium- or tungsten)carbonyl]amine, N-copper chelate, N-zinc chelate, N-nitroamine, N-nitrosoamine, amine N-oxide, diphenylphosphinamide (Dpp), dimethylthiophosphinamide (Mpt), diphenylthiophosphinamide (Ppt), dialkyl phosphoramidates, dibenzyl phosphoramidate, diphenyl phosphoramidate, benzenesulfenamide, o-nitrobenzenesulfenamide (Nps), 2,4-dinitrobenzenesulfenamide, pentachlorobenzenesulfenamide, 2-nitro-4-methoxybenzenesulfenamide, triphenylmethylsulfenamide, 3-nitropyridinesulfenamide (Npys), p-toluenesulfonamide (Ts), benzenesulfonamide, 2,3,6-trimethyl-4-methoxybenzenesulfonamide (Mtr), 2,4,6-trimethoxybenzenesulfonamide (Mtb), 2,6-dimethyl-4-methoxybenzenesulfonamide (Pme), 2,3,5,6-tetramethyl-4-methoxybenzenesulfonamide (Mte), 4-methoxybenzenesulfonamide (Mbs), 2,4,6-trimethylbenzenesulfonamide (Mts), 2,6-dimethoxy-4-methylbenzenesulfonamide (iMds), 2,2,5,7,8-pentamethylchroman-6-sulfonamide (Pmc), methanesulfonamide (Ms), β -trimethylsilylethanesulfonamide (SES), 9-


anthracenesulfonamide, 4-(4',8'-dimethoxynaphthylmethyl)benzenesulfonamide (DNMBS), benzylsulfonamide, trifluoromethylsulfonamide, and phenacysulfonamide.

Exemplary hydroxyl protecting groups include methyl, methoxymethyl (MOM),
 5 methylthiomethyl (MTM), t-butylthiomethyl, (phenyldimethylsilyl)methoxymethyl (SMOM), benzyloxymethyl (BOM), p-methoxybenzyloxymethyl (PMBM), (4-methoxyphenoxy)methyl (p-AOM), guaiacolmethyl (GUM), t-butoxymethyl, 4-pentenylloxymethyl (POM), siloxymethyl, 2-methoxyethoxymethyl (MEM), 2,2,2-trichloroethoxymethyl, bis(2-chloroethoxy)methyl, 2-(trimethylsilyl)ethoxymethyl (SEMOR), tetrahydropyranyl (THP), 3-
 10 bromotetrahydropyranyl, tetrahydrothiopyranyl, 1-methoxycyclohexyl, 4-methoxytetrahydropyranyl (MTHP), 4-methoxytetrahydrothiopyranyl, 4-methoxytetrahydrothiopyranyl S,S-dioxide, 1-[(2-chloro-4-methyl)phenyl]-4-methoxypiperidin-4-yl (CTMP), 1,4-dioxan-2-yl, tetrahydrofuranyl, tetrahydrothiofuranyl, 2,3,3a,4,5,6,7,7a-octahydro-7,8,8-trimethyl-4,7-methanobenzofuran-2-yl, 1-ethoxyethyl, 1-
 15 (2-chloroethoxy)ethyl, 1-methyl-1-methoxyethyl, 1-methyl 1 benzyloxyethyl, 1-methyl-1-benzyloxy-2-fluoroethyl, 2,2,2-trichloroethyl, 2-trimethylsilylethyl, 2-(phenylselenyl)ethyl, t-butyl, allyl, p-chlorophenyl, p-methoxyphenyl, 2,4-dinitrophenyl, benzyl, p-methoxybenzyl, 3,4-dimethoxybenzyl, o-nitrobenzyl, p-nitrobenzyl, p-halobenzyl, 2,6-dichlorobenzyl, p-cyanobenzyl, p-phenylbenzyl, 2-picolyl, 4-picolyl, 3-methyl-2-picolyl N-oxido,
 20 diphenylmethyl, p,p'-dinitrobenzhydryl, 5-dibenzosuberyl, triphenylmethyl, α-naphthyldiphenylmethyl, p-methoxyphenyldiphenylmethyl, di(p-methoxyphenyl)phenylmethyl, tri(p-methoxyphenyl)methyl, 4-(4'-bromophenacyloxyphenyl)diphenylmethyl, 4,4',4''-tris(4,5-dichlorophthalimidophenyl)methyl, 4,4',4''-tris(levulinoyloxyphenyl)methyl, 4,4',4''-tris(benzoyloxyphenyl)methyl, 3-(imidazol-1-yl)bis(4',4''-dimethoxyphenyl)methyl, 1,1-bis(4-methoxyphenyl)-1'-pyrenylmethyl, 9-anthryl, 9-(9-phenyl)xanthenyl, 9-(9-phenyl-10-oxo)anthryl, 1,3-benzodithiolan-2-yl, benzisothiazolyl S,S-dioxido, trimethylsilyl (TMS), triethylsilyl (TES), triisopropylsilyl (TIPS), dimethylisopropylsilyl (IPDMS), diethylisopropylsilyl (DEIPS), dimethylhexylsilyl, t-butyl dimethylsilyl (TBDMS), t-butyl diphenylsilyl (TBDPS), tribenzylsilyl, tri-p-xylylsilyl, triphenylsilyl, diphenylmethylsilyl
 30 (DPMS), t-butylmethoxyphenylsilyl (TBMPS), formate, benzoylformate, acetate, chloroacetate, dichloroacetate, trichloroacetate, trifluoroacetate, methoxyacetate, triphenylmethoxyacetate, phenoxyacetate, p-chlorophenoxyacetate, 3-phenylpropionate, 4-oxopentanoate (levulinate), 4,4-(ethylenedithio)pentanoate (levulinoyldithioacetal), pivaloate, adamantate, crotonate, 4-methoxycrotonate, benzoate, p-phenylbenzoate, 2,4,6-trimethylbenzoate (mesitoate), alkyl

methyl carbonate, 9-fluorenylmethyl carbonate (Fmoc), alkyl ethyl carbonate, alkyl 2,2,2-trichloroethyl carbonate (Troc), 2-(trimethylsilyl)ethyl carbonate (TMSEC), 2-(phenylsulfonyl) ethyl carbonate (Psec), 2-(triphenylphosphonio) ethyl carbonate (Peoc), alkyl isobutyl carbonate, alkyl vinyl carbonate alkyl allyl carbonate, alkyl p-nitrophenyl carbonate, alkyl benzyl
 5 carbonate, alkyl p methoxybenzyl carbonate, alkyl 3,4-dimethoxybenzyl carbonate, alkyl o-nitrobenzyl carbonate, alkyl p-nitrobenzyl carbonate, alkyl S-benzyl thiocarbonate, 4-ethoxy-1-naphthyl carbonate, methyl dithiocarbonate, 2-iodobenzoate, 4-azidobutyrate, 4-nitro-4-methylpentanoate, o-(dibromomethyl)benzoate, 2-formylbenzenesulfonate, 2-(methylthiomethoxy)ethyl, 4-(methylthiomethoxy)butyrate, 2-(methylthiomethoxymethyl)benzoate, 2,6-dichloro-4-methylphenoxyacetate, 2,6-dichloro-4-(1,1,3,3-tetramethylbutyl)phenoxyacetate, 2,4-bis(1,1-dimethylpropyl)phenoxyacetate, chlorodiphenylacetate, isobutyrate, monosuccinoate, (E)-2-methyl-2-butenate, o-(methoxycarbonyl)benzoate, α -naphthoate, nitrate, alkyl N,N,N',N'-tetramethylphosphorodiamidate, alkyl N-phenylcarbamate, borate, dimethylphosphinothioyl,
 15 alkyl 2,4-dinitrophenylsulfonate, sulfate, methanesulfonate (mesylate), benzylsulfonate, and tosylate (Ts). For protecting 1,2- or 1,3-diols, the protecting groups include methylene acetal, ethylidene acetal, 1-t-butylethylidene ketal, 1-phenylethylidene ketal, (4-methoxyphenyl)ethylidene acetal, 2,2,2-trichloroethylidene acetal, acetonide, cyclopentylidene ketal, cyclohexylidene ketal, cycloheptylidene ketal, benzylidene acetal, p-methoxybenzylidene
 20 acetal, 2,4-dimethoxybenzylidene ketal, 3,4-dimethoxybenzylidene acetal, 2-nitrobenzylidene acetal, methoxymethylene acetal, ethoxymethylene acetal, dimethoxymethylene ortho ester, 1-methoxyethylidene ortho ester, 1-ethoxyethylidene ortho ester, 1,2-dimethoxyethylidene ortho ester, α methoxybenzylidene ortho ester, 1-(N,N-dimethylamino)ethylidene derivative, α -(N,N'-dimethylamino)benzylidene derivative, 2-oxacyclopentylidene ortho ester, di-t-butylsilylene group (DTBS), 1,3-(1,1,3,3-tetraisopropylidisiloxanylidene) derivative (TIPDS), tetra-t-butoxydisiloxane-1,3-diylidene derivative (TBDS), cyclic carbonates, cyclic boronates, ethyl boronate, and phenyl boronate.

One of ordinary skill in the art will appreciate that the choice of hydroxyl and amine protecting
 30 groups can be such that these groups are removed at the same time (e.g., when both protecting groups are acid labile or base labile). Alternatively, such groups can be removed in a step-wise fashion (e.g., when one protecting group is removed first by one set of removal conditions and the other protecting group is removed second by a different set of removal conditions). Such methods are readily understood by one of ordinary skill in the art.


In certain embodiments, the present invention provides a compound of any of formulae **II-a**, **II-b**, **II-c**, and **II-d**:



5

U-a

II-b





**II-ε**

II-d


wherein each of X, Y, m, n, p, L¹, L², R¹, R², R³, R⁴, R⁵, and R⁶ is as defined and described herein.


10

Exemplary triblock copolymers of the present invention are set forth below:



15






5 wherein each of m, n, and p is as defined and described herein.

In some embodiments, the present invention provides a polymer foam, comprising:

(a) one or more triblock copolymers of formula I:



10

wherein each of X, Y, m, n, p, L¹, L², R¹, R², R³, R⁴, R⁵, and R⁶ is as defined and described herein; and


(b) wherein the copolymers are chemically interspersed (bound) between urethane and/or urea linkages (i.e., at the bond designated with ζ).

15

The invention further provides a pre-formed soft segment of the formula I as defined above. In some embodiments, the present invention provides a polyurethane/urea foam comprising a soft segment triblock copolymer of formula I.

In some embodiments, the present invention provides a viscoelastic biostable water blown foam, comprising:

(a) one or more triblock copolymers of formula I:



wherein each of X, Y, m, n, p, L¹, L², R¹, R², R³, R⁴, R⁵, and R⁶ is as defined and described herein; and

(b) wherein the copolymers are chemically interspersed (bound) between urethane and/or
10 urea linkages (i.e., at the bond designated with ζ).

It has been surprisingly found that polyurethanes and/or polyureas comprising a triblock copolymer of the present invention are stable to gastric fluid. Such polyurethanes and polyureas prepared using triblock copolymers of the present invention are viscoelastic and stable to gastric
15 fluid. In some embodiments, a provided viscoelastic material is a foam.

In certain embodiments, a provided biostable foam is stable to gastric fluid. In some embodiments, a provided biostable foam is stable to gastric fluid for at least one year. In some embodiments, a provided biostable foam is stable to gastric fluid for at least 3 months, for at
20 least 4 months, for at least 5 months, for at least 6 months, for at least 7 months, for at least 8 months, for at least 9 months, for at least 10 months, for at least 11 months, or for at least one year. Methods for determining stability of a provided biostable foam are known in the art utilizing simulated gastric fluid and include those described in detail in the Exemplification,
infra.

25

In some embodiments, a provided viscoelastic foam, comprising a triblock copolymer of the present invention, is characterized in that the foam takes up less than about 30% by weight of water at equilibrium. In certain embodiments, a provided viscoelastic foam takes up less than about 5%, less than about 10%, less than about 15%, less than about 20%, less than about 25%,
30 or less than about 30% by weight of water at equilibrium. One of ordinary skill in the art will appreciate that such chemical stability (i.e., in gastric fluid and therefore at very low pH) and hydrophobicity (i.e., water uptake of less than about 30% by weight) are characteristics that differ

dramatically from known siloxane polymers that are utilized in, e.g., the manufacture of contact lenses. For example, siloxane polymer that are utilized in, e.g., the manufacture of contact lenses require a water uptake of 50-120%.

- 5 As described above, the present invention provides a viscoelastic foam comprising a triblock copolymer of the present invention. It was surprisingly found that a provided foam has a high elongation capacity and the ability to recover very slowly following elongation. Indeed, it was found that a provided viscoelastic foam has an elongation capacity of about 200-1200%. In some embodiments, a provided viscoelastic foam has an elongation capacity of about 500%.

10

In some embodiments, a provided viscoelastic foam has a tensile strength of about 0.1 to about 1.0 MPa. In certain embodiments, a provided viscoelastic foam has a tensile strength of about 0.25 to about 0.5 MPa.

- 15 In some embodiments, a provided viscoelastic foam has a Young's Modulus of about 0.1 to about 0.6 MPa. In certain embodiments, a provided viscoelastic foam has a Young's Modulus of about 0.1 to about 0.5 MPa.

- One of ordinary skill in the art will appreciate that, depending upon the physical characteristics required for a particular use of a provided foam, a foam of varying densities can be prepared. For example, a valve having a thinner wall would require a foam having a higher density than a similar valve having a thicker wall in order to result in each valve having a similar physical characteristic (e.g., tensile strength, and the like). Thus, in certain embodiments, a provided viscoelastic foam has a density of 0.1 to 1.5 g/cm³. In certain embodiments, a provided viscoelastic foam has a density of 0.3 to 1.2 g/cm³. In certain embodiments, a provided viscoelastic foam has a density of 0.8 to 0.9 g/cm³. In some embodiments, a provided viscoelastic foam has a density of 0.5 to 0.6 g/cm³.
- 20
- 25

- In certain embodiments, the present invention provides polyether-siloxane and polyether-fluorosiloxane polyurethane materials with a greatly reduced number of weak-links as illustrated by Figure 98 and Figure 99. This was achieved by preforming the soft segment prior to the polyurethane reaction. In the examples below a triblock copolymer based on polydimethyl siloxane and polypropylene oxide was used but it will be appreciated that other triblock copolymers such as those formed from polysiloxanes and poly(ethylene oxide),
- 30

poly(difluoromethyl ethylene oxide), poly(trifluoromethyl ethylene oxide), poly(propylene oxide), poly(difluoromethyl propylene oxide), poly(propylene oxide), poly(trifluoromethyl propylene oxide), poly(butylene oxide), poly(tetramethylene ether glycol), poly(tetrahydrofuran), poly(oxymethylene), poly(ether ketone), poly(etherether ketone) and copolymers thereof,
 5 poly(dimethylsiloxane), poly(diethylsiloxane) and higher alkyl siloxanes, poly(methyl phenyl siloxane), poly(diphenyl siloxane), poly(methyl di-fluoroethyl siloxane), poly(methyl tri-fluoroethyl siloxane), poly(phenyl di-fluoroethyl siloxane), poly(phenyl tri-fluoroethyl siloxane) and copolymers thereof, poly(ethylene terephthalate) (PET), poly(ethylene terephthalate ionomer) (PETI), poly(ethylene naphthalate) (PEN), poly(methylene naphthalate) (PTN),
 10 poly(butylene terephthalate) (PBT), poly(butylene naphthalate) (PBN) and polycarbonate could be used.

Referring to Figure 98, copolymers of the form ABA, ABC and BAB were produced from homopolymers of polysiloxane and polypropylene oxide which were covalently linked using
 15 bonds less labile than urethane/urea. The molecular weight and chemical characteristics of such homopolymers were tailored to achieve a pre-soft-segment with the appropriate balance of hydrophilicity/hydrophobicity. Without wishing to be bound by any particular theory, it is believed that by using a non-urethane linked tri-block copolymer instead of the constituent homopolymers as soft segments that the mechanical characteristics and hydrolytic stability of the
 20 resulting material is substantially improved.

In some embodiments, the present invention provides a foam comprising a copolymer of the present invention. Such foams offer specific advantages over solid elastomers, especially for gastrointestinal device applications. These advantages include enhanced biostability in the
 25 gastric environment, compressibility, viscoelasticity and high 'surface area to volume ratio'. The foam formulations of the invention can mimic mechanical characteristics of the native gastrointestinal tissue.

A biostable water blown foam was prepared from heterogeneous reagents.

30

The prior art describes polyurethane foams that are prepared by the sequential reaction of polymer chains to one another resulting in a high molecular weight solid material. In all cases the polymeric precursors described in the art are linked together by urethane/urea linkages as illustrated in Figure 97. However, each urethane/urea linkage is a possible site for degradation.

In the invention we have prepared a biostable polyurethane/urea foam with much fewer 'weak links' by using co-polymer precursors as shown in Figure 98.


- 5 Polyurethane reactions have historically been carried out in a single phase due to ease of processing. However, we have made novel materials by combining physically heterogenous reaction pre-cursors together to form a stable two-phase dispersion ('water-in-oil') which was then reacted to form a foam.

10

EXEMPLIFICATION

In two specific examples X and Y are both polyethers namely poly(propylene oxide) (PPO). These were formulated into copolymers with poly(dimethylsiloxane) (PDMS) and poly(trifluoropropyl methylsiloxane) respectively in varying ratios as described by the following formulae:


15



The formulations contained a number of other components including:


Branching agent – DEOA

20



Diethanolamine (DEOA) is used as a branching agent although it is sometimes known as a crosslinking agent. The molecular weight of DEOA is 105.14 g/mol. The effect of the DEOA is to influence softness and elasticity of the end polymer.

Gelling catalyst – Bismuth Neodecanoate (BICAT)



Bismuth neodecanoate is supplied as BiCat 8108M from Shepherd. It has a molecular weight of 722.75 g/mol. This catalyst is used to facilitate the complete reaction between isocyanate and hydroxyl or amine functional groups.

5 **Blowing Catalyst – DABCO 33-iv**



DABCO is a common blowing catalyst for reaction between NCO and H₂O. It has a molecular weight of 112.17 g/mol. This catalyst has the effect, in combination with H₂O, of manipulating the foam rise characteristics.

10


Example 1

Synthesis of aliphatic linked fluorosiloxane based triblock copolymer pre-soft-segment:

This is a 2 step process. In the first step silanol terminated poly(trifluoropropyl methyl siloxane) is converted into its dihydride derivative. In the next step, this dihydride derivative is reacted
15 with the allyl terminated poly(propylene glycol).

The synthetic procedure is as follows:

Step 1:




20 To a 4 neck separable flask fitted with mechanical stirrer, was added 40 g of Silanol terminated poly(trifluoropropyl methylsiloxane) (FMS-9922 from Gelest Inc.) and this was mixed with 50ml of toluene and fitted with a continuous flush of Nitrogen. To the reaction mixture 7.57 g of dimethyl chlorosilane (DMCS, from Sigma Aldrich) was added slowly over about 20 minutes keeping the temperature of the mixture constant at 30°C. With each addition of dimethyl
25 chlorosilane, the mixture became hazy but cleared in a short period of time. Once the addition of dimethyl chlorosilane was complete, the mixture was heated to 90°C for 3 hours. The reaction

was then washed with excess water several times to reduce the acidity of the mixture. The resulting mixture was dried over silica gel, filtered and vacuumed to remove solvent and traces of water at 65°C overnight. A clear fluid was then obtained with a very strong Si-H band in infra red spectroscopy (IR) at 2130 cm^{-1} , which confirms the reaction. GPC analysis showed the

5 molecular weight to be 1200g/mol.

Step 2:



To 90 ml of reagent grade toluene in a 4 neck separable flask fitted with mechanical stirrer, 46.67g of Allyl terminated poly(propylene glycol) (MW=700g/mol, Jiangsu GPRO Group Co.)

10 was added and then heated to reflux. Then 40g of Hydride terminated FMS-9922 was dissolved in 50ml of reagent grade toluene and the temperature raised to around 90°C. To the reaction mixture 2 drops of hexachloroplatinic(IV) acid (0.01M H_2PtCl_6 from Sigma) solution in isopropanol (by Merck) was then added. After this catalyst solution had been added, the mixture was refluxed for 1 hour and the solvent distilled off in order to get the final product. The

15 reaction was followed by H-NMR and gel permeation chromatography (GPC) confirmed the final molecular weight to be 2700g/mol.


Table 1. Resulting polymer block ratios

Stoichiometric ratios for reaction product:

Polymer block	PO	F-SiO	PO
	m	n	p
Ratio	11	9.7	11

Synthesis of aliphatic linked dimethylsiloxane based triblock copolymer pre-soft-segment:

To 130ml of reagent grade toluene in a separable flask fitted with a mechanical stirrer, was added 64g of allyl terminated poly(propylene glycol) (MW=700g/mol, Jiangsu GPRO Co.) and both were mixed and heated to reflux. Then 40g of hydride terminated poly(dimethyl siloxane) (Silmer H Di 10 by Siltech Corp.) was dissolved in 50ml reagent grade toluene and the temperature raised to around 90°C. To this reaction mixture 2 drops of hexachloroplatinic(IV) acid (0.01M H_2PtCl_6 from Sigma) solution in isopropanol was added. After this catalyst solution was added, the mixture was refluxed for 1 hour and then the solvent was distilled off in order to get the final product. The reaction was followed with H-NMR and gel permeation chromatography (GPC) confirmed the final molecular weight of the product to be 2300g/mol.



10


Table 2. Polymer block ratios

Stoichiometric ratios for reaction product:

Polymer block	PO	SiO	PO
	m	n	p
Ratio	11	11	11

Example 3**Synthesis of aromatic linked siloxane based triblock copolymer pre-soft-segment:**

55



To a 100 ml separable flask fitted with a mechanical stirrer, 15g of hydroxy terminated polydimethyl siloxane (DMS-S14 from Gelest Inc.) was added along with 5.36g of di-chloro p-xylene (from Sigma) and 0.0089g of Copper(II) acetylacetonate ($\text{Cu}(\text{Acac})_2$ from Sigma). The reaction mixture was refluxed at 110°C for 5 hrs. At this point, 19.77g of hydroxy terminated poly(propylene glycol) (from Sigma) was added dropwise and the reaction mixture was then refluxed for another 15hr. The progress of reaction was followed by ^1H -NMR and the final molecular weight, determined by gel permeation chromatography (GPC), was 3000 g/mol.

H-NMR analysis: Solvent used for ^1H -NMR analysis is CDCl_3 .

- 10 Aromatic H = 7.25-7.45 ppm, $-\text{CH}_2 = 4.5\text{-}4.6$ ppm, $-\text{CH}_3$ (of PPO) = 1-1.4 ppm, $-\text{CH}_2$ (of PPO) = 3.2-3.8 ppm, $-\text{OH}$ (of PPO) = 3.8-4 ppm, $-\text{CH}_3$ (silanol) = 0.5-0.8 ppm.

Table 3. Resulting polymer block ratios


Stoichiometric ratios for reaction product:

Polymer block	PO	SiO	PO
	m	n	p
Ratio	14	15.5	14

Example 4

- 15 **Synthesis of aromatic linked fluorosiloxane based triblock copolymer pre-soft-segment:**

56



To a 100 ml separable flask fitted with a mechanical stirrer, 15g of hydroxy terminated polytrifluoromethyl siloxane (FMS-9922 , Gelest inc.) was added along with 5.9g of di-chloro p-xylene and 0.0098g of copper(II) acetylacetonate ($\text{Cu}(\text{Acac})_2$ from Sigma). The reaction mixture was refluxed at 110 °C for 5 hrs. At this point, 21.75g of hydroxy terminated poly(propylene glycol) (from Sigma) was added dropwise to the reaction mixture. The reaction was refluxed for another 15hr. The progress of reaction was followed by ^1H -NMR analysis and the molecular weight, determined by gel permeation chromatography (GPC), was 3100 g/mol.

^1H -NMR analysis: Solvent used for H-NMR analysis is CDCl_3 .

- 10 Aromatic ^1H = 7.25-7.45 ppm, $-\text{CH}_2$ = 4.5-4.6 ppm, $-\text{CH}_3$ (of PPO)= 1-1.4 ppm, $-\text{CH}_2$ (of PPO)= 3.2-3.8 ppm, $---\text{OH}$ (of PPO)= 3.8-4 ppm, $-\text{CH}_3$ (silanol)= 0.5-0.8 ppm.

Table 4. Polymer block ratios

Stoichiometric ratios for reaction product:

Polymer block	PO	FSiO	PO
	m	n	p
Ratio	14	9.2	14

Example 5

15 Preparation of water blown foam:

The pre-soft segments prepared can be described as having polymer block ratios which are numerically represented by the letters m, n and o for the constituents PO/SiO/PO respectively.

The triblock copolymers prepared in Examples 1 and 2 with specific m, n, o ratios were formulated into polyurethane/urea foams as illustrated by Table 7.

The process for preparing the foam was a two-step procedure. The following describes the method of manufacture of the first product in Table 7. The same procedure was used to prepare other foams as described by Table 8.

- Step 1) Firstly a mixture was made with 0.041g of DABCO LV-33 (Airproducts), 0.120g of bismuth neodecanoate (Bicat 8108M from Shepherd chemicals), 0.467g of diethanol amine (DEOA, from Sigma), 7.917 g of synthesized block copolymer, 0.200g water and 0.1 g of surfactant (Niax L-618 from Airproducts) in a plastic flat bottomed container. This is then thoroughly mixed manually for 30 sec until a homogenous mixture was obtained.
- Step 2) To the above mixture, 15g of a diisocyanate prepolymer (PPT 95A Airproducts) was added. This was then thoroughly mixed by a mechanical stirrer for about 5 seconds. The material was then molded and cured at 70°C for 2.5 hours and post cured at 50°C for another 3 hours.

Table 5. Formulation details for foam

Formulation Identification	Polymer block (PO/SiO/PO) Ratio m:n:p	DABCO	BICAT	DEOA	H ₂ O
VF230209A	11:11:11	0.0325	0.015	0.40	1.0
VF090309B	11:9:11	0.0325	0.015	0.40	1.0

Example 6

Comparative example of formulation of water blown foam from triblock copolymer pre-soft segment and individual homopolymers:

- Polyurethane/urea polymer foams from Example 5 were compared to foams made from the stoichiometric equivalent homopolymer soft segments. The foams with homopolymer based soft segments (VF130309 and VF190309) shown in Figure 100 were produced as follows (VF130309):

- Step 1) Firstly a mixture was made with 0.041g of DABCO LV-33 (Airproducts), 0.120g of bismuth neodecanoate (Bicat 8108M from Shepherd chemicals), 0.467g of diethanol amine (DEOA, from Sigma), 3.056g of poly(dimethyl siloxane) diol (DMS-s14 Gelest Inc.), 1.633 g of polypropylene oxide (Mw = 700g/mol), 0.200g water and 0.1 g of surfactant (Niax L-618 from Airproducts). These were added to a plastic flat bottomed container and were thoroughly mixed manually for 30 sec until a homogenous mixture was obtained.
- Step 2) To the above mixture, 15g of a diisocyanate prepolymer (PPT 95A Airproducts) was added. This was then thoroughly mixed by a mechanical stirrer for 5 seconds. The material was then molded and cured at 70°C for 2.5 hours and post cured at 50°C for another 3 hours.

The foams in this example were made into dumbell shapes for tensile testing. Figures 100 and 101 illustrate the difference in mechanical behaviour between the comparative materials indicating a favourable lowering in modulus for the triblock copolymer pre-soft-segments.

Example 7

Comparative stability of triblock copolymer soft segment versus homopolymer soft segment [0001] Tensile test specimens were prepared in the same manner to the materials used in Example 4 and were subjected to accelerated aging in simulated gastric fluid (as per United States Pharmacopeia, "USP"). The materials produced with the pre-synthesised triblock copolymer soft segments resulted in substantially improved mechanical stability in gastric fluid as compared to the urethane/urea linked homopolymer equivalent as illustrated in Figure 90. This facilitates the use of such materials for prolonged periods in digestive and more specifically gastric environments.

Example 8

Preparation of water blown foams

Several water blown polyurethane/urea foams were also produced with varying PO/EO/SiO polymer block ratios. The process for preparing the foam as described above was used.

Table 6. Water blown formulations incorporating siloxane containing copolymer pre-soft-segments.

Polymer block ratio (PO/EO/SiO) m:n:p	DABCO	BICAT	DEOA	H ₂ O
41.5:8.3:0.5	0.114	0.022	0.22	2.72
40.2:7.8:0.5	0.114	0.022	0.22	2.72
37.5:7:0.5	0.114	0.022	0.22	2.72
33.5:5.7:0.5	0.114	0.022	0.22	2.72
29.6:4.4:0.5	0.114	0.022	0.22	2.72
21.6:1.8:0.5	0.114	0.022	0.22	2.72
19:1:0.5	0.114	0.022	0.22	2.72
29.6:4.5:1.1	0.114	0.022	0.22	2.72

The results from the formulations described in Table 6 are shown in Table 7.

Table 7. Results from mechanical testing of foams from Table 5

Polymer block ratio (PO/EO/SiO) m:n:p	% Elongation	Tensile Strength (N)
41.5:8.3:0.5	233	0.46
40.2:7.8:0.5	243	0.31
37.5:7:0.5	237	0.3
33.5:5.7:0.5	260	0.23
29.6:4.4:0.5	320	0.23
21.6:1.8:0.5	497	0.23
19:1:0.5	462	0.22
29.6:4.5:1.1	437	0.29

5

Example 9

Use Example

Devices for use in the gastrointestinal system have historically not been made from specifically designed materials. Off the shelf materials used for application in the corrosive environment of the stomach have limited biostability and generally lose their functionality after a short time.

10

The foam of the invention can be used for production of a valve of the type described in our US2007-0198048A, the entire contents of which are incorporated herein by reference. The valve has an open position and a closed position. The valve will have a proximal end and a distal end. The valve material can open from the proximal direction when the action of swallowing (liquid

or solid) stretches an orifice by between 100% and 3000% in circumference. The open orifice optionally closes non-elastically over a prolonged period of time, thus mimicing the body's natural response. The duration taken to close may be between 2 and 15 sec. The material can stretch to between 100% - 300% from the distal direction when gas, liquid or solids exceeds a

5 pre-determined force of between 25cmH₂O and 60cmH₂O. In some embodiments, the material absorbs less than 15% of its own mass of water at equilibrium. In some embodiments, the material loses (leaches) less than 3% of it's own mass at equilibrium in water or alcohol. In some embodiments, the material loses less than 10% of its tensile strength when immersed in a simulated gastric fluid at pH 1.2 for 30 days. In some embodiments, the valve material loses less

10 than 25% of its % elongation when immersed in a simulated gastric fluid at pH 1.2 for 30 days.

Example 10

Valve functional testing

The healthy lower esophageal sphincter (LES) remains closed until an individual induces

15 relaxation of the muscle by swallowing and thus allowing food to pass in the antegrade direction. Additionally when an individual belches or vomits they generate enough pressure in the stomach in the retrograde direction to overcome the valve. An anti-reflux valve must enable this functionality when placed in the body, thus a simple functional test is carried out to asses performance.

20

It has been reported that post fundoplication patients have yield pressures between 22 – 45 mmHg and that most of the patients with gastric yield pressure above 40 mmHg experienced problems belching. *See Yield pressure, anatomy of the cardia and gastro-oesophageal reflux.* Ismail, J. Bancewicz, J. Barow British Journal of Surgery. Vol: 82, 1995, pages: 943-947. Thus,

25 in order to facilitate belching but prevent reflux, an absolute upper GYP value of 40 mmHg (550 mmH₂O) is reasonable. It was also reported that patients with visible esophagitis all have gastric yield pressure values under 15 mmHg, therefore, there is good reason to selectively target a minimum gastric yield pressure value that exceeds 15 mmHg. *See Id.* An appropriate minimum gastric yield pressure value would be 15mmHg + 25% margin of error thus resulting in a

30 minimum effective valve yield pressure value of 18.75 mmHg or 255 mmH₂O.

The test apparatus consists of a 1m high vertical tube as shown in Figure 103, to which is connected a peristaltic pump and a fitting that is designed to house the valve to be tested.

The valve to be tested is placed in a water bath at 37 °C for 30 minutes to allow its temperature to equilibrate. Once the temperature of the valve has equilibrated it is then installed into the housing such that the distal closed end of the valve faces the inside of the test apparatus. The pump is then switched on at a rate of 800 ml/min to begin filling the vertical tube. The rising
 5 column of water exerts a pressure that forces the valve shut initially. As the pressure in the column rises the valve reaches a point where it everts and allows the water to flow through. This point, known as the yield pressure, is then recorded and the test repeated four times.

Example 11

10 Rationale for accelerated aging of material

Clinical Condition being simulated

The lower oesophagus of a normal patient can be exposed to the acidic contents of the stomach periodically without any adverse side effects. However, patients with gastro esophageal reflux disease experience damage to the mucosa of the lower oesophagus due to increased exposure to
 15 the gastric contents. Exposure of the lower oesophagus to acidic gastric contents is routinely measured in the clinic using dedicated pH measurement equipment. A typical procedure involves measuring pH over a 24-hour period. The levels of acid exposure in pathological reflux disease patients is summarised in Table 8 from six clinical references. See DeMeester TR, Johnson LF, Joseph GJ, et al. *Patterns of Gastroesophageal Reflux in Health and Disease* Ann. Surg. Oct
 20 1976 459-469; Pandolfino JE, Richter JE, Ours T, et al. *Ambulatory Esophageal pH Monitoring Using a Wireless System* Am. J. Gastro 2003; 98:4; Mahmood Z, McMahon BP, Arfin Q, et al. *Results of endoscopic gastroplasty for gastroesophageal reflux disease: a one year prospective follow-up* Gut 2003; 52:34-9; Park PO, Kjellin T, Appcyard MN, et al. *Results of endoscopic gastroplasty suturing for treatment of GERD: a multicentre trial* Gastrointest endosc 2001;
 25 53:AB115; Filipi CJ, Lehman GA, Rothstein RI, et al. *Transoral flexible endoscopic suturing for treatment of GERD: a multicenter trial* Gastrointest endosc 2001; 53 416-22; and Arts J, Slootmaekers S Sifrim D, et al. *Endoluminal gastroplication (Endocinch) in GERD patient's refractory to PPI therapy* Gastroenterology 2002; 122:A47.

30 **Table 8. Summary of acid exposure in patients with reflux disease**

Investigator	Number of patients	Details	% 24h <pH4
DeMeester	54	Combined refluxers	13.5
Pandolfino	41	Gerd	6.5
Mahmood	21	Gerd	11.11
Park	142	Gerd	8.5
Filipi	64	Gerd	9.6
Arts	20	Gerd	17
Average			<u>11.035</u>

Key Clinical Parameters

Considering that the lower oesophagus is exposed to the acidic pH exposure time for an average of 11% of the measurement period, an accelerated aging methodology can easily be conceived.

- 5 Constant exposure of a test material to the gastric contents (or USP Simulated Gastric Fluid – Reference USP Pharmacopeia) would represent an almost 10-fold increase in the rate of aging. Thus the time required to simulate one year of exposure of the lower oesophagus to the gastric contents is described by equation 1.

$$10 \quad \left(\frac{11.035}{100} \right) \times 365 \text{days} = 40.28 \text{days} \quad \text{Equation 1}$$

Clinical Rationale

- Immersion of test specimens in USP Simulated gastric fluid for 40.27 days at 37 °C will approximate one year's exposure of the lower oesophagus to acidic gastric contents in a GERD
15 patient's scenario.

Simulated Exposure	Real Time
1 year	40.28 days
2 years	80.56 days
3 years	120.84 days

Results of accelerated stability of a valve prepared from a viscoelastic foam of the present invention are depicted in Figures 104 and 105.

20

While we have described a number of embodiments of this invention, it is apparent that our basic examples may be altered to provide other embodiments that utilize the compounds and methods of this invention. Therefore, it will be appreciated that the scope of this invention is to be defined by the appended claims rather than by the specific embodiments that have been
25 represented by way of example.

Various features of the invention are described in detail and illustrated herein. Appropriate features described with reference to one embodiment may be utilised in addition to and/or as a substitute for features described in other embodiments.

30

WO 2011/073969

PCT/IE2010/000075

63

The invention is not limited to the embodiments hereinbefore described which may be varied in detail.

Claims

1. A urological device comprising:
a urological valve, the valve comprising a plurality of valve leaflets, the valve having internally located, stiffening reinforcement members, the stiffening reinforcement members defining a fulcrum or hinge region about which the valve leaflets are movable from a normally closed configuration to an open configuration, the stiffening reinforcement members extending vertically,
the valve having a region of co-action between the valve leaflets, the valve having the normally closed configuration in which the valve leaflets are engaged at the region of co-action and the open configuration in which the leaflets are separated at the co-action region for fluid flow through the valve, the valve being configured to evert automatically on movement between the closed configuration and the open configuration in response to applied urological pressure.
2. A urological device as claimed in claim 1 wherein the valve is of a viscoelastic polymeric foam material.
3. A urological device as claimed in claim 1 or 2 wherein the valve leaflets evert on movement between the closed and the open configuration in response to applied urological pressure.
4. A urological device as claimed in any one of claims 1 to 3 wherein the valve is adapted to open in response to a preset pressure applied over a preset time.
5. A urological device as claimed in claim 4 wherein the valve is adapted to open in response a pressure of at least 750mm H₂O applied for at least 5 seconds.
6. A urological device as claimed in any one of claims 1 to 5 wherein the valve is adapted to remain closed in response to a spike pressure applied for a short time as would be generated by a user coughing.

7. A urological device as claimed in claim 6 wherein the spike pressure is 900mm H₂O applied for a period of less than 0.5 seconds.
8. A urological device as claimed in any one of claims 1 to 7 wherein the valve remains open as fluid flows therethrough without a requirement for a user to apply urological pressure.
9. A urological device as claimed in claim 8 wherein the valve returns to the closed configuration when flow through the valve has substantially stopped.
10. A urological device as claimed in any one of claims 1 to 9 wherein the valve everts on movement from the closed to the open configuration.
11. A urological device as claimed in any one of claims 1-10 wherein the valve reverts on return from the open to the closed configuration.
12. A urological device as claimed in any one of claims 1 to 11 wherein the valve comprises at least three valve leaflets.
13. A urological device as claimed in any one of claims 1 to 12 wherein the valve comprises a main body having a region which defines a hinge about which portion of the valve main body is movable between the closed and open configurations.
14. A urological device as claimed in any one of claims 1 to 13 comprising a support for the valve.
15. A urological device as claimed in claim 14 wherein the support is generally cylindrical.
16. A urological device as claimed in claim 14 or 15 wherein the support is of the same material as that of the valve.
17. A urological device as claimed in claim 16 wherein the valve and support are integrally moulded.

18. A urological device as claimed in any one of claims 14 to 17 comprising a first retainer for locating the device in the bladder.
19. A urological device as claimed in claim 18 wherein the first retainer comprises a flare extending radially outwardly of the support.
20. A urological device as claimed in claim 18 or 19 wherein the first retainer is of the same material as that of the support.
21. A urological device as claimed in any one of claims 18 to 20 wherein the first retainer, the support and the valve are integrally moulded.
22. A urological device as claimed in any one of claims 18 to 21 comprising stiffening means for the first retainer.
23. A urological device as claimed in claim 22 wherein the retainer stiffening means is of a shape memory material such as Nitinol.
24. A urological device as claimed in any one of claims 14 to 23 comprising a second retainer to prevent proximal migration of the device.
25. A urological device as claimed in claim 24 wherein the second retainer comprises a meatal tab.
26. A urological device as claimed in claim 24 wherein the second retainer comprises a bulbous region of compressive material.
27. A urological device as claimed in any one of claims 1 to 26 wherein the device comprises an antimicrobial coating.
28. A urological device as claimed in any one of claims 1 to 27 comprising a support to which the valve is mounted.

29. A urological device as claimed in claim 28 wherein the support is adapted for mounting in a urinary tract.
30. A urological device as claimed in claim 28 or 29 wherein the support comprises a generally tubular member.
31. A urological device as claimed in claim 30 wherein the tubular member comprises a catheter.
32. A urological device as claimed in any one of claims 29 to 31 comprising an anchor for anchoring the support and valve in situ.
33. A urological device as claimed in claim 1 comprising a housing for the valve, the housing having an inlet on one side of the valve and an outlet on the opposite side of the valve.
34. A urological device as claimed in claim 33 wherein the inlet is adapted for mounting to a catheter such as a Foley catheter.
35. A urological device as claimed in claim 33 or 34 wherein the outlet is adapted for mounting to a drainage bag.
36. A urological device as claimed in any one of claims 33 to 35 comprising a collar to support the valve in the housing.
37. A urological device as claimed in claim 36 wherein the valve comprises a valve body and the collar is arranged to engage the valve body to control the pressure at which the valve moves from the open to the closed configuration and/or from the closed to the open configuration.
38. A urological device comprising:
a urological valve, the valve comprising a plurality of valve leaflets, the valve having internally located, stiffening reinforcement members, the stiffening reinforcement members defining a fulcrum or hinge region about which the valve leaflets are moveable from a normally

closed configuration to an open configuration, the stiffening reinforcement members being spaced about an internal circumference of the valve,

the valve having a region of co-action between the valve leaflets, the valve having the normally closed configuration in which the valve leaflets are engaged at the region of co-action and the open configuration in which the leaflets are separated at the co-action region for fluid flow through the valve, the valve being configured to evert automatically on movement between the closed configuration and the open configuration in response to applied urological pressure.

39. The urological device as claimed in claim 38, wherein the valve is adapted to open in response to a preset pressure applied over a preset time.

40. The urological device as claimed in claim 39, wherein the valve is adapted to open in response to a pressure of at least 750 mm H₂O applied for at least 5 seconds.

41. The urological device as claimed in claim 38, wherein the valve is adapted to remain closed in response to a spike pressure applied for a short time as would be generated by a user coughing.

42. The urological device as claimed in claim 41, wherein the spike pressure is 900 mm H₂O applied for a period of less than 0.5 seconds.

43. The urological device as claimed in claim 38, wherein the valve remains open as fluid flows therethrough without a requirement for a user to apply urological pressure.

44. The urological device as claimed in claim 43, wherein the valve returns to the closed configuration when flow through the valve has substantially stopped.



45. The urological device as claimed in claim 38, wherein the valve reverts on return from the open to the closed configuration.

46. The urological device as claimed in claim 38, wherein the valve includes at least three valve leaflets.
47. The urological device as claimed in claim 38, wherein the valve includes a main body having a region which defines a hinge about which a portion of the valve main body is movable between the closed and open configurations .
48. A kit comprising a Foley catheter, an external housing, and a urological valve;
wherein the urological valve comprises a plurality of valve leaflets, the urological valve having a region of co-aptation between the valve leaflets, the urological valve having a normally closed configuration in which the valve leaflets are engaged at the region of co-aptation and an open configuration in which the leaflets are separated at the region of co-aptation for fluid flow through the urological valve, with the urological valve being configured to evert automatically on movement between the closed configuration and the open configuration in response to an applied urological pressure;
wherein the external housing is configured to house the urological valve and includes a fitting in a proximal end configured to connect to the Foley catheter and a fitting in a distal end configured to connect to a drainage bag.
49. The kit of claim 48, wherein the urological valve has internally located stiffening reinforcement members, the stiffening reinforcement members defining a fulcrum or hinge region about which the valve leaflets are movable from the normally closed configuration to the open configuration.
50. The kit of claim 49, wherein the stiffening reinforcement members extend vertically.
51. The kit of claim 49, wherein the stiffening reinforcement members are spaced about an internal circumference of the valve.

52. The kit of claim 48, wherein the urological valve is of a viscoelastic polymeric foam material.
53. The kit of claim 48, wherein the valve leaflets evert on movement between the closed and the open configuration in response to applied urological pressure.
54. The kit of claim 53, wherein the urological valve is adapted to open in response to a preset pressure applied over a preset time.
55. The kit of claim 54, wherein the urological valve is adapted to open in response to a pressure of at least 750 mm H₂O applied for at least 5 seconds.
56. The kit of claim 48, wherein the urological valve is adapted to remain closed in response to a spike pressure applied for a short time as would be generated by a user coughing.
57. The kit of claim 56, wherein the spike pressure is 900 mm H₂O applied for a period of less than 0.5 seconds.
58. The kit of claim 48, wherein the urological valve remains open as fluid flows therethrough without a requirement for a user to apply urological pressure.
59. The kit of claim 48, wherein the urological valve returns to the closed configuration when flow through the valve has substantially stopped.
60. The kit of claim 48, wherein the urological valve everts on movement from the closed to the open configuration.
61. The kit of claim 48, wherein the urological valve reverts on return from the open to the closed configuration.
62. The kit of claim 48, wherein the urological valve comprises at least three valve leaflets.

- 63. The kit of claim 48, wherein the urological valve comprises a main body having a region which defines a hinge about which portion of the valve main body is movable between the closed and open configurations.
- 64. The kit of claim 48, wherein the external housing comprises a proximal section and a distal section, which are separable for insertion of a valve.
- 65. The kit of claim 48, wherein the external housing comprises proximal and distal caps.
- 66. The kit of claim 48, wherein the external housing comprises an area for seating the valve.
- 67. The kit of claim 48, wherein the external housing comprises an extended collar, which is adapted for protruding into the proximal lumen of the valve.

1/47

Fig. 1Fig. 2

2/47




Fig. 3








Fig. 4

3/47

Fig. 6Fig. 5Fig. 8Fig. 7

4/47






Fig. 10




Fig. 14




Fig. 13




Fig. 12

5/47




Fig. 15




Fig. 18




Fig. 16




Fig. 19




Fig. 17





Fig. 20

6/47

Fig. 21

7/47




Fig. 23




Fig. 22

8/47




Fig. 26





Fig. 25



30

Fig. 24

9/47




Fig. 27




Fig. 28




Fig. 29




Fig. 34

11/47




Fig. 30

12/47




Fig. 33




Fig. 32






Fig. 31

13/47



14/47




Fig. 39




Fig. 38




Fig. 37

15/47




Fig. 40

16/47




Fig. 42




Fig. 43




Fig. 41

17/47








Fig. 44

18/47






WO 2011/073969

PCT/IE2010/000075



20/47





22/47




Fig. 54




Fig. 53






Fig. 55

23/47



24/47




Fig. 59




Fig. 58




Fig. 60

25/47

Time to encrustation
Proteus Mirabilis




Fig. 61

26/47




Fig. 63




Fig. 62

27/47




Fig. 65

Fig. 64

28/47









Fig. 67

Fig. 66



WO 2011/073969

PCT/IE2010/000075






Fig. 74




Fig. 75

32/47




Fig. 76




Fig. 77




Fig. 78




Fig. 79




Fig. 80




Fig. 81




Fig. 82

34/47




Fig. 83







Fig. 84

35/47



36/47









Fig. 89


38/47



39/47



40/47

Fig. 94

Pressure profile of 9mm (Internal) urological valve during accelerated
bladder filling simulation






Fig. 95




43/47


Prior Art





———— Homopolymer A
----- Homopolymer B
..... Homopolymer C

Fig. 97Fig. 98


44/47




Or

Fig. 99Fig. 100

45/47

Fig. 101

Tensile strength change

Fig. 102

46/47






Fig. 103

47/47

Valve Function stability in Simulated Gastric Fluid

Fig. 104

Mass uptake of Simulated Gastric Fluid

Fig. 105

