



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>B05D 7/14, 3/10, 7/00, C25D 11/18</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/19086</b> <b>(43) International Publication Date:</b> 22 April 1999 (22.04.99)
<b>(21) International Application Number:</b> PCT/GB98/03091 <b>(22) International Filing Date:</b> 13 October 1998 (13.10.98) <b>(30) Priority Data:</b> 9721650.1      13 October 1997 (13.10.97)      GB <b>(71) Applicant (for all designated States except US):</b> ALCAN INTERNATIONAL LIMITED [CA/CA]; 1188 Sherbrooke Street West, Montreal, Québec H3A 3G2 (CA). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> BARLOW, Eric [GB/GB]; 1 Deers Close, Bodicote, Banbury, Oxfordshire OX15 4EA (GB). FOSTER, Mark [GB/GB]; 13 Blenheim Road, Banbury, Oxfordshire OX16 9TQ (GB). PARGETER, Chris [GB/GB]; 27 Beaulieu Close, Banbury, Oxfordshire OX16 8FG (GB). LIMBACH, Peter, Karl, Ferdinand [DE/DE]; Zum Hohen Brunnen 21, D-37075 Göttingen (DE). <b>(74) Agents:</b> PENNANT, Pyers et al.; Stevens Hewlett & Perkins, 1 Serjeants' Inn, Fleet Street, London, Greater London EC4Y 1LL (GB).		<b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> COATED ALUMINIUM WORKPIECE  <b>(57) Abstract</b>  Aluminium alloy sheet having on a surface an anodic oxide film and an overlying coating consisting essentially of at least one adhesion promoter excluding silanes. Sheet for architectural use carries a paint layer over the adhesion promoter coating. Sheet for automobile use may carry an electroconductive paint primer layer over the adhesion promoter coating. Preferred adhesion promoters are polyacrylic acid and pretreatments containing Cr, Mn, Mo, Si, Ti, Zr and F values.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

### COATED ALUMINIUM WORKPIECE

5                   There is a large market in painted aluminium sheet, both for architectural use and for automotive use. There is also a large market for lacquered aluminium sheet for canstock use. In all these applications, the adhesion of the organic coating (typically paint, lacquer or adhesive) to the aluminium metal may not be adequate. Various surface pretreatments  
10   have been proposed and are widely used to improve such adhesion:

- An anodic oxide film is formed on the aluminium surface. Particularly when anodising is done in a phosphoric acid based electrolyte, the outer surface of the anodic oxide film may be extremely rough, including filaments or whiskers, such as to provide an excellent mechanical  
15   key for subsequently applied organic coatings.
- Adhesion promoters are a class of materials that have been used to improve the adhesion of organic coatings to an underlying metal substrate. One example is polyacrylic acid. A chromium-fluoride-phosphate pretreatment has been successfully marketed under the  
20   tradename Accomet C. Other similar treatments contain fluoride values and other transition metals. Such pretreatments may act as adhesion promoters and also provide corrosion resistance.

                    Adhesion promoters have in general been applied to bare metal. This invention is based on the idea that additional advantages may  
25   be obtained if such adhesion promoters are applied to an aluminium metal surface which is not bare.

                    Thus the invention provides an aluminium workpiece having on a surface thereof an anodic oxide film and a coating which consists essentially of at least one adhesion promoter excluding silanes.

30                   A workpiece is an object of indeterminate size and shape. While the invention may have application in connection with extrusions and

- 2 -

other workpieces, it is of principal interest in connection with aluminium sheet, either continuous sheet in the form of coil, or cut sheet which is either flat or has been formed into shaped components e.g. for architectural or automotive or canstock use. Depending on the intended application,  
5 either one surface or both surfaces of the sheet may have the artificially applied aluminium oxide or hydroxide film and the coating.

The term aluminium is here used to include both the pure metal and alloys in which Al is a major component. Preferred are alloys of the 2000, 3000, 5000 and 6000 series of the Aluminum Association Inc  
10 Register.

Preferably the oxide film is an anodic oxide film, e.g. formed by anodising the metal workpiece in an acidic electrolyte. Preferred electrolytes are sulphuric acid, and particularly phosphorus oxyacids including phosphoric acid. Anodising conditions may be chosen, in  
15 accordance with criteria well known in the field, to generate an anodic oxide film having a rough outer surface. The artificially applied aluminium oxide or hydroxide film needs to be thick enough to provide abrasion and corrosion resistance; but not so thick as to have a tendency to spall or crack when a workpiece carrying the film is formed to shape; and, in a  
20 preferred aspect of the invention discussed below, not so thick as to make the coating so electrically resistant that spot-welding is impossible. Preferred thicknesses are in the range 10 – 200 nm particularly 15 - 150 nm, more especially 15 – 50 nm.

Adhesion promoters are known and employed to enhance  
25 adhesive bond strength, or more commonly to enhance the environmental resistance of the substrate surface/adhesive interface to attack by moisture. Adhesion promoters were described by P E Cassidy *et al* in Ind. Eng. Chem. Prod. Res. Development Volume 11, No 2 (1972) pages 170-7; and by A J Kinlock in J Mat. Sci., 15(1980), pages 2141-66 at page  
30 2159. Commercial pretreatments (adhesion promoters) include Alodine NR1453., Alodine NR2010, zirconia/polyacrylic acid, Accomet C

and Safeguard 6000 which contain Ti, Zr, Cr, Mn, Si, F, polyacrylic acid and substituted styrenes.

An adhesion promoter may be a pretreatment comprising one or more of Cr, Mn, Mo, Si, Ti, Zr values. These values are preferably  
5 inorganic, in the sense that they do not contain metal-carbon (or Si-C) bonds, although they may be used in conjunction with organic polymers. The adhesion promoter may also comprise fluoride values or another acid value. They may conveniently be provided by dissolving fluorozirconic acid  $\text{H}_2\text{ZrF}_6$ , or a soluble fluorozirconate salt, in water; alternatively, a  
10 corresponding acid or salt of Cr, Mn, Mo, Si or Ti may be used. Cr is preferably absent on account of its toxicity and effluent problems. Fluorozirconate (or other fluoro complex) is preferably present at a concentration of 0.1 – 200 g/l, particularly from 10 – 100 g/l, of a formulation for application to an aluminium workpiece.

15 In the case of Cr and Mn, there is probably some dissolution of an anodic oxide film and reduction by Al of the Cr or Mn from a higher to a lower oxidation state. In the case of formulations based on Ti or Zr there are no oxidation states to change. It is thought that the hydrofluoric acid may attack the anodic oxide film causing a local pH change resulting in the  
20 formation of a pretreatment/ $\text{Al}_2\text{O}_3$  gel followed by further pretreatment deposition. These pretreatments may be applied in the form of no-rinse solutions.

These pretreatment formulations based on fluoride and transition metals may also contain an organic polymer such as polyacrylic  
25 acid or polyvinylpyrrolidone. Whether or not such polymer is present, the pretreatment coating is preferably provided at a coat weight of 2 - 500  $\text{mg/m}^2$ , e.g. 5 – 100  $\text{mg/m}^2$ , particularly 10 – 60  $\text{mg/m}^2$ .

Other possible adhesion promoters include siloxanes, polyvinylphenols, polyacrylic acids and salts and esters thereof, and  
30 polyacrylic acid/zirconia mixtures. These adhesion promoters are preferably present at a coat weight of 5 – 500  $\text{mg/m}^2$  preferably

10 - 500 mg/m<sup>2</sup>. While adhesion promoters are effective to improve surface properties of the aluminium workpieces of this invention, it is surprisingly found that lower concentrations are sometimes more effective than higher concentrations.

5                   In another aspect the invention provides a method of treating an aluminium workpiece, which method comprises precleaning a surface of the workpiece, anodising the workpiece so as to form an anodic oxide film on the surface, applying to the anodic oxide film a coating of an adhesion promoter excluding silanes and preferably applying to the adhesion  
10 promoter coating an organic layer. Anodising may be effected in less than 60s e.g. less than 10s, and is preferably performed continuously. The adhesion promoter is preferably applied, either as a no-rinse coating, e.g. a composition consisting essentially of the adhesion promoter in a volatile vehicle which evaporates from the surface of the workpiece leaving a film  
15 of the adhesion promoter without the need for rinsing. Or a conversion coating composition may be used which reacts chemically with the substrate, e.g. the artificial oxide layer, to form a film of the adhesion promoter which is not removed by rinsing.

                  In one embodiment, a porous anodic oxide film is formed of  
20 thickness preferably 50 – 200 nm. When polyacrylic acid or other adhesion promoter is applied on top of the porous film, it generally fills the pores and forms a continuous layer on top of them. This embodiment has surprisingly good corrosion resistance and is particularly suitable as painted sheet for architectural use.

25                   In another embodiment, a barrier layer anodic oxide film is formed of thickness preferably 20 – 50 nm. A pretreatment e.g. NR1453 (adhesive promoter) is applied over this; the anodic film is sometimes found to be thinner after application of the pretreatment but never disappears altogether. A paint film, e.g. a conductive paint primer may be  
30 applied over the pretreatment, which primer film may be thin so as to permit electro-welding. Sheet according to this embodiment may have

- 5 -

surprisingly good forming characteristics and is particularly suitable for automotive use where components formed from the sheet are adhesively bonded to other components. Components formed from the sheet, and structures made by adhesively joining the components, can be painted on an electrophoretic or electrostatic paint line. Primed aluminium sheet is widely sold for automotive use, where the presence of the primer gives the sheet improved forming properties.

The aluminium sheet or other workpiece according to this invention carries on its surface a composite coating consisting of an anodic aluminium oxide film and a coating consisting of an adhesion promoter overlying the film or occupying pores adjacent the outer surface of the film. This composite coating is found to improve adhesion to the workpiece of an applied organic coating such as a paint, lacquer, varnish, enamel or adhesive. In another aspect, the invention provides such an aluminium workpiece where paint, lacquer, varnish, enamel or adhesive is present overlying the artificially applied aluminium oxide or hydroxide film and the adhesion promoter coating.

#### **EXAMPLE 1**

Sheets of AA6016, 1.2 mm thick, and AA5182, 1.15 mm thick, were electrolytically cleaned in 200 g/l phosphoric acid at 90°C for 3 seconds at 3 kA/m<sup>2</sup>. Half of the sheets were anodised in phosphoric acid to produce a film typically 15 – 50 nm thick. Treatment conditions were:

Phosphoric acid 200 g/l  
Temp 65°C  
Time 0.5 secs  
Spray rinse in 30–50 g/l phosphoric acid then deionised water  
Dry 120°C for 2 mins.

After rinsing and drying, the bare and anodised sheets were coated with a Ti containing no-rinse pretreatment Alodine NR 1453 to give a coating weight 5 – 15 mg/m<sup>2</sup> expressed as the weight of Ti. Alodine

- 6 -

NR1453 contains F, Zr and Ti, and has in addition a polymer present (a poly(hydroxyphenyl) styrene derivative).

Comparison samples were prepared by applying a Cr containing no-rinse treatment, Accomet C, at conventional levels.

5           After drying the sheets were coated on one side with electro conducting epoxy based paint Bonazinc 2004, (containing Al pigment) or Bonazinc 2000 (containing Al/Zn pigments). Coating thickness was about  $7\pm 2$  microns.

#### 10    **Formability Tests**

Formability was measured by means of an Erichsen dome test BS 3855 arranged so that the paint film on the convex side of the dome was extended 20% in biaxial tension. This corresponds to a bulge height of 8 mm. The coating area deformed by the dome was cross hatched. The punch side of the sheet was lubricated. Adhesion in the domed area was measured by means of BS 3900 Part 2 test using a sticky tape. Scoring was as per the BS 3900 Part 2 test in which the best result is 0 and the worst is 5.

The results are presented in Table 1 from which it can be seen that:

1.           In the absence of an anodised film the NR1453 was inferior to Accomet C. Performance generally improved as the coating weight decreased.
2.           In the presence of an anodised film the NR1453 gave results comparable to or better than Accomet C.

#### **Adhesive Bonding Tests**

30           Sheets prepared as described above were adhesively bonded and tested in T-Peel. 25 mm wide strips were overlapped and adhesively bonded with an epoxy adhesive XD4600, the coated side being towards the adhesive. The overlapped joint was then peeled apart at a cross head



- 7 -

movement rate of 20 mm/min.

On initial application of the peel load, the load rises to a peak and then drops to a constant level as the joints begins to separate. The constant load is measured and must exceed 7N/mm of width of joint and  
5 the failure mechanism be cohesive in the adhesive.

All of the NR 1453 equalled or exceeded 7N/mm when applied to pretreated anodic film, and all failed by cohesive failure within the adhesive.

**Table 1 – Automotive Primer Evaluation – Phase II**

Alloy	Additional Treatment	Pretreatment	Erichsen (Gt) 8mm Dome
AA 6016	None	Alodine NR 1453 ( $\approx 5 \text{ mg/m}^2$ )	2
		Alodine NR 1453 ( $\approx 10 \text{ mg/m}^2$ )	4
		Alodine NR 1453 ( $\approx 15 \text{ mg/m}^2$ )	4
		Accomet C	1
	Anodised	Alodine NR 1453 ( $\approx 5 \text{ mg/m}^2$ )	1
		Alodine NR 1453 ( $\approx 10 \text{ mg/m}^2$ )	1
		Alodine NR 1453 ( $\approx 15 \text{ mg/m}^2$ )	2
		Accomet C	2
AA 5182	None	Alodine NR 1453 ( $\approx 5 \text{ mg/m}^2$ )	2
		Alodine NR 1453 ( $\approx 10 \text{ mg/m}^2$ )	3
		Alodine NR 1453 ( $\approx 15 \text{ mg/m}^2$ )	5
		Accomet C	2
	Anodised	Alodine NR 1453 ( $\approx 5 \text{ mg/m}^2$ )	1
		Alodine NR 1453 ( $\approx 10 \text{ mg/m}^2$ )	0
		Alodine NR 1453 ( $\approx 15 \text{ mg/m}^2$ )	1
		Accomet C	1

**EXAMPLE 2**

The conditions of Example 1 were reproduced using a production line comprising an electrolytic etch, anodising to form a barrier layer about 20 nm thick, to which the pretreatment was applied by roller  
5 coating at 60 m/min. Erichsen test bulges were made having a height of 8 mm. Results are summarised in Table 2.

On both alloys the presence of a barrier film under the pretreatment improved performance.

**Table 2 – Primer Applications – Summary of Erichsen Dome Test Adhesion Performance\***

Surface Cleaning	Pretreatment	Bonazinc 2000		Bonazinc 2004	
		AA6016	AA5182	AA6016	AA5182
Electrolytic etch	Alodine NR 1453	3	4	2	4
≈20 nm barrier layer (anodised)	None	3	3	2	3
	Alodine NR 1453	1	2	2	0

\* BS 3900 Part 2 Erichsen Dome Height 8 mm

**EXAMPLE 3**

Samples of AA6016 T4 in the form of coils 1.2 mm thick were passed through an electrolytic cleaning and anodising section of a production line at a rate of 26 m/min. The line contained three baths each  
 5 containing 200 g/l phosphoric acid with less than 5 g/l dissolved aluminium and operated under the following conditions.

	Temp °C			Charge Density kCm <sup>-2</sup>		
Clean only	90	90	90	2	2	1
Clean and anodise	90	90	70	2	2	3.5

To the pretreated coils was applied an adhesion promoter  
 10 Alodine NR1453 (Henkel, containing fluorotitanate, fluoro-zirconate and poly(hydroxyphenyl) styrene derivative) at a rate of about 10 mg/m<sup>2</sup>.

To the resulting coils was applied a coating of an electroconducting epoxy-based paint primer Bonazinc 2004 (containing Al pigment) at a coating thickness of about 7 µm. Samples of primed sheet  
 15 were subjected to formability tests and adhesive bonding tests as described in Example 1.

Samples that had been cleaned only gave an Erichsen dome test result of 2. Samples that had been cleaned and anodised gave an Erichsen dome test result of 0, a substantial improvement.

20 Samples that had been cleaned only and that had been cleaned and anodised were subjected to the T-peel test. All samples passed the test, for joint failure was in all cases in the adhesive rather than at any adhesive-metal interface.

This work was repeated with other pretreatments (adhesion  
 25 promoters) as shown.

- NR 2010 (Henkel, fluorotitanate) at about 5 mg/m<sup>2</sup>.
- NR 778 (Henkel, fluoro-zirconate) at about 10 mg/m<sup>2</sup>.

- 12 -

- Ammonium zirconium carbonate / polyacrylic acid reaction product, at about 10 mg/m<sup>2</sup>.
- Accomet C (Albright & Wilson, Cr and Si values).
- Safeguard 6000 (Sanchem, permanganate).
- 5 • PT2 (Alcan, Si values).

The Erichsen dome results (not reported in detail) for the cleaned-and-anodised samples were all satisfactory (3 or less), and all equal to or better than the cleaned-only samples. In T-peel tests, substantially all failures were clearly within the adhesive layer, indicating  
10 that bonding was satisfactory.

#### **EXAMPLE 4**

Aluminium sheet intended for use as closure stock for cans was anodised in sulphuric acid on a commercial production line run at  
15 90 m/min. Some of the anodised sheet was then treated with polyacrylic acid (MW 60000 PAA). Panels were then bar coated with two white polyester external enamels plus clear overprint varnishes using normal commercial practices. 60 mm deep drawn shells were produced from the lacquered panels lubricated with castor oil, again in accordance with  
20 normal commercial practice. The following lacquer adhesion tests were performed.

#### **Feathering Test**

At the closure base a small cup was extended round the shell  
25 circumference. The relative lacquer feathering characteristics for each experimental substrate were assessed by comparing with specimen standards, and ranked on a scale 0 to 4 with the highest value showing the worst coating adhesion.

### Cross-hatch adhesion loss

At the closure base where the coating had received the most deformation, grid lines were scored through the lacquer into the panel using a metal scribe. Lacquer adhesion was assessed by firm application of adhesive tape on to the grid lines, followed by quick removal and the film percentage adhesion loss estimated and performance ranked on a scale 0 to 4.

### Adhesion after Autoclaving

Closures were immersed in water held at 120°C for 30 mins in an autoclave, and the lacquer adhesion characteristics were assessed.

The results are set out in Table 3. It can there be seen that PAA improved the performance of the coating.

**Table 3 - Lacquer Adhesion Characteristics**

Substrate Identification	Lacquer Performance			
	Feathering Test	Cross-hatch Adhesion Loss	Adhesion after Autoclaving	Total Score
Without PAA	0	1	0.5	1.5
With PAA	0	0	0	0

### EXAMPLE 5

Two alloys were used in this work, AA3005 which was 0.4 mm thick, and AA5754 which was 0.95 mm thick. Panels of each alloy were precleaned by treatment with phosphoric acid for 3 seconds at 90°C. They were then anodised in phosphoric acid at 65°C using a current of 3 A. In some cases the anodised surfaces were given further treatment with adhesion promoters:-

- 14 -

Accomet C, a commercial no rinse treatment based on hexavalent chromium and containing fluoride and phosphate values; 1:1 by weight mixtures of zirconium oxide and polyacrylic acid;

5 Polyacrylic acid alone.

The pretreated specimens were then painted and exposed to acid salt spray according to DIN 50021-ESS. Results set out in Table 4 below are expressed on a scale of 0 to 5 where 0 is excellent, 1 and 2 are acceptable, 3 is borderline and 4 and 5 are unacceptable. The alloy here  
10 was AA3005. Paint A was a single coat polyester. Paint B was a 2-coat polyester system.

**Table 4**

Paint	Anodised (secs)	Adhesion Promoter	Hours exposed to acetic acid salt spray			
			Panel & Scribe		Creep	
			336	1008	336	1008
A	2	-	4	X	1	X
A	2	Accomet C	1	2	1	1
A	2	Zr:PAA	3	4	4	5
A	2	PAA	1	2	1	5
B	2	-	4	X	1	X
B	2	Accomet C	1	2	1	3
B	2	Zr:PAA	2	3	1	1
B	2	PAA	1	2	1	5

15

X = Test discontinued



- 15 -

Anodic film thicknesses were determined from TEM micrographs. The anodising parameters used and the resulting pretreatment thicknesses are summarised in Table 5 below.

5

**Table 5**

Anodising Parameters		Anodic Film Thickness		Additional Pretreatment	
Temp. (°C)	Time (Secs)	(nm)		Adhesion Promoter	Thickness (nm)
		Barrier	Total		
65	2	40	80	None	None
		35	80	Accomet C	25
		40	80	1:1 Zr:PAA	40
		40	100	PAA	-

**EXAMPLE 6**

10 Panels of the same alloys as used in Example 5 were precleaned and then anodised for 3 seconds in phosphoric acid at 65°C using an anodising current of 3 A. The anodising process time was varied to produce either a 30 nm barrier layer or a 100 nm fully filamented anodic film. Some anodised panels were additionally treated with polyacrylic acid  
 15 (PAA) or Henkel poly(hydroxyphenyl) styrene derivative (PHS) solutions at two different spin coating concentrations. The treated panels were painted with a base coat and a clear coat, cured, and exposed to acetic acid salt spray tests (DIN 50021). The experiments are summarised in the following Table 6 and the results given in Table 7. The findings can be summarised:-

- 20 1. Phosphoric acid anodised pretreatments gave poor acetic acid salt spray test irrespective of anodic film structure.
2. The acetic acid salt spray test performance of the phosphoric acid anodised pretreatment was significantly improved by subsequent

- 16 -

treatment with PAA or PHS solutions. A 2% PAA spin coated application produced the best overall performance and without any failures.

**Table 6**

5

Expt	ALLOY	ANODISING PARAMETERS			ADDITIONAL PRETREATMENT	Spin Coating % Conc.
		Amps	Temp. (°C)	Time (secs)		
1	AA3005	3	65	1.5	None	
2				3		
3				PAA	0.5	
4					2	
5				PHS	0.5	
6					2	
7	AA5754	3	65	1.5	None	
8				3		
9				PAA	0.5	
10					2	
11				PHS	0.5	
12					2	

- 17 -

**Table 7**

Hours exposed to acetic acid salt spray (DIN 50021)									
Expt.	Panel & Scribe			Bend			Creep		
	336	504	1008	336	504	1008	336	504	1008
1	4	4	5	5	5	5	1	1	5
2	4	4	5	2	2	5	1	1	5
3	1	1	2	2	2	2	1	1	1
4	1	1	2	2	2	2	1	1	1
5	1	1	2	1	3	3	1	1	1
6	1	1	2	1	1	2	1	1	1
7	4	4	5	2	2	5	1	1	5
8	4	4	4	1	1	1	1	1	5
9	1	1	3	1	1	1	1	1	1
10	1	1	1	1	1	1	1	1	1
11	1	1	1	1	1	5	1	1	3
12	1	1	1	1	2	4	1	1	3

**EXAMPLE 7**

Panels of AA5754 H42 0.76 mm thick were electrolytically cleaned in phosphoric acid for 3 seconds at 90°C and were then (in some cases) anodised under various conditions as shown in Table 8 below. The treated panels were spin coated with an adhesion promoter as indicated:-

Accomet C (Albright & Wilson, Cr and Si values)

PAA (polyacrylic acid)

10 PSSA Polystyrene sulphonic acid-co-maleic acid

PHS Henkel, poly(hydroxyphenyl)-styrene derivative

Alodine NR1453N (Henkel, Zr, Ti values plus PHS)

The coated panels were painted (Wulf PVDF-1 2923-40 + Becker PK 16-40) and exposed to acid salt spray according to  
15 DIN 50021-ESS. Results are set out in Table 9 below.

**Table 8**

Anodising Parameters			Additional Treatment	Spin Coating Conc. %	Coat Weight (mg/m <sup>2</sup> )	Test No.
Amps (kA)	Temp. (°C)	Time (Secs)				
3	65	3	Anodised only		None	1
			PAA Mol. wt 5K	2	163	2
				2	164	3
				5	245	4
				10	407	5
			PAA Mol. wt 250K	2	277	6
			PHS	0.5		7
				2		8
				5		9
			PSSA	1		10
			Accomet C	5		11
			Hydroxquinoline	1		12
ac sulphuric acid anodised			Anodised only		None	13
3	60	2	PAA Mol. wt 50K	2	176	14
				5	207	15

- 20 -

**Table 9**

Test No	Hours exposed to acetic acid salt spray (DIN50021)								
	Panel & Scribe			Bend			Creep		
	336	504	840	336	504	840	336	504	840
1	4	4	5	1	1	2	1	5	5
2	1	2	4	1	1	2	1	1	1
3	1	1	1	2	2	2	1	1	1
4	1	1	1	1	1	1	1	1	1
5	1	2	3	1	1	1	1	1	1
6	1	1	2	1	1	1	1	1	1
7	1	1	1	2	2	2	1	1	1
8	3	4	5	1	1	2	1	1	5
9	4	5	5	1	5	5	5	5	5
10	4	4	5	1	1	2	1	5	5
11	1	1	1	2	2	2	1	1	1
12	1	4	4	2	2	2	1	1	5
13	4	5	5	2	2	3	5	5	5
14	1	1	1	2	2	2	1	1	1
15	1	1	2	1	1	1	1	1	1

**CLAIMS**

- 5     1.             An aluminium workpiece having on a surface thereof an anodic oxide film and a coating which consists essentially of at least one adhesion promoter excluding silanes.
2.             The aluminium workpiece of claim 1, wherein there is a paint,  
10     lacquer, varnish or enamel layer overlying the adhesion promoter coating.
3.             The aluminium workpiece of claim 2, which is aluminium sheet of which at least one surface has the anodic oxide film, the adhesion promoter coating and the paint, lacquer, varnish or enamel layer.
- 15             4.             The aluminium workpiece of claim 2 or claim 3, wherein the anodic oxide film is 50 – 200 nm thick.
5.             The aluminium workpiece of any one of claims 2 to 4, wherein  
20     the adhesion promoter coating is present at a weight of 5 – 500 mg/m<sup>2</sup>.
6.             The aluminium workpiece of any one of claims 2 to 5, which is painted sheet for architectural use.
- 25     7.             The aluminium workpiece of any one of claims 2 to 6, wherein the adhesion promoter is selected from at least one of polyacrylic acid, poly(hydroxyphenyl) styrene and pretreatments comprising one or more of Cr, Mn, Mo, Si, Ti, Zr and F values.
- 30     8.             The aluminium workpiece of claim 1, wherein the adhesion promoter is one containing one or more of Cr, Mn, Mo, Si, Ti and Zr values.

- 22 -

9. The aluminium workpiece of claim 8, which is aluminium sheet of which at least one surface has the anodic oxide film, the adhesion promoter and a paint layer or an adhesive overlying the adhesion promoter.
- 5 10. The aluminium workpiece of claim 8 or claim 9, wherein the anodic oxide film is 10 – 50 nm thick.
11. The aluminium workpiece of any one of claims 8 to 10, wherein the adhesion promoter coating is present at a weight of  
10 2 – 100 mg/m<sup>2</sup>.
12. The aluminium workpiece of any one of claims 8 to 11, wherein the Cr, Mn, Mo, Si, Ti, Zr and F values of the adhesion promoter are inorganic.
- 15 13. The aluminium workpiece of any one of claims 8 to 12, which is primed sheet for automotive use.
14. The aluminium workpiece of claim 9, wherein the paint layer  
20 is of an electro-conductive paint primer.
15. A method of treating an aluminium workpiece, which method comprises precleaning a surface of the workpiece, anodising the workpiece so as to form an anodic oxide film on the surface and applying to the  
25 anodic oxide film a coating consisting essentially of at least one adhesion promoter excluding silanes.
16. The method of claim 15, wherein there is applied over the adhesion promoter coating a paint, lacquer, varnish or enamel layer.



- 23 -

17. The method of claim 16, wherein the adhesion promoter is applied as a no-rinse coating or a conversion coating.
18. The method of claim 16 or claim 17, wherein the aluminium  
5 workpiece is aluminium sheet.
19. The method of claim 18, wherein the precleaned surface of the sheet is continuously anodised to form an anodic oxide film on the surface.
- 10 20. The method of any one of claims 15 to 19, wherein the adhesion promoter is one containing one or more of Cr, Mn, Mo, Si, Ti, Zr and F values.
- 15 21. The method of claim 20, wherein a paint layer or adhesive is applied over the adhesion promoter coating.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/03091

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B05D7/14 B05D3/10 B05D7/00 C25D11/18

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B05D C25D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 935 349 A (TERAI SHIRO ET AL) 27 January 1976  see the whole document ---	1-3, 7-9, 15, 16, 18-21
X	US 5 439 747 A (STURDEVANT SHELLEY D ET AL) 8 August 1995  see the whole document ---	1-3, 7-9, 15, 16, 18-21
X	EP 0 426 328 A (SHINTO PAINT CO LTD) 8 May 1991  see page 4, line 37 - line 41; examples --- -/--	1-3, 7-9, 14-16, 18-21

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

18 February 1999

Date of mailing of the international search report

25/02/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Brothier, J-A

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/03091

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4 138 526 A (BORRESEN THOR ET AL) 6 February 1979  see the whole document ---	1-3,7-9, 15,16, 18-21
X	US 5 139 601 A (HOLMES-FARLEY STEPHEN R ET AL) 18 August 1992  see page 1, column 1, line 26 - line 34; examples ---	1-3,7-9, 15,16, 18-21
X	US 4 897 231 A (SCHEURER ROBERT S ET AL) 30 January 1990 see the whole document ---	1,2,15
X	US 4 889 718 A (SUGAMA TOSHIFUMI) 26 December 1989  see the whole document ---	1-3,7, 15,16, 18,19
X	DE 27 05 652 A (BOEING CO) 3 May 1978  see claims 1,6,9 ---	1-4,15, 16,18,19
X	FR 2 252 421 A (BEREDAY SIGMUND) 20 June 1975 see the whole document ---	1,15
A	DE 195 48 740 A (ABB RESEARCH LTD) 26 June 1997 see the whole document -----	1,2

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Internal Application No

PCT/GB 98/03091

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3935349 A	27-01-1976	JP 848935 C JP 49100129 A JP 51024292 B DE 2350360 A GB 1422050 A	19-03-1977 21-09-1974 23-07-1976 02-05-1974 21-01-1976
US 5439747 A	08-08-1995	AU 6218694 A WO 9421387 A	11-10-1994 29-09-1994
EP 0426328 A	08-05-1991	JP 2811335 B JP 3146696 A AU 633637 B AU 6468490 A CA 2028088 A CN 1051373 A,B DE 69007234 D DE 69007234 T ES 2050381 T KR 9605431 B RU 2070905 C US 5354441 A	15-10-1998 21-06-1991 04-02-1993 02-05-1991 01-05-1991 15-05-1991 14-04-1994 29-09-1994 16-05-1994 25-04-1996 27-12-1996 11-10-1994
US 4138526 A	06-02-1979	AR 221580 A AT 354743 B AT 956576 A AU 509169 B CA 1090210 A CH 624141 A DE 2657901 A EG 12165 A FI 763672 A,B, FR 2336460 A GB 1570778 A GR 62648 A IE 44111 B JP 52081349 A LU 76439 A NL 7614232 A PT 65995 B SE 429762 B SE 7614013 A BE 849693 A DK 440876 A,B,	27-02-1981 25-01-1979 15-06-1979 24-04-1980 25-11-1980 15-07-1981 30-06-1977 31-12-1978 23-06-1977 22-07-1977 09-07-1980 16-05-1979 12-08-1981 07-07-1977 26-09-1977 24-06-1977 16-06-1978 26-09-1983 23-06-1977 15-04-1977 23-06-1977
US 5139601 A	18-08-1992	NONE	
US 4897231 A	30-01-1990	NONE	
US 4889718 A	26-12-1989	NONE	
DE 2705652 A	03-05-1978	AU 511699 B AU 2262577 A CA 1118708 A FR 2342356 A JP 53055423 A NL 7701977 A,B,	04-09-1980 31-08-1978 23-02-1982 23-09-1977 19-05-1978 30-08-1977
FR 2252421 A	20-06-1975	DE 2361860 A	26-06-1975

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat 1 Application No

PCT/GB 98/03091

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 2252421 A		NL 7316233 A	29-05-1975
		LU 68869 A	29-01-1975
DE 19548740 A	26-06-1997	EP 0781860 A	02-07-1997