

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
3 December 2009 (03.12.2009)

(10) International Publication Number
WO 2009/146352 A1

(51) International Patent Classification:
C08F 20/00 (2006.01)

(21) International Application Number:
PCT/US2009/045398

(22) International Filing Date:
28 May 2009 (28.05.2009)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
61/057,510 30 May 2008 (30.05.2008) US

(71) Applicant (for all designated States except US): **CORNERSTONE RESEARCH GROUP, INC.** [US/US];
2750 Indian Ripple Road, Dayton, OH 45440 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **TONG, Tat, Hung**
[US/US]; 1284 Kables Mill Drive, Bellbrook, OH 45305
(US).

(74) Agent: **SUNDAY, Eugene, Patrick**; Cornerstone Research Group, Inc., 2750 Indian Ripple Road, Dayton, OH 45440 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))



WO 2009/146352 A1

(54) Title: SHAPE MEMORY POLYMER FORMED BY SELF-CROSSLINKING OF COPOLYMERS

(57) Abstract: The present discovery shows how to make a self-crosslinking SMP. Shape Memory Polymer (SMP) can be formulated as a castable coating. This process allows the polymer to dissolve in solvent, and as the solvent evaporates the polymers self-crosslink at room temperature in air, creating a copolymer coating wherein the copolymer coating is an SMP. This technology has coating applications where shape memory would be an asset: from shape memory textile and fabric to self-healing coatings for vehicles and morphing skins for aircraft.

**SHAPE MEMORY POLYMERS FORMED BY SELF-CROSSLINKING OF
COPOLYMERS**

CROSS-REFERENCE TO RELATED APPLICATION

[0001] Priority benefit of U.S. provisional application Serial No. 61/057,510 filed May 30, 2008 is claimed.

BACKGROUND OF THE INVENTION

Field of the Invention

[0002] The present invention is directed to self-crosslinking shape memory polymers, their production and use. Particularly the current invention comprises a reaction product of a polymer with a self-crosslinking functional group which will self-crosslink under a given environmental stimulus. More particularly, the current invention comprises a reaction product of a small portion of silane crosslinker which is incorporated into the polymer chain by copolymerizing it with acrylates forming alkylsiloxyl groups in the acrylate copolymers.

[0003] Shape memory polymers (SMPs) are a unique class of polymers, which soften and harden quickly and repetitively on demand. This feature provides the ability to temporarily soften, change shape, and harden back to a solid structural state in various new highly detailed shapes and forms. Typical SMPs have a very narrow temperature span in which they transition between hard and soft states. This narrow glass transition temperature span is a key physical property that allows a SMP to maintain full structural rigidity up to a specifically designed activation temperature. Yet with as little as 5 °C to 10 °C increase above that temperature it quickly softens and allows shape change and subsequent re-hardening into new shapes.

Background of Prior Art

[0004] Shape memory materials are materials capable of distortion above their glass transition temperatures (T_g s), which store such distortion at temperatures below their T_g as potential mechanical energy in the material, and release this energy when heated again to above the T_g , returning to their original “memory” shape. In essence, these materials can be

“fixed” to a temporary shape under specific conditions of temperature and stress and later, under thermal, electrical, or other environmental command, the associated elastic deformation can be completely or substantially relaxed to the original, stress-free, condition.

SMAs

[0005] The first materials known to have these properties were shape memory metal alloys (SMAs), including TiNi (Nitinol), CuZnAl, and FeNiAl alloys. The shape-memory capabilities of these metallic materials capable of exhibiting shape-memory characteristics occur as the result of the metallic alloy undergoing a reversible crystalline phase transformation from one crystalline state to another crystalline state with a change in temperature and/or external stress. With a temperature change of as little as about 10 °C, these alloys can exert a stress as large as 415 MPa when applied against a resistance to changing its shape from its deformed state. Such alloys have been used for such applications as intelligent materials and biomedical devices. These materials have been proposed for various uses, including vascular stents, medical guide wires, orthodontic wires, vibration dampers, pipe couplings, electrical connectors, thermostats, actuators, eyeglass frames, and brassiere underwires. However, these materials have not yet been widely used, in large part because they are very expensive. Additionally, their applications have been limited due to limited ability to withstand strains greater than approximately 8%.

SMPs

[0006] Shape memory polymers (SMPs) are being developed to replace or augment the use of SMAs, in part because the polymers are lightweight, high in shape recovery ability, easy to manipulate, and economical as compared with SMAs. SMPs are materials capable of distortion above their glass transition temperature (T_g), storing such distortion at temperatures below their T_g as potential mechanical energy, via elastic deformation, in the polymer, and release this energy when heated to temperatures above their T_g , returning to their original memory shape. When the polymer is heated to near its transition state it becomes soft and malleable and can be more easily deformed. When the temperature is decreased below its T_g , the deformed shape is fixed by the higher rigidity of the material at a lower temperature while, at the same time, the mechanical energy expended on the material during deformation will be stored. Thus, favorable properties for SMPs will closely link to

the network architecture and to the sharpness of the transition separating the rigid and rubbery states.

[0007] Polymers intrinsically show shape memory effects on the basis of rubber elasticity, but with varied characteristics of temporary shape fixing, strain recovery rate, work capability during recovery, and retracted state stability. The first shape memory polymer (SMP) reported as such was cross-linked polyethylene; however, the mechanism of strain recovery for this material was immediately found to be far different from that of the shape memory alloys. When the polymer is heated to a soft, pliable state, it can be deformed under resistance of ~ 1 MPa modulus. When the temperature is decreased below the glass transition temperature (T_g), the deformed shape is fixed by the higher rigidity of the material at lower temperature while, at the same time, the mechanical energy expended on the material during deformation will be stored. When the temperature is raised above the T_g , the polymer will recover to its original form as driven by the restoration of network chain conformation entropy. Thus favorable properties for SMPs will be closely linked to the network architecture and to the sharpness of the transition separating the rigid and rubber states. Compared with SMAs, SMPs can withstand high strains, typically at least 100% to 400%, while the maximum strain of the SMA is typically less than 8%. As an additional advantage, due to the versatility of polymers, the properties of SMP can be tailored according to the application requirements, a factor that is very important in industry.

[0008] Several physical properties of SMPs other than the ability to memorize shape are significantly altered in response to external changes in temperature and stress. These properties include the elastic modulus, hardness, flexibility, vapor permeability, damping, index of refraction, and dielectric constant. The elastic modulus (the ratio of the stress in a body to the corresponding strain) of an SMP can change by a factor of up to 200 when heated above its melting point or glass transition temperature. Also, the hardness of the material changes dramatically when it is at or above its melting point or glass transition temperature. When the material is heated to a temperature above the melting point or glass transition temperature, the damping ability can be up to five times higher than a conventional rubber product. The material can readily recover to its original molded shape following numerous thermal cycles.

[0009] Heretofore, numerous polymers have been found to have particularly attractive shape memory effects, most notably acrylates, polyurethanes, polynorbornene, styrene-butadiene copolymers, and cross-linked polyethylene.

[0010] In the literature, polyurethane-type SMPs have generally been characterized as phase segregated linear block copolymers having a hard segment and a soft segment. The hard segment is typically crystalline, with a defined melting point, and the soft segment is typically amorphous, with a defined glass transition temperature. In some embodiments, however, the hard segment is amorphous and has a glass transition temperature rather than a melting point. In other embodiments, the soft segment is crystalline and has a melting point rather than a glass transition temperature. The melting point or glass transition temperature of the soft segment is substantially less than the melting point or glass transition of the hard segment.

[0011] Examples of polymers used to prepare hard and soft segments of known SMPs include various polyethers, polyacrylates, polyamides, polysiloxanes, polyurethanes, polyether amides, polyurethane/ureas, polyether esters, and urethane/butadiene copolymers. See, for example, U.S. Patent 5,506,300 to Ward et al.; U.S. Patent 5,145,935 to Hayashi; U.S. Patent 5,665,822 to Bitler et al.; and U.S. Patent 6,720,420 to Langer et al.

[0012] Conventional SMPs generally are segmented polyurethanes and have hard segments that include aromatic moieties. U.S. Patent 5,145,935 to Hayashi, for example, discloses a shape memory polyurethane elastomer molded article formed from a polyurethane elastomer polymerized from of a difunctional diisocyanate, a difunctional polyol, and a difunctional chain extender.

[0013] Recently, however, SMPs have been created using reactions of different polymers to eliminate the need for a hard and soft segment, creating instead, a single continuous piece of SMP. U.S. Patent 6,759,481 to Tong, discloses such a SMP using a reaction of styrene, a vinyl compound, a multifunctional cross-linking agent and an initiator to create a styrene based SMP.

Waterborne polymers

[0014] Waterborne polymer dispersions are rapidly becoming the coating of choice for an increasing number of industrial and applications, thanks to their being environmentally, healthy and relatively safe. Indeed, over the last 20 years a rapid

improvement of both performance and production costs has been prompted by a better understanding of the chemistry and mechanisms of film formation and development of main microscopic properties relevant to coating applications, such as adhesion, cohesion, curing mechanisms, surface properties, surface dynamics, and stability against aging.

[0015] However, while the technology gap between conventional solvent-based and waterborne coating formulations has progressively narrowed, some issues related to mechanism and physics of the film formation and to the role of the various components in providing a given coating performance are still challenging and require further research.

[0016] Among the features to be considered as a selection of functional groups or additives inducing the cross-linking in a latex polymer, the nature of the chemical reaction involved and schematics are crucial. In fact, untimely cross-linking during polymerization or in the latex dispersion can negatively affect both colloidal stability, causing coagulation, and film formation, hampering the last stage of inter-particle polymer diffusion.

[0017] Despite the many excellent properties of siloxanes, the poor compatibility between poly-siloxane and acrylics (or acrylic styrene) brings disadvantages to their polymerization and products, so trialkoxysilane has often been used as a cross-linking agent to form a middle transition later between the core and show to improve the compatibility between poly-siloxane and poly acrylics. Much research on the cross-linking poly-siloxane products and on improving product properties have been reported; however, reports about the self cross-linking properties of organo-silicone acrylic emulsions with vinyl trialkoxysilane have seldom been seen. One report states that latex particles incorporate these chemicals to give them self cross-linking properties in the film forming process. However, this report shows that the film is cast and then cross-linking occurs additionally only between latex to latex particles but not spontaneously within the polymer composition. Therefore there is still a need in the industry for a film that is cross-linked during casting instead of after and which cross-links across the entire mixture not just one portion to another.

SUMMARY OF THE INVENTION

[0018] The present discovery shows how to make a self-crosslinking SMP . Shape Memory Polymer (SMP) can be formulated as a castable coating. This process allows the

polymer to dissolve in solvent, and as the solvent evaporates the polymers self-crosslinks at room temperature in air, creating a copolymer coating wherein the copolymer coating is an SMP. This technology has coating applications where shape memory would be an asset: shape memory fabric and textile to self-healing coatings for vehicles and morphing skins for aircraft.

DETAILED DESCRIPTION OF THE INVENTION

[0019] Shape memory polymer (SMP) can provide both elastic force and shape recovery capabilities with the potential to generate a new type of SMP technology. Though SMP coatings on a substrate help to prevent damage and assist in the repair of a substrate, the technology has not previously been optimized to replace technologies currently available. New SMP coatings and processes demonstrating increased performance benefits that are equal to or exceed that of current durable press treatments are presented herein.

[0020] There are two approaches involving wet chemistry that allow films to form on fabric, via solution casting. A first monomer must be mixed with a second monomer, or also referred herein to as a co-monomer that is capable of initiating the self-crosslinking feature under certain stimuli in the presence of an initiator.

[0021] The first monomer may be selected from among the following: vinyl neodecanoate, vinyl benzoate, vinyl propionate, vinyl stearate, a methylstyrene, which may be a mixture, styrene, 3-methylstyrene or 4-methylstyrene, a vinyl pyridine, which may be a mixture, 2-vinyl pyridine, 3-vinyl pyridine or 4-vinyl pyridine, vinyl laurate, vinyl butyrate, vinyl acetate, vinyl stearate, vinyl 2-furate, vinyl phenylacetate, vinyl carbazole, 4-vinylbenzyl acetate, 4-vinylbenzoic acid, vinyl methyl sulfone, vinyl octadecyl ether, vinyl isooctyl ether, N-vinyl-2-pyrrolidone, N-vinyl-N-methylacetamide, 1-vinylimidazole, N-vinylformamide, N-vinylcaprolactam, vinyl azolactone, N-vinylurea, 4-(vinyloxy)butyl stearate, 4-(vinyloxy)butyl benzoate, 4-(vinyloxymethyl)cyclohexyl-methyl benzoate, methyl acrylate, methyl methacrylate, butyl acrylate, t-butyl acrylate, butyl methacrylate, t-butyl methacrylate, hexyl acrylate, acrylic acid, methacrylic acid, benzyl acrylate, benzyl methacrylate, 2-n-butoxyethyl methacrylate, 2-cyanoethyl acrylate, cyclohexyl acrylate, cyclohexyl methacrylate, decyl acrylate, dicyclopentenyl acrylate, dicyclopentenyl oxyethyl acrylate, dicyclopentenyl oxyethyl methacrylate, dodecyl acrylate, dodecyl methacrylate, 2-ethoxyethyl methacrylate, 2-

ethylhexyl acrylate, ethyl methacrylate, 2-hydroxyethyl acrylate, 2-hydroxyethyl methacrylate, isobornyl acrylate, isobornyl methacrylate, 2-(2-methoxyethoxy)ethyl acrylate, 2-(2-methoxyethoxy)ethyl methacrylate, 2-methoxyethyl acrylate, 2-methoxyethyl methacrylate, 2-methoxypropyl acrylate, 2-methoxypropyl methacrylate, octyl methacrylate, 2-phenoxyethyl acrylate, 2-phenoxyethyl methacrylate, phenyl acrylate, 2-phenylethyl acrylate, 2-phenylethyl methacrylate, phenyl methacrylate, propyl acrylate, propyl methacrylate, stearyl acrylate, stearyl methacrylate, 2,4,6-tribromophenyl acrylate, undecyl acrylate or undecyl methacrylate, 2-(acryloyloxy)acetoacetate, 2-(methacryloyloxy)acetoacetate, 2-(3,4-epoxy cyclohexyl)ethyltriethoxysilane; 2-(3,4-epoxy cyclohexyl)ethyltrimethoxysilane; (3-glycidoxpropyl) methyl diethoxysilane; (3-glycidoxpropyl) methyl dimethoxysilane; 3-glycidoxpropyl) trimethyl silane; 5,6-epoxyhexyl triethoxysilane.

[0022] Co-monomers which can be used to initiate the self-crosslinking upon exposure to water are: (3-Acryloxypropyl)trimethoxysilane; (3-Acryloxypropyl)methyl dimethoxysilane; 3-(N-Allylamino)propyltrimethoxysilane; Allyltrimethoxysilane; Docosenyltriethoxysilane; Dodecyltriethoxysilane; o-(methacryloxyethyl)-N-triethoxysilylpropyl)urethane; methacryloxymethyltriethoxysilane; methacryloxymethyltrimethoxysilane; methacryloxypropyltrimethoxysilane; Vinyltriethoxysilane; and vinyltrimethoxysilane.

[0023] The first monomers which can be used to initiate the self-crosslinking upon exposure to thermal energy are: Chloromethylstyrene (vinylbenzyl chloride), vinyl chloride, 3-chloro-2-methyl-1-propene. Co-monomers which can be used to initiate the self-crosslinking upon exposure to thermal energy are: 2-(dimethylamino)ethylacrylate, 2-(dimethylamino)ethyl methacrylate, 2-vinyl pyridine, 3-vinyl pyridine, 4-vinylpyridine, acrylamide, acrylomorpholine, methacrylamide, and vinyl imidazole,.

[0024] While there are some chemicals that can be both the first monomer and the co-monomer, no single chemical can be the first monomer and co-monomer in one single formulation. For example, 4-vinyl pyridine may be the first monomer or may be used as the co-monomer which will self-crosslink when exposed to heat, however, if 4-vinyl pyridine, is used as either the first monomer or the co-monomer, it then cannot be used as both.

[0025] The initiator of the reaction mixture may be a free radical or an ionic initiator. Free radical initiators within the scope of the present invention include organic

peroxides, azo compounds and water soluble oxidizers. Commercially available organic peroxides may be utilized, tert-butyl peroxide, tert-butyl hydroperoxide, benzoyl peroxide, dicumyl peroxide and lauroyl peroxide are particularly preferred. Similarly, although any commercially available azo initiating compounds may be utilized, 2,2'-azobisisobutyronitrile is particularly preferred. Water soluble oxidizers that may be employed are potassium persulfate, ammonium persulfate. The ionic initiators are preferably cationic initiators. Preferred cationic initiators include boron trifluoride, boron trifluoride diethyl etherate, aluminum trichloride and tin (IV) chloride.

[0026] Several SMP formulations with each pathway mentioned above can be used and should focus on obtaining low glass transition temperature (T_g) SMPs for greatest usefulness of the SMP films. The preferred ranges for these temperatures are 10 °C to 60 °C.

[0027] One approach is to a two-step process to form an ambient self cross-linking system based on siloxane-acrylate polymers. The first step incorporates a small molecule siloxane monomer (such as vinyl triethoxysilane) into the polymer chain by copolymerizing it with acrylates during polymerization. The acrylate chain will be long and weigh at least 1000 MW. In the second step water causes the alkoxy groups of the siloxane to hydrolyze into silanol groups, via acid-base catalysts which allow the network to be formed by poly condensation.

[0028] The siloxane containing acrylates will be polymerized before the application to the substrate to impart shape memory. Also the Si-O-C bond is much easier to hydrolyze and condense both in acidic and alkaline media, so the controlling pH can also prevent the silane from hydrolyzing during backbone polymerization and storage.

[0029] It is possible to tailor the degree of cross-linking by changing the composition of the siloxane group and the number of siloxane groups on each polymer chain. These polymers will self cross-link at room temperatures as the polymer coating is applied to the fabric if there is enough water in the environment. The water-based, room temperature cross-linking process would avoid or reduce the use of organic solvents and provide an out-of-hood curing process for transition to product development.

[0030] The process to form a self cross-linking system: A small portion of silane cross-linker is incorporated into the polymer chain by copolymerizing it with acrylates

forming alkylsiloxyl groups in the acrylate copolymers; the copolymer is dissolved in a solvent to form a polymer solution. These polymers will self-crosslink at room temperatures as the polymer solution is applied to the substrate. The alkylsiloxyl groups are converted into silanol groups, via hydrolysis. The hydrolysis allows the formation of network structure by polycondensation to achieve shape memory effect. To speed up self-crosslinking, film can be exposed to steam to aid hydrolysis.

[0031] A second approach is an ambient temperature self cross-linking system based on the Menshutkin reaction (quaternatization) of halides with tertiary amines. Halide functionalized acrylates with amine functionalized acrylates are produced via separate emulsion polymerizations. When the halide and amine functionalized acrylates are mixed in a water dispersion and cast they form elastic films by cross-linking. These cross-links are stable up to 215 °C and since the washer/dryer cycle operates at temperatures well below 200 °C the SMP film will maintain its shape recovery properties throughout the washer/dryer cycle. This Menshutkin reaction is expected to be suitable for SMP coatings because it does not require a catalyst or organic solvents, occurs at room temperature and both functional groups are stable in aqueous media.

[0032] Film forming, curing and coating processes for each of the chemical approaches can be used to create a shape memory textile and fabric substrate. For self cross-linking SMPs where the final chemical cross-linking will occur on the fabric, elastic film formation is best.

[0033] There are significant differences between the prior art and the presently disclosed composition. The presently disclosed chemicals chemically cross-link as a neat resin. The presently disclosed chemicals cross-link as a castable latex film. The presently disclosed chemicals are a more homogeneous mixture where everything cross-links with each other. The prior art has a relatively high degree of cross-linking and is not an SMP or self-crosslinking, whereas the presently disclosed chemical is only 2-20% crosslinking density with a preferred cross-linking density of 5-15% and is a self-crosslinking SMP. The presently disclosed polymers have shape memory properties. The presently disclosed chemicals do not need to be made in one step and can be applied as a solution.

[0034] Shape Memory Polymer (SMP) can be formulated as a castable coating. This process allows the SMP to dissolve in solvent, and as the solvent evaporates the SMP

self-crosslinks at room temperature in air, creating coating. The water-based, room temperature cross-linking process avoids or reduces the use of organic solvents and provides an out-of-hood coating process.

[0035] This technology has coating applications where shape memory would be an asset: shape memory textile and fabric to self-healing coatings for vehicles and morphing skins for aircraft.

[0036] It is possible to tailor the degree of cross-linking by changing the ratio of the silane cross-linker on the polymer backbone, while the other desirable thermomechanical properties, such as elongation and T_g (glass transition temperature), can be fine tuned by the choice of acrylate co-monomers.

[0037] In one sample a 50/50 weight ratio of butyl methacrylate to methyl methacrylate, with 0.5% initiator and 2.5% cross-linker (by weight) was made. In a second sample butyl methacrylate, with 2% initiator and 2.5% cross-linker was made. In a third sample a 50/50 weight ratio of butyl methacrylate to hexyl methacrylate, with 2% initiator and 2.5% (by weight) was made.

[0038] Each solution was made from 10g of polymer in 190g of THF (making a 5% solution by weight). Each solution was cast as thin films from the 5% solutions by measuring out 12g solution into Teflon petrie dishes and letting the THF evaporate in the fume hood. Three films were from each sample solution, 12 films total. The film from sample A seemed to form on the top of solution, forming a thin layer on top, while the films for samples B and C formed at the bottom.

[0039] The invention has been described above in conjunction with various exemplary embodiments of practicing the invention. It will be apparent to those skilled in the art that modifications can be made to those specifically disclosed embodiments without departing from the invention herein disclosed and described; the scope of the invention being limited only by the scope of the attached claims.

[0040] What is claimed is:

CLAIMS

1. A self-crosslinking shape memory polymer comprising: a polymer chain with at least one self-crosslinking functional group which will chemically self-crosslink when exposed to a self-crosslinking stimuli creating a thermoplastic chemically self-crosslinking shape memory polymer.

2. The self-crosslinking shape memory polymer of claim 1 wherein said self-crosslinking functional group is an alkylsiloxy type silane functional group.

3. The self-crosslinking shape memory polymer of claim 2 wherein said chemical self-crosslinking occurs by polycondensation.

4. The self-crosslinking shape memory polymer of claim 2 wherein said self-crosslinking stimuli is water content of air is greater than 3 grams per one kilogram of air.

5. The self-crosslinking shape memory polymer of claim 2 wherein said self-crosslinking stimuli is water content of air is greater than 5 grams per one kilogram of air.

6. The self-crosslinking shape memory polymer of claim 2 wherein said self-crosslinking stimuli is water content of air is greater than 10 grams per one kilogram of air.

7. The self-crosslinking shape memory polymer of claim 1 wherein said self-crosslinking functional groups are an amine and a chlorine or halogen substitute.

8. The self-crosslinking shape memory polymer of claim 7 wherein said chemical self-crosslinking occurs by the Menschutkin reaction.

9. The self-crosslinking shape memory polymer of claim 7 wherein said self-crosslinking stimuli is a temperature of at least 20 °C.

10. The self-crosslinking shape memory polymer of claim 1 wherein said self-crosslinking shape memory polymer obtains a cross-linking density of at least 2% and no more than 20%.

11. The self-crosslinking shape memory polymer of claim 10 wherein said self-crosslinking shape memory polymer obtains a cross-linking density of at least 5% and no more than 15%.

12. The self-crosslinking shape memory polymer of claim 1 wherein said copolymer chain is polyacrylate, polystyrene, polyethylene, polymethacrylate, polyvinyl, polycarbonate or epoxy.

13. The self-crosslinking shape memory polymer of claim 1 wherein said polymer chain has a molecular weight of at least 1000.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 09/45398

A. CLASSIFICATION OF SUBJECT MATTER
IPC(8) - C08F 20/00 (2009.01)
USPC - 525/445
According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC(8) - C08F 20/00 (2009.01)
USPC - 525/445

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
USPC - 525/445,424; 528/28,73,74; 524/404,424,428,433,434

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
PubWEST (PGPB; USPT; EPAB; JPAB); Google; Google Scholar
Search Terms Used: shape memory polymers, self-crosslinking, siloxane, alkoxyxilane, alkyloxyxilane, silanol, thermoplastic, polycondensation, latex, self-healing, waterborne, quaternization, menschutkin reaction, hydrolysis

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	MOLENAAR. Novel Alkoxyxilane Comonomers for 1-Pack Post-Crosslinkable Latex Systems. CIP-Data Library Technische Universiteit Eindhoven [online], 2000 [retrieved on 2009-07-07]. Retrieved from the Internet: <URL: http://alexandria.tue.nl/extra2/200011664.pdf > <ISBN: 90-386-2941-9> pg 3, para [0002]; pg 4, para [0001]-[0004]; pg 5, para [0001]; pg 131, para [0001]; pg 190, para [0007]-[0008]	1-13
Y	US 2008/0021166 A1 (TONG, et al.) 24 January 2008 (24.01.2008) para [0004], [0029]	1-13
Y	CHEN, et al. Long-Term Stability of an Ambient Self-Curable Latex Based on Colloidal Dispersions in Water of Two Reactive Polymers. Journal of Polymer Science Part A: Polymer Chemistry, Vol 43, Issue 12, 10 May 2005, (abstract) [online], [retrieved on 2009-07-07]. Retrieved from the Internet: <URL: http://www3.interscience.wiley.com/journal/76504872/abstract?CRETRY=1&SRETRY=0 > <DOI: 10.1002/pola.20731> abstract	7-9

Further documents are listed in the continuation of Box C.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier application or patent but published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 08 July 2009 (08.07.2009)	Date of mailing of the international search report 17 JUL 2009
--	--

Name and mailing address of the ISA/US Mail Stop PCT, Attn: ISA/US, Commissioner for Patents P.O. Box 1450, Alexandria, Virginia 22313-1450 Facsimile No. 571-273-3201	Authorized officer: Lee W. Young PCT Helpdesk: 571-272-4300 PCT OSP: 571-272-7774
---	--