



(86) Date de dépôt PCT/PCT Filing Date: 2003/05/02

(87) Date publication PCT/PCT Publication Date: 2004/08/12

(45) Date de délivrance/Issue Date: 2012/04/03

(85) Entrée phase nationale/National Entry: 2005/07/07

(86) N° demande PCT/PCT Application No.: IB 2003/002500

(87) N° publication PCT/PCT Publication No.: 2004/066760

(30) Priorités/Priorities: 2003/01/27 (GB0301869.4);
2003/01/29 (US60/443,450)

(51) Cl.Int./Int.Cl. *C08L 91/06* (2006.01),
A21D 13/00 (2006.01), *A21D 13/08* (2006.01),
A23L 1/00 (2006.01), *A23L 3/3517* (2006.01),
A23P 1/08 (2006.01), *A61K 47/44* (2006.01),
C08K 5/10 (2006.01), *C09D 191/06* (2006.01)



(72) Inventeurs/Inventors:
NEILSEN, JENS MOGENS, DK;
HOEGH, LARS, DK

(73) Propriétaire/Owner:
DANISCO A/S, DK

(74) Agent: GOWLING LAFLEUR HENDERSON LLP

(54) Titre : COMPOSITION QUI PREVIENT LE DEPLACEMENT DE L'EAU DANS UN ALIMENT

(54) Title: COMPOSITION THAT PREVENTS WATER MOVEMENT IN A FOODSTUFF



(57) Abrégé/Abstract:

There is provided a composition comprising: i) a wax in an amount of 10 to 40 wt. % based on the composition, ii) a compound in an amount of 60 to 90 wt. % based on the composition, having the formula (I), wherein t is an integer, wherein each R₁, R₂ and R₃

(57) **Abrégé(suite)/Abstract(continued):**

is independently selected from an acyl group or a hydrogen atom, wherein at least one of R_1 , R_2 and R_3 is H or an acyl group (a short acyl group) having 2 to 6 carbons atoms, wherein at least one of R_1 , R_2 and R_3 is an optionally branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
12 August 2004 (12.08.2004)

PCT

(10) International Publication Number
WO 2004/066760 A3

(51) International Patent Classification⁷: **A23P 1/08**,
C08L 91/06, C07C 69/675, 69/26, 69/33

(21) International Application Number:
PCT/IB2003/002500

(22) International Filing Date: 2 May 2003 (02.05.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0301869.4 27 January 2003 (27.01.2003) GB
60/443,450 29 January 2003 (29.01.2003) US

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **NEILSEN, Jens, Mogens** [DK/DK]; Pebbelparken 16, Stjaer, DK-8464 Galten (DK). **HØEGH, Lars** [DK/DK]; Højbailevej 60, DK-8320 Mårslet (DK).

(74) Agents: **ALCOCK, David** et al.; D Young & Co., 21 New Fetter Lane, London EC4A 1DA (GB).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(71) Applicant (*for all designated States except US*): **DANISCO A/S** [DK/DK]; Langebrogade 1, P.O. Box 17, DK-1001 Copenhagen K (DK).

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: COMPOSITION





Figure 1

(57) Abstract: There is provided a composition comprising: i) a wax in an amount of 10 to 40 wt. % based on the composition, ii) a compound in an amount of 60 to 90 wt. % based on the composition, having the formula (I), wherein t is an integer, wherein each R₁, R₂ and R₃ is independently selected from an acyl group or a hydrogen atom, wherein at least one of R₁, R₂ and R₃ is H or an acyl group (a short acyl group) having 2 to 6 carbons atoms, wherein at least one of R₁, R₂ and R₃ is an optionally branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group.

WO 2004/066760 A3

WO 2004/066760 A3



European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(88) Date of publication of the international search report:
7 October 2004

Published:

— *with international search report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Composition that Prevents Water Movement in a Foodstuff

The present invention relates to a compound. In particular, the present invention relates to a composition which may act as a barrier against water and moisture particularly
5 when used to coat foodstuffs.

As discussed in US 6,472,006 for many food products, moisture levels must be maintained if the product is to exhibit optimum organoleptic properties, quality, and taste. Moisture migration in finished food products can seriously compromise quality,
10 stability, and organoleptic properties. In addition, many chemical and enzymatic deteriorative reactions proceed at rates partially governed by the moisture content of foods. Excessive rates of these reactions can promote deleterious changes in the flavour, colour, texture, and nutritive value of food products.

15 In multi-component food products, particularly those having components with different moisture contents and water activities (e.g., pre-packaged cheese and crackers or pre-packaged bagel and cheese cream products), moisture can migrate between adjacent components, altering the component's characteristics and organoleptic properties. In addition to compromising the quality of finished food products, moisture migration can
20 hinder production and distribution of food products. Thus, for example, the cheese in a cheese/cracker product could dry out while, at the same time, the cracker loses its crispness.

One method to prevent moisture migration in foods involves coating one or more
25 surfaces of the food product with an edible moisture barrier. Such barriers should have a low moisture permeability in order to prevent the migration of water between areas of differing water activities. In addition, the barrier should cover the food surface completely, including crevices, and adhere well to the food product surface. The moisture barrier should be sufficiently strong, soft, and flexible to form a continuous
30 surface that will not crack upon handling, yet can be easily penetrated during consumption. In addition, the barrier film's organoleptic properties of taste, aftertaste, and mouthfeel should be imperceptible so that the consumer is not aware of the barrier when the food product is consumed. Finally, the moisture barrier should be easy to manufacture and easy to use.


Because lipids, such as, for example, oils, fats, and waxes, are composed of lipophilic or water insoluble molecules capable of forming a water impervious structure, they have been investigated for use in moisture barrier films. With respect to oleaginous materials (i.e., fats, oils, sucrose polyesters, and the like) and/or other film forming lipids, it has been taught that, unless an undesirably thick coating is used, the barrier is not effective. Wax barriers have disadvantages as moisture barriers because they tend to crack upon handling or with changes in temperatures. Mixture of waxes with other components have been taught in the art, for example by Greener *et al.*, 34-38, Lipid Technology, March – April 1992. However, these previously disclosed mixture also have suffered from the fragility problems of pure waxes such as beeswax.

The present invention alleviates problems of the prior art.

Aspects of the invention are defined in the appended claims.

15

In one aspect the present invention provides a composition comprising i) a wax in an amount of 10 to 40 wt. % based on the composition, ii) a compound in an amount of 60 to 90 wt. % based on the composition, having the formula




20 wherein t is an integer, wherein each R₁, R₂ and R₃ is independently selected from an acyl group or a hydrogen atom, wherein at least one of R₁, R₂ and R₃ is H or an acyl group (a short acyl group) having from 2 to 6 carbon atoms, wherein at least one of R₁, R₂ and R₃ is an optionally branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group.

25

In one aspect the present invention provides a coated foodstuff comprising (a) a foodstuff substrate, (b) a coating comprising a composition as defined herein .


30 In one aspect the present invention provides a process for preparing a coated foodstuff, comprising coating a foodstuff with a composition as defined herein.

5 based on the composition, having the formula



10 R₂ and R₃ is an optionally branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group.


15 ii) a compound having the formula



20 R₂ and R₃ is an optionally branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group; wherein the kit is formulated to provide the wax in an amount of 2 to 50 wt. % based on the composition, and the compound in an amount of 50 to 98 wt. % based on the composition.

In one aspect the present invention provides use of a composition for preventing and/or

reducing migration of water into or out of a material, wherein the composition comprises
 i) a wax in an amount of 2 to 50 wt. % based on the composition; and ii) a compound in
 an amount of 50 to 98 wt. % based on the composition, having the formula



- 5 wherein t is an integer, wherein each R_1 , R_2 and R_3 is independently selected from an
 acyl group or a hydrogen atom, wherein at least one of R_1 , R_2 and R_3 is H or an acyl
 group (a short acyl group) having from 2 to 6 carbon atoms, wherein at least one of R_1 ,
 R_2 and R_3 is an optionally branched chain acyl group (a long acyl group) consisting of a
 saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch
 10 group.

SOME ADVANTAGES

- We have found that by mixing a wax in an amount of 10 to 40 wt.% with a compound
 15 described above, for example GRINDSTED^{RTM} ACETEM Acetic Acid Ester available
 from Danisco A/S, Brabrand, Denmark, excellent moisture barrier properties may be
 observed. It is believed that the above compound acts as a plasticiser when mixed with
 a wax. Wax is extremely effective in preventing water migration if the wax film or coating
 is uniform and unbroken. However waxes are typically very brittle and easily form cracks
 20 and pinholes, which result in loss of barrier properties. We have found that addition of up
 to 90% of the above defined compound improves the texture of a wax dramatically
 without altering its excellent resistance to water migration.

- As will be described below in the examples section measurement of the permeability
 25 coefficient (P-value) shows that a pure wax such as beeswax has a P-value less than
 14 at 5°C and pure GRINDSTED^{RTM} ACETEM Acetic Acid Ester approximately 750. A
 mixture of 80% GRINDSTED^{RTM} ACETEM Acetic Acid Ester and 20% beeswax has a P-
 value of 27 (unit = mg μm / m² mmHg min).

- 30 PREFERRED ASPECTS

5

WAX

In one preferred aspect the wax is selected from beeswax, candelilla wax, carnauba wax, jojoba wax, whale wax, paraffin wax, mineral wax, and microcrystalline wax.

5

In one highly preferred aspect the wax is beeswax.

The wax may be deodorised and/or refined.

10 **COMPOUND**


In one preferred aspect t is from 1 to 10.

In one preferred aspect t is from 1 to 5

15

In one preferred aspect t is 1 or 2.

In one preferred aspect the compound is of the formula




20

In one preferred aspect at least one of R_1 , R_2 and R_3 is an acyl group (a short acyl group) having from 2 to 6 carbon atoms.

Preferably two of R_1 , R_2 and R_3 are short acyl groups as described above and the other of R_1 , R_2 and R_3 is a long acyl group as described above. In this aspect, the compound may be of the formula

25




In one preferred aspect at least one of R_1 , R_2 and R_3 is H, and at least one of R_1 , R_2 and

R₃ is an acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms.

In a preferred aspect of the present invention the chain of the long acyl group consists of
5 a chain having 14 to 20 carbon atoms, preferably the chain of the long acyl group consists of a chain having 16 to 20 carbon atoms.

In a preferred aspect of the present invention the chain of the long acyl group consists of a saturated chain having 14 to 20 carbon atoms. In a more preferred aspect, the chain
10 of the long acyl group consists of a saturated chain having 16 to 20 carbon atoms.

In a preferred aspect of the present invention the short acyl group is an acyl group having from 2 to 5 carbon atoms. In a more preferred aspect, the short acyl group is an acyl group having 2 carbon atoms. The short acyl group is preferably of the formula



In certain aspects, it is desirable for the short acyl groups to be present in a maximum amount with respect to the total amount of glycerol and esters thereof present in the composition. Preferably the short acyl group is present in an amount, on average, of no
20 greater than 2 moles per mole of glycerol and esters thereof present in the composition.

In certain aspects, it is desirable for the long acyl groups to be present in a minimum amount with respect to the total amount glycerol and esters thereof present in the composition. Preferably the long acyl group is present in an amount, on average, of at
25 least 0.4 moles, preferably from 0.9 to 2 moles, more preferably from 0.9 to 1 moles per mole of glycerol and esters thereof present in the composition.

It may also be preferred for the majority of the glycerol present in the composition to be fully acylated. Accordingly, in a preferred aspect the total amount of acyl groups is, on
30 average, 0.8 to 3.0 moles per mole of glycerol and esters thereof

UNBRANCHED

In a preferred aspect of the present invention at least one of R₁, R₂ and R₃ is an
35 unbranched acyl group.

In a preferred aspect of the present invention at least one of R_1 , R_2 and R_3 is an unbranched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms.

5

In a preferred aspect of the present invention the or each long acyl group is unbranched.

In a preferred aspect of the present invention each R_1 , R_2 and R_3 is independently selected from an acyl group or a hydrogen atom, wherein at least one of R_1 , R_2 and R_3 is H or an acyl group (a short acyl group) having from 2 to 6 carbon atoms, wherein at least one of R_1 , R_2 and R_3 is an unbranched acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms.

10

BRANCHED

15

In one aspect of the present invention at least one of R_1 , R_2 and R_3 is a branched chain acyl group (a long acyl group).

In one aspect of the present invention at least one of R_1 , R_2 and R_3 is a branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and a hydrophilic branch group.

20


In one aspect of the present invention at least one of R_1 , R_2 and R_3 is a branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and a hydrophilic branch group.

25

In one aspect each R_1 , R_2 and R_3 is independently selected from an acyl group or a hydrogen atom, wherein at least one of R_1 , R_2 and R_3 is an acyl group (a short acyl group) having from 2 to 6 carbon atoms, wherein at least one of R_1 , R_2 and R_3 is an optionally branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group.

30


WO 01/14466 teaches a thermoplastic polymer composition containing a compound having the formula



wherein R_1 , R_2 and R_3 are independently selected from an acyl group or a hydrogen atom, wherein at least one of R_1 , R_2 and R_3 is an acyl group (a short acyl group) having from 2 to 6 carbon atoms, wherein at least one of R_1 , R_2 and R_3 is a branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and a hydrophilic branch group. The compound of the present invention may be as described in WO 01/14466 or may be prepared in accordance with the teaching of WO 01/14466.


- 10 The hydrophilic branch group may be a group selected from acyl and derivatives thereof. Preferred derivatives include groups of the formula -O-acyl.

The hydrophilic branch group may be a group of the formula



- 15 wherein p is from 0 to 4 or 0 to 3.

The long acyl group may be of the formula




wherein n is from 10 to 20 and m is $2n$, and wherein p is from 0 to 4 or 0 to 3.

20

In one aspect n is from 16 to 20, from 16 to 18, or 17.

The group C_nH_m may be a straight chain hydrocarbon group.


- 25 In a one aspect the long acyl group is a group of the formula



wherein x is from 7 to 10, for example x is 10, and y is $2x$, and wherein p is from 0 to 4 or 0 to 3, for example p is 0.


The group C_xH_y may be a straight chain hydrocarbon group.

The long acyl group may be a group of the formula




5

The short acyl group and the hydrophilic branch group may contain the same number of carbon atoms. The hydrophilic branch group may be a group of the formula



and the short acyl group may be of the formula



10

wherein $p = q$ and is from 0 to 4 or 0 to 3.

PROCESS

- 15 The compound of the present invention may be prepared by interesterification between glycerol and one or more oils, including natural oils and hardened natural oils followed by acylation. Thus, the compound of the present invention may be the product of a two part process comprising (i) an interesterification between glycerol and an oil selected from castor oil, including hardened castor oil, unhardened castor oil and mixtures thereof, and (ii) acylation.

Typical oil feedstocks for a process outlined above include fully hydrogenated, partly hydrogenated and non-hydrogenated fats and oils including palm oil, soy oil, rape seed oil, high erusic rape seed oil, sunflower oil, safflower oil, corn oil, cottonseed oil, lard, tallow, palm kernel oil, coconut oil, peanut oil, castor oil and fractions thereof.

The compound of the present invention may be prepared from one or more relevant fatty acids rather than from an oil or fat containing one or more fatty acids. Suitable fatty acids for use in the preparation of the compound include lauric acid, palmitic acid, stearic acid, oleic acid, linoleic acid, linolenic acid, behenic acid, erucic acid, elaidic acid, and hydroxy acids such as 12 hydroxy oleic acid and 12 hydroxy stearic acid.

30

The process of the present invention may utilise, for example, castor oil or hardened castor oil. The compound of the present invention may be prepared from hardened castor oil. A typical fatty acid profile of castor oil and hardened castor oil is given below.

Castor Oil

Fatty Acid	Content [%]
Palmitic (C16)	1.0
Stearic (C18)	1.1
Oleic (C18:1)	3.8
Linoleic (C18:2)	4.4
Linolenic (C18:3)	0.5
Gadoleic (C20:1)	0.5
Ricinoleic (C18:1-OH)	87.4


Hardened Castor Oil

Fatty Acid	Content [%]
Palmitic (C16)	1.3
Stearic (C18)	9.3
Oleic (C18:1)	0.9
Linoleic (C18:2)	0.2
Arachidic (C20)	0.7
<u>Ricinoleic, hard (C18-OH)</u>	<u>84.9</u>

5

The nomenclature in parenthesis is Cxx:y where xx is the fatty acid carbon number and y indicates number of double bonds. Ricinoleic acid, hard (also known as 12-hydroxy stearic acid) has a hydroxyl group (OH) on the 12th carbon.

- 10 Particularly preferred compounds of the present invention are set out below with reference to the following formula



- 15 Compounds 1 to 42 are based on distilled monoglycerides. Particularly preferred are compounds 1 to 12. Compounds 43 to 70 are based on diglycerides. For each of the compounds below the chain may be saturated, cis-unsaturated or trans-unsaturated. It is particularly preferred that the chains are saturated.

Compound	Chain Length (including C=O group)		
	R1	R2	R3
1	18	2	2
2	18	H	2
3	18	2	H
4	2	18	2

Compound	Chain Length (including C=O group)		
	R1	R2	R3
5	H	18	2
6	2	18	H
7	16	2	2
8	16	H	2
9	16	2	H
10	2	16	2
11	H	16	2
12	2	16	H
13	14	2	2
14	14	H	2
15	14	2	H
16	2	14	2
17	H	14	2
18	2	14	H
19	12	2	2
20	12	H	2
21	12	2	H
22	2	12	2
23	H	12	2
24	2	12	H
25	10	2	2
26	10	H	2
27	10	2	H
28	2	10	2
29	H	10	2
30	2	10	H
31	8	2	2
32	8	H	2
33	8	2	H
34	2	8	2
35	H	8	2
36	2	8	H

Compound	Chain Length (including C=O group)		
	R1	R2	R3
37	22	2	2
38	22	H	2
39	22	2	H
40	2	22	2
41	H	22	2
42	2	22	H
43	18	18	2
44	18	18	H
45	18	2	18
46	18	H	18
47	16	16	2
48	16	16	H
49	16	2	16
50	16	H	16
51	14	14	2
52	14	14	H
53	14	2	14
54	14	H	14
55	12	12	2
56	12	12	H
57	12	2	12
58	12	H	12
59	10	10	2
60	10	10	H
61	10	2	10
62	10	H	10
63	8	8	2
64	8	8	H
65	8	2	8
66	8	H	8
67	22	22	2
68	22	22	H

Compound	Chain Length (including C=O group)		
	R1	R2	R3
69	22	2	22
70	22	H	22

COMPOSITION

In a preferred aspect of the present invention the wax is present in an amount of 2 to 40 wt. % based on the composition, preferably in an amount of 5 to 40 wt. % based on the composition, preferably in an amount of 10 to 40 wt. % based on the composition, preferably in an amount of 10 to 30 wt. % based on the composition, preferably in an amount of 15 to 25 wt. % based on the composition, more preferably in an amount of approximately 20 wt. % based on the composition.

10

In one preferred aspect of the present invention the wax is present in an amount of 5 to 50 wt. % based on the composition, preferably in an amount of 10 to 50 wt. % based on the composition.

15 In a preferred aspect of the present invention the compound as defined herein is present in an amount of 60 to 98 wt. % based on the composition, preferably in an amount of 60 to 95 wt. % based on the composition, preferably in an amount of 60 to 90 wt. % based on the composition, preferably in an amount of 70 to 90 wt. % based on the composition, preferably in an amount of 75 to 85 wt. % based on the composition, more preferably in an amount of approximately 80 wt. % based on the composition.

20


In one preferred aspect of the present invention the compound is present in an amount of 50 to 95 wt. % based on the composition, preferably in an amount of 50 to 90 wt. % based on the composition.

25

The composition of the present invention may comprise one or more components in addition to the wax and compound described herein. These additional components are typically referred to as auxiliary materials. In a preferred aspect of the present invention the composition further comprises an auxiliary material selected from ionic emulsifiers and sorbitan esters. Preferably the auxiliary material is selected from citric acid esters, diacetylated tartaric acid esters of monoglycerides, sorbitan esters, and lecithin.

30

We have surprisingly found that when the composition of the present invention contains an auxiliary material selected from ionic emulsifiers and sorbitan esters (such as citric acid esters, diacetylated tartaric acid esters of monoglycerides, sorbitan esters, and lecithin) it is not essential for the wax to be present in an amount of 10 to 40 wt.% and the compound to be present in an amount of 60 to 90 wt.%. The flexibility in the composition containing the auxiliary material when used as a coating may be sufficient at a large range of wax and compound amounts to achieve the necessary barrier properties without puncturing or cracking of the barrier. Thus in a further aspect the present provides a composition comprising i) wax, ii) a compound having the formula



wherein t is an integer, wherein each R₁, R₂ and R₃ is independently selected from an acyl group or a hydrogen atom, wherein at least one of R₁, R₂ and R₃ is H or an acyl group (a short acyl group) having from 2 to 6 carbon atoms, wherein at least one of R₁, R₂ and R₃ is an optionally branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group, and iii) an auxiliary material selected from ionic emulsifiers and sorbitan esters (such as an emulsifier selected from citric acid esters, diacetylated tartaric acid esters of monoglycerides, sorbitan esters, and lecithin).

20

In a preferred aspect of the present invention the auxiliary material is present in an amount of from 0.1 to 1.0 wt. % based on the composition, preferably in an amount of from 0.25 to 0.75 wt. % based on the composition, more preferably in an amount of from 0.4 to 0.6 wt. % based on the composition, more preferably is present in an amount of approximately 0.5 wt. % based on the composition.

25

The composition may be prepared by any suitable process. One skilled in the art would be able to provide suitable processes for the preparation of the present composition.

30


In one preferred aspect the present invention is prepared by heating the compound (such as ACETEM) to a temperature above its melting point but below the melting point

15

of the wax and contacting the compound with the wax. The composition may then be applied to a food material or allowed to cool.

Thus in a further aspect the present invention provides a process for the preparation of a composition comprising

i) a wax and ii) a compound, having the formula



wherein t is an integer; wherein each R₁, R₂ and R₃ is independently selected from an acyl group or a hydrogen atom; wherein at least one of R₁, R₂ and R₃ is H or an acyl group (a short acyl group) having from 2 to 6 carbon atoms; wherein at least one of R₁, R₂ and R₃ is an optionally branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group;

the process comprising the steps of

- (a) heating the compound to a temperature above its melting point but below the melting point of the wax and
- (b) contacting the compound with the wax.

Preferably the wax is present in an amount of 2 to 50 wt. % based on the composition

Preferably the compound is present in an amount of 50 to 98 wt. % based on the composition

In one aspect the composition formed in the above process may be milled or micro-milled. However, as small wax crystals are formed during the crystallisation of the composition, milling or micro-milling is not essential.

In a further aspect a composition in accordance with the present invention (irrespective of its process of production) may be heated to a temperature above the melting point of the compound (such as ACETEM) but below the melting point of the wax and then applied to a food material.

When the composition is prepared by heating or the composition is heated to heated to a temperature above the melting point of the compound (such as ACETEM) but below the melting point of the wax it forms a viscous fluid system. The viscous fluid system is able to absorb and retain the fluid compound inside the viscous fluid system thereby preventing migration of the fluid part into the food component on to which it is applied. Thus the composition becomes applicable as a heat stable barrier system in which the barrier may be applied or melted on a cold or medium tempered food item at which the barrier will crystallise. During the subsequent heating the barrier system will remain on the food item and not drain off or be absorbed into the food. In these aspects the barrier system may be heat stable up to approximately 75-80°C if one selected high melting wax types.

We have found that the composition of the present invention, not only but particularly when prepared by the above process, provides a heat stable barrier. By "heat stable" it is meant a barrier system which can be heated to an elevated temperature without losing functionality during the subsequent cooling. In particular the present composition provides a barrier system which remains at the point at which it is applied to a food material without draining off or be absorbed by the food component at the elevated temperature. This is believed to be achieved by maintenance of an internal structure at the elevated temperature which prevents the composition/barrier system from flowing. The strength of this internal structure can be measured as yield stress. As can be seen from Examples 18A and 18B, the internal structure of the barrier system at the elevated temperature may be modified and controlled to provide a barrier system which may be thickened to a consistency ranging from a thin paste to a thick paste depending on the composition of the barrier system.

The heat stability of the composition/barrier system allows for use in production of food items which are heated or baked during the food preparation and where a water migration barrier is required. The heat stability of the composition/barrier system makes it possible to apply the barrier before the baking process.

FOODSTUFF

As described above in one aspect the present invention provides a coated foodstuff

comprising (a) a foodstuff substrate, (b) a coating comprising a composition as defined herein .

The foodstuff may be selected from confectionery including sugar confectionery, chocolate, candy such as liquorice and water jellies, chewing gum, nuts; dairy products including cheese, whipped desserts, and ice cream; bakery products, either frozen or fresh and including bread, pizza, biscuits, crackers, cakes, pies; meat products including sausages, fish, ham, pork and beef, such as joints of pork or beef; fresh and dried fruit; and snacks.

10

In one preferred aspect the foodstuff comprises one or more food materials at least one of which is coated with the present composition. This is particularly advantageous because in such applications, it is often required to mix different food materials having different water contents. The present composition may prevent or reduce movement of water from one food material to another, which may result in degradation of the foodstuff

15

The foodstuff may comprise more than one coating layer on any given surface, for example two coating layers. The multiple coating layers may comprise a plurality of layers consisting of a composition in accordance with the present invention or may comprises layers of a composition in accordance with the present invention together with one or more layers not formed from the present composition.

20

In a preferred aspect the foodstuff may first be coated with a compound as defined herein and subsequently coated with a composition as defined herein. Thus the present invention may provide a foodstuff comprising a (a) a foodstuff substrate and a first coating material, wherein the first coating material is a compound as defined herein, (b) a second coating material applied on the first coating material and comprising a composition as defined herein.

25

30


We have surprisingly found that when a foodstuff is coated with a system comprising a least two layers such as that described above it is not essential for the wax to be present in an amount of 10 to 40 wt.% and the compound to be present in an amount of 60 to 90 wt.%. The flexibility in the composition when used as a coating may be sufficient at a large range of wax and compound amounts to achieve the necessary barrier properties

35


without puncturing or cracking of the barrier. It is believed that this results from the flexibility of the first coating material moderating movement of the food substrate with respect to the second coating material. Consequently the forces on the second coating material are moderated. Thus in a further aspect the present provides a coated foodstuff

5 comprising a

(a) a foodstuff substrate and a first coating material, wherein the first coating material is a compound having the formula



wherein t is an integer, wherein each R_1 , R_2 and R_3 is independently selected from an acyl group or a hydrogen atom, wherein at least one of R_1 , R_2 and R_3 is H or an acyl group (a short acyl group) having from 2 to 6 carbon atoms, wherein at least one of R_1 , R_2 and R_3 is an optionally branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group
 10 (b) a second coating composition applied on the first coating material, wherein the second coating composition comprises i) a wax, ii) a compound having the formula



wherein t is an integer, wherein each R_1 , R_2 and R_3 is independently selected from an acyl group or a hydrogen atom, wherein at least one of R_1 , R_2 and R_3 is H or an acyl group (a short acyl group) having from 2 to 6 carbon atoms, wherein at least one of R_1 , R_2 and R_3 is an optionally branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group.
 20

It will be appreciated by one skilled in the art that the composition of the present invention may be utilised to prevent water from ingress into a material, such as a foodstuff, or may be used to retain water within a material, such as a foodstuff. In one
 25

aspect of the invention the present composition is applied to prevent ingress of water in to foodstuff wherein the foodstuff is a cracker. In one alternative the present invention may be used in or to coat medicinal products, including pharmaceutical products and veterinary products.

5

The present invention will now be described in further detail by way of example only with reference to the accompanying figures in which:-

Figure 1 shows a yield stress curve for a barrier system as described in Example 18A; and

10

Figure 2 shows yield stress curve for a barrier system as described in Example 18B.

The present invention will now be described in further detail in the following examples.

EXAMPLES

15

Method

Water vapour permeability

Water vapour coefficients were measured using a SGA-100 Vapour Sorption Analyser from VTI Corporation 7650 West 26th Ave., Hialeah, FL 33016 USA. An aluminium cup of 2 cm in diameter was partly filled with deionised and de-aerated water leaving 3-5 mm
20 free head space. On top of the cup a film consisting of the barrier composition was placed. The cup had a small flange to which the film was sealed with a high vacuum grease purchased from Dow Corning GmbH, 65201 Wiesbaden, Germany. Water phases other than pure water can be used. Pure water secures a water activity of 1 at any test temperature. Using a salty solution instead of water reduces the water activity
25 and any desired water activity can be reached by adjusting the salt concentration or the type of salt in the water phase. The cup was placed in the weighing chamber of the VTI instrument. The temperature and relative humidity was adjusted to test conditions and weight loss was registered and monitored over time. The test temperature could be varied between 5-80°C and relative humidity could be adjusted between 0 and 100%.

30

The film was prepared by melting the barrier composition to 80°C and carefully blending all ingredients to a homogeneous system.

A small (3 x 5cm) nylon filter, having no resistance to water migration and water
35 evaporation, was placed on top of a hot microscope slide with a small pin in each end of

the slide. The height of the pins could be varied. Hot and melted barrier composition was gently poured on top of the filter and another hot microscope slide was placed on top of the pins and the barrier composition was allowed to cool and crystallise. After complete crystallisation the glasses were gently removed and the film was transferred to the aluminium cup and sealed. The nylon filter provides a support matrix for the barrier composition. Another way of preparing the film was to immerse the nylon filter directly into the hot and melted barrier composition and allow it to crystallise before sealing it on top of the aluminium cup.

- 10 The monitoring of the weight loss due to water migration through the film and subsequent water evaporation was continued for 5-600 minutes.

The weight was then plotted vs. time leaving out the first 100 min, which was used to adapt to the specific measuring conditions in the beginning of each trial.

15

The slope of the plotted line was determined. The slope equals (area through which the water migrates) x (the difference in water vapour pressure across the film) x (the ratio between the permeability coefficient and film thickness). The film thickness was measured after each experiment with a micrometer using the average of 4 measurements. The area of the film was calculated from the diameter. The difference in water vapour pressure was controlled by the water phase composition in the aluminium cup and by the relative humidity in the weighing chamber of the VTI instrument.

25 With pure water in the cup the head space above the water surface has a relative humidity of 100%. The water vapour pressure in the head space was then 100% of the saturated water vapour pressure at the specific test temperature. Adjusting the relative humidity in the weighing chamber of the VTI instrument resulted in a water vapour pressure of 15% of the saturated water vapour pressure at the specific test temperature.

- 30 The overall driving force for water migration and evaporation from the film was then 85% of the saturated water vapour pressure at the test temperature.

10 to 15 films of each barrier composition were prepared and analysed as above. For all samples the ratio between the permeability coefficient and the film thickness was plotted against the reciprocal film thickness. The slope of this line equals the permeability

35

coefficient.

Example 1

- 5 Distilled monoglyceride acetylated to 70% with a fatty acid composition mainly comprised of stearic acid and palmitic acid was analysed at 25°C with a water vapour pressure difference of 20.2 mmHg. The permeability coefficient was calculated to 995 mg mm / m² mmHg min.

10 **Example 2**

- Distilled monoglyceride acetylated to 70% with a fatty acid composition mainly comprised of stearic acid and palmitic acid was analysed at 5°C with a water vapour pressure difference of 5.5 mmHg. The permeability coefficient was calculated to 721 mg
15 mm / m² mmHg min.

Example 3

- White beeswax was analysed at 25°C with a water vapour pressure difference of 20.2
20 mmHg. The permeability coefficient was calculated to 14 mg mm / m² mmHg min.

Example 4

- Distilled monoglyceride acetylated to 70% and a fatty acid composition comprising
25 mainly of stearic acid and palmitic acid was provided in an amount of 50% and heated to 80°C, 50% white beeswax was added, melted and carefully mixed with the acetylated monoglyceride by agitation. The films were prepared as described above using microscope slides. The permeability coefficient was measured and calculated at 5°C and yielded 20 mg mm / m² mmHg min.

30

Example 5

- Distilled monoglyceride acetylated to more than 99% and a fatty acid composition comprised of mainly stearic acid and palmitic acid was mixed in a 90-10 ratio with white
35 beeswax as described in Example 4 and analysed at 5°C. The permeability coefficient

22

was calculated to 82 mg mm / m² mmHg min .

Example 6

- 5 Distilled monoglycerides acetylated to 70% with a fatty acid composition comprising of mainly stearic and palmitic acid was provided in an amount of 95% and mixed with 5% white beeswax as described in Example 4 and analysed at 5°C. The permeability coefficient was calculated to 115 mg mm / m² mmHg min.

10 Example 7

- Distilled monoglyceride acetylated to 70% with a fatty acid composition comprising of mainly stearic acid and palmitic acid was provided in an amount of 90% and mixed with 10% white beeswax as described in Example 4 and analysed at 5°C. The permeability
15 coefficient was calculated to 32 mg mm / m² mmHg min.

Example 8

- A commercial product from Loders Croklaan Hogeweg 1, 1521 AZ, Wormerveer,
20 Netherland, Coatbar A, which is a triglyceride composition was prepared as described in Example 4 without the use of beeswax and analysed at 5°C. The product was very brittle and easily formed cracks and holes. Furthermore it melted partly at ambient temperature and became soft. The permeability coefficient was calculated to 166 mg mm / m² mmHg min.

25

Texture

- Samples of barrier compositions were melted and carefully mixed at 80°C and poured into cylindrical glass beakers 6 cm in diameter and approximately 5 cm tall. After 3 days
30 of storage at the test temperature the consistency of the samples were analysed by use of a Texture Analyser TA-XT2 from Stable Micro Systems, Vienna Court, Lammas ad, Godalming, Surrey GU7 1YL, UK, equipped with a 2 mm P2 DIA CYLINDER STAINLESS probe. The probe penetrated the samples in one cycle with a prespeed of 2.0 mm/s and a penetrating speed of 0.5 mm/s. Distance was set to 10.0 mm and post
35 speed was 2.0 mm/s. Trigger weight was 3.0 g.

Each measurement provided a graph showing the force in gram required to penetrate the samples vs. time. All curves exhibited the same basic shape with an initial steep raising and an inflection point where the slope of the graph decreases.

5

The measured force in gram at the inflection point (from now on called inflection force) was used for comparison between the samples. A decrease in the measured force at the deflection point was seen for softer and more elastic compositions.

10 Example 9

The inflection force for different barrier compositions are shown below:

Barrier composition	Inflection force g at 5°C	Inflection force g at 20°C
100% Acetylated monoglycerides from ex 5	165	
90% Acetylated monoglycerides from ex 5 + 10% white beeswax	500	
80% Acetylated monoglycerides from ex 5 + 20% white beeswax	1000	
100 % White beeswax	4000	2200
20% Acetylated monoglyceride from ex 1 + 80% white beeswax	3400	
50% Acetylated monoglyceride from ex 1 + 50% white beeswax	2700	
60% Acetylated monoglyceride from ex 1 + 40% white beeswax	2000	
70% Acetylated monoglyceride from ex 1 + 30% white beeswax	1700	
80% Acetylated monoglyceride from ex 1 + 20% white beeswax	1400	700
90% Acetylated monoglyceride from ex 1 + 10% white beeswax	900	400
100% Acetylated monoglyceride from ex 1 +	340	200

Solid Fat Content

Mixtures of acetylated monoglycerides listed in Example 9 and white beeswax in different proportions ranging from pure beeswax to pure acetylated monoglycerides were tempered according to IUPAC 2.150a standard tempering method and the SFC (solid fat content) was measured on Bruker NMS 120 Minispec NMR Analyser, 762287 Rheinstetten, Germany, at 5°C and 20°C. The results show a linear relationship between mixing ratio of the acetylated monoglycerides and the white beeswax and the SFC without any sign of eutectic effect, which would have seriously damaged the water vapour barrier properties. The SFC measurements also showed that especially the acetylated monoglyceride listed in Example 1 mixed with white beeswax only loses approximately 2% point of the total solid fat content when heated from 5°C to 20°C. The barrier is then able to persist temperature fluctuations.

Barrier composition	SFC at 5°C	SFC at 20°C
100 % White beeswax	93.8	90.6
20% Acetylated monoglyceride from ex no 1 + 80% white beeswax	94.0	89.9
50% Acetylated monoglyceride from ex 1 + 50% white beeswax	92.9	89.8
60% Acetylated monoglyceride from ex 1 + 40% white beeswax	92.5	89.5
70% Acetylated monoglyceride from ex 1 + 30% white beeswax	92.2	89.6
80% Acetylated monoglyceride from ex 1 + 20% white beeswax	91.9	89.5
90% Acetylated monoglyceride from ex 1 + 10% white beeswax	91.5	89.3
100% Acetylated monoglyceride from ex 1	90.9	88.9

Application**Example 10**

A model application system was prepared by spraying approximately 400 mm on a

square cracker, namely a Barber Cream Cracker, produced by The Horizon Biscuit Company Ltd. Pasture Road, Moreton, Merseyside CH46 SE England. The melted 80°C hot barrier compositions were sprayed on the cracker in a 4-run-cycle on both sides on a conveyor belt. Between each cycle the cracker was turned 90°. Prior to the heating the cracker was preheated for a few seconds in 50-60°C hot air. After adapting to ambient room temperature for 1 hour a carrageenan gel was placed on top of the cracker. The gel had a water activity of 1 and it was prepared by dissolving 0.2% CaCl₂ and 0.2% KCl in distilled water and adding 3% carrageenan, during slow agitation. After heating the water to 85-90°C 0.1% Na-benzoate was added. After cooling to less than 75°C 0.6% citric acid solution was added (50% w/w). The liquid gel phase was poured in glass beakers and stored at 5°C.

The water activity of the cracker was 0.2 at 22°C.

- Before applying the gels on the top of the crackers all crackers were weighed (zero-value). The crackers with gels placed on the top were stored at 5°C. Over the following days 10 crackers were weighed each day after gentle removal of the gel. The gel did not stick to the cracker.
- For each cracker the respective zero-value was subtracted from the daily weight and the weight gain was calculated as the average of the 10 zero-value corrected measurements.

A barrier formulation as described in Example 1 was used and the weight gain (gram water per gram cracker) due to water migration was

Day 1	0.8 g
Day 2	1.5 g
Day 4	2.2 g
Day 7	2.8 g
Day 14	3.5 g

A cracker with no barrier system applied but treated similarly resulted in the following results:

Day 1	1.8 g
Day 2	2.2 g
Day 4	3.2 g

5 Example 11

A barrier system as described in Example 3 was tested as described in Example 10. The following weight gain due to water absorption was recorded.

10	Day 1	0.9 g
	Day 2	1.6 g
	Day 4	2.8 g
	Day 7	3.5 g
	Day 10	4.1 g
15	Day 14	4.3 g

Example 12

A barrier system as described in Example 4 was tested as described in Example 10 and
20 it provided the following weight gain results due to water migration:

	Day 1	0.1 g
	Day 4	0.5 g
	Day 7	1.4 g
25	Day 10	2.0 g
	Day 14	2.6 g

Example 13

30 A barrier system made of 20% pure white beeswax and 80% acetylated monoglycerides with a fatty acid composition comprising of mainly stearic and palmitic acid was applied on the crackers as described in Example 10. The weight gain due to water migration was:

35	Day 2	0.1 g
----	-------	-------

Day 4	0.2 g
Day 8	0.5 g
Day 14	0.8 g

5 **Example 14**

A barrier system as described in Example 1 was applied in 150 mm thickness as described in Example 10 followed by application of a new barrier layer on top of the first one. The second barrier system was similar to the barrier system described in Example 10 13. The weight gain due to water migration was:

Day 2	0.1 g
Day 4	0.2 g
Day 8	0.3 g
15 Day 12	0.5 g
Day 16	0.6 g

Example 15

20 A barrier system as described in Example 1 was applied on 75 mm thickness as described in Example 10 followed by application of 150 mm of the barrier system described in Example 13. On top of the second barrier layer new 75 mm layer of the barrier system described in Example 1 was applied. The weight gain due to water migration was:

25

Day 1	0.1 g
Day 5	0.2 g
Day 12	0.4 g
Day 16	0.5 g

30

Example 16

Distilled monoglyceride acetylated to 70% with a fatty acid composition comprising mainly stearic and palmitic acid was mixed in an amount of 80% with 20% white 35 beeswax as described in Example 4. The barrier system was applied on crackers as

described in Example 10 in 300 mm with the change that the applied gel had a water activity of 0.62.

The gel was prepared by premix 2% GRINDSTED^{RTM} PECTIN CF 140B, from DANISCO
5 A/S, Brabrand, Denmark, with 3% sugar and 20% water. The premix was added to a boiling mixture of 66% white sugar syrup 80% SS and 25% sugar. The mixture and the premix were boiled until a weight of 100% followed by addition of citric acid.

The weight gain due to water migration was:

10

Day 1	0.01 g
Day 2	0.04 g
Day 5	0.05 g
Day 8	0.11 g
15 Day 16	0.17 g

Example 17

A barrier system as described in Example 7 was prepared with the change that standard
20 soy lecithin, was melted into the original barrier mixture in the following concentrations: 0.05%, 0.1%, 0.2% and 0.3%. The texture of the barrier system was evaluated as described in "Texture" with the change that the force at 10 mm penetration was registered instead of the inflection force.

Lecithin	Force g at 10 mm 5°C
0%	2488
0.05%	2752
0.10%	2592
0.20%	2406
0.30%	2971

25

Example 18A

Acetylated distilled monoglycerides as described in Example 4 were mixed with 20% carnauba wax and melted and mixed at 90°C followed by cooling and crystallisation at

room temperature. After further 24 hours storage at room temperature the mixture was heated to 60°C and the yield stress was measured at 60°C on a Reological StressTech reometer using a CC 25 CCE measuring probe. The applied stress sweep clearly showed the yield stress and the subsequent break down of the internal structure when the applied stress was higher than the yield stress. The yield stress curve is shown in Figure 1 (Figure A). The yield stress was analysed to 0.1 Pa at 60°C.

Example 18B

Acetylated distilled monoglycerides as described in Example 18A were mixed and melted with 30% carnauba wax at 90°C and treated similar as in Example 18A except that the yield stress measurement was performed at 70°C. The yield stress curve is shown in Figure 2 (Figure B). The yield stress was analysed to 0.1 Pa.

Comments - The internal structure of the barrier system breaks down in both cases (Examples 18A and 18B) at a shear stress of 0.1 Pa. As long as the structure is intact the sample resists to flow and it is able to overcome increased stress applied from the instrument. This increased resistance to flow is measured as an viscosity increase. As soon the structure breaks down the measured viscosity decreases rapidly. This takes place at 0.1 Pa.


Various modifications and variations of the described methods and system of the invention will be apparent to those skilled in the art without departing from the scope and spirit of the invention. Although the invention has been described in connection with specific preferred embodiments, it should be understood that the invention as claimed should not be unduly limited to such specific embodiments. Indeed, various modifications of the described modes for carrying out the invention which are obvious to those skilled in chemistry or related fields are intended to be within the scope of the following claims.

CLAIMS:

1. A foodstuff comprising a first food material and a second food material wherein the first food material is coated with a composition comprising

5 i) a wax in an amount of 2 to 50 wt. % based on the composition

ii) a compound in an amount of 50 to 98 wt. % based on the composition, having the formula



wherein t is an integer

10 wherein each R₁, R₂ and R₃ is independently selected from an acyl group or a hydrogen atom,

wherein at least one of R₁, R₂ and R₃ is H or a short acyl group having from 2 to 6 carbon atoms

15 wherein at least one of R₁, R₂ and R₃ is an optionally branched chain acyl group, a long acyl group, consisting of a saturated chain having 10 to 20 carbon atoms and an optional hydrophilic branch group,

such that the composition prevents or reduces movement of water from one food material to the other.

20 2. A foodstuff according to claim 1, wherein the wax is selected from beeswax, candelilla wax, carnauba wax, jojoba wax, whale wax, paraffin wax, mineral wax, and microcrystalline wax.

3. A foodstuff according to claim 1 or 2, wherein the wax is beeswax.

25

4. A foodstuff according to any one of claims 1 to 3, wherein at least one of R₁, R₂ and R₃ is a short acyl group having from 2 to 6 carbon atoms.

5. A foodstuff according to any one of claims 1 to 4, wherein at least one of R_1 , R_2 and R_3 is a branched chain acyl group, a long acyl group.

6. A foodstuff according to any one of claims 1 to 3, wherein at least one of R_1 , R_2 and R_3 is an unbranched acyl group.

7. A foodstuff according to claim 6, wherein at least one of R_1 , R_2 and R_3 is an unbranched chain acyl group, a long acyl group consisting of a saturated chain having 10 to 20 carbon atoms.


8. A foodstuff according to any one of claims 1 to 3, wherein the or each long acyl group is unbranched.

9. A foodstuff according to any one of claims 1 to 8, wherein t is from 1 to 10.

10. A foodstuff according to claim 9, wherein t is from 1 to 5

11. A foodstuff according to claim 10, wherein t is 1 or 2.

12. A foodstuff according to any one of claims 1 to 11, wherein the compound is of the formula



13. A foodstuff according to any one of claims 1 to 12, wherein at least one of R_1 , R_2 and R_3 is H, and at least one of R_1 , R_2 and R_3 is a long acyl group consisting of a saturated chain having 10 to 20 carbon atoms.

14. A foodstuff according to any one of claims 1 to 12, wherein at least one of R_1 , R_2 and R_3 is a short acyl group having from 2 to 6 carbon atoms, and at least one of R_1 , R_2 and R_3 is an unbranched chain acyl group, a long acyl group, consisting of a saturated chain having 10 to 20 carbon atoms.

15. A foodstuff according to claim 14, wherein two of R_1 , R_2 and R_3 are the short acyl groups and wherein the other of R_1 , R_2 and R_3 is the long acyl group.

5 16. A foodstuff according to claim 14 or 15, wherein the short acyl group is present in an amount, on average, of no greater than 2 moles per mole of glycerol and esters thereof.

17. A foodstuff according to claim 14 or 15, wherein the long acyl group is present in an amount, on average, of at least 0.4 moles per mole of glycerol and esters thereof.

10

18. A foodstuff according to claim 14 or 15, wherein the long acyl group is present in an amount, on average, from 0.9 to 2 moles per mole of glycerol and esters thereof.

15 19. A foodstuff according to claim 14 or 15, wherein the long acyl group is present in an amount, on average, from 0.9 to 1 moles per mole of glycerol and esters thereof.

20. A foodstuff according to claim 14 or 15, wherein the total amount of the acyl groups is, on average, 0.8 to 3.0 moles per mole of glycerol and esters thereof.

20 21. A foodstuff according to any one of claims 1 to 20, wherein the chain of the long acyl group consists of a chain having 14 to 20 carbon atoms.

22. A foodstuff according to claim 21, wherein the chain of the long acyl group consists of a chain having 16 to 20 carbon atoms.

25

23. A foodstuff according to any one of claims 1 to 22, wherein the short acyl group is an acyl group having from 2 to 5 carbon atoms.

30 24. A foodstuff according to claim 23, wherein the short acyl group is an acyl group having 2 carbon atoms.

25. A foodstuff according to any one of claims 1 to 24, wherein the compound is an acetylated interesterification product of glycerol and an oil selected from fully hydrogenated,

partly hydrogenated and non-hydrogenated fats and oils.

26. A foodstuff according to any one of claims 1 to 24, wherein the compound is an acetylated interesterification product of glycerol and an oil selected from palm oil, soy oil, rape seed oil, high erusic rape seed oil, sunflower oil, safflower oil, corn oil, cottonseed oil, lard, tallow, palm kernel oil, coconut oil, peanut oil, castor oil and fractions thereof.

27. A foodstuff according to any one of claims 1 to 26, wherein the wax is present in an amount of 2 to 40 wt. % based on the composition.

28. A foodstuff according to any one of claims 1 to 27, wherein the wax is present in an amount of 5 to 40 wt. % based on the composition.

29. A foodstuff according to any one of claims 1 to 28, wherein the wax is present in an amount of 10 to 40 wt. % based on the composition.

30. A foodstuff according to any one of claims 1 to 29, wherein the wax is present in an amount of 10 to 30 wt. % based on the composition.

31. A foodstuff according to any one of claims 1 to 30, wherein the wax is present in an amount of 15 to 25 wt. % based on the composition.

32. A foodstuff according to any one of claims 1 to 31, wherein the wax is present in an amount of approximately 20 wt. % based on the composition.

33. A foodstuff according to any one of claims 1 to 32, wherein the compound is present in an amount of 60 to 98 wt. % based on the composition.

34. A foodstuff according to any one of claims 1 to 33, wherein the compound is present in an amount of 60 to 95 wt. % based on the composition.

35. A foodstuff according to any one of claims 1 to 34, wherein the compound is present in an amount of 60 to 90 wt. % based on the composition.

36. A foodstuff according to any one of claims 1 to 35, wherein the compound is present in an amount of 70 to 90 wt. % based on the composition.

5 37. A foodstuff according to any one of claims 1 to 36, wherein the compound is present in an amount of 75 to 85 wt. % based on the composition.

38. A foodstuff according to any one of claims 1 to 37, wherein the compound is present in an amount of approximately 80 wt. % based on the composition.

10

39. A foodstuff according to any one of claims 1 to 38, wherein the composition further comprises

(iii) an auxiliary material selected from ionic emulsifiers and sorbitan esters.

15

40. A foodstuff according to claim 39, wherein the auxiliary material is selected from citric acid esters, diacetylated tartaric acid esters of monoglycerides, sorbitan esters, and lecithin.

20

41. A foodstuff according to claim 39 or 40, wherein the auxiliary material is present in an amount of from 0.1 to 1.0 wt. % based on the composition.

42. A foodstuff according to claim 41, wherein the auxiliary material is present in an amount of from 0.25 to 0.75 wt. % based on the composition.

25

43. A foodstuff according to claim 41, wherein the auxiliary material is present in an amount of from 0.4 to 0.6 wt. % based on the composition.

44. A foodstuff according to claim 41, wherein the auxiliary material is present in an amount of approximately 0.5 wt. % based on the composition.

30

45. A foodstuff according to any one of claims 1 to 44, wherein the foodstuff is selected from confectionery, chewing gum, nuts; dairy products; bakery products, either frozen or fresh meat products; fresh and dried fruit; and snacks.

46. A foodstuff according to claim 45, wherein the confectionery is selected from sugar confectionery, chocolate, candy, liquorice and water jellies.

5 47. A foodstuff according to claim 45, wherein the dairy product is selected from cheese, whipped desserts, and ice cream.

48. A foodstuff according to claim 45, wherein the bakery product is selected from bread, pizza, biscuits, crackers, cakes and pies.

10

49. A foodstuff according to claim 45, wherein the meat product is selected from sausages, fish, ham, pork and beef.

50. A process for preparing a foodstuff as defined in any one of the claims 1 to 41,
15 comprising coating the food material with the composition.

1/1


Figure A

Figure 1



Figure B

Figure 2



(I)

