



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D06M 11/40, 16/00, D06P 1/673	A1	(11) International Publication Number: WO 95/24524 (43) International Publication Date: 14 September 1995 (14.09.95)
(21) International Application Number: PCT/GB95/00484 (22) International Filing Date: 6 March 1995 (06.03.95) (30) Priority Data: 9404510.1 9 March 1994 (09.03.94) GB (71) Applicant (for all designated States except US): COUR- TAULDS FIBRES (HOLDINGS) LIMITED [GB/GB]; 50 George Street, London W1A 2BB (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): TAYLOR, James, Martin [GB/GB]; 146 Field Lane, Alveston, Derby DE24 0GW (GB). (74) Agent: HALE, Stephen, Geoffrey; J.Y. & G.W. Johnson, Furnival House, 14-18 High Holborn, London WC1V 6DE (GB).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
(54) Title: FIBRE TREATMENT (57) Abstract The colour properties (i.e. freedom from a frosted visual appearance, especially in dyed form) of lyocell fibre, in particular in fabric form, can be improved by mercerising the fabric. The hand of the mercerised fabric can be softened to a marked degree by treatment with a cellulase enzyme.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

FIBRE TREATMENTField of the invention

This invention is concerned with methods of improving the visual appearance of lyocell fabrics.

5 It is known that man-made cellulose fibre can be made by extrusion of a solution of cellulose in a suitable solvent into a coagulating bath. One example of such a process is described in US-A-4,246,221, the contents of which are incorporated herein by way of reference.

10 Cellulose is dissolved in a solvent such as an aqueous tertiary amine N-oxide, for example N-methylmorpholine N-oxide. The resulting solution is then extruded through a suitable die into an aqueous bath to produce an assembly of filaments which is washed in water to remove the solvent and

15 is subsequently dried. This process is referred to as "solvent-spinning", and the cellulose fibre produced thereby is referred to as "solvent-spun" cellulose fibre or as lyocell fibre. Lyocell fibre is to be distinguished from cellulose fibre made by other known processes, which rely on

20 the formation of a soluble chemical derivative of cellulose and its subsequent decomposition to regenerate the cellulose, for example the viscose process.

As used herein, the term "lyocell fibre" means a cellulose fibre obtained by an organic solvent spinning

25 process, wherein the organic solvent essentially comprises a mixture of organic chemicals and water, and wherein solvent spinning involves dissolving cellulose in the organic solvent to form a solution which is spun into fibre without formation of a derivative of the cellulose. As used

30 herein, the terms "solvent-spun cellulose fibre" and "lyocell fibre" are synonymous. As used herein, the term "lyocell yarn" means a yarn which contains lyocell fibre, alone or in blend with other type(s) of fibre. As used herein, the term "lyocell fabric" means a fabric woven or

- 2 -

knitted from yarns, at least some of which are lyocell yarns.

Fibres may exhibit a tendency to fibrillate, particularly when subjected to mechanical stress in the wet state. Fibrillation occurs when fibre structure breaks down in the longitudinal direction so that fine fibrils become partially detached from the fibre, giving a hairy appearance to the fibre and to fabric containing it, for example woven or knitted fabric. Dyed fabric containing fibrillated fibre tends to have a "frosted" visual appearance, which may be aesthetically undesirable. Such fibrillation is believed to be caused by mechanical abrasion of the fibres during treatment in a wet and swollen state. Wet treatment processes such as dyeing processes inevitably subject fibres to mechanical abrasion. Higher temperatures and longer times of treatment generally tend to produce greater degrees of fibrillation. Lyocell fibres appear to be particularly sensitive to such abrasion in comparison with other types of cellulose fibre, in particular cotton which has an inherently very low fibrillation tendency.

It is an object of the present invention to provide dyed lyocell fabric which does not exhibit a "frosted" appearance and which does not develop such a "frosted" appearance after repeated laundering. This improvement is referred to hereinafter as improving the colour properties of the lyocell fabric. This term "colour properties" is to be distinguished from the terms "uniform dyeability" and "level dyeing" commonly used in the art. In general, the levelness of dyeing of a fabric does not change on repeated laundering. Cotton is a natural fibre, and its dyeability varies from fibre to fibre. In contrast, lyocell fibres are made by a controlled manufacturing process and exhibit uniform dyeability. Cotton does not fibrillate, and so its colour properties do not change during processing or laundering. The colour properties of known lyocell fabric may change depending on the type of treatment to which it is

- 3 -

subjected. For example, repeated laundering commonly induces fibrillation and worsens the colour properties of lyocell fabric, whereas enzyme (cellulase) treatment removes fibrils and generally improves the colour properties of the fabric.

Background art

It has been known for many years to subject cotton fibres, in particular in the form of yarn or fabric, to the process known as mercerisation. Mercerisation consists in treating the fibres with a strong alkali, usually aqueous sodium hydroxide, followed by washing with water and dilute acid to remove the alkali and drying. Cotton yarn and fabric may be held under tension during the treatment with alkali. The reasons for mercerising are to obtain (1) increased colour yield on dyeing or printing, (2) improved easy-care properties, (3) improved fibre lustre (when the cotton is held under tension during mercerising), and (4) more uniform dyeability. Cotton fibres are coated with mineral waxes and pectins which are removed by this treatment with aqueous alkali. Removal of these impurities increases the absorbency and dye receptiveness of the cotton fibres. If cotton contains a high proportion of thin-walled immature fibres, mercerising swells these fibres and makes them dye more like maturer fibres, thereby promoting uniform dyeing.

It is well known that man-made cellulose fibres such as viscose rayon and cuprammonium rayon fibres have naturally high dye receptiveness and lustre, generally higher than that of cotton. It is also well-known that such rayon fibres do not contain non-cellulosic waxy impurities. It is further well known that such rayon fibres are much less resistant than cotton to the action of sodium hydroxide. When rayon fibre is mercerised using 10 to 30 percent by weight aqueous sodium hydroxide, as might be used for cotton, the fibre becomes harsh and brittle, loses lustre

- 4 -

and may partially dissolve in the mercerising liquor. When rayon fabric soaked with such strong solutions of sodium hydroxide is washed with water, it becomes very swollen and loses nearly all its strength, with the result that the fabric becomes very liable to mechanical damage.

Disclosure of the invention

According to the invention a method of improving the colour properties of lyocell fibre consists in mercerising the fibre.

10 The lyocell fibre may be subjected to mercerisation in the form of staple fibre, tow, continuous filaments, spun yarn or lyocell fabric. Mercerisation of lyocell fabric may be preferred.

15 A typical mercerisation process for cotton yarn or fabric includes the steps of:

(1) wetting the cotton with a solution of caustic soda (10 to 30, often 20 to 25, per cent by weight sodium hydroxide in water) at ambient or slightly elevated temperature, for example at up to about 20 35°C;

(1a) optionally washing with water;

(2) souring with dilute aqueous acid (for example up to 3, preferably 1 to 3, per cent by weight of an inorganic acid such as sulphuric acid or 25 hydrochloric acid or an organic acid such as acetic acid);

(3) washing one or more times with water to remove the acid; the final wash may optionally contain a slightly alkaline softener to neutralise the last 30 traces of acid; and

- 5 -

- (4) drying the cotton, for example in an air dryer for 15 to 20 minutes at about 120°C or other conventional manner.

Similar conditions and equipment are appropriate for lyocell fibre.

It is highly surprising that lyocell fibre, which is a man-made cellulose fibre, can satisfactorily be treated with strong alkali in a mercerisation process. Other man-made cellulose fibres, for example viscose rayon and cuprammonium rayon fibre, suffer severe damage under such conditions.

Lyocell fibre treated according to the method of the invention may subsequently be dyed using known dyestuffs for cellulose in known manner. Dyed lyocell fabric containing fibre treated by the method of the invention has good colour properties and retains good colour properties on repeated laundering. In particular, such fabric has a much less "frosted" appearance than fabric subjected to the same processing steps but with omission of the mercerising treatment of the invention.

Procedures are known in which lyocell fibre is treated with a variety of chemical reagents, for example cross-linking agents, thereby reducing the degree of fibrillation and/or the tendency to fibrillation of the fibre. Such procedures generally cause an improvement in the colour properties of the fibre. However, such known procedures may suffer from the disadvantage that the improvement thereby produced may not be permanent. The colour properties of the fibre may for example deteriorate during repeated laundering. Furthermore, such known procedures may impair the dyeability or physical properties of the fibre. The method of the invention has advantages over such known procedures in that the improvement in colour properties thereby obtained remains through repeated laundering cycles; that the mercerised fibre has good dyeability; and that the

- 6 -

mercerised fibre has good physical properties. In particular, lyocell fabric containing lyocell fibre treated by the method of the invention exhibits the characteristic attractive drape and soft hand associated with lyocell
5 fabrics.

The reason for the improvement in the colour properties afforded by the invention is not fully understood. Unmercerised and mercerised samples of lyocell fabric appear very similar under the microscope, in particular in their
10 degree of fibrillation, provided that they have otherwise been treated in the same way.

Lyocell fibre or fabric, particularly fabric, treated by the method of the invention may subsequently be treated with an aqueous solution of a cellulase enzyme to remove
15 fibrils from the fabric in known manner. Many cellulase preparations suitable for the treatment of cellulosic fabrics are available commercially. Mercerisation generally hardens the handle of cellulosic fabrics. It has surprisingly been found that cellulase treatment softens the
20 handle of mercerised lyocell fabric to an unexpectedly large extent.

The degree of fibrillation of lyocell fibres and fabrics may be assessed by the following test method:-

Test Method (Assessment of Fibrillation)

25 There is no universally accepted standard for assessment of fibrillation, and the following method was used to assess Fibrillation Index (F.I.). Samples of fibre were arranged into a series showing increasing degrees of fibrillation. A standard length of fibre from each sample
30 was then measured and the number of fibrils (fine hairy spurs extending from the main body of the fibre) along the standard length was counted. The length of each fibril was measured, and an arbitrary number, being the number of

- 7 -

fibrils multiplied by the average length of each fibril, was determined for each fibre. The fibre exhibiting the highest value of this product was identified as being the most fibrillated fibre and was assigned an arbitrary 5 Fibrillation Index of 10. A wholly unfibrillated fibre was assigned a Fibrillation Index of zero, and the remaining fibres were evenly ranged from 0 to 10 based on the microscopically measured arbitrary numbers.

The measured fibres were then used to form a standard 10 graded scale. To determine the Fibrillation Index for any other sample of fibre, five or ten fibres were visually compared under the microscope with the standard graded fibres. The visually determined numbers for each fibre were then averaged to give a Fibrillation Index for the sample 15 under test. It will be appreciated that visual determination and averaging is many times quicker than measurement, and it has been found that skilled fibre technologists are consistent in their rating of fibres.

Fibrillation Index of fabrics can be assessed on fibres 20 drawn from the surface of the fabric. Woven and knitted fabrics having F.I. of more than about 2.0 to 2.5 are normally found to exhibit an unsightly appearance.

The invention is illustrated by the following Examples, in which parts and proportions are by weight unless 25 otherwise specified:-

Example 1

A piece of 2x1 twill fabric (190 g/m^2) woven from 100% Tencel 20 tex yarn (fibre 1.7 dtex) was prepared in open width by scouring with sodium carbonate and an anionic 30 detergent at 90°C and can-drying at 140°C . (Tencel is a Trade Mark of Courtaulds Fibres (Holdings) Limited for lyocell.) For mercerising, it was immersed in 14% aqueous sodium hydroxide at ambient temperature for 45 seconds, and

- 8 -

mangled to give 70% add-on. The fabric was rinsed in water at 95°C, neutralised in water containing 1 ml/l acetic acid, rinsed again and dried.

This treated (mercerised) fabric was dyed together with
5 an untreated piece in a rotary laboratory dyeing machine using a bath containing 4% Procion Blue HE-GN(Procion is a Trade Mark of Zeneca plc), 80 g/l Glaubers salt and 20 g/l soda ash at 80°C. The treated fabric dyed to a deeper shade than the untreated piece.

10 The two pieces of fabric were then washed at 60°C and tumble-dried a total of five times. The appearance of the treated piece was considerably less frosty than that of the untreated control piece. Under the microscope, the fibrils in the treated sample appeared shorter than those in the
15 control and appeared to be stuck to the main part of the fibre.

Samples of fibre were removed from the pieces of fabric and their F.I. assessed by the Test Method described above. The F.I. of fibres from the untreated control and the
20 treated fabric were 5.2 and 3.1 respectively. The appearance of the mercerised fabric was satisfactory despite its relatively high F.I.

Example 2

A piece of Tencel fabric as used in Example 1 was
25 treated (mercerised) and dyed as in Example 1, except that a 25% solution of sodium hydroxide was used. The treated piece and an untreated control piece were washed a single time, after which fibrillation was observed to be more evident in the untreated piece. The two pieces of fabric
30 were then immersed in an aqueous solution containing 3 ml/l Primafast 100 (a cellulase preparation available from Genencor) (Primafast is a Trade Mark) at pH 5.0 for 60 minutes at 55°C to remove fibrils, rinsed and dried. The two

- 9 -

pieces were then laundered five times in the manner described in Example 1. The F.I. of fibres removed from both pieces of fabric was 2.0. Nevertheless, the visual appearance of the treated piece was much cleaner and less
5 frosted than that of the untreated control. The handle of both samples was very soft, with a "peach-skin" touch. The handle of the mercerised and cellulase-treated sample was markedly softer than that of a sample which had not been treated with cellulase.

- 10 -

CLAIMS

1. A method of improving the colour properties of lyocell fibre, characterised in that it includes the step of mercerising the fibre.
- 5 2. A method according to claim 1, characterised in that the lyocell fibre is present in a lyocell fabric.
3. A method according to claim 1 or claim 2, characterised in that the lyocell fibre is subsequently treated with a solution of a cellulase enzyme.
- 10 4. A method according to any preceding claim, characterised in that the lyocell fibre is subsequently dyed.

INTERNATIONAL SEARCH REPORT

 International Application No
 PCT/GU 95/00484

 A. CLASSIFICATION OF SUBJECT MATTER
 IPC 6 D06M11/40 D06M16/00 D06P1/673

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

 Minimum documentation searched (classification system followed by classification symbols)
 IPC 6 D06M D06P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB,A,303 958 (THE SILVER SPRINGS BLEACHING & DYEING COMPANY, LIMITED) 7 February 1929 see page 2, left column, line 42 - line 54; claims ---	1, 4
A	FR,A,1 292 813 (LIPACO S.A.) 4 May 1962 see the whole document ---	1
A	WO,A,82 00164 (LINTREND LICENSING CO ;SLOAN F (GB)) 21 January 1982 see page 1, line 27 - page 2, line 5 see page 4, line 31 - page 5, line 12 see page 9, line 29 - line 37; claims --- -/--	1, 2, 4

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

21 July 1995

Date of mailing of the international search report

28. 07. 95

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+ 31-70) 340-3016

Authorized officer

Blas, V

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP 95/00484

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	TEXTIL PRAXIS INTERNATIONAL, vol. 47, no. 10, October 1992 LEINFELDEN DE, pages 972-974, XP 000311561 JOEL BAZIN ET AL. 'Cellulasebehandlung von Cellulosewaren mit Hilfe von Enzymen' see the whole document ---	1,3
P,A	TEXTILE CHEMIST AND COLORIST, vol. 26, no. 4, April 1994 NORTH CAROLINA US, pages 17-24, XP 000442817 GISELA BUSCHLE-DILLER AND S. HAIG ZERONIAN 'Enzymatic and Acid Hydrolysis of Cotton Cellulose After Slack and Tension Mercerization' see the whole document ---	1,3
P,A	LENZINGER BERICHTe, no. 74, September 1994 LENZING AT, pages 95-97, DIPL. ING. (FH) MICHAEL SCHMIDT 'BIO-POLISHING TM - EIN NEUER ALTERNATIVER VEREDLUNGSPROZESS FÜR CELLULOSEFASERN' see tables 6,7 ---	1-4
P,A	LENZINGER BERICHTe, no. 74, September 1994 LENZING AT, pages 99-101, RUDI BREIER 'DIE VEREDLUNG VON LYOCELLFASERN - EIN ERFAHRUNGSBERICHT' see the whole document ---	1-4
P,A	LENZINGER BERICHTe, no. 74, September 1994 LENZING AT, pages 19-25, DR. JURGEN LENZ ET AL. 'PROPERTIES AND STRUCTURE OF LYOCELL AND VISCOSE - TYPE FIBRES IN THE SWOLLEN STATE' see the whole document -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/L 95/00484

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB-A-303958		NONE	
FR-A-1292813	03-10-62	CH-A- 372634 DE-B- 1226980 GB-A- 936519	
WO-A-8200164	21-01-82	AU-A- 7320281 EP-A- 0044172	02-02-82 20-01-82