



(21) (A1) **2,253,798**
(86) 1997/04/24
(87) 1997/11/13

(72) BREITENBACH, Jörg, DE

(72) KOLTER, Karl, DE

(72) SCHMITT, Angelika, DE

(71) BASF AKTIENGESELLSCHAFT, DE

(51) Int.Cl.⁶ C08J 3/12, A61K 9/32, A61K 47/30, A61K 7/00

(30) 1996/05/03 (196 17 716.2) DE

(54) **POUDRES POLYMERES REDISPERSIBLES EN SOLUTION
AQUEUSE**

(54) **POLYMER POWDERS REDISPERSIBLE IN AQUEOUS
SOLUTION**

(57) L'invention concerne des poudres polymères redispersibles en solution aqueuse, leur utilisation dans des préparations cosmétiques ou pharmaceutiques, ou encore, phytosanitaires, ainsi qu'un procédé de fabrication des poudres précitées renfermant des copolymères porteurs de groupes acides ou basiques libres et, éventuellement, des produits auxiliaires, caractérisé en ce qu'on ajuste, avant séchage, le pH de la dispersion, par addition d'au moins un système tampon, à une valeur comprise entre 2,0 et 6,5, dans le cas de copolymères porteurs de groupes acides, et à une valeur comprise entre 7,5 et 12, dans le cas de copolymères porteurs de groupes basiques.

(57) Polymer powders redispersible in aqueous solution, their use in cosmetic, pharmaceutical or plant-protection preparations and a process for producing polymer powders redispersible in aqueous solution, containing free acid or basic group-bearing copolymers and possibly auxiliaries, in which the pH of the dispersion is adjusted by the addition of at least one buffer system before drying at 2.0 to 6.5 in the case of acid group-bearing copolymers and at 7.5 to 12 in the case of basic group-bearing copolymers.

PCT

WELTORGANISATION FÜR GEISTIGES EIGENTUM

Internationales Büro

INTERNATIONALE ANMELDUNG VERÖFFENTLICH NACH DEM VERTRAG ÜBER DIE
INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES PATENTWESENS (PCT)

(51) Internationale Patentklassifikation ⁶ : C08J 3/12		A1	(11) Internationale Veröffentlichungsnummer: WO 97/42255 (43) Internationales Veröffentlichungsdatum: 13. November 1997 (13.11.97)
<p>(21) Internationales Aktenzeichen: PCT/EP97/02097</p> <p>(22) Internationales Anmeldedatum: 24. April 1997 (24.04.97)</p> <p>(30) Prioritätsdaten: 196 17 716.2 3. Mai 1996 (03.05.96) DE</p> <p>(71) Anmelder (für alle Bestimmungsstaaten ausser US): BASF AKTIENGESELLSCHAFT [DE/DE]; D-67056 Ludwigshafen (DE).</p> <p>(72) Erfinder; und (75) Erfinder/Anmelder (nur für US): BREITENBACH, Jörg [DE/DE]; Hans-Sachs-Ring 7a, D-68199 Mannheim (DE). KOLTER, Karl [DE/DE]; Studentenstrasse 1, D-67117 Limburgerhof (DE). SCHMITT, Angelika [DE/DE]; Obere Hauptstrasse 69, D-67551 Worms (DE).</p> <p>(74) Gemeinsamer Vertreter: BASF AKTIENGESELLSCHAFT; D-67056 Ludwigshafen (DE).</p>		<p>(81) Bestimmungsstaaten: AU, BG, BR, CA, CN, CZ, GE, HU, IL, JP, KR, LV, MX, NO, NZ, PL, RO, RU, SG, SI, SK, TR, UA, US, eurasisches Patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), europäisches Patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Veröffentlicht <i>Mit internationalem Recherchenbericht. Vor Ablauf der für Änderungen der Ansprüche zugelassenen Frist. Veröffentlichung wird wiederholt falls Änderungen eintreffen.</i></p>	

(54) Title: POLYMER POWDERS REDISPERSIBLE IN AQUEOUS SOLUTION

(54) Bezeichnung: IN WÄSSRIGER LÖSUNG REDISPERGIERBARE POLYMERPULVER

(57) Abstract

Polymer powders redispersible in aqueous solution, their use in cosmetic, pharmaceutical or plant-protection preparations and a process for producing polymer powders redispersible in aqueous solution, containing free acid or basic group-bearing copolymers and possibly auxiliaries, in which the pH of the dispersion is adjusted by the addition of at least one buffer system before drying at 2.0 to 6.5 in the case of acid group-bearing copolymers and at 7.5 to 12 in the case of basic group-bearing copolymers.

(57) Zusammenfassung

In wässriger Lösung redispersierbare Polymerpulver, deren Verwendung in kosmetischen oder pharmazeutischen Zubereitungen oder Zubereitungen für den Pflanzenschutz sowie ein Verfahren zur Herstellung von in wässriger Lösung redispersierbaren Polymerpulvern, enthaltend freie säure- oder basengruppentragende Copolymere und gegebenenfalls Hilfsstoffe, dadurch gekennzeichnet, daß man den pH-Wert der Dispersion durch Zugabe mindestens eines Puffersystems auf 2,0 bis 6,5 im Falle säuregruppentragender Copolymere bzw. pH 7,5 bis 12 im Falle basengruppentragender Copolymere vor der Trocknung einstellt.

Polymer powders redispersible in aqueous solution

Description

5

The present invention relates to a process for preparing polymer powders redispersible in aqueous solution comprising copolymers carrying free acid or base groups and, if appropriate, auxiliaries, which comprises adjusting the pH of the dispersion 10 by the addition of a buffer system to a pH of from 2.0 to 6.5 in the case of copolymers carrying acid groups or a pH of from 7.5 to 12 in the case of copolymers carrying base groups.

The invention further relates to polymer powders redispersible in 15 aqueous solution and their use in cosmetic and pharmaceutical formulations and compositions for crop protection.

Patent DE 2 512 238 discloses film-forming polymer powders prepared from aqueous plastic dispersions. These film-forming 20 powders are used, after dissolution in an organic solvent, for coating solid drug formulations.

The use of organic solvents when coating solid drug formulations presents considerable technical problems. All the equipment used 25 has to be explosion-proof to prevent ignition of the solvent. For environmental and cost reasons, the evaporated solvent has to be recovered from the waste air. In addition, the solvent has to be removed completely from the pharmaceutical formulations.

Alternatives to using organic solvents were therefore sought.

30

Consequently, a number of processes employing water as solvent were developed. However, these processes have a number of disadvantages.

35

In US Patent 5 252 704, Bright et al. disclose redispersible polymer powders which can be prepared from copolymers by adding large amounts of polyvinylpyrrolidone prior to spray-drying. The high percentage of polyvinylpyrrolidone added, however, detrimentally affects the solubility of the polymer film obtained 40 after film-forming.

EP-B 88 951 and EP-B 161 326 disclose the redispersion of emulsion polymer powder having free carboxyl or amino groups by converting these groups into their salts. Free carboxyl groups are thus 45 converted into their salts by adding bases, and free amino groups are converted into their salts by adding acids. This is carried out after drying the polymer dispersion, by stirring an alkaline

solution into the carboxyl-containing polymer powder which is finely dispersed in water.

If the polymer carries free amino groups, an acid solution is 5 stirred in for dispersion.

For carboxyl-containing polymers, the possibility of partial neutralization of the free carboxyl groups by adding alkali prior to spray-drying has been described.

10

In this case, however, the dispersion viscosity and the degree of coagulum formation prior to spray-drying are critical parameters. In addition, if the alkali is added prior to drying, undesirable coagulum is easily formed during the subsequent redispersion. The 15 neutralization of the polymer powders, ie. the salt formation, is therefore preferably carried out after drying the powders, just before the solid drug formulations are prepared. For the user, this poses the problem of having to provide additional facilities for the neutralization and storage of the bases or acids.

20

It is an object of the present invention to develop redispersible polymers which can be dispersed directly without the disadvantages described to give an aqueous solution, and to make them available for applications in the cosmetic and 25 pharmaceutical sectors and in crop protection.

We have found that this object is achieved by adjusting the pH of the dispersion prior to drying by the addition of at least one buffer system to a pH of from 2.0 to 6.5 in the case of copolymers 30 carrying acid groups or a pH of from 7.5 to 12 in the case of copolymers carrying base groups, so as to provide a polymer powder which is readily redispersible.

The polymer powder according to the invention, which has a very 35 long shelf life, redisperses quickly in aqueous solution without forming coagulum, for example.

They are [sic] therefore ideally suitable as a film former in cosmetic, pharmaceutical or crop protection formulations.

40

Suitable buffers for the process according to the invention are, in principle, all known buffers such as described for example in Handbook of Biochemistry (H.A. Sober, R.A. Horte (Eds.), The Chemical Rubber Co., J 195-J 199, 1968).

45

The pH of the dispersion containing copolymers carrying free acid or base groups is advantageously adjusted prior to drying by the addition of at least one buffer system to a pH of from 2.0 to 6.5 in the case of copolymers carrying acid groups or a pH of from 5 7.5 to 12 in the case of copolymers carrying base groups. Preferably, the pH is adjusted prior to drying to a pH of from 3.0 to 6.0 in the case of copolymers carrying acid groups and to a pH of from 7.5 to 11 in the case of copolymers carrying base groups. By adjusting the pH, some of the free acid or base groups 10 of the copolymers are converted to their salts.

Buffer systems are conventional buffers and/or polymeric buffers.

Suitable buffers are, for example, all salts formed from weak 15 acids and strong bases or strong acids and weak bases, the salts being from identical acids or bases or mixtures of salts from different acids or bases.

The buffers used in the case of copolymers carrying free acid 20 groups, for example copolymers having free phosphono, sulfo or carboxyl groups, comprise at least one buffer system. The buffer region of the buffer system is preferably from pH 1 to 7. Suitable buffers or buffer solutions having a buffer region in the acidic range from pH 1 to 7 are for example buffers such as 25 the Walpole buffer (acetic acid/Na acetate, pH 3.6-5.6), Gomori aconitate buffer (aconitic acid/NaOH, pH 2.5-5.7), Kolthoff buffer (borax/succinate, pH 3.5-5.8), Sørensen citrate buffer (disodium citrate/HCl, pH 2.2-4.8), Sørensen glycine buffer I (glycine, NaCl/HCl, pH 1.2-3.6), Clark and Lub phthalate buffer I 30 (potassium biphthalate/HCl, pH 2.2-3.8), Clark and Lub phthalate buffer II (potassium biphthalate/NaOH, pH 4.0-6.2), Smith and Smith piperazine buffer (piperazine [sic], HCl/NaOH, pH 4.8-7.0), Clark and Lub potassium chloride/HCl buffer (KCl/HCl, pH 1.0-2.2), Gomori tris maleate buffer (tris maleate/NaOH, pH 35 5.2-8.6) or Gomori succinate buffer (succinate/NaOH, pH 3.8-6.0). Likewise, suitable buffers are MES, ADA, PIPES or ACES, which are common buffers in biochemistry, or amino acid buffers. Preference is given to buffers which are advantageously prepared from weak acids and their salts, such as sodium acetate/acetic acid, sodium 40 borate/boric acid, sodium phosphate/phosphoric acid, hydrogen carbonate/sodium carbonate, sodium hydroxide/citric acid, sodium hydroxide/tartaric acid. Suitable buffers are also buffers prepared from weak bases and their salts. Individual buffers or mixtures can be used for adjusting the pH of the dispersions. The 45 buffers used in the case of copolymers carrying free base groups, for example copolymers having free N-alkyl, amino or imino groups, comprise at least one buffer system. The buffer region of

the buffer system is preferably from pH 7 to 13. Suitable buffers or buffer solutions having a buffer region in the basic range from pH 7 to 13 are for example buffers such as Clark and Lub borate buffer (boric acid, KCl/NaOH, pH 7.8-10.0), Delory and King 5 buffer (carbonate/bicarbonate, pH 9.2-10.7) or Sørensen glycine buffer II (glycine, NaCl/HCl, pH 8.4-13). Likewise, suitable buffers are cholamine chloride, BES, TES, HEPES, acetamidoglycine, glycinamide, Tris, Bicine, Tricine or glycylglycine, which are common buffers in biochemistry, or amino 10 acid buffers.

Preferred are buffers which can advantageously be prepared from weak acids and their salts. Suitable buffers are also buffers prepared from weak bases and their salts. Single buffers or 15 mixtures can be used for adjusting the pH of the dispersions.

If polymeric buffers or buffer solutions are used for neutralizing the free acid groups or the free base groups of the copolymer, these polymeric buffers can be prepared advantageously 20 by adding a neutralizing agent to a polymer carrying free acid groups or free base groups. Suitable polymers are copolymers carrying free acid groups or free base groups prepared by free-radical polymerization of (meth)acrylic acid, its derivatives, maleic acid, fumaric acid, itaconic acid, crotonic 25 acid, vinylsulfonic acid, vinylphosphonic acid, polyethyleneimine and/or their salts, their esters and, if appropriate, their anhydrides. Suitable anhydrides are, for example, acrylic anhydride, methacrylic anhydride or maleic anhydride. Suitable polymers for preparing polymeric buffers are also natural 30 polymers having free acid or base groups, such as alginic acid or hyaluronic acid. The monomer composition of the dispersion in the added polymeric buffer solution may be identical or different. The polymeric buffer or the polymeric buffer solution is preferably prepared from a portion of the dispersion to be dried 35 by adding a neutralization agent. When preparing the polymer solution, the neutralization of the monomer units may be carried out partially or completely. Advantageously, from 50 to 100% by weight of the buffer polymer monomers able to form salts are in the salt form. Preferably, from 70 to 95% by weight of the 40 monomers are in the salt form. Particularly preferred is the complete neutralization. Depending on what kind of free groups the polymer is carrying, bases or acids are used for neutralizing. Suitable neutralizing agents are all physiologically acceptable bases or acids, such as sodium 45 hydroxide, sodium acetate, sodium phosphate, sodium carbonate, citric acid, tartaric acid, phosphoric acid, acetic acid and/or

formic acid. However, the abovementioned buffers or buffer solutions are also suitable.

Single acids, bases or buffers for neutralizing or their combinations can be used for preparing the polymeric buffer solution.

The starting dispersion can thus be converted into a dispersion which affords a redispersible powder after drying simply by 10 adjusting to an acidic or basic pH by the addition of at least one buffer system. Suitable buffer systems are single buffers and/or polymeric buffers or mixtures of buffers and/or polymeric buffers.

15 Irrespective of the nature of the salt-forming group, the same buffer and/or polymeric buffer can be used in all instances. The addition of an additional acid or base is not required, although perfectly possible. It is also possible to redisperse the dispersion powders obtained by free-radical polymerization and 20 dried without the addition of buffer by stirring into at least one buffer and/or at least one polymeric buffer.

For economic reasons, the solids content of the dispersion to be dried is normally above 25% by weight. However, when preparing 25 the polymeric buffer solution from such a dispersion, it is advantageous to adjust initially to a solids content of less than 15% by weight and to admix a neutralizing agent thereafter.

The dilute polymeric buffer solution prepared in this way is 30 subsequently combined with the dispersion to be dried.

The solids content of the combination of dispersion and buffer and/or polymeric buffer solution is from 1 to 50% by weight. Preferred are 5 to 40% by weight, particularly preferred are 20 35 to 35% by weight.

It is an advantage that the dispersions prepared using the buffer and/or polymeric buffer addition according to the invention can withstand pH-fluctuations during processing without the formation 40 of coagulum. By adding the buffer, the opening-pH, ie. the pH at which a polymer starts to swell and then dissolve, can be varied within precise ranges. This is particularly advantageous if a controlled release of an active compound is desired and optimum bioavailability is to be obtained by these means.

In principle, all copolymers obtainable by free-radical polymerization are suitable for preparing the redispersible polymer powders according to the invention.

5 Suitable monomer building blocks of these copolymers include monoethylenically unsaturated C₃-C₈-mono- and dicarboxylic acids, their anhydrides, esters, amides or salts, or mixtures of the carboxylic acids, anhydrides, esters, amides and salts mentioned.

10 Suitable carboxylic acids are, for example, acrylic acid, methacrylic acid, maleic acid, fumaric acid, itaconic acid or crotonic acid. Suitable anhydrides are, for example, acrylic anhydride, methacrylic anhydride or maleic anhydride.

15 Suitable esters are, for example, the C₁-C₁₀-alkyl esters or C₁-C₁₀-hydroxyalkyl esters of the abovementioned carboxylic acids. Preferred alkyl esters are the methyl, ethyl, propyl, butyl, i-butyl, tert-butyl, pentyl, i-pentyl-2,2-dimethylpropyl [sic], hexyl, i-hexyl, heptyl, i-heptyl, octyl, i-octyl-, 2-ethylhexyl, 20 nonyl, i-nonyl, decyl or i-decyl esters of acrylic and/or methacrylic acid. Particularly preferred are the methyl, ethyl, propyl, butyl, i-butyl or tert-butyl esters.

If the monomers are used for polymerization in the form of their 25 salts, alkaline earth metal, alkali metal or ammonium salts or the salts of organic amines are preferred; particularly preferred are alkali metal and ammonium salts.

Suitable basic monomer building blocks of the copolymers are 30 vinylimidazole, vinylimidazoline, vinylimidazolidine, vinylpyridine, monoalkyl- or dialkylaminoalkyl esters or monoalkyl- or dialkylaminoalkylamides of the abovementioned unsaturated carboxylic esters.

35 Single monomers or mixtures can be used as starting monomers for preparing the copolymers.

Suitable for the redispersible dispersion powders according to the invention are advantageously copolymers comprising from 80 to 40 15% by weight, preferably from 70 to 30% by weight, of a free-radically polymerizable monomer capable of forming salts.

The dispersion powders preferably comprise from 20 to 85% by weight of units [sic], preferably from 30 to 70% by weight, of 45 another monomer component consisting of at least one of the abovementioned alkyl esters of acrylic and/or methacrylic acid.

Suitable polymers are advantageously copolymers of methacrylic acid and ethyl acrylate, methacrylic acid and methacrylic esters, terpolymers of dimethylaminomethyl methacrylate, methyl and butyl methacrylate and copolymers of vinyl acetate and crotonic acid.

5 Preferred copolymers are copolymers of methacrylic acid and ethyl acrylate.

Moreover, the polymer solution or dispersion can comprise other auxiliaries.

10

Auxiliaries include polysaccharides such as celluloses, for example hydroxyalkylcellulose [sic] such as methylcellulose or ethylcellulose, or hydroxy(alkyl)alkylcelluloses such as hydroxypropylcellulose or hydroxypropylmethylcellulose phthalate,

15 starch, degraded starch, pectin, chitin, chitosan, arabinogalactan, xylan, gum xanthan, galactomannans such as gum ghatti, locust bean gum or gum tragacanth.

Proteins such as casein or gelatin or shellac can also be used as
20 auxiliaries.

Also suitable are sugars, such as mono-, di- and trisaccharides, for example glucose, mannose or sucrose, sugar derivatives, sugar alcohols or urea. Auxiliaries also include substances such as
25 pentaerythritol, pentaerythritol tetraacetate, polymers, such as polyethylene oxides or polypropylene oxides and their block copolymers, phosphatides, such as lecithin and lysolecithin, homo- and copolymers of vinylpyrrolidone, surfactants, citric acid, succinic acid, bile acids, sterols and other materials as
30 described by J.L. Ford (Pharm. Acta Helv. 61, 69-88, 1986).

Surfactants are, for example, the various types of Brij® i.e. cetyl, lauryl, oleyl or stearyl ethers having from 2 to 100 polyoxyethylene units, the various types of Myrij® stearyl esters
35 having from 8 to 100 polyoxyethylene units (=POE), the various types of Span® such as Span 20 (sorbitan monolaurates [sic]), Span 40 (sorbitan monopalmitates [sic]), Span 60 (sorbitan monostearates [sic]) or Span 80 (sorbitan monooleates [sic]), the various types of Tween® such as Tween 20 (POE (20) sorbitan
40 monolaurate), Tween 40 (POE (20) sorbitan monopalmitates [sic]), Tween 60 (POE (20) sorbitan monostearates [sic]) or Tween 80 (POE (20) sorbitan monooleates [sic]), the various types of Triton® (octylphenol ethoxylates) such as Triton X-15, X-35, X-100 CG, X-305 (70%), X-405 (70%), X-705 (70%), ethoxylated
45 castor oils such as polyoxyethylene glycerol triricinoleate 35 (Cremophor® EL) or polyoxyethylene glycerol trihydroxystearate 40 (Cremophor® RH40), ethoxylated 12-hydroxystearic acid such as

polyoxyethylene-660-12'-hydroxystearate (Solutol® HS15) or sodium lauryl sulfate.

Auxiliaries further include, for example, fillers, smoothers, 5 polishers, wetting agents, lubricants, mold parting agents, plasticizers, blowing agents, stabilizers, emulsifiers, colorants, flavors, plug-in agents [sic], flow agents and their mixtures.

10 Examples of plasticizers are low-molecular weight poly(alkylene oxides), such as poly(ethylene glycols), poly(propylene glycols), poly(ethylene propylene glycols), low-molecular weight organic plasticizers, such as glycerol, pentaerythritol, glycerol monoacetate, diacetate or triacetate, propylene glycol or sodium 15 diethylsulfosuccinate, phthalates, citrates, sebacates or acetylated fatty acid glycerides.

Examples of colorants are known azo dyes, organic or inorganic 20 pigments or colorants of natural origin. Preference is given to inorganic pigments.

Additionally other additives can be added, such as animal or vegetable fats, preferably in their hydrogenated form, in particular those that are solid at room temperature (20°C). These 25 fats are preferably of a melting point of 50°C or higher. Preference is given to triglycerides of the C₁₂-, C₁₄-, C₁₆- and C₁₈-fatty acids. The same function can also be performed by waxes, such as carnauba wax, candelilla wax, ouricurri [sic] wax, sugar cane wax, retamo wax, animal waxes, such as beeswax, shellac 30 waxes, Chinese insect waxes or lanolins, petroleum, lignite, peat and other montan waxes, polyolefin waxes, paraffin waxes, acid waxes, ester waxes, alcohol or amide waxes. These waxes can be unmodified or modified, partially or fully synthetic. Of course, single wax components such as wax acids, wax alcohols, wax 35 ketones, wax hydroxyacids, paraffins, resin acids, polyterpenes, resin alcohols, sterols, petroleum jelly or fatty acids or mixtures can also be added.

These fats, waxes, fat or wax derivatives can be mixed in 40 advantageously on their own or together with mono- and/or diglycerides or phosphatides, especially lecithin. The mono- and diglycerides are preferably derived from the abovementioned types of fats, ie. C₁₂-, C₁₄-, C₁₆- and C₁₈-fatty acids.

45 Further suitable auxiliaries are various emulsifiers. Commercially available emulsifiers are listed for example in M. and I. Ash, Handbook of Industrial Surfactants, Gower

Publishing Co., Hants, (1993). They can be low-molecular weight or polymeric compounds. Low-molecular weight compounds generally contain a straight-chain or branched, saturated or unsaturated or unsaturated [sic], cyclic or acyclic, aromatic or aliphatic alkyl radical having from 8 to 40, preferably from 10 to 30, in particular from 12 to 22 carbon atoms in the molecule.

Moreover, stabilizers such as antioxidants, photostabilizers, hydroperoxide decomposers, radical scavengers and stabilizers to prevent microbial attacks may be added.

Auxiliaries are also bases and acids added to control the solubility of an active compound (cf. for example K. Thoma et al., Pharm. Ind. 51, 98-101 (1989)).

The auxiliaries can be added to the dispersion before or after drying.

If appropriate, the auxiliaries are added to the dispersion in an amount of from 0.5 to 50% by weight, preferably from 1 to 30% by weight, based on the total solids content of the dispersion.

Polymers containing free acids or bases are prepared in a conventional manner by free-radical polymerization by any of the known processes.

The copolymers employed advantageously for preparing the redispersible polymer powders can be prepared by various processes, for example by precipitation polymerization, inverse emulsion polymerization, inverse suspension polymerization, emulsion polymerization, suspension polymerization or solution polymerization.

The polymerization may be carried out batchwise or continuously, with or without the use of seed polymers, by initially charging all or some of the components of the reaction mixture, or by first partially charging and then making-up all or some of the components of the reaction mixture, or by metering in the components without initial charge.

DE-A-4 325 158, for example, discloses a process for precipitation polymerization.

For drying the ready-prepared dispersion, any of the customary techniques may be employed, such as thin film drying, fluidized-bed spray drying, spray drying or lyophilization.

In addition, the dispersions to be atomized can contain auxiliaries for spraying, such as polyvinyl alcohols, cellulose derivatives, starch derivatives, ligninsulfonates, polyacrylic acid and polyacrylamides. Suitable antiblocking agents which may be added are aluminum silicates, such as bentonites, kieselguhr, colloidal silica gel, diatomaceous earth, calcium carbonate, magnesium silicates such as talc or tricalcium phosphate.

The atomizing is preferably carried out as hydrodynamic atomizing by liquid pressure or air pressure through nozzles such as single component nozzles, multicomponent nozzles or disk nozzles using conventional atomizing equipment.

The basic principle is the atomization of the solution into very small droplets. These droplets have a very large surface area allowing fast evaporation. The small droplet diameter required is achieved by the speed of the atomizer wheel or the pressure of the atomizer gas. The degree of evaporation obtainable is sufficient to remove completely the moisture from the droplets. Owing to the heat of evaporation lost and the short length of time the particles remain suspended, thermal damage to the product is avoided.

The liquid droplets can be dried in a conventional spray tower by using air or an inert gas such as nitrogen, argon or helium as drying gas which is passed through the drying tower in a cocurrent or countercurrent flow with the liquid droplets. The drying gas is preferably used in a cocurrent flow, the temperature of the gas when entering the tower being from 60 to 160, preferably from 90 to 140°C, and the temperature when leaving the tower being from 40 to 100, preferably from 60 to 80°C. The evaporation of the solvent can be carried out at atmospheric pressure or at from 0.6 to 1.2 bar.

The resulting powder can be separated off from the gas stream in a customary manner by using a cyclone.

The residual solvent content of the powder formed this way is generally not above 7.5% by weight. The particle size of the resulting powder particles is generally from 10 to 150 µm. Employing spray granulation, particles sizes of up to 450 µm can be achieved.

The polymer powders according to the invention redispersible in aqueous solution are far more readily redispersed than the prior art. In all experiments, redispersion was > 90 %. It is an advantage that films prepared from the dispersions according to

11

the invention dissolve more quickly than films prepared from starting dispersions. Therefore, in the small intestine, the active compound is released more quickly from coated administration forms.

5

The redispersible dispersion powders according to the invention or the dispersions prepared therefrom or other secondary products are suitable for all solid or semisolid cosmetic or pharmaceutical formulations or for compositions used in crop or

10 animal protection.

Solid or semisolid cosmetic or pharmaceutical formulations include, in a nonlimiting manner, tablets, crystals comprising an active compound, microtablets, sugar-coated tablets, pellets,

15 pastilles, capsules, microcapsules and granules.

A particular method of application of the redispersible dispersion powders is the preparation of transdermal therapeutic systems.

20

Applications in crop protection include pheromone traps for harmful insects requiring a targeted, sustained release of the pheromone.

25 Examples:

Example 1

Buffers used in Examples 1, 2, 5 and 6

30

- Merck buffer pH 5.0 contains in 1 l
20.256 g of citric acid
7.84 g of NaOH

35

- Merck buffer pH 6.0 contains in 1 l
12.526 g of citric acid
6.32 g of NaOH

40

- Merck buffer pH 4.66 contains in 1 l
6.005 g of acetic acid
8.204 g of Na acetate

600 g of a 30 % strength dispersion of Eudragit® L30D are admixed with 100 g of a 0.9% strength citric acid buffer with stirring.

45 The resulting pH is then 4.0. The entire solution is then spray-dried by known methods (drying gas: cocurrent nitrogen, inlet temperature: 125°C, outlet temperature: 50°C). A redispersible

12

polymer powder is obtained which can be redispersed by stirring into water. The percentage of coagulum of < 50 μm is 0% (determination see Example 7 [sic]). The opening-pH is 5.5.

5 Example 2

180 g of a methacrylic acid/ethyl acrylate copolymer (ratio 1:1) are stirred into an aqueous solution containing a 0.8% strength citrate buffer. This gives a dispersion of the methacrylic acid 10 copolymer which was previously not redispersible.

Example 3

Preparation of a redispersible powder made of Eudragit® L30D 15 (Röhm GmbH, acrylate dispersion made of ethyl acrylate and methacrylic acid)

a) Preparation of an aqueous polyacrylate buffer solution

20 93.4 g of a 10% strength dispersion (Eudragit® L30D) is converted into 114.1 g of an aqueous acrylate solution having a pH of 7.0 by the addition of 20.7 g of an aqueous 10% strength NaOH solution.

25 b) Preparation of the mixture

1000 g of a 30% strength dispersion (Eudragit® L30D, pH about 2-3) are admixed with 114 g of the solution prepared 30 under a). This gives a polyacrylate dispersion having a pH of 5.2. The dispersion is then spray-dried. This yields a redispersible powder.

Example 4

35 a) Preparation of an aqueous polyacrylate buffer solution

93.4 g of a 10% strength dispersion (Kollicoat® MAE 30D, 40 BASF AG, acrylate dispersion made of ethyl acrylate and methacrylic acid, solids content about 30%) is converted into 114.1 g of an aqueous acrylate solution having a pH of 7.0 by the addition of 20.7 g of an aqueous 10% strength NaOH solution.

b) Preparation of the mixture

5 1000 g of a 30% strength dispersion (Kollicoat® MAE 30D, BASF AG, acrylate dispersion made of ethyl acrylate and methacrylic acid, solids content about 30%, pH about 2-3) are admixed with 114 g of the solution prepared under a). This gives a polyacrylate dispersion having a pH of 5.2. The dispersion is then spray-dried. This yields a redispersible powder.

10

Example 5

Coating for tablets

15 20 In a horizontal drum coater (type Accela Cota, Manesty), 5000 g of propanolol [sic] tablets having an active compound content of 40 mg and a tablet weight of 250 mg were coated with a gastric juice-resistant film coating based on a redispersible methacrylic acid/ethyl acrylate copolymer comprising 2% of acetate buffer pH 4.66 based on the film former, thus applying 6 mg/cm² of gastric juice-resistant film former or 8 mg/cm² of solids.

The dispersion sprayed on was of the following composition:

25	Pigment suspension: Titanium dioxide	0.5 %
	Talc	2.0%
	Sicovit Red 30	0.5 %
	Kollidon 30	0.5 %
	Water	10.0 %

30

Coating suspension: Methacrylic acid/ethyl acrylate copolymer containing 2% of acetate buffer

35	pH 4.66	15.0 %
	Triethyl citrate	1.5 %
	Water	70.0 %
	Total weight	100.0 %

40 45 The pigment suspension was homogenized in a corundum disk mill. The methacrylic acid/ethyl acrylate copolymer containing 2% of acetate buffer was redisperséed by slowly stirring the solids into water using a paddle stirrer, thus immediately forming a very fine dispersion.

14

1680.8 g of the spray suspension was sprayed on at an incoming air temperature of 46°C, an outgoing air temperature of 33°C and a spray rate of 40 g/min. The coating was very smooth, even and a uniform red color.

5

The release in artificial gastric juice (pH: 1.2) showed the coating to be gastric juice-resistant for over 2 h, and the subsequent rebuffering to pH 6.8 demonstrated the rapid opening of the coating in the neutral region (99% release within 60 min).

10

Release rate:

15

60 min	pH 1.2	0.5 %	of active compound released
--------	--------	-------	-----------------------------

120 min	pH 1.2	0.8 %	of active compound released
---------	--------	-------	-----------------------------

Rebuffering to pH 6.8 using phosphate buffer

20

150 min	99.0 %	of active compound released
---------	--------	-----------------------------

Example 6

25

Redispersibility

20 g of redispersible methacrylic acid/ethyl acrylate copolymer comprising 2% of acetate buffer or 5% of citrate buffer based in each case on the film former were suspended in 80 g of demineralized water using a magnetic stirrer. The total stirring time was 60 min. The suspension was then passed through two sieves stacked on top of each other having mesh sites of 125 µm and 50 µm, and the residue - if present - was washed with a little water. After drying, the residue was determined gravimetrically.

35

Result	Residue	
	125 µm	50 µm
Methacrylic acid/ethyl acrylate copolymer comprising 2% of acetate buffer pH 4.66	0.00 %	0.02 %
Methacrylic acid/ethyl acrylate copolymer comprising 5 % of citrate buffer pH 6.0	0.00 %	0.01 %

45

We claim

1. A process for preparing polymer powders redispersible in aqueous solution comprising copolymers carrying free acid or base groups and, if appropriate, auxiliaries, which comprises adjusting the pH of the dispersion by the addition of at least one buffer system to a pH of from 2.0 to 6.5 in the case of copolymers carrying acid groups or to a pH of from 7.5 to 12 in the case of copolymers carrying base groups prior to drying.
5
2. A process as claimed in claim 1, wherein the pH of the dispersion is adjusted by the addition of at least one buffer system to a pH of from 3.0 to 6.0 in the case of copolymers carrying acid groups or to from 7.5 to 11 in the case of copolymers carrying base groups prior to drying.
15
3. A process as claimed in claim 1 or 2, wherein the buffer system used comprises salts of weak acids and strong bases or salts of strong acids and weak bases.
20
4. A process as claimed in claim 1 or 2, wherein the buffer system used comprises polymeric buffers obtainable by adding a neutralizing agent to a polymer carrying free acid or base groups.
25
5. A process as claimed in any of claims 1 to 4, wherein the polymer powder used comprises copolymers carrying free carboxyl or amino groups.
30
6. A process as claimed in any of claims 1 to 5, wherein the polymer powder used comprises copolymers having from 20 to 85% by weight of an alkyl ester of acrylic and/or methacrylic acid and from 80 to 15% by weight of a free-radically polymerizable monomer capable of forming salts.
35
7. Polymer powders redispersible in aqueous solution obtainable by any of the processes as claimed in claims 1 to 6.
40
8. The use of polymer powders redispersible in aqueous solution as claimed in claim 7 in cosmetic or pharmaceutical formulations or compositions for crop protection.
45

16

9. The use of a buffer system as claimed in claims 3 or 4 for redispersing polymer powders comprising copolymers carrying free carboxyl or amino groups dried without the addition of buffer.

5

10. Cosmetic, pharmaceutical or crop protection formulations comprising polymer powders redispersible in aqueous solution as claimed in claim 7 and customary additives.

10

15

20

25

30

35

40

45