




(86) Date de dépôt PCT/PCT Filing Date: 2013/09/25
(87) Date publication PCT/PCT Publication Date: 2014/04/03
(45) Date de délivrance/Issue Date: 2021/10/26
(85) Entrée phase nationale/National Entry: 2015/04/22
(86) N° demande PCT/PCT Application No.: US 2013/061725
(87) N° publication PCT/PCT Publication No.: 2014/052477
(30) Priorités/Priorities: 2012/09/25 (US61/705,403);
2013/03/15 (US61/801,597)

(51) Cl.Int./Int.Cl. *A61F 2/44* (2006.01),
A61B 17/70 (2006.01), *A61F 2/28* (2006.01)
(72) Inventeur/Inventor:
HUNT, JESSEE, US
(73) Propriétaire/Owner:
4WEB, INC., US
(74) Agent: RIDOUT & MAYBEE LLP

(54) Titre : IMPLANTS PROGRAMMABLES ET PROCEDES D'UTILISATION D'IMPLANTS PROGRAMMABLES POUR
REPARER DES STRUCTURES OSSEUSES
(54) Title: PROGRAMMABLE IMPLANTS AND METHODS OF USING PROGRAMMABLE IMPLANTS TO REPAIR BONE
STRUCTURES



(57) Abrégé/Abstract:

Various embodiments of implant systems and related apparatus, and methods of operating the same are described herein. In various embodiments, an implant for interfacing with a bone structure includes a web structure, including a space truss, configured to interface with human bone tissue. The space truss includes two or more planar truss units having a plurality of struts joined at nodes. Implant are optimized for the expected stress applied at the bone structure site.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(10) International Publication Number
WO 2014/052477 A1

(43) International Publication Date
3 April 2014 (03.04.2014)

(51) International Patent Classification:

A61F 2/44 (2006.01) A61B 17/70 (2006.01)
A61F 2/28 (2006.01)

(21) International Application Number:

PCT/US2013/061725

(22) International Filing Date:

25 September 2013 (25.09.2013)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/705,403 25 September 2012 (25.09.2012) US
61/801,597 15 March 2013 (15.03.2013) US

(71) Applicant: 4WEB, INC. [US/US]; 6170 Research Rd.,
Suite 219, Frisco, Texas 75033 (US).

(72) Inventor: HUNT, Jesse; 6629 Whispering Woods Court,
Plano, Texas 75024 (US).

(74) Agent: DELUCA, Mark, R.; Meyertons, Hood, Kivlin,
Kowert & Goetzel, P.C., P.O. Box 398, Austin, Texas
78767-0398 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME,
MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ,
OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA,
SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: PROGRAMMABLE IMPLANTS AND METHODS OF USING PROGRAMMABLE IMPLANTS TO REPAIR BONE
STRUCTURES




FIG. 10

(57) Abstract: Various embodiments of
implant systems and related apparatus, and
methods of operating the same are de-
scribed herein. In various embodiments,
an implant for interfacing with a bone
structure includes a web structure, includ-
ing a space truss, configured to interface
with human bone tissue. The space truss
includes two or more planar truss units
having a plurality of struts joined at nodes.
Implant are optimized for the expected
stress applied at the bone structure site.

**TITLE: PROGRAMMABLE IMPLANTS AND METHODS OF USING
PROGRAMMABLE IMPLANTS TO REPAIR BONE STRUCTURES**

BACKGROUND OF THE INVENTION

5 1. Field of the Invention

[0001] The present invention relates generally to medical devices and, more specifically, to implants.

2. Description of the Relevant Art

10 [0002] Implants may be used in human and/or animals to support and/or secure one or more bones. For example, implants may be used in the spine to support and/or replace damaged tissue between the vertebrae in the spine. Once implanted between two vertebrae, the implant may provide support between the two vertebrae and bone growth may take place around and through the implant to at least partially fuse the two vertebrae for long-term support. Implants may include relatively large rims with solid material that may cover, for example, 50% of the area that
15 interacts with the endplate. The rim may provide a contact area between the implant and the vertebral endplates. Large rims may have several drawbacks. For example, large rims may impede bone growth and reduce the size of the bone column fusing the superior and inferior vertebral bodies. Additionally, large rims preferentially support and regionalize loads, preventing distribution of force and accommodating response. The process of localizing loading also serves
20 to under load other areas of the vertebral bodies, thereby activating regional resorption according to negative microstrain.

[0003] Spinal implants may include open channels through the center of the supporting rims in a superior/inferior direction. The open channel design may require members of the implant that separate the rims that interact with the vertebral endplates to absorb the compressive forces
25 between the vertebral endplates. This may increase the pressure on smaller areas of the vertebral endplates and may potentially lead to stress risers in the vertebral endplates. Further, while bone graft material is often used in conjunction with implants to encourage bone growth, the open column design of implants may reduce the likelihood of bone graft material from securing itself to the implant which could result in a bio-mechanical cooperation that is not conducive to
30 promoting good fusion.

[0004] Bone graft material may be packed into the implant in a high-pressure state to prevent bone graft material from exiting the implant while being placed between the vertebral endplates. The high-pressure state may also reduce the potential for the bone graft material loosening due to

motion between the implant and the vertebral endplates or compressive forces experienced during settling of the implant. In addition, a high-pressure environment may allow the bone graft material to re-model and fuse at greater strength. High-pressure states, however, may be difficult to create and maintain for the bone graft material in an implant. In particular, the lack of attachment of the bulk graft cannot fully accept or integrate the differential loading anticipated in normal kinetic scope.

SUMMARY OF THE INVENTION

[0005] Various embodiments of implant systems and related apparatus, and methods of operating the same are described herein. In various embodiments, an implant for interfacing with a bone structure includes a web structure, including a space truss, configured to interface with human bone tissue, including cells, matrix, and ionic milieu. The space truss includes two or more planar truss units having a plurality of struts joined at nodes.

[0006] In an embodiment, an implant for interfacing with a bone structure includes: a web structure that is formed from a plurality of struts joined at nodes, wherein the web structure is configured to interface with human bone tissue. The diameter and/or length of the struts and/or the density of the web structure are predetermined such that when the web structure is in contact with the bone structure, its matrix, or the cells from which it is derived, at least a portion of the struts create a microstrain, that is transferred to the adherent osteoblasts, bone matrix, or lamellar tissue, of between about 1 $\mu\epsilon$ and about 5000 $\mu\epsilon$, or between about 500 $\mu\epsilon$ and 2000 $\mu\epsilon$, or between about 1000 $\mu\epsilon$ and about 1500 $\mu\epsilon$ or to a negative reflection of compression in interval and resonance with loading in both flexion, extension, torque, or combinations thereof. These ranges are optimized to known load-response dynamics, but are meant as guides rather than limitations to the activity and response. The diameter and/or length of the struts is predetermined so that at least a portion of the struts during loading create a change in length of the adherent osteoblasts, bone matrix, or lamellar tissue, of between about 0.05% and about 0.2% or between about 0.1% and about 0.15% causing an osteogenic response. Struts may have a length of between about 1mm to about 100mm. The diameter of the strut may be predetermined such that the struts create a change in length of the adhered osteoblasts of between about 0.05% and 0.2% when the web structure is in contact with the bone structure. Alternatively, the diameter of the strut is predetermined such that the strut undergoes a change of length of between about 0.000125% and 0.0005%, or between about 0.00025% and 0.000375%. In some embodiments, at

least a portion of the struts are composed of struts having a length of 1mm to 100mm and a diameter ranging between .250mm and 5mm.

[0007] In an embodiment, an implant for interfacing with a bone structure includes a web structure that is formed from a plurality of struts joined at nodes, wherein the web structure is configured to interface with human bone tissue. The web structure, in some embodiments, includes a first bone contact surface and a second bone contact surface. A first portion of struts that comprise the space truss have a physical property that is different from a second portion of the struts that comprise the space truss. The first portion of struts that comprise the space truss may have: a deformation strength; a defined length; a diameter; a differential diameter along its length; a density; a porosity; or any combination of these physical properties; that is different from the second portion of the struts that comprise the space truss. In an embodiment, the space truss includes one or more central struts extending from the first bone contact surface to the second bone contact surface, wherein the central struts have a deformation strength that is greater than or less than the surrounding struts. In an embodiment, the space truss comprises one or more longitudinal struts extending parallel to the first bone contact surface and/or the second bone contact surface, wherein the longitudinal struts have a deformation strength that is greater than or less than the surrounding struts. The diameter of the first portion of the struts may be greater than a diameter of the second portion of the struts. The material used to form the first portion of struts may be different from the material used to form the second portion of struts.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] Advantages of the present invention will become apparent to those skilled in the art with the benefit of the following detailed description of embodiments and upon reference to the accompanying drawings in which:

[0009] FIGS. 1A-1B illustrate views of an implant with lordosis, according to an embodiment;

[0010] FIGS. 2A-2D illustrate views of an implant without lordosis, according to an embodiment;

[0011] FIGS. 3A-3B illustrate a web structure formed with triangular-shaped building blocks, according to an embodiment;

[0012] FIGS. 4A-4B illustrate a top structure of an internal web structure of the implant, according to an embodiment;

[0013] FIGS. 5A-5C illustrate progressive sectioned views of the implant showing the internal structure of the implant, according to an embodiment;

[0014] FIG. 5D illustrates an isometric view of the implant, according to an embodiment;

[0015] FIGS. 6A-6D illustrate another configuration of the web structure, according to an embodiment;

[0016] FIG. 7 illustrates a random web structure, according to an embodiment;

5 [0017] FIG. 8 illustrates a flowchart of a method for making an implant, according to an embodiment;

[0018] FIG. 9 illustrates a flowchart of a method for implanting a spinal implant, according to an embodiment;

[0019] FIG. 10 depicts a diagram of stresses distributed through an implant; and

10 [0020] FIGS 11A-C depict schematic diagrams of the effect of compression on osteoblast cells.

[0021] While the invention is susceptible to various modifications and alternative forms, specific embodiments thereof are shown by way of example in the drawings and will herein be described in detail. It should be understood, however, that the drawings and detailed description thereto are not intended to limit the invention to the particular form disclosed, but on the contrary, the
15 intention is to cover all modifications, equivalents, and alternatives falling within the spirit and scope of the present invention as defined by the appended claims. Note, the headings are for organizational purposes only and are not meant to be used to limit or interpret the description or claims.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

20 [0022] FIGS. 1A-1B illustrate views of implant **100**, according to an embodiment. The specifically depicted implant **100** may be used, for example, in anterior lumbar inter-body fusion (ALIF) or posterior lumbar inter-body fusion (PLIF), however, it should be understood that implant **100** may have a variety of shapes suitable for bone fusion applications. In some
25 embodiments, implant **100** may include a web structure with one or more trusses **102** (e.g., planar and space trusses). Implant **100** may be used in various types of implants for humans or animals such as spinal implants, corpectomy devices, knee replacements, hip replacements, long bone reconstruction scaffolding, and cranio-maxifacial implants, foot and ankle, hand and wrist, shoulder and elbow (large joint, small joint, extremity as well as custom trauma implants). Other implant uses are also contemplated.

30 [0023] As used herein a “truss structure” is a structure having one or more elongate struts connected at joints referred to as nodes. Trusses may include variants of a pratt truss, king post truss, queen post truss, town’s lattice truss, planar truss, space truss, and/or a vierendeel truss

(other trusses may also be used). A “truss unit” is a structure having a perimeter defined by three or more elongate struts.”

[0024] As used herein a “planar truss” is a truss structure where all of the struts and nodes lie substantially within a single two-dimensional plane. A planar truss, for example, may include one or more “truss units” where each of the struts is a substantially straight member such that the entirety of the struts and the nodes of the one or more truss units lie in substantially the same plane. A truss unit where each of the struts is a substantially straight strut and the entirety of the struts and the nodes of the truss unit lie in substantially the same plane is referred to as a “planar truss unit.”

[0025] As used herein a “space truss” is a truss having struts and nodes that are not substantially confined in a single two-dimensional plane. A space truss may include two or more planar trusses (e.g., planar truss units) wherein at least one of the two or more planar trusses lies in a plane that is not substantially parallel to a plane of at least one or more of the other two or more planar trusses. A space truss, for example, may include two planar truss units adjacent to one another (e.g., sharing a common strut) wherein each of the planar truss units lie in separate planes that are angled with respect to one another (e.g., not parallel to one another).

[0026] As used herein a “triangular truss” is a structure having one or more triangular units that are formed by three straight struts connected at joints referred to as nodes. For example, a triangular truss may include three straight elongate strut members that are coupled to one another at three nodes to form a triangular shaped truss. As used herein a “planar triangular truss” is a triangular truss structure where all of the struts and nodes lie substantially within a single two-dimensional plane. Each triangular unit may be referred to as a “triangular truss unit.” A triangular truss unit where each of the struts is a substantially straight member such that the entirety of the struts and the nodes of the triangular truss units lie in substantially the same plane is referred to as a “planar triangular truss unit.” As used herein a “triangular space truss” is a space truss including one or more triangular truss units.

[0027] In various embodiments, the trusses 102 of the web structure may include one or more planar truss units (e.g., planar triangular truss units) constructed with straight or curved/arched members (e.g., struts) connected at various nodes. In some embodiments, the trusses 102 may be micro-trusses. A “micro-truss” is a truss having dimensions sufficiently small enough such that a plurality of micro-trusses can be assembled or otherwise coupled to one another to form a web structure having a small enough overall dimension (e.g., height, length and width) such that substantially all of the web structure can be inserted into an implant location (e.g., between two

vertebra). Such a web structure and its micro-trusses can thus be employed to receive and distribute throughout the web structure loading forces of the surrounding tissue (e.g., vertebra, bone, or the like). In one embodiment, the diameters of the struts forming the micro-truss may be between about 0.25 millimeters (mm) and 5mm in diameter (e.g., a diameter of about 0.25mm, 5 0.5 mm, 0.6 mm, 0.7 mm, 0.8 mm, 0.9 mm, 1 mm, 2 mm, 3 mm, 4 mm, or 5 mm). In one embodiment, a micro-truss may have an overall length or width of less than about 1 inch (e.g., a length less than about 0.9 in, 0.8 in, 0.7 in, 0.6 in, 0.5 in, 0.4 in, 0.3 in, 0.2 in, 0.1 in) .

[0028] As depicted, for example, in FIGS. 1A-1B, the web structure may extend throughout implant **100** (including the central portion of implant **100**) to provide support throughout implant 10 **100**. Trusses **102** of implant **100** may thus support implant **100** against tensile, compressive, and shear forces. Web structure may also reinforce implant **100** along multiple planes. The external truss structure may, for example, provide support against tensile and compressive forces acting vertically through the implant, and the internal web structure may provide support against tensile, compressive, and shear forces along the various planes containing the respective trusses. In some 15 embodiments, the web structure includes trusses **102** that form a triangulated web structure with multiple struts (e.g., struts 103a-f) (struts are generally referred to herein as “struts 103”).

[0029] In one embodiment, web structure of the implant **100** may include an internal web structure that is at least partially enclosed by an external truss structure. For example, in one embodiment, web structure **101** may include an internal web structure that includes a space truss 20 having at least a portion of the space truss surrounded by an external truss structure that includes one or more planar trusses formed with a plurality of planar truss units that lie substantially in a single plane. FIG. 1A depicts an embodiment of implant **100** having an internal web structure **104** and an external truss structure **105**. In the illustrated embodiment, internal web structure **104** includes a space truss defined by a plurality of planar truss units **106** coupled at an angle with 25 respect to one another such that each adjacent truss unit is not co-planar with each adjacent truss units. Adjacent truss units may include two truss units that share a strut and the respective two nodes at the ends of the shared strut.

[0030] In one embodiment, external truss structure **105** includes a plurality of planar trusses that are coupled about an exterior, interior or other portion of the implant. For example, in the 30 illustrated embodiment, the external truss structure **105** includes a series of planar trusses **107a,b** that are coupled to one another. Planar truss **107a** is denoted by a dashed line [- - - -], planar truss **107b** is denoted by dotted-dashed line [- · - · -]. Each planar truss is formed from a plurality

of planar truss units (e.g., triangular planar truss units. As depicted, planar truss **107a** includes four triangular planar truss units **108a,b,c,d** having a common vertex **110** and arranged to form a generally rectangular structure that lies in a single common plane. In other words, the four triangular planar truss units are arranged to form a substantially rectangular structure having “X” shaped struts extend from one corner of the rectangular structure to the opposite corner of the rectangular structure. As depicted, the substantially rectangular structure may include a trapezoidal shape. As described in more detail below, the trapezoidal shape may be conducive to providing an implant including lordosis. Lordosis may include an angled orientation of surfaces (e.g., top and bottom) of an implant that provides for differences in thickness in anterior and posterior regions of the implant such that the implant is conducive for supporting the curvature of a vertebral column.

[0031] In one embodiment, the planar trusses that form the external truss are coupled to one another, and are aligned along at least one axis. For example, in FIG. 1A, planar truss section **107a** is coupled to an adjacent planar truss **107b**. Planer truss sections **107a,b** are not parallel in all directions. Planar truss sections **107a,b** are, however, arranged parallel to one another in at least one direction (e.g., the vertical direction between the top and the bottom faces of implant **100**). For example, planar trusses **107a,b** and the additional planar trusses are arranged in series with an angle relative to one another to form a generally circular or polygon shaped enclosure having substantially vertical walls defined by the planar trusses and the planar truss units arranged in the vertical direction.

[0032] In one embodiment, the external truss portion may encompass the sides, top, and/or bottom of the implant. For example, in one embodiment, the external truss portion may include a top region, side regions, and/or a bottom region. FIG. 1A depicts an embodiment of implant **100** wherein external truss portion **105** includes a top **111**, bottom **112** and a side region **113**. As described above, side region **113** includes a series of planar trusses arranged vertically to form a circular/polygon ring-like structure that completely or at least partially surrounds the perimeter of the space truss disposed in the central portion of implant **100**. In the depicted embodiment, top portion **111** of external truss structure **105** includes a plurality of truss units coupled to one another to form a planar truss that cover substantially all of the top region of internal web structure **104**. In the illustrated embodiment, the top portion **111** spans entirely the region between top edges of the side portion **113** of external truss structure **105**. In the illustrated embodiment, top portion **111** is formed from a single planar truss that includes a plurality of truss

units that lie in substantially the same plane. In other words, the planar truss of top portion **111** defines a generally flat surface. Although difficult to view in FIG. 1, the underside of implant **100** may include the bottom portion **112** having a configuration similar to that of the top portion **111**. In other embodiments, external truss structure **105** may include a partial side, top and/or bottom external truss portions. Or may not include one or more of the side, top and bottom external truss portions. For example, as described in more detail below, FIG. 2C depicts an embodiment of implant **100** that includes an internal web structure formed from space trusses, that does not have an external truss structure.

[0033] In some embodiments, implant **100** may be formed from a biocompatible material such as a titanium alloy (e.g., γ Titanium Aluminides), cobalt, chromium, stainless steel, Polyetheretherketone (PEEK), ceramics, etc. Other materials are also contemplated. In some embodiments, implant **100** may be made through a rapid prototyping process (e.g., electron beam melting (EBM) process) as further described below. Other processes are also possible (e.g., injection molding, casting, sintering, selective laser sintering (SLS), Direct Metal Laser Sintering (DMLS), etc). SLS may include laser-sintering of high-performance polymers such as that provided by EOS of North America, Inc., headquartered in Novi, Michigan, U.S.A. High-performance polymers may include various forms of PEEK (e.g., HP3 having a tensile strength of up to about 95 mega Pascal (MPa) and a Young's modulus of up to about 4400 MPa and continuous operating temperature between about 180 °C (356 °F) and 260 °C (500 °F)). Other materials may include PA 12 and PA 11 provided by EOS of North America, Inc.

[0034] As described above, in some embodiments the web structure may be formed from a plurality of triangular planar truss units. In some embodiments, the planar truss units may be coupled to each other to define polyhedrons that define the internal web structure. Examples of polyhedron structures that may be created by joining planar truss units include, but are not limited to, tetrahedrons, pentahedrons, hexahedrons, heptahedrons, pyramids, octahedrons, dodecahedrons, icosahedrons, and spherical fullerenes. In some embodiments, such as those described above, the space truss of the web structure may connect multiple midpoints of tetrahedron building blocks and include a regular pattern of tetrahedron blocks arranged adjacent one another. In some embodiments, the web structure may not include a pattern of geometrical building blocks. For example, FIG. 7 illustrates an irregular pattern of struts that may be used in an implant **905**. Other web structures are also contemplated. Examples of implants composed of a web structure are described in U.S. Published Patent Applications Nos.: 2010/0161061; 2011/0196495; 20110313532; and 2013/0030529.

[0035] FIGS. 3A-3B illustrate a schematic view of a portion of an internal web structure formed with space units formed from triangular planar truss units. Triangular planar truss units may be joined together to form tetrahedrons **300a,b** that may also be used as building blocks (other patterns from the triangles are also contemplated). Other building blocks are also contemplated (e.g., square-shaped building blocks). In some embodiments, a web structure may include a single tetrahedron, such as tetrahedron **300a** or **300b** alone or in combination with one or more other polyhedron. In some embodiments, a web structure may include two or more tetrahedrons **300a,b**. Tetrahedron **300a** may include four triangular faces in which three of the four triangles meet at each vertex. In some embodiments, two tetrahedrons **300a** and **300b** may be placed together at two adjacent faces to form space truss **313** with a hexahedron-shaped frame (including six faces). Hexahedron-shaped space truss **313** may include first vertex **301**, second vertex **309**, third vertex **303**, fourth vertex **305**, and fifth vertex **307**. Common plane **311** may be shared by two tetrahedrons (e.g., common plane **311** may include third vertex **303**, fourth vertex **305**, and fifth vertex **307**) to form a hexahedron with first vertex **301** and second vertex **309** spaced away from common plane **311**. As depicted, the center portion of the triangular shaped building blocks may have a void region in their center that does not include any additional members (e.g., no members other than the struts forming the triangular shaped building blocks) extending there through.

[0036] As seen in FIG. 3B, in some embodiments, multiple hexahedron-shaped space trusses **313** may be arranged in a side-by-side manner. Two space trusses **313** of implant **100** may be connected via their first vertices **301a,b** through strut **103r** and connected via their second vertices **309a,b** through strut **103t**. Similarly, two space trusses **313** may be connected via their first vertices **301c,d** through strut **103p** and connected via their second vertices **309c,d** through strut **103s**. Other connections are also possible. For example, space trusses **313** may connect directly through side vertices (e.g., directly through corresponding vertices (such as vertices **303a,b**) and/or share a common strut (such as strut **103u**)) and/or through a side face (e.g., side faces **111a,b**).

[0037] FIG. 4A illustrates additional struts **103** (e.g., struts **103p** and **103r**) connecting the first vertices (represented respectively by **301a**, **301b**, **301c**, and **301d**) of four hexahedron-shaped space trusses in implant **100**. FIG. 4B illustrates additional struts **103** (e.g., struts **103s** and **103t**) connecting second vertices **309** (represented respectively by **309a**, **309b**, **309c**, and **309d**) of four hexahedron-shaped space trusses in implant **100**. In some embodiments, additional struts **103**

may also be used internally between one or more vertices of the web structures to form additional trusses (e.g., see web structures in FIGS. 1A-2B) (other structures are also possible).

[0038] As shown in FIG. 1A, top surface **115a** and bottom surface **115b** of implant **100** may include triangles, squares, circles or other shapes (e.g., a random or custom design). Top and bottom surfaces **115a,b** may be used to connect the top and bottom vertices of various geometrical building blocks used in the web structure of implant **100**. For example, each vertex may be connected through struts to the neighboring vertices of other geometrical building blocks.

Top surface **115a** may include other strut networks and/or connections. In some embodiments, bottom surface **115b** may mirror the top surface (and/or have other designs). In some embodiments, top surface **115a** and bottom surface **115b** may engage respective surfaces of two adjacent vertebrae when implant **100** is implanted.

[0039] As depicted in FIG. 1B, implant **100** may include lordosis (e.g., an angle in top and/or bottom surfaces **115a,b** approximately in a range of 4 to 15 degrees (such as 4, 5, 6, 7, 8, 9, 10, 11, 12, 13, 14, or 15 degrees)) to further support the adjacent vertebrae when implanted. As described above, lordosis may include an angled orientation of surfaces (e.g., top and bottom) that provide for differences in thickness in the anterior and posterior portions of the implant such that the implant is conducive for supporting the curvature of a vertebral column. In the illustrated embodiment, the thickness of implant **100** is greater at or near the anterior portion **118** and lesser at or near the posterior portion **120** of the implant. In the illustrated embodiment, the side portions of external truss structure are arranged substantially vertically, and the lordosis is formed by the angles of the top portion **111** and bottom portion **112** of external truss structure. For example, in the illustrated embodiment, top portion **111** and bottom portion **112** of external truss structure are not perpendicular to the vertical plane defined by the side portion **113**. Rather, the top portion **111** and bottom portion **112** are arranged with an acute angle relative to the vertical plane of side portion **113** at or near the anterior region **118** of implant **100** and with an obtuse angle relative to the vertical plane of side portion **113** at or near posterior region **120** of implant **100**. As depicted, the vertical struts that form the planar truss of side portion **113** of external truss structure proximate posterior region **120** of implant **100** are shorter than struts that form side portion of external truss structure proximate anterior region **118** of implant **100**. In the illustrated embodiment, in which the vertical trusses are substantially evenly spaced, the struts forming the “X” cross members of the side planar trusses proximate the posterior region **120** of implant **100** are shorter than struts forming the “X” cross members of the side planar trusses proximate the

anterior region **118** of implant **100**. Other embodiments may include variations in the arrangement of the trusses to provide various configurations of the implant. For example, in some embodiments only one or neither of the top and bottom external truss portions may be non-perpendicular to the side portions of the external truss proximate the anterior and posterior portions of the implant. Further, the side, top, and/or bottom portions may include multiple planar trusses angled relative to one another in any orientation. For example, the top or bottom portions may include four planar trusses, each formed of multiple truss units, such that the portion(s) includes a pyramidal like shape.

[0040] In some embodiments, the implant may not include lordosis. For example, FIGS. 2A-2B illustrate two views of an embodiment of an implant **200** without lordosis. In some embodiments, the top surface and bottom surface may not include connecting struts. For example, FIGS. 2C-2D illustrate two views of implant **250** without outer struts (e.g., without external truss portions formed of planar trusses). In the illustrated embodiment, implant **250** includes an internal web structure and does not include an external truss structure. For example, in the illustrated embodiment, the exterior faces of implant **250** are defined by a plurality of truss units that are angled relative to each of its adjacent truss units. The relative alignment of the truss units results in a non-planar exterior that includes a plurality of pointed junctions. The pointed junctions (e.g., pointed junction **201**) may operate to dig into the surrounding bone to hold the implant in place (for example, if the implant is being used in a corpectomy device).

[0041] FIGS. 5A-5C illustrate progressive sectioned views of implant **100** showing the internal structure of implant **100**, according to an embodiment. FIG. 5A illustrates a sectioned view of a lower portion of implant **100**. Bottom surface **115b** is shown with various struts (e.g., struts **103**) extending upward from bottom surface **115b**. FIG. 5B illustrates a sectioned view approximately mid-way through implant **100**. Struts, such as struts **103e,f**, shared by various stacked tetrahedrons in the web structure are shown. Some struts extend through central portion **501a** and/or **501b** of implant **100**. FIG. 5B also shows central portions **501a,b** of implant **100**. In some embodiments, central portion **501a** may include a rectangular region that has a width of approximately 50% of the implant width, a height of approximately 50% of the implant height, and a length of approximately 50% of the implant length and located in the center of implant **100**. In some embodiments, central portion **501b** may encompass a region (e.g., a spherical region, square region, etc.) of approximately a radius of approximately 1/8 to 1/4 of the width of implant **100** around a position located approximately at one half the width, approximately one half the

length, and approximately one-half the height of implant 100 (i.e., the center of implant 100). Other central portions are also contemplated. For example, the central portion may include a square region with a length of one of the sides of the square region approximately $\frac{1}{4}$ to $\frac{1}{2}$ the width of implant 100 around a position approximately at one half the width, approximately one half the length, and approximately one half the height of the implant. An example height 502a, width 502b, and length 502c, is shown in FIG. 5D. In some embodiments, the height may be up to about 75mm or more. In some embodiments, such as those used for long bone reconstruction, the width and/or length could be approximately 7 inches or longer. In some embodiments, the width, length, and/or height may vary along implant 100 (e.g., the height may vary if the implant includes lordosis). The height may be taken at one of the opposing sides, the middle, and/or may be an average of one or more heights along the length of implant 100. The web structure may extend through central portion 501a,b of the implant (e.g., at least one strut of the web structure may pass at least partially through central portion 501a,b). FIG. 5C illustrates another sectioned view showing sectioned views of top tetrahedrons in the web structure. FIG. 5D shows a complete view of implant 100 including top surface 115a with vertices 301a-d.

[0042] FIGS. 6A-6D illustrate alternate embodiments of an implant. In some embodiments, different sections of the hexahedron-shaped geometric design may be used. For example, as seen in FIG. 6A, the bottom half of the hexahedron-shaped geometric design may be used (primarily including the lower tetrahedron structures). If using the bottom half of the design, implant 600 may be expanded proportionately to have similar overall dimensions as the hexahedron-shaped geometric design (e.g., the tetrahedrons may be expanded to approximately twice the height of the tetrahedrons in the hexahedron-shaped geometric design to give implant 600 a height approximately the same as the hexahedron-shaped geometric design). In some embodiments, implant 600 may also be angled (e.g., on top surface 601a and/or bottom surface 601b) to provide implant 600 with lordosis to, in some embodiments, have a better fit between the vertebral endplates. Top surface 601a and/or bottom surface 601b may also include struts to connect nodes of implant 600 (e.g., see the strut network on the top surface in FIG. 6a). Other patterns of struts for top surface 601a and/or bottom surface 601b may also be used. In some embodiments, implant 600 may not include negative angles between struts and may thus be easier to create through a casting or molding process.

[0043] FIGS. 6C-6D illustrate another alternate embodiment of an implant. In some embodiments, approximately the middle 40 to 60 percent of the hexahedron-shaped geometric

design may be used in implant **650**. For example, if an overall height of the hexahedron-shaped geometric design is approximately 37 mm, approximately the bottom 10 mm and approximately the top 10 mm of the design may be removed and approximately the middle 17 mm of the design may be used for the implant. Middle portion of implant **650** may then be expanded proportionately such that the approximate height of the expanded design may be approximately 37 mm (or a different height as needed). Top surface **651a** and bottom surface **651b** may include a network of struts (e.g., see the struts on top surface **651a** of FIG. 6C) (other networks of struts are also contemplated). Other portions of the design for the implant are also contemplated (e.g., the top half of the design shown in FIG. 1A, the bottom half of the design shown in FIG. 1A, etc).

Design portions may be proportionately expanded to meet specified dimensions (e.g., specified height, width, and length). In some embodiments, the amount of struts may be reduced or material in the implant may be redistributed so that some struts may have a larger diameter and some may have a smaller diameter (e.g., the different diameters may reinforce against different directional forces). In some embodiments, a partial-design cage may be used (e.g., with half of the web structure so that the structure includes a tetrahedron. Further, in some embodiments, the implant may include angled surfaces (e.g., an angled top surface **651a** and/or angled bottom surface **651b**) to provide lordosis for implants to be implanted between the vertebral endplates.

[0044] In some embodiments, the web structure of an implant may distribute forces throughout the implant when implanted. For example, the connecting struts of the web structure may extend throughout the core of an implant, and the interconnectivity of struts may disperse the stress of compressive forces throughout implant to reduce the potential of stress risers (the distribution of forces throughout the implant may prevent concentration of stress on one or more portions of the vertebrae that may otherwise result in damage to the vertebrae).

[0045] In some embodiments, the web structure of an implant (e.g., the external and internal struts of the implant) may also provide surface area for bone graft fusion. For example, the web structure extending throughout an implant may add additional surface areas (e.g., on the surface of the struts making up the implant) to fuse to the bone graft material and prevent bone graft material from loosening or migrating from the implant. In some embodiments, the web structure may also support bone in-growth. For example, when implanted, adjacent bone (e.g., adjacent vertebrae if the implant is used as a spinal implant) may grow over at least a portion of struts of the implant. The bone growth and engagement between the bone growth and the implant may further stabilize the implant. In some embodiments, the surfaces of the implant may be formed with a rough surface to assist in bone in-growth adhesion.

[0046] In some embodiments, struts may have a diameter approximately in a range of about 0.025 to 5 millimeters (mm) (e.g., 1.0 mm, 1.5 mm, 3 mm, etc). Other diameters are also contemplated (e.g., greater than 5 mm). In some embodiments, the struts may have a length approximately in a range of 0.5 to 20 mm (e.g., depending on the implant size needed to, for example, fit a gap between vertebral endplates). As another example, struts may have a length approximately in a range of 30-40 mm for a hip implant. In some embodiments, the reduced strut size of the web structure may allow the open cells in implant 100 to facilitate bone growth (e.g., bone may grow through the open cells once implant 100 is implanted in the body). Average subsidence for implants may be approximately 1.5 mm within the first 3 weeks post op (other subsidence is also possible (e.g., approximately between 0.5 to 2.5 mm)). A strut size that approximately matches the subsidence (e.g., a strut size of approximately 1.5 mm in diameter and a subsidence of approximately 1.5 mm) may result in a net 0 impedance (e.g., the bone growth growing around the struts) after the implant has settled in the implanted position. The net 0 impedance throughout the entire surface area of the implant/vertebrae endplate interface may result in a larger fusion column of bone that may result in more stable fusion. Other fusion column sizes are also contemplated. The configuration of the implant may redistribute the metal throughout the implant. In some embodiments, a rim may not be included on the implant (in some embodiments, a rim may be included). The resulting bone growth (e.g., spinal column) may grow through the implant.

[0047] In some embodiments, greater than 50% of the interior volume of implant 100 may be open. In some embodiments, greater than 60%, greater than 70%, and/or greater than 80% of implant 100 may be open (e.g., 95%). In some embodiments, the open volume may be filled with bone growth material. For example, cancellous bone may be packed into an open/internal region of implant.

[0048] In some embodiments, at least a portion of the surfaces of the implant may be coated/treated with a material intend to promote bone growth and/or bone adhesion and/or an antimicrobial agent to prevent infections. For example, in some embodiments, the surface of the struts may be coated with a biologic and/or a bone growth factor. In some embodiments, a biologic may include a coating, such as hydroxyapatite, bone morphogenetic protein (BMP), insulinlike growth factors I and II, transforming growth factor-beta, acidic and basic fibroblast growth factor, platelet-derived growth factor, and/or similar bone growth stimulant that facilitates good biological fixation between the bone growth and a surface of the implant. In some embodiments, a bone growth factor may include a naturally occurring substance capable of

stimulating cellular growth, proliferation and cellular differentiation (e.g., a protein or steroid hormone). In some embodiments, the surface of the implant (e.g., the struts, the external truss structure, etc.) may be coated with collagen.

5 [0049] In some embodiments, a biologic and/or growth factor may be secured to a central region of an implant. For example, in some embodiments, a biologic or growth factor may be provided on at least a portion of a strut that extends through central portion **501a** and/or **501b** of implant **100**, see FIG. 5B. Such an embodiment may enable the delivery of a biologic and or a growth factor to a central portion of an implant. For example, the biologic or growth factor may be physically secured to a strut in a central portion of the implant as opposed to being packed into an open volume that does not include a strut provided therein for the physical attachment of the biologic and/or growth factor.

10 [0050] As the implant settles into the implant site, subsidence may place additional pressure on the bone graft material (which may already be under compressive forces in the implant) and act to push the bone graft material toward the sides of the implant (according to Boussinesq's theory of adjacent material, when a force is applied to a member that is adjacent to other materials (such as sand, dirt, or bone graft material) the force against the member creates a zone of increased pressure (e.g., 60 degrees) in the adjacent material). Struts of the implant may resist bone graft material protrusion from the sides of the web structure and may increase the pressure of the bone graft material. Bone graft material may need to be implanted in a higher-pressure environment to create an environment conducive to strong bone growth (e.g., according to Wolf's law that bone in a healthy person or animal will adapt to the loads it is placed under). The web structure may thus increase the chance of stronger fusion.

15 [0051] Web structures formed from other truss configurations are also contemplated. For example, the trusses may include a series of packing triangles, a two-web truss, a three-web truss, etc. Further, the web structure for an implant may include one or more trusses as described in U.S. Patent No. 6,931,812 titled "Web Structure and Method For Making the Same", which issued August 23, 2005.

20 [0052] FIG. 8 illustrates a flowchart of a method for making an implant. In some embodiments, an implant may be made through rapid prototyping (e.g., electron beam melting, laser sintering, etc). It should be noted that in various embodiments of the methods described below, one or more of the elements described may be performed concurrently, in a different order than shown, or may be omitted entirely. Other additional elements may also be performed as desired. In

some embodiments, a portion or the entire method may be performed automatically by a computer system.

[0053] At 1001, a three dimensional model of an implant is generated and stored in a storage medium accessible to a controller operable to control the implant production process. At 1003, a layer of material (e.g., a powder, liquid, etc.) is applied to a support. In some embodiments, the powder may include γ TiAl (γ Titanium Aluminides) which may be a high strength/low weight material. Other materials may also be used. The powder may be formed using a gas atomization process and may include granules with diameters approximately in a range of 20 to 200 micrometers (μ m) (e.g., approximately 80 μ m). The powder may be delivered to the support through a distributor (e.g., delivered from a storage container). The distributor and/or the support may move during distribution to apply a layer (e.g., of powder) to the support. In some embodiments, the layer may be approximately a uniform thickness (e.g., with an average thickness of 20 to 200 micrometers (μ m)). In some embodiments, the distributor and support may not move (e.g., the material may be sprayed onto the support). At 1005, the controller moves an electron beam relative to the material layer. In some embodiments, the electron beam generator may be moved, and in some embodiments the support may be moved. If the material is γ TiAl, a melting temperature approximately in a range of 1200 to 1800 degrees Celsius (e.g., 1500 degrees Celsius) may be obtained between the electron beam and the material. At 1007, between each electron beam pass, additional material may be applied by the distributor. At 1009, the unmelted material is removed and the implant cooled (e.g., using a cool inert gas). In some embodiments, the edges of the implant may be smoothed to remove rough edges (e.g., using a diamond sander). In some embodiments, the implant may include rough edges to increase friction between the implant and the surrounding bone to increase adhesion of the implant to the bone.

[0054] Other methods of making an implant are also contemplated. For example, an implant may be cast or injection molded. In some embodiments, multiple parts may be cast or injection molded and joined together (e.g., through welding, melting, etc). In some embodiments, individual struts forming the implant may be generated separately (e.g., by casting, injection molding, etc.) and welded together to form the implant. In some embodiments, multiple implants of different sizes may be constructed and delivered in a kit. A medical health professional may choose an implant (e.g., according to a needed size) during the surgery. In some embodiments, multiple implants may be used at the implant site.

[0055] Specialized tools may be used to insert the implants described herein. Examples of tools that may be used are described in U.S. Published Patent Applications Nos.: 2010/0161061; 2011/0196495; 20110313532; and 2013/0030529.

[0056] FIG. 9 illustrates a flowchart of a method for implanting a spinal implant, according to an embodiment. It should be noted that in various embodiments of the methods described below, one or more of the elements described may be performed concurrently, in a different order than shown, or may be omitted entirely. Other additional elements may also be performed as desired. In some embodiments, a portion or the entire method may be performed automatically by a computer system.

5 [0057] At step 1301, an intersomatic space is accessed. For example, an anterior opening may be made in a patient's body for an anterior lumbar inter-body fusion (ALIF) approach or a posterior opening may be made for a posterior lumbar inter-body fusion (PLIF) approach. At 1303, at least a portion of the intersomatic space is excised to form a cavity in the intersomatic space. At 1305, the implant is inserted into the cavity in the intersomatic space. In some embodiments, a handler, or some other device, is used to grip the implant. In some embodiments, a force may be applied to the implant (e.g., through a hammer) to insert the implant into the cavity. At 1307, before and/or after insertion of the implant, the implant and/or space in the cavity may be packed with bone graft material. At 1309, the access point to the intersomatic space may be closed (e.g., using sutures).

15 [0058] In some embodiments, the implant may be customized. For example, three dimensional measurements and/or shape of the implant may be used to construct an implant that distributes the web structure throughout a three-dimensional shape design.

[0059] In some embodiments, a truss/web structure may be disposed on at least a portion of an implant to facilitate coupling of the implant to an adjacent structure. For example, where an implant is implanted adjacent a bony structure, one or more truss structures may be disposed on and/or extend from a surface (e.g., an interface plate) of the implant that is intended to contact, and at least partially adhere to, the bony structure during use. In some embodiments, such as those including an intervertebral implant disposed between the end plates of two adjacent vertebrae during, one or more truss structures may be disposed on a contact surface of the intervertebral implant to facilitate bone growth that enhances coupling of the intervertebral implant to the bony structure. For example, a truss structure may include one or more struts that extend from the contact surface to define an open space for bone growth therethrough, thereby enabling bone through growth to interlock the bone structure and the truss structure with one

another to couple the implant to the bony structure at or near the contact face. Such interlocking bone through growth may inhibit movement between the implant and the bony structure which could otherwise lead to loosening, migration, subsidence, or dislodging of the implant from the intended position. Similar techniques may be employed with various types of implants, including those intended to interface with tissue and/or bone structures. For example, a truss structure may be employed on a contact surface of knee implants, in a corpectomy device, in a hip replacement, in a knee replacement, in a long bone reconstruction scaffold, or in a cranio-maxifacial implant hip implants, jaw implant, an implant for long bone reconstruction, foot and ankle implants, shoulder implants or other joint replacement implants or the like to enhance adherence of the implant to the adjacent bony structure or tissue. Examples of truss structures, and other structures, that may extend from the surface of an implant to facilitate coupling of the implant to an adjacent structure are described in U.S. Published Patent Application No. 2011/0313532, which is incorporated herein by reference.

[0060] While implants described herein are depicted as being composed of substantially straight struts, it should be understood that the struts can be non-linear, including, but not limited to curved, arcuate and arch shaped. Examples of implants having non-linear struts are described in U.S. Patent Application No. 13/668,968.

[0061] It is known that osteoblasts under an appropriate load produce bone morphogenetic protein ("BMP"). BMPs are a group of growth factors also known as cytokines and as metabologens. BMPs act as morphogenetic signals that signal the formation of bone (i.e., an osteogenic response). Thus, by increasing the production of one or more BMPs the osteogenic response to an implant is increased, creating an implant that is integrated into the newly formed bone. A web structure that includes a plurality of joined truss units exhibits a number of deformations in response to loading. FIG.10 below depicts some of the forces that are dispersed along the struts of the truss units that make up the web structure. When used as a bone implant, web structures as described herein may promote the growth of bone in and around the web structure, in part, because of the enhanced BMP production. As shown in FIGS. 11A-C, osteoblasts become attached to the struts of a web structure. Under loading, the micro strain in the struts causes localized deformation which in turn transfers the strain to the adhered osteoblasts which cause the osteoblasts to elute BMP.

[0062] FIG. 11A depicts a schematic diagram of an implant 400 that includes a space truss 410. Bone structures, not shown, are typically disposed against a top face 420 and a bottom face 425 of implant 400. During use, the stress from the contacting bone structures (denoted by arrows

430) can cause implant 400 to lengthen (denoted by arrow 435) as the implant is compressed. This lengthening can have a beneficial effect on the formation of BMP by osteoblasts that adhere to the implant. Adjacent bone adds compression forces to the slanted struts. This compression may lead to bone remodeling. The combination of the two forces (compression and lengthening) creates bone growth/remodeling which leads to accelerated healing and achieving a mature fusion in a shorter amount of time as compared to predicate devices.

[0063] FIG. 11B depicts a close-up view of strut 415 of implant 400. Strut 415, in FIG. 11B is shown in a non-elongated state. This may represent the state of strut 415 when the implant is not under load from the contacting bone structures. Osteoblasts are depicted as adhered to strut 415.

The osteoblasts are shown in their normal, non-elongated form. FIG. 11C depicts strut 415 in an elongated state, which exists when the bone structures are applying a compressive force to implant 400. As shown, the osteoblasts are believed to be stretched due to the elongation of strut 415. Elongation of the osteoblasts lead to an influx of calcium which is then converted into BMP and eluted back out. Studies have shown that the creating a microstrain in the osteoblasts of between 500 $\mu\epsilon$ and 2000 $\mu\epsilon$ or between about 1000 $\mu\epsilon$ and about 1500 $\mu\epsilon$ enhances the production of BMP. Alternatively, the production of BMP may be attained when the length of the attached osteoblasts is changed between about 0.05% and about 0.2% or between about 0.1% and about 0.15%. Configuring a truss system to intentionally create lengthening/microstrain in osteoblasts may reduce the time needed for the bone structure to be repaired.

[0064] In an embodiment, an implant for interfacing with a bone structure includes a web structure comprising a plurality of struts joined at nodes. The web structure is configured to interface with human bone tissue. In one embodiment, a diameter and/or length of the struts are predetermined such that when the web structure is in contact with the bone structure, BMP production from osteoblasts adhering to the implant surface is achieved. In one embodiment, the diameter and/or length of the struts is predetermined so that at least a portion of the struts create a microstrain in the adhered osteoblasts of between about 1 and 5000 microstrain, 500 $\mu\epsilon$ and about 2000 $\mu\epsilon$ or between about 1000 $\mu\epsilon$ and about 1500 $\mu\epsilon$. In an embodiment, the diameter and/or length of the struts is predetermined so that at least a portion of the struts create a change in length of the adhered osteoblasts of between about 0.05% and about 0.2% or between about 0.1% and about 0.15%.

[0065] An implant may be prepared having struts of a length of between about 1 to 100 mm. The diameter of the struts may be set such that the strut undergoes a change of length of between about 0.05% and 0.2% when the web structure is in contact with the bone structure. In some

embodiments, the diameter of the struts is predetermined such that the strut undergoes a change of length of between about 0.000125% and 0.0005% or between about 0.00025% and 0.000375%.

5 [0066] Any implant described herein may be modified so that at least a portion of the struts the form the web structure produce the appropriate microstrain/lengthening of adhered osteoblasts. In some embodiments, most if not all of the struts that form the web structure of an implant may be 'programmed' (or designed) to stimulate BMP production. In other embodiments, some struts may be programmed/designed for BMP production, while other struts have different physical properties than the programmed struts.

10 [0067] An implant may be optimized to distribute stresses encountered by the implant. Most implants used for bone repair are placed in locations that apply non-uniform stress to the implant. The non-uniform stress creates different forces across the implant. If an implant is designed to withstand a certain homogenous force, the implant may fail when subjected to non-uniform stress. In a non-uniform stress situation, some of the stress on the implant may be sufficient to
15 deform the implant. It is desirable to have an implant that is customized to the expected non-uniform stress that will be encountered in the bone structure being repaired.

[0068] In an embodiment, an implant for interfacing with a bone structure, includes a web structure having a plurality of struts joined at nodes. The web structure is configured to interface with human bone tissue, and has a first bone contact surface and a second bone contact surface.
20 A first portion of struts that are part of the space truss have a physical property that is different from a second portion of the struts that are a part of the space truss. In this manner an implant may be created which optimizes the stresses encountered by the implant to help inhibit failure of the implant.

[0069] In one embodiment, the first portion of struts that are part of the space truss have a
25 deformation strength that is different from a second portion of the struts that are a part of the space truss. The space truss may include one or more central struts extending from the first bone contact surface to the second bone contact surface. The central struts may have a deformation strength that is greater than or less than the surrounding struts, depending on the location of the implant. The space truss may include one or more longitudinal struts extending parallel to the
30 first bone contact surface and/or the second bone contact surface, wherein the longitudinal struts have a deformation strength that is greater than or less than the surrounding struts.

[0070] The physical properties of the struts of the implant may be varied such that the diameter of the first portion of the struts is greater than a diameter of the second portion of the struts. In

some embodiments, the first portion of struts are formed from a material that is different from the material used to form the second portion of struts. In some embodiments, the first portion of struts have a diameter that is different from the diameter of the second portion of struts. In some embodiments, the first portion of struts have a density that is different from the density of the second portion of struts. In some embodiments, the first portion of struts have a porosity that is different from the porosity of the second portion of struts. Any combination of these different physical properties may be present in an implant to help optimize the distribution of stress throughout the implant.

[0071] In accordance with the above descriptions, in various embodiments, an implant may include a web structure. The web structure for the implant may include a micro truss design. In some embodiments, the micro truss design may include a web structure with multiple struts. Other web structures are also contemplated. The web structure may extend throughout the implant (including a central portion of the implant). The web structure may thus reinforce the implant along multiple planes (including internal implant load bearing) and provide increased area for bone graft fusion. The web structure may be used in implants such as spinal implants, corpectomy devices, hip replacements, knee replacements, long bone reconstruction scaffolding, and cranio-maxillofacial implants foot and ankle, hand and wrist, shoulder and elbow (large joint, small joint, extremities). Other implant uses are also contemplated. In some embodiments, the web structure for the implant may include one or more geometric objects (e.g., polyhedrons). In some embodiments, the web structure may not include a pattern of geometrical building blocks (e.g., an irregular pattern of struts may be used in the implant). In some embodiments, the web structure may include a triangulated web structure including two or more tetrahedrons. A tetrahedron may include four triangular faces in which three of the four triangles meet at each vertex. The web structure may further include two tetrahedrons placed together at two adjacent faces to form a web structure with a hexahedron-shaped frame (including six faces). In some embodiments, multiple hexahedron-shaped web structures may be arranged in a side-by-side manner. The web structures may connect directly through side vertices (e.g., two or more hexahedron-shaped web structures may share a vertex). In some embodiments, the web structure may be angled to provide lordosis to the implant.

[0072] Further modifications and alternative embodiments of various aspects of the invention may be apparent to those skilled in the art in view of this description. For example, although in certain embodiments, struts have been described and depicts as substantially straight elongated members, struts may also include elongated members curved/arched along at least a portion of

their length. Accordingly, this description is to be construed as illustrative only and is for the purpose of teaching those skilled in the art the general manner of carrying out the invention. It is to be understood that the forms of the invention shown and described herein are to be taken as embodiments. Elements and materials may be substituted for those illustrated and described
5 herein, parts and processes may be reversed, and certain features of the invention may be utilized independently, all as would be apparent to one skilled in the art after having the benefit of this description of the invention. Changes may be made in the elements described herein without departing from the spirit and scope of the invention as described in the following claims. Furthermore, it is noted that the word “may” is used throughout this application in a permissive
10 sense (i.e., having the potential to, being able to), not a mandatory sense (i.e., must). The term “include”, and derivations thereof, mean “including, but not limited to”. As used in this specification and the claims, the singular forms “a”, “an” and “the” include plural referents unless the content clearly indicates otherwise. Thus, for example, reference to “a strut” includes a combination of two or more struts. The term “coupled” means “directly or indirectly connected”.

15

WHAT IS CLAIMED IS:

1. An implant for interfacing with a bone structure, comprising:
 - 5 a web structure comprising a plurality of struts joined at nodes, wherein the web structure is configured to interface with human bone tissue;

wherein at least one of a diameter of the struts, a length of the struts, and a density of the web structure are predetermined such that when the web structure is in contact
10 with the bone, an applied load to the web structure creates a microstrain in the struts thereby producing a mechanical transduction of the microstrain to adjacent cellular material, bony structure, or tissue.
2. The implant of claim 1, wherein at least one of the diameter of the struts, the length of the
15 struts, and the density of the web structure is predetermined so that the struts under the applied load, produce a microstrain in the adjacent cellular material, bony structure, or tissue, wherein the produced microstrain is within a range that stimulates an osteogenic response.
3. The implant of claim 1, wherein at least one of the diameter of the struts, the length of the
20 struts, and the density of the web structure is predetermined so that a microstrain produced in the adjacent cellular bony material, bony structure, or tissue is between 1 $\mu\epsilon$ and 5000 $\mu\epsilon$; or 500 $\mu\epsilon$ and 2000 $\mu\epsilon$; or 1000 $\mu\epsilon$ and 1500 $\mu\epsilon$.
4. The implant of claim 1, wherein at least one of the diameter of the struts, the length of the
25 struts, and the density of the web structure is predetermined so that at least a portion of the struts create a change in length of the adjacent cellular material, bony structure, or tissue of between 0.05% and 0.2%; or 0.1% and 0.15%.
5. The implant of claim 1, wherein the struts have a length of between about 1mm to about
30 20mm, and wherein a diameter of the strut is predetermined such that the struts create a change in length of the adjacent cellular material, bony structure, or tissue of between 0.05% and 0.2% when the web structure is in contact with the bone structure.

6. The implant of claim 1, wherein the web structure comprises a space truss comprising two or more planar truss units.
7. The implant of claim 6, wherein one or more of the planar truss units comprise one or more planar triangular truss units having three substantially straight struts and three nodes in a triangular configuration.
8. The implant of claim 6, wherein one or more of the planar truss units are coupled to one another such that one or more planar truss units lie in a plane that is not substantially parallel to a plane of a planar truss unit that shares at least one strut with the one or more planar truss units.
9. The implant of claim 6, wherein one or more of the planar truss units comprises a first planar triangular truss unit coupled to a second planar triangular truss unit, wherein the first and second planar triangular truss units are coupled in an opposing manner with a single node defining the apex of each planar triangular truss unit.
10. The implant of claim 1, wherein the at least some of the struts define triangular trusses having at least one node shared by two different triangular planar truss units having different corresponding angles.
11. The implant of claim 1, wherein the web structure comprises a first bone contact surface and a second bone contact surface; and wherein a first portion of the struts that comprise a space truss have a physical property that is different from a second portion of the struts that comprise the space truss.
12. The implant of claim 11, wherein the first portion of struts that comprises the space truss have a deformation strength that is different from the second portion of the struts that comprises the space truss.
13. The implant of claim 11, wherein the space truss comprises one or more central struts extending from the first bone contact surface to the second bone contact surface, wherein the central struts have a deformation strength that is greater than surrounding struts.

14. The implant of claim 11, wherein the space truss comprises one or more longitudinal struts extending parallel to the first bone contact surface and/or the second bone contact surface, wherein the longitudinal struts have a deformation strength that is greater than surrounding struts.
- 5 15. The implant of claim 11, wherein the space truss comprises one or more central struts extending from the first bone contact surface to the second bone contact surface, wherein the central struts have a deformation strength that is less than surrounding struts.
16. The implant of claim 11, wherein the space truss comprises one or more longitudinal struts
10 extending parallel to the first bone contact surface and/or the second bone contact surface, wherein the longitudinal struts have a deformation strength that is less than surrounding struts.
17. The implant of claim 11, wherein the diameter of the first portion of the struts is greater than a diameter of the second portion of the struts.
- 15 18. The implant of claim 11, wherein the first portion of struts are formed from a material that is different from the material used to form the second portion of struts.
19. The implant of claim 11, wherein the first portion of struts have a diameter that is different
20 from the diameter of the second portion of struts.
20. The implant of claim 11, wherein the first portion of struts have a density that is different from the density of the second portion of struts.
- 25 21. The implant of claim 1, wherein the adjacent cellular material, bony structure, or tissue includes one or more of osteoblasts, bone matrix, and lamellar tissue.
22. The implant of claim 1, wherein the web structure is an internal web structure at least partially enclosed by an external frame, the external frame at least partially defining an exterior
30 surface of the implant, and wherein at least one strut of the internal web structure passes into a central portion of the implant.
23. Use of the implant according to any one of claims 1-22 for repairing a bone structure.

1 / 17




FIG. 1A




FIG. 1B

2 / 17




FIG. 2A

3 / 17




FIG. 2B

4 / 17




FIG. 2C

5 / 17




FIG. 2D

6 / 17





FIG. 3A

7 / 17






FIG. 4A




FIG. 4B

9 / 17




FIG. 5A




FIG. 5B

10 / 17




FIG. 5C




FIG. 5D

11 / 17




FIG. 6A




FIG. 6B

12 / 17




FIG. 6C




FIG. 6D

13 / 17




FIG. 7

14 / 17




FIG. 8

15 / 17




FIG. 9

16 / 17




FIG. 10




FIG. 11A

17 / 17




FIG. 11B




FIG. 11C

