



(22) **Date de dépôt/Filing Date:** 1992/04/03
(41) **Mise à la disp. pub./Open to Public Insp.:** 1992/10/06
(45) **Date de délivrance/Issue Date:** 2003/03/18
(30) **Priorités/Priorities:** 1991/04/05 (73 049/91) JP;
1991/04/05 (73 048/91) JP

(51) **Cl.Int.⁵/Int.Cl.⁵** D21C 5/02, C09D 9/00

(72) **Inventeurs/Inventors:**
HAMAGUCHI, KOJI, JP;
ISHIBASHI, YOICHI, JP;
URUSHIBATA, HIDEAKI, JP

(73) **Propriétaire/Owner:**
KAO CORPORATION, JP

(74) **Agent:** SMART & BIGGAR

(54) **Titre : COMPOSITION ET METHODE DE DESENCRAGE**
(54) **Title: DEINKING COMPOSITION AND DEINKING METHOD**

(57) **Abrégé/Abstract:**

A deinking composition which comprises a specified nonionic surfactant having a specified solubility parameter as an essential component. A deinking method which comprises adding the above-described deinking composition during in the pulping step (the preceding step) and in any of the subsequent steps (the succeeding step). By use of the deinking composition and the deinking method of the present invention, an excellent deinking performance, including an elevated whiteness, a decrease in the number of unliberated large ink spots and an improved defoaming property of the flotation reject, can be achieved in deinking waste papers, in particular, waste OA papers and blends containing thereof.

Abstract

A deinking composition which comprises a specified nonionic surfactant having a specified solubility parameter as an essential component.

A deinking method which comprises adding the above-described deinking composition during in the pulping step (the preceding step) and in any of the subsequent steps (the succeeding step).

By use of the deinking composition and the deinking method of the present invention, an excellent deinking performance, including an elevated whiteness, a decrease in the number of unliberated large ink spots and an improved defoaming property of the flotation reject, can be achieved in deinking waste papers, in particular, waste OA papers and blends containing thereof.

DEINKING COMPOSITION AND DEINKING METHOD

Background of the Invention

Field of the Invention

The present invention relates to a deinking composition and a deinking method for use in the reclamation of waste paper including newspapers, magazines and waste office automation (OA) papers. More particularly, the present invention relates to a deinking composition and a deinking method whereby a deinked pulp can be obtained that has a high whiteness and a high b value with little contamination from unliberated ink spots, particularly unliberated large ink spots having a particle size of 30 μm or more. The deinked pulp can be obtained from, for example, newspapers, magazines or waste OA papers by flotation, washing or a combination procedure thereof.

Description of the Related Art

It has been a practice to reclaim waste papers including newspapers, magazines and waste OA papers. Recently the effective utilization of waste papers has become more and more important in conjunction with the problems of the global environment such as the conservation of forest resources and refuse disposal. Further, it has been attempted to utilize deinked pulp as a pulp of a higher rank, for example, to reclaim

old newspapers for use in making a paper of intermediate grade.

On the other hand, recent improvements in printing techniques, printing systems and printing ink compositions have made it difficult to deink waste papers. In order to facilitate deinking, therefore, attempts have been made to improve deinking devices.

Meanwhile, conventional deinking compositions are as follows. In order to remove inks and other impurities from waste paper, there have been used alkaline agents such as caustic soda, sodium silicate, sodium carbonate and sodium phosphate, bleaching agents such as hydrogen peroxide, hydrosulfites and hypochlorites, and sequestering agents such as EDTA and DTPA together with one or more deinking agents. The deinking agents include anionic surfactants such as alkylbenzenesulfonates, higher alcohol sulfates, α -olefinsulfonates and dialkyl sulfosuccinates, nonionic surfactants such as ethylene oxide adducts of higher alcohols, alkylphenols and fatty acids and alkanolamides. Although these deinking compositions show excellent foaming properties in the flotation step, their ability to collect ink are limited. In the washing step, on the other hand, they are poor in detergency and, furthermore, their good foaming

properties cause trouble in the effluent disposal step. As a result, only a deinked pulp of a low grade can be obtained by these methods. In order to deink waste OA papers including plain paper copy (PPC) and computer print output (CPO), in particular, it is required to either apply a large shear force energy or use a large amount of alkalis, since printing inks (toners) used therein comprise styrene/acrylic binders or polyester binders, which differ from the conventional newspaper ink, result in large ink spots (i.e., a particle size of 30 μm or more) remaining unliberated after the completion of a common deinking treatment. However, the use of a large amount of alkalis suffers from some disadvantages, including an increase in the sticky matters, the load in the effluent disposal step and the brittleness of the pulp. Thus no method for effectively deinking waste OA papers and blends thereof has been established so far.

Description of the Invention

Summary of the Invention

The present inventors have conducted extensive studies in order to develop a deinking composition and a deinking method showing a good deinking performance without any foaming troubles whereby a deinked pulp of

a high whiteness can be obtained from various waste papers and, in particular, large ink spots having a particle size of 30 μm or more can be removed from waste OA papers and blends containing thereof while requiring neither a large shearing energy nor a large amount of alkalis in the flotation, washing or combination procedure thereof. As a result, they have surprisingly found out that the aforesaid problems can be solved by using a deinking composition containing a specified nonionic surfactant deinking agent as an essential component and a method wherein said deinking composition is added in the pulping step and in one or more the subsequent steps, thus completing the present invention.

Accordingly, the present invention provides a deinking composition comprising a deinking agent selected from the group consisting of;

(I) a reaction product mixture having a solubility parameter of 8.9 to 10.2, which is obtained from (a) a polyfunctional alcohol having up to 12 carbon atoms and/or (b) a polyfunctional fatty acid having up to 11 carbon atoms and (c) an alkylene oxide, said reaction product mixture including therein 1 to 4 moles of alkylene oxide units per 1 functional group of (a) or (b), including 22 moles or less of alkylene oxide

units in total of one molecule of the product,

(II) a partial ester mixture having a solubility parameter of 8.9 to 9.8, which is formed by reacting a reaction product mixture which obtained from (a) a polyfunctional alcohol having up to 12 carbon atoms and/or (b) a polyfunctional fatty acid having up to 11 carbon atoms and (c) an alkylene oxide, said reaction product mixture including therein 1 to 4 moles of alkylene oxide units per 1 functional group of (a) or (b), including 22 moles or less of alkylene oxide units in total of one molecule of the product, with (d) a fatty acid having 2 to 8 carbon atoms, and

(III) an alkylene oxide adduct compound mixture having a solubility parameter of 9.0 to 11.8, the alkylene oxide adduct compound mixture comprising or essentially consisting compounds represented by the following general formula (1):



wherein R represents an alkyl, alkenyl, acyl or aryl group having 1 to 8 carbon atoms;

AO represents an alkylene oxide having 2 to 4 carbon atoms; and

m is a value such that the entire alkylene oxide adduct compound mixture has the average mole number of AO units ranging from 1 to 6.

65702-396

The present invention further provides a method for deinking waste paper, comprising;

(I) pulping the waste paper,

(II) subjecting the pulp to at least one
5 treatment step selected from the group consisting of kneading, dispersing, chemical mixing and refining, and

(III) subjecting the treated pulp to a flotation or washing step, wherein the above-described deinking composition is added in portions in steps (I) and (II)
10 and/or (III).

Further scope of the applicability of the present invention will become apparent from the detailed description given hereinafter. However, it should be understood that the detailed description and specific examples, while
15 indicating preferred embodiments of the invention, are given by way of illustration only, since various changes and modifications within the spirit and scope of the invention will become apparent to those skilled in the art from this detailed description.

20 The expression "a deinking composition" found throughout the specification would perhaps be better referred to as "a deinking agent", since often it is composed of a single component, namely, the reaction product mixture (I), the partial ester mixture (II) or the alkylene
25 oxide adduct compound mixture (III), although it may also be composed of the single component with one or more other substances that are used for deinking.

65702-396

Detailed Description of the Invention

The reaction product mixture (I) to be used as a deinking agent in the present invention may be obtained from (a) a polyfunctional alcohol having up to 12 carbon atoms and/or (b) a polyfunctional fatty acid

having up to 11 carbon atoms and (c) an alkylene oxide, that is, by adding (c) an alkylene oxide to (a) a polyfunctional alcohol having up to 12 carbon atoms and/or (b) a polyfunctional fatty acid having up to 11 carbon atoms by any known method. The obtained reaction product mixture includes 1 to 4 moles, on average, of alkylene oxide units per 1 functional group of (a) or (b), and 22 moles or less, on average, of alkylene oxide units in total of one molecule of the product. The present invention includes a deinking agent comprising a compound obtained by
10 adding from 1 to 4 mol per functional group of an alkylene oxide to a polyfunctional alcohol having up to 12 carbon atoms or a polyfunctional fatty acid having up to 11 carbon atoms, provided that the total addition mole number does not exceed 22 mol, and having a solubility parameter ranging from 8.9 to 10.2 as an essential component.

The term "polyfunctional" as used herein means "having two or more functional groups carrying active hydrogen".

Specific examples of (a) the polyfunctional alcohol having up to 12, preferably up to 10, carbon atoms usable as
20 the starting material include those having 2 to 10 hydroxyl group such as ethylene glycol, trimethylene glycol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,7-heptanediol, 1,8-octanediol, 1,9-

nonanediol, 1,10-decanediol, 1,2-octanediol, 1,2-decanediol, butanoyl- α -glycol, 1,3-butanediol, trans-2-butene-1,4-diol, 2-butyne-1,4-diol, 2,4-pentanediol, 2,5-hexanediol, 2-methyl-1,3-pentanediol, 2-methyl-2,4-pentanediol, 2,3-dimethyl-2,3-butanediol, 2,4-heptanediol, 2,2-diethyl-1,3-propanediol, 2-ethyl-1,3-hexanediol, 2-ethyl-2-butyl-1,3-propanediol, diethylene glycol, triethylene glycol, tetraethylene glycol, dipropylene glycol, 1,2-cyclononanediol, 1,2-cyclodecanediol, glycerol, erythritol, pentaerythritol, arabitol, sorbitol, sorbitan, mannitol, mannitan, 1,2,3-butanetriol, 2-methylpropane-1,2,3-triol, 2,3,4-pentanetriol, 2-methylbutane-1,2,3-triol, 2,3,4-hexanetriol, 2-ethylbutane-1,2,3-triol, 2,3,4-trimethylpentane-2,3,4-triol, D-glycero-D-galaheptose, D-glycero-D-glucoheptose, D-glycero-D-mannoheptose, D-glycero-L-mannoheptose, D-glycero-D-galaheptitol, D-altroheptulose, D-altro-3-heptulose, D-mannoheptulose, D-erythro-D-galaocitol, D-glycero-D-manno-octulose, D-erythro-L-gulononulose, cellobiose, maltose and lactose.

Among these compounds, polyfunctional alcohols having up to 6 carbon atoms are particularly preferable. It is further preferable to use saturated polyfunctional alcohols having 1 to 3 carbon atoms.

65702-396

Examples of (b) the polyfunctional fatty acid having up to 11 carbon atoms usable as the starting material include those having two carboxyl groups, those having one hydroxyl group and one carboxyl group, those having one hydroxyl group and two carboxyl groups, those having two hydroxyl groups and one carboxyl group, such as oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, ethylmalonic acid, 2-hydroxyvaleric acid, 2-hydroxycaproic acid, 2-hydroxycaprylic acid, 2-hydroxypelargonic acid, 2-hydroxyundecanoic acid, 3-hydroxycaprylic acid, 3-hydroxypelargonic acid, 3-hydroxycapric acid, 6-hydroxycaproic acid, 7-hydroxyenanthic acid, 8-hydroxycaprylic acid, 9-hydroxypelargonic acid, 10-hydroxycapric acid, 2-methylhydroxyenanthic acid, 2-hydroxy-3-pentenoic acid, 5-hydroxy-2,4-pentadienoic acid, 2,3-dihydroxycaproic acid, 2,3-dihydroxyenanthic acid, 2,3-dihydroxycaprylic acid, 2,3-dihydroxypelargonic acid, 2,3-dihydroxycapric acid, 1-nonene-1,9-dicarboxylic acid and 2-nonene-1,9-dicarboxylic acid.

20 Among these compounds, polyfunctional fatty acids having up to 10 carbon atoms are preferred and polyfunctional fatty acids having up to 6 carbon atoms are particularly preferred. It is further preferable to use saturated polyfunctional fatty acids having 1 to 3 carbon atoms.

As (c) the alkylene oxide to be added to (a) the polyfunctional alcohol and (b) the polyfunctional

fatty acid, ethylene oxide (hereinafter referred to simply as EO), propylene oxide (hereinafter referred to simply as PO) and butylene oxide (hereinafter referred to simply as BO) may be used either alone or as a mixture thereof. It is particularly preferable to use EO, PO or a mixture thereof. Although (c) the alkylene oxide may be added by either random addition or block addition, the random addition is preferable when taking foaming troubles in the papermaking and effluent disposal steps into consideration.

For producing the above-described reaction product mixture (I), the addition of (c) the alkylene oxide may be effected by any common method without restriction. Namely, it may be carried out under the conditions commonly employed for adding an alkylene oxide to a compound having active hydrogen. Specifically, it may be performed by adding a catalytic amount of an alkali to (a) the polyfunctional alcohol and/or (b) the polyfunctional fatty acid according to the present invention and then reacting (a) the polyfunctional alcohol and/or (b) the polyfunctional fatty acid with (c) the alkylene oxide at a temperature of approximately 100 to 200°C under a pressure of 1 to 3 kg/cm² (gauge) for several hours.

The partial ester mixture (II) to be used as a

deinking agent in the present invention is a partial ester of the aforesaid reaction product mixture (I) with (d) a fatty acid having 2 to 8 carbon atoms.

Namely, the present invention includes a deinking agent comprising a compound which is a partial ester of a compound obtained by adding from 1 to 4 mol per functional group of an alkylene oxide to a polyfunctional alcohol or a polyfunctional fatty acid having up to 12 carbon atoms, provided that the total addition mole number does not exceed 22 mol, with a fatty acid having 2 to 8 carbon atoms and has a solubility parameter ranging from 8.9 to 9.8 as an essential component.

Examples of (d) the fatty acid having 2 to 8 carbon atoms to be used for producing the aforesaid partial ester include acetic acid, propionic acid, propynoic acid, butyric acid, isobutyric acid, tetrolic acid, valeric acid, α -methylbutyric acid, isovaleric acid, trimethylpropanoic acid, 2-pentynoic acid, allylacetic acid, 2,4-pentadienoic acid, caproic acid, 2-methylpentanoic acid, 3-methylpentanoic acid, 4-isocaproic acid, 2-hexynoic acid, sorbic acid, 2-hexenoic acid, 3-hexenoic acid, 4-hexynoic acid, 5-hexenoic acid, heptanoic acid, 2-heptenoic acid, 3-heptenoic acid, 5-heptenoic acid, 6-heptenoic acid,

2-heptynoic acid, 6-heptynoic acid, caprylic acid, 2-ethylhexanoic acid, 2-octenoic acid, 3-octenoic acid, 2-octynoic acid, 7-octynoic acid, 2-methyl-2-heptenoic acid, benzoic acid, methylbenzoic acid, cyclohexylacetic acid, 2-fluorovaleric acid, 2-fluorocaproic acid, 2-fluoroenanthic acid, 2-chlorocaprylic acid, 2-bromovaleric acid, 2-bromocaproic acid, 2-bromoenanthic acid, 2-bromocaprylic acid, 5-chlorovaleric acid, oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, ethylmalonic acid, 2-hydroxyvaleric acid, 2-hydroxycaproic acid, 2-hydroxycaprylic acid, 2-hydroxypelargonic acid, 2-hydroxyundecanoic acid, 3-hydroxycaprylic acid, 6-hydroxycaproic acid, 7-hydroxyenanthic acid, 8-hydroxycaprylic acid, 2-methyl-hydroxyenanthic acid, 2-hydroxy-3-pentenoic acid, 4-hydroxy-3-pentenoic acid, 4-hydroxy-4-pentenoic acid, 5-hydroxy-2,4-pentadienoic acid, 2,3-dihydroxycaproic acid, 2,3-dihydroxyenanthic acid, 2,3-dihydroxycaprylic acid and anhydrides of these acids. It is particularly preferable to use fatty acids having 2 to 4 carbon atoms, still preferably saturated ones.

Since the numerical values specified with respect to the carbon atom number and physicochemical

65702-396

constants of the reaction product mixture (I) and the partial ester mixture (II) are critical ones, any compound similar thereto cannot exert the remarkable effects of the present invention. As will be apparent from the Examples to be given hereinafter, when (a) the polyfunctional alcohol or (b) polyfunctional fatty acid has more than 12 carbon atoms, for example, foaming troubles occur in the draining step, due to the high foaming properties, and thus the productivity of the deinked pulp is seriously deteriorated.

Further, it is important that the addition of the alkylene oxide per functional group fall within the range of from 1 to 4, provided that the total addition of alkylene oxide does not exceed 22 mole per one molecule in (I) and (II). When the addition of the alkylene oxide, per functional group, is smaller than 1, a number of large ink spots, that is spots having a particle size of 30 μm or more, will remain unliberated. When it exceeds 4, on the contrary, the high foaming properties often cause foaming troubles in the effluent disposal step. When the total addition of the alkylene oxide exceed 22 mole, the above-mentioned foaming troubles occur frequently.

When (d) the fatty acid used in the esterification to produce the partial ester mixture

(II) has less than 2 carbon atoms, the number of the remaining unliberated large ink spots is elevated. When (d) the fatty acid has more than 8 carbon atoms, on the contrary, the high foaming properties often cause foaming troubles in the effluent disposal step.

Furthermore, the degree of esterification of the partial ester mixture (II), should range from 15 to 75% by mole. When it is smaller than 15% by mole, a large amount of the large ink spots which have a particle size of 30 μm or more, will remain unliberated. This restricts the utilization of the deinked pulp (for example, decreases the amount of its incorporation under the top side of board). When the degree of esterification exceeds 75% by mole, on the contrary, the ink particles become excessively fine, which makes it difficult to obtain a deinked pulp of a high whiteness.

The present inventors have tried to further improve the deinking performance of waste OA papers and blends containing waste OA papers. As a result, they have surprisingly found that a mixture having a solubility parameter in a specified range can efficiently lower the number of unliberated large ink spots having a particle size of 30 μm or more.

It is important that the solubility parameter of

65702-396

the reaction product mixture (I) range from 8.9 to 10.2, preferably from 9.1 to 10.0 and still preferably from 9.4 to 9.8, and the solubility parameter of the partial ester mixture (II) ranges from 8.9 to 9.8, preferably from 9.1 to 9.7 and still preferably from 9.2 to 9.5. When the solubility parameter is smaller than the lower limit as specified above, the obtained deinked pulp is contaminated with many unliberated large ink spots. When it exceeds the upper limit, on the contrary, ink particles become
10 excessively small and thus cannot be sufficiently removed in the flotation step. As a result, the obtained deinked pulp has low whiteness. Additionally, problems including poor defoaming properties of the flotation reject and foaming troubles in the effluent disposal step, are likely to occur.

15 The term "solubility parameter" as used herein means a physicochemical constant that is defined based on the regular solution theory established by Hildebrand.

Whether two substances are mutually soluble or not is determined by the free energy of mixing, ΔG , as defined
20 by the following formula:

$$\Delta G = \Delta H - T\Delta S$$

wherein ΔH is the change in enthalpy, ΔS is the change in entropy, and T is the absolute temperature.

When the ΔG value is negative, these substances

65702-396

are soluble. This ΔG is expressed as a function of the solubility parameter. From the viewpoint of the regular solution theory, the molar free energy of mixing, ΔG , is given by the following formula:

$$\Delta G = RT(X_1 \ln X_1 + X_2 \ln X_2) + V_1 X_1 \phi_2^2 (\delta_1 - \delta_2)^2 + V_2 X_2 \phi_1^2 (\delta_1 - \delta_2)^2$$

wherein X_1 and X_2 represent the molar fractions of components 1 and 2, respectively; V_1 and V_2 represent the molar volume of components 1 and 2, respectively; ϕ_1 and ϕ_2 represent the volume fraction of components 1 and 2, respectively; δ_1 and δ_2 represent the solubility parameter of components 1 and 2, respectively; and R is the gas constant (8.314 J/mol.K).

The alkylene oxide adduct compound mixture (III) to be used as a deinking agent in the present invention is a mixture comprising or essentially consisting compounds represented by the following general formula (1):



wherein R represents an alkyl, alkenyl, acyl or aryl group having 1 to 8 carbon atoms;

AO represents an alkylene oxide having 2 to 4 carbon atoms; and

m is a value such that the entire alkylene oxide adduct compound mixture has the average mole

number of AO units ranging from 1 to 6.

Namely, the present invention includes a deinking agent comprising a compound represented by the following general formula (1):



wherein R represents an alkyl, alkenyl, acyl or aryl group having 1 to 8 carbon atoms;

AO represents an alkylene oxide having 2 to 4 carbon atoms; and

m ranges from 1 to 6 on average.

The alkylene oxide adduct compound mixture (III) can be obtained by adding an alkylene oxide(s) to an alcohol(s) and/or a fatty acid(s) having 1 to 8 carbon atoms by any known method.

Examples of the alcohol having 1 to 8 carbon atoms usable as the starting material for producing the alkylene oxide adduct compound mixture (III) include methyl alcohol, ethyl alcohol, n-propyl alcohol, isopropyl alcohol, butyl alcohol, trimethylpropyl alcohol, 1-hexanol, 2-hexanol, 2-hexen-1-ol, 5-hexen-1-ol, 1-heptanol, 2-heptanol, 2-hepten-1-ol, 6-hepten-1-ol, 1-octanol, 2-octanol, 2-octen-1-ol, 2-ethylhexanol, benzyl alcohol, phenol and cyclohexyl alcohol.

Examples of the fatty acid usable as the starting

material for producing the alkylene oxide adduct compound mixture (III) include acetic acid, propinoic acid, propyenoic acid, butyric acid, isobutyric acid, tetrolic acid, n-valeric acid, α -methylbutyric acid, isovaleric acid, trimethylpropanoic acid, 2-pentynoic acid, allylacetic acid, 2,4-pentadienoic acid, caproic acid, 2-methylpentanoic acid, 3-methylpentanoic acid, 4-isocaproic acid, 2-hexynoic acid, sorbic acid, 2-hexenoic acid, 3-hexenoic acid, 4-hexenoic acid, 5-hexenoic acid, heptanoic acid, 2-heptenoic acid, 3-heptenoic acid, 5-heptenoic acid, 6-heptenoic acid, 2-heptynoic acid, 6-heptynoic acid, caprylic acid, 2-ethylhexanoic acid, 2-octenoic acid, 3-octenoic acid, 2-octynoic acid, 7-octynoic acid, 2-methyl-2-heptenoic acid, benzoic acid, methylbenzoic acid, cyclohexylacetic acid, 2-fluorovaleric acid, 2-fluorocaproic acid, 2-fluoroenanthic acid, 2-fluorocaprylic acid, 2-chlorocaproic acid, 2-chloroenanthic acid, 2-chlorocaprylic acid, 2-bromovaleric acid, 2-bromocaproic acid, 2-bromoenanthic acid, 2-bromocaprylic acid and 5-chlorovaleric acid.

R of general formula (1) represents preferably a group having 1 to 6 carbon atoms, more preferably an alkyl or an acyl group having 1 to 6 carbon atoms.

As the alkylene oxide to be added to the alcohol

or fatty acid usable as the starting material for producing the alkylene oxide adduct compound mixture (III), EO, PO and BO may be used either alone or as a mixture thereof. It is particularly preferable to use EO, PO or a mixture thereof. Although the alkylene oxide may be added by either random addition or block addition, the random addition is preferable by taking foaming troubles in the papermaking and effluent disposal steps into consideration.

For producing the alkylene oxide adduct compound mixture (III), the addition of the alkylene oxide may be effected by any common method without restriction. Namely, it may be carried out under the conditions commonly employed for adding an alkylene oxide to a compound having active hydrogen. Specifically, it may be performed by adding a catalytic amount of an alkali to the alcohol or fatty acid and then reacting the alcohol or fatty acid with the alkylene oxide at a temperature of approximately 100 to 200°C under a pressure of 1 to 3 kg/cm² (gauge) for several hours.

The present inventors have examined the relationship in the deinking performance between deinking various waste papers and deinking agents having various chemical structures and solubility parameters. As a result, they have surprisingly found

that a mixture having a solubility parameter falling within a specified range and comprising compounds which have a specified chemical structure is effective in reducing the number of unliberated large ink spots (i.e., a particle size of 30 μm or more).

Since the numerical values specified with respect to general formula (1) and the solubility parameter of the alkylene oxide adduct compound mixture (III) are critical ones, a merely similar compound cannot achieve the remarkable effects of the present invention. Therefore the specification of the carbon atom in general formula (1) and the physicochemical constants of the alkylene oxide adduct compound mixture (III) are very important. As will be apparent from the Examples to be given hereinafter, when R in general formula (1) represents a group having less than 1 carbon atom (i.e., neither an alkyl group nor an alkenyl group), the compound shows a poor ability to collect ink and thus deinked pulp of a high whiteness can not be obtained. When said carbon atom number exceeds 8, on the contrary, the high foaming properties cause foaming troubles in the effluent disposal step, thus seriously deteriorating the productivity of the deinked pulp. The addition mole number (m) of the alkylene oxide ranges from 1 to 6,

preferably from 1 to 4, on average. When it is smaller than 1, many large ink spots having a particle size of 30 μm or more remain unliberated. When it exceeds 6, on the contrary, the high foaming properties frequently cause foaming troubles in the effluent disposal step.

It is important that the solubility parameter of the alkylene oxide adduct compound mixture (III) ranges from 9.0 to 11.8, preferably from 9.5 to 11.3 and more preferably from 9.8 to 10.8. When the solubility parameter is smaller than 9.0, the obtained deinked pulp is contaminated with many unliberated large ink spots. When it exceeds 11.8, on the contrary, ink particles become excessively small and thus cannot be sufficiently removed in the flotation step. As a result, the obtained deinked pulp has only a low whiteness. Additionally, some problems, including a poor defoaming property of the flotation reject and foaming troubles in the effluent disposal step, might occur.

As an essential component of a deinking composition of the present invention, the use of a deinking agent, the numerical values of which fall within the ranges specified in the present invention, makes it possible to obtain a deinked pulp of

excellent qualities, i.e., having a high whiteness and scarcely contaminated with unliberated large ink spots (i.e., a particle size of 30 μm or more) without incurring any trouble in the operation.

The compounds disclosed in the prior arts (Japanese Patent Laid-Open No. 81107/1977, No. 51891/1980, No. 51892/1980, No. 79795/1981 and No. 109696/1983) are not as effective as the present deinking agents in reducing the number of unliberated large ink spots. Although the carbon atom number and alkylene oxide addition mole number are specified in the above-mentioned references, most of the starting materials used in the Examples therein have 12 or more carbon atoms and no particular example shows a compound having 11 or less carbon atoms. Further, although Japanese Patent Laid-Open No. 137588/1984 and 40690/1989 disclose alkylene oxide adducts of special polyfunctional alcohols, all of these compounds either have an aryl group or are themselves aromatic compounds. Clearly these compounds differ from the compounds used in the present invention. Furthermore, while Japanese Patent Laid-Open No. 266292/1989 points out that an ether surfactant is effective as a deinking agent for waste OA papers, this compound, wherein the AO moiety of the general formula (1) of

the present invention is ethylene oxide and the terminal group of the general formula (1) is replaced by an alkyl or alkenyl group having 1 to 18 carbon atoms, is clearly different in chemical structure from the compound used in the present invention.

In addition, the conventional deinking agents are employed for deinking newspapers and magazines, while the present invention is characterized by being particularly effective in deinking waste OA papers and blends thereof. Printing inks for newspapers contain phenol resins as the ink binder. On the other hand, inks used in waste OA papers contain styrene/acrylic resin or polyester resin as the binder. Thus these inks differ from each other in physicochemical properties. It is therefore required to design a deinking agent and a deinking composition for waste OA papers from a different point of view than that used for waste newspaper deinking compositions. The present invention has been completed based on the fact that a mixture having a solubility parameter within a strictly limited range is effective in deinking, as the result of extensive examination on the solubility parameter which has not been studied hitherto. Thus the present invention clearly differs from prior art.

The deinking agent according to the present

invention can also exert the excellent deinking performance when used together with other known deinking agent(s). Namely, the deinking composition of the present invention preferably contains the deinking agent according to the present invention and other known deinking agent(s), or, the deinking composition of the present invention preferably uses together with other deinking composition comprising other known deinking agent(s). The other known deinking agent includes, for example, higher alcohol sulfates, alkylbenzenesulfonates, ethylene oxide adducts of higher alcohols and alkylphenols, fatty acids and salts thereof, alkylene oxide adducts of fatty acids and alkylene oxide adducts of fats and oils. The deinking agent according to the present invention and the known one may be used at a weight ratio of from 90/10 to 10/90, preferably from 20/80 to 60/40.

In the conventional deinking method, a deinking composition is added in either one or both of the mixing step, which consists of the pulping, kneading, dispersing, chemical mixing and refining steps, and the flotation step.

In contrast, the deinking method of the present invention comprises adding the deinking composition

according to the present invention during the pulping step (the preceding step) and in one or more of the subsequent steps (the succeeding step) of the mixing step.

Namely, the present invention provides a method for deinking waste paper, comprising;

- (I) pulping the waste paper,
- (II) subjecting the pulp to at least one treatment step selected from the group consisting of kneading, dispersing, chemical mixing and refining, and
- (III) subjecting the treated pulp to a flotation or washing step,

wherein the deinking composition according to the present invention is added in portions in steps (I) and, (II) and/or (III).

The present invention further provides a method for deinking waste paper, comprising;

- (I) pulping the waste paper,
- (II) subjecting the pulp to at least one treatment step selected from the group consisting of kneading, dispersing, chemical mixing and refining, and
- (III) subjecting the treated pulp to a flotation or washing step,

wherein the deinking composition according to the present invention is added during steps (I) and (II).

The deinking composition may be preferably added at a weight ratio of the preceding step amount to the succeeding step amount of from 10/90 to 90/10. When the deinking composition comprises one or both of the reaction product mixture (I) and the partial ester mixture (II) as the essential component, the weight ratio of addition may be still more preferably from 40/60 to 60/40 (the preceding step to the succeeding step). When the deinking composition comprises the alkylene oxide adduct compound mixture (III) as the essential component, the weight ratio of addition may be still more preferably from 30/70 to 70/30 (the preceding step to the succeeding step).

Alternately, the deinking composition of the present invention may be added all at once or in portions during the succeeding step.

It is desirable to use the deinking composition of the present invention at such a ratio as to achieve an economic advantage without deteriorating the operating characteristics. It is recommended to add the deinking composition so as to achieve a deinking agent concentration of from 0.03 to 1.0% by weight based on the waste paper.

The deinking composition and the deinking method of the present invention are suitable for deinking

waste office automation (OA) papers or blends containing waste OA papers. When the deinking composition comprises the alkylene oxide adduct compound mixture (III) as the essential component, the deinking composition and the deinking method of the present invention are still suitable for deinking waste OA papers or blends containing waste OA papers.

Examples

To further illustrate the present invention in detail, and not by way of limitation, the following Examples will be given.

Production Example 1

260.1 g of ethylene glycol and 4.7 g of 100% KOH were fed into a 1.5-ℓ autoclave and heated to 150°C under stirring at approximately 600 rpm. Next, 730.2 g of propylene oxide was added to the obtained mixture and reacted with ethylene glycol at a temperature of from 120 to 130°C under a pressure of from 1 to 3 kg/cm² (gauge). After the completion of the addition reaction, the reaction mixture was cooled to 80°C and the pH value was adjusted to about 6 with acetic acid. The yield of the obtained reaction product (used as a deinking agent in invention example No. 1 given in Table 1) was 99%.

Production Example 2

292.7 g of sorbitol and 2.7 g of 100% KOH were fed into a 1.5-ℓ autoclave and heated to 150°C under stirring at approximately 600 rpm. Next, 424.7 g of ethylene oxide was added to the obtained mixture and reacted with sorbitol at a temperature of from 150 to 160°C under a pressure of from 1 to 3 kg/cm² (gauge). Then, 280.0 g of propylene oxide was added to the obtained mixture and was reacted at a temperature of from 120 to 130°C under a pressure of from 1 to 3 kg/cm². After cooling to 80°C, the pH value of the reaction mixture was adjusted to about 6 with acetic acid. The yield of the obtained reaction product (used as a deinking agent in invention example No. 23 given in Table 2) was 99%.

Comparative Production Example 1

286.3 g of 2-hydroxycaproic acid and 3.4 g of 100% KOH were fed into a 1.5-ℓ autoclave and heated to 130°C under stirring at approximately 600 rpm. Next, 491.0 g of an ethylene oxide/propylene oxide/butylene oxide mixture (molar ratio: 20/40/20) was added to the obtained mixture and reacted with 2-hydroxycaproic acid at a temperature of from 130 to 140°C under a pressure of from 1 to 3 kg/cm² (gauge). After the completion of the addition reaction, the reaction

mixture was cooled to 80°C and the pH value thereof was adjusted to about 6 with acetic acid. The yield of the obtained reaction product (used as a deinking agent in comparative example No. 30 given in Table 2) was 99%.

Production Example 3

229.1 g of glycerol and 4.2 g of 100% KOH were fed into a 1.5-ℓ autoclave and heated to 130°C under stirring at approximately 600 rpm. Next, 762.2 g of an ethylene oxide/propylene oxide mixture (molar ratio: 50/50) was added to the obtained mixture and reacted with glycerol at a temperature of from 130 to 140°C under a pressure of from 1 to 3 kg/cm² (gauge). After the completion of the addition reaction, the reaction mixture was cooled to 80°C and the pH value thereof was adjusted to about 6 with acetic acid. The yield of the obtained reaction product (used as a deinking agent in invention example No. 71 given in Table 4) was 99%.

Production Example 4

804.2 g of the product obtained in the Production Example 1, 194.5 g of 2-ethylhexanoic acid and 1.2 g of 100% NaOH, employed as a catalyst, were fed into a 1.5-ℓ autoclave and allowed to react at 230°C under a nitrogen atmosphere while stirring at approximately

500 rpm. The yield of the obtained reaction product (used as a deinking agent in invention example No. 73 given in Table 4) was 99%.

Example 1

In this Example, a deinking agent was added at once in the pulping step.

Waste PPC papers (100%), printed with 2.4 g/m² of a printing ink comprising a styrene/acrylic binder, were cut into pieces (2 x 5 cm). A given amount thereof was fed into a bench disintegrator. Then, water, 0.5 wt.% (based on waste PPC papers) of caustic soda, 1.0 wt.% (based on waste PPC papers) of sodium silicate No. 3, 1.0 wt.% (based on waste PPC papers) of 30 wt.% hydrogen peroxide and 0.2 wt.% (based on waste PPC papers) of each deinking agent listed in Table 1 were added thereto. After disintegrating at a pulp concentration of 5 wt.% at 45°C for 20 minutes, the mixture was aged at 45°C for 60 minutes. Next, the mixture was dehydrated on a high-speed dehydrator until the pulp concentration reached 22 wt.% and then kneaded on a twin-screw laboratory kneader at 200 rpm. After diluting with water so as to give a pulp concentration of 4 wt.%, it was disintegrated again on the bench disintegrator for 30 seconds. The obtained slurry was concentrated on an 80-mesh wire gauze so as

to give a pulp concentration of 10 wt.% and then diluted with water so as to give a pulp concentration of 1 wt.%. Subsequently, it was treated on a TAPPI standard sheet machine to thereby give a pulp sheet.

The whiteness of the obtained pulp sheet was measured with a color difference meter and the unliberated ink spots having a particle size of 30 μm or more were counted with an image analyzer (magnification: x100). The defoaming property of the flotation reject was determined for use as an indicator of foaming troubles in the effluent disposal step. A larger numerical value of the defoaming property means a higher possibility of causing foaming troubles in the effluent disposal step. The defoaming property of the flotation reject as used herein is defined as follows:

$$\text{defoaming property of flotation reject} = \frac{\text{foam volume (ml) after 30 sec}}{\text{foam volume (ml) immediately after}} \times 100 (\%)$$

Table 1 shows the results of the evaluation of the deinking performances of the deinking agents.

Table 1

		Deinking agent				Whiteness (%)	No. of unliberated ink spots ($\geq 30\ \mu\text{m}$)	Defoaming property (%)
		polyfunctional alcohol	AO*1	added AO mole no.*2	solubility parameter			
Invention Example	No.							
	1	ethylene glycol	PO	1.5 (3)	9.7	89.4	9	20
	2	ethylene glycol	PO	1 (2)	10.2	88.3	15	25
	3	ethylene glycol	PO	4 (8)	8.9	88.4	15	26
	4	1,4-butanediol	EO	2 (4)	9.9	88.1	16	28
	5	1,4-butanediol	EO/PO(1/1)	2 (4)	9.6	88.4	15	25
	6	1,4-butanediol	EO/BO(1/1)	2 (4)	9.4	88.4	14	22
	7	1,4-butanediol	PO/BO(1/1)	2 (4)	9.2	88.2	16	25
	8	1,6-hexanediol	EO/PO(2/1)	3 (6)	9.3	88.2	16	23
	9	glycerol	EO/PO(6/6)	4 (12)	9.0	88.5	14	30
10	glycerol	EO/PO(2/1)	1 (3)	10.1	88.6	13	22	

Note

*1 AO: alkylene oxide (the same will apply hereinafter), added at random in all cases.

*2 added AO mole no.: It means AO mole no. per functional group on average and each figure given in parentheses means total AO mole no. of one molecule of the product on average (the same will apply hereinafter).

Table 1 (contd.)

		Deinking agent					Whiteness (%)	No. of unliberated ink spots ($\geq 30 \mu\text{m}$)	Defoaming property (%)
		polyfunctional alcohol	AO*1	added AO mole no. *2	solubility parameter				
Invention Example	No.								
	11	1,2,3-butanetriol	EO	1 (3)	10.2	88.2	16	20	
	12	1,2-3-butanetriol	PO	1 (3)	9.8	88.5	14	18	
Comparative Example	13	1,2,3-butanetriol	PO	3 (9)	8.9	88.1	20	28	
	14	ethylene glycol	PO	5 (10)	8.8	86.3	30	65	
	15	ethylene glycol	PO	13 (26)	8.5	86.3	32	78	
	16	glycerol	EO/PO(2/1)	5 (15)	8.9	86.2	31	68	
	17	glycerol	EO/PO(2/1)	10 (30)	8.7	86.2	31	92	
	18	1,20-eicosanediol	PO	4 (8)	9.1	85.0	42	48	
	19	1,20-eicosanediol	PO	5 (4)	9.0	85.2	40	55	
	20	2-methylpropane-1,2,3-triol	BO	5 (15)	8.3	85.3	38	50	
	21	$\text{CH}_3-(\text{CH}_2)_3-\text{O}-(\text{EO})_2-(\text{CH}_2)_3-\text{CH}_3$				9.6	86.2	30	76
	22	$\text{CH}_3-(\text{CH}_2)_5-\text{O}-(\text{EO})_2-\text{CH}_3$				9.6	86.5	26	74

Note

*1 AO: alkylene oxide (the same will apply hereinafter), added at random in all cases.

*2 added AO mole no.: It means AO mole no. per functional group on average and each figure given in parentheses means total AO mole no. of one molecule of the product on average (the same will apply hereinafter).

Example 2

In this Example, a deinking agent was added in portions in the pulping step and in the kneading step.

Waste PPC papers (100%), printed with 2.4 g/m² of a printing ink comprising a styrene/acrylic binder, were cut into pieces (2 x 5 cm). A given amount thereof was fed into a bench disintegrator. Then, water, 0.3 wt.% (based on waste PPC papers) of caustic soda and 0.1 wt.% (based on waste PPC papers) of each deinking agent listed in Table 2 were added thereto. After disintegrating at a pulp concentration of 5 wt.% at 45°C for 20 minutes, the mixture was aged at 45°C for 60 minutes. Next, the mixture was dehydrated on a high-speed dehydrator until the pulp concentration reached 22 wt.%, and then 0.2 wt.% (based on waste PPC papers) of caustic soda, 1.0 wt.% (based on waste PPC papers) of sodium silicate No. 3, 1.0 wt.% (based on waste PPC papers) of 30 wt.% hydrogen peroxide and 0.1 wt.% (based on waste PPC papers) of each deinking agent listed in the Table 2 were added thereto. Then the mixture was kneaded on a twin-screw laboratory kneader at 200 rpm. After diluting with water so as to give a pulp concentration of 4 wt.%, it was disintegrated again on the bench disintegrator for 30 seconds. The obtained slurry was diluted with water

so as to give a pulp concentration of 1 wt.% and subjected to flotation at 30°C for 10 minutes. Subsequently, it was concentrated on an 80-mesh wire gauge until the pulp concentration reached 10 wt.% and diluted with water so as to give a concentration of 1 wt.%. Then it was treated on a TAPPI standard sheet machine to thereby give a pulp sheet.

The whiteness of the obtained pulp sheet was measured with a color difference meter and the unliberated ink spots having a particle size of 30 μm or more were counted with an image analyzer (magnification: x100). The defoaming property of the flotation reject was determined for use as an indicator of foaming troubles in the effluent disposal step, similar to the Example 1. Table 2 shows the results of the evaluation of the deinking performances of the deinking agents.

Table 2

No.	Deinking agent					Whiteness (%)	No. of unliberated ink spots ($\geq 30 \mu\text{m}$)	Defoaming property (%)
	polyfunctional alcohol or polyfunctional fatty acid	AO	added AO mole no. 2	solubility parameter				
Invention Example	23	sorbitol	EO/PO(6/3)	1.5 (9)	9.6	90.1	8	18
	24	sorbitol	EO/PO(8/4)	2 (12)	9.4	90.2	7	20
	25	pentaerythritol	PO	2 (8)	9.5	90.1	8	22
	26	2-decene-1,10-dicarboxylic acid	EO	2 (4)	9.4	90.1	8	21
	27	adipic acid	BO	1 (2)	9.3	89.9	10	15
	28	1,2-cyclononanediol	EO	2 (4)	9.5	90.1	9	17
	29	2,3-dihydroxy-enanthic acid	EO	2 (6)	9.4	90.0	9	20
Comparative Example	30	2-hydroxycapric acid	EO/PO/BO (2/4/2)	4 (8)	8.8	86.8	29	65
	31	sorbitol	EO/PO (20/10)	5 (30)	8.8	86.4	29	96
	32	sorbitol	PO	4 (24)	8.7	86.5	29	90

Example 3

In this Example, a deinking agent was added in portions in the pulping step and in the dispersing step.

Waste PPC papers (100%), printed with 3.0 g/m² of a printing ink comprising a polyester binder, were cut into pieces (2 x 5 cm). A given amount thereof was fed into a bench disintegrator. Then, water, 0.3 wt.% (based on waste PPC papers) of caustic soda and 0.1 wt.% (based on waste PPC papers) of each deinking agent listed in Table 3 were added thereto. After disintegrating at a pulp concentration of 15 wt.% at 45°C for 20 minutes, the mixture was aged at 55°C for 120 minutes. Next, the mixture was dehydrated on a high-speed dehydrator until the pulp concentration reached 22 wt.%, and then 0.7 wt.% (based on waste PPC papers) of caustic soda, 1.0 wt.% (based on waste PPC papers) of sodium silicate No. 3, 1.5 wt.% (based on waste PPC papers) of 30 wt.% hydrogen peroxide and 0.1 wt.% (based on waste PPC papers) of each deinking agent listed in the Table 3 were added thereto. Then, the mixture was dispersed on a laboratory disperser at 300 rpm. After diluting with water so as to give a pulp concentration of 4 wt.%, it was disintegrated again on the bench disintegrator for 30 seconds. The

obtained slurry was diluted with water so as to give a pulp concentration of 1 wt.% and subjected to flotation at 30°C for 10 minutes. Subsequently, it was concentrated on an 80-mesh wire gauze until the pulp concentration reached 10 wt.% and diluted with water so as to give a concentration of 1 wt.%. Then, it was treated on a TAPPI standard sheet machine to thereby give a pulp sheet.

The whiteness of the obtained pulp sheet was measured with a color difference meter and the unliberated ink spots having a particle size of 30 μm or more were counted with an image analyzer (magnification: x100). The defoaming property of the flotation reject was determined for use as an indicator of foaming troubles in the effluent disposal step, similar to the Example 1. Table 4 shows the results of the evaluation of the deinking performances of the deinking agents.

Table 3

No.		Deinking agent						solubility parameter
		polyfunctional alcohol or polyfunctional fatty acid	AO	added AO mole no.	ester compound			
					fatty acid	degree of esterification (mol %)		
Invention Example	44	ethylene glycol	PO	1 (2)	propionic acid	25	9.7	
	45	ethylene glycol	PO	1 (2)	acetic acid	60	9.2	
	46	1,2,3-butanetriol	EO	1 (3)	butyric acid	20	9.8	
	47	1,2,3-butanetriol	EO	1 (3)	α -methylbutyric acid	50	9.2	
	48	1,2,3-butanetriol	EO	1 (3)	2-octenoic acid	70	9.2	
	49	mannitan	PO/EO(4/8)	3 (12)	isovaleric acid	15	8.9	
	50	ethylene glycol	EO/PO(2/2)	2 (4)	2-ethylhexanoic acid	20	9.4	
	51	ethylene glycol	PO	1 (2)	propionic acid	12	9.9	
	52	ethylene glycol	PO	1 (2)	propionic acid	80	9.0	
	53	1,2,3-butanetriol	EO	1 (3)	butyric acid	10	10.0	
Comparative Example	54	1,2,3-butanetriol	EO	1 (3)	butyric acid	78	9.0	
	55	ethylene glycol	PO	1 (2)	lauric acid	25	9.6	
	56	ethylene glycol	PO	13 (26)	lauric acid	25	8.5	
	57	sorbitol	EO	2 (12)	lauric acid	25	9.1	
	58	sorbitol	EO	2 (12)	acetic acid	80	8.6	

Table 3 (contd.)

Deinking agent							
No.	polyfunctional alcohol or polyfunctional fatty acid	AO	added AO mole no.	ester compound		solubility parameter	
				fatty acid	degree of esterification (mol %)		
Comparative Example	59	cellobiose	P0	2 (16)	2-ethylhexanoic acid	40	8.6
	60	stachyose	E0	1 (14)	lauric acid	25	8.8
	61	stachyose	E0	1 (14)	acetic acid	25	8.6
	62	stachyose	E0	1 (14)	acetic acid	75	8.2
	63	stachyose	E0	1 (14)	acetic acid	15	8.7
	64	ethylene glycol	EO/P0(2/2)	5 (10)	2-ethylhexanoic acid	20	8.9
	65	ethylene glycol	EO/P0(2/2)	13 (26)	2-ethylhexanoic acid	20	8.6
	66	ethylmalonic acid	P0	1 (2)	2-bromocaprylic acid	15	8.8
	67	oleyl alcohol (EO) ₁₂ (PO) ₅					
	68	ammonium oleate					
69	sodium dodecylbenzenesulfonate						

Table 4

		Whiteness (%)	No. of unliberated ink spots ($\geq 30 \mu\text{m}$)	Defoaming property (%)
No.				
Invention Example	44	88.4	15	20
	45	89.8	8	15
	46	88.2	16	18
	47	89.9	10	22
	48	89.9	9	18
	49	88.1	18	25
	50	89.9	8	22
	51	87.8	21	29
	52	86.9	24	35
	53	86.3	24	41
	54	86.4	20	40
Comparative Example	55	86.9	39	52
	56	86.2	31	95
	57	86.3	30	86
	58	86.3	32	84

Table 4 (contd.)

	No.	Whiteness (%)	No. of unliberated ink spots ($\geq 30 \mu\text{m}$)	Defoaming property (%)
Comparative Example	59	86.2	32	72
	60	86.3	30	88
	61	86.1	32	85
	62	86.0	36	82
	63	86.2	32	90
	64	86.8	29	85
	65	86.8	29	92
	66	86.9	29	50
	67	86.4	32	53
	68	85.4	44	40
	69	85.5	46	95

Example 4

In this Example, a deinking agent was added in portions in the pulping step and in the kneading step.

Waste PPC papers (100%), printed with 3.2 g/m^2 of a printing ink comprising a styrene/acrylic binder, were cut into pieces (2 x 5 cm). A given amount thereof was fed into a bench disintegrator. Then water, 0.3 wt.% (based on waste PPC papers) of caustic soda and a given amount of each deinking agent listed in Table 5 were added thereto. After disintegrating at a pulp concentration of 5 wt.% at 45°C for 20

minutes, the mixture was aged at 45°C for 60 minutes. Next, the mixture was dehydrated on a high-speed dehydrator until the pulp concentration reached 22 wt.% and then 0.2 wt.% (based on waste PPC papers) of caustic soda, 1.0 wt.% (based on waste PPC papers) of sodium silicate No. 3, 1.0 wt.% (based on waste PPC papers) of 30 wt.% hydrogen peroxide and a given amount of each deinking agent listed in Table 5 were added thereto. Then the mixture was kneaded on a twin-screw laboratory kneader at 200 rpm. After diluting with water so as to give a pulp concentration of 4 wt.%, it was disintegrated again on the bench disintegrator for 30 seconds. The obtained slurry was diluted with water so as to give a pulp concentration of 1 wt.% and subjected to flotation at 30°C for 10 minutes. Subsequently, it was concentrated on an 80-mesh wire gauze until the pulp concentration reached 10 wt.% and diluted with water so as to give a concentration of 1 wt.%. Then it was treated on a TAPPI standard sheet machine to thereby give a pulp sheet.

The whiteness of the obtained pulp sheet was measured with a color difference meter and the unliberated ink spots having a particle size of 30 μm or more were counted with an image analyzer

(magnification: x100). The defoaming property of the flotation reject was determined for use as an indicator of foaming troubles in effluent disposal step, similar to the Example 1. Table 6 shows the results of the evaluation of the deinking performances of the deinking agents.

Table 5

		Deinking agent							Added deinking agent (based on waste PPC papers; % by weight)			
		polyfunctional alcohol or polyfunctional fatty acid	A0	added A0 mole no.	ester compound		solubility parameter	pulping step (I)			kneading step (II)	weight ratio I/II
					fatty acid	degree of esterifi- cation (mol %)						
Invention Example	No.											
	70	2-hydroxyvaleric acid	P0	1 (2)	-	-	9.6	0.02	0.18	10/90		
	71	glycerol	E0/P0(3/3)	2 (6)	-	-	9.4	0.2	0.2	50/50		
	72	ethylmalonic acid	P0	1 (2)	-	-	9.4	0.18	0.02	90/10		
Comparative Example	73	ethylene glycol	P0	1.5 (3)	2-ethylhexanoic acid	20	9.4	0.15	0.10	60/40		
	74	sorbitol	E0/P0(6/3)	1.5 (9)	propionic acid	60	8.9	0.03	0.17	15/85		
	75	glycerol	E0/P0(10/5)	5 (15)	-	-	8.9	0.2	0.2	50/50		
	76	sorbitol	E0/P0(20/10)	5 (30)	acetic acid	25	8.7	0.03	0.17	15/85		

Table 6

		Whiteness (%)	No. of unliberated ink spots ($\geq 30 \mu\text{m}$)	Defoaming property (%)
	No.			
Invention Example	70	90.2	6	20
	71	91.2	4	12
	72	90.3	6	15
	73	90.5	5	20
	74	90.2	6	28
Comparative Example	75	86.0	28	75
	76	85.8	32	80

As described above, the deinking agents according to the present invention, i.e., the deinking compositions of the present invention in the above-described cases, each of which is a reaction product mixture which is obtained by adding 1 to 4 mol per functional group of an alkylene oxide to a polyfunctional alcohol or a polyfunctional fatty acid having 1 to 10 carbon atoms, provided that the total addition mole number of the alkylene oxide does not exceed 22 mol, and has a solubility parameter of from 8.9 to 10.2, exert excellent effects, including elevating the whiteness, reducing the number of unliberated large ink spots and improving the defoaming property of the flotation reject, when they

are used in deinking waste OA papers or blends containing waste OA papers.

Further, the deinking agents according to the present invention, i.e., the deinking compositions of the present invention in the above-described cases, each of which is a partial ester mixtures which is obtained by partially esterifying the aforesaid reaction product mixture with a fatty acid having 2 to 8 carbon atoms and has a solubility parameter of from 8.9 to 9.8, can exert similar effects to those described above, when they are used in deinking waste OA papers or blends containing waste OA papers.

Furthermore, a deinked pulp having more excellent qualities can be obtained by adding the deinking agent according to the present invention in portions, i.e., in the pulping step and in any of the subsequent steps.

Production Example 5

774.8 g of 2-ethylhexyl alcohol and 1.6 g of 100% KOH were fed into a 1.5-ℓ autoclave and heated to 150°C under stirring at approximately 600 rpm. Then, 251.9 g of ethylene oxide was added to the obtained mixture and reacted with 2-ethylhexyl alcohol at a temperature of from 150 to 160°C under a pressure of from 1 to 3 kg/cm² (gauge). After the completion of

the addition reaction, the reaction mixture was cooled to 80°C and the pH value thereof was adjusted to 6 with acetic acid. The yield of the obtained reaction product (used as a deinking agent in invention example No. 77 given in Table 7) was 99%.

Production Example 6

262.9 g of propionic acid and 6.0 g of 100% KOH were fed into a 1.5-ℓ autoclave and heated to 150°C under stirring at approximately 600 rpm. Then, 724.8 g of an ethylene oxide/propylene oxide mixture (molar ratio: 50/50) was added to the obtained mixture and reacted with propionic acid at a temperature of from 150 to 160°C under a pressure of from 1 to 3 kg/cm² (gauge). After the completion of the addition reaction, the reaction mixture was cooled to 80°C and the pH value thereof was adjusted to 6 with acetic acid. The yield of the obtained reaction product (used as a deinking agent in invention example No. 92 given in Table 8) was 99%.

Production Example 7

194.2 g of propyl alcohol and 3.6 g of 100% KOH were fed into a 1.5-ℓ autoclave and heated to 150°C under stirring at approximately 600 rpm. Then, 426.9 g of ethylene oxide was added to the obtained mixture and reacted with propyl alcohol at a temperature of

from 150 to 160°C under a pressure of from 1 to 3 kg/cm² (gauge). After the completion of the reaction, 375.3 g of propylene oxide was added to the obtained mixture and reacted at a temperature of from 120 to 130°C under a pressure of from 1 to 3 kg/cm². Then, the reaction mixture was cooled to 80°C, the pH value thereof was adjusted to 6 with acetic acid. The yield of the obtained reaction product (used as a deinking agent in invention example No. 106 given in Table 9) was 99%.

Production Example 8

239.5 g of butyric acid and 4.6 g of 100% NaOH were fed into a 1.5-ℓ autoclave and heated to 150°C under stirring at approximately 600 rpm. Then, 560.0 g of an ethylene oxide/propylene oxide/butylene oxide mixture (molar ratio: 40/40/20) was added to the obtained mixture and reacted with butyric acid at a temperature of from 150 to 160°C under a pressure of from 1 to 3 kg/cm² (gauge). After the completion of the addition reaction, the reaction mixture was cooled to 80°C and the pH value thereof was adjusted to 6 with acetic acid. The yield of the obtained reaction product (used as a deinking agent in invention example No. 114 given in Table 10) was 99%.

Example 5

In this Example, a deinking agent was added at once in the pulping step.

Waste PPC papers (100%), printed with 2.4 g/m^2 of a printing ink comprising a styrene/acrylic binder, were cut into pieces (2 x 5 cm). A given amount thereof was fed into a bench disintegrator. Then, water, 0.5 wt.% (based on waste PPC papers) of caustic soda, 1.0 wt.% (based on waste PPC papers) of sodium silicate No. 3, 1.0 wt.% (based on waste PPC papers) of 30 wt.% hydrogen peroxide and 0.2 wt.% (based on waste PPC papers) of each deinking agent listed in Table 7 were added thereto. After disintegrating at a pulp concentration of 5 wt.% at 45°C for 20 minutes, the mixture was aged at 45°C for 60 minutes. Next, the mixture was dehydrated on a high-speed dehydrator until the pulp concentration reached 22 wt.% and then kneaded on a twin-screw laboratory kneader at 200 rpm. After diluting with water so as to give a pulp concentration of 4 wt.%, it was disintegrated again on the bench disintegrator for 30 seconds. The obtained slurry was concentrated on an 80-mesh wire gauze until the pulp concentration reached 10 wt.% and diluted with water so as to give a pulp concentration of 1 wt.%. Subsequently, it was treated on a TAPPI standard sheet machine to thereby give a pulp sheet.

The whiteness of the obtained pulp sheet was measured with a color difference meter and the unliberated ink spots having a particle size of 30 μm or more were counted with an image analyzer (magnification: x100). The defoaming property of the flotation reject was determined for use as an indicator of foaming troubles in effluent disposal step, similar to the Example 1.

Table 7 shows the results of the evaluation of the deinking performances of the deinking agents.

Table 7

No.	Deinking agent						Whiteness (%)	No. of unliberated ink spots ($\geq 30 \mu\text{m}$)	Defoaming property (%)
	RO(AO) _m H					solubility parameter			
	R	average C number in R	AO	m					
77	$\text{CH}_3(\text{CH}_2)_3\text{CHCH}_2-\text{C}_2\text{H}_5$	8	EO	1		10.2	88.8	12	26
78	$\text{CH}_3(\text{CH}_2)_3\text{CHCH}_2-\text{C}_2\text{H}_5$	8	EO	6		9.3	88.1	15	24
79	CH_3-	1	EO	1		11.7	88.2	16	23
80	CH_3-	1	EO	6		9.4	88.3	15	23
81	$\text{CH}_3\text{CH}-\text{CH}_3$	3	PO	1		10.4	89.0	12	25
82	$\text{CH}_3-\text{C}-\text{O}$	2	EO/PO (1/1)	2		9.7	88.7	14	27
83	$\text{CH}_3-\text{C}-\text{O}$	2	EO/PO (1/1)	5		9.1	88.0	18	26

Invention Example

Example 6

In this Example, a deinking agent was added in portions in the pulping step and in the kneading step.

Waste PPC papers (100%), printed with 2.4 g/m^2 of a printing ink comprising a styrene/acrylic binder, were cut into pieces (2 x 5 cm). A given amount thereof was fed into a bench disintegrator. Then, water, 0.3 wt.% (based on waste PPC papers) of caustic soda and 0.1 wt.% (based on waste PPC papers) of each deinking agent listed in Table 8 were added thereto. After disintegrating at a pulp concentration of 5 wt.% at 45°C for 20 minutes, the mixture was aged at 45°C for 60 minutes. Next, the mixture was dehydrated on a high-speed dehydrator until the pulp concentration reached 22 wt.% and then 0.2 wt.% (based on waste PPC papers) of caustic soda, 1.0 wt.% (based on waste PPC papers) of sodium silicate No. 3, 1.0 wt.% (based on waste PPC papers) of 30 wt.% hydrogen peroxide and 0.1 wt.% (based on waste PPC papers) of each deinking agent listed in the Table 8 were added thereto, followed by kneading on a twin-screw laboratory kneader at 200 rpm. After diluting with water so as to give a pulp concentration of 4 wt.%, it was disintegrated again on the bench disintegrator for 30 seconds. The obtained slurry was diluted with water

to give a pulp concentration of 1 wt.%, and then subjected to flotation at 30°C for 10 minutes. Next, the pulp slurry was concentrated on an 80-mesh wire gauze until the pulp concentration reached 10 wt.% and diluted with water so as to give the pulp concentration of 1 wt.%. Subsequently, it was treated on a TAPPI standard sheet machine to thereby give a pulp sheet.

The whiteness of the obtained pulp sheet was measured with a color difference meter and the unliberated ink spots having a particle size of 30 μm or more were counted with an image analyzer (magnification: x100). The defoaming property of the flotation reject was determined, by method of the Example 1, for use as an indicator of foaming troubles in the effluent disposal step. Table 8 shows the deinking performances of various deinking agents.

Table 8

		Deinking agent					Whiteness (%)	No. of unliberated ink spots (≥ 30 μm)	Defoaming property (%)
		RO(AO) _m H							
		R	average C number in R	AO	m	solubility parameter			
Invention Example	No.								
	92	$\text{CH}_3\text{CH}_2\text{C}-\overset{\overset{\text{O}}{\parallel}}{\quad}$	3	EO/PO (2/2)	4	9.2	89.0	10	22
	93	$\text{CH}_3\text{CH}_2\text{C}-\overset{\overset{\text{O}}{\parallel}}{\quad}$	3	EO/PO (2/2)	1	10.1	90.3	8	24
	94	$\text{CH}_3\text{CH}_2\text{C}-\overset{\overset{\text{O}}{\parallel}}{\quad}$	3	EO/PO (2/2)	6	9.0	89.0	10	24
	95	$\text{CH}_3\text{CH}-\overset{\overset{\text{CH}_3}{\mid}}{\quad}$	3	PO	1	10.4	90.2	7	21
	96	$\text{CH}_3(\text{CH}_2)_2\text{CH}=\text{CHCH}_2^-$	6	PO	1	10.3	90.1	8	28
	97	$\text{CH}_3(\text{CH}_2)_2\text{CH}=\text{CHCH}_2^-$	6	EO/BO (1/1)	2	9.7	89.4	9	22
98	$\text{CH}_2=\text{CH}(\text{CH}_2)_5^-$	7	EO/PO (3/3)	6	9.1	89.0	10	25	

Example 7

In this Example, a deinking agent was added at once in the pulping step.

Waste CPO papers (100%), printed with 3.0 g/m^2 of a printing ink comprising a polyester binder, were cut into pieces (2 x 5 cm). A given amount thereof was fed into a bench disintegrator. Then, water, 1.0 wt.% (based on waste CPO papers) of caustic soda, 1.0 wt.% (based on waste CPO papers) of sodium silicate No. 3, 1.5 wt.% (based on waste CPO papers) of 30 wt.% hydrogen peroxide and 0.2 wt.% (based on waste CPO papers) of each deinking agent listed in Table 9 were added thereto. After disintegrating at a pulp concentration of 15 wt.% at 45°C for 20 minutes, the mixture was aged at 55°C for 120 minutes. Next, the mixture was dehydrated on a high-speed dehydrator until the pulp concentration reached 22 wt.% and then dispersed on a laboratory disperser at 300 rpm. After diluting with water so as to give a pulp concentration of 4 wt.%, it was disintegrated again on the bench disintegrator for 30 seconds. The obtained slurry was diluted with water to give a pulp concentration of 1 wt.% and subjected to flotation at 30°C for 10 minutes. Then, the slurry was concentrated on an 80-mesh wire gauze until the pulp concentration

reached 10 wt.% and diluted with water so as to give the pulp concentration of 1 wt.%. Subsequently, it was treated on a TAPPI standard sheet machine to thereby give a pulp sheet.

The whiteness of the obtained pulp sheet was measured with a color difference meter and the unliberated ink spots having a particle size of 30 μm or more were counted with an image analyzer (magnification: x100). The defoaming property of the flotation reject was determined, using the same method as in Example 1, for use as an indicator of foaming troubles in the effluent disposal step. Table 9 shows the deinking performances of various deinking agents.

Table 9

		Deinking agent						Whiteness (%)	No. of unliberated ink spots ($\geq 30 \mu\text{m}$)	Defoaming property (%)
		RO(AO) _g H								
		R	average C number in R	AO	m	solubility parameter				
No.	Invention Example	106	CH ₃ (CH ₂) ₂ ⁻	3	EO/PO (3/2)	5	9.3	87.4	15	29
		107	CH ₃ (CH ₂) ₂ ⁻ /CH ₃ ⁻ (50/50)	2	PO	1	10.1	88.3	16	24
	108	CH ₃ (CH ₂) ₂ ⁻	3	EO/PO (2/4)	6	9.1	88.1	14	25	
Comparative Example	109	CH ₃ (CH ₂) ₁₇ ⁻ /CH ₃ ⁻ (40/60)	7.2	PO	0.9	10.2	86.2	30	45	
	110	CH ₃ (CH ₂) ₁₇ ⁻ /CH ₃ ⁻ (40/60)	7.2	PO	12	8.7	87.0	32	85	
	111	CH ₃ (CH ₂) ₁₇ ⁻ /CH ₃ ⁻ (40/60)	7.2	EO/PO (20/10)	30	8.7	86.5	31	88	
	112	ammonium oleate					85.4	44	40	
	113	sodium dodecylbenzenesulfonate					85.5	46	95	

Example 8

In this Example, a deinking agent was added in portions in the pulping step and in the dispersing step.

Waste CPO papers (100%), printed with 3.0 g/m^2 of a printing ink comprising a polyester binder, were cut into pieces (2 x 5 cm). A given amount thereof was fed into a bench disintegrator. Then, water, 0.3 wt.% (based on waste CPO papers) of caustic soda and 0.1 wt.% (based on waste CPO papers) of each deinking agent listed in Table 10 were added thereto. After disintegrating at a pulp concentration of 15 wt.% at 45°C for 20 minutes, the mixture was aged at 55°C for 120 minutes. Next, the mixture was dehydrated on a high-speed dehydrator until the pulp concentration reached 22 wt.%, and then 0.7 wt.% (based on waste CPO papers) of caustic soda, 1.0 wt.% (based on waste CPO papers) of sodium silicate No. 3, 1.5 wt.% (based on waste CPO papers) of 30 wt.% hydrogen peroxide and 0.1 wt.% (based on waste CPO papers) of each deinking agent listed in the Table 10 were added thereto, followed by dispersing on a laboratory disperser at 300 rpm. After diluting with water so as to give a pulp concentration of 4 wt.%, it was disintegrated again on the bench disintegrator for 30 seconds. The

obtained slurry was diluted with water to give a pulp concentration of 1 wt.% and then subjected to flotation at 30°C for 10 minutes. Next, the pulp slurry was concentrated on an 80-mesh wire gauze until the pulp concentration reached 10 wt.% and diluted with water so as to give the pulp concentration of 1 wt.%. Subsequently, it was treated on a TAPPI standard sheet machine to thereby give a pulp sheet.

The whiteness of the obtained pulp sheet was measured with a color difference meter and the unliberated ink spots having a particle size of 30 μm or more were counted with an image analyzer (magnification: x100). The defoaming property of the flotation reject was determined, as in Example 1, for use as an indicator of foaming troubles in the effluent disposal step. Table 10 shows the deinking performances of various deinking agents.

Table 10

	No.	Deinking agent						Whiteness (%)	No. of unliberated ink spots ($\geq 30 \mu\text{m}$)	Defoaming property (%)
		RO(AO) _m H					solubility parameter			
		R	average C number in R	AO	m					
Invention Example	114	$\text{CH}_3(\text{CH}_2)_2\text{C}-\begin{array}{c} \text{H} \\ \\ \text{O} \end{array}$	4	EO/PO/BO (2/2/1)	5	9.0	89.3	9	24	
	115	$\text{CH}_3(\text{CH}_2)_2\text{C}-\begin{array}{c} \text{H} \\ \\ \text{O} \end{array}$	4	EO/PO (2/3)	5	9.1	89.4	9	25	
	116	$\text{CH}_3(\text{CH}_2)_2\text{C}-\begin{array}{c} \text{H} \\ \\ \text{O} \end{array}$	4	EO	5	9.3	89.3	8	25	
	117	$\text{CH}_3(\text{CH}_2)_2\text{C}-\begin{array}{c} \text{H} \\ \\ \text{O} \end{array}$	4	PO	5	9.0	89.2	9	22	
	118	$\text{CH}_3(\text{CH}_2)_2-$	3	EO/PO (2/4)	6	9.1	90.5	7	18	
	119	$\text{CH}_2=\text{CH}(\text{CH}_2)_5-$	7	PO	5	9.4	89.1	9	20	
	120	CH_3CH_2-	2	PO	1	10.8	90.6	5	15	

Table 10 (contd.)

		Deinking agent						Whiteness (%)	No. of unliberated ink spots ($\geq 30 \mu\text{m}$)	Defoaming property (%)
		RO(AO) _m H					solubility parameter			
		R	average C number in R	AO	m					
Invention Example	No.	121	$\text{CH}_3(\text{CH}_2)_4^-$	5	PO	1	10.4	90.7	4	17
		122	CH_3CH_2^-	2	BO	1	10.3	90.6	4	18
		123	$\text{CH}_3(\text{CH}_2)_4^-$	5	BO	1	10.0	90.6	4	15
Comparative Example		124	$\text{CH}_3(\text{CH}_2)_2\text{C}-$ $\begin{array}{c} \\ \text{O} \end{array}$	4	BO	5	8.6	86.9	34	65
		125	$\text{CH}_3(\text{CH}_2)_2\text{C}-$ $\begin{array}{c} \\ \text{O} \end{array}$	4	EO/PO/BO (4/4/2)	10	8.7	87.0	32	65
		126	$\text{CH}_3(\text{CH}_2)_2\text{C}-$ $\begin{array}{c} \\ \text{O} \end{array}$	4	EO	0.6	10.2	86.9	28	74
		127	$\text{CH}_3(\text{CH}_2)_2\text{C}-$ $\begin{array}{c} \\ \text{O} \end{array}$	10	EO/PO/BO (2/2/2)	6	8.9	87.2	35	72

Example 9

In this Example, a deinking agent was added in portions in the pulping step and in the kneading step.

Waste PPC papers (100%), printed with 3.2 g/m² of a printing ink comprising a styrene/acrylic binder, were cut into pieces (2 x 5 cm). A given amount thereof was fed into a bench disintegrator. Then, water, 0.3 wt.% (based on waste PPC papers) of caustic soda and a given amount of each deinking agent listed in Table 11 were added thereto. After disintegrating at a pulp concentration of 5 wt.% at 45°C for 20 minutes, the mixture was aged at 45°C for 60 minutes. Next, the mixture was dehydrated on a high-speed dehydrator until the pulp concentration reached 22 wt.%, and then 0.2 wt.% (based on waste PPC papers) of caustic soda, 1.0 wt.% (based on waste PPC papers) of sodium silicate No. 3, 1.0 wt.% (based on waste PPC papers) of 30 wt.% hydrogen peroxide and a given amount of each deinking agent listed in Table 11 were added thereto, followed by kneading on a twin-screw laboratory kneader at 200 rpm. After diluting with water so as to give a pulp concentration of 4 wt.%, it was disintegrated again on the bench disintegrator for 30 seconds. The obtained slurry was diluted with water to give a pulp concentration of 1 wt.% and then

subjected to flotation at 30°C for 10 minutes. Next, the pulp slurry was concentrated on an 80-mesh wire gauze until the pulp concentration reached 10 wt.% and diluted with water so as to give the pulp concentration of 1 wt.%. Subsequently, it was treated on a TAPPI standard sheet machine to thereby give a pulp sheet.

The whiteness of the obtained pulp sheet was measured with a color difference meter and the unliberated ink spots having a particle size of 30 μm or more were counted with an image analyzer (magnification: x100). The defoaming property of the flotation reject was determined, as in Example 1, for use as an indicator of foaming troubles in the effluent disposal step. Table 12 shows the deinking performances of various deinking agents.

Table 11

No.	Deinking agent					Addition of deinking agent (based on waste PPC papers)		
	R	RO(AO) _m H			solubility parameter	pulping step (I)	kneading step (II)	I/II wt. ratio
		average C number in R	AO	m				
128	$\text{CH}_3(\text{CH}_2)_3\text{CHCH}_2^-$ C_2H_5	8	EO	1	10.2	0.1	0.1	50/50
129	$\text{CH}_3(\text{CH}_2)_3\text{CHCH}_2^-$ C_2H_5	8	EO	1	10.2	0.18	0.02	90/10
130	$\text{CH}_3(\text{CH}_2)_3\text{CHCH}_2^-$ C_2H_5	8	EO	1	10.2	0.02	0.18	10/90
131	$\text{CH}_3\text{C}-$ O	2	EO/PO (1/1)	2	9.7	0.12	0.08	60/40
132	$\text{CH}_3\text{C}-$ O	2	EO/PO (1/1)	2	9.7	0.17	0.03	85/15
133	$\text{CH}_3\text{C}-$ O	2	EO/PO (1/1)	2	9.7	0.03	0.17	15/85
134	$\text{CH}_3(\text{CH}_2)_2^-$	3	EO/PO (3/2)	5	9.3	0.2	0.3	40/60
135	$\text{CH}_3(\text{CH}_2)_2^-$	3	EO/PO (3/2)	5	9.3	0.4	0.1	80/20
136	$\text{CH}_3(\text{CH}_2)_2^-$	3	EO/PO (3/2)	5	9.3	0.1	0.4	20/80

Invention
Example

Table 11 (contd.)

No.	Deinking agent					Addition of deinking agent (based on waste PPC papers)		
	R	RO(AO) _{gr} H				pulping step (I)	kneading step (II)	I/II wt. ratio
		average C number in R	AO	m	solubility parameter			
137	$\text{CH}_3(\text{CH}_2)_3\text{CHCH}_2^-$ C_2H_5	8	EO	1	10.2	0.184	0.016	92/ 8
138	$\text{CH}_3(\text{CH}_2)_3\text{CHCH}_2^-$ C_2H_5	8	EO	1	10.2	0.016	0.184	8/92
139	$\text{CH}_3\text{C}-$ O	2	EO/PO (1/1)	2	9.7	0.182	0.018	91/ 9
140	$\text{CH}_3\text{C}-$ O	2	EO/PO (1/1)	2	9.7	0.018	0.182	9/91
141	$\text{CH}_3(\text{CH}_2)_2^-$	3	EO/PO (3/2)	5	9.3	0.186	0.014	93/ 7
142	$\text{CH}_3(\text{CH}_2)_2^-$	3	EO/PO (3/2)	5	9.3	0.014	0.186	7/93
143	$\text{CH}_3(\text{CH}_2)_{16}\text{C}-$ O	18	EO/PO (15/10)	25	8.7	0.1	0.1	50/50
144	$\text{CH}_3(\text{CH}_2)_{17}^-$	18	EO	8	9.3	0.2	0.3	40/60

Table 12

	No.	Whiteness (%)	No. of unliberated ink spots ($\geq 30 \mu\text{m}$)	Defoaming property (%)
Invention Example	128	91.2	3	10
	129	90.4	5	15
	130	90.2	5	15
	131	89.8	7	20
	132	89.5	8	22
	133	89.4	8	24
	134	89.8	7	22
	135	89.4	8	25
	136	89.2	9	24
	137	89.0	11	24
	138	89.1	10	22
	139	89.2	11	18
	140	89.2	11	18
	141	89.0	12	15
	142	88.9	13	17
Comp. Example	143	86.4	25	92
	144	86.2	27	90

As described above, the deinking agents according to the present invention, i.e., the deinking compositions of the present invention in the above-described cases, each of which is an alkylene oxide adduct compound mixture which comprises or essentially consists compounds represented by the general formula

(1) and has a solubility parameter of from 9.0 to 11.8, exert excellent effects in elevating the whiteness, reducing the number of unliberated large ink spots and improving the defoaming property of the flotation reject, when they are used in deinking waste OA papers or blends containing waste OA papers.

Further, a deinked pulp having more excellent qualities can be obtained by adding the deinking agent according to the present invention in portions, i.e., in the pulping step and in any of the subsequent steps.

The invention being thus described, it will be obvious that the same may be varied in many ways. Such variations are not to be regarded as a departure from the spirit and a scope of the invention, and all such modifications as would be obvious to one skilled in the art are intended to be included within the scope of the following claims.

65702-396

CLAIMS:

1. A deinking agent consisting essentially of a partial ester mixture having a solubility parameter of 8.9 to 9.8, which is formed by reacting:

5 a reaction product mixture, which is obtained by reacting (a) a polyfunctional alcohol having up to 12 carbon atoms or (b) a polyfunctional fatty acid having up to 11 carbon atoms with (c) a C₂₋₄ alkylene oxide, the reaction product mixture including therein 1 to 4 moles of alkylene
10 oxide units per each functional group of (a) or (b), provided that the total alkylene oxide unit in the product is not more than 22 moles, with,

(d) a fatty acid having 2 to 8 carbon atom.

2. The deinking agent according to claim 1, wherein:

15 the polyfunctional alcohol (a) is at least one compound selected from the group consisting of ethylene glycol, trimethylene glycol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,7-heptanediol, 1,8-octanediol, 1,9-nonanediol, 1,10-decanediol, 1,2-octanediol,
20 1,2-decanediol, butanoyl- α -glycol, 1,3-butanediol, trans-2-butene-1,4-diol, 2-butyne-1,4-diol, 2,4-pentanediol, 2,5-hexanediol, 2-methyl-1,3-pentanediol, 2-methyl-2,4-pentanediol, 2,3-dimethyl-2,3-butanediol, 2,4-heptanediol, 2,2-diethyl-1,3-propanediol, 2-ethyl-1,3-hexanediol, 2-
25 ethyl-2-butyl-1,3-propanediol, diethylene glycol, triethylene glycol, tetraethylene glycol, dipropylene glycol, 1,2-cyclononanediol, 1,2-cyclodecanediol, glycerol, erythritol, pentaerythritol, arabitol, sorbitol, sorbitan, mannitol, mannitan, 1,2,3-butanetriol, 2-methylpropane-
30 1,2,3-triol, 2,3,4-pentanetriol, 2-methylbutane-1,2,3-triol,

65702-396

2,3,4-hexanetriol, 2-ethylbutane-1,2,3-triol, 2,3,4-trimethylpentane-2,3,4-triol, D-glycero-D-galaheptose, D-glycero-D-glucoheptose, D-glycero-D-mannoheptose, D-glycero-L-mannoheptose, D-glycero-D-galaheptitol, D-altroheptulose,
5 D-altro-3-heptulose, D-mannoheptulose, D-erythro-D-galaoctitol, D-glycero-D-manno-octulose, D-erythro-L-gulononulose, cellobiose, maltose and lactose; and

the polyfunctional fatty acid (b) is at least one compound selected from the group consisting of oxalic acid,
10 malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, ethylmalonic acid, 2-hydroxyvaleric acid, 2-hydroxycaproic acid, 2-hydroxycaprylic acid, 2-hydroxypelargonic acid, 2-hydroxyundecanoic acid, 3-hydroxycaprylic acid, 3-
15 hydroxypelargonic acid, 3-hydroxycapric acid, 6-hydroxycaproic acid, 7-hydroxyenanthic acid, 8-hydroxycaprylic acid, 9-hydroxypelargonic acid, 10-hydroxycapric acid, 2-methylhydroxyenanthic acid, 2-hydroxy-3-pentenoic acid, 5-hydroxy-2,4-pentadienoic acid, 2,3-dihydroxycaproic acid,
20 2,3-dihydroxyenanthic acid, 2,3-dihydroxycaprylic acid, 2,3-dihydroxypelargonic acid, 2,3-dihydroxycapric acid, 1-nonene-1,9-dicarboxylic acid and 2-nonene-1,9-dicarboxylic acid.

3. The deinking agent according to claim 1 or 2,
25 wherein the polyfunctional alcohol (a) has up to 10 carbon atoms and the polyfunctional fatty acid (b) has up to 10 carbon atoms.

4. The deinking agent according to claim 1, 2 or 3,
wherein the average degree of the partial esterification of
30 the partial ester mixture is from 15 to 75% by mole.

65702-396

5. The deinking agent according to any one of claims 1 to 4, wherein the reaction product mixture is a reaction product of a polyfunctional alcohol having up to 6 carbon atoms with a C₂₋₄ alkylene oxide.

5 6. The deinking agent according to any one of claims 1 to 4, wherein the reaction product mixture is a reaction product of a polyfunctional fatty acid having up to 6 carbon atoms with a C₂₋₄ alkylene oxide.

7. The deinking agent according to any one of claims 10 1 to 6, wherein the fatty acid having 2 to 8 carbon atoms (d) is at least one member selected from the group consisting of acetic acid, propionic acid, propynoic acid, butyric acid, isobutyric acid, tetrolic acid, valeric acid, α -methylbutyric acid, isovaleric acid, trimethylpropanoic acid, 2-pentynoic acid, allylacetic acid, 2,4-pentadienoic acid, caproic acid, 2-methylpentanoic acid, 3-methylpentanoic acid, 4-isocaproic acid, 2-hexynoic acid, sorbic acid, 2-hexenoic acid, 3-hexenoic acid, 4-hexynoic acid, 5-hexenoic acid, heptanoic acid, 2-heptenoic acid, 3-heptenoic acid, 5-heptenoic acid, 6-heptenoic acid, 2-heptynoic acid, 6-heptynoic acid, caprylic acid, 2-ethylhexanoic acid, 2-octenoic acid, 3-octenoic acid, 2-octynoic acid, 7-octynoic acid, 2-methyl-2-heptenoic acid, benzoic acid, methylbenzoic acid, cyclohexylacetic acid, 2-fluorovaleric acid, 2-fluorocaproic acid, 2-fluoroenanthic acid, 2-chlorocaprylylic acid, 2-bromovaleric acid, 2-bromocaproic acid, 2-bromoenanthic acid, 2-bromocaprylylic acid, 5-chlorovaleric acid, oxalic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, 30 suberic acid, ethylmalonic acid, 2-hydroxyvaleric acid, 2-hydroxycaproic acid, 2-hydroxycaprylylic acid, 2-hydroxypelargonic acid, 2-hydroxyundecanoic acid, 3-

65702-396

hydroxycaprylic acid, 6-hydroxycaproic acid, 7-hydroxyenanthic acid, 8-hydroxycaprylic acid, 2-methyl-hydroxyenanthic acid, 2-hydroxy-3-pentenoic acid, 4-hydroxy-3-pentenoic acid, 4-hydroxy-4-pentenoic acid, 5-hydroxy-2,4-pentadienoic acid, 2,3-dihydroxycaproic acid, 2,3-dihydroxyenanthic acid, 2,3-dihydroxycaprylic acid and anhydrides of these acids.

8. The deinking agent according to any one of claims 1 to 7, wherein the fatty acid (d) has 2 to 4 carbon atoms.

10 9. A method of deinking waste paper, comprising:

(i) pulping the waste paper to form a pulp,

(ii) subjecting the pulp to at least one treatment step selected from the group consisting of kneading, dispersing, chemical mixing and refining, and

15 (iii) subjecting the treated pulp to a flotation or washing step,

wherein the deinking agent according to any one of claims 1 to 7 is added in portions in steps (i) and at least one of (ii) and (iii).

20 10. A method for deinking waste paper, comprising:

(i) pulping the waste paper to form a pulp,

(ii) subjecting the pulp to at least one treatment step selected from the group consisting of kneading, dispersing, chemical mixing and refining, and

25 (iii) subjecting the treated pulp to a flotation or washing step,

65702-396

wherein the deinking agent according to any one of claims 1 to 8 is added during steps (i) and (ii).

11. The method for deinking waste paper according to claim 9, wherein the ratio of the deinking agent added in
5 step (i) to at least one of steps (ii) and (iii) is 10/90 to 90/10 by weight.

12. The method of claim 9, 10, or 11, wherein the deinking agent is added in an amount to achieve a deinking agent concentration of from 0.03 to 1.0% by weight based on
10 the waste paper.

13. The method for deinking waste paper according to any one of claims 9 to 12, wherein the waste paper is waste office automation (OA) papers or blends containing thereof.

SMART & BIGGAR
OTTAWA, CANADA

PATENT AGENTS