



US 20060097348A1

(19) **United States**(12) **Patent Application Publication****Gealy et al.**(10) **Pub. No.: US 2006/0097348 A1**(43) **Pub. Date: May 11, 2006**(54) **STRUCTURES HAVING AN ELECTRODE FORMED FROM A TRANSITION METAL OR A CONDUCTIVE METAL-OXIDE**

6,960,513, which is a division of application No. 09/286,807, filed on Apr. 6, 1999, now Pat. No. 6,696,718.

(75) Inventors: **F. Daniel Gealy**, Kuna, ID (US);
Thomas M. Graettinger, Boise, ID (US)**Publication Classification**(51) **Int. Cl.**
H01L 29/00 (2006.01)
H01L 29/94 (2006.01)
(52) **U.S. Cl.** **257/534**; 257/532; 257/309;
257/306


Correspondence Address:

**KIRKPATRICK & LOCKHART NICHOLSON
GRAHAM LLP
535 SMITHFIELD STREET
PITTSBURGH, PA 15222 (US)**(73) Assignee: **Micron Technology, Inc.**(21) Appl. No.: **11/315,638**(22) Filed: **Dec. 22, 2005****Related U.S. Application Data**

(60) Continuation of application No. 10/299,145, filed on Nov. 19, 2002, which is a division of application No. 09/770,699, filed on Jan. 26, 2001, now Pat. No.

(57) **ABSTRACT**

Structures having an electrode formed from a transition metal or a conductive metal oxide are disclosed. The structures may comprise a first electrode made of a material selected from the group consisting of transition metals, conductive metal-oxides, alloys thereof, and combinations thereof. The first electrode may comprise a first non-smooth surface, and the first non-smooth surface may comprise a concave hemispherical grain. The structures may also comprise a dielectric in contact with the first electrode and a surface of a substrate assembly.






FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14

STRUCTURES HAVING AN ELECTRODE FORMED FROM A TRANSITION METAL OR A CONDUCTIVE METAL-OXIDE

CROSS REFERENCE TO RELATED APPLICATIONS

[0001] The present application is a continuation of copending U.S. patent application Ser. No. 10/299,145, filed Nov. 19, 2002, ("the parent application"), which is a divisional of U.S. patent application Ser. No. 09/770,699, filed Jan. 26, 2001 and now issued as U.S. Pat. No. 6,960,513, which is a divisional of U.S. patent application Ser. No. 09/286,807, filed Apr. 6, 1999 and now issued as U.S. Pat. No. 6,696,718.

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

[0002] Not Applicable.

BACKGROUND OF THE INVENTION

[0003] 1. Field of the Invention

[0004] The present invention is directed generally to a capacitor and method for forming a capacitor and, more particularly, to a capacitor and method for forming a capacitor having an electrode formed from a transition metal, a conductive metal-oxide, alloys thereof, or combinations thereof.

[0005] 2. Description of the Background

[0006] Minimum feature sizes in integrated circuits are sufficiently small that some fabrication processes are no longer effective. For example, in many applications sputter deposition is not effective for filling openings. Furthermore, the smaller dimensions are requiring higher performance from components and devices. For example, greater capacitance is required from small capacitors. One way to obtain higher capacitance is to use dielectrics having greater dielectric constants. Often, however, it is necessary to heat the dielectric to high temperatures in order to obtain the higher dielectric constant, and such heating can have adverse effects on the electrodes used to form the capacitor. For example, the electrodes will often oxidize, and the oxide will act as a lower permittivity dielectric in series with a higher permittivity dielectric. As a result, the oxide formed from the electrode will increase the effective distance between the electrodes, thereby decreasing the capacitance.

[0007] Therefore, the need exists for a capacitor and method for forming capacitors that do not suffer adverse effects when used with dielectrics having high dielectric constants.

BRIEF SUMMARY OF THE INVENTION

[0008] The present invention is directed to a capacitor including a first electrode selected from a group consisting of transition metals, conductive metal-oxides, alloys thereof, and combinations thereof. The capacitor also includes a second electrode and a dielectric between the first and second electrodes. The present invention may be used to form capacitors in integrated circuits, such as those in memory devices and processors.

[0009] The present invention also includes a method of forming a capacitor. The method includes forming a first electrode selected from a group consisting of transition metals, conductive metal-oxides, alloys thereof, and combinations thereof. The method also includes forming a second electrode and forming a dielectric between the first and second electrodes.

[0010] The present invention solves problems experienced with the prior art because it provides for capacitors having improved physical structures, such as higher capacitance, smaller physical size, and smaller footprint, by utilizing improved dielectric properties, including electrodes that do not form dielectrics during subsequent processing steps. Those and other advantages and benefits of the present invention will become apparent from the description of the preferred embodiments hereinbelow.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWING

[0011] For the present invention to be clearly understood and readily practiced, the present invention will be described in conjunction with the following figures, wherein:

[0012] **FIG. 1** is a cross-sectional view of a capacitor constructed according to the teachings of the present invention;

[0013] **FIG. 2** is a cross-sectional view of a capacitor in an early stage of fabrication;

[0014] **FIG. 3** is a cross-sectional view of the capacitor of **FIG. 2** after the material forming the first electrode is removed from the top surface of the substrate assembly;

[0015] **FIG. 4** is a cross-sectional view of the capacitor of **FIG. 3** after a portion of the substrate assembly is removed from around the first electrode;

[0016] **FIG. 5** is a cross-sectional view of the capacitor of **FIG. 4** after a dielectric and second conductor, including a strap, are formed;

[0017] **FIG. 6** is a cross-sectional view of the capacitor of **FIG. 5** after an additional layer is formed over the capacitor;

[0018] **FIG. 7** is a cross-sectional view of an alternative embodiment of a capacitor wherein the dielectric and second electrode are formed only on the inside of the first electrode;

[0019] **FIG. 8** is a cross-sectional view of the capacitor of **FIG. 7** after an additional layer and interconnect are formed;

[0020] **FIG. 9** is a cross-sectional view of a post capacitor according to the teachings of the present invention;

[0021] **FIG. 10** is a cross-sectional view of the capacitor including the first electrode, second electrode, and dielectric are formed from a non-smooth material;

[0022] **FIG. 11** is a cross-sectional view of the capacitor of **FIG. 10** in an early stage of fabrication after a layer of hemispherical grain polysilicon is formed in the opening;

[0023] **FIG. 12** is a cross-sectional view of the capacitor of **FIG. 11** after the material forming the first electrode is formed;

[0024] **FIG. 13** is a cross-sectional view of the capacitor of **FIG. 12** after the substrate is partially removed and after the hemispherical grain polysilicon is removed; and

[0025] FIG. 14 is a block diagram of a system including devices constructed according to the teachings of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

[0026] It is to be understood that the figures and descriptions of the present invention have been simplified to illustrate elements that are relevant for a clear understanding of the present invention, while eliminating, for purposes of clarity, other elements. Those of ordinary skill in the art will recognize that other elements may be desirable. However, because such elements are well known in the art, and because they do not facilitate a better understanding of the present invention, a discussion of such elements is not provided herein.

[0027] Advantages of the present invention may be realized using a number of structures and technologies, such as doped silicon substrate, silicon-on-insulator, silicon-on-sapphire, and thin film transistor. The term “substrate”, as used herein, refers to a structure that is often the lowest layer of semiconductor material in a wafer or die, although in some technologies the substrate is not a semiconductor material. The term “substrate assembly”, as used herein, shall mean a substrate having one or more layers or structures formed thereon or therein. The substrate assembly may include one or more active or operable portions of a semiconductor device.

[0028] FIG. 1 is a cross-sectional view of a capacitor 10 formed according to the present invention. The capacitor 10 includes a first electrode 12, a second electrode 14, and a dielectric 16 formed between the first and second electrodes 12, 14. The capacitor 10 is illustrated as a crown-shaped capacitor, although benefits of the present invention may be realized with capacitors 10 having many forms, including flat capacitors and post capacitors. The capacitor 10 may be formed on a substrate assembly 18, and may include an interconnect 20 to, for example, a doped region 22.

[0029] The first electrode 12 may be formed from a transition metal, such as Pt, Rh, Ir, Ru, and Pd; from metals that form conductive metal oxides, such as IrO_x , RuO_x , and RhO_x (where $x < 4$); from conductive oxides; and from alloys of any of those materials. The first electrode 12 may also be formed from any combination of the foregoing materials. The first electrode 12 may also be formed from other materials that either do not oxidize during the formation of the capacitor 10, or whose oxidized forms are conductive.

[0030] The second electrode 14 may be formed from any of the materials that may be used for the first electrode 12. However, because the second electrode 14 is often not exposed to a high temperature processing step, the second electrode 14 may be formed from other materials that may not be suitable for use as the first electrode 12. Examples of those other materials are conductive metal nitrides, WN, aluminum, TiN, TaN, and polysilicon.

[0031] The dielectric 16 may be formed from a material that will provide a high dielectric constant, such as an insulating transition metal binary, ternary, or quaternary oxide. For example, the dielectric may be formed by a chemical vapor deposition (CVD) of barium strontium titanate (BST), SrTiO_3 , $\text{Sr}_w\text{Bi}_x\text{Ta}_y\text{O}_z$, $\text{Ba}_x\text{Sr}_{1-x}\text{TiO}_3$ where

$0 < x < 1$, or Ta_2O_5 , followed by heating the dielectric 16 to 400 degrees C. or more in the presence of oxygen-containing ambient, such as O_2 , N_2O , O_3 , or NO.

[0032] The substrate assembly 18 may be formed, for example, from borophosphosilicate glass (BPSG), TEOS oxide, SiO_2 , or Si_3N_4 . The interconnect 20 may be formed, for example, from polysilicon, TiN, or tungsten. Alternatively, the interconnect 20 may be omitted and the first electrode 12 may be connected directly to the doped region 22. Alternatively, the first electrode 12 may be connected to a metal contact or metal line rather than the doped region 22, or the first electrode 12 may be left floating. The substrate assembly 18 may be formed from one or more layers. For example, in the illustrated embodiment a first substrate layer may be formed and planarized. The first layer may be masked and etched, and the interconnect 20 formed in the first substrate layer. Thereafter, an additional substrate layer may be formed above the first layer and covering the interconnect 20.

[0033] FIG. 2 is a cross-sectional view of the capacitor 10 in an early stage of fabrication. The substrate assembly 18 may be formed from a first substrate layer 24 and a second substrate layer 26. The first substrate layer 24 is formed first, and the interconnect 20 may be formed in the first substrate layer 24 at that time. The interconnect 20 may connect the capacitor 10 to another portion 22 of the device in which the capacitor 10 is formed, such as a doped region. Thereafter, the second substrate layer 26 may be formed on top of the first substrate layer 24, and an opening 28 may be formed in the second substrate layer 26 at that time. The opening 28 may be formed, for example, by selectively masking the second substrate layer 26 so that only the portion of the second substrate layer 26 where the opening 28 is to be formed is exposed, by selectively and anisotropically etching the second substrate layer 26 to form the opening 28, and then removing the mask. The first electrode 12 may be formed in the opening 28 by, for example, depositing a layer of material that will form the first electrode 12, masking that layer, etching the material that is to be removed, and removing the mask to leave the first electrode 12.

[0034] FIG. 3 is a cross-sectional view of the capacitor 10 after the first electrode 12 has been removed from the top surface of the substrate assembly 18. The removal may be performed by, for example, a mechanical abrasion step, such as chemical mechanical planarization (“CMP”). In that example, a protective material, such as photoresist, may be used to fill the opening 28 to prevent materials removed by the CMP from falling into the opening 28. Alternatively, the removal can be performed by a blanket etch back process.

[0035] FIG. 4 is a cross-sectional view of the capacitor 10 after a portion of the substrate assembly 18 has been removed to expose vertical portions of the first electrode 12. The substrate assembly 18 may be removed by, for example, an etch that is selective to the substrate assembly 18 but which does not etch the first electrode 12. The substrate assembly 18 may be etched so that the first electrode 12 remains partially recessed in the substrate assembly 18, thereby providing structural stability to the capacitor 10.

[0036] FIG. 5 is a cross-sectional view of the capacitor 10 after the dielectric 16 and a second electrode 14 have been formed over the first electrode 12, thereby completing the capacitor 10. The dielectric 16 may be formed, for example,

by forming a layer of the dielectric **16** on the entire surface, and then selectively removing the dielectric **16** so that it remains only where desired. In particular, the dielectric **16** may be deposited over the entire surface by sputtering or CVD. The dielectric **16** on the first electrode **12** may be masked, such as with photoresist, and the exposed dielectric may be removed with a selective etch. Alternatively, the insulating dielectric **16** need not be removed at all. The second electrode **14** may be formed after the dielectric **16** and in a manner similar to that used to form the dielectric **16**. In contrast to the embodiment illustrated in **FIG. 1**, the capacitor **10** may include a portion **30** of the second electrode **14**, known as a strap **30**, formed as a contact for connecting the second electrode **14** to another portion of the device in which the capacitor **10** is formed. Similarly, another portion **32** of the second electrode **14** may connect to other capacitors so as to tie several second electrodes together at a common potential, such as ground.

[0037] **FIG. 6** is a cross-sectional view of the capacitor **10** after an additional layer **40** is formed over the capacitor **10**. The additional layer **40** may be used to separate the capacitor **10** from whatever may be formed above the capacitor **10**. The additional layer **40** may be formed, for example, by a CVD process and from the same materials used to form lower layers of the substrate assembly **18**. The additional layer **40** may be planarized, such as by CMP, and an interconnect **42** may be formed in the additional layer **40** to connect the second electrode **14**, via the strap **30**, to another portion of the device in which the capacitor **10** is formed.

[0038] **FIG. 7** is a cross-sectional view of an alternative embodiment of the capacitor **10** in which the dielectric **16** and the second electrode **14** are formed only within the first electrode **12**. In that embodiment, the substrate assembly **18** may not be etched as described hereinabove with respect to **FIG. 4**. The dielectric **16** and second electrode **14** may be formed in a manner similar to the first electrode **12**, such as by CVD followed by mechanical abrasion to remove unwanted material from the top surface of the substrate assembly **18**.

[0039] **FIG. 8** is a cross-sectional view of the capacitor **10** illustrated in **FIG. 7** after an additional layer **40** has been formed and after an interconnect **42** has been formed connecting the second electrode **14** to another portion of the device in which the capacitor **10** is formed. In the illustrated embodiment, the interconnect **42** is connected to the second electrode **14** without the use of the strap **30** (illustrated in **FIGS. 5 and 6**).

[0040] **FIG. 9** is a cross-sectional view of an alternative embodiment of the present invention formed as a post capacitor **10**. That embodiment includes the first electrode **12**, the second electrode **14**, and the dielectric **16** formed on a post **50**. The post **50** may be formed, for example, by forming a temporary layer on the substrate assembly **18**, forming an opening in the temporary layer, filling the opening with a material to form the post **50**, and removing the temporary layer to leave the post **50**. The post **50** may be formed, for example, from polysilicon.

[0041] **FIG. 10** is a cross-sectional view of an alternative embodiment of the present invention wherein the first and second electrodes **12, 14** and the dielectric **16** have a non-smooth surface. The non-smooth surfaces increases the surface area of the first and second electrodes **12, 14** and the

dielectric **16**, thereby increasing the capacitance of the capacitor **10**. The capacitor **10** may be formed, for example, by using a non-smooth mold, such as hemispherical grain (HSG) polysilicon, on which the first electrode **12** may be formed. Such a process results in the first electrode **12** having an inverted hemispherical grain on the side formed on the HSG polysilicon (that is the outside in the illustrated embodiment), and an inverted hemispherical grain on the side opposite that formed on the HSG polysilicon (that is the inside in the illustrated embodiment). Thereafter, the mold may be removed and the dielectric **16** and second electrode **14** may be formed over the first electrode **12**, conforming to its non-smooth surface and assuming a similar non-smooth surface. The dielectric **16** and the second electrode **14** formed by that process have hemispherical grain on one side and inverted hemispherical grain on another side, in a manner analogous to the first electrode **12**. It is desirable that the first electrode **12** be set into a recess, such as a recessed interconnect **20**, so as to provide structural stability to the first electrode **12**.

[0042] **FIG. 11** is a cross-sectional view of the capacitor **10** illustrated in **FIG. 10** in an early stage of fabrication wherein a layer of HSG polysilicon **60** is formed in the opening **28** and on the top surface of the substrate assembly **18**. The layer of HSG polysilicon **60** may be formed, for example, with a CVD process. The interconnect **20** is recessed below the bottom surface of the opening **26**.

[0043] **FIG. 12** is a cross-sectional view of the capacitor **10** after a conductive layer that will form the first electrode **12** is formed over the HSG polysilicon **60**. HSG polysilicon has a coarse, grainy surface, and when the layer that will form the first electrode **12** is formed on the HSG polysilicon **60**, that layer conforms to the HSG polysilicon **60** and assumes a similar, non-smooth surface. The non-smooth surface of the HSG polysilicon has a surface area that is between about 150% and about 200% greater than the surface area of smooth polysilicon. It is desirable to etch the HSG polysilicon **60** from the recessed interconnect **20** before the layer that will form the first electrode **12** is formed, as is done in the illustrated embodiment. As a result, the first electrode **12** will be in direct contact with the interconnect **20**. Otherwise, if the HSG polysilicon **60** is between the first conductor **12** and the interconnect **20**, it may oxidize and increase the resistance of between the interconnect **20** and the first electrode **12**. Furthermore, if HSG polysilicon **60** is supporting the first electrode **12**, the first electrode **12** may be damaged or destroyed when the HSG polysilicon **60** is removed in a subsequent fabrication step.

[0044] **FIG. 13** is a cross-sectional view of the capacitor **10** after the substrate assembly **18** is partially removed and the HSG polysilicon **60** is removed. The partial removal of the substrate assembly **18** exposes the HSG polysilicon **60**, which may then be removed with a selective etch, such as tetra methyl ammonium hydroxide, leaving the first electrode **12**. Thereafter, the dielectric **16** and the second electrode **14** may be formed to result in the capacitor illustrated in **FIG. 10**. The dielectric **16** and second electrode **14**, when formed over the first electrode **12**, will also have a grainy surface, thereby increasing their surface areas.

[0045] **FIG. 14** is a high level block diagram illustrating a system **61** including a first device **62**, a bus **64**, and a

second device 66. The system 61 may be, for example, a memory system or a computer system. The first device 62 may be a processor, and the second device 66 may be a memory. The first device 62 and the second device 66 may communicate via the bus 64. The first and second devices 62, 66 may include capacitors 10, constructed according to the teaching of the present invention.

[0046] The present invention also includes a method of forming structures and devices, such as capacitors. The method includes forming a first electrode selected from a group consisting of transition metals, conductive metal-oxides, and alloys thereof. The method also includes forming a second electrode and forming a dielectric between the first and second electrodes. The method includes many variations, as described in the teachings hereinabove.

[0047] Those of ordinary skill in the art will recognize that many modifications and variations of the present invention may be implemented. For example, one of the interconnects 22, 42 may be omitted and the corresponding conductor may be left to "float". The foregoing description and the following claims are intended to cover all such modifications and variations.

1-80. (canceled)

81. A structure comprising:

a first electrode made of a material selected from the group consisting of transition metals, conductive metal-oxides, alloys thereof, and combinations thereof, wherein the first electrode comprises a first non-smooth surface, and wherein the first non-smooth surface comprises a concave hemispherical grain; and

a dielectric in contact with the first electrode and a surface of a substrate assembly.

82. The structure of claim 81, wherein the first electrode further comprises a second non-smooth surface, the second non-smooth surface comprising a convex hemispherical grain.

83. The structure of claim 81, wherein the dielectric includes a vertical portion having at least one non-smooth surface.

84. The structure of claim 81, wherein the dielectric comprises a non-smooth surface comprising a concave hemispherical grain.

85. The structure of claim 84, wherein the dielectric comprises a second non-smooth surface comprising a convex hemispherical grain.

86. The structure of claim 81, wherein the first electrode is set within a recess defined by the substrate assembly.

87. The structure of claim 81, further comprising an interconnect recessed in the substrate assembly, and wherein the first electrode is formed on the interconnect.

88. A structure comprising:

a first electrode made of a material selected from the group consisting of transition metals, conductive metal-

oxides, alloys thereof, and combinations thereof, wherein the first electrode comprises a first non-smooth surface, and wherein the first non-smooth surface comprises a convex hemispherical grain; and

a dielectric in contact with the first electrode and a surface of a substrate assembly.

89. The structure of claim 88, wherein the dielectric includes a vertical portion having at least one non-smooth surface.

90. The structure of claim 88, wherein the dielectric comprises a non-smooth surface comprising a concave hemispherical grain.

91. The structure of claim 91, wherein the dielectric comprises a second non-smooth surface comprising a convex hemispherical grain.

92. The structure of claim 88, wherein the first electrode is set within a recess defined by the substrate assembly.

93. The structure of claim 88, further comprising an interconnect recessed in the substrate assembly, and wherein the first electrode is formed on the interconnect.

94. A structure comprising:

a surface of a substrate assembly defining an opening;

a non-smooth mold positioned at least partially within the opening;

a first electrode positioned on top of the non-smooth mold, the first electrode made of a material selected from the group consisting of transition metals, conductive metal-oxides, alloys thereof, and combinations thereof.

95. The structure of claim 94, wherein the non-smooth mold comprises HSG polysilicon.

96. The structure of claim 94, wherein a non-smooth surface of the first electrode conforms to the non-smooth mold.

97. A structure comprising:

a substrate assembly; and

a first electrode positioned on the substrate assembly, the first electrode made of a material selected from the group consisting of transition metals, conductive metal-oxides, alloys thereof, and combinations thereof, wherein the first electrode comprises a first surface comprising a concave hemispherical grain and a second surface comprising a convex hemispherical grain.

98. The structure of claim 97, further comprising a dielectric in contact with the first electrode.

99. The structure of claim 98, wherein the first electrode is set within a recess defined by the substrate assembly.

100. The structure of claim 97, wherein the first surface of the first electrode and at least a portion of the second surface of the first electrode do not contact the substrate assembly.

* * * * *