



(86) Date de dépôt PCT/PCT Filing Date: 1997/09/04
(87) Date publication PCT/PCT Publication Date: 1998/03/26
(45) Date de délivrance/Issue Date: 2014/04/29
(85) Entrée phase nationale/National Entry: 1999/03/22
(86) N° demande PCT/PCT Application No.: US 1997/015544
(87) N° publication PCT/PCT Publication No.: 1998/012761
(30) Priorité/Priority: 1996/09/23 (US08/717,979)

(51) Cl.Int./Int.Cl. *H01M 4/58* (2010.01),
C01B 25/45 (2006.01), *H01M 10/052* (2010.01),
H01M 4/136 (2010.01), *H01M 4/1397* (2010.01)

(72) Inventeurs/Inventors:
BARKER, JEREMY, US;
SAIDI, MOHAMED-YAZID, US

(73) Propriétaire/Owner:
VALENCE TECHNOLOGY, INC., US

(74) Agent: OSLER, HOSKIN & HARCOURT LLP

(54) Titre : PHOSPHATES CONTENANT DU LITHIUM ET A LITHIUM INTERCALE, UTILES EN TANT QUE MATERIAUX D'ELECTRODE POSITIVE OU NEGATIVE DANS UN ACCUMULATEUR ELECTRIQUE AU LITHIUM
(54) Title: LITHIUM-CONTAINING, LITHIUM-INTERCALATING PHOSPHATES AND THEIR USE AS THE POSITIVE OR NEGATIVE ELECTRODE MATERIAL IN A LITHIUM SECONDARY BATTERY

(57) **Abrégé/Abstract:**

The invention provides an electrochemical cell which comprises a first electrode and a second electrode which is a counter electrode to said first electrode. The first electrode comprises a phosphorous compound of the nominal general formula $\text{Li}_3\text{E}'_a\text{E}''_b(\text{PO}_4)_3$, desirably at least one E is a metal; and preferably, $\text{Li}_3\text{M}'\text{M}''(\text{PO}_4)_3$. E' and E'' are the same or different from one another. Where E' and E'' are the same, they are preferably metals having more than one oxidation state. Where E' and E'' are different from one another, they are preferably selected from the group of metals where at least one of E' and E'' has more than one oxidation state. More specifically, there is disclosed a rechargeable lithium battery comprising an electrode, preferably the positive electrode, formed from a lithium intercalating metal phosphate of the type $\text{M}'\text{M}''(\text{PO}_4)_3$ where M', M'' are metals selected from Ti, Fe, V, Al, Mo, and Cr.



WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

(51) International Patent Classification ⁶ : H01M 4/58, 4/52, 10/40		A1	(11) International Publication Number: WO 98/12761
			(43) International Publication Date: 26 March 1998 (26.03.98)
(21) International Application Number: PCT/US97/15544 (22) International Filing Date: 4 September 1997 (04.09.97) (30) Priority Data: 08/717,979 23 September 1996 (23.09.96) US (60) Parent Application or Grant (63) Related by Continuation US 08/717,979 (CON) Filed on 23 September 1996 (23.09.96) (71) Applicant (for all designated States except US): VALENCE TECHNOLOGY, INC. [US/US]; 301 Conestoga Way, Henderson, NV 89015 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): BARKER, Jeremy [GB/US]; 1700 North Green Valley Parkway #4021, Henderson, NV 89014 (US). SAIDI, Mohamed-Yazid [DZ/US]; 1800 N. Green Valley Parkway #424, Henderson, NV 89014 (US).		(74) Agents: DESCHERE, Linda, M. et al.; Barnes, Kisselle, Raisch, Choate, Whittemore & Hulbert, P.C., 3500 Penobscot Building, 645 Griswold Street, Detroit, MI 48226 (US). (81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	

(57) Abstract

the same or different from one another. Where E' and E'' are the same, they are preferably metals having more than one oxidation state. Where E' and E'' are different from one another, they are preferably selected from the group of metals where at least one of E' and E'' has more than one oxidation state. More specifically, there is disclosed a rechargeable lithium battery comprising an electrode, preferably the positive electrode, formed from a lithium intercalating metal phosphate of the type $M'M''(PO_4)_3$ where M', M'' are metals selected from Ti, Fe, V, Al, Mo, and Cr.

LITHIUM-CONTAINING, LITHIUM-INTERCALATING PHOSPHATES AND THEIR USE AS THE
POSITIVE OR NEGATIVE ELECTRODE MATERIAL IN A LITHIUM SECONDARY BATTERY

5

Field of the Invention

This invention relates to improved materials
usable as electrode active materials, method for making
10 such improved materials, and electrodes formed from it for
electrochemical cells in batteries.

Background of the Invention

15 Lithium batteries are prepared from one or more
lithium electrochemical cells containing electrochemically
active (electroactive) materials. Such cells typically
include an anode (negative electrode), a cathode (positive
electrode), and an electrolyte interposed between spaced
20 apart positive and negative electrodes. Batteries with
anodes of metallic lithium and containing metal
chalcogenide cathode active material are known. The
electrolyte typically comprises a salt of lithium dissolved
in one or more solvents, typically nonaqueous (aprotic)
25 organic solvents. Other electrolytes are solid
electrolytes typically called polymeric matrixes that
contain an ionic conductive medium, typically a metallic
powder or salt, in combination with a polymer that itself
may be ionically conductive which is electrically
30 insulating. By convention, during discharge of the cell,
the negative electrode of the cell is defined as the anode.
Cells having a metallic lithium anode and metal
chalcogenide cathode are charged in an initial condition.
During discharge, lithium ions from the metallic anode pass
35 through the liquid electrolyte to the electrochemical

WO 98/12761

PCT/US97/15544

active (electroactive) material of the cathode whereupon they release electrical energy to an external circuit.

It has recently been suggested to replace the lithium metal anode with an intercalation anode, such as a lithium metal chalcogenide or lithium metal oxide. Carbon anodes, such as coke and graphite, are also intercalation materials. Such negative electrodes are used with lithium-containing intercalation cathodes, in order to form an electroactive couple in a cell. Such cells, in an initial condition, are not charged. In order to be used to deliver electrochemical energy, such cells must be charged in order to transfer lithium to the anode from the lithium-containing cathode. During discharge the lithium is transferred from the anode back to the cathode. During a subsequent recharge, the lithium is transferred back to the anode where it reintercalates. Upon subsequent charge and discharge, the lithium ions (Li^+) are transported between the electrodes. Such rechargeable batteries, having no free metallic species are called rechargeable ion batteries or rocking chair batteries. See U.S. Patent Numbers 5,418,090; 4,464,447; 4,194,062; and 5,130,211.

Preferred positive electrode active materials include LiCoO_2 , LiMn_2O_4 , and LiNiO_2 . The cobalt compounds are relatively expensive and the nickel compounds are difficult to synthesize. A relatively economical positive electrode is LiMn_2O_4 , for which methods of synthesis are known, and involve reacting generally stoichiometric quantities of a lithium-containing compound and a manganese containing compound. The lithium cobalt oxide (LiCoO_2), the lithium manganese oxide (LiMn_2O_4), and the lithium nickel oxide (LiNiO_2) all have a common disadvantage in that the charge capacity of a cell comprising such cathodes suffers a significant loss in capacity. That is, the initial capacity available (amp hours/gram) from LiMn_2O_4 ,

WO 98/12761

PCT/US97/15544

LiNiO₂, and LiCoO₂, is less than the theoretical capacity because less than 1 atomic unit of lithium engages in the electrochemical reaction. Such an initial capacity value is significantly diminished during the first cycle operation and such capacity further diminishes on every successive cycle of operation. The specific capacity for LiMn₂O₄ is at best 148 milliamp hours per gram. As described by those skilled in the field, the best that one might hope for is a reversible capacity of the order of 110 to 120 milliamp hours per gram. Obviously, there is a tremendous difference between the theoretical capacity (assuming all lithium is extracted from LiMn₂O₄) and the actual capacity when only 0.8 atomic units of lithium are extracted as observed during operation of a cell. For LiNiO₂ and LiCoO₂ only about 0.5 atomic units of lithium is reversibly cycled during cell operation. Many attempts have been made to reduce capacity fading, for example, as described in U.S. Patent No. 4,828,834 by Nagaura et al. However, the presently known and commonly used, alkali transition metal oxide compounds suffer from relatively low capacity. Therefore, there remains the difficulty of obtaining a lithium-containing chalcogenide electrode material having acceptable capacity without disadvantage of significant capacity loss when used in a cell.

25

Summary of the Invention

The invention provides novel lithium-containing phosphate materials having a high proportion of lithium per formula unit of the material. Upon electrochemical interaction, such material deintercalates lithium ions, and is capable of reversibly cycling lithium ions. The invention provides a rechargeable lithium battery which comprises an electrode formed from the novel lithium-containing phosphates, preferably lithium-metal-phosphates. Methods for making the novel phosphates and methods for

35

using such phosphates in electrochemical cells are also provided. Accordingly, the invention provides a rechargeable lithium battery which comprises an electrolyte; a first electrode having a compatible active material; and a second electrode comprising the novel phosphate materials. The novel materials, preferably used as a positive electrode active material, reversibly cycle lithium ions with the compatible negative electrode active material. Desirably, the phosphate has a proportion in excess of 2 atomic units of lithium per formula unit of the phosphate, and upon electrochemical interaction the proportion of lithium ions per formula unit become less. Desirably, the lithium-containing phosphate is represented by the nominal general formula $\text{Li}_a\text{E}'_b\text{E}''_c(\text{PO}_4)_3$, where in an initial condition "a" is about 3, and during cycling varies as $0 < a < 3$; b and c are both greater than 0 and b plus c is about 2. In one embodiment, elements E' and E'' are both transition metals and are the same. In another embodiment, E' and E'' are different from one another with at least one being a transition metal. At least one of E' and E'' is an element capable of an oxidation state higher than that initially present in the lithium phosphate compound. Correspondingly, at least one of E' and E'' has more than one oxidation state. Both E' and E'' may have more than one oxidation state and both may be oxidizable from the state initially present in the phosphate compound. Preferably, the metal phosphate is represented by the nominal general formula $\text{Li}_3\text{E}'_b\text{E}''_c(\text{PO}_4)_3$, where E' and E'' are each metals, b plus c is about 2, and E' and E'' satisfy the conditions of oxidizability and oxidation state given for E' and E''. Many combinations satisfying the above conditions are possible. For example, in one embodiment E' and E'' are each transition metals. In still another embodiment where the formulation $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$ comprises two different metals, E' and E'', one metal E' may be a non-transition metal. In another embodiment, such non-transition metal has only one oxidation state and is nonoxidizable from its oxidation state in the final compound $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$. In this case, E' may be selected from metals, such as aluminum, magnesium, calcium, potassium, and other Groups I and II metals. In this case, E'' is a metal having more than one oxidation state, and is oxidizable from its oxidation state in the end product, and E'' is preferably a transition metal. In another embodiment, the non-transition metal has more than one oxidation state.

Metallic elements include metals and semi-metals, such as semi-conductors, including silicon (Si), tellurium (Te), selenium (Se), antimony (Sb), and arsenic (As). The metal phosphates are alternatively represented by the nominal general formula $\text{Li}_{3-x}\text{E}'\text{E}''(\text{PO}_4)_3$ ($0 \leq x \leq 3$), signifying capability to deintercalate and reinsert lithium. $\text{Li}_{3-x}\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$ signifies that the relative amount of E' and E'' may vary, with $0 < y < 2$, some E' and E'' are each present. The same criteria as to the values of x and y apply to $\text{Li}_{3-x}\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$.

The active material of the counter electrode is any material compatible with the lithium-metal-phosphate of the invention. Where the lithium-metal-phosphate is used as a positive electrode active material, metallic lithium may be used as the negative electrode active material where lithium is removed and added to the metallic negative electrode during use of the cell. The negative electrode is desirably a nonmetallic intercalation compound. Desirably, the negative electrode comprises an active material from the group consisting of metal oxide, particularly transition metal oxide, metal chalcogenide, carbon, graphite, and mixtures thereof. It is preferred that the anode active material comprises graphite. The lithium-metal-phosphate of the invention may also be used as a negative electrode material.

The present invention resolves the capacity problem posed by widely used cathode active material. It has been found that the capacity of cells having the preferred $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$, active material of the invention are greatly improved, for example, over LiMn_2O_4 . Optimized cells containing lithium-metal-phosphates of the invention potentially have performance greatly improved over all of the presently used lithium metal oxide compounds. Advantageously, the novel lithium-metal-phosphate compounds of the invention are relatively easy to make, and readily adaptable to commercial production, are relatively low in cost, and have very good specific capacity.

Aspects, features, and advantages of the invention include an improved electrochemical cell or battery based on lithium which has improved charging and discharging characteristics, a large discharge

capacity, and which maintains its integrity during cycling. Another object is to provide a cathode active material which combines the advantages of large discharge capacity and with relatively lesser capacity fading. It is also an aspect of the present invention to provide positive electrodes which can be manufactured more economically and relatively more conveniently, rapidly, and safely than present positive electrodes which react readily with air and moisture. Another aspect is to provide a method for forming cathode active material which lends itself to commercial scale production providing for ease of preparing large quantities.

These and other embodiments, features, and advantages will become apparent from the following description of the preferred embodiments, claims, and accompanying drawings.

15

In one aspect of the present invention there is provided a method for operating an electrochemical cell, comprising: a. providing a first composition comprising an active material compound, a counter composition which does not contain lithium, and an electrolyte therebetween; b. electrochemically deintercalating lithium ions from the active material compound and transferring the ions to the counter composition to charge the cell; and then c. electrochemically removing at least a portion of the transferred lithium ions from the counter composition for reintercalation into the active material compound, whereupon electrochemical energy is obtained from the cell during discharge; and provided that: in step (a), the active material compound is represented by the nominal general formula $\text{Li}_{3-x}\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$ ($0 \leq y \leq 2$), wherein E' and E'' are the same or different from one another, wherein at least one of E' and E'' is a transition metal and at least one of E' and E'' is an element capable of an oxidation state higher than that initially present in the active material compound, and $x = 0$; and wherein after step (b) and before step (c) the active material compound is

30

represented by the nominal general formula where x is greater than 0 and less than or equal to 3; and wherein after step (c) steps (b) and (c) are repeated in sequence.

5 In another aspect of the present invention there is provided a composition of a matter having an active material represented by the nominal general formula $\text{Li}_3\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$, wherein $0 \leq y \leq 2$, E' and E'' are the same or different and are selected from metals and at least one of E' and E'' is a transition metal, and at least one of E' and E'' is an element
10 capable of an oxidation state higher than that initially present in the active material.

In yet another aspect of the present invention there is provided a battery, comprising: a first composition comprising a
15 composition active material represented by the nominal formula $\text{Li}_{3-x}\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$ ($0 \leq y \leq 2$), wherein E' and E'' are the same or different from one another, wherein at least one of E' and E'' is a transition metal and at least one of E' and E'' has more than one oxidation state; a second counter-composition comprising an
intercalation active material; and an electrolyte; wherein in a first
20 condition, $x = 0$; and wherein in a second condition $0 \leq x \leq 3$ and at least one E' and E'' has an oxidation state higher than its oxidation state in the first condition.

25 In still yet another aspect of the present invention there is provided a use of the lithium metal-phosphate compound for forming an electrode.

In still yet another aspect of the present invention there is provided a reactive composition for forming an active material
30 represented by the nominal general formula $\text{Li}_{3-x}\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$ ($0 \leq y \leq 2$), wherein E' and E'' are the same or different from one another, wherein at least one of E' and E'' is a transition metal, and at least one of E' and E'' is an element capable of an
oxidation state higher than that initially present in the active material, comprising: intermingled particles of a first metal
35 compound; particles of a lithium compound; and particles of a phosphate salt compound; the compounds being in a proportion which upon reaction provides the active material compound of the nominal formula proportion.

In still yet another aspect of the present invention there is provided a method of making a lithium-vanadium-phosphate compound, comprising the steps of: forming a mixture of a lithium-containing compound, at least one vanadium oxide compound, and a phosphoric acid-containing compound; and heating the mixture at a temperature and for a time sufficient to form a lithium-vanadium-phosphate compound.

In still yet another aspect of the present invention there is provided a method of making a compound represented by the nominal formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$, comprising the steps of: forming a mixture of a lithium-containing compound, at least one vanadium oxide compound, and a phosphoric acid-containing compound, in proportions to provide a compound represented by the nominal

formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$; and heating the mixture at a temperature and for a time sufficient to form the compound.

In still yet another aspect of the present invention
5 there is provided a compound represented by the nominal formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$, made by a process comprising the steps of: forming a mixture of a lithium-containing compound, at least one vanadium oxide compound, and a phosphoric acid-containing compound, in proportions to provide a compound represented by the nominal
10 formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$; and heating the mixture at a temperature and for a time sufficient to form the compound.

WO 98/12761

PCT/US97/15544

Brief Description of the Drawings

Figure 1 is an EVS (Electrochemical Voltage Spectroscopy) voltage/capacity profile for a cell embodying the lithium-metal-phosphate material of the invention $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ in combination with a lithium metal counter electrode in an electrolyte comprising ethylene carbonate (EC) and dimethyl carbonate (DMC) in a weight ratio of 2:1 and including a 1 molar concentration of LiPF_6 salt. The lithium-metal-phosphate containing electrode and the lithium metal counter electrode are maintained spaced apart by a separator of fiber glass which is interpenetrated by the solvent and the salt. The conditions are ± 10 mV steps, between about 3.0 and 4.2 volts, and the critical limiting current density is less than or equal to 0.05 mA/cm^2 .

Figure 2 is an EVS differential capacity plot for the cell as described in connection with Figure 1.

Figure 3 is a voltage/capacity plot of $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ cycled with a lithium metal anode using constant current cycling at ± 0.2 milliamps per square centimeter in a range of 3.0 to 4.3 volts.

Figure 4 is a two-part graph based on multiple constant current cycling of $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ cycled with a lithium metal anode using the electrolyte as described in connection with Figure 1 and cycled, charge and discharge at ± 0.25 milliamps per square centimeter, 3.0 to 4.2 volts. In the two-part graph, Figure 4A shows the excellent rechargeability of the lithium-metal-phosphate/lithium metal cell. Figure 4B shows the excellent cycling and capacity of the cell.

Figure 5 is an illustration of a cross section of a thin battery or cell embodying the invention.


Figure 6 shows the results of an x-ray diffraction analysis of the $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ prepared according to the invention using $\text{CuK}\alpha$ radiation, $\lambda = 1.5418 \text{ \AA}$.

Detailed Description of the Preferred Embodiments


10

The present invention provides lithium-containing phosphate materials, preferably lithium-metal-phosphates, which are usable as electrode active materials, for the first time, as a source of lithium (Li^+) ions. Upon extraction of x lithium ions from the preferred $\text{Li}_{3-x}\text{E}'\text{E}''(\text{PO}_4)_3$ significant capacity is achieved. Such specific capacity achieved from preferred lithium-metal-phosphates is far in excess of the specific capacity from $\text{Li}_1\text{Mn}_2\text{O}_4$ ($\text{Li}_{1-x}\text{Mn}_2\text{O}_4$) an example on a currently used cathode active material. In the method of the invention, electrochemical energy is provided by deintercalation of lithium from lithium-metal-phosphates ($\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$). For example, when lithium is removed per formula unit of the $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$, vanadium is oxidized from vanadium III to vanadium IV or V in $\text{Li}_3\text{E}_2(\text{PO}_4)_3$, $\text{E}_2 = \text{V}_2$.

When 1 lithium is removed per formula unit of the lithium vanadium phosphate, V^{III} is oxidized to V^{IV} . The electrochemical reaction is as shown below:



Further extraction is possible according to:



WO 98/12761

PCT/US97/15544

Note that the average oxidation state of vanadium is +4 (IV). It is thought that both of the vanadium atomic species carry a +4 charge, it is less likely that one of the vanadium species carries a +3 charge and the other a +5 charge. Advantageously, still further oxidation is possible with the removal of the final lithium ion according to the Equation:



10

In the overall equation $\text{Li}_3\text{V}^{+3}\text{V}^{+3}(\text{PO}_4)_3 \rightarrow \text{V}^{+4}\text{V}^{+5}(\text{PO}_4)_3 + 3\text{Li}^+ + 3\text{e}^-$, this material has a theoretical capacity of 197 milliamp hours per gram upon electrochemical oxidation as per the reaction shown herein. The electrochemical extraction of lithium from $\text{Li}_3\text{M}'\text{M}''(\text{PO}_4)_3$ is heretofore not known to have been described. Similarly, a mixed metal compound, such as $\text{Li}_3\text{FeV}(\text{PO}_4)_3$, has two oxidizable elements. In contrast, $\text{Li}_3\text{AlTm}(\text{PO}_4)_3$ has one oxidizable metal, the transition metal (Tm).

20

Figures 1 through 4 which will be described more particularly below shows capacity in actual use where the lithium-metal-phosphate cathode (positive electrode) of the invention was tested in a cell comprising a lithium metal counter electrode (negative electrode) and an EC:DMC-LiPF₆ electrolyte, with operation between about 3.0 and 5.0 volts versus L/Li⁺ where lithium is cycled between the positive electrode and the negative electrode.

30

In another aspect, the invention provides a lithium ion battery which comprises an electrolyte; a negative electrode having an intercalation active material; and a positive electrode comprising a lithium-metal-phosphate active material characterized by an ability to deintercalate lithium ions for intercalation into the negative electrode active material. The lithium-metal-

35

phosphate is desirably represented by the nominal general formula $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$. In one aspect, the metals E' and E'' are the same and in another aspect, the metals E' and E'' are different. Desirably, the phosphate is the compound $\text{Li}_3\text{E}_2(\text{PO}_4)_3$ where E is a transition metal, and
5 E is most desirably V, Fe, Sr, and Mn. The lithium-metal-phosphate is preferably a compound represented by the nominal general formula $\text{Li}_{3-x}\text{V}_2(\text{PO}_4)_3$, signifying the preferred composition and its capability to deintercalate lithium. The present invention resolves a capacity problem posed by conventional cathode active materials. Such problems
10 with conventional active materials are described by Tarascon in U.S. Patent No. 5,425,932, using LiMn_2O_4 as an example. Similar problems are observed with LiCoO_2 , LiNiO_2 , and many, if not all, lithium metal chalcogenide materials. The present invention demonstrates that such capacity problems are overcome and greater proportion of potential in
15 the cathode active material is utilizable providing a great improvement over conventional active materials.

The positive electrode active material in an initial condition is represented by the molecular formula $\text{Li}_{3-x}\text{E}'\text{E}''(\text{PO}_4)_3$. When
20 used in a cell it deintercalates a quantity of x lithium ions for intercalation into the negative electrode, where the amount of x ions deintercalated is greater than 0 and less than or equal to 3. Accordingly, during cycling, charge and discharge, the value of x varies as x greater than or equal to 0 and less than or equal to 3.

25 Positive electrode lithium-metal-phosphate active material was prepared and tested in electrochemical cells and the results are reported in Figures 1 through 4. A typical cell configuration will be described with reference to Figure 5.

WO 98/12761

PCT/US97/15544

A description of the electrochemical cell or battery which uses the novel active material of the invention will now be described. By convention, an electrochemical cell comprises a first electrode, a counter electrode which reacts electrochemically with the first electrode, and an electrolyte which is capable of transferring ions between the electrodes. A battery refers to one or more electrochemical cells. Referring to Figure 5, an electrochemical cell or battery 10 has a negative electrode side 12, a positive electrode side 14, and an electrolyte/separator 16 therebetween. The negative electrode is the anode during discharge, and the positive electrode is the cathode during discharge. The negative electrode side includes current collector 18, typically of nickel, iron, stainless steel, and copper foil, and negative electrode active material 20. The positive electrode side includes current collector 22, typically of aluminum, nickel, and stainless steel, and such foils may have a protective conducting coating foil, and a positive electrode active material 24. The electrolyte/separator 16 is typically a solid electrolyte, or separator and liquid electrolyte. Solid electrolytes typically referred to as polymeric matrixes which contain an ionic conductive medium. Liquid electrolytes typically comprise a solvent and an alkali metal salt which form an ionically conducting liquid. In this latter case, the separation between the anode and cathode is maintained, for example, by a relatively inert layer of material such as glass fiber. The electrolyte is not an essential feature of the invention. Essentially, any lithium ion containing conducting electrolyte may be used, that is stable up to 4.5 volts or more. Essentially any method may be used to maintain the positive and negative electrodes spaced apart and electrically insulated from one another in the cell. Accordingly, the essential features of the cell are the positive electrode, a negative electrode electrically

insulated from the positive electrode, and an ionically conducting medium between the positive and negative electrodes. Examples of a suitable separator/electrolyte, solvents, and salts are described in U.S. Patent No. 4,830,939 showing a solid matrix containing an ionically conducting liquid with an alkali metal salt where the liquid is an aprotic polar solvent; and U.S. Patent Numbers 4,935,317; 4,990,413; 4,792,504; and 5,037,712.

Electrodes of the invention are made by mixing a binder, the active material, and carbon powder (particles of carbon). The binder desirably is a polymer. A paste containing the binder, active material, and carbon, is coated onto a current collector.

Positive Electrode

A positive electrode containing the lithium phosphate compound, preferably lithium-metal-phosphate, active material of the invention is prepared by the following method. For the positive electrode, the content was as follows: 50 to 90 percent by weight active material ($\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$); 5 to 30 percent carbon black as the electrically conductive diluent; and 3 to 20 percent binder. The stated ranges are not critical. The amount of active material may range from 25 to 85 weight percent. The formation of each electrode will now be described. The positive electrode was prepared from mixtures of lithium-metal-phosphate (active material) and EPDM (ethylene propylene diene monomer) as the binder, Shawinigan Black[®] was used as the carbon powder conductive diluent. The carbon powder conductive diluent is used to enhance electronic conductivity of the lithium-metal-phosphate. Shawinigan Black[®], available from Chevron Chemical Company,

WO 98/12761

PCT/US97/15544

San Ramone, California, has a BET average surface area of about 70 ± 5 square meters per gram. Other suitable carbon blacks are sold under the designation Super P™ and Super S™ available from MMM, a subsidiary of Sedema, which carbons have BET surface areas of about 65 ± 5 square meters per gram. (MMM has its headquarters in Brussels, Belgium.) Examples of suitable polymeric binders include EPDM (ethylene propylene diene termonomers), PVDF (polyvinylidene difluoride), ethylene acrylic acid copolymer, EVA (ethylene vinyl acetate copolymer), copolymer mixtures, and the like. It is desirable to use either PVDF available from Polysciences Corporation with a molecular weight of 120,000 or EPDM available from Exxon Corporation and sold under the designation EPDM 2504™. EPDM is also available from The Aldrich Chemical Company. The description of carbon powders and binders constitute representative examples and the invention is not limited thereby. For example, other carbon powders are available from Exxon Chemicals, Inc., Chicago, Illinois under the trade name Ketjen Black EC 600 JD® and polyacrylic acid of average molecular weight 240,000 is commercially available from BF Goodrich, Cleveland, Ohio under the name Good-Rite K702™. The positive electrodes of the invention comprised mixtures of the lithium-metal-phosphate active material, the binder (EPDM), and the carbon particles (Shawinigan Black®). These were mixed and blended together with a solvent. Xylene is a suitable solvent. The mixture was then coated onto an aluminum foil current collector to achieve a desired thickness for the final electrode.

30

Electrolyte

The electrolyte used to form the completed cell is preferably a combination of EC/DMC when a carbon counter electrode is used. That is, ethylene carbonate (EC) and dimethyl carbonate (DMC). The ratio of EC:DMC was about

35

WO 98/12761

PCT/US97/15544

2:1 by weight. Generally, when a lithium metal anode is used, the choice of an electrolyte is less restricted. It may be the EC:DMC in a ratio of 2:1 by weight or, for example, EC:PC (propylene carbonate) in 50:50 by weight ratio. In any case, the preferred salt is 1 molar LiPF_6 . Positive and negative electrodes are maintained in a separated condition using a fiber glass layer. Such separation can also be achieved using a layer of Celgard™. Hoechst - Celanese Corp., Celgard 2400™, porous polypropylene, 25 microns thick.

Negative Electrode

The electrochemical cell used with the positive electrode and electrolyte may contain one of a variety of negative electrode active materials. In one embodiment, the negative electrode may be metallic lithium. In more desirable embodiments, the negative electrode is an intercalation active material, such as, metal oxides and graphite. When a metal oxide active material is used, the components of the electrode are the metal oxide, electrically conductive carbon black, and binder in the proportions as described above for the positive electrode. Representative, but not limiting, examples include coke, graphite, WO_3 , Nb_2O_5 , and V_6O_{13} . In a preferred embodiment, the negative electrode active material is graphite particles. For test purposes, for determining capacity of a positive electrode, test cells were fabricated using the lithium metal active material. When test cells are formed such as to be used as batteries, a nonmetallic intercalation graphite electrode is preferred. The preferred graphite-based negative electrode comprises about 80 to 95 percent by weight graphite particles, and more preferably about 90 percent by weight with the balance constituted by a binder. Preferably, the anode is prepared from a graphite slurry as follows. A polyvinylidene

WO 98/12761

PCT/US97/15544

difluoride (PVDF) solution is prepared by mixing 300 grams of 120,000 MW PVDF (PolyScience) in 300 ml of dimethyl formamide. The mixture was stirred for 2 to 3 hours with a magnetic stirrer to dissolve all of the PVDF. The PVDF functions as a binder for the graphite in the anode. Next, a PVDF/graphite slurry is prepared by first adding 36 grams of graphite (SFG-15) into about 38.5 grams of the PVDF solution. The mixture is homogenized with a commercial homogenizer or blender. (For example, Tissue Homogenizer System from Cole-Parmer Instrument Co., Niles, IL). The viscosity of the slurry is adjusted to about 200 cp with additional PVDF solution. The slurry is coated onto a bare copper foil by standard solvent casting techniques, such as by a doctor blade type coating. (Alternatively, the slurry can be coated onto a copper foil having a polymeric adhesion promoter layer, described above.) In preparing the slurry, it is not necessary to grind or dry the graphite, nor is it necessary to add conductive carbon black to the graphite anode formulation. Finally, the electrodes are dried at approximately 150°C for 10 hours to remove residual water prior to making the electrochemical cells.

In one embodiment, the negative electrode has the lithium-metal-phosphate compound as the active material. In the case of $\text{Li}_3\text{V}^{+3}\text{V}^{+3}(\text{PO}_4)_3$, the V^{+3} would theoretically be reduced to V^{+2} . For $\text{Li}_3\text{Fe}^{+3}\text{Fe}^{+3}(\text{PO}_4)_3$, the same activity is theoretically possible, since Fe^{+2} is a stable and common oxidation state for Fe. This should allow two more lithium ions to be inserted. That is, $\text{Li}_{3+x}\text{Fe}_2(\text{PO}_4)_3$, x is about 2.

Various methods for fabricating electrochemical cells and for forming electrode components are described herein. The invention is not, however, limited by any particular fabrication method as the novelty lies in the unique positive electrode material itself and combination of positive and negative electrode materials. Accordingly,

additional methods for preparing electrochemical cells and batteries may be selected and are described in the art, for example, in U.S. Patent Nos. 5,435,054 (Tonder & Shackle); 5,300,373 (Shackle); 5,262,253 (Golovin); 4,668,595; and 4,830,939 (Lee & Shackle).

5

In one embodiment, the present invention provides a method of preparing a compound of the nominal general formula $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$. The method comprises providing a lithium-containing compound, one or more metal oxide compounds, and a phosphoric acid containing compound. Preferably, the lithium-containing compound is a lithium salt and the phosphoric acid compound is a phosphoric acid salt. The lithium compound, one or more metal oxide compounds, and phosphoric acid based compound are mixed together in a proportion which provides the stated nominal general formula. Such precursor compounds are intimately mixed and then reacted together where the reaction is initiated by heat and is preferably conducted in a nonoxidizing, reducing atmosphere, whereby the lithium, metal from a metal oxide, and phosphate combine to form the $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$. Before reacting the compounds, the particles are intermingled to form an essentially homogeneous powder mixture of the precursors. Such intermingling is preferably conducted by forming a wet mixture using a volatile solvent and then the intermingled particles are pressed together in pellet form in grain-to-grain contact with one another. Although it is desired that the precursor compounds be present in a proportion which provides the stated general formula of the product, the lithium compound may be present in an excess amount on the order of 5 percent excess lithium compared to a stoichiometric mixture of the precursors. Although a number of lithium compounds are available as precursors, such as lithium acetate, lithium hydroxide, and lithium nitrate, lithium carbonate (Li_2CO_3) is preferred for the solid state reaction. The aforesaid precursor compounds are generally crystals, granules, and powders and are generally referred to as being in particle form. Although many types of phosphate salts are known, it is preferred to use ammonium phosphate ($(\text{NH}_4)_2\text{HPO}_4$). In the case where the compound of the formulation $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$ is desired where E' and E'' are the same metal, a transition metal, such as vanadium, a suitable precursor is vanadium pentoxide (V_2O_5).

The starting materials are available from a number of sources. The following are typical. Vanadium pentoxide of the

general formula V_2O_5 is obtainable from any number of suppliers including Kerr McGee, Johnson Matthey, or Alpha Products of Davers, Massachusetts. It had a melting point of about 690°C , decomposed at 1750°C , a particle size of less than about 60 mesh (250 microns) and
 5 had a specific gravity of 3.357 grams per cc at 18°C . It was a yellow-red crystalline powder. Vanadium pentoxide has a CAS number of 1314-62-1. Alternatively, the vanadium pentoxide may be prepared from ammonium metavanadate (NH_4VO_3). The ammonium metavanadate is heated to a temperature of about 400°C to about 450°C to decompose it to
 10 vanadium pentoxide (V_2O_5). Processes for production of vanadium pentoxide are described in U.S. Patent Numbers 3,728,442, 4,061,711 and 4,119,707.

In another embodiment, for the formation of $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$,
 15 where E' and E'' are different from one another and are metals, preferably transition metals, one may select two different metal oxide powders, such as titanium oxide (TiO_2), vanadium oxide (V_2O_5), iron oxide (FeO , Fe_2O_3), chromium oxide (CrO_2 , CrO , Cr_2O_3), manganese oxide (MnO_2 , Mn_3O_4), and the like. In still another embodiment where
 20 the formulation $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$ comprises two different metals, E' and E'' , one metal E' may be selected from non-transition metals and semi-metals. In another embodiment, non-transition metal has only one oxidation state and is nonoxidizable from its oxidation state in the final compound $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$. In this case, E' may be selected from
 25 metals, such as aluminum and magnesium, calcium, potassium, and other Groups I and II metals, alkali Group I, and semi-metals. Semi-metals are located in the Periodic Table on the right hand side and roughly separate the nonmetals from metals, as is well known in the art. In this case, E'' is a metal having more than one oxidation state, and is
 30 oxidizable from its oxidation state in the end product, and E'' is preferably a transition metal. Examples are $\text{Li}_3\text{KCr}(\text{PO}_4)_3$ and $\text{Li}_3\text{KMo}(\text{PO}_4)_3$, where the transition metal (Tm) is, respectively, chromium and molybdenum.

35 Example I

A preferred procedure for forming the $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$ compound active material will now be described. The method for making
 40 $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$ will be illustrated by formation of $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ ($\text{Li}_3\text{E}_2(\text{PO}_4)_3$). The basic procedure comprised conducting a reaction

between a lithium compound, preferably lithium carbonate (Li_2CO_3), a metal oxide, preferably vanadium pentoxide (V_2O_5), and a phosphoric acid derivative, preferably the phosphoric acid ammonium acid salt, ammonium phosphate, $\text{NH}_4\text{H}_2(\text{PO}_4)_3$ or $(\text{NH}_4)_2\text{H}(\text{PO}_4)_3$. Each of the precursor
5 starting materials are available from a number of chemical outfits including Aldrich Chemical Company and Fluka. The $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ was prepared with approximately a stoichiometric mixture of Li_2CO_3 , V_2O_5 , and $(\text{NH}_4)_2(\text{HPO}_4)$. However, a 5 percent excess of lithium (as lithium carbonate) was used to minimize any lithium loss as (Li_2O) . The
10 precursor materials were initially intimately mixed and ground for about 30 minutes

WO 98/12761

PCT/US97/15544

in a methanol solution. The intimately mixed compounds were then dried and pressed into pellets. Reaction was conducted by heating in an oven at a preferred ramped heating rate of 1°C per minute up to a temperature of about 5 725°C, and held at 725°C for about 12 hours to decompose the carbonate. Then heating continued at the same ramp rate (1°C per minute) up to a temperature of about 875°C. The mixture was held at this temperature for about 24 hours. The entire reaction was conducted in a reducing 10 atmosphere under flowing pure hydrogen gas. The flow rate will depend upon the size of the oven and the quantity needed to maintain a reducing atmosphere. Based on the size of the oven used in this example a flow rate of 25 cubic centimeters per minute was used. The oven was 15 permitted to cool down at the end of the 24 hour period, where cooling occurred at a rate of about 3°C per minute. Then the entire procedure was repeated once again for a further 24 hours. The repeated steps were also conducted under reducing atmosphere. Although hydrogen gas was 20 selected to provide the reducing atmosphere, other means for obtaining the reducing atmosphere may be used.

The general aspects of the above synthesis route are applicable to a variety of starting materials. For 25 example, LiOH and LiNO₃ salts may replace Li₂CO₃ as the source of lithium. In this case, the temperature for the first step will vary due to the differing melting points, 450°C for LiOH and 700°C for LiNO₃. The vanadium oxide V₂O₅ (V⁺⁵), combined with the oxidizing power of the phosphate 30 anion, is required to be offset by a strong reducing agent, for example, the hydrogen atmosphere. Alternatively, lower oxidation state vanadium complexes could be used, e.g., V₂O₃. This is a vanadium in the 3+ state. But because of the presence of PO₄, a certain degree of oxidation might 35 occur. Therefore, a reducing agent is used. For example, a mixture of 90:10 of Ar:H₂ can be used. The same

considerations apply to other lithium-metal- and phosphate-containing precursors. The relative oxidizing strength of the selected precursors, and the melting point of the salts will cause adjustment in the general procedure, such as, selection of the reducing agent, its reducing capability and flow rate, and the temperature of reaction.

The final product appeared lime-green in color, and its CuK α x-ray diffraction pattern contained all of the peaks expected for this material as shown in Figure 6. The x-ray diffraction was conducted using CuK α radiation, $\lambda = 1.5418 \text{ \AA}$. The pattern evident in Figure 6 is consistent with a single oxide compound $\text{Li}_3\text{V}_2(\text{PO}_4)_3$. This is evidenced by the position of the peaks in terms of the scattering angle 2θ (theta), x axis. The x-ray pattern showed no peaks due to the presence of precursor oxides indicating that the solid state reaction is essentially entirely completed. Chemical analysis for lithium and vanadium by atomic absorption spectroscopy showed, on a percent by weight basis, 5.17 percent lithium and 26 percent vanadium. This is close to the expected result of 5.11 percent lithium and 25 percent vanadium.

The chemical analysis and x-ray pattern demonstrate that the product of the invention was indeed the nominal general formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ corresponding to the more generic nominal general formula $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$. The term "nominal general formula" refers to the fact that the relative proportion of atomic species may vary slightly on the order of 2 percent to 5 percent, or more typically, 1 percent to 3 percent.

Example II

The $\text{Li}_3\text{V}_2(\text{PO}_4)_3$, prepared as described immediately above, was tested in an electrochemical cell. The positive electrode was prepared as described above under the section designated "Positive Electrode". The negative electrode was metallic lithium. The electrolyte was a

2:1 weight ratio mixture of ethylene carbonate and dimethyl carbonate within which was dissolved 1 molar LiPF_6 . The cell was cycled between about 3.0 and about 4.3 volts with performance as shown in Figures 1, 2, 3, 4A, and 4B.

5

Figure 1 shows a voltage profile of the test cell, based on the $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$ positive electrode active material of the invention, and using a lithium metal counter electrode as described in the examples. The data shown in Figure 1 is based on the Electrochemical
10 Voltage Spectroscopy (EVS) technique. Electrochemical and kinetic data were recorded using the Electrochemical Voltage Spectroscopy (EVS) technique. Such technique is known in the art as described by J. Barker in Synth, Met 28, D217 (1989); Synth. Met. 32, 43 (1989); J. Power Sources, 52, 185 (1994); and Electrochimica Acta, Vol. 40, No.
15 11, at 1603 (1995). Figure 1 clearly shows and highlights the very high and unexpected degree of reversibility of the lithium ion reactions of the $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$, specifically $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ active material of the invention. The positive electrode contained about 16.8 milligrams of the $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ active material. The total electrode
20 weight including the binder and conductive carbon diluent was about 31.2 milligrams. The positive electrode showed a performance of about 136 milliamp hours per gram on the first discharge. In Figure 1, the capacity in is essentially 136 milliamp hours per gram, and the capacity out is essentially 131 milliamp hours per gram, resulting in
25 essentially no capacity change. Figure 2 is an EVS differential capacity plot based on Figure 1. As can be seen from Figure 2, the relatively symmetrical nature of peaks indicates good electrical reversibility, there are small peak separations (charge/discharge), and good correspondence between peaks

WO 98/12761

PCT/US97/15544

above and below the zero axis. There are essentially no peaks that can be related to irreversible reactions, since all peaks above the axis (cell charge) have corresponding peaks below the axis (cell discharge), and there is essentially no separation between the peaks above and below the axis.

Figure 3 shows the results of the first constant current cycling at 0.20 milliamps per square centimeter between about 3.0 and 4.3 volts based upon about 16.8 milligrams of the $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ active material in the cathode (positive electrode). In an as prepared, as assembled, initial condition, the positive electrode active material is $\text{Li}_3\text{V}_2(\text{PO}_4)_3$. The lithium is deintercalated from the $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ during charging of the cell. When fully charged, about 2 units of lithium have been removed per formula unit of the original lithium-vanadium-phosphate. Consequently, the positive electrode active material corresponds to $\text{Li}_{3-x}\text{V}_2(\text{PO}_4)_3$ where x is greater than 0 and less than 3, and in the operation of this cell, x appears to be equal to about 2, when the cathode material is at 4.2 volts versus Li/Li^+ . In this charged condition, the electrochemical potential versus lithium of the $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ is about 4.2 volts. The deintercalation of 2 lithium from $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ resulting in the $\text{Li}_1\text{V}_2(\text{PO}_4)_3$, represents approximately 127 milliamp hours per gram corresponding to about 2.2 milliamp hours based on 16.8 milligrams active material. Next, the cell is discharged whereupon a quantity of lithium is reintercalated into the $\text{Li}_1\text{V}_2(\text{PO}_4)_3$. The average voltage is approximately 3.8 volts versus Li/Li^+ . The reintercalation corresponds to approximately 101 milliamp hours per gram proportional to the intercalation of about 1.54 atomic units of lithium. The bottom of the curve corresponds to approximately 3.0 volts.

35

Figure 4 presents data obtained by multiple constant current cycling at 0.25 milliamp hours per square centimeter of the $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ versus lithium metal counter electrode between 3.0 and 4.2 volts using the electrolyte and with electrodes formed as described earlier and with an initial specific capacity of 115 milliamp hours per gram. Figure 4 is a two part graph with Figure 4A showing the excellent rechargeability of the $\text{Li}/\text{Li}_3\text{V}_2(\text{PO}_4)_3$ cell. Figure 4B shows good cycling and capacity of the cell. The performance shown after 113 cycles is good and shows that electrode formulations of the type $\text{Li}_3\text{E}'\text{E}''(\text{PO}_4)_3$ are very desirable.

It should be noted that the formulations obtained by the method of the invention demonstrated capacity less than the achievable theoretical capacity. This is because the method of preparation and cell configurations have not yet been optimized for this remarkable material. Nevertheless, this material is highly desirable as an active material to replace the widely used LiMn_2O_4 , Li_3CoO_2 , and LiNiO_2 as can be seen by considering its theoretical capacity. The theoretical specific capacity for $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ is about 190 milliamp hours per gram. This is based on extracting all 3 lithium from the original starting material. Actually, the theoretical capacity is closer to about 197 milliamp hours per gram corresponding to about 66 milliamp hours for each atomic unit of lithium extracted from the $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ compound. Assuming that each such extracted unit of lithium corresponds to 66 milliamp hours, it can be seen that in Figure 1 the charge extracted of 136 milliamp hours per gram corresponds to the extraction of slightly more than 2 units of lithium from the $\text{Li}_3\text{V}_2(\text{PO}_4)_3$. It should be noted that chemical deintercalation of potassium does not occur from potassium metal phosphates. Heretofore there has been no attempt to deintercalate lithium from a lithium-containing metal phosphate. Thus, the electrochemical reaction demonstrated by the present invention is remarkable as it has not heretofore been suggested. The product of the present invention may be compared to a Nasicon ($\text{Na}_3\text{Zr}_2\text{PSi}_2\text{O}_{12}$) framework which is a skeleton structure with an interconnected interstitial space. There are also

the Langbeinite-type ($K_2Mg_2(SO_4)_3$) structures which are true cage structures. Such structures do not permit mobility of mobile metal ions through the crystal. Some Nasicon-type structures possess ionic conductivity but have very poor electronic conductivity. Some Nasicon-type structures are usable as solid electrolytes, but are not usable as electrode materials. Such Nasicon structures do not have an oxidizable metal in their structure, therefore, an ion cannot be extracted. Thus, such structures and compounds are useless for ion battery, rocking chair battery, application. In contrast to the known art, the present invention provides a lithium-metal-phosphate compound having an oxidizable metal. Such metal is capable of more than one oxidation state. The metal is present in the lithium-metal-phosphate compound at less than its highest oxidation state. Therefore, the metal is oxidizable to provide capability to extract out one or more Li^+ ions. This is demonstrated by oxidation of V in $LiV_2(PO_4)_3$ from $V^{+3}V^{+3}$ to $V^{+4}V^{+5}$. It should be noted that based on formation of $LiVV(PO_4)_3$ and $LiVFe(PO_4)_3$ there are other combinations which may make possible extraction/insertion of Li in such lithium-phosphate compounds. The oxidation states for all such combinations are not verified, but are thought to be as per the examples. Note that the amount of Li^+ removed or added will determine the relative oxidation state of E' and E". Fe in $Li_3Fe_2(PO_4)_3$ from $Fe^{+3}Fe^{+4}$ to $Fe^{+4}Fe^{+5}$; Mn in $Li_3Mn_2(PO_4)_3$ from $Mn^{+3}Mn^{+3}$ to $Mn^{+4}Mn^{+4}$; and other $Li_3E_1E_2(PO_4)_3$ as per $Fe^{+2}Ti^{+3}$ to $Fe^{+3}Ti^{+4}$; $Co^{+2}Mn^{+2}$ to $Co^{+3}Mn^{+4}$; $Cu^{+2}Mn^{+2}$ to $Cu^{+3}Mn^{+4}$, and $Fe^{+3}V^{+3}$ to $Fe^{+4}V^{+5}$.

Lithium ion batteries made with this technology are made in the discharged state and need a conditioning charge (pre-charge) before use. In the initial condition (pre-charged state), anodes of lithium ion batteries are essentially free of lithium, and often free of ions thereof, as in the case of graphite. Therefore, such batteries are inherently more stable and relatively less reactive than batteries containing $LiMn_2O_4$ or lithium metal.

To achieve a useable potential difference, the (positive electrode) is electrochemically oxidized, while the anode (negative

electrode) is reduced. Thus, during charging, a quantity (x) of lithium ions (Li^+) leave the positive electrode, $\text{Li}_{3-x}\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$ and the positive electrode is oxidized, increasing its potential; during charging, the Li ions are accepted at or intercalated into a negative electrode, preferably a carbon-based negative electrode, which is reduced. As a result, the negative electrode has a potential very close to-the-lithium metal potential, which is zero volts. A typical graphite electrode can intercalate up to about 1 atom of lithium per each of 6 carbons, that is LiC_6 . During discharging, the reverse occurs, and a quantity of (x) of lithium (Li^+) ions leave the negative electrode, increasing its potential. During discharge, the lithium ions are accepted (intercalated) back into the positive electrode, which is reduced, and its potential is reduced. If the $\text{Li}_3\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$ compound were used as a negative electrode, during charge, Li ions would be transferred to the negative electrode, $\text{Li}_{3-x}\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$ and the E' , E'' , or both, would theoretically achieve a higher oxidation state. On discharge, the Li^+ ions would be transferred back to the positive electrode.

While this invention has been described in terms of certain embodiments thereof, the scope of the claims should not be limited by the preferred embodiments described, but should be given the broadest interpretation consistent with the description as a whole.

The embodiments of the invention in which an exclusive
property or privilege is claimed are defined in the following
5 claims.

10

15

20

25

30

35

WHAT IS CLAIMED IS:

1. A method for operating an electrochemical cell, comprising:

(a) providing a first electrode comprising an active material compound, a counter electrode comprising a non-lithiated intercalation active material, and an electrolyte therebetween;

(b) electrochemically deintercalating lithium ions from the active material compound and transferring the ions to the counter electrode to charge the cell; and then

(c) electrochemically removing at least a portion of the transferred lithium ions from the counter electrode for reintercalation into the active material compound, whereupon electrochemical energy is obtained from the cell during discharge; and provided that:

in step (a), the active material compound is represented by the normal general formula $\text{Li}_{3-x}\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$ wherein $0 \leq y \leq 2$, wherein E' and E'' are the same or different from one another, wherein at least one of E' and E'' is a transition metal capable of an oxidation state higher than that initially present in the active material compound, and $x = 0$; and

wherein after step (b) and before step (c) the active material compound is represented by the nominal general formula where x is greater than 0 and less than or equal to 3;

and wherein after step (c) steps (b) and (c) are repeated in sequence.

2. The method of Claim 1, wherein both E' and E'' are capable of an oxidation state higher than that initially present in the active material compound.

3. The method of Claim 1, wherein E' and E'' are each a transition metal.
4. The method of Claim 1, wherein E' and E'' are the same metal.
5. The method of Claim 1, wherein E' and E'' are each independently selected from the group consisting of titanium (Ti), vanadium (V), chromium (Cr), manganese (Mn), iron (Fe), cobalt (Co), molybdenum (Mo), nickel (Ni), and copper (Cu).
6. The method of Claim 1, wherein one of E' and E'' is a non-transition metal.
7. The method of Claim 1 or 6, wherein one of E' and E'' is a non-transition metal and is non-oxidizable from its initial oxidation state in the active material compound.
8. The method of Claim 1, 6 or 7, wherein one of E' and E'' is selected from the group consisting of metals from Group I of the Periodic Table, metals from Group II of the Periodic Table, Al, and mixtures thereof.
9. The method of any one of Claims 1, 6, 7 or 8, wherein one of E' and E'' is selected from the group consisting of Al, Mg, Ca, and K.
10. The method of Claim 1, wherein one of E' and E'' is a non-transition metal and is oxidizable from its initial oxidation state in the active material compound.

11. The method of Claim 1 or 10, wherein one of E' and E'' is selected from the group consisting of Si, Te, Se, Sb, As, Sn, Pb, and mixtures thereof.

12. The method of Claim 1, wherein in step (a), the active material compound is represented by the nominal formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$.

13. The method of any one of Claims 1 through 12, wherein the counter electrode comprises an active material selected from the group consisting of a metal oxide, a metal chalcogenide, carbon, graphite, and mixtures thereof.

14. The method of any one of Claims 1 through 13, wherein the counter electrode comprises graphite.

15. The method of any one of Claims 1 through 14, wherein the first electrode comprises an electrically conductive diluent.

16. The method of Claim 15, wherein the electrically conductive diluent is carbon.

17. The method of Claim 16, wherein the electrically conductive diluent is carbon black.

18. The method of Claim 17, wherein the carbon black has a BET average surface area of $70 \pm 5 \text{ m}^2/\text{gr}$.

19. The method of any one of Claims 1 through 18, wherein the first electrode comprises from 5 to 30% by weight carbon black.

20. The method of any one of Claims 1 through 19, wherein the first electrode comprises a binder.

21. The method of Claim 20, wherein the binder is selected from the group consisting of an ethylene propylene diene termonomer, polyvinylidene difluoride, an ethylene acrylic acid copolymer, and an ethylene vinyl acetate copolymer.

22. The method of any one of Claims 1 through 21, wherein the first electrode comprises from 3 to 20% by weight binder.

23. The method of any one of Claims 1 through 22, wherein the active material compound is $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ and has an x-ray powder diffraction pattern containing the following 2θ peaks measured using CuK α radiation, $\lambda = 1.5418 \text{ \AA}$: 12, 20, 22.5, 28, 31 and 35.

24. The method of any one of Claims 1 through 22, wherein $0 < y < 2$.

25. An electrode comprising an active material represented by the nominal general formula $\text{Li}_3\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$, wherein $0 \leq y \leq 2$, E' and E'' are the same or different and are metals other than Cr or Fe when y is 2, and at least one of E' and E'' is a transition metal capable of an oxidation state higher than that initially present in the active material.

26. The electrode of Claim 25, wherein E' and E'' are each a transition metal.

27. The electrode of Claim 25 or 26, wherein E' and E'' are each independently selected from the group consisting of titanium (Ti), vanadium (V), manganese (Mn), cobalt (Co), molybdenum (Mo), nickel (Ni), and copper (Cu).
28. An electrode comprising an active material selected from the group consisting of $\text{Li}_3\text{V}_y\text{Ti}_{2-y}(\text{PO}_4)_3$, $\text{Li}_3\text{Fe}_y\text{V}_{2-y}(\text{PO}_4)_3$, and $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ wherein $0 \leq y \leq 2$.
29. The electrode of Claim 25, wherein the active material is represented by the nominal formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$.
30. The electrode of Claim 25, wherein one of E' and E'' is a non-transition metal.
31. The electrode of Claim 30, wherein one of E' and E'' is a non-transition metal and is non-oxidizable from its initial oxidation state in the active material.
32. The electrode of Claim 25, 30 or 31, wherein one of E' and E'' is selected from the group consisting of metals from Group I of the Periodic Table, metals from Group II of the Periodic Table, Al, and mixtures thereof.
33. The electrode of any one of Claims 25 or 30-32, wherein one of E' and E'' is selected from the group consisting of Al, Mg, Ca, and K.
34. The electrode of Claim 25, wherein one of E' and E'' is a non-transition metal and is oxidizable from its initial oxidation state in the active material.

35. The electrode of Claim 34, wherein one of E' and E'' is selected from the group consisting of Sb, Sn, Pb, and mixtures thereof.

36. The electrode of any one of Claims 25 through 35, wherein the electrode further comprises an electrically conductive diluent.

37. The electrode of Claim 36, wherein the electrically conductive diluent is carbon.

38. The electrode of Claim 37, wherein the electrically conductive diluent is carbon black.

39. The electrode of Claim 38, wherein the carbon black has a BET average surface area of $70 \pm 5 \text{ m}^2/\text{gr}$.

40. The electrode of any one of Claims 36 through 39, wherein the electrode comprises from 5 to 30% by weight carbon black.

41. The electrode of any one of Claims 25 through 40, wherein the electrode further comprises a binder.

42. The electrode of Claim 41, wherein the binder is selected from the group consisting of an ethylene propylene diene termonomer, polyvinylidene difluoride, an ethylene acrylic acid copolymer, and an ethylene vinyl acetate copolymer.

43. The electrode of any one of Claims 41 through 42, wherein the electrode comprises from 3 to 20% by weight binder.

44. The electrode of any one of Claims 25 through 43, wherein the active material compound is $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ and has an x-ray powder diffraction pattern containing the following 2θ peaks measured using CuK α radiation, $\lambda = 1.5418 \text{ \AA}$: 12, 20, 22.5, 28, 31 and 35.

45. The electrode of any one of Claims 25 through 43, wherein $0 < y < 2$.

46. A lithium ion battery, comprising:

an electrode comprising an active material represented by the nominal formula $\text{Li}_{3-x}\text{E}'_y\text{E}''_{2-y}(\text{PO}_4)_3$ wherein $0 \leq y \leq 2$, wherein E' and E'' are the same or different from one another, wherein at least one of E' and E'' is a transition metal;

a counter-electrode comprising a non-lithiated intercalation active material; and

an electrolyte;

wherein in a first condition, $x = 0$; and

wherein in a second condition $0 < x \leq 3$ and at least one E' and E'' has an oxidation state higher than its oxidation state in the first condition.

47. The battery of Claim 46, wherein both E' and E'' are capable of an oxidation state higher than that initially present in the active material.

48. The battery of Claim 46, wherein E' and E'' are each a transition metal.

49. The battery of Claim 46, wherein E' and E'' are each independently selected from the group consisting of titanium (Ti), vanadium (V), chromium (Cr), manganese (Mn), iron (Fe), cobalt (Co), molybdenum (Mo), nickel (Ni), and copper (Cu).

50. The battery of Claim 46, wherein one of E' and E'' is a non-transition metal.

51. The battery of Claim 46 or 50, wherein one of E' and E'' is a non-transition metal and is non-oxidizable from its initial oxidation state in the active material.

52. The battery of Claim 46, 50 or 51, wherein one of E' and E'' is selected from the group consisting of metals from Group I of the Periodic Table, metals from Group II of the Periodic Table, Al, and mixtures thereof.

53. The battery of any one of Claims 46 or 50 to 52, wherein one of E' and E'' is selected from the group consisting of Al, Mg, Ca, and K.

54. The battery of Claim 46, wherein one of E' and E'' is a non-transition metal and is oxidizable from its initial oxidation state in the active material.

55. The battery of Claim 46 or 54, wherein one of E' and E'' is selected from the group consisting of Sb, Sn, Pb, and mixtures thereof.

56. The battery of Claim 46, wherein the active material is represented by the nominal formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$.

57. The battery of any one of Claims 46 through 56, wherein the counter electrode is selected from the group consisting of a metal oxide, a metal chalcogenide, carbon, graphite, and mixtures thereof.

58. The battery of any one of Claims 46 through 57, wherein the counter electrode is graphite.

59. The battery of any one of Claims 46 through 58, wherein the electrode further comprises an electrically conductive diluent.

60. The battery of Claim 59, wherein the electrically conductive diluent is carbon.

61. The battery of Claim 60, wherein the electrically conductive diluent is carbon black.

62. The battery of Claim 61, wherein the carbon black has a BET average surface area of $70 \pm 5 \text{ m}^2/\text{gr}$.

63. The battery of any one of Claims 59 through 62, wherein the electrode comprises from 5 to 30% by weight carbon black.

64. The battery of any one of Claims 46 through 63, wherein the electrode further comprises a binder.

65. The battery of Claim 64, wherein the binder is selected from the group consisting of an ethylene propylene diene termonomer, polyvinylidene difluoride, an ethylene acrylic acid copolymer, and an ethylene vinyl acetate copolymer.

66. The battery of Claim 64 or 65, wherein the electrode comprises from 3 to 20% by weight binder.

67. The battery of any one of Claims 46 through 66, wherein the active material compound is $\text{Li}_3\text{V}_2(\text{PO}_4)_3$ and has an x-ray powder diffraction pattern containing the following 2θ peaks measured using CuK α radiation, $\lambda = 1.5418 \text{ \AA}$: 12, 20, 22.5, 28, 31 and 35.

68. A reactive composition for forming an active material represented by the formula selected from the group consisting of $\text{Li}_3\text{V}_y\text{Ti}_{2-y}(\text{PO}_4)_3$ and $\text{Li}_3\text{V}_2(\text{PO}_4)_3$, wherein $0 \leq y \leq 2$, comprising:

intermingled particles of a metal compound selected from the group consisting of vanadium (V), titanium (Ti) and mixtures thereof, particles of a lithium compound; and particles of a phosphate salt compound;

the compounds being in a proportion which upon reaction provides the active material compound of the nominal formula proportion.

69. A method of making a compound represented by the nominal formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$, comprising the steps of:

forming a mixture of a lithium-containing compound, at least one vanadium oxide compound, and a phosphoric acid-containing compound, in proportions to provide a compound represented by the nominal formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$; and heating the mixture at a temperature and for a time sufficient to form the compound in an atmosphere selected from the group consisting of a non-oxidizing atmosphere, a reducing atmosphere, and mixtures thereof.

70. The method of Claim 69, wherein the lithium-containing compound is selected from the group consisting of lithium acetate, lithium hydroxide, lithium nitrate, and lithium carbonate.

71. The method of Claim 69, wherein the at least one vanadium oxide compound is selected from the group consisting of V_2O_5 and V_2O_3 .

72. The method of Claim 69, wherein the at least one vanadium oxide compound is V_2O_3 .

73. The method of Claim 69, wherein the phosphoric acid-containing compound is ammonium phosphate.

74. The method of Claim 69, wherein the step of forming a mixture further comprises blending the mixture together with a solvent to form a wet mixture, wherein the wet mixture is heated at a temperature and for a time sufficient to form the lithium-vanadium-phosphate compound.

75. The method of Claim 74, wherein the solvent is selected from the group consisting of xylene and methanol.

76. The method of Claim 74, wherein the step of forming a mixture further comprises the steps of drying the wet mixture to form a dry mixture, and pressing the dry mixture into pellets, wherein the pellets are heated at a temperature and for a time sufficient to form the compound.

77. The method of Claim 69, wherein the reducing atmosphere is a hydrogen atmosphere.

78. A compound represented by the nominal formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$, made by a process comprising the steps of:
forming a mixture of a lithium-containing compound, at least one vanadium oxide compound, and a phosphoric acid-containing compound, in proportions to provide a compound represented by the nominal formula $\text{Li}_3\text{V}_2(\text{PO}_4)_3$; and heating the mixture at a temperature and for a time sufficient to form the compound in an atmosphere selected from the group consisting of a non-oxidizing atmosphere, a reducing atmosphere, and mixtures thereof.

79. The compound of Claim 78, wherein the lithium-containing compound is selected from the group consisting of lithium acetate, lithium hydroxide, lithium nitrate, and lithium carbonate.

80. The compound of Claim 78, wherein the at least one vanadium oxide compound is selected from the group consisting of V_2O_5 and V_2O_3 .

81. The compound of Claim 78, wherein the phosphoric acid-containing compound is ammonium phosphate.

82. The compound of Claim 78, wherein the step of forming a mixture further comprises blending the mixture together with a solvent to form a wet mixture, wherein the wet mixture is heated at a temperature and for a time sufficient to form the lithium-vanadium-phosphate compound.



83. The compound of Claim 82, wherein the solvent is selected from the group consisting of xylene and methanol.

84. The compound of Claim 82, wherein the step of forming a mixture further comprises the steps of drying the wet mixture to form a dry mixture, and pressing the dry mixture into pellets, wherein the pellets are heated at a temperature and for a time sufficient to form the compound.




85. The compound of Claim 78, wherein the reducing atmosphere is a hydrogen atmosphere.

86. Use of the electrode as defined in any one of Claims 25 to 45, for forming a lithium ion battery.

1/3

FIG. 1FIG. 2

2/3

FIG. 3FIG. 5FIG. 6




FIG. 4A




FIG. 4B