



Europäisches
Patentamt
European
Patent Office
Office européen
des brevets



EP 2 006 403 A1

(12)

EUROPEAN PATENT APPLICATION
published in accordance with Art. 153(4) EPC

(43) Date of publication:
24.12.2008 Bulletin 2008/52

(51) Int Cl.:
C22C 21/00 (2006.01)

(21) Application number: **07747842.8**

(86) International application number:
PCT/RU2007/000109

(22) Date of filing: **07.03.2007**

(87) International publication number:
WO 2007/111529 (04.10.2007 Gazette 2007/40)

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU LV MC MT NL PL PT RO SE
SI SK TR**

(30) Priority: **27.03.2006 RU 2006109658**

(71) Applicant: **Otkrytoe Akcionerное
Общество "Каменск-Уральский
Каменск-Уральский, Свердловская Obl. 623405
(RU)**

(72) Inventors:

- **POPOV, Valeriy Ivanovich**
Sverdlovskaya obl., 623422 (RU)
- **OVSYANNIKOV, Boris Vladimirovich**
Sverdlovskaya obl., 623412 (RU)
- **ZAMYATIN, Viktor Mikhailovich**
Sverdlovskaya obl., 620020 (RU)

(74) Representative: **Hössle Kudlek & Partner
Sendlinger Strasse 29
80331 München (DE)**

(54) **ALUMINIUM-BASED ALLOY**

(57) The invention covers a field of metallurgy of alloys based on aluminum, in particular, to the alloy of aluminum-copper-magnesium-lithium system applied for manufacturing semi-finished products and parts thereof used as structural materials for aerospace engineering. The invention is directed to enhancement of ductility and processibility of aluminum-copper-magnesium-lithium system alloys, increase of yields by manufacturing semi-finished products and parts thereof, assurance of possibility to produce thin sheets, thin-walled sections and die-forgings by reducing production labor intensiveness, by preservation required strength and operation characteristics demanded to structural materials for aerospace en-

gineering.

The indicated technical result is achieved by the fact, that the alloy contains the following component ratio, wt %: lithium- 1.6 - 1.9; copper- 1.3 - 1.5; magnesium- 0.7 - 1.1; zirconium- 0.04 - 0.2; beryllium- 0.02 - 0.2; titanium- 0.01 - 0.1; nickel-0.01-0.15; manganese- 0.01 - 0.2; gallium- ГО 0.001; ЦИНК- 0.01 - 0.3; sodium- up to 0.0005; calcium- 0.005 - 0.02; and, at least, one element selected from the group including vanadium- 0.005 - 0.01 and scandium-0.005 - 0.01; aluminum- remainder.

Description

Pertinent art

5 [0001] An invention covers a field of metallurgy of alloys based on aluminum, in particular to the alloy of aluminum-copper-magnesium-lithium system applied for manufacturing semi-finished products and parts thereof used as structural materials for aerospace engineering.

10 [0002] It is known that aluminum-lithium alloys possess an unique combination of mechanical properties, namely of low density, increased elasticity modulus, and sufficiently high strength characteristics. Availability of indicated properties enables to use alloys of this system as structural material for aerospace engineering, that allows to improve a number of aircraft performance features of flying vehicles, in particular, reduction of vehicle weight, fuel economy, increase of load capacity.

15 [0003] However, aluminium-lithium alloys have one disadvantage - low ductility on conditions close to maximum strength (N.I. Fridlyander, K.V. Chuistov, A.L. Berezina, N.I. Kolobnev, Aluminum-lithium alloys. Structure and Properties, Kiev: Nauk. Dumka, 1992, page 177).

Prior Art

20 [0004] Aluminum-based alloy is known having wt %:

20	Lithium	1.7 - 2.0
	Copper	1.6 - 2.0
	Magnesium	0.7 - 1.1
25	Zirconium	0.04 - 0.16
	Beryllium	0.02 - 0.2
	Titanium	0.01 - 0.07
	Nickel	0.02 - 0.15
	Manganese	0.01 - 0.4
30	Aluminum	Remainder

(Inventor's Certificate of USSR No. 1767916, IPC C 22 C 21/16, date of publication 1997.08.20).

35 [0005] Disadvantages of the indicated alloy are its low processibility, high manufacturing labor intensiveness, and low yields by manufacturing semi-finished products and parts thereof, impossibility to obtain thin sheets, thin-walled sections and die-forgings in it.

40 [0006] Reasons causing occurrence of above mentioned disadvantages by using the known alloy include the fact, that relatively high contents of copper in the known alloy negatively influences hot brittleness and ductility by shaping, that leads to increased cracking, higher rejections on folds and non-flatness by finishing operations, namely, by flattening and stretching semi-finished products.

[0007] Aluminum-based alloy is known - 8093, (alloy designation is in conformance with alloy numbers and comply with definitions registered by Aluminum Assosiation, Washington, USA) having wt %:

45	Lithium	1.9 - 2.6
	Copper	1.0 - 1.6
	Magnesium	0.9 - 1.6
	Zirconium	0.04 - 0.14
	Titanium	Up to 0.1
50	Manganese	Up to 0.1
	Zinc	Up to 0.25
	Aluminum	Remainder

(International designation of alloys and limits of chemical composition of wrought aluminum and aluminum alloys, Aluminum Association: 2004, pages 12, 13)

55 [0008] Disadvantages of the indicated alloy are increased cost of the alloy, its low processibility, high manufacturing labor intensiveness, and low yields by manufacturing semi-finished products and parts thereof, impossibility to obtain thin sheets, thin-walled sections and die-forgings in it.

[0009] Reasons causing occurrence of above mentioned disadvantages by using the known alloy include the fact, that the known alloy has increased contents of lithium, besides, increased contents of lithium lead to formation of strengthening phases slightly increasing alloy strength characteristics, but, at the same time, considerably reducing its ductility by casting and shaping, that leads to increased cracking, higher rejections on folds and non-flatness by finishing operations, namely, by flattening and stretching semi-finished products.

[0010] The closest alloy on chemical composition and function to the claimed aluminum-based alloy is the alloy having wt %:

10	Lithium	1.7 - 2.0
	Copper	1.6 - 2.0
	Magnesium	0.7 - 1.1
	Zirconium	0.04 - 0.2
	Beryllium	0.02 - 0.2
15	Titanium	0.01 - 0.1
	Nickel	0.01 - 0.15
	Manganese	0.001 - 0.05
	Gallium	0.001 - 0.05
	Zinc	0.01 - 0.3
20	Sodium	0.0005 - 0.001
	Aluminum	Remainder

(Patent of the Russian Federation No. 2180928, IPC 7 C 22 C 21/00, C 22 C 21/16, date of publication 2002.03.27).

[0011] Disadvantages of the indicated alloy taken for a prototype are its relatively low processibility, high manufacturing labor intensiveness, and low yields by manufacturing semi-finished products and parts thereof, impossibility to obtain thin sheets, thin-walled sections and die-forgings in it.

[0012] Reasons causing occurrence of above mentioned disadvantages by using the known alloy taken for a prototype refer to the fact, that the known alloy is characterized by increased copper contents, that negatively influences hot brittleness and ductility by shaping, that leads to increased cracking, higher rejections on folds and non-flatness by finishing operations, namely, by flattening and stretching semi-finished products, moreover, increased contents of sodium and gallium lead to considerable increase of hot brittleness of the alloy, to much more reduction of its ductile characteristics (A.V. Kurdyumov, S.V. Inkin, V.S. Chulkov, G.G. Shadrin, Metallurgical Admixtures in Aluminum Alloys, M.: Metallurgy. 1988, pages 90, 99), that considerably complicates an objective to obtain acceptable ingots and further to receive semi-finished products by various types of shaping, and also to perform quality cladding for rolled semi-finished products, as a result of formation of substantial areas of non-welded cladding on their surface.

Invention disclosure

[0013] The objective, which the invention is directed to solve, consists in development of the aluminum-based alloy intended for manufacturing semi-finished products and parts in it for aerospace engineering, free from the above listed disadvantages and inherent to known engineering solutions. A technical result achieved by an embodiment of the invention comprises obtaining an alloy possessing increased ductility, that will allow to improve its processibility, to increase yields by manufacturing semi-finished products and parts thereof, to ensure possibility to produce thin sheets, thin-walled sections and die-forgings by reducing production labor intensiveness, by preservation required strength and operation characteristics of the alloy, and also semi-finished products and parts thereof demanded to structural materials for aerospace engineering.

[0014] The posed objective with achievement of the aforesaid technical result by invention embodiment is solved by the fact, that the known aluminum-based alloy containing lithium, copper, magnesium, zirconium, beryllium, titanium, nickel, manganese, gallium, zinc, sodium, additionally contains calcium and, at least, one element selected from a group including vanadium and scandium, with the following component ratio, wt %:

55	Lithium	1.6 - 1.9
	Copper	1.3 - 1.5
	Magnesium	0.7 - 1.1
	Zirconium	0.04 - 0.2
	Beryllium	0.02 - 0.2

(continued)

5	Titanium	0.01 - 0.1
	Nickel	0.01 - 0.15
	Manganese	0.01 - 0.2
	Gallium	up to 0.001
	Zinc	0.01 - 0.3
10	Sodium	up to 0.0005
	Calcium	0.005 - 0.02

At least, one element selected from a group including:

15	Vanadium	0.005 - 0.01
	Scandium	0.005 - 0.01
	Aluminum	Remainder

[0015] The aluminum-based alloy used for manufacturing semi-finished products and parts differs from the prior art both quantitatively (reduced contents of copper, gallium, and sodium) and qualitatively (in addition it contains calcium, and, at least, one element selected from a group including vanadium and scandium).

[0016] We have determined that increased contents of copper results in formation of coarse irregular-shaped intermetallic compounds being copper-bearing phases formed by alloy crystallization in areas with increased copper contents inside grains and on their boundaries. These phases are represented not by separate particles, but extensive accumulations impeding shear deformations in the shaping process, which results in considerable reduction of alloy ductility.

[0017] Reduction of copper contents in the alloy up to limits of 1.3 - 1.5 wt % allows practically total transfer to solid solution which results in considerable reduction of inclusion volume ratio of coarse intermetallic compounds of copper-bearing phases as determined by electron-microscopical analysis of the alloy, and, consequently, enhancement of alloy ductility. Reduction of copper contents to less than 1.3 wt % will have no enhancing influence on ductility characteristics of the alloy, but will considerably reduce its strength features.

[0018] Additionally, we have determined that gallium and sodium do not form phases with aluminum and accumulate on grain boundaries resulting in brittle fracture along grain boundary in processes of alloy crystallization and its shaping.

[0019] We have determined that with gallium and sodium contents less than 0.001 and 0.0005 wt % respectively, they practically totally dissolve in solid solution resulting in enhancement of alloy ductility.

[0020] Calcium in quantity of 0.005 - 0.02 wt % is an additive binding excess sodium and other residual elements of the alloy resulting in formation of a rounder shape of isolated intermetallic compounds and their coagulation resulting in more favorable conditions of shear deformation, and, consequently, in enhancement of alloy process ductility.

[0021] Introduction of one or more elements from a group of vanadium, scandium in indicated quantities facilitates formation of a homogeneous, fine-grained structure that promotes intensification of the role of zirconium as a modifying agent ensuring structural strengthening of semi-finished products and parts in the alloy, that allows to achieve a necessary level of alloy strength properties.

[0022] From the proposed aluminum-based alloy it is possible to manufacture various semi-finished products: sheets and plates, die-forgings, extrusions. From semi-finished products of the proposed alloy it is possible to obtain various parts, for example, panels for skin of aircraft fuselage structures, elements of bulkhead frame, welded fuel tanks, and other elements of aerospace engineering.

45 Examples of embodiments of the invention

[0023] Under industrial conditions a flat ingot with cross-section of 300x1,100 mm and round ingots with diameters of 190 mm and 350 mm have been cast in each alloy, which chemical composition is given in Table 1.

[0024] Alloy No. 1 corresponds to the alloy taken as a prototype, alloys No. 2, 3, 4 correspond to the proposed one.

[0025] Charge material melting, degassing and ingot casting have been done at temperature of 710 - 730°C.

Example 1

55 **[0026]** Later on, clad sheets have been manufactured from flat ingots in each alloy. The sheets have been manufactured based on one process flow by means of hot rolling at temperature of 430°C up to 6.5 mm of thickness with reeling to coils, and afterwards, after annealing at temperature of 400°C, by means of cold rolling.

EP 2 006 403 A1

[0027] It should be mentioned, that it has been achieved to roll a sheet in alloy No. 1 only up to 0.9 mm of thickness, and further rolling has been stopped due to presence of tears 30 mm deep on sheet side edges and presence of 2 ruptures in a coil.

[0028] Sheets in alloys No. 2, 3, 4 have been rolled without ruptures up to 0.5 mm of thickness.

5 **[0029]** Further finishing operations, flattening and stretching sheets in alloys No. 2, 3, 4, in comparison with alloy No. 1 and despite their lower thickness, have been done more successfully and with less rejections at release inspection on defects: folds, non-flatness, and cracks.

10

15

20

25

30

35

40

45

50

55

Table 1

Alloy	Alloy composition No.	Component contents, wt %										Remainder Al			
		Li	Cu	Mg	Zr	Be	Ti	Ni	Mn	Ga	Zn	Na	Ca	V	Sc
Prototype	1	1.9	1.7	0.9	0.10	0.03	0.02	0.04	0.08	0.002	0.015	0.0007	—	—	—
	2	1.9	1.5	1.0	0.11	0.02	0.02	0.05	0.06	0.0004	0.014	0.0003	0.005	0.007	0.006
Claimed	3	1.8	1.3	0.9	0.11	0.03	0.02	0.04	0.07	0.0002	0.014	0.0001	0.02	0.01	—
	4	1.8	1.4	0.8	0.10	0.04	0.02	0.04	0.07	0.0001	0.015	0.0002	0.01	—	0.009

[0030] Yield by manufacturing sheets in alloys No. 2, 3, 4 has been higher by 30%, than in alloy No. 1.

[0031] Later on, specimens from sheets in alloys No. 1, 2, 3, 4 have been tested at static tension with determination of tensile strength (σ_B), yield strength ($\sigma_{0.2}$), elongation ($\sigma, \%$).

5 [0032] Specimens have been cut off lengthwise, crosswise, and at angle of 45° relative to rolling direction.

[0033] Results of mechanical testing are presented in Table 2.

[0034] Table 2 shows that the proposed alloy surpasses the known alloy (the prototype) on ductility characteristics with preservation of required strength characteristics.

Example 2

10 [0035] Sections (angles with flange thickness up to 5 mm) have been manufactured from round ingots with diameter of 190 mm in each alloy.

[0036] Sections in different alloys have been manufactured based on one process flow by means of extruding at temperature of 400°C, with further section water quenching, and ageing at temperature of 150°C within 24 hours.

15 [0037] Yield by manufacturing sheets in alloys No. 2, 3, 4 has been higher by 15%, than in alloy No. 1.

Example 3

20 [0038] Die-forgings with wall thickness of 40 mm have been manufactured from round ingots with diameter of 350 mm in each alloy.

Table 2

Alloy	Alloy composition No.	Sampling direction	Mechanical properties		
			σ_B , MPa	$\sigma_{0.2}$, MPa	$\sigma, \%$
Prototype	1	Longitudinal	432	347.5	13.5
		Transverse	440	343	10.7
		At angle of 45°	419	323	13.9
Claimed	2	Longitudinal	430	349	14.6
		Transverse	438	352	13.8
		At angle of 45°	424	328	14.5
	3	Longitudinal	431	351	14.8
		Transverse	438	345	13.9
		At angle of 45°	425	329	14.9
	4	Longitudinal	432	345	14.9
		Transverse	439	339	14.1
		At angle of 45°	423	328	15.1

45 [0039] Die-forgings in different alloys have been manufactured on one process flow by means of blanking forging at temperature of 410°C, preliminary forging at temperature of 410°C, and after etching by means of final forging at temperature of 400°C, with further quenching at temperature of 500°C during 2 hours and ageing at temperature of 150 °C during 24 hours.

[0040] The yield by manufacturing die-forgings in alloy No. 2, 3, 4 has been higher than alloy No. 1 by 10%.

50 [0041] Thus, the suggested alloy ensures achievement of the posed objective - improvement of alloy ductility characteristics, and, consequently, improvement of its processibility, increase of yields by manufacturing semi-finished products and parts thereof, assurance of possibility to produce thin sheets, thin-walled sections and die-forgings by reducing production labor intensiveness, and preservation of required strength and operation characteristics of the alloy and parts thereof demanded to structural materials for aerospace engineering.

Claims

1. The aluminum-based alloy containing lithium, copper, magnesium, zirconium, beryllium, titanium, nickel, manganese, gallium, zinc, sodium, which differs by the fact, that it additionally contains calcium, and, at least, one element selected from a group including vanadium and scandium, with the following component ratio, wt %:

5	Lithium	1.6 - 1.9
10	Copper	1.3 - 1.5
	Magnesium	0.7 - 1.1
	Zirconium	0.04 - 0.2
	Beryllium	0.02 - 0.2
15	Titanium	0.01 - 0.1
	Nickel	0.01 - 0.15
	Manganese	0.01 - 0.2
	Gallium	up to 0.001
	Zinc	0.01 - 0.3
20	Sodium	up to 0.0005
	Calcium	0.005 - 0.02, and
	at least, one element selected from a group including:	
	Vanadium	0.005 - 0.01
25	Scandium	0.005 - 0.01
	Aluminum	Remainder.

30

35

40

45

50

55

INTERNATIONAL SEARCH REPORT

International application No.
PCT/RU 2007/000109

A. CLASSIFICATION OF SUBJECT MATTER		C22C 21/00 (2006.01)
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
C22C 21/00, C22C 21/12, C22C 21/16		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	RU 2180928 C1 (GOSUDARSTVENNOE PREDPRIYATIE "VSEROSSIJSKII NAUCHNO-ISSLEDOVATELSKII INSTITUT AVIATSIONNYKH MATERIALOV") 27.03.2002, the claims	1
A	RU 2163940 C1 (GOSUDARSTVENNOE PREDPRIYATIE "VSEROSSIJSKII NAUCHNO-ISSLEDOVATELSKII INSTITUT AVIATSIONNYKH MATERIALOV") 10.03.2001, the claims	1
A	JP 02-294448 A (CEGEDUR PECHINEY RHENALU) 05.12.1990, the abstract	1
A	US 4832910 A (ALUMINUM CO OF AMERICA) 23.05.1989, the claims	1
<input type="checkbox"/> Further documents are listed in the continuation of Box C.		<input type="checkbox"/> See patent family annex.
<p>* Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier application or patent but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art</p> <p>"&" document member of the same patent family</p>		
Date of the actual completion of the international search	Date of mailing of the international search report	
10 May 2007 (10.05.2007)	12 July 2007 (12.07.2007)	
Name and mailing address of the ISA/ RU Facsimile No.	Authorized officer	
	Telephone No.	

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 1767916 A [0004]
- RU 2180928 [0010]

Non-patent literature cited in the description

- N.I. FRIDLYANDER ; K.V. CHUISTOV ; A.L. BEREZINA ; N.I. KOLOBNEV. *Aluminum-lithium alloys. Structure and Properties*, 1992, 177 [0003]
- A.V. KURDYUMOV ; S.V. INKIN ; V.S. CHULKOV ; G.G. SHADRIN. *Metallurgical Admixtures in Aluminum Alloys*, M.: Metallurgy, 1988, 90, 99 [0012]