



(43) International Publication Date
12 September 2014 (12.09.2014)

WIPO | PCT

(10) International Publication Number
WO 2014/138351 A1

- (51) **International Patent Classification:**
A61L 27/52 (2006.01) *A61F 2/02* (2006.01)
- (21) **International Application Number:**
PCT/US2014/021065
- (22) **International Filing Date:**
6 March 2014 (06.03.2014)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
61/773,615 6 March 2013 (06.03.2013) US
- (71) **Applicants:** UNIVERSITY OF PITTSBURGH - OF THE COMMONWEALTH SYSTEM OF HIGHER EDUCATION [US/US]; 200 Gardner Steel Conference Center, Pittsburgh, PA 15260 (US). CORNELL UNIVERSITY [US/US]; 395 Pine Tree Road, Suite 310, Ithaca, NY 14850 (US).
- (72) **Inventors:** BROWN, Bryan, Nicklaus; 157 West Hutchinson Avenue, Pittsburgh, PA 15218 (US). CHEETHAM, Jonathan; 356 Snyder Road, Ithaca, NY 14850 (US).
- (74) **Agents:** KOLE, Lisa, B. et al.; Baker Botts L.L.P., 30 Rockefeller Plaza, New York, NY 10112-4498 (US).

(81) **Designated States** (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) **Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) **Title:** INJECTABLE PERIPHERAL NERVE SPECIFIC HYDROGEL

(57) **Abstract:** The present invention relates to a peripheral nerve-specific hydrogel material, which is deliverable in a minimally invasive fashion, sustains the growth of neurons, and speeds recovery following surgical reconstruction.



WO 2014/138351 A1

INJECTABLE PERIPHERAL NERVE SPECIFIC HYDROGEL

SPECIFICATION

5

1. PRIORITY CLAIM

This application claims priority to United States Provisional Patent Application Serial No. 61/773,615, filed March 6, 2013, the contents of which are hereby incorporated by reference in their entirety herein.

10

2. INTRODUCTION

The present invention relates to a peripheral nerve-specific hydrogel material, which is deliverable in a minimally invasive fashion, sustains the growth of neurons, and speeds recovery following surgical reconstruction.

15

3. BACKGROUND OF THE INVENTION

Neuromuscular denervation is a common consequence following peripheral nerve injury. Functional outcomes following repair are often disappointing as the capacity of motor axons to regenerate is decreased with prolonged denervation.

20 Despite advances in microsurgical technique and extensive studies on nerve repair, presently used reinnervation methods produce moderate results and full functional recovery after peripheral nerve injury is seldom achieved.

In cases where anastomosis of the nerve is not possible ("critically sized defect") the current clinical "gold standard" is often nerve autografting. However, autograft harvest is associated with morbidity at the donor site including pain, sensitivity, or loss of sensation and approximately 50% of patients do not regain function following nerve autografting. Allogeneic graft materials have also been suggested. However, fresh allogeneic tissue is subject to an undesirable immune response from the host in the absence of immunosuppression.

30 For these reasons, a number of alternative approaches have been suggested. These have included both synthetic and biologically derived guidance conduits and hydrogel delivery systems. A wide range of synthetic polymers have been examined for construction of nerve guidance conduits, both with and without cell scale features which either mimic the natural extracellular matrix or provide guidance cues for axonal elongation. However, synthetic nerve guidance conduits

35

are desirably specifically tailored not only to support cellular growth, but also to allow for nutrient diffusion, and to degrade with new tissue formation within the conduit. Long-term implantation of slow degrading synthetic biomaterials is also often associated with a detrimental foreign body type reaction which can hinder recovery.

5 Various biologically derived materials have been investigated for the fabrication of nerve guidance conduits. The use of a number of individual extracellular matrix (ECM) proteins including collagen, fibronectin, and laminin as well as other biologic materials have been suggested for the fabrication of nerve guidance conduits into simple tubes, or tubes with intraluminal structures intended for
10 guidance of tissue ingrowth. Many of these approaches have been shown to improve outcomes in animal models, although only over relatively short lengths. Others have suggested the use of decellularized allograft nerve tissues as scaffolds for reconstruction of peripheral nerves due to maintenance of the native tissue architecture and functional molecules in their relative tissue specific constituent
15 proportions. However, not all of the proposed decellularization methods have been shown to be effective for removal of sufficient cellular content and maintenance of tissue structure, resulting ineffective recovery in some studies.

4. SUMMARY OF THE INVENTION

20 The present invention relates to a decellularized peripheral nerve specific scaffold which can be formulated into an injectable hydrogel form. It is based, at least in part, on the discovery of a decellularized tissue which substantially lacks immunogenic cellular components but retains sufficient amounts of nerve specific components to be effective at supporting nerve regrowth and reducing or
25 preventing muscular atrophy. In certain non-limiting embodiments, the decellularized tissue scaffold is formulated into a hydrogel through the use of enzymatic degradation. These hydrogels have been shown to be non-cytotoxic to neurons and also support neuronal outgrowth of cultured cells. When injected into injured recurrent laryngeal nerves in a canine model, the hydrogel was shown to improve
30 reinnervation and slow atrophy of the laryngeal muscles as compared to surgical correction without injection.

5. BRIEF DESCRIPTION OF THE FIGURES

FIGURES 1A-F. Confirmation of decellularization. Decellularization was confirmed by the absence of nuclei in DAPI stained sections of decellularized nerve (B). Native nerve shown in (A). Luxol fast blue staining confirmed the removal of potentially immunogenic cellular myelin (D). Native nerve shown in (C). DNA content was assessed by PicoGreen Assay and shown to be reduced by nearly 85% to levels (average 175 ng DNA/mg scaffold dry weight) below those reported for most commercially available ECM scaffold materials (E). DNA was further shown to be reduced on agarose gel analysis (F).

FIGURE 2A-D. Electron microscopy (A,C) and histologic evaluation (B,E) of structure. Under SEM, the decellularized sciatic nerves (B) were characterized by an ultrastructure similar to that of native tissue (A). In cross section, distinct nerve bundles can be observed, as can individual structures including the epineureal connective tissues and dense, intact perineurium surrounding each individual nerve bundle. The epineurium is less dense and larger pores are observed than in the native tissue. A number of individual reticular fibers can also be observed. These larger and smaller fibers likely represent the collagen I and III which comprise the majority of the extracellular matrix of the native epineurium. The endoneurial structure is slightly disrupted as compared to native tissue. However, the areas previously occupied by individual nerve fibers (basal lamina) can be observed, and remain highly parallel within the tissue. This is also evident in longitudinal section, where aligned channels and connective tissues can be observed more clearly. Intact blood vessels were also observed in the decellularized samples. These findings were supported by histologic staining. Hematoxylin and eosin stained samples (B,D) in cross section were characterized by a diffuse epineurium, a dense and intact perineurium and basal lamina devoid of cells. Longitudinal sections further confirmed the SEM findings, and were characterized by aligned connective tissue within the epineurium, and patent spaces indicative of basal lamina devoid of axonal and supporting cells.

FIGURE 3. Maintenance of specific ECM components. Immunolabeling confirmed the presence of collagen I, III, and IV within the decellularized samples. These components were observed present in an architecture

that resembled that of native nerve. However, the intensity of the staining was less and the architecture slightly disrupted as compared to native tissue.

FIGURE 4A-D. Hydrogel formation. Enzymatically digested samples of the decellularized nerve described above were neutralized and reconstituted at multiple concentrations and placed into an incubator at physiologic temperature to induce gelation (A,B). Hydrogel formation was improved at concentrations of 12.5+mg/mL. SEM of hydrogels demonstrates a highly fibrous architecture of hydrogel (C,D).

FIGURE 5A-C. Nerve ECM digest is non-cytotoxic and promotes neurite outgrowth. When a neuronal cell line was exposed to the digested ECM, neurite extension was seen as early as Day 1 of culture and continued with increasing extension length for up to 3 days in culture. Longer time periods were not examined. Day 0 (A), Day 1 (B), and Day 3 (C) are shown. Neurite extension following exposure to ECM digest was equivalent to results obtained for neurons exposed to neurite outgrowth media (positive control) suggesting the decellularized nerve hydrogel promotes nerve outgrowth.

FIGURE 6. Gross morphology of control (left panel) and treated (right panel) sciatic nerves at 21 days post-surgery. There was little to no tissue growth within empty conduit compared to conduit filled with nerve specific (NS)-ECM. Top panels show conduit before explant and bottom panels show tissue formed within the conduit (conduit removed).

FIGURE 7A-G. Qualitative assessment of decellularization. Few cells remained while maintaining much of the structure. The Tubular structure remained after decellularization. (A & B) H&E, Native and Decell, (C & D) Luxol Fast Blue for Myelin, Native and Decell, and (E & F) Dapi stain, Native and Decell, (G) Picogreen assay for DNA content shows dsDNA content of the decellularized tissue (158.07 ± 34.53 ng/mg) was significantly decreased as compared to native tissues (1043.65 ± 291.20 ng/mg).

FIGURE 8A-N. Immunohistology, Electromicroscopic and Biochemical analysis for major extracellular matrix molecules. Native and decellularized nerve tissue stained for (A) Collagen I native, (B) Collagen I NS-ECM, (C) Collagen III native, (D) Collagen III NS-ECM, (E) Collagen IV native, (F) Collagen IV NS-ECM. (G and H) Electromicroscopic appearance of intact nerve. (I

and J) Electromicroscopic appearance of decellularized nerve. (K-N) Biochemical assays for hydroxyproline, GAG, NGF, and CNTF content.

FIGURE 9A-D. (A) Degradation products of decellularized nerves were introduced at different concentrations to primary neurons over four days. (B) Images from neurite outgrowth with pepsin control and positive (b27 supplement) control and nerve and urinary bladder matrix (UBM) at 500 ug/ml. (C and D) Digested decellularized nerve products were formed into a stable gel. Concentration of gel was 15 mg/mL.

FIGURE 10A-D. (A) Intraoperative photo of silicon conduit placement after anastomosis of transected recurrent laryngeal nerve (RLn). (B) Compound muscle action potential amplitude measured at the vocalis muscle after super-stimulation of the RLn. (C) Duration between stimulation of the RLn and recorded action potential at the vocalis muscle. (D) Muscle fiber diameter of the posterior cricoarytenoid muscle. All three measurements were taken after 6 months of recovery, post-surgery.

FIGURE 11. NS-ECM injection. NS-ECM was injected within a silicone conduit to support the grafting of the first cervical nerve to the RLn three months post-injury.

20 6. DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to a peripheral nerve-specific hydrogel material, which is deliverable in a minimally invasive fashion, that is capable of sustaining the growth of neurons and promoting recovery following surgical reconstruction.

25 In certain non-limiting embodiments, the present invention provides for a nerve tissue-specific decellularized scaffold and hydrogel for peripheral nerve repair, wherein the scaffold material is derived through the decellularization of a peripheral nerve. In non-limiting embodiments, as exemplified below, a portion of the peripheral nerve may be used to form the scaffold. Said peripheral nerve can be
30 obtained from an autologous or a non-autologous source. In one non-limiting embodiment, said peripheral nerve is obtained from a non-autologous source, such as syngenic, allogeneic or xenogenic source which may be of the same or a different species, such as a human or a non-human animal such as a non-human primate, a dog, a cat, a horse, a cow, a sheep, a goat, or a pig. In non-limiting embodiments, the

peripheral nerve is a sciatic nerve, femoral nerve, ulnar nerve, median nerve, musculocutaneous nerve, common peroneal nerve, sural nerve or other motor or sensory nerve. In one specific non-limiting embodiment, the peripheral nerve is an equine sciatic nerve.

5 The scaffold material retains sufficient nerve specific components so as to effectively support nerve repair. The hydrogel form of the scaffold is injectable at sites of nerve repair, and has been shown effective in promoting nerve functional recovery and in reducing muscular atrophy when used at sites of nerve repair in the recurrent laryngeal nerve.

10 In certain non-limiting embodiments, the present invention provides one or more of the following advantages:

- a method of decellularization which reduces immunogenic cellular components to a minimal level while retaining a large number of peripheral nerve-specific components;
- 15 • a hydrogel which is peripheral nerve specific (the inventors are not aware of any other peripheral nerve specific decellularized hydrogel, and data supports the concept that tissue specific scaffolds generate a superior response to generic xenogeneic scaffolds); and
- the material has been demonstrated to promote recovery following injection
20 around surgically reconstructed peripheral nerves in a clinically relevant large animal model.

Accordingly, in certain embodiments the invention provides for a hydrogel comprising a decellularized peripheral nerve scaffold that has been enzymatically degraded to form a hydrogel, wherein the hydrogel promotes peripheral
25 nerve repair. In specific non-limiting embodiments, the hydrogel is injected into or comprised in a conduit, as is known in the art to facilitate or guide the regrowth of nerves. The conduits can be absorbable or non-absorbable. Suitable conduits include, but are not limited to, three types of bioabsorbable conduit that have been approved by the US Food and Drug Administration: conduits constructed of collagen,
30 polyglycolic acid, or caprolactone (Deal 2012).

In a non-limiting embodiment, peripheral nerve extracellular matrix (ECM) may be prepared as follows. A peripheral nerve, for example a sciatic nerve, may be harvested and then frozen for at least 16h at -80°C. The epineurium may be stripped and the tissue quartered longitudinally and cut into lengths of < 5cm.

Decellularization may then be performed as previously described by Medberry (2013). For example, the decellularization process may comprise a series of agitated washes: water (type 1), 0.02% trypsin/0.05% EDTA (60 min at 37°C), 3.0% Triton X-100 (60 min), water rinse (type 1, repeated until agitation no longer produced bubbles), 1M sucrose (15 min), 4.0% sodium deoxycholate (60 min), 0.1% peracetic acid/4% ethanol (120 min), 1X PBS (15 min), water (15 min), water (15 min), 1X PBS (15 min). Following treatment samples may be frozen (-80°C) and then lyophilized.

In non-limiting embodiments, enzymatic degradation product and ECM hydrogel may be prepared as follows. Lyophilized scaffold materials may be powdered using a Wiley mill through a 40 mesh screen. The powdered material may be solubilized at a concentration of 20 mg/mL in a solution containing 2.0 mg/mL pepsin in 0.01 N HCl at a constant stir rate for 48h. The ECM digest solution may then be frozen at -20°C until use. Enzymatic digestion may be stopped by raising the pH of the solution to 7.4 using NaOH and diluting the solution to the desired concentration with PBS. Gellation of the neutralized digest may be induced by increasing the temperature of the gel into the physiologic range 37°C.

Alternative decellularization processes and methods of generating ECM degradation product are known in the art and may be used where the resulting product is at least 50% or at least 80% or at least 90% as peripheral nerve specific as the hydrogel prepared according to the method set forth above. Other potential variations upon the hydrogel may include addition of bioactive components or therapeutic agents. Therapeutic agents within the hydrogel can be used in various ways. The therapeutic agent can be released from the hydrogel. For example, an anti-inflammatory drug can be released from the hydrogel to decrease an immune response. Additionally or alternatively, the therapeutic agent can be substantially remain within the hydrogel. For example, a chemoattractant can be maintained within the hydrogel to promote cellular migration and/or cellular infiltration into the hydrogel. At least one therapeutic agent can be added to the hydrogel before it is injected into a conduit. Suitable therapeutic agents can include any substance that can be coated on, embedded into, absorbed into, adsorbed onto, or otherwise attached to or incorporated onto or into the hydrogel that would provide a therapeutic benefit to an intended recipient. Suitable therapeutic agents include, but are not limited to, antimicrobial agents, growth factors, emollients, retinoids, and topical steroids. Each

therapeutic agent may be used alone or in combination with others. In one non-limiting embodiment, the hydrogel comprises neurotrophic agents or cells that express neurotrophic agents, which hydrogel is used for nerve repair.

The therapeutic agent can be a growth factor, such as a neurotrophic or angiogenic factor, which optionally may be prepared using recombinant techniques. Suitable growth factors include, but are not limited to, basic fibroblast growth factor (bFGF), acidic fibroblast growth factor (aFGF), vascular endothelial growth factor (VEGF), hepatocyte growth factor (HGF), insulin-like growth factors 1 and 2 (IGF-1 and IGF-2), platelet derived growth factor (PDGF), stromal derived factor 1 alpha (SDF-1 alpha), nerve growth factor (NGF), ciliary neurotrophic factor (CNTF), neurotrophin-3, neurotrophin-4, neurotrophin-5, pleiotrophin protein (neurite growth-promoting factor 1), midkine protein (neurite growth-promoting factor 2), brain-derived neurotrophic factor (BDNF), tumor angiogenesis factor (TAF), corticotrophin releasing factor (CRF), transforming growth factors α and β (TGF- α and TGF- β), interleukin-8 (IL-8), granulocyte-macrophage colony stimulating factor (GM-CSF), interleukins, and interferons. Commercial preparations of various growth factors, including neurotrophic and angiogenic factors, are available from R & D Systems, Minneapolis, Minnesota; Biovision, Inc, Mountain View, California; ProSpec-Tany TechnoGene Ltd., Rehovot, Israel; and Cell Sciences®, Canton, Massachusetts.

Additionally or alternatively, the therapeutic agent can be an antimicrobial agent. Suitable antimicrobial agents include, but are not limited to, isoniazid, ethambutol, pyrazinamide, streptomycin, clofazimine, rifabutin, fluoroquinolones, ofloxacin, sparfloxacin, rifampin, azithromycin, clarithromycin, dapsone, tetracycline, erythromycin, ciprofloxacin, doxycycline, ampicillin, amphotericin B, ketoconazole, fluconazole, pyrimethamine, sulfadiazine, clindamycin, lincomycin, pentamidine, atovaquone, paromomycin, diclazaril, acyclovir, trifluorouridine, foscarnet, penicillin, gentamicin, ganciclovir, iatroconazole, miconazole, Zn-pyrithione, and silver salts such as chloride, bromide, iodide and periodate.

The therapeutic agent can be an anti-inflammatory agent. Suitable anti-inflammatory agents include, but are not limited to, a NSAID, such as salicylic acid, indomethacin, sodium indomethacin trihydrate, salicylamide, naproxen, colchicine, fenoprofen, sulindac, diflunisal, diclofenac, indoprofen, sodium salicylamide; an anti-inflammatory cytokine; an anti-inflammatory protein; a steroidal

anti-inflammatory agent; and an anti-clotting agent, such as heparin. Other drugs that may promote wound healing and/or tissue regeneration may also be included.

Another variation may include polymeric components or additional biologic components in addition to the hydrogel. Another variation would include the hydrogel which has been seeded with cells prior to or at the time of injection. The cells that are integrated may remain after the hydrogel has fully disintegrated within the conduit. However, the microintegrated cells may also be merely cells that act as precursors to the final tissue that is formed when the hydrogel has fully degraded. Cells may be autologous (obtained from the intended recipient), from an allogeneic or xenogeneic source or from any useful cell line, including, but not limited to, stem cells or precursor cells (cells that can differentiate into another cell type) that are capable of cellular growth, remodeling, and/or differentiation. Suitable cells that can be incorporated onto or into the hydrogel include, but are not limited to, stem cells, precursor cells, smooth muscle cells, skeletal myoblasts, myocardial cells, endothelial cells, fibroblasts, chondrocytes and genetically modified cells. Various commercially available cell lines include Clonetics® Primary Cell Systems (Lonza Group, Inc., Switzerland), ATCC.

Non-limiting examples of uses of the hydrogel of the invention include the following.

In certain non-limiting embodiments, the hydrogel may be injected within a conduit to be used to bridge critically sized defects. A “critically sized defect”, as used herein, is a defect not amenable to joining anastomosis, for example, but not limited to, a gap of at least about 10 mm, or a gap of at least about 15 mm, or a gap of at least about 20 mm.

In certain non-limiting embodiments, the hydrogel may be used to support direct peripheral nerve repair either soon after injury (acute) or after a period of delay (chronic), *e.g.*, at least about two weeks delay, at least about 1-month delay, at least about 2-months delay, at least about 3-months delay, at least about 4-months delay, at least about 5-months delay, at least about 6-months delay, at least about 12-months delay, or at least about 24-months delay, and/or up to about 2-years delay, up to about 3-years delay, up to about 4-years delay, or up to about 5-years delay. Delays often occur prior to nerve repair to allow soft tissue and orthopedic injuries to heal.

In certain non-limiting embodiments, the hydrogel may be used to support a peripheral nerve graft used to reinnervate a denervated nerve either soon after injury (acute) or more commonly after a period of delay (chronic), *e.g.*, at least about two weeks delay, at least about 1-month delay, at least about 2-months delay, at least about 3-months delay, at least about 4-months delay, at least about 5-months delay, at least about 6-months delay, at least about 12-months delay, or at least about 24-months delay, and/or up to about 2-years delay, up to about 3-years delay, up to about 4-years delay, or up to about 5-years delay. In one non-limiting embodiment, the delay is about 3 months.

In certain non-limiting embodiments, the hydrogel may be used to bridge critical gaps in peripheral nerves. These gaps could arise as a result of traumatic injury or iatrogenic injury during surgery for example tumour removal.

7. EXAMPLES

15 *Example 1:*

Equine sciatic nerve was harvested at the Cornell University College of Veterinary Medicine following euthanasia of adult animals for reasons unrelated to the sciatic nerve. The tissue was then frozen for at least 16h at -80°C. The epineurium was stripped and the tissue was quartered longitudinally and cut into lengths of < 5cm. Decellularization was then performed as previously described by Medberry (2013). Briefly, the decellularization process consisted of a series of agitated washes: water (type 1), 0.02% trypsin/0.05% EDTA (60 min at 37°C), 3.0% Triton X-100 (60 min), water rinse (type 1, repeated until agitation no longer produced bubbles), 1M sucrose (15 min), 4.0% sodium deoxycholate (60 min), 0.1% peracetic acid/4% ethanol (120 min), 1X PBS (15 min), water (15 min), water (15 min), 1X PBS (15 min). Following treatment samples were frozen (-80°C) and then lyophilized.

Enzymatic degradation products were generated as previously described. Briefly, lyophilized scaffold materials were powdered using a Wiley mill through a 40 mesh screen. The powdered material was solubilized at a concentration of 20 mg/mL in a solution containing 2.0 mg/mL pepsin in 0.01 N HCl at a constant stir rate for 48h. The ECM digest solution was then frozen at -20°C until use in subsequent experiments. Enzymatic digestion was stopped by raising the pH of the solution to 7.4 using NaOH and diluting the solution to the desired concentration with

PBS. Gellation of the neutralized digest is induced by increasing the temperature of the gel into the physiologic range 37° C.

Example 2:

Animals (Sprague Dawley rats, female 240-280g) were anesthetized and an approach made through the lateral thigh to the sciatic nerve. The nerve was transected proximal to the bifurcation, The nerve ends were drawn 1 mm into a 17 mm silicone conduit and secured with 9/0 ETHILON™ Nylon Suture to create a critical gap defect of 15 mm. The conduit was filled with either nerve specific (NS)-ECM hydrogel or left empty. The ECM was prepared from a canine source. Two minutes were allowed for hydrogel formation and the muscle and skin layers were closed.

Regenerating nerve gaps were excised at 21 days, inspected grossly and fixed for immunohistochemistry. Gaps filled with NS-ECM showed improved axonal regrowth from the proximal nerve stump compared to empty conduits both grossly (Figure 6) and on immunohistochemical section.

These data support the ability of NS-ECM to bridge critical gaps in peripheral nerves.

Example 3 - Nerve-Specific Extracellular Matrix Hydrogel Promotes Recovery Following Reconstruction of the Recurrent Laryngeal Nerve

1. SUMMARY

Damage to the nerves that innervate the larynx, in particular the recurrent laryngeal nerve (RLn) can result in severe consequences for patients. Permanent RLn impairment may significantly impact quality of life by increasing vocal effort and reducing voice quality, and in some patients the condition can become life threatening. A number of clinical solutions exist, however functional recovery following these procedures is slow and often incomplete. Therefore, methods that accelerate or improve re-innervation following reconstruction of the RLn are of significant clinical interest. This example describes the production, characterization and use of an injectable, peripheral nerve-specific extracellular matrix (NS-ECM) based hydrogel to improve outcomes following reconstruction of the RLn. The hydrogel was tested in a canine model of RLn transection and anastomosis. The anastomosis was enclosed by a silicon conduit and either left empty or injected with either a NS-ECM hydrogel or a non-nerve-specific extracellular matrix, urinary bladder matrix (UBM) hydrogel. After 6 months, both NS-ECM and UBM

significantly increased the amplitude of stimulation reaching the vocalis muscle (0.744 mV and 0.719mV respectively) compared to the conduit alone (0.343mV). Afterwards, the posterior cricoarytenoid muscle was harvested and muscle fiber diameter was measured. Differences between the control and treatment groups (NS-
5 ECM and UBM) are small but significant, *e.g.*, 53.5µm compared to 58.4µm and 61.7µm, respectively. These results show that the NS-ECM hydrogel can provide supportive scaffolding to promote in vivo axonal repair of the RLn.

2. MATERIALS AND METHODS

10 2.1. Preparation of Peripheral Nerve ECM

Equine sciatic nerve was harvested following euthanasia of adult animals for reasons unrelated to nerve injury or neurological disease. The tissue was then frozen for at least 16h at -80°C. The epineurium was stripped and the tissue was sectioned longitudinally and cut into lengths of < 5cm. Decellularization was
15 performed as described in Example 1.

2.2. Confirmation of Decellularization

Qualitative assessment of DNA content was performed using immuno fluorescence staining. Fixation of lyophilized ECM scaffolds was performed in 10%
20 formalin. Samples were embedded in paraffin, sectioned, and stained with H&E or with DAPI to verify removal of nuclei. Additional samples were stained using Luxol™ fast blue (registered trademark of Rohm and Haas Co.) to determine removal of myelin. Qualitative assessment of DNA content was conducted by digesting the ECM scaffold in 0.1 mg/mL proteinase K solution. The protein was removed by
25 repeated Trizol extraction and centrifugation (10,000 G) until no white precipitation (protein) was observed at the interface while the aqueous layer extract was mixed with 3 M sodium acetate and 100 % ethanol. The solution was frozen using dried ice and centrifuged to produce a DNA pellet. The pellet was rinsed with 70% ethanol, centrifuged (10,000 G), and dried. Double-stranded DNA was quantified using
30 PicoGreen following kit instructions.

2.3 Assessment of Scaffold Architecture

Scaffold architecture was assessed by scanning electron microscopy (SEM), histologic staining, and immunolabeling. For SEM, lyophilized samples were

fixed in cold 2.5% (v/v) glutaraldehyde in PBS for at least 24 h, followed by three washes in PBS. Lipid fixation was performed in 1% (w/v) osmium tetroxide (Electron Microscopy Sciences) for 1 h followed by three washes in PBS. Fixed samples were then dehydrated using a graded series of ethanol–water solutions (30%–100%) followed by 15 min in hexamethyldisilylthane and subsequent air-drying. The dried samples were mounted onto aluminum stubs and sputter coated with a 3.5 nm layer of gold–palladium alloy using a Sputter Coater 108 Auto (Cressington Scientific Instruments). Images were taken with a scanning electron microscope (JEOL JSM6330f).

For histologic analysis, scaffold materials were fixed in 10% neutral buffered formalin, embedded in paraffin and sectioned at 5 μ m. Samples were dewaxed using xylenes and a graded series of ethanol washes (100–70%) then stained using hematoxylin and eosin. Stained samples were dehydrated using the reverse of the procedure above, coverslipped, and viewed under a light microscope (Nikon e600).

Immunolabeling was performed with antibodies specific to ECM components indicative of the neuronal basal lamina (collagen IV and laminin) and more general connective components (collagen I and III). Briefly, after deparaffination, all slides were subjected to antigen retrieval by immersion in 95°C–100°C in citric acid solution (10 mM, pH 6.0; 20 min) followed by rinsing in a 1X Tris buffered saline/Tween-20 solution (0.1% Tween 20 v/v, pH 7.4; 3 washes, 5 min each). Samples were then washed in PBS and treated with a pepsin digestion (0.05% pepsin w/v in 10 mM HCl) solution for further antigen retrieval. Samples were blocked against nonspecific binding using a solution consisting of 2% horse serum, 1% bovine serum albumin, 0.1% Tween-20, and 0.1% Triton X-100 in PBS for 30 min at room temperature. Primary antibodies were diluted in the blocking solution and applied to sections overnight at 4°C. Antibodies to collagen I, III, and IV (Sigma) were used at a concentration of 1/200. Samples were washed in PBS and appropriate fluorescently labeled secondary antibodies (AlexaFluor 488) were applied for 30 min at room temperature. All secondary antibodies were diluted 1:250 in the blocking solution. Slides were washed in PBS and coverslipped in the aqueous mounting medium before observation under a fluorescent microscope (Nikon e600).

2.4 Generation of enzymatic degradation products

Enzymatic degradation products were generated as described in Example 1.

5

2.5 Evaluation of effects of enzymatic degradation products upon neurite outgrowth

Spinal cord neurons were isolated from embryonic day 14 Sprague-Dawley rat pups. Spinal cords were collected in cold Hanks' buffered salt solution without Ca^{2+} and Mg^{2+} (14 170-112, Gibco, Carlsbad, CA, USA), minced into pieces approximately 0.5 mm in size and enzymatically dissociated in 2 ml 0.25% trypsin solution containing 0.05% collagenase L1 (MP Biomedicals, Solon, OH, USA) at 37°C for 20 min. Cell digestion was inhibited by adding 2 ml SBTI-DNase solution (0.52 mg/ml soybean trypsin inhibitor, T-9003; 3.0 mg/ml BSA, A-2153; 0.04 mg/ml bovine pancreas DNase, D-4263; Sigma). The cell suspension was gently triturated and centrifuged at 800×g for 5 min. The resulting pellet was then resuspended in plating medium and gently triturated. The plating medium consisted of 20% horse serum (16 050-130, Gibco), (25 030- 081, Gibco), 5 ml HBSS without Ca^{2+} and Mg^{2+} (14 170- 112, Gibco) and 9.8 ml Dulbecco's modified Eagle's medium with L-glutamine (DMEM; D5648, Sigma). All non-dispersed tissue was allowed to settle before being discarded. Spinal cord neurons were seeded on poly-L-lysine-coated coverslips (12.5 µg/ml in H_2O ; P1274, Sigma) in plating medium at a plating density of 3×10^5 cells/mL and allowed to adhere for 4 h in culture conditions of 5% CO_2 and 37°C. After 4h, the medium was exchanged with 1 ml serum-free culture medium containing Neurobasal-A (NBA, 10 888-022, Gibco), and 1 mM Glutamax (35 050-061, Gibco). As a positive control, 1× B27 supplement was added to the media. The cells were maintained in a humidified 5% CO_2 atmosphere at 37°C, with 50% of the culture medium changed every 4 days. Three images at 20X magnification were taken per well. The number of cells with neurite extensions and the length of neurite extensions were counted using NeuronJ (ImageJ,NIH).

30

2.6 Formation of hydrogel from enzymatic degradation products

Gelation was induced by adjusting the pH of the pepsin digest to 7.4 using 0.1M NaOH and PBS. Neutralization was accomplished by the addition of one-

tenth the digest volume of 0.1 N NaOH, one-ninth the digest volume of 10X PBS, and then diluting to the desired final ECM concentration. Concentrations between 8 and 15 mg/mL were examined for their ability to form a hydrogel. Dilutions were performed on ice and ECM pre-gel was cast into a stainless steel ring within a 6 well cell culture cluster. The gel solution was placed in a non-humidified 37°C and allowed to gel for 1h. Resultant hydrogels were then investigated using SEM as described above.

2.7 Evaluation of hydrogel cellular compatibility

N1E-115 mouse neuroblastoma cells (ATCC No. CRL 2263), were cultured in DMEM (Sigma) with 10% fetal bovine serum (FBS; Thermo Fisher Scientific, Waltham MA, USA) /1% pen/strep (Sigma) in T-75 flasks. N1E-115 cells in DMEM with 2.5% FBS/1%pen strep were seeded at a concentration of 8,500 cells on the surface of a 6mg/mL nerve ECM or UBM-ECM gel in a 96 well plate. Wells seeded with cells in a media containing pepsin digest instead of ECM digest were used as controls. Following 18-24hrs in culture with ECM, 2µM calcein-AM and 2µM ethidium homodimer-1 was added to each well to evaluate cytotoxicity. Membrane-permeable calcein-AM, but not ethidium homodimer-1, is hydrolyzed in live cells that fluoresce in green and dead cells that bind and activate ethidium homodimer-1, but not calcein-AM, fluoresce in red.

2.8 Animal anesthetic and surgical procedures

2.8.1 Ethics Statement

This study was performed in accordance with the PHS Policy on Humane Care and Use of Laboratory Animals, the NIH guide for Care and Use of Laboratory Animals, federal and state regulations , and was approved by the Cornell University Institutional Animal Care and Use Committee (IACUC). Animals were brought into the research unit and given a 7 day acclimatization period prior to any procedure. Daily record logs of medical procedures were maintained. Cages with elevated floors were cleaned daily and disinfected biweekly. The animals were fed twice a day to maintain proper body condition, and allowed water ad libitum. Group housing provided socialization and ample space for exercise.

2.8.2 *Animals and Instrumentation*

Eleven female Beagle dogs (age 5-7 years, body weight 6.8 ± 0.7 kg, range 6.4-8.7kg) with no history of upper airway disease and normal laryngeal function, determined endoscopically, were used. Dogs were chosen at random and fasted for at least six hours before anesthetic procedures. At the conclusion of each procedure, dogs were monitored for one hour before returning to their group housing.

After fasting overnight, each dog was anesthetized with dexmedetomidine (2 mcg/kg IV followed by 2 mcg/kg/hour) and maintained under anesthesia at a constant expired isoflurane concentration (approximately 1MAC, 1.3%). Monitoring consisted of continuous electrocardiogram, pulse oximetry, non-invasive blood pressure, capnography and temperature.

Analgesia was provided with pre-operative Meloxicam (0.2 mg/kg body weight) subcutaneously (SQ), followed by meloxicam given as an oral suspension (0.1 mg/kg body weight), daily for four additional days.

2.8.3 *Surgery*

Animals were placed in left lateral recumbency and a lateral approach to the larynx was made in a standard fashion anterior to the right linguofacial vein, the subcutaneous fascia was divided and the main trunk of the right Recurrent Laryngeal nerve (RLn) identified. The RLn was identified and transected 15mm inferior to the cricoid. These experiments were performed on the right side of the larynx as there is evidence for reduced functional recovery of left RLn injury compared to right (Woodson (2008)). Endoscopy using a rigid endoscope (2.7mm diameter, Olympus) was performed to verify right sided paralysis immediately after surgery.

2.8.4 *Experimental Groups*

Animals were randomly (computer generated code) divided into three groups. In the control group, RLn transection was immediately followed by end-end RLn-RLn anastomosis performed using 3–5 epineural stitches of nylon 9-0 suture. Care was taken to avoid driving the needle or suture through the nerve fascicles. The anastomosis was surrounded by a preplaced empty 7mm silicone conduit (3.5mm internal diameter,, Silastic; Dow Corning, Midland,MI) tagged to the perineurium at

either end. In the two treatment groups the conduit was filled with either ECM derived from equine motor nerve (NS-ECM); or with ECM derived from Urinary Bladder Matrix (UBM) and introduced into the conduit lumen via an 18 gauge needle. Hydrogels were brought to room temperature 5 minutes prior to injection into the
5 conduit. The incision was then closed in layers.

Animals were euthanized at 6 months following implantation and laryngeal muscles and nerves harvested bilaterally for histology and immunohistochemistry.

10 2.8.5 Endoscopy

Endoscopy using a rigid endoscope (2.7mm diameter, Olympus) immediately following surgery, and at 2 and 6 months to assess arytenoid movement under light sedation (dexmedetomidine (1 mcg/kgIV), Jansson (2000); Ducharme (2010)).

15

2.8.6 Evoked CMAP detection

Immediately prior to euthanasia, animals were anesthetized and
20 anesthesia was maintained with isoflurane in O₂ via an endotracheal tube capable of detecting evoked compound motor action potentials (CMAP) from the vocalis muscle following proximal stimulation of the recurrent laryngeal nerve (NIM EMG Endotracheal tube, (inner diameter 7.0mm, outer diameter 10.5mm) Medtronic) (Dralle (2008)).

25 The right RLn was exposed by dissection in the mid cervical region and a single monopolar needle (Neuroline monopolar, AMBO Inc.) placed adjacent to the RLn 10cm caudal to the anterior ring of the cricoid cartilage. A supramaximal pulse (8-14mA) was applied to the monopolar needle and the corresponding CMAP recorded at the vocalis muscle (Sierra Wave II, Caldwell Laboratories, Kennewick,
30 WA). Presence/absence and peak amplitude of each CMAP was recorded for each of three repetitions. This procedure was repeated on the left side.

Endoscopy was performed during the same anesthetic episode and the degree of arytenoid abduction at peak inspiration determined under light sedation (Jansson (2000); Ducharme (2010)).

2.8.7 Immunohistochemistry-Muscle

Posterior cricoarytenoid (PCA) and lateral cricoarytenoid (LCA) muscles were harvested from explanted larynges and weighed. Collagen V immunohistochemistry was performed on mid sections of left and right PCA and LCA muscles and minimum fiber (Feret's) diameters determined using custom semi-automated software written in Matlab. 8 μm -thick cryosections of acetone-fixed muscle were used for immunohistochemical analysis. Cryosections were washed with phosphate buffered saline containing 0.05% Tween 20 (PBST) for 3 times (5 min each). Nonspecific staining was blocked with a mixture of 10% rabbit serum and 2xcasein for 30 minutes at room temperature. The primary antibody goat anti-type V collagen antibody (SouthernBiotech, Birmingham, AL) was diluted to 1:1,000 in PBS containing 1xcasein, and the sections were incubated for 1.5 hr at 37°C. Biotinylated rabbit anti-goat IgG (Vector Laboratories, Burlingame, CA) was diluted to 1:200 in PBS, and incubated for 30 min at room temperature. Finally, streptavidin-Texas Red (Molecular Probe, Life Technologies, Grand Island, NY) was used to visualize positive staining (used at 1:200 in PBS), and then the sections were mounted in Vectashield containing Dapi (Vector Laboratories). PBST was used for washing throughout the procedure. Goat IgG was diluted to the same final concentration as primary antibody was used as a negative control. IHC results were examined and photographed using Olympus AX 70 compound microscope.

2.8.8 Histomorphologic Examination-Nerve

Cross-sections were obtained 5mm proximal and 5mm distal to the anastomosis, stained with azur 2-methylene blue-safranin and total number of axons, percentage of myelinated axons, number of fascicles and the number of axons in the largest fascicle delineated using semi-automated software (VLOCITY). Axon number was divided by the area sampled to calculate average myelinated axon density. Samples were stained also with hematoxylin and eosin for histomorphologic examination.

2.8.9 Data Analysis

Raw CMAP data was exported as a text file and analyzed using custom software written in MATLAB to determine peak amplitude and area of the CMAP.

Mean values were determined from the three CMAPs recorded on each side. For each parameter, differences between left and right CMAPs was determined using Wilcoxon-signed rank tests.

5 3. RESULTS

3.1 Confirmation of Decellularization

Effective decellularization of ECM based biomaterials is essential to remove the majority of immunogenic cellular constituents while leaving the tissue-specific structural and functional components intact and promoting an appropriate
10 regenerative response (Brown (2013), Crapo (2011)). A nerve-specific decellularization protocol was used to decellularize equine sciatic nerve (Medberry (2013)). The NS-ECM generated was then fully characterized.

Following decellularization, no nuclei were visible in hematoxylin and eosin (H&E) stained sections under light microscopy (Figure 7A and 7B). In some
15 samples, a small number of nuclei (2-3 nuclei/40X field) were observed when labeled with DAPI (Figure 7C and 7D). When present, retained nuclei were observed within the inner most bundles of the treated tissues. Myelin, a potentially immunogenic axonal component, was removed effectively by the decellularization process (Figure 7E and 7F, Luxol® fast blue).

20 dsDNA content was significantly decreased by approximately 85% in the decellularized tissue (158.1 ± 34.5 ng/mg) was compared to native tissue ($1,043.65 \pm 291.20$ ng/mg (Figure 7G, Quantitative PicoGreen assay). These values are consistent with those reported for multiple FDA approved, commercially available ECM scaffold materials (Gilbert (2009)). Results were compared to those obtained
25 for an ECM material derived from urinary bladder, prepared as reported in Brown (2006), for comparison.

3.2 Maintenance of Extracellular Matrix Ultrastructure and Components

The maintenance of nerve-specific structural and functional
30 components was investigated using electron microscopy, immunofluorescent labeling, and biochemical assays. Decellularized sciatic nerves were characterized under scanning electron microscopy (SEM) by an ultrastructure similar to that of native tissue (Figure 8A-D). In cross section, distinct nerve bundles were observed, with intact epineureum and a dense, intact perineurium surrounding each individual nerve

bundle. The epineurium was less dense and larger pores were observed than in the native tissue. A number of individual reticular fibers were also observed. These larger and smaller fibers likely represent the collagen I and III which comprise the majority of the extracellular matrix of the native epineurium. The architecture of the endoneurium was retained but no longer contained individual nerve fibers (Figure 8G-J).

Organization of collagen I, III, and IV within the decellularized tissues was similar to that of native nerve tissue (Figure 8E-J). Although some structural components were disrupted, the basal lamina was strongly preserved as evidenced by the distribution of collagen IV (a major constituent of the basal lamina) within the decellularized samples. Collagen IV was present both within the endoneurial basal lamina and within the perineurium. The intensity of the staining within the endoneurium, however, was less and the architecture slightly disrupted as compared to native tissue.

Biochemical testing was performed to assess the quantity of basic ECM components including hydroxyproline and glycosaminoglycans (GAG) as well as for nerve-specific growth factors including ciliary neurotrophic factor (CNTF) and nerve growth factor (NGF). The decellularization process increased the hydroxyproline concentration from 34.9 ± 9.1 ug/mg in native tissue to 65.0 ± 9.4 ug/mg in NS-ECM (Figure 8K). This enrichment of hydroxyproline content was likely a consequence of removal of other components of the ECM. Conversely, only 60% of initial GAG content was preserved (native 51.3 ± 8.0 ug/mg to 31.0 ± 16.7 ug/mg) (Figure 8M). Enzyme-linked immunosorbent assay (ELISA) showed that 26% and 50% of the native levels of NGF (native 680.9 pg NGF/g tissue ± 160.8 pg/g; NS-ECM 177.0 pg NGF/g ECM ± 33.2 pg/g) and CNTF, respectively, were conserved in the nerve ECM scaffold (Figure 8L and 8N). Despite a non-nerve tissue origin, similar levels of NGF (161.0 pg NGF/g UBM ± 38.5 pg/g) and CNTF were found in the UBM scaffold ((Figure 8L and 8N; and results were similar to those previously reported for UBM.

3.3 Bioactivity of Degradation Products

The degradation products of ECM based scaffold materials derived from decellularization of multiple tissues possess bioactivity including the ability to promote chemotaxis, proliferation and cell differentiation. Once decellularized, NS-

ECM was degraded for processing into a hydrogel as described in Medberry (2013). Briefly, NS-ECM was milled into a powder and digested in a solution of 1 mg/mL pepsin in 0.01 M HCl. The digest solution was then neutralized using 0.1 M NaOH, 10X and 1X PBS at varying concentrations.

5 Bioactivity of the degradation products were analyzed through a neurite outgrowth assay. Primary spinal cord neurons were harvested from E14 Sprague-Dawley rat embryos. Cells were then plated and media supplemented with a range of concentrations of NS-ECM and UBM digests (125, 250, 500 ng/mL). Neurite outgrowth was assessed at time points 1, 2, and 4 days post-plating using an
10 ImageJ based algorithm as previously reported. Results were compared to media supplemented with a neuron survival and growth supplement (B27, positive control), media alone (negative control), or media containing neutralized pepsin at a concentration equal to that of the digested ECM treatment groups (Figure 9A-D). A dose dependent increase in neurite outgrowth was observed at all time points with
15 increasing neurite outgrowth observed to correspond to increasing ECM supplementation.

3.4 Formation of Injectable Hydrogel

The decellularized tissue has been enzymatically digested and those
20 nerve-specific degradation products were found to promote neuronal outgrowth. Those same degradation peptides can be formed into a thermally-sensitive hydrogel. The pepsin digest spontaneously polymerized at neutral pH and body temperature. The ability of this material to gel at various concentrations was investigated. It was found that the digest formed a loose gel as low as 8 mg/mL. The gel was more firm
25 the more concentrated it was prepared. The decellularized tissue was enzymatically digested using pepsin under acidic conditions. The decellularized nerve was formed into a hydrogel which spontaneously polymerized at neutral pH and body temperature at a concentration between 8 mg/ml and 15 mg/ml (Figure 4A-D).

Fiber length was measured by analyzing SEM images at 3000-4000
30 times magnification using Image J. Approximate fiber end-to-end lengths were found to be 10-16 microns on average ($12.1 \mu\text{m} \pm 3.5 \mu\text{m}$). Individual pores were isolated and their diameters were measured using ImageJ software. Pores were randomly distributed throughout the gel and possessed average pore diameter of $2.23 \pm 1.46 \mu\text{m}$ microns.

3.5 Restoration of Nerve Function following Reconstruction of the RLn

Following characterization of the decellularized NS-ECM and corresponding nerve-specific hydrogel, a pilot study evaluating the effects of NS-ECM on anastomosis of the recurrent laryngeal nerve was performed. A canine preclinical model of laryngeal nerve injury, a widely accepted preclinical animal model of human laryngeal disease (Sanders (1993), Kim (2004)), was used.

The right recurrent laryngeal nerve was transected and immediately anastomosed, the anastomosis was surrounded by a silicone conduit and filled with either NS-ECM or UBM hydrogel (15mg/ml, Figure 10A) or left empty (control). Surgical implantation was straightforward with rapid gelling of both hydrogels within the conduit.

Six months after implantation, laryngeal endoscopy revealed arytenoid movement but ineffective abduction, due to synkinetic reinnervation following anastomosis of the common RLn trunk. Under a terminal anesthetic episode, motor action potential conduction across the anastomosis site was determined using supramaximal RLn proximal stimulation and Compound Motor Action Potential (CMAP) recording at the vocalis muscle (Figure 10C)

Both NS-ECM and UBM significantly increased the amplitude of stimulation reaching the vocalis muscle (0.744 mV and 0.719mV respectively) compared to the conduit alone (0.343mV) (Figure 10B).

Minimum Fiber diameter was increased in the NSECM and UBM groups compared to controls in collagen V immuno-labelled right posterior cricoarytenoid (PCA) muscles (Figure 10D). Differences between the control and treatment groups (NS-ECM and UBM) are small but significant, 53.5 μm compared to 58.4 μm and 61.7 μm respectively. Together these data suggest that NS-ECM and UBM hydrogels improve nerve repair with anastomosis.

4. *DISCUSSION*

4.1 Effective decellularization

Decellularization of xenogeneic tissue offers a number of potential benefits: the minimization of immunogenic reactions that would lead to graft rejection, the provision of an optimized biomaterial without competing donor cells, and a reduced risk of disease transmission. However, any processing step intended to

remove cells will alter the native three-dimension architecture of the ECM to some degree. Therefore it is generally desirable to use the mildest protocol possible that yields an acellular material with the least disruption to the structural and functional components of the ECM. The decellularization method used in this Example
5 produced an 85% decrease in DNA content when compared to native tissue (85%; 158.1 ± 34.5 ng/mg, $1,043.65 \pm 291.20$ ng/mg).

The above-presented results demonstrate effective generation of NS-ECM hydrogel, and that NS-ECM hydrogel retains microarchitecture and promotes dose-dependent neurite extension (bioactive). The results also show that NS-ECM is
10 a practical solution for supporting nerve repair, *e.g.*, gels rapidly (within 60 seconds) and is readily injected into conduit at site of injury.

4.2 Determination of reinnervation of the vocalis muscle using the above-described method

15 Supramaximal proximal nerve stimulation and recording of a compound motor action potential at the vocalis muscle allows quantification of reinnervation across the anastomosis site. Reinnervation of the thyroarytenoid complex is crucial to the restoration of vocal cord function and voice. Although posterior cricoarytenoid muscle fiber diameters were increased in both treated groups,
20 functional recover was poor with un-coordinated arytenoid movement and little abduction was achieved. This result is expected with repair to the common trunk of the RLn in which abductor and adductor fibers are spatially intermingled (Crumley (2000), Benjamin (2003), Zealear (2006)).

Manipulation of the microenvironment at the site of nerve injury
25 promotes improved repair. An inert but non-absorbable silicone conduit was used in this Example to maintain this microenvironment. Multiple interventions have been shown to improve axonal regrowth in rodent models, however, the translation to clinical therapies in human patients has been slow. A preclinical large animal model of laryngeal nerve injury was used in this Example to assess NS-ECM. One of the
30 advantages of this approach is that nerve regrowth in large animal models is slower and less regenerative than in rodent systems. Even the gold standard of care for nerve gap defects, the autologous nerve graft is associated with various clinical complications, including donor site morbidity, limited availability, nerve site mismatch, and the formation of neuromas.

Scaffold based approaches using individual extracellular matrix proteins such as keratin, collagen and fibronectin have also been shown to support axonal regrowth (Hill (2011); Madison (1985); Madison (1988); Toba (2001); Lee (2006); Sierpinski (2008a)) and enhance Schwann cell function (Sierpinski (2008b)).

5 Here, the complete milieu of NS- ECM products to promote repair was recruited.

The ECM is the framework including both structural and functional proteins that provides the environment that cells live in. The ECM provides cues for cell attachment, migration, and proliferation but also is manipulated by resident cells. This dynamic interaction between ECM and cells is key for tissue development and
10 homeostasis. Because of these important functions, biological scaffolds composed of ECM have been used in a wide variety of tissue engineering and regenerative medicine applications, including ventral hernia repair, musculoskeletal tissue reconstruction, dura mater replacement, reconstructive breast surgery, pelvic floor reconstruction, and the treatment of cutaneous ulcers, among others. These materials
15 act as inductive templates for the generation of new functional, site-appropriate tissue formation (Brown (2013); Badylak (2014)).

An inductive, ECM based scaffold approach was investigated as a solution to this problem. The advantage of using a decellularized tissue or ECM scaffold is that it promotes constructive remodeling by initially providing an acellular
20 structure that degrades rapidly, releasing mitogenic and chemotactic proteins. These modulate the innate immune system to promote a friendly rather than destructive immune response. As a whole, it encourages the formation of new functional tissue (Sobotka (2011)).

ECM scaffolds derived through the decellularization of a wide array of
25 tissues and organs have been successfully to treat injuries in variety of preclinical and clinical applications, including skeletal muscle, the esophagus, and lower urinary tract, among others (Wang (2011a)). Recent evidence suggests that ECM scaffolds derived from site-specific tissue can elicit a superior functional recovery in some applications (Wang (2011b)). The presence of a site specific advantage was
30 investigated by comparing the peripheral nerve based scaffold used in this Example to urinary bladder matrix, which is a widely used biologic scaffold.

Not all of the proposed decellularization methods have been shown to be effective for removal of sufficient cellular content and maintenance of tissue structure, resulting in ineffective recovery in some studies. For this reason, histologic,

immunologic, and quantitative methods was used to validate the decellularization process.

A peripheral nerve based hydrogel was derived, characterized and tested in a canine model of laryngeal nerve transection and reconstruction in this Example. A peripheral nerve was decellularized maintaining peripheral NS-ECM components, including nerve specific growth factors. The decellularized tissue was enzymatically digested into a mixture of degradation peptides. That mixture of peptides was found to be bioactive and to promote neurite outgrowth. The peptide mixture was then formed into a hydrogel and injected it into a clinically relevant model of nerve transection. It was found that the NS-ECM hydrogel improves recovery with anastomosis.

Example 4:

Animals as described in Example 3 were anesthetized and placed in left lateral recumbency and a lateral approach to the larynx was made in a standard fashion anterior to the right linguofacial vein. The subcutaneous fascia was divided and the main trunk of the right RLn was identified. The RLn was identified and transected 15 mm inferior to the cricoid. The incisions were then closed in layers and animals were allowed to develop chronic denervation of the RLn for three months. After three months, the animals were again anesthetized as described above and a nerve graft was performed. The cervical nerve was grafted to the recurrent laryngeal nerve by anastomosis of the two ends of each nerve. The anastomosis was surrounded by a preplaced empty 7 mm silicone conduit (3.5 mm internal diameter, Silastic; Dow Corning, Midland, MI) tagged to the perineurium at either end. As shown in Figure 11, in the treatment group, the conduit was filled with ECM derived from equine motor nerve (NS-ECM introduced into the conduit lumen via an 18 gauge needle). Hydrogels were brought to room temperature 5 minutes prior to injection into the conduit. The incision was then closed in layers.

These data demonstrate that NS-ECM can be used to support nerve grafting either soon after injury (acute) or after a period of delay (chronic).

7. REFERENCES

- 1, Nagao RJ, Lundy S, Khaing ZZ, Schmidt CE., Neurol Res. 2011 Jul;33(6):600-8

2. Hudson TW, Zawko S, Deister C, Lundy S, Hu CY, Lee K, Schmidt CE, Tissue Eng. 2004 Nov-Dec;10(11-12):1641-51.
3. Hudson TW, Liu SY, Schmidt CE. Tissue Eng. 2004 Sep-Oct;10(9-10):1346-58.
- 5 4. Medberry CJ, Crapo PM, Siu BF, Carruthers CA, Wolf MT, Nagarkar SP, Agrawal V, Jones KE, Kelly J, Johnson SA, Velankar SS, Watkins SC, Modo M, Badylak SF., Biomaterials. 2013 Jan;34(4):1033-40.
5. Crapo PM, Medberry CJ, Reing JE, Tottey S, van der Merwe Y, Jones KE, Badylak SF., Biomaterials. 2012 May;33(13):3539-47.
- 10 6. Wolf MT, Daly KA, Brennan-Pierce EP, Johnson SA, Carruthers CA, D'Amore A, Nagarkar SP, Velankar SS, Badylak SF., Biomaterials. 2012 Oct;33(29):7028-38.
7. US 8,361,503 B2
8. PCT/US2012/045682
- 15 9. Brown BN, Badylak SF. Extracellular matrix as an inductive scaffold for functional tissue reconstruction. Transl Res. 2013 Nov 8. pii: S1931-5244(13)00382-4.
10. Badylak SF. Decellularized Allogeneic and Xenogeneic Tissue as a Bioscaffold for Regenerative Medicine: Factors that Influence the Host Response. Ann Biomed Eng. 2014 Jan 9. [Epub ahead of print]
- 20 11. Nichols, C. M., Brenner, M. J., Fox, I. K., Tung, T. H., Hunter, D. A., Rickman, S. R. & Mackinnon, S. E. Effects of motor versus sensory nerve grafts on peripheral nerve regeneration. *Exp. Neurol.* **190**, 347-355 (2004).
12. Lee, S. K. & Wolfe, S. W. Peripheral nerve injury and repair. *J. Am. Acad. Orthop. Surg.* **8**, 243-252 (2000).
- 25 13. Mackinnon, S. E., Doolabh, V. B., Novak, C. B. & Trulock, E. P. Clinical outcome following nerve allograft transplantation. *Plast. Reconstr. Surg.* **107**, 1419-1429 (2001).
14. Kingham, P. J., Birchall, M. A., Burt, R., Jones, A. & Terenghi, G. Reinnervation of laryngeal muscles: a study of changes in myosin heavy chain expression. *Muscle Nerve* **32**, 761-766 (2005).
- 30 15. Wang, W., Chen, D., Chen, S., Li, D., Li, M., Xia, S. & Zheng, H. Laryngeal reinnervation using ansa cervicalis for thyroid surgery-related unilateral

vocal fold paralysis: a long-term outcome analysis of 237 cases. *PLoS One* **6**, e19128 (2011a). PMID: PMC3084757.

16. Wang, W., Chen, S., Chen, D., Xia, S., Qiu, X., Liu, Y. & Zheng, H. Contralateral ansa cervicalis-to-recurrent laryngeal nerve anastomosis for unilateral
5 vocal fold paralysis: A long-term outcome analysis of 56 cases. *Laryngoscope* **121**, 1027-1034 (2011b).

17. Sobotka, S. & Mu, L. Force characteristics of the rat sternomastoid muscle reinnervated with end-to-end nerve repair. *J. Biomed. Biotechnol.* **2011**, 173471 (2011). PMID: PMC3238804.

- 10 18. Lorenz, R. R., Esclamado, R. M., Tekker, A. M., Strome, M., Scharpf, J., Hicks, D., Milstein, C. & Lee, W. T. Ansa cervicalis-to-recurrent laryngeal nerve anastomosis for unilateral vocal fold paralysis: experience of a single institution. *Ann. Otol. Rhinol. Laryngol.* **117**, 40-45 (2008).

- 15 19. Smith, M. E., Roy, N. & Stoddard, K. Ansa-RLN reinnervation for unilateral vocal fold paralysis in adolescents and young adults. *Int. J. Pediatr. Otorhinolaryngol.* **72**, 1311-1316 (2008).

20. Aynehchi, B. B., McCoul, E. D. & Sundaram, K. Systematic review of laryngeal reinnervation techniques. *Otolaryngol. Head. Neck. Surg.* **143**, 749-759 (2010).

- 20 21. Birchall, M. A., Lorenz, R. R., Berke, G. S., Genden, E. M., Haughey, B. H., Siemionow, M. & Strome, M. Laryngeal transplantation in 2005: a review. *Am. J. Transplant.* **6**, 20-26 (2006).

22. Hill, P. S., Apel, P. J., Barnwell, J., Smith, T., Koman, L. A., Atala, A. & Van Dyke, M. Repair of peripheral nerve defects in rabbits using keratin hydrogel
25 scaffolds. *Tissue Eng. Part A.* **17**, 1499-1505 (2011).

23. Madison, R., Da Silva, C. F., Dikkes, P., Chiu, T. H. & Sidman, R. L. Increased rate of peripheral nerve regeneration using bioresorbable nerve guides and a laminin-containing gel. *Exp. Neurol.* **88**, 767-772 (1985).

24. Madison, R. D., Da Silva, C. F. & Dikkes, P. Entubulation repair with
30 protein additives increases the maximum nerve gap distance successfully bridged with tubular prostheses. *Brain Res.* **447**, 325-334 (1988).

25. Toba, T., Nakamura, T., Shimizu, Y., Matsumoto, K., Ohnishi, K., Fukuda, S., Yoshitani, M., Ueda, H., Hori, Y. & Endo, K. Regeneration of canine peroneal nerve with the use of a polyglycolic acid-collagen tube filled with laminin-

soaked collagen sponge: a comparative study of collagen sponge and collagen fibers as filling materials for nerve conduits. *J. Biomed. Mater. Res.* **58**, 622-630 (2001).

26. Lee, D. Y., Choi, B. H., Park, J. H., Zhu, S. J., Kim, B. Y., Huh, J. Y., Lee, S. H., Jung, J. H. & Kim, S. H. Nerve regeneration with the use of a poly(l-lactide-co-glycolic acid)-coated collagen tube filled with collagen gel. *J. Craniomaxillofac. Surg.* **34**, 50-56 (2006).
27. Sierpinski, P., Garrett, J., Ma, J., Apel, P., Klorig, D., Smith, T., Koman, L. A., Atala, A. & Van Dyke, M. The use of keratin biomaterials derived from human hair for the promotion of rapid regeneration of peripheral nerves. *Biomaterials* **29**, 118-128 (2008a).
28. Sierpinski, P., Garrett, J., Ma, J., Apel, P., Klorig, D., Smith, T., Koman, L. A., Atala, A. & Van Dyke, M. The use of keratin biomaterials derived from human hair for the promotion of rapid regeneration of peripheral nerves. *Biomaterials* **29**, 118-128 (2008b).
29. Sanders, I., Jacobs, I., Wu, B. L. & Biller, H. F. The three bellies of the canine posterior cricoarytenoid muscle: implications for understanding laryngeal function. *Laryngoscope* **103**, 171-177 (1993).
30. Zeale, D. L., Billante, C. R., Chongkolwatana, C., Rho, Y. S., Hamdan, A. L. & Herzon, G. D. The effects of chronic electrical stimulation on laryngeal muscle physiology and histochemistry. *ORL J. Otorhinolaryngol. Relat. Spec.* **62**, 81-86 (2000).
31. Broome, C., Burbidge, H. M. & Pfeiffer, D. U. Prevalence of laryngeal paresis in dogs undergoing general anaesthesia. *Aust. Vet. J.* **78**, 769-772 (2000).
32. Woodson, G. E., Hughes, L. F. & Helfert, R. Quantitative assessment of laryngeal muscle morphology after recurrent laryngeal nerve injury: right vs. left differences. *Laryngoscope* **118**, 1768-1770 (2008).
33. Jansson, N., Ducharme, N. G., Hackett, R. P. & Mohammed, H. O. An in vitro comparison of cordopexy, cordopexy and laryngoplasty, and laryngoplasty for treatment of equine laryngeal hemiplegia. *Vet. Surg.* **29**, 326-334 (2000).
34. Ducharme, N. G., Cheetham, J., Sanders, I., Hermanson, J. W., Hackett, R. P., Soderholm, L. V. & Mitchell, L. M. Considerations for pacing of the cricoarytenoid dorsalis muscle by neuroprosthesis in horses. *Equine Vet. J.* **42**, 534-540 (2010).

35. Goslin, K., Schreyer, D. J., Skene, J. H. & Banker, G. Changes in the distribution of GAP-43 during the development of neuronal polarity. *J. Neurosci.* **10**, 588-602 (1990).
36. Triolo, D., Dina, G., Lorenzetti, I., Malaguti, M., Morana, P., Del
5 Carro, U., Comi, G., Messing, A., Quattrini, A. & Previtali, S. C. Loss of glial fibrillary acidic protein (GFAP) impairs Schwann cell proliferation and delays nerve regeneration after damage. *J. Cell. Sci.* **119**, 3981-3993 (2006).
37. Cheetham, J., Radcliffe, C. R., Ducharme, N. G., Sanders, I., Mu, L. & Hermanson, J. W. Neuroanatomy of the equine dorsal cricoarytenoid muscle: Surgical
10 implications. *Equine Vet. J.* **40**, 70-75 (2008).
38. Crumley, R. L. Laryngeal synkinesis revisited. *Ann. Otol. Rhinol. Laryngol.* **109**, 365-371 (2000).
39. Affleck BD, Swartz K, Brennan J 2003 Surgical consideration and controversies in thyroid and parathyroid surgery. *Otolaryngol Clin North Am* 36:159–
15 187Spector BC, Netterville JL, Billante C, Clary J, Reinisch L, Smith TL 2001 Quality-of-life assessment in patients with unilateral vocal cord paralysis. *Otolaryngol Head Neck Surg* 125:176–182
40. Laccourreye O, Crevier-Buchman L, Pacona R, Ageel M, Brasnu D 1999 Intracordal fat injection for aspiration after recurrent laryngeal nerve paralysis.
20 *Eur Arch Otolaryngol* 256:458–461
41. Negus VE 1929 The mechanism of the larynx. London: W. M. Heinemann Ltd.; 1–45
42. Wolf, M., Daly, K., Reing, J., & Badylak, S. (2012). Biologic scaffold composed of skeletal muscle extracellular matrix. *Biomaterials*, 33(10), 2916-25.
- 25 43. Sawkings, M., Bowen, W., Dhadda, P., Markides, H., Sidney, L., Taylor, A., & White, L. (2013). Hydrogels derived from demineralized and decellularized bone extracellular matrix. 9(8), 7865-73.
44. Badylak, S. (2011, October). *Regenerative medicine: Possibilities and potencial*. The singularity summit.
- 30 45. Dralle H. Intraoperative monitoring of the recurrent laryngeal nerve in thyroid surgery. *World J Surg.* 2008 32(7): 1358-1366.
46. Crapo PM, Gilbert TW, Badylak SF. An overview of tissue and whole organ decellularization processes. *Biomaterials*. 2011 Apr;32(12):3233-43.

47. Gilbert TW, Freund JM, Badylak SF. Quantification of DNA in biologic scaffold materials. *J Surg Res.* 2009 Mar;152(1):135-9.
48. Brown B, Lindberg K, Reing J, Stolz DB, Badylak SF. The basement membrane component of biologic scaffolds derived from extracellular matrix. *Tissue Eng.* 2006 Mar;12(3):519-26.
49. Kim, M. J., Hunter, E. J. & Titze, I. R. Comparison of human, canine, and ovine laryngeal dimensions. *Ann. Otol. Rhinol. Laryngol.* 113, 60-68 (2004).
50. Benjamin, B. Vocal cord paralysis, synkinesis and vocal fold motion impairment. *ANZ J Surg* 73, 784-786 (2003).
51. Zealear, D. L. & Billante, C. R. . In: *Vocal Fold Paralysis* (eds Sulica, L. & Blitzer, A.) 17-32 (Springer Berlin, Heidelberg, 2006).
52. Deal DN, Griffin JW, Hogan MV, Nerve conduits for nerve repair or reconstruction. *J Am Acad Orthop Surg.* 2012 Feb;20(2):63-8.

Various references are cited herein, the contents of which are hereby incorporated by reference in their entirety.

WE CLAIM

1. A hydrogel comprising a decellularized peripheral nerve scaffold that has been enzymatically degraded to form a hydrogel, wherein the hydrogel promotes peripheral nerve repair.
- 5 2. The hydrogel of claim 1, comprised in a conduit.
3. The hydrogel of claim 1 or claim 2, where the peripheral nerve is non-autologous to an intended recipient of the hydrogel.
4. The hydrogel of claim 3, where the peripheral nerve is from an organism that is the same species as the intended recipient.
- 10 5. The hydrogel of claim 3, where the peripheral nerve is from an organism that is not the same species as the intended recipient.
6. A method of repairing a nerve injury, comprising injecting a hydrogel comprising a decellularized peripheral nerve scaffold that has been enzymatically degraded, so as to bridge a gap in the nerve.
- 15 7. The method of claim 6, where the gap is a critically sized defect.
8. The method of claim 6, where the hydrogel is injected into a conduit.
9. The method of claim 7, where the hydrogel is injected into a conduit.
10. The method of any one of claims 6-9, where the peripheral nerve is non-autologous to an intended recipient of the hydrogel.
- 20 11. The method of claim 10, where the peripheral nerve is from an organism that is the same species as the intended recipient.
12. The method of claim 10, where the peripheral nerve is from an organism that is not the same species as the intended recipient.
13. A method of promoting incorporation of a graft to repair a gap in a nerve, comprising providing, into the gap, a graft and a hydrogel comprising a decellularized peripheral nerve scaffold that has been enzymatically degraded.
- 25 14. The method of claim 13, where the gap is a critically sized defect.
15. The method of claim 13, where the hydrogel is injected into a conduit.
16. The method of claim 14, where the hydrogel is injected into a conduit.
- 30 17. The method of any one of claims 13-16, where the peripheral nerve is non-autologous to an intended recipient of the hydrogel.
18. The method of claim 17, where the peripheral nerve is from an organism that is the same species as the intended recipient.

19. The method of claim 17, where the peripheral nerve is from an organism that is not the same species as the intended recipient.

1/15




FIG. 1A




FIG. 1C




FIG. 1B




FIG. 1D




FIG. 1E





FIG. 1F

2/15



3/15




FIG. 3

4/15




FIG. 4A




FIG. 4B




FIG. 4C




FIG. 4D

5/15




FIG. 5A




FIG. 5B





FIG. 5C

6/15

Empty Conduit



NSECM Conduit






FIG. 6

7/15



FIG. 7A




FIG. 7B



FIG. 7C




FIG. 7D




FIG. 7E




FIG. 7F

8/15




FIG. 7G




FIG. 8A FIG. 8B




FIG. 8C FIG. 8D




FIG. 8E FIG. 8F




FIG. 8G FIG. 8H




FIG. 8I FIG. 8J

10/15




FIG. 8K




FIG. 8L




FIG. 8M




FIG. 8N

11/15




FIG. 9A

12/15




FIG. 9B

13/15




FIG. 9C





FIG. 9D

14/15



Scale: conduit=
7.5mm long, 3.5mm I.D

FIG. 10A




FIG. 10B




FIG. 10C




FIG. 10D

15/15




FIG. 11

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US2014/021065**A. CLASSIFICATION OF SUBJECT MATTER****A61L 27/52(2006.01)i, A61F 2/02(2006.01)i**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

A61L 27/52; A61N 1/30; A61F 2/02; A61K 31/715; A61L 27/56; A61K 38/39; A61L 27/38; A61B 17/08

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean utility models and applications for utility models

Japanese utility models and applications for utility models

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKOMPASS(KIPO internal) & keywords: hydrogel, decellularized, peripheral nerve scaffold, extracellular matrix, ECM

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 2012-002986 A2 (THE REGENTS OF THE UNIVERSITY OF CALIFORNIA) 5 January 2012 See abstract; paragraphs [0030]-[0032]; and claims 1, 5, 11.	1-5
Y	US 2008-0125870 A1 (CARMICHAEL, R. W. et al.) 29 May 2008 See abstract; paragraphs [0046], [0051], [0073]; claims 1, 3, 8-9; and figures 1-2.	1-5
A	WO 2013-009595 A2 (UNIVERSITY OF PITTSBURGH OF THE COMMON WEALTH SYSTEM OF HIGHER EDUCATION) 17 January 2013 See abstract; paragraphs [0006], [0047]; and claim 1.	1-5
A	WOLF, M. T. et al. A hydrogel derived from decellularized dermal extracellular matrix. Biomaterials. October 2012, Volume 33, Issue 29, pages 7028-7038. See abstract; pages 7028-7030, 7037.	1-5
A	DEQUACH, M.S., J. A. et al. Decellularized porcine brain matrix for cell culture and tissue engineering scaffolds. Tissue Engineering Part A. 2011, Volume 17, Numbers 21 and 22, pages 2583-2592. See abstract; pages 2583, 2587.	1-5



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

07 May 2014 (07.05.2014)

Date of mailing of the international search report

07 May 2014 (07.05.2014)

Name and mailing address of the ISA/KR

International Application Division
Korean Intellectual Property Office
189 Cheongsu-ro, Seo-gu, Daejeon Metropolitan City, 302-701,
Republic of Korea

Facsimile No. +82-42-472-7140

Authorized officer

MOON, Sun Heup

Telephone No. +82-42-481-8242



INTERNATIONAL SEARCH REPORTInternational application No.
PCT/US2014/021065**Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)**

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☒ Claims Nos.: 6-19
because they relate to subject matter not required to be searched by this Authority, namely:
Claims 6-19 pertain to methods for treatment of the human body and thus relate to a subject-matter which this International Searching Authority is not required, under Article 17(2)(a)(i) of the PCT and Rule 39.1(iv) of the Regulations under the PCT, to search.
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fees, this Authority did not invite payment of any additional fees.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☐ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☐ No protest accompanied the payment of additional search fees.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US2014/021065

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2007-0100358 A2 (ROMERO-ORTEGA, M. et al.) 3 May 2007 See abstract; paragraph [0019]; claims 1-2; and figures 1-2.	1-5

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/US2014/021065

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2012-002986 A2	05/01/2012	US 2012-0264190 A1 WO 2012-002986 A3	18/10/2012 08/03/2012
US 2008-0125870 A1	29/05/2008	EP 2086601 A2 WO 2008-063878 A2 WO 2008-063878 A3	12/08/2009 29/05/2008 19/11/2009
WO 2013-009595 A2	17/01/2013	WO 2013-009595 A3 WO 2013-009595 A9	18/04/2013 11/07/2013
US 2007-0100358 A2	03/05/2007	US 2003-0049839 A1 US 2007-0010831 A1 WO 2005-046457 A2 WO 2005-046457 A3	13/03/2003 11/01/2007 26/05/2005 16/08/2007