

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
4 January 2007 (04.01.2007)

PCT

(10) International Publication Number  
**WO 2007/001569 A1**

(51) International Patent Classification:

*C08G 63/199* (2006.01) *C08J 5/18* (2006.01)  
*C08L 67/02* (2006.01) *G02F 1/1333* (2006.01)

(71) Applicant: **EASTMAN CHEMICAL COMPANY**  
[US/US]; 100 North Eastman Road, Kingsport, TN 37660 (US).

(21) International Application Number:

PCT/US2006/011970

(72) Inventors: **CRAWFORD, Emmett, Dudley**; 3818 Woodleaf Lane, Kingsport, TN 37663 (US). **PECORINI, Thomas, Joseph**; 208 Remington Court, Kingsport, TN 37663 (US). **MCWILLIAMS, Douglas, Stephens**; 291 Grandview Court, Kingsport, TN 37664 (US). **PORTER, David, Scott**; 365 Glasgow Lane, Blountville, TN 37617 (US). **CONNELL, Gary, Wayne**; 212 Gilda Avenue, Church Hill, TN 37642 (US).

(22) International Filing Date: 30 March 2006 (30.03.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:



60/691,567	17 June 2005 (17.06.2005)	US
60/731,389	28 October 2005 (28.10.2005)	US
60/731,454	28 October 2005 (28.10.2005)	US
60/738,869	22 November 2005 (22.11.2005)	US
60/739,058	22 November 2005 (22.11.2005)	US
60/750,547	15 December 2005 (15.12.2005)	US
60/750,682	15 December 2005 (15.12.2005)	US
60/750,692	15 December 2005 (15.12.2005)	US
60/750,693	15 December 2005 (15.12.2005)	US

(74) Agent: **MORENO, Louis, N.**; P.O. Box 511, Kingsport, TN 37662-5075 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI,

[Continued on next page]

(54) Title: POLYESTER COMPOSITIONS CONTAINING HIGH AMOUNTS OF CYCLOBUTANEDIOL AND ARTICLES MADE THEREFROM



(57) Abstract: Described are polyester compositions comprising at least one polyester which comprises terephthalic acid residues, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol, wherein the inherent viscosity and the T<sub>g</sub> of the polyester provides for certain polyester properties. The polyesters may be manufactured into articles such as fibers, films, bottles or sheets.



NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**(84) Designated States** (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,

**Published:**

— *with international search report*

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

## **POLYESTER COMPOSITIONS CONTAINING HIGH AMOUNTS OF CYCLOBUTANEDIOL AND ARTICLES MADE THEREFROM**

### **CROSS-REFERENCES TO RELATED APPLICATIONS**

[001] This application claims priority under 35 U.S.C. § 119(e) to United States Provisional Application Serial No. 60/691,567 filed on June 17, 2005, United States Provisional Application Serial No. 60/731,454 filed on October 28, 2005, United States Provisional Application Serial No. 60/731,389, filed on October 28, 2005, United States Provisional Application Serial No. 60/739,058, filed on November 22, 2005, and United States Provisional Application Serial No. 60/738,869, filed on November 22, 2005, United States Provisional Application Serial No. 60/750,692 filed on December 15, 2005, United States Provisional Application Serial No. 60/750,693, filed on December 15, 2005, United States Provisional Application Serial No. 60/750,682, filed on December 15, 2005, and United States Provisional Application Serial No. 60/750,547, filed on December 15, 2005, all of which are hereby incorporated by this reference in their entireties.

### **FIELD OF THE INVENTION**

[002] The present invention generally relates to polyester compositions made from terephthalic acid, an ester thereof, or mixtures thereof; 2,2,4,4-tetramethyl-1,3-cyclobutanediol; and 1,4-cyclohexanedimethanol, the polyester having a certain combination of inherent viscosity and glass transition temperature ( $T_g$ ). These compositions are believed to have a certain combination of two or more of high impact strengths, high glass transition temperature ( $T_g$ ), toughness, e.g., low ductile-to-brittle transition temperatures, certain inherent viscosities, good color and clarity, low densities, chemical resistance, hydrolytic stability, and long crystallization half-times, which allow them to be easily formed into articles.

## BACKGROUND OF THE INVENTION

[003] Poly(1,4-cyclohexylenedimethylene terephthalate (PCT), a polyester based solely on terephthalic acid or an ester thereof or mixtures thereof and 1,4-cyclohexanedimethanol, is known in the art and is commercially available. This polyester crystallizes rapidly upon cooling from the melt, making it very difficult to form amorphous articles by methods known in the art such as extrusion, injection molding, and the like. In order to slow down the crystallization rate of PCT, copolyesters can be prepared containing additional dicarboxylic acids or glycols such as isophthalic acid or ethylene glycol. These ethylene glycol- or isophthalic acid-modified PCTs are also known in the art and are commercially available.

[004] One common copolyester used to produce films, sheeting, and molded articles is made from terephthalic acid, 1,4-cyclohexanedimethanol, and ethylene glycol. While these copolyesters are useful in many end-use applications, they exhibit deficiencies in properties such as glass transition temperature and impact strength when sufficient modifying ethylene glycol is included in the formulation to provide for long crystallization half-times. For example, copolyesters made from terephthalic acid, 1,4-cyclohexanedimethanol, and ethylene glycol with sufficiently long crystallization half-times can provide amorphous products that exhibit what is believed to be undesirably higher ductile-to-brittle transition temperatures and lower glass transition temperatures than the compositions revealed herein.

[005] The polycarbonate of 4,4'-isopropylidenediphenol (bisphenol A polycarbonate) has been used as an alternative for polyesters known in the art and is a well known engineering molding plastic. Bisphenol A polycarbonate is a clear, high-performance plastic having good physical properties such as dimensional stability, high heat resistance, and good impact strength. Although bisphenol-A polycarbonate has many good physical properties, its relatively high melt viscosity leads to poor melt processability and the polycarbonate exhibits poor chemical resistance. It is also difficult to thermoform.

[006] Polymers containing 2,2,4,4-tetramethyl-1,3-cyclobutanediol have also been generally described in the art. Generally, however, these polymers can exhibit high inherent viscosities, high melt viscosities and/or high Tgs (glass transition temperatures) such that the equipment used in industry can be insufficient to manufacture or post-polymerization process these materials.

[007] Thus, there is a need in the art for a polymer having a combination of two or more properties chosen from at least one of the following: toughness, high glass transition temperatures, high impact strength, hydrolytic stability, chemical resistance, long crystallization half-times, low ductile to brittle transition temperatures, good color and clarity, lower density and/or thermoformability of polyesters while retaining processability on the standard equipment used in the industry.

## **SUMMARY OF THE INVENTION**

[008] It is believed that certain compositions formed from terephthalic acid residues, or an ester thereof, 1,4-cyclohexanedimethanol residues; and 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues with a certain combination of inherent viscosity and glass transition temperatures are superior to polyesters known in the art and to polycarbonate with respect to one or more of high impact strengths, hydrolytic stability, toughness, chemical resistance, good color and clarity, long crystallization half-times, low ductile to brittle transition temperatures, lower specific gravity and/or thermoformability. These compositions are believed to be similar to polycarbonate in heat resistance and are still processable on the standard industry equipment.

[009] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and

ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues, wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to less than 0.70 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 110 to 200°C.

[010] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

i) 70 to 100 mole % of terephthalic acid residues;

ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and

ii) 1 to less than 19 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 110 to 200°C.

[011] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
    - i) 70 to 100 mole % of terephthalic acid residues;
    - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
    - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
  - (b) a glycol component comprising:
    - i) 40 to 85 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
    - ii) 15 to 60 mole % of 1,4-cyclohexanedimethanol residues,
- wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 110 to 200°C.

[012] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
    - i) 70 to 100 mole % of terephthalic acid residues;
    - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
    - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
  - (b) a glycol component comprising:
    - i) 40 to 85 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
    - ii) 15 to 60 mole % of 1,4-cyclohexanedimethanol residues,
- wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5

g/100 ml at 25°C; and wherein said polyester has a Tg from greater than 148 to 200°C.

[013] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 40 to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 20 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 110 to 200°C.

[014] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,



wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 110 to 200°C.

[015] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 40 to 64.9 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 35 to 59.9 mole % of 1,4-cyclohexanedimethanol residues,
  - iii) 0.10 to less than 15 mole % ethylene glycol;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 0.75 dL/g or less as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein said polyester has a Tg from 110 to 200°C.

[016] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 40 to 55 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 45 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein said polyester has a Tg from 110 to 200°C.

[017] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 45 to 55 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 45 to 55 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein said polyester has a Tg of 110 to 200°C.

[018] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;

- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein said polyester has a Tg from 110 to 200°C and optionally, wherein one or more branching agents is added prior to or during the polymerization of the polymer.

[019] In one aspect, this invention relates to a polyester composition comprising:

- (A) at least one polyester which comprises:
  - (a) a dicarboxylic acid component comprising:
    - i) 70 to 100 mole % of terephthalic acid residues;
    - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
    - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
  - (b) a glycol component comprising:
    - i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
    - ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues, and
- (B) residues of at least one branching agent;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein said polyester has a Tg from 110 to 200°C.

[020] In one aspect, this invention relates to a polyester composition comprising:

- (A) at least one polyester which comprises:
  - (a) a dicarboxylic acid component comprising:
    - i) 70 to 100 mole % of terephthalic acid residues;
    - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
    - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
  - (b) a glycol component comprising:
    - i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
    - ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

(B) residues of at least one branching agent;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein said polyester has a Tg from 110 to 200°C.

[021] In one aspect, this invention relates to a polyester composition comprising:

- (A) at least one polyester which comprises:
  - (a) a dicarboxylic acid component comprising:
    - i) 70 to 100 mole % of terephthalic acid residues;

- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues, and
- (B) residues of at least one branching agent;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein said polyester has a Tg from 110 to 200°C.

[022] In one aspect, this invention relates to a polyester composition comprising:

- (A) at least one polyester which comprises:
  - (a) a dicarboxylic acid component comprising:
    - i) 70 to 100 mole % of terephthalic acid residues;
    - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
    - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
  - (b) a glycol component comprising:
    - i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
    - ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues, and
- (B) at least one thermal stabilizer or reaction products thereof;

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein said polyester has a Tg from 110 to 200°C.

[023] In one aspect, this invention relates to a polyester composition comprising:

- (A) at least one polyester which comprises:
  - (a) a dicarboxylic acid component comprising:
    - i) 70 to 100 mole % of terephthalic acid residues;
    - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
    - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
  - (b) a glycol component comprising:
    - i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
    - ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues, and

(B) at least one thermal stabilizer or reaction products thereof; wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein said polyester has a Tg from 110 to 200°C.

[024] In one aspect, this invention relates to a polyester composition comprising:

- (A) at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
    - i) 70 to 100 mole % of terephthalic acid residues;
    - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
    - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
  - (b) a glycol component comprising:
    - i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
    - ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,
- and

(B) at least one thermal stabilizer or reaction products thereof; wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt)phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; wherein said polyester has a Tg from 110 to 200°C.

[025] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 110 to 150°C.

[026] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 40 to 65 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 35 to 60 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 120 to 135°C.

[027] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and



iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and

ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.35 to 0.75 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from greater than 148°C up to 200°C.

[028] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

i) 70 to 100 mole % of terephthalic acid residues;

ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and

ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 127°C to 200°C.

[029] This invention relates to a polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) 1 to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 20 to 99 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg of greater than 124°C to 200°C. In other embodiments, the Tg may be greater than 125°C to 200°C; or greater than 126°C to 200°C; or greater than 127°C to 200°C.

[030] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) greater than 50 up to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) 1 to less than 50 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and

the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 110°C to 200°C.

[031] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 50 up to 80 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 20 to less than 50 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.35 to 01.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 110°C to 200°C.

[032] In one aspect, this invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:

- i) 1 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 1 to 99 mole % of 1,4-cyclohexanedimethanol residues,
- wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is greater than 0.76 up to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 110°C to 200 °C.

[033] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 1 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

[034] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;

- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 1 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 140 to 200°C.

[035] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 1 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[036] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 1 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

[037] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:

- i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) less than 19 to 1 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 140 to 200°C.

[038] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 1 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[039] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;

ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;

ii) less than 15 to 1 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and

iii) optionally less than 18 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

[040] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

i) 70 to 100 mole % of terephthalic acid residues;

ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and

ii) less than 15 to 1 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and

iii) optionally less than 18 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,



the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 140 to 200°C.

[041] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 15 to 1 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
  - iii) optionally less than 18 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[042] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

i) greater than 85 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;

ii) less than 15 to 1 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and

iii) optionally less than 14 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

[043] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

(a) a dicarboxylic acid component comprising:

i) 70 to 100 mole % of terephthalic acid residues;

ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

i) greater than 85 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and

ii) less than 15 to 1 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and

iii) optionally less than 14 mole % of 1,4-cyclohexanedimethanol residues,

the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 140 to 200°C.

[044] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 85 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 15 to 1 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
  - iii) optionally less than 14 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[045] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

- (b) a glycol component comprising:
  - i) greater than 81 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 2 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

[046] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 2 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 140 to 200°C.

[047] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:

- i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
- i) greater than 81 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 2 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[048] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 2 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a T<sub>g</sub> from 135 to 200°C.

**[049]** In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 2 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a T<sub>g</sub> from 140 to 200°C.

**[050]** In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:

- i) greater than 81 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) less than 19 to 2 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[051] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
  - ii) less than 15 to 2 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
  - iii) optionally less than 17 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

[052] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
    - i) 70 to 100 mole % of terephthalic acid residues;
    - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
    - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
  - (b) a glycol component comprising:
    - i) greater than 81 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
    - ii) less than 15 to 2 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
    - iii) optionally less than 17 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,
- the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a T<sub>g</sub> from 140 to 200°C.

[053] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 15 to 2 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and



iii) optionally less than 17 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,  
wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and  
wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[054] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 85 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
  - ii) less than 15 to 2 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
  - iii) optionally less than 13 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and  
wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

[055] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;

- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

(b) a glycol component comprising:

- i) greater than 85 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) less than 15 to 2 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
- iii) optionally less than 13 mole % of 1,4-cyclohexanedimethanol residues,

the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 140 to 200°C.

[056] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 85 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 15 to 2 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
  - iii) optionally less than 13 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and

the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[057] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to less than 100 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to greater than 0 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

[058] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:

- i) greater than 81 to less than 100 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
- ii) less than 19 to greater than 0 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 140 to 200°C.

[059] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to less than 100 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to greater than 0 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[060] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;

- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 80 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 20 to 1 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[061] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 80 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 20 to 1 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[062] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 80 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 15 to 1 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
  - iii) optionally less than 19 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a T<sub>g</sub> greater than 148 to 200°C.

[063] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 80 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and

- ii) less than 15 to 1 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
- iii) optionally less than 19 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[064] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 80 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 20 to 2 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[065] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;

- ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 80 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 20 to 2 mole % of 1,4-cyclohexanedimethanol residues,wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[066] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 80 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 15 to 2 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
  - iii) optionally less than 18 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and



wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a T<sub>g</sub> greater than 148 to 200°C.

[067] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 80 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 15 to 2 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
  - iii) optionally less than 18 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a T<sub>g</sub> greater than 148 to 200°C.

[068] In one aspect, the invention relates to a polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and

- (b) a glycol component comprising:
- i) 80 to less than 100 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 20 to greater than 0 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

[069] In one aspect, the polyester compositions contain at least one polycarbonate.

[070] In one aspect, the polyester compositions contain no polycarbonate.

[071] In one aspect, the polyester useful in the invention contains less than 15 mole % ethylene glycol residues, such as, for example, 0.01 to less than 15 mole % ethylene glycol residues.

[072] In one aspect, the polyesters useful in the invention contain no ethylene glycol residues.

[073] In one aspect, the polyester compositions useful in the invention contain at least one thermal stabilizer and/or reaction products thereof.

[074] In one aspect, the polyesters useful in the invention contain no branching agent, or alternatively, at least one branching agent is added either prior to and/or during polymerization of the polyester.

[075] In one aspect, the polyesters useful in the invention contain at least one branching agent without regard to the method or sequence in which it is added.

[076] In one aspect, the polyesters useful in the invention are made from no 1, 3-propanediol, or 1, 4-butanediol, either singly or in combination. In other aspects, 1,3-propanediol or 1,4-butanediol, either singly or in combination, may be used in the making of the polyesters useful in this invention.

[077] In one aspect of the invention, the mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol useful in certain polyesters useful in the invention is greater

than 50 mole % or greater than 55 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol or greater than 70 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol; wherein the total mole percentage of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol and trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol is equal to a total of 100 mole %.

[078] In one aspect of the invention, the mole % of the isomers of 2,2,4,4-tetramethyl-1,3-cyclobutanediol useful in certain polyesters useful in the invention is from 30 to 70 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol or from 30 to 70 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol, or from 40 to 60 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol or from 40 to 60 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol, wherein the total mole percentage of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol and trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol is equal to a total of 100 mole %.

[079] In one aspect, the polyester compositions are useful in articles of manufacture including, but not limited to, calendered, extruded and/or molded articles including, but not limited to, injection molded articles, extruded articles, cast extrusion articles, profile extrusion articles, melt spun articles, thermoformed articles, extrusion molded articles, injection blow molded articles, injection stretch blow molded articles, extrusion blow molded articles, and extrusion stretch blow molded articles. These articles can include, but are not limited to, films, bottles (including but not limited to baby bottles), film, sheet and/or fibers. In one aspect, the polyester compositions useful in the invention may be used in various types of film and/or sheet, including but not limited to extruded film(s) and/or sheet(s), calendered film(s) and/or sheet(s), compression molded film(s) and/or sheet(s), solution casted film(s) and/or sheet(s). Methods of making film and/or sheet include but are not limited to extrusion, calendering, compression molding, and solution casting.

[080] Also, in one aspect, use of the polyester compositions of the invention can minimize and/or eliminate the drying step prior to melt processing and/or thermoforming.

[081] In one aspect, certain polyesters useful in the invention can be amorphous or semicrystalline. In one aspect, certain polyesters useful in the invention can have a relatively low crystallinity. Certain polyesters useful in the invention can thus have a substantially amorphous morphology, meaning that the polyesters comprise substantially unordered regions of polymer.

## BRIEF DESCRIPTION OF THE DRAWINGS

[082] Figure 1 is a graph showing the effect of comonomer on the fastest crystallization half-times of modified PCT copolyesters.

[083] Figure 2 is a graph showing the effect of comonomer on the brittle-to-ductile transition temperature ( $T_{bd}$ ) in a notched Izod impact strength test (ASTM D256, 1/8-in thick, 10-mil notch).

[084] Figure 3 is a graph showing the effect of 2,2,4,4-tetramethyl-1,3-cyclobutanediol composition on the glass transition temperature ( $T_g$ ) of the copolyester.

## DETAILED DESCRIPTION OF THE INVENTION

[085] The present invention may be understood more readily by reference to the following detailed description of certain embodiments of the invention and the working examples. In accordance with the purpose(s) of this invention, certain embodiments of the invention are described in the Summary of the Invention and are further described herein below. Also, other embodiments of the invention are described herein.

[086] It is believed that polyesters and/or polyester compositions useful in the invention described herein can have a combination of two or more physical properties such as high impact strengths, high glass transition temperatures, chemical resistance, hydrolytic stability, toughness, e.g., low ductile-to-brittle transition temperatures, good color and clarity, low densities, and long crystallization half-times, and good processability thereby easily permitting them to be formed into articles. In some of the embodiments of the invention, the

polyesters have a unique combination of the properties of good impact strength, heat resistance, chemical resistance, density and/or the combination of the properties of good impact strength, heat resistance, and processability and/or the combination of two or more of the described properties, that have never before been believed to be present in a polyester.

[087] As used herein, the term "polyester" includes copolyesters and is understood to mean a synthetic polymer prepared by the reaction of one or more difunctional carboxylic acids and/or multifunctional carboxylic acids with one or more difunctional hydroxyl compounds and/or multifunctional hydroxyl compounds. Typically the difunctional carboxylic acid can be a dicarboxylic acid and the difunctional hydroxyl compound can be a dihydric alcohol such as, for example, glycols and diols. The term "glycol" as used in this application includes, but is not limited to, diols, glycols, and/or multifunctional hydroxyl compounds. Alternatively, the difunctional carboxylic acid may be a hydroxy carboxylic acid such as, for example, p-hydroxybenzoic acid, and the difunctional hydroxyl compound may be an aromatic nucleus bearing 2 hydroxyl substituents such as, for example, hydroquinone. The term "residue", as used herein, means any organic structure incorporated into a polymer through a polycondensation and/or an esterification reaction from the corresponding monomer. The term "repeating unit", as used herein, means an organic structure having a dicarboxylic acid residue and a diol residue bonded through a carbonyloxy group. Thus, for example, the dicarboxylic acid residues may be derived from a dicarboxylic acid monomer or its associated acid halides, esters, salts, anhydrides, or mixtures thereof. As used herein, therefore, the term dicarboxylic acid is intended to include dicarboxylic acids and any derivative of a dicarboxylic acid, including its associated acid halides, esters, half-esters, salts, half-salts, anhydrides, mixed anhydrides, or mixtures thereof, useful in a reaction process with a diol to make polyester. As used herein, the term "terephthalic acid" is intended to include terephthalic acid itself and residues thereof as well as any derivative of terephthalic acid, including its associated acid halides, esters, half-esters, salts, half-salts, anhydrides, mixed anhydrides, or mixtures thereof or residues thereof

useful in a reaction process with a diol to make polyester. Furthermore, as used in this application, the term "diacid" includes multifunctional acids such branching agents.

[088] In one embodiment, terephthalic acid may be used as the starting material. In another embodiment, dimethyl terephthalate may be used as the starting material. In another embodiment, mixtures of terephthalic acid and dimethyl terephthalate may be used as the starting material and/or as an intermediate material.

[089] The polyesters used in the present invention typically can be prepared from dicarboxylic acids and diols which react in substantially equal proportions and are incorporated into the polyester polymer as their corresponding residues. The polyesters of the present invention, therefore, can contain substantially equal molar proportions of acid residues (100 mole%) and diol (and/or multifunctional hydroxyl compounds) residues (100 mole%) such that the total moles of repeating units is equal to 100 mole%. The mole percentages provided in the present disclosure, therefore, may be based on the total moles of acid residues, the total moles of diol residues, or the total moles of repeating units. For example, a polyester containing 30 mole% isophthalic acid, based on the total acid residues, means the polyester contains 30 mole% isophthalic acid residues out of a total of 100 mole% acid residues. Thus, there are 30 moles of isophthalic acid residues among every 100 moles of acid residues. In another example, a polyester containing 30 mole% 2,2,4,4-tetramethyl-1,3-cyclobutanediol, based on the total diol residues, means the polyester contains 30 mole% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues out of a total of 100 mole% diol residues. Thus, there are 30 moles of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues among every 100 moles of diol residues.

[090] In other aspects of the invention, the Tg of the polyesters useful in the polyester compositions of the invention include, but are not limited to, 85 to 200°C; 85 to 190°C; 85 to 180°C; 85 to 170°C; 85 to 160°C; 85 to 155°C; 85 to 150°C; 85 to 145°C; 85 to 140°C; 85 to 138°C; 85 to 135°C; 85 to 130°C; 85 to 125°C; 85 to 120°C; 85 to 115°C; 85 to 110°C; 85 to 105°C; 85 to 100°C; 85 to

95°C; 85 to 90°C; 90 to 200°C; 90 to 190°C; 90 to 180°C; 90 to 170°C; 90 to  
 160°C; 90 to 155°C; 90 to 150°C; 90 to 145°C; 90 to 140°C; 90 to 138°C; 90 to  
 135°C; 90 to 130°C; 90 to 125°C; 90 to 120°C; 90 to 115°C; 90 to 110°C; 90 to  
 105°C; 90 to 100°C; 90 to 95°C; 95 to 200°C; 95 to 190°C; 95 to 180°C; 95 to  
 170°C; 95 to 160°C; 95 to 155°C; 95 to 150°C; 95 to 145°C; 95 to 140°C; 95 to  
 138°C; 95 to 135°C; 95 to 130°C; 95 to 125°C; 95 to 120°C; 95 to 115°C; 95 to  
 110°C; 95 to 105°C; 95 to less than 105°C; 95 to 100°C; 100 to 200°C; 100 to  
 190°C; 100 to 180°C; 100 to 170°C; 100 to 160°C; 100 to 155°C; 100 to 150°C;  
 100 to 145°C; 100 to 140°C; 100 to 138°C; 100 to 135°C; 100 to 130°C; 100 to  
 125°C; 100 to 120°C; 100 to 115°C; 100 to 110°C; 105 to 200°C; 105 to 190°C;  
 105 to 180°C; 105 to 170°C; 105 to 160°C; 105 to 155°C; 105 to 150°C; 105 to  
 145°C; 105 to 140°C; 105 to 138°C; 105 to 135°C; 105 to 130°C; 105 to 125°C;  
 105 to 120°C; 105 to 115°C; 105 to 110°C; greater than 105 to 125°C; greater  
 than 105 to 120°C; greater than 105 to 115°C; greater than 105 to 110°C; 110 to  
 200°C; 110 to 195°C; 110 to 190°C; 110 to 185°C; 110 to 180°C; 110 to 175°C;  
 110 to 170°C; 110 to 165°C; 110 to 160°C; 110 to 155°C; 110 to 150°C; 110 to  
 145°C; 110 to 138°C; 110 to 140°C; 110 to 135°C; 110 to 130°C; 110 to 125°C;  
 110 to 120°C; 110 to 115°C; 115 to 200°C; 115 to 195°C; 115 to 190°C; 115 to  
 185°C; 115 to 180°C; 115 to 175°C; 115 to 170°C; 115 to 165°C; 115 to 160°C;  
 115 to 155°C; 115 to 150°C; 115 to 145°C; 115 to 140°C; 115 to 138°C; 115 to  
 135°C; 115 to 125°C; 115 to 120°C; 120 to 200°C; 120 to 195°C; 120 to 190°C;  
 120 to 185°C; 120 to 180°C; 120 to 175°C; 120 to 170°C; 120 to 165°C; 120 to  
 160°C; 120 to 155°C; 120 to 150°C; 120 to 145°C; 120 to 140°C; 120 to 138°C;  
 120 to 135°C; 125 to 180°C; 125 to 170°C; 125 to 160°C; 125 to 155°C; 125 to  
 150°C; 125 to 145°C; 125 to 140°C; 125 to 138°C; 125 to 135°C; 135 to 180°C;  
 127 to 180°C; 127 to 170°C; 127 to 160°C; 127 to 150°C; 127 to 145°C; 127 to  
 140°C; 127 to 138°C; 127 to 135°C; 130 to 200°C; 130 to 195°C; 130 to 190°C;  
 130 to 185°C; 130 to 180°C; 130 to 175°C; 130 to 170°C; 130 to 165°C; 130 to  
 160°C; 130 to 155°C; 130 to 150°C; 130 to 145°C; 130 to 140°C; 130 to 138°C;  
 130 to 135°C; 135 to 170°C; 135 to 160°C; 135 to 155°C; 135 to 150°C; 135 to  
 145°C; 135 to 140°C; 135 to 135°C; 140 to 200°C; 140 to 195°C; 140 to 190°C;

140 to 185°C; 140 to 180°C; 140 to 170°C; 140 to 165°C; 140 to 160°C; 140 to 155°C; 140 to 150°C; 140 to 145°C; 148 to 200°C; 148 to 190°C; 148 to 180°C; 148 to 170°C; 148 to 160°C; 148 to 155°C; 148 to 150°C; 150 to 200°C; 150 to 195°C; 150 to 190°C; 150 to 185°C; 150 to 180°C; 150 to 175°C; 150 to 170°C; 150 to 165°C; 150 to 160°C; 150 to 155°C; 155 to 200°C; 155 to 190°C; 155 to 180°C; 155 to 170°C; and 155 to 165°C; greater than 124°C up to 200°C; greater than 125°C up to 200°C; greater than 126°C up to 200°C; greater than 148°C up to 200°C.

[091] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 1 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 65 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 70 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 25 mole % 2,2,4,4-



tetramethyl-1,3-cyclobutanediol and 75 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 20 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 80 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 15 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 85 to 99 mole % 1,4-cyclohexanedimethanol; 1 to 10 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 90 to 99 mole % 1,4-cyclohexanedimethanol; and 1 to 5 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 95 to 99 mole % 1,4-cyclohexanedimethanol.

[092] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 5 to less than 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 50 to 95 mole % 1,4-cyclohexanedimethanol; 5 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 95 mole % 1,4-cyclohexanedimethanol; 5 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 95 mole % 1,4-cyclohexanedimethanol; 5 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 65 to 95 mole % 1,4-cyclohexanedimethanol; 5 to less than 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 65 to 95 mole % 1,4-cyclohexanedimethanol; 5 to 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 70 to 95 mole % 1,4-cyclohexanedimethanol; 5 to 25 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 75 to 95 mole % 1,4-cyclohexanedimethanol; 5 to 20 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 80 to 95 mole % 1,4-cyclohexanedimethanol; 5 to 15 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 85 to 95 mole % 1,4-cyclohexanedimethanol; 5 to 10 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 90 to 95 mole % 1,4-cyclohexanedimethanol; greater than 5 to less than 10 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 90 to greater than 95 mole % 1,4-cyclohexanedimethanol; 5.5 mole % to 9.5 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 94.5 mole % to 90.5 mole % 1,4-cyclohexanedimethanol; and 6 to 9 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 94 to 91 mole % 1,4-cyclohexanedimethanol.

[093] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the

following combinations of ranges: 10 to 100 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 0 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 90 mole % 1,4-cyclohexanedimethanol, 10 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 90 mole % 1,4-cyclohexanedimethanol; 10 to less than 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 50 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 65 to 90 mole % 1,4-cyclohexanedimethanol; 10 to less than 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 65 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 70 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 25 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 75 to 90 mole % 1,4-cyclohexanedimethanol; 10 to 20 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 80 to 90 mole % 1,4-cyclohexanedimethanol; and 10 to 15 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 85 to 90 mole % 1,4-cyclohexanedimethanol.

[094] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 14 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 86 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 14 to 86 mole % 1,4-cyclohexanedimethanol, 14 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 86 mole % 1,4-cyclohexanedimethanol; 14 to less than 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 50 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 65 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 70 to 86 mole % 1,4-cyclohexanedimethanol; 14 to 24 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 76 to 86 mole % 1,4-cyclohexanedimethanol; and 14 to 25 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 75 to 86 mole % 1,4-cyclohexanedimethanol.

[095] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 15 to 99 mole % 2,2,4,4-tetramethyl-1,3-

cyclobutanediol and 1 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 86 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 86 mole % 1,4-cyclohexanedimethanol, 15 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 85 mole % 1,4-cyclohexanedimethanol; 15 to less than 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 50 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 65 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 70 to 85 mole % 1,4-cyclohexanedimethanol; 15 to 25 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 75 to 85 mole % 1,4-cyclohexanedimethanol; and 15 to 24 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 76 to 85 mole % 1,4-cyclohexanedimethanol.

[096] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 20 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol

and 10 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 80 mole % 1,4-cyclohexanedimethanol, 20 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 80 mole % 1,4-cyclohexanedimethanol; 20 to less than 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 50 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 65 to 80 mole % 1,4-cyclohexanedimethanol; 20 to 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 70 to 80 mole % 1,4-cyclohexanedimethanol; and 20 to 25 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 75 to 80 mole % 1,4-cyclohexanedimethanol.

[097] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 25 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 75 mole % 1,4-cyclohexanedimethanol, 25 to 75 mole % 2,2,4,4-tetramethyl-1,3-

cyclobutanediol and 25 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 75 mole % 1,4-cyclohexanedimethanol; 25 to less than 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 50 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 75 mole % 1,4-cyclohexanedimethanol; 25 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 65 to 75 mole % 1,4-cyclohexanedimethanol; and 25 to 30 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 70 to 75 mole % 1,4-cyclohexanedimethanol.

[098] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 30 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 70 mole % 1,4-cyclohexanedimethanol, 30 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 70 mole %

1,4-cyclohexanedimethanol; 30 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 70 mole % 1,4-cyclohexanedimethanol; 30 to less than 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 50 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 70 mole % 1,4-cyclohexanedimethanol; 30 to 35 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 65 to 70 mole % 1,4-cyclohexanedimethanol.

[099] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 35 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 65 mole % 1,4-cyclohexanedimethanol; 35 to less than 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 50 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 65 mole % 1,4-cyclohexanedimethanol; 35 to 40 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 60 to 65 mole % 1,4-cyclohexanedimethanol.

[0100] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 40 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 60 mole % 1,4-cyclohexanedimethanol; 40 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 60 mole % 1,4-cyclohexanedimethanol; 40 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 60 mole % 1,4-cyclohexanedimethanol; 40 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 60 mole % 1,4-cyclohexanedimethanol; 40 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 60 mole % 1,4-cyclohexanedimethanol, 40 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 60 mole % 1,4-cyclohexanedimethanol; 40 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 60 mole % 1,4-cyclohexanedimethanol; 40 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 60 mole % 1,4-cyclohexanedimethanol; 40 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 60 mole % 1,4-cyclohexanedimethanol; 40 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 60 mole % 1,4-cyclohexanedimethanol; 40 to less than 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and greater than 50 to 60 mole % 1,4-cyclohexanedimethanol; 40 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 60 mole % 1,4-cyclohexanedimethanol; and 40 to 45 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 55 to 60 mole % 1,4-cyclohexanedimethanol.

[0101] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 45 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 55 mole % 1,4-cyclohexanedimethanol; 45 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 55 mole % 1,4-cyclohexanedimethanol; 45 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 55 mole % 1,4-cyclohexanedimethanol; 45 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 55 mole % 1,4-cyclohexanedimethanol; 45 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 55 mole % 1,4-cyclohexanedimethanol, 45 to 75 mole % 2,2,4,4-tetramethyl-1,3-



cyclobutanediol and 25 to 55 mole % 1,4-cyclohexanedimethanol; 45 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 55 mole % 1,4-cyclohexanedimethanol; 45 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 55 mole % 1,4-cyclohexanedimethanol; 45 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 55 mole % 1,4-cyclohexanedimethanol; greater than 45 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to less than 55 mole % 1,4-cyclohexanedimethanol; 45 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 55 mole % 1,4-cyclohexanedimethanol; 45 to 50 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 50 to 55 mole % 1,4-cyclohexanedimethanol; greater than 45 to 52 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 48 to 55 mole % 1,4-cyclohexanedimethanol; 46 to 55 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 45 to 54 mole % 1,4-cyclohexanedimethanol; and 48 to 52 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 48 to 52 mole % 1,4-cyclohexanedimethanol.

[0102] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: greater than 50 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to less than 50 mole % 1,4-cyclohexanedimethanol; greater than 50 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to less than 50 mole % 1,4-cyclohexanedimethanol; greater than 50 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to less than 50 mole % 1,4-cyclohexanedimethanol; greater than 50 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to less than 50 mole % 1,4-cyclohexanedimethanol, greater than 50 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to less than 50 mole % 1,4-cyclohexanedimethanol; greater than 50 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to less than 50 mole % 1,4-cyclohexanedimethanol; greater than 50 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to less than 50 mole % 1,4-cyclohexanedimethanol; greater than 50 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to less than 50 mole % 1,4-cyclohexanedimethanol.

[0103] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 55 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 45 mole % 1,4-cyclohexanedimethanol, 55 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 45 mole % 1,4-cyclohexanedimethanol; 55 to 65 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 35 to 45 mole % 1,4-cyclohexanedimethanol; and 55 to 60 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 40 to 45 mole % 1,4-cyclohexanedimethanol.

[0104] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 60 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 40 mole % 1,4-cyclohexanedimethanol; 60 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 40 mole % 1,4-cyclohexanedimethanol; 60 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 40 mole % 1,4-cyclohexanedimethanol; 60 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 40 mole % 1,4-cyclohexanedimethanol; 60 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 40 mole % 1,4-cyclohexanedimethanol, 60 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 40 mole % 1,4-cyclohexanedimethanol; and 60 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 40 mole % 1,4-cyclohexanedimethanol.

[0105] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 65 to 99 mole % 2,2,4,4-tetramethyl-1,3-

cyclobutanediol and 1 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 35 mole % 1,4-cyclohexanedimethanol; 65 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 35 mole % 1,4-cyclohexanedimethanol, 65 to 75 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 25 to 35 mole % 1,4-cyclohexanedimethanol; and 65 to 70 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 30 to 35 mole % 1,4-cyclohexanedimethanol.

[0106] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 70 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 30 mole % 1,4-cyclohexanedimethanol; 70 to 80 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 30 mole % 1,4-cyclohexanedimethanol.

[0107] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 75 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1 to 25 mole % 1,4-cyclohexanedimethanol; 75 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 25 mole % 1,4-cyclohexanedimethanol; 75 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 25 mole % 1,4-cyclohexanedimethanol; and 75 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to 25 mole % 1,4-cyclohexanedimethanol.

[0108] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 80 to 99 mole % 2,2,4,4-tetramethyl-1,3-

cyclobutanediol and 1 to 20 mole % 1,4-cyclohexanedimethanol; 80 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to 20 mole % 1,4-cyclohexanedimethanol; 80 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to 20 mole % 1,4-cyclohexanedimethanol; greater than 80 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to less than 20 mole % 1,4-cyclohexanedimethanol; and greater than 81 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to less than 19 mole % 1,4-cyclohexanedimethanol.

[0109] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: greater than 81 to less than 100 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to more than 0 mole % modifying glycol; greater than 81 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 1 mole % modifying glycol; greater than 81 to 98 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 2 mole % modifying glycol; greater than 81 to 97 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 3 mole % modifying glycol; greater than 81 to 96 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 4 mole % modifying glycol; greater than 81 to 96 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 4 mole % modifying glycol; greater than 81 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 5 mole % modifying glycol; greater than 81 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 10 mole % modifying glycol; greater than 81 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 15 mole % modifying glycol.

[0110] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: greater than 81 to less than 100 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to more than 0 mole % 1,4-cyclohexanedimethanol; greater than 81 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 1 mole % 1,4-cyclohexanedimethanol; greater than 81 to 98 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less

than 19 to 2 mole % 1,4-cyclohexanedimethanol; greater than 81 to 97 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 3 mole % 1,4-cyclohexanedimethanol; greater than 81 to 96 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 4 mole % 1,4-cyclohexanedimethanol; greater than 81 to 96 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 4 mole % 1,4-cyclohexanedimethanol, greater than 81 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 5 mole % 1,4-cyclohexanedimethanol; greater than 81 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 10 mole % 1,4-cyclohexanedimethanol; greater than 81 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and less than 19 to 15 mole % 1,4-cyclohexanedimethanol.

[0111] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 80 to 99 % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 1 mole % modifying glycol; 80 to 98 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 2 mole % modifying glycol; 80 to 97 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 3 mole % modifying glycol; 80 to 96 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 4 mole % modifying glycol; 80 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 5 mole % modifying glycol; 80 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 10 mole % modifying glycol; and 80 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to 15 mole % modifying glycol.

[0112] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 80 to less than 100 % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 20 to greater than 0 mole % modifying glycol; 85 to less than 100 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 15 to greater than 0 mole % modifying glycol; 90 to less than 100 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 10 to greater than 0 mole % modifying glycol; 95 to less than 100 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 5 to greater than 0 mole % modifying glycol; 96 to less than 100 mole % 2,2,4,4-tetramethyl-1,3-

cyclobutanediol and 4 to greater than 0 mole % modifying glycol; 97 to less than 100 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 3 to greater than 0 mole % modifying glycol; 98 to less than 100 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 2 to greater than 0 mole % modifying glycol; and 9 to less than 100 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol and to greater than 0 mole % modifying glycol.

[0113] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: greater than 81 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 1 mole % ethylene glycol and less than 18 mole % modifying glycol; greater than 81 to 98 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 2 mole % ethylene glycol and less than 17 mole % modifying glycol; greater than 81 to 97 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 3 mole % ethylene glycol and less than 16 mole % modifying glycol; greater than 81 to 96 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 4 mole % ethylene glycol and less than 15 mole % modifying glycol; greater than 81 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 5 mole % ethylene glycol and less than 14 mole % modifying glycol; greater than 81 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 10 mole % ethylene glycol and less than 9 mole % modifying glycol; and greater than 81 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 mole % ethylene glycol and less than 4 mole % modifying glycol.

[0114] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: 80 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 1 mole % ethylene glycol and less than 19 mole % modifying glycol; 80 to 98 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 2 mole % ethylene glycol and less than 18 mole % modifying glycol; 80 to 97 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 3 mole % ethylene glycol and less than 17 mole % modifying glycol; 80 to 96 mole %

2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 4 mole % ethylene glycol and less than 16 mole % modifying glycol; 80 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 5 mole % ethylene glycol and less than 15 mole % modifying glycol; 80 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 10 mole % ethylene glycol and less than 10 mole % modifying glycol; and 80 to 85 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 mole % ethylene glycol and less than 5 mole % modifying glycol.

[0115] In other aspects of the invention, the glycol component for the polyesters useful in the invention include but are not limited to at least one of the following combinations of ranges: greater than 85 to 99 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 1 mole % ethylene glycol and less than 14 mole % modifying glycol; greater than 85 to 98 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 2 mole % ethylene glycol and less than 13 mole % modifying glycol; greater than 85 to 97 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 3 mole % ethylene glycol and less than 12 mole % modifying glycol; greater than 85 to 96 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 4 mole % ethylene glycol and less than 11 mole % modifying glycol; greater than 85 to 95 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 5 mole % ethylene glycol and less than 10 mole % modifying glycol; and greater than 85 to 90 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol, less than 15 to 10 mole % ethylene glycol and less than 5 mole % modifying glycol.

[0116] In addition to the diols set forth above, the polyesters useful in the polyester compositions of the invention may also be made from 1,3-propanediol, 1,4-butanediol, or mixtures thereof. It is contemplated that compositions of the invention made from 1,3-propanediol, 1,4-butanediol, or mixtures thereof can possess at least one of the T<sub>g</sub> ranges described herein, at least one of the inherent viscosity ranges described herein, and/or at least one of the glycol or diacid ranges described herein. In addition or in the alternative, the polyesters made from 1,3-propanediol or 1,4-butanediol or mixtures thereof may also be made from 1,4-cyclohexanedimethanol in at least one of the following amounts:

from 0.1 to 99 mole %; from 0.1 to 95 mole %; from 0.1 to 90 mole %; from 0.1 to 85 mole %; from 0.1 to 80 mole %; from 0.1 to 75 mole %; from 0.1 to 70 mole %; from 0.1 to 60 mole %; from 0.1 to 50 mole %; from 0.1 to 40 mole %; from 0.1 to 35 mole %; from 0.1 to 30 mole %; from 0.1 to 25 mole %; from 0.1 to 20 mole %; from 0.1 to 15 mole %; from 0.1 to 10 mole %; from 0.1 to 5 mole %; from 1 to 99 mole %; from 1 to 95 mole; from 1 to 90 mole %; from 1 to 85 mole %; from 1 to 80 mole %; from 1 to 70 mole %; from 1 to 60 mole %; from 1 to 50 mole %; from 1 to 40 mole %; from 1 to 35 mole %; from 1 to 30 mole %; from 1 to 25 mole %; from 1 to 20 mole %; from 1 to 15 mole %; from 1 to 10 mole %; from 1 to 5 mole %; 5 to 99 mole %; from 5 to 95 mole; from 5 to 90 mole %; from 5 to 85 mole %; from 5 to 80 mole %; from 5 to 75 mole %; 5 to 70 mole %; from 5 to 60 mole %; from 5 to 50 mole %; from 5 to 40 mole %; from 5 to 35 mole %; from 5 to 30 mole %; from 5 to 25 mole %; from 5 to 20 mole %; and from 5 to 15 mole %; from 5 to 10 mole %; from 10 to 99 mole %; from 10 to 95 mole; from 10 to 90 mole %; from 10 to 85 mole %; from 10 to 80 mole %; from 10 to 75 mole %; from 10 to 70 mole %; from 10 to 60 mole %; from 10 to 50 mole %; from 10 to 40 mole %; from 10 to 35 mole %; from 10 to 30 mole %; from 10 to 25 mole %; from 10 to 20 mole %; from 10 to 15 mole %; from 20 to 99 mole %; from 20 to 95 mole; from 20 to 90 mole %; from 20 to 85 mole %; from 20 to 80 mole %; from 20 to 75 mole %; from 20 to 70 mole %; from 20 to 60 mole %; from 20 to 50 mole %; from 20 to 40 mole %; from 20 to 35 mole %; from 20 to 30 mole %; and from 20 to 25 mole %.

[0117] For certain embodiments of the invention, the polyesters may exhibit any of the following inherent viscosities as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C: 0.35 to less than 0.70 dL/g; 0.35 to 0.68 dL/g; 0.35 to less than 0.68 dL/g; 0.35 to 0.65 dL/g.; 0.40 to 0.70 dL/g; 0.40 to less than 0.70 dL/g; 0.40 to 0.68 dL/g; 0.40 to less than 0.68 dL/g; 0.40 to 0.65 dL/g.; 0.45 to less than 0.70 dL/g; 0.45 to 0.68 dL/g; 0.45 to less than 0.68 dL/g; 0.45 to 0.65 dL/g; 0.50 to less than 0.70 dL/g; 0.50 to 0.68 dL/g; 0.50 to less than 0.68 dL/g; 0.50 to 0.67 dL/g; 0.50 to 0.66 dL/g; 0.50 to 0.65 dL/g; 0.55 to less than 0.70 dL/g; 0.55 to 0.68 dL/g; 0.55 to less than 0.68 dL/g;



0.55 to 0.65 dL/g; 0.58 to less than 0.70 dL/g; 0.58 to 0.68 dL/g; 0.58 to less than 0.68 dL/g; or 0.58 to 0.65 dL/g.

[0118] For embodiments of the invention where the inherent viscosity of the polyesters of the invention ranges from 0.35 to 0.75 or higher dL/g, these polyesters may also exhibit any of the following inherent viscosities as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C: 0.35 to less than 0.75 dL/g; 0.35 to 0.72 dL/g; or 0.35 to 0.70 dL/g.

[0119] For embodiments of the invention, the polyesters useful in the invention may exhibit at least one of the following inherent viscosities as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C: 0.10 to 1.2 dL/g; 0.10 to 1.1 dL/g; 0.10 to 1 dL/g; 0.10 to less than 1 dL/g; 0.10 to 0.98 dL/g; 0.10 to 0.95 dL/g; 0.10 to 0.90 dL/g; 0.10 to 0.85 dL/g; 0.10 to 0.80 dL/g; 0.10 to 0.75 dL/g; 0.10 to less than 0.75 dL/g; 0.10 to 0.72 dL/g; 0.10 to 0.70 dL/g; 0.10 to less than 0.70 dL/g; 0.10 to 0.68 dL/g; 0.10 to less than 0.68 dL/g; 0.10 to 0.65 dL/g; 0.10 to 0.6 dL/g; 0.10 to 0.55 dL/g; 0.10 to 0.5 dL/g; 0.10 to 0.4 dL/g; 0.10 to 0.35 dL/g; 0.20 to 1.2 dL/g; 0.20 to 1.1 dL/g; 0.20 to 1 dL/g; 0.20 to less than 1 dL/g; 0.20 to 0.98 dL/g; 0.20 to 0.95 dL/g; 0.20 to 0.90 dL/g; 0.20 to 0.85 dL/g; 0.20 to 0.80 dL/g; 0.20 to 0.75 dL/g; 0.20 to less than 0.75 dL/g; 0.20 to 0.72 dL/g; 0.20 to 0.70 dL/g; 0.20 to less than 0.70 dL/g; 0.20 to 0.68 dL/g; 0.20 to less than 0.68 dL/g; 0.20 to 0.65 dL/g; 0.20 to 0.6 dL/g; 0.20 to 0.55 dL/g; 0.20 to 0.5 dL/g; 0.20 to 0.4 dL/g; and 0.20 to 0.35 dL/g.

[0120] For embodiments of the invention where the inherent viscosity ranges from 0.35 to 1.2 dL/g, these polyesters may also exhibit any of the following inherent viscosities as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C: 0.35 to 1.2 dL/g; 0.35 to 1.1 dL/g; 0.35 to 1 dL/g; 0.35 to less than 1 dL/g; 0.35 to 0.98 dL/g; 0.35 to 0.95 dL/g; 0.35 to 0.9 dL/g; 0.35 to 0.85 dL/g; 0.35 to 0.8 dL/g; 0.35 to 0.75 dL/g; 0.35 to less than 0.75 dL/g; 0.35 to 0.72 dL/g; 0.40 to 1.2 dL/g; 0.40 to 1.1 dL/g; 0.40 to 1 dL/g; 0.40 to less than 1 dL/g; 0.40 to 0.98 dL/g; 0.40 to 0.95 dL/g; 0.40 to 0.9 dL/g; 0.40 to 0.85 dL/g; 0.40 to 0.8 dL/g; 0.40 to 0.75 dL/g; 0.40 to less than 0.75 dL/g; 0.40 to

0.72 dL/g; greater than 0.42 to 1.2 dL/g; greater than 0.42 to 1.1 dL/g; greater than 0.42 to 1 dL/g; greater than 0.42 to less than 1 dL/g; greater than 0.42 to 0.98 dL/g; greater than 0.42 to 0.95 dL/g; greater than 0.42 to 0.9 dL/g; greater than 0.42 to 0.85 dL/g; greater than 0.42 to 0.80 dL/g; greater than 0.42 to 0.75 dL/g; greater than 0.42 to less than 0.75 dL/g; 0.42 to 0.70 dL/g; 0.42 to less than 0.70 dL/g; greater than 0.42 to 0.72 dL/g; greater than 0.42 to 0.70 dL/g; greater than 0.42 to 0.68 dL/g; greater than 0.42 to less than 0.68 dL/g; 0.42 to 0.68 dL/g; greater than 0.42 to 0.65 dL/g; 0.45 to 1.2 dL/g; 0.45 to 1.1 dL/g; 0.45 to 1 dL/g; 0.45 to 0.98 dL/g; 0.45 to 0.95 dL/g; 0.45 to 0.9 dL/g; 0.45 to 0.85 dL/g; 0.45 to 0.80 dL/g; 0.45 to 0.75 dL/g; 0.45 to less than 0.75 dL/g; 0.45 to 0.72 dL/g; 0.45 to 0.70 dL/g; 0.50 to 1.2 dL/g; 0.50 to 1.1 dL/g; 0.50 to 1 dL/g; 0.50 to less than 1 dL/g; 0.50 to 0.98 dL/g; 0.50 to 0.95 dL/g; 0.50 to 0.9 dL/g; 0.50 to 0.85 dL/g; 0.50 to 0.80 dL/g.; 0.50 to 0.75 dL/g; 0.50 to less than 0.75 dL/g; 0.50 to 0.72 dL/g; 0.50 to 0.70 dL/g; 0.55 to 1.2 dL/g; 0.55 to 1.1 dL/g; 0.55 to 1 dL/g; 0.55 to less than 1 dL/g; 0.55 to 0.98 dL/g; 0.55 to 0.95 dL/g; 0.55 to 0.9 dL/g; 0.55 to 0.85 dL/g; 0.55 to 0.80 dL/g; 0.55 to 0.75 dL/g; 0.55 to less than 0.75 dL/g; 0.55 to 0.72 dL/g; 0.55 to 0.70 dL/g; 0.58 to 1.2 dL/g; 0.58 to 1.1 dL/g; 0.58 to 1 dL/g; 0.58 to less than 1 dL/g; 0.58 to 0.98 dL/g; 0.58 to 0.95 dL/g; 0.58 to 0.9 dL/g; 0.58 to 0.85 dL/g; 0.58 to 0.80 dL/g; 0.58 to 0.75 dL/g; 0.58 to less than 0.75 dL/g; 0.58 to 0.72 dL/g; 0.58 to 0.70 dL/g; 0.60 to 1.2 dL/g; 0.60 to 1.1 dL/g; 0.60 to 1 dL/g; 0.60 to less than 1 dL/g; 0.60 to 0.98 dL/g; 0.60 to 0.95 dL/g; 0.60 to 0.90 dL/g; 0.60 to 0.85 dL/g; 0.60 to 0.80 dL/g; 0.60 to 0.75 dL/g; 0.60 to less than 0.75 dL/g; 0.60 to 0.72 dL/g; 0.60 to 0.70 dL/g; 0.60 to less than 0.70 dL/g; 0.60 to 0.68 dL/g; 0.60 to less than 0.68 dL/g; 0.60 to 0.65 dL/g; 0.65 to 1.2 dL/g; 0.65 to 1.1 dL/g; 0.65 to 1 dL/g; 0.65 to less than 1 dL/g; 0.65 to 0.98 dL/g; 0.65 to 0.95 dL/g; 0.65 to 0.90 dL/g; 0.65 to 0.85 dL/g; 0.65 to 0.80 dL/g; 0.65 to 0.75 dL/g; 0.65 to less than 0.75 dL/g; 0.65 to 0.72 dL/g; 0.65 to 0.70 dL/g; 0.65 to less than 0.70 dL/g; 0.68 to 1.2 dL/g; 0.68 to 1.1 dL/g; 0.68 to 1 dL/g; 0.68 to less than 1 dL/g; 0.68 to 0.98 dL/g; 0.68 to 0.95 dL/g; 0.68 to 0.90 dL/g; 0.68 to 0.85 dL/g; 0.68 to 0.80 dL/g; 0.68 to 0.75 dL/g; 0.68 to less than 0.75 dL/g; 0.68 to 0.72 dL/g; greater than 0.70 dL/g to 1.2 dL/g; greater than 0.76 dL/g to 1.2 dL/g;

greater than 0.76 dL/g to 1.1 dL/g; greater than 0.76 dL/g to 1 dL/g; greater than 0.76 dL/g to less than 1 dL/g; greater than 0.76 dL/g to 0.98dL/g; greater than 0.76 dL/g to 0.95 dL/g; greater than 0.76 dL/g to 0.90 dL/g; greater than 0.80 dL/g to 1.2 dL/g; greater than 0.80 dL/g to 1.1 dL/g; greater than 0.80 dL/g to 1 dL/g; greater than 0.80 dL/g to less than 1 dL/g; greater than 0.80 dL/g to 1.2 dL/g; greater than 0.80 dL/g to 0.98dL/g; greater than 0.80 dL/g to 0.95 dL/g; greater than 0.80 dL/g to 0.90 dL/g.

[0121] For certain embodiments of the invention, the polyester may exhibit any of the following inherent viscosities as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C: 0.05 to less than 0.31 dL/g; 0.10 to less than 0.31 dL/g; 0.15 to less than 0.31 dL/g; 0.20 to less than 0.31 dL/g; 0.55 to less than 0.31 dL/g; 0.05 to 0.30 dL/g; 0.05 to 0.25 dL/g; 0.05 to 0.20 dL/g; 0.05 to 0.15 dL/g; 0.05 to 0.10 dL/g; 0.10 to 0.30 dL/g; 0.10 to 0.25 dL/g; 0.10 to 0.20 dL/g; 0.10 to 0.15 dL/g; 0.15 to 0.30 dL/g; 0.15 to 0.25 dL/g; 0.15 to 0.20 dL/g; and 0.20 to 0.25 dL/g.

[0122] For certain embodiments of the invention, the polyester may exhibit any of the following inherent viscosities as determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C: 0.30 to less than 0.75 dL/g; 0.30 to 0.68 dL/g; 0.30 to less than 0.68 dL/g; 0.30 to 0.60 dL/g; 0.30 to 0.55 dL/g; 0.30 to 0.50; 0.30 to 0.45 dL/g; and 0.30 to 0.40 dL/g.

[0123] It is contemplated that the compositions of the invention can possess at least one of the inherent viscosity ranges described herein and at least one of the monomer ranges for the compositions described herein unless otherwise stated. It is also contemplated that compositions of the invention can possess at least one of the T<sub>g</sub> ranges described herein and at least one of the monomer ranges for the compositions described herein unless otherwise stated. It is also contemplated that compositions of the invention can possess at least one of the T<sub>g</sub> ranges described herein, at least one of the inherent viscosity ranges described herein, and at least one of the monomer ranges for the compositions described herein unless otherwise stated.

[0124] For the desired polyester, the molar ratio of cis/trans 2,2,4,4-tetramethyl-1,3-cyclobutanediol can vary from the pure form of each or mixtures thereof. In certain embodiments, the molar percentages for cis and/or trans 2,2,4,4,-tetramethyl-1,3-cyclobutanediol are greater than 50 mole % cis and less than 50 mole % trans; or greater than 55 mole % cis and less than 45 mole % trans; or 30 to 70 mole % cis and 70 to 30 % trans; or 40 to 60 mole % cis and 60 to 40 mole % trans or 50 to 70 mole % trans and 50 to 30 % cis or 50 to 70 mole % cis and 50 to 30 % trans; or 60 to 70 mole % cis and 30 to 40 mole % trans; or greater than 70 mole % cis and up to 30 mole % trans; wherein the total sum of the mole percentages for cis- and trans- 2,2,4,4-tetramethyl-1,3-cyclobutanediol is equal to 100 mole %. The molar ratio of cis/trans 1,4-cyclohexandimethanol can vary within the range of 50/50 to 0/100, e.g., between 40/60 to 20/80.

[0125] In certain embodiments, terephthalic acid or an ester thereof, such as, for example, dimethyl terephthalate, or a mixture of terephthalic acid and an ester thereof, makes up most or all of the dicarboxylic acid component used to form the polyesters useful in the invention. In certain embodiments, terephthalic acid residues can make up a portion or all of the dicarboxylic acid component used to form the polyesters of the invention at a concentration of at least 70 mole %, such as at least 80 mole %, at least 90 mole %, at least 95 mole %, at least 99 mole %, or even a mole % of 100. In certain embodiments, higher amounts of terephthalic acid residues can be used in order to produce a higher impact strength polyester. In one embodiment, dimethyl terephthalate is part or all of the dicarboxylic acid component used to make the polyesters useful in the present invention. For the purposes of this disclosure, the terms "terephthalic acid" and "dimethyl terephthalate" are used interchangeably herein. In all embodiments, ranges of 70 to 100 mole %; or 80 to 100 mole %; or 90 to 100 mole %; or 99 to 100 mole %; or 100 mole % terephthalic acid and/or dimethyl terephthalate may be used.

[0126] In addition to terephthalic acid residues, the dicarboxylic acid component of the polyesters useful in the invention can comprise up to 30 mole %, up to 20 mole %, up to 10 mole %, up to 5 mole %, or up to 1 mole % of one or

more modifying aromatic dicarboxylic acids. Yet another embodiment contains 0 mole % modifying aromatic dicarboxylic acids. Thus, if present, it is contemplated that the amount of one or more modifying aromatic dicarboxylic acids can range from any of these preceding endpoint values including, for example, from 0.01 to 30 mole %, 0.01 to 20 mole %, from 0.01 to 10 mole %, from 0.01 to 5 mole % and from 0.01 to 1 mole %. In one embodiment, modifying aromatic dicarboxylic acids that may be used in the present invention include but are not limited to those having up to 20 carbon atoms, and which can be linear, para-oriented, or symmetrical. Examples of modifying aromatic dicarboxylic acids which may be used in this invention include, but are not limited to, isophthalic acid, 4,4'-biphenyldicarboxylic acid, 1,4-, 1,5-, 2,6-, 2,7-naphthalenedicarboxylic acid, and trans-4,4'-stilbenedicarboxylic acid, and esters thereof. In one embodiment, the modifying aromatic dicarboxylic acid is isophthalic acid.

[0127] The carboxylic acid component of the polyesters useful in the invention can be further modified with up to 10 mole %, such as up to 5 mole % or up to 1 mole % of one or more aliphatic dicarboxylic acids containing 2-16 carbon atoms, such as, for example, malonic, succinic, glutaric, adipic, pimelic, suberic, azelaic and dodecanedioic dicarboxylic acids. Certain embodiments can also comprise 0.01 or more mole %, such as 0.1 or more mole %, 1 or more mole %, 5 or more mole %, or 10 or more mole % of one or more modifying aliphatic dicarboxylic acids. Yet another embodiment contains 0 mole % modifying aliphatic dicarboxylic acids. Thus, if present, it is contemplated that the amount of one or more modifying aliphatic dicarboxylic acids can range from any of these preceding endpoint values including, for example, from 0.01 to 15 mole % and from 0.1 to 10 mole %. The total mole % of the dicarboxylic acid component is 100 mole %.

[0128] Esters of terephthalic acid and the other modifying dicarboxylic acids or their corresponding esters and/or salts may be used instead of the dicarboxylic acids. Suitable examples of dicarboxylic acid esters include, but are not limited to, the dimethyl, diethyl, dipropyl, diisopropyl, dibutyl, and diphenyl esters. In one

embodiment, the esters are chosen from at least one of the following: methyl, ethyl, propyl, isopropyl, and phenyl esters.

[0129] The 1,4-cyclohexanedimethanol may be cis, trans, or a mixture thereof, such as a cis/trans ratio of 60:40 to 40:60. In another embodiment, the trans-1,4-cyclohexanedimethanol can be present in an amount of 60 to 80 mole %.

[0130] The glycol component of the polyester portion of the polyester compositions useful in the invention can contain 25 mole % or less of one or more modifying glycols which are not 2,2,4,4-tetramethyl-1,3-cyclobutanediol or 1,4-cyclohexanedimethanol; in one embodiment, the polyesters useful in the invention may contain less than 15 mole % of one or more modifying glycols. In another embodiment, the polyesters useful in the invention can contain 10 mole % or less of one or more modifying glycols. In another embodiment, the polyesters useful in the invention can contain 5 mole % or less of one or more modifying glycols. In another embodiment, the polyesters useful in the invention can contain 3 mole % or less of one or more modifying glycols. In another embodiment, the polyesters useful in the invention can contain 0 mole % modifying glycols. Certain embodiments can also contain 0.01 or more mole %, such as 0.1 or more mole %, 1 or more mole %, 5 or more mole %, or 10 or more mole % of one or more modifying glycols. Thus, if present, it is contemplated that the amount of one or more modifying glycols can range from any of these preceding endpoint values including, for example, from 0.01 to 15 mole % and from 0.01 to 10 mole %.

[0131] Modifying glycols useful in the polyesters useful in the invention can refer to diols other than 2,2,4,4-tetramethyl-1,3-cyclobutanediol and 1,4-cyclohexanedimethanol and may contain 2 to 16 carbon atoms. Examples of suitable modifying glycols include, but are not limited to, ethylene glycol, diethylene glycol, 1,2-propanediol, 1,3-propanediol, neopentyl glycol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, p-xylene glycol, or mixtures thereof. In one embodiment, the modifying glycol is ethylene glycol. In another embodiment, the modifying glycols include, but are not limited to, 1,3-propanediol and/or 1,4-butanediol. In another embodiment, ethylene glycol is excluded as a

modifying diol. In another embodiment, 1,3-propanediol and 1,4-butanediol are excluded as modifying diols. In another embodiment, 2, 2-dimethyl-1,3-propanediol is excluded as a modifying diol.

[0132] The polyesters and/or the polycarbonates useful in the polyesters compositions of the invention can comprise from 0 to 10 mole percent, for example, from 0.01 to 5 mole percent, from 0.01 to 1 mole percent, from 0.05 to 5 mole percent, from 0.05 to 1 mole percent, or from 0.1 to 0.7 mole percent, or 0.1 to 0.5 mole percent, based the total mole percentages of either the diol or diacid residues; respectively, of one or more residues of a branching monomer, also referred to herein as a branching agent, having 3 or more carboxyl substituents, hydroxyl substituents, or a combination thereof. In certain embodiments, the branching monomer or agent may be added prior to and/or during and/or after the polymerization of the polyester. The polyester(s) useful in the invention can thus be linear or branched. The polycarbonate can also be linear or branched. In certain embodiments, the branching monomer or agent may be added prior to and/or during and/or after the polymerization of the polycarbonate.

[0133] Examples of branching monomers include, but are not limited to, multifunctional acids or multifunctional alcohols such as trimellitic acid, trimellitic anhydride, pyromellitic dianhydride, trimethylolpropane, glycerol, pentaerythritol, citric acid, tartaric acid, 3-hydroxyglutaric acid and the like. In one embodiment, the branching monomer residues can comprise 0.1 to 0.7 mole percent of one or more residues chosen from at least one of the following: trimellitic anhydride, pyromellitic dianhydride, glycerol, sorbitol, 1,2,6-hexanetriol, pentaerythritol, trimethylolethane, and/or trimesic acid. The branching monomer may be added to the polyester reaction mixture or blended with the polyester in the form of a concentrate as described, for example, in U.S. Patent Nos. 5,654,347 and 5,696,176, whose disclosure regarding branching monomers is incorporated herein by reference.

[0134] Glass transition temperature ( $T_g$ ) can be determined using a TA DSC 2920 from Thermal Analyst Instrument at a scan rate of 20°C/min.

[0135] Because of the long crystallization half-times (e.g., greater than 5 minutes) at 170°C exhibited by certain polyesters useful in the present invention, it can be possible to produce articles, including but not limited to, injection molded parts, injection blow molded articles, injection stretch blow molded articles, extruded film, extruded sheet, extrusion blow molded articles and fibers. The polyesters of the invention can be amorphous or semicrystalline. In one aspect, certain polyesters useful in the invention can have relatively low crystallinity. Certain polyesters useful in the invention can thus have a substantially amorphous morphology, meaning that the polyesters comprise substantially unordered regions of polymer.

[0136] In one embodiment, an "amorphous" polyester can have a crystallization half-time of greater than 5 minutes at 170°C or greater than 10 minutes at 170°C or greater than 50 minutes at 170 °C or greater than 100 minutes at 170°C. In one embodiment, of the invention, the crystallization half-times can be greater than 1,000 minutes at 170°C. In another embodiment of the invention, the crystallization half-times of the polyester useful in the invention can be greater than 10,000 minutes at 170°C. The crystallization half time of the polyester, as used herein, may be measured using methods well-known to persons of skill in the art. For example, the crystallization half time of the polyester,  $t_{1/2}$ , can be determined by measuring the light transmission of a sample via a laser and photo detector as a function of time on a temperature controlled hot stage. This measurement can be done by exposing the polymers to a temperature,  $T_{max}$ , and then cooling it to the desired temperature. The sample can then be held at the desired temperature by a hot stage while transmission measurements were made as a function of time. Initially, the sample can be visually clear with high light transmission and became opaque as the sample crystallizes. The crystallization half-time is the time at which the light transmission is halfway between the initial transmission and the final transmission.  $T_{max}$  is defined as the temperature required to melt the crystalline domains of the sample (if crystalline domains are present). The sample can be



heated to  $T_{max}$  to condition the sample prior to crystallization half time measurement. The absolute  $T_{max}$  temperature is different for each composition. For example PCT can be heated to some temperature greater than 290°C to melt the crystalline domains.

[0137] As shown in Table 1 and Figure 1 of the Examples, 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective than other comonomers such ethylene glycol and isophthalic acid at increasing the crystallization half-time, i.e., the time required for a polymer to reach half of its maximum crystallinity. By decreasing the crystallization rate of PCT, i.e. increasing the crystallization half-time, amorphous articles based on modified PCT may be fabricated by methods known in the art such as extrusion, injection molding, and the like. As shown in Table 1, these materials can exhibit higher glass transition temperatures and lower densities than other modified PCT copolyesters.

[0138] The polyester can exhibit an improvement in toughness combined with processability for some of the embodiments of the invention. For example, lowering the inherent viscosity slightly of the polyesters useful in the invention results in a more processable melt viscosity while retaining good physical properties of the polyesters such as toughness and heat resistance.

[0139] Increasing the content of 1,4-cyclohexanedimethanol in a copolyester based on terephthalic acid, ethylene glycol, and 1,4-cyclohexanedimethanol can improve toughness, which can be determined by the brittle-to-ductile transition temperature in a notched Izod impact strength test as measured by ASTM D256. This toughness improvement, by lowering of the brittle-to-ductile transition temperature with 1,4-cyclohexanedimethanol, is believed to occur due to the flexibility and conformational behavior of 1,4-cyclohexanedimethanol in the copolyester. Incorporating 2,2,4,4-tetramethyl-1,3-cyclobutanediol into PCT is believed to improve toughness, by lowering the brittle-to-ductile transition temperature, as shown in Table 2 and Figure 2 of the Examples. This is unexpected given the rigidity of 2,2,4,4-tetramethyl-1,3-cyclobutanediol.

[0140] In one embodiment, the melt viscosity of the polyester(s) useful in the invention is less than 30,000 poise as measured at 1 radian/second on a rotary

melt rheometer at 290°C. In another embodiment, the melt viscosity of the polyester(s) useful in the invention is less than 20,000 poise as measured at 1 radian/second on a rotary melt rheometer at 290°C.

[0141] In one embodiment, the melt viscosity of the polyester(s) useful in the invention is less than 15,000 poise as measured at 1 radian/second (rad/sec) on a rotary melt rheometer at 290°C.

[0142] In one embodiment, the melt viscosity of the polyester(s) useful in the invention is less than 10,000 poise as measured at 1 radian/second (rad/sec) on a rotary melt rheometer at 290°C. In another embodiment, the melt viscosity of the polyester(s) useful in the invention is less than 6,000 poise as measured at 1 radian/second on a rotary melt rheometer at 290°C. Viscosity at rad/sec is related to processability. Typical polymers have viscosities of less than 10,000 poise as measured at 1 radian/second when measured at their processing temperature. Polyesters are typically not processed above 290°C. Polycarbonate is typically processed at 290°C. The viscosity at 1 rad/sec of a typical 12 melt flow rate polycarbonate is 7000 poise at 290°C.

[0143] The present polyesters useful in the invention can possess one or more of the following properties. Notched Izod impact strength, as described in ASTM D256, is a common method of measuring toughness. The present polyesters useful in this invention can possess one or more of the following properties. In one embodiment, the polyesters useful in the invention exhibit an impact strength of at least 150 J/m (3 ft-lb/in) at 23°C with a 10-mil notch in a 3.2mm (1/8-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least (400 J/m) 7.5 ft-lb/in at 23°C with a 10-mil notch in a 3.2mm (1/8-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least 1000 J/m (18 ft-lb/in) at 23°C with a 10-mil notch in a 3.2mm (1/8-inch) thick bar determined according to ASTM D256. In one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least 150 J/m (3 ft-lb/in) at 23°C with a 10-mil notch in a 6.4mm (1/4-inch) thick bar determined according to

ASTM D256; in one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least (400 J/m) 7.5 ft-lb/in at 23°C with a 10-mil notch in a 6.4mm (1/4-inch) thick bar determined according to ASTM D256; in one embodiment, the polyesters useful in the invention exhibit a notched Izod impact strength of at least 1000 J/m (18 ft-lb/in) at 23°C with a 10-mil notch in a 6.4mm (1/4-inch) thick bar determined according to ASTM D256.

[0144] In another embodiment, certain polyesters useful in the invention can exhibit an increase in notched Izod impact strength when measured at 0°C of at least 3% or at least 5% or at least 10% or at least 15% as compared to the notched Izod impact strength when measured at -5°C with a 10-mil notch in a 1/8-inch thick bar determined according to ASTM D256. In addition, certain other polyesters can also exhibit a retention of notched Izod impact strength within plus or minus 5% when measured at 0°C through 30°C with a 10-mil notch in a 1/8-inch thick bar determined according to ASTM D256.

[0145] In yet another embodiment, certain polyesters useful in the invention can exhibit a retention in notched Izod impact strength with a loss of no more than 70% when measured at 23°C with a 10-mil notch in a 1/4-inch thick bar determined according to ASTM D256 as compared to notched Izod impact strength for the same polyester when measured at the same temperature with a 10-mil notch in a 1/8-inch thick bar determined according to ASTM D256.

[0146] In one embodiment, the polyesters useful in the invention can exhibit a ductile-to-brittle transition temperature of less than 0°C based on a 10-mil notch in a 1/8-inch thick bar as defined by ASTM D256.

[0147] In one embodiment, the polyesters useful in the invention can exhibit at least one of the following densities as determined using a gradient density column at 23°C: a density of less than 1.2 g/ml at 23°C; a density of less than 1.18 g/ml at 23°C; a density of 0.8 to 1.3 g/ml at 23°C; a density of 0.80 to 1.2 g/ml at 23°C; a density of 0.80 to less than 1.2 g/ml at 23°C; a density of 1.0 to 1.3 g/ml at 23°C; a density of 1.0 to 1.2 g/ml at 23°C; a density of 1.0 to 1.1 g/ml at 23°C; a density of 1.13 to 1.3 g/ml at 23°C; a density of 1.13 to 1.2 g/ml at 23°C.

[0148] In one embodiment, the polyesters useful in this invention can be visually clear. The term "visually clear" is defined herein as an appreciable absence of cloudiness, haziness, and/or muddiness, when inspected visually. In another embodiment, when the polyesters are blended with polycarbonate, including but not limited to, bisphenol A polycarbonates, the blends can be visually clear.

[0149] In other embodiments of the invention, the polyesters useful in the invention may have a yellowness index (ASTM D-1925) of less than 50 or less than 20.

[0150] In one embodiment, the polyesters useful in the invention and/or the polyester compositions of the invention, with or without toners, can have color values  $L^*$ ,  $a^*$  and  $b^*$  which can be determined using a Hunter Lab Ultrascan Spectra Colorimeter manufactured by Hunter Associates Lab Inc., Reston, Va. The color determinations are averages of values measured on either pellets of the polyesters or plaques or other items injection molded or extruded from them. They are determined by the  $L^*a^*b^*$  color system of the CIE (International Commission on Illumination) (translated), wherein  $L^*$  represents the lightness coordinate,  $a^*$  represents the red/green coordinate, and  $b^*$  represents the yellow/blue coordinate. In certain embodiments, the  $b^*$  values for the polyesters useful in the invention can be from -10 to less than 10 and the  $L^*$  values can be from 50 to 90. In other embodiments, the  $b^*$  values for the polyesters useful in the invention can be present in one of the following ranges: from -10 to 9; -10 to 8; -10 to 7; -10 to 6; -10 to 5; -10 to 4; -10 to 3; -10 to 2; from -5 to 9; -5 to 8; -5 to 7; -5 to 6; -5 to 5; -5 to 4; -5 to 3; -5 to 2; 0 to 9; 0 to 8; 0 to 7; 0 to 6; 0 to 5; 0 to 4; 0 to 3; 0 to 2; 1 to 10; 1 to 9; 1 to 8; 1 to 7; 1 to 6; 1 to 5; 1 to 4; 1 to 3; and 1 to 2. In other embodiments, the  $L^*$  value for the polyesters useful in the invention can be present in one of the following ranges: 50 to 60; 50 to 70; 50 to 80; 50 to 90; 60 to 70; 60 to 80; 60 to 90; 70 to 80; 79 to 90.

[0151] In some embodiments, use of the polyester compositions useful in the invention minimizes and/or eliminates the drying step prior to melt processing and/or thermoforming.

[0152] The polyester portion of the polyester compositions of the invention can be made by processes known from the literature such as, for example, by processes in homogenous solution, by transesterification processes in the melt, and by two phase interfacial processes. Suitable methods include, but are not limited to, the steps of reacting one or more dicarboxylic acids with one or more glycols at a temperature of 100°C to 315°C at a pressure of 0.1 to 760 mm Hg for a time sufficient to form a polyester. See U.S. Patent No. 3,772,405 for methods of producing polyesters, the disclosure regarding such methods is hereby incorporated herein by reference..

[0153] In another aspect, the invention relates to a process for producing a polyester. The process comprises:

- (I) heating a mixture comprising the monomers useful in any of the polyesters in the invention in the presence of a catalyst at a temperature of 150 to 240°C for a time sufficient to produce an initial polyester;
- (II) heating the initial polyester of step (I) at a temperature of 240 to 320°C for 1 to 4 hours; and
- (III) removing any unreacted glycols.

[0154] Suitable catalysts for use in this process include, but are not limited to, organo-zinc or tin compounds. The use of this type of catalyst is well known in the art. Examples of catalysts useful in the present invention include, but are not limited to, zinc acetate, butyltin tris-2-ethylhexanoate, dibutyltin diacetate, and/or dibutyltin oxide. Other catalysts may include, but are not limited to, those based on titanium, zinc, manganese, lithium, germanium, and cobalt. Catalyst amounts can range from 10 ppm to 20,000 ppm or 10 to 10,000 ppm, or 10 to 5000 ppm or 10 to 1000 ppm or 10 to 500 ppm, or 10 to 300 ppm or 10 to 250 based on the catalyst metal and based on the weight of the final polymer. The process can be carried out in either a batch or continuous process.

[0155] Typically, step (I) can be carried out until 50% by weight or more of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol has been reacted. Step (I) may be

carried out under pressure, ranging from atmospheric pressure to 100 psig. The term "reaction product" as used in connection with any of the catalysts useful in the invention refers to any product of a polycondensation or esterification reaction with the catalyst and any of the monomers used in making the polyester as well as the product of a polycondensation or esterification reaction between the catalyst and any other type of additive.

[0156] Typically, Step (II) and Step (III) can be conducted at the same time. These steps can be carried out by methods known in the art such as by placing the reaction mixture under a pressure ranging, from 0.002 psig to below atmospheric pressure, or by blowing hot nitrogen gas over the mixture.

[0157] In one embodiment, the invention further relates to a polyester product made by the process described above.

[0158] The invention further relates to a polymer blend. The blend comprises:

- (a) 5 to 95 wt % of at least one of the polyesters described above; and
- (b) 5 to 95 wt % of at least one polymeric component.

[0159] Suitable examples of the polymeric components include, but are not limited to, nylon, polyesters different from those described herein, polyamides such as ZYTEL® from DuPont; polystyrene, polystyrene copolymers, styrene acrylonitrile copolymers, acrylonitrile butadiene styrene copolymers, poly(methylmethacrylate), acrylic copolymers, poly(ether-imides) such as ULTEM® (a poly(ether-imide) from General Electric); polyphenylene oxides such as poly(2,6-dimethylphenylene oxide) or poly(phenylene oxide)/polystyrene blends such as NORYL 1000® (a blend of poly(2,6-dimethylphenylene oxide) and polystyrene resins from General Electric); polyphenylene sulfides; polyphenylene sulfide/sulfones; poly(ester-carbonates); polycarbonates such as LEXAN® (a polycarbonate from General Electric); polysulfones; polysulfone ethers; and poly(ether-ketones) of aromatic dihydroxy compounds; or mixtures of any of the foregoing polymers. The blends can be prepared by conventional processing techniques known in the art, such as melt blending or solution blending. In one embodiment, the polycarbonate is not present in the polyester composition. If

polycarbonate is used in a blend in the polyester compositions useful in the invention, the blends can be visually clear. However, the polyester compositions useful in the invention also contemplate the exclusion of polycarbonate as well as the inclusion of polycarbonate.

[0160] Polycarbonates useful in the invention may be prepared according to known procedures, for example, by reacting the dihydroxyaromatic compound with a carbonate precursor such as phosgene, a haloformate or a carbonate ester, a molecular weight regulator, an acid acceptor and a catalyst. Methods for preparing polycarbonates are known in the art and are described, for example, in U.S. Patent 4,452,933, where the disclosure regarding the preparation of polycarbonates is hereby incorporated by reference herein.

[0161] Examples of suitable carbonate precursors include, but are not limited to, carbonyl bromide, carbonyl chloride, or mixtures thereof; diphenyl carbonate; a di(halophenyl)carbonate, e.g., di(trichlorophenyl) carbonate, di(tribromophenyl) carbonate, and the like; di(alkylphenyl)carbonate, e.g., di(tolyl)carbonate; di(naphthyl)carbonate; di(chloronaphthyl)carbonate, or mixtures thereof; and bis-haloformates of dihydric phenols.

[0162] Examples of suitable molecular weight regulators include, but are not limited to, phenol, cyclohexanol, methanol, alkylated phenols, such as octylphenol, para-tertiary-butyl-phenol, and the like. In one embodiment, the molecular weight regulator is phenol or an alkylated phenol.

[0163] The acid acceptor may be either an organic or an inorganic acid acceptor. A suitable organic acid acceptor can be a tertiary amine and includes, but is not limited to, such materials as pyridine, triethylamine, dimethylaniline, tributylamine, and the like. The inorganic acid acceptor can be either a hydroxide, a carbonate, a bicarbonate, or a phosphate of an alkali or alkaline earth metal.

[0164] The catalysts that can be used include, but are not limited to, those that typically aid the polymerization of the monomer with phosgene. Suitable catalysts include, but are not limited to, tertiary amines such as triethylamine, tripropylamine, N,N-dimethylaniline, quaternary ammonium compounds such as, for example, tetraethylammonium bromide, cetyl triethyl ammonium bromide,

tetra-n-heptylammonium iodide, tetra-n-propyl ammonium bromide, tetramethyl ammonium chloride, tetra-methyl ammonium hydroxide, tetra-n-butyl ammonium iodide, benzyltrimethyl ammonium chloride and quaternary phosphonium compounds such as, for example, n-butyltriphenyl phosphonium bromide and methyltriphenyl phosphonium bromide.

[0165] The polycarbonates useful in the polyester compositions of the invention also may be copolyestercarbonates such as those described in U.S. Patents 3,169,121; 3,207,814; 4,194,038; 4,156,069; 4,430,484, 4,465,820, and 4,981,898, where the disclosure regarding copolyestercarbonates from each of the U.S. Patents is incorporated by reference herein.

[0166] Copolyestercarbonates useful in this invention can be available commercially and/or can be prepared by known methods in the art. For example, they can be typically obtained by the reaction of at least one dihydroxyaromatic compound with a mixture of phosgene and at least one dicarboxylic acid chloride, especially isophthaloyl chloride, terephthaloyl chloride, or both.

[0167] In addition, the polyester compositions and the polymer blend compositions containing the polyesters of this invention may also contain from 0.01 to 25% by weight or 0.01 to 20% by weight or 0.01 to 15% by weight or 0.01 to 10% by weight or 0.01 to 5% by weight of the total weight of the polyester composition of common additives such as colorants, dyes, mold release agents, flame retardants, plasticizers, nucleating agents, stabilizers, including but not limited to, UV stabilizers, thermal stabilizers and/or reaction products thereof, fillers, and impact modifiers. Examples of typical commercially available impact modifiers well known in the art and useful in this invention include, but are not limited to, ethylene/propylene terpolymers; functionalized polyolefins, such as those containing methyl acrylate and/or glycidyl methacrylate; styrene-based block copolymeric impact modifiers; and various acrylic core/shell type impact modifiers. For example, UV additives can be incorporated into articles of manufacture through addition to the bulk, through application of a hard coat, or through coextrusion of a cap layer. Residues of such additives are also contemplated as part of the polyester composition.



[0168] The polyesters of the invention can comprise at least one chain extender. Suitable chain extenders include, but are not limited to, multifunctional (including, but not limited to, bifunctional) isocyanates, multifunctional epoxides, including for example, epoxylated novolacs, and phenoxy resins. In certain embodiments, chain extenders may be added at the end of the polymerization process or after the polymerization process. If added after the polymerization process, chain extenders can be incorporated by compounding or by addition during conversion processes such as injection molding or extrusion. The amount of chain extender used can vary depending on the specific monomer composition used and the physical properties desired but is generally about 0.1 percent by weight to about 10 percent by weight, preferably about 0.1 to about 5 percent by weight based on the total weight of the polyester.

[0169] Thermal stabilizers are compounds that stabilize polyesters during polyester manufacture and/or post polymerization, including but not limited to phosphorous compounds including but not limited to phosphoric acid, phosphorous acid, phosphonic acid, phosphinic acid, phosphonous acid, and various esters and salts thereof. These can be present in the polyester compositions useful in the invention. The esters can be alkyl, branched alkyl, substituted alkyl, difunctional alkyl, alkyl ethers, aryl, and substituted aryl. In one embodiment, the number of ester groups present in the particular phosphorous compound can vary from zero up to the maximum allowable based on the number of hydroxyl groups present on the thermal stabilizer used. The term "thermal stabilizer" is intended to include the reaction product(s) thereof. The term "reaction product" as used in connection with the thermal stabilizers of the invention refers to any product of a polycondensation or esterification reaction between the thermal stabilizer and any of the monomers used in making the polyester as well as the product of a polycondensation or esterification reaction between the catalyst and any other type of additive.

[0170] Reinforcing materials may be useful in the compositions of this invention. The reinforcing materials may include, but are not limited to, carbon filaments, silicates, mica, clay, talc, titanium dioxide, Wollastonite, glass flakes,

glass beads and fibers, and polymeric fibers and combinations thereof. In one embodiment, the reinforcing materials are glass, such as fibrous glass filaments, mixtures of glass and talc, glass and mica, and glass and polymeric fibers.

[0171] In another embodiment, the invention further relates to articles of manufacture comprising any of the polyesters and blends described above.

[0172] In another embodiment, the invention further relates to articles of manufacture comprising any of the polyesters and blends described herein. extruded, calendered, and/or molded articles including but not limited to, injection molded articles, extruded articles, cast extrusion articles, profile extrusion articles, melt spun articles, thermoformed articles, extrusion molded articles, injection blow molded articles, injection stretch blow molded articles, extrusion blow molded articles, and extrusion stretch blow molded articles. These articles can include, but are not limited, to films, bottles (including, but not limited to, baby bottles), containers, sheet and/or fibers.

[0173] The present polyesters and/or polyester blend compositions can be useful in forming fibers, films, molded articles, containers, and sheeting. The methods of forming the polyesters into fibers, films, molded articles, containers, and sheeting are well known in the art. Examples of potential molded articles include without limitation: medical devices such as dialysis equipment, medical packaging, healthcare supplies, commercial food service products such as food pans, tumblers and storage boxes, baby bottles, food processors, blender and mixer bowls, utensils, water bottles, crisper trays, washing machine fronts, and vacuum cleaner parts. Other potential molded articles could include, but are not limited to, ophthalmic lenses and frames. For instance, this material can be used to make bottles, including but not limited to, baby bottles, as it is clear, tough, heat resistant, and displays good hydrolytic stability.

[0174] In another embodiment, the invention further relates to articles of manufacture comprising the film(s) and/or sheet(s) containing polyester compositions described herein.

[0175] The films and/or sheets useful in the present invention can be of any thickness which would be apparent to one of ordinary skill in the art. In one

embodiment, the film(s) of the invention have a thickness of no more than 40 mils. In one embodiment, the film(s) of the invention have a thickness of no more than 35 mils. In one embodiment, the film(s) of the invention have a thickness of no more than 30 mils. In one embodiment, the film(s) of the invention have a thickness of no more than 25 mils. In one embodiment, the film(s) of the invention have a thickness of no more than 20 mils.

[0176] In one embodiment, the sheet(s) of the invention have a thickness of no less than 20 mils. In another embodiment, the sheet(s) of the invention have a thickness of no less than 25 mils. In another embodiment, the sheet(s) of the invention have a thickness of no less than 30 mils. In another embodiment, the sheet(s) of the invention have a thickness of no less than 35 mils. In another embodiment, the sheet(s) of the invention have a thickness of no less than 40 mils.

[0177] The invention further relates to the film(s) and/or sheet(s) comprising the polyester compositions of the invention. The methods of forming the polyesters into film(s) and/or sheet(s) are well known in the art. Examples of film(s) and/or sheet(s) of the invention including but not limited to extruded film(s) and/or sheet(s), calendered film(s) and/or sheet(s), compression molded film(s) and/or sheet(s), solution casted film(s) and/or sheet(s). Methods of making film and/or sheet include but are not limited to extrusion, calendering, compression molding, and solution casting.

[0178] Examples of potential articles made from film and/or sheet include, but are not limited, to uniaxially stretched film, biaxially stretched film, shrink film (whether or not uniaxially or biaxially stretched, liquid crystal display film (including but not limited to diffuser sheets, compensation films and protective films), thermoformed sheet, graphic arts film, outdoor signs, skylights, coating(s), coated articles, painted articles, laminates, laminated articles, and/or multiwall films or sheets.

[0179] Examples of graphic arts film include, but are not limited to, nameplates, membrane switch overlays; point-of-purchase displays; flat or in-mold decorative panels on washing machines; flat touch panels on refrigerators; flat panel on

ovens; decorative interior trim for automobiles; instrument clusters for automobiles; cell phone covers; heating and ventilation control displays; automotive console panels; automotive gear shift panels; control displays or warning signals for automotive instrument panels; facings, dials or displays on household appliances; facings, dials or displays on washing machines; facings, dials or displays on dishwashers; keypads for electronic devices; keypads for mobile phones, PDAs (hand-held computers) or remote controls; displays for electronic devices; displays for hand-held electronic devices such as phones and PDAs; panels and housings for mobile or standard phones; logos on electronic devices; and logos for hand-held phones.

[0180] Multiwall film or sheet refers to sheet extruded as a profile consisting of multiple layers that are connected to each other by means of vertical ribs. Examples of multiwall film or sheet include but are not limited to greenhouses and commercial canopies.

[0181] Examples of extruded articles include but are not limited to film for graphic arts, applications, outdoor signs, skylights, film for plastic glass laminates, and liquid crystal display (LCD) films, including, but not limited to, diffuser sheets, compensation films, and protective films.

[0182] As used herein, the abbreviation "wt" means "weight".

[0183] The following examples further illustrate how the polyesters and/or polyester compositions of the invention can be made and evaluated, and are intended to be purely exemplary of the invention and are not intended to limit the scope thereof. Unless indicated otherwise, parts are parts by weight, temperature is in degrees C or is at room temperature, and pressure is at or near atmospheric.

## EXAMPLES

### Measurement Methods

[0184] The inherent viscosity of the polyesters was determined in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C.

[0185] Unless stated otherwise, the glass transition temperature ( $T_g$ ) was determined using a TA DSC 2920 instrument from Thermal Analyst Instruments at a scan rate of 20°C/min according to ASTM D3418.

[0186] The glycol content and the cis/trans ratio of the compositions were determined by proton nuclear magnetic resonance (NMR) spectroscopy. All NMR spectra were recorded on a JEOL Eclipse Plus 600MHz nuclear magnetic resonance spectrometer using either chloroform-trifluoroacetic acid (70-30 volume/volume) for polymers or, for oligomeric samples, 60/40(wt/wt) phenol/tetrachloroethane with deuterated chloroform added for lock. Peak assignments for 2,2,4,4-tetramethyl-1,3-cyclobutanediol resonances were made by comparison to model mono- and dibenzoate esters of 2,2,4,4-tetramethyl-1,3-cyclobutanediol. These model compounds closely approximate the resonance positions found in the polymers and oligomers.

[0187] The crystallization half-time,  $t_{1/2}$ , was determined by measuring the light transmission of a sample via a laser and photo detector as a function of time on a temperature controlled hot stage. This measurement was done by exposing the polymers to a temperature,  $T_{max}$ , and then cooling it to the desired temperature. The sample was then held at the desired temperature by a hot stage while transmission measurements were made as a function of time. Initially, the sample was visually clear with high light transmission and became opaque as the sample crystallized. The crystallization half-time was recorded as the time at which the light transmission was halfway between the initial transmission and the final transmission.  $T_{max}$  is defined as the temperature required to melt the crystalline domains of the sample (if crystalline domains are present). The  $T_{max}$  reported in the examples below represents the temperature at

which each sample was heated to condition the sample prior to crystallization half time measurement. The  $T_{\max}$  temperature is dependant on composition and is typically different for each polyester. For example, PCT may need to be heated to some temperature greater than 290°C to melt the crystalline domains.

[0188] Density was determined using a gradient density column at 23°C.

[0189] The melt viscosity reported herein was measured by using a Rheometrics Dynamic Analyzer (RDA II). The melt viscosity was measured as a function of shear rate, at frequencies ranging from 1 to 400 rad/sec, at the temperatures reported. The zero shear melt viscosity ( $\eta_0$ ) is the melt viscosity at zero shear rate estimated by extrapolating the data by known models in the art. This step is automatically performed by the Rheometrics Dynamic Analyzer (RDA II) software.

[0190] The polymers were dried at a temperature ranging from 80 to 100°C in a vacuum oven for 24 hours and injection molded on a Boy 22S molding machine to give 1/8x1/2x5-inch and 1/4x1/2x5-inch flexure bars. These bars were cut to a length of 2.5 inch and notched down the 1/2 inch width with a 10-mil notch in accordance with ASTM D256. The average Izod impact strength at 23°C was determined from measurements on 5 specimens.

[0191] In addition, 5 specimens were tested at various temperatures using 5°C increments in order to determine the brittle-to-ductile transition temperature. The brittle-to-ductile transition temperature is defined as the temperature at which 50% of the specimens fail in a brittle manner as denoted by ASTM D256.

[0192] Color values reported herein were determined using a Hunter Lab Ultrascan Spectra Colorimeter manufactured by Hunter Associates Lab Inc., Reston, Va. The color determinations were averages of values measured on either pellets of the polyesters or plaques or other items injection molded or extruded from them. They were determined by the  $L^*a^*b^*$  color system of the CIE (International Commission on Illumination) (translated), wherein  $L^*$  represents the lightness coordinate,  $a^*$  represents the red/green coordinate, and  $b^*$  represents the yellow/blue coordinate.

[0193] In addition, 10-mil films were compression molded using a Carver press at 240°C.

[0194] Unless otherwise specified, the cis/trans ratio of the 1,4-cyclohexanedimethanol used in the following examples was approximately 30/70, and could range from 35/65 to 25/75. Unless otherwise specified, the cis/trans ratio of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol used in the following examples was approximately 50/50.

[0195] The following abbreviations apply throughout the working examples and figures:

TPA	Terephthalic acid
DMT	Dimethyl terephthalate
TMCD	2,2,4,4-tetramethyl-1,3-cyclobutanediol
CHDM	1,4-cyclohexanedimethanol
IV	Inherent viscosity
$\eta_o$	Zero shear melt viscosity
$T_g$	Glass transition temperature
$T_{bd}$	Brittle-to-ductile transition temperature
$T_{max}$	Conditioning temperature for crystallization half time measurements

#### Example 1

[0196] This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective at reducing the crystallization rate of PCT than ethylene glycol or isophthalic acid. In addition, this example illustrates the benefits of 2,2,4,4-tetramethyl-1,3-cyclobutanediol on the glass transition temperature and density.

[0197] A variety of copolyesters were prepared as described below. These copolyesters were all made with 200 ppm dibutyl tin oxide as the catalyst in order to minimize the effect of catalyst type and concentration on nucleation during crystallization studies. The cis/trans ratio of the 1,4-cyclohexanedimethanol was 31/69 while the cis/trans ratio of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol is reported in Table 1.

[0198] For purposes of this example, the samples had sufficiently similar inherent viscosities thereby effectively eliminating this as a variable in the crystallization rate measurements.

[0199] Crystallization half-time measurements from the melt were made at temperatures from 140 to 200°C at 10°C increments and are reported in Table 1. The fastest crystallization half-time for each sample was taken as the minimum value of crystallization half-time as a function of temperature, typically occurring around 170 to 180°C. The fastest crystallization half-times for the samples are plotted in Figure 1 as a function of mole% comonomer modification to PCT.

[0200] The data shows that 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective than ethylene glycol and isophthalic acid at decreasing the crystallization rate (i.e., increasing the crystallization half-time). In addition, 2,2,4,4-tetramethyl-1,3-cyclobutanediol increases  $T_g$  and lowers density.



**Table 1**  
Crystallization Half-times (min)

Example	Comonomer (mol %) <sup>1</sup>	IV (dl/g)	Density (g/ml)	T <sub>g</sub> (°C)	T <sub>max</sub> (°C)	at 140 °C (min)	at 150 °C (min)	at 160 °C (min)	at 170 °C (min)	at 180 °C (min)	at 190 °C (min)	at 200 °C (min)
1A	20.2 % A <sup>2</sup>	0.630	1.198	87.5	290	2.7	2.1	1.3	1.2	0.9	1.1	1.5
1B	19.8 % B	0.713	1.219	87.7	290	2.3	2.5	1.7	1.4	1.3	1.4	1.7
1C	20.0 % C	0.731	1.188	100.5	290	>180	>60	35.0	23.3	21.7	23.3	25.2
1D	40.2 % A <sup>2</sup>	0.674	1.198	81.2	260	18.7	20.0	21.3	25.0	34.0	59.9	96.1
1E	34.5 % B	0.644	1.234	82.1	260	8.5	8.2	7.3	7.3	8.3	10.0	11.4
1F	40.1 % C	0.653	1.172	122.0	260	>10 days	>5 days	>5 days	19204	> 5 days	>5 days	>5 days
1G	14.3 % D	0.646 <sup>3</sup>	1.188	103.0	290	55.0	28.8	11.6	6.8	4.8	5.0	5.5
1H	15.0 % E	0.728 <sup>4</sup>	1.189	99.0	290	25.4	17.1	8.1	5.9	4.3	2.7	5.1

1 The balance of the diol component of the polyesters in Table 1 is 1, 4-cyclohexanedimethanol; and the balance of the dicarboxylic acid component of the polyesters in Table 1 is dimethyl terephthalate; if the dicarboxylic acid is not described, it is 100 mole % dimethyl terephthalate.

2 100 mole % 1,4-cyclohexanedimethanol.

3 A film was pressed from the ground polyester of Example 1G at 240°C. The resulting film had an inherent viscosity value of 0.575 dL/g.

4 A film was pressed from the ground polyester of Example 1H at 240°C. The resulting film had an inherent viscosity value of 0.0652 dL/g.

where:

A is Isophthalic Acid

B is Ethylene Glycol

C is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (approx. 50/50 cis/trans)

D is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (98/2 cis/trans)

E is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (5/95 cis/trans)

[0201] As shown in Table 1 and Figure 1, 2,2,4,4-tetramethyl-1,3-cyclobutanediol is more effective than other comonomers, such ethylene glycol and isophthalic acid, at increasing the crystallization half-time, *i.e.*, the time required for a polymer to reach half of its maximum crystallinity. By decreasing

the crystallization rate of PCT (increasing the crystallization half-time), amorphous articles based on 2,2,4,4-tetramethyl-1,3-cyclobutanediol-modified PCT as described herein may be fabricated by methods known in the art. As shown in Table 1, these materials can exhibit higher glass transition temperatures and lower densities than other modified PCT copolyesters.

[0202] Preparation of the polyesters shown on Table 1 is described below.

**Example 1A**

[0203] This example illustrates the preparation of a copolyester with a target composition of 80 mol% dimethyl terephthalate residues, 20 mol % dimethyl isophthalate residues, and 100 mol% 1,4-cyclohexanedimethanol residues (28/72 cis/trans).

[0204] A mixture of 56.63 g of dimethyl terephthalate, 55.2 g of 1,4-cyclohexanedimethanol, 14.16 g of dimethyl isophthalate, and 0.0419 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210°C for 5 minutes and then the temperature was gradually increased to 290°C over 30 minutes. The reaction mixture was held at 290°C for 60 minutes and then vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 5 minutes. A pressure of 0.3 mm of Hg was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 87.5°C and an inherent viscosity of 0.63 dl/g. NMR analysis showed that the polymer was composed of 100 mol% 1,4-cyclohexanedimethanol residues and 20.2 mol% dimethyl isophthalate residues.

**Example 1B**

[0205] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 20 mol % ethylene glycol residues, and 80 mol% 1,4-cyclohexanedimethanol residues (32/68 cis/trans).

[0206] A mixture of 77.68 g of dimethyl terephthalate, 50.77 g of 1,4-cyclohexanedimethanol, 27.81 g of ethylene glycol, and 0.0433 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 200°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 200°C for 60 minutes and then the temperature was gradually increased to 210°C over 5 minutes. The reaction mixture was held at 210°C for 120 minutes and then heated up to 280°C in 30 minutes. Once at 280°C, vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 10 minutes. A pressure of 0.3 mm of Hg was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 87.7°C and an inherent viscosity of 0.71 dl/g. NMR analysis showed that the polymer was composed of 19.8 mol% ethylene glycol residues.

**Example 1C**

[0207] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 20 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, and 80 mol% 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

[0208] A mixture of 77.68 g of dimethyl terephthalate, 48.46 g of 1,4-cyclohexanedimethanol, 17.86 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. This polyester was prepared in a manner similar to that described in Example 1A. A high melt

viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 100.5°C and an inherent viscosity of 0.73 dl/g. NMR analysis showed that the polymer was composed of 80.5 mol% 1,4-cyclohexanedimethanol residues and 19.5 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**Example 1D**

[0209] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 40 mol % dimethyl isophthalate residues, and 100 mol% 1,4-cyclohexanedimethanol residues (28/72 cis/trans).

[0210] A mixture of 42.83 g of dimethyl terephthalate, 55.26 g of 1,4-cyclohexanedimethanol, 28.45 g of dimethyl isophthalate, and 0.0419 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210°C for 5 minutes and then the temperature was gradually increased to 290°C over 30 minutes. The reaction mixture was held at 290°C for 60 minutes and then vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 5 minutes. A pressure of 0.3 mm of Hg was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 81.2°C and an inherent viscosity of 0.67 dl/g. NMR analysis showed that the polymer was composed of 100 mol% 1,4-cyclohexanedimethanol residues and 40.2 mol% dimethyl isophthalate residues.

**Example 1E**

[0211] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 40 mol % ethylene

glycol residues, and 60 mol% 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

[0212] A mixture of 81.3 g of dimethyl terephthalate, 42.85 g of 1,4-cyclohexanedimethanol, 34.44 g of ethylene glycol, and 0.0419 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 200°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 200°C for 60 minutes and then the temperature was gradually increased to 210°C over 5 minutes. The reaction mixture was held at 210°C for 120 minutes and then heated up to 280°C in 30 minutes. Once at 280°C, vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 10 minutes. A pressure of 0.3 mm of Hg was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 82.1°C and an inherent viscosity of 0.64 dl/g. NMR analysis showed that the polymer was composed of 34.5 mol% ethylene glycol residues.

#### Example 1F

[0213] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 40 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues, and 60 mol% 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

[0214] A mixture of 77.4 g of dimethyl terephthalate, 36.9 g of 1,4-cyclohexanedimethanol, 32.5 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210°C for 3 minutes and then the temperature was gradually increased to 260°C over 30 minutes. The reaction mixture was held at 260°C for 120

minutes and then heated up to 290°C in 30 minutes. Once at 290°C, vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 5 minutes. A pressure of 0.3 mm of Hg was maintained for a total time of 90 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 122°C and an inherent viscosity of 0.65 dl/g. NMR analysis showed that the polymer was composed of 59.9 mol% 1,4-cyclohexanedimethanol residues and 40.1 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**Example 1G**

[0215] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 20 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues (98/2 cis/trans), and 80 mol% 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

[0216] A mixture of 77.68 g of dimethyl terephthalate, 48.46 g of 1,4-cyclohexanedimethanol, 20.77 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210°C. The stirring speed was set to 200 RPM throughout the experiment. The contents of the flask were heated at 210°C for 3 minutes and then the temperature was gradually increased to 260°C over 30 minutes. The reaction mixture was held at 260°C for 120 minutes and then heated up to 290°C in 30 minutes. Once at 290°C, vacuum was gradually applied over the next 5 minutes until the pressure inside the flask reached 100 mm of Hg and the stirring speed was also reduced to 100 RPM. The pressure inside the flask was further reduced to 0.3 mm of Hg over the next 5 minutes and the stirring speed was reduced to 50 RPM. A pressure of 0.3 mm of Hg was maintained for a total time of 60 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 103°C and an inherent viscosity of

0.65 dl/g. NMR analysis showed that the polymer was composed of 85.7 mol% 1,4-cyclohexanedimethanol residues and 14.3 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**Example 1H**

[0217] This example illustrates the preparation of a copolyester with a target composition of 100 mol% dimethyl terephthalate residues, 20 mol % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues (5/95 cis/trans), and 80 mol% 1,4-cyclohexanedimethanol residues (31/69 cis/trans).

[0218] A mixture of 77.68 g of dimethyl terephthalate, 48.46 g of 1,4-cyclohexanedimethanol, 20.77 g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 0.046 g of dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 210°C. The stirring speed was set to 200 RPM at the beginning of the experiment. The contents of the flask were heated at 210°C for 3 minutes and then the temperature was gradually increased to 260°C over 30 minutes. The reaction mixture was held at 260°C for 120 minutes and then heated up to 290°C in 30 minutes. Once at 290°C, vacuum was gradually applied over the next 5 minutes with a set point of 100 mm of Hg and the stirring speed was also reduced to 100 RPM. The pressure inside the flask was further reduced to a set point of 0.3 mm of Hg over the next 5 minutes and the stirring speed was reduced to 50 RPM. This pressure was maintained for a total time of 60 minutes to remove excess unreacted diols. It was noted that the vacuum system failed to reach the set point mentioned above, but produced enough vacuum to produce a high melt viscosity, visually clear and colorless polymer with a glass transition temperature of 99°C and an inherent viscosity of 0.73 dl/g. NMR analysis showed that the polymer was composed of 85 mol% 1,4-cyclohexanedimethanol residues and 15 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**Example 2**

[0219] This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol improves the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol).

[0220] Copolyesters based on 2,2,4,4-tetramethyl-1,3-cyclobutanediol were prepared as described below. The cis/trans ratio of the 1,4-cyclohexanedimethanol was approximately 31/69 for all samples. Copolyesters based on ethylene glycol and 1,4-cyclohexanedimethanol were commercial polyesters. The copolyester of Example 2A (Estar PCTG 5445) was obtained from Eastman Chemical Co. The copolyester of Example 2B was obtained from Eastman Chemical Co. under the trade name Spectar. Example 2C and Example 2D were prepared on a pilot plant scale (each a 15-lb batch) following an adaptation of the procedure described in Example 1A and having the inherent viscosities and glass transition temperatures described in Table 2 below. Example 2C was prepared with a target tin amount of 300ppm (Dibutyltin Oxide). The final product contained 295 ppm tin. The color values for the polyester of Example 2C were  $L^* = 77.11$ ;  $a^* = -1.50$ ; and  $b^* = 5.79$ . Example 2D was prepared with a target tin amount of 300ppm (Dibutyltin Oxide). The final product contained 307 ppm tin. The color values for the polyester of Example 2D were  $L^* = 66.72$ ;  $a^* = -1.22$ ; and  $b^* = 16.28$ .

[0221] Materials were injection molded into bars and subsequently notched for Izod testing. The notched Izod impact strengths were obtained as a function of temperature and are also reported in Table 2.

[0222] For a given sample, the Izod impact strength undergoes a major transition in a short temperature span. For instance, the Izod impact strength of a copolyester based on 38 mol% ethylene glycol undergoes this transition between 15 and 20°C. This transition temperature is associated with a change in failure mode; brittle/low energy failures at lower temperatures and ductile/high energy failures at higher temperatures. The transition temperature is denoted as the brittle-to-ductile transition temperature,  $T_{bd}$ , and is a measure of toughness.  $T_{bd}$  is reported in Table 2 and plotted against mol% comonomer in Figure 2.



[0223] The data shows that adding 2,2,4,4-tetramethyl-1,3-cyclobutanediol to PCT lowers  $T_{bd}$  and improves the toughness, as compared to ethylene glycol, which increases  $T_{bd}$  of PCT.

**Table 2**

Notched Izod Impact Energy (ft-lb/in)

Example	Comonomer (mol %) <sup>1</sup>	IV (dl/g)	T <sub>g</sub> (°C)	T <sub>bd</sub> (°C)	at -20 °C	at -15 °C	at -10 °C	at -5 °C	at 0 °C	at 5 °C	at 10 °C	at 15 °C	at 20 °C	at 25 °C	at 30 °C
2A	38.0 % B	0.68	86	18	NA	NA	NA	1.5	NA	NA	1.5	1.5	32	32	NA
2B	69.0 % B	0.69	82	26	NA	NA	NA	NA	NA	NA	2.1	NA	2.4	13.7	28.7
2C	22.0 % C	0.66	106	-5	1.5	NA	12	23	23	NA	23	NA	NA	NA	NA
2D	42.8 % C	0.60	133	-12	2.5	2.5	11	NA	14	NA	NA	NA	NA	NA	NA

<sup>1</sup> The balance of the glycol component of the polyesters in the Table is 1,4-cyclohexanedimethanol. All polymers were prepared from 100 mole % dimethyl terephthalate.

NA = Not available.

where: B is Ethylene glycol  
C is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (50/50 cis/trans)

**Example 3**

[0224] This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol can improve the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol). Polyesters prepared in this example fall comprise more than 25 to less than 40 mol% of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

[0225] Copolyesters based on dimethyl terephthalate, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol (31/69 cis/trans) were prepared as described below, having the composition and properties shown on Table 3. The balance up to 100 mol% of the diol component of the polyesters in Table 3 was 1,4-cyclohexanedimethanol (31/69 cis/trans).

[0226] Materials were injection molded into both 3.2mm and 6.4mm thick bars and subsequently notched for Izod impact testing. The notched Izod impact strengths were obtained at 23°C and are reported in Table 3. Density, T<sub>g</sub>, and

crystallization halftime were measured on the molded bars. Melt viscosity was measured on pellets at 290°C.

**Table 3**

Compilation of various properties for certain polyesters useful in the invention

Example	TMCD mole%	% cis TMCD	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched Izod of 3.2mm thick bars at 23°C (J/m)	Notched Izod of 6.4mm thick bars at 23°C (J/m)	Specific Gravity (g/mL)	Tg (°C)	Crystallization Halftime from melt at 170°C (min)	Melt Viscosity at 1 rad/sec at 290°C (Poise)
A	27	47.8	0.714	0.678	877	878	1.178	113	280	8312
B	31	NA	0.667	0.641	807	789	1.174	116	600	6592

NA = Not available.

**Example 3A**

[0227] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 11.82 lb (37.28 gram-mol) 1,4-cyclohexanedimethanol, and 6.90 lb (21.77 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250°C and 20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. The temperature of the reaction mixture was then increased to 270°C and the pressure was decreased to 90 mm of Hg. After a 1 hour hold time at 270°C and 90 mm of Hg, the agitator speed was decreased to 15 RPM, the reaction mixture temperature was increased to 290°C, and the pressure was decreased to <1 mm of Hg. The reaction mixture was held at 290°C and at a pressure of <1 mm of Hg until the power draw to the agitator no longer increased (50 minutes). The pressure of the pressure vessel was then increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.714 dL/g and a Tg of 113°C. NMR analysis showed that

the polymer was composed of 73.3 mol% 1,4-cyclohexane-dimethanol residues and 26.7 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

**Example 3B**

[0228] The polyester of Example 3B was prepared following a procedure similar to the one described for Example 3A. The composition and properties of this polyester are shown in Table 3.

**Example 4**

[0229] This example illustrates that 2,2,4,4-tetramethyl-1,3-cyclobutanediol can improve the toughness of PCT-based copolyesters (polyesters containing terephthalic acid and 1,4-cyclohexanedimethanol). Polyesters prepared in this example comprise 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues in an amount of 40 mol% or greater.

[0230] Copolyesters based on dimethyl terephthalate, 2,2,4,4-tetramethyl-1,3-cyclobutanediol, and 1,4-cyclohexanedimethanol were prepared as described below, having the composition and properties shown on Table 4. The balance up to 100 mol% of the diol component of the polyesters in Table 4 was 1,4-cyclohexanedimethanol (31/69 cis/trans).

[0231] Materials were injection molded into both 3.2mm and 6.4mm thick bars and subsequently notched for Izod impact testing. The notched Izod impact strengths were obtained at 23°C and are reported in Table 4. Density, Tg, and crystallization half-time were measured on the molded bars. Melt viscosity was measured on pellets at 290°C.

**Table 4**

Compilation of various properties for certain polyesters useful in the invention

Example	TMCD mole%	% cis TMCD	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched Izod of 3.2mm thick bars at 23°C (J/m)	Notched Izod of 6.4mm thick bars at 23°C (J/m)	Specific Gravity (g/mL)	Tg (°C)	Crystallization Halftime from melt at 170°C (min)	Melt Viscosity at 1 rad/sec at 290°C (Poise)
A	44	46.2	0.657	0.626	727	734	1.172	119	NA	9751
B	45	NA	0.626	0.580	748	237	1.167	123	NA	8051
C	45	NA	0.582	0.550	671	262	1.167	125	19782	5835
D	45	NA	0.541	0.493	424	175	1.167	123	NA	3275
E	59	46.6	0.604	0.576	456	311	1.156	139	NA	16537
F	45	47.2	0.475	0.450	128	30	1.169	121	NA	1614

NA = Not available.

**Example 4A**

[0232] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 8.84 lb (27.88 gram-mol) 1,4-cyclohexanedimethanol, and 10.08 lb (31.77 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250°C and 20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. Then the agitator speed was decreased to 15 RPM, the temperature of the reaction mixture was then increased to 290°C and the pressure was decreased to 2 mm of Hg. The reaction mixture was held at 290°C and at a pressure of 2 mm of Hg until the power draw to the agitator no longer increased (80 minutes). The pressure of the pressure vessel was then increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.657 dL/g and a Tg of 119°C. NMR analysis showed that the polymer was composed of 56.3 mol% 1,4-cyclohexane-dimethanol residues

and 43.7 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of:  $L^* = 75.04$ ,  $a^* = -1.82$ , and  $b^* = 6.72$ .

**Example 4B to Example 4D**

[0233] The polyesters described in Example 4B to Example 4D were prepared following a procedure similar to the one described for Example 4A. The composition and properties of these polyesters are shown in Table 4.

**Example 4E**

[0234] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 6.43 lb (20.28 gram-mol) 1,4-cyclohexanedimethanol, and 12.49 lb (39.37 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250°C and 20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. Then the agitator speed was decreased to 15 RPM, the temperature of the reaction mixture was then increased to 290°C and the pressure was decreased to 2 mm of Hg. The reaction mixture was held at 290°C and at a pressure of <1 mm of Hg until the power draw to the agitator no longer increased (50 minutes). The pressure of the pressure vessel was then increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.604 dL/g and a  $T_g$  of 139°C. NMR analysis showed that the polymer was composed of 40.8 mol% 1,4-cyclohexanedimethanol residues and 59.2 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of:  $L^* = 80.48$ ,  $a^* = -1.30$ , and  $b^* = 6.82$ .

**Example 4F**

[0235] 21.24 lb (49.71 gram-mol) dimethyl terephthalate, 8.84 lb (27.88 gram-mol) 1,4-cyclohexanedimethanol, and 10.08 lb (31.77 gram-mol) 2,2,4,4-tetramethyl-1,3-cyclobutanediol were reacted together in the presence of 200 ppm of the catalyst butyltin tris(2-ethylhexanoate). The reaction was carried out under a nitrogen gas purge in an 18-gallon stainless steel pressure vessel fitted with a condensing column, a vacuum system, and a HELICONE-type agitator. With the agitator running at 25 RPM, the reaction mixture temperature was increased to 250°C and the pressure was increased to 20 psig. The reaction mixture was held for 2 hours at 250°C and 20 psig pressure. The pressure was then decreased to 0 psig at a rate of 3 psig/minute. The temperature of the reaction mixture was then increased to 270°C and the pressure was decreased to 90 mm of Hg. After a 1 hour hold time at 270°C and 90 mm of Hg, the agitator speed was decreased to 15 RPM and the pressure was decreased to 4 mm of Hg. When the reaction mixture temperature was 270°C and the pressure was 4 mm of Hg, the pressure of the pressure vessel was immediately increased to 1 atmosphere using nitrogen gas. The molten polymer was then extruded from the pressure vessel. The cooled, extruded polymer was ground to pass a 6-mm screen. The polymer had an inherent viscosity of 0.475 dL/g and a T<sub>g</sub> of 121°C. NMR analysis showed that the polymer was composed of 55.5 mol% 1,4-cyclohexane-dimethanol residues and 44.5 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues. The polymer had color values of: L\* = 85.63, a\* = -0.88, and b\* = 4.34.

**Example 5—Comparative Example**

[0236] This example shows data for comparative materials are shown in Table 5. The PC was Makrolon 2608 from Bayer, with a nominal composition of 100 mole% bisphenol A residues and 100 mole% diphenyl carbonate residues. Makrolon 2608 has a nominal melt flow rate of 20 grams/10 minutes measured at 300C using a 1.2 kg weight. The PET was Eastar 9921 from Eastman Chemical Company, with a nominal composition of 100 mole% terephthalic acid, 3.5 mole% cyclohexanedimethanol (CHDM) and 96.5 mole% ethylene glycol. The PETG

was Eastar 6763 from Eastman Chemical Company, with a nominal composition of 100 mole% terephthalic acid, 31 mole% cyclohexanedimethanol (CHDM) and 69 mole % ethylene glycol. The PCTG was Eastar DN001 from Eastman Chemical Company, with a nominal composition of 100 mole% terephthalic acid, 62 mole% cyclohexanedimethanol (CHDM) and 38 mole % ethylene glycol. The PCTA was Eastar AN001 from Eastman Chemical Company, with a nominal composition of 65 mole% terephthalic acid, 35 mole% isophthalic acid and 100 mole% cyclohexanedimethanol (CHDM). The Polysulfone was Udel 1700 from Solvay, with a nominal composition of 100 mole% bisphenol A residues and 100 mole% 4,4-dichlorosulfonyl sulfone residues. Udel 1700 has a nominal melt flow rate of 6.5 grams/10 minutes measured at 343C using a 2.16 kg weight. The SAN was Lustran 31 from Lanxess, with a nominal composition of 76 weight % styrene and 24 weight % acrylonitrile. Lustran 31 has a nominal melt flow rate of 7.5 grams/10 minutes measured at 230C using a 3.8 kg weight. The examples of the invention show improved toughness in 6.4mm thickness bars compared to all of the other resins.

**Table 5**

Compilation of various properties for certain commercial polymers

Example	Polymer name	Pellet IV (dl/g)	Molded Bar IV (dl/g)	Notched Izod of 3.2mm thick bars at 23°C (J/m)	Notched Izod of 6.4mm thick bars at 23°C (J/m)	Specific Gravity (g/mL)	Tg (°C)	Crystallization Halftime from melt (min)
A	PC	12 MFR	NA	929	108	1.20	146	NA
B	PCTG	0.73	0.696	NB	70	1.23	87	30 at 170°C
C	PCTA	0.72	0.702	98	59	1.20	87	15 at 150°C
D	PETG	0.75	0.692	83	59	1.27	80	2500 at 130°C
E	PET	0.76	0.726	45	48	1.33	78	1.5 at 170°C
F	SAN	7.5 MFR	NA	21	NA	1.07	~110	NA
G	PSU	6.5 MFR	NA	69	NA	1.24	~190	NA

NA = Not available

**Example 6**

[0237] This example illustrates the effect of the amount of 2,2,4,4-tetramethyl-1,3-cyclobutanediol used for the preparation of the polyesters of the invention on the glass transition temperature of the polyesters.

**Example 6A**

[0238] The polyester of this example was prepared by carrying out the ester exchange and polycondensation reactions in separate stages. The ester exchange experiments were conducted in a continuous temperature rise (CTR) reactor. The CTR was a 3000 ml glass reactor equipped with a single shaft impeller blade agitator, covered with an electric heating mantle and fitted with a heated packed reflux condenser column. The reactor was charged with 777g ( 4 moles) of dimethyl terephthalate, 230g (1.6 moles) of 2,2,4,4-tetramethyl-1,3,-cyclobutanediol, 460.8g (3.2 moles) of cyclohexane dimethanol and 1.12g of butyltin tris-2-ethylhexanoate (such that there will be 200ppm tin metal in the final polymer). The heating mantle was set manually to 100 % output. The set points and data collection were facilitated by a Camile process control system. Once the reactants were melted, stirring was initiated and slowly increased to 250 rpm. The temperature of the reactor gradually increased with run time. The weight of methanol collected was recorded via balance. The reaction was stopped when methanol evolution stopped or at a pre-selected lower temperature of 260°C. The oligomer was discharged with a nitrogen purge and cooled to room temperature. The oligomer was frozen with liquid nitrogen and broken into pieces small enough to be weighed into a 500 ml round bottom flask.

[0239] In the polycondensation reaction, a 500 ml round bottom flask was charged with approximately 150 g of the oligomer prepared above. The flask was equipped with a stainless steel stirrer and polymer head. The glassware was set up on a half mole polymer rig and the Camile sequence was initiated. The stirrer was positioned one full turn from the flask bottom once the oligomer melted. The temperature/pressure/stir rate sequence controlled by the Camile software for this example is reported in the following table.



[0240] Camile Sequence for Example 6A

Stage	Time (min)	Temp (°C)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	3	25
7	110	290	3	25

[0241] The resulting polymer was recovered from the flask, chopped using a hydraulic chopper, and ground to a 6 mm screen size. Samples of each ground polymer were submitted for inherent viscosity in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C, catalyst level (Sn) by x-ray fluorescence, and color ( $L^*$ ,  $a^*$ ,  $b^*$ ) by transmission spectroscopy. Polymer composition was obtained by  $^1\text{H}$  NMR. Samples were submitted for thermal stability and melt viscosity testing using a Rheometrics Mechanical Spectrometer (RMS-800).

[0242] The table below shows the experimental data for the polyester of this example. Figure 3 also shows the dependence of  $T_g$  on composition and inherent viscosity. The data shows in general that an increase in the level of 2,2,4,4-tetramethyl-1,3-cyclobutanediol raises the glass transition temperature in an almost linear fashion, for a constant inherent viscosity.

**Table 6**

Glass transition temperature, inherent viscosity, and composition

Example	mol% TMCD	% cis TMCD	IV (dL/g)	$T_g$ (°C)	$\eta_o$ at 260°C (Poise)	$\eta_o$ at 275°C (Poise)	$\eta_o$ at 290°C (Poise)
A	22.7	53	0.69	112	NA	NA	NA

NA = Not available

**Example 7**

[0243] This example illustrates the effect of the amount of 2,2,4,4-tetramethyl-1,3-cyclobutanediol used for the preparation of the polyesters of the invention on the glass transition temperature of the polyesters. Polyesters prepared in this example fall comprise more than 25 to less than 40 mol% of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

[0244] Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were weighed into a 500-ml single neck round bottom flask. NMR analysis on the 2,2,4,4-tetramethyl-1,3-cyclobutanediol starting material showed a cis/trans ratio of 53/47. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200°C and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210°C and these conditions were held for an additional 2 hours. The temperature was raised to 285°C (in approximately 25 minutes) and the pressure was reduced to 0.3 mm of Hg over a period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete, the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295°C during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 32 mol%.

[0245] Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by  $^1\text{H}$  NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20°C/min.

[0246] The table below shows the experimental data for the polyesters of this example. Figure 3 also shows the dependence of  $T_g$  on composition and inherent viscosity. The data shows that an increase in the level of 2,2,4,4-tetramethyl-1,3-cyclobutanediol raises the glass transition temperature in an almost linear fashion, for a constant inherent viscosity.

**Table 7**

Glass transition temperature as a function of inherent viscosity and composition

Example	mol% TMCD	% cis TMCD	IV (dL/g)	$T_g$ (°C)	$\eta_o$ at 260°C (Poise)	$\eta_o$ at 275°C (Poise)	$\eta_o$ at 290°C (Poise)
A	31.6	51.5	0.55	112	5195	2899	2088
B	31.5	50.8	0.62	112	8192	4133	2258
C	30.7	50.7	0.54	111	4345	2434	1154
D	30.3	51.2	0.61	111	7929	4383	2261
E	29.0	51.5	0.67	112	16322	8787	4355

NA = Not available

#### Example 8

[0247] This example illustrates the effect of the amount of 2,2,4,4-tetramethyl-1,3-cyclobutanediol used for the preparation of the polyesters of the invention on the glass transition temperature of the polyesters. Polyesters prepared in this example comprise 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues in an amount of 40 mol% or greater.

#### Examples A to AC

[0248] These polyesters were prepared by carrying out the ester exchange and polycondensation reactions in separate stages. The ester exchange experiments were conducted in a continuous temperature rise (CTR) reactor. The CTR was a 3000 ml glass reactor equipped with a single shaft impeller blade agitator,

covered with an electric heating mantle and fitted with a heated packed reflux condenser column. The reactor was charged with 777g of dimethyl terephthalate, 375g of 2,2,4,4-tetramethyl-1,3-cyclobutanediol, 317g of cyclohexane dimethanol and 1.12g of butyltin tris-2-ethylhexanoate (such that there will be 200ppm tin metal in the final polymer). The heating mantle was set manually to 100 % output. The set points and data collection were facilitated by a Camile process control system. Once the reactants were melted, stirring was initiated and slowly increased to 250 rpm. The temperature of the reactor gradually increased with run time. The weight of methanol collected was recorded via balance. The reaction was stopped when methanol evolution stopped or at a pre-selected lower temperature of 260°C. The oligomer was discharged with a nitrogen purge and cooled to room temperature. The oligomer was frozen with liquid nitrogen and broken into pieces small enough to be weighed into a 500 ml round bottom flask.

[0249] In the polycondensation reactions, a 500 ml round bottom flask was charged with 150 g of the oligomer prepared above. The flask was equipped with a stainless steel stirrer and polymer head. The glassware was set up on a half mole polymer rig and the Camile sequence was initiated. The stirrer was positioned one full turn from the flask bottom once the oligomer melted. The temperature/pressure/stir rate sequence controlled by the Camile software for these examples is reported in the following table, unless otherwise specified below.

**Camile Sequence for Polycondensation Reactions**

Stage	Time (min)	Temp (°C)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	6	25
7	110	290	6	25

[0250] Camile Sequence for Examples A, C, R, Y, AB, AC

Stage	Time (min)	Temp (°C)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	6	25
7	110	290	6	25

[0251] For Examples B, D, F, the same sequence in the preceding table was used, except the time was 80 min in Stage 7. For Examples G and J, the same sequence in the preceding table was used, except the time was 50 min in Stage 7. For Example L, the same sequence in the preceding table was used, except the time was 140 min in Stage 7.

[0252] Camile Sequence for Example E

Stage	Time (min)	Temp (°C)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	300	90	50
6	5	300	7	25
7	110	300	7	25

[0253] For Example I, the same sequence in the preceding table was used, except the vacuum was 8 torr in Stages 6 and 7. For Example O, the same sequence in the preceding table was used, except the vacuum was 6 torr in Stages 6 and 7. For Example P, the same sequence in the preceding table was used, except the vacuum was 4 torr in Stages 6 and 7. For Example Q, the same sequence in the preceding table was used, except the vacuum was 5 torr in Stages 6 and 7.

**[0254]** Camile Sequence for Example H

<b>Stage</b>	<b>Time (min)</b>	<b>Temp (°C)</b>	<b>Vacuum (torr)</b>	<b>Stir (rpm)</b>
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	280	90	50
6	5	280	5	25
7	110	280	5	25

**[0255]** For Example U and AA, the same sequence in the preceding table was used, except the vacuum was 6 torr in Stages 6 and 7. For Example V and X, the same sequence in the preceding table was used, except the vacuum was 6 torr and stir rate was 15 rpm in Stages 6 and 7. For Example Z, the same sequence in the preceding table was used, except the stir rate was 15 rpm in Stages 6 and 7.

**[0256]** Camile Sequence for Example K

<b>Stage</b>	<b>Time (min)</b>	<b>Temp (°C)</b>	<b>Vacuum (torr)</b>	<b>Stir (rpm)</b>
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	300	90	50
6	5	300	6	15
7	110	300	6	15

**[0257]** For Example M, the same sequence in the preceding table was used, except the vacuum was 8 torr in Stages 6 and 7. For Example N, the same sequence in the preceding table was used, except the vacuum was 7 torr in Stages 6 and 7.

[0258] Camile Sequence for Examples S and T

Stage	Time (min)	Temp (°C)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	5	290	6	25
5	110	290	6	25

[0259] The resulting polymers were recovered from the flask, chopped using a hydraulic chopper, and ground to a 6 mm screen size. Samples of each ground polymer were submitted for inherent viscosity in 60/40 (wt/wt) phenol/tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C, catalyst level (Sn) by x-ray fluorescence, and color ( $L^*$ ,  $a^*$ ,  $b^*$ ) by transmission spectroscopy. Polymer composition was obtained by  $^1\text{H}$  NMR. Samples were submitted for thermal stability and melt viscosity testing using a Rheometrics Mechanical Spectrometer (RMS-800).

#### Examples AD to AK and AS

[0260] The polyesters of these examples were prepared as described above for Examples A to AC, except that the target tin amount in the final polymer was 150ppm for examples AD to AK and AS. The following tables describe the temperature/pressure/stir rate sequences controlled by the Camile software for these examples.

[0261] Camile Sequence for Examples AD, AF, and AH

Stage	Time (min)	Temp (°C)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	400	50
5	110	290	400	50
6	5	290	8	50
7	110	295	8	50

[0262] For Example AD, the stirrer was turned to 25 rpm with 95 min left in Stage 7.

[0263] Camile Sequence for Example AE

Stage	Time (min)	Temp (°C)	Vacuum (torr)	Stir (rpm)
1	10	245	760	0
2	5	245	760	50
3	30	283	760	50
4	3	283	175	50
5	5	283	5	50
6	5	283	1.2	50
7	71	285	1.2	50

[0264] For Example AK, the same sequence in the preceding table was used, except the time was 75 min in Stage 7.

[0265] Camile Sequence for Example AG

Stage	Time (min)	Temp (°C)	Vacuum (torr)	Stir (rpm)
1	10	245	760	0
2	5	245	760	50
3	30	285	760	50
4	3	285	175	50
5	5	285	5	50
6	5	285	4	50
7	220	290	4	50

[0266] Camile Sequence for Example AI

Stage	Time (min)	Temp (°C)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	285	90	50
6	5	285	6	50
7	70	290	6	50



[0267] Camile Sequence for Example AJ

Stage	Time (min)	Temp (°C)	Vacuum (torr)	Stir (rpm)
1	5	245	760	0
2	5	245	760	50
3	30	265	760	50
4	3	265	90	50
5	110	290	90	50
6	5	290	6	25
7	110	295	6	25

**Examples AL to AR**

[0268] Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were weighed into a 500-ml single neck round bottom flask. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200°C and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210°C and these conditions were held for an additional 2 hours. The temperature was raised to 285°C (in approximately 25 minutes) and the pressure was reduced to 0.3 mm of Hg over a period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete, the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295°C during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 45 mol%.

[0269] Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by  $^1\text{H}$  NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20°C/min.

[0270] The table below shows the experimental data for the polyesters of this example. The data shows that an increase in the level of 2,2,4,4-tetramethyl-1,3-cyclobutanediol raises the glass transition temperature in an almost linear fashion, for a constant inherent viscosity. Figure 3 also shows the dependence of Tg on composition and inherent viscosity.

**Table 8**

Glass transition temperature as a function of inherent viscosity and composition

Example	mol% TMCD	% cis TMCD	IV (dL/g)	T <sub>g</sub> (°C)	η <sub>o</sub> at 260°C (Poise)	η <sub>o</sub> at 275°C (Poise)	η <sub>o</sub> at 290°C (Poise)
A	43.9	72.1	0.46	131	NA	NA	NA
B	44.2	36.4	0.49	118	NA	NA	NA
C	44	71.7	0.49	128	NA	NA	NA
D	44.3	36.3	0.51	119	NA	NA	NA
E	46.1	46.8	0.51	125	NA	NA	NA
F	43.6	72.1	0.52	128	NA	NA	NA
G	43.6	72.3	0.54	127	NA	NA	NA
H	46.4	46.4	0.54	127	NA	NA	NA
I	45.7	47.1	0.55	125	NA	NA	NA
J	44.4	35.6	0.55	118	NA	NA	NA
K	45.2	46.8	0.56	124	NA	NA	NA
L	43.8	72.2	0.56	129	NA	NA	NA
M	45.8	46.4	0.56	124	NA	NA	NA
N	45.1	47.0	0.57	125	NA	NA	NA
O	45.2	46.8	0.57	124	NA	NA	NA
P	45	46.7	0.57	125	NA	NA	NA
Q	45.1	47.1	0.58	127	NA	NA	NA
R	44.7	35.4	0.59	123	NA	NA	NA
S	46.1	46.4	0.60	127	NA	NA	NA
T	45.7	46.8	0.60	129	NA	NA	NA
U	46	46.3	0.62	128	NA	NA	NA
V	45.9	46.3	0.62	128	NA	NA	NA
X	45.8	46.1	0.63	128	NA	NA	NA
Y	45.6	50.7	0.63	128	NA	NA	NA
Z	46.2	46.8	0.65	129	NA	NA	NA
AA	45.9	46.2	0.66	128	NA	NA	NA
AB	45.2	46.4	0.66	128	NA	NA	NA
AC	45.1	46.5	0.68	129	NA	NA	NA
AD	46.3	52.4	0.52	NA	NA	NA	NA
AE	45.7	50.9	0.54	NA	NA	NA	NA
AF	46.3	52.6	0.56	NA	NA	NA	NA
AG	46	50.6	0.56	NA	NA	NA	NA
AH	46.5	51.8	0.57	NA	NA	NA	NA
AI	45.6	51.2	0.58	NA	NA	NA	NA
AJ	46	51.9	0.58	NA	NA	NA	NA
AK	45.5	51.2	0.59	NA	NA	NA	NA
AL	45.8	50.1	0.624	125	NA	NA	7696
AM	45.7	49.4	0.619	128	NA	NA	7209
AN	46.2	49.3	0.548	124	NA	NA	2348
AP	45.9	49.5	0.72	128	76600	40260	19110
AQ	46.0	50	0.71	131	68310	32480	17817
AR	46.1	49.6	0.383	117	NA	NA	387
AS	47.2	NA	0.48	NA	NA	NA	NA

NA = Not available

**Example 9**

[0271] This example illustrates the effect of the predominance of the type of 2,2,4,4-tetramethyl-1,3-cyclobutanediol isomer (cis or trans) on the glass transition temperature of the polyester.

[0272] Dimethyl terephthalate, 1,4-cyclohexanedimethanol, and 2,2,4,4-tetramethyl-1,3-cyclobutanediol were weighed into a 500-ml single neck round bottom flask. The polyesters of this example were prepared with a 1.2/1 glycol/acid ratio with the entire excess coming from the 2,2,4,4-tetramethyl-1,3-cyclobutanediol. Enough dibutyltin oxide catalyst was added to give 300 ppm tin in the final polymer. The flask was under a 0.2 SCFC nitrogen purge with vacuum reduction capability. The flask was immersed in a Belmont metal bath at 200°C and stirred at 200 RPM after the reactants had melted. After about 2.5 hours, the temperature was raised to 210°C and these conditions were held for an additional 2 hours. The temperature was raised to 285°C (in approximately 25 minutes) and the pressure was reduced to 0.3 mm of Hg over a period of 5 minutes. The stirring was reduced as the viscosity increased, with 15 RPM being the minimum stirring used. The total polymerization time was varied to attain the target inherent viscosities. After the polymerization was complete, the Belmont metal bath was lowered and the polymer was allowed to cool to below its glass transition temperature. After about 30 minutes, the flask was reimmersed in the Belmont metal bath (the temperature had been increased to 295°C during this 30 minute wait) and the polymer mass was heated until it pulled away from the glass flask. The polymer mass was stirred at mid level in the flask until the polymer had cooled. The polymer was removed from the flask and ground to pass a 3 mm screen. Variations to this procedure were made to produce the copolyesters described below with a targeted composition of 45 mol%.

[0273] Inherent viscosities were measured as described in the "Measurement Methods" section above. The compositions of the polyesters were determined by <sup>1</sup>H NMR as explained before in the Measurement Methods section. The glass transition temperatures were determined by DSC, using the second heat after quench at a rate of 20°C/min.

[0274] The table below shows the experimental data for the polyesters of this Example. The data shows that cis 2,2,4,4-tetramethyl-1,3-cyclobutanediol is approximately twice as effective as trans 2,2,4,4-tetramethyl-1,3-cyclobutanediol at increasing the glass transition temperature for a constant inherent viscosity.

**Table 9**

Effect of 2,2,4,4-tetramethyl-1,3-cyclobutanediol cis/trans composition on  $T_g$

Example	mol% TMCD	IV (dL/g)	$T_g$ (°C)	$\eta_o$ at 260°C (Poise)	$\eta_o$ at 275°C (Poise)	$\eta_o$ at 290°C (Poise)	% cis TMCD
A	45.8	0.71	119	N.A.	N.A.	N.A.	4.1
B	43.2	0.72	122	N.A.	N.A.	N.A.	22.0
C	46.8	0.57	119	26306	16941	6601	22.8
D	43.0	0.67	125	55060	36747	14410	23.8
E	43.8	0.72	127	101000	62750	25330	24.5
F	45.9	0.533	119	11474	6864	2806	26.4
G	45.0	0.35	107	N.A.	N.A.	N.A.	27.2
H	41.2	0.38	106	1214	757	N.A.	29.0
I	44.7	0.59	123	N.A.	N.A.	N.A.	35.4
J	44.4	0.55	118	N.A.	N.A.	N.A.	35.6
K	44.3	0.51	119	N.A.	N.A.	N.A.	36.3
L	44.0	0.49	128	N.A.	N.A.	N.A.	71.7
M	43.6	0.52	128	N.A.	N.A.	N.A.	72.1
N	43.6	0.54	127	N.A.	N.A.	N.A.	72.3
O	41.5	0.58	133	15419	10253	4252	88.7
P	43.8	0.57	135	16219	10226	4235	89.6
Q	41.0	0.33	120	521	351	2261	90.4
R	43.0	0.56	134	N.A.	N.A.	N.A.	90.6
S	43.0	0.49	132	7055	4620	2120	90.6
T	43.1	0.55	134	12970	8443	3531	91.2
U	45.9	0.52	137	N.A.	N.A.	N.A.	98.1

NA = not available

### Example 10

[0275] This example illustrates the preparation of a copolyester containing 100 mol% dimethyl terephthalate residues, 55 mol% 1,4-cyclohexanedimethanol residues, and 45 mol% 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

[0276] A mixture of 97.10 g (0.5 mol) dimethyl terephthalate, 52.46 g (0.36 mol) 1,4-cyclohexanedimethanol, 34.07 g (0.24 mol) 2,2,4,4-tetramethyl-1,3-

cyclobutanediol, and 0.0863 g (300 ppm) dibutyl tin oxide was placed in a 500-milliliter flask equipped with an inlet for nitrogen, a metal stirrer, and a short distillation column. The flask was placed in a Wood's metal bath already heated to 200°C. The contents of the flask were heated at 200°C for 1 hour and then the temperature was increased to 210°C. The reaction mixture was held at 210°C for 2 hours and then heated up to 290°C in 30 minutes. Once at 290°C, a vacuum of 0.01 psig was gradually applied over the next 3 to 5 minutes. Full vacuum (0.01 psig) was maintained for a total time of about 45 minutes to remove excess unreacted diols. A high melt viscosity, visually clear and colorless polymer was obtained with a glass transition temperature of 125°C and an inherent viscosity of 0.64 dl/g.

#### **Example 11—Comparative Example**

[0277] This example illustrates that a polyester based on 100% 2,2,4,4-tetramethyl-1,3-cyclobutanediol has a slow crystallization half-time.

[0278] A polyester based solely on terephthalic acid and 2,2,4,4-tetramethyl-1,3-cyclobutanediol was prepared in a method similar to the method described in Example 1A with the properties shown on Table 10. This polyester was made with 300 ppm dibutyl tin oxide. The trans/cis ratio of the 2,2,4,4-tetramethyl-1,3-cyclobutanediol was 65/35.

[0279] Films were pressed from the ground polymer at 320°C. Crystallization half-time measurements from the melt were made at temperatures from 220 to 250°C at 10°C increments and are reported in Table 10. The fastest crystallization half-time for the sample was taken as the minimum value of crystallization half-time as a function of temperature. The fastest crystallization half-time of this polyester is around 1300 minutes. This value contrasts with the fact that the polyester (PCT) based solely on terephthalic acid and 1,4-cyclohexanedimethanol (no comonomer modification) has an extremely short crystallization half-time (<1 min) as shown in Figure 1.

**Table 10**  
Crystallization Half-times (min)

Comonomer (mol %)	IV (dl/g)	T <sub>g</sub> (°C)	T <sub>max</sub> (°C)	at 220°C (min)	at 230°C (min)	at 240°C (min)	at 250°C (min)
100 mol% F	0.63	170.0	330	3291	3066	1303	1888

where: F is 2,2,4,4-Tetramethyl-1,3-cyclobutanediol (65/35 Trans/Cis)

**Example 12—Comparative Example**

[0280] Sheets comprising a polyester that had been prepared with a target composition of 100 mole % terephthalic acid residues, 80 mole % 1,4-cyclohexanedimethanol residues, and 20 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues were produced using a 3.5 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 177 mil and then various sheets were sheared to size. Inherent viscosity and glass transition temperature were measured on one sheet. The sheet inherent viscosity was measured to be 0.69 dl/g. The glass transition temperature of the sheet was measured to be 106°C. Sheets were then conditioned at 50% relative humidity and 60°C for 2 weeks. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example G). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 106°C can be thermoformed under the conditions shown below, as evidenced by these

sheets having at least 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	86	145	501	64	N
B	100	150	500	63	N
C	118	156	672	85	N
D	135	163	736	94	N
E	143	166	760	97	N
F	150	168	740	94	L
G	159	172	787	100	L

**Example 13—Comparative Example**

[0281] Sheets comprising a polyester that had been prepared with a target composition of 100 mole % terephthalic acid residues, 80 mole % 1,4-cyclohexanedimethanol residues, and 20 mole % 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues were produced using a 3.5 inch single screw. A sheet was extruded continuously, gauged to a thickness of 177 mil and then various sheets were sheared to size. Inherent viscosity and glass transition temperature were measured on one sheet. The sheet inherent viscosity was measured to be 0.69 dl/g. The glass transition temperature of the sheet was measured to be 106°C. Sheets were then conditioned at 100% relative humidity and 25°C for 2 weeks. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 60/40/40% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example G). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L),



or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 106°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having at least 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	141	154	394	53	N
B	163	157	606	82	N
C	185	160	702	95	N
D	195	161	698	95	N
E	215	163	699	95	L
F	230	168	705	96	L
G	274	174	737	100	H
H	275	181	726	99	H

**Example 14—Comparative Example**

[0282] Sheets consisting of Kelvx 201 were produced using a 3.5 inch single screw extruder. Kelvx is a blend consisting of 69.85% PCTG (Estar from Eastman Chemical Co. having 100 mole % terephthalic acid residues, 62 mole % 1,4-cyclohexanedimethanol residues, and 38 mole % ethylene glycol residues); 30% PC (bisphenol A polycarbonate); and 0.15% Weston 619 (stabilizer sold by Crompton Corporation). A sheet was extruded continuously, gauged to a thickness of 177 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 100°C. Sheets were then conditioned at 50% relative humidity and 60°C for 2 weeks. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume

divided by the maximum part volume achieved in this set of experiments (Example E). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 100°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having at least 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	90	146	582	75	N
B	101	150	644	83	N
C	111	154	763	98	N
D	126	159	733	95	N
E	126	159	775	100	N
F	141	165	757	98	N
G	148	168	760	98	L

**Example 15—Comparative Example**

[0283] Sheets consisting of Kelvex 201 were produced using a 3.5 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 177 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 100°C. Sheets were then conditioned at 100% relative humidity and 25°C for 2 weeks. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 60/40/40% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example H). The thermoformed part was visually inspected for any blisters and

the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 100°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	110	143	185	25	N
B	145	149	529	70	N
C	170	154	721	95	N
D	175	156	725	96	N
E	185	157	728	96	N
F	206	160	743	98	L
G	253	NR	742	98	H
H	261	166	756	100	H

NR = Not recorded

**Example 16—Comparative Example**

[0284] Sheets consisting of PCTG 25976 (100 mole % terephthalic acid residues, 62 mole % 1,4-cyclohexanedimethanol residues, and 38 mole % ethylene glycol residues) were produced using a 3.5 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 118 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 87°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.17 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as

the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 87°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	102	183	816	100	N
B	92	171	811	99	N
C	77	160	805	99	N
D	68	149	804	99	N
E	55	143	790	97	N
F	57	138	697	85	N

**Example 17—Comparative Example**

[0285] A miscible blend consisting of 20 wt% Teijin L-1250 polycarbonate (a bisphenol-A polycarbonate), 79.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 1.25 inch single screw extruder. Sheets consisting of the blend were then produced using a 3.5 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 118 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 94°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.25 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and

visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 94°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	92	184	844	100	H
B	86	171	838	99	N
C	73	160	834	99	N
D	58	143	787	93	N
E	55	143	665	79	N

**Example 18—Comparative Example**

[0286] A miscible blend consisting of 30 wt% Teijin L-1250 polycarbonate, 69.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 1.25 inch single screw extruder. Sheets consisting of the blend were then produced using a 3.5 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 118 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 99°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.25 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the

thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 99°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	128	194	854	100	H
B	98	182	831	97	L
C	79	160	821	96	N
D	71	149	819	96	N
E	55	145	785	92	N
F	46	143	0	0	NA
G	36	132	0	0	NA

NA = not applicable. A value of zero indicates that the sheet was not formed because it did not pull into the mold (likely because it was too cold).

**Example 19—Comparative Example**

[0287] A miscible blend consisting of 40 wt% Teijin L-1250 polycarbonate, 59.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 1.25 inch single screw extruder. Sheets consisting of the blend were then produced using a 3.5 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 118 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 105°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.265 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as

shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Examples 8A to 8E). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 105°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	111	191	828	100	H
B	104	182	828	100	H
C	99	179	827	100	N
D	97	177	827	100	N
E	78	160	826	100	N
F	68	149	759	92	N
G	65	143	606	73	N

**Example 20—Comparative Example**

[0288] A miscible blend consisting of 50 wt% Teijin L-1250 polycarbonate, 49.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 1.25 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 118 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 111°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.225 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the

table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Examples A to D). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 111°C can be thermoformed under the conditions shown below, as evidenced by the production of sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	118	192	815	100	H
B	99	182	815	100	H
C	97	177	814	100	L
D	87	171	813	100	N
E	80	160	802	98	N
F	64	154	739	91	N
G	60	149	0	0	NA

NA = not applicable. A value of zero indicates that the sheet was not formed because it did not pull into the mold (likely because it was too cold).

**Example 21—Comparative Example**

[0289] A miscible blend consisting of 60 wt% Teijin L-1250 polycarbonate, 39.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 1.25 inch single screw extruder. Sheets consisting of the blend were then produced using a 3.5 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 118 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 117°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.215 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming machine. The thermoforming oven heaters were set to 70/60/60%



output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 117°C cannot be thermoformed under the conditions shown below, as evidenced by the inability to produce sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	114	196	813	100	H
B	100	182	804	99	H
C	99	177	801	98	L
D	92	171	784	96	L
E	82	168	727	89	L
F	87	166	597	73	N

**Example 22—Comparative Example**

[0290] A miscible blend consisting of 65 wt% Teijin L-1250 polycarbonate, 34.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 1.25 inch single screw extruder. Sheets consisting of the blend were then produced using a 3.5 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 118 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 120°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.23 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown

thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 120°C cannot be thermoformed under the conditions shown below, as evidenced by the inability to produce sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	120	197	825	100	H
B	101	177	820	99	H
C	95	174	781	95	L
D	85	171	727	88	L
E	83	166	558	68	L

**Example 23—Comparative Example**

[0291] A miscible blend consisting of 70 wt% Teijin L-1250 polycarbonate, 29.85 wt% PCTG 25976, and 0.15 wt% Weston 619 was produced using a 1.25 inch single screw extruder. Sheets consisting of the blend were then produced using a 3.5 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 118 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 123°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.205 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown

thermoforming machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw, and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Examples A and B). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 123°C cannot be thermoformed under the conditions shown below, as evidenced by the inability to produce sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	126	198	826	100	H
B	111	188	822	100	H
C	97	177	787	95	L
D	74	166	161	19	L
E	58	154	0	0	NA
F	48	149	0	0	NA

NA = not applicable. A value of zero indicates that the sheet was not formed because it did not pull into the mold (likely because it was too cold).

#### **Example 24—Comparative Example**

[0292] Sheets consisting of Teijin L-1250 polycarbonate were produced using a 3.5 inch single screw extruder. A sheet was extruded continuously, gauged to a thickness of 118 mil and then various sheets were sheared to size. The glass transition temperature was measured on one sheet and was 149°C. Sheets were then conditioned at 50% relative humidity and 60°C for 4 weeks. The moisture level was measured to be 0.16 wt%. Sheets were subsequently thermoformed into a female mold having a draw ratio of 2.5:1 using a Brown thermoforming

machine. The thermoforming oven heaters were set to 70/60/60% output using top heat only. Sheets were left in the oven for various amounts of time in order to determine the effect of sheet temperature on the part quality as shown in the table below. Part quality was determined by measuring the volume of the thermoformed part, calculating the draw and visually inspecting the thermoformed part. The draw was calculated as the part volume divided by the maximum part volume achieved in this set of experiments (Example A). The thermoformed part was visually inspected for any blisters and the degree of blistering rated as none (N), low (L), or high (H). The results below demonstrate that these thermoplastic sheets with a glass transition temperature of 149°C cannot be thermoformed under the conditions shown below, as evidenced by the inability to produce sheets having greater than 95% draw and no blistering, without predrying the sheets prior to thermoforming.

Example	Thermoforming Conditions		Part Quality		
	Heat Time (s)	Sheet Temperature (°C)	Part Volume (mL)	Draw (%)	Blisters (N, L, H)
A	152	216	820	100	H
B	123	193	805	98	H
C	113	191	179	22	H
D	106	188	0	0	H
E	95	182	0	0	NA
F	90	171	0	0	NA

NA = not applicable. A value of zero indicates that the sheet was not formed because it did not pull into the mold (likely because it was too cold).

[0293] It can be clearly seen from a comparison of the data in the above relevant working examples that the polyesters of the present invention offer a definite advantage over the commercially available polyesters with regard to glass transition temperature, density, slow crystallization rate, melt viscosity, and toughness.

[0294] The invention has been described in detail with reference to the embodiments disclosed herein, but it will be understood that variations and modifications can be effected within the spirit and scope of the invention.

**CLAIMS**

We claim:

1. A polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 1 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

2. A polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 85 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
  - ii) less than 15 to 1 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
  - iii) optionally less than 14 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

3. A polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 81 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) less than 19 to 2 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and

wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

4. A polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) greater than 85 to 98 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues;
  - ii) less than 15 to 2 mole % of ethylene glycol residues comprising 2 to 16 carbon atoms; and
  - iii) optionally less than 13 mole % of 1,4-cyclohexanedimethanol residues,

wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg from 135 to 200°C.

5. A polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and

- iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 80 to 99 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 20 to 1 mole % of 1,4-cyclohexanedimethanol residues,wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.

6. A polyester composition comprising at least one polyester which comprises:

- (a) a dicarboxylic acid component comprising:
  - i) 70 to 100 mole % of terephthalic acid residues;
  - ii) 0 to 30 mole % of aromatic dicarboxylic acid residues having up to 20 carbon atoms; and
  - iii) 0 to 10 mole % of aliphatic dicarboxylic acid residues having up to 16 carbon atoms; and
- (b) a glycol component comprising:
  - i) 80 to less than 100 mole % of 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues; and
  - ii) 20 to greater than 0 mole % of modifying glycol residues comprising 2 to 16 carbon atoms,wherein the total mole % of the dicarboxylic acid component is 100 mole %, and the total mole % of the glycol component is 100 mole %; and wherein the inherent viscosity of said polyester is from 0.10 to 1.2 dL/g as determined in 60/40 (wt/wt) phenol/ tetrachloroethane at a concentration of 0.5 g/100 ml at 25°C; and wherein said polyester has a Tg greater than 148 to 200°C.



7. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.10 to 0.75
8. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.10 to less than 0.75.
9. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.10 to 0.68.
10. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.10 to less than 0.68.
11. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.10 to 0.6.
12. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.10 to 0.5.
13. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.10 to 0.4.
14. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.20 to 0.75.
15. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.20 to less than 0.75.
16. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.20 to 0.68.

17. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.20 to less than 0.68.
18. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.20 to 0.6.
19. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.20 to 0.5.
20. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.20 to 0.4.
21. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.30 to 0.75
22. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.30 to less than 0.75.
23. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.30 to 0.68.
24. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.30 to less than 0.68.
25. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.30 to 0.6.
26. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.30 to 0.5.

27. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.30 to 0.4.

28. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.05 to less than 0.31.

29. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.10 to less than 0.31.

30. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.15 to less than 0.31.

31. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.20 to less than 0.31.

32. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.25 to less than 0.31.

33. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.05 to 0.30.

34. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.05 to 0.25.

35. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.05 to 0.20.

36. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.05 to 0.15.

37. The polyester according to any of Claims 1 to 6, wherein the inherent viscosity ranges from 0.05 to 0.10.
38. The polyester according to any of Claims 1 to 4, wherein the Tg ranges from 140 to 200°C.
39. The polyester according to any of Claims 1 to 4, wherein the Tg ranges from 145 to 200°C.
40. The polyester according to any of Claims 1 to 6, wherein the Tg ranges from 150 to 200°C.
41. The polyester according to any of Claims 1 to 6, wherein the Tg ranges from 160 to 200°C.
42. The polyester according to any of Claims 1 to 6, wherein the Tg ranges from 170 to 200°C.
43. The polyester according to any of Claims 1 to 6, wherein the Tg ranges from 180 to 200°C.
44. The polyester according to any of Claims 1 to 6, wherein the Tg ranges from 190 to 200°C.
45. The composition of any of Claims 1 to 6, wherein the dicarboxylic acid component comprises 80 to 100 mole % of terephthalic acid residues.
46. The composition of any of Claims 1 to 6, wherein the dicarboxylic acid component comprises 90 to 100 mole % of terephthalic acid residues.

47. The composition of any of Claims 1 to 6, wherein the dicarboxylic acid component comprises 95 to 100 mole % of terephthalic acid residues.
48. The composition of any of Claims 1 to 6, wherein said polyester comprises 1,3-propanediol residues, 1,4-butanediol residues, or mixtures thereof.
49. The composition of any of Claims 1 to 6, wherein said 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues is a mixture comprising greater than 50 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues and less than 50 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.
50. The composition of any of Claims 1 to 6, wherein said 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues is a mixture comprising greater than 55 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues and less than 45 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.
51. The composition of any of Claims 1 to 6, wherein said 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues is a mixture comprising from 30 to 70 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues and from 30 to 70 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

52. The composition of any of Claims 1 to 6, wherein said 2,2,4,4-tetramethyl-1,3-cyclobutanediol residues is a mixture comprising from 40 to 60 mole % of cis-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues and from 40 to 60 mole % of trans-2,2,4,4-tetramethyl-1,3-cyclobutanediol residues.

53. The composition of any of Claims 1 to 6, wherein said polyester composition comprises at least one polymer chosen from at least one of the following: nylons; polyesters other than in Claim 1; polyamides; polystyrene; polystyrene copolymers; styrene acrylonitrile copolymers; acrylonitrile butadiene styrene copolymers; poly(methylmethacrylate); acrylic copolymers; poly(ether-imides); polyphenylene oxides, such as poly(2,6-dimethylphenylene oxide); or poly(phenylene oxide)/polystyrene blends; polyphenylene sulfides; polyphenylene sulfide/sulfones; poly(ester-carbonates); polycarbonates; polysulfones; polysulfone ethers; and poly(ether-ketones) of aromatic dihydroxy compounds; or mixtures thereof.

54. The composition of any of Claims 1 to 6, wherein said polyester composition comprises at least one polycarbonate.

55. The composition of any of Claims 1 to 6, wherein said polyester comprises residues of at least one branching agent for the polyester.

56. The composition of any of Claims 1 to 6, wherein said polyester comprises residues of at least one branching agent in an amount of 0.01 to 10 weight % based on the total weight of the polyester.

57. The composition of any of Claims 1 to 6, wherein the melt viscosity of said polyester is less than 30,000 poise as measured at 1 radian/second on a rotary melt rheometer at 290°C.

58. The composition of any of Claims 1 to 6, wherein said polyester has a crystallization half-time of greater than 5 minutes at 170°C.

59. The composition of any of Claims 1 to 6, wherein said polyester has a crystallization half-time of greater than 1,000 minutes at 170°C.

60. The composition of any of Claims 1 to 6, wherein said polyester has a crystallization half-time of greater than 10,000 minutes at 170°C.

61. The composition of any of Claims 1 to 6, wherein said polyester composition has a density of less than 1.2 g/ml at 23°C.

62. The composition of any of Claims 1 to 6, wherein said polyester composition comprises at least one thermal stabilizer or reaction products thereof.

63. The composition of any of Claims 1 to 6, wherein the yellowness index of said polyester according to ASTM D-1925 is less than 50.



64. The composition of any of Claims 1 to 6, wherein said polyester has a notched Izod impact strength of at least 3 ft-lbs/in at 23°C according to ASTM D256 with a 10-mil notch in a 1/8-inch thick bar.
65. The composition of any of Claims 1 to 6, wherein said polyester has a notched Izod impact strength of at least 10 ft-lbs/in at 23°C according to ASTM D256 with a 10-mil notch in a 1/8-inch thick bar.
66. The composition of any of Claims 1 to 6, wherein the polyester comprises the residue of at least one catalyst comprising a tin compound or reaction products thereof.
67. The polyester composition of Claim 1, wherein the polyester is amorphous.
68. An article of manufacture comprising the polyester composition of Claim 1.
69. A film or sheet comprising a polyester composition according to Claim 1.
70. A liquid crystal display film comprising a polyester composition according to Claim 1.
71. A liquid crystal display film according to Claim 70 comprising a diffuser sheet.
72. A liquid crystal display film according to Claim 70 comprising a compensation film.





73. A liquid crystal display film according to Claim 70 comprising a protective film.
74. The article of Claim 70 wherein the article of manufacture is formed by extrusion blow molding.
75. The article of Claim 70 wherein the article of manufacture is formed by extrusion stretch blow molding.
76. The article of Claim 70 wherein the article of manufacture is formed by injection molding.
77. The article of Claim 70 wherein the article of manufacture is formed by injection stretch blow molding.
78. A film or sheet comprising the polyester composition according to Claim 1.
79. A film or sheet according to Claim 78 wherein said film or sheet was produced by extrusion or calendering.
80. An injection molded article comprising a polyester composition according to Claim 1.
81. A blend comprising:
- (a) at least one polyester of Claim 1 in an amount from 5 to 95 weight %; and
  - (b) at least one polymeric component in an amount from 5 to 95 weight %.
82. A blend of Claim 81, wherein the at least one polymeric component is chosen from at least one of the following: nylons; polyesters other than the

polyester of Claim 1; polyamides; polystyrene; polystyrene copolymers; styrene acrylonitrile copolymers; acrylonitrile butadiene styrene copolymers; poly(methylmethacrylate); acrylic copolymers; poly(ether-imides); polyphenylene oxides, such as poly(2,6-dimethylphenylene oxide); or poly(phenylene oxide)/polystyrene blends; polyphenylene sulfides; polyphenylene sulfide/sulfones; poly(ester-carbonates); polycarbonates; polysulfones; polysulfone ethers; and poly(ether-ketones) of aromatic dihydroxy compounds.


1/3

*Fig. 1*

2/3

*Fig. 2*

3/3

*Fig. 3*

# INTERNATIONAL SEARCH REPORT

International application No  
PCT/US2006/011970

## A. CLASSIFICATION OF SUBJECT MATTER

INV. C08G63/199 C08L67/02 C08J5/18 G02F1/1333

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C08J C08L C08G G02F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 6 011 124 A (SCOTT ET AL) 4 January 2000 (2000-01-04) column 2, line 3 - column 3, line 14; claims; example 2H -----	6
A	US 5 942 585 A (SCOTT ET AL) 24 August 1999 (1999-08-24) column 2, line 11 - column 3, line 6; claims; examples -----	1-82
X	US 5 705 575 A (KELSEY ET AL) 6 January 1998 (1998-01-06) examples 3,4 -----	6
A	US 6 043 322 A (SCOTT ET AL) 28 March 2000 (2000-03-28) example 1E -----	1-82
	-/-	

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

\* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

7 August 2006

Date of mailing of the international search report

16/08/2006

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Masson, P

# INTERNATIONAL SEARCH REPORT

International application No

PCT/US2006/011970

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 1 044 015 A (KODAK LIMITED) 28 September 1966 (1966-09-28) example 8	1-82
A	US 6 096 854 A (MORRIS ET AL) 1 August 2000 (2000-08-01) column 2, line 7 - line 27 column 3, line 1 - line 22 column 6, line 9 - line 14 column 9, line 31 - line 36; examples	1-82
A	US 6 120 889 A (TURNER ET AL) 19 September 2000 (2000-09-19) examples com,6,7	1-82
A	FR 1 278 284 A (KODAK-PATHE) 8 December 1961 (1961-12-08) example 13	1-82
A	US 2002/188092 A1 (MOSKALA ERIC JON ET AL) 12 December 2002 (2002-12-12) the whole document	1-82
A	US 4 379 802 A (WEAVER ET AL) 12 April 1983 (1983-04-12) the whole document	1-82
A	US 4 738 880 A (ASADA ET AL) 19 April 1988 (1988-04-19) the whole document	1-82

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2006/011970

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6011124	A	04-01-2000	NONE	
US 5942585	A	24-08-1999	NONE	
US 5705575	A	06-01-1998	DE 69620292 D1 DE 69620292 T2 EP 0745628 A2 JP 3448158 B2 JP 8333442 A	08-05-2002 21-11-2002 04-12-1996 16-09-2003 17-12-1996
US 6043322	A	28-03-2000	NONE	
GB 1044015	A	28-09-1966	FR 83790 E	09-10-1964
US 6096854	A	01-08-2000	US 5989663 A	23-11-1999
US 6120889	A	19-09-2000	BR 0011264 A CN 1365371 A DE 60013276 D1 DE 60013276 T2 EP 1185575 A1 JP 2003501532 T MX PA01012459 A WO 0075215 A1	02-04-2002 21-08-2002 30-09-2004 13-01-2005 13-03-2002 14-01-2003 04-06-2002 14-12-2000
FR 1278284	A	08-12-1961	NONE	
US 2002188092	A1	12-12-2002	BR 0207418 A CN 1494567 A EP 1392764 A1 JP 2004519539 T MX PA03007495 A TW 592965 B WO 02068513 A1	10-08-2004 05-05-2004 03-03-2004 02-07-2004 04-12-2003 21-06-2004 06-09-2002
US 4379802	A	12-04-1983	NONE	
US 4738880	A	19-04-1988	DE 3673202 D1 EP 0196528 A2 JP 61213147 A	13-09-1990 08-10-1986 22-09-1986