



(86) Date de dépôt PCT/PCT Filing Date: 2005/07/07
(87) Date publication PCT/PCT Publication Date: 2006/02/16
(85) Entrée phase nationale/National Entry: 2007/01/25
(86) N° demande PCT/PCT Application No.: NL 2005/000486
(87) N° publication PCT/PCT Publication No.: 2006/016800
(30) Priorité/Priority: 2004/08/10 (EP04077284.0)

(51) Cl.Int./Int.Cl. *C09D 7/12* (2006.01),
C09C 1/30 (2006.01), *C09C 3/10* (2006.01)
(71) Demandeur/Applicant:
DSM IP ASSETS B.V., NL
(72) Inventeurs/Inventors:
CURRIE, EDWIN PETER KENNEDY, NL;
THIES, JENS CHRISTOPH, NL;
HOLMES, PAUL, NL
(74) Agent: FETHERSTONHAUGH & CO.

(54) Titre : COMPOSITION DE REVETEMENT, REVETEMENT ET UN OBJET REVETU DE LA COMPOSITION DE
REVETEMENT
(54) Title: COATING COMPOSITION, COATING AND AN OBJECT COATED WITH THE COATING COMPOSITION

(57) **Abrégé/Abstract:**

Coating composition comprising particles grafted with reactive groups and hydrophilic polymer chains. The hydrophilic polymer chains dissolves in water at least one temperature between 0 and 100 °C. The reactive group may react with the substrate and or reacts to form a cross-linked coating, comprising the particles. The invention also relates to a coating obtained from the coating composition, an object coated with the coating and the particles.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
16 February 2006 (16.02.2006)

PCT

(10) International Publication Number
WO 2006/016800 A1

(51) International Patent Classification⁷: **C09D 7/12**,
C09C 1/30, 3/10

(74) Agent: **DORRESTIJN, Antoon**; DSM Intellectual Property, P.O. Box 9, NL-6160 MA Geleen (NL).

(21) International Application Number:
PCT/NL2005/000486

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(22) International Filing Date: 7 July 2005 (07.07.2005)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
04077284.0 10 August 2004 (10.08.2004) EP

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **DSM IP ASSETS B.V.** [NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **CURRIE, Edwin, Peter, Kennedy** [NL/NL]; Pastoor Jacobsstraat 11, NL-6133 AM SITTARD (NL). **THIES, Jens, Christoph** [NL/NL]; Heugemer Molenstraat 8, NL-6229 AL Maas-tricht (NL). **HOLMES, Paul** [GB/NL]; Burgemeester Cortenstraat 35, NL-6226 GP Maastricht (NL).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: COATING COMPOSITION, COATING AND AN OBJECT COATED WITH THE COATING COMPOSITION

(57) Abstract: Coating composition comprising particles grafted with reactive groups and hydrophilic polymer chains. The hydrophilic polymer chains dissolves in water at least one temperature between 0 and 100 °C. The reactive group may react with the substrate and or reacts to form a cross-linked coating, comprising the particles. The invention also relates to a coating obtained from the coating composition, an object coated with the coating and the particles.

WO 2006/016800 A1

COATING COMPOSITION, COATING AND AN OBJECT COATED WITH THE
COATING COMPOSITION

5

The invention relates to a coating composition and a coating comprising a hydrophilic polymer, a device coated with the coating composition and particles for use in the coating composition.

Coating compositions comprising hydrophilic polymers are applied on
10 different objects, to give all kind of properties to those objects. It is possible that the coating composition is applied to objects with the purpose to suppress or prevent biofouling. Objects made of synthetic materials in contact with water are generally prone to suffer from undesired accumulation of biologically derived organic species, also referred to as biofouling, be it by example protein adsorption, bacterial adsorption
15 and subsequent spreading, or thrombosis. This undesired accumulation has serious consequences; for example, in the medical area bacterial infections via catheters may be caused by the accumulation and in industry the clogging of filters, accumulation of organic material on surfaces etc also causes problems.

Grafting hydrophilic polymer chains to the surface of the articles
20 made of the synthetic materials has been seen as a manner to decrease or even to prevent biofouling.

It is also possible that that such a coating containing hydrophilic polymers also comprises specific additives, like for example therapeutic species. Also specific functional groups may be adhered to the hydrophilic polymers or otherwise
25 incorporated into the coating, to make the coating for example bioreactive, for example to bind anti-bodies, cell receptors, enzymes etc.

A coating composition and a coating comprising hydrophilic polymer chains is known from S.J. Sophia, et al, Macromolecules 31, 5059 (1998). The coating is obtained by grafting to a surface hydrophilic polymer chains to obtain a coating
30 comprising hydrophilic polymer chains, by using hydrophilic polymer chains with one reactive group that react with reactive groups in the surface. However the thickness of the layer of grafted hydrophilic polymers is limited to only a few molecules. Therefore the layer has insufficient mechanical robustness and is easily damaged, so that anti-biofouling properties are lost. A further disadvantage is that that the processing is
35 laborious, i.e. the chemical grafting of groups often necessitates an extra treatment of

the surface to make the reaction feasible. Yet a further problem is that the anti-biofouling properties are insufficient.

Another method is using Langmuir Blodgett technique to transfer hydrophilic chains to a surface, optionally grafting them afterwards, as described in
5 E.P.K. Currie et al, Applied Chem. 71, 1227 (1999). However this process is time consuming and it is only suitable for batch-wise processes and specific substrates. A further problem is that the anti-biofouling properties are not optimal and again the mechanical robustness of such a coating is insufficient.

Yet another method is to use a cross-linked coating comprising
10 reactive polymers. These can be either linear polymers crosslinked in situ by electron beam, as described in P. Krsko et al, Langmuir 19, 5618 (2003) or starlike polymers which crosslink via e.g. isocyanate groups. This results in hydrogel coatings which have protein repellant properties, are lubricious but lack mechanical robustness.

In DE-10239762 a composition nanoparticles having poly-
15 propyleneglycol sulfogroups on their surface is disclosed. In this case no hydrophilic polymer chains are used, since the water solubility is obtained by the ionic -SO₃Na group and not by the polypropyleneglycol chains, so that the composition is not suitable for anti-fouling applications. Furthermore the particles are very complicated to produce and there are no or only limited possibilities to change the composition of the particles
20 to optimise the composition with respect to its intended use.

Aim of the present invention is to provide a coating composition comprising a hydrophilic polymer, which may be applied to various objects having all kind of functions.

Surprisingly this object is obtained by a coating composition
25 comprising particles being chemically grafted with reactive groups and hydrophilic polymers.

A further advantage of the resulting coating shows good mechanical properties, like hardness and scratch resistance.

Yet a further advantage is that the coating shows good anti-biofouling
30 properties.

Yet another advantage is that the coating shows good anti-fogging properties.

Yet a further advantage is that the coating shows a good adhesion to substrates.

35 Yet a further advantage is that the coating may have good lubricious

properties.

Yet a further advantage is that the coating can be designed to be bioreactive, by grafting specific groups to the surface of the particles, or incorporating them in the network formed by said reactive particles.

5 Yet another advantage of the coating composition is its optical clarity, especially in the dry state.

Particles

The coating composition may comprise all kind of particles, as long
10 as the particles are grafted with the reactive groups and the hydrophilic polymer chains. It is possible that the coating composition comprises organic and/or anorganic particles. Examples of organic particles are carbon nano tubes or carbon nano spheres. Preferably the coating composition comprises anorganic particles, because in this way a very strong coating is obtained. Preferably the average largest diameter of
15 the particles is less than 10 micron, preferably less than 1 micron. Still more preferably the average largest diameter of the particles is less than 100 nm, still more preferably less than 50 nm. This is because this provides a very strong coating, having a smooth surface. It is also possible with particles of these very small diameters to provide a transparent coating.

20 In the case of spherical particles there is only one diameter to consider, so that the diameter is equal to the smallest diameter. For non-spherical particles (for instance but not limited to rods and platelets) the largest diameter is measured as the largest straight line drawn across the particle. Methods for determining the particle dimensions include optical microscopy, scanning microscopy
25 and atomic force microscopy (AFM). If a microscopical method is used the dimensions of 100 randomly chosen particles are measured and the average is calculated. Examples of suitable anorganic particles are particles that comprise SiO₂, TiO₂, ZnO₂, TiO₂, SnO₂, Am-SnO₂, ZrO₂, Sb-SnO₂, Al₂O₃, Au or Ag.

30 *Hydrophilic polymers*

It is possible that the particles are grafted with all kind of hydrophilic polymer chains. A hydrophilic polymer chain is a polymer chain that dissolves in water at at least one temperature between 0 and 100 °C. Preferably a polymer is used that dissolves in water in a temperature range between 20 and 40 °C. Preferably the
35 hydrophilic polymer dissolves for at least 0.1 gram per litre of water, more preferably for

at least 0.5 grams per litre, most preferably for at least 1.0 gram per litre. For determining the solubility in water the polymer chains are taken not comprising the groups for grafting the polymer chains or any other group that is attached to the polymer after the polymerisation, for example an ionic group. Preferably the solubility is
5 determined in water having a pH of between 3 and 10, more preferably in between 5.5 and 9, most preferably having a pH of 7.

The polymer chain may comprise one monomer species (homopolymer), or more species (copolymer) arranged in a random manner or in ordered blocks.

10 Preferably the hydrophilic polymer chains comprise monomer units of ethylenoxide, (meth)acrylic acid, (meth)acrylamide, vinylpyrrolidone, 2-hydroxyethyl(meth)acrylate, phosphorylcholine, glycidyl(meth)acrylate or saccharides.

One of the typical advantages that the coating imparts to the coated object are very good anti-biofouling properties of the coating, resulting from the
15 hydrophilicity of the polymer chain. These properties increase with increasing concentration and length of hydrophilic polymer chain at the surface of the coating.

Preferably the chains of the hydrophilic polymer comprise at least an average of 5 monomeric units, more preferably the polymer comprises at least an average of 7 monomeric units, still more preferably the polymer comprises at least an
20 average of 10 monomeric units, most preferably the polymer comprises at least an average of 15 monomeric units.

The concentration may for example be increased by increasing the density of grafted polymers to the particles, increasing the length, or by increasing the weight ratio of the particles in the coating composition.

25 For obtaining good anti-fogging properties polymer chains having a relatively short length are preferred.

Another advantage of the coating composition is a low static water contact angle. Preferably the static water contact angle is below 50°, more preferably below 40°, still more preferably below 30°.

30

Groups used for grafting

Groups for grafting the hydrophilic polymer chains and compounds comprising the reactive groups to the particles may comprise all groups known in the art for grafting, for instance but not limited to (trialkoxo)silanes, thiols, amines, silane
35 hydrides. Due to the grafting reaction the hydrophilic polymer chains and the

compounds comprising the reactive groups are chemically bounded to the surface of the particles. It is possible that the hydrophilic polymers and the compounds comprising the reactive group comprise more than one group for grafting per molecule. In a more preferred embodiment the hydrophilic polymers and the compounds reactive groups have on average one group for grafting per molecule. In case of the hydrophilic polymer the group for grafting preferably is an endgroup attached to the chain of the hydrophilic polymer.

Reactive groups.

As reactive groups are used that may react with the substrate and/or react to form a cross-linked phase so to form a coating comprising the particles. It is possible that a single species of reactive groups is used, able to mutually react, for example in a homo polymerisation reaction. Examples of such reactive groups include acrylate and methacrylate groups. Another possibility is that a mixture of groups is used, for example groups that are able to react in a copolymerisation reaction. Examples of such groups include carboxylic acids and/or carboxylic anhydrides combined with epoxies, acids combined with hydroxy compounds, especially 2-hydroxyalkylamides, amines combined with isocyanates, for example blocked isocyanate, uretdion or carbodiimide, epoxies combined with amines or with dicyandiamides, hydrazinamides combined with isocyanates, hydroxy compounds combined with isocyanates, for example blocked isocyanate, uretdion or carbodiimide, hydroxy compounds combined with anhydrides, hydroxy compounds combined with (etherified) methylolamide ("amino-resins"), thiols combined with isocyanates, thiols combined with acrylates or other vinylic species (optionally radical initiated), acetoacetate combined with acrylates, and when cationic crosslinking is used epoxy compounds with epoxy or hydroxy compounds. Addition reactions such as 2+2 photo cyclo addition and 4+2 thermal additions are also possible.

It is also possible that reactive groups are attached to the hydrophilic polymer chains, however preferably at least 20 wt.% of the hydrophilic polymer chains do not comprise such a reactive group. More preferably at least 50 wt. %, still more preferably at least 80 wt. % of the hydrophilic polymer chains do not comprise such a reactive group. Most preferably the hydrophilic polymer chains do not comprise any of such reactive groups at all.

Reactive diluents

The coating composition may comprise one or more reactive diluents, defined as a compound that has at least one group capable of reacting mutually and or capable of reacting with the reactive groups grafted to the particles.

In principle a wide variety of compounds are suitable to be used as the reactive diluent, for example monomers or oligomers having the same groups as the reactive groups as defined above. In a preferred embodiment, these reactive diluents are water soluble in the same temperature range as the grafted hydrophilic polymer.

Possible compounds that may be used as the reactive diluent are isocyanates, alkoxy titanates, alkoxy zirconates, or urea-, urea/melamine-, melamine-formaldehyde or phenol-formaldehyde (resol, novolac types), or radical curable (peroxide- or photo-initiated) unsaturated mono- and polyfunctional monomers and polymers, e.g. acrylates, methacrylates, maleate/vinyl ether), or radical curable (peroxide- or photo-initiated) unsaturated e.g. maleic or fumaric, polyesters in styrene and/or in methacrylates.

Method for crosslinking.

Any cross-linking method that may cause the reactive groups to react and so to form the cross-linked phase so that a coating is formed is suitable to be used in the process according to the invention. Suitable ways to initiate crosslinking are for example electron beam radiation, electromagnetic radiation (UV, Visible and Near IR), thermally and by adding moisture, in case moisture curable compounds are used. In a preferred embodiment crosslinking is achieved by UV-radiation. The UV-crosslinking may take place through a free radical mechanism or by a cationic mechanism, or a combination thereof. In another preferred embodiment the crosslinking is achieved thermally. Also combinations of different cure methods are possible.

Initiator

An initiator may be present in the mixture to initiate the crosslinking reaction. The amount of initiator may vary between wide ranges. A suitable amount of initiator is for example between above 0 and 5 wt% with respect to total weight of the compounds that take part in the crosslinking reaction.

When UV-crosslinking is used, the mixture preferably comprises one or more UV-photo-initiators. Any known UV-photo-initiators may be used in the process according to the invention.

Coating thickness

The coating according to the invention can be prepared in any desired thickness. The coatings according to the invention typically have a thickness
5 ranging between 50 nm to tens of micrometers.

Substrates

A wide variety of substrates may be used as a substrate in the process according to the invention. Suitable substrates are for example flat or curved,
10 rigid or flexible substrates including films of for example polycarbonate, polyester, polyvinyl acetate, polyvinyl pyrrolidone, polyvinyl chloride, polyimide, polyethylene naphthalate, polytetrafluoro ethylene, nylon, polynorbornene or amorphous solids, for example glass or crystalline materials, such as for example silicon or gallium arsenide. Metallic substrates such as steel may also be used.

15 A free-standing coating obtainable by a process according to the invention may be obtained by preparing a film or coating on a substrate and subsequently removing the film or coating from the substrate after crosslinking.

Application of the mixture to a substrate

20 The mixture may be applied onto the substrate by any process known in the art of wet coating deposition in one or multiple steps. Examples of suitable processes are spin coating, dip coating, spray coating, flow coating, meniscus coating, capillary coating and roll coating. An object may be totally coated or partially coated with the coating composition. Also partial crosslinking of the coating and removal of the
25 non-crosslinked part is possible, by for instance but not limited to photolithography.

In a first embodiment the mixture according to the invention is applied as the only coating on the substrate. In a second embodiment the coating is applied on top of one or more coatings. Those versed in the art will know which coatings to select to optimise properties such as adhesion, hardness, optical clarity etc.

30 After application and curing of the coating, further processing steps such as but not limited to a heat treatment or radiation treatment is possible.

Solvent

The composition according to the invention may comprise a solvent,
35 for example to prepare a composition according to the invention that is suitable for

application to the substrate using the chosen method of application.

In principle, a wide variety of solvents may be used. The solvent preferably has the ability to form stable suspensions of the particles grafted with the reactive groups and the hydrophilic polymer chains, in order to obtain good quality coatings i.e. after evaporation of the solvent. The particles typically are added to the mixture in the form of a suspension. The same solvent as used in the suspension may be used to adjust the mixture so that it has the desired properties. However, other solvents may also be used.

Preferably the solvent used evaporates after applying the mixture onto the substrate. In the process according to the invention, optionally the mixture may after application to the substrate be heated or treated in vacuum to aid evaporation of the solvent.

Examples of solvent that may be suitable are 1,4-dioxane, acetone, acetonitrile, chloroform, chlorophenol, cyclohexane, cyclohexanone, cyclopentanone, dichloromethane, diethyl acetate, diethyl ketone, dimethyl carbonate, dimethylformamide, dimethylsulphoxide, ethanol, ethyl acetate, m-cresol, mono- and di-alkyl substituted glycols, N,N-dimethylacetamide, p-chlorophenol, 1,2-propanediol, 1-pentanol, 1-propanol, 2-hexanone, 2-methoxyethanol, 2-methyl-2-propanol, 2-octanone, 2-propanol, 3-pentanone, 4-methyl-2-pentanone, hexafluoroisopropanol, methanol, methyl acetate, methyl acetoacetate, methyl ethyl ketone, methyl propyl ketone, n-methylpyrrolidone-2, n-pentyl acetate, phenol, tetrafluoro-n-propanol, tetrafluoroisopropanol, tetrahydrofuran, toluene, xylene and water. Alcohols, ketones and esters based solvents may also be used, although the solubility of acrylates may become an issue with high molecular weight alcohols. Halogenated solvents (such as dichloromethane and chloroform) and hydrocarbons (such as hexanes and cyclohexanes), may also be suitable. Preferably methanol, methyl ethyl ketone or isopropanol are used.

In a more preferred embodiment mixtures of organic solvents with water are used. In the most preferred embodiment water is used as solvent.

Adhesion promoters

Preferably the composition according to the invention comprises a compound that increases the adhesion of the coating to the substrate. These may be for example silane acrylate compounds for usage of acrylate-containing coatings on glass. The skilled artisan will be able to select a suitable adhesion promotor for the

desired substrate.

Additional additives

In a further embodiment the composition according to the invention
5 may contain one or more species that diffuse out of the coating during usage. Such
species may be used for lubricity, adhesional purposes or comprise therapeutic
species. Examples of such species are for instance but not limited to heparin,
vitamines, anti-inflammatory agents, antimicrobial functionalities such as quaternium
ammonium ions, peptide sequences, halogen labile species etc., biomolecule receptor
10 sites.

Post-processing steps, after the composition has been applied to the
substrate may include: addition of migreatable species, for instance drugs, via
reversible sorption, or chemical grafting of bioactive species to remnant reactive groups
in the coating.

15 The invention also relates to a film or coating obtainable from the
coating composition according to the present invention. The invention also relates to
objects partly or in whole coated with the coating composition according to the present
invention.

The invention also relates to particles grafted with reactive groups
20 and hydrophilic polymers as used in the composition according to the invention.

Applications

Applications of the coating include coatings with anti-biofouling or
anti-thrombogenic properties, coatings with anti-inflammatory properties, anti-microbial
25 coatings, coatings to prevent biofilm formation, coatings for bioreceptors, coatings with
anti-fogging properties. It is also possible that the coating is applied to an object to
enhance wetting by aqueous solutions of the object.

The invention also relates to a process for producing the coating
30 composition according to the present invention comprising the step of chemically
grafting a hydrophilic chain to a particle.

With this process various coating compositions may be obtained,
suitable for all kind of applications.

Examples

The invention will be further explained by the examples, without being limited by that.

5 *Materials used in the examples*

A list of the materials used in the examples and their suppliers are reported in Table 1 and the properties of the nano-silicate particle suspension (MT-ST) is listed in Table 2 below.

10 Table 1: Materials used in examples and their supplier.

Material	Supplier
Mono methyl ether polyethylene glycol (Mw 1100 g mol ⁻¹)	Fluka
Mono methyl ether polyethylene glycol (Mw 2000 g mol ⁻¹)	Fluka
Toluene	Merck
Triethoxy(3-isocyanatopropyl)silane	Sigma-Aldrich
Dibutyltin dilaurate	Aldrich
Silicon oxide nano particles in methanol (MT-ST)	Nissan Chemical American Corporation
Acrylpropyltrimethoxysilane (Acr-Pr-TMS)	ABCR Chemicals
Hydroquinone monoethyl ether	Sigma-Aldrich
Trimethyl orthoformate	Sigma-Aldrich
Methanol	Merck
Polyethylene glycol diacrylate (Mw 248 g mol ⁻¹)	Sigma-Aldrich
Irgacure 184	Ciba Chemicals

Table 2: Properties of dispersed silicon oxide nano particles.

Particle suspension	Particle shape	Particle size / nm	SiO ₂ / wt %	H ₂ O / %	Viscosity / mPa.s	Specific gravity	pH	Solvent
MT-ST	Spherical	10-15	30.6	1.7	1.5	0.998	2-4	Methanol

Preparation of mPEG trimethoxysilane polymer chains.

Mono methyl ether polyethylene glycol (mPEG) ($M_w = 1100$ and 2000 g mol^{-1}) was dissolved in toluene and the mixture was dried.

At room temperature and under nitrogen, a molar equivalent with
5 respect to mPEG of triethoxy(3-isocyanatopropyl)silane, was added drop wise to the
reaction mixture. As a catalyst a few drops of dibutyltin dilaurate were added, where
after the reaction mixture was stirred continuously for 24 hours at 50°C . The reaction
was followed by infrared spectroscopy; the isocyanate signal occurs at ca. 2271 cm^{-1} .
Upon completion, approximately two thirds of the toluene was removed by rotary
10 evaporation and the mPEG trimethoxysilane was precipitated into hexane and washed
several times. The resulting solid was dried and characterized by ^1H NMR. Reaction
yields of $> 90 \%$ were obtained.

Preparation of the particles grafted with a hydrophilic polymer chains and reactive
15 groups

Silicon oxide nano particles suspended in methanol (MT-ST) were
grafted with acrylpropyltrimethoxysilane (Acr-Pr-TMS) and one of the mPEG
trimethoxysilane polymers obtained as above, together with hydroquinone monoethyl
ether to inhibit the polymerization of the acrylate groups.

20 For preparing the silicon oxide nano particles, the above mentioned
silane compounds hydroquinone monoethyl ether were stirred together in an excess of
water (with respect to the Acr-Pr-TMS concentration) and heated under reflux for two
hours. Table 3 shows the exact amounts of each chemical used.

Table 3: Compounds in weight percentages used for the preparation of hydrophilic reactive particles.

Material	Modified Silicon oxide nano particle A	Modified Silicon oxide nano particle B	Modified Silicon oxide nano particle C	Modified Silicon oxide nano particle D
MT-ST Silicon oxide nano particles	27.0 wt %	25.65 wt %	26.14 wt %	26.4 wt %
Acr-Pr-TMS	3.75 wt %	3.56 wt %	3.16 wt %	3.91 wt %
mPEG trimethoxysilane (Mw 1100 g mol ⁻¹)	3.81 wt %	7.29 wt %	7.32 wt %	-
mPEG trimethoxysilane (Mw 2000 g mol ⁻¹)	-	-	-	4.09 wt %
Hydroquinone monoethyl ether (inhibit polymerisation)	0.05 wt %	0.05 wt %	0.05 wt %	0.05 wt %
Trimethyl orthoformate (dehydrating agent)	3.07 wt %	4.77 wt %	3.74 wt %	3.79 wt %
Methanol (solvent)	61.67 wt %	58.18 wt %	59.0 wt %	61.0 wt %
Water	0.65 wt %	0.50 wt %	0.59 wt %	0.55 wt %
Total	100 wt %	100 wt %	100 wt %	100 wt %

5 Examples 1-9. Preparation of coated substrates.

Various formulations were prepared by mixing the modified silicon oxide nano particles A – D, according to Table 3 above, with a reactive diluent,

polyethylene glycol diacrylate ($M_w = 248 \text{ g mol}^{-1}$), an adhesion promoter comprising Acr-Pr-TMS, and a photo initiator, Irgacure 184. The exact weights used for the formulations are shown in Tables 4 and 5.

Thin films of various formulations were prepared on glass microscope slides (for measurements of wetting properties, nanoindentation) and on silicon wafers with a 2.5 nm silica oxide layer (for measurements of durability, thickness determination and protein adsorption experiments).

A drop of the formulation (see Tables 4 and 5) was applied to the cleaned substrate and allowed to spin at a rate of 2000 r.p.m. for 20 seconds. The resultant wet spin-coated samples were cross-linked with UV radiation using a D-bulb in an inert environment at a dose of $\sim 2.0 \text{ J/cm}^2$. The coated substrates were then post baked (i.e. heated) by exposure to an IR lamp up to the temperature 120°C and then placed in an oven at 70°C for 12 hours.

15 Measurement of static water contact angle

Static contact angle measurements were measured of coatings according to examples 1-6 using an apparatus comprising a syringe, sample stage and video camera. Images were analysed using Vision Gauge Software (standard edition, version 6.39).

20 Prior to the measurements, calibration of the camera and the surface tension of the water in the syringe were measured. The latter was carried out by dispensing a droplet of water from the syringe, and then recording the image whilst the droplet was still attached to the syringe. The software measured the dimensions of the droplet and used them to calculate the surface tension.

25 The static contact angle of the samples was measured by dispensing a $50 \mu\text{l}$ droplet of distilled water onto the surface of the coated substrate. Ten images of the droplet were taken over a 135 second period. From the images, the software determined the baseline (the surface) and the edges of the droplet; the contact angle was calculated where these lines intercept. After that the average value of the 10
30 images was calculated. The contact angles were determined for at least two droplets deposited different areas of the surface.

Results of the static water contact angle for the coatings formulations on glass substrates according to Examples formulations 1 – 6 are reported in Table 4.

Table 4: Example formulations for coatings prepared on glass substrates and their static water contact angle.

	Example 1	Example 2	Example 3	Example 4	Example 5	Example 6
Material	g	g	g	g	g	g
Modified Silicon oxide nano particle A	3.0	3.0	3.0	-	-	-
Modified Silicon oxide nano particle D	-	-	-	3.0	3.0	3.0
Polyethylene glycol diacrylate Mw 248 g mol ⁻¹	-	0.05	0.1	-	0.1	0.1
Acr-Pr-TMS	0.05	0.05	0.1	0.1	-	0.1
Photo initiator Irgacure 184 (trademark by Ciba)	0.002	0.002	0.002	0.002	0.002	0.002
Water contact angle after 135 s / °	18	12	31	32	27	26

Table 5: Example formulations for coatings prepared on silicon wafer substrates with a 2.5 nm silica oxide layer.

	Example 7	Example 8	Example 9
Material	g	g	g
Modified Silicon oxide nano particle A	0.61	-	-
Modified Silicon oxide nano particle B	-	0.57	-
Modified Silicon oxide nano particle C	-	-	0.52
Acr-Pr-TMS	0.01	0.01	0.01
Methanol	2.79	2.79	2.82
Water	6.50	6.53	6.58
Photo initiator Irgacure 184 100 wt % solution in methanol (trademark by Ciba)	0.02	0.02	0.02

Durability measurements

Coating formulations prepared on the Silicon wafers were deposited in water at room temperature and visually inspected over time. The ranking was performed after 14 days and their appearance is shown in Table 6. It can be seen that
5 coatings retained their integrity after prolonged immersion in water.

Table 6: Appearance of coatings after immersion for 14 days in water.

Example	Appearance
7	Intact
8	Intact
9	Intact

Nanoindentation measurements

10 In order to measure the hardness of the coatings, nanoindentation was performed on several samples in the dry state. The reference materials for such indentations were polycarbonate and a typical UV-curable hard-coat comprising reactive nanoparticles.

The indentations were performed with a Micromaterials 600 using a
15 typical SiN Berkovitch indenter. Indentation were made at 500 nm and 10 measurements were made, which are averaged. The hardness and reduced modulus of the coating are determined via the standard Oliver & Pharr method. In Table 7 these values are given.

It can be seen that the reduced modulus and hardness of the
20 coatings comprising hydrophilic reactive particles are in the same regime as typical values for UV-curable hard-coats and surpass those of thermoplastic polymers.

Table 7: Hardness and Reduced modulus from nanoindentation results on dry coatings at 500 nm depth for Example formulations 3 and 6, reference hard-coat and
25 reference polycarbonate.

Coating	Hardness (GPa)	Reduced modulus (GPa)
Example formulation 3	0.72 +/- 0.02	13.0 +/- 0.5
Example formulation 6	0.49 +/- 0.02	8.0 +/- 0.3
Reference hard-coat	0.60 +/- 0.02	7.0 +/- 0.13
Reference polycarbonate	0.17 +/- 0.02	2.1 +/- 0.42

Protein adsorption measurements

Protein adsorption measurements on the coatings prepared on the silicon wafer were carried out by stagnation point flow reflectometry. The instrument set-up, described by Dijt *et al.* J. Colloids Surf. 51, 141 (1990), consists of a polarized light from a He-Ne laser that is reflected by the coating at the Brewster angle in a hydrodynamically well-defined position (stagnation point) of the incoming fluid. The detector splits the reflected beam into its parallel (p) and perpendicular ($\perp$) components and the ratio $S = I_p / I_{\perp}$ of the respective intensities is measured continuously. Adsorption of material onto the coating interface results in a change, ΔS , and under appropriate conditions (e.g. coating thickness, adsorbed mass) the adsorbed amount, Γ , exhibits a good linear relationship according to:

$$\Gamma = \frac{\Delta S}{S_0} \cdot Q_f \quad [1]$$

where S_0 is the initial ratio prior to adsorption. The constant Q_f is referred to as the quality factor, has units mg m^{-2} , and is dependent on the optical system. This was evaluated using a computer programme where an optical model consisting of a layered matrix is used to describe the system. The programme requires values of the coating refractive index, n , and thickness. These were determined by computer null ellipsometry (Sentech Instruments GmbH) at $\lambda = 632.8 \text{ nm}$ and angle = 70° and the values are reported in Table 8.

A protein solution of lysozyme (Aldrich, Lot 51K7028) (0.156 mg ml^{-1}) in 10 mM sodium nitrate buffer (pH 6.2, 250 ml) was prepared. Lysozyme is a small protein ($M_w = 15 \text{ kDa}$, $pI = 10.9$) that is often used as a model in studies of electrostatic adsorption. Coatings were immersed in the buffer solution prior to the protein adsorption measurements for at least two minutes allowing the coating to equilibrate. All the measurements were carried out using a flow rate of 1.0 ml min^{-1} and the protein sample was allowed to flow following approximately two minutes in the buffer solution flowing in the chamber. Once a plateau had been reached following the introduction of the protein sample, the buffer solution was then allowed to flow. This allows any non-adsorbed proteins to be washed from the coating. The average plateau values of the adsorbed amount of lysozyme protein following the flow of buffer solution, Γ^{pla} , calculated from three separate samples are reported in Table 8 for Examples 7 - 9. For comparison, a silicon wafer not comprising a coating was tested too.

Table 8: Coating thickness, refractive index (determined by ellipsometry), average Γ^{pla} values for films exposed to lysozyme protein solution and then buffer solution for example formulations and a reference silicon wafer with a 75 nm silica oxide layer values.

	Coating thickness / nm	Refractive index, n	Average Γ^{pla} lysozyme protein / mg m ⁻²	Average Γ^{pla} lysozyme protein with flow of buffer solution / mg m ⁻²
Example 7	55.8	1.41	0.90	0.65
Example 8	64.4	1.47	0.44	0.28
Example 9	47.1	1.47	0.10	0
Silicon wafer with a 75 nm silica oxide layer	75	1.47	2.07	1.69

5

It can be seen that the coatings according to Examples 7 – 9 result in a reduction in the amount of adsorbed lysozyme protein when compared with the silicon wafer with a 75 nm oxide layer. It is also interesting to note that a significant amount of protein is desorbed when the buffer solution is allowed to flow into the cell following the protein solution. Moreover, and in agreement with theoretical predications and experimental observations, a decrease in the adsorbed amount of protein is found with increasing the grafting density of mPEG silane on the silicon oxide nano particles.

10

CLAIMS

1. Coating composition comprising particles being grafted with reactive groups and hydrophilic polymer chains.
- 5 2. Coating composition according to claim 1, wherein the particles are anorganic.
3. Coating composition according to claim 1 or 2, wherein the average smallest diameter of the particles is below 10 micron.
4. Coating composition according to any one of claims 1 to 3, wherein the particles comprise SiO₂, TiO₂, ZnO₂, TiO₂, SnO₂, Am-SnO₂, ZrO₂, Sb-SnO₂,
10 Al₂O₃, Au or Ag
5. Coating composition according to any one of claims 1-4, wherein the hydrophilic polymer chain comprise monomer units of ethylenoxide, (meth)acrylic acid, (meth)acrylamide, vinylpyrrolidone, 2-hydroxyethyl(meth)acrylate, phosphorylcholine, glycidyl(meth)acrylate or
15 saccharides.
6. Coating composition according to any one of claims 1- 5, wherein the coating composition comprises a compound that increases the adhesion of the coating to a substrate.
7. Particles used in the coating composition according to any one of claims 1-6.
- 20 8. Coating obtainable from the coating composition according to any one of claims 1-7.
9. Coating according to claim 8, comprising one more species that diffuse out of the coating during usage.
10. Process for producing the coating composition according any one of claims 1-
25 6 comprising the step of chemically grafting a hydrophilic chain to a particle.