

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
6 February 2003 (06.02.2003)

PCT

(10) International Publication Number
WO 03/010206 A1

(51) International Patent Classification⁷: C08B 37/00,
3/14, 11/06, 11/18, 15/06, 15/00, 31/00, 31/04, 31/08,
37/14, 3/22, 7/00, 11/193, 11/20, 13/00

(21) International Application Number: PCT/EP02/07683

(22) International Filing Date: 10 July 2002 (10.07.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
0117767.4 20 July 2001 (20.07.2001) GB

(71) Applicant (for AE, AG, AU, BB, BZ, CA, GB, GD, GH, GM, IL, KE, LC, LK, LS, MN, MW, NZ, OM, SD, SG, SL, TT, TZ, UG, ZA, ZM, ZW, SZ, CY, IE only): UNILEVER PLC [GB/GB]; Unilever House, Blackfriars, London EC4P 4BQ (GB).

(71) Applicant (for AL, AM, AT, AZ, BA, BG, BR, BY, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GE, HR, HU, ID, IS, JP, KG, KP, KR, KZ, LR, LT, LU, LV, MA, MD, MG, MK, MX, MZ, NO, PH, PL, PT, RO, RU, SE, SI, SK, TJ, TM, TN, TR, UA, UZ, VN, YU, BE, FR, GR, IT, MC, NL, BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG only): UNILEVER NV [NL/NL]; Weena 455, NL-3013 AL Rotterdam (NL).

(71) Applicant (for IN only): HINDUSTAN LEVER LIMITED [IN/IN]; Hindustan Lever House, 165/166 Backbay Reclamation, Maharashtra, 400 020 Mumbai (IN).

(72) Inventors; and

(75) Inventors/Applicants (for US only): ROGERS, Susanne, Henning [DE/GB]; Unilever Research Port Sunlight, Quarry Road East, Bebington, Wirral, Merseyside

CH63 3JW (GB). ROYLES, Brodyck, James, Lachlan [GB/GB]; Unilever Research Port Sunlight, Quarry Road East, Bebington, Wirral, Merseyside CH63 3JW (GB). WHITE, Michael, Stephen [GB/GB]; Unilever Research Port Sunlight, Quarry Road East, Bebington, Wirral, Merseyside CH63 3JW (GB).

(74) Agents: FRANSELLA, Mary, Evelyn et al.; Unilever PLC, Patent Department, Colworth House, Sharnbrook, Bedford, Bedfordshire MK44 1LQ (GB).

(81) Designated States (national): AE, AG, AL, AM, AT (utility model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (utility model), DE, DK (utility model), DK, DM, DZ, EC, EE (utility model), EE, ES, FI (utility model), FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK (utility model), SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: POLYMERS AND THEIR SYNTHESIS

(57) Abstract: The invention relates to polysaccharide graft polymers useful for incorporation as benefit agents in laundry detergent and fabric treatment compositions, and their preparation. The invention also relates to substituted polysaccharides useful as macroinitiator intermediates for the preparation of the polysaccharide graft polymers, and the preparation of the macroinitiators. The polysaccharide graft polymers may be used, for example, to impart soil release and/or fabric care benefits to laundry detergent or fabric treatment compositions.



WO 03/010206 A1

POLYMERS AND THEIR SYNTHESISTECHNICAL FIELD

5

The present invention relates to substituted polysaccharides, their synthesis, and graft polysaccharide polymers made therefrom. The graft polymers find utility in laundry cleaning operations and provide soil release, fabric
10 care and other laundry cleaning benefits.

BACKGROUND AND PRIOR ART

15 The grafting of synthetic polymers onto a cellulosic backbone has been the subject of research activities for a long time with the object of producing a polymer that has the beneficial properties of both cellulose and the synthetic polymers. Enormous research and development
20 efforts have occurred over the last 40 years, but no polymer or process has yet been discovered which has proceeded to commercialisation.

The grafting of polymers on a cellulosic backbone proceeds
25 through radical polymerisation wherein an ethylenic monomer is contacted with a soluble or insoluble cellulosic material together with a free radical initiator. The radical thus formed reacts on the cellulosic backbone (usually by proton abstraction), creates radicals on the cellulosic chain,
30 which subsequently react with monomers to form graft chains on the cellulosic backbone. Related techniques use other

- 2 -

sources of radical such as high energy irradiation or oxidising agents such as cerium salt or redox systems such as thiocarbonate-potassium bromate. These methods are well known, see, eg, McDonald, et al. Prog. Polym. Sci. 1984, 10, 5 1; Hebeish et al, "The Chemistry and Technology of cellulosic copolymers", (Springer Verlag, 1981); Samal et al. J Macromol. Sci-Rev.Macromol. Chem. 1986, 26, 81; Waly et al, Polymers & polymer composites 4,1,53,1996; and D. Klenn et al,, Comprehensive Cellulose Chemistry, vol. 2 10 "Functionalization of Cellulose" pp. 17-31 (Wiley-VCH, Weinheim, 1998).

Another strategy involves functionalising the cellulose backbone with a reactive double bond and polymerising in the 15 presence of monomers under conventional free radical polymerisation conditions, see, eg, US 4 758 645 (Nippon Paint). Alternatively, a free radical initiator is covalently linked to the polysaccharide backbone to generate a radical from the backbone to initiate polymerisation and 20 form graft copolymers. For example, in US 4 206 108 (Du Pont), a thiol is covalently bound to a polymeric backbone with pendant hydroxy groups via a urethane linkage; this polymer containing mercapto group is then reacted with ethylenically unsaturated monomers to form the graft 25 copolymer.

Unfortunately, none of these techniques lead to a well-defined material with a controlled macrostructure and microstructure. For instance, none of these techniques leads 30 to a good control of both the number of graft chains per cellulose backbone molecule and molecular weight of the

- 3 -

graft chains. Moreover, side reactions are difficult, if not impossible, to avoid, including the formation of un-grafted polymer, graft chain degradation and/or crosslinking of the grafted chains.

5

In an attempt to solve these problems, pre-formed chains have been chemically grafted onto cellulosic polymers. For instance, in US 4 891 404, polystyrene chains were grown in an anionic polymerisation and capped with, eg, CO₂. These
10 grafts were then attached to mesylated or tosylated cellulose triacetate by nucleophilic displacement. This method is difficult to commercialise because of the stringent conditions required by the method. Moreover, the set of monomers that can be used in this method is
15 restricted to non-polar olefins, thus precluding any application in water media.

Block copolymers based on cellulose esters have been reported. See, eg, Oliveira et al, *Polymer*, 35, 9, 1994;
20 Feger et al, *Polymer Bulletin*, 3,407, 1980; Feger et al, *Ibid*, 6, 321, 1982; U.S. Patent No. 3,386,932; Steinmann, *Polym. Preprint, Am. Chem.Soc. Div. Polym. Chem.* 1970, 11, 285; Kim et al, *J.Polym. Sci. Polym, Lett. Ed.*, 1973, 11, 731; and Kim et al. *J Macromol. Sci., Chem (A)* 1976, 10,
25 671. A major problem with these references is the generation of considerable chain branching, grafting or crosslinking. Mezger et al, *Angew. Makromol Chem.*, 116,13,1983 prepared oligomeric, monohydroxy-terminated cellulose coupled with 4,-4'-diphenyldisocyanate, which was
30 then used as a UV-macro-photo-initiator to prepare triblock copolymers. The reaction is known as the iniferter technique

- 4 -

and uses UV initiation, which limits its applicability to certain processing methods. Furthermore, it is typically applicable to styrenic and methacrylic monomers. Other monomers, such as acrylics, vinyl acetate, acrylamide type
5 monomers, which are in widespread use in waterborne systems, might require another technique.

So-called "living" radical polymerisation techniques are known which can give better defined polymers in terms of
10 molecular structure. Three approaches to preparation of controlled polymers in a "living" radical process have been described (Greszta et al, Macromolecules, 27, 638 (1994)). The first approach involves the situation where growing radicals react reversibly with scavenging radicals to form
15 covalent species. The second approach involves the situation where growing radicals react reversibly with covalent species to produce persistent radicals. The third approach involves the situation where reaction which regenerates the same type of radicals. However, none of
20 these techniques have been successfully applied to polysaccharide substrates.

It has previously been recognised in the art that cellulose based materials adhere to cotton fibres. For example,
25 WO 00/18861A and WO 00/18862A (Unilever) disclose cellulosic compounds having a benefit agent attached, so that the benefit agent will be attached to the fibre. See also WO 99/14925A (Procter & Gamble). However, the ability of polysaccharide, especially cellulose based materials to
30 adhere has not been fully investigated, and a need exists to

- 5 -

find polysaccharide based materials that are of commercial significance.

There is therefore a strong need to develop a process that
5 makes it possible to prepare grafted materials from
polysaccharide polymers, with a predictable number of graft
chains per polysaccharide backbone. These graft chains
should be controlled in length and chemical composition.
Moreover, the method of synthesis should be capable of
10 commercial application. In addition, a need exists to
provide polysaccharide-based polymers which provide benefits
to fibres and surfaces.

15 DEFINITION OF THE INVENTION

The invention is concerned with polysaccharide graft
polymers useful as benefit agents in laundry detergent and
fabric treatment compositions, and their preparation by
20 controlled graft polymerisation from a substituted
polysaccharide intermediate (macroinitiator). The novel
substituted polysaccharide intermediate (macroinitiator)
itself, and its preparation from a polysaccharide, are also
subjects of the invention.

25


For reasons of clarity, it is necessary to define these
inventive concepts in the following order:

- (i) the macroinitiator,
- (ii) preparation of the macroinitiator,
- 30 (iii) the polysaccharide graft polymer,
- (iv) preparation of the polysaccharide graft polymer.

- 6 -

Definition (i): the macroinitiator

A first aspect of the present invention provides a substituted polysaccharide useful as a macroinitiator for preparing graft polysaccharide polymers by controlled graft polymerisation, in which at least one sugar unit of the polysaccharide is substituted by a group of the general formula



10 wherein W represents a group -O- or -NR¹-, where R¹ represents a hydrogen atom or an optionally substituted alkyl group, preferably a hydrogen atom;


p, q and r are each independently 0 or 1;

L represents an optionally substituted alkylene, cycloalkylene, arylene or heteroarylene group;

X and Y each independently represent a group -CH₂-, -CO-, -O-CO-, -CO-O-, -NH-CO-, -CO-NH-, -CH(OH)-CH₂-, -CH₂-CH(OH)-, -CH₂-O-CO-, -CO-O-CH₂-, -CH₂-CO-O-, -O-CO-CH₂-, -O-CO-NH-, -NH-CO-O-, -(CR²R³)_s-CO-, -CO-(CR²R³)_s-, -(CR²R³)_t-O-, -O-(CR²R³)_t-,
 20 -(CR²R³)_u-SO-, -SO-(CR²R³)_u-, -(CR²R³)_v-SO₂-, -SO₂-(CR²R³)_v- or -NH-CO-NH, where s, t, u and v are each independently 0, 1, 2 or 3 and R² and R³ each independently represent a hydrogen atom or an optionally substituted alkyl group, preferably a hydrogen atom; and

25 Z represents a control agent site from which a polymer may propagate during a free radical polymerisation process,

the substituted polysaccharide having the general formula



5

wherein each SU represents a sugar unit in a polysaccharide backbone;

10

a represents the number of unsubstituted sugar units as a percentage of the total number of sugar units and is in the range from 0 to 99.9%, preferably 65 to 99%, more preferably 80 to 99%;

15


b represents the number of substituted sugar units as a percentage of the total number of sugar units and is in the range from 0.1 to 100%, preferably 1 to 35%, more preferably 1 to 20%;

20

m represents the degree of substitution per sugar unit and is from 1 to 3.

Definition (ii): preparation of the macroinitiator .

A second aspect of the present invention provides a process for preparing a substituted polysaccharide (macroinitiator) as defined in the previous paragraph, which process
 5 comprises reacting a polysaccharide with a compound of the general formula




in which p, q, r, X, L, Y and Z are as defined above and Q represents a leaving group.

10 Definition (iii): the polysaccharide graft polymer benefit agent

A third aspect of the present invention provides a graft polysaccharide polymer useful in laundry detergent and fabric treatment compositions, having the general formula:

15



- 9 -

wherein p, q, r, W, X, L and Y are as defined above; each SU represents a sugar unit in a polysaccharide backbone; a represents the number of unsubstituted sugar units as a percentage of the total number of sugar units and is in the range from 0 to 99.9%, preferably 65 to 99%, more preferably 80 to 99%; b represents the number of substituted sugar units as a percentage of the total number of sugar units and is in the range from 0.1 to 100%, preferably 1 to 35%, more preferably 1 to 20%; m represents the degree of substitution per sugar unit and is from 1 to 3; Z¹ represents a group Z as defined above from which a halogen atom has been removed; P represents a polymer chain; Hal² represents a halogen, preferably chlorine or bromine and more preferably a bromine, atom; and k is from 10 to 200, preferably 10 to 100.

Definition (iv): preparation of the polysaccharide graft polymer benefit agent

A fourth aspect of the present invention provides a process for preparing a polysaccharide graft polymer according to the invention, which process comprises polymerising at least one free radically polymerisable monomer from the control agent site of a substituted polysaccharide as defined above in the presence of a transition metal compound and a ligand, and isolating the (co)polymer so formed.

- 10 -

DETAILED DESCRIPTION OF THE INVENTION

Benefits

5 The graft polymers of the present invention provide one or more of the following benefits, according to the compound in question: soil release, anti-redeposition, soil repellancy, colour care especially anti-dye transfer and dye fixation, anti-wrinkling, ease of ironing, fabric rebuild, anti-fibre
10 damage, anti-pilling, anti-colour fading, dimensional stability, good drape and body, waterproofing, fabric softening and/or conditioning, fungicidal properties and insect repellancy.

15 Definitions

The following definitions pertain to chemical structures, molecular segments and substituents:

20 As used herein, the term "compound" includes materials of any molecular weight, be they simple structures which are generally considered to be monomers, dimers, trimers, higher oligomers as well as polymers.

25 The phrase "having the structure" is not intended to be limiting and is used in the same way that the term "comprising" is commonly used. The term "independently selected from the group consisting of" is used herein to indicate that the recited elements, eg, R groups or the
30 like, can be identical or different.

- 11 -

"Optional" or "optionally" means that the subsequently described event or occurrence may or may not occur, and that the description includes instances where said event or circumstance occurs and instances where it does not. For example, the phrase "optionally substituted hydrocarbyl" means that a hydrocarbyl moiety may or may not be substituted and that the description includes both unsubstituted hydrocarbyl and hydrocarbyl where there is substitution.

10

The term "alkyl" as used herein refers to a branched or unbranched saturated hydrocarbon group typically although not necessarily containing 1 to about 24 carbon atoms, such as methyl, ethyl, n-propyl, isopropyl, n-butyl, isobutyl, t-butyl, octyl, decyl, and the like, as well as cycloalkyl groups such as cyclopentyl, cyclohexyl and the like. Generally, although again not necessarily, alkyl groups herein contain 1 to about 12 carbon atoms. More preferably, an alkyl group, sometimes termed a "lower alkyl" group, contains one to six carbon atoms, preferably one to four carbon atoms. "Substituted alkyl" refers to alkyl substituted with one or more substituent groups, and the terms "heteroatom-containing alkyl" and "heteroalkyl" refer to alkyl in which at least one carbon atom is replaced with a heteroatom.

25

The term "alkenyl" as used herein refers to a branched or unbranched hydrocarbon group typically although not necessarily containing 2 to about 24 carbon atoms and at least one double bond, such as ethenyl, n-propenyl, isopropenyl, n-butenyl, isobutenyl, octenyl, decenyl, and

30

- 12 -

the like. Generally, although again not necessarily, alkenyl groups herein contain 2 to about 12 carbon atoms. More preferably, an alkenyl group, sometimes termed a 'lower alkenyl' group, contains two to six carbon atoms, preferably
5 two to four carbon atoms. "Substituted alkenyl" refers to alkenyl substituted with one or more substituent groups, and the terms "heteroatom-containing alkenyl" and "heteroalkenyl" refer to alkenyl in which at least one carbon atom is replaced with a heteroatom.

10

The term "alkynyl" as used herein refers to a branched or unbranched hydrocarbon group typically although not necessarily containing 2 to about 24 carbon atoms and at least one triple bond, such as ethynyl, n-propynyl,
15 isopropynyl, n-butynyl, isobutynyl, octynyl, decynyl, and the like. Generally, although again not necessarily, alkynyl groups herein contain 2 to about 12 carbon atoms. More preferably, an alkynyl group, sometimes termed a "lower alkynyl" group, contains two to six carbon atoms, preferably
20 three or four carbon atoms. "Substituted alkynyl" refers to alkynyl substituted with one or more substituent groups, and the terms "heteroatom-containing alkynyl" and "heteroalkynyl" refer to alkynyl in which at least one carbon atom is replaced with a heteroatom.

25

The term "alkoxy" as used herein intends an alkyl group bound through a single, terminal ether linkage; that is, an "alkoxy" group may be represented as -O-alkyl where alkyl is as defined above. More preferably, an alkoxy group,
30 sometimes termed a "lower alkoxy" group, contains one to six, more preferably one to four, carbon atoms. The term

- 13 -

"aryloxy" is used in a similar fashion, with aryl as defined below.

Similarly, the term "alkyl thio" as used herein intends an
5 alkyl group bound through a single, terminal thioether
linkage; that is, an "alkyl thio" group may be represented
as -S-alkyl where alkyl is as defined above. More
preferably, an alkythio group, sometimes termed a "lower
alkyl thio" group, contains one to six, more preferably one
10 to four, carbon atoms.

The term "aryl" as used herein, and unless otherwise
specified refers to an aromatic substituent containing a
single aromatic ring or multiple aromatic rings that are
15 fused together, linked covalently, or linked to a common
group such as a methylene or ethylene moiety. The common
linking group may also be a carbonyl as in benzophenone, an
oxygen atom as in diphenylether, or a nitrogen atom as in
diphenylamine, Preferred aryl groups contain one aromatic
20 ring or two fused or linked aromatic rings, eg, phenyl,
naphthyl, biphenyl, diphenylether, diphenylamine,
benzophenone, and the like. In particular embodiments, aryl
substituents have 1 to about 200 carbon atoms, typically 1
to about 50 carbon atoms, and preferably 1 to about 20
25 carbon atoms. More preferably, aryl groups contain from 6 to
18, preferably 6 to 16 and especially 4 to 14, carbon atoms.
Phenyl and naphthyl, particularly phenyl, groups are
especially preferred. "Substituted aryl" refers to an aryl
moiety substituted with one or more substituent groups, (eg,
30 tolyl, mesityl and perfluorophenyl) and the terms
"heteroatom-containing aryl" and "heteroaryl" refer to aryl

- 14 -

in which at least one carbon atom is replaced with a heteroatom.

The term "aralkyl" refers to an alkyl group with an aryl
5 substituent, and the term "aralkylene" refers to an alkylene
group with an aryl substituent; the term "alkaryl" refers to
an aryl group that has an alkyl substituent, and the term
"alkarylene" refers to an arylene group with an alkyl
substituent. Preferred aralkyl groups contain from 7 to 16,
10 especially 7 to 10, carbon atoms, a particularly preferred
aralkyl group being a benzyl group.

The terms "halo" and "halogen" are used in the conventional
sense to refer to a chloro, bromo, fluoro or iodo
15 substituent. The terms "haloalkyl," "haloalkenyl" or
"haloalkynyl" (or "halogenated alkyl", "halogenated
alkenyl," or "halogenated alkynyl") refer to an alkyl,
alkenyl or alkynyl group, respectively, in which at least
one of the hydrogen atoms in the group has been replaced
20 with a halogen atom.

The term "heteroatom-containing" as in a
"heteroatom-containing hydrocarbyl group" refers to a
molecule or molecular fragment in which one or more carbon
25 atoms is replaced with an atom other than carbon, eg,
nitrogen, oxygen, sulphur, phosphorus or silicon. Similarly,
the term "heteroalkyl" refers to an alkyl substituent that
is heteroatom-containing, the term "heterocyclic" refers to
a cyclic substituent that is heteroatom-containing, the term
30 "heteroaryl" refers to an aryl substituent that is
heteroatom-containing, and the like. When the term

- 15 -

"heteroatom-containing" appears prior to a list of possible heteroatom-containing groups, it is intended that the term apply to every member of that group. That is, the phrase "heteroatom-containing alkyl, alkenyl and alkynyl" is to be interpreted as "heteroatom-containing alkyl, heteroatom-containing alkenyl and heteroatom-containing alkynyl." Preferably, a heterocyclic group is 3- to 18-membered, particularly a 3- to 14- membered, and especially a 5- to 10- membered ring system containing at least one heteroatom.

"Hydrocarbyl" refers to univalent hydrocarbyl radicals containing 1 to about 30 carbon atoms, preferably 1 to about 24 carbon atoms, most preferably 1 to about 12 carbon atoms, including branched or unbranched, saturated or unsaturated species, such as alkyl groups, alkenyl groups, aryl groups, and the like. The term "lower hydrocarbyl" intends a hydrocarbyl group of one to six carbon atoms, preferably one to four carbon atoms. "Substituted hydrocarbyl" refers to hydrocarbyl substituted with one or more substituent groups, and the term "heteroatom-containing hydrocarbyl" and "heterohydrocarbyl" refer to hydrocarbyl in which at least one carbon atom is replaced with a heteroatom.

By "substituted" as in "substituted hydrocarbyl," "substituted aryl," "substituted alkyl," "substituted alkenyl" and the like, as alluded to in some of the aforementioned definitions, is meant that in the hydrocarbyl, hydrocarbylene, alkyl, alkenyl or other moiety, at least one hydrogen atom bound to a carbon atom is replaced with one or more substituents that are functional

- 16 -

groups such as hydroxyl, alkoxy, thio, phosphino, amino, halo, silyl, and the like. When the term "substituted" appears prior to a list of possible substituted groups, it is intended that the term apply to every member of that group. That is, the phrase "substituted alkyl, alkenyl and alkynyl" is to be interpreted as "substituted alkyl, substituted alkenyl and substituted alkynyl". Similarly, "optionally substituted alkyl, alkenyl and alkynyl" is to be interpreted as "optionally substituted alkyl, optionally substituted alkenyl and optionally substituted alkynyl."

When any of the foregoing substituents are designated as being optionally substituted, the substituent groups which are optionally present may be any one or more of those customarily employed in the development of laundry treatment compounds and/or the modification of such compounds to influence their structure/activity, stability or other property. Specific examples of such substituents include, for example, halogen atoms, nitro, cyano, hydroxyl, cycloalkyl, alkyl, haloalkyl, cycloalkyloxy, alkoxy, haloalkoxy, amino, alkylamino, dialkylamino, formyl, alkoxycarbonyl, carboxyl, alkanoyl, alkylthio, alkylsulphinyl, alkylsulphonyl, alkylsulphonato, carbamoyl and alkylamido groups. When any of the foregoing substituents represents or contains an alkyl substituent group, this may be linear or branched and may contain up to 12, preferably up to 6, and especially up to 4, carbon atoms. A cycloalkyl group may contain from 3 to 8, preferably from 3 to 6, carbon atoms. A halogen atom may be a fluorine, chlorine, bromine or iodine atom and any group

- 17 -

which contains a halo moiety, such as a haloalkyl group, may thus contain any one or more of these halogen atoms.

The term "amino" is used herein to refer to the group $-NZ^1Z^2$ where each of Z^1 and Z^2 is independently selected from the group consisting of hydrido and optionally substituted alkyl, alkenyl, alkynyl, aryl, aralkyl, alkaryl and heterocyclic.

The term "thio" is used herein to refer to the group $-SZ^1$, where Z^1 is selected from the group consisting of hydrido and optionally substituted alkyl, alkenyl, alkynyl, aryl, aralkyl, alkaryl and heterocyclic.

As used herein all reference to the elements and groups of the Periodic Table of the Elements is to the version of the table published by the Handbook of Chemistry and Physics, CRC Press, 1995, which sets forth the new IUPAC system for numbering groups.

20 The polysaccharide before substitution

As used herein, the term "polysaccharides" includes natural polysaccharides, synthetic polysaccharides, polysaccharide derivatives and modified polysaccharides. Suitable polysaccharides for use in preparing the compounds of the present invention include, but are not limited to, gums, arabinans, galactans, seeds and mixtures thereof as well as cellulose and derivatives thereof.

Suitable polysaccharides that are useful in the present invention include polysaccharides with a degree of

- 18 -

polymerisation (DP) over 40, preferably from about 50 to about 100 000, more preferably from about 500 to about 50 000. Constituent saccharides preferably include, but are not limited to, one or more of the following saccharides:

5 isomaltose, isomaltotriose, isomaltotetraose,
isomaltooligosaccharide, fructooligosaccharide,
levooligosaccharides, galactooligosaccharide,
xylooligosaccharide, gentiooligosaccharides, disaccharides,
glucose, fructose, galactose, xylose, mannose, sorbose,
10 arabinose, rhamnose, fucose, maltose, sucrose, lactose,
maltulose, ribose, lyxose, allose, altrose, gulose, idose,
talose, trehalose, nigerose, kojibiose, lactulose,
oligosaccharides, maltooligosaccharides, trisaccharides,
tetrasaccharides, pentasaccharides, hexasaccharides,
15 oligosaccharides from partial hydrolysates of natural
polysaccharide sources and mixtures thereof.

The polysaccharides can be extracted from plants, produced by organisms, such as bacteria, fungi, prokaryotes, eukaryotes, extracted from animal and/or humans. For
20 example, xanthan gum can be produced by *Xanthomonas campestris*, gellan by *Sphingomonas paucimobilis*, xyloglucan can be extracted from tamarind seed.

The polysaccharides can be linear, or branched in a variety of ways, such as 1-2, 1-3, 1-4, 1-6, 2-3 and mixtures
25 thereof. Many naturally occurring polysaccharides have at least some degree of branching, or at any rate, at least some saccharide rings are in the form of pendant side groups on a main polysaccharide backbone.

- 19 -

It is desirable that the polysaccharides of the present invention have a molecular weight in the range of from about 10 000 to about 10 000 000, more preferably from about 50 000 to about 1 000 000, most preferably from about 50 000
5 to about 500 000.

Preferably, the polysaccharide is selected from the group consisting of: tamarind gum (preferably consisting of xyloglucan polymers), guar gum, locust bean gum (preferably consisting of galactomannan polymers), and other industrial
10 gums and polymers, which include, but are not limited to, Tara, Fenugreek, Aloe, Chia, Flaxseed, Psyllium seed, quince seed, xanthan, gellan, welan, rhamsan, dextran, curdlan, pullulan, scleroglucan, schizophyllan, chitin, hydroxyalkyl cellulose, arabinan (preferably from sugar beets), de-
15 branched arabinan (preferably from sugar beets), arabinoxylan (preferably from rye and wheat flour), galactan (preferably from lupin and potatoes), pectic galactan (preferably from potatoes), galactomannan (preferably from carob, and including both low and high viscosities),
20 glucomannan, lichenan (preferably from icelandic moss), mannan (preferably from ivory nuts), pachyman, rhamnogalacturonan, acacia gum, agar, alginates, carrageenan, chitosan, clavan, hyaluronic acid, heparin, inulin, cellodextrins, cellulose, cellulose derivatives and
25 mixtures thereof. These polysaccharides can also be treated (preferably enzymatically) so that the best fractions of the polysaccharides are isolated.

Polysaccharides can be used which have an α - or β -linked backbone. However, more preferred polysaccharides have a β -
30 linked backbone, preferably a β -1,4 linked backbone. It is

- 20 -

preferred that the β -1,4-linked polysaccharide is cellulose;
a cellulose derivative, particularly cellulose sulphate,
cellulose acetate, sulphoethyl cellulose, cyanoethyl
cellulose, methyl cellulose, ethyl cellulose,
5 carboxymethylcellulose, hydroxyethylcellulose or
hydroxypropylcellulose; a xyloglucan, particularly one
derived from Tamarind seed gum; a glucomannan,
particularly Konjac glucomannan; a galactomannan,
particularly Locust Bean gum and Guar gum; a side chain
10 branched galactomannan, particularly Xanthan gum; chitosan
or a chitosan salt. Other β -1,4-linked polysaccharides
having an affinity for cellulose, such as mannan, are also
preferred.

The natural polysaccharides can be modified with amines
15 (primary, secondary, tertiary), amides, esters, ethers,
urethanes, alcohols, carboxylic acids, tosylates,
sulphonates, sulphates, nitrates, phosphates and mixtures
thereof. Such a modification can take place in position 2,
3 and/or 6 of the saccharide unit. Such modified or
20 derivatised polysaccharides can be included in the
compositions of the present invention in addition to the
natural polysaccharides.

Nonlimiting examples of such modified polysaccharides
include: carboxyl and hydroxymethyl substitutions (eg
25 glucuronic acid instead of glucose); amino polysaccharides
(amine substitution, eg glucosamine instead of glucose); C₁-
C₆ alkylated polysaccharides; acetylated polysaccharide
ethers; polysaccharides having amino acid residues attached
(small fragments of glycoprotein); polysaccharides
30 containing silicone moieties. Suitable examples of such

- 21 -

modified polysaccharides are commercially available from Carbomer and include, but are not limited to, amino alginates, such as hexanediamine alginate, amine functionalised cellulose-like O-methyl-(N-1,12-
5 dodecanediamine) cellulose, biotin heparin, carboxymethylated dextran, guar polycarboxylic acid, carboxymethylated locust bean gum, carboxymethylated xanthan, chitosan phosphate, chitosan phosphate sulphate, diethylaminoethyl dextran, dodecylamide alginate, sialic
10 acid, glucuronic acid, galacturonic acid, mannuronic acid, guluronic acid, N-acetylglucosamine, N-acetylgalactosamine, and mixtures thereof.

Especially preferred polysaccharides include cellulose, ether, ester and urethane derivatives of cellulose,
15 particularly cellulose monoacetate, xyloglucans and galactomannans, particularly Locust Bean gum.

It is preferred that the polysaccharide has a total number of sugar units from 10 to 7000, although this figure will be dependent on the type of polysaccharide chosen, at least to
20 some extent.

In the case of cellulose and water-soluble modified celluloses, the total number of sugar units is preferably from 50 to 1000, more preferably 50 to 750 and especially 200 to 300. The preferred molecular weight of such
25 polysaccharides is from 10 000 to 150 000.

In the case of cellulose monoacetate, the total number of sugar units is from 10 to 200, preferably 100 to 150. The preferred molecular weight is from 10 000 to 20 000.

- 22 -

In the case of Locust Bean gum, the total number of sugar units is preferably from 50 to 7000. The preferred molecular weight is from 10 000 to 1000 000.


In the case of xyloglucan, the total number of sugar units is preferably from 1000 to 3000. the preferred molecular weight is from 250 000 to 600 000.

The polysaccharide can be linear, like in hydroxyalkyl cellulose, it can have an alternating repeat like in carrageenan, it can have an interrupted repeat like in pectin, it can be a block copolymer like in alginate, it can be branched like in dextran, or it can have a complex repeat like in xanthan. Descriptions of the polysaccharides are given in "An introduction to Polysaccharide Biotechnology", by M. Tombs and S. E. Harding, T.J. Press 1998.

15

The substituted polysaccharide (macroinitiator)

The substituted polysaccharides or macroinitiators according to the first aspect of the invention have a structure in which at least one sugar unit of the polysaccharide is substituted by a group of the general formula



25

in which p, q, r, W, X, L, Y and Z are as defined above.

The group W is derived from the polysaccharide substrate. Thus, W may be -O- in the case of polysaccharides such as cellulose monoacetate or Locust Bean gum or -W- may be -NH-

30

- 23 -

in the case of polysaccharides such as chitosan and its salts. It is particularly preferred that W is -O-.

Preferably, L represents a C₁₋₆ alkylene (particularly C₁₋₄ alkylene and especially methylene) group, a C₃₋₈ (particularly C₃₋₆ and especially C₅ or C₆) cycloalkylene group, a C₆₋₁₄ arylene (particularly C₆₋₁₀ arylene and especially phenylene) group or a 5- to 14- membered heteroarylene (particularly 5- to 10- membered heteroarylene and especially triazine, specifically 1,3,5,-triazine) group, each group being optionally substituted by one or more halogen atoms, C₁₋₄ alkyl or C₁₋₄ groups. More preferably, L, if present, represents a methylene or triazine group, with a methylene group being especially preferred.

15

It is preferred that X and Y each independently represent a group -CH₂-, -CO-, -O-CO-, -CO-O-, -NH-CO-, -CO-NH-, -CH(OH)-CH₂-, -CH₂-CH(OH)-, -CH₂-O-CO-, -CO-O-CH₂-, -CH₂-CO-O-, -O-CO-CH₂-, -O-CO-NH-, -NH-CO-O-, -(CR²R³)_s-CO-, -CO-(CR²R³)_s-, -(CR²R³)_t-O-, -O-(CR²R³)_t-, -(CR²R³)_u-SO-, -SO-(CR²R³)_u-, -(CR²R³)_v-SO₂-, -SO₂-(CR²R³)_v- or -NH-CO-NH, where s, t, u and v are each independently 0, 1, 2 or 3 and R² and R³ each independently represent a hydrogen atom or an optionally substituted alkyl group, preferably a hydrogen atom. If R² and/or R³ represents an optionally substituted alkyl group, this is preferably a C₁₋₆, especially a C₁₋₄, alkyl group optionally substituted by one or more halogen atoms, C₁₋₄ alkyl or C₁₋₄ alkoxy groups. Preferably, X and Y, if present (i.e. p and/or r is 1) independently represent a group -CH₂-, -CO-, -O-CO-, -CO-O-, -NH-CO-, -CO-NH-, -CH(OH)-CH₂-, -CH₂-CH(OH)-, -CH₂-O-CO-, -CO-O-CH₂-, -CH₂-CO-O-

30


- 24 -

, -O-CO-CH₂-, -O-CO-NH-, -NH-CO-O-, -CH₂-CH₂-CO-, -CO-CH₂-CH₂-
 , -(CR²R³)_t-O-, -O-(CR²R³)_t-,
 -CH₂-CH₂-SO-, -SO-CH₂-CH₂-, -CH₂-CH₂-SO₂-, -SO₂-CH₂-CH₂- or -
 NH-CO-NH- where t is 1 or 2 and R² and R³ both represent a
 5 hydrogen atom.

More preferably, X and Y, if present, independently
 represent a group -CH₂-, -CO-, -CO-NH- or -NH-CO-, with the
 groups -CH₂- and -CO- being especially preferred.

10

In one preferred embodiment, Z represents a group of formula



15

in which R⁴ and R⁵ each independently represent an optionally
 substituted alkyl, cycloalkyl or aralkyl group and Hal
 represents a halogen atom.

20

Preferably, R⁴ and R⁵ each independently represent a C₁₋₆
 (especially C₁₋₄) alkyl, C₃₋₈ (especially C₃₋₆) cycloalkyl or
 C₇₋₁₄ (especially C₇₋₁₀) aralkyl (particularly benzyl) group,
 each group being optionally substituted by one or more
 25 halogen atoms, C₁₋₄ alkyl or C₁₋₄ alkoxy groups. More
 preferably, R⁴ and R⁵ independently represent a C₁₋₄ alkyl,
 especially a methyl group.

Hal may represent any halogen atom, that is, a fluorine,
 30 chlorine, bromine or iodine atom. However, it is preferred


- 25 -

that Hal represents a chlorine or bromine, especially a bromine, atom.

In a particularly preferred embodiment, R⁴ and R⁵ both
5 represent a methyl group and Hal represents a bromine atom.

In an alternative preferred embodiment, Z represents a group of formula

10



15 in which w is 0, 1, 2, 3 or 4; R⁶ represents a halogen atom or an optionally substituted alkyl group; and R⁷ represents a hydrogen atom or an optionally substituted alkyl group.

Preferably, R⁶, if present, represents a halogen atom or a
20 C₁₋₆ (especially C₁₋₄) alkyl group optionally substituted by one or more halogen atoms. Preferably, w is 0. R⁷ preferably represents a hydrogen atom or a C₁₋₆ (especially C₁₋₄) alkyl group optionally substituted by one or more halogen atoms. More preferably, R⁷ represents a hydrogen
25 atom.


Hal¹ may represent any halogen atom, that is, a fluorine, chlorine, bromine or iodine atom. However, it is preferred that Hal represents a chlorine or bromine, especially a
30 bromine, atom.

In a particularly preferred embodiment, w is O, R⁷ represents a hydrogen atom and Hal¹ represents a bromine atom.

Substituted polysaccharides in which W represents a group -
 5 O- or -NH-, p, q and r are 0 and Z represents a group
 -CO-C(CH₃)₂-Br are also preferred.


Another preferred group of substituted polysaccharides are
 those in which W represents a group -O- or -NH-, p and q are
 both 0, r is 1, Y represents a group -CH₂- or -CO- and Z
 10 represents a 4-(bromomethyl)phenyl group.

The substituted polysaccharides of the present invention
 have the general formula




in which Su, a, b, k, m, p, q, r, W, X, L, Y and Z are as defined above.


In one preferred embodiment, the substituted polysaccharides have the general formula:




wherein at least one or more -OR groups of the polymer are independently replaced by a group -W-(X)_p-(L)_q-(Y)_r-Z, in
 15 which p, q, r, W, X, L, Y and Z are as defined above and at least one or more R groups are independently selected from groups of formulae:



- 28 -



5



10

wherein each R^8 is independently selected from C_{1-20} (preferably C_{1-6}) alkyl, C_{2-20} (preferably C_{2-6}) alkenyl (eg vinyl) and C_{5-7} aryl (eg phenyl) any of which is optionally substituted by one or more substituents independently selected from C_{1-4} alkyl, C_{1-12} (preferably C_{1-4}) alkoxy, hydroxyl, vinyl and phenyl groups;

each R^9 is independently selected from hydrogen and groups R^8 as hereinbefore defined;

R^{10} is a bond or is selected from C_{1-4} alkylene, C_{2-4} alkenylene and C_{5-7} arylene (eg phenylene) groups, the carbon atoms in any of these being optionally substituted by one or more substituents independently selected from C_{1-12} (preferably C_{1-4}) alkoxy, vinyl, hydroxyl, halo and amine groups;

each R^{11} is independently selected from hydrogen, counter cations such as alkali metal (preferably Na) or $\frac{1}{2}\text{Ca}$ or $\frac{1}{2}\text{Mg}$, and groups R^8 as hereinbefore defined;

30

- 29 -

R¹² is selected from C₁₋₂₀ (preferably C₁₋₆) alkyl, C₂₋₂₀
(preferably C₂₋₆) alkenyl (eg vinyl) and C₅₋₇ aryl (eg
phenyl), any of which is optionally substituted by one or
more substituents independently selected from C₁₋₄ alkyl, C₁₋₁₂
5 (preferably C₁₋₄) alkoxy, hydroxyl, carboxyl, cyano,
sulphonato, vinyl and phenyl groups;

x is from 1 to 3; and

groups R which together with the oxygen atom forming the
linkage to the respective saccharide ring forms an ester or
10 hemi-ester group of a tricarboxylic- or higher
polycarboxylic- or other complex acid such as citric acid,
an amino acid, a synthetic amino acid analogue or a protein;
any remaining R groups being selected from hydrogen and
ether substituents.

15 It is particularly preferred that R¹² is a methyl, ethyl,
phenyl, hydroxyethyl, hydroxypropyl, carboxymethyl,
sulphoethyl or cyanoethyl group.

For the avoidance of doubt, as already mentioned, in formula
20 (II), some of the R groups may optionally have one or more
structures, for example as hereinbefore described. For
example, one or more R groups may simply be hydrogen or an
alkyl group.

25 Preferred groups may for example be independently selected
from one or more of acetate, propanoate, trifluoroacetate,
2-(2-hydroxy-1-oxopropoxy) propanoate, lactate, glycolate,
pyruvate, crotonate, isovalerate cinnamate, formate,

- 30 -

salicylate, carbamate, methylcarbamate, benzoate, gluconate, methanesulphonate, toluene, sulphonate, groups and hemiester groups of fumaric, malonic, itaconic, oxalic, maleic, succinic, tartaric, aspartic, glutamic, and malic acids.

5

Particularly preferred such groups are the monoacetate, hemisuccinate, and 2-(2-hydroxy-1-oxopropoxy)propanoate. The term "monoacetate" is used herein to denote those acetates with the degree of substitution of about 1 or less
10 on a cellulose or other β -1,4 polysaccharide backbone. Thus, "cellulose monoacetate" refers to a molecule that has acetate esters in a degree of substitution of about 1.1 or less, preferably about 1.1 to about 0.5. "Cellulose triacetate" refers to a molecule that has acetate esters in
15 a degree of substitution of about 2.7 to 3.

Cellulose esters of hydroxyacids can be obtained using the acid anhydride in acetic acid solution at 20-30°C and in any case below 50°C. When the product has dissolved the liquid
20 is poured into water (b.p. 316,160). Tri-esters can be converted to secondary products as with the triacetate. Glycollic and lactic ester are most common.

Cellulose glycollate may also be obtained from cellulose
25 chloracetate (as described in GB 320 842) by treating 100 parts with 32 parts of NaOH in alcohol added in small portions.

An alternative method of preparing cellulose esters consists
30 in the partial displacement of the acid radical in a cellulose ester by treatment with another acid of higher

- 31 -

ionisation constant (FR-A-702 116). The ester is heated at about 100°C with the acid which, preferably, should be a solvent for the ester. By this means cellulose acetate-oxalate, tartrate, maleate, pyruvate, salicylate and phenylglycollate have been obtained, and from cellulose tribenzoate a cellulose benzoate-pyruvate. A cellulose acetate-lactate or acetate-glycollate could be made in this way also. As an example cellulose acetate (10 g.) in dioxan (75 ml.) containing oxalic acid (10 g.) is heated at 100°C for 2 hours under reflux.

Multiple esters are prepared by variations of this process. A simple ester of cellulose, eg the acetate, is dissolved in a mixture of two (or three) organic acids, each of which has an ionisation constant greater than that of acetic acid (1.82 x 10⁻⁵). With solid acids suitable solvents such as propionic acid, dioxan and ethylene dichloride are used. If a mixed cellulose ester is treated with an acid this should have an ionisation constant greater than that of either of the acids already in combination.

A cellulose acetate-lactate-pyruvate is prepared from cellulose acetate, 40 per cent. acetyl (100 g.), in a bath of 125 ml. pyruvic acid and 125 ml. of 85 per cent. lactic acid by heating at 100°C for 18 hours. The product is soluble in water and is precipitated and washed with ether-acetone. M.p. 230-250°C.

In the case when solubilising groups are attached to the polysaccharide, this is typically via covalent bonding and, may be pendant upon the backbone or incorporated therein.

- 32 -

The type of solubilising group may alter according to where the group is positioned with respect to the backbone.

The molecular weight of the substituted polysaccharide part
5 may typically be in the range of 1000 to 2 000 000, for
example 10 000 to 1 500 000.

Other substituents

10 As well as the groups of formula $-W-(X)_p-(L)_q-(Y)_r-Z$, pendant
groups of other types may optionally be present, i.e. groups
which do not confer a benefit and/or which do not undergo a
chemical change to enhance substrate affinity. Within that
class of other groups is the sub-class of groups for
15 enhancing the solubility of the material (eg groups which
are, or contain one or more free carboxylic acid/salt and/or
sulphonic acid/salt and/or sulphate groups).


Examples of solubility enhancing substituents include
20 carboxyl, sulphonyl, hydroxyl, (poly)ethyleneoxy- and/or
(poly)propyleneoxy-containing groups, as well as amine
groups.

The other pendant groups preferably comprise from 0% to 65%,
25 more preferably from 0% to 10% of the total number of
pendant groups. The water-solubilising groups could
comprise from 0% to 100% of those other groups but
preferably from 0% to 20%, more preferably from 0% to 10%,
still more preferably from 0% to 5% of the total number of
30 other pendant groups.

- 33 -

Synthesis of the substituted polysaccharide (macroinitiator)

The substituted polysaccharides or macroinitiators according to the first aspect of the invention are prepared by a process which comprises reacting a polysaccharide with a compound of the general formula



in which p, q, r, X, L, Y and Z are as defined above and Q represents a leaving group. Preferably, Q is a halogen atom (F, Cl, Br, I) derived from an acid halide or an imidazole derived from the imidazolidine, a urea derived from the O-acylisourea or an acid derived from the anhydride.


The reaction may be carried out as a suspension or solution in a polar solvent or mixture of polar solvents, such as water, alcohol, dimethylformamide (DMF), dimethyl sulfoxide (DMSO), N,N-dimethylacetamide (DMAC) etc. In one preferred embodiment, the polysaccharide is dissolved in an aprotic polar solvent, especially an anhydrous aprotic polar solvent, such as DMSO or DMAC. The reaction suitably takes place at a temperature in the range from 0 to 100°C, preferably 0 to 80°C, more preferably 0 to 65°C.

Preferably, the reaction is carried out over a period of 12 to 24 hours, more preferably, 14 to 18 hours. It is also preferred that the reaction is carried out under an inert atmosphere, preferably a nitrogen atmosphere.

30


The polysaccharide graft polymer benefit agents

The graft polymers according to the third aspect of the invention are polysaccharides in which at least one sugar unit of the polysaccharide has been substituted by a group of the general formula



in which k, m, p, q, r, P, W, X, L, Y and Z¹ and Hal² are as defined above.

Thus, preferred graft polymers have the general formula




in which SU, a, b, k, m, p, q, r, W, X, L, Y, Z¹, P and Hal² are as defined above.

- 35 -

It is preferred that m is from 1 to 2, preferably 1.

The various substituted polysaccharides or macroinitiators of the present invention work for any radically polymerisable monomer, especially an alkene monomer, including (meth)acrylates, styrenes and dienes. They also provide various controlled copolymers, including block, random, star, gradient, graft or "comb", hyperbranched and dendritic (co)polymers. (In the present application, "(co)polymer" refers to a homopolymer, copolymer, or mixture thereof). Preferably, P is a single polymer chain, a random copolymer of two or more monomers or a gradient block copolymer of two or more monomers.

In the present invention, any radically polymerisable alkene can serve as a monomer for polymerisation. However, monomers suitable for polymerisation according to one embodiment of the present invention include those of the formula:



20

wherein R^{13} and R^{14} are independently selected from the group consisting of H, halogen, CN, CF_3 , straight or branched C_{1-20} (preferably C_{1-6} , more preferably C_{1-4}) alkyl, α , β -unsaturated straight or branched C_{2-10} (preferably C_{2-6} , more preferably C_{2-4}) alkenyl or alkynyl, α , β -unsaturated straight or branched C_{2-6} alkenyl (preferably vinyl)

25

- 36 -

substituted (preferably at the α -position) with a halogen (preferably chlorine), C₃-C₈ cycloalkyl, heterocyclyl, C(=T)R¹⁷, C(=T)NR¹⁸R¹⁹ and TC(=T)R²⁰, where T may be NR²⁰ or O (preferably O), R¹⁷ is C₁₋₂₀ alkyl, C₁₋₂₀ alkoxy, aryloxy or
 5 heterocycloxy, R¹⁸ and R¹⁹ are independently H or C₁₋₂₀ alkyl or R¹⁸ and R¹⁹ may be joined together to form an alkylene group of from 2 to 5 carbon atoms, thus forming a 3- to 6-membered ring, and R²⁰ is H, straight or branched C₁₋₂₀ alkyl or aryl; and

10 R¹⁵ and R¹⁶ are independently selected from the group consisting of H, halogen (preferably fluorine or chlorine), C₁₋₆ (preferably C₁) alkyl, and COOR²¹ and CONHR²¹ (where R²¹ is H, an alkali metal, or a C₁₋₆ alkyl group optionally substituted by a hydroxy, amino, C₁₋₆ alkylamino or di(C₁₋₆
 15 alkyl)amino group); or a heterocyclyl group optionally substituted by a C₁₋₆ alkyl or hydroxy C₁₋₆ alkyl group; or

R¹³ and R¹⁵ may be joined to form a group of the formula (CH₂)_{n'} (which may be substituted with from 1 to 2n' halogen atoms
 20 or C₁₋₄ alkyl groups) or C(=O)-T-C(=O), where n' is from 2 to 6 (preferably 3 or 4) and T is as defined above; and at least two of R¹³, R¹⁴, R¹⁵ and R¹⁶ are H or halogen.

In another preferred embodiment, P represents a polymer
 25 chain derived from a monomer selected from the group consisting of sodium methacrylate, t-butylaminoethyl methacrylate, dimethylaminoethyl methacrylate, diethylaminoethyl methacrylate, dimethylaminopropyl methacrylamide, hydroxyethyl methacrylate, hydroxypropyl
 30 methacrylate, hydroxyethylmorpholine methacrylate,

- 37 -

2-methacryloxyethyl glucoside, methoxypolyethyleneglycol methacrylate, glycerol monomethacrylate, 2-(sulphoxy)ethyl methacrylate ammonium salt, 3-sulphopropyl methacrylate potassium salt,

5 [2-(methacryloxy)ethyl]dimethyl(3-sulphopropyl)-ammonium hydroxide inner salt, 4-vinyl benzoic acid and 4-styrenesulphonic acid sodium salt.

A second monomer can also be used to form copolymeric grafts. This can be any of those listed above. However, in
10 a further preferred embodiment, P represents a polymer chain which is a copolymer derived from a monomer as listed in the previous paragraph and a hydrophobic monomer selected from the group consisting of alkyl methacrylates (eg stearyl methacrylate), perfluoroalkyl methacrylates (eg
15 1H,1H,2H,2H-heptadeca-fluorodecyl methacrylate), and siloxane methacrylates (eg monomethacryloxypropyl terminated polydimethylsiloxane).

Preferably, the grafts have a number average molecular weight of from 1000 to 200 000, more preferably 1000 to
20 100 000.

Preferably, the polysaccharide backbone has a number average molecular weight from 10 000 to 1 000 000.

It is also preferred that the polymer is water soluble at a concentration of at least 0.2 mg/ml.

25

- 38 -

Synthesis of polysaccharide graft polymers

The graft polymers according to the third aspect of the invention can be prepared by a process which forms the fourth aspect of the invention. This process comprises a process for preparing a graft polymer which comprises polymerising at least one free radically polymerisable monomer from the control agent site of a substituted polysaccharide in the presence of a transition metal compound and a ligand, and isolating the (co)polymer so formed.

The transition metal compound may be any transition metal compound which can participate in a redox cycle with the initiator and dormant polymer chain, but which does not form a direct carbon-metal bond with the polymer chain. Preferred transition metal compounds are those of the formula $M^{j+}N_j$, where

M^{j+} may be selected from the group consisting of $Cu^{1+}, Cu^{2+}, Fe^{2+}, Fe^{3+}, Ru^{2+}, Ru^{3+}, Cr^{2+}, Cr^{3+}, Mo^0, Mo^+, Mo^{2+}, Mo^{3+}, W^{2+}, W^{3+}, Rh^{3+}, Rh^{4+}, Co^+, Co^{2+}, Re^{2+}, Re^{3+}, Ni^0, Ni^+, Mn^{3+}, Mn^{4+}, V^{2+}, V^{3+}, Zn^+, Zn^{2+}, Au^+, Au^{2+}, Ag^+$ and Ag^{2+} ;

N is selected from the group consisting of halogen, C_{1-6} alkoxy, $(SO_4)_{1/2}$, $(PO_4)_{1/3}$, $(HPO_4)_{1/2}$, (H_2PO_4) , triflate, hexafluorophosphate, methanesulphonate, arylsulphonate (preferably benzenesulphonate or toluenesulphonate), CN, $R^{22}CO_2$, and SeR^{23} where R^{22} is H or a straight or branched C_{1-6} alkyl (preferably methyl) which may be substituted from


- 39 -

1 to 5 times with a halogen atom (preferably 1 to 3 times with a fluorine or chlorine) and R^{23} is aryl or a straight or branched C_{1-20} (preferably C_{1-10}) alkyl group; ; and

j is the formal charge on the metal (eg, $0 \leq j \leq 7$).

5 Preferably, the transition metal compound is a copper (I) halide, especially copper (I) bromide.

Suitable ligands for use in the present invention include ligands having one or more nitrogen, oxygen, phosphorus
 10 and/or sulphur atoms which can coordinate to the transition metal through a σ -bond, ligands containing two or more carbon atoms which can coordinate to the transition metal through a π -bond, and ligands which can coordinate to the transition metal through a μ -bond or a η -bond. However,
 15 preferred N-, O-, P- and S- containing ligands may have one of the following formulas:



wherein R^{24} and R^{25} are independently selected from the group consisting of H, C_{1-20} alkyl, aryl, heterocyclyl, and C_{1-6} alkyl substituted with C_{1-6} alkoxy, C_{1-4} dialkylamino,
 25 $C(=T)R^{17}$, $C(=T)R^{18}R^{19}$ and $TC(=T)R^{20}$, where T, R^{17} , R^{18} , R^{19} and R^{20} are as defined above; or

- 40 -

R^{24} and R^{25} can be joined to form a saturated, unsaturated or heterocyclic ring as described above for the "heterocyclyl" group;

5 Z is O, S, NR^{27} or PR^{27} , where R^{27} is selected from the same group as R^{24} and R^{25} ,

each R^{26} is independently a divalent group selected from the group consisting of C_{2-4} alkylene (alkanediyl) and C_{2-4}
10 alkenylene where the covalent bonds to each Z are at vicinal positions (eg, in a 1,2-arrangement) or at β -positions e.g., in a 1,3-arrangement), and from C_{3-8} cycloalkanediyl, C_{3-8} cycloalkenediyl, arenediyl and heterocyclylene where the covalent bonds to each Z are at vicinal positions;

15

and h is from 1 to 6.

In addition to the above ligands, each of R^{24} -J and R^{25} -J can form a ring with the R^{26} group to which the J is bound to
20 form a linked or fused heterocyclic ring system (such as is described above for "heterocyclyl"). Alternatively, when R^{24} and/or R^{25} are heterocyclyl, J can be a covalent bond (which may be single or double), CH_2 or a 4- to 7-membered ring fused to R^{24} and/or R^{25} , in addition to the definitions given
25 above for J. Exemplary ring systems for the present ligand include bipyridine, bipyrrrole, 1,10-phenanthroline, a cryptand, a crown ether, etc.


Where Z is PR^{27} , R^{27} can also be C_{1-20} -alkoxy.

30

- 41 -

Also included as suitable ligands in the present invention are CO (carbon monoxide), porphyrins and porphycenes, the latter two of which may be substituted with from 1 to 6 (preferably from 1 to 4) halogen atoms, C₁₋₆ alkyl groups, C₁₋₆ alkoxy groups, C₁₋₆ alkoxy carbonyl, aryl groups, heterocyclyl groups, and C₁₋₆ alkyl groups further substituted with from 1 to 3 halogens.

Further ligands suitable for use in the present invention include compounds of the formula



wherein T and R¹⁷ are as defined above, and each of R²⁸ and R²⁹ is independently selected from the group consisting of H, halogen, C₁₋₂₀ alkyl, aryl and heterocyclyl, and R²⁸ and R²⁹ may be joined to form a C₃₋₈ cycloalkyl ring or a hydrogenated (i.e., reduced, non-aromatic or partially or fully saturated) aromatic or heterocyclic ring (consistent with the definitions of "aryl" and "heterocyclyl" above), any of which (except for H and halogen) may be further substituted with 1 to 5 and preferably 1 to 3 C₁₋₆ alkyl groups, C₁₋₆ alkoxy groups, halogen atoms and/or aryl groups.

Preferably, one of R²⁸ and R²⁹ is H or a negative charge.

Additional suitable ligands include, for example, ethylenediamine and propylenediamine, both of which may be substituted from one to four times on the amino nitrogen atom with a C₁₋₄ alkyl group or a carboxymethyl group; aminoethanol and aminopropanol, both of which may be

- 42 -

substituted from one to three times on the oxygen and/or nitrogen atom with a C₁₋₄ alkyl group; ethylene glycol and propylene glycol, both of which may be substituted one or two times on the oxygen atoms with a C₁₋₄ alkyl group;
5 diglyme, triglyme, tetraglyme, etc.

Suitable carbon-based ligands include arenes (as described above for the "aryl" group) and the cyclopentadienyl ligand. Preferred carbon-based ligands include benzene (which may be
10 substituted with from one to six C₁₋₄ alkyl groups >eg, methyl!) and cyclopentadienyl (which may be substituted with from one to five methyl groups, or which may be linked through an ethylene or propylene chain to a second cyclopentadienyl ligand). Where the cyclopentadienyl ligand
15 is used, it may not be necessary to include a counteranion (N) in the transition metal compound.

Preferred ligands include unsubstituted and substituted pyridines and bipyridines, acetonitrile, (R³⁰O)₃ P,
20 PR³⁰₃, 1,10-phenanthroline, porphyrin, cryptands such as K₂₂₂ and crown ethers such as 18-crown-6. The most preferred ligands are bipyridine and (R³⁰O)₃ P where R³⁰ is C₁₋₂₀ alkyl optionally substituted by one or more halogen (preferably fluorine or chlorine atoms, C₂₋₂₀ alkenyl (preferably vinyl),
25 C₂₋₁₀ alkynyl (preferably acetylenyl), phenyl optionally substituted by one or more halogen or C₁₋₄ alkyl groups or phenyl C₁₋₆ alkyl.

In the present polymerisation, the amounts and relative
30 proportions of initiator, transition metal compound and ligand are those effective to conduct this type of

- 43 -

polymerisation which is known as atom transfer radical
polymerisation (ATRP). Initiator efficiencies with the
present initiator/transition metal compound/ligand system
are generally very good (at least 50%, preferably $\geq 80\%$,
5 more preferably $\geq 90\%$). Accordingly, the amount of initiator
can be selected such that the initiator concentration is
from 10^{-4} M to 1M, preferably 10^{-3} - 10^{-1} M. Alternatively, the
initiator can be present in a molar ratio of from 10^{-4} :1 to
 10^{-1} :1, preferably from 10^{-3} :1 to 5×10^{-2} :1, relative to
10 monomer.

An initiator concentration of 0.1-1M is particularly useful
for preparing end-functional polymers.

15 The molar proportion of transition metal compound relative
to initiator is generally that which is effective to
polymerize the selected monomer(s), but may be from 0.0001:1
to 10:1, preferably from 0.1:1 to 5:1, more preferably from
0.3:1 to 2:1, and most preferably from 0.9:1 to 1.1:1.

20 Conducting the polymerisation in a homogeneous system may
permit reducing the concentration of transition metal and
ligand such that the molar proportion of transition metal
compound to initiator is as low as 0.001:1.

25 Similarly, the molar proportion of ligand relative to
transition metal compound is generally that which is
effective to polymerize the selected monomer(s), but can
depend upon the number of coordination sites on the
transition metal compound which the selected ligand will
30 occupy. (One of ordinary skill understands the number of
coordination sites on a given transition metal compound

- 44 -

which a selected ligand will occupy.) The amount of ligand may be selected such that the ratio of (a) coordination sites on the transition metal compound to (b) coordination sites which the ligand will occupy is from 0.1:1 to 100:1, preferably from 0.2:1 to 10:1, more preferably from 0.5:1 to 3:1, and most preferably from 0.8:1 to 2:1. However, as is also known in the art, it is possible for a solvent or for a monomer to act as a ligand. For the purposes of this application, a monomer is treated as being (a) distinct from and (b) not included within the scope of the ligand.

The present polymerisation may be conducted in the absence of solvent ("bulk" polymerisation). However, when a solvent is used, the reaction can be carried out as a suspension or a solution. Suitable solvents include water, ethers, cyclic ethers, C₅₋₁₀ alkanes, C₅₋₈ cycloalkanes which may be substituted with from 1 to 3 C₁₋₄ alkyl groups, aromatic hydrocarbon solvents, halogenated hydrocarbon solvents, acetonitrile, dimethylformamide, DMSO, DMAC, mixtures of such solvents, and supercritical solvents (such as CO₂, C₁₋₄ alkanes in which any H may be replaced with F, etc.). Aprotic polar solvents are especially preferred. The present polymerisation may also be conducted in accordance with known suspension, emulsion and precipitation polymerisation processes.

Suitable ethers include compounds of the formula R³¹OR³², in which each of R³¹ and R³² is independently an alkyl group of from 1 to 6 carbon atoms which may be further substituted with a C₁₋₄ -alkoxy group. Preferably, when one of R³¹ and R³² is methyl, the other of R³¹ and R³² is alkyl of from 4 to 6

- 45 -

carbon atoms or C₁₋₄ -alkoxyethyl. Examples include diethyl ether, ethyl propyl ether, dipropyl ether, methyl t-butyl ether, di-t-butyl ether, glyme (dimethoxyethane) diglyme (diethylene glycol dimethyl ether), etc.

5

Suitable cyclic ethers include THF and dioxane. Suitable aromatic hydrocarbon solvents include benzene, toluene, o-xylene, m-xylene, p-xylene and any isomer or mixture of isomers of cumene. Suitable halogenated hydrocarbon solvents include CH₂Cl₂, 1,2-dichloroethane and benzene substituted from 1 to 6 times with fluorine and/or chlorine, although one should ensure that the selected halogenated hydrocarbon solvent(s) does not act as an initiator under the reaction conditions.

15

Keys to controlling the polymerisation reaction may include (1) matching the reactivity of the groups in the initiator with the group(s) on the monomer (R¹³-R¹⁶), and (2) matching the energetics of bond breaking and bond forming in dormant species (eg, dormant polymer chains) and transition metal species (as discussed elsewhere in the specification). Matching the reactivities of the initiator with the monomer depends to some degree on the radical stabilizing effects of the substituents. Thus, where the monomer is a simple alkene or halogenated alkene (eg, ethylene, propylene, vinyl chloride, etc.), one may select an alkyl halide initiator. On the other hand, if one wishes to polymerise an arene- or ester-stabilized monomer (eg, a (meth)acrylate, acrylonitrile or styrene), one may select an initiator which is stabilized by a similar group (ie. it contains an aryl, heterocyclyl, alkoxy-carbonyl, CN, carboxyamido group, etc.).

30

- 46 -

Such "matching" of substituents on the initiator and monomer provides a beneficial balance of the relative reactivities of the initiator and monomer.

5 Preferably, the monomer, initiator, transition metal compound and ligand are selected such that the rate of initiation is not less than 1000 times (preferably not less than 100 times) slower than the rate of propagation and/or transfer of the X group to the polymer radical. (In the
10 present application, "propagation" refers to the reaction of a polymer radical with a monomer to form a polymer-monomer adduct radicals.)

The present polymerisation may be conducted in bulk, in the
15 gas phase (eg, by passing the monomer in the gas phase over a bed of the catalyst which has been previously contacted with the initiator and ligand), in a sealed vessel or in an autoclave. Polymerising may be conducted at a temperature of from -78° to 200° , preferably from 0° to 160° and most
20 preferably from 10° to 80° . The reaction should be conducted for a length of time sufficient to convert at least 10% (preferably at least 50%, more preferably at least 75% and most preferably at least 90%) of the monomer to polymer. Typically, the reaction time will be from several minutes to
25 5 days, preferably from 30 minutes to 3 days, and most preferably from 1 to 24 hours. Polymerising may be conducted at a pressure of from 0.1 to 100 atmospheres, preferably from 1 to 50 atmospheres and most preferably from 1 to 10 atmospheres (although the pressure may not be measurable
30 directly if conducted in a sealed vessel).

- 47 -

One may also conduct a "reverse" ATRP, in which the transition metal compound is in its oxidized state, and the polymerisation is initiated by, for example, a radical initiator such as azobis(isobutyronitrile) ("AIBN"), a
5 peroxide such as benzoyl peroxide (BPO) or a peroxy acid such as peroxyacetic acid or peroxybenzoic acid.

After the polymerising step is complete, the formed polymer is isolated. The isolating step of the present process is
10 conducted by known procedures, and may comprise precipitating in a suitable solvent, filtering the precipitated polymer, washing the polymer and drying the polymer.

15 Precipitation can be typically conducted using a suitable C₅₋₈-alkane or C₅₋₈-cycloalkane solvent, such as pentane hexane, heptane, cyclohexane or mineral spirits, or using a C₁₋₆-alcohol, such as methanol, ethanol or isopropanol, or any mixture of suitable solvents. Preferably, the solvent for
20 precipitating is hexane, mixtures of hexanes, or methanol.

The precipitated (co)polymer can be filtered by gravity or by vacuum filtration, in accordance with known methods (eg using a Buchner funnel and an aspirator). The polymer can
25 then be washed with the solvent used to precipitate the polymer, if desired. The steps of precipitating, filtering and washing may be repeated, as desired.

Once isolated, the (co)polymer may be dried by drawing air
30 through the (co)polymer, by vacuum, etc., in accordance with known methods (preferably by vacuum). The present

- 48 -

(co)polymer may be analyzed and/or characterized by size exclusion chromatography, in accordance with known procedures.

5 The (co)polymers of the present invention may have a number average molecular weight of from 1000 to 500 000 g/mol, preferably of from 2000 to 250 000 g/mol, and more preferably of from 3000 to 200 000 g/mol. When produced in bulk, the number average molecular weight may be up to
10 1 000 000 (with the same minimum weights as mentioned above). The number average molecular weight may be determined by size exclusion chromatography (SEC) or, when the initiator has a group which can be easily distinguished from the monomer(s) by NMR spectroscopy

15

Thus, the present invention also encompasses novel block, multi-block, star, gradient, random hyperbranched and dendritic copolymers, as well as graft or "comb" copolymers. Each of the these different types of copolymers will be
20 described hereunder.

Because ATRP is a "living" polymerisation, it can be started and stopped, practically at will. Further, the polymer product retains the functional group "X" necessary to
25 initiate a further polymerisation. Thus, in one embodiment, once the first monomer is consumed in the initial polymerising step, a second monomer can then be added to form a second block on the growing polymer chain in a second polymerising step. Additional polymerisations with the same
30 or different monomer(s) can be performed to prepare multi-block copolymers.

- 49 -

Furthermore, since ATRP is a radical polymerisation, blocks can be prepared in essentially any order. One is not necessarily limited to preparing block copolymers where the sequential polymerising steps must flow from the least
5 stabilized polymer intermediate to the most stabilized polymer intermediate, such as is necessary in ionic polymerisation. (However, as is described throughout the application, certain advantageous reaction design choices will become apparent. However, one is not limited to those
10 advantageous reaction design choices in the present invention.) Thus, one can prepare a multi-block copolymer in which a polyacrylonitrile or a poly(meth)acrylate block is prepared first, then a styrene or butadiene block is attached thereto, etc.

15


Furthermore, a linking group is not necessary to join the different blocks of the present block copolymer. One can simply add successive monomers to form successive blocks. Further, it is also possible (and in some cases
20 advantageous) to first isolate a (co)polymer produced by the present ATRP process, then react the polymer with an additional monomer using a different initiator/catalyst system (to "match" the reactivity of the growing polymer chain with the new monomer). In such a case, the product
25 polymer acts as the new initiator for the further polymerisation of the additional monomer. Thus, the present invention also encompasses block copolymers. Preferably the number average molecular weight of each block is from 1000 to 250 000 g/mol.

30

- 50 -

The present invention is also useful for making essentially random copolymers. By "essentially random" copolymers, the copolymers are as close to statistically random as is possible under radical polymerisation conditions. The present ATRP process is particularly useful for producing random copolymers where one of the monomers has one or two bulky substituents (eg, 1,1-diarylethylene, didehydromalonate C₁₋₂₀ diesters, C₁₋₂₀ diesters of maleic or fumaric acid, maleic anhydride and/or maleic diimides from which homopolymers may be difficult to prepare, due to steric considerations. Preferably, the number average molecular weight of the copolymer is from 1000 to 1 000 000 g/mol. The ratio of (1) the total number of "blocks" of statistically random units to (2) the total number of monomer units is preferably at least 1:5, more preferably at least 1:8, and most preferably at least 1:10. The present random copolymer can also serve as a block in any of the present block copolymers.

Preferably, at least one of the monomers has the formula:



wherein at least one of R¹³ and R¹⁴ is CN, CF₃, straight or branched alkyl of from 4 to 20 carbon atoms (preferably from 4 to 10 carbon atoms, more preferably from 4 to 8 carbon atoms), C₃₋₈ cycloalkyl, aryl, heterocyclyl, C(=T)R¹⁷,

- 51 -

$C(=T)NR^{18}R^{19}$ and $TC(=T)R^{20}$, where aryl, heterocyclyl, T, R^{17} , R^{18} , R^{19} and R^{20} are as defined above; and

R^{15} and R^{16} are as defined above; or

5

R^{13} and R^{15} are joined to form a group of the formula $C(=O)-T-C(=O)$, where T is as defined above.

More preferred monomers for the present (co)polymer include
10 styrene, acrylonitrile, C_{1-8} esters of (meth)acrylic acid and
1,1-diphenylethylene and derivatives thereof, especially
sodium methacrylate, t-butylaminoethyl methacrylate,
dimethylaminoethyl methacrylate, diethylaminoethyl
methacrylate, dimethylaminopropyl methacrylamide,
15 hydroxyethyl methacrylate, hydroxypropyl methacrylate,
hydroxyethylmorpholine methacrylate,
2-methacryloxyethylglucoside, methoxypolyethyleneglycol
methacrylate, glycerol monomethacrylate, 2-(sulphooxy)ethyl
methacrylate ammonium salt, 3-sulphopropyl methacrylate
20 potassium salt, [2-(methacryloxy)ethyl]dimethyl-
(3-sulphopropyl)ammonium hydroxide inner salt, 4-vinyl
benzoic acid and 4-styrenesulphonic acid sodium salt.

The present invention is also useful for forming so-called
"star" polymers and copolymers.

25 In the present copolymers, each of the blocks may have a
number average molecular weight in accordance with the
homopolymers described above. Thus, the present copolymers
may have a molecular weight which corresponds to the number
of blocks (or in the case of star polymers, the number of

- 52 -

branches times the number of blocks) times the number average molecular weight range for each block.

The present invention also encompasses graft or "comb" copolymers, prepared by sequential ATRPs. Thus, a (co)polymer is produced by a first ATRP, in which at least one of the monomers has a halogen substituent. Preferably, this substituent is Cl or Br. Examples of preferred monomers would thus include vinyl chloride, 1- or 2- chloropropene, vinyl bromide, 1,1- or 1,2-dichloro- or dibromoethene, trichloro- or tribromoethylene, tetrachloro- or tetrabromoethylene, chloroprene, 1-chlorobutadiene, 1- or 2-bromodutadiene, etc. More preferred monomers conclude vinyl chloride, vinyl bromide and chloroprene. It may be necessary to hydrogenate (by known methods) a (co)polymer produced in the first ATRP of chloroprene prior to the second ATRP, using the polymer produced by the first ATRP as the initiator.

Gradient or tapered copolymers can be produced using ATRP by controlling the proportion of two or more monomers being added. For example, one can prepare a first block or a oligomer) of a first monomer, then a mixture of the first monomer and a second, distinct monomer can be added in proportions of from, for example, 1:1 to 9:1 of first monomer to second monomer. After conversion of all monomer(s) is complete, sequential additions of first monomer-second monomers mixtures can provide subsequent "blocks" in which the proportions of first monomer to second monomer vary.

- 53 -

Preferably, the proportions of first and second monomers in subsequent "blocks" vary by at least 10%, preferably by at least 20%, up to 50%, from the preceding block. In a further embodiment, the relative proportions of first monomer to
5 second monomer can be controlled in a continuous manner, using for example a programmable syringe or feedstock supply pump.

When either the initiator or monomer contains a substituent
10 bearing a remote (ie unconjugated) ethylene or acetylene moiety, ATRP can be used to prepare cross-linked polymers and copolymers.

Polymers and copolymers produced by the present process have
15 surprisingly low polydispersity for (co)polymers produced by radical polymerization. Typically, the ratio of the weight average molecular weight to number average molecular weight " M_w / M_n " is ≤ 1.5 , preferably ≤ 1.4 , and can be as low as 1.10 or less.

20

EXAMPLES

The present invention will now be explained in more detail by reference to the following non-limiting examples:

25

- 54 -

Example 1Preparation of controlled cellulose monoacetate (CMA)-graft-copolymers by atom transfer radical polymerisation (ATRP).5 (i) Preparation of CMA based ATRP macroinitiator

Method A: Under an atmosphere of nitrogen, 2-bromoisobutyryl bromide (5.98 g, 26 mmol) was added to a pre-cooled (0°C) solution of 2-bromoisobutyric acid (4.34 g, 26 mmol) in a mixture of dry pyridine (5 mL) and N,N-dimethylacetamide (5 mL). Upon mixing, a yellow colour developed and precipitation was observed. The mixture was stirred for 10 minutes to allow complete formation of 2-bromoisobutyric anhydride) then added, in one lot, to a rapidly stirred solution of cellulose monoacetate (10.00 g, DS 0.7, 51.4 mmol anhydroglucose unit) in N,N-dimethylacetamide (50 mL) and 4-dimethylaminopyridine (0.10 g, 0.8 mmol). The resulting pale yellow solution was stirred for 16 hours overnight then the viscous reaction mixture was then poured very slowly into vigorously stirred methanol (600 mL) and the resulting precipitate filtered off (however, if this was too fine it was isolated by centrifugation). The solids were slurried in methanol (500 mL) and refiltered/centrifuged; this process being carried out two times. Following the second wash cycle the material was dried overnight in a vacuum oven at 40°C. This gave 5.53 g of the macroinitiator as a white powder.

¹H NMR (20% DCl in D₂O) δ_H/ppm: 1.9 (0.22H, s, C[CH₃]₂); 2.1 (6.12H, s, CH₃CO); 3.1-3.9 (12H, m, glucose CH's and CH₂); 4.7

- 55 -

and 5.3 (2H, d, anomeric H's). Thus the NMR showed that the DS of the initiator group was 0.04.

Method B: Cellulose monoacetate (10.00 g, DS 0.7, 51.4 mmol
5 anhydroglucose unit) was dissolved in N,N-dimethylacetamide
(55 mL) by rapid stirring and heating to 80°C. This
solution was allowed to cool to room temperature then dry
pyridine (5 mL) was added. 2-Bromoisobutyryl bromide was
added slowly to this stirred homogeneous mixture during 15
10 minutes whilst a blanket of nitrogen was maintained over the
reaction flask. The cloudy mixture was stirred at room
temperature for 18 hours overnight. The viscous reaction
mixture was then poured very slowly into vigorously stirred
methanol (600 ml) and the resulting precipitate filtered off
15 (however, if this was too fine it was isolated by
centrifugation). The solids were slurried in methanol (500
mL) and refiltered/centrifuged; this process being repeated
two times. Following the second wash cycle the material was
dried overnight in a vacuum oven at 40°C. This gave 6.86 g
20 of the macroinitiator as a white powder. The NMR showed (as
before) that the DS of the initiator group was 0.04.

(ii) Preparation of CMA-graft-poly(styrene-4-sulphonic acid
sodium salt)

25 To a three-neck round bottomed flask equipped with a
nitrogen inlet (via a closeable tap) was added a solution
(heating was required to achieve full dissolution) of
styrene 4-sulphonic acid sodium salt (2.062g, 10.0 mmol) in

- 56 -

N,N-dimethylacetamide (20 mL). A vigorous stream of nitrogen was passed through this solution in order to remove any dissolved oxygen. N-(n-Pentyl)-2-pyridylmethanimine (0.066 g, 0.4 mmol) and a solution of the
5 CMA/bromoisobutyrate initiator ($DS_{\text{initiator}}=0.04$; 0.857 g, 2.3 mmol, so 0.2 mmol Br sites) in N,N-dimethylacetamide (5 mL) were added and the degassing continued. Copper(I)bromide (0.029 g, 0.2 mmol) was added and the mixture degassed for a further 10 minutes before being sealed under nitrogen. The
10 brown coloured reaction mixture was stirred and heated to 80°C for 16 hours, allowed to cool, then transferred to a single neck flask. The solvent was evaporated under reduced pressure and the solid residue dissolved in demineralised water (70 mL). The green coloured aqueous solution was
15 filtered through a short column (45 x 35 mm, W x H) of silica gel (60H) so as to remove the copper. The pale yellow filtrate was frozen (using dry ice) then lyophilised to give 2.12 g of the grafted polysaccharide as a soft white flaky solid.

20 ^1H NMR (D_2O), δ/ppm : 0.9-2.4 (bm, vinylic polymer backbone + acetyl CH_3 groups); 3.2-4.4 (bm, cellulosic $\text{CH}'\text{s}$ and $\text{CH}_2'\text{s}$); 6.2-7.1 (bm) and 7.3-7.9, (bm, aryl $\text{CH}'\text{s}$).

- 57 -

Example 2Preparation of Locust Bean Gum-graft-copolymers(i) Preparation of Locust Bean Gum macroinitiator

A 9% w/v solution of lithium chloride (LiCl) in N,N-
5 dimethylsulphoxide (DMSO) was prepared by heating 9g of LiCl
in 100cm³ of anhydrous DMSO to 150°C in a 2-necked round
bottom flask fitted with an overhead stirrer. Once a
homogeneous solution had been obtained, Locust Bean Gum
(LBG, MUD 246B ex Rhodia) (5g, 0.031 mol of
10 anhydromannose/galactose unit) was added to the solution
gradually, maintaining the temperature at 150°C until a
highly viscous, clear, yellow solution had formed. This
solution was then cooled to 65°C.

In a separate beaker, a solution of 2-bromoisobutyric acid
15 (10.33g, 0.062 mol) in anhydrous DMSO (50cm³) was prepared.
To this solution, 1,1'-carbonyldiimidazole (CDI) (10g,
0.00617 mol) was added slowly. Once the evolution of CO₂ had
ceased, this solution was added to the LBG/DMSO/LiCl
solution with stirring. The reaction mixture was maintained
20 at 65°C for 24 hours. It was then poured into a 3-fold
volume of methanol, causing the product to precipitate.
This was collected on a sinter funnel, then re-dispersed
into methanol, filtered and washed with copious amounts of
methanol. The product was dried under vacuo at 60°C for 48
25 hours, yielding 3.5g of a creamy, crystalline solid.

Characterisation:IR: 1736 cm⁻¹ (s, saturated ester carbonyl)

- 58 -

NMR ($^1\text{H-D}_2\text{O}$): 1.84 (d, ester CH_3 , 6H);

3.4-4.6 (m, mannose/galactose CH and CH_2 , 36H)

From the NMR, the degree of substitution (DS) of ester group per repeat unit of Locust Bean Gum is 0.83.

5

(ii) Preparation of Locust Bean Gum-graft-poly(methacrylic acid)

To a 3-necked round bottom flask fitted with an N_2 inlet, thermometer and suba seal fitted with a syringe needle were added Locust Bean Gum - macroinitiator (1g, 9.294×10^{-4} mol),
10 sodium methacrylate (5.02g, 0.04647 mol) and a magnetic stirrer bar. The solids were dissolved in demineralised water (15 cm^3) and the resulting solution de-gassed by bubbling nitrogen gas through for 45 minutes. A mixture of
15 copper (I) bromide (0.1333g, 9.294×10^{-4} mol) and 2,2'-dipyridyl (0.2937g, 1.859×10^{-3} mol) was added to the reaction flask. A polymerisation exotherm of 10°C was noted. The reaction was stirred for 2 hours at ambient temperature. The contents of the flask was then diluted with
20 demineralised water and the solution passed through a slurry of silica on a sinter funnel, yielding a water-white, clear solution. This was added to a 3-fold volume of methanol, causing the product to precipitate. This was collected on a filter and dried in vacuo at 40°C to constant weight,
25 yielding 2.8 g of white, crystalline powder.

- 59 -

Characterisation

IR: 1544 cm^{-1} (vs, carboxylate ion)


NMR ($^1\text{H-D}_2\text{O}$): 0.7-1.4 (m, CH_3 polymer main chain, 130H)

3.4-4.4 (m, mannose/galactose CH and CH_2 , 36H).

- 5 This indicates that the number of repeat units (or degree of polymerisation, DP) of the grafted poly(methacrylic acid, Na salt) is 44.

CLAIMS

1 A substituted polysaccharide useful as a macroinitiator
 for preparing graft polysaccharide polymers by controlled
 5 graft polymerisation, in which at least one sugar unit of
 the polysaccharide is substituted by a group of the general
 formula



in which

10 W represents a group $-O-$ or $-NR^1-$, where R^1 represents a
 hydrogen atom or an optionally substituted alkyl group,
 preferably a hydrogen atom;


p, q and r are each independently 0 or 1;

L represents an optionally substituted alkylene,
 15 cycloalkylene, arylene or heteroarylene group;

X and Y each independently represent a group $-CH_2-$, $-CO-$, $-O-$,
 $CO-$, $-CO-O-$, $-NH-CO-$, $-CO-NH-$, $-CH(OH)-CH_2-$, $-CH_2-CH(OH)-$, $-$
 $CH_2-O-CO-$, $-CO-O-CH_2-$, $-CH_2-CO-O-$, $-O-CO-CH_2-$, $-O-CO-NH-$, $-NH-$
 20 $CO-O-$, $-(CR^2R^3)_s-CO-$, $-CO-(CR^2R^3)_s-$, $-(CR^2R^3)_t-O-$, $-O-(CR^2R^3)_t-$,
 $-(CR^2R^3)_u-SO-$, $-SO-(CR^2R^3)_u-$, $-(CR^2R^3)_v-SO_2-$, $-SO_2-(CR^2R^3)_v-$ or $-$
 $NH-CO-NH$, where s, t, u and v are each independently 0, 1, 2
 or 3 and R^2 and R^3 each independently represent a hydrogen
 atom or an optionally substituted alkyl group, preferably a
 hydrogen atom; and

25 Z represents a control agent site from which a polymer may
 propagate during a free radical polymerisation process,

the substituted polysaccharide having the general formula



5

10 wherein each SU represents a sugar unit in a polysaccharide backbone;

a represents the number of unsubstituted sugar units as a percentage of the total number of sugar units and is in the range from 0 to 99.9%, preferably 65 to 99%, more preferably
 15 80 to 99%;

b represents the number of substituted sugar units as a percentage of the total number of sugar units and is in the range from 0.1 to 100%, preferably 1 to 35%, more preferably 1 to 20%;

20 m represents the degree of substitution per sugar unit and is from 1 to 3.

- 62 -


2 A substituted polysaccharide according to claim 1 in
 which W represents a group -O- or -NH-.

3 A substituted polysaccharide according to claim 1 or
 5 claim 2, in which q is I and L is a -CH₂- group.

4 A substituted polysaccharide according to any one of the
 preceding claims, in which p and/or r is I and X and/or Y
 represents a group -CH₂-, -CO-, -CO-NH- or -NH-CO-.

10

5 A substituted polysaccharide according to any one of the
 preceding claims in which Z is a group of the general formula



wherein Hal and Hal¹ each represent a halogen atom, preferably
 a chlorine or bromine atom, more preferably a bromine atom;

R⁴ and R⁵ each independently represent an optionally
 substituted alkyl, cycloalkyl or aralkyl group;

20 w is 0, 1, 2, 3 or 4;

R⁶ represents a halogen atom or an optionally substituted
 alkyl group; and

- 63 -

R⁷ represents a hydrogen atom or an optionally substituted alkyl group.

6 A substituted polysaccharide according to claim 5, in
5 which R⁴ and R⁵ both represent a methyl group and Hal
represents a bromine atom.

7 A substituted polysaccharide according to claim 5, in
which w is 0, R⁷ represents a hydrogen atom and Hal¹
10 represents a bromine atom.

8 A substituted polysaccharide according to any one of
claims 1 to 6, in which W represents a group -O- or -NH-, p,
q and r are 0 and Z represents a group -CO-C(CH₃)₂-Br.

15


9 A substituted polysaccharide according to any one of
claims 1 to 5 or 7, in which W represents a group -O- or -
NH-, p and q are both 0, r is 1, Y represents a group -CH₂-
or -CO- and Z represents a 4-(bromomethyl)phenyl group.

20

10 A substituted polysaccharide according to any one of
the preceding claims in which the polysaccharide has a β -
linked backbone, preferably a β -1,4- linked backbone.

11 A substituted polysaccharide according to any one of the preceding claims in which the polysaccharide is selected from the group consisting of cellulose, cellulose derivatives (preferably cellulose sulphate, cellulose acetate, sulphoethyl cellulose, cyanoethyl cellulose, methyl cellulose, ethyl cellulose, carboxymethylcellulose, hydroxyethylcellulose or hydroxypropylcellulose), xyloglucans (preferably those derived from Tamarind seed gum), glucomannans (preferably Konjac glucomannan), galactomannans (preferably Locust Bean gum, Guar gum and Xanthan gum), chitosan and chitosan salts.



12 A substituted polysaccharide according to any one of the preceding claims, having the general formula





15

wherein at least one or more -OR groups of the polymer are independently replaced by a group $-W-(X)_p-(L)_q-(Y)_r-Z$, in which p, q, r, W, X, L, Y and Z are as defined in any one of the preceding claims, and at least one or more R groups are



independently selected from hydrogen atoms and groups of formulae:







5



10



15



- 66 -

wherein each R⁸ is independently selected from C₁₋₂₀
(preferably C₁₋₆) alkyl, C₂₋₂₀ (preferably C₂₋₆) alkenyl (eg
vinyl) and C₅₋₇ aryl (eg phenyl) any of which is optionally
substituted by one or more substituents independently
5 selected from C₁₋₄ alkyl, C₁₋₁₂ (preferably C₁₋₄) alkoxy,
hydroxyl, vinyl and phenyl groups;

each R⁹ is independently selected from hydrogen and groups R⁸
as hereinbefore defined;

R¹⁰ is a bond or is selected from C₁₋₄ alkylene, C₂₋₄ alkenylene
10 and C₅₋₇ arylene (eg phenylene) groups, the carbon atoms in
any of these being optionally substituted by one or more
substituents independently selected from C₁₋₁₂ (preferably
C₁₋₄) alkoxy, vinyl, hydroxyl, halo and amine groups;

each R¹¹ is independently selected from hydrogen, counter
15 cations such as alkali metal (preferably Na) or $\frac{1}{2}$ Ca or $\frac{1}{2}$ Mg,
and groups R⁸ as hereinbefore defined;

R¹² is selected from C₁₋₂₀ (preferably C₁₋₆) alkyl, C₂₋₂₀
(preferably C₂₋₆) alkenyl (eg vinyl) and C₅₋₇ aryl (eg
phenyl), any of which is optionally substituted by one or
20 more substituents independently selected from C₁₋₄ alkyl, C₁₋₁₂
(preferably C₁₋₄) alkoxy, hydroxyl, carboxyl, cyano,
sulphonato, vinyl and phenyl groups;

x is from 1 to 3; and

groups R which together with the oxygen atom forming the
25 linkage to the respective saccharide ring forms an ester or
hemi-ester group of a tricarboxylic- or higher

- 68 -

wherein SU, a, b, m, p, q, r, W, X, L and Y are as defined in any one of the preceding claims, Z¹ represents a group Z as defined in any one of the preceding claims from which a halogen atom has been removed, P represents a polymer chain,
5 Hal² represents a halogen, preferably chlorine or bromine and more preferably a bromine, atom and k is from 10 to 200, preferably from 10 to 100.

15 A graft polysaccharide polymer according to claim 14,
10 in which m is from 1 to 2, preferably 1.

16 A graft polysaccharide polymer according to claim 14 or claim 15, in which P represents a single polymer chain, a random copolymer of two or more monomers or a gradient block
15 copolymer of two or more monomers.

17 A graft polysaccharide polymer according to any one of claims 14 to 16, in which the polysaccharide backbone has a number average molecular weight from 10 000 to 1 000 000.

20


18 A graft polysaccharide polymer according to any one of claims 14 to 17, in which the polymer is water soluble at a concentration of at least 0.2mg/ml.

- 69 -

19 A graft polysaccharide polymer according to any one of claims 14 to 18, in which the grafts have a number average molecular weight of from 1000 to 200 000.

5 20 A graft polysaccharide polymer according to any one of claims 14 to 19, in which P represents a polymer chain derived from a free radically polymerisable alkene monomer.

21 A graft polysaccharide polymer according to any one of
10 claims 14 to 20, in which P represents a polymer chain derived from a free radically polymerisable monomer selected from the group consisting of compounds of the general formula



wherein R^{13} and R^{14} are independently selected from the group consisting of H, halogen, CN, CF_3 , straight or branched C_{1-20}
20 (preferably C_{1-6} , more preferably C_{1-4}) alkyl, α , β -unsaturated straight or branched C_{2-10} (preferably C_{2-6} , more preferably C_{2-4}) alkenyl or alkynyl, α , β -unsaturated straight or branched C_{2-6} alkenyl (preferably vinyl) substituted (preferably at the α -position) with a halogen (preferably
25 chlorine), C_3 - C_8 cycloalkyl, heterocyclyl, $\text{C}(=\text{T})\text{R}^{17}$, $\text{C}(=\text{T})\text{NR}^{18}\text{R}^{19}$ and $\text{TC}(=\text{T})\text{R}^{20}$, where T may be NR^{20} or O

- 70 -

(preferably O), R¹⁷ is C₁₋₂₀ alkyl, C₁₋₂₀ alkoxy, aryloxy or heterocycloxy, R¹⁸ and R¹⁹ are independently H or C₁₋₂₀ alkyl, or R¹⁸ and R¹⁹ may be joined together to form a C₂₋₅ alkylene group, thus forming a 3- to 6-membered ring, and R²⁰ is H, straight or branched C_{1-C₂₀} alkyl or aryl; and R¹⁵ and R¹⁶ are independently selected from the group consisting of H, halogen (preferably fluorine or chlorine), C_{1-C₆} (preferably C₁) alkyl, COOR²¹ and CONHR²¹ (where R²¹ is H, an alkali metal, or a C_{1-C₆} alkyl group optionally substituted by a hydroxy, amino, C₁₋₆ alkylamino or di-(C₁₋₆alkyl)amino group); or a heterocyclyl group optionally substituted by a C₁₋₆ alkyl or hydroxy C₁₋₆ alkyl group; R¹³ and R¹⁵ may be joined to form a group of the formula (CH₂)_n, (which may be substituted with from 1 to 2n' halogen atoms or C_{1-C₄} alkyl groups) or C(=O)-T-C(=O), where n' is from 2 to 6 (preferably 3 or 4) and T is as defined above; and at least two of R¹³, R¹⁴, R¹⁵ and R¹⁶ are H or halogen.

20 22 A graft polysaccharide polymer according to any one of claims 14 to 20, in which P represents a polymer chain derived from a monomer selected from the group consisting of sodium methacrylate, t-butylaminoethyl methacrylate, dimethylaminoethyl methacrylate, diethylaminoethyl methacrylate, dimethylaminopropyl methacrylamide, hydroxyethyl methacrylate, hydroxypropyl methacrylate, hydroxyethylmorpholine methacrylate, 2-methacryloxyethyl glucoside, methoxypolyethyleneglycol methacrylate, glycerol monomethacrylate, 2-(sulphooxy)ethyl methacrylate ammonium salt, 3-sulphopropyl methacrylate potassium salt,

- 71 -

[2-(methacryloxy)ethyl]dimethyl- (3-sulphopropyl) ammonium hydroxide inner salt, 4-vinyl benzoic acid and 4-styrenesulphonic acid sodium salt.

5 23 A graft polysaccharide polymer according to any one of claims 14 to 20, in which P represents a polymer chain which is a copolymer derived from a monomer as defined in claim 22 or claim 23 and a monomer selected from the group consisting of alkyl methacrylates (eg stearyl methacrylate),
10 perfluoroalkyl methacrylates (eg 1H,1H,2H,2H-heptadecafluorodecyl methacrylate), and siloxane methacrylates (eg monomethacryloxypropyl terminated polydimethylsiloxane).

15 24 A process for preparing a graft polysaccharide polymer as defined in any one of claims 14 to 23, which comprises polymerising at least one free radically polymerisable monomer as defined in any one of claims 20 to 23 from the control agent site of a substituted polysaccharide according
20 to any one of claims 1 to 13 in the presence of a transition metal compound and a ligand, and isolating the (co)polymer so formed.

25 A process according to claim 24, in which the transition metal compound is a compound of the formula $M^{j+}N_j$ where M^{j+} is selected from the group consisting of Cu^+ , Cu^{2+} , Fe^{2+} , Fe^{3+} , Ru^{2+} , Ru^{3+} , Cr^{2+} , Cr^{3+} , Mo^{2+} , Mo^{3+} , W^{2+} , W^{3+} , Mn^{3+} ,

- 72 -

Mn⁴⁺, Rh³⁺, Rh⁴⁺, Re²⁺, Re³⁺, Co⁺, Co²⁺, V²⁺, V³⁺, Zn⁺, Zn²⁺, Au⁺, Au²⁺, Ag⁺ and Ag²⁺;

N is selected from the group consisting of halogen, C₁₋₆ alkoxy, (SO₄)_½, (PO₄)_{1/3}, (HPO₄)_½, (H₂PO₄), triflate, 5 hexafluorophosphate, methanesulphonate, arylsulphonate, CN and R²²CO₂, where R²² represents a hydrogen atom or a straight or branched C₁₋₆ alkyl (preferably methyl) group which may be substituted from 1 to 5 times with a halogen atom (preferably 1 to 3 times with a fluorine or chlorine atom); 10 and j is the formal charge on the metal.

26 A process according to claim 24 or claim 25, in which the ligand is a N-, O-, P- or S- containing compound which can coordinate in a σ - bond to the transition metal or any 15 carbon-containing compound which can coordinate in a π -bond to the transition metal.

27 A process according to any one of claims 24 to 26, in which the molecular weight of the polymer chain P is 20 controlled to a desired point based on living-type kinetics.

INTERNATIONAL SEARCH REPORT

Inte	Application No
PCT/EP 02/07683	

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 C08B37/08 C08F251/00 C08F251/02				
According to International Patent Classification (IPC) or to both national classification and IPC				
B. FIELDS SEARCHED				
Minimum documentation searched (classification system followed by classification symbols)				
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched				
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)				
C. DOCUMENTS CONSIDERED TO BE RELEVANT				
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.		
X	STENZEL-ROSENBAUM M H ET AL: "SYNTHESIS OF POLY(STYRENE) STAR POLYMERS GROWN FROM SUCROSE, GLUCOSE, AND CYCLODEXTRIN CORES VIA LIVING RADICAL POLYMERIZATION MEDIATED BY A HALF-METALLOCENE IRON CARBONYL COMPLEX" MACROMOLECULES, AMERICAN CHEMICAL SOCIETY. EASTON, US, vol. 34, no. 16, July 2001 (2001-07), pages 5433-5438, XP001115057 ISSN: 0024-9297 Published on the Web 06-07-2001 --- -/--	1-27		
<table style="width: 100%; border: none;"> <tr> <td style="width: 50%; border: none;"><input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.</td> <td style="width: 50%; border: none;"><input checked="" type="checkbox"/> Patent family members are listed in annex.</td> </tr> </table>			<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.	<input checked="" type="checkbox"/> Patent family members are listed in annex.
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.	<input checked="" type="checkbox"/> Patent family members are listed in annex.			
* Special categories of cited documents :				
<table style="width: 100%; border: none;"> <tr> <td style="width: 50%; border: none;"> *A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed </td> <td style="width: 50%; border: none;"> *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *&* document member of the same patent family </td> </tr> </table>			*A* document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *&* document member of the same patent family
A document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *&* document member of the same patent family			
Date of the actual completion of the international search		Date of mailing of the international search report		
21 November 2002				
Name and mailing address of the ISA		Authorized officer		
European Patent Office, P.B. 5618 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Mazet, J-F		

INTERNATIONAL SEARCH REPORT

 International Application No
 PCT/EP 02/07683

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 231 809 A (LEON LILIENFELD) 30 September 1925 (1925-09-30) page 3, line 19 - line 32 page 3, line 68 - line 108 page 4, line 1 - line 13 page 5, line 33 - line 48 ---	1-6,8, 10-13
X	US 2 518 203 A (DOROTHY D. THOMPSON) 8 August 1950 (1950-08-08) column 1, line 5 - line 26 column 5, line 70 - column 6, line 11 column 7, line 65 - line 69 ---	1-4, 10-13
X	GB 1 044 751 A (GEOFFREY ROBERT AMES) 5 October 1966 (1966-10-05) claims ---	1-3,10, 11,13
P,X	WO 02 50174 A (POLYMERAT PTY LTD) 27 June 2002 (2002-06-27) page 7, line 12 - line 15 page 29, line 15 - page 30, line 8 page 32, line 14 - page 33, line 20 ---	1-27
P,X	DE 100 27 746 A (BAYER AG) 6 December 2001 (2001-12-06) the whole document ---	1-27
X	K. OHNO ET AL.: "Synthesis of well-defined cyclodextrin-core star polymers" JOURNAL OF POLYMER SCIENCE: PART A: POLYMER CHEMISTRY, vol. 39, 2001, pages 2206-2214, XP001127410 the whole document ---	1-27
P,X	A. CARLMARK ET AL.: "Transfer radical polymerization from cellulose fibers" POLYMER PREPRINTS, vol. 43, no. 2, 2002, pages 57-58, XP008010467 the whole document ---	1-27
X	D. M. HADDLETON ET AL.: "Glucose derived star polymers by atom transfer polymerization" POLYMERIC MATERIALS SCIENCE AND ENGINEERING, vol. 80, 1999, pages 145-146, XP008010586 USA the whole document ---	1-27
	-/--	

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/07683

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	R. EDMONDS ET AL.: "Carbohydrate-based initiators for transition-metal mediated atom transfer polymerization" POLYMER PREPRINTS, vol. 41, no. 1, 2000, pages 444-445, XP008010584 USA the whole document	1-27
P,X	A. CARLMARKET AL.: "Atom Transfer Radical Polymerization from Cellulose Fibers at Ambient Temperature" JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol. 124, no. 6, 16 January 2002 (2002-01-16), pages 900-901, XP001127401 USA the whole document	1-27
A	EP 0 725 131 A (BASF AKTIENGESELLSCHAFT) 7 August 1996 (1996-08-07)	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 02/07683

Patent document cited in search report	A	Publication date	Patent family member(s)	Publication date
GB 231809	A	30-09-1925	NONE	
US 2518203	A	08-08-1950	NONE	
GB 1044751	A	05-10-1966	NONE	
WO 0250174	A	27-06-2002	WO 0250174 A1 AU 1682402 A	27-06-2002 01-07-2002
DE 10027746	A	06-12-2001	DE 10027746 A1	06-12-2001
EP 725131	A	07-08-1996	DE 19503116 A1 EP 0725131 A1	08-08-1996 07-08-1996