



HU000028073T2

(19) **HU**(11) Lajstromszám: **E 028 073**(13) **T2****MAGYARORSZÁG**  
Szellemi Tulajdon Nemzeti Hivatala**EURÓPAI SZABADALOM**  
**SZÖVEGÉNEK FORDÍTÁSA**

- (21) Magyar ügyszám: **E 13 739509**
- (22) A bejelentés napja: **2013. 06. 13.**
- (96) Az európai bejelentés bejelentési száma:  
**EP 20130739509**
- (97) Az európai bejelentés közzétételi adatai:  
**EP 2785483 A1**                      **2013. 12. 19.**
- (97) Az európai szabadalom megadásának meghirdetési adatai:  
**EP 2785483 B1**                      **2015. 08. 12.**
- (51) Int. Cl.: **B22F 9/24**                      (2006.01)  
**B01J 13/00**                      (2006.01)  
**B22F 1/00**                      (2006.01)  
**C22C 1/04**                      (2006.01)  
**B22F 1/02**                      (2006.01)
- (86) A nemzetközi (PCT) bejelentési szám: **PCT/IB 13/054857**
- (87) A nemzetközi közzétételi szám: **WO 13186740**

(30) Elsőbbségi adatok: <b>39950512</b> <b>2012. 06. 13.</b> <b>PL</b>	(73) Jogosult(ak): <b>Uniwersytet Warszawski, 00-927 Warszawa (PL)</b>
(72) Feltaláló(k): <b>JURCZAKOWSKI, Rafal, PL-05-840 Brwinow (PL)</b> <b>KULBOKA, Pawel, PL-78-500 Drawsko Pomorskie (PL)</b> <b>LEWERA, Adam, PL-02-744 Warszawa (PL)</b>	(74) Képvisező: <b>dr. Fehérvári Flóra, DANUBIA Szabadalmi és Jogi Iroda Kft., Budapest</b>

- (54) **Eljárás tiszta nanorészecskék előállítására folyamatos áramlási rendszer alkalmazásával**

Az európai szabadalom ellen, megadásának az Európai Szabadalmi Közlönyben való meghirdetésétől számított kilenc hónapon belül, felszólalást lehet benyújtani az Európai Szabadalmi Hivatalnál. (Európai Szabadalmi Egyezmény 99. cikk(1))

A fordítást a szabadalmas az 1995. évi XXXIII. törvény 84/H. §-a szerint nyújtotta be. A fordítás tartalmi helyességét a Szellemi Tulajdon Nemzeti Hivatala nem vizsgálta.



(11) **EP 2 785 483 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention of the grant of the patent:  
**12.08.2015 Bulletin 2015/33**

(51) Int Cl.:  
**B22F 9/24** <sup>(2006.01)</sup> **B22F 1/00** <sup>(2006.01)</sup>  
**B01J 13/00** <sup>(2006.01)</sup> **C22C 1/04** <sup>(2006.01)</sup>  
**B22F 1/02** <sup>(2006.01)</sup>

(21) Application number: **13739509.1**

(86) International application number:  
**PCT/IB2013/054857**

(22) Date of filing: **13.06.2013**

(87) International publication number:  
**WO 2013/186740 (19.12.2013 Gazette 2013/51)**

(54) **METHOD FOR PREPARING PURE NANOPARTICLES USING A CONTINUOUS FLOW SYSTEM**

VERFAHREN ZUR HERSTELLUNG REINER NANOPARTIKEL, DAS EIN SYSTEM FÜR EINEN KONTINUIERLICHEN DURCHFLUSS GEBRAUCHT

PROCÉDÉ POUR LA PRÉPARATION DE NANOPARTICULES PRATIQUEMENT PURES UTILISANT UN SYSTÈME À CIRCULATION

(84) Designated Contracting States:  
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR**

(30) Priority: **13.06.2012 PL 39950512**

(43) Date of publication of application:  
**08.10.2014 Bulletin 2014/41**

(73) Proprietor: **Uniwersytet Warszawski 00-927 Warszawa (PL)**

(72) Inventors:  
• **JURCZAKOWSKI, Rafal PL-05-840 Brwinow (PL)**  
• **KULBOKA, Pawel PL-78-500 Drawsko Pomorskie (PL)**  
• **LEWERA, Adam PL-02-744 Warszawa (PL)**

(74) Representative: **Patpol Kancelaria Patentowa Sp. z o.o. Nowoursynowska 162J 02-776 Warszawa (PL)**

(56) References cited:  
**EP-A1- 1 741 717 WO-A1-2010/108837**  
**US-A1- 2006 054 506 US-A1- 2007 207 335**

- **WAGNER J ET AL: "Continuous synthesis of gold nanoparticles in a microreactor", NANO LETTERS, AMERICAN CHEMICAL SOCIETY, US, vol. 5, no. 4, 1 April 2005 (2005-04-01), pages 685-691, XP002535013, ISSN: 1530-6984, DOI: 10.1021/NL050097T [retrieved on 2005-03-16] cited in the application**
- **KOHLER J M ET AL: "Preparation of metal nanoparticles with varied composition for catalytical applications in microreactors", CHEMICAL ENGINEERING SCIENCE, OXFORD, GB, vol. 63, no. 20, 1 October 2008 (2008-10-01), pages 5048-5055, XP025874326, ISSN: 0009-2509, DOI: 10.1016/J.CES.2007.11.038 [retrieved on 2007-12-05] cited in the application**
- **J.?M. KÖHLER ET AL: "Formation of Au/Ag Nanoparticles in a Two Step Micro Flow-Through Process", CHEMICAL ENGINEERING & TECHNOLOGY, vol. 30, no. 3, 1 March 2007 (2007-03-01), pages 347-354, XP055083275, ISSN: 0930-7516, DOI: 10.1002/ceat.200600388**
- **WAGNER J ET AL: "Generation of metal nanoparticles in a microchannel reactor", CHEMICAL ENGINEERING JOURNAL, ELSEVIER SEQUOIA, LAUSANNE, CH, vol. 101, no. 1-3, 1 August 2004 (2004-08-01), pages 251-260, XP002595440, ISSN: 1385-8947, DOI: 10.1016/J.CEJ.2003.11.021 [retrieved on 2004-02-03] cited in the application**

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

**EP 2 785 483 B1**

- MA XIAOYUAN ET AL: "Biocatalytically induced growth of gold nanoshells: using enzyme reaction for the controllable fabrication of nanomaterials", JOURNAL OF NANOSCIENCE AND NANOTECHNOLOGY, AMERICAN SCIENTIFIC PUBLISHERS, US, vol. 12, no. 2, 1 February 2012 (2012-02-01), pages 870-878, XP009173380, ISSN: 1533-4880

**Description**

## TECHNICAL FIELD

5 **[0001]** The invention provides a flow system method for preparing substantially pure nanoparticles.

## BACKGROUND ART

10 **[0002]** In recent years nanomaterials have become a subject of significant interest due to their size-dependent properties and potential application in the field of catalysts, sensors and other fields of nanotechnology and microelectronics. Nanoparticles of metals or their alloys with diameter ranging from several to several dozens of nanometers are of particular interest. Metallic nanoparticles display increased reactivity of the surface atoms and exceptional optical properties. Moreover, because of their highly developed surface area, nanoparticles are considered an attractive material for use in heterogenic catalysis. Metallic nanoparticles can also be used in medicine as carriers for therapeutic substances.

15 **[0003]** Different methods of nanoparticle synthesis are known. One of such methods utilizes continuous-flow microreactors. A continuous-flow microreactor is a device used for carrying out a chemical reaction in a small volume. It comprises one or more channels of small diameter for transporting the reagents in and the product out of the system, as well as a mixing compartment or a combination of mixing compartments, which allow for the mixing of the reagents. Use of such type of a device has many advantages, as it allows for quick and thorough mixing of the reagents and makes the temperature control easy. The continuous-flow microsystems for nanoparticle synthesis have been described, for example in publication WO 2004/076056 and WO 2009/133418. Use of continuous-flow microsystems for synthesis of nanoparticles of noble metals, such as Pt, Pd and Au, has been discussed in a review article by Wojnicki M. et al. ("Zastosowanie mikroreaktorów przepływowych do syntezy nanocząstek metali szlachetnych (Pt, Pd, Au). Przegląd literatury", Rudy Metale, 2011, vol. 56, no 12, p. 745-752).

25 **[0004]** Methods for nanoparticle synthesis using continuous-flow microreactors comprise chemical reduction of metal precursors, i.e. metal salts, such as Pd(OAc)<sub>2</sub>, PdCl<sub>2</sub>, PtCl<sub>4</sub>, AuCl<sub>3</sub>, AgNO<sub>3</sub>, Cu(OAc)<sub>2</sub>, CuCl<sub>2</sub>, RhCl<sub>3</sub> and FeCl<sub>3</sub>, in a solution and in the presence of surfactants or other organic molecules, which aim to stabilize nanoparticles (their concentration and type determine nanoparticle size) and prevent nanoparticle aggregation.

30 **[0005]** Sodium citrate, ascorbic acid, hydrazine, sodium borohydride, lithium tetraethylborohydride, methyl alcohol, ethylene glycol, 1,2-hexadecandiol and glucose are commonly used as reducing agents (see, for example Streszewski B. et al., "Synteza nanocząstek złota metodą redukcji jonów kompleksowych złota (III) za pomocą hydrazyny w układzie mikroreaktora przepływowego", Rudy Metale, 2011, vol. 56, no 12, p. 752-761).

35 **[0006]** Polyvinylpyrrolidone (PVP) (as discussed in, for example, in Wagner J. et al., "Generation of metal nanoparticles in a microchannel reactor", Chemical Engineering Journal, 2004, no 101, p. 251-260; Köhler J.M. et al., "Formation of isolated and clustered Au nanoparticles in the presence of polyelectrolyte molecules using a flow-through Si chip reactor", Journal of Materials Chemistry, 2005, no 15, p. 1924-1930; Wagner J. et al., "Continuous synthesis of gold nanoparticles in a microreactor", Nano Letters, 2005, vol. 5, no 4, p. 685-691.) and polyvinyl alcohol (PVA) (as discussed in, for example, in Köhler J. M. et al., "Formation of Au/Ag Nanoparticles in a Two Step Micro Flow-Through Process", Chem. Eng. Technol. 2007, vol. 30, no 3, p. 347-354; Köhler J. M. et al., "Preparation of metal nanoparticles with varied composition for catalytically applications in microreactors", Chemical Engineering Science, 2008, vol. 63, p. 5048-5055;

40 Wojnicki M. et al., "Synteza nanocząstek złota stabilizowanych PVA (alkohol poliwinylowy) w mikroreaktorze przepływowym"; Rudy Metale, 2009, vol. 54, no 12, p. 848-852) are often used as stabilizing agents. Other stabilizing agents used in the art include sulfobetaine (Song Y. et al., "Synthesis of palladium nanoparticles using a continuous flow polymeric microreactor", Journal of Nanoscience and Nanotechnology, 2004, vol.4, no 7, p. 788-793) and poly(benzyl ether) (Torgoe K. et al., "Microflow reactor synthesis of palladium nanoparticles stabilized with poly(benzyl ether) Dendron ligands", Journal of Nanoparticle Research, 2010, vol. 12, no 3, p. 951-960). Sometimes a reducing agent can, at the same time, play a role of a stabilizing agent, as it is in the case of sodium citrate (Weng C. H. et al., "Synthesis of hexagonal gold nanoparticles using a microfluidic reaction system", Journal of Micromechanics and Microengineering, 2008, vol. 18, p. 1-8; Sung-Yi Yang, "Size controlled synthesis of gold nanoparticles using a micromixing system", Microfluid Nanofluid, 2009, vol. 8, p. 303-311).

45 **[0007]** Straightforward size control of the produced nanoparticles is an advantage of using continuous-flow microsystems for nanoparticle synthesis. Nanoparticle size depends on temperature, reagent flow rate and length of the channels, where reduction reaction takes place. Use of surfactants and other organic molecules as stabilizing agents is a disadvantage of nanoparticle synthesis methods known in the art. Use of stabilizing agents is very unfavorable, because they strongly adsorb on the surface of the newly formed nanoparticles and before further use of the nanoparticles it is necessary to use complex procedures, for example electrochemical methods, to purify their surface (see, for example, publication

of Solla-Gullon J. et al., "Electrochemical characterization of platinum nanoparticles prepared by microemulsion: how to clean them without loss of crystalline surface structure", J. Electroanal. Chem., 2000, vol. 491, no 1-2, p. 69-77), and this, very often, alters the nanoparticle properties (for example, catalytic properties). Furthermore, very often it is not possible to remove the adsorbed stabilizing agents entirely from the nanoparticle surface (see, for example, Park, J. Y. et al., "The Role of Organic Capping Layers of Platinum Nanoparticles in Catalytic Activity of CO Oxidation", Catalysis Letters 2009, vol. 129, no 1-2, p. 1-6).

**[0008]** A further disadvantage related to use of continuous-flow microsystems known in the art is that they are limited to low reagent concentrations, which results in obtaining of colloids having low concentration of nanoparticles.

**[0009]** Therefore there exists a considerable demand for a method enabling nanoparticle synthesis, in particular nanoparticles of metals or their alloys, in essentially pure form, which method would make it possible to use such nanoparticles directly, i.e. without the need of performing the inconvenient purification processes. It would be also advantageous, if a method was developed, whose application would lead to obtaining stable nanoparticle colloids of high concentration and would make it possible to produce nanoparticles on a large scale.

## DISCLOSURE OF INVENTION

**[0010]** The inventors of the present invention have developed a synthesis method for producing pure nanoparticles, which makes it possible to control size of the synthesized nanoparticles and at the same time eliminates the need to use the stabilizing agents, in particular stabilizing agents in the form of surfactants and other organic molecules. Moreover, this method results in nanoparticles in the form of colloids having high concentration of nanoparticles, the said colloids being characterized by high stability. This method further makes it possible to produce the nanoparticles on a large scale.

**[0011]** The invention relates to the method of claim 1. Examples of continuous-flow systems used to carry out the method of the invention are presented schematically in Fig. 1a and Fig. 1b.

**[0012]** In the preferred embodiment the method of the invention comprises one step, in which the precursor substance solution undergoes reduction reaction using the reducing agent solution and homogeneous nanoparticles are obtained. The term "homogeneous nanoparticles" should be understood as nanoparticles having uniform atom distribution throughout the entire volume of the nanoparticle. The homogeneous nanoparticles include, in particular, both the metal nanoparticles, as well as metal alloy nanoparticles. Fig. 1a presents a system, in which the method comprising one reduction step is carried out. In this system the tube, in which the reducing agent solution is flowing, is fed with the precursor substance solution through a different tube. After mixing of the two solutions, nanoparticles are formed as a result of the reduction reaction. These formed nanoparticles flow together with the stream of the reaction mixture in the direction of the site, where the tube feeding the substance neutralizing the reducing agent is connected. The nanoparticle colloidal solution flows out of the system.

**[0013]** In another preferred embodiment the method of the invention comprises at least two steps, in which the precursor substance solution undergoes reduction reaction using the reducing agent solution and layered nanoparticles of core-shell type are obtained. Fig. 1b presents a system, in which the method comprising two reduction steps is carried out. In this system the tube, in which the reducing agent solution is flowing, is fed with the solution of the first precursor substance (precursor substance 1) through a different tube. After mixing of the two solutions nanoparticles, which constitute the core, are formed as a result of the reduction reaction (step no 1). These formed nanoparticles flow together with the stream of the reaction mixture in the direction of the site, where the tube feeding the second precursor substance (precursor substance 2) is connected. The reduction of the second precursor substance (step no 2) results in formation of the shell made of a different substance on the nanoparticles formed in the first step. The layered nanoparticles flow with the stream of the reaction mixture in the direction of the site, where the tube feeding the substance neutralizing the reducing agent is connected. The colloidal solution of the core-shell nanoparticles flows out of the system.

**[0014]** Also, as the substance neutralizing the reducing agent, a redox buffer can possibly be used having a potential at which the reducing agent becomes oxidized. A possibility to control precisely the potential of the colloid solution is an advantage resulting from using the redox buffer. The redox potential control of the colloid solution makes the control of the nanoparticle surface charge possible, and thus it is possible to select appropriate conditions under which the colloid is stable. Also formation of the outer shell consisting of an atomic monolayer deposited on the core of a different metal is also possible when the redox buffer is used. In order to do that it is necessary to prepare a colloid of nanoparticles, which nanoparticles constitute the cores, wherein to the said colloid a redox buffer is added having a potential suitable for under-potential reduction (i.e. Under-Potential Deposition, UPD) of the metal outer layer (i.e. shell) on the metal of the core. At the same time, the buffer potential has to be high enough to prevent the over-potential reduction (i.e. Over-Potential Deposition, OPD) of the metal outer layer, and thus the formation of the subsequent metal layers of the shell is avoided. In case of the most of the noble metals the UPD and OPD processes are noticeably separated on the potential scale and this method is used for monolayer deposition on the surface of metallic electrodes, whose potential is controlled by the means of a potentiostat (see, for example, S. Szabó, "Underpotential deposition of metals on foreign metal substrates", International Reviews in Physical Chemistry 1991, vol. 10, no 2, p. 207-248).

**[0015]** As used herein the phrase "pure nanoparticles" refers to the nanoparticles on surface of which neither surfactants nor other organic molecules are adsorbed. Not limiting to any theory, it can be stated that nanoparticles obtained by the method of the invention are stabilized by addition of the substance neutralizing the reducing agent to the reaction system, due to a rapid elimination of the reducing agent and as a result of formation of hydrated oxides and/or hydroxides and/or hydroxysalts on the surface of the nanoparticles. Use of the precursor substances that do not provide the reaction mixture with ions, which could strongly adsorb on the surface of the nanoparticles formed in the reduction process, is particularly preferred.

**[0016]** The method of the invention can be used, in particular, in the synthesis of nanoparticles of metals and their alloys. Therefore, in the preferred embodiment, the precursor substance is a metal precursor or a mixture of metal precursors, preferably a metal salt or a mixture of different metal salts. The method of the invention is preferably used for the synthesis of metal nanoparticles selected from a group comprising palladium, silver, gold, platinum, ruthenium, osmium, iridium, rhodium, copper, nickel, cobalt and iron, as well as alloys thereof. More preferably, the method of the invention is used for synthesis of nanoparticles of noble metals, i.e. platinum, palladium, ruthenium, osmium, iridium, rhodium, silver and gold, and their alloys. In another, particularly preferred, embodiment copper nanoparticles are obtained.

**[0017]** Semiconductor nanoparticles, such as nanoparticles of copper (I) oxide ( $\text{Cu}_2\text{O}$ ) and palladium (II) oxide ( $\text{PdO}$ ), are also obtained by the method of the invention. In a particularly preferred embodiment  $\text{Cu}_2\text{O}$  nanoparticles are obtained.

**[0018]** A possibility to synthesize copper (I) oxide is very beneficial, because this material is a p-type semiconductor with a narrow band gap of  $\sim 2$  eV and attractive Fermi level position for the process of water photolysis. It is widely used as a photocathode material in the photoelectrolytic cells in heterojunction with zinc oxide, as well as in the technology lithium ion batteries. It should be emphasized that  $\text{Cu}_2\text{O}$  has to be coated with a thin layer of another semiconductor, which is resistant to reduction or photoreduction in aqueous solutions at the hydrogen evolution potential. It has recently been shown that  $\text{Cu}_2\text{O}$  can effectively be protected by a thin layer of  $\text{TiO}_2$  deposited by a method of atomic layer deposition (ALD) (A. Paracchino et al., Nature Materials, 10, 2011, 456-461).

**[0019]** Any substances whose reduction under specific reaction conditions results in nanoparticle formation can be used as a precursor substance in the method of the invention. The preferred precursor substances, whose solutions are used in the method of the invention, are salts selected from a group comprising  $\text{AgNO}_3$ ,  $\text{AgClO}_4$ ,  $\text{AgHSO}_4$ ,  $\text{Ag}_2\text{SO}_4$ ,  $\text{AgF}$ ,  $\text{AgBF}_4$ ,  $\text{AgPF}_6$ ,  $\text{CH}_3\text{COOAg}$ ,  $\text{AgCF}_3\text{SO}_3$ ,  $\text{CuCl}_2$ ,  $\text{Cu}(\text{NO}_3)_2$ ,  $\text{CuSO}_4$ ,  $\text{Cu}(\text{HSO}_4)_2$ ,  $\text{Cu}(\text{ClO}_4)_2$ ,  $\text{CuF}_2$ ,  $(\text{CHCOO})_2\text{Cu}$ ,  $\text{H}_2\text{PtCl}_6$ ,  $\text{H}_6\text{Cl}_2\text{N}_2\text{Pt}$ ,  $\text{PtCl}_2$ ,  $\text{PtBr}_2$ ,  $\text{K}_2[\text{PtCl}_4]$ ,  $\text{Na}_2[\text{PtCl}_4]$ ,  $\text{Li}_2[\text{PtCl}_4]$ ,  $\text{H}_2\text{Pt}(\text{OH})_6$ ,  $\text{Pt}(\text{NO}_3)_2$ ,  $[\text{Pt}(\text{NH}_3)_4]\text{Cl}_2$ ,  $[\text{Pt}(\text{NH}_3)_4](\text{HCO}_3)_2$ ,  $[\text{Pt}(\text{NH}_3)_4](\text{OAc})_2$ ,  $(\text{NH}_4)_2\text{PtBr}_6$ ,  $\text{K}_2\text{PtCl}_6$ ,  $\text{PtSO}_4$ ,  $\text{Pt}(\text{HSO}_4)_2$ ,  $\text{Pt}(\text{ClO}_4)_2$ ,  $\text{H}_2\text{PdCl}_6$ ,  $\text{H}_6\text{Cl}_2\text{N}_2\text{Pd}$ ,  $\text{PdCl}_2$ ,  $\text{PdBr}_2$ ,  $\text{K}_2[\text{PdCl}_4]$ ,  $\text{Na}_2[\text{PdCl}_4]$ ,  $\text{Li}_2[\text{PdCl}_4]$ ,  $\text{H}_2\text{Pd}(\text{OH})_6$ ,  $\text{Pd}(\text{NO}_3)_2$ ,  $[\text{Pd}(\text{NH}_3)_4]\text{Cl}_2$ ,  $[\text{Pd}(\text{NH}_3)_4](\text{HCO}_3)_2$ ,  $[\text{Pd}(\text{NH}_3)_4](\text{OAc})_2$ ,  $(\text{NH}_4)_2\text{PdBr}_6$ ,  $(\text{NH}_3)_2\text{PdCl}_6$ ,  $\text{PdSO}_4$ ,  $\text{Pd}(\text{HSO}_4)_2$ ,  $\text{Pd}(\text{ClO}_4)_2$ ,  $\text{HAuCl}_4$ ,  $\text{AuCl}_3$ ,  $\text{AuCl}$ ,  $\text{AuF}_3$ ,  $(\text{CH}_3)_2\text{SAuCl}$ ,  $\text{AuF}$ ,  $\text{AuCl}(\text{SC}_4\text{H}_8)$ ,  $\text{AuBr}$ ,  $\text{AuBr}_3$ ,  $\text{Na}_3\text{Au}(\text{S}_2\text{O}_3)_2$ ,  $\text{HAuBr}_4$ ,  $\text{K}[\text{Au}(\text{CN})_2]$ ,  $\text{CoF}_2$ ,  $\text{Co}(\text{NO}_3)_2$ ,  $\text{CoCl}_2$ ,  $\text{CoSO}_4$ ,  $\text{Co}(\text{HSO}_4)_2$ ,  $\text{Co}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Co}$ ,  $\text{CoBr}_2$ ,  $[\text{Co}(\text{NH}_3)_6]\text{Cl}_3$ ,  $[\text{CoCl}(\text{NH}_3)_5]\text{Cl}_2$ ,  $[\text{Co}(\text{NO}_2)(\text{NH}_3)_5]\text{Cl}_2$ ,  $\text{NiF}_2$ ,  $\text{Ni}(\text{NO}_3)_2$ ,  $\text{NiCl}_2$ ,  $\text{NiSO}_4$ ,  $\text{Ni}(\text{HSO}_4)_2$ ,  $\text{Ni}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Ni}$ ,  $\text{NiBr}_2$ ,  $\text{Ni}(\text{OH})\text{HSO}_4$ ,  $\text{Ni}(\text{OH})\text{Cl}$ ,  $\text{FeF}_2$ ,  $\text{Fe}(\text{NO}_3)_2$ ,  $\text{FeCl}_2$ ,  $\text{FeSO}_4$ ,  $\text{Fe}(\text{HSO}_4)_2$ ,  $\text{Fe}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Fe}$ ,  $\text{FeBr}_2$ ,  $\text{FeF}_3$ ,  $\text{Fe}(\text{NO}_3)_3$ ,  $\text{FeCl}_3$ ,  $\text{Fe}_2(\text{SO}_4)_3$ ,  $\text{Fe}(\text{HSO}_4)_3$ ,  $\text{Fe}(\text{ClO}_4)_3$ ,  $(\text{CHCOO})_3\text{Fe}$ ,  $\text{FeBr}_3$ ,  $\text{RuCl}_2((\text{CH}_3)_2\text{SO})_4$ ,  $\text{RuCl}_3$ ,  $[\text{Ru}(\text{NH}_3)_5(\text{N}_2)]\text{Cl}_2$ ,  $\text{Ru}(\text{NO}_3)_3$ ,  $\text{RuBr}_3$ ,  $\text{RuF}_3$ ,  $\text{Ru}(\text{ClO}_4)_3$ ,  $\text{Os}$ ,  $\text{OsI}_2$ ,  $\text{OsBr}_3$ ,  $\text{OsCl}_4$ ,  $\text{OsF}_5$ ,  $\text{OsF}_6$ ,  $\text{OsOF}_5$ ,  $\text{OsF}_7$ ,  $\text{IrF}_6$ ,  $\text{IrCl}_3$ ,  $\text{IrF}_4$ ,  $\text{IrF}_5$ ,  $\text{Ir}(\text{ClO}_4)_3$ ,  $\text{K}_3[\text{IrCl}_6]$ ,  $\text{K}_2[\text{IrCl}_6]$ ,  $\text{Na}_3[\text{IrCl}_6]$ ,  $\text{Na}_2[\text{IrCl}_6]$ ,  $\text{Li}_3[\text{IrCl}_6]$ ,  $\text{Li}_2[\text{IrCl}_6]$ ,  $[\text{Ir}(\text{NH}_3)_4\text{Cl}_2]\text{Cl}$ ,  $\text{RhF}_3$ ,  $\text{RhF}_4$ ,  $\text{RhCl}_3$ ,  $[\text{Rh}(\text{NH}_3)_5\text{Cl}]\text{Cl}_2$ ,  $\text{RhCl}[\text{P}(\text{C}_6\text{H}_5)_3]_3$ ,  $\text{K}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Na}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Li}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Rh}_2(\text{SO}_4)_3$ ,  $\text{Rh}(\text{HSO}_4)_3$  and  $\text{Rh}(\text{ClO}_4)_3$ , their hydrates or mixtures of these salts and/or hydrates. In the preferred embodiment, the precursor substance is selected from a group consisting of  $\text{Pd}(\text{NO}_3)_2$ ,  $\text{Cu}(\text{NO}_3)_2$ ,  $\text{HAuCl}_4$ ,  $\text{Pt}(\text{NO}_3)_2$  and  $\text{K}_2\text{PtCl}_4$ . In a further preferred embodiment the precursor substance is a mixture of  $\text{Pd}(\text{NO}_3)_2$  and  $\text{Pt}(\text{NO}_3)_2$ .

**[0020]** According to the invention a concentration of the precursor substance solution used in the method of the invention is preferably in the range from 1 mM to 1 M, and more preferably amounts to 5 or 10 mM.

**[0021]** Alternatively the precursor substances can be selected in a way resulting in synthesis of semiconductor nanoparticles, for example metal oxide nanoparticles.

**[0022]** In the method of the invention any substance can be used as a reducing agent, provided that under specific reaction conditions it is capable of reducing the precursor substance while being oxidized. The reducing agent used in the method of the invention is preferably selected from a group comprising hydrazine, hydrazine sulfate, hydrazine nitrate, ascorbic acid, sodium borohydride, sodium hypophosphite, lithium tetraethylborohydride, methanol, 1,2-hexadecanediol, hydroxylamine and dimethylborazane DMAB. Hydrazine is the particularly preferred reducing agent used in the method of the invention.

**[0023]** According to the invention a concentration of the reducing agent solution used in the method of the invention is preferably in the range from 0.5 mM to 4 M, and most preferably amounts to 20 mM.

**[0024]** The selection of the substance neutralizing the reducing agent is of particular importance. The substance neutralizing the reducing agent, also called the terminator, is designed to remove rapidly the reducing agent from the reaction system. Therefore, it preferably exhibits oxidizing properties. Not limiting to any theory, the Inventors have found that use of an oxidizing agent as the substance neutralizing the reducing agent is also preferred because it can lead to

control of the redox potential of the colloid solution, thus stabilizing the colloid dispersion: under higher potential the Coulomb repulsion of the positively charged nanoparticles exceeds the van der Waals forces of nanoparticle attraction. The selection of the redox potential determines the level of surface charge (the surface charge density of the metal/semiconductor). By alteration of the electrokinetic potential, it is possible to select conditions under which the colloid exhibits extremely high stability. At higher potentials oxidation of the surface of the newly formed nanoparticles takes place (i.e. oxides are formed on the nanoparticle surface), providing stability to the nanoparticles. Hydrolysis products of unreduced metal, hydroxides and hydrated oxides or hydroxysalts may also favor stabilization of the nanoparticles. The hydrated oxides, hydroxides and hydroxysalts do not adsorb strongly on the nanoparticle surface, therefore the said surface can be easily modified further. Oxide formation and/or surface adsorption of hydrated oxides may also prevent nanoparticle aggregation. The process of nanoparticle aggregation is unfavorable and makes further applications of the nanoparticles impossible.

**[0025]** A substance neutralizing the reducing agent used in the method of the invention is preferably selected from a group comprising hydrogen peroxide, oxygen, ozone and  $\text{NO}_2$ . More preferably, the substance neutralizing the reducing agent is supplied to the system in the form of a solution, and most preferably it is the hydrogen peroxide solution.

**[0026]** The choice of the neutralizing substance will also be influenced by properties of the metal of the nanoparticles. For example, the surface of platinum and gold nanoparticles cannot be oxidized using hydrogen peroxide. For this purpose a stronger oxidizing agent should be used, for example ozone.

**[0027]** A redox buffer can also be used as a substance neutralizing the reducing agent, wherein the said redox buffer comprises a redox pair whose oxidized (ox) and reduced (red) form concentration are comparable (i.e.  $\log([\text{ox}]/[\text{red}]) = \pm 2$ ). Example of such redox pairs can include:  $\text{Fe}(\text{CN})_6^{3-}/\text{Fe}(\text{CN})_6^{4-}$ ,  $\text{Fe}^{3+}/\text{Fe}^{2+}$ ,  $[\text{Co}(\text{bipy})_3]^{2+}/[\text{Co}(\text{bipy})_3]^{3+}$ ,  $\text{Co}(\text{phen})_3^{3+}/\text{Co}(\text{phen})_3^{2+}$ ,  $[\text{Ru}(\text{bipy})_3]^{3+}/[\text{Ru}(\text{bipy})_3]^{2+}$ ,  $[\text{Ru}(\text{NH}_3)_6]^{3+}/[\text{Ru}(\text{NH}_3)_6]^{2+}$ ,  $[\text{Ru}(\text{CN})_6]^{3-}/[\text{Ru}(\text{CN})_6]^{4-}$ ,  $\text{Fe}(\text{phen})_3^{3+}/\text{Fe}(\text{phen})_3^{2+}$  and  $\text{Ce}^{4+}/\text{Ce}^{3+}$ .

**[0028]** The use of a redox buffer comprising nicotinamide adenine dinucleotide (NADH - reduced form,  $\text{NAD}^+$  - oxidized form) is preferred for biomedical applications.

**[0029]** According to the invention a concentration of the solution of a substance neutralizing the reducing agent used in the method of the invention is preferably in the range from 0.1 mM to 10 M, and more preferably amounts to 35 mM or 40 mM or 9.8 M.

**[0030]** In the preferred embodiment the pH of the solution of a substance neutralizing the reducing agent is adjusted by addition of a buffer, acid or base. Selection of an appropriate pH is of particular importance for synthesis of base metal nanoparticles. In other preferred embodiment the pH of the reaction mixture and the final colloid solution can be adjusted by adding a solution of an acid or base to one, two or all solutions of the precursor substance, reducing agent and terminator used in the method of the invention.

**[0031]** It is also possible to supply the reducing agent to the reaction mixture in the gaseous form.

**[0032]** In the method of the invention, it is important to select the precursor substance, reducing agent and substance neutralizing the reducing agent so that they do not become a source of contamination for the newly formed nanoparticles, in particular the source of surfactants or other organic molecules, which during the reaction or afterwards could adsorb on the nanoparticle surface. It is, however, possible to use in the method of the invention salts of lower organic acids, such as acetates, as precursor substances.

**[0033]** Use of the system hydrazine (as a reducing agent) and hydrogen peroxide (as a substance neutralizing the reducing agent) is particularly preferred in the method of the invention, since as a result of hydrazine oxidation by hydrogen peroxide primarily only nitrogen and water are formed.

**[0034]** In the method of the invention the reduction reaction is carried out preferably in temperature in the range from 0 to  $100^\circ\text{C}$ , and most preferably in  $40^\circ\text{C}$ . The temperature is a significant factor, which influences the size of the synthesized nanoparticles. The inventors have shown that the increase in temperature results in the size increase of the nanoparticles synthesized by the method of the invention and at the same time widens the size distribution of the obtained nanoparticles.

**[0035]** In the preferred embodiment the particular tubing segments of the continuous flow system, through which the stream of the reagents, the reaction mixture and products flow in the flow system are either thermostated or maintained at the room temperature. More preferably, the particular tubing segments of the continuous flow system, through which the stream of the reagents, the reaction mixture and products flow are maintained at different temperatures. In the particularly preferred embodiment of the method of the invention, the stream of products is cooled down, most preferably to room temperature, after the substance neutralizing the reducing agent is supplied to the system.

**[0036]** Fig. 1a presents a continuous flow system, in which the reduction reaction is carried out in the thermostated region having specific temperature (Temp. 1), for example  $40^\circ\text{C}$ , whereas the stream of products is adjusted to room temperature (Temp. 2). Of course the reduction reaction in the method of the invention can be carried out in the room temperature. It is also possible to control the temperature of the product stream, in the form of the colloid solution of the homogenous nanoparticles, in a thermostat.

**[0037]** Fig. 1b presents a continuous flow system, in which in the first step the reduction reaction is carried out in the

thermostated region having specific temperature (Temp. 1), for example 40°C, in the second step the reduction reaction is carried out in the thermostated region having specific temperature (Temp. 2), for example 50°C, whereas the product stream in the form of the layered core-shell type nanoparticles is adjusted to room temperature (Temp. 3). Temperature Temp. 1 and Temp. 2 can be the same or different. It is also possible to control the temperature of the product stream in a thermostat.

**[0038]** In a particularly preferred embodiment the method is carried out in the aqueous environment, in which metal nanoparticles are formed as a result of reduction of metal aqua complexes.

**[0039]** The method of the invention is preferably carried out in a continuous flow system, in which the inner diameter of the tubes ranges from 2" to 1/64", preferably from 1/8" to 1/32". As tubing having greater diameter is employed, it is possible not only to use higher reagent concentration, but also to obtain colloid solution of nanoparticles of high concentration. Thus it is possible to use the method of the invention on a large scale. The method of the invention can also be used in the microflow systems, in which the diameter of the channels is several or several dozens micrometers in diameter.

**[0040]** The method of the invention is preferably carried out in the continuous flow system, in which the length of tubes, wherein the reduction reaction takes place, ranges from 1 cm to 5 m, more preferably from 40 cm to 60 cm.

**[0041]** In the preferred embodiment the reagent flow rate in the continuous flow system, wherein the method of the invention is carried out, ranges from 1 ml/h to 100 l/h, more preferably from 200 ml/h to 3200 ml/h.

**[0042]** The length of the tubes, in which the reduction reaction takes place, and the reagent flow rate in the continuous flow system are selected in such a manner, so that an appropriate reduction reaction time is ensured. Preferably the reduction reaction time ranges from 0.01 s to 1 h.

**[0043]** Most preferably, palladium nanoparticles are obtained by the method of the invention, wherein in the method 10 mM Pd(NO<sub>3</sub>)<sub>2</sub> is used as a precursor substance, 20 mM hydrazine is used as a reducing agent and 35 mM hydrogen peroxide is used as a substance neutralizing the reducing agent.

**[0044]** Alternatively copper (I) oxide nanoparticles are obtained by the method of the invention, wherein in the method 10 mM Cu(NO<sub>3</sub>)<sub>2</sub> is used as a precursor substance, 20 mM hydrazine is used as a reducing agent and 3.79 mM hydrogen peroxide is used as a substance neutralizing the reducing agent supplemented with 2.69 mM NaOH (pH≈12). The pH of the obtained nanoparticle colloid solution was about 7.

**[0045]** Moreover, gold nanoparticles are obtained by the method of the invention, wherein in the method 5 mM HAuCl<sub>4</sub> is used as a precursor substance, 3 mM hydrazine is used as a reducing agent and 9.8 M hydrogen peroxide is used as a substance neutralizing the reducing agent.

**[0046]** Platinum nanoparticles are also obtained by the method of the invention, wherein in the method 10 mM K<sub>2</sub>PtCl<sub>4</sub> is used as a precursor substance, 20 mM hydrazine is used as a reducing agent and 40 mM hydrogen peroxide is used as a substance neutralizing the reducing agent.

**[0047]** In a further embodiment homogeneous Pd/Pt alloy nanoparticles are obtained by the method of the invention as a result of the reduction reaction of the mixture of Pd(NO<sub>3</sub>)<sub>2</sub> and Pt(NO<sub>3</sub>)<sub>2</sub>, which is used as a precursor substance.

**[0048]** In another embodiment in the first step of the method of the invention the solution of Cu(NO<sub>3</sub>)<sub>2</sub> as a precursor substance undergoes the reduction reaction using hydrazine solution, which results in formation of the copper core, and in the second step to the reaction mixture Pd(NO<sub>3</sub>)<sub>2</sub> solution as a precursor substance is supplied, whose reduction results in formation of the palladium shells on the copper nanoparticles formed in step 1, and the reduction reaction is terminated by addition of hydrogen peroxide solution and a base, wherein the base concentration is sufficient to ensure neutral pH of the product stream.

**[0049]** In the method of the invention a stable nanoparticle colloid is obtained (stable even for a period longer than 4 months), preferably metal or metal alloy nanoparticle colloid, which is characterized by very high purity and high concentration of the reduced metal (even about 1000 ppm and higher). The concentration of the nanoparticles in the colloid can be controlled through the concentration of the reagents used, especially concentration of the precursor substance. For example, in case of 10 mM concentration of Pd(NO<sub>3</sub>)<sub>2</sub> the colloid solution was obtained, in which palladium content in the form of nanoparticles amounted to approximately 360 ppm.

**[0050]** The synthesized nanoparticles have diameters in the range from 1 to 50 nm, preferably 1.5 to 30 nm, more preferably 2 to 15 nm, and most preferably from 3 to 10 nm. Moreover, the method of the invention makes it possible to obtain nanostructures with specific sizes, because size distribution of the nanoparticles synthesized under specific reaction conditions is relatively narrow. The nanoparticles can be also fractionated from the colloid by centrifugation.

**[0051]** In the preferred embodiment the method of the invention comprises further a colloid nanoparticle centrifugation and/or drying step, wherein nanoparticle powder is obtained.

**[0052]** As a result of a specific reagent selection the product obtained by the method of the invention is a stable colloid of substantially pure nanoparticles or nanoparticles *per se*. The fact that the nanoparticles obtained by the method according to the invention are not contaminated by surfactants or other organic molecules enables their direct use (nanoparticles as such or in the form of the obtained colloids). Such nanoparticles, especially metal nanoparticles, are used *inter alia* as very effective heterogeneous catalysts. Modification of their surface with selected substances, such

as therapeutic substances, is also possible. Stable metal nanoparticle colloids can also be used as inks for printing elements to be applied in electronics or as material for SERS studies (especially, for example, Au, Ag, Cu) and in fuel cells as selective catalysts of oxygen reduction (especially nanoparticles of Pt, Pd and Pt/Pd alloys).

**[0053]** Significant purity of the nanostructured materials obtained by the method according to the invention enables their use in photoelectrochemical cells. This applies in particular to metal oxide semiconductor (MOS) nanoparticles. For example, iron (III) oxide is an attractive photoanode material (U. Björkstén et al., Chem. Mater., 1994, 6, 858-863), and copper (I) oxide is a very active photocathode material in cells of this type.

**[0054]** The method of the invention leads to synthesis of copper (I) oxide nanoparticles, which do not comprise surfactants and can be coated with a protective layer obtained, for example, in the process of atomic layer deposition (ALD), as discussed above. It is noteworthy, that until now in the state of the art no method of synthesis of pure  $\text{Cu}_2\text{O}$  have not been disclosed, whereas the surfactants exclude a possibility of using ALD for further nanoparticle surface modification.

**[0055]** Pure Pt and Pd nanoparticles can also find application in photoelectrochemical cells as catalysts of the reaction of hydrogen evolution/storage. Use of nanostructured metals of platinum group significantly improves the photocathode effectiveness. Nanoparticles of Cu and Au, which exhibit the surface plasmon resonance effect, can, in turn, be employed to increase the effectiveness of the photoelectrodes (R. Solarska et al., Angewandte Chem. - Int. Ed., 2010, 49 (43), 7980-7983) or as sensors operating based on a characteristic resonance frequency resulting from alteration of the dielectric environment of the nanoparticles (K.L. Kelly et al., J. Phys. Chem. B, 2003, 107 (3), 668-677). It should be underlined that for such application use of pure nanoparticles is required.

**[0056]** The nanoparticles obtained by the method of the invention can be used in medicine and as heterogeneous catalysts or their use in fuel cells and photoelectrochemical cells.

**[0057]** The above and other advantages and benefits will become more apparent based on the examples of the invention embodiments presented below.

#### BRIEF DESCRIPTION OF DRAWINGS

**[0058]** The subject of the invention was illustrated in a drawing, in which:

Figure 1a presents a scheme of the continuous flow system for synthesis of the substantially pure homogenous nanoparticles that is used in the method of the invention;

Figure 1b presents a scheme of the continuous flow system for synthesis of the substantially pure core-shell nanoparticles that is used in the method of the invention;

Figure 2 presents a TEM micrograph of palladium nanoparticles obtained in Example 1A;

Figure 3 presents a size distribution histogram of palladium nanoparticles obtained in Example 1A;

Figure 4 presents a representative chronovoltamperometric curve for palladium nanoparticles obtained in Example 1A;

Figure 5 presents representative size distribution histograms of palladium nanoparticles present in the supernatants after centrifuging a sample of the 16-day colloid obtained in Example 1A at 6 kRPM (Fig. 5a) and 15 kRPM (Fig. 5b), respectively;

Figure 6 presents a TEM micrograph of palladium nanoparticles obtained in Example 1B;

Figure 7 presents a TEM micrograph of palladium nanoparticles obtained in Example 1C;

Figure 8 presents a chronovoltamperometric curve for palladium nanoparticles obtained in Example 1C;

Figure 9 presents a chronovoltamperometric curve for  $\text{Cu}_2\text{O}$  nanoparticles obtained in Example 3;

Figure 10 presents a UV/VIS spectrum for  $\text{Cu}_2\text{O}$  nanoparticles obtained in Example 3;

Figure 11 presents a current-potential characteristics for  $\text{Cu}_2\text{O}$  nanoparticles obtained in Example 3 under chopped illumination;

Figure 12 presents a TEM micrograph of  $\text{Cu}_2\text{O}$  nanoparticles obtained in Example 3;

Figure 13 presents a TEM micrograph of gold nanoparticles obtained in Example 4;

Figure 14 presents X-ray diffraction patterns registered for  $\text{Cu}_2\text{O}$ , Au, Pt and Pd nanoparticles according to Example 8.

#### EXAMPLES

##### *Continuous flow system used in Examples*

**[0059]** Continuous flow system for synthesis of substantially pure nanoparticles used in the method of the invention is presented schematically on Fig. 1a i 1b. It is composed of a set of Teflon tubes, through which the reagents are pumped and the product in the form of the nanoparticle colloid is discharged. Pumps are an important element of this system because they ensure a fixed flow rate of the reagents throughout the system. The region, where reduction of a precursor substance takes place is thermostated.

## A list of the used reagents

## [0060]

- 5 • palladium: Pd(NO<sub>3</sub>)<sub>2</sub>·xH<sub>2</sub>O, 99.9%, *Alfa Aesar*
- hydrazine: N<sub>2</sub>H<sub>4</sub>·H<sub>2</sub>O, 50-60% concentration, *Aldrich*
- Perhydrol: hydrogen peroxide 30% solution, pure for analysis, *Chempur*
- copper: Cu(NO<sub>3</sub>)<sub>2</sub>·3H<sub>2</sub>O pure for analysis, *POCH*
- gold: HAuCl<sub>4</sub>, 99.99%, *Alfa Aesar*
- 10 • platinum: K<sub>2</sub>PtCl<sub>4</sub>, 99.99%, *Alfa Aesar*
- sodium hydroxide: NaOH, pure for analysis, *POCH*
- nitric acid: HNO<sub>3</sub> 65% pure for analysis, *POCH*
- sulfuric acid, 99.999%, *Sigma Aldrich*

15 **Example 1. Synthesis of palladium nanoparticles of controlled size and their properties characteristic**

[0061] A) Reduction reaction is carried out in the continuous flow system presented in Fig. 1a, in a Teflon tube having the inner diameter of 1/32" and length of 40 cm, wherein the flow rate of the reagents in the reaction tube is 200 ml/h.

20 [0062] Aqueous solution of 10 mM palladium (II) nitrate (Pd(NO<sub>3</sub>)<sub>2</sub>) is used to obtain a stable colloid of palladium nanoparticles. 20 mM aqueous solution of hydrazine is used as the reducing agent.

[0063] The reaction is carried out in temperature of 40°C, and 35 mM solution of hydrogen peroxide is used to terminate the reaction.

25 [0064] A stable black colloid of palladium nanoparticles is the product of the reaction. The metal concentration in the obtained colloid amounts to about 360 ppm. The colloid obtained is stable for a period of 4 months (or even longer) without a need for mixing and/or sonication in the ultrasonic bath.

[0065] A TEM micrograph of palladium nanoparticles obtained by the described method is presented in Fig. 2.

[0066] Diameter of the obtained palladium nanostructures ranges from 1.5 to 5 nm. A representative histogram of nanoparticle size distribution is presented in Fig. 3. By the method described in the present example nanoparticles having relatively narrow size distribution are obtained.

30 [0067] The purity for palladium nanoparticles was confirmed by electrochemical methods. A representative chrono-voltamperometric curve for the obtained palladium nanoparticles is presented in Fig. 4. The curve was recorded for palladium nanoparticles, after they were transferred to a gold electrode, in 0.5 M solution of sulfuric acid. The polarization rate was 5 mVs<sup>-1</sup>. The potential scale was presented in reference to the sulfate-mercury electrode.

35 [0068] Peaks that are clearly apparent at potential E = -0.43V indicate high purity of the material surface. Peaks related to the processes of hydrogen absorption and desorption from the nanoparticle depth are present at more cathodic potentials.

[0069] The presence of the hydrated oxides and/or palladium hydroxides at the surface of the newly formed palladium nanoparticles was also confirmed by the cyclic chronovoltamperometry (data not presented).

40 [0070] The colloid stability was investigated by comparing TEM micrographs of nanoparticles taken directly after reaction termination and 16 days after the nanoparticles were obtained (data not shown).

[0071] A possibility to fractionate the palladium nanoparticles based on their diameter was demonstrated by taking TEM micrographs of nanoparticles from the supernatant of the 16-day colloid after it was centrifuged at 6 kRPM and 15 kRPM, as presented in Fig. 5a and Fig. 5b, respectively. B) Reduction reaction is carried out in the continuous flow system presented in Fig. 1a, in a Teflon tube having the inner diameter of 1/32" and length of 40 cm, wherein the flow rate of the reagents in the reaction tube is 200 ml/h.

45 [0072] Aqueous solution of 10 mM palladium (II) nitrate (Pd(NO<sub>3</sub>)<sub>2</sub>) in 10 mM HNO<sub>3</sub> (pH=2) is used to obtain a stable colloid of palladium nanoparticles. 20 mM aqueous solution of hydrazine is used as the reducing agent.

[0073] The reaction is carried out in temperature of 40°C, and 40 mM solution of hydrogen peroxide is used to terminate the reaction.

50 [0074] A black colloid of palladium nanoparticles is the product of the reaction. Fig. 6 presents a TEM micrograph of palladium nanoparticles obtained under such conditions. The diameter of the obtained palladium nanostructures amounts to about 15 nm.

[0075] C) Reduction reaction is carried out in the continuous flow system presented in Fig. 1a, in a Teflon tube having the inner diameter of 1/16" and length of 60 cm, wherein the flow rate of the reagents in the reaction tube is 320 ml/h.

55 [0076] Aqueous solution of 1 mM palladium (II) nitrate (Pd(NO<sub>3</sub>)<sub>2</sub>) is used to obtain a stable colloid of palladium nanoparticles. 2 mM aqueous solution of hydrazine is used as the reducing agent.

[0077] The reaction is carried out in temperature of 80°C, and 12.8 mM solution of hydrogen peroxide is used to terminate the reaction.

[0078] A stable black colloid of palladium nanoparticles is the product of the reaction. The colloid obtained is stable for a period of 2 months (or even longer) without a need for mixing and/or sonication in the ultrasonic bath. Fig. 7 presents a TEM micrograph of palladium nanoparticles obtained under such conditions. The diameter of the obtained palladium nanostructures amounts to about 3 nm.

5 [0079] The purity for palladium nanoparticles was confirmed by electrochemical methods. A representative chronovoltamperometric curve for the obtained palladium nanoparticles is presented in Fig. 8. The curve was recorded for palladium nanoparticles, after they were transferred to a gold electrode, in 0.5 M solution of sulfuric acid. The polarization rate was 5 mVs<sup>-1</sup>. The potential scale was presented in reference to the sulfate-mercury electrode.

10 [0080] Peaks that are clearly apparent at potential E = -0.43V indicate high purity of the material surface. Peaks related to the processes of hydrogen absorption and desorption from the nanoparticle depth are present at more cathodic potentials. The separation of these processes from the reaction of hydrogen evolution (below E = -0.7 V) is indicative of very small nanoparticle volume.

#### Reference example. Synthesis of palladium nanoparticles without addition of hydrogen peroxide

15 [0081] Nanostructure synthesis was carried out as described in Example 1A, except that no hydrogen peroxide solution is added.

[0082] An unstable black colloid of palladium nanoparticles is the product of the reaction. The metal concentration in the obtained colloid is high. Nevertheless the colloid is not stable and the nanoparticles undergo aggregation.

#### Example 2. Synthesis of palladium nanoparticles having controlled size in a powder form

25 [0083] A portion of the colloid obtained in Example 1A-C was centrifuged, subsequently dried and black powder was obtained.

#### Example 3. Synthesis of copper (I) oxide nanoparticles of controlled size and their properties characteristic

[0084] Reduction reaction is carried out in the continuous flow system presented in Fig. 1a, in a Teflon tube having the inner diameter of 1/32" and length of 40 cm, wherein the flow rate of the reagents in the reaction tube is 200 ml/h.

30 [0085] Aqueous solution of 10 mM Cu(NO<sub>3</sub>)<sub>2</sub> is used to obtain a stable colloid of copper (I) oxide nanoparticles. 20 mM aqueous solution of hydrazine is used as the reducing agent. The reaction is carried out in temperature of 40°C, and 3.79 mM solution of hydrogen peroxide with addition of 2.69 mM NaOH (pH≈12) is used to terminate the reaction. The obtained colloid solution has pH≈7.

35 [0086] A stable orange-yellow colloid of copper (I) oxide nanoparticles is the product of the reaction. The colloid obtained is stable for a period of 2 weeks (or even longer) without a need for mixing and/or sonication in the ultrasonic bath.

[0087] A representative chronovoltamperometric curve for the obtained copper (I) oxide nanoparticles is presented in Fig. 9. The curve was recorded for copper (I) oxide nanoparticles, after they were transferred to a gold electrode, in a saturated solution of Na<sub>2</sub>CO<sub>3</sub>. The polarization rate was 5 mVs<sup>-1</sup>. The potential scale was presented in reference to the sulfate-mercury electrode.

40 [0088] Fig. 10 presents a UV/VIS spectrum recorded for copper (I) oxide nanoparticles. The spectrum shows an absorption band ( $\lambda_{\max}$  = 525 nm) corresponding to surface plasmon resonance (SPR) characteristic for copper nanoparticles. The exact band position depends on the nanoparticle size (see Mott et al., "Synthesis of Size-Controlled and Shaped Copper Nanoparticles", Langmuir, 2007, 23, 5740-5745).

45 [0089] Nanoparticles of copper (I) oxide obtained by the described method also exhibit photocatalytic activity. Fig. 11 presents a chronovoltamperometric curve (a cathodic part) recorded for 50 μg of Cu<sub>2</sub>O nanoparticles obtained directly from synthesis on fluorine-doped tin oxide (FTO) electrode in a buffered solution (pH=9) of 1M Na<sub>2</sub>SO<sub>4</sub>. During polarization at the rate of 1 mVs<sup>-1</sup>, the electrode was illuminated with a halogen lamp (100 mWcm<sup>-2</sup>) equipped with a shutter comprising a mechanic diaphragm triggered every 3 seconds. Thus obtained curve displays a characteristic oscillation between light and dark currents.

50 [0090] This experiment confirms the photocatalytic activity of copper (I) oxide nanoparticles. The obtained nanoparticles 'direct from synthesis' (i.e. without further treatment or purification) exhibit substantial photocurrents with an order of magnitude amounting to about 50μA cm<sup>-2</sup>.

55 [0091] Resulting from the significant purity of nanoparticles obtained by the method of the invention, a possibility of their coating with a protective layer of other semiconductors using an ALD method in combination with the photocatalytic activity, renders this material useful as an active photocathode material in the process of water photoelectrolysis.

[0092] Fig. 12 presents a TEM micrograph of Cu<sub>2</sub>O nanoparticles obtained under conditions described above.

**Example 4 Synthesis of gold nanoparticles**

[0093] Reduction reaction is carried out in the continuous flow system presented in Fig. 1a, in a Teflon tube having the inner diameter of 1/32" and length of 5 cm, wherein the flow rate of the reagents in the reaction tube is 100 ml/h.

5 [0094] Aqueous solution of 5 mM  $\text{HAuCl}_4$  is used to obtain a stable colloid of gold nanoparticles. 3 mM aqueous solution of hydrazine is used as the reducing agent.

[0095] The reaction is carried out in temperature of 40°C, and 9.8 M solution of hydrogen peroxide is used to terminate the reaction.

10 [0096] A stable pink colloid of gold nanoparticles is the product of the reaction. The metal concentration in the obtained colloid amounts to about 350 ppm. The colloid obtained is stable for a period of 5 weeks (or even longer) without a need for mixing and/or sonication in the ultrasonic bath.

[0097] A TEM micrograph of gold nanoparticles obtained by the described method is presented in Fig. 13. Diameter of the obtained gold nanostructures is about 50 nm.

**Example 5 Synthesis of platinum nanoparticles**

[0098] Reduction reaction is carried out in the system presented in Fig. 1a, in a Teflon tube having the inner diameter of 1/32" and length of 40 cm, wherein the flow rate of the reagents in the reaction tube is 100 ml/h.

20 [0099] Aqueous solution of 10 mM  $\text{K}_2\text{PtCl}_4$  is used to obtain a stable colloid of platinum nanoparticles. 20 mM aqueous solution of hydrazine is used as the reducing agent.

[0100] The reaction is carried out in temperature of 40°C, and 40 mM solution of hydrogen peroxide is used to terminate the reaction.

[0101] A stable black colloid of platinum nanoparticles is the product of the reaction.

**Example 6. Synthesis of alloy Pd/Pt nanoparticles**

[0102] Reduction reaction is carried out in the system presented in Fig. 1a, in a Teflon tube having the inner diameter of 1/32" and length of 40 cm, wherein the flow rate of the reagents in the reaction tube is 200 ml/h.

30 [0103] Aqueous solution of 5 mM palladium (II) nitrate ( $\text{Pd}(\text{NO}_3)_2$ ) and 5 mM platinum (II) nitrate ( $\text{Pt}(\text{NO}_3)_2$ ) is used to obtain a stable colloid of palladium - platinum alloy nanoparticles. 20 mM aqueous solution of hydrazine is used as the reducing agent.

[0104] The reaction is carried out in temperature of 40°C, and 35 mM solution of hydrogen peroxide is used to terminate the reaction.

35 [0105] A stable black colloid of Pd/Pt alloy nanoparticles is the product of the reaction. The colloid obtained is stable for a period of 2 weeks (or even longer) without a need for mixing and/or sonication in the ultrasonic bath.

**Example 7. Synthesis of core-shell type nanoparticles of copper and palladium**

40 [0106] Reduction reaction is carried out in the continuous flow system presented in Fig. 1b, in a Teflon tube having the inner diameter of 1/32" and length of 40 cm for each of the two steps, wherein the flow rate of the reagents in the reaction tube is 200 ml/h in the first step and 300 ml/h in the second step.

[0107] In the first step a solution of 10 mM  $\text{Cu}(\text{NO}_3)_2$  undergoes a reduction reaction using 20 mM aqueous solution of hydrazine as the reducing agent. In the second step a solution of 10 mM  $\text{Pd}(\text{NO}_3)_2$  is fed to the reaction mixture. 3.79 mM solution of hydrogen peroxide with addition of 2.69 mM NaOH is used to terminate the reaction.

45 [0108] A stable colloid of nanoparticles is the product of the reaction. It is stable for a period of 2 weeks (or even longer) without a need for mixing and/or sonication in the ultrasonic bath.

**Example 8. X-ray powder diffraction analysis of  $\text{Cu}_2\text{O}$ , Au, Pt and Pd nanoparticles**

50 [0109] The presence of metal oxides, such as PdO or  $\text{Cu}_2\text{O}$ , to the extent dependent on concentration of hydrogen peroxide and pH of the solution, was confirmed by X-ray powder diffraction.

[0110] The X-ray diffractograms were registered in Bragg-Brentano geometry with the X-Pert Philips diffractometer, using a tube with a copper anode, supplied with a current of 30 mA at voltage of 40 kV, and a curved graphite monochromator. The wavelength of radiation ( $\lambda_{\text{CuK}\alpha}$ ) amounted to 1.54178 Å. The diffraction lines were recorded by "step-scanning" method in the range from 20° to 140° 2 $\theta$  and 0.05° step.

55 [0111] Fig. 14 presents X-ray diffractograms for 10 nm palladium nanoparticles, 50 nm gold nanoparticles, 5 nm platinum nanoparticles and 10 nm copper (I) oxide nanoparticles.

[0112] Diffractograms indicate the presence of metal oxides and lack of other crystalline phases, apart from the metals

and oxides thereof. Moreover, broadening of half-width at maximum intensity (FWHM) is an evidence of nanocrystalline phase presence.


#### Example 9. Use of palladium nanoparticle colloid as a catalyst

[0113] In the present Example palladium nanoparticles synthesized in Example 1A were used as a catalyst in the Suzuki reaction.

[0114] The Suzuki reaction plays an important role in organic synthesis of polyalkenes, styrene derivatives and substituted diaryl compounds. Because of availability and low prices of phenylboronic acids, the Suzuki reaction is a method widely used by pharmaceutical industry [*Przemysł Chemiczny* 3/2012].

[0115] Palladium nanoparticles obtained by the method of the invention exhibit significantly higher catalytic activity in the Suzuki reaction than palladium nanoparticles stabilized by PVP. This is due to blocking of the catalyst active sites by PVP. A decrease in Pd catalyst activity together with the surfactant concentration increase was described by Narayanan et al. [Radha Narayanan and Mostafa A. El-Sayed, *J. Am. Chem. Soc.*, 2003, 125 (27), p. 8340-8347].

[0116] In the following reaction



after 1 hour of synthesis in 40°C and in the presence of Pd nanoparticles as a catalyst, significantly larger amounts of biphenyl were obtained in case of pure nanoparticles in comparison to the synthesis in which PVP stabilized nanoparticles are used.

[0117] This example shows that nanoparticles of the invention can be used directly as heterogenic catalysts.

#### Example 10. Modification of palladium and copper nanoparticles with paracetamol

[0118] Palladium nanoparticles obtained in Example 1A and copper nanoparticles obtained in Example 3 were incubated in paracetamol solution for 1 day, without their prior purification.

[0119] After rinsing the nanoparticles were analyzed by spectroscopic means and the presence of paracetamol adsorbed at the nanoparticle surface was demonstrated.

[0120] This example shows that nanoparticles obtained by the method of the invention can be modified directly after synthesis with therapeutic substances and used in treatment.

#### Claims

1. A method of synthesis of pure nanoparticles, on the surface of which neither surfactants nor other organic molecules are adsorbed, of controlled size in a continuous-flow system, wherein said continuous-flow system comprises tubing, in which a stream of reagents and products flows in a continuous manner, and wherein said method comprises at least one step, in which a precursor substance solution undergoes the reduction reaction using a reducing agent solution and nanoparticles are produced, **characterized in that** the reduction reaction is terminated after the last step by adding a substance neutralizing the reducing agent and a nanoparticle colloid is produced.
2. The method of claim 1, wherein the method comprises one step, in which the precursor substance solution undergoes the reduction reaction using the reducing agent solution and homogeneous nanoparticles are obtained.
3. The method of claim 1, wherein the method comprises at least two steps, in which the precursor substance solution undergoes the reduction reaction using the reducing agent solution and layered nanoparticles of core-shell type are obtained.
4. The method of one of claims 1-3, wherein the precursor substance is a metal precursor or a mixture of metal precursors.
5. The method of claim 4, wherein the metal precursor is a metal salt or a mixture of different metal salts.
6. The method of claim 4 or 5, wherein the metal is selected from a group comprising palladium, silver, gold, platinum, ruthenium, osmium, iridium, rhodium, nickel, cobalt, copper and iron.

7. The method of one of claims 1 - 6, wherein the precursor substance is a salt selected from a group comprising AgNO<sub>3</sub>, AgClO<sub>4</sub>, AgHSO<sub>4</sub>, Ag<sub>2</sub>SO<sub>4</sub>, AgF, AgBF<sub>4</sub>, AgPF<sub>6</sub>, CH<sub>3</sub>COOAg, AgCF<sub>3</sub>SO<sub>3</sub>, CuCl<sub>2</sub>, Cu(NO<sub>3</sub>)<sub>2</sub>, CuSO<sub>4</sub>, Cu(HSO<sub>4</sub>)<sub>2</sub>, Cu(ClO<sub>4</sub>)<sub>2</sub>, CuF<sub>2</sub>, (CHCOO)<sub>2</sub>Cu, H<sub>2</sub>PtCl<sub>6</sub>, H<sub>6</sub>Cl<sub>2</sub>N<sub>2</sub>Pt, PtCl<sub>2</sub>, PtBr<sub>2</sub>, K<sub>2</sub>[PtCl<sub>4</sub>], Na<sub>2</sub>[PtCl<sub>4</sub>], Li<sub>2</sub>[PtCl<sub>4</sub>], H<sub>2</sub>Pt(OH)<sub>6</sub>, Pt(NO<sub>3</sub>)<sub>2</sub>, [Pt(NH<sub>3</sub>)<sub>4</sub>]Cl<sub>2</sub>, [Pt(NH<sub>3</sub>)<sub>4</sub>](HCO<sub>3</sub>)<sub>2</sub>, [Pt(NH<sub>3</sub>)<sub>4</sub>](OAc)<sub>2</sub>, (NH<sub>4</sub>)<sub>2</sub>PtBr<sub>6</sub>, K<sub>2</sub>PtCl<sub>6</sub>, PtSO<sub>4</sub>, Pt(HSO<sub>4</sub>)<sub>2</sub>, Pt(ClO<sub>4</sub>)<sub>2</sub>, H<sub>2</sub>PdCl<sub>6</sub>, H<sub>6</sub>Cl<sub>2</sub>N<sub>2</sub>Pd, PdCl<sub>2</sub>, PdBr<sub>2</sub>, K<sub>2</sub>[PdCl<sub>4</sub>], Na<sub>2</sub>[PdCl<sub>4</sub>], Li<sub>2</sub>[PdCl<sub>4</sub>], H<sub>2</sub>Pd(OH)<sub>6</sub>, Pd(NO<sub>3</sub>)<sub>2</sub>, [Pd(NH<sub>3</sub>)<sub>4</sub>]Cl<sub>2</sub>, [Pd(NH<sub>3</sub>)<sub>4</sub>](HCO<sub>3</sub>)<sub>2</sub>, [Pd(NH<sub>3</sub>)<sub>4</sub>](OAc)<sub>2</sub>, (NH<sub>4</sub>)<sub>2</sub>PdBr<sub>6</sub>, (NH<sub>3</sub>)<sub>2</sub>PdCl<sub>6</sub>, PdSO<sub>4</sub>, Pd(HSO<sub>4</sub>)<sub>2</sub>, Pd(ClO<sub>4</sub>)<sub>2</sub>, HAuCl<sub>4</sub>, AuCl<sub>3</sub>, AuCl, AuF<sub>3</sub>, (CH<sub>3</sub>)<sub>2</sub>SAuCl, AuF, AuCl(SC<sub>4</sub>H<sub>8</sub>), AuBr, AuBr<sub>3</sub>, Na<sub>3</sub>Au(S<sub>2</sub>O<sub>3</sub>)<sub>2</sub>, HAuBr<sub>4</sub>, K[Au(CN)<sub>2</sub>], CoF<sub>2</sub>, Co(NO<sub>3</sub>)<sub>2</sub>, CoCl<sub>2</sub>, CoSO<sub>4</sub>, Co(HSO<sub>4</sub>)<sub>2</sub>, Co(ClO<sub>4</sub>)<sub>2</sub>, (CHCOO)<sub>2</sub>Co, CoBr<sub>2</sub>, [Co(NH<sub>3</sub>)<sub>6</sub>]Cl<sub>3</sub>, [CoCl(NH<sub>3</sub>)<sub>5</sub>]Cl<sub>2</sub>, [Co(NO<sub>2</sub>)(NH<sub>3</sub>)<sub>5</sub>]Cl<sub>2</sub>, NiF<sub>2</sub>, Ni(NO<sub>3</sub>)<sub>2</sub>, NiCl<sub>2</sub>, NiSO<sub>4</sub>, Ni(HSO<sub>4</sub>)<sub>2</sub>, Ni(ClO<sub>4</sub>)<sub>2</sub>, (CHCOO)<sub>2</sub>Ni, NiBr<sub>2</sub>, Ni(OH)HSO<sub>4</sub>, Ni(OH)Cl, FeF<sub>2</sub>, Fe(NO<sub>3</sub>)<sub>2</sub>, FeCl<sub>2</sub>, FeSO<sub>4</sub>, Fe(HSO<sub>4</sub>)<sub>2</sub>, Fe(ClO<sub>4</sub>)<sub>2</sub>, (CHCOO)<sub>2</sub>Fe, FeBr<sub>2</sub>, FeF<sub>3</sub>, Fe(NO<sub>3</sub>)<sub>3</sub>, FeCl<sub>3</sub>, Fe<sub>2</sub>(SO<sub>4</sub>)<sub>3</sub>, Fe(HSO<sub>4</sub>)<sub>3</sub>, Fe(ClO<sub>4</sub>)<sub>3</sub>, (CHCOO)<sub>3</sub>Fe, FeBr<sub>3</sub>, RuCl<sub>2</sub>((CH<sub>3</sub>)<sub>2</sub>SO)<sub>4</sub>, RuCl<sub>3</sub>, [Ru(NH<sub>3</sub>)<sub>5</sub>(N<sub>2</sub>)]Cl<sub>2</sub>, Ru(NO<sub>3</sub>)<sub>3</sub>, RuBr<sub>3</sub>, RuF<sub>3</sub>, Ru(ClO<sub>4</sub>)<sub>3</sub>, OsI, OsI<sub>2</sub>, OsBr<sub>3</sub>, OsCl<sub>4</sub>, OsF<sub>5</sub>, OsF<sub>6</sub>, OsOF<sub>5</sub>, OsF<sub>7</sub>, IrF<sub>6</sub>, IrCl<sub>3</sub>, IrF<sub>4</sub>, IrF<sub>5</sub>, Ir(ClO<sub>4</sub>)<sub>3</sub>, K<sub>3</sub>[IrCl<sub>6</sub>], K<sub>2</sub>[IrCl<sub>6</sub>], Na<sub>3</sub>[IrCl<sub>6</sub>], Na<sub>2</sub>[IrCl<sub>6</sub>], Li<sub>3</sub>[IrCl<sub>6</sub>], Li<sub>2</sub>[IrCl<sub>6</sub>], [Ir(NH<sub>3</sub>)<sub>4</sub>Cl<sub>2</sub>]Cl, RhF<sub>3</sub>, RhF<sub>4</sub>, RhCl<sub>3</sub>, [Rh(NH<sub>3</sub>)<sub>5</sub>Cl]Cl<sub>2</sub>, RhCl[P(C<sub>6</sub>H<sub>5</sub>)<sub>3</sub>]<sub>3</sub>, K[Rh(CO)<sub>2</sub>Cl<sub>2</sub>], Na[Rh(CO)<sub>2</sub>Cl<sub>2</sub>], Li[Rh(CO)<sub>2</sub>Cl<sub>2</sub>], Rh<sub>2</sub>(SO<sub>4</sub>)<sub>3</sub>, Rh(HSO<sub>4</sub>)<sub>3</sub> and Rh(ClO<sub>4</sub>)<sub>3</sub>, their hydrates or mixtures of these salts and/or hydrates.
8. The method of one of claims 1 - 7, wherein the reducing agent is selected from a group comprising hydrazine, ascorbic acid, sodium borohydride, sodium hypophosphite, lithium tetraethylborohydride, methanol, 1,2-hexadecanediol, hydroxylamine and dimethylborazane DMAB.
9. The method of one of claims 1 - 8, wherein the substance neutralizing the reducing agent is selected from a group comprising hydrogen peroxide, oxygen, ozone, NO<sub>2</sub> and a redox buffer.
10. The method of one of claims 1 - 9, wherein the particular tubing segments of the continuous flow system, through which the stream of the reagents, the reaction mixture and products flows, are maintained at different temperatures.
11. The method of one of claims 1, 2, 4 - 10, wherein the precursor substance is Pd(NO<sub>3</sub>)<sub>2</sub>, the reducing agent is hydrazine, and the substance neutralizing the reducing agent is hydrogen peroxide.
12. The method of one of claims 1, 2, 4 - 10, wherein precursor substance is Cu(NO<sub>3</sub>)<sub>2</sub>, the reducing agent is hydrazine, and the substance neutralizing the reducing agent is hydrogen peroxide, wherein the solution of the substance neutralizing the reducing agent further comprises NaOH.
13. The method of one of claims 1, 3 - 10, wherein in the first step the solution of the precursor substance Cu(NO<sub>3</sub>)<sub>2</sub> undergoes the reduction reaction using hydrazine solution, which results in formation of the copper core, and in the second step to the reaction mixture the solution of the precursor substance Pd(NO<sub>3</sub>)<sub>2</sub> is supplied, whose reduction results in formation of the palladium shells on the copper nanoparticles formed in the first step, and the reduction reaction is terminated by addition of hydrogen peroxide solution and a base, wherein the base concentration is sufficient to ensure neutral pH of the product stream.
14. The method of one of claims 1, 2, 4 - 10, wherein the precursor substance is a mixture of Pd(NO<sub>3</sub>)<sub>2</sub> and Pt(NO<sub>3</sub>)<sub>2</sub>, whose reduction results in formation of homogenous nanoparticles of Pd/Pt alloy.
15. The method of one of claims 1 - 10, wherein the substance neutralizing the reducing agent is a redox buffer having a potential suitable for an under-potential reduction of the metal outer layer on the metal core.
16. The method of one of claims 1 - 15, wherein the method comprises further a step of colloid nanoparticle centrifugation and/or drying, wherein nanoparticle powder is obtained.

## Patentansprüche

1. Verfahren zur Synthese von reinen Nanopartikeln, auf deren Oberfläche weder Tenside noch andere organische Moleküle adsorbiert werden, mit kontrollierter Größe, in einem kontinuierlichen Durchflusssystem, wobei das Durchflusssystem eine Verschlauchung umfasst, worin der Strom von Reagenzien und Produkten in einer kontinuierlichen Weise fließt, und wobei das genannte Verfahren mindestens einen Schritt umfasst, bei dem eine Vorstufensubstanzlösung der Reduktionsreaktion unter Verwendung von einer Reduktionsmittellösung unterliegt und wobei Nanopartikeln hergestellt werden, **dadurch gekennzeichnet, dass** die Reduktionsreaktion nach dem letzten Schritt

## EP 2 785 483 B1

durch Zugabe einer das Reduktionsmittel neutralisierenden Substanz beendet wird und ein Nanopartikelkolloid wird hergestellt.

- 5 2. Das Verfahren nach Anspruch 1, wobei das Verfahren einen Schritt umfasst, bei dem die Vorstufensubstanzlösung der Reduktionsreaktion unter Verwendung von der Reduktionsmittellösung unterliegt und homogene Nanopartikel werden erhalten.
- 10 3. Das Verfahren nach Anspruch 1, wobei das Verfahren mindestens zwei Stufen umfasst, worin die Vorstufensubstanzlösung der Reduktionsreaktion unter Verwendung von der Reduktionsmittellösung unterliegt und geschichtete Nanopartikel vom Kern-Hülle-Typ werden erhalten.
- 15 4. Das Verfahren nach einem der Ansprüche 1-3, wobei die Vorstufensubstanz eine Metallvorstufe oder eine Mischung von Metallvorstufen ist.
- 20 5. Das Verfahren nach Anspruch 4, wobei die Metallvorstufe ein Metallsalz oder eine Mischung von verschiedenen Metallsalzen ist.
- 25 6. Das Verfahren nach Anspruch 4 oder 5, wobei das Metall aus einer Gruppe umfassend Palladium, Silber, Gold, Platin, Ruthenium, Osmium, Iridium, Rhodium, Nickel, Kobalt, Kupfer und Eisen ausgewählt ist.
- 30 7. Das Verfahren nach einem der Ansprüche 1-6, wobei die Vorstufensubstanz ein Salz, aus einer Gruppe umfassend  $\text{AgNO}_3$ ,  $\text{AgIO}_4$ ,  $\text{AgHSO}_4$ ,  $\text{Ag}_2\text{SO}_4$ ,  $\text{AgF}$ ,  $\text{AgBF}_4$ ,  $\text{AgPF}_6$ ,  $\text{CH}_3\text{COOAg}$ ,  $\text{AgCF}_3\text{SO}_3$ ,  $\text{CuCl}_2$ ,  $\text{Cu}(\text{NO}_3)_2$ ,  $\text{CuSO}_4$ ,  $\text{Cu}(\text{HSO}_4)_2$ ,  $\text{Cu}(\text{ClO}_4)_2$ ,  $\text{CuF}_2$ ,  $(\text{CHCOO})_2\text{Cu}$ ,  $\text{H}_2\text{PtCl}_6$ ,  $\text{H}_6\text{Cl}_2\text{N}_2\text{Pt}$ ,  $\text{PtCl}_2$ ,  $\text{PtBr}_2$ ,  $\text{K}_2[\text{PtCl}_4]$ ,  $\text{Na}_2[\text{PtCl}_4]$ ,  $\text{Lb}[\text{PtCl}_4]$ ,  $\text{H}_2\text{Pt}(\text{OH})_6$ ,  $\text{Pt}(\text{NO}_3)_2$ ,  $[\text{Pt}(\text{NH}_3)_4]\text{Cl}_2$ ,  $[\text{Pt}(\text{NH}_3)_4](\text{HCO}_3)_2$ ,  $[\text{Pt}(\text{NH}_3)_4](\text{OAc})_2$ ,  $(\text{NH}_4)_2\text{PtBr}_6$ ,  $\text{K}_2\text{PtCl}_6$ ,  $\text{PtSO}_4$ ,  $\text{Pt}(\text{HSO}_4)_2$ ,  $\text{Pt}(\text{ClO}_4)_2$ ,  $\text{H}_2\text{PdCl}_6$ ,  $\text{H}_6\text{Cl}_2\text{N}_2\text{Pd}$ ,  $\text{PdCl}_2$ ,  $\text{PdBr}_2$ ,  $\text{K}_2[\text{PdCl}_4]$ ,  $\text{Na}_2[\text{PdCl}_4]$ ,  $\text{Li}_2[\text{PdCl}_4]$ ,  $\text{H}_2\text{Pd}(\text{OH})_6$ ,  $\text{Pd}(\text{NO}_3)_2$ ,  $[\text{Pd}(\text{NH}_3)_4]\text{Cl}_2$ ,  $[\text{Pd}(\text{NH}_3)_4](\text{HCO}_3)_2$ ,  $[\text{Pd}(\text{NH}_3)_4](\text{OAc})_2$ ,  $(\text{NH}_4)_2\text{PdBr}_6$ ,  $(\text{NH}_3)_2\text{PdCl}_6$ ,  $\text{PdSO}_4$ ,  $\text{Pd}(\text{HSO}_4)_2$ ,  $\text{Pd}(\text{ClO}_4)_2$ ,  $\text{HauCl}_4$ ,  $\text{AuCl}_3$ ,  $\text{AuCl}$ ,  $\text{AuF}_3$ ,  $(\text{CH}_3)_2\text{SAuCl}$ ,  $\text{AuF}$ ,  $\text{AuCl}(\text{SC}_4\text{H}_8)$ ,  $\text{AuBr}$ ,  $\text{AuBr}_3$ ,  $\text{Na}_3\text{Au}(\text{S}_2\text{O}_3)_2$ ,  $\text{HAuBr}_4$ ,  $\text{K}[\text{Au}(\text{CN})_2]$ ,  $\text{CoF}_2$ ,  $\text{Co}(\text{NO}_3)_2$ ,  $\text{CoCl}_2$ ,  $\text{CoSO}_4$ ,  $\text{Co}(\text{HSO}_4)_2$ ,  $\text{Co}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Co}$ ,  $\text{CoBr}_2$ ,  $[\text{Co}(\text{NH}_3)_6]\text{Cl}_3$ ,  $[\text{CoCl}(\text{NH}_3)_5]\text{Cl}_2$ ,  $[\text{Co}(\text{NO}_2)(\text{NH}_3)_5]\text{Cl}_2$ ,  $\text{NiF}_2$ ,  $\text{Ni}(\text{NO}_3)_2$ ,  $\text{NiCl}_2$ ,  $\text{NiSO}_4$ ,  $\text{Ni}(\text{HSO}_4)_2$ ,  $\text{Ni}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Ni}$ ,  $\text{NiBr}_2$ ,  $\text{Ni}(\text{OH})\text{HSO}_4$ ,  $\text{Ni}(\text{OH})\text{Cl}$ ,  $\text{FeF}_2$ ,  $\text{Fe}(\text{NO}_3)_2$ ,  $\text{FeCl}_2$ ,  $\text{FeSO}_4$ ,  $\text{Fe}(\text{HSO}_4)_2$ ,  $\text{Fe}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Fe}$ ,  $\text{FeBr}_2$ ,  $\text{FeF}_3$ ,  $\text{Fe}(\text{NO}_3)_3$ ,  $\text{FeCl}_3$ ,  $\text{Fe}_2(\text{SO}_4)_3$ ,  $\text{Fe}(\text{HSO}_4)_3$ ,  $\text{Fe}(\text{ClO}_4)_3$ ,  $(\text{CHCOO})_3\text{Fe}$ ,  $\text{FeBr}_3$ ,  $\text{RuCl}_2((\text{CH}_3)_2\text{SO})_4$ ,  $\text{RuCl}_3$ ,  $[\text{Ru}(\text{NH}_3)_5(\text{N}_2)]\text{Cl}_2$ ,  $\text{Ru}(\text{NO}_3)_3$ ,  $\text{RuBr}_3$ ,  $\text{RuF}_3$ ,  $\text{Ru}(\text{ClO}_4)_3$ ,  $\text{OsI}$ ,  $\text{OsI}_2$ ,  $\text{OsBr}_3$ ,  $\text{OsCl}_4$ ,  $\text{OsF}_5$ ,  $\text{OsF}_6$ ,  $\text{OsOF}_5$ ,  $\text{OsF}_7$ ,  $\text{IrF}_6$ ,  $\text{IrCl}_3$ ,  $\text{IrF}_4$ ,  $\text{IrF}_5$ ,  $\text{Ir}(\text{ClO}_4)_3$ ,  $\text{K}_3[\text{IrCl}_6]$ ,  $\text{K}_2[\text{IrCl}_6]$ ,  $\text{Na}_3[\text{IrCl}_6]$ ,  $\text{Na}_2[\text{IrCl}_6]$ ,  $\text{Li}_3[\text{IrCl}_6]$ ,  $\text{Li}_2[\text{IrCl}_6]$ ,  $[\text{Ir}(\text{NH}_3)_4]\text{Cl}_2$ ,  $\text{RhF}_3$ ,  $\text{RhF}_4$ ,  $\text{RhCl}_3$ ,  $[\text{Rh}(\text{NH}_3)_5\text{Cl}]\text{Cl}_2$ ,  $\text{RhCl}[\text{P}(\text{C}_6\text{H}_5)_3]_3$ ,  $\text{K}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Na}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Li}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Rh}_2(\text{SO}_4)_3$ ,  $\text{Rh}(\text{HSO}_4)_3$  und  $\text{Rh}(\text{ClO}_4)_3$ , ihrer Hydrate oder Mischungen dieser Salze und/oder Hydrate, ausgewählt ist.
- 35 8. Das Verfahren nach einem der Ansprüche 1-7, wobei das Reduktionsmittel aus einer Gruppe umfassend Hydrazin, Ascorbinsäure, Natriumborhydrid, Natriumhypophosphit, Lithiumtetraethylborhydrid, Methanol, 1,2-Hexadecandiol, Hydroxylamin und Dimethylborazan DMAB ausgewählt ist.
- 40 9. Das Verfahren nach einem der Ansprüche 1-8, wobei die das Reduktionsmittel neutralisierende Substanz aus einer Gruppe umfassend Wasserstoffperoxid, Sauerstoff, Ozon,  $\text{NO}_2$  und ein Redox-Puffer ausgewählt ist.
- 45 10. Das Verfahren nach einem der Ansprüche 1 - 9, wobei einzelne Verschlauchungsabschnitte des Durchflusssystems, durch die der Strom von Reagenzien, das Reaktionsgemisch und Produkte fließen, bei unterschiedlichen Temperaturen gehalten werden.
- 50 11. Das Verfahren nach einem der Ansprüche 1, 2, 4 - 10, wobei die Vorstufensubstanz  $\text{Pd}(\text{NO}_3)_2$  ist, das Reduktionsmittel Hydrazin ist, und die das Reduktionsmittel neutralisierende Substanz Wasserstoffperoxid ist.
- 55 12. Das Verfahren nach einem der Ansprüche 1, 2, 4 - 10, wobei die Vorstufensubstanz  $\text{Cu}(\text{NO}_3)_2$  ist, das Reduktionsmittel Hydrazin ist, und die das Reduktionsmittel neutralisierende Substanz Wasserstoffperoxid ist, wobei ferner die Lösung von der das Reduktionsmittel neutralisierenden Substanz  $\text{NaOH}$  enthält.
13. Das Verfahren nach einem der Ansprüche 1, 3 - 10, wobei im ersten Schritt die Lösung von der Vorstufensubstanz  $\text{Cu}(\text{NO}_3)_2$  der Reduktionsreaktion unter Verwendung von der Hydrazinlösung unterliegt, was zur Bildung des Kupferkernes führt, im zweiten Schritt wird zu dem Reaktionsgemisch die Lösung von der Vorstufensubstanz  $\text{Pd}(\text{NO}_3)_2$  zugeführt, deren Reduktion zur Bildung der Palladium-Hülle auf den in dem ersten Schritt gebildeten Kupfer-Nano-

partikeln führt, und die Reduktionsreaktion durch Zugabe von der Wasserstoffperoxid-Lösung und einer Base beendet wird, wobei die Konzentration der Base ausreichend ist, um die neutrale pH-Wert des Produktstroms zu gewährleisten.

- 5 14. Das Verfahren nach einem der Ansprüche 1, 2, 4 - 10, wobei die Vorstufensubstanz eine Mischung von  $\text{Pd}(\text{NO}_3)_2$  und  $\text{Pt}(\text{NO}_3)_2$  ist, deren Reduktion zur Bildung homogener Nanopartikeln von der Legierung Pd/Pt führt.
- 15 15. Das Verfahren nach einem der Ansprüche 1 - 10, wobei die das Reduktionsmittel neutralisierende Substanz ein Redox-Puffer mit einem Potential geeignet für eine Unterpotential-Reduktion der Metall-Außenschicht auf dem Metallkern ist.
- 10 16. Das Verfahren nach einem der Ansprüche 1 - 15, wobei das Verfahren ferner einen Schritt der Zentrifugation und/oder Trocknen von kolloiden Nanopartikeln umfasst, wobei ein Nanopartikelpulver erhalten wird.

15

### Revendications

1. Méthode de synthèse de nanoparticules pures, sur la surface desquelles ni tensioactifs ni d'autres molécules organiques ne sont pas adsorbés, de taille contrôlée dans un système à écoulement continu, dans laquelle ledit système à écoulement continu comprend un tube dans lequel un flux de réactifs et de produits s'écoule de manière continue, et dans laquelle ladite méthode comprend au moins une étape dans laquelle une solution de substance précurseur est soumise à la réaction de réduction en utilisant une solution d'agent réducteur, et des nanoparticules sont produites, **caractérisée en ce que** la réaction de réduction est terminée après la dernière étape par addition d'une substance neutralisant l'agent réducteur, et un colloïde de nanoparticules est produit.
- 20 2. Méthode selon la revendication 1, dans laquelle la méthode comprend une étape, dans laquelle la solution de substance précurseur est soumise à la réaction de réduction en utilisant la solution d'agent réducteur, et des nanoparticules homogènes sont obtenues.
- 30 3. Méthode selon la revendication 1, dans laquelle la méthode comprend au moins deux étapes, dans lesquelles la solution de substance précurseur est soumise à la réaction de réduction en utilisant la solution d'agent réducteur, et des nanoparticules en couches de type noyau-coquille sont obtenues.
- 35 4. Méthode selon l'une des revendications 1 - 3, dans laquelle la substance précurseur est un précurseur métallique ou un mélange de précurseurs métalliques.
5. Méthode selon la revendication 4, dans laquelle le précurseur métallique est un sel métallique ou un mélange de différents sels métalliques.
- 40 6. Méthode selon la revendication 4 ou 5, dans laquelle le métal est choisi dans un groupe comprenant le palladium, l'argent, l'or, le platine, le ruthénium, l'osmium, l'iridium, le rhodium, le nickel, le cobalt, le cuivre et le fer.
7. Méthode selon l'une des revendications 1 - 6, dans laquelle la substance précurseur est un sel choisi dans un groupe comprenant  $\text{AgNO}_3$ ,  $\text{AgClO}_4$ ,  $\text{AgHSO}_4$ ,  $\text{Ag}_2\text{SO}_4$ ,  $\text{AgF}$ ,  $\text{AgBF}_4$ ,  $\text{AgPF}_6$ ,  $\text{CH}_3\text{COOAg}$ ,  $\text{AgCF}_3\text{SO}_3$ ,  $\text{CuCl}_2$ ,  $\text{Cu}(\text{NO}_3)_2$ ,  $\text{CuSO}_4$ ,  $\text{Cu}(\text{HSO}_4)_2$ ,  $\text{Cu}(\text{ClO}_4)_2$ ,  $\text{CuF}_2$ ,  $(\text{CHCOO})_2\text{Cu}$ ,  $\text{H}_2\text{PtCl}_6$ ,  $\text{H}_6\text{Cl}_2\text{N}_2\text{Pt}$ ,  $\text{PtCl}_2$ ,  $\text{PtBr}_2$ ,  $\text{K}_2[\text{PtCl}_4]$ ,  $\text{Na}_2[\text{PtCl}_4]$ ,  $\text{Li}_2[\text{PtCl}_4]$ ,  $\text{H}_2\text{Pt}(\text{OH})_6$ ,  $\text{Pt}(\text{NO}_3)_2$ ,  $[\text{Pt}(\text{NH}_3)_4]\text{Cl}_2$ ,  $[\text{Pt}(\text{NH}_3)_4](\text{HCO}_3)_2$ ,  $[\text{Pt}(\text{NH}_3)_4](\text{OAc})_2$ ,  $(\text{NH}_4)_2\text{PtBr}_6$ ,  $\text{K}_2\text{PtCl}_6$ ,  $\text{PtSO}_4$ ,  $\text{Pt}(\text{HSO}_4)_2$ ,  $\text{Pt}(\text{ClO}_4)_2$ ,  $\text{H}_2\text{PdCl}_6$ ,  $\text{H}_6\text{Cl}_2\text{N}_2\text{Pd}$ ,  $\text{PdCl}_2$ ,  $\text{PdBr}_2$ ,  $\text{K}_2[\text{PdCl}_4]$ ,  $\text{Na}_2[\text{PdCl}_4]$ ,  $\text{Li}_2[\text{PdCl}_4]$ ,  $\text{H}_2\text{Pd}(\text{OH})_6$ ,  $\text{Pd}(\text{NO}_3)_2$ ,  $[\text{Pd}(\text{NH}_3)_4]\text{Cl}_2$ ,  $[\text{Pd}(\text{NH}_3)_4](\text{HCO}_3)_2$ ,  $[\text{Pd}(\text{NH}_3)_4](\text{OAc})_2$ ,  $(\text{NH}_4)_2\text{PdBr}_6$ ,  $(\text{NH}_3)_2\text{PdCl}_6$ ,  $\text{PdSO}_4$ ,  $\text{Pd}(\text{HSO}_4)_2$ ,  $\text{Pd}(\text{ClO}_4)_2$ ,  $\text{HAuCl}_4$ ,  $\text{AuCl}_3$ ,  $\text{AuCl}$ ,  $\text{AuF}_3$ ,  $(\text{CH}_3)_2\text{SAuCl}$ ,  $\text{AuF}$ ,  $\text{AuCl}(\text{SC}_4\text{H}_8)$ ,  $\text{AuBr}$ ,  $\text{AuBr}_3$ ,  $\text{Na}_3\text{Au}(\text{S}_2\text{O}_3)_2$ ,  $\text{HAuBr}_4$ ,  $\text{K}[\text{Au}(\text{CN})_2]$ ,  $\text{CoF}_2$ ,  $\text{Co}(\text{NO}_3)_2$ ,  $\text{CoCl}_2$ ,  $\text{CoSO}_4$ ,  $\text{Co}(\text{HSO}_4)_2$ ,  $\text{Co}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Co}$ ,  $\text{CoBr}_2$ ,  $[\text{Co}(\text{NH}_3)_6]\text{Cl}_3$ ,  $[\text{CoCl}(\text{NH}_3)_5]\text{Cl}_2$ ,  $[\text{Co}(\text{NO}_2)(\text{NH}_3)_5]\text{Cl}_2$ ,  $\text{NiF}_2$ ,  $\text{Ni}(\text{NO}_3)_2$ ,  $\text{NiCl}_2$ ,  $\text{NiSO}_4$ ,  $\text{Ni}(\text{HSO}_4)_2$ ,  $\text{Ni}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Ni}$ ,  $\text{NiBr}_2$ ,  $\text{Ni}(\text{OH})\text{HSO}_4$ ,  $\text{Ni}(\text{OH})\text{Cl}$ ,  $\text{FeF}_2$ ,  $\text{Fe}(\text{NO}_3)_2$ ,  $\text{FeCl}_2$ ,  $\text{FeSO}_4$ ,  $\text{Fe}(\text{HSO}_4)_2$ ,  $\text{Fe}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Fe}$ ,  $\text{FeBr}_2$ ,  $\text{FeF}_3$ ,  $\text{Fe}(\text{NO}_3)_3$ ,  $\text{FeCl}_3$ ,  $\text{Fe}_2(\text{SO}_4)_3$ ,  $\text{Fe}(\text{HSO}_4)_3$ ,  $\text{Fe}(\text{ClO}_4)_3$ ,  $(\text{CHCOO})_3\text{Fe}$ ,  $\text{FeBr}_3$ ,  $\text{RuCl}_2$ ,  $((\text{CH}_3)_2\text{SO})_4$ ,  $\text{RuCl}_3$ ,  $[\text{Ru}(\text{NH}_3)_5(\text{N}_2)]\text{Cl}_2$ ,  $\text{Ru}(\text{NO}_3)_3$ ,  $\text{RuBr}_3$ ,  $\text{RuF}_3$ ,  $\text{Ru}(\text{ClO}_4)_3$ ,  $\text{OsI}$ ,  $\text{OsI}_2$ ,  $\text{OsBr}_3$ ,  $\text{OsCl}_4$ ,  $\text{OsF}_5$ ,  $\text{OsF}_6$ ,  $\text{OsOF}_5$ ,  $\text{OsF}_7$ ,  $\text{IrF}_6$ ,  $\text{IrCl}_3$ ,  $\text{IrF}_4$ ,  $\text{IrF}_5$ ,  $\text{Ir}(\text{ClO}_4)_3$ ,  $\text{K}_3[\text{IrCl}_6]$ ,  $\text{K}_2[\text{IrCl}_6]$ ,  $\text{Na}_3[\text{IrCl}_6]$ ,  $\text{Na}_2[\text{IrCl}_6]$ ,  $\text{Li}_3[\text{IrCl}_6]$ ,  $\text{Li}_2[\text{IrCl}_6]$ ,  $[\text{Ir}(\text{NH}_3)_4\text{Cl}_2]\text{Cl}$ ,  $\text{RhF}_3$ ,  $\text{RhF}_4$ ,  $\text{RhCl}_3$ ,  $[\text{Rh}(\text{NH}_3)_5\text{Cl}]\text{Cl}_2$ ,  $\text{RhCl}[\text{P}(\text{C}_6\text{H}_5)_3]_3$ ,  $\text{K}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Na}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Li}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Rh}_2(\text{SO}_4)_3$ ,  $\text{Rh}(\text{HSO}_4)_3$  et  $\text{Rh}(\text{ClO}_4)_3$  leurs hydrates ou des mélanges de ces sels et/ou hydrates.

## EP 2 785 483 B1

8. Méthode selon l'une des revendications 1 - 7, dans laquelle l'agent réducteur est choisi dans un groupe comprenant l'hydrazine, l'acide ascorbique, le borohydrure de sodium, l'hypophosphite de sodium, le tétraéthyleborohydrure de sodium, le méthanol, le 1,2-hexadécane-1,2-diol, l'hydroxylamine et le diméthylamineborane DMAB.
- 5 9. Méthode selon l'une des revendications 1 - 8, dans laquelle la substance neutralisant l'agent réducteur est choisie dans un groupe comprenant le peroxyde d'hydrogène, l'oxygène, l'ozone, le  $\text{NO}_2$  et un tampon redox.
- 10 10. Méthode selon l'une des revendications 1 - 9, dans laquelle les segments de tube particuliers du système à écoulement continu, à travers lesquels le flux des réactifs, du mélange réactionnel et des produits s'écoule, sont maintenus à des températures différentes.
11. Méthode selon l'une des revendications 1, 2, 4 - 10, dans laquelle la substance précurseur est le  $\text{Pd}(\text{NO}_3)_2$ , l'agent réducteur est l'hydrazine, et la substance neutralisant l'agent réducteur est le peroxyde d'hydrogène.
- 15 12. Méthode selon l'une des revendications 1, 2, 4 - 10, dans laquelle la substance précurseur est le  $\text{Cu}(\text{NO}_3)_2$ , l'agent réducteur est l'hydrazine, et la substance neutralisant l'agent réducteur est le peroxyde d'hydrogène, dans laquelle la solution de la substance neutralisant l'agent réducteur comprend en outre le  $\text{NaOH}$ .
- 20 13. Méthode selon l'une des revendications 1, 3 - 10, dans laquelle dans la première étape, la solution de substance précurseur  $\text{Cu}(\text{NO}_3)_2$  est soumise à la réaction de réduction en utilisant une solution d'hydrazine, ce qui conduit à la formation du noyau de cuivre, et dans la deuxième étape la solution de substance précurseur  $\text{Pd}(\text{NO}_3)_2$  est fournie au mélange réactionnel, dont la réduction conduit à la formation des coquilles de palladium sur les nanoparticules de cuivre formées dans la première étape, et la réaction de réduction est terminée par addition d'une solution de peroxyde d'hydrogène et d'une base, dans laquelle la concentration de base est suffisante pour assurer un pH neutre du flux de produits.
- 25 14. Méthode selon l'une des revendications 1, 2, 4 - 10, dans laquelle la substance précurseur est un mélange du  $\text{Pd}(\text{NO}_3)_2$  et  $\text{Pt}(\text{NO}_3)_2$ , dont la réduction conduit à la formation des nanoparticules homogènes d'alliage de Pd/Pt.
- 30 15. Méthode selon l'une des revendications 1 - 10, dans laquelle la substance neutralisant l'agent réducteur est un tampon redox ayant un potentiel approprié pour une réduction sous-nerstienne de la couche extérieure métallique sur le noyau métallique.
- 35 16. Méthode selon l'une des revendications 1 - 15, dans laquelle la méthode comprend en outre une étape de centrifugation et/ou de séchage des nanoparticules colloïdales, dans laquelle une poudre de nanoparticules est obtenue.

40


45

50

55

Fig. 1

a)



b)




Fig. 2




Fig. 3




Fig. 4






Fig. 5


a)



b)



**Fig. 6**



**Fig. 7**




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12




Fig. 13





Fig. 14



## REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

## Patent documents cited in the description

- WO 2004076056 A [0003]
- WO 2009133418 A [0003]

## Non-patent literature cited in the description

- **WAGNER J. et al.** Generation of metal nanoparticles in a microchannel reactor. *Chemical Engineering Journal*, 2004, vol. 101, 251-260 [0006]
- **KÖHLER J.M. et al.** Formation of isolated and clustered Au nanoparticles in the presence of polyelectrolyte molecules using a flow-through Si chip reactor. *Journal of Materials Chemistry*, 2005, vol. 15, 1924-1930 [0006]
- **WAGNER J. et al.** Continuous synthesis of gold nanoparticles in a microreactor. *Nano Letters*, 2005, vol. 5 (4), 685-691 [0006]
- **KÖHLER J. M. et al.** Formation of Au/Ag Nanoparticles in a Two Step Micro Flow-Through Process. *Chem. Eng. Technol.*, 2007, vol. 30 (3), 347-354 [0006]
- **KÖHLER J. M. et al.** Preparation of metal nanoparticles with varied composition for catalytically applications in microreactors. *Chemical Engineering Science*, 2008, vol. 63, 5048-5055 [0006]
- **SONG Y. et al.** Synthesis of palladium nanoparticles using a continuous flow polymeric microreactor. *Journal of Nanoscience and Nanotechnology*, 2004, vol. 4 (7), 788-793 [0006]
- **TORGOE K. et al.** Microflow reactor synthesis of palladium nanoparticles stabilized with poly(benzyl ether) Dendron ligands. *Journal of Nanoparticle Research*, 2010, vol. 12 (3), 951-960 [0006]
- **WENG C. H. et al.** Synthesis of hexagonal gold nanoparticles using a microfluidic reaction system. *Journal of Micromechanics and Microengineering*, 2008, vol. 18, 1-8 [0006]
- **SUNG-YI YANG.** Size controlled synthesis of gold nanoparticles using a micromixing system. *Microfluid Nanofluid*, 2009, vol. 8, 303-311 [0006]
- **SOLLA-GULLON J. et al.** Electrochemical characterization of platinum nanoparticles prepared by microemulsion: how to clean them without loss of crystalline surface structure. *J. Electroanal. Chem.*, 2000, vol. 491 (1-2), 69-77 [0007]
- **PARK, J. Y. et al.** The Role of Organic Capping Layers of Platinum Nanoparticles in Catalytic Activity of CO Oxidation. *Catalysis Letters*, 2009, vol. 129 (1-2), 1-6 [0007]
- **S. SZABÓ.** Underpotential deposition of metals on foreign metal substrates. *International Reviews in Physical Chemistry*, 1991, vol. 10 (2), 207-248 [0014]
- **A. PARACCHINO et al.** *Nature Materials*, 2011, vol. 10, 456-461 [0018]
- **U. BJÖRKSTÉN et al.** *Chem. Mater.*, 1994, vol. 6, 858-863 [0053]
- **R. SOLARSKA et al.** *Angewandte Chem. - Int. Ed.*, 2010, vol. 49 (43), 7980-7983 [0055]
- **K.L. KELLY et al.** *J. Phys. Chem. B*, 2003, vol. 107 (3), 668-677 [0055]
- **MOTT et al.** Synthesis of Size-Controlled and Shaped Copper Nanoparticles. *Langmuir*, 2007, vol. 23, 5740-5745 [0088]
- **RADHA NARAYANAN ; MOSTAFA A. EL-SAYED.** *J. Am. Chem. Soc.*, 2003, vol. 125 (27), 8340-8347 [0115]

## Szabadalmi igénypontok

1. Eljárás tiszta, szabályozott méretű nanorészecskék folyamatos áramlási rendszerben történő előállítására, amely nanorészecskék felszínén felületaktív anyagok vagy egyéb szerves molekulák nincsenek adszorbeálva, ahol a folyamatos áramlási rendszer olyan csővezetékot tartalmaz, amelyben a reagensek és termékek árama folyamatosan halad, és amely eljárás legalább egy olyan lépést tartalmaz, amelyben egy prekursor anyag oldatot redukációs reakciónak vetjük alá egy redukálószer oldat alkalmazásával, és nanorészecskéket állítunk elő, azzal jellemezve, hogy a redukációs reakciót az utolsó lépés után egy, a redukálószer semlegesítő anyag hozzáadásával leállítjuk, és nanorészecske kolloidot állítunk elő.

2. Az 1. igénypont szerinti eljárás, amely eljárás tartalmaz egy olyan lépést, amelyben a prekursor anyag oldatot redukációs reakciónak vetjük alá redukálószer oldat alkalmazásával, és homogén nanorészecskéket állítunk elő.

3. Az 1. igénypont szerinti eljárás, amely eljárás legalább két olyan lépést tartalmaz, amelyben a prekursor anyag oldatot redukációs reakciónak vetjük alá redukálószer oldat alkalmazásával, és mag-héj típusú réteges nanorészecskéket állítunk elő.

4. Az 1-3. igénypontok bármelyike szerinti eljárás, ahol a prekursor anyag egy fém prekursor vagy fém prekursorok keveréke.

5. A 4. igénypont szerinti eljárás, ahol a fém prekursor egy fémsó vagy különböző fémsók keveréke.

6. A 4. vagy 5. igénypont szerinti eljárás, ahol a fém palládium, ezüst, arany, platina, ruténium, ozmium, irídium, ródium, nikkel, kobalt, réz és vas csoportjából van kiválasztva.

7. Az 1-6. igénypontok bármelyike szerinti eljárás, ahol a prekursor anyag egy só  $\text{AgNO}_3$ ,  $\text{AgClO}_4$ ,  $\text{AgHSO}_4$ ,  $\text{Ag}_2\text{SO}_4$ ,  $\text{AgF}$ ,  $\text{AgBF}_4$ ,  $\text{AgPF}_6$ ,  $\text{CH}_3\text{COOAg}$ ,  $\text{AgCF}_3\text{SO}_3$ ,  $\text{CuCl}_2$ ,  $\text{Cu}(\text{NO}_3)_2$ ,  $\text{CuSO}_4$ ,  $\text{Cu}(\text{HSO}_4)_2$ ,  $\text{Cu}(\text{ClO}_4)_2$ ,  $\text{CuF}_2$ ,  $(\text{CHCOO})_2\text{Cu}$ ,  $\text{H}_2\text{PtCl}_6$ ,  $\text{H}_6\text{Cl}_2\text{N}_2\text{Pt}$ ,  $\text{PtCl}_2$ ,  $\text{PtBr}_2$ ,  $\text{K}_2[\text{PtCl}_4]$ ,  $\text{Na}_2[\text{PtCl}_4]$ ,  $\text{Li}_2[\text{PtCl}_4]$ ,  $\text{H}_2\text{Pt}(\text{OH})_6$ ,  $\text{Pt}(\text{NO}_3)_2$ ,  $[\text{Pt}(\text{NH}_3)_4]\text{Cl}_2$ ,  $[\text{Pt}(\text{NH}_3)_4](\text{HCO}_3)_2$ ,  $[\text{Pt}(\text{NH}_3)_4](\text{OAc})_2$ ,  $(\text{NH}_4)_2\text{PtBr}_6$ ,  $\text{K}_3\text{PtCl}_6$ ,  $\text{PtSO}_4$ ,  $\text{Pt}(\text{HSO}_4)_2$ ,  $\text{Pt}(\text{ClO}_4)_2$ ,  $\text{H}_2\text{PdCl}_6$ ,  $\text{H}_6\text{Cl}_2\text{N}_2\text{Pd}$ ,  $\text{PdCl}_2$ ,  $\text{PdBr}_2$ ,  $\text{K}_2[\text{PdCl}_4]$ ,  $\text{Na}_2[\text{PdCl}_4]$ ,  $\text{Li}_2[\text{PdCl}_4]$ ,  $\text{H}_2\text{Pd}(\text{OH})_6$ ,  $\text{Pd}(\text{NO}_3)_2$ ,  $[\text{Pd}(\text{NH}_3)_4]\text{Cl}_2$ ,  $[\text{Pd}(\text{NH}_3)_4](\text{HCO}_3)_2$ ,  $[\text{Pd}(\text{NH}_3)_4](\text{OAc})_2$ ,  $(\text{NH}_4)_2\text{PdBr}_6$ ,  $(\text{NH}_4)_2\text{PdCl}_6$ ,  $\text{PdSO}_4$ ,  $\text{Pd}(\text{HSO}_4)_2$ ,  $\text{Pd}(\text{ClO}_4)_2$ ,  $\text{HAuCl}_4$ ,  $\text{AuCl}_3$ ,  $\text{AuCl}$ ,  $\text{AuF}_3$ ,  $(\text{CH}_3)_2\text{SAuCl}$ ,  $\text{AuF}$ ,  $\text{AuCl}(\text{SC}_6\text{H}_5)$ ,  $\text{AuBr}$ ,  $\text{AuBr}_3$ ,  $\text{Na}_3\text{Au}(\text{S}_2\text{O}_7)_2$ ,  $\text{HAuBr}_4$ ,  $\text{K}[\text{Au}(\text{CN})_2]$ ,  $\text{CoF}_2$ ,  $\text{Co}(\text{NO}_3)_2$ ,  $\text{CoCl}_2$ ,  $\text{CoSO}_4$ ,  $\text{Co}(\text{HSO}_4)_2$ ,  $\text{Co}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Co}$ ,  $\text{CoBr}_2$ ,  $[\text{Co}(\text{NH}_3)_6]\text{Cl}_2$ ,  $[\text{CoCl}(\text{NH}_3)_5]\text{Cl}_2$ ,  $[\text{Co}(\text{NO}_2)(\text{NH}_3)_5]\text{Cl}_2$ ,  $\text{NiF}_2$ ,  $\text{Ni}(\text{NO}_3)_2$ ,  $\text{NiCl}_2$ ,  $\text{NiSO}_4$ ,  $\text{Ni}(\text{HSO}_4)_2$ ,  $\text{Ni}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Ni}$ ,  $\text{NiBr}_2$ ,  $\text{Ni}(\text{OH})\text{HSO}_4$ ,  $\text{Ni}(\text{OH})\text{Cl}$ ,  $\text{FeF}_2$ ,  $\text{Fe}(\text{NO}_3)_2$ ,  $\text{FeCl}_2$ ,  $\text{FeSO}_4$ ,  $\text{Fe}(\text{HSO}_4)_2$ ,  $\text{Fe}(\text{ClO}_4)_2$ ,  $(\text{CHCOO})_2\text{Fe}$ ,  $\text{FeBr}_2$ ,  $\text{FeF}_3$ ,  $\text{Fe}(\text{NO}_3)_3$ ,  $\text{FeCl}_3$ ,  $\text{Fe}_2(\text{SO}_4)_3$ ,  $\text{Fe}(\text{HSO}_4)_3$ ,  $\text{Fe}(\text{ClO}_4)_3$ ,  $(\text{CHCOO})_3\text{Fe}$ ,  $\text{FeBr}_3$ ,  $\text{RuCl}_2$ ,  $(\text{CH}_3)_2\text{SO}$ ,  $\text{RuCl}_3$ ,  $[\text{Ru}(\text{NH}_3)_5(\text{N}_3)]\text{Cl}_2$ ,  $\text{Ru}(\text{NO}_3)_2$ ,  $\text{RuBr}_2$ ,  $\text{RuF}_3$ ,  $\text{Ru}(\text{ClO}_4)_3$ ,  $\text{OsI}$ ,  $\text{OsI}_2$ ,  $\text{OsBr}_3$ ,  $\text{OsCl}_4$ ,  $\text{OsF}_5$ ,  $\text{OsF}_6$ ,  $\text{OsOF}_5$ ,  $\text{OsF}_7$ ,  $\text{IrF}_6$ ,  $\text{IrCl}_3$ ,  $\text{IrF}_4$ ,  $\text{IrF}_5$ ,  $\text{Ir}(\text{ClO}_4)_3$ ,  $\text{K}_3[\text{IrCl}_6]$ ,  $\text{K}_2[\text{IrCl}_6]$ ,  $\text{Na}_3[\text{IrCl}_6]$ ,  $\text{Na}_2[\text{IrCl}_6]$ ,  $\text{Li}_3[\text{IrCl}_6]$ ,  $\text{Li}_2[\text{IrCl}_6]$ ,  $[\text{Ir}(\text{NH}_3)_4\text{Cl}_2]\text{Cl}$ ,  $\text{RbF}_3$ ,  $\text{RbF}_4$ ,  $\text{RhCl}_3$ ,  $[\text{Rh}(\text{NH}_3)_5\text{Cl}]\text{Cl}_2$ ,  $\text{RbCl}[\text{P}(\text{C}_6\text{H}_5)_3]$ ,  $\text{K}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Na}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Li}[\text{Rh}(\text{CO})_2\text{Cl}_2]$ ,  $\text{Rh}_2(\text{SO}_4)_3$ ,  $\text{Rh}(\text{HSO}_4)_3$  és  $\text{Rh}(\text{ClO}_4)_3$ , ezek hidrátjai vagy ezen sók és/vagy hidrátok keverékei csoportjából kiválasztva.

8. Az 1-7. igénypontok bármelyike szerinti eljárás, ahol a redukálószer hidrazin, aszkorbinsav, nátrium-bórhidrid, nátrium-hipofoszfít, lítium-tetraetilbórhidrid, metanol, 1,2-hexadekándiol, hidroxilamin és dimetilforazán DMAB csoportjából van kiválasztva.

9. Az 1-8. igénypontok bármelyike szerinti eljárás, ahol a redukálószer semlegesítő anyag hidrogén-peroxid, oxigén, ózon,  $\text{NO}_2$  és egy redox puffer csoportjából van kiválasztva.

10. Az 1-9. igénypontok bármelyike szerinti eljárás, ahol a folyamatos áramlási rendszer meghatározott csőszakaszát, amelyen a reagensek, a reakciókeverék és a termékek árama áthalad, különböző hőmérsékleteken tartjuk.

11. Az 1., 2., 4-10. igénypontok bármelyike szerinti eljárás, ahol a prekursor anyag  $\text{Pd}(\text{NO}_3)_2$ , a redukálószer hidrazin és a redukálószer semlegesítő anyag hidrogén-peroxid.

12. Az 1., 2., 4-10. igénypontok bármelyike szerinti eljárás, ahol a prekursor anyag  $\text{Cu}(\text{NO}_3)_2$ , a redukálószer hidrazin és a redukálószer semlegesítő anyag hidrogén-peroxid, ahol a redukálószer semlegesítő anyag oldata  $\text{NaOH}$ -t is tartalmaz.

13. Az 1., 3-10. igénypontok bármelyike szerinti eljárás, ahol az első lépésben a  $\text{Cu}(\text{NO}_3)_2$  prekursor anyag oldatát redukációs reakciónak vetjük alá hidrazin oldat alkalmazásával, ami rézmag képződését eredményezi, és a második lépésben a reakciókeverékhez a  $\text{Pd}(\text{NO}_3)_2$  prekursor anyag oldatát adjuk, amelynek redukciója az első lépésben képződött réz nanorészecskéken palládium héjak képződését eredményezi, és a redukációs reakciót hidrogén-peroxid oldat és egy bázis hozzáadásával leállítjuk, ahol a bázis koncentrációja a termékáram semleges pH-jának biztosításához elegendő.

14. Az 1., 2., 4-10. igénypontok bármelyike szerinti eljárás, ahol a prekursor anyag  $\text{Pd}(\text{NO}_3)_2$  és  $\text{Pt}(\text{NO}_3)_2$  keveréke, amelyek reakciója Pd/Pt ötvözet homogén nanorészecskéinek képződését eredményezi.

15. Az 1-10. igénypontok bármelyike szerinti eljárás, ahol a redukálószer semlegesítő anyag egy redox puffer, amelynek potenciálja a fémmagon lévő külső fémréteg potenciál alatti redukálására alkalmas.

16. Az 1-15. igénypontok bármelyike szerinti eljárás, amely eljárás tartalmaz egy, a koloid nanorészecske centrifugálására és/vagy szárítására vonatkozó további lépést, amelynek során nanorészecske port állítunk elő.