



(51) International Patent Classification:

B32B 27/32 (2006.01) B29C 55/18 (2006.01)

C08J 5/18 (2006.01) B65D 30/02 (2006.01)

B29C 55/12 (2006.01) B32B 27/30 (2006.01)

B29C 55/04 (2006.01) B65D 30/08 (2006.01)

(21) International Application Number:

PCT/CN2020/113202

(22) International Filing Date:

03 September 2020 (03.09.2020)

(25) Filing Language:

English

(26) Publication Language:

English

(71) Applicant: THE PROCTER & GAMBLE COMPANY

[US/US]; One Procter & Gamble Plaza, Cincinnati, Ohio 45202 (US).

(72) Inventors; and

(71) Applicants (for US only): CHENG, Zhan [CN/CN]; No. 35, Yu'an Road, B Zone, Tianzhu Konggang Development Zone, Shunyi District, Beijing 101312 (CN). ZHOU, Lei [CN/CN]; No. 35, Yu'an Road, B Zone, Tianzhu Konggang Development Zone, Shunyi District, Beijing 101312 (CN). RONG, Jiashao [CN/CN]; No. 35, Yu'an Road, B Zone, Tianzhu Konggang Development Zone, Shunyi District, Beijing 101312 (CN). YAN, Dong [CN/CN]; No. 35, Yu'an Road, B Zone, Tianzhu Konggang Development Zone, Shunyi District, Beijing 101312 (CN).

(74) Agent: CHINA SCIENCE PATENT & TRADEMARK

AGENT LTD.; Suite 4-1105, No. 87, West 3rd Ring North Rd., Haidian District, Beijing 100089 (CN).

(81) Designated States (unless otherwise indicated, for every

kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,

HR, HU, ID, IL, IN, IR, IS, IT, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every

kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: CONTAINER COMPRISING LAMINATE OF POLYETHYLENE




FIG. 1

(57) Abstract: A container comprising a laminate is provided, wherein the laminate comprises a first layer of machine direction oriented polyethylene (MDO-PE), a second layer of biaxial oriented polyethylene (BO-PE), and a third layer of polyethylene (PE).



CONTAINER COMPRISING LAMINATE OF POLYETHYLENE

FIELD OF THE INVENTION

The present application is directed to a container comprising a laminate of polyethylene.

BACKGROUND OF THE INVENTION

Plastic packaging including rigid bottles and flexible bags (also called pouches herein) are widely used in a variety of applications. One of the most important requirements for plastic packaging, especially for heavy duty plastic packaging for products such as detergent powders or liquids, is the mechanical strength of the thermoplastic material that is employed to prepare the plastic packaging, because the plastic packaging needs to resist impact to some extents and maintain packaging integrity till the end of the product usage. In order to assess whether the plastic packaging is robust enough to contain the content therein, some tests are employed to measure mechanical performances. The most common tests include tensile strength, sealing strength and drop test. The test for tensile strength is to measure how much tensile stress to make the plastic film break. The test for sealing strength is to measure how much tensile stress to make the plastic packaging (such as a flexible bag) sealing break. The drop test is to measure the holistic robustness of the plastic packaging, in which the plastic packaging is dropped from a certain height and then check if any leakage happens.

Particularly, Stand Up Pouch (SUP) with bottom gusset feature is one of the most widely used flexible packages due to its standup ability and improved usage experiences, and is typically used for containing powders or liquids for products such as in the area of fabric care. Such pouches has very high mechanical performance requirements to prevent leakage due to dropping from a height or stocks by other objects throughout the entire product life cycle. In this case, the selection of the thermoplastic material that is employed to prepare such plastic packaging is very limited, because most of thermoplastic materials cannot provide sufficient mechanical strength as required. Further, in order to meet the requirements for mechanical strength, a laminate comprising two or more layers of thermoplastic materials is commonly employed. Currently, the commercially available laminate which can pass the drop test for detergent pouches includes polyethylene terephthalate / polyethylene (PET/PE) laminate, polyamide/polyethylene (PA/PE) laminate, PET/PA/PE laminate, and PET/Vacuum metalized PET/PE laminate. However, none of these laminates are recyclable, because all of them comprise at least two different

thermoplastic polymers. Thus, there is a need to develop a laminate which has sufficient mechanical strength and also is recyclable.

Polyethylene (PE) is a common thermoplastic polymer for plastic packaging. However, PE films are in general of lower mechanical strength and heat resistance compared to other thermoplastic polymer films such as PET and PA. Recently, some new types of PE films such as oriented PE films have been developed to improve the mechanical property of PE films. However, there is no known pouches made of mono-polymer PE laminate can pass the drop test especially under heavy load above 1kg for liquid products prior to the present invention. Thus, the plastic packaging such as Stand Up Pouch (SUP) made of mono-polymer PE laminates is still technically challenging in the term of heavy duty applications for liquids (especially the drop test).

SUMMARY OF THE INVENTION

The present disclosure meets one or more of the above-mentioned needs based on the surprising discovery that a mono-polymer PE laminate comprising a first layer of machine direction oriented polyethylene (MDO-PE), a second layer of biaxial oriented polyethylene (BO-PE), and a third layer of polyethylene (PE) can provide sufficient mechanical strength, especially is capable of passing the drop test. Further, the laminate according to the present disclosure may be recyclable because the laminate is a mono-polymer PE laminate, i.e. the principle thermoplastic polymer in the laminate is PE.

In one aspect, the present disclosure provides a container comprising a laminate in which the laminate comprises a first layer of MDO-PE, a second layer of BO-PE, and a third layer of PE.

In another aspect, the present disclosure provides a laundry detergent bag containing from 0.1 kg to 3 kg of laundry detergent, wherein the bag is constructed from a laminate comprising a first layer of MDO-PE, a second layer of BO-PE, and a third layer of PE.

In a further aspect, the present disclosure provides a laminate comprising a first layer of MDO-PE, a second layer of BO-PE, and a third layer of PE.

It is an advantage of the laminate to have sufficient mechanical strength to prevent leakage due to dropping from a height, stocking contents or stabbing by sharp objects.

It is another advantage of the laminate to be capable of passing the drop test for detergent stand-up bags.

It is another advantage of the laminate to be capable of making a container for detergent powders or liquids that is recyclable.

It is another advantage of the laminate to allow a sufficient heat-sealing between two laminates according to the present disclosure.

These and other features, aspects and advantages of specific embodiments will become evident to those skilled in the art from a reading of the present disclosure.

BRIEF DESCRIPTION OF THE DRAWINGS

The embodiments set forth in the drawings are illustrative in nature and not intended to limit the invention defined by the claims. The following detailed description of the illustrative embodiments can be understood when read in conjunction with the following drawings, and in which:

Figure 1 illustrates an embodiment of the laminate according to the present disclosure.

Figure 2 illustrates another embodiment of the laminate according to the present disclosure.

DETAILED DESCRIPTION OF THE INVENTION

The following text sets forth a broad description of numerous different embodiments of the present disclosure. The description is to be construed as exemplary only and does not describe every possible embodiment since describing every possible embodiment would be impractical, if not impossible. It will be understood that any feature, characteristic, component, composition, ingredient, product, step or methodology described herein can be combined with or substituted for, in whole or part, any other feature, characteristic, component, composition, ingredient, product, step or methodology described herein. Numerous alternative embodiments could be implemented, using either current technology or technology developed after the filing date of this patent, which would still fall within the scope of the claims. All publications and patents cited herein are incorporated herein by reference.

The present disclosure is directed to a container comprising a laminate in which the laminate comprises a first layer of MDO-PE, a second layer of BO-PE, and a third layer of PE. The total thickness of the laminate according to the present disclosure may be from 70 microns to 400 microns, preferably from 100 microns to 350 microns, more preferably from 120 microns to 300 microns, most preferably from 140 microns to 250 microns. Particularly, the first layer may

have a thickness of from 5 microns to 50 microns, preferably from 10 microns to 45 microns, more preferably from 15 microns to 40 microns, most preferably from 20 microns to 30 microns; and/or the second layer may have a thickness of from 5 microns to 50 microns, preferably from 8 microns to 45 microns, more preferably from 12 microns to 40 microns, most preferably from 15 microns to 25 microns; and/or the third layer may have a thickness of from 10 microns to 250 microns, preferably from 30 microns to 230 microns, more preferably from 100 microns to 200 microns, most preferably from 120 microns to 160 microns.

Preferably, the container may be recyclable. More preferably, the laminate according to the present disclosure may comprise no more than 10% by weight, preferably no more than 7%, more preferably no more than 5%, most preferably no more than 3%, of thermoplastic polymer that is not PE.

Preferably, the laminate according to the present disclosure may have a tensile strength along the machine direction as measured by the method according to Test 2 of more than 100 N/inch, preferably more than 120 N/inch, more preferably more than 130 N/inch, most preferably more than 140 N/inch.

Preferably, the laminate according to the present disclosure may have a tensile strength along the transverse direction as measured by the method according to Test 2 of more than 100 N/inch, preferably more than 120 N/inch, more preferably more than 130 N/inch, most preferably more than 140 N/inch; and/or

Preferably, the laminate according to the present disclosure may have a sealing strength at the side seal as measured by the method according to Test 3 of more than 70 N/inch, preferably more than 80 N/inch, more preferably more than 90 N/inch, most preferably more than 100 N/inch; and/or

Preferably, the laminate according to the present disclosure may have a sealing strength at the bottom seal as measured by the method according to Test 3 of more than 70 N/inch, preferably more than 80 N/inch, more preferably more than 90 N/inch, most preferably more than 100 N/inch.

Preferably, the container according to the present disclosure may be a flexible bag (also called “pouch”), preferably a flexible stand-up bag. The term of “stand-up bag”, “Stand Up Bag” or “Stand Up Pouch” used herein refers to a bag having a bottom gusset feature which is capable of allowing the bag to stand up without being supported by any external articles.

Preferably, the container may contain from 0.05 kg to 10kg, preferably 0.1 kg to 5 kg, more preferably 0.2kg to 3 kg of product, for example 0.1kg, 0.2kg, 0.3kg, 0.4kg, 0.5kg, 1kg,

2kg, 3kg, 4kg, 5kg or any ranges thereof. More preferably, the product may be selected from the group consisting of fabric care products, home care products, hair care products, beauty care products, and personal care products, preferably a laundry detergent product, more preferably a granule laundry detergent or a liquid laundry detergent.

The layers in the laminate according to the present disclosure may be arranged in any sequence. Preferably, the layers in the laminate according to the present disclosure may be arranged as being i), ii), and iii) or ii), i) and iii) in turn from outside to inside. In the context of the present disclosure, the term “inside” refers to a side of the laminate in the packaging (e.g. a flexible bag) which is facing to the content (e.g. detergent liquids) contained in the packaging and the term “outside” refers to a side of the laminate that is opposite to the inside.

The entire laminate and layers in the laminate according to the present disclosure may have different initial sealing temperatures as measured by the method according to Test 4. Particularly, the entire laminate according to the present disclosure may have an initial sealing temperature of no more than 125°C, preferably no more than 120°C, more preferably no more than 118°C, most preferably no more than 115°C, as measured by the method according to Test 4, and the first layer may have an initial sealing temperature of at least 130°C, preferably at least 135°C, more preferably at least 140°C, most preferably at least 145°C, as measured by the method according to Test 4.

In another aspect, the present disclosure provides a bag containing from 0.05 kg to 10kg, preferably 0.1 kg to 5 kg, more preferably 0.2kg to 3 kg of laundry detergent, wherein the bag is constructed from a laminate comprising a first layer of MDO-PE, a second layer of BO-PE, and a third layer of PE.

In a further aspect, the present disclosure provides a laminate comprising a first layer of MDO-PE, a second layer of BO-PE, and a third layer of PE. FIGS. 1 and 2 illustrate embodiments of laminates according to the present disclosure.

FIG. 1 illustrates a laminate **1** comprising a first layer **11** of MDO-PE, a second layer **12** of BO-PE, and a third layer **13** of PE, in which adhesive between layers are not shown.

FIG. 2 illustrates a laminate **2** comprising a first layer **21** of BO-PE, a second layer **22** of MDO-PE, and a third layer **23** of PE, in which adhesive between layers are not shown.

Polyethylene (“PE”)

The laminate of the present disclosure comprises polyethylene (PE) as a principle thermoplastic polymer (i.e., a PE-based laminate). In turn, the PE component may comprise one

or more divisions (or even sub-divisions) of PE polymers. PE is generally divided into high-density (HDPE, density 0.941 g/cc or greater), medium-density (MDPE, density from 0.926 to 0.940 g/cc), low-density (LDPE, density from 0.910 to 0.925 g/cc), and linear low-density polyethylene (LLDPE, density from 0.910 to 0.925 g/cc). See e.g., ASTM D4976-98: Standard Specification for Polyethylene Plastic Molding and Extrusion Materials. In turn, these PE divisions can be further divided into mono-modal or multi-modal (e.g., bi-modal) sub-divisions.

One of the main uses of polyethylene (HDPE, LLDPE, and LDPE) is in film applications, such as grocery sacks, institutional and consumer can liners, merchandise bags, shipping sacks, food packaging films, multi-wall bag, liners, produce bags, stretch wraps, shrink wraps, and the like. The key physical properties of PE-based film layer may include tear strength, impact strength, tensile strength, stiffness, and transparency. Different combinations of PE divisions, and sub-divisions be used herein depending upon the application and/or desired film property. In some embodiments, the PE component in the laminate of the present disclosure, will comprise some level of a linear low density polyethylene (LLDPE) polymer.

At least one layer of the film comprises 70% to 99%, by weight of the at least one layer of the film of a PE component. Preferably the at least one layer of the film comprises from 75% to 98%, more preferably 80% to 95%, yet more preferably 82% to 93%, by weight of the at least one layer, of the PE component. The PE component has at least one PE polymer, optionally two or more PE polymers. At least one layer of the film comprises from 70% to 99%, by weight of the at least one layer, of at least one PE polymer of the PE component. Preferably the at least one layer of film comprises from 75% to 98%, more preferably 80% to 95%, yet more preferably 82% to 93%, by weight of the at least one layer, of the at least one PE polymer of the PE component.

In some embodiments, the at least one film layer comprises from 1% to 100% by weight of the PE component, of a LLDPE polymer. More preferably the LLDPE is from 25% to 100%, alternatively from 25% to 90%, yet more preferably from 30% to 100%, yet more preferably the LLDPE is greater than 50%, preferably greater than at least 60%, more preferably greater than at least 70%, by weight of the PE component (in the at least one film layer).

In some embodiments, the at least one film layer comprises from 1% to 100% by weight of the PE component, of a HDPE or MDPE polymer. More preferably the HDPE or MDPE is from 10% to 80%, alternatively from 20% to 60%, yet more preferably from 30% to 50% by weight of the PE component (in the at least one film layer).

Suitable suppliers/products for PE may include Dowlex™ from Dow Chemical, and Borstar™ from Borealis and Borouge and Enable™ from Exxon Mobile

Machine Direction Oriented Polyethylene (MDO-PE)

The laminate of the present disclosure comprises a layer of machine direction oriented polyethylene (MDO-PE). The machine direction (MD) is also known as the longitudinal direction (generally perpendicular to the traverse direction (TD)). MD orientating is a preferred initial step after an unconverted film is formed. During the MD orientation, the unconverted film from the blown or casted line is heated to an orientation temperature via one or multiple hot rollers. The heated film is fed into a slow draw roll with a nip roller, which has the same rolling speed as the heating rollers. The film then enters a fast draw roll. The fast draw roll has a speed that is 2 to 10 times faster than the slow draw roll, which effectively stretches the film on a continuous basis. There can be another fast draw roll which is even faster than the first fast draw roll so that the film is subjected to two step stretching. Between the two stretching steps there is another set of heating rolls which sets the temperature of the film after the first stretching and before the second stretching. The temperatures in these two stretching steps can be the same or different. The orientation can also be a single stretching instead of two step stretching.

The total MD stretch ratio is from 2:1 to 10:1, more preferably from 3:1 to 9:1, and even more preferably from 5:1 to 8:1. The total MD stretch ratio includes all orientation steps. For example, if a two-step orientation is used with first stretch ratio 2:1 and second stretch ratio 3:1, the total stretch ratio is therefore 6:1.

The orientation temperature in a MD orientation, is around 50° C to below 140° C, preferably below 130° C, more preferably below 120° C, alternatively 60° C to 120° C, or below 115° C, or from 70° C to 115° C. The temperature also depends on the process speed. In general, higher process speed requires relatively higher temperature due to the relative shorter contacting time between film and hot rollers; while slower process speed requires relatively lower temperature due to the longer contacting time.

A typical thickness of the MDO-PE layer is from 5 microns to 50 microns, preferably from 10 microns to 45 microns, more preferably from 15 microns to 40 microns, most preferably from 20 microns to 30 microns.

Biaxial Oriented Polyethylene (BO-PE)

The laminate of the present disclosure comprises a layer of biaxial oriented polyethylene (BO-PE). BO-PE film is a film stretched in both MD and TD, resulting in molecular chain orientation in two directions. One of the common processes for preparing BO-PE is the

sequential process, in which a thick extruded sheet is heated to its softening point (not to the melting point) and is mechanically drawn in the machine direction using heated rollers and subsequently drawn in the transverse direction, i.e. orthogonally to the direction of travel, in a heated oven. It is also possible to draw the film in both directions simultaneously, although the equipment required for this is somewhat more elaborate. Particularly, BO-PE may be produced by a tubular process, in which a tubular bubble is inflated, or a tenter frame process, in which a thick extruded sheet is heated to its softening point (not to the melting point) and is mechanically stretched. Biaxial oriented polyethylene film process has been disclosed in patents WO201270373A1, US10363700B2, and US6689857B1 as examples.

The MD stretch ratio may be from 4.5:1 to 6:1, and the TD stretch ratio may be from 7:1 to 8:1, although these ratios are fully adjustable.

A typical thickness of the BO-PE layer is from 5 microns to 50 microns, preferably from 8 microns to 45 microns, more preferably from 12 microns to 40 microns, most preferably from 20 microns to 40 microns.

Test Method

Test 1. Drop test

The drop test conducted in the present disclosure is based on Neyer drop test as follows.

30 pcs filled pouches are subject to a free-fall experiment from a height ranging from 73.9 cm to 182cm. Particularly, every single pouch is dropped for 4~5 times (2x base, 1x front, 1x back, 1x spout if have to face downward during dropping) from the height of 73.9 cm to see if it can pass (no leakage) or fails. If it can pass at the height of 73.9 cm, then the free-fall experiment will be repeated from an increased height until the height of 182cm or it fails at some height. The tolerable height is calculated by the average of maximum height minus 3 standard deviation for total 30 pcs as an outcome. Success criteria is the tolerable height ≥ 1.0 meter. Testing condition is room temperature (25°C).

Test 2. Tensile strength test

The tensile strength is measured on an Instron tensile tester under room temperature along both the machine direction and the transverse direction. The samples are obtained by cutting the body or the bottom of pouches into film strips having a width of 25.4mm and a length of 250mm. Tensile tester (cross head) moving speed is 300mm/min. The breaking force for each film strip is

recorded as the outcome, i.e., the tensile strength along the machine direction and the tensile strength along the transverse direction.

Test 3. Seal strength test

The seal strength is also measured on an Instron tensile tester under room temperature. The samples are obtained by cutting the sealed laminates at different locations of the pouch into film strips having a width of 25.4mm. For the side seal, the samples are obtained at 6 different locations (3 for left and 3 for right), and for the bottom seal, the samples are obtained at 6 different locations (3 for front and 3 for back). Tensile tester (cross head) moving speed is 300mm/min. The average of separation forces for film strips from both different locations of the side seal and different locations of the bottom seal are recorded as the outcome, i.e., the seal strength of the side seal and the seal strength of the bottom seal.

Test 4. Measurements of initial sealing temperature

The initial sealing temperature is measured on a hot tack equipment (SL-10 from Testing Machines Inc., New Castle – Delaware, USA) which can precisely control the temperature, time and pressure of heat seal by setting the control panel. The samples are heated on the equipment under 4bar, 0.72s by using different temperatures (starting from a relatively low temperature) to determine if it can be sealed. If it cannot be sealed, the test is repeated at a higher temperature. The minimum temperature interval for this equipment can be 1°C. If the sample can be sealed starting from a certain temperature, such temperature is recorded as the initial sealing temperature.

EXAMPLES

Example 1. Drop test for Stand Up Pouches with mono-polymer PE laminates

Pouches were made respectively using different mono-polymer PE laminates in which Laminate 1 had a 3-layer structure (MDO-PE, BO-PE and PE) and Comparative Laminates 1 and 2 had a 2-layer structure (MDO-PE and PE for Comparative Laminate 1 and BO-PE and PE for Comparative Laminate 2). Each laminate was prepared by dry lamination, in which an adhesive was applied on one layer of film, dried and then put another layer of film onto the adhesive surface to form bond. In case of 3-layer structure, the same process was applied again between a third layer of film and the 2-layer laminate. The specific structures of Laminate 1 and Comparative Laminate 1 and 2 are shown in the following Table 1. The initial sealing

temperatures for MDO-PE, BO-PE and PE as measured by the method according to Test 4 are $>155^{\circ}\text{C}$, 125°C and 125°C , respectively.

Stand Up Pouches (SUPs) were made by using Laminate 1 and Comparative Laminates 1 and 2. The SUP comprised three panels which were front panel, back panel and bottom panel. The pouch making process included film slitting, body panels (front panel and back panel) two-side sealing, bottom panel two-side sealing, Gusset part four-side sealing, Gusset punching, and spout insertion. Particularly, the bottom panel was a rectangle which could be folded at the centerline horizontally. The two edges of the bottom panel along the longer side were sealed with the front and back panels respectively. At the gusset part, the body panels two-side sealing and the gusset part four-side sealing were formed simultaneously. The SUP was made by using Totani BH-60D pouch making machine from Totani, Kyoto, Japan (sealing temperatures: 125 to 130°C and sealing pressures: 3 to 4 bar). The spout was inserted in a continuous spout insertion machine.

The pouches made of Laminate 1 as well as Comparative Laminate 1 and 2 had the identical design, i.e., the design of the pouch for Ariel Japan, 1.35kg heavy detergent liquid (pouch dimension was Width 198mm, Height 272mm, Gusset Depth 55mm). The MDO-PE and BO-PE film used in all these laminates were identical. The blown PE used across all these laminates were with identical PE composite and only varies in the thickness. Pouches for all these three laminates were formed on the same pouch making machine. Pouches were successfully prepared by using Laminate 1 and Comparative Laminate 1, but Pouches were failed to be made by using Comparative Laminate 2 because the pouches could not be heat-sealed without sealing problems. Particularly, the pouches for Comparative Laminate 2 were either not well sealed leaving weak or open seals, or over sealed with significantly wrinkled or burnt seals. No operational window was found on the pouch making machine. Water was filled with target filling weight of 1.36kg.

Table 1. Structures of mono-polymer PE laminates

	Laminate 1	Comparative Laminate 1	Comparative Laminate 2
Outer layer	MDO-PE ¹ , 25 μm	MDO-PE, 25 μm	BO-PE, 20 μm
Middle layer	BO-PE ² , 20 μm	-	-
Inner layer	Blown PE ³ , 140 μm	Blown PE ⁴ , 170 μm	Blown PE, 170 μm
Total thickness	~ 185 to 190 μm ⁵	~ 195 to 200 μm	~ 190 to 195 μm

1: MDO-PE from Huangshan Novel Co., Ltd., Huangshan, Anhui, China

- 2: BO-PE from Guangdong Decro Film New Materials co., ltd., Foshan, Guangdong, China
- 3: Blown PE from Huangshan Novel Co., Ltd., Huangshan, Anhui, China
- 4: Blown PE from Huangshan Novel Co., Ltd., Huangshan, Anhui, China
- 5: The total thickness comprises thickness of all PE layers and thickness of adhesive between PE layers.

The drop test was conducted according to Test 1. 30 pcs of pouches prepared as above were subject to the drop test under room temperature. The tolerable height was calculated by the average of maximum height minus 3 standard deviation for total 30 pcs. The results of the drop test are shown in Table 2 below, in which Laminate 1 shows significant better drop resistance than Comparative Laminate 1, although Laminate 1 has a thinner total thickness than Comparative Laminate 1.

Table 2. Results of the drop test

	Tolerable height	Note
Laminate 1	>182.0cm	21 pcs passed 182.0cm
Comparative Laminate 1	83.4cm	0 pcs passed 182.0cm

Example 2. Improved tensile strength of 3-layer mono-polymer PE laminates compared to 2-layer mono-polymer PE laminates

Laminate 1 and Comparative Laminate 1 were subject to the tensile strength test according to Test 2. The results of the tensile strength test are shown in Table 3 below in which Laminate 1 shows significant improved tensile strength especially in transverse direction compared to Comparative Laminate 1, although Laminate 1 has a thinner total thickness than Comparative Laminate 1.

Table 3. Results of the tensile strength test

	Machine direction (N/inch)	Transverse direction (N/inch)
Laminate 1	178.87	167.06
Comparative Laminate 1	175.46	128.00

Example 3. Improved sealing strength of 3-layer mono-polymer PE laminates compared to 2-layer mono-polymer PE laminates

Samples were taken from different locations including at least three locations at bottom and at least three locations at side of the stand-up bags prepared in Example 1, and then subject to the sealing strength test according to Test 3. The results of the sealing strength test are shown in Table 4 below in which Laminate 1 shows much higher sealing strength for bottom seal of the stand-up bags compared to Comparative Laminate 1, although Laminate 1 has a thinner total thickness than Comparative Laminate 1.

Table 4. Results of the sealing strength test

	Side seal (N/inch)	Bottom seal (N/inch)
Laminate 1	115.2	130.7
Comparative Laminate 1	124.9	62.0

The dimensions and values disclosed herein are not to be understood as being strictly limited to the exact numerical values recited. Instead, unless otherwise specified, each such dimension is intended to mean both the recited value and a functionally equivalent range surrounding that value. For example, a dimension disclosed as “40 mm” is intended to mean “about 40 mm.”

Every document cited herein, including any cross referenced or related patent or application and any patent application or patent to which this application claims priority or benefit thereof, is hereby incorporated herein by reference in its entirety unless expressly excluded or otherwise limited. The citation of any document is not an admission that it is prior art with respect to any invention disclosed or claimed herein or that it alone, or in any combination with any other reference or references, teaches, suggests or discloses any such invention. Further, to the extent that any meaning or definition of a term in this document conflicts with any meaning or definition of the same term in a document incorporated by reference, the meaning or definition assigned to that term in this document shall govern.

While particular embodiments of the present invention have been illustrated and described, it would be obvious to those skilled in the art that various other changes and modifications can be made without departing from the spirit and scope of the invention. It is therefore intended to cover in the appended claims all such changes and modifications that are within the scope of this invention.

CLAIMS

What is claimed is:

1. A container comprising a laminate comprising:
 - i) a first layer of machine direction oriented polyethylene (MDO-PE),
 - ii) a second layer of biaxial oriented polyethylene (BO-PE), and
 - iii) a third layer of polyethylene (PE).
2. The container according to claim 1, wherein the total thickness of the laminate is from 70 microns to 400 microns, preferably from 100 microns to 350 microns, more preferably from 120 microns to 300 microns, most preferably from 140 microns to 250 microns; and/or
wherein the first layer has a thickness of from 5 microns to 50 microns, preferably from 10 microns to 45 microns, more preferably from 15 microns to 40 microns, most preferably from 20 microns to 30 microns; and/or
wherein the second layer has a thickness of from 5 microns to 50 microns, preferably from 8 microns to 45 microns, more preferably from 12 microns to 40 microns, most preferably from 15 microns to 25 microns; and/or
wherein the third layer has a thickness of from 10 microns to 250 microns, preferably from 30 microns to 230 microns, more preferably from 100 microns to 200 microns, most preferably from 120 microns to 160 microns.
3. The container according to claim 1 or 2, wherein said container is recyclable, preferably wherein said laminate comprises no more than 10% by weight, preferably no more than 7%, more preferably no more than 5%, most preferably no more than 3%, of thermoplastic polymer that is not PE.
4. The container according to any one of claims 1 to 3, wherein said laminate has a tensile strength along the machine direction as measured by the method according to Test 2 of more than 100 N/inch, preferably more than 120 N/inch, more preferably more than 130 N/inch, most preferably more than 140 N/inch; and/or
wherein said laminate has a tensile strength along the transverse direction as measured by the method according to Test 2 of more than 100 N/inch, preferably more than 120 N/inch, more preferably more than 130 N/inch, most preferably more than 140 N/inch; and/or

wherein said laminate has a sealing strength at the side seal as measured by the method according to Test 3 of more than 70 N/inch, preferably more than 80 N/inch, more preferably more than 90 N/inch, most preferably more than 100 N/inch; and/or

wherein said laminate has a sealing strength at the bottom seal as measured by the method according to Test 3 of more than 70 N/inch, preferably more than 80 N/inch, more preferably more than 90 N/inch, most preferably more than 100 N/inch.

5. The container according to any one of claims 1 to 4, wherein said container is a flexible bag, preferably a flexible stand-up bag.
6. The container according to any one of claims 1 to 5, wherein said container contains from 0.05 kg to 10kg, preferably 0.1 kg to 5 kg, more preferably 0.2kg to 3 kg of product.
7. The container according to claim 6, wherein said product is selected from the group consisting of fabric care products, home care products, hair care products, beauty care products, and personal care products, preferably a laundry detergent product, more preferably a granule laundry detergent or a liquid laundry detergent.
8. The container according to any one of claims 1 to 7, wherein the layers in said laminate are arranged as being i), ii), and iii) or ii), i) and iii) in turn from outside to inside.
9. The container according to any one of claims 1 to 8, wherein said first layer has an initial sealing temperature of at least 130°C, preferably at least 135°C, more preferably at least 140°C, most preferably at least 145°C, as measured by the method according to Test 4; and wherein said laminate has an initial sealing temperature of no more than 125°C, preferably no more than 120°C, more preferably no more than 118°C, most preferably no more than 115°C, as measured by the method according to Test 4.
10. A laundry detergent bag containing from 0.1 kg to 5 kg of laundry detergent, wherein the bag is constructed from a laminate comprising:
 - i) a first layer of MDO-PE,
 - ii) a second layer of BO-PE, and
 - iii) a third layer of PE.

11. The laundry detergent bag according to claim 10, wherein the total thickness of the laminate is from 70 microns to 400 microns, preferably from 100 microns to 350 microns, more preferably from 120 microns to 300 microns, most preferably from 140 microns to 250 microns; and/or

wherein the first layer has a thickness of from 5 microns to 50 microns, preferably from 10 microns to 45 microns, more preferably from 15 microns to 40 microns, most preferably from 20 microns to 30 microns; and/or

wherein the second layer has a thickness of from 5 microns to 50 microns, preferably from 8 microns to 45 microns, more preferably from 12 microns to 40 microns, most preferably from 15 microns to 25 microns; and/or

wherein the third layer has a thickness of from 10 microns to 250 microns, preferably from 30 microns to 230 microns, more preferably from 100 microns to 200 microns, most preferably from 120 microns to 160 microns.

12. The laundry detergent bag according to claim 10 or 11, wherein said laminate has a tensile strength along the machine direction as measured by the method according to Test 2 of more than 100 N/inch, preferably more than 120 N/inch, more preferably more than 130 N/inch, most preferably more than 140 N/inch; and/or

wherein said laminate has a tensile strength along the transverse direction as measured by the method according to Test 2 of more than 100 N/inch, preferably more than 120 N/inch, more preferably more than 130 N/inch, most preferably more than 140 N/inch; and/or

wherein said laminate has a sealing strength at the side seal as measured by the method according to Test 3 of more than 70 N/inch, preferably more than 80 N/inch, more preferably more than 90 N/inch, most preferably more than 100 N/inch; and/or

wherein said laminate has a sealing strength at the bottom seal as measured by the method according to Test 3 of more than 70 N/inch, preferably more than 80 N/inch, more preferably more than 90 N/inch, most preferably more than 100 N/inch.

13. A laminate comprising:

- i) a first layer of MDO-PE,
- ii) a second layer of BO-PE, and
- iii) a third layer of PE.

14. The laminate according to claim 13, wherein the total thickness of the laminate is from 70 microns to 400 microns, preferably from 100 microns to 350 microns, more preferably from 120 microns to 300 microns, most preferably from 140 microns to 250 microns; and/or
- wherein the first layer has a thickness of from 5 microns to 50 microns, preferably from 10 microns to 45 microns, more preferably from 15 microns to 40 microns, most preferably from 20 microns to 30 microns; and/or
- wherein the second layer has a thickness of from 5 microns to 50 microns, preferably from 8 microns to 45 microns, more preferably from 12 microns to 40 microns, most preferably from 15 microns to 25 microns; and/or
- wherein the third layer has a thickness of from 10 microns to 250 microns, preferably from 30 microns to 230 microns, more preferably from 100 microns to 200 microns, most preferably from 120 microns to 160 microns.
15. The laminate according to claim 13 or 14, wherein said laminate has a tensile strength along the machine direction as measured by the method according to Test 2 of more than 100 N/inch, preferably more than 120 N/inch, more preferably more than 130 N/inch, most preferably more than 140 N/inch; and/or
- wherein said laminate has a tensile strength along the transverse direction as measured by the method according to Test 2 of more than 100 N/inch, preferably more than 120 N/inch, more preferably more than 130 N/inch, most preferably more than 140 N/inch; and/or
- wherein said laminate has a sealing strength at the side seal as measured by the method according to Test 3 of more than 70 N/inch, preferably more than 80 N/inch, more preferably more than 90 N/inch, most preferably more than 100 N/inch; and/or
- wherein said laminate has a sealing strength at the bottom seal as measured by the method according to Test 3 of more than 70 N/inch, preferably more than 80 N/inch, more preferably more than 90 N/inch, most preferably more than 100 N/inch.




FIG. 1




FIG. 2

INTERNATIONAL SEARCH REPORT

International application No.

PCT/CN2020/113202

A. CLASSIFICATION OF SUBJECT MATTER

B32B 27/32(2006.01)i; C08J 5/18(2006.01)i; B29C 55/12(2006.01)i; B29C 55/04(2006.01)i; B29C 55/18(2006.01)i;
B65D 30/02(2006.01)i; B32B 27/30(2006.01)i; B65D 30/08(2006.01)i

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

B32B27/-; C08J5/-; B29C55/-; B65D30/-

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, EPODOC, STN, CNKI, CNPAT: laminate, polyethylene, PE, polyolefin, container, machine w direction w oriented, MDO-PE, MD, biaxial, oriented, BOPE, BO-PE, longitudinal, first w layer, outer W layer, barrier W layer, lower layer, second w layer, third w layer, thickness, upper, middle, flexible w bag, stand-up, recyclable

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	JP H07241967 A (TOPPAN PRINTING CO. LTD.) 19 September 1995 (1995-09-19) description, paragraphs 0001, 0015-0018, 0025-0027	1-15
Y	US 2012033901 A1 (VOTAW BRIAN E.) 09 February 2012 (2012-02-09) description, paragraphs 0008, 0018, 0021	1-15
A	CN 110770016 A (DOW GLOBAL TECHNOLOGIES INC.) 07 February 2020 (2020-02-07) description, paragraphs 0006-0010	1-15
A	CN 107683206 A (DOW GLOBAL TECHNOLOGIES INC.) 09 February 2018 (2018-02-09) description, paragraphs 0004-0006, 0019-0024	1-15
A	CN 87104944 A (CANADIAN IND. LTD.) 03 February 1988 (1988-02-03) description, page 1 paragraph 1-page 11 paragraph 3	1-15

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents:

“A” document defining the general state of the art which is not considered to be of particular relevance
“E” earlier application or patent but published on or after the international filing date
“L” document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
“O” document referring to an oral disclosure, use, exhibition or other means
“P” document published prior to the international filing date but later than the priority date claimed

“T” later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
“X” document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
“Y” document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
“&” document member of the same patent family

Date of the actual completion of the international search

20 May 2021

Date of mailing of the international search report

01 June 2021

Name and mailing address of the ISA/CN

**National Intellectual Property Administration, PRC
6, Xitucheng Rd., Jimen Bridge, Haidian District, Beijing
100088
China**

Authorized officer

WANG, Lina

Facsimile No. (86-10)62019451

Telephone No. (86)-10-53962217

INTERNATIONAL SEARCH REPORT
Information on patent family members

International application No.

PCT/CN2020/113202

Patent document cited in search report			Publication date (day/month/year)	Patent family member(s)	Publication date (day/month/year)
JP	H07241967	A	19 September 1995	JP H07241967 A	19 September 1995
US	2012033901	A1	09 February 2012	None	
CN	110770016	A	07 February 2020	JP 2020526412 A	31 August 2020
				WO 2019006053 A1	03 January 2019
				AR 112245 A1	09 October 2019
				BR 112019026858 A2	30 June 2020
				EP 3645272 A1	06 May 2020
				MX 2019015423 A	17 February 2020
CN	107683206	A	09 February 2018	JP 2018520908 A	02 August 2018
				CN 107683206 B	25 December 2020
				EP 3317103 B1	02 September 2020
				CO 2018000357 A2	10 April 2018
				JP 6691141 B2	28 April 2020
				AR 105037 A1	30 August 2017
				EP 3317103 A1	09 May 2018
				PL 3317103 T3	25 January 2021
				US 2018099492 A1	12 April 2018
				WO 2017000339 A1	05 January 2017
				EP 3317103 A4	16 January 2019
				MX 2017016000 A	20 April 2018
				BR 112017026912 A2	14 August 2018
CN	87104944	A	03 February 1988	US 4680207 A	14 July 1987
				AU 7343987 A	28 January 1988
				DK 385187 D0	23 July 1987
				EP 0260791 A2	23 March 1988
				DE 3783186 T2	22 April 1993
				EP 0260791 A3	26 October 1988
				NO 172739 C	01 September 1993
				FI 873003 A	24 January 1988
				NO 172739 B	24 May 1993
				ZA 874565 B	24 February 1988
				CA 1286642 C	23 July 1991
				NO 873068 L	25 January 1988
				NZ 220697 A	29 August 1989
				ZA 8704565 A	24 February 1988
				DK 385187 A	24 January 1988
				NO 873068 A	25 January 1988
				DK 168329 B1	14 March 1994
				FI 873003 A0	07 July 1987
				EP 0260791 B1	23 December 1992
				JP S6344447 A	25 February 1988
				DE 3783186 D1	04 February 1993
				FI 94401 C	11 September 1995
				NO 873068 D0	22 July 1987
				AR 245416 A1	31 January 1994
				FI 94401 B	31 May 1995
				BR 8703753 A	29 March 1988
				MX 168033 B	29 April 1993
				AU 587548 B2	17 August 1989