



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C04B 41/81	A1	(11) International Publication Number: WO 00/10941 (43) International Publication Date: 2 March 2000 (02.03.00)
(21) International Application Number: PCT/EP99/06086 (22) International Filing Date: 19 August 1999 (19.08.99) (30) Priority Data: MI98A001913 21 August 1998 (21.08.98) IT (71)(72) Applicant and Inventor: VIGNALI, Graziano [IT/IT]; Via Della Pace, 2, I-40037 Sasso Marconi (IT). (72) Inventor; and (75) Inventor/Applicant (for US only): GUIZZARDI, Fabrizio [IT/IT]; Via Gabella, 1, I-40129 Bologna (IT). (74) Agent: GERVASI, Gemma; Notarbartolo & Gervasi, Corso di Porta Vittoria, 9, I-20122 Milan (IT).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: FORMULATIONS BASED ON WATER SOLUBLE GOLD COMPOUNDS SUITABLE FOR COLOURING CERAMIC MANUFACTURED ARTICLES (57) Abstract Composition whereby ceramic manufactured articles are coloured in shades from pink to purple to violet, said composition consisting of a monovalent gold thiolate water solution or mixture of water with a water soluble organic solvent according to the following formulas: Au-S-R-X and Au-S-R-H, where R stands for a linear or branched bivalent radical of aliphatic or aromatic or cycloaliphatic or heterocyclic type optionally with substituents, such as for example aminic, amidic, hydroxylic, carboxylic, hydrocarbylic or carbonylic groups or CONH-, in the chain; X stands for a monovalent group selected out of -COOH, SO ₂ OH, -OH, -CONH ₂ , -NH ₂ ; O-P(O)(OH) ₂ , in which H atoms may be replaced by alkyl groups and wherein acid groups may be salified with amines or alkaline or alkaline earth metals and basic groups may optionally be salified with organic acids.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

FORMULATIONS BASED ON WATER SOLUBLE GOLD COMPOUNDS SUITABLE FOR COLOURING CERAMIC MANUFACTURED ARTICLES

Field of the invention

The present invention relates to compositions suitable for colouring ceramic
5 manufactured articles and to the relevant colouring process.

In particular, the compositions of the invention consist of water solutions or
solutions of water and water-miscible solvents, of gold organic complexes
compatible with other colouring cations optionally present in the solution releasing
low quantities of corrosive vapours during the firing cycle.

10 Said solutions allow the obtainment of ceramic manufactured articles in shades
from pink to purple to violet after a firing cycle ranging from 750°C to 1,300°C.

State of the art

The use of coloured ceramic manufactured articles as well as the compositions
and process adopted to obtain the relevant colours have been known since long.

15 One of the methods most commonly used consists in the addition of powdered
pigments, in particular inorganic oxides and mineral colouring matters, to the
ceramic mixture (vitrified stoneware) before firing. The ceramic manufactured
article is thus coloured through its whole thickness, although with large
consumption of colouring matter, which is the most expensive component.

20 According to a process used, the surface of the ceramic material is caused to
absorb, either after partial firing (as disclosed e.g. in German patent 2,012,304) or
simply after moulding and before firing (as disclosed e.g. in Swiss patent
575,894), a water solution of inorganic salts or metal complexes (as disclosed e.g.
in Sprehsal, vol. 119, No. 10, 1986, in EP 0704411 and in patent PCT, WO
25 97/38952), which become stable colours at high temperature during the ceramic
firing cycle.

The water solution is applied to the ceramic material before final firing. This
process is particularly advantageous because it allows the colouring of very thin
layers: therefore, it is widely used for flat manufactured articles (such as e.g. floor
30 and wall tiles).

Another problem to be solved when using colours in a water solution is the obtainable depth of colour penetration into the ceramic material. In fact, it was experimentally found that the depth of penetration depends on several parameters, such as the viscosity and surface tension of the colouring solution, the application temperature, the quantity of water optionally sprayed on the manufactured article once the colouring solution has been applied. The water solution is applied to the ceramic manufactured article by immersion, spraying, disk, and silk-screen techniques.

Of cardinal importance is the application technique: in particular, the quantity of colouring solution that may be applied by disk and spraying techniques is as high as 400 to 600 g/m²; by silk-screen type techniques it usually amounts to 100 to 200 g/m² and sometimes even to 400 g/m², when thickened screens made of a small number of threads are used.

Silk-screen type techniques are very much in demand, being the only techniques allowing graphic decorations and drawings, which otherwise cannot be obtained, and requiring lower quantities of colouring matter. When said techniques are used, the colouring solutions are to be thickened with appropriate thickening agents, e.g. modified glucomannans, starch and modified starch derivatives, cellulose and modified cellulose derivatives, or other polymeric substances, soluble or dispersible in a water solution.

Colour penetration into the ceramic material before firing can be obtained by spraying relatively high quantities of water on the manufactured article after application of the colouring solution. However, the resulting colours are less intense than those obtained using other techniques.

Colour penetration into the material is particularly important in the case of "smoothed" vitrified stoneware tiles.

The term "smoothed" means that the vitrified stoneware surface has been abraded with diamond wheels by 0.8 to 1.5 mm and subsequently smoothed or polished with appropriate felt until obtaining a glassy surface.

It follows that colour penetration into stoneware articles to be smoothed after firing must reach a depth of 1.6 mm min.

Other methods have been developed for the smoothing of very thin (1 to 10 μ) surface layers of the manufactured article.

Prior art

The use of water solutions of gold compounds for the colouring also in-depth of ceramic manufactured articles is well known. The compounds disclosed in German patent 4,320,072 for said application substantially are gold chlorides also reported in the preceding literature (cf. "Encyclopedia der technischen Chemie", F. Ullmann, 1929, vol. 4, pp. 837-838). However, the gold chloride solution suffers from the inconvenience of being strongly acid, as it contains hydrochloric acid. In the absence of excess hydrochloric acid, the solution is unstable and the gold compound hydrolyses easily with formation of insoluble compounds.

It follows that the solution is corrosive and impairs the apparatus used. In particular, in the case of silk-screen type technique, it rapidly impairs the printing screen.

WO 97/21646 discloses the use of gold sodium thiosulphate solutions, $\text{Na}_3\text{Au}(\text{S}_2\text{O}_3)_2$, stabilised with sodium sulphite, for ceramic surfaces colouring by water solution absorption.

From the compositions of solutions 1, 2, and 3 described therein, it is possible to calculate that 4.7 g SO_2 or 5.88 g SO_3 , or an intermediate value in the case of mixtures thereof is released per g Au deposited on the surface.

In both cases (use of gold chloride and gold thiosulphate), high amounts of strongly corrosive vapours rapidly impairing the heater metal structures, are released. Therefore, vapours are to be abated to prevent the emission of same into the environment.

The use of precious metals water solutions in high concentrations, in the form of thiol derivatives, to obtain thin metal films for decorative purposes, e.g. for dishes, or for electronic purposes, e.g. for printed circuits, is already known.

The following are examples of said use:

1. US patent No. 5,545,452 discloses the use of Au thiolates water solutions with a metal content of 2 to 25% by wt. (column 3, rows 10 to 20) to obtain thin metal films for decorative purposes (column 1, rows 38 to 40);

2. EP No. 514,073, like the US patent above, discloses the use of thiolates water solutions to obtain thin films made of Au or other precious metals to decorate the outer surface, and not the inside, of baked ceramic manufactured articles.

Technical problem

5 Considering that it is very simple to colour ceramic materials by disk, spraying and silk-screen techniques, the ceramic industry is highly interested in the possibility of using colouring water solutions based on gold to be applied by said techniques, and offering the advantage of

- 10 • releasing the lowest possible quantity of very noxious or corrosive vapours in the heater;
- being compatible with water solutions of organic derivatives of other cations used for the superficial and in-depth colouring of ceramic manufactured articles.

Therefore, it is an object of the present invention to provide colouring formulations in the form of water solutions, which

- 15 • release low quantities of corrosive vapours (≤ 2 g SO₂/g Au deposited);
- are compatible with water solutions of organic derivatives of other cations used for the superficial and in-depth colouring of ceramic manufactured articles;
- colour the ceramic manufactured articles at their surface and to a depth of at least 1 mm.

20 The Applicant, who has full-fledged experience in the production and sale of colouring matters for ceramic tiles, has now found that water solutions or water mixtures with alcohols or other water-miscible organic solvents, of monovalent gold organic derivatives, can be used to obtain - after firing - colour shades varying from pink to purple to violet on manufactured articles consisting of a
25 conventional ceramic mixture.

The water or hydroalcoholic solutions being an object of the present invention are particularly useful for colouring tiles of vitrified stoneware, either at their surface or to a depth of 1 to 3 mm from their surface.

In-depth colouring is essential for maintaining the manufactured article decoration
30 after smoothing.

It is, therefore, a fundamental feature of the present invention to use water solutions or water mixtures with hydrophilic organic solvents, of gold organic complexes, which are compatible with derivatives of other cations and release low quantities of corrosive vapours (≤ 2 g SO₂/g Au deposited).

5 Said solutions are used to treat ceramic articles before firing. This makes it possible, after firing, to obtain pink, purple and violet coloured articles, when solutions contain gold only, or new colour shades when solutions are mixed with derivatives of one or several of the following cations: Fe, Cr, Co, Mn, Cu, Ru, Pd, Zr, V, Ni, Sb, W, Zn, Sn.

10 The gold compounds that may be used according to the present invention belong to the class of monovalent gold thiolates, wherein Au is bound to an S atom, and are substantially represented by the following general formulas:

Au-S-R-X and Au-S-R-H

15 where R stands for a linear or branched bivalent radical of aliphatic or aromatic or cycloaliphatic or heterocyclic type, optionally with substituents, such as for example aminic, amidic, hydroxylic, carboxylic, hydrocarbylic or carbonylic groups or CONH-, in the chain;

X stands for a monovalent group selected out of -COOH, SO₂OH, -OH, -CONH₂, -NH₂; -O-P(O)(OH)₂, in which H atoms may be replaced by alkyl groups and
20 wherein acid groups may be salified with amines or alkaline or alkaline earth metals and basic groups may optionally be salified with organic acids.

In particular, monovalent Au thiolates to be used according to the present invention may be in the form of alkaline, alkaline earth metal salts or of variously substituted amines.

25 The water solutions of Au compounds according to the invention are stable, substantially neutral and release a quantity of corrosive vapours of 2 g SO₂ max./g Au deposited on the manufactured article surface to be coloured.

Said solutions are used in quantities corresponding to 0.1 to 20 g Au (as element) per m² of surface to be coloured.

30 By way of example, the gold thiolates that may be used according to the invention derive from:

(N) acetylcysteine: $\text{H-S-CH}_2\text{-}\underset{\begin{array}{c} | \\ \text{NHCOCH}_3 \end{array}}{\text{CH-COOH}}$

The compatibility of the gold thiolates according to the invention with the ceramic colouring systems based on metallic compounds (in particular of Fe, Ni, Cr, Co, Sn, Mn, Cu, Ru, Pd, Zr, V, Sb, W, Zn, Sn) in aqueous solutions has been ascertained through stability tests of the aqueous solutions containing beside Au thiolate also one or more compounds of the above mentioned metals and also through ceramic coloration tests by the same aqueous solutions after ageing. Unforeseeable very valuable colours were obtained.

Gold thiolates to be used according to the invention may generally be prepared by causing an Au(III), in the form of a tetrachloroauric acid, to react in water solution with a thioether $S(R')_2$, giving the reduction of Au(III) to Au(I), and then with the desired thiol HSR'' ($R'' = -RX$ or $-RH$ as per the general formulas shown above): This method, described in *Inorganic Synthesis*, 23 (1985) pp. 191-195, is based on some reactions reported therein.

A typical process for applying colouring compositions according to the invention consists in the following steps:

- a) drying at 100°C of the article to be coloured to a water residue of 0.5% by wt. max.;
 - a.1) pre-treatment, if any, of the dried article with water up to a max. quantity of 300 g/m² manufactured article;
- b) treatment of the pre-treated article with a water solution of the colouring composition in a quantity of 30 to 600 g/m² of the final coloured surface;
 - b.1) post-treatment, if any, of the treated article with water up to a max. quantity of absorbed water of 300 g/m² ceramic manufactured article;
- c) equalisation of the post-treated article at room temperature for 8 hours to homogenise the solution absorption;
- d) oven firing according to the usual ceramic cycle at a temperature of 1,000 to 1,300°C.

The concentration of Au thiolate solution to be used according to the invention generally ranges from 0.1 to 2% Au (expressed as element).

Some examples of the colours obtained by experimental runs are shown in the Table 1 reported hereinafter.

All runs were carried out on the basis of the following process:

- 1) drying at 100°C of two 33x33 cm supports made of mixture A to a water residue of 0.5% by wt. max.;
- 2) supports cooling to room temperature;
- 5 3) deposition of 0.4 g of each solution on 10 cm² of surface of each support;
- 4) supports equalisation at room temperature for 2 hrs and for additional 2 hrs in a thermoventilated oven at 60°C to homogenise the solutions absorption;
- 5) oven firing according to the usual ceramic cycle;
- 6) removal of a surface layer (0.8-0.9 mm) and smoothing;
- 10 7) colour detection on non-smoothed and smoothed support;
- 8) non-smoothed support cutting and penetration depth detection.

Table 1

Ex. n°	Complexing agent % element	Colour before smoothing	Colour after smoothing	Penetration (mm)
5 1	D,L mercaptosuccinic acid, 0.4% gold	Parma red	Pink	1.2
2	acetylcysteine, 0.4% gold	Pink	Light pink	2
3	thiolactic acid, 0.4% gold	Pink	Light pink	2
4	cysteine, 0.4% gold	Parma red	Pink	1.4

10

The composition of the ceramic mixture used is as follows (% by wt.)

SiO₂ 64.4%; Al₂O₃ 21.8%; K₂O 3.8%; Na₂O 0.8%; CaO 0.6%; MgO 0.1%; TiO₂ 0.3%; Fe₂O₃ 0.2%; ZrSiO₄ 5%; H₂O to 100%.

Colours are as per the Colour Atlas.

15 Example 5

Compatibility of some Au thiolates with other cations

Compatibility tests were carried out with the following water solutions: Au acetylcysteinate prepared with the method disclosed in the following at page 11, line 6 and diluted up to 0.4% Au, Au mercaptosuccinate (0.4% Au), cobalt ammonium citrate (2% Co), Ni ammonium citrate (2% Ni); chromium ammonium citrate (2% Cr), iron ammonium citrate (Fe 2%), tin glycolate (Sn 2%).

20

The mixtures consist of Au derivative solution (50%) and of another cation solution (50%).

The results obtained, after the days reported below, are as follows:

	Au acetylcysteinate	Au mercaptosuccinate
5	Co 30 days, clear solution	30 days, clear solution
	60 days, clear solution	60 days, clear solution
	colour turned from reddish violet to wine red	--
	Ni 30 days, clear solution	30 days, clear solution
	60 days, clear solution	60 days, clear solution
10	Cr 30 days, clear solution	30 days, clear solution
	60 days, slightly opaque sol.	60 days, slightly opaque sol.
	Fe 30 days, clear solution	30 days, clear solution
	60 days, clear solution	60 days, clear solution
15	Sn 30 days, clear solution	30 days, clear solution
	60 days, clear solution	60 days, clear solution

Example 6

The compatibility of some Au thiolate according to the invention with other colouring cations has been tested in comparison with two Au compounds of the prior art, namely NaAuCl_4 and gold-sodium thiosulphate $\text{Na}_3\text{Au}(\text{S}_2\text{O}_3)_2$. The obtained results are reported in Tables 3 and 4.

The tested products in form of aqueous solutions containing 1% by w. Au are prepared as follows.

Product (1) Au thiolacetate (Au-TL/3)

30 g aqueous solution of tetrachloroauric acid (corresponding to 1 g Au) is added with aqueous solution of NaOH up to a pH of 8 (solution A). Thiolactic acid 1.65 g is dissolved in 30 g H_2O and added with NH_4OH aqueous solution 30% by w. up to a pH = 7 (solution B). The solution B is added to the solution A, then the mixture is added with NH_4OH up to pH 9 and with H_2O up to a total weight of 100 g.

Product (2) Au sodium thiosulphate (Au-Bk.Giulini)

30 Comparison test.

In 91.6 g of H₂O are dissolved 1.7 g Na₃Au(S₂O₃)₂ and 6.7 g of Na sulphite (molar ratio Au/Na₂SO₃ = 0.9/10) as disclosed by WO97/21646 in Table 3. This ratio is the best as it regards the stabilization of the solution as declared by the Applicant: no precipitate occurs in the solution when it comes in contact with a piece of metal.

Product (3) Au acetylcysteine (Au/CST)

30 g of aqueous solution of tetrachloroauric acid (corresponding to 1 g Au) are added with NaOH aqueous solution up to a pH of 8 (solution A). N-acetylcysteine 5.1 g in 30 g H₂O are added with NH₄OH aqueous solution 30%, up to a pH of 7 (solution B). The solution B is added to the solution A, then the mixture is added with NH₄OH up to pH 9.5 and with H₂O up to a total amount of 100 g.

Product (4) Au acetylcysteine (Au-CST/9)

30 g of aqueous solution of tetrachloroauric acid (≈ 1 g Au) are added with NaOH aqueous solution up to a pH 8 (solution A). N-acetylcysteine 5.1 g in 30 g H₂O are added with NaOH aqueous solution up to a pH 7 (solution B). The solution B is added to the solution A, then the mixture is added with NaOH up to pH 9 and with H₂O up to a total amount of 100 g.

Product (5) Au acetylcysteine (Au-CST/2)

30 g of aqueous solution of tetrachloroauric acid (≈ 1 g Au) are added with NaOH aqueous solution up to a pH of 8 (solution A). N-acetylcysteine 2.55 g in 30 g H₂O are added with NH₄OH 30% aqueous solution up to a pH 7 (solution B). The solution B is added to the solution A, then the mixture is added with NH₄OH up to a pH 9.5 and with H₂O up to a total amount of 100 g.

Product (6) NaAuCl₄ (Au-Cl)

Comparison test.

30 g of aqueous solution of tetrachloroauric acid (≈ 1 g Au) are added with NaOH aqueous solution up to a pH of 2.5 and with H₂O up to a total amount of 100 g.

Product (7) Au acetylcysteine (Au-CST/10)

30 g of aqueous solution of tetrachloroauric acid (≈ 1 g Au) are added with NaOH aqueous solution up to a pH of 8 (solution A). N-acetylcysteine 2.55 g in 30 g H₂O are added with NaOH aqueous solution up to a pH 7 (solution B). The solution B is

added to the solution A, then the mixture is added with NaOH up to a pH of 9.5 and with a H₂O up to a total amount of 100 g.

In the following Table 2 are reported the tested products with the neutralizing agent used (NaOH or NH₄OH) and the molar ratio between Au and SO₂ (or SO₃) developed during the ceramic firing of the treated manufactured articles.

The Au acetylcysteine solutions products 3 and 4 have been prepared using an excess of acetylcysteine and consequently these solutions show a content of S higher than in the products 5 and 7. The use of an excess of acetylcysteine affords an higher stability of the Au-acetylcysteine solution.

Table 2

Product n°	ref.	Au compound	Neutralizing agent	Au/SO ₂
1	Au-TL/3	Au thiolactate	NH ₄ OH+NaOH	1:1
2	Au -Bk.Giulini	Na-Au thiosulphate stabil. Na ₂ SO ₃	---	1:4.7
3	Au/CST	Au acetylcysteine	NH ₄ OH+NaOH	1:2
4	Au-CST/9	"	NaOH	1:2
5	Au-CST/2	"	NH ₄ OH+NaOH	1:1
6	Au-Cl	NaAuCl ₄	--	--
7	Au-CST/10	Au acetylcysteine	NaOH	1:1

The tests reported in the following tables 3 and 4 have been carried out with solutions consisting of mixtures of Au derivative solution (50%) and of other cations solutions (50%)

Table 3 - Comparative tests for Au-acetylcysteine and Au-thiolactate, reference product Na-Au thiosulphate (Au-Bk.Giulini)

Aqueous sol. %cations and pH	Au-TL/3 (1)	Au- Bk.Giulini (2)	Au-CST (3)	Au-CST/9 (4)
Co amm. Citrate Co=8% pH 7.5-8.5	60 d: OK	9 d: little XXX on the bottom 16 d: many XXX of both Au and Co, on the bottom and on the wall	60 d: OK	60 d: OK
Co amm. Citrate Co=4% pH 7.5-8.5	60 d: OK	23 d: some very little XXX 30 d: many XXX (ocher colour) 60 d: many XXX of Au and Co on the bottom and on the wall	60 d: OK	60 d: OK
NaSb tartrate Cr acetate Sb=12.8% Cr=1.8% pH 4.5-5	60 d: OK	8 d: little greyish sediment on the bottom 15 d: little greyish sediment on the bottom and on the wall 22 d: Au sed. on the bottom and on the wall	60 d: OK	60 d: OK
NaSb tartrate Cr acetate Sb=6.4% Cr=0.9% pH 4.5-5	60 d: OK	60 d: little dark sed. on the bottom	60 d: OK	60 d: OK
Cr amm. Citrate Cr=6.8% pH 7-8	60 d: OK	60 d: OK	60 d: OK	60 d: OK
Cr amm. Citrate Cr=3.4% pH 7-8	60 d: OK	60 d: OK	60 d: OK	60 d: OK

Aqueous sol. %cations and pH	Au-TL/3 (1)	Au- Bk.Giulini (2)	Au-CST (3)	Au-CST/9 (4)
Ni amm. Citrate Ni=7.6% pH 7-8	60 d: OK (transparent greenish sol.)	60 d: OK (transparent greenish sol.)	60 d: OK (dark sol.)	60 d: OK (dark sol.)
Ni amm. Citrate Ni=3.8% pH 7-8	60 d: OK (transparent greenish sol.)	60 d: OK (transparent greenish sol.)	60 d: OK (dark sol.)	60 d: OK (transparent green sol.)
Cu amm. Citrate Cu=8% pH 7.5-8.5	60 d: OK	60 d: little sediment on the bottom	60 d: OK	60 d: OK
Fe amm. Citrate Fe=9.8% pH 4.5-5	60 d: OK	60 d: OK	60 d: OK	60 d: OK
Fe amm. Citrate Fe=4.9 pH 4.5-5	60 d: very light, black dust	22 d: very light, black dust = 29 d 60 d: very light, black dust	60 d: OK	60 d: OK
Fe CTR/13 (see foot note)	60 d: OK	8 d: sediment on the bottom	60 d: OK	60 d: OK
Sn glycolate Sn=7.6% pH 4.5-5	60 d: OK	60 d: very light black sediment on the bottom	60 d: OK	60 d: sol. is gelled on all the wall and on the bottom of the test tube, but it is yet liquid and transparent
Mn amm. Citrate Mn=4.5% pH 7.8-8.8	60 d: OK	8 d: white precipitate on the bottom and on the walls	60 d: OK	60 d: OK

Aqueous sol. %cations and pH	Au-TL/3 (1)	Au- Bk.Giulini (2)	Au-CST (3)	Au-CST/9 (4)
Sodium metavanadate V=6.8% pH 9.5-10	60 d: OK	8 d: very light white sediment (=15 d = 22 d) 29 d: bright, light sediment	15 d: some very little black mote 22 d: some very little black mote 29 d: some black extended XXX (little rods) =60 d	60 d: OK
V glycolate V=8% pH 5-5.5	60 d: OK	29 d: very light black dust 60 d: ppt Au and V	60 d: OK	60 d: OK
Ru glycolate Ru=6% pH 2-2.5	28 d: ppt of Au on the wall 60 d: wall and bottom of the test tube coated by Au	7 d: remarkable black sediment 14 d: remarkable black sediment on the bottom and on the wall	60 d: OK	7 d: light black precipitate 14 d: very light black precipitate = 60 d
Ru glycolate Ru=3% pH 2-2.5	28 d: very light coat on the wall 60 d: Au on the wall and on the bottom	7 d: remarkable black precipitate. On the wall noticeable sediment of Au	60 d: OK	7 d: very light black precipitate 14 d: very light black precipitate = 60 d

d = days

XXX = crystals

5 ppt = precipitate

sol. = solution

Fe citr/13 = 10 g hydrate iron citrate Aldrich (Fe 18 ÷ 19%) in 20 g H₂O are added with 10 g of NH₄OH 30%, find pH = 7; Fe = 4.5 ÷ 4.75% by w.

Table 4 - Comparative tests for Au-acetylcysteine: reference product Na Au Cl₄ (Au-Cl)

Aqueous sol. %cations and pH	Au-CST/2 (5)	Au-Cl (6)	Au-CST/10 (7)
Co amm. Citrate Co=8% pH 7.5-8.5	60 d: OK	9 d: very light sed. sol. of violet colour 16 d: as 9 d 23 d: light sed. =30 d=60d	60 d: OK
Co amm. Citrate Co=4 pH 7.5-8.5	60 d: OK	9 d: OK sol. of violet colour 16 d: OK (violet sol.) 23 d: very light sed. 30 d: light sed. Au=60 d	60 d: OK
NaSb tartrate Cr acetate Sb=12.8% Cr=0.9% pH 4.5-5	60 d: OK	8 d: black ppt on the bottom 15 d: black ppt on the bottom and very weak on the wall =60 d	60 d: OK
NaSb tartrate Cr acetate Sb=6.4% Cr=0.9% pH 4.5-5	60 d: OK	8 d: black ppt on the bottom 15 d: black ppt on the bottom and very light on the wall =60 d	60 d: OK
Cr amm. Citrate Cr=6.8% pH 7-8	60 d: OK	8 d: light brownish sed. (from the colour it seems Au) 15 d: brownish sed.	60 d: OK
Cr amm. Citrate Cr=3.4% pH 7-8	60 d: OK	8 d: light brownish sed. (from the colour it seems Au) 15 d: light brownish sed 22 d: brownish sed	60 d: OK
Ni amm citrate Ni=7.6% pH 7-8	60 d: OK (green transparent sol.)	60 d: OK (green transparent sol.)	60 d: OK (greenish transparent sol.)

Aqueous sol. %cations and pH	Au-CST/2 (5)	Au-Cl (6)	Au-CST/10 (7)
Ni amm. citrate Ni=3.8% pH 7-8	60 d: OK (green transparent sol.)	60 d: OK (green transparent sol.)	60 d: OK (greenish transparent sol.)
Cu amm. citrate Cu=8% pH 7.5-8.5	60 d: OK	60 d: OK	60 d: OK
Fe amm. citrate Fe=9.8% pH 4.5-5	60 d: OK	8 d: ppt Au on the bottom and on the wall	60 d: OK
Fe amm. citrate Fe=4.9% pH 4.5-5	60 d: OK	8 d: ppt Au on the bottom and on the wall	60 d: OK
Fe-CTR/13	60 d: OK	8 d: sed. on the bottom (Au)	60 d: OK
Sn glycolate Sn=7.6% pH 4.5-5	60 d: OK	7 d: ppt Au	60 d: OK
Mn amm. citrate Mn=4.5%	60 d: OK	8 d: very light brownish sed. (=15 d=22 d=29g) 60 d: light black sed.)	60 d: OK
Sodium metavanadate V=6.8% pH 9.5-10	60 d: OK	60 d: very thin black film on the wall	60 d: OK
V glycolate V=8% pH 5-5.5	60 d: OK	8 d: brownish sed. on the bottom 60 d: many blue XXX ppt	22 d: very light black sed. = 60 d
Ru glycolate Ru=6% pH2-2.5	14 d: very light black sed.=21 d=28 d 60 d: black ppt and sed. on the wall	7 d: brownish ppt. on the bottom and weak sed. on the wall	7 d: black ppt
Ru glycolate Ru=3% pH2-2.5	60 d: OK	7 d: very light greenish ppt. (=14 d=21 d=28 d) 60 d: greenish sed.	7 d: black ppt

d = days

5 XXX = crystals

ppt = precipitate

sol. = solution

Claims

1. Composition suitable for colouring ceramic manufactured articles at their surface and to a depth of 1 mm min. in shades from pink to purple to violet, said composition consisting of a solution in water or in mixture of water with a water
5 soluble organic solvent of a monovalent gold thiolate comprised in the formulas
Au-S-R-X and Au-S-R-H
where R stands for a linear or branched bivalent radical of aliphatic or aromatic or cycloaliphatic or heterocyclic type, optionally with substituents, such as for example aminic, amidic, hydroxylic, carboxylic, hydrocarbylic or carbonylic groups
10 or CONH-, in the chain;
X stands for a monovalent group selected out of -COOH, SO₂OH, -OH, -CONH₂, -NH₂, -O-P(O)(OH)₂, in which H atoms may be replaced by alkyl groups and wherein acid groups may be salified with amines or alkaline or alkaline earth metals and basic groups may optionally be salified with organic acids.
- 15 2. The composition as claimed in claim 1, wherein Au thiolate derives from one of the following thio-compounds: (N) acetyl-cysteine; 4-mercaptopyridine; 2-mercaptopyridine; 2-mercaptoacetyl-glycine; mercaptopropionyl-glycine; 3-mercapto-
propionyl-glycine; (d,l) mercaptosuccinic acid; cysteine; 2-mercapto-
propionic acid.
- 20 3. The composition as claimed in claim 1 containing, in addition to Au thiolate, other metal compounds having colouring properties for the ceramic material, selected from the organic or inorganic derivatives of the following elements: Co, Cr, Ni, Ru, Mn, Sb, W, Cu, Fe, Zr, V, Zn, Pd, Sn.
4. The composition as claimed in claim 1, containing in addition to Au thiolate
25 selected from Au thiolactate and/or Au acetylcysteinate, other metal compounds having colouring properties for the ceramic material selected from the following compounds: Cobalt ammonium citrate; Chromium acetate; Chromium ammonium citrate; Nickel ammonium citrate, Ru glycolate; Ru ammonium citrate; Mn ammonium citrate; NaSb tartrate; KSb tartrate, NaW citrate; Cu ammonium citrate,
30 Fe ammonium citrate; sodium metavanadate; V glycolate; V ammonium citrate; Zn ammonium citrate, Pd glycolate; Pd ammonium citrate, Sn glycolate.

5. Process for colouring ceramic manufactured articles obtained by moulding a conventional ceramic mixture, said process using the composition as claimed in claim 1 and consisting in the following steps:

a) drying at 100°C of the article to be coloured to a water residue of 0.5% by wt. max.;

a.1) pre-treatment, if any, of the dried article with water up to a max. quantity of 300 g/m² manufactured article;

b) treatment of the pre-treated article with a water solution of the colouring composition in a quantity of 30 to 600 g/m² of the final coloured surface;

10 b.1) post-treatment, if any, of the article treated with water up to a max. quantity of absorbed water of 300 g/m² ceramic manufactured article;

c) equalisation of the post-treated article at room temperature for 8 hours to homogenise the solution absorption;

15 d) oven firing according to the usual ceramic cycle at a temperature of 1,000 to 1,300°C.

6. The process as claimed in claim 5, wherein the solution of the colouring composition, thickened with appropriate thickening agents, is applied to the ceramic manufactured article in step (b) by the silk-screen technique.

20 7. Vitrified stoneware tiles obtained by the colouring process as claimed in any of claims 5 and 6.

8. Vitrified stoneware tiles coloured by the process as claimed in any of claims 5 or 6, followed by removal by smoothing of the superficial layer to a depth of 1.5 mm, and by final polishing

25 9. The process as claimed in claim 5, wherein the treatment with a gold thiolate solution is carried out so as to apply 0.1 to 20 g Au (as element) per m² of surface to be coloured.

10. The colouring composition as claimed in claim 1, wherein, during the firing cycle, the gold thiolate used releases corrosive vapours in low quantities, i.e. not higher than 2 g SO₂/g Au deposited.

11. The colouring composition as claimed in claim 1, wherein, during the firing cycle, the gold thiolate used releases corrosive vapours in low quantities, not higher than 1 g SO₂/g Au deposited.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 99/06086

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C04B41/81

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 514 073 A (JOHNSON MATTHEY PLC) 19 November 1992 (1992-11-19) cited in the application	1-4, 10, 11
Y	claims 1,5-7,19-21 page 3, line 26 -page 5, line 42 page 6, line 51 -page 7, line 3 page 8, line 42 - line 46	5-9
X	DE 44 05 932 C (CERDEC AG) 4 May 1995 (1995-05-04) cited in the application	1-4, 10, 11
A	claims 1-4,8,9 page 3, line 29 - line 36 page 5, line 3 - line 6 table 1	5-7

-/-

☒

Further documents are listed in the continuation of box C.

☒

Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention.

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

22 December 1999

Date of mailing of the international search report

11/01/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Rosenberger, J

INTERNATIONAL SEARCH REPORT

Int'l Application No

PCT/EP 99/06086

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	W0 97 38952 A (VIGNALI GRAZIANO) 23 October 1997 (1997-10-23) cited in the application	5-9
A	claims 5-12,14,15 page 7, line 27 -page 8, line 4 page 9, line 7 - line 10	3,4
A	DE 195 46 325 C (BENCKISER KNAPSACK LADENBURG ;HERAEUS GMBH W C (DE)) 5 June 1997 (1997-06-05) claim 1 page 2, line 44 - line 48 page 3, line 22 page 3, line 53 - line 57	1,5,7,9

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int lional Application No

PCT/EP 99/06086

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0514073 A	19-11-1992	AT 124678 T	15-07-1995
		CN 1066863 A, B	09-12-1992
		DE 69203291 D	10-08-1995
		DE 69203291 T	21-12-1995
		DK 514073 T	21-08-1995
		ES 2073866 T	16-08-1995
		HK 179795 A	01-12-1995
		HU 215017 B	28-08-1998
		JP 5163576 A	29-06-1993
		PL 168425 B	29-02-1996
		TR 25693 A	01-09-1993
		US 5401535 A	28-03-1995
		US 5744245 A	28-04-1998
		US 5281635 A	25-01-1994
DE 4405932 C	04-05-1995	DE 59404208 D	06-11-1997
		EP 0669300 A	30-08-1995
		ES 2108360 T	16-12-1997
		JP 7315968 A	05-12-1995
		US 5545452 A	13-08-1996
WO 9738952 A	23-10-1997	IT MI960706 A	13-10-1997
		AT 183486 T	15-09-1999
		AU 2509597 A	07-11-1997
		CN 1218446 A	02-06-1999
		CZ 9803078 A	17-02-1999
		DE 69700438 D	23-09-1999
		DE 894081 T	06-05-1999
		EP 0894081 A	03-02-1999
		ES 2125845 T	16-03-1999
DE 19546325 C	05-06-1997	AU 1139597 A	03-07-1997
		WO 9721646 A	19-06-1997
		EP 0886629 A	30-12-1998