



(86) Date de dépôt PCT/PCT Filing Date: 2015/03/20
(87) Date publication PCT/PCT Publication Date: 2015/10/01
(45) Date de délivrance/Issue Date: 2019/10/29
(85) Entrée phase nationale/National Entry: 2016/09/21
(86) N° demande PCT/PCT Application No.: CA 2015/050211
(87) N° publication PCT/PCT Publication No.: 2015/143553
(30) Priorité/Priority: 2014/03/25 (US61/969,945)

(51) Cl.Int./Int.Cl. *A61L 27/44* (2006.01),
A61K 31/7036 (2006.01), *A61K 38/14* (2006.01),
A61K 47/30 (2006.01), *A61K 9/00* (2006.01),
A61L 27/54 (2006.01), *A61P 31/04* (2006.01)
(72) Inventeurs/Inventors:
RODGERS, LUKE M.B., US;
PETRAK, MARTIN, CA
(73) Propriétaire/Owner:
ORTHOPAEDIC INNOVATION CENTRE INC., CA
(74) Agent: GOWLING WLG (CANADA) LLP

(54) Titre : ARTICLES ANTIMICROBIENS PRODUITS PAR FABRICATION ADDITIVE
(54) Title: ANTIMICROBIAL ARTICLES PRODUCED BY ADDITIVE MANUFACTURING

(57) **Abrégé/Abstract:**

An antibiotic-eluting article for implantation into a mammalian subject, produced by an additive manufacturing process wherein a polymeric material is concurrently deposited with a selected antibiotic. The additive manufacturing process may be a selective laser sintering process or a selective laser melting process or a selective heat sintering process or an electron beam melting process. The antibiotic-eluting article may be temporary or permanent orthopaedic skeletal component, an orthopaedic articulating joint replacement component, and/or an external hard-shell casing for an implantable device. One or more bone-growth-promoting compositions may be concurrently deposited with the polymeric material. The implantable device may be a cardiac pacemaker, a spinal cord stimulator, a neurostimulation system, an intrathecal drug pump for delivery of medicants into the spinal fluid, and infusion pump for delivery of chemotherapeutics and/or anti-spasmodics, an insulin pump, an osmotic pump, and a heparin pump.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)
(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
1 October 2015 (01.10.2015)

(10) International Publication Number
WO 2015/143553 A1

(51) International Patent Classification:

A61L 27/44 (2006.01) *A61K 9/00* (2006.01)
A61K 31/7036 (2006.01) *A61L 27/54* (2006.01)
A61K 38/14 (2006.01) *A61P 31/04* (2006.01)
A61K 47/30 (2006.01)

(21) International Application Number:

PCT/CA2015/050211

(22) International Filing Date:

20 March 2015 (20.03.2015)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/969,945 25 March 2014 (25.03.2014) US

(71) Applicant: **ORTHOPAEDIC INNOVATION CENTRE INC.** [CA/CA]; Suite 320 - 1155 Concordia Avenue, Winnipeg, Manitoba R2K 2M9 (CA).

(72) Inventors: **PETRAK, Martin**; c/o Orthopaedic Innovation Centre Inc., Suite 320 - 1155 Concordia Avenue, Winnipeg, Manitoba R2K 2M9 (CA). **RODGERS, Luke M.b.**; 1064 Rosemary Circle, Chaska, Minnesota 55318 (US).

(74) Agents: **POLONENKO, Daniel R.** et al.; Gowling Lafleur Henderson LLP, Suite 1600, 421 - 7 Avenue SW, Calgary, Alberta T2P 4K9 (CA).

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.


(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(54) Title: ANTIMICROBIAL ARTICLES PRODUCED BY ADDITIVE MANUFACTURING

(57) Abstract: An antibiotic-eluting article for implantation into a mammalian subject, produced by an additive manufacturing process wherein a polymeric material is concurrently deposited with a selected antibiotic. The additive manufacturing process may be a selective laser sintering process or a selective laser melting process or a selective heat sintering process or an electron beam melting process. The antibiotic-eluting article may be temporary or permanent orthopaedic skeletal component, an orthopaedic articulating joint replacement component, and/or an external hard-shell casing for an implantable device. One or more bone-growth-promoting compositions may be concurrently deposited with the polymeric material. The implantable device may be a cardiac pacemaker, a spinal cord stimulator, a neurostimulation system, an intrathecal drug pump for delivery of medicants into the spinal fluid, and infusion pump for delivery of chemotherapeutics and/or anti-spasmodics, an insulin pump, an osmotic pump, and a heparin pump.



WO 2015/143553 A1

TITLE: ANTIMICROBIAL ARTICLES PRODUCED BY ADDITIVE
MANUFACTURING

TECHNICAL FIELD

Various embodiments disclosed herein generally relate to implantable medical
5 devices. More specifically, this disclosure pertains to implantable medical devices provided
with antimicrobial properties throughout their structures and on their surfaces.

BACKGROUND

Numerous types of medical devices have been developed for implantation into
patients' bodies. For example, it has become common practice for dentists to provide their
10 patients with custom dental prosthesis and/or implants to replace non-functional or missing
teeth. The replacement prosthesis and/or implants can be individually designed and
manufactured for precise installation into specific pre-identified sites. It has become routine
for patients with abnormal or irregular rates of heart contractions, to have pacemaker devices
installed under their skin in the chest area or alternatively, in their abdomens. Patients with
15 debilitating degenerative diseases affecting their joints and/or skeletal elements are now able
to have a large measure of their quality of life restored by replacement of the afflicted
structures with man-made artificial implants such as replacement hip components, knee joint
components, shoulder components, and the like. Patients who've suffered extreme trauma
resulting in severely fractured bones are often provided with fracture fixation plates, fixtures,
20 pins, nails, intramedullary rods, and the like to hold fractured bone segments together during
the healing process and/or to replace destroyed or missing skeletal segments. However, all of
these types of implantable devices expose the patients to risk of post-installation infection
along and/or about the outer surfaces of the devices serving as colonization sites. Particularly
problematic is the establishment of infectious biofilms on the surfaces of implanted devices.
25 More severe cases of infection often result in microbial penetration into the inner structural
components of the implants requiring their removal and replacement.

Numerous strategies have been employed in attempts to prevent post-installation
infections occurring on and about the surfaces the implanted medical devices. For example,
flexible resilient silicone-based coatings with antimicrobial and/or anti-fungal additives have
30 been developed for encasing the outer surfaces of medical implants at the time of implant

manufacture. Such coatings are typically produced by first, dissolving a suitable silicone exemplified by methyltri-methoxy silanes, methyl tri-acetoxy silanes, tetrachlorosilanes, vinyl trimethoxy silanes, gamma-ureidopropyltrimethoxy silanes, and the like, in a suitable solvent exemplified by toluenes, hexanes, xylenes, tetrahydrofurans, cyclohexanones, and the like. Second, dissolving an antimicrobial compound and/or an anti-fungal compound in a suitable solvent exemplified by n-methylpyrrolidinone, alkylesters of C₁₋₁₂ carboxylic acids, and the like. Third, mixing together the silane solution and the antimicrobial and/or anti-fungal solution. Four, immersing medical implants into the mixed solutions followed by removal and air-drying of the encased implants, then baking at about 90° C for up to one hour to set the coating and to completely evaporate the solvents. Such antibiotic-encased implants are purported to release the antimicrobial and/or anti-fungal compounds upon contact of the medical implant with tissues after implantation.

Another common approach has been to incorporate antimicrobial compounds and/or drugs into implants comprising polymeric materials, during their manufacture so that the antimicrobial compounds are eluted from the implants into the surrounding. These types of implants are generally referred to as drug-eluting implants. Some such implants are manufactured by dissolving the antimicrobial compounds into one or more solvents used for solubilising selected polymeric materials. The solubilised polymeric materials and antimicrobial compounds are mixed together and then poured or dispensed into forms wherein they solidify, and then are finished into the final implant. Other strategies involve first preparing an implant, then producing one or more recesses and/or crevices in selected locations on the outer surface, and then filling with recesses and/or crevices with a drug delivery matrix that this allowed to at least semi-harden. The drugs are then eluted from the matrix over a period of time. In some implant combinations, for example a “ball” and “socket” combination for a complete hip replacement or a total knee replacement package comprising a femoral component, a tibial tray, a tibial insert, and a patellar component, the drug delivery matrix may be incorporated into weight-bearing surfaces of one or more components so that the drugs are released by frictional forces created when two or more implant components rub against each other during their normal articulating functions. Other implant drug-eluting strategies have reservoirs cast into the implants’ interior structure. The reservoirs are filled with drug solutions prior to installation of an implant into a patient. Some implants are configured to communicate and cooperate with external reservoirs containing drug solutions that are externally pumped into and/or about the implants on prophylactic

schedules or alternatively, when an infection is detected. It is general practise to use antibiotic-loaded cements exemplified by PROSTALAC[®] (PROSTALAC is a registered trademark of Depuy Orthopaedic Inc., Warsaw, IN, USA) and SIMPLEX[®] (SIMPLEX is a registered trademark of Howmedica Osteonics Corp., Mahwah, NJ, USA) for installation of orthopaedic implants. While these cements have considerable value for minimizing the occurrence of post-operative infections immediately after installation of orthopaedic implants, their long-term benefits are limited because the antibiotics tend to rapidly dissipate from the surfaces of the cements upon exposure to mammalian tissues.

There still remain numerous infection-susceptibility related problems with the implants commonly available and in general use. There are concerns that the efficacies of some antimicrobial compounds and/or drugs are altered or compromised by the solvents which are used for their dissolution and/or by solvents used for dissolution of polymeric materials used for casting implants. Furthermore, it is known that the efficacies of drug-eluting implants increasingly diminish over time and are limited by drug "loading" limitations by the implant manufacturing processes. Implants provided with drug-loaded recesses / crevices may provide protection from infections about the crevice sites for a period of time, but are quite susceptible to microbial colonization and biofilm formation on their surface areas at locations removed from the recesses / crevices. Compounding these problems, are the surgical challenges of removing the infected implants, abrading surrounding infected skeletal structures, excising surrounding infected tissues, and installing replacement implants.

SUMMARY

The present disclosure pertains to implantable antimicrobial medical devices having antimicrobial compounds evenly sequestered throughout their structural matrices and distributed across their surfaces. The antimicrobial compounds may be eluted from the surfaces and from within the structural matrices after implantation of the medical devices into a mammalian subject. The present disclosure also pertains to methods for producing implantable medical devices comprising elutable antimicrobial compounds sequestered within their structural matrices and distributed across their surfaces.

DETAILED DESCRIPTION

The present disclosure pertains to methods for producing implantable antibiotic-eluting polymeric medical devices having antimicrobial compounds and/or bactericidal compounds homogenously distributed and sequestered throughout their structural matrix and across their surfaces. The present disclosure also pertains to implantable antibiotic-sequestering and eluting medical devices produced by the exemplary methods disclosed herein.

The exemplary methods of the present disclosure are particularly useful for producing substantially rigid articles that are suitable for surgical implantation into mammalian bodies, for example humans, primates, livestock, ruminants, equines, canines, felines, and the like.

The exemplary methods are also useful for producing external hard-shell casings for implantable devices such as cardiac pacemakers, spinal cord stimulators, neurostimulation systems, intrathecal drug pumps for delivery of medicants into the spinal fluid, infusion pumps for delivery of chemotherapeutics and/or anti-spasmodics, insulin pumps, osmotic pumps, heparin pumps, and the like. The exemplary methods are also useful for producing dental prosthesis, dental implants comprising one or more replacement tooth components, and the like. The exemplary methods are also useful for producing transcutaneous skin surface treatment devices exemplified by devices for providing transcutaneous electrical nerve stimulation and by devices for providing long-term percutaneous access. The exemplary methods are also useful for producing wound treatment surface devices exemplified by staples and sutures, and the like. The exemplary methods are particularly useful for producing three-dimensional intricate orthopaedic skeletal components including but not limited to articulating joint replacements, hip joint spacers, knee joint spacers, shoulder joint spacers, and the like. The three-dimensional intricate orthopaedic skeletal components may be temporary structures or alternatively, permanent structures.

The exemplary methods generally incorporate into manufacturing processes using additive manufacturing technologies, the concurrent deposition of one or more antimicrobial and/or biocidal compositions with the base feedstock materials to form the three-dimensional physical structures comprising the implantable antimicrobial articles of the present disclosure. The articles may be formed into solid and dense non-porous three-dimensional structures. Alternatively, the structures may be formed into heterogenous three-dimensional structures comprising solid regions and porous regions. Alternatively, the structures may

comprise inner cores having heterogenous three-dimensional structures that are overlaid with outer coverings comprising one or more solid dense layers. One or more selected antimicrobial compositions may be incorporated into the inner cores and/or into the outer coverings. Alternatively, the structures may comprise inner cores comprising a first
5 heterogenous three dimensional structure with a first degree of porosity, overlaid with one or more layers of a second heterogenous three dimensional structure with a second degree of porosity. One or more selected antibiotic compositions may be incorporated into the inner cores and/or into the outer layers. If so desired, the articles can be formed having more than three zones of porosity ranging from the inner cores to the outer surfaces.

10 Suitable additive manufacturing technologies include molten polymer deposition exemplified by selective laser sintering, selective laser melting, selective heat sintering, electron beam melting, and the like. One or more antibiotic compositions are concurrently deposited with the polymeric materials resulting in sequestration of the antibiotic compositions within and about the matrix formed by the polymeric materials. The antibiotic
15 compositions are deposited at rates that will provide in the articles of the present disclosure, from about 0.01% w/w to about 25% w/w of the antibiotic active ingredient by weight of the total weight of an antimicrobial article. For example, about 0.01% w/w, about 0.05% w/w, about 0.1% w/w, about 0.2% w/w, about 0.3% w/w, about 0.4% w/w, about 0.5% w/w, about 0.75% w/w, about 1.0% w/w, about 1.25% w/w, about 1.5% w/w, about 1.75% w/w, about
20 2.0% w/w, about 2.25% w/w, about 2.5% w/w, about 2.75% w/w, about 3.0% w/w, about 3.25% w/w, about 3.5% w/w, about 3.75% w/w, about 4.0% w/w, about 4.25% w/w, about 4.5% w/w, about 4.75% w/w, about 5.0% w/w, about 5.25% w/w, about 5.5% w/w, about 5.75% w/w, about 6.0% w/w, about 7.0% w/w, about 8.0% w/w, about 9.0% w/w, about 10.0% w/w, about 15.0% w/w, about 20.0% w/w, about 25.0% w/w, and therebetween.

25 The term “antimicrobial” as used herein means antibiotic, antiseptic, disinfectant. Classes of antibiotic compositions that may be useful for in the methods of the present disclosure for producing antimicrobial implantable medical devices include aminoglycosides exemplified by tobramycin, gentamicin, neomycin, streptomycin, and the like; azoles exemplified by fluconazole, itraconazole, and the like; β -lactam antibiotics exemplified by
30 penams, cepheids, carbapenems, monobactams, β -lactamase inhibitors, and the like; cephalosporins exemplified by cefacetrile, cefadroxyl, cephalexin, cephalazolin, cefproxil, cefbuperazone, and the like; chloramphenicol; clindamycin; fusidic acid; glycopeptides

exemplified by vancomycin, teicoplanin, ramoplanin, and the like; macrolides exemplified by azithromycin, clarithromycin, dirithromycin, erythromycin, spiramycin, tylosin, and the like; metronidazole; mupirocin; penicillins exemplified by benzylpenicillin, procaine benzylpenicillin, benzathine benzylpenicillin, phenoxymethylpenicillin, and the like; 5 polyenes exemplified by amphotericin B, nystatin, natamycin, and the like; quinolones exemplified by ciprofloxacin, ofloxacin, danofloxacin, and the like; rifamycins exemplified by rifampicin, rifabutin, rifapentine, rifaximin, and the like; sulfonamides exemplified by sulfacetamine, sulfadoxine, and the like; tetracyclines exemplified by doxycycline, minocycline, tigecycline, and the like; and trimethoprim, among others. It is expected that 10 tobramycin and/or gentamicin and/or neomycin and/or vancomycin are particularly suitable for concurrent deposition with polymeric materials for additive manufacturing of the antimicrobial medical devices of the present disclosure.

Various thermoplastic polymers and/or free radical polymers and/or cross-linked polymers may be used for concurrent deposition with antibiotic compositions to produce the 15 antimicrobial articles disclosed herein. For example poly(methyl methacrylates), acrylonitrile butadiene styrenes, polycarbonates, blends of acrylonitrile butadiene styrene(s) and polycarbonate(s), polyether ether ketones, polyethylenes, polyamides, polylactic acids, polyphenylsulfones, polystyrenes, nylon particularly nylon 12, among others. Also useful are methylmethacrylates, polylactides, polyglycolides, polycaprolactones, polyanhydrides, 20 polyamines, polyurethanes, polyesteramides, polyorthoesters, polydioxanones, polyacetals, polyketals, polycarbonates, polyorthocarbonates, polyphosphazenes, succinates, poly(malic acid), poly(amino acids), polyvinylpyrrolidone, polyethylene glycol, polyhydroxycellulose, polysaccharides, chitin, chitosan, and copolymers, block copolymers, multi-block copolymers, multi-block co-polymers with polyethylene glycol (PEG), polyols, terpolymers and 25 mixtures thereof. Also useful is incorporation of glass fibres during deposition of selected polymers and antibiotic compositions.

If so desired for manufacture of the three-dimensional intricate orthopaedic skeletal components disclosed herein, one or more bone-growth-promoting compositions may be deposited concurrently with the polymeric materials and the antibiotic compositions resulting 30 in sequestration of the antibiotic compositions and bone-growth-promoting compositions within and about the matrix formed by the polymeric materials. Suitable bone-growth-promoting compositions are exemplified by hyaluronic acid, β -TCP compositions,

SOST(sclerostin) antagonists for modulating the Wnt signaling pathway, Wnt antagonists for modulating the Wnt signaling pathway, LRP antagonists for modulating the Wnt signaling pathway, (3-(((4-tert-butyl-benzyl)-(pyridine-3-sulfonyl)-amino)-methyl)-phenoxy)-acetic-acid and its analogs, 7-[(4-butyl-benzyl)-methanesulfonyl-amino]-heptanoic acid and its analogs, 7-{[2-(3,5-dichloro-phenoxy)-ethyl]-methanesulfonyl-amino}-heptanoic acid and its analogs, 3-benzothiepin derivatives, and the like.

Granular materials binding processes exemplified by selective laser sintering, selective laser liquefying, selective heat sintering and electron beam liquefying (all referred to herein as “SLS”), comprise selective fusing of print media in a granular bed. In this type of method, a high power laser is used to fuse small particles of plastic, metal, ceramic, or glass powders into a mass that has a desired three-dimensional shape. The laser selectively fuses powdered material by scanning cross-sections generated from a 3-D digital description of the part (for example from a CAD file or scan data) on the surface of a powder bed. After each cross-section is scanned, the powder bed is lowered by one layer thickness, a new layer of material is applied on top, and the process is repeated until the part is completed. Because finished part density depends on peak laser power rather than laser duration, a SLS machine typically uses a pulsed laser. A suitable SLS machine preheats the bulk powder material in the powder bed somewhat below its melting point, to make it easier for the laser to raise the temperature of the selected regions the rest of the way to the melting point.

Accordingly, the exemplary implantable polymeric antimicrobial devices disclosed herein may also be produced by SLS 3D printing machines by providing powdered blends of one or more selected granular polymers with one or more selected antibiotic compositions and/or one or more bone-growth-promoting composition. Suitable SLS 3D printing machines are manufactured by EOS GmbH (Munich, Fed. Rep. Germany) and are available in North America from EOS of North America Inc. (Novi, MI, USA). Suitable EOS SLS 3D printing machines include their FORMIGA[®] P 110, EOSINT[®] P 395, EOSINT[®] P 760, and EOSINT[®] P 800 equipment (FORMIGA and EOSINT are registered trademarks of EOS GmbH Electro Optical Systems Co., Krailling, Fed. Rep. Germany). Suitable SLS 3D printing machines are also manufactured and supplied by 3D Systems Inc. (Rock Hill, SC, USA) and are exemplified by their SPRO[®] line of equipment (SPRO is a registered trademark of 3D Systems Inc.). Suitable electron beam melting (also referred to as EBM) 3D printing machines are manufactured by Arcam AB (Molndal, Sweden) and are available in North

America from their office in Chicago, IL. Suitable Arcam EBM 3D printing machines include their Q10 and A2 equipment.

Suitable exemplary powdered antibiotic/polymer compositions for SLS 3D printing may comprise granules of one or more of poly(methyl methacrylates), acrylonitrile butadiene
 5 styrenes, polycarbonates, blends of acrylonitrile butadiene styrene(s) and polycarbonate(s),
 polyether ether ketones, polyethylenes, polyamides, polylactic acids, polyphenylsulfones,
 polystyrenes, nylon particularly nylon 12, among others. Also useful are
 methylmethacrylates, polylactides, polyglycolides, polycaprolactones, polyanhydrides,
 polyamines, polyurethanes, polyesteramides, polyorthoesters, polydioxanones, polyacetals,
 10 polyketals, polycarbonates, polyorthocarbonates, polyphosphazenes, succinates, poly(malic
 acid), poly(amino acids), polyvinylpyrrolidone, polyethylene glycol, polyhydroxycellulose,
 polysaccharides, chitin, chitosan, and copolymers, block copolymers, multi-block co-
 polymers, multi-block co-polymers with polyethylene glycol (PEG), polyols, terpolymers and
 mixtures thereof.

15 Suitable powdered antibiotic/polymer compositions for SLS 3D printing may
 comprise one or more of aminoglycosides exemplified by tobramycin, gentamicin, neomycin,
 streptomycin, and the like; azoles exemplified by fluconazole, itraconazole, and the like; β -
 lactam antibiotics exemplified by penams, cepheams, carbapenems, monobactams, β -
 lactamase inhibitors, and the like; cephalosporins exemplified by cefacetrile, cefadroxyl,
 20 cephalexin, cephalosin, cefprozil, cefbuperazone, and the like; chloramphenicol;
 clindamycin; fusidic acid; glycopeptides exemplified by vancomycin, teicoplanin,
 ramoplanin, and the like; macrolides exemplified by azithromycin, clarithromycin,
 dirithromycin, erythromycin, spiramycin, tylosin, and the like; metronidazole; mupirocin;
 penicillins exemplified by benzylpenicillin, procaine benzylpenicillin, benzathine
 25 benzylpenicillin, phenoxymethylpenicillin, and the like; polyenes exemplified by
 amphotericin B, nystatin, natamycin, and the like; quinolones exemplified by ciprofloxacin,
 ofloxacin, danofloxacin, and the like; rifamycins exemplified by rifampicin, rifabutin,
 rifapentine, rifaximin, and the like; sulfonamides exemplified by sulfacetamine, sulfadoxine,
 and the like; tetracyclines exemplified by doxycycline, minocycline, tigecycline, and the like;
 30 and trimethoprim, among others. The antibiotic content of exemplary powdered
 antibiotic/polymer compositions for SLS 3D printing may comprise about 0.01% w/w, about
 0.05% w/w, about 0.1% w/w, about 0.2% w/w, about 0.3% w/w, about 0.4% w/w, about

0.5% w/w, about 0.75% w/w, about 1.0% w/w, about 1.25% w/w, about 1.5% w/w, about 1.75% w/w, about 2.0% w/w, about 2.25% w/w, about 2.5% w/w, about 2.75% w/w, about 3.0% w/w, about 3.25% w/w, about 3.5% w/w, about 3.75% w/w, about 4.0% w/w, about 4.25% w/w, about 4.5% w/w, about 4.75% w/w, about 5.0% w/w, about 5.25% w/w, about 5.5% w/w, about 5.75% w/w, about 6.0% w/w, about 7.0% w/w, about 8.0% w/w, about 9.0% w/w, about 10.0% w/w, about 15.0% w/w, about 20.0% w/w, about 25.0% w/w, and therebetween.

Suitable powdered antibiotic/polymer compositions for SLS 3D printing may comprise one or more of hyaluronic acid, β -TCP compositions, SOST(sclerostin) antagonists for modulating the Wnt signaling pathway, Wnt antagonists for modulating the Wnt signaling pathway, LRP antagonists for modulating the Wnt signaling pathway, (3-(((4-tert-butyl-benzyl)-(pyridine-3-sulfonyl)-amino)-methyl)-phenoxy)-acetic-acid and its analogs, 7-[(4-butyl-benzyl)-methanesulfonyl-amino]-heptanoic acid and its analogs, 7-{[2-(3,5-dichloro-phenoxy)-ethyl]-methanesulfonyl-amino}-heptanoic acid and its analogs, 3-benzothiepin derivatives, and the like. The bone-growth-promoting composition content of exemplary powdered antibiotic/polymer compositions for SLS 3D printing may comprise about 0.01% w/w, about 0.05% w/w, about 0.1% w/w, about 0.2% w/w, about 0.3% w/w, about 0.4% w/w, about 0.5% w/w, about 0.75% w/w, about 1.0% w/w, about 1.25% w/w, about 1.5% w/w, about 1.75% w/w, about 2.0% w/w, about 2.25% w/w, about 2.5% w/w, about 2.75% w/w, about 3.0% w/w, about 3.25% w/w, about 3.5% w/w, about 3.75% w/w, about 4.0% w/w, about 4.25% w/w, about 4.5% w/w, about 4.75% w/w, about 5.0% w/w, about 5.25% w/w, about 5.5% w/w, about 5.75% w/w, about 6.0% w/w, about 7.0% w/w, about 8.0% w/w, about 9.0% w/w, about 10.0% w/w, about 15.0% w/w, about 20.0% w/w, about 25.0% w/w, and therebetween.

The 3D printing methods of the present disclosure may additionally include additionally or alternatively comprise steps of concurrent deposition of a first antibiotic composition or mixture of antibiotic compositions and/or a first bone-growth-promoting composition with a selected polymeric material in several layers to form the core of a three-dimensional antimicrobial article, followed by concurrent deposition of a second first antibiotic composition or mixture of antibiotic compositions and/or a second bone-growth-promoting composition with the selected polymeric material to form the outer regions and surfaces of the antimicrobial article. The methods may additionally comprise concurrent

deposition of additional layers of a third antibiotic composition or mixture of antibiotic compositions and/or a third bone-growth-promoting composition if so desired. It is optional to provide a final outer surface layer to which is added a biocidal composition exemplified by silver nanoparticles, zinc pyrithione, cationic polymeric biocides, and the like. It is optional to provide a final outer surface layer to which is added a bone-growth-promoting composition exemplified by hyaluronic acid, β -TCP compositions, 3-benzothiepin derivatives, and the like.

It is also optional to provide a final outer surface layer to which is added mixture of a biocidal composition and a bone-growth-promoting composition. The outer surface layer comprising the biocidal coating and/or the bone-growth-promoting composition may be applied by the same additive manufacturing process used to produce the core structural matrix of the three-dimensional antimicrobial article. Alternatively, the outer surface layer may be applied as a coating over the core structural matrix of the three-dimensional antimicrobial article. The outer coating may be applied by processes exemplified by dipping, spraying, soaking, infusing, powder-coating, sputter-coating, arc depositing, and the like.

The antibiotic-eluting articles of the present disclosure are exemplified by orthopaedic skeletal components, orthopaedic articulating joint replacement components, and bone spacers. Also included are temporary orthopaedic components for short-term implantation while the permanent replacement orthopaedic components are being produced. The term “short-term” as used herein means three hundred and sixty five (365) days and less. The antibiotic-eluting articles of the present disclosure are also exemplified by external hard-shell casings for implantable devices such as cardiac pacemakers, spinal cord stimulators, neurostimulation systems, intrathecal drug pumps for delivery of medicants into the spinal fluid, infusion pumps for delivery of chemotherapeutics and/or anti-spasmodics, insulin pumps, osmotic pumps, heparin pumps, and the like. The antibiotic-eluting articles of the present disclosure are also exemplified by implantable dental prosthesis, dental implants comprising one or more replacement tooth components, and the like. The antibiotic-eluting articles of the present disclosure are also exemplified by transcutaneous skin surface treatment devices for providing transcutaneous electrical nerve stimulation and by devices for providing long-term percutaneous access. The antibiotic-eluting articles of the present disclosure are also exemplified by wound treatment surface devices exemplified by staples and sutures, and the like.

EXAMPLES

Example 1:

Poly(lactide (PLA) granules were sourced from NatureWorks LLC (Blair, NE, USA). Polycaprolactone (PCL) granules (CAPATM 6500) were sourced from Plastics Systems Inc. (Lakewood, WA, USA). Vancomycin and Gentamicin were sourced from Gold Biotechnology (St. Louis, MO, USA). 0.28 kg of Vancomycin was dry-blended together with a 5.8 Kg batch of PLA granules to produce a PLA blend comprising about 5% Vancomycin. 0.122 kg of Vancomycin was dry-blended together with a 5.8 Kg batch of PLA granules to produce a PLA blend comprising about 2% Vancomycin. 0.125 Kg of Gentamicin was dry-blended together with a 2.5 Kg batch of PCL granules to produce a PCL blend comprising about 5% Gentamicin. A PCL blend comprising about 2% Gentamicin was prepared by dry-blending a PCL blend comprising about 5% Gentamicin with additional PCL to adjust the Gentamicin content to about 2%.

A SINTERSTATION[®] HiQ SLS[®] system (SINTERSTATION and SLS are registered trademarks of 3D Systems Inc., Valencia, CA, USA) was used to print round discs having about diameter of about 1 inch (2.54 cm) and a thickness of about 0.125 inch (0.3175 cm) from each batch of polymer/antibiotic blends. Control discs were printed from pure PLA granules and PCL granules. About 4 inches of a polymer/antibiotic blend was placed into the machine's feed cylinders, and a powder bed was then generated by depositing powder onto the part cylinder. A warm up cycle was then used to warm both the feed cylinder and part cylinder, after which, the discs printed according to STL CAD software files loaded into 3D System's "Build Setup" Version 3.602 software. A portion of each polymer/antibiotic blend was used for SLS printing of discs for assessment of their antibiotic-eluting performance, and the remainder of the polymer/antibiotic blend was used for printing Type IV dumb-bell-shaped test specimens for tensile testing.

The system operating conditions for SLS printing of discs and Type IV dumb-bell-shaped specimens from PCL/Vancomycin blends and from PCL/Gentamicin blends were:

	Particle bed temperature:	48° C
	Feed temperature:	ambient
5	Smart feed gain:	1.3
	Fill laser power (W):	49
	Fill scan speed (inches/sec):	500
	Fill scan spacing (inches):	0.01
	Outline laser power (W):	14
10	Outline scan speed (inches/sec):	70

The system operating conditions for SLS printing of the discs from PLA/Vancomycin blends and from PLA/Gentamicin blends were:

	Particle bed temperature:	75° C
	Feed temperature:	40° C
15	Smart feed gain:	1.3
	Fill laser power (W):	67
	Fill scan speed (inches/sec):	500
	Fill scan spacing (inches):	0.01
	Outline laser power (W):	14
20	Outline scan speed (inches/sec):	70

Example 2:

Selected physical properties of the antibiotic-containing plastic Type IV dumb-bell-shaped test specimens were determined following the test methods set out in ASTM D638-08 document titled “Standard Test Method for Tensile Properties of Plastics” published by
 25 ASTM International and publicly available from their website:
<http://www.astm.org/Standards/D638.htm>. The physical properties of the SLS-printed antibiotic-containing plastic discs are listed in Tables 1-4.

Table 1: Physical properties of Type IV dumb-bell-shaped specimens printed with PCL/Gentamicin dry blends*.

Physical parameter	Gentamicin content in PCL discs		
	0	2%	5%
Thickness (in)	0.134	0.134±0.001	0.138±0.001
Modulus (lbf/in ²)	53200	47700±1700	314000±4330
0.2% Offset yield strength (lbf/in ²)	1970	1150±67	1210±191
Ultimate strength (lbf/in ²)	3090	1990±26	1830±13
% elongation at offset yield (%) break	407	4032.72±0.96	1.23±0.68

* data are means of three replicates ± SD

Table 2: Physical properties of Type IV dumb-bell-shaped specimens printed with PCL/Vancomycin dry blends.

Physical parameter	Vancomycin content in PCL discs		
	0	2%	5%
Thickness (in)	0.134	0.128±0.001	0.129±0.001
Modulus (lbf/in ²)	53200	94200±3720	65900±4750
0.2% Offset yield strength (lbf/in ²)	1970	1150±67	1130±71
Ultimate strength (lbf/in ²)	3090	1430±130	1930±167
% elongation at offset yield (%) break	407	1.41±0.25	1.76±0.28

* data are means of three replicates ± SD

Table 3: Physical properties of Type IV dumb-bell-shaped specimens printed with PLA/Gentamicin dry blends*.

Physical parameter	Gentamicin content in PCL discs		
	0**	2%	5%
Thickness (in)	-	0.156±0.001	0.158±0.001
Modulus (lbf/in ²)	-	155000±5680	164000±7010
0.2% Offset yield strength (lbf/in ²)	-	919±45	980±191
Ultimate strength (lbf/in ²)	-	1130±75	1170±104
% elongation at offset yield (%) break	-	0.569±0.2	0.66±0.13

* data are means of three replicates ± SD

** the control PLA granules did not sinter well and did not hold its structure

Table 4: Physical properties of Type IV dumb-bell-shaped specimens printed with PLA/Vancomycin dry blends*.

Physical parameter	Vancomycin content in PCL discs		
	0**	2%	5%
Thickness (in)	-	0.152±0.001	0.156±0.001
Modulus (lbf/in ²)	-	161000±7950	124000±1930
0.2% Offset yield strength (lbf/in ²)	-	903±190	849±111
Ultimate strength (lbf/in ²)	-	1090±69	962±67
% elongation at offset yield (%) break	-	0.538±0.14	0.545±0.12

* data are means of three replicates ± SD

5 ** the control PLA granules did not sinter well and none of the control Type IV dumb-bell-shaped specimens held their structures

Example 3:

The elution of antibiotics from the discs produced in Example 1 was assessed by the inhibition of the growth of *Staphylococcus aureus* on the surfaces of Mueller Hinton agar contained within Petri dishes onto which test coupons placed. *S. aureus* cultures were grown on TSA amended with 5% sheep blood. A sufficient amount of *S. aureus* culture was transferred from the TSA culture plates to a 0.85% sterile saline solution to provide a uniform suspension that fell within a 0.5-2.0 McFarland turbidity standard. Aliquots of the *S. aureus* culture were plated onto Mueller Hinton agar in Petri dishes after which, two test coupons/dish (or alternatively, control coupons) were placed on the agar; one with its shiny side up and the other with its matte side up. The Mueller Hinton agar-containing Petri dishes were then incubated for about 72 hrs at temperatures in the range of about 35° C to about 37° C. The zones of inhibition around each coupon were then measured and recorded (in mm). A clear zone around a test coupon indicates the inhibition of growth of *S. aureus*. The diameter of the PLA/Antibiotic blend coupons were 25mm and 26mm for the PCL/Antibiotic coupons. The diameters of the PLA control coupon were 25 mm and 26 mm respectively, and considered as the “0” points. If no inhibition occurred, then the value “25” was recorded and indicates that no inhibition of microbial growth occurred. The data shown in Table 5 confirm that the antibiotics were eluted from articles printed from each polymer/antibiotic blend.

Table 5: Elution of antibiotics from 3d-printed articles comprising PCL or PLA*.

Polymer/antibiotic blend	Antibiotic concentration		
	0	2%	5%
PCL/Gentamicin	25	43.7	45.0
PCL/Vancomycin	25	42.0	41.7
PLA/Gentamicin	32	41.7	43.7
PLA/Vancomycin	32	40.3	43.7

* data are means of three replicates $\pm$ SD

CLAIMS

1. A dry antibiotic-containing polymeric granular powder blend for use with any of a selective laser sintering machine, a selective laser liquefying machine, a selective heat sintering machine, and an electron beam liquefying machine, to prepare therefrom a medical device having antimicrobial properties throughout its structure and on its surfaces, said dry antibiotic-containing polymeric granular powder blend comprising:

a polymer in granular powder form; and

at least one antibiotic in powder form,

wherein the polymer and the at least one antibiotic are thoroughly mixed together to produce the antibiotic-containing polymeric granular powder,

whereby the at least one antibiotic is homogenously distributed throughout the antibiotic-containing polymeric granular powder, and

wherein the antibiotic-containing polymeric granular powder has a concentration of the at least one antibiotic from a range of 0.1% w/w to 25% w/w.

2. The dry antibiotic-containing polymeric granular powder blend of claim 1, wherein the polymer is selected from a group consisting of poly(methyl methacrylates), acrylonitrile butadiene styrenes, polycarbonates, blends of acrylonitrile butadiene styrene(s) and polycarbonate(s), polyether ether ketones, polyethylenes, polyamides, polylactic acids, polyphenylsulfones, polystyrenes, nylons, methylmethacrylates, polylactides, polyglycolides, polycaprolactones, polyanhydrides, polyamines, polyurethanes, polyesteramides, polyorthoesters, polydioxanones, polyacetals, polyketals, polycarbonates, polyorthocarbonates, polyphosphazenes, succinates, poly(malic acid), poly(amino acids), polyvinylpyrrolidone, polyethylene glycol, polyhydroxycellulose, polysaccharides, chitin, chitosan, and copolymers, block copolymers, multi-block co-polymers, multi-block co-polymers with polyethylene glycol (PEG), polyols, terpolymers, and mixtures thereof.

3. The dry antibiotic-containing polymeric granular powder of claim 1, wherein the polymer is selected from a group consisting of polylactic acid, polycaprolactones,

REPLACEMENT SHEET

nylons, and high-density polyethylene.

4. The dry antibiotic-containing polymeric granular powder of claim 1, wherein the antibiotic is selected from a group consisting of an aminoglycoside, an azole, a β -lactam antibiotic, a β -lactamase inhibitor, a cephalosporin, chloramphenicol, clindamycin, fusidic acid, a glycopeptide, a macrolide, metronidazole, mupirocin, a penicillin, a polyene, a quinolone, a rifamycin, a sulfonamide, a tetracycline, and combinations thereof.

5. The dry antibiotic-containing polymeric granular powder of claim 1, wherein the concentration of the at least one antibiotic is selected from a range of 0.5% w/w to 10.0% w/w.

6. The dry antibiotic-containing polymeric granular powder of claim 1, wherein the concentration of the at least one antibiotic is selected from a range of 0.75% w/w to 5.0% w/w.

7. The dry antibiotic-containing polymeric granular powder of claim 1, additionally comprising a bone-growth-promoting composition selected from a group consisting of hyaluronic acid, β -TCP compositions, sclerostin antagonists for modulating the Wnt signaling pathway, Wnt antagonists for modulating the Wnt signaling pathway, LRP antagonists for modulating the Wnt signaling pathway, (3-(((4-tert-butyl-benzyl)-(pyridine-3-sulfonyl)-amino)-methyl)-phenoxy)-acetic-acid and its analogs, 7-[(4-butyl-benzyl)-methanesulfonyl-amino]-heptanoic acid and its analogs, and 7-{[2-(3,5-dichlorophenoxy)-ethyl]-methanesulfonyl-amino}-heptanoic acid and its analogs, and 3-benzothiepin derivatives.

8. Use of the dry antibiotic-containing polymeric granular powder according to any one of claims 1 to 7, to produce therefrom an antibiotic-eluting orthopaedic article for implantation into a mammalian subject, said antibiotic-eluting orthopaedic article having antimicrobial properties throughout its structure and on its surfaces.

REPLACEMENT SHEET

9. Use according to claim 8, wherein a bone-growth-promoting composition is deposited with the dry antibiotic-containing polymeric granular powder.
10. An implantable antibiotic-eluting orthopaedic article as defined in claim 8 or 9, wherein the implantable antibiotic-eluting orthopaedic article is additionally provided with a final outer surface layer comprising a biocidal coating or a bone-growth-promoting composition or a mixture thereof.
11. The implantable antibiotic-eluting orthopaedic article of claim 10, wherein the biocidal coating is one or more of silver nanoparticles, zinc pyrithione, and cationic polymeric biocides.
12. The implantable antibiotic-eluting orthopaedic article of claim 10, wherein the article is an orthopaedic articulating joint replacement component.
13. The implantable antibiotic-eluting orthopaedic article of claim 10, wherein the article is an orthopaedic bone replacement component.