

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶ :

C08G 69/10, 73/10

A1

(11) International Publication Number:

WO 96/25450

(43) International Publication Date:

22 August 1996 (22.08.96)

(21) International Application Number: PCT/US96/02079

(22) International Filing Date: 14 February 1996 (14.02.96)

(30) Priority Data:

08/390,202

16 February 1995 (16.02.95)

US

(71) Applicant: MONSANTO COMPANY [US/US]; 800 North Lindbergh Boulevard, St. Louis, MO 63167 (US).

(72) Inventors: ALEXANDER, Gregory, Clifford; 8120 Amherst Avenue, University City, MO 63130 (US). JASON, Mark, Edward; 34 Ridge Point Drive, Chesterfield, MO 63017 (US). KALOTA, Dennis, Jerome; 1306 Green Mist Drive, Fenton, MO 63026 (US).

(74) Agent: PASSLEY, Paul, Leonard; Monsanto Company, 800 North Lindbergh Boulevard, St. Louis, MO 63167 (US).

(81) Designated States: AM, AU, AZ, BB, BG, BR, BY, CA, CN, CZ, EE, FI, GE, HU, IS, JP, KG, KR, KZ, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, RU, SG, SI, SK, TJ, TM, TR, TT, UA, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AZ, BY, KG, KZ, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).

Published*With international search report.*

(54) Title: PREPARATION OF ANHYDROPOLYAMINO ACIDS

(57) Abstract

There is disclosed a process for preparing polyaspartic acid by thermal condensation of L-aspartic acid in a novel catalyst which shortens the reaction time and increases the molecular weight of the polymer. The novel catalyst is a catalytically effective methylenephosphonic acid. Typical catalysts are 1-hydroxyethylidene-1,1-diphosphonic acid and aminotris(methylenephosphonic acid). The methylenephosphonic acid is blended with the amino acid in a molar ratio of amino acid to catalyst in the range of from about 1:1 to 40:1.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BG	Burkina Faso	IE	Ireland	NZ	New Zealand
BH	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

-1-

Preparation of Anhydropolyamino Acids

This invention relates to a process for preparing anhydropolyamino acids and the hydrolysis thereof to form polyamino acids. More particularly
5 this invention relates to novel catalytic processes for preparing polysuccinimide with reduced reaction time.

BACKGROUND OF THE INVENTION

The thermal condensation of alpha amino
10 acids to form polymers with loss of water has been known for many years. Early interest in such processes related to theories for formation of prebiotic polypeptides. For the purpose of testing such theories laboratory experiments used powdered
15 L-aspartic acid, usually packed in the bottom of a flask which was then heated below the melting point of the acid. Such reactions were slow and took place over many hours. One such example is reported by Kokufuta et al. in Bulletin of the Chemical
20 Society of Japan Vol. 51 (5) 1555-1556 (1978) "Temperature Effect on the Molecular Weight and the Optical Purity of Anhydropolyaspartic Acid Prepared by Thermal Polycondensation." The structure of anhydropolyaspartic acid has been thoroughly
25 investigated such as by J. Kovacs et al. in J.O.C.S. Vol. 26 1084-1091 (1961).

In recent years many utilities have been suggested for polyamino acid. Such polyamides have been suggested as potential drug carriers by Neuse
30 et al. in Die Angewandte Makromolekulare Chemie 192 35-50 (1991) "Water-soluble polyamides as potential drug carriers." They have also been tested as scale inhibitors with respect to natural sea water and calcium sulfate in particular by Sarig et al. as
35 reported by the National Council on Research and Development (NRCD 8-76, Seawater Desalination 150-157 (1977)). Polyaspartic acid has been well known

-2-

for its ability to disperse solid particles in detergent formulations, having been mentioned as a dispersant in numerous patents, a few of which are U.S. Patents 4,363,497; 4,333,844; 4,407,722 and 4,428,749. As a departure from the usual manner of utilizing polyaspartic acid in detergent formulations it is reported in Australian Patent A-14775/92 that the polyimide is added to the wash liquor which, upon hydrolysis in situ, is converted into a biodegradable polypeptide builder. Also, as described in U.S. Patent 4,971,724 to Kalota et al., it has been discovered that compositions comprising polyamino acids such as aspartic acid, when ionized at alkaline pH, effectively inhibit corrosion of ferrous metals in the presence of aqueous medium. Various derivatives of polyamino acids have also been made wherein attributes have been supplied by groups attached to reactive sites on the molecule. One such example is disclosed in U.S. Patent 3,846,380 to Fujimoto et al.

With the increasing importance of polyaspartic acid in the detergent industry, the efficient production of large quantities with low color has become important. One method known to provide low colored polyaspartic acid is one in which phosphoric acid is employed as a catalyst. Although the color of the product is improved with phosphoric acid catalyst, such catalyst must be removed from the product before use. Furthermore, the particulate L-aspartic acid undergoes phases during the reaction in which it becomes tacky and difficult to handle in large industrial reactors. There is therefore needed a more convenient catalyst which not only speeds the reaction thereby shortening reaction time and improve color, but also provide a more easily handled reaction mass and eliminate the need for removal of the catalyst from the product.

BRIEF DESCRIPTION OF THE INVENTION

In accordance with this invention there has been discovered a process for producing anhydropolyamino acids by thermal condensation of L-aspartic acid in high yield in shortened reaction time by including a catalytic amount of a methylene phosphonic acid. Methylenephosphonic acids are well known for their use in water treatment, particularly for the purposes of scale inhibition and sequestration. The preferred methylenephosphonic acid is 1-hydroxyethylidene-1,1-diphosphonic acid (HEDP). Other typical methylene phosphonic acids are aminotris(methylenephosphonic acid), ethylenediaminetetra(methylenephosphonic acid), hexamethylenediaminetetra(methylenephosphonic acid) and diethylenetriaminepenta(methylenephosphonic acid) or mixtures thereof.

More specifically, the invention comprises a process for the production of anhydropolyamino acids in high yield by heating L-aspartic acid at a temperature in the range of above about 140°C in the presence of a catalytically effective amount of a methylenephosphonic acid and then hydrolysing the resultant anhydropolyamino acid to polyaspartic acid in basic aqueous medium. Because the methylenephosphonic acids are useful as anti-scale agents and sequestrants in industrial water treatment and find uses in oil field chemicals and pharmaceuticals, their presence in anhydropolyaspartic acid or polyaspartic acid is not objectionable, particularly when the product is intended for use in aqueous solutions such as in the detergent industries.

DETAILED DESCRIPTION OF THE INVENTION

In accordance with this invention a catalytically active methylenephosphonic acid is thoroughly mixed with L-aspartic acid prior to the thermal condensation reaction wherein

-4-

anyhydropolyamino acids are made. The most convenient means to provide thorough mixing is by dissolving both L-aspartic acid and the methylenephosphonic acid in water. The solution is then mixed and dried to recover dry, particulate L-aspartic acid having methylenephosphonic acid dispersed throughout the dry material. The dried material is then subjected to thermal condensation by any of the known means such as by subjecting the dried material to elevated temperature in an oven, tray driers (see U.S. patent 5,319,145 and 5,315,010) or a rotary drier (see U.S. 5,057,597), said patents being incorporated by reference, and the like. The resultant anhydropolyamino acid is then converted by alkaline hydrolysis to the polyamino acid salt.

Typically the minimum amount of methylenephosphonic acid included with L-aspartic acid for catalytic purposes is at least about 1 mole methylenephosphonic acid to 40 moles of L-aspartic acid up to a molar ratio of 1:1. Higher amounts can be employed in the event there is a utility for the end product in which it is desirable to have methylenephosphonic acid present in larger quantities. For example, HEDP may be included with L-aspartic acid up to a 1:1 mole ratio if desired.

Many methylenephosphonic acids are commercially available under the trade name Dequest® from Monsanto Company, St. Louis, Mo. They are widely used in water treatment applications for scale control, sequestration, industrial water treatment and bleach stabilization. These functions are not lost by the use of HEDP as a catalyst in the process of this invention. Therefore, when polyaspartic acid or anhydropolyaspartic acid is employed in the detergent industry there is no need to remove it from the product as it will function in an

-5-

advantageous manner along with polyaspartic acid or salt thereof.

There is thus provided a convenient process for making an anhydropolyamino acid by continuously feeding an alpha amino acid reactant such as an L-aspartic acid to a reactor together with a catalytically effective amount of a methylenephosphonic acid.

10 Description of the Preferred Embodiments

In the following examples percentage figures are given in percent by weight unless otherwise noted. All molecular weight values are given as a weight average.

15 EXAMPLE 1

A blend comprising 85% L-aspartic acid (1.003 mole) and 15% HEDP (0.1141 mole) was prepared by dissolving the acids in water. After thorough mixing, the water was removed by means of a rotary evaporator. This dried blend was then placed in a pan and admitted to an oven held at a temperature in the range of 153°C at the beginning and 199°C at termination. The time the blend was held at that temperature range was about 3 hrs. 10 minutes. One hundred twenty-five grams of a light yellow polymer was recovered having a molecular weight of 12,499. Into 38.5 g of water was placed 17.22 g of the polymer and to this solution was added 4.32 g of 50% sodium hydroxide resulting in a clear solution of sodium polyaspartate.

30 EXAMPLE 2

To a beaker was added 133.09 g (1 mole) of L-aspartic acid and to this powder was added 38.83 g of HEDP in 60% water solution. The mixture was blended easily as it was a non-tacky and non-sticking, solid. The blend was transferred to a stainless steel pan and placed in an oven held at

-6-

228°C beginning temperature. The blend was held in the oven for a period of 2.5 hrs. during which time the temperature fluctuated between 165°C and 241°C. There was recovered 117.1 g of yellow colored polysuccinimide. The hydrolysed material had a molecular weight of 12,608.

EXAMPLE 3

The procedure of Example 2 was repeated except no HEDP was contained in the water blended with L-aspartic acid. The temperature of the oven was held to a range of from 226°C to 243°C and the acid was held in the oven for a period of 4.5 hrs. There was recovered 96.4 g of polysuccinimide which, when hydrolysed, indicated a molecular weight of 10,653.

EXAMPLE 4

To a beaker was added 133.31 (1.001 mole) of L-aspartic acid and 23.52 g (0.0787 mole) of aminotris(methylenephosphonic acid) available under the trade name Dequest 2000® and 52 g of water. The mixture was blended and then placed into a stainless steel pan and then heated in a forced draft oven held at a temperature in the range of from 211°C to 242°C. The reaction was completed in 2 hrs. 17 minutes to provide polysuccinimide. The hydrolysed product had a molecular weight of 12,508.

EXAMPLE 5

The procedure of Example 4 was repeated except that water was substituted for the methylene-phosphonic acid. The reaction required 3.5 hrs. for completion. The hydrolysed product had a molecular weight of 10,913.

35

- 7 -

EXAMPLE 6

To 1 mole of L-aspartic acid was added 18.79 g of a 60% solution of HEDP. The mixture was blended well and placed in a stainless steel pan. The pan
5 was placed in an oven held to a temperature in the range of from 226 to 251 for a period of 1 hr. 40 minutes. providing a complete reaction to form the polymer, polysuccinimide. The polymer was hydrolysed by placing 20.03 g into 64.43 g of water
10 containing 50 g of 50% sodium hydroxide. The hydrolysed polymer had a molecular weight of 12,210.

EXAMPLE 7

The procedure of Example 6 was repeated except
15 that only L-aspartic acid was placed in the pan. The reaction required 2 hrs. 20 minutes to complete and the hydrolysed polymer was found to have a molecular weight of 11,824.

EXAMPLE 8

The procedure of Example of Example 4 was repeated except that only 21.64 g of a 50% aqueous solution of aminotris(methylenephosphonic acid) was blended with 1 mole of L-aspartic acid. The blend
25 was held in a stainless steel pan in an oven at a temperature in the range of from 224°C to 247°C for a period of 1 hr. 45 minutes to reach 99.7% completion. The hydrolysed polymer had a molecular weight of 12,915. A control sample of L-aspartic
30 acid without catalyst was also polymerized but required 2 hrs. 45 minutes to complete. The molecular weight of the hydrolysed material was found to be 11,269.

Although the invention has been described
35 in terms of specific embodiments which are set forth in considerable detail, it should be understood that this description is by way of illustration only and

- 8 -

that the invention is not necessarily limited thereto since alternative embodiments and operating techniques will become apparent to those skilled in the art in view of the disclosure. Accordingly, 5 modifications are contemplated which can be made without departing from the spirit of the described invention.

WHAT IS CLAIMED IS:

1. In a process for the production of anhydropolyamino acid by the thermal polymerization of L-aspartic acid, the improvement comprising heating said L-aspartic acid in the presence of a catalytically effective amount of methylenephosphonic acid.
2. The process of Claim 1 wherein the mole ratio of L-aspartic acid is aspartic acid to methylene phosphonic acid is from about 40:1 to 10:1.
3. The process of Claim 2 further including the step of hydrolyzing the anhydropolyamino acid in alkaline solution to produce polyamino acid or salt thereof.
4. The process of Claim 1 wherein the methylenephosphonic acid is 1-hydroxyethylidene-1,1-diphosphonic acid.
5. The process Claim 1 wherein the methylenephosphonic acid is aminotris(methylenephosphonic acid).
6. The process of Claim 1 wherein the mole ratio of L-aspartic acid to methylenephosphonic acid is in the range of from about 1:1 to about 40:1.
7. The process of Claim 6 wherein the ratio is about 10:1.
8. The process of Claim 6 wherein the mole ratio of L-aspartic acid to methylenephosphonic acid is 40:1.
9. The process of Claim 1 wherein the methylenephosphonic acid is selected from the group consisting of aminotris(methylenephosphonic acid), ethylenediaminetetra(methylenephosphonic acid), hexamethylenediaminetetra(methylenephosphonic acid) and diethylenetriaminepenta(methylenephosphonic acid) and mixtures thereof.

-10-

10. The process of Claim 1 wherein the L-aspartic acid is heated in a tray drier.

11. The process of Claim 10 wherein the tray drier is a rotary tray drier.

5 12. The process of Claim 10 wherein the tray drier is an indirectly heated tray drier.

13. The process of Claim 1 wherein the L-aspartic acid is heated in a rotary drier.

INTERNATIONAL SEARCH REPORT

Int. Application No
PCT/US 96/02079

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08G69/10 C08G73/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,4 363 797 (JACQUET BERNARD ET AL) 14 December 1982 cited in the application see column 3, line 61 - column 4, line 32 ---	1
A	US,A,5 329 020 (KALOTA DENNIS J ET AL) 12 July 1994 see claim 1 -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

30 April 1996

Date of mailing of the international search report

05.06.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Hoffmann, K

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 96/02079

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4363797	14-12-82	FR-A- 2403353	13-04-79
		DE-A- 2839869	29-03-79
		GB-A,B 2005705	25-04-79

US-A-5329020	12-07-94	CA-A- 2133621	06-04-95
		EP-A- 0646615	05-04-95
		JP-A- 7165910	27-06-95
