

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
29 April 2010 (29.04.2010)

(10) International Publication Number
WO 2010/048101 A2

(51) International Patent Classification:
B29C 70/50 (2006.01) C08J 5/24 (2006.01)

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(21) International Application Number:
PCT/US2009/061211

(22) International Filing Date:
20 October 2009 (20.10.2009)

(25) Filing Language:
English

(26) Publication Language:
English

(30) Priority Data:
61/106,905 20 October 2008 (20.10.2008) US

(71) Applicant (for all designated States except US): CYTEC TECHNOLOGY CORP. [US/US]; 300 Delaware Avenue, Wilmington, DE 19801 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): BONGIOVANNI, Christopher, Lee [US/US]; 2245 W. Broadway, Apt. N207, Anaheim, CA 92804 (US). BOYD, Jack, Douglas [US/US]; 29184 Sleepy Hollow, Silverado, CA 92676 (US).

(74) Agents: BELL, Charles et al.; Cytec Industries, Inc., 1937 West Main Street, Stamford, CT 06904-0060 (US).

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report (Rule 48.2(g))

(54) Title: PREPREGS WITH IMPROVED PROCESSING




FIG.3A

(57) Abstract: Systems and methods for the fabrication of prepregs possessing enhanced ability for the removal of gases from within prepregs and prepreg layups prior to and/or during at least a portion of consolidation and cure process to form composite structures are disclosed. In certain embodiments, perforations of selected configurations may be introduced into the prepregs prior to, during, and after layup. The perforations provide routes for gases trapped within and between the perforated prepregs and prepreg lay-ups to escape during consolidation and cure process, reducing the residual porosity within the resulting composite. For example, composites having residual porosities less than 10 vol. %, on the basis of the volume of the composite, may be achieved in this manner.

WO 2010/048101 A2

PREPREGS WITH IMPROVED PROCESSING

BACKGROUND

FIELD

[0001] Embodiments of the present disclosure relate to pre-impregnated fibers and, in particular, to methods for the fabrication of perforated prepgs, perforated prepreg layups, and composite structures.

DESCRIPTION OF THE RELATED ART

[0002] Fiber reinforced composites (FRCs) are hybrid structural materials that comprise a matrix component surrounding at least a portion of a fiber reinforcement that is configured in one or more layers. Owing to their relatively high stiffness to weight ratio, as well as their relatively low density, FRCs have found utility in applications, such as aircraft components, where weight is a significant concern.

[0003] FRC components may be manufactured using fibers that are pre-impregnated with the matrix component, also known as prepgs. To form a composite part from the prepgs, one or more layers of prepgs are assembled within a mold and heat may be applied to cause the matrix resin to flow, enabling consolidation of the prepreg layers. The applied heat may additionally cure or polymerize the matrix components.

[0004] The consolidation of prepgs to form composites in this manner is difficult, however. Gases may be trapped inside the prepreg and between the prepgs during layup and may also evolve during heating and/or curing of the prepgs. These gases are difficult to remove from the layup, as the matrix substantially inhibits movement of the gases and may result in porosity within the composite. This porosity can further reduce the mechanical properties of the composite.

[0005] Techniques have been developed to enhance removal of entrapped gases during composite fabrication, however, problems remain. For example, edge breathers may be employed to apply vacuum to the edge of prepgs in order to

draw out gases from the sides of prepreg layers. However, removal of trapped gases from preprints in this manner is slow and may not provide substantially complete removal of the trapped gases.

SUMMARY

[0006] In an embodiment, preprints possessing enhanced ability for the removal of gases, such as air and other volatile species, from within preprints and prepreg layups are provided. In certain embodiments, perforations of selected configuration are present within the preprints. The perforations provide routes for gases trapped within the perforated preprints to escape the preprints.

[0007] In an embodiment, a perforated prepreg is provided where perforations are distributed through at least a portion of the prepreg. The perforations are also dimensionally stable at about room temperature and further enable gas movement through the perforated prepreg.

[0008] In another embodiment, a composite made using one or more of the perforated preprints is provided. The composite possess a porosity of less than 10 vol. % on the basis of the total volume of the composite.

[0009] In a further embodiment, a method of making the perforated prepreg is provided. The method comprises applying mechanical manipulation or energy to the prepreg to form in at least a portion of the prepreg one or more perforations.

[0010] In an alternative embodiment, a method of forming a fiber-reinforced composite is provided. The method comprises introducing one or more perforations into a prepreg comprising a matrix resin and a fiber embedded within at least a portion of the matrix to form a perforated prepreg. The one or more perforations are configured so as to enable gases to travel from within the body of the perforated prepreg to an external surface of the perforated prepreg.

[0011] In another embodiment, a perforated prepreg layup is provided. The perforated prepreg layup may comprise one or more perforated preprints as discussed above. The perforated prepreg layup may further comprise combinations of the perforated prepreg and preprints not containing perforations. In a further

embodiment, a perforated prepreg is provided wherein the weight fraction of fiber reinforcement in the perforated prepreg is less than 20wt.% such as for an adhesive film or surfacing film, and may be zero such as for a resin film.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] Figures 1A-1C are illustrations of embodiments of fully impregnated (1A) and partially impregnated (1B and 1C) prepgregs;

[0013] Figures 2A-2B are illustrations of embodiments of fully and partially impregnated prepgregs, respectively, having perforations;

[0014] Figures 3A-3B are illustrations of possible mechanisms by which gases may be substantially removed from the fully and partially perforated prepgregs and prepgreg layups of Figures 2A-2B, respectively;

[0015] Figure 4 illustrates methods for the introduction of perforations within prepgreg systems;

[0016] Figures 5A-5B are top down views of embodiments of prepgregs having distributed perforations; (A) random perforation distribution; (B) substantially uniform perforation distribution; and

[0017] Figure 6 illustrates one embodiment of a system for the consolidation and cure of perforated prepgregs to form composite structures.

DETAILED DESCRIPTION

[0018] The terms “approximately”, “about”, and “substantially” as used herein represent an amount close to the stated amount that still performs the desired function or achieves the desired result. For example, the terms “approximately”, “about”, and “substantially” may refer to an amount that is within less than 10% of, within less than 5% of, within less than 1% of, within less than 0.1% of, and within less than 0.01% of the stated amount.

[0019] A perforation that possesses a circular cross-section that is substantially uniform may exhibit diameters that are within less than 10% of the mean diameter, within less than 5% of the mean diameter, within less than 1% of the mean diameter, within less than 0.1% of the mean diameter, and within less than 0.01% of the mean diameter. In another

example, a perforation that extends substantially perpendicular to a selected plane of a fiber may exhibit orientations that are within less than 10% of the angle of the normal to the plane of the fiber, within less than 5% of the angle of the normal to the plane of the fiber, within less than 1% of the angle of the normal to the plane of the fiber, within less than 0.1% of the angle of the normal to the plane of the fiber, and within less than 0.01% of the angle of the normal to the plane of the fiber.

[0020] The term “at least a portion of” as used herein represents an amount of a whole that comprises an amount of the whole that may include the whole. For example, the term “a portion of” may refer to an amount that is greater than 0.01% of, greater than 0.1% of, greater than 1% of, greater than 10% of, greater than 20% of, greater than 30% of, greater than 40% of, greater than 50% of, greater than 60%, greater than 70% of, greater than 80% of, greater than 90% of, greater than 95% of, greater than 99% of, and 100% of the whole.

[0021] The term “room temperature” as used herein has its ordinary meaning as known to those skilled in the art and may include temperatures within the range of about 15°C to 43°C.

[0022] The term “fiber” or “fibers” as used herein has its ordinary meaning as known to those skilled in the art and may include one or more fibrous materials adapted for the reinforcement of composites. Fibers may take the form of any of particles, flakes, whiskers, short fibers, continuous fibers, sheets, plies, and combinations thereof. Continuous fibers may further adopt any of unidirectional, multi-dimensional (e.g. two-or three-dimensional), non-woven, woven, knitted, stitched, wound, and braided fibers, as well as swirl mat, felt mat, and chopped mat structures. Woven fibers may comprise a plurality of woven tows having less than about 1000 filaments, less than about 3000 filaments, less than about 6000 filaments, less than about 12000 filaments, less than about 24000 filaments, less than about 48000 filaments, less than about 56000 filaments, less than about 125000 filaments, and greater than about 125000 filaments. Woven tows may be held in position by cross-tow stitches, weft-insertion knitting stitches, or a small amount of resin, such as a sizing.

[0023] The composition of the fibers may be varied, as necessary. Fibers include, but are not limited to, glass, carbon, aramid, quartz, polyethylene, polyester, poly-p-phenylene-benzobisoxazole (PBO), boron, silicon carbide, polyamide, Nylon®, silicon nitride, Astroquartz®, Tyranno®, Nextel®, Nicalon®, and graphite, and combinations thereof.

[0024] The terms “matrix”, “resin”, and “matrix resin” as used herein have their ordinary meaning as known to those skilled in the art and may include one or more compounds comprising a thermoset and/or thermoplastic materials. Examples may include, but are not limited to, epoxies, epoxy curing agents, phenolics, phenols, cyanates, imides (e.g., polyimides, bismaleimide (BMI), polyetherimides), polyesters, benzoxazines, polybenzimidazoles, polybenzothiazoles, polyamides, polyamidimides, polysulphones, polyether sulphones, polycarbonates, polyethylene terephthalates, and polyether ketones (e.g. polyether ketone (PEK), polyether ether ketone (PEEK), polyether ketone ketone (PEKK) and the like), combinations thereof, and precursors thereof.

[0025] Matrices, as discussed herein, may further comprise soluble, insoluble or partially soluble additives. Such additives may be provided to influence one or more of mechanical, rheological, electrical, optical, chemical, and/or thermal properties of the matrix. Such additives may further comprise materials that chemically react with the matrix, interact with the matrix, or are unreactive with the matrix. The size distribution, and geometry of such additives may also be varied, as necessary. For example, the size of the additives may range between nanoscale dimensions (approximately 1 nm-100 nm), microscale dimensions (approximately 100 nm-100 µm), and macroscale dimensions, greater than about 100 µm. In other examples, the additives may be configured in geometries including, but not limited to, particles, flakes, rods, and the like. In additional examples, the additives may be distributed within a selected area of the matrix (e.g. adjacent a surface of the matrix) or evenly distributed or dissolved within the matrix. Examples of additives may include, but are not limited to, organic and inorganic substances such as flame retardants, ultraviolet (UV) protectors, thickeners (e.g., Cabosil®), and

reinforcements to enhance one or more of damage tolerance, toughness, wear resistance (e.g., rubbers, ceramics, and/or glasses).

[0026] Particularly advantageous additives are rubber particles, thermoplastic particles or combinations which are well known in the art to improve damage tolerance.

[0027] The term “impregnate” as used herein has its ordinary meaning as known to those skilled in the art and may include the introduction of a matrix film, powder, liquid, and or solution into at least a portion of the fibers. Impregnation may be facilitated by the application of one or more of heat, pressure, and solvents. “Full impregnation”, as discussed herein, may include its ordinary meaning and may further include impregnations that embed substantially all of the fibers within the matrix, such as in prepreg. “Partial impregnation”, as discussed herein, includes its ordinary meaning and may include impregnations that are less than substantially full impregnation and contain regions of dry fibers where a portion of the fibers are not embedded within the matrix.

[0028] The term “prepreg” as used herein has its ordinary meaning as known to those skilled in the art and thus includes sheets or lamina of fibers that have been impregnated with a matrix resin within at least a portion of their volume. The matrix may be present in a partially cured or uncured state.

[0029] The term “layup” as used herein has its ordinary meaning as known to those skilled in the art and may include one or more prepgs that are placed adjacent one another. In certain embodiments, the prepgs within the layup may be positioned in a selected orientation with respect to one another. In a further embodiment, the prepgs may optionally be stitched together with a threading material in order to inhibit their relative motion from a selected orientation. In additional embodiments, “layups” may comprise any combination of fully impregnated prepgs, partially impregnated prepgs, and perforated prepgs as discussed herein. Layups may be manufactured by techniques that may include, but are not limited to, hand layup, automated tape layup (ATL), advanced fiber placement (AFP), and filament winding.

[0030] The term “dimensional stability” as used herein has its ordinary meaning as known to those skilled in the art and thus includes the ability of a structure to maintain dimension within a selected range for a selected period of time. In certain embodiments, the selected range may be determined by the ability of the structure to perform an intended function, such as allowing the passage of a gas at a selected rate under a selected pressure.

[0031] The term “consolidation” as used herein has its ordinary meaning as known to those skilled in the art and thus includes processes in which the resin or matrix resin flows so as to displace void space. For example, “consolidation” may include, but is not limited to, flow of matrix into void spaces between and within fibers and prepgs, perforations, and the like. “Consolidation” may further take place under the action of one or more of heat, vacuum, and applied pressure.

[0032] The terms “cure” and “curing” as used herein have their ordinary meaning as known to those skilled in the art and may include polymerizing and/or cross-linking processes. Curing may be performed by processes that include, but are not limited to, heating, exposure to ultraviolet light, and exposure to radiation. In certain embodiments, curing may take place within the matrix. Prior to curing, the matrix may further comprise one or more compounds that are, at about room temperature, liquid, semi-solid, crystalline solids, and combinations thereof. In further embodiments, the matrix within the prepg may be formulated or partially cured in order to exhibit a selected stickiness or tack. In certain embodiments, consolidation and curing may be performed in a single process.

[0033] Embodiments of the present disclosure provide perforated prepgs, perforated prepg layups, and methods of manufacture. The perforated prepg possess enhanced ability for the removal of gases trapped within and between the perforated prepgs and perforated prepg layups. Trapped gases may be further removed prior to and/or during at least a portion of the consolidation process from the perforated prepgs alone, or when incorporated into perforated prepg layups, as well as prior to and/or during at least a portion of consolidation processes to form composite structures. In certain embodiments, perforations having selected configurations are introduced into the prepgs prior to layup. In

alternative embodiments, perforations having selected configurations are introduced into the prepregs during or after layup. Prior to and/or during at least a portion of consolidation of the prepregs, the perforations provide routes for gases trapped within and between the perforated prepregs or perforated prepeg layups to escape, reducing the residual porosity within the resulting composite and may elevate its mechanical properties. For example, composites having residual porosities of less than 10 vol. %, less than 4 vol. %, and less than 1 vol. %, on the basis of the total volume of the composite, may be achieved in this manner.

[0034] In certain embodiments, the perforated prepeg are configured to enable dimensional stability of the perforations. As a result, the perforations, once introduced, may remain dimensionally stable for a selected period of time. In certain embodiments, the perforations may remain dimensionally stable during storage of the perforated prepeg. In other embodiments, the perforations may remain dimensionally stable during at least a portion of the consolidation process. Beneficially, this design of the perforated prepeg allows removal of gases that are trapped within perforated prepeg and between layers of perforated prepeg within perforated prepeg layups.

[0035] In certain embodiments, dimensional stability may be provided by tailoring the viscosity of the matrix. For example, relatively high matrix viscosities, greater than about 1,000,000 centepoise (cp) at about room temperature, may provide perforations with dimensional stability. Preferably, the matrix resin is adapted to form dimensionally stable perforations at about room temperature and is capable of flowing at a selected temperature greater than room temperature to fill one or more of the perforations.

[0036] In further embodiments, perforations may be introduced into fully or partially impregnated prepeg. As discussed in greater detail below, it is possible to fabricate perforated prepeg in which a portion of the prepeg fibers are not impregnated with the matrix resin, a partially impregnated prepeg. By introducing perforations within such partially impregnated prepeg, gases may travel through the non-impregnated portions of the perforated prepeg, the perforated portions, inter-layer areas between prepeg in prepeg layups, and combinations thereof,

enhancing the ability of gases to escape partially impregnated, perforated preprints and layups. Beneficially, the ability of perforations to be introduced into either fully or partially impregnated preprints allows the methods discussed herein to be used with a wide range of preprints and applications.

[0037] In additional embodiments, the configuration of the perforations may be further varied in order to further enhance the ability of gases to escape from the preprints prior to and/or during at least a portion of the consolidation. In one example, the perforations may extend partially or completely through the thickness of the preprints. In another example, the perforations may be distributed through the preprint in a controlled manner, allowing for removal of gases from throughout the preprint, facilitating the formation of homogenous composites. In a further example, parameters of the perforations, including, but not limited to, size, shape, distribution, and perforation density (number of perforations per unit area) may be varied, as necessary.

[0038] Figures 1A-1B illustrate embodiments of fully and partially impregnated preprints 100, 108. In one embodiment, the preprints 100, 108 comprise fibers 104, and a matrix 102 that has been impregnated into at least a portion of the fibers 104.

[0039] The matrix 102 may be fully or partially impregnated into the fibers 104 in the form of solids, semi-solid films, powders, and liquids, with or without application of heat and/or pressure. In one example, a fully impregnated preprint 100 may have fibers that are substantially embedded within the matrix 102. In another example, a partially impregnated preprint 108 may contain selected areas that are substantially free from the matrix 102, such as matrix free zone 114 containing dry fibers 116 that are not substantially embedded within matrix 102 as shown in Fig 1C. In another example, a partially impregnated preprint 108 may contain selected areas that are partially free from matrix 102, such as shown as matrix free zone 114 containing mostly dry fiber 116, with some fibers in matrix free zone 114 embedded within matrix 102 as shown in Fig 1B. In one embodiment, partially impregnated preprints 108 may be formed by impregnating fibers 104 from two sides, leaving a matrix free zone 114 that is substantially without matrix 102

within the interior of the prepreg 108. In another example, partially impregnated prepgregs 108 may be formed by impregnating fibers 104 from a single side. As discussed below, the matrix free region 114 may cooperate with introduced perforations to enable removal of gases from partially impregnated prepgregs 108 during the consolidation and/or cure process.

[0040] Prepgregs 100, 108 may be formed using a number of techniques including, but not limited to, solution processes, such as solution dip and solution spray, as well as melt and working processes, such as direct melt and film calendaring. These processes are designed to bring at least a portion of the fibers 104 into contact with the matrix 102 in a flowable or malleable state and impregnate the fibers 104 with the matrix 102. To facilitate the layup process, the tack of the matrix 102 may be adjusted accordingly during and/or after matrix impregnation.

[0041] In solution dip processes, the fibers 104 may be passed through a bath of matrix solids that are dissolved within a solvent. As the fibers 104 pass through the bath, they pick up an amount of matrix solids that varies with factors such as the speed at which the fibers 104 are passed through the bath and the content of matrix solids within the bath. In solution spray processes, a selected amount of matrix solids are sprayed upon the fiber 104. In each case of solution processing, the impregnated fiber 104 is heated after exposure to the bath or spray in order to substantially remove the solvents and may further cause the matrix to begin the curing process.

[0042] In direct melt processes, the matrix 102 is provided as an approximately solvent-less coating directly upon the fiber 104. At application temperatures, the matrix 102 is sufficiently flowable so as to impregnate at least a portion of the fibers 104 to form the prepgregs 100, 108. Alternatively, in film calendaring, the matrix 102 is cast into a film from melt or solution. The fibers 104 are subsequently sandwiched between one or more matrix films, or one film applied from one side, and calendared so as to work matrix films into the fibers 104.

[0043] Additives may also be added to the matrix 102 prior to or after impregnation. In one embodiment, additives may comprise particulates that are added by sprinkling upon or within the matrix 102. Such additives may also be

advantageous for the removal of gases between layup plies because gases may move more freely through the passageways created by the additives positioned between the plies. Such particulate additives may include but are not limited to particles, such as any combination of thermoplastic particles, thermoset particles, siliceous particles, glass particles, rubber and inorganic particles having a mean diameter less than about 200 μ m.

[0044] The fiber content of the prepreg 100, 108 may also be varied, as dictated by the application. In one embodiment, the weight fraction of fiber 104 may range between about 20 to 80 wt. %, on the basis of the total weight of the prepgs 100, 108. In a further embodiment the weight fraction of fiber 104 in a perforated prepreg is less than 20wt.% such as for an adhesive or surfacing film, and may be zero such as for a resin film. The perforated prepreg of such an embodiment may be advantageously used as an adhesive or surfacing film where the perforations provide pathways for the removal of gases from a surface, from between adherents or from core. Such adhesives would include co-curable bonding applications for composites, metal and sandwich structure applications. Advantageous embodiments where the weight fraction of fiber 104 in a perforated prepreg is less than 20wt.% or none at all include an adhesive, for example wherein the fibers in the adhesive are a lightweight polyester or nylon scrim.

[0045] The fraction of the prepgs 100, 108 occupied by the matrix 102 may also be varied, as desired. In certain embodiments, the matrix 102 may occupy between about 20 to 80 wt. % of the prepgs 100, 108, on the basis of the total weight of the prepgs 100, 108.

[0046] Figures 2A-2B illustrate embodiments of fully and partially impregnated prepgs 200, 202 having perforations 204A and partial perforations 204B. In certain embodiments, perforations 204A may extend substantially through the width of prepgs 200, 202, while partial perforations 204B may extend through a selected portion of the width of prepgs 200, 202.

[0047] The perforations 204A, 204B may comprise passageways that are introduced into the prepgs 100, 108 and may include, but are not limited to, penetrations, holes, pores, slits, gaps, cracks, and combinations thereof. The

perforations 204A, 204B may be substantially uniform along their length, substantially non-uniform along their length, and combinations thereof. The perforations 204A, 204B may be further oriented at a selected angle with respect to the long axis of the fibers 104. For example, the perforations 204A, 204B, may extend approximately perpendicular to the long axis of the fibers 104.

[0048] Without being bound to a specific theory, perforated prepgs 200, 202 may facilitate the removal of gases from individual perforated prepgs 200, 202 and prepg layups 300, 310 incorporating perforated prepgs 200, 202 (Figures 3A-3B) prior to and/or during at least a portion of the consolidation and thus reduce the volume of porosity within composites formed therefrom, as compared to composites formed without perforated prepgs 200, 202. For example, perforations 204A, 204B provide escape routes for gases from the perforated prepgs 200, 202 and enable the gases to be removed from the perforated prepgs 200, 202 with greater ease and in greater volume as compared with non-perforated prepgs. The gases may include intralayer gases 302A that originate from within the matrix 102 or matrix free zone 114 of partially and/or fully impregnated prepgs 200, 202 and interlayer gases 302B, 302C that originate from the interlayer region from within the matrix 102 and between prepg layers in prepg layups. In particular, perforated prepgs 200, 202 are believed to be suited to the removal of gases that may evolve during consolidation.

[0049] Figures 3A and 3B illustrate embodiments of partially impregnated perforated prepg layups 300 and fully impregnated perforated prepg layups 310 from which gases may be removed. It may be understood that embodiments of the disclosure may include layups comprising any combination of fully impregnated prepgs 100, partially impregnated prepgs 102, fully impregnated perforated prepgs 200, and partially impregnated perforated prepgs 202.

[0050] As illustrated in Figures 3A-3B, gases 302A, 302B, 302C within the perforated prepgs 200, 202 may move through any combination of the matrix 102, matrix free zones 114, and perforations 204A, 204B in order to travel out of the perforated prepgs 200, 202. For example, under the influence of a force, which may arise due to matrix flow, applied pressure, and/or vacuum, the gases 302A,

302B, 302C may be urged from between and/or within an adjacent perforation 204. Once in the perforation 204, the gases 302A, 302B, 302C may easily travel out of the perforated preps 200, 202, without substantial resistance from the matrix 102.

[0051] As further illustrated in the partially impregnated perforated prepreg layup 300 of Figure 3A, the matrix free zone 114 may enable communication of gases 302A, 302C between any combination of two or more perforations 204A and 204B. For example, once gases 302A, 302C enter perforation 204A, instead of following the perforation 204A to travel out of the perforated prepreg 202, the gases 302A, 302C may travel through the matrix free zone 114 to perforation 204C before traveling out of the perforated prepreg 202. In another example, gases 302A, 302C may travel through one or more perforations 204A, 204B to the matrix free zone 114, where the gases 302A, 302C may travel through the matrix free zone 114 in order to escape the partially impregnated perforated prepreg layup 300. Beneficially, the ability of the gases 302A, 302C to move between perforations 204A, 204B may allow the gases 302A, 302C a variety of routes from the perforated prepreg 202. Such alternative routes may be beneficial under circumstances in which one or more perforations 204A, 204B is blocked or otherwise impassible, as the gases 302A, 302C may still travel out of the perforated preps 200, 202 through other combinations of perforations 204A, 204B and the matrix free zone 114.

[0052] In certain embodiments, the perforations 204A, 204B may be introduced into the preps 100, 108 after matrix impregnation by the application of energy, as illustrated in Figure 4. The energy may further comprise at least one of mechanical and heat energy. While fully and partially impregnated preps 100, 108 are discussed below in the context of introducing perforations 204A, 204B, it may be understood that perforations may also be introduced into fully impregnated perforated preps 200 and partially impregnated perforated preps 202. Furthermore, perforations 204A, 204B may be introduced into layups having any combination of fully impregnated preps 100, partially impregnated preps 102, fully impregnated perforated preps 200 and partially impregnated perforated preps 202.

[0053] In certain embodiments, the perforation process may break a number of fibers in the prepreg. In certain embodiments, the perforations 204A, 204B are introduced such that mechanical properties such as tensile strength, tensile modulus, and compression strength of composites formed from perforated prepgs 200, 202 is reduced by less than 10%, less than 5%, and/or less than 1%, as compared to a composite fabricated from comparable prepgs without perforations.

[0054] In one embodiment, mechanical energy may be applied through the use of a piercing tool 400 having one or more protrusions 402, such as a pin roller. In one embodiment the piercing tool 400 may be a pin roller containing a plurality of pins each pin being from about 100 μm high to about 5 cm high or more, more preferably about 1 mm to about 25 mm, as is needed to penetrate the prepreg to the desired depth. Each pin may be of any assorted shape such as conical, trapazoidal, beveled, etc. with a mean diameter of about 1 μm to about 10 mm, more preferably about 500 μm to 1500 μm at the surface of the prepreg when penetrated into the prepreg. The plurality of pins may be of the same or different height and diameters. The pins are preferably terminated in a sharp tip, but may be terminated by a tip that is blunt, rounded beveled or other desired shape. The protrusions 402 of the piercing tool 400 may pierce the prepgs 100, 108, through at least a portion of their thickness in order to introduce the perforations 204A, 204B. The protrusions 402 may be further configured in about the size, density, and/or pattern desired for the perforations 204A, 204B. In alternative embodiments, a plurality of piercing tools 400 may be employed in order to achieve the desired configuration of perforations 204A, 204B.

[0055] In a further embodiment, mechanical energy may be applied to the prepgs 100, 108 through the use of an ultrasound device 406 capable of emitting ultrasound waves 410. The ultrasound waves 410 comprise pressure waves having a frequency within the ultrasonic range. Upon entering the prepreg 100, 108, the pressure waves may cause the matrix 102 to fracture, generating the penetrations 204A, 204B. The formation of penetrations 204A, 204B by ultrasound waves 410 may also be facilitated by cooling the prepgs 100, 108 so as to reduce the energy

required to fracture the matrix 102. In a further embodiment, mechanical manipulation is applied to cooled preprints to form pores or perforations.

[0056] In another example, heat energy may be applied through the use of a laser 404. A beam 412 of the laser 404 is configured to burn a perforation 204A, 204B of selected depth through the preprints 100, 108. The cross-sectional area of the beam 412 may be approximately equal to the cross-sectional area of the desired perforation 204.

[0057] The perforations formed may be of any size diameter sufficient for the escape of gases from the perforated preprint or perforated preprint layup. For example, the mean diameter of each perforation may be from about 1 μm , or less, to about 5000 μm , or more, and preferably about 50 μm to about 500 μm , depending upon the density of the perforations and other factors such that the plurality of perforations allows sufficient escape of gases. In further embodiments, the distribution of the perforations 204 may be selected so as to enable the gases 302A, 302B, 302C to escape the perforated preprints 200, 202, as illustrated in the top down views of Figures 5A-5B. For example, the perforations 204 may be distributed over approximately the entire volume of the perforated preprints 200, 202. The distribution may be random, as illustrated in Figure 5A, or approximately uniform, as illustrated in Figure 5B. In one embodiment, the perforations 204 may be present in an average density greater than about one perforation per 20 square cm to as many as needed to allow sufficient escape of gases depending on perforation diameter. In a further example, the perforations 204 may be distributed in a selected pattern. Additionally, the perforations 204 may be separated by a selected distance (e.g. edge to edge distance, center to center distance, and the like), such as about 0.01 to 100 mm. Advantageously, by distributing the perforations 204 within the entire volume of the perforated preprints 200, 202, gases 302A, 302B, 302C may escape from throughout the volume of the perforated preprints 200, 202, inhibiting the development of regions of inhomogeneous porosity. It may be understood, however, that in alternative embodiments, perforations 204A, 204B may be introduced into a selected portion of the preprints 100, 108, rather than through substantially the entire volume of the preprints 100, 108.

[0058] In further embodiments, the viscosity of the matrix 102 may be configured so as to enable the perforations 204 to remain dimensionally stable. Beneficially, dimensional stability of the perforations 204 may permit handling of the perforated preprints 200, 202 during manufacture, storage, and use, without excessive precautions. The perforations formed are completely or substantially devoid of carbon fibers as well as matrix resin.

[0059] In another embodiment, the viscosity of the matrix 102 may be configured to flow and fill void spaces within and between the perforated preprints 200, 202 during consolidation. For example, in one embodiment, the viscosity of the matrix 102 may be configured to flow and fill void spaces upon application of heat, without external pressure. In other embodiments, the viscosity of the matrix 102 may be configured to flow and fill void spaces upon application of heat and external pressure and/or vacuum. Beneficially, by allowing the perforations 204A, 204B and other void spaces to be filled during consolidation, the perforations 204A, 204B and other void spaces can be configured so as to not contribute to the porosity of the resultant composite.

[0060] In further embodiments, perforated preprints 200, 202 may be configured to exhibit varying levels of tack. Advantageously, perforated preprints 200, 202 exhibiting a relatively high level of tack may be suitable for the fabrication of complex composite parts, as they may be positioned in relatively tight radii.

[0061] Figure 6 illustrates one embodiment of a system 600 for the consolidation and cure of perforated preprints 200, 202. In certain embodiments, the perforated preprints 200, 202 are configured as lamina that are designed to be stacked together in a selected orientation or layup 602, consolidated, and cured to form a composite part. For example, in perforated preprints 200, 202 having unidirectional orientations of the fiber 104, the fibers 104 may be oriented at 0°, 90°, or a selected angle θ with respect to the largest dimension of the prepreg 100, 108. Perforated preprints 200, 202 having any combination of orientations may be combined to form the layup 602. Similarly, layups 602 may be generated for perforated preprints 200, 202 having other fiber architectures.

[0062] The layup 602 may further comprise materials placed between one or more of the perforated prepreg layers within the layup 602. In one embodiment, a center core comprising wood, foam, honeycomb, or other structural materials may be so placed. Alternatively or additionally, doubler layers may be placed between the perforated prepreg layers so as to create elongated reinforcing regions. Furthermore, unimpregnated, or partially impregnated lightweight scrims, such as fiberglass, carbon, thermoplastic or other materials woven or unwoven, for example as described in U.S. Patent Publication No. 2005/0255766, may be introduced within the layup 602 in selected localities in order to facilitate removal of gases 302A, 302B, 302C or to increase mechanical properties such as damage tolerance.

[0063] In further embodiments, a continuous or discontinuous resin film having a lower viscosity than the matrix resin may be added to the prepreg 200/202 and/or layup 602 in order to improve tack. The addition of such a resin film to the layup 602 may facilitate preparation of the prepreg 200/202 layup 602, especially under circumstances where the matrix of the prepgs 200, 202 comprise additives, such as particles, or scrims. The resin film may be, and is preferably, perforated.

[0064] In embodiments of the layup 602 incorporating core structures, an adhesive material may also be employed in order to bond the core to the prepreg material during curing of the prepgs. As open center core structures, such as honeycomb structures, may contain a significant amount of gases, the adhesive layer may also be perforated or reticulated in order to facilitate removal of the gases. In additional embodiments, perforations 204A, 204B may be introduced through the prepgs 100, 102A, adhesive layers, and core layers in order to provide a substantially unobstructed path for gases 302A, 302B, 302C to be removed.

[0065] The layup 602 may be placed in contact with a tool 604 which provides a template shape for the perforated prepgs 200, 202 to adopt during consolidation and curing. For example, the tool 604 may comprise a relatively planar surface, curved surfaces, and combinations thereof. In one embodiment, a second tool may be located opposite the tool 604 so as to mold the face of the layup 602 adjacent the second tool. A force may be applied to tool 604 and the second tool to consolidate perforated prepgs 200, 202 and heated to cure perforated prepgs

200, 202 in a press cure system. A vacuum envelope 610 is optional to such a press cure system. To inhibit flow of the matrix 102 outside of the layup 602, or to improve gas flow one or more dams 606 may also be placed adjacent the edges of the layup 602.

[0066] Layup 602 and tool 604 may be further enclosed by a vacuum envelope 610 with a breather 612, such as unimpregnated fiberglass. In one embodiment, the breather 612 may be positioned adjacent at least one of the horizontal surfaces of the layup 602 for surface breathing. In another embodiment, the breather 612 may be placed adjacent one or more edges of the layup 602 for edge breathing. In further embodiments, the breather 612 may be positioned for both surface and edge breathing. Sealant tapes may be further employed, as necessary, to create an approximately vacuum tight seal between the tool 604 and the vacuum envelope 610.

[0067] In further embodiments, a separator film 614 may be introduced between the preps 200, 202 and the breather 612 at one or more surfaces in order to facilitate removal of fabricated composites from the system 600. In certain embodiments, the separator film 614 may be gas permeable. In alternative embodiments, the separator film 614 may be perforated. In additional embodiments, the separator film 614 may be substantially gas impermeable but may allow gases 302A, 302B, 302C to travel to edges of the layup 602 for removal.

[0068] Vacuum may be applied to the vacuum envelope 610 via the breather 612, to facilitate the removal of gases 302A, 302B, 302C from the layup 602. The layup 602 may be further heated with pressure, such as within an autoclave, or without pressure, such as within an oven, in order to lower the viscosity of the matrix 102 and induce pressure differentials that allow the matrix 102 to flow. The matrix flow may fill evacuated areas and displace gases 302A, 302B, 302C from the layup 602. The matrix 102 may further flow and enter the perforations 204 and other evacuated or open volume within the lay-up when the viscosity of the matrix 102 is sufficiently low in order to facilitate consolidation.

[0069] Upon completion of consolidation and curing of the layup 602, the layup 602 forms the composite part, which may possess a porosity less than about 10 vol. % on the basis of the total volume of the composite.

Examples

[0070] The following examples are provided to demonstrate the benefits of the embodiments of the disclosed perforated prepgs. For instance, it has been observed that perforated prepgs 200, 202 significantly improve the removal of gases from perforated prepreg layups 300, 310, without edge breathing, as compared to prepgs without perforations, and yield low porosity composites upon consolidation and curing. Furthermore, the examples show that the rate of removal of gases 302A, 302B, 302C from within and between layers of perforated prepgs within a layup was found to be greater than that of comparable prepgs without perforations. These examples are discussed for illustrative purposes and should not be construed to limit the scope of the disclosed embodiments.

Example 1 – Carbon fiber/Epoxy composites fabricated from partially impregnated prepgs with vacuum bag only (VBO) conditions in an oven

[0071] Three carbon fiber/epoxy composites, trials 1, 2, and 3, were fabricated from partially impregnated prepgs enclosed within a vacuum bag enclosure and subjected to vacuum pressure only (no autoclave pressure). This manner of processing is also referred to as vacuum bag only (VBO) processing. The use of edge breathing or sealing and the presence and absence of perforations were varied to examine the effect of each upon the composite porosity. It was observed that composites fabricated from perforated prepgs with sealed edges (without edge breathing), exhibited significantly lower porosity than composites fabricated under substantially identical conditions from prepgs without perforations. Furthermore, the porosity level of composites fabricated from perforated prepgs, with edges sealed, exhibited approximately the same porosity

level as comparable composites fabricated from non-perforated preprints with edge breathing.

Trial 1 – Non-perforated preprints with edge breathing

[0072] The carbon fiber/epoxy composite of Trial 1 was fabricated from unidirectional preprints comprising a polyacrylonitrile (PAN) based fiber, Thorne® T40/800 (Cytec Industries, West Paterson, NJ), having an areal fiber weight of about 145 g/m². The matrix, comprising CYCOM® 5215 epoxy resin (Cytec Industries, West Paterson, NJ), was partially impregnated such that the matrix weight fraction of the preprint was approximately 35 wt. %. The preprint was cut into sheets of approximately 30.5 cm x 30.5 cm and approximately 30 of these sheets were stacked in a (0)₃₀ layup. The layup was bagged with silicone dams having breather strings along the edges to facilitate edge breathing, placed within a vacuum envelope, and subjected to a vacuum of approximately 20 mm Hg absolute for about 4 hours. Subsequently, the layup was cured by heating to a temperature of about 82°C for about 4 hours. The composite laminate so formed was sectioned and polished and observed to possess a porosity of less than about 0.1 volume %.

Trial 2 – Non-perforated preprints with edges sealed

[0073] The carbon fiber/epoxy composite of Trial 2 was fabricated in a manner similar to Trial 1, except that the layup was bagged with all edges sealed using sealant tape, which substantially inhibited edge breathing. The composite laminate so formed was sectioned and polished and observed to possess a porosity of about 5.5 volume %.

Trial 3 – Perforated preprints with edges sealed

[0074] The carbon fiber/epoxy composite of Trial 3 was fabricated in a manner similar to Trial 2, except that the preprints were mechanically perforated with a wood, cylindrically shaped pin roller about 18" long and 4" in diameter containing conical-shaped stell pins with dimensions of 6 mm high and 1 mm diameter at the base which terminate in a sharp tip evenly space approximately 6 mm apart. The pin

roller pins penetrate a prepreg a selected distance through the thickness of the prepreg to form perforations. The greater the distance of penetration, the greater the size of the resulting perforation. The perforations may vary in size from about 100 μm to about 1 mm in diameter as desired, depending upon the density of the penetrations. Multiple passes of the pin roller across a prepreg will increase the density of resulting perforations as desired while maintaining a relatively consistent size of each perforation provide a perforation density of approximately 2 perforations/cm². The perforations extended substantially through the thickness of each prepreg layer resulting in perforation of about 300 μm in diameter and were introduced into the prepgs prior to layup. Composite laminates so formed were sectioned and polished and observed to possess a porosity of less than about 0.1 volume %.

Example 1 – Summary

Table 1 – Summary of Example 1

Trial	Matrix	Fiber	Partial Impregnation	Matrix Fraction (wt. %)	Perforations	Edge Breathing	Porosity (volume %)
1	Cycom 5215	T40/80 0	Yes	35	No	Yes	less than 0.1
2	Cycom 5215	T40/80 0	Yes	35	No	No	5.5
3	Cycom 5215	T40/80 0	Yes	35	Yes	No	less than 0.1

[0075] The data of Table 1 show that the use of edge breathing, when fabricating non-perforated prepreg layups using vacuum pressure only, enabled a significant reduction in the porosity of the composite, from about 5.5 vol. % to less than about 0.1 vol. %. It was further observed that a similar reduction in the composite porosity could be achieved through the use of perforated prepgs, without the need for edge breathing.

Example 2 – Carbon fiber/Epoxy composites fabricated from partially impregnated preprints using autoclave pressure and vacuum

[0076] Three carbon fiber/epoxy composites, trials 4, 5, and 6, were fabricated from partially impregnated preprints with vacuum and autoclave pressure. Edge breathing and the presence and absence of perforations were varied to examine the effect of each upon the composite porosity. It was observed that composites fabricated with autoclave pressure from partially impregnated, perforated preprints, without edge breathing, exhibited significantly lower porosity than composites fabricated under substantially identical conditions from partially impregnated preprints without perforations. The porosity level of composites fabricated with autoclave pressure from perforated preprints, without edge breathing, exhibited approximately the same porosity level as comparable composites fabricated from non-perforated preprints with edge breathing and substantially less than a non-perforated preprint without edge breaking.

Trial 4 – Non-perforated preprints with edge breathing

[0077] The carbon fiber/epoxy composite of Trial 4 was fabricated from unidirectional preprints comprising a polyacrylonitrile (PAN) based fiber, HTS (Toho Tenax) having an areal fiber weight of about 190 g/m². The matrix, comprising CYCOM® 977-2 epoxy resin (Cytec Industries, West Paterson, NJ), was partially impregnated such that the weight fraction of the preprint was approximately 34 wt %. A layup that was about 50.8 cm x 50.8 cm was formed having multiple ply build-ups ranging in size between about 7.6 cm x 7.6 cm to 10.2 cm x 10.2 cm at about the center of the panel. The layup was configured with preprints in an alternating, 0°/90° orientation about 20 plies with the buildup about an additional 20 plies interspersed within the larger plies. The layup was further configured such that a large amount of air, approximately 200 cm³ in total was trapped between the preprint layers near the build-up. The layup was bagged with silicone edge dams with breather strings along the edge such that the edges were attached to the breather. The layup was placed into a vacuum envelope and subjected to a vacuum of approximately 20 mm Hg absolute for about 4 hours. Subsequently, the layup was

cured by heating to a temperature of about 177°C and application of about 100 psi pressure for about 2 hours. The composite laminate so formed was sectioned and polished and observed to possess a porosity less than about 0.1 volume % throughout the laminate and in and around the ply build up areas.

Trial 5 – Non-perforated prepregs with edges sealed

[0078] The carbon fiber/epoxy composite of Trial 5 was fabricated in a manner similar to Trial 4, except that the layup was bagged with all four edges sealed with vacuum sealant tape, substantially inhibiting edge breathing. The porosity of the composite laminate so formed, in and around the ply build up areas, was measured to more than about 5 volume %.

Trial 6 – Perforated prepregs with edges sealed

[0079] The carbon fiber/epoxy composite of Trial 6 was fabricated in a manner similar to Trial 5 with all four edges sealed with vacuum sealant tape, except that the prepregs were mechanically penetrated with a pin roller to provide a perforation density of approximately 2 perforations/cm² using the pin roller described in Example 1. The perforations extended substantially through the thickness of each prepeg layer prior to layup. The composite laminate so formed was sectioned and polished and observed to have porosity less than about 0.1 volume % throughout the laminate and in and around the ply build up areas.

Example 2 – Summary

Table 2 – Summary of Example 2

Trial	Matrix	Fiber	Partial Impregnation	Matrix Fraction (vol. %)	Perforations	Edges Sealed	Porosity (volume %)
4	Cycom 977-2	HTS	Yes	34	No	No	less than 0.1
5	Cycom 977-2	HTS	Yes	34	No	Yes	greater than 5
6	Cycom 977-2	HTS	Yes	34	Yes	Yes	less than 0.1

[0080] The data in Summary Table 2, show that the use of edge breather when fabricating non-perforated prepreg layups using vacuum and autoclave pressure enables a significant reduction in the porosity of the composite, from about 5 vol. % to less than about 0.1 vol. %. The data further shows that a similar reduction in the composite porosity could be achieved through the use of perforated preps, without the need for edge breathing.

Example 3 – Carbon fiber/Epoxy composites fabricated from fully impregnated preps with vacuum bag only (VBO) conditions in an oven.

[0081] Two carbon fiber/epoxy composites, trials 7 and 8, were fabricated from substantially fully impregnated preps. It was observed that, in composites fabricated with vacuum pressure only from fully impregnated, perforated preps, exhibit lower porosity than composites consolidated under substantially identical conditions from preps without perforations.

Trial 7 – Non-perforated fully impregnated preps without edge breathing

[0082] The carbon fiber/epoxy composite of Trial 7 was fabricated from unidirectional preps comprising Thorne[®] T40/800 having an areal fiber weight of about 145 g/m². The matrix, comprising CYCOM[®] 5215 epoxy resin, was substantially fully impregnated and the matrix weight fraction of the prep was approximately 35 vol. %. The prep was impregnated at a temperature of about 105°C, at approximately 1 meter/min speed and using slower line speeds so as to allow the resin to substantially fully impregnate the prep. The prep was cut

into sheets of approximately 30.5 cm x 30.5 cm and approximately 30 of these sheets were stacked in a (0)₃₀ layup. The layup was bagged with all four edges sealed with vacuum sealant tape and a pin pricked separator overlaid the edge sealed layup. The overlaid separator substantially inhibited gas removal by edge breathing and simulated a very large, slit tape part processed with vacuum only pressure. The bagged layup was placed within a vacuum envelope containing breathers and subjected to a vacuum of approximately 20 mm Hg absolute for about 4 hours. Subsequently, the layup was cured under vacuum only pressure by heating to a temperature of about 82°C for about 4 hours. The composite laminate so formed was sectioned and polished and observed to possess a porosity of about 5 volume %.

Trial 8 – Perforated fully impregnated prepregs without edge breathing

[0083] The carbon fiber/epoxy composite of Trial 8 was fabricated in a manner similar to Trial 7, except that the prepregs were mechanically penetrated with a pin roller to provide approximately 2 perforations/cm² using the pin roller described in Example 1. The perforations extended substantially through the thickness of each prepreg layer prior to layup. The composite laminate so formed was polished and observed to possess a porosity of about 0.1 volume %.

Table 3 – Summary of Example 3

Trial	Matrix	Fiber	Full Impregnation	Matrix Fraction (vol. %)	Perforations	Edges Sealed	Porosity (volume %)
7	Cycom 5215	Thornel T40/800	Yes	35	No	Yes	5
8	Cycom 5215	Thornel T40/800	Yes	35	Yes	Yes	0.1

[0084] The data in summary Table 3, show that subjecting fully impregnated, perforated prepreg layups to vacuum during the composite fabrication process enabled a significant reduction in the porosity of the composite, as compared with non-perforated prepreg layups, from about 5 vol. % to about 0.1 vol.

%. These results show that the introduction of perforations within substantially fully impregnated prepregs significantly enhanced the removal of gases from the prepreg. Sealing the edges was performed in order to simulate a large part.

[0085] Although the foregoing description has shown, described, and pointed out the fundamental novel features of the present teachings, it will be understood that various omissions, substitutions, and changes in the form of the detail of the apparatus as illustrated, as well as the uses thereof, may be made by those skilled in the art, without departing from the scope of the present teachings. Consequently, the scope of the present teachings should not be limited to the foregoing discussion, but should be defined by the appended claims.

WHAT IS CLAIMED IS:

1. A perforated prepreg, comprising:
 - a prepreg comprising a matrix resin and fibers embedded within at least a portion of the matrix resin; and
 - a plurality of perforations distributed through at least a portion of the prepreg to enable gas movement through the prepreg;
 - wherein the matrix resin is adapted to form dimensionally stable perforations at about room temperature and is capable of flowing at a selected temperature greater than room temperature to fill one or more of the perforations.
2. The perforated prepreg of Claim 1, wherein the matrix resin possesses a viscosity such that the matrix resin for a selected period of time at about room temperature does not substantially flow into the perforations.
3. The perforated prepreg of Claim 1, wherein the viscosity of the matrix resin is greater than about 1,000,000 cp at about room temperature.
4. The perforated prepreg of Claim 1, wherein the viscosity of the matrix resin is less than about 300,000 cp during consolidation and/or cure to facilitate flow of the matrix resin into void spaces within the perforated prepgs including the perforations.
5. The perforated prepreg of any of Claim 1, wherein the one or more perforations comprise penetrations, holes, pores, cracks, slits, gaps and combinations thereof.
6. The perforated prepreg of Claim 1, wherein the one or more perforations extend a selected distance through the thickness of the perforated prepreg.
7. The perforated prepreg of Claim 1, wherein the perforations are present in a density greater than about one perforation per 20 square centimeters within the perforated prepreg.
8. The perforated prepreg of Claim 1, wherein the perforations possess a diameter of about 100 μ m to about 500 μ m at a density of about 2 perforations per square centimeter.

9. The method of Claim 1, wherein the perforated prepreg is partially impregnated or fully impregnated.

10. The perforated prepreg of Claim 1 wherein the fibers comprise a weight fraction of the perforated prepreg of less than 20wt.%.

11. A method of forming a fiber-reinforced composite, comprising:

introducing one or more perforated prepgs comprising a matrix resin and fibers embedded within at least a portion of the matrix resin;

applying at least one of heat, vacuum or pressure to consolidate and/or cure at least one of the perforated prepgs to form a composite;

wherein the one or more perforations are configured so as to enable transport of gases from within the body of the one or more perforated prepgs to an external surface of the perforated prepreg.

12. The method of Claim 11, wherein the perforated prepreg is partially impregnated or fully impregnated.

13. The composite made by the method of Claim 11 having a porosity less than 10 vol. % on the basis of the total volume of the composite.

14. A method of making a perforated prepreg comprising:

transmitting energy to a prepreg to form one or more perforations in a portion of the prepreg extending a selected distance through the thickness of the prepreg.

15. The method of Claim 14, wherein the energy is transmitted in the form of a pin press to pierce the prepreg from the outer surface a selected distance through the thickness of the prepreg.

16. The method of Claim 14, wherein the energy is transmitted in the form of an ultrasonic pressure wave.

17. The method of Claim 14, wherein the energy is transmitted by the application of heat energy.

18. The method of Claim 14, wherein, on average, at least 1 perforation is present per about 1.0 cm² of the prepreg.

19. The method of making a perforated prepreg of Claim 14 wherein the prepreg comprises fibers with a weight fraction of the prepreg of less than 20wt.%.

20. A perforated prepreg layup comprising one or more perforated prepgs.

21. The perforated prepreg layup of Claim 20, wherein the perforated prepreg layup further comprises one or more prepgs without perforations.

22. The perforated prepreg layup of Claim 20, wherein prepgs with and/or without perforations are assembled into a layup and subsequently perforations are introduced within at least a portion of the prepreg layup.




FIG. 1A




FIG. 1B







FIG. 1C








FIG. 3B






FIG. 4






FIG. 6