



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2713123 C 2013/02/19

(11)(21) **2 713 123**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(86) Date de dépôt PCT/PCT Filing Date: 2008/12/19
(87) Date publication PCT/PCT Publication Date: 2009/07/02
(45) Date de délivrance/Issue Date: 2013/02/19
(85) Entrée phase nationale/National Entry: 2010/07/23
(86) N° demande PCT/PCT Application No.: EP 2008/068070
(87) N° publication PCT/PCT Publication No.: 2009/080772
(30) Priorité/Priority: 2007/12/21 (DE10 2007 062 600.4)

(51) Cl.Int./Int.Cl. *B32B 21/06* (2006.01),
B32B 38/14 (2006.01), *B44C 5/04* (2006.01)
(72) Inventeur/Inventor:
BUHLMANN, CARSTEN, DE
(73) Propriétaire/Owner:
SURFACE TECHNOLOGIES GMBH & CO. KG, DD
(74) Agent: RIDOUT & MAYBEE LLP

(54) Titre : PROCEDE DE FABRICATION DE STRATIFIE DECORATIF
(54) Title: PROCESS FOR PRODUCING A DECORATIVE LAMINATE

(57) **Abrégé/Abstract:**

A method for producing a decorated laminate having a plate-shaped core made of wood or wood material, a decorative layer on at least one side of the core, and a cover layer having aminoplast on the decorative layer, comprising the following steps: providing the plate-shaped core, fastening a cellulose nonwoven material on at least one side of the core, printing the decoration on the exposed side of the cellulose nonwoven material, attaching at least one curable cover layer on the printed decoration, and curing the curable layers.



(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES
PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG(19) Weltorganisation für geistiges Eigentum
Internationales Büro(43) Internationales Veröffentlichungsdatum
2. Juli 2009 (02.07.2009)

PCT

(10) Internationale Veröffentlichungsnummer
WO 2009/080772 A1(51) Internationale Patentklassifikation:
B32B 21/06 (2006.01) **B32B 38/14** (2006.01)
B44C 5/04 (2006.01)(74) Anwalt: LIPPERT, STACHOW & PARTNER; Postfach
30 02 08, 51412 Bergisch Gladbach (DE).

(21) Internationales Aktenzeichen: PCT/EP2008/068070

(22) Internationales Anmeldedatum:
19. Dezember 2008 (19.12.2008)

(25) Einreichungssprache: Deutsch

(26) Veröffentlichungssprache: Deutsch

(30) Angaben zur Priorität:
10 2007 062 600.4
21. Dezember 2007 (21.12.2007) DE(71) Anmelder (für alle Bestimmungsstaaten mit Ausnahme
von US): **AKZENTA PANELEE + PROFILE GMBH**
[DE/DE]; Werner-von-Siemens-Str. 18-20, 56759 Kaisers-
esch (DE).

(72) Erfinder; und

(75) Erfinder/Anmelder (nur für US): **BUHLMANN,**
Carsten [DE/DE]; Friedensallee 14, 15834 Rangsdorf
(DE).(81) Bestimmungsstaaten (soweit nicht anders angegeben, für
jede verfügbare nationale Schutzrechtsart): AE, AG, AL,
AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ,
CA, CH, CN, CO, CR, CU, CZ, DK, DM, DO, DZ, EC, EE,
EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID,
IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK,
LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW,
MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT,
RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ,
TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM,
ZW.(84) Bestimmungsstaaten (soweit nicht anders angegeben, für
jede verfügbare regionale Schutzrechtsart): ARIPO (BW,
GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG,
ZM, ZW), eurasisches (AM, AZ, BY, KG, KZ, MD, RU,
TJ, TM), europäisches (AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF,
BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN,
TD, TG).

Veröffentlicht:

— mit internationalem Recherchenbericht

(54) Title: METHOD FOR PRODUCING A DECORATIVE LAMINATE

(54) Bezeichnung: VERFAHREN ZUR HERSTELLUNG EINES DEKORATIVEN LAMINATS

(57) Abstract: A method for producing a decorated laminate having a plate-shaped core made of wood or wood material, a decorative layer on at least one side of the core, and a cover layer having aminoplast on the decorative layer, comprising the following steps: providing the plate-shaped core, fastening a cellulose nonwoven material on at least one side of the core, printing the decoration on the exposed side of the cellulose nonwoven material, attaching at least one curable cover layer on the printed decoration, and curing the curable layers.

(57) Zusammenfassung: Verfahren zum Herstellen eines dekorierten Laminats mit einem plattenförmigen Kern aus Holz oder Holzwerkstoff, einer Dekorschicht auf mindestens einer Seite des Kerns und einer Deckschicht mit Aminoplast auf der Dekorschicht, umfassend die Schritte: Bereitstellen des plattenförmigen Kerns, Befestigen eines Cellulosevlieses auf mindestens einer Seite des Kerns, Drucken des Dekors auf die freiliegende Seite des Cellulosevlieses, Anbringen von mindestens einer aushärtbaren Deckschicht auf dem gedruckten Dekor, Aushärten der aushärtbaren Schichten.

WO 2009/080772 A1

WO 2009/080772

PCT/EP2008/068070

Process for producing a decorative laminate

The invention concerns a process for producing a decorative
5 laminate, in particular a laminate having a carrier based on wood materials
with a decoration and at least one cover or protective layer arranged
thereover.

Such laminates are frequently employed for example for floors, wall
and ceiling claddings, working panels and furniture. In that case the
10 decoration can imitate another material, for example wood, ceramic,
natural or artificial stone or can take account of artistic or practical aspects.
Usually the decoration is protected from wear by a more or less transparent
thermoplastic layer. It is also usual for the surface of that cover layer to be
provided with a structure which is in spatial relationship with the decoration
15 and which is referred to as Synchronpore.

Technical development hitherto has led essentially to two different
groups of materials for the cover layers. So-called lacquer layers are
formed from compositions which contain components which by heat and/or
radiation can be polymerised and/or crosslinked and thereby hardened,
20 such as for example acrylates, epoxies, maleimides.

The second group of material used for the cover layers includes the
so-called aminoplasts. That term is used to denote polycondensation
products of carbonyl compounds, in particular formaldehyde, and
compounds containing amino groups such as for example urea, melamine
25 and urethane. Production of the layers in the laminate is usually
implemented by employing aqueous solutions of condensation products of a
carbonyl compound and amine with an excess of the carbonyl compound
which crosslink upon drying and heating to give a thermosetting structure.
As in that case both the water present as the solvent and also the water
30 which occurs in the condensation reaction escapes in the form of vapour
hardening must be effected at least substantially in a press so that the
product acquires the desired strength and surface quality.

The decoration is conventionally implemented in the form of a
printed paper or paper otherwise provided with a pattern, or other cellulose

nonwoven material impregnated with hardenable lacquer or synthetic resin and arranged between the carrier and a wear-resistant outer cover layer. Usually production of the impregnated decorative paper requires separate working operations in respect of printing and impregnation which generally
5 are performed in operations outside the actual laminate production process and represent a considerable cost factor. It is also necessary for the impregnation material for the decorative paper to be compatible with the lacquer or synthetic resin of the decorative layer, which cannot be presupposed in particular when the lacquer and the synthetic resin come
10 together.

A further problem of this technology is that upon impregnation of the decorative paper, it experiences a change in size which has to be taken into consideration in the further course of the process if the spatial relationship between the decoration and the surface structure (Synchronpore) is to be
15 retained. That turns out to be difficult in particular when the product is frequently changed.

WO 03/095202 A1, to solve that problem, proposes applying a resin-bearing intermediate layer to the carrier before application of the decorative paper, and using a decorative paper which contains only little or
20 no impregnation resin at all. That solution however also does not appear to be optimal because the application of the intermediate layer signifies an additional working step and the decorative paper also has to be printed upon prior to the laminate production operation.

There have therefore long been endeavours to produce the
25 decoration directly on the carrier in the laminate production process by so-called direct printing. Then no further process steps which change the dimensions need to take place between production of the decoration and production of the surface structure. DE 19532819 A1 discloses a process for the production of a wood material panel having an optically
30 configurable surface, wherein the carrier panel is successively provided with a base colouration, a sealing means, a print base and a decorative print. In that respect a surface lacquer is used as the print base. In that structure therefore no paper is now contained in the decorative layer.

WO 2006/002917 A2 describes a process for producing a panel having a surface which has a decoration, in which the surface to be provided with the decoration is primed, smoothed with a plurality of filler layers and a roller treatment and printed upon to produce the decoration.

5 The primer layer can be applied in the form of a synthetic resin layer and the printed surface can be provided with a sealing means which can comprise synthetic resin.

10 Parkettmagazin 5/2007, pages 49 to 51, describes the structure of such a directly printed panel which under the printed colour layer has at least one primer and a plurality of rolled base layers.

What is common to the known processes operating with direct printing is that a relatively large number of working operations is necessary for preparation of the surface to be printed upon.

15 The problem of the present invention is that of providing a process with which the decoration can be more easily and less expensively applied to decorated laminates.

That problem is solved by a process as set forth in the main claim.

20 More specifically it was surprisingly found that it is possible to apply to a cellulose nonwoven material fixed on at least one side of the core of wood or wood material, a decoration which is of outstanding quality and to which the usual hardenable cover layers can be applied without difficulty and hardened. The nonwoven material can therefore replace the priming and smoothing layers without the print suffering from quality impairments.

25 The carrier or core of the laminate substantially comprises a preferably plate-shaped wood or wood material. Fibre panels, in particular HDF and MDF panels are preferred.

Preferably the cellulose nonwoven material is glued on the core. For that purpose advantageously either one side of the core and/or a side of the cellulose nonwoven material is coated with adhesive.

30 The adhesive is preferably a fluid hardening glue, particularly preferably a urea formaldehyde glue.

The term cellulose nonwoven material is used here to denote all flat structures essentially comprising cellulose fibres, including paper. The

various qualities of the nonwoven materials differ for example in terms of thickness, fibre strength and porosity. Depending on the respective desired detail resolution of the print image, an upper limit in terms of pore size must be observed. On the other hand porosity promotes the absorption of the printing ink and anchoring with the adhesive.

The cellulose nonwoven material is preferably a paper, in particular a so-called printing base paper. That is used to denote for example the paper qualities usually employed for printing the decorative paper. The printing base paper can already have a light basic shade of the decoration, but it can also be white or be of another colour. Papers of a weight in relation to surface area of from 20 to 200 g/m² are preferred, particularly preferably from 40 to 80 g/m².

When a liquid glue is used, it is then desirable for the nonwoven material to be joined to the core by at least partial hardening of the glue under the effect of pressure and heat. An advantage of the process using liquid glue however is also that upon hardening the liquid glue can compensate for irregularities in the surface of the core, whereby contact between the printing mould and the printing material is improved and the quality of the print increased. That applies in particular when the printing is performed by means of a smoothing roller on the nonwoven material.

It may be necessary to match the flow and wetting properties and the application weight of the glue to the properties of the cellulose nonwoven material used in order to avoid glue passing through the nonwoven material to the exposed surface. Such glue penetration can be troublesome in regard to the subsequent printing operation, particularly if it occurs in locally irregular manner, and possibly also interferes with the visual impression of the finished laminate. The man skilled in the art however is capable of avoiding that problem by a variation in the above-mentioned parameters.

Basically all known printing processes are suitable for producing the decoration. Preferred processes however are those which have a certain tolerance in relation to irregularities in the printing material such as offset printing, indirect intaglio printing (transfer from the engraved roller to the

printing material by means of a rubber blanket), flexoprinting and digital printing processes such as for example ink jet or transfer printing.

The decoration can be printed in one colour with a printing mechanism, in which case advantageously a second colour can
5 implemented by the shade of the printing base paper. It is equally possible for a plurality of colours to be successively printed with a plurality of printing mechanisms.

When carrying that process into effect it was found that the surface of the nonwoven material fixed on the core remains sufficiently absorbent if
10 penetration of the glue therethrough is avoided. The consequence of this is that the printing ink is readily absorbed by the nonwoven material and there is no risk of smearing in further working steps such as for example further printing stages or the application of the cover layer. Relatively short drying times after the individual printing operations are therefore
15 sufficient.

Basically the known synthetic resins and lacquers are suitable as the material for the at least one hardenable cover layer. Thus it is possible to also apply radiation-crosslinkable lacquers as the cover layer. However cover layers of aminoplasts, in particular melamine formaldehyde resins,
20 are preferred.

It is advantageous for a particulate hard solid material, preferably aluminium oxide, silicon dioxide, silicon carbide or boron nitride to be incorporated into the at least one cover layer. The solid material is of a suitable mean particle size for example of 30 to 200 µm.

25 In another advantageous embodiment according to the invention the cover layer is applied in the form of a so-called overlay. This involves a fibre material layer, for example a paper, which is impregnated with the hardenable aminoplast intended for the cover layer, for example melamine formaldehyde resin. The hard solid material can also be incorporated into
30 that overlay.

It is particularly advantageous for the cover layer of aminoplast to be applied in the form of a plurality of sublayers and for each sublayer to be dried prior to application of the next. In that way the mechanical

properties of the hardened cover layer are improved. Optionally the particulate hard solid material is preferably incorporated into the lower one of the sublayers and not into the outermost sublayer. That provides that the solid material particles do not protrude from the surface of the finished laminate, which can both be detrimental for the appearance and touch and also in terms of use and damage to the tools for further processing, for example the press surfaces.

After application of the cover layer the laminate is heated under pressure. A short-cycle or double-belt press is preferably used for that purpose. The pressures and temperatures to be applied depend on the nature of the resin and the structure of the laminate layers. Suitable ranges are between 20 and 60 kN/cm² and 160 to 220°C respectively. In the pressing operation, the definitive structure of the laminate surface is established by the shape of the pressing surface. The surface structure can be flexibly altered upon a change in product if preferably an interchangeable pressing sheet or a pressing belt or a pressing film is inserted between the press jaws and the laminate surface. Thus it is also possible to provide a pore structure (Synchronpore) which is positive (sunk) or negative (raised) in spatial relationship with the decoration, or a high-sheen or controlledly matted surface. The process according to the invention in that case affords the particular advantage that irregularities in the layers are compensated without a further intermediate treatment or subsequent treatment such as the application of grinding and smoothing lacquer layers or treatment with a smoothing roller, in the pressing operation. The Synchronpore can be embodied in a simple manner if a digitally controlled process is used for production of the pressing plate, pressing belt or pressing film, and the same data set is used for the digital printing operation as for the pressing plate, pressing belt or pressing film, possibly after conversion, because the print image no longer shrinks after the printing operation.

Advantageously on the non-decorated side of the core the laminate is provided with a stabilising layer to prevent deformation under changing climatic conditions. In the simplest way that is achieved if the stabilising

layer corresponds in its layer structure to the structure of the decoration side. When using the process according to the invention that stabilising layer can be respectively applied simultaneously with the corresponding layers of the decoration side, that is to say possibly gluing on a stabilising
5 layer paper and applying the layer or layers corresponding to the decorative layer.

The process according to the invention provides that in the production of the laminates preparation of the cores for the direct printing operation is substantially more economical than the state of the art
10 because only one layer of cellulose nonwoven material, in particular paper, is applied, and the multiple coating and smoothing operations necessary with the known processes are avoided.

Embodiment

MDF panels measuring about 2 x 3 m are cleaned, smoothed and
15 heat-treated. By means of a roller coating installation an acid hardener for urea formaldehyde glue (hardener 2547-Akzo Nobel) is applied with an application weight of about 8 g per square metre at ambient temperature and slightly dried with an IR radiating device. Thereupon a glue layer of about 40 g per square metre (urea formaldehyde glue 1206-Akzo Nobel) is
20 again applied with a roller. A cream-coloured printing base paper of a weight in relation to surface area of 60 g per square metre is applied by the roller to the glue layer while still wet and pressed in a calender at 160 kN/cm² and at a roller temperature of 190°C, the glue being at least partially hardened. In that case the outside surface of the paper remains
25 unchanged, that is to say no glue penetrates through. Thereafter the paper is cut in the gap between the panels. The panels are immediately conveyed to a printing station in which a first colour of the decoration is applied by means of indirect intaglio printing. In a further printing station the second and third colours are applied, in which case brief airing between
30 the stations is sufficient to dry the printing ink. Now a thin layer of a melamine formaldehyde resin (MFR, about 10 g/m²) is applied and dried with an IR radiating device until the surface is bone-dry. In that condition the panels can be stacked or stored.

Further processing of the decorated panels is effected either directly after the printing operation (without application of the thin MFR layer) or after application of that layer and storage. Now a layer of a melamine resin in water which contains particles of aluminium oxide (corundum) of a mean
5 size of 180 – 220 μm is applied to the decoration on the top side of the panel or the thin MFR layer by means of an application roller (for the purposes of low wear of ceramic). The viscosity of the resin solution is 120 mPas with a solid content of 60 percent by weight. The application weight of the resin solution is about 50 g/m^2 while that of the corundum is 15 – 20
10 g/m^2 . The resin application is not sufficient to completely cover the corundum particles. The resin application weight corresponds to a layer thickness of about 40 μm (density 1.25 g/cm^3). The resin application is dried by means of an IR radiating device until its surface is bone dry and has sufficient adhesion to the decoration. In that case a flow of air is
15 passed over the surface of the resin layer. At the same time as the application of resin to the top side an identical application but without corundum is applied to the underside of the panel as a stabilising layer and is subjected to initial drying. In the conveying operation the panel rests on a suitable conveyor means, for example a so-called disc transport means
20 which is known from the painting and lacquering art and which bears the panel in point relationship and thus permits drying of the underside of the panel. After the initial drying operation the panel lies in the edge region on narrow rollers.

After the drying step a further layer of about 50 g/m^2 of the aqueous
25 melamine resin is applied to the decoration side and to the underside and once again dried. That operation is repeated up to three times. As a result the resin layer is now of a thickness of up to 250 μm and completely covers the corundum particles.

The panel now coated with the useful layer and the stabilising layer
30 is placed in an SC press and pressed for about 8 – 15 s at a temperature of the pressing plates of about 200°C (corresponding approximately to 160°C at the product) and under a pressure of 35 – 60 kN/cm^2 . In that case the surface relief corresponding to the decor is embossed (Synchronpore).

CLAIMS:

1. A process for producing a decorated laminate comprising a plate-shaped core of wood or wood material, a decorative layer on at least one side of the core and a cover layer having aminoplast on the decorative layer, comprising the steps:

- providing the plate-shaped core,
 - fixing a cellulose nonwoven material on at least one side of the core,
 - printing the decoration onto the exposed side of the cellulose nonwoven material,
 - applying at least one hardenable cover layer to the printed decoration, and
 - hardening the hardenable layers,
- characterised in that
- the cellulose nonwoven material is glued onto the core using a liquid hardenable glue.

2. A process according to claim 1 characterised in that prior to the step of gluing on the cellulose nonwoven material at least one side of the core is coated with adhesive.

3. A process according to claim 2 characterised in that prior to the gluing operation the cellulose nonwoven material is coated on one side with adhesive.

4. A process according to any one of claims 1 to 3 characterised in that the hardening glue is a urea formaldehyde glue.

5. A process according to claims 1 to 4, characterised in that the cellulose nonwoven material is a paper.

6. A process according to claim 5, characterised in that the paper is a printing base paper.

7. A process according to claim 5 or claim 6, characterised in that the paper has a weight in relation to surface area of between 20 and 200 g per square metre.

8. A process according to claim 7, characterised in that the paper has a weight in relation to surface area of between 40 and 80 g per square metre.

9. A process according to one of claims 1 and 4, characterised in that the nonwoven material is joined to the plate-shaped core under pressure and heat with at least partial hardening of the glue.

10. A process according to one of claims 1 to 9, characterised in that the decoration is applied by offset printing, indirect intaglio printing, flexoprinting or a digital printing process.

11. A process according to one of claims 1 to 10, characterised in that the decoration is printed in one colour.

12. A process according to claims 1 to 10, characterised in that the decoration is printed in a plurality of colours.

13. A process according to one of claims 1 to 12, characterised in that the at least one cover layer is formed from an aminoplast.

14. A process according to claim 13, characterised in that the aminoplast is a melamine formaldehyde resin.

15. A process according to claim 13 or claim 14, characterised in that there is a particulate hard solid material in at least one cover layer.

16. A process according to claim 15, characterised in that the solid material is aluminium oxide, silicon dioxide, silicon carbide or boron nitride.

17. A process according to one of claims 13 to 16, characterised in that the cover layer is applied in the form of an overlay.

18. A process according to one of claims 13 to 17, characterised in that a plurality of cover layers are applied.

19. A process according to claim 18, characterised in that each cover layer is surface-dried after the application operation.

20. A process according to claim 18 or claim 19, characterised in that the hard solid material is applied with the lowermost layer and the uppermost layer contains no solid material.

21. A process according to one of claims 1 to 20, characterised in that the laminate of at least core, cellulose nonwoven material and a cover layer is hardened under pressure and heat.

22. A process according to claim 21 characterised in that the laminate is heated and pressed in a double-belt or short-cycle press.

23. A process according to claim 21 or claim 22, characterised in that in the heating and pressing procedure a structure is embossed into the surface of the outermost cover layer.

24. A process according to claim 23, characterised in that the structure is in relation to the decoration.

25. A process according to one of claims 1 to 24, characterised in that a stabilising layer is applied on the side of the core, that is remote from the decoration.

26. A process according to claim 25, characterised in that the stabilising layer is applied simultaneously with the decoration layers.