

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
26 June 2008 (26.06.2008)

PCT

(10) International Publication Number
WO 2008/075206 A2

(51) International Patent Classification:
A61K 9/00 (2006.01)

(21) International Application Number:
PCT/IB2007/004413

(22) International Filing Date: 18 May 2007 (18.05.2007)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/801,975 19 May 2006 (19.05.2006) US

(71) Applicant (for all designated States except US): **THE UNIVERSITY OF HONG KONG** [CN/CN]; Pokfulam Road, Hong Kong (CN).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **CHAN, Barbara, Pui** [—/CN]; Flat D, 15/F., Tower 2, Marina Habitat, Ap Lei Chau, Hong Kong (CN). **CHAN, Godfrey, Chi-Fung** [—/CN]; 4F, Block E#1, Fontana Gardens, Ka Ning Path, Causeway Bay, Hong Kong (CN). **WONG, Hoi Ling** [—/CN]; Flat H, 21/F, Block 14, Chevalier Garden, Ma On Shan, Hong Kong (CN). **CHEUNG, Pik To** [—/CN]; Flat D, 17/F, Tower 17, Laguna Verde, Hung

Hom, Kowloon, Hong Kong (CN). **CHEAH, Kathryn, Song-Eng** [—/CN]; 5G Tam Gardens, 25 Sha Wan Drive, Hong Kong (CN). **CHAN, Danny** [AU/CN]; Flat F, 24/F, Tower 8, South Horizons, Apleichau, Hong Kong (CN).


(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

(54) Title: CELL-MATRIX MICROSPHERES, METHODS FOR PREPARATION AND APPLICATIONS



(57) Abstract: A method has been developed to produce stable cell-matrix microspheres with up to 100% encapsulation efficiency and high cell viability, using matrix or biomaterial systems with poor shape and mechanical stability for applications including cell therapeutics via microinjection or surgical implantation, 3D culture for *in vitro* expansion without repeated cell splitting using enzymatic digestion or mechanical dissociation and for enhanced production of therapeutic biomolecules, and *in vitro* modelling for morphogenesis studies. The modified droplet generation method is simple and scalable and enables the production of cell-matrix microspheres when the matrix or biomaterial system used has low concentration, with slow phase transition, with poor shape and mechanical stability.

WO 2008/075206 A2

CELL-MATRIX MICROSPHERES, METHODS FOR PREPARATION AND APPLICATIONS

CROSS-REFERENCE TO RELATED APPLICATIONS

5 This application claims priority to U.S.S.N. 60/801,975 filed 19 May
2007.

FIELD OF INVENTION

 The present invention relates generally to cell-matrix microspheres,
associated products, methods for preparation and applications. More
10 specifically, it relates to methods producing cell-matrix microspheres and
immobilizing living cells, methods and processes for culturing these cells;
methods and processes for using these microspheres as therapeutics, as three
dimensional ("3D") microcarriers, and for production of biomolecules such
as therapeutic proteins, in a more efficient and economical manner.

15 BACKGROUND OF INVENTION

 Cell-based therapy provides a minimally invasive approach by local
injection at the site of defect via microsyringe needles and presents a
promising approach for tissue repair and regenerative medicine. However,
technological challenges associated with the localization, long term viability,
20 host tissue-integration and functional remodeling (Tatard, et al., *Curr. Drug*
Targets, 6(1):81-96 (2005); Tatard, et al., *Biomaterials*, 26(17):3727-37
(2005); Pittenger and Martin, *Circ. Res.*, 95(1):9-20 (2004); Bonaros, et al.,
Panminerva Med., 46(1):13-23 (2004)) of the injected cells, and injectability
and mechanical stability of the carriers (Crevensten, et al., *Ann. Biomed.*
25 *Eng.*, 32(3):430-4 (2004)) need to be resolved before clinical applications

can be successfully achieved.

Microencapsulation entraps cells within the confinement of a semi-permeable membrane or a homologous solid. It has been used for many years to aid immunoisolation during allogenic or xenogenic cell transplantation (Uludag et al., *Adv. Drug Deliv. Rev.*, 42(1-2):29-64 (2000); Orive, et al., *Trends Biotechnol.*, 22(2):87-92 (2004)). Sodium alginate dominates the field while other materials such as agarose (Batorsky, et al., *Biotechnol. Bioeng.*, 92(4):492-500 (2005)) and polyethylene glycol (PEG) (Nuttelman, et al., *Matrix Biol.*, 24(3):208-18 (2005)) are also used. None of these materials, if unmodified, support cell attachment and growth (Grohn, et al., *Biotechniques*, 22(5):970-5 (1997); Zimmermann, et al., *Biomaterials*, 24(12):2083-96 (2003); Nuttelman, et al., *Matrix Biol.*, 24(3):208-18 (2005)) thus requiring supplementation of natural extracellular matrix such as collagen for improvement (Grohn, et al., *Biotechniques*, 22(5):970-5 (1997); Batorsky, et al., *Biotechnol. Bioeng.*, 92(4):492-500 (2005)). Furthermore, since these systems avoid direct contact of the delivered cells with the host tissue, they do not allow cell migration and penetration. This prevents their use in regenerative medicine and tissue engineering, which entails host-implant integration at cellular level. Natural extracellular matrices such as collagen, fibrin and hyaluronic acid are suitable materials supporting cell growth (Yannas, *Natural Materials*, Ratner, et al. editors, *Biomaterials Sciences – An introduction to materials in medicine*, California, Academic Press, pp.84-93 (1996)). However, there is no microencapsulation system for these materials because of their poor mechanical and shape stability (Yannas, *Natural Materials*, Ratner, et al. editors, *Biomaterials Sciences – An*

introduction to materials in medicine, California, Academic Press, pp.84-93
(1996); Crevensten, et al., *Ann. Biomed. Eng.*, 32(3):430-4 (2004); Zhang, et
al., *Appl. Biochem. Biotechnol.*, 134(1):61-76 (2006), which is incompatible
with the existing microencapsulation techniques (Uludag, et al., *Adv. Drug*
5 *Deliv. Rev.*, 42(1-2):29-64 (2000)).

Existing encapsulation techniques include formation of emulsions
with an oil phase and generation of cell-containing droplets in a stirred
collection bath using a custom-made droplet generator, or injection of cells
into preformed matrix microspheres or microcapsules using a microinjector
10 (Grohn, et al., *Biotechniques*, 22(5):970-5 (1997); Batorsky, et al.,
Biotechnol. Bioeng., 92(4):492-500 (2005)). However, these methods
encounter problems when the matrix materials are low in concentration, or
with poor shape and mechanical stability such as collagen gel or hyaluronic
acid gel. First, the cell-matrix droplets or emulsions formed barely survive
15 the shear stress generated upon stirring during emulsification or stirring in
the liquid collection bath. Second, stirring is required immediately after
addition of the cell-matrix phase to mix well with the oil phase during
emulsification and to prevent the cell-matrix droplets from fusing together
during droplet generation. This does not allow sufficient time for the
20 formation of cell-matrix microspheres if the phase transition of the matrix
takes a longer time and fragmentizes the microspheres, leading to low
encapsulation efficiency.

Using living organisms with biosynthetic capability for large and
industrial scale production of useful biomolecules such as therapeutic protein
25 is commonly used in biotechnology. Although *E.coli* and yeasts have been

used for this purpose, the resulting molecules may differ from the natural products because of the absence of co- and post-modifications mechanisms in these microorganisms. Mammalian cells are therefore particularly good sources for proteins and vaccines. Culturing cells in suspensions can attain

5 high efficiency, reduce cost and favor mass production of therapeutic proteins. However, not all cells grow successfully in suspension, only cells such as hybridomas and tumor cells. Microcarrier technology has been developed for decades to enable large scale 3D culture by providing significantly increased surface area that is particularly advantageous for

10 anchorage dependent eukaryotes. Microcarriers have been used for large scale cell culture as early as the 70's. The first generation microcarrier, CYTODEX®, dextran microspheres with a cationic surface, has been used to scale up cell cultures by dramatically increasing the total surface area for cell binding. The technology evolved in the 80's to include collagen-coated

15 dextran beads, for better attachment and growth of cells and higher yield). There has been a trend in coating or mixing the solid microcarriers with natural extracellular matrix of cells such as collagen-coated alginate beads (Grohn, et al., *Biotechniques*, 22(5):970-5 (1997)), gelatin-coated poly-lactic-glycolic acid (PLGA) beads (Voigt, et al., *Tissue Eng.*,

20 8(2):263-72 (2002)) and gelatin-chitin composite beads (Li, et al., *Biotechnol. Lett.*, 26(11):879-83 (2004)), or crosslinking with natural peptide sequence governing cell adhesion and attachment such as RGD modified poly(ethylene glycol) (Nuttelman, et al., *Matrix Biol.*, 24(3):208-18 (2005)) to improve cell attachment and growth. This has led to development of newer generations of

25 microcarriers, CULTISPHER® G, which are either solid (Liu, et al., *Cell*

Transplant., 13(7-8): 809-16 (2004)) or porous (Bancel and Hu, *Biotechnol. Prog.*, 12(3):398-402 (1996)) gelatin beads, and CELLAGEN®, which are porous collagen beads (Overstreet, et al., *In Vitro Cell Dev. Biol. Anim.*, 39(5-6):228-34 (2003)). However, these systems employ technologically demanding fabrication process for the bead preparations, making the commercial preparations costly. The bead preparation has to be separated from the cell attachment procedure since most of the bead fabrication systems employ harsh conditions such as high temperature, freeze-drying, organic solvent extraction and chemical crosslinking treatment that cells do not survive. Moreover, the cell attachment procedure is a rate-limiting step of the microcarrier culture system (Sun, et al., *J. Biosci. Bioeng.*, 90(1):32-6 (2000)) requiring prolonged culture for cell attachment to the solid surfaces or cell penetration into the porous beads (Bancel and Hu, *Biotechnol. Prog.*, 12(3):398-402 (1996)). As a result, simple bead preparation using natural extracellular matrix materials without harsh fabrication conditions and prolonged cell attachment procedure will improve the efficiency and reduce the cost of the microcarrier culture system.

It is generally accepted that 3D culture provides a platform for cells to proliferate rapidly in an unrestricted manner (Geserick, et al., *Biotechnol. Bioeng.*, 69(3):266-74 (2000)) for scaling up (Dürschmid, et al., *Biotechnol. Bioeng.*, 83(6):681-6 (2003)). However, the productivity of actively and unrestrictedly proliferating cells is usually low because these cells may not synthesize proteins at a maximal rate outside their tissue-specific microenvironment and in actively proliferating cells, most of the metabolic energy is devoted to reproduction rather than synthetic activities

(Sanchez-Bustamante, et al., *Biotechnol. Bioeng.*, 93(1):169-180 (2005)).

Controlled proliferation technologies such as starvation of cells for essential nutrient or addition of DNA synthesis inhibitors (Suzuki and Ollis, *Biotechnol. Prog.*, 6(3):231-6 (1990)), isolation of specific cell lines such as

5 temperature sensitive CHO cells, which produce more proteins upon temperature shift to 39°C (Jenkins and Hovey, *Biotechnol. Bioeng.*, 42(9):1029-36 (1993)) and genetic manipulation with growth cycle controlling genes such as over-expressing tumor suppressor genes p53 (Kastan, et al., *Cancer Research*, 51:6304-11 (1991)), p21 (Watanabe,

10 *Biotechnol. Bioeng.*, 77:1-7 (2002)) and p27 (Coats, et al., *Science*, 272:877-80 (1996)), are usually employed to enhance the protein productivity of cells (U.S. Patent No. 6,274,341 to Bailey, et al.; Wurm, *Nature Biotechnol.*, 2(11):1393-1398 (2004)). However, these proliferation controlling strategies lead to reduced cell viability (Mercille, et al.,

15 *Cytotechnology*, 15(1-3):117-28 (1994)) and increased apoptosis (Ko and Prives, *Genes Dev.*, 10(9):1054-72 (1996)). Co-expressing the cell cycle controlling tumor suppressor genes with anti-apoptotic genes such as bcl-2 has been used to improve the cell viability problem (U.S. Patent No. 6,274,341 to Bailey, et al.). However, this system requires complicated

20 designs for the vector systems and complicated genetic manipulation that interferes the cell metabolism internally. Moreover, auto-regulated control for biphasic proliferation and production cycles has been achieved by using external repressable agent, tetracycline switch system (Mazur, et al., *Biotechnol. Bioeng.*, 65:144-150 (1999)) to preserve the inducible

25 growth-arresting production phase when the optimal cell density is reached

so that a longer window for enhanced productivity for 7 days can be achieved. The advantages of this system include the use of external agents that do not interfere with the overall metabolism of cells but the problems are the downstream purification procedures eliminating this antibiotic, the

5 genetic instability introduced by genetic manipulation as well as the instability of tetracycline in cultures. Recently, 3D multi-cellular micro-tissue cultures using a hanging-drop method with enhanced protein productivity in mammalian cells have been developed (Sanchez-Bustamante, et al., *Biotechnol. Bioeng.*, 93(1):169-180 (2005)).

10 It is therefore an object of the invention to provide methods for making cell microcarriers that are relatively inexpensive, efficient and favorable to cell viability, controlled proliferation and production of biomolecules, and the resulting cell matrix microcarriers.

It is a further object of the invention to provide methods for use

15 thereof in cell therapy and tissue engineering and manufacturing of biomolecules.

SUMMARY OF THE INVENTION

A method has been developed to produce stable cell-matrix microspheres with up to 100% encapsulation efficiency and high cell

20 viability, using matrix or biomaterial systems with poor shape and mechanical stability for applications including cell therapeutics via microinjection or surgical implantation, 3D culture for *in vitro* expansion without repeated cell splitting using enzymatic digestion or mechanical dissociation and for enhanced production of therapeutic biomolecules, and *in*

25 *vitro* modelling for morphogenesis studies. The modified droplet

generation method is simple and scalable and enables the production of cell-matrix microspheres when the matrix or biomaterial system used has low concentration, with slow phase transition, with poor shape and mechanical stability.

5 The method uses a formulation including cells, a first extracellular matrix (ECM), and other biomolecules. In the preferred embodiment, the first ECM, being capable of providing support to the cells, interacting with the cells to allow cell growth without introducing toxicity, and permitting cell migration and penetration, is a collagen, or other material that supports
10 cell growth and migration and has phase transition properties at conditions mild enough to support cell survival, such as, fibrin and hyaluronic acid. The composition can include a second ECM, such as a proteoglycan or GAG. These can interact in such a way that the interaction leads to a change in cellular responses in growth and differentiation and physical properties of
15 microspheres such as the volume of the structures, ECM density, cell density, mechanical property and stability, etc. The composition can also include a growth-stimulating signal such as human serum, platelet rich plasma or other blood products. Therapeutic components such as anti-inflammatory drugs and antibiotics can also be incorporated into the composition.

20 The method of forming microspheres includes the steps of mixing and dispensing the composition into liquid droplets in the right order and the right time with a dispensing unit. The pH of the first matrix is adjusted to be suitable for cell survival. The cell suspension and other biomolecules are mixed thoroughly with the matrix components as soon as possible to evenly
25 distribute cells throughout the solution form of the matrix before accelerating

phase transition. The liquid droplets are collected with a dry collection platform without mechanical disturbance. The platform has a surface property for maintaining the spherical shape of the liquid droplets, such as high surface tension. By maintaining the temperature low, the rate of matrix phase transition can be controlled as low as possible at a range between 2 minutes to 10 hours depending on the matrix concentration, preferably 30 minutes. The volume of the microspheres dispensed is preferably about 2.5 μ l. The diameter of the dispensed liquid droplets is preferably 2mm. In addition, the method comprises accelerating the rate of matrix phase transition after dispensing by raising the temperature at the collection platform preferably to 37 °C. The matrix components of the liquid droplets are allowed to undergo phase transition to form cell-matrix microspheres for a period of time, sufficient for phase transition to reach equilibrium.

The microspheres are stabilized by collecting the cell-matrix microspheres from the collection platform with minimal mechanical disturbance; maintaining the microspheres free-floating in a first medium for an extended period of time until the size of the microspheres becomes substantially constant; and releasing the microspheres from the first medium. The microspheres can be maintained free-floating either by keeping in suspension status in non-adhesive culture dish such as a Petri dish, or by culturing the microspheres in spinner flask or rotating vessel bioreactors. The size and mechanical strength of the microspheres can be controlled by controlled by at least one of the following parameters:: cell density, collagen concentration, serum concentration, composition of the ECM, ratio of the first and second ECM, volume of the liquid droplets, duration of the

free-floating status of microspheres. Increasing cell density, decreasing matrix concentration or decreasing volume of liquid droplets decreases size and increases stability of cell-matrix microspheres.

A system for producing microspheres includes the composition
5 described above, a dispensing unit for dispensing the composition into liquid droplets; and a collection platform for collecting the dispensed liquid droplets, comprising a surface with a surface property such that the spherical shape of the microspheres can be maintained; and for gelation of the matrix to form cell-matrix microspheres. The system can further comprise a
10 control unit for controlling the dispensing speed and volume, as well as a temperature control unit for maintaining the temperature of the composition during dispensing and during phase transition of the matrix.

The cell-matrix microspheres consisting of undifferentiated and viable cells can be injected or implanted, for example, for tissue repair or
15 regeneration. The method includes the steps of sedimenting the microspheres; removing the excess supernatant; re-suspending the microspheres in a liquid for injection or implantation; adding the microsphere suspension in the container for injection or implantation; and injecting or implanting the microspheres into defective tissues in animals or
20 humans such as a skin wound or an injured cartilage. In one embodiment, the method includes injecting or implanting the cell-matrix microspheres consisting of specifically differentiated and viable cells, wherein the matrix embeds these cells into defective tissues of animals or humans. The cell matrix microspheres are also useful for 3D cultures. These have numerous
25 advantages over the existing microcarrier systems. The system can be used to

culture protein-secreting cells in physiologically relevant microenvironment with significantly increased protein productivity via matrix-induced proliferation control as compared to monolayer cultures with unrestricted proliferation.

5 BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a schematic drawing showing the production setup for making cell-matrix microspheres.

Fig. 2 is a flow chart showing the production of mechanically stable cell-matrix microspheres with controllable size.

10 Fig. 3 is a flow chart showing the method controlling of the cell migration from the cell-matrix microspheres

Fig. 4A, 4B and 4C are graphs showing changes in diameters of hMSC-collagen microspheres (microns) against time (hours) as functions of cell density (Fig. 4A), collagen concentration (Fig. 4B) and droplet volume
15 (Fig. 4C).

Fig. 5A and 5B are graphs of the cell number (Figure 5A) and viability of encapsulated hMSCs, cell number over time post-encapsulation (days). All data are presented as mean +/- SD.

Fig. 6A-6D are graphs showing cell number versus cell density in
20 microspheres, cells/ml, (Fig. 6A), cell number versus plating density, microspheres/cm² (Fig. 6B), cell number, 95% CI versus monoplating, 3D first plating, 3D second plating, 3D third plating, and 3D fourth plating, (Fig. 6C), and microsphere number for the first, second, third and fourth plating (Fig. 6D). The central line is the median; the upper most and lower most bar
25 are the 2.5th and 97.5th percentile of data, respectively; the upper and lower

limit of the box are the 25th and 75th percentile of data, respectively, showing showed the number of outgrowing cells as functions of cell density (Fig. 6A) and plating density (Fig. 6B); Error bar plot (data are presented as mean +/- 95% Confidence Interval) compared the cell number between monolayer
5 culture and 3D microspheres (Fig. 6C); Box plot showed the number of microspheres at different platings (Fig. 6D).

Fig. 7 is a bar chart showing the number of single-cell derived colonies formed from cell outgrowths from the hMSC-collagen microspheres, in two subjects, comparing mono, first, second and third platings.

10 Fig. 8A and 8B are graphs showing the extent of fibroblast-induced contraction of collagen gel (mm) in the presence of glycosaminoglycans at different cell densities (G:C, 3:1, 1:1, 1:3, no GAG) over time (days).

Fig. 9 is a graph showing the temporal change in diameter (mm) of the cell-matrix microspheres encapsulating cells at different densities: 50,
15 500 and 5000 cells/microsphere over time (days).

Fig. 10A and 10B are graphs of the cell viability (10A) and number (10B) of HEK293 cells in 3D microspheres and monolayer cultures with different initial cell numbers: 2500, 25,000, 250,000 cells.

Fig. 11A and 11B are graphs showing the temporal change in cell
20 viability, percent (3A) and cell number (3B) of HEK293 cells in 3D microsphere and monolayer cultures over time in days.

Fig. 12A-F are graphs showing GDNF productivity in HEK293 cells. Accumulative secretion (ng GDNF) (Fig. 12A) and rate of secretion (ng GDNF/million cells/day) (Fig. 12B) of GDNF from HEK293 cells in 3D
25 microspheres and monolayer cultures over time in days. Total GDNF (ng)

secreted from (Fig. 12C) and secretion rate (ng GDNF/million cells/day) of HEK293 cells in 3D microspheres and monolayer cultures with different initial cell numbers (Fig. 12F). Total GDNF (ng) secreted from (Fig. 12E) and secretion rate (ng GDNF/million cells/day) of HEK293 cells in 3D microspheres and monolayer cultures (ng GDNF/million cells/day) with different serum concentrations: 2, 5, and 10%.

Fig. 13A and 13B are graphs of the cell viability, percent (13A) and number (13B) of HEK293 cells in 3D microspheres and monolayer cultures with different serum concentrations: 2, 5, and 10%.

Fig. 14A and 14B are graphs of the amount (micrograms) GAG (Fig. 14A) and GA/DNA (Fig. 14B) in samples with different cell seeding densities, 0, 0.5, 1, and 5×10^6 /ml, for different collagen concentrations: 0.5, 1.0, 2.0 and 3.0 mg/ml.

DETAILED DESCRIPTION OF THE INVENTION

I. Definitions

As used herein, encapsulated in microspheres refers to formation of a nanofibrous microsphere having embedded therein cells as a result of a phase change of the material forming the microsphere.

As used herein, "ECM" refers to an extracellular matrix material, in pure, isolated, partially isolated, recombinant or synthetic form, or a synthetic material having comparable physical and biological properties to ECM

As used herein a mechanically stable microsphere, is one that, after reaching equilibrium, can be mechanically manipulated by forceps and are resistant to the shear stress and turbulence generated during pipetting up and

down at rapid rate such as 20ml/min or even vortexed with maximal speed.

II. Materials for Manufacturing Cell-Matrix Microspheres

A method has been developed to produce stable cell-matrix microspheres with up to 100% encapsulation efficiency and high cell viability, using matrix or biomaterial systems with poor shape and mechanical stability for applications including cell therapeutics via microinjection or surgical implantation, 3D culture for *in vitro* expansion without repeated cell splitting using enzymatic digestion or mechanical dissociation and for enhanced production of therapeutic biomolecules, and *in vitro* modeling for morphogenesis studies. The modified droplet generation method is simple and scalable and enables the production of cell-matrix microspheres when the matrix or biomaterial system used has low concentration, with slow phase transition, with poor shape and mechanical stability. The method uses a formulation including cells, a first extracellular matrix (ECM), optionally a second ECM, and other biomolecules.

A. ECM Materials

The composition includes at least one ECM. The ECM must be capable of providing support to the cells, interacting with the cells to allow cell growth without introducing toxicity, and permitting cell migration and penetration, can be collagen of different types, such as type I, II, and III, or any materials that are good in supporting cell growth and migration and have phase transition properties at conditions mild enough to support cell survival, such as fibrin and hyaluronic acid. The collagen used can be of bovine origin such as those used in FDA-approved skin equivalents Integra® and Apligraf® and the soft tissue fillers or products that have been used

clinically for wrinkle reduction such as DermaLive and DermaDeep
(Bergeret-Galley, et al., *Aesthetic Plast. Surg.*, 25(4):249-55 (2001), or for
urinary incontinence treatment (Corcos, et al., *Urology*, 65(5):898-904
(2005)). The ECM can be derived from either natural or synthetic sources,
5 and it can be induced to reconstitute into solid form under specific conditions
that are mild enough to support cellular survival and growth. The ECM can
be produced from isolation or extraction from various animal sources, such
as rat tail, porcine skin, bovine Achilles tendon, or human placenta.
Preferably, the first ECM is isolated from different fractions during the
10 extraction process, such as acid-soluble, pepsin-soluble, or insoluble
fractions.

The composition can further comprise a second ECM, which can be a
proteoglycan or glycosaminoglycan ("GAG") produced from shark cartilage,
fibrin, elastin or hyaluronic acid. The first ECM can interact with living cells
15 or with the second ECM in such a way that the interaction leads to a change
in cellular responses in growth and differentiation and physical properties of
microspheres such as the volume of the structures, ECM density, cell density,
mechanical property and stability, etc.

The matrix components also include other hydrogels whose
20 fabrication conditions are mild enough to maintain high cell viability after
encapsulation without the use of organic solvents or other substances toxic to
cells, and without harsh conditions, such as alginate gel which is gelled by
addition of calcium.

B. Cells

25 The cells may be mature cells or stem cells from human or clinically

feasible sources, such as autologous, allogeneic, fetal, embryonic and xenogenic sources. The cells can be of diverse origin. In preferred embodiments, cells are human bone marrow derived mesenchymal stem cells (hMSCs), human embryonic and fetal stem cells capable of therapeutic use, 5 adult stem cells isolated from sources including but are not limited to human skin, GI tract, adipose tissue, placenta, and adult cells capable of therapeutic use such as those from healthy biopsies of the intervertebral discs, cartilage, muscles, skin, tendon and ligament, etc. The cells can be genetically manipulated to over-express one or more specific biomolecules such as 10 proteins or physiologically active in secreting one or more specific biomolecules such as proteins, examples are HEK293 cells, 3T3 fibroblasts, osteosarcoma cells, C2C12 cell line, human bone marrow derived mesenchymal stem cells (hMSCs), etc. The cells can also be obtained from 15 allogenic sources capable for therapeutic use, such as rabbit MSCs, mouse MSCs and other animal cells for therapeutic use in animal disease models. Preferably, the cells are bone marrow-derived mesenchymal stem cells (MSCs), either autologous or allogeneic from HLA-matched donors. Preferably, the mature cells are keratinocytes isolated from biopsies of healthy skin from burn patients; chondrocytes isolated from biopsies of 20 healthy articular cartilage from osteoarthritis patients; intervertebral disc cells isolated from biopsies of healthy discs from patients with severely degenerated discs; or Schwann cells isolated from autologous peripheral nerve grafts in patients with spinal cord or other CNS injuries.

The examples utilized HEK293 secreting GDNF as an example of 25 production of biomolecules. Other cells such as 3T3 fibroblasts and CHO

cells can be used while other useful biomolecules such as glycoproteins and proteoglycans can also be used.

C. Optional Growth Factors

The composition can also include a growth-stimulating signal such as human serum, platelet rich plasma or other blood products. Preferably, an additional factor affecting the differentiation of MSCs is included in the composition. Exemplary factors include TGF-beta for chondrogenic lineage.

D. Cell Culture Media

The aqueous media can be culture medium, with or without serum, buffered saline, or other liquid phase compatible with cell viability and with suitable ionic strength. Typical mediums include DMEM, DMEM-LG, MEM, and RPMI.

E. Optional Therapeutic, Prophylactic or Bioactive Agents

The formulation can also include therapeutic, prophylactic or diagnostic agents. For example, therapeutic components such as anti-inflammatory drugs and antibiotics can also be incorporated into the composition. Diagnostic agents such as dyes or radio-opaque agents can be incorporated. Preservatives can be included for storage.

20 III. Method of Making Cell-Matrix Microspheres

The system for producing microspheres includes the composition described above, a unit for dispensing the composition as liquid droplets; and a collection platform for collecting the dispensed liquid droplets, comprising a surface with a surface property such that the spherical shape of the microspheres can be maintained; and for gelation of the matrix to form

cell-matrix microspheres. The substratum onto which the droplets are dispensed can be a parafilm wrapped or a gelatin coated, or other material having similar surface properties, plastic or metal or glass platform having a high surface tension to maintain the spherical shape of the droplets as much
5 as possible. The system can further comprise a control unit for controlling the dispensing speed and volume, as well as a temperature control unit for maintaining the temperature of the composition during dispensing and during phase transition of the matrix.

The method of forming microspheres includes the steps of mixing
10 and dispensing the composition into liquid droplets in the right order and the right time with a dispensing unit. The pH of the ECM matrix is adjusted to be suitable for cell survival. The first and the second matrix are mixed well if specific interaction between these components is needed. The cell suspension and other biomolecules are mixed thoroughly with the matrix components as
15 soon as possible to evenly distribute cells throughout the solution forming the matrix before accelerating phase transition. The dispensing unit can be manual or automatic. The liquid droplets are collected with a dry collection platform without mechanical disturbance.

The platform has a surface property for maintaining the spherical
20 shape of the liquid droplets, such as high surface tension. The dispensing environment is maintained at a temperature between -5 to 20 °C, 0 to 15°C, or more preferably between 0°C to 10°C. By maintaining the temperature low, the rate of matrix phase transition can be controlled as low as possible, for example, within a range between 2 minutes to 10 hours depending on the
25 matrix concentration, preferably 30 minutes. The volume of the microspheres

dispensed is controlled at between about 0.01 to 100 μ l, 0.05 to 50 μ l, 0.1 to 20 μ l, 0.1 to 10 μ l, 0.5 \pm 1 μ l, or preferably about 2.5 μ l. The diameter of the dispensed liquid droplets ranges from 0.5mm to 3mm, preferably 2mm.

Sol-gel transition process of the liquid matrix is initiated by
5 controlling the temperature, the pH and the ionic strength of the liquid environment at appropriate time. The temperature is raised from 4°C to 10°C, 16°C, 25°C, 37°C and preferably 37°C. The pH is raised from 2 to 5, 6, 7, 8, great than 8 and preferably 7. The speed of gelation of the gelling matrix can be slowed immediately after initiating the gelation by maintaining
10 the temperature of the mixtures as low as 4°C. The speed of gelation of the gelling matrix can be increased immediately after dispensing the gelling matrix into droplets at the collecting unit by raising the temperature of the mixture to 37°C or by increasing the ionic strength of the solution.

The matrix components of the liquid droplets undergo phase
15 transition to form cell-matrix microspheres for a period of time sufficient for phase transition to reach equilibrium, typically for about 10 to 30 minutes, 15 to 60 minutes, 0.5 to 5 hours, preferably 45 minutes.

The gelled droplets are detached or released from the collecting platform by gentle flushing with liquid such as culture medium and
20 phosphate buffered saline, or immersing the platform in a liquid bath with gentle agitation, or other appropriate methods mild enough to retain the integrity of the soft microspheres. The microspheres are stabilized by collecting the cell-matrix microspheres from the collection platform with minimal mechanical disturbance; maintaining the microspheres free-floating
25 in a first medium for an extended period of time until the size of the

microspheres becomes substantially constant; and releasing the microspheres from the first medium. The microspheres can be maintained free-floating either by keeping in suspension in non-adhesive culture dish such as a Petri dish, or by culturing the microspheres in spinner flask or rotating vessel bioreactors. The microspheres can be maintained free-floating from 2 hours to 10 days, 12 hours to 8 days, or about 2 to 7 days, most preferably 3 days. The temperature can be maintained at about 25 to 45 °C, 30 to 40°C, or about 37 °C.

The size and mechanical strength of the microspheres can be controlled by at least one of the following parameters: cell density, collagen concentration, serum concentration, composition of the ECM, ratio of the first and optional second ECM, volume of the liquid droplets, and duration of the free-floating status of microspheres. The mechanical strength and size of the microspheres can be controlled by at least one of the parameters mentioned above. For example, the initial cell density or the cell number per microsphere can be controlled at a range between 1 to 2500, 1 to 1000, 1 to 500, or about 250 cells/microsphere; concentration of the first ECM can be controlled at a range between about 0.01 to 10.0 mg/ml, 0.1 to 5.0 mg/ml, 0.1 to 3.0 mg/ml, or about 0.5mg/ml; the ratio of the first ECM to the second ECM can ranged from 1:10 to 10:1, 1:5 to 5:1, 1:2 to 2:1, or about 1:1; the serum concentration can range from 0.1% to 50%, 0.5 to 30%, 1 to 25%, 5% to 15%, or about 10%. Increasing cell density, decreasing matrix concentration or decreasing volume of liquid droplets decreases size and increases stability of cell-matrix microspheres.

The size of the microspheres can be precisely controlled by multiple

parameters including, but are not limited to, the initial cell density or the cell number per microsphere, ranging from 1 to 2500 preferably 250 cells per microsphere; the concentration of the collagen ranging from 0.1 to 8.0 preferably 0.5 mg/ml; the serum concentration ranging from 2 to 20 preferably 10%; and the ratio between different matrix components such as collagen to GAGs ranging from 10:1 to 1:10 preferably 1:1.

Formulation parameters of cell-matrix microspheres can be optimized for better differentiation of encapsulated stem cells. For example, collagen-mesenchymal stem cells (MSC) microspheres can be prepared with different parameters such as cell density and collagen concentration. Parameters can be varied to give optimized differentiation outcomes such as GAGs production. Cell density between 1×10^4 to 1×10^7 cells per ml, preferably 5×10^5 cells per ml, can be used. Increasing cell density favors differentiation of human MSCs inside the microspheres into chondrocyte-like cells. Collagen concentration between 0.1 to 10mg/ml, preferably 2mg/ml, can be used. Increasing collagen concentration favors differentiation of human MSCs inside the microspheres into chondrocyte-like cells. Therefore these parameters can be optimized to give the best differentiation outcome during tissue regeneration.

In a preferred embodiment, the mechanical strength of the microspheres is controlled by controlling initial cell density or the cell number per microsphere, ranging from 1 to 2500 preferably 250 cells per microsphere; the initial concentration of the collagen matrix ranging from 0.1 to 8.0 preferably 0.5mg/ml; the serum concentration ranging from 2 to 20 preferably 10%; the ratio between different matrix components such as

collagen to GAGs ranging from 10:1 to 1:10, preferably 1:1.; and the duration of the free-floating incubation ranging from 2 hours to 14 days, preferably 48 hours. Increasing cell density, decreasing matrix concentration and decreasing volume of liquid droplets dispensed, decreasing

5 GAGs composition, increasing serum concentration and an increasing free-floating incubation time result in an increasing mechanical strength of microspheres obtained.

Fig. 1 shows a schematic drawing of a system **101** for producing the cell-matrix microspheres. The system **101** comprises a dispensing unit **100**,

10 which consists of a manual or automatic dispenser **102**, a control unit **104** controlling the volume of the dispensing liquid, the speed of dispensing and X-Y position of the dispenser, and a cooling unit **106** (or ice chamber) accommodating the dispensing unit **100** at around 4°C. The system also includes a collecting unit **108**, which consists of a scalable collecting

15 platform **110** with non-adhering surface, a moving X-Y-Z stage **112** to which the collecting platform is mounted, a plate control unit **114** controlling the speed, frequency and direction of movement of the moving stage. The system may be manual or automatic, custom-made, or modified from commercially available instruments such as liquid handlers.

20 The method of forming microspheres via the system **101** comprises dispensing small liquid droplets such as 0.5µl of mixtures containing the cells, the aqueous media and the liquid matrix, mixed in the right order of sequence and timing. The rate of matrix phase transition can be controlled by adjusting the temperature of the dispensing chamber side and is maintained

25 slow by keeping the temperature low at the dispensing side. The diameter of

the droplets range from 0.5mm to 3mm, preferably 2mm. The liquid droplets collected at the collection platform are allowed to gel at 37°C for sufficiently long to form the solid cell-matrix microspheres. The microspheres are released from the collection platform and maintained free-floating in culture conditions until stable microspheres are formed.

Figure 2 shows a method of producing cell-matrix microspheres with controllable size and mechanical strength. The size and mechanical strength of the microspheres are controlled by multiple parameters including, but not limited to, the volume of cell-matrix mixture, the cell density or cell number per microsphere, the matrix density, the ratio of different matrix composition, the serum concentration, the volume of the liquid droplets dispensed and the duration of free floating incubation of the cell-matrix microspheres.

The method comprises Step **200**: maintaining the gelled cell-matrix microspheres free floating or in suspension in static non-adhesive culture vessels, such as those for bacterial culture, or in spinning or rotating culture vessels, after releasing or detaching them from the non-adhesive collection platform **110**, for sufficiently long period of time, ranging from 2 hours to 14 days, preferably 72 hours. Step **202**: collecting the microspheres by flushing the microspheres with a medium on the collection platform **110**. Step **203** involves allowing the microspheres to maintain for a period of time. Step **204**: Examine the size of the microspheres until equilibrium is reached, i.e., the size of microspheres become constant. Step **206**: collect the mechanically stable microspheres for injection or implantation or 3D cultures.

The duration of free floating depends on the rate of the cell-matrix interaction before reaching equilibrium where the size of the microspheres

becomes constant. The rate of interaction is thus cell type and matrix type dependent. The diameter of the cell-matrix microspheres at equilibrium should be appropriate for in vivo therapeutic injection, ranging from 50 to 800 microns, preferably 300 microns.

5 IV. **Method for Modifying Cell Behavior after Formation of Cell-Matrix Microspheres**

Cell migration from microspheres can be manipulated by providing a mechanical support to the microspheres by plating them onto a solid substratum of culture dishes or placing them into a gelling matrix or onto a gelled matrix; plating the microspheres into a culture dish or gelling matrix or onto gelled matrix wherein each microsphere is kept at a distance from each other; adding a second medium into the culture system for holding the microspheres; allowing cells to migrate out from the microspheres for a period of time; and releasing the microspheres from the attached substratum and the second medium. The microspheres are typically held in the culture system for a period of time before the second medium is added, for example, 30, 60, 90, or 120 minutes, preferably 60 minutes. The steps can be repeated several times to allow full migration of the cells. For example, the steps can be repeated 3, 5, 7, and preferably 10 times. The period of time for cell migration can range from 2, 4, 12, 48 hours to 12 days, preferably about 3 days. The cells that migrate out from the microspheres are allowed to grow for a period of time and can be harvested for future use or re-encapsulated. The culture system can be a 2D or 3D environment. The medium is preferably DMEM, DMEM-LG, MEM, or RPMI.

V. The Cell-Matrix Microspheres

The cell-matrix microspheres produced are mechanically stable and able to resist shear stress produced during rapid injection at a flow rate of as high as 20ml/min, are able to survive mechanical manipulation such as
5 picking up and down by forceps, and are able to survive turbulence produced during vortexing at maximal speed.

The collagen and other matrix provide the natural microenvironment stimulating growth of the cells, protect the cells from enzymatic digestion at the local hostile environment upon injection or implantation, immobilize
10 soluble reagents, stimulating growth and differentiation if necessary, and the adhesive cell-matrix microspheres easily fuse together with the host tissue and fill any irregular gaps with the host tissue, therefore filling the tissue defects. The cell-matrix microspheres are permeable to free exchange of nutrients and metabolites. According to the rules of mass transfer in 3D
15 tissue-like structures, the dimension of tissue-like structure is limited (Muschler, et al., *J. Bone Joint Surg. Am.*, 86-A(7):1541-58 (2004)). While in the 3D cell-microsphere system, the size of the microspheres can be always controlled to as small as 100-300 microns, which is the suitable dimension of 3D structures with sufficient nutrient exchange. Another factor affecting the
20 size of the microsphere is the matrix concentration. A higher concentration results in a stiffer matrix and therefore the traction force generated as the cells interact with the low concentration gelling matrix is not sufficient to produce a large extent of volume reduction. In addition, the encapsulated cells are able to migrate out the microspheres to integrate with the host tissue
25 or grow rapidly when there is a close contact between the microspheres and

the attached environment such as the host tissue thus may promote implants-host integration and engraftment rate.

The cell-matrix microspheres can also be used to immobilize other therapeutic molecules, for example, factors inducing specific differentiation lineage such as Transforming Growth Factor (TGF) beta for chondrogenic differentiation, and anti-inflammatory drugs.

The method includes steps of controlling the amount of cells obtained and the speed of obtaining such number of cells in a predictable manner by factors including but are not limited to the plating density of the microspheres ranged from 0.5 to 500 preferably 5 microspheres per cm^2 ; cell density ranged from 1 to 2500 preferably 250 cells / microsphere; concentration of matrix such as collagen ranged from 0.1 to 5.0 preferably 0.5mg/ml; collagen to GAGs ratio ranged from 1:10 to 10:1 preferably 1:1; serum concentration ranged from 2 to 20 preferably 10%. An increasing plating density, an increasing cell density with a decreasing matrix concentration, a decreasing collagen to GAGs ratio and an increasing serum concentration result in an increasing number of cells obtained and an increasing speed of obtaining such number of cells.

Figure 3 shows a method of controlling the migration and growth of encapsulated cells. Step 300 involves production of mechanically stable microspheres according to the steps described in **Fig. 1** and **Fig. 2**. Step 301 involves providing a mechanical support for the microspheres to attach, in the absence of medium supplementation, for a period of time sufficient for attachment, 5 minutes to 60 minutes, half an hour to 6 hours, preferably 45 minutes, via Steps 302-304. Step 302 and 303 involves plating microspheres

(302a) onto the solid substratum of a culture dish and a layer of collagen gel (303a), respectively. Step 304 involves suspending microspheres in a volume of gelling collagen matrix (304a) and cast the mixture into a culture dish for gelation by raising the temperature to 37°C. Step 305 involves adding full
5 medium (305a) into the culture dishes without disturbing the attached microspheres. Step 306 involves allowing cell migration (306b) from the circumference of the microspheres for a period of time, from 12 hours to 3 days, from 2 days to 8 days, from 4 days to 14 days, preferably 3 days. Step 307 involves retrieval or releasing of the cell-matrix microspheres from the
10 attached substratum by methods such as gentle flushing the substratum with full medium. Step 308 involved immediate supplementation of full medium to the culture dish where the migrated cells (308a) are allowed to continue to grow with regular medium change. Step 309 involves recycle of the detached microspheres for plating and cell outgrowths in steps 301-307 (not shown).
15 The cells migrated can be harvested in Step 310 for future use.

The method includes providing attachment to the floating microspheres by plating the contracted cell-matrix microspheres onto an adhesive substratum such as culture dishes in the absence of medium for certain period of time ranging from 30 minutes to 12 hours, preferably 45
20 minutes, until attachment is achieved. The method also includes steps of replenishing the microspheres with sufficient medium without disturbing the attached microspheres.

The method includes steps of allowing cell outgrowth from the attached cell-matrix microspheres. The collagen matrix is permissive to
25 cell migration. Together with the population pressure built up in the fully

contracted cell-matrix microspheres, it results in cell outgrowth from the periphery of the attached microspheres onto the substratum or surrounding environment and the migrated cells proliferate. Cell outgrowth is induced for a certain period of time ranged from 12 hours to 14 days preferably 3 days.

5 The method includes removing the attachment of the cell-matrix microspheres when sufficient number of cells migrate out from the microspheres that the microspheres are surrounded with cell outgrowths. This occurs at 12 hours to 14 days, preferably 3 days. The step does not need enzymatic digestion such as trypsinization, which may change the surface
10 marker and cellular activities, and without mechanical disruption of the microspheres; but simply by flushing the microspheres gently with medium or PBS or by picking up with forceps.

 The cell-matrix microspheres are intact and are collected by sedimentation or mild centrifugation ranged from 800 to 2000rpm
15 preferably 1000rpm.

 The cell-matrix microspheres can be replated in new empty culture vessels multiple times, up to 10 platings depending on the microsphere size, cell density per microsphere, so as to provide large number of cells in the same passage without changing the cell growth and differentiation potential
20 as well as surface markers.

 The method can be used to provide cells on demand by maintaining the cell-matrix microspheres in suspension for at least one week if no cells are needed. The free-floating microspheres are provided with attachment in order to allow cell migration and outgrowth until confluence for future use
25 when cells are needed. The method enables the constant supply of cells

from the same passage in the cell-matrix microspheres by plating the microspheres for multiple times until the cell migration ceases. The migrated cells can be obtained at regular intervals, preferably daily, for a period of time ranging from 2 to 30 days, preferably 10 days, that is the period of time necessary for building multi-layered heterogenous tissue-like structure including, but are not limited to, the IVD, GI tract and blood vessels.

The cell-matrix microspheres can be dissembled simply by enzymatic digestion specific to the matrix components of the microspheres, such as collagenase for collagen, chondroitinase for chondroitin sulfate GAGs. The single cell suspension can be used further.

The natural extracellular matrix materials such as collagen used to encapsulate cells provide a physiologically relevant microenvironment in 3D to the encapsulated cell by forming cell-matrix microspheres. The tissue-like matrix microenvironment imposed on the encapsulated cells constrains cell proliferation. As a result, the cells are temporarily controlled for proliferation and the cell number in 3D microspheres increases only slightly higher than 2 fold on day 4 while cells in traditional monolayer cultures increase over 20 fold for the same period of time. The proliferation index for cells in 3D microspheres is consistently lower than that in traditional monolayer culture at different time points and for different cell densities. This method presents a naturally occurring and externally applied control for proliferation that no genetic manipulation on cell metabolism is needed.

IV. Applications

A. Tissue Repair or Regeneration

The methods and cell matrix microspheres are useful for treatment of cardiovascular diseases such as repair of myocardial infarction, for
5 neurological diseases such as spinal cord injury and for musculoskeletal diseases such as cartilage injury, disc degeneration and muscular dystrophy. Services or products associated with stem cell therapies can also use the method and cell matrix microspheres to culture stem cells in 3D or in combination with monolayer cultures, to produce stem cells in large quantity
10 and with a request-by-demand approach without changing their identity, self-renewal and differentiation capacity.

The cell-matrix microspheres consisting of undifferentiated and viable cells can be injected or implanted, for example, for tissue repair or regeneration. The method includes the steps of sedimenting the
15 microspheres for a period of time, preferably 10 minutes or centrifuging the microsphere suspensions mildly at a speed of 800-2000rpm, preferably 800rpm, for a period of time, preferably 5 minutes; removing the excess supernatant; re-suspending the microspheres in a liquid for injection or implantation such as saline or medium or phosphate buffered saline or a low
20 concentration hydrogel such as collagen gel with a known volume; adding the microsphere suspension to a container for injection or implantation such as a syringe with G18-G30 needles, preferably G27; and injecting or implanting the microspheres into defective tissues in animals or humans such as a skin wound or an injured cartilage.

25 In one embodiment, the method includes injecting or implanting the

cell-matrix microspheres consisting of specifically differentiated and viable cells, wherein the matrix embeds these cells into defective tissues of animals or humans. The method comprises adding differentiation medium where chemical signals such as TGF- β is included in the microsphere suspensions
5 for a period of time sufficient to induce chondrogenic differentiation of stem cells present in the microspheres into chondrogenic cells; allowing the microspheres with differentiated cells to sediment for a certain period of time, preferably 10 minutes, or centrifuging the microsphere suspensions mildly at a speed of 800-2000rpm, preferably 800rpm, for a period of time, preferably
10 5 minutes; removing the excess supernatant; re-suspending the microspheres in a liquid for injection or implantation such as saline or medium or phosphate buffered saline or a low concentration hydrogel such as collagen gel with a known volume; adding the microsphere suspension in the container for injection or implantation such as a syringe with G18-G30
15 needle, preferably G27; and injecting or implanting the microspheres into defective tissues in animals or humans such as a skin wound or an injured cartilage. The microspheres can be used for cell therapy via injection or implantation for disorders including, but are not limited to, those of the musculoskeletal, cardiovascular and neurological systems.

20 The cell-matrix microspheres can be used as long term sources for cells from the same passage without the need for cell splitting as conventionally used in both monolayer culture and seeding cells on 3D scaffolds such as using repeated enzymatic digestion and mechanical disruption.

B. Cell-Matrix Microspheres as BioReactors

Companies that provide services or products associated with 3D microcarriers in culture of cells, genetically modified or not, for production of therapeutic biomolecules such as but not limited to growth factors, can use the methods and compositions to produce self-assembled microcarriers that further enhance the yield of therapeutic molecules produced. Cell-matrix microspheres can be used for 3D cultures as traditional microcarrier cultures used in biotechnology and pharmaceutical industries. They can be cultured as suspensions so as to easily increase the bed volume and scale up the culture system. Comparing with traditional microcarrier cultures, the method provides several important advantages in enhancing efficiency and reducing costs. Cells are immobilized within the gelling matrix at almost 100% encapsulation efficiency that almost all cells can be encapsulated. This encapsulation procedure takes only 30-60 minutes in static culture conditions. On the other hand, traditional microcarrier culture system needs a time-consuming and inefficient cell binding procedure to allow cells to bind to the surface of the pre-fabricated microcarriers in suspension. In order to increase the efficiency of cell binding to the pre-made microcarriers, complicated culture vessel design such as rotating vessel bioreactors, perfused bioreactors, spinning flasks and other methods such as constant agitation are needed. This cell binding step sometime may take more than 1 week. Since the method eliminates the necessity of these complicated and time-consuming steps, it presents a more efficient and less costly 3D culture method. Second, the microencapsulation system combines the formation of the microspheres and the immobilization of cells in a matrix system into one

step. This significantly reduces the cost and saves time. Moreover, it eliminates the necessity of fabricating microcarriers separately that dramatically reduces the cost of the system because technologically demanding steps for fabrication of microcarriers such as phase separation, solvent evaporation, chemical crosslinking can be avoided. Third, the microencapsulation system is conducted in physiologically relevant temperature and conditions that assures high cell viability. On the other hand, residues of organic solvents and toxic chemical crosslinking reagent such as glutaraldehyde used during fabrication process of microcarriers may compromise cell viability.

The cell matrix microspheres are also useful for 3D cultures. These have numerous advantages over the existing microcarrier systems. The system can be used to culture protein-secreting cells in physiologically relevant microenvironment with significantly increased protein productivity via matrix-induced proliferation control as compared to monolayer cultures with unrestricted proliferation.

The productivity in 3D microspheres increases when the microspheres are cultured in low serum concentrations such as 2%. This indicates that the culture system can be maintained at low serum concentrations and the downstream purification of proteins can be simplified. The cells are cultured in culture vessels or bioreactors with or without constant agitation or spinning or rotation or perfusion.

The secreted proteins in the culture medium are harvested with replacement at regular periods ranging from 1 day to 10 days, preferably 2 days, before reaching the maximal cell density inside the microspheres, for a

period of time after microsphere suspension culture, ranging from 7 day to 3 months preferably 14 days. Wider windows for protein production can be achieved by encapsulating the cells in sub-optimal concentrations in the liquid matrix, ranging from 1×10^4 to 1×10^7 cells/ml, preferably at 1×10^5 cells/ml. The productivity of cells is significantly increased when cells proliferation inside the matrix microspheres is controlled. This window can be maintained for at least 2 weeks, much longer than the window with enhanced productivity in other controlled proliferation strategies. Unlike other proliferation control technologies, this method provides a temporary and reversible control for proliferation by encapsulating the cells in natural extracellular matrix materials at appropriate concentrations and time.

Similar to 2D culture without the matrix microspheres, the cell number increases linearly during the log phase. During this phase, total protein production increased linearly with cell number and the productivity of specific proteins is reduced. This may be due to the fact that more energy is channeled to reproduction rather than protein production. Specific proteins produced during this phase can also be harvested. Cells will reach a maximal or optimal density due to the space limitation and nutrients competition, and the proliferation rate of the cells will be reduced. This is usually accompanied by an increase in protein production. However, during this phase, cell apoptosis and death may be induced and the release of intracellular contents may degrade the secreted products. It is therefore advantageous to harvest the secreted proteins at appropriate time points during the optimization. Unlike other systems, this method allows separation of high protein productivity and rapid proliferation. This protein

production phase is prior to and accompanied by a log proliferation phase. This system is therefore sustainable and typically ends with dramatically increased cell numbers.

Efficiency and cost reduction of the culture system can be achieved
5 by recycling the encapsulated cells after reaching the optimal cell density after a period of time ranging from 2 weeks to 3 months, preferably one month, via re-encapsulation. It is economically efficient because the protein harvest can start well before active proliferation phase while the output of the system includes not only the specific proteins produced but also increased
10 cell numbers with high viability. Moreover, the cycle can be restarted by enzymatically releasing the cells and re-encapsulating into new matrix microspheres so that the cycle of matrix-induced proliferation control with high protein productivity and the subsequent active cell proliferation in 3D microspheres can be initiated again.

15 Another advantage of this system is that, unlike traditional proliferation controlling technologies such as nutrients deprivation and over-expression of tumor suppressor genes, to control cell metabolism and to induce cell apoptosis or death, where high cell viability (almost 100%) is always maintained at different time points, with different cell densities and
20 serum concentrations, proliferation of cells can be controlled directly, increasing protein productivity. In the example using GDNF-secreting HEK293 cells, the productivity of cells in 3D microspheres is always higher (ranging from 3 to 67 fold) than that from the monolayer cultures at different time points, with different cell densities and at different serum
25 concentrations.

EXAMPLES

The present invention will be further understood by reference to the following non-limiting examples.

Example 1: Production of hMSC-collagen microspheres

5 Rat-tail collagen solution type I in acetic acid, which mainly consists of triple helical monomers, was neutralized by NaOH and diluted into a final concentration of 0.5mg/ml. All procedures were done in an ice-bath to prevent collagen gel formation. Human bone marrow derived mesenchymal stem cells (MSCs) in full medium, DMEM-LG with 10% FBS and 1% P/S,
10 were suspended thoroughly in the neutralized collagen solution as soon as possible. A dispenser was then loaded with the ice-cold cell mixture and a small volume of 2.5µl was dispensed at a time onto a bacterial culture dish covered with UV-irradiated parafilm. To prevent air-bubble formation in the liquid droplets, the dispenser was moved upwards or the collection platform
15 downwards after dispensing the liquid droplets. The liquid droplets were thermally induced to reconstitute into a gel meshwork of organized collagen fibrils, interacting with the encapsulated cells, to form solid microspheres by incubating in a 37°C incubator for 1 hr. The cell-matrix microspheres formed
20 were collected into a full medium containing bath with non-adherent substratum by gently flushing the parafilm with medium.

Example 2: Production of mechanically stable cell-matrix microspheres and controlling parameters of the microsphere size.

Materials and Methods

Following the steps shown in Fig. 2, rat-tail collagen solution type I
25 was neutralized and diluted into different concentrations (0.5, 1.0, 2.0 and

3.0mg/ml) in the presence of different concentrations (2×10^4 , 1×10^5 and 5×10^5 cells/ml) of human bone marrow derived MSCs in DMEM medium with 10%FBS as described in Example 1. The cell-matrix microspheres were collected into a DMEM medium containing bacterial culture dish. The collected microspheres were maintained at their free-floating state in the culture vessel at 37°C for 2 to 7 days until the equilibrium is reached as characterized by a constant microsphere size.

Results

The temporal morphological change of the cell-matrix microspheres with different cell densities and collagen matrix densities were recorded. Microspheres at day 0 showed individual cells embedding in the collagen matrices and the microspheres were still transparent. Microspheres at higher cell densities such as 1×10^5 and 5×10^5 cells/ml and lower collagen matrix densities of 0.5, 1.0 and 2.0mg/ml contract as time goes by and become more opaque and dense. This indicates that hMSCs are reorganizing the matrix to form a tighter matrix in the microspheres. Microspheres at lower cell density (2×10^4 cells/ml) took much longer time to contract to a constant size while microspheres with higher collagen matrix density, 3.0mg/ml, showed so little contraction that the matrix appears transparent. The extent of hMSC-induced collagen microspheres contraction was directly proportional to the cell density, collagen concentration and droplet volume (Figures 4A, 4B and 4C, respectively), establishing that that these parameters can be used to control the final size of the microspheres. The hMSC-collagen microspheres, after reaching the equilibrium, can be mechanically manipulated by forceps and are resistant to the shear stress and

turbulence generated during pipetting up and down at rapid rate such as 20ml/min or even vortexed with maximal speed. As a result, these microspheres are mechanically stable enough to resist shear stress generated during microsyringe injection and are ready for injection and implantation for cell therapy and tissue engineering purposes.

Example 3: Controlling the growth rate of encapsulated hMSCs inside the collagen microspheres.

Materials and Methods

hMSCs were isolated from bone marrow aspirates from donors with informed consent in compliance with the Institute human ethics regulations. hMSCs were cultured as described by Li et al. 2004. Cells harvested from passage 2 and 3 by traditional monolayer culture were cryopreserved and used for production of cell-matrix microspheres with different collagen density: 0.5 and 2mg/ml. Fully contracted mechanically stable hMSCs-collagen microspheres were obtained as described in Examples 1 and 2. These microspheres were incubated with 2 μ M Calcein AM and 4 μ M Ethidium homodimer-1 for 45 minutes for simultaneous staining of live and dead cells. Stained microspheres were fixed in 4% paraformaldehyde for 1 hour and examined using a laser confocal scanning microscope for stacked images. In a separate experiment, microspheres, with 100 microspheres per plate in triplicates, were cultured in full medium for 10hours, 3, 6 and 9 days. At the end of incubation, the microspheres were digested with bacterial collagenase at 100U/ml for 45-80minutes at 37oC followed by digestion with 0.05% Trypsin/EDTA for 5 minutes. The single cell suspension obtained was counted for cell number and viability.

Results

Both live and dead cells were found initially after microencapsulation. After 3 days, most cells in microspheres with lower collagen concentrations were alive while dead cells could be found in microspheres with higher collagen concentrations. All live cells exhibited elongated morphology. At day 6, cells were more elongated and achieved cell-to-cell contact. In microspheres with lower collagen concentrations, cells were distributed throughout the matrix while those with 3mg collagen/ml, had more cells aligned at the circumference. Growth of the microencapsulated cells was collagen concentration dependent, as shown by Fig. 5A. At 8 hours post-encapsulation, the cell number fell to approximately 40% of those initially microencapsulated in both concentrations. There was only slight increase in cell number after day 6 for the 0.5mg/ml group but a rapid increase in cell number was observed in the 2mg/ml group. Two-way ANOVA showed that both time and collagen concentration significantly affected the cell number ($p < 0.001$). Bonferroni's post-hoc tests showed significant difference between day 6 or 9 and earlier time points ($p < 0.001$). A significant reduction in cell viability ($p \leq 0.033$) was found at 8 hours but not thereafter ($p = 0.959$), as shown by Fig. 5B.

Example 4: Controlling the migration and growth of encapsulated hMSCs from collagen microcapsules

Materials and Methods

Free-floating hMSC-collagen microspheres with cell densities of 2×10^4 , 1×10^5 or 5×10^5 cells/ml were transferred into 100mm diameter tissue culture plates at 3 days post-encapsulation, at plating densities of 63, 125 or

250 microspheres per plate corresponding to 0.64, 1.59 and 3.18
microspheres / cm². The microspheres were allowed to attach to the culture
plate for 1 hour after aspiration of excess medium and supplemented with
full medium. At 72 hours, the microspheres were detached from the culture
5 plates by gently flushing with full medium, allowed to sediment and replated
in new culture plates several times until cell out-growing ceased. In separate
experiment, microspheres were seeded on collagen gel at 0.5mg/ml to
evaluate whether cells would migrate into soft substratum. Cells growing out
from the microspheres after different platings were cultured for 12 days with
10 regular medium change while their morphology recorded at 3, 38 and 154hrs.
The outgrowing cells from 250 microspheres were trypsinized for cell count
for comparison with the conventional monolayer cultures seeded with the
same initial cell number.

Results

15 There was no cell migration immediately after plating of microsphere.
At 38 hours, cells migrated out and formed clusters. After detaching the
microspheres at 72 hours, the outgrowing cells grew to form large colonies.
These cells were homogeneously small and elongated and can be
cryopreserved for future use such as cell-based assays, frozen stocks,
20 re-encapsulation and fabricating tissue-like structures. The morphology of
the outgrowing hMSCs was maintained even after 10 platings and the
morphology simulated that from the early passages of the monolayer culture.
By contrast, scarce out-growing cells were noted in microspheres with low
cell density. The number of out-growing cells increased linearly when cell
25 density (Fig.6A) and microsphere plating density (Fig.6B) increased.

Kruskal Wallis tests showed significant differences between groups (p=0.044). The detached microspheres could be replated several times without enzymatic digestion. Microspheres encapsulated with 250 cells could be plated for at least three times while those with 500 cells for at least six times. Moreover, the cell number obtained from early platings of microspheres was comparable with monolayer cultures (Fig.6C) while a significant decrease (p<=0.018) in later platings was noted. This was related to the significant decrease (p=0.009) in microsphere number (Fig.6D) due to aggregation and disintegration. Microencapsulated hMSCs were also able to migrate into soft collagen gel. The viability of cells from different platings showed no difference. Microspheres aggregation and disintegration can be observed after 72 hours post-attachment. Outgrowing cells at 24 hours post-attachment penetrated into the collagen gel.

Example 5: Maintenance of the surface marker of hMSCs outgrowing from the microspheres after multiple platings.

Materials and Methods

hMSCs migrated out from microspheres after 10 platings were trypsinized with 0.05% trypsin in EDTA for 6-9 minutes and then fixed and labeled with antibodies against surface markers including CD34, CD14, CD29, CD105, CD45 and HLA. Flow cytometry was performed using appropriate isotype controls as described previously (Li et al. 2004).

Results

hMSCs showed the same surface markers panels, negative for CD14, CD34 and CD45, positive for CD105, CD29 and HLA-A,B,C, as that obtained from P1 of monolayer cultures. This indicates that the identity of

the hMSCs was not changed even after 10 cycles of plating and replating of the hMSC-collagen microspheres. Since these cells are from a single aliquot of monolayer cultures of the same passage and these plating cycles can be repeated using another aliquot or aliquots from another passage from the monolayer culture, by combining this 3D culture system and traditional monolayer cultures, long term storage and rich sources for cells, which are necessary for cell-based assays and fabrication of tissue-like structures in tissue engineering can be achieved.

Example 6: Maintenance of the self-renewal capacity of hMSCs
outgrowing from the microspheres after multiple platings

Materials and Methods

A colony formation assay was used to characterize the self-renewal potential of hMSCs obtained from the 3D and the monolayer cultures. hMSCs obtained from the 3rd – 5th passages of the traditional monolayer culture and from the 1st – 5th platings of the 3D culture were seeded at very low density at 250 cells per 100mm diameter culture plate in triplicates and were cultured for 14 days with regular medium replenishment. The colonies formed were stained and fixed with 5% crystal violet (Sigma) in methanol for 10 minutes and rinsed with distilled water twice. The number of colonies with diameter greater than 2mm was counted and the single-cell-derived colony forming efficiency was calculated as the percentage of colony formed of all cells seeded.

Results

Self-renewal capacity of the cell outgrowths from the microspheres after multiple platings was comparable with that obtained from traditional

monolayer cultures, as shown by Fig. 7. One-way ANOVA showed that there was no statistically significant difference in the number of single-cell-derived-colonies in all groups ($p>0.05$).

Example 7: Maintenance of the multiple differentiation potential of

hMSCs outgrowing from the microspheres after multiple platings.

Materials and Methods

Multiple differentiation potential of cell outgrowths

Differentiation assays for chondrogenesis, osteogenesis and adipogenesis were performed to investigate whether hMSCs obtained from the 3D microspheres still retain the multiple differentiation potential according to standard protocols in previous reports (Pittenger et al., *Science*, 284(5411):143-7 (1999); Okamoto, et al., *Biochem. Biophys. Res. Commun.*, 295(2):354-61 (2002); Romanov, et al., *Bull. Exp. Biol. Med.*, 140(1):138-43 (2005)). Cells obtained from the passage 2 of monolayer culture and the 3rd and 10th platings of the 3D cultures were used.

Chondrogenesis

Aliquots of 2×10^5 cells in a 15ml centrifuge tube (Falcon) were centrifuged at 800rpm for 5 minutes at room temperature. The pellet was resuspended in chondrogenic differentiation induction medium, which was defined as DMEM high glucose, supplemented with 10ng/ml recombinant human transforming growth factor beta 3 (hrTGF- β 3), 100nM dexamethasone, 6mg/ml insulin, 100mM ascorbic acid 2-phosphate, 1mM sodium pyruvate, 6mg/ml transferrin, 0.35mM proline and 1.25mg/ml bovine serum albumin. Cells were centrifuged as pellet again and maintained for 3 weeks with regular induction medium replacement every 2

days. At the end of the incubation, pellets were fixed and processed for 5 μ M thick paraffin sections for Alcian blue staining.

Osteogenesis

Full medium was further supplemented with 100nM dexamethasone, 50 μ M ascorbic acid 2-phosphate, and 10mM β -glycerophosphate as the osteogenic differentiation induction medium. hMSCs were seeded at 3×10^3 cells / cm^2 in 4 or 6 well plates in duplicates or triplicates and were maintained in the differentiation induction medium for 3 weeks with regular medium replacement every 3 days. At the end of the incubation, cells were rinsed with PBS, fixed with 10% buffered formalin for 10 minutes at room temperature and stained with 5% silver nitrate (Nakarai Tesque, Kyoto, Japan) for von Kossa staining.

Adipogenesis

Adipogenic differentiation induction medium was prepared by supplementing the full medium with 1 μ M dexamethasone, 0.2mM indomethacin, 10 μ g/ml insulin and 0.5mM 3-isobutyl-1-methylxanthine while the maintenance medium was prepared by supplementing the full medium with only 10 μ g/ml insulin. hMSCs were seeded at 2×10^4 cells / cm^2 in 4 or 6 well plates in duplicates or triplicates in full medium until confluence. Adipogenic differentiation induction medium was added for 3 days followed by 2 days in maintenance medium and three induction / maintenance cycles were performed. Cells were rinsed, fixed and then stained with 0.3% Oil-Red-O (Nakarai) for oil droplets staining.

Results

Multiple differentiation potential of hMSCs was maintained after

multiple cycles of plating. Cell outgrowths obtained from the microspheres after 3rd and 11th platings were still able to differentiate into osteoblasts, adipocytes and chondrocytes. This was demonstrated by the positive staining in von Kossa, Oil Red O and Alcian blue stainings for calcium deposits, oil droplets and proteoglycans, respectively.

Example 8: Chondrogenic differentiation of hMSC in collagen microspheres

Materials and Methods

hMSCs at a final concentration of 5×10^6 cells/ml was suspended in 100 μ l of neutralized collagen solution (2mg/ml). Microspheres so prepared were incubated in chondrogenic differentiation medium for 3 weeks as described in Example 7. The differentiated microspheres were stained for cartilage-specific matrix markers as described in Example 7.

Results

Cartilage micro-tissues could be formed as the microencapsulated hMSCs were able to be chondrogenically differentiated into chondrocyte-like cells with typical round morphology. The differentiated cells lost their ability to migrate and produced cartilage-specific extracellular matrix as shown by the positive staining for glycosaminoglycans, aggrecan and type II collagen.

Example 9: *In vivo* subcutaneous implantation of collagen-hMSC microspheres in NOD/SCID mice.

Materials and Methods

Animal experimentation was conducted with appropriate ethical approval according to institutional regulations. Collagen-hMSC microspheres with 0.5 and 2mg/ml collagen and 250 cells per microsphere

were incubated with 2 μ M Calcein AM for 45 minutes for live cell labeling. Twelve NOD/SCID mice (25-30g) were anaesthetized. An incision was made at the back to create a subcutaneous pocket of approximately 1x1cm. One thousand collagen-hMSC microspheres were implanted and the incision
5 closed by 5.0 non-absorbable silk sutures. After 2, 7 and 14 days post-implantation, animals were sacrificed by overdose anesthesia. Skin flaps at the implantation site were harvested and observed under fluorescence microscope to trace for live cells.

Results

10 The microspheres remained intact and localized at the implantation site while the encapsulated cells were retained viable in NOD/SCID mice for at least 14 days. Clusters of microspheres encapsulating viable hMSCs, which were stained with vital fluorescent dye, can be identified on day 2, 7 and 14 days post-implantation. Viable hMSCs exhibited their typical
15 elongated morphology. Their human origin was confirmed by the immunopositive staining of human antigen beta2-microglobulin. Immunopositive staining for the human antigen was also found in cells, which are participating in the formation of blood vessels.

**Example 10: Extent of contraction of fibroblast-seeded collagen gel in
20 the presence of glycosaminoglycans (GAGs).**

Materials and Methods

Acidic rat-tail collagen solution was neutralized by NaOH and diluted into a final concentration of 0.5mg/ml. Glycosaminoglycans (Chondroitin-6-sulfate) was added to the gelling mixture at a mass ratio of
25 (1:3, 1:1 and 3:1). All procedures were done in an ice-bath so as to prevent

collagen gel formation. Human bone marrow derived mesenchymal stem cells (MSCs), and in the presence of full medium, DMEM-LG with 10% FBS and 1% P/S was then suspended thoroughly in the neutralized collagen solution with GAGs as soon as possible to make a final density of 1 or 5×10^5 cells/ml. The mixture was cast in 4well culture plate and incubated in a 37°C incubator for 1 hr to allow for gelation. The gel was detached from the walls of the culture plate using a syringe needle and supplemented with sufficient medium. The size of the gel was measured under a dissection microscope at different time points to record the extent of contraction.

10 Results

At all cell densities, fibroblasts-seeded gels contracted significantly over time due to the migration and proliferation of cells, as shown by Fig. 8A and 8B. The presence of a second matrix such as GAGs did affect the cellular responses in collagen gel. In particular, presence of GAGs reduced the extent of fibroblasts-induced gel contraction and was in a dose-dependent manner that a higher mass ratio of GAGs:Collagen resulted in a less extent of contraction, as demonstrated by comparing the results for 1×10^5 cells/ml in Fig. 8A with the results for 5×10^5 cells/ml in Fig. 8B.

Example 11: HEK293 cell culture and encapsulation

20 Materials and Methods

HEK293 cells (Passage 4) were transfected to over-express GDNF. Cells were cultured at 37°C with 5% CO₂ using T75 flask with 10ml complete Dulbeco's Modified Eagle Medium -- High Glucose (DMEM-HG, 2%, 5% or 10% FBS, 1% PS) and 500µg/ml G418 Sulfate. Fresh medium and G418 sulfate were replaced every 2 days. These cells were used for the

subsequent encapsulation.

The HEK293 cells were trypsinized using 0.25% Trypsin-EDTA.

Rat-tail collagen solution type I was neutralized by NaOH and diluted into a final concentration of 4mg/ml, in the presence of HEK293 cells in DMEM.

- 5 The cell mixture was kept at 4°C in an ice bath before use. The dispenser was loaded with the cell mixture and dispensed a small volume of 5µl at a time onto a collection platform or a bacterial culture dish covered with UV-irradiated parafilm. The microdroplets were allowed to reconstitute into solid microspheres by incubating in a 37°C incubator with 5% CO₂ for 1 hr.
- 10 The cell-matrix microspheres formed were collected into a DMEM medium containing bath with non-adherent substratum by gently flushing the parafilm with medium. Complete medium was used to suspend the cell-encapsulated capsules in 35mm petri dish. Cell proliferation, cell viability, GDNF productivity of HEK293 cells in 3D microspheres were
- 15 compared with that cultured in traditional monolayer cultures.

Results

Morphological analysis of the microspheres

The cell-encapsulated capsules were viewed under an inverted microscope. Diameter of the capsules was measured at 40x magnification.

- 20 The diameters of 5 out of 50 cell-encapsulated capsules in each set up were measured and the average value determined. The rate of contraction of the cell-encapsulated capsules depended on the cell-seeding density, as shown by Fig. 9. With a higher cell-seeding density, the cell-encapsulated capsules contracted at an earlier time point and at a higher rate. Using the high
- 25 cell-seeding density of 5000 cell/capsule, contraction began at day 4. The

mean diameters were $2.42 \text{ mm} \pm 0.05$ and $1.77 \text{ mm} \pm 0.07$ on day 0 and day 12 respectively. For cell-seeding density of 500 cells/microsphere, the mean diameter was $2.4 \text{ mm} \pm 0.01$ on day 0. There were no contractions until day 8 and the mean diameter was $2.24 \text{ mm} \pm 0.15$ on day 12. For the low

5 cell-seeding density of 50 cell/microsphere, the mean diameter of capsule was $2.4 \text{ mm} \pm 0.04$ on both day 0 and day 12. This showed that there were no observable contractions of the microspheres. The percentage changes of the mean diameters were (-)26.9%, (-)6.67% and 0% for cell-seeding density of 5000, 500 and 50 cell/microsphere respectively. Colonies or aggregates of

10 cells started to form at day 6 and the size of the aggregates increased throughout day 8 to day 14.

Example 12: Fate of encapsulated cells, viability and number of cells

Materials and Methods

For traditional monolayer cultures, the HEK293 cells were

15 trypsinized using 0.25% trypsin-EDTA. The viability tests were done using the trypan blue staining. The numbers of cells were counted using the hemacytometer. For 3D microspheres, collagenase (30 unit/ml) was used to digest the cell-encapsulated capsules. Trypsin/EDTA was then added into the colonies suspension and was incubated at 37°C with 5% CO_2 for 3 min to

20 prepare single cell suspension. Viability test using trypan blue and cell counting were conducted.

Results

At the early time points, single cells were found inside the capsules. The cell size increased and small aggregates of cells were formed at day 6.

25 Cell aggregation continued to form a network and the morphology of cells

resembled those in monolayer culture. The cell viability was shown in Figure 10A. The viabilities of cells were almost the same at different cell-seeding densities. This showed that cell-seeding density did not affect the cell viability. Moreover, there was no practical difference between the viability of cells in monolayer culture and the viability of the encapsulated cells. The number of cells is shown in Figure 10B. There was significant difference between the monolayer group and the microsphere group. The proliferation index of the monolayer group was always higher than that of the microsphere group, ranging from 4 to 140 fold. There was also a significant difference between different cell-seeding densities. The interaction between cell density and group was significant as well. The proliferation index of the monolayer group decreased with cell-seeding density but the effect was not obvious in the microsphere group.

Example 13: GDNF quantification

Materials and Methods

GDNF was measured using the GDNF E_{max}[®] ImmunoAssay System following the instructions provided by the manufacturer (Promega). The 96-well plates were coated with Anti-GDNF Monoclonal Antibody (mAb), which binds soluble GDNF, overnight and at 4°C without shaking. The captured GDNF is bound by Anti-Human GDNF polyclonal antibody (pAb, 1 µg/ml) and incubated without shaking at 4°C overnight. After washing, the amount of specifically bound pAb is then detected by incubating with Anti-Chicken IgY, horseradish peroxidase (HRP) conjugate for 2 hr at room temperature with regular agitation. The unbound conjugate is removed by washing, and followed by incubating with the TMB One Solution, a

chromogenic substrate, for 15 min at room temperature without shaking. The reaction is stopped by adding 1N HCl. The absorbance at 450nm was measured using a microplate reader within 30 min after stopping the reaction. The amount of GDNF in the test solutions is proportional to the color generated in the oxidation-reduction reaction. This ELISA system can detect a minimum of 31.2 pg/ml of GDNF and the linear range is from 31pg/ml to 1000pg/ml GDNF.

The HEK293 cells were trypsinized using 0.25% Trypsin-EDTA. For monolayer cultures, 2.5×10^4 HEK293 cells were seeded onto the 6-well plate with 2ml complete medium (DMEM, 10% FBS, 1% PS) and 500µg/ml G418 sulfate. For 3D cultures, microspheres were formed as described above. The cell-seeding density was 500 cells/microsphere and the number of microsphere per 35mm petri dish was 50. The microspheres were suspended in petri dishes with 2ml complete medium (DMEM, 10% FBS, 1% PS) and 500µg/ml G418 sulfate. Different time points included day 2, 4, 8, 10, 14. For both monolayer and microsphere cultures, there were four samples per each time point ($n = 4$). Medium was collected and replaced every 2 days in all set up for GDNF quantification.

The HEK293 cells were trypsinized using 0.25% Trypsin-EDTA. For monolayer cultures, 2.5×10^3 , 2.5×10^4 or 2.5×10^5 HEK293 cells were seeded onto the 6-well plate with 2ml complete medium (DMEM, 10% FBS, 1% PS) and 500µg/ml G418 sulfate. For 3D cultures, the microspheres were formed as stated in Example 2. The cell-seeding density was 50, 500 or 5000 cells/microsphere. Fifty microspheres were suspended in each 35mm petri dish with 2ml complete medium (DMEM, 10% FBS, 1% PS) and 500µg/ml

G418 sulfate. The initial cell number for the 3D cultures is the same as that in monolayer cultures. For both monolayer and 3D cultures, there were four samples per each initial cell number group ($n = 4$). Medium was collected and replaced every 2 days in all groups for GDNF collection and subsequent quantification. Cell viability test and cell counting were conducted on day 12.

The HEK293 cells were trypsinized using 0.25% trypsin-EDTA. For monolayer cultures, 2.5×10^4 HEK293 cells were seeded onto the 6-well plate with 2ml medium having different serum percentage (2%, 5%, 10%) and 500 μ g/ml G418 sulfate. For 3D cultures, microspheres were formed as stated in Example 2. The cell-seeding density was 500 cell/microspheres and there were 50 microspheres per 35mm petri dish equivalent to an initial cell number of 2.5×10^4 cells. The microspheres were suspended in 2ml medium having different serum percentage (2%, 5%, 10%) and 500 μ g/ml G418 sulfate. For both monolayer and 3D cultures, there were four samples per each serum percentage ($n = 4$). Medium was collected and replaced every 2 days in all set up for GDNF quantification. Cell viability test and cell counting were conducted on day 12.

Results

The cell viability and number of HEK293 cells in both monolayer and 3D microspheres at each time point (Day 2, 4, 8, 10, 14, 18, 22, 26 and 30) are shown in Fig. 11A and 11B, respectively. The cell number of the monolayer group was always higher than that of the microsphere group and there was a significant difference between them. Apart from an initial lower cell viability of around 80% in 3D microspheres, the cell viability of all

groups in all subsequent time points was close to 100%. The accumulative secretion of GDNF was linearly proportional to time in both the monolayer group and the microsphere group (Figure 12). There was a significant difference in accumulative secretion of GDNF between monolayer group and
5 microsphere group. Post hoc testing showed a significant difference between day 2 and day 4 with all other time points. The secretion rates of GDNF in different groups over different time points were shown in Figure 12B. For both monolayer and microsphere groups, the secretion rate of GDNF continued to increase until day 8. There was a significant difference between
10 the secretion rate of monolayer group and that of the microsphere group. The secretion rates of GDNF from HEK293 cells in the 3D microspheres were 67, 12, 10, 10 and 3.5 times that from monolayer cultures for day 2, 4, 8, 10 and 14, respectively. This demonstrates significantly higher productivity in 3D microspheres.

15 The total GDNF secretion of both monolayer and microsphere groups were linearly proportional to the cell-seeding density (Figure 12C). There was a significant difference in total GDNF secretion between the monolayer and microsphere groups, and among different cell densities. The total GDNF secretion of the monolayer group is higher than that of the microsphere
20 group, due to the large difference in cell number. At each cell-seeding density, the number of cell in monolayer group is about 7 – 20 times higher than the number of cell in microsphere group at day 12. However, the secretion rate of GDNF from HEK293 cells was found to be higher than that from monolayer cultures in all groups (Fig. 12D) and the difference was

statistically significant between monolayers and microsphere cultures and among groups with different initial cell numbers.

The total GDNF secreted from day 0 to day 12 was linearly proportional to the serum percentage in medium in both monolayer and
5 microsphere groups (Figure 12E). There were significant differences in total GDNF secretion between the monolayer and microsphere groups and among different serum percentages in medium. The total GDNF secretion in monolayer group was always higher than that in microsphere group and the differences were less than 2 folds at all serum percentages. There was no
10 interaction between group and serum percentage in medium. However, the secretion rate of GDNF from HEK293 cells per million cells per day (Fig. 12F) was significantly higher than that from monolayer cultures at all serum percentages. The difference in GDNF secretion rate in 3D microspheres was more than 4 folds in all serum concentrations indicating that the enhanced
15 productivity of HEK293 cells in 3D microspheres was independent of the serum percentage. It also demonstrated that the encapsulated cells secreted the highest rate of GDNF when they were sustained with medium with 2% serum. The cell viability and number of HEK293 cells in microspheres cultured with different serum concentration are shown in Fig. 13A and 13B,
20 respectively and the viability in all serum concentrations showed almost 100% (Fig. 13A) indicating that the cell viability was not significantly affected by reducing the serum concentration, as a result, reducing serum concentration can be used to ease the downstream purification steps of the secreted proteins.

Example 14: Bioactivity assay of GDNF in conditioned medium of HEK293 cells

Materials and Methods

PC 12 cells were grown on 24-well plates in 81.5% F12K medium, supplemented with 15% House serum, 2.5% Fetal bovine serum and 1% PS. Conditioned medium containing the secreted GDNF was mixed with the full medium for PC12 culture at 1:1 volume ratio and used to culture the PC12 cells. The cells were plated at a density of approximately 3000 cells (in 800 ul) per well. After 2 days, the cells were fixed for visualization under the phase microscope. Cells with neurite outgrowth longer than one body length of the cell were regarded as positive results. Standard GDNF with known concentrations were also used as positive controls. Full medium without conditioned medium was used as negative control.

Results

Both GDNF standards (10 and 50ng/ml) and all conditioned medium samples showed neurite growth in PC12 cells while the negative controls showed no neurite outgrowth. This demonstrated that GDNF released by the HEK293 cells into the conditioned medium does retain their bioactivity.

Example 15: Bioactivity assay of GDNF in conditioned medium of HEK293 cells

GDNF-secreting HEK293 cells were encapsulated in 3D collagen microspheres and cultured for 14 days. The microspheres were fixed in 4% paraformaldehyde for 3 hours followed by 30% sucrose solution for overnight before cryosections of 10 μ m thick were prepared. Immunohistochemistry of GDNF was conducted to confirm its secretion

using a primary antibody, chicken anti-human GDNF polyclonal antibody (Promega) at 1:100-1:50 dilution and a secondary antibody, rabbit anti-chicken IgY (Promega) at 1:100-1:50 dilution. HRP-DAB substrate system was used to visualize the immuno-positively stained GDNF inside the microspheres. The synthesis of GDNF was confirmed by immunohistochemistry. Immunopositive staining of GDNF was localized at the cell colonies inside the 3D microspheres.

Example 16: Optimization of Formulation Parameters of Cell-Matrix Microspheres

Materials and Methods

Culture medium, NaOH, collagen solution, chondroitin sulfate solution and cell suspension were added and mixed in order, and microspheres of 100ul of the mixture were prepared as described in Example 1. The microspheres were cultured in normal medium for 1 day and then changed to chondrogenic differentiation medium (DMEM high glucose, 10ng/ml recombinant human transforming growth factor beta 3 (Merck), 100nM dexamethasone (Sigma), 6 µg/ml insulin (Merck), 100mM 2-phospho-L-ascorbate (Fluka), 1mM sodium pyruvate (Gibco), 6µg/ml transferrin (Sigma), 0.35mM L-proline (Merck) and 1.25mg/ml bovine serum albumin (Sigma)).

The microspheres were cultured for 21 days, with medium changed every two days. After 21 days of culture, the samples were either processed for immunohistochemistry and histology for qualitative analysis or digested in papain solution (300 µg/ml papain in 50mM PB, containing 5mM L-cysteine and 5mM EDTA) at 60°C overnight for quantitative analysis of

chondrogenesis. 1,9-Dimethylmethylene blue (DMMB) assay was used for GAG quantification. In brief, 1ml of DMMB dye solution was added to the sample digest in a tube and the content was mixed on a shaker for 30 minutes. The tube was centrifuged at 13.2k rpm for 10minutes to form the GAG-dye
5 complex precipitate. The precipitate was resuspended in 200 μ l of dissociation reagent and mixed by vortex and the absorbance at 656nm was measured. From the digestion mixture, DNA content was also quantified by a fluorometric assay. In brief, 100 μ l of Hoechst 33258 dye solution was added to the sample digest and fluorescence measurement was made with excitation
10 and emission at 365nm and 458nm respectively. The GAGs content was then normalized by DNA content.

Results

The amount of GAGs deposited into the collagen microspheres increased with increasing cell seeding density and collagen concentration, as
15 shown in Fig. 14A. Statistical analysis shows that the difference among the four cell seeding density groups and among collagen density groups are all significant ($p < 0.05$). When normalized by DNA content, the amount of GAG/DNA also increased with increasing cell seeding density and collagen concentration, as demonstrated by Fig. 14B. Statistical analysis also shows
20 significant difference among various groups ($p < 0.05$).

We claim:

1. Cell-matrix microspheres comprising cells, a first extracellular matrix (ECM) forming a nanofibrous microsphere having embedded therein cells as a result of a phase change of the ECM.
2. The microspheres of claim 1, wherein the first ECM provides support to the cells, interacts with the cells to allow cell growth without introducing toxicity and permits cell migration from the microspheres for growth.
3. The microspheres of claim 1, wherein the first ECM is collagen.
4. The microspheres of claim 1, wherein the first ECM can be induced to reconstitute into solid form under specific conditions that are mild enough to support cellular survival and growth.
5. The microspheres of claim 1, further comprising a second ECM selected from a group consisting of proteoglycans and glycosaminoglycans (GAGs).
6. The microspheres of claim 5, wherein the second ECM is produced from the group consisting of cartilage, fibrin, elastin and hyaluronic acid.
7. The microspheres of claim 5, wherein the first ECM can interact with living cells or with the second ECM in such a way that the interaction leads to change in volume or dimension, ECM density, cell density, mechanical property or stability.
8. The microspheres of claim 1, wherein the cells comprise mature cells, mesenchymal cells or stem cells isolated from bone marrow, skin, GI tract, adipose tissue, placenta, intervertebral discs, cartilage, muscles, skin, tendon, ligament, and nerve.

9. The microspheres of claim 1, wherein the cells are bone marrow-derived mesenchymal stem cells (MSCs), either autologous or allogeneic from HLA-matched donors.
10. The microspheres of claim 1, wherein the cells are genetically engineered or selected for production of biomolecules.
11. The microspheres of claim 1, further comprising growth-stimulating factor, which may be selected from the group consisting of human serum, platelet rich plasma and other blood products.
12. The microspheres of claim 1, further comprising a differentiation factor.
13. The microspheres of claim 1 further comprising a therapeutic, prophylactic or diagnostic agent.
14. A method of producing microspheres, comprising
mixing and dispensing an ECM in combination with cells at a temperature promoting a phase transition of the ECM to form a cell-matrix microsphere,
dispensing the cell-ECM mixture to form droplets onto a surface maintaining the spherical shape of the droplets,
accelerating phase transition or gelation of the ECM to form the cell-matrix microspheres.
15. The method of claim 14 comprising collecting the cell-matrix microspheres on a platform.
16. The method of claim 15 comprising maintaining the composition at a temperature between 0°C-10°C at the dispensing side.
17. The method of claim 14 comprising raising the temperature of the collection platform to 25-37°C to accelerate phase transition for a period of time sufficient for gelation of the ECM but insufficient for cell morphological change.

18. The method of claim 14 wherein the speed of gelation of the matrix is immediately slowed down after initiating the gelation by maintaining the temperature of the mixtures as low as 4°C.
19. The method of Claim 14 wherein the gelation of the matrix is accelerated immediately after dispensing the gelling matrix into droplets at the collecting unit by raising the temperature of the mixture to 37°C.
20. The method of claim 14 comprising
- collecting the microspheres from the collection platform with minimal mechanical disturbance;
 - maintaining the microspheres free-floating in a first medium for an extended period of time until the size of the microspheres becomes substantially constant; and
 - releasing the microspheres from the first medium.
21. The method of claim 20, wherein the microspheres are maintained free-floating for about 2 to about 7 days at a temperature of about 37°C.
22. A method for manipulating cell migration from microspheres formed of ECM encapsulated cells as defined by any of claims 1-13, comprising the following steps:
- providing a mechanical support for the microspheres by plating them onto the solid substratum of culture dishes or placing them into a gelling matrix or onto a gelled matrix;
 - plating the microspheres wherein each microsphere is kept at a distance from each other;
 - adding a second medium into the culture system for holding the microspheres;

allowing cell migration from the microspheres; and
releasing the microspheres from the second medium after an extended period of time.

23. The method of claim 22, wherein the cells migrating out from the microspheres are cryopreserved or re-encapsulated.

24. A method for injecting or implanting cell-matrix microspheres as defined by any of claims 1-13 into tissues of animals or humans comprising
providing cell-ECM matrix microspheres in a pharmaceutically acceptable medium for injection or implantation in a tissue.

25. The method of claim 24 further comprising injecting or implanting the microspheres in the tissue.

26. The method of claim 25 wherein the cells are mesenchymal stem cells, chondrogenic cells or cells isolated from tissue.

27. The method of claim 26 further comprising inducing the cells to differentiate prior to injection or implantation.

28. A method for production of a biomolecule comprising culturing cells in cell-ECM matrix microspheres as defined by any of claims 1-13.


29. A system for making microspheres from ECM and encapsulating cells comprising

a dispensing unit for dispensing a mixture of ECM and cells in liquid droplets;

a collection platform for collecting the dispensed droplets, the platform having a surface with a surface property such that the spherical shape of the droplets is maintained and allows gelation of the matrix to form solid cell-matrix microspheres.

30. The system of claim 29, further comprising a control unit for controlling the dispensing speed, volume and position of the dispenser.
31. The system of claim 29, further comprising a temperature control unit.
32. The system of claim 29 wherein the phase transition process can be initiated by controlling the temperature, the pH and the ionic strength of the liquid environment at appropriate time.
33. The method of claim 29 further comprising static culture vessels or bioreactors with regular agitation or spinning or rotation.

Fig. 1 - Schematic drawing of the production setup for making cell-matrix microspheres



The whole setup is installed inside culture hood

Fig. 2 - Flow chart showing the production of mechanically stable cell-matrix microspheres with controllable size.




Fig. 3 – Flow chart showing the method controlling of the cell migration from the cell-matrix microspheres




FIG. 4A-4C




FIG. 5A AND FIG. 5B




FIG. 6A-6D




FIG. 7




FIG. 8A AND FIG. 8B




FIG. 9




FIG. 10A




FIG. 10B




FIG. 11A




FIG. 11B




FIG. 12A-FIG. 12F




FIG. 13A




FIG. 13B




FIG. 14A




FIG. 14B

