



(43) International Publication Date
29 June 2017 (29.06.2017)

(10) International Publication Number
WO 2017/108644 A1

(51) International Patent Classification:

B65D 1/26 (2006.01) **C08K 5/00** (2006.01)
C08F 110/06 (2006.01) **C08L 23/14** (2006.01)

(21) International Application Number:

PCT/EP2016/081635

(22) International Filing Date:

19 December 2016 (19.12.2016)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

15201634.1 21 December 2015 (21.12.2015) EP

(71) Applicant: **BOREALIS AG** [AT/AT]; Wagramer Strasse
17-19, 1220 Vienna (AT).

(72) Inventors: **WANG, Jingbo**; Fröhlerweg 12/1/36, 4040
Linz (AT). **GAHLEITNER, Markus**; Kohlwinkel 4, 4501
Neuhofen/Krems (AT). **KLIMKE, Katja**; Tower 2, Apt.
2108, Corniche Road, PO Box 108243, Abu Dhabi (AE).
BRAUN, Juliane; Tomaschekweg 32, 4040 Linz (AT).
LESKINEN, Pauli; Tuiskutie 5a, 00700 Helsinki (FI).

(74) Agent: **LUX, Berthold**; Maiwald Patentanwalts GmbH,
Elisenhof / Elisenstrasse 3, 80335 Munich (DE).

(81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,

AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KH, KN,
KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA,
MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG,
NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS,
RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY,
TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN,
ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, KM, ML, MR, NE, SN, TD, TG).

Published:

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments (Rule 48.2(h))

(54) Title: ARTICLES WITH IMPROVED OPTICAL PROPERTIES

(57) Abstract: Moulded articles comprising a polypropylene homopolymer with rather high melt flow rate, high stiffness, improved optical properties and an advantageous balance between stiffness and optical properties.



WO 2017/108644 A1

Articles with improved optical properties

The present invention relates to injection moulded articles comprising a polypropylene homopolymer with rather high melt flow rate, high stiffness, improved optical properties and an advantageous balance between stiffness and optical properties.

In the field of thin-wall packaging of the moulding market it is of great importance to have a material of high flowability with good mechanical properties, i.e. stiffness and good optical properties. Good flowability is needed for achieving a good processability in various manufacturing methods of articles, such as injection moulding processes, thereby allowing the production of articles having low wall thicknesses and/or long flow paths in the mould.

The mechanical properties are also critical in view of the thin-walled articles. Particularly, in the field of containers there is a need to have a material sufficiently stiff to be stacked. Good stiffness of the material is also desired for reducing wall-thickness of the final articles and hence saving raw-material, while maintaining impact properties at the same time.

Further, materials should also withstand mechanical compression damage, which is frequently incurred by e.g. dropping the articles.

At the same time it is a constant desire to provide materials with low haze and hence better see-through-properties on the content of the article.

Therefore, it is a constant need for polypropylene homopolymer to balance the conflicting requirements of good processability, stiffness, and good optical performance, i.e. low haze.

Description of the prior art:

Polypropylene compositions are known in the art. The European patent application EP1514893A1, for example, discloses polypropylene compositions comprising a clarifier selected from one or more phosphate-based α -nucleating agents and/or polymeric nucleating agents, selected from the group consisting of vinylcycloalkane polymers and vinylalkane polymers. Similar nucleating agents are also disclosed in the international applications WO 99/24478 and WO 99/24479. The European patent application EP316187A2 discloses a crystalline polypropylene homopolymer incorporated therein a polymer of a vinyl cycloalkane. The international application WO2004/055101 discloses a heterophasic propylene copolymer, containing nucleating agents, selected from phosphate-derived nucleating agents, sorbitol-derived nucleating agents, metal salts of aromatic or aliphatic carboxylic acids as nucleating agents, polymeric nucleating agents, such as polyvinyl cyclohexane and inorganic nucleating agents, such as talc.

EP1801155A1 refers to a polypropylene composition comprising a nucleated propylene homopolymer having improved optical properties, especially on injection moulded articles.

However, the patent requires very high loadings of polymeric nucleating agents to improve optical properties.

All polypropylene compositions mentioned above are produced using a Ziegler-Natta catalyst, in particular a high yield Ziegler-Natta catalyst (so called fourth and fifth generation type to differentiate from low yield, so called second generation Ziegler-Natta catalysts), which comprises a catalyst component, a co-catalyst component and an internal donor based on phthalate-compositions.

WO2012007430 is one example of a limited number of patent applications, describing phthalate free catalysts based on citraconate as internal donor.

However, up to now the mechanical properties of polypropylenes produced with catalyst having citraconate compositions as internal donors, did not fulfill all the desired requirements, especially in view of stiffness/optical properties.

Still there is a constant need for polypropylene homopolymers and articles made thereof, which provide good flowability, i.e. a high melt flow rate, improved stiffness and better transparency, while maintaining impact behaviour at a satisfying level.

Hence, it is an object of the present invention to provide a material with good flowability, i.e. a high melt flow rate, improved stiffness and better transparency, while maintaining impact behaviour.

It is a further object of the present invention to provide articles with an improved balance of said properties.

Seen from another point of view, the current invention provides articles with improved Top Load and haze while maintaining drop height behaviour unchanged.

Object of the invention

It has now surprisingly been found that the above object can be achieved by moulded articles characterized by comprising a polypropylene homopolymer, wherein the polypropylene homopolymer is polymerised in the presence of a Ziegler-Natta catalyst (ZN-C) and further characterised in that the polypropylene homopolymer

- a. comprises 0 – 1.0 wt% of ethylene and/or a C4-C10 α -olefin determined according to ^{13}C -NMR,
- b. comprises at least one α -nucleating agent
- c. is free of phthalic acid esters as well as their respective decomposition products and
- d. has a MFR230/2.16 determined according to ISO1133 in the range of 20 - 200 g/10 min, and has
- e. a haze of ≤ 45 % when measured according to ASTM D1003 on 1mm plaques.

In a special embodiment the inventors also identified a method to improve Heat distortion Temperature and/or optical properties such as haze in polypropylene homopolymers.

In a further special embodiment the invention concerns the use of the articles in household applications or packaging applications.

Detailed description:

The polypropylene homopolymer in accordance with the present invention may have a melt flow rate (MFR_2) as measured in accordance with ISO 1133 at 230 °C and 2.16 kg load of at least 20 g/10 min, such 30 g/10 min or 38 g/10 min or more. Preferably the polypropylene homopolymer may have a melt flow rate MFR_2 of at least 45 g/10 min, like 52 g/10 min, or at least 58 or 62 g/10 min.

The polypropylene homopolymer in accordance with the present invention may have a melt flow rate (MFR_2) of up to 200 g/10 min, such as up to 180 g/10 min, 150 g/10 min or below or 120 g/10 min or below.

Further preferred is that the polypropylene homopolymer of present invention is in the range of 20 - 200 g/10 min, preferably in the range of 38 to 180 g/10 min, like in the range of 52 to 150 g/10 min. Even more preferably the MFR_2 is in the range of 58 - 120 g/10 min.

It is within the scope of the invention that the MFR of the polypropylene homopolymer can be achieved either directly in the reactor or during a post-polymerisation visbreaking step using peroxides, wherein the peroxidic visbreaking is preferred.

The modality with respect to molecular weight distribution and thus with respect to melt flow ratio is not critical.

Thus the polypropylene composition in accordance with the present invention may be unimodal or multimodal including bimodal with respect to molecular weight distribution.

The polypropylene homopolymer according to the present invention relates to a polypropylene homopolymer that consists substantially, i.e. of at least 99.0 wt.-%, more preferably of at least 99.3 wt.-%, still more preferably of at least 99.6 wt.-%, like of at least 99.8 wt.-% or at least 99.9 wt.-%, of propylene units. In another embodiment only propylene units are detectable, i.e. only propylene has been polymerised.

The comonomers units other than propylene are selected from ethylene and C4 to C10 α -olefins, like butene or hexene. Preferably, the comonomer is ethylene.

The total comonomer content of the nucleated propylene composition may be in the range of up to 1.0 wt.%, like up to 0.7 wt.%, such as up to 0.4 wt.% preferably in the range of 0.2 – 1.0 wt.%, like in the range of 0.4 to 0.7 wt.%.

Alternatively preferred are polypropylene homopolymers with a comonomer content of 0 – 0.40 wt%. Further preferred are polypropylene homopolymers a comonomer content of >0.40 - 0.90 wt%. In a preferred embodiment the polypropylene homopolymer according to the present invention consists of propylene as sole monomer.

5

The polypropylene homopolymer in accordance with the present invention may be further characterized by low haze ≤ 45 % when measured according to ASTM 1003 on 1 mm plaques, such as $\leq 42\%$, $\leq 40\%$, $\leq 35\%$, $\leq 32\%$, or $\leq 29\%$.

10 The polypropylene homopolymer in accordance with the present invention may be further characterized by and Heat distortion Temperature HDT, determined according to ISO75B of at least 95 °C, preferably at least 99 °C, such as 105 °C or 110 °C or 115 °C or above.

Especially preferred are polypropylene homopolymers with a comonomer content of 0 – 0.40 wt% and a haze value of ≤ 45 % or a HDT, determined according to ISO75B of at least 95 °C.

15

Equally preferred are polypropylene homopolymers with a comonomer content of > 0.40 – 0.90 wt% and a haze value of ≤ 45 % and/or a HDT, determined according to ISO75B of at least 100 °C and/or a Top Load of ≥ 360 N.

20

The polypropylene homopolymer according to the present invention may have a Flexural Modulus determined according to ISO178 of 1700 MPa or higher, such as 1740 MPa or higher.

Nucleating agents

25 The α -nucleating agent according the present invention may be selected from the group consisting of:

(i) salts of monocarboxylic acids and polycarboxylic acids, e.g. sodium benzoate or aluminum tert-butylbenzoate;

(ii) soluble nucleating agents, like sorbitol derivatives, e.g. di(alkylbenzylidene)sorbitols as 1,3:2,4-25 dibenzylidene sorbitol, 1,3:2,4-di(4-methylbenzylidene) sorbitol, 1,3:2,4-di(4-ethylbenzylidene) sorbitol and 1,3:2,4-Bis(3,4-dimethylbenzylidene) sorbitol, as well as nonitol derivatives, e.g. 1,2,3-trideoxy-4,6;5,7-bis-O-[(4-propylphenyl)methylene] nonitol, and benzene-trisamides like substituted 1,3,5-benzenetrisamides as N,N',N''-tris-tert-butyl-1,3,5-benzenetricarboxamide, N,N',N''-tris-cyclohexyl-1,3,5-benzene-tricarboxamide and N-[3,5-bis-(2,2-dimethyl-propionylamino)-phenyl]-2,2-dimethyl-propionamide, wherein 1,3:2,4-di(4-methylbenzylidene) sorbitol and N-[3,5-bis-(2,2-dimethyl-propionylamino)-phenyl]-2,2-dimethyl-propionamide are equally preferred,

30

35

(iii) salts of diesters of phosphoric acid, e.g. sodium 2,2'-methylenebis (4, 6,-di-tert-butylphenyl) phosphate or aluminium-hydroxy-bis[2,2'-methylene-bis(4,6-di-t-butylphenyl)phosphate], and hydroxybis (2,4,8,10-tetra-tert- butyl-6-hydroxy-12Hdibenzo(d,g)(1,3,2) dioxaphosphocin 6-oxidato) aluminium, wherein hydroxybis (2,4,8,10-tetra-tert- butyl-6-hydroxy-12H-

dibenzo(d,g)(1,3,2) dioxaphosphocin 6-oxidato) aluminium is preferred; and

(iv) polymeric nucleating agents, such as polymerized vinyl compounds, in particular vinyl cycloalkanes, like vinyl cyclohexane (VCH), poly(vinyl cyclohexane) (PVCH), vinylcyclopentane, and vinyl-2-methyl cyclohexane, 3-methyl-1-butene, 3-ethyl-1-hexene, 3-methyl-1-pentene, 4-methyl-1-pentene or mixtures thereof. PVCH is a particularly preferred.

It is especially preferred that the nucleating agent comprised in the polypropylene homopolymer of the present invention is selected from the group of soluble nucleating agents (ii) or from the group of polymeric nucleating agents (iv) of above list.

In a specific embodiment the polypropylene homopolymer comprises at least two, such as exactly two nucleating agents. These two (or more) nucleating agents are preferably selected from group (ii) for the one and from group (iv) for the other.

Polymeric nucleating agents from group (iv) can either be incorporated by in-reactor nucleation or by the so called Masterbatch technology (compounding technology) as mentioned below.

In a preferred embodiment of the present invention, the polymeric nucleating agent is introduced into the heterophasic polypropylene composition by means of a suitably modified catalyst, into the reactor (i.e. **in-reactor nucleation**) i.e. the catalyst to be used in catalysing the polymerization of any of the fractions a) or b), preferably a) is subjected to a polymerization of a suitable monomer for the polymeric nucleating agent to produce first said polymeric nucleating agent. The catalyst is then introduced together with the obtained polymeric nucleating agent to the actual polymerization step of the propylene polymer component(s).

In a particularly preferred embodiment of the present invention, the propylene polymer is prepared in the presence of such a modified catalyst to obtain said reactor made polypropylene homopolymer. With such modified catalyst, it is also possible to carry out the above-identified preferred polymerization sequence for the preparation of in-situ blended multimodal, including bimodal, polypropylenes.

The polymeric nucleating agent introduced via in-reactor-nucleation usually is present in the final product in an amount of from at least 10 ppm, typically at least 13 ppm, (based on the weight of the polypropylene homopolymer). Preferably this agent is present in the polypropylene homopolymer in a range of from 10 to 1000 ppm, more preferably from 15 to 500 ppm, such as 20 to 100 ppm.

In case of applying in-reactor nucleation, the inventive composition comprises a propylene homopolymer fraction received from a step of pre-polymerization which is carried out before the

polymerization of the first fraction as defined above. More preferably, said fraction is a propylene homopolymer fraction.

The polymeric nucleating agent may also be present in the final product also in lower concentrations, like in an amount of from at least 0.5 ppm, typically at least 1.0 ppm, (based on the weight of the polypropylene homopolymer). Preferably this agent is present in the polypropylene homopolymer in a range of 2 to 100 ppm, more preferably from 3 to 80 ppm, such as 5 to 50 ppm.

Another embodiment, different to the above mentioned in-reactor blend, is a mechanical blend of a polymer with a nucleating agent, wherein the polymer is first produced in the absence of a polymeric nucleating agent and is then blended mechanically with the polymeric nucleating agent or with a small amount of nucleated polymer or with polymers, which already contain the polymeric nucleating agent (so-called **master batch technology**) in order to introduce the polymeric nucleating agent into the polymer mixture. The preparation of a reactor made polymer composition ensures the preparation of a homogenous mixture of the components, for example a homogeneously distributed polymeric nucleating agent in the polypropylene homopolymer, even at high concentrations of polymer nucleating agent.

As outlined above, the **reactor made polymer** composition is a preferred embodiment of the present invention, although also mechanical blends prepared, for example, by using master batch technology are envisaged by the present invention.

Preparation Process:

The polypropylene composition in accordance with the present invention may be prepared by any suitable polymerisation process.

In a preferred embodiment of the present invention, the polymeric nucleating agent is introduced into the polypropylene composition by means of a suitably modified catalyst, i.e. the catalyst to be used in catalysing the polymerisation of the propylene polymer is subjected to a polymerisation of a suitable monomer for the polymeric nucleating agent to produce first said polymeric nucleating agent (so called BNT-technology is mentioned below). The catalyst is then introduced together with the obtained polymeric nucleating agent to the actual polymerisation step of the propylene polymer component(s).

In a particularly preferred embodiment of the present invention, the propylene polymer is prepared in the presence of such a modified catalyst to obtain said reactor made polypropylene composition.

The polypropylene homopolymer according to the invention is preferably prepared by a sequential polymerisation process, as described below, in the presence of a catalyst system

comprising a Ziegler-Natta Catalyst, a cocatalyst and optionally an external donor, as described below.

In the pre-polymerisation reactor a polypropylene is produced. The pre-polymerisation is conducted in the presence of the Ziegler-Natta catalyst. According to this embodiment the Ziegler-Natta catalyst, the co-catalyst, and the external donor are all introduced to the pre-polymerisation step. However, this shall not exclude the option that at a later stage for instance further co-catalyst and/or external donor is added in the polymerisation process, for instance in the first reactor. In one embodiment the Ziegler-Natta catalyst, the co-catalyst, and the external donor are only added in the pre-polymerisation reactor.

The pre-polymerisation reaction is typically conducted at a temperature of 0 to 60 °C, preferably from 15 to 50 °C, and more preferably from 20 to 45 °C.

The pressure in the pre-polymerisation reactor is not critical but must be sufficiently high to maintain the reaction mixture in liquid phase. Thus, the pressure may be from 20 to 100 bar, for example 30 to 70 bar.

In a preferred embodiment, the pre-polymerisation is conducted as bulk slurry polymerisation in liquid propylene, i.e. the liquid phase mainly comprises propylene, with optionally inert components dissolved therein. Furthermore, according to the present invention, an ethylene feed can be employed during pre-polymerisation as mentioned above.

It is possible to add other components also to the pre-polymerisation stage. Thus, hydrogen may be added into the pre-polymerisation stage to control the molecular weight of the polypropylene as is known in the art. Further, antistatic additive may be used to prevent the particles from adhering to each other or to the walls of the reactor.

The precise control of the pre-polymerisation conditions and reaction parameters is within the skill of the art.

Due to the above defined process conditions in the pre-polymerisation, a mixture of the Ziegler-Natta catalyst and the polypropylene produced in the pre-polymerisation reactor (PR) is obtained. Preferably the Ziegler-Natta catalyst is (finely) dispersed in the polypropylene. In other words, the Ziegler-Natta catalyst particles introduced in the pre-polymerisation reactor (PR) split into smaller fragments which are evenly distributed within the growing polypropylene. The sizes of the introduced Ziegler-Natta catalyst particles as well as of the obtained fragments are not of essential relevance for the instant invention and within the skilled knowledge.

Polymerisation Process

Accordingly, the polypropylene homopolymer is preferably produced in a process comprising the following steps under the conditions set out above:

a) In the pre-polymerisation, a mixture of the Ziegler-Natta catalyst and the polypropylene produced in the pre-polymerisation reactor is obtained. Preferably the Ziegler-Natta catalyst is (finely) dispersed in the polypropylene. Subsequent to the pre-polymerisation, the mixture of the Ziegler-Natta catalyst and the polypropylene produced in the pre-polymerisation reactor is

transferred to the first reactor. Typically the total amount of the polypropylene (coming from the prepolymerisation) in the final propylene polymer is rather low and typically not more than 5.0 wt.-%, more preferably not more than 4.0 wt.-%, still more preferably in the range of 0.5 to 4.0 wt.-%, like in the range 1.0 of to 3.0 wt.-%.

b) In the first polymerisation reactor, i.e. in a loop reactor, propylene is polymerised obtaining a first propylene homopolymer fraction of the propylene homopolymer, transferring said first propylene homopolymer fraction to any optional further polymerisation reactors.

In any further optional reactor propylene is polymerised in the presence of any precedingly produced polypropylene fraction

Within the invention it is envisaged, that comonomers may be applied in any of the polymerisation reactors.

A preferred multistage process is a "loop-gas phase"-process, such as developed by Borealis A/S, Denmark (known as BORSTAR® technology) is described e.g. in patent literature, such as in EP 0 887 379, WO 92/12182 WO 2004/000899, WO 2004/111095, WO 99/24478, WO 99/24479 or in WO 00/68315.

A further suitable slurry-gas phase process is the Spheripol® process of Basell.

Catalyst system

A possible catalyst for being used in the production of the polypropylene homopolymer is described herein:

The catalyst is a solid Ziegler-Natta catalyst (ZN-C), which comprises compounds (TC) of a transition metal of Group 4 to 6 of IUPAC, like titanium, a Group 2 metal compound (MC), like a magnesium, and an internal donor (ID) being a non-phthalic compound, preferably a non-phthalic acid ester, still more preferably being a diester of non-phthalic dicarboxylic acids as described in more detail below. Thus, the catalyst is in a preferred embodiment fully free of undesired phthalic compounds. Further, the solid catalyst is free of any external support material, like silica or MgCl_2 , but the catalyst is self-supported.

The Ziegler-Natta catalyst can be further defined by the way as obtained. Accordingly, the Ziegler-Natta catalyst is preferably obtained by a process comprising the steps of

a)

a₁) providing a solution of at least a Group 2 metal alkoxy compound (Ax) being the reaction product of a Group 2 metal compound (MC) and a monohydric alcohol (A)

comprising in addition to the hydroxyl moiety at least one ether moiety optionally in an organic liquid reaction medium; or

a₂) a solution of at least a Group 2 metal alkoxy compound (Ax') being the reaction product of a Group 2 metal compound (MC) and an alcohol mixture of the monohydric alcohol (A)

and a monohydric alcohol (B) of formula ROH, optionally in an organic liquid reaction medium; or

a₃) providing a solution of a mixture of the Group 2 alkoxy compound (Ax) and a Group 2 metal alkoxy compound (Bx) being the reaction product of a Group 2 metal compound (MC) and the monohydric alcohol (B), optionally in an organic liquid reaction medium; or

a₄) providing a solution of Group 2 alkoxide of formula $M(OR_1)_n(OR_2)_mX_{2-n-m}$ or mixture of Group 2 alkoxides $M(OR_1)_nX_{2-n'}$ and $M(OR_2)_mX_{2-m'}$, where M is Group 2 metal, X is halogen, R₁ and R₂ are different alkyl groups of C₂ to C₁₆ carbon atoms, and $0 \leq n < 2$, $0 \leq m < 2$ and $n+m+(2-n-m) = 2$, provided that both n and m $\neq 0$, $0 < n' \leq 2$ and $0 < m' \leq 2$; and

b) adding said solution from step a) to at least one compound (TC) of a transition metal of Group 4 to 6 and

c) obtaining the solid catalyst component particles, and adding an internal electron donor (ID), preferably a non-phthalic internal donor (ID), at any step prior to step c).

The internal donor (ID) or precursor thereof is thus added preferably to the solution of step a) or to the transition metal compound before adding the solution of step a).

According to the procedure above the Ziegler-Natta catalyst (ZN-C) can be obtained via precipitation method or via emulsion- solidification method depending on the physical conditions, especially temperature used in steps b) and c). Emulsion is also called in this application liquid/liquid two-phase system.

In both methods (precipitation or emulsion-solidification) the catalyst chemistry is the same.

In precipitation method combination of the solution of step a) with at least one transition metal compound (TC) in step b) is carried out and the whole reaction mixture is kept at least at 50 °C, more preferably in the temperature range of 55 to 110 °C, more preferably in the range of 70 to 100 °C, to secure full precipitation of the catalyst component in form of a solid particles (step c).

In emulsion - solidification method in step b) the solution of step a) is typically added to the at least one transition metal compound (TC) at a lower temperature, such as from -10 to below 50 °C, preferably from -5 to 30 °C. During agitation of the emulsion the temperature is typically kept at -10 to below 40 °C, preferably from -5 to 30 °C. Droplets of the dispersed phase of the

emulsion form the active catalyst composition. Solidification (step c) of the droplets is suitably carried out by heating the emulsion to a temperature of 70 to 150 °C, preferably to 80 to 110 °C.

5 The catalyst prepared by emulsion - solidification method is preferably used in the present invention.

In a preferred embodiment in step a) the solution of a_2) or a_3) are used, i.e. a solution of (Ax') or a solution of a mixture of (Ax) and (Bx), especially the solution of a_2).

10 Preferably the Group 2 metal (MC) is magnesium.

The magnesium alkoxy compounds as defined above can be prepared *in situ* in the first step of the catalyst preparation process, step a), by reacting the magnesium compound with the alcohol(s) as described above, or said magnesium alkoxy compounds can be separately
15 prepared magnesium alkoxy compounds or they can be even commercially available as ready magnesium alkoxy compounds and used as such in the catalyst preparation process of the invention.

20 Illustrative examples of alcohols (A) are glycol monoethers. Preferred alcohols (A) are C_2 to C_4 glycol monoethers, wherein the ether moieties comprise from 2 to 18 carbon atoms, preferably from 4 to 12 carbon atoms. Preferred examples are 2-(2-ethylhexyloxy)ethanol, 2-butyloxy ethanol, 2-hexyloxy ethanol and 1,3-propylene-glycol-monobutyl ether, 3-butoxy-2-propanol, with 2-(2-ethylhexyloxy)ethanol and 1,3-propylene-glycol-monobutyl ether, 3-butoxy-2-propanol being particularly preferred.

25 Illustrative monohydric alcohols (B) are of formula ROH, with R being straight-chain or branched C_2 - C_{16} alkyl residue, preferably C_4 to C_{10} , more preferably C_6 to C_8 alkyl residue. The most preferred monohydric alcohol is 2-ethyl-1-hexanol or octanol.

30 Preferably a mixture of Mg alkoxy compounds (Ax) and (Bx) or mixture of alcohols (A) and (B), respectively, are used and employed in a mole ratio of Bx:Ax or B:A from 10:1 to 1:10, more preferably 6:1 to 1:6, most preferably 4:1 to 1:4.

35 Magnesium alkoxy compound may be a reaction product of alcohol(s), as defined above, and a magnesium compound selected from dialkyl magnesium, alkyl magnesium alkoxides, magnesium dialkoxides, alkoxy magnesium halides and alkyl magnesium halides. Further, magnesium dialkoxides, magnesium diaryloxides, magnesium aryloxyhalides, magnesium aryloxides and magnesium alkyl aryloxides can be used. Alkyl groups can be a similar or

different C₁-C₂₀ alkyl, preferably C₂-C₁₀ alkyl. Typical alkyl-alkoxy magnesium compounds, when used, are ethyl magnesium butoxide, butyl magnesium pentoxide, octyl magnesium butoxide and octyl magnesium octoxide. Preferably the dialkyl magnesium are used. Most preferred dialkyl magnesium are butyl octyl magnesium or butyl ethyl magnesium.

5

It is also possible that magnesium compound can react in addition to the alcohol (A) and alcohol (B) also with a polyhydric alcohol (C) of formula R'' (OH)_m to obtain said magnesium alkoxide compounds. Preferred polyhydric alcohols, if used, are alcohols, wherein R'' is a straight-chain, cyclic or branched C₂ to C₁₀ hydrocarbon residue, and m is an integer of 2 to 6.

10

The magnesium alkoxy compounds of step a) are thus selected from the group consisting of magnesium dialkoxides, diaryloxy magnesium, alkyloxy magnesium halides, aryloxy magnesium halides, alkyl magnesium alkoxides, aryl magnesium alkoxides and alkyl magnesium aryloxides. In addition a mixture of magnesium dihalide and a magnesium dialkoxide can be used.

15

The solvents to be employed for the preparation of the present catalyst may be selected among aromatic and aliphatic straight chain, branched and cyclic hydrocarbons with 5 to 20 carbon atoms, more preferably 5 to 12 carbon atoms, or mixtures thereof. Suitable solvents include benzene, toluene, cumene, xylene, pentane, hexane, heptane, octane and nonane. Hexanes and pentanes are particular preferred.

20

The reaction for the preparation of the magnesium alkoxy compound may be carried out at a temperature of 40 to 70 °C. Most suitable temperature is selected depending on the Mg compound and alcohol(s) used.

25

The transition metal compound of Group 4 to 6 is preferably a titanium compound, most preferably a titanium halide, like TiCl₄.

The internal donor (ID) used in the preparation of the catalyst used in the present invention is preferably selected from (di)esters of non-phthalic carboxylic (di)acids, 1,3-diethers, derivatives and mixtures thereof. Especially preferred donors are diesters of mono-unsaturated dicarboxylic acids, in particular esters belonging to a group comprising malonates, maleates, succinates, citraconates, glutarates, cyclohexene-1,2-dicarboxylates and benzoates, and any derivatives and/or mixtures thereof. Preferred examples are e.g. substituted maleates and citraconates, most preferably citraconates.

35

In emulsion method, the two phase liquid-liquid system may be formed by simple stirring and optionally adding (further) solvent(s) and additives, such as the turbulence minimizing agent

(TMA) and/or the emulsifying agents and/or emulsion stabilizers, like surfactants, which are used in a manner known in the art for facilitating the formation of and/or stabilize the emulsion. Preferably, surfactants are acrylic or methacrylic polymers. Particular preferred are unbranched C₁₂ to C₂₀ (meth)acrylates such as poly(hexadecyl)-methacrylate and poly(octadecyl)-methacrylate and mixtures thereof. Turbulence minimizing agent (TMA), if used, is preferably selected from α -olefin polymers of α -olefin monomers with 6 to 20 carbon atoms, like polyoctene, polynonene, polydecene, polyundecene or polydodecene or mixtures thereof. Most preferable it is polydecene.


The solid particulate product obtained by precipitation or emulsion – solidification method may be washed at least once, preferably at least twice, most preferably at least three times with an aromatic and/or aliphatic hydrocarbons, preferably with toluene, heptane or pentane and or with TiCl₄. Washing solutions can also contain donors and/or compounds of Group 13, like trialkyl aluminum, halogenated alkyl aluminum compounds or alkoxy aluminum compounds. Aluminum compounds can also be added during the catalyst synthesis. The catalyst can further be dried, as by evaporation or flushing with nitrogen, or it can be slurried to an oily liquid without any drying step.

The finally obtained Ziegler-Natta catalyst is desirably in the form of particles having generally an average particle size range of 5 to 200 μ m, preferably 10 to 100. Particles are compact with low porosity and have surface area below 20 g/m², more preferably below 10 g/m². Typically the amount of Ti is 1 to 6 wt-%, Mg 10 to 20 wt-% and donor 10 to 40 wt-% of the catalyst composition.

Detailed description of preparation of catalysts is disclosed in WO 2012/007430, EP2610271, EP 2610270 and EP2610272 which are incorporated here by reference.

The Ziegler-Natta catalyst (ZN-C) is preferably used in association with an alkyl aluminum cocatalyst and optionally external donors.

As further component in the instant polymerisation process an external donor (ED) is preferably present. Suitable external donors (ED) include certain silanes, ethers, esters, amines, ketones, heterocyclic compounds and blends of these. It is especially preferred to use a silane. It is most preferred to use silanes of the general formula



wherein R^a, R^b and R^c denote a hydrocarbon radical, in particular an alkyl or cycloalkyl group, and wherein p and q are numbers ranging from 0 to 3 with their sum p + q being equal to or less than 3. R^a, R^b and R^c can be chosen independently from one another and can be the same or

different. Specific examples of such silanes are (tert-butyl)₂Si(OCH₃)₂, (cyclohexyl)(methyl)Si(OCH₃)₂, (phenyl)₂Si(OCH₃)₂ and (cyclopentyl)₂Si(OCH₃)₂, or of general formula



- 5 wherein R³ and R⁴ can be the same or different and represent a hydrocarbon group having 1 to 12 carbon atoms.

R³ and R⁴ are independently selected from the group consisting of linear aliphatic hydrocarbon group having 1 to 12 carbon atoms, branched aliphatic hydrocarbon group having 1 to 12
10 carbon atoms and cyclic aliphatic hydrocarbon group having 1 to 12 carbon atoms. It is in particular preferred that R³ and R⁴ are independently selected from the group consisting of methyl, ethyl, n-propyl, n-butyl, octyl, decanyl, iso-propyl, iso-butyl, iso-pentyl, tert.-butyl, tert.-amyl, neopentyl, cyclopentyl, cyclohexyl, methylcyclopentyl and cycloheptyl.

- 15 More preferably both R¹ and R² are the same, yet more preferably both R³ and R⁴ are an ethyl group.

Especially preferred external donors (ED) are the pentyl dimethoxy silane donor (D-donor) or the cyclohexylmethyl dimethoxy silane donor (C-Donor).

- 20 In addition to the Ziegler-Natta catalyst (ZN-C) and the optional external donor (ED) a co-catalyst can be used. The co-catalyst is preferably a compound of group 13 of the periodic table (IUPAC), e.g. organo aluminum, such as an aluminum compound, like aluminum alkyl, aluminum halide or aluminum alkyl halide compound. Accordingly, in one specific embodiment
25 the co-catalyst (Co) is a trialkylaluminium, like triethylaluminium (TEAL), dialkyl aluminium chloride or alkyl aluminium dichloride or mixtures thereof. In one specific embodiment the co-catalyst (Co) is triethylaluminium (TEAL).

- Advantageously, the triethyl aluminium (TEAL) has a hydride content, expressed as AlH₃, of
30 less than 1.0 wt% with respect to the triethyl aluminium (TEAL). More preferably, the hydride content is less than 0.5 wt%, and most preferably the hydride content is less than 0.1 wt%.

- Preferably the ratio between the co-catalyst (Co) and the external donor (ED) [Co/ED] and/or the ratio between the co-catalyst (Co) and the transition metal (TM) [Co/TM] should be carefully
35 chosen.


Accordingly,

(a) the mole ratio of co-catalyst (Co) to external donor (ED) [Co/ED] must be in the range of 5 to 45, preferably is in the range of 5 to 35, more preferably is in the range of 5 to 25; and optionally

(b) the mole ratio of co-catalyst (Co) to titanium compound (TC) [Co/TC] must be in the range of
5 above 80 to 500, preferably is in the range of 100 to 350, still more preferably is in the range of 120 to 300.

As mentioned above the Ziegler-Natta catalyst (ZN-C) is preferably modified by the so called
BNT-technology during the above described pre-polymerisation step in order to introduce the
10 polymeric nucleating agent.

Such a polymeric nucleating agent is as described above a vinyl polymer, such as a vinyl
polymer derived from monomers of the formula



wherein R₁ and R₂, together with the carbon atom they are attached to, form an optionally
20 substituted saturated or unsaturated or aromatic ring or a fused ring system, wherein the ring or
fused ring moiety contains four to 20 carbon atoms, preferably 5 to 12 membered saturated or
unsaturated or aromatic ring or a fused ring system or independently represent a linear or
branched C₄-C₃₀ alkane, C₄- C₂₀ cycloalkane or C₄-C₂₀ aromatic ring. Preferably R₁ and R₂,
together with the C-atom wherein they are attached to, form a five- or six-membered saturated
25 or unsaturated or aromatic ring or independently represent a lower alkyl group comprising from
1 to 4 carbon atoms. Preferred vinyl compounds for the preparation of a polymeric nucleating
agent to be used in accordance with the present invention are in particular vinyl cycloalkanes, in
particular vinyl cyclohexane (VCH), vinyl cyclopentane, and vinyl-2-methyl cyclohexane, 3-
methyl-1-butene, 3-ethyl-1-hexene, 3-methyl-1-pentene, 4-methyl-1-pentene or mixtures
30 thereof. VCH is a particularly preferred monomer.

The weight ratio of vinyl compound to polymerisation catalyst in the modification step of the
polymerisation catalyst preferably is 0.3 or more up to 40, such as 0.4 to 20 or more preferably
0.5 to 15, like 0.5 to 2.0.

35 The polymerisation of the vinyl compound, e. g. VCH, can be done in any inert fluid that does
not dissolve the polymer formed (e. g. polyVCH). It is important to make sure that the viscosity

of the final catalyst/polymerised vinyl compound/inert fluid mixture is sufficiently high to prevent the catalyst particles from settling during storage and transport.

The adjustment of the viscosity of the mixture can be done either before or after the polymerisation of the vinyl compound. It is, e. g., possible to carry out the polymerisation in a low viscosity oil and after the polymerisation of the vinyl compound the viscosity can be adjusted by addition of a highly viscous substance. Such highly viscous substance can be a "wax", such as an oil or a mixture of an oil with a solid or highly viscous substance (oil-grease). The viscosity of such a viscous substance is usually 1,000 to 15,000 cP at room temperature. The advantage of using wax is that the catalyst storing and feeding into the process is improved. Since no washing, drying, sieving and transferring are needed, the catalyst activity is maintained.

The weight ratio between the oil and the solid or highly viscous polymer is preferably less than 5: 1.

In addition to viscous substances, liquid hydrocarbons, such as isobutane, propane, pentane and hexane, can also be used as a medium in the modification step.

The polypropylenes produced with a catalyst modified with polymerised vinyl compounds contain essentially no free (unreacted) vinyl compounds. This means that the vinyl compounds shall be completely reacted in the catalyst modification step. To that end, the weight ratio of the (added) vinyl compound to the catalyst should be in the range of 0.05 to 10, preferably less than 3, more preferably about 0.1 to 2.0, and in particular about 0.1 to 1.5. It should be noted that no benefits are achieved by using vinyl compounds in excess.

Further, the reaction time of the catalyst modification by polymerisation of a vinyl compound should be sufficient to allow for complete reaction of the vinyl monomer, i. e. the polymerisation is continued until the amount of unreacted vinyl compounds in the reaction mixture (including the polymerisation medium and the reactants) is less than 0.5 wt-%, in particular less than 2000 ppm by weight (shown by analysis). Thus, when the prepolymerised catalyst contains a maximum of about 0.1 wt-% vinyl compound, the final vinyl compound content in the polypropylene will be below the limit of determination using the GC-MS method (< 0.01 ppm by weight). Generally, when operating on an industrial scale, a polymerisation time of at least 30 minutes is required, preferably the polymerisation time is at least 1 hour and in particular at least 5 hours. Polymerisation times even in the range of 6 to 50 hours can be used. The modification can be done at temperatures of 10 to 70 °C, preferably 35 to 65 °C.

According to the invention, nucleated high-stiffness propylene polymers are obtained when the modification of the catalyst is carried out in the presence of strongly coordinating external donors.

- 5 General conditions for the modification of the catalyst are also disclosed in WO 00/6831, incorporated herein by reference with respect to the modification of the polymerisation catalyst. The preferred embodiments as described previously in the present application with respect to the vinyl compound also apply with respect to the polymerisation catalyst of the present invention and the preferred polypropylene composition in accordance with the present invention.
- 10 Suitable media for the modification step include, in addition to oils, also aliphatic inert organic solvents with low viscosity, such as pentane and heptane. Furthermore, small amounts of hydrogen can be used during the modification.

Moulded Articles

- 15 As used herein the term "moulded article" is intended to encompass articles that are produced by any conventional moulding technique, e.g. injection moulding, blow moulding, stretch moulding, compression moulding, roto-moulding or injection stretch blow moulding. Preferably the moulded article is an article that is produced by injection moulding.
- The moulded articles preferably are thin-walled articles having a wall thickness of 300 µm to 2
- 20 mm. More preferably the thin-walled articles have a wall thickness of 300 µm to 1400 µm, and even more preferably the thin-walled articles have a wall thickness of 300 µm to 900 µm.

The articles of the current invention can be containers, such as cups, crates, tubs, bins, boxes, buckets, beakers, bowls, trays, or parts of such articles, such as see-through-windows, lids, or

25 the like.

The articles of the current invention can also be used in houseware applications, for e.g. cutlery or toys.

The articles are further useful for storage or for packaging applications.

The articles of the current invention can also be devices used in the medical industry, like

30 syringes, testing tips, sample containers or the like.

The articles of the current invention are especially suitable for stackable applications like boxes, e.g. transport boxes, lidded pails or containers e.g. storage containers.

The articles of the current invention are characterized by an improved Top load, providing better stacking behavior. The topload, when measured on 850 ml-cups as described below, may be

35 360 N or higher, such as 370 N or higher.

The articles of the current invention are characterized by a drop height of 0.5 m or above.

The method for producing moulded articles with improved HDT as well as the method for producing moulded articles with improved optical properties such as haze, comprises the steps of

- 5 a) polymerising propylene and optionally ethylene in the presence of a Ziegler-Natta catalyst, wherein the Ziegler-Natta-catalyst comprises
- i) compounds of a transition metal of Group 4 to 6 of IUPAC,
 - ii) a Group 2 metal compound (MC) and
 - iii) an internal donor (ID), wherein said internal donor (ID) is a non-phthalic compound, preferably is a non-phthalic acid ester,
 - 10 iv) a co-catalyst (Co), and
 - v) optionally an external donor (ED)
- b) optionally incorporating at least one α -nucleating agent and
- c) moulding articles comprising said polymer obtained in step i).

- 15 The α -nucleating agent incorporating in step b) is preferably a polymeric nucleating agent and/or a soluble nucleating agent.

In a preferred embodiment the invention encompasses a method for producing moulded articles improved haze or improved clarity.

- 20 In a preferred embodiment the invention encompasses a method for producing moulded articles with improved HDT and improved optical properties.

The present invention will now be described in further detail by the examples provided below.

Examples:

Measuring methods

5 Melt Flow Rate

The melt flow rate (MFR) is determined according to ISO 1133 and is indicated in g/10 min. The MFR is an indication of the flowability, and hence the processability, of the polymer. The higher the melt flow rate, the lower the viscosity of the polymer. The MFR₂ of polypropylene is determined at a temperature of 230 °C and a load of 2.16 kg.

10

Xylene Soluble Fraction and Amorphous Phase

The xylene soluble fraction (XCS) as defined and described in the present invention is determined as follows: 2.0 g of the polymer were dissolved in 250 ml p-xylene at 135 °C under agitation. After 30 minutes, the solution was allowed to cool for 15 minutes at ambient temperature and then allowed to settle for 30 minutes at 25 ± 0.5 °C. The solution was filtered with filter paper into two 100 ml flasks. The solution from the first 100 ml vessel was evaporated in nitrogen flow and the residue dried under vacuum at 90 °C until constant weight is reached. The xylene soluble fraction (percent) can then be determined as follows:

$$\text{XCS\%} = (100 \times m_1 \times v_0) / (m_0 \times v_1),$$

20 wherein m_0 designates the initial polymer amount (grams), m_1 defines the weight of residue (grams), v_0 defines the initial volume (millilitre) and v_1 defines the volume of the analysed sample (millilitre).

The fraction insoluble in p-xylene at 25 °C (XCU) is then equal to 100% - XCS%.

25 The solution from the second 100 ml flask was treated with 200 ml of acetone under vigorous stirring. The precipitate was filtered and dried in a vacuum oven at 90 °C. This solution can be employed in order to determine the amorphous part (AM) of the polymer (wt%) using the following equation:

$$\text{AM} = (100 \times m_1 \times v_0) / (m_0 \times v_1)$$

30 wherein m_0 designates the initial polymer amount (g), m_1 defines the weight of residue (g), v_0 defines the initial volume (ml) and v_1 defines the volume of the analysed sample (ml).

Flexural Modulus

The Flexural Modulus is determined in 3-point-bending according to ISO 178 on injection moulded specimens of 80 x 10 x 4 mm³ prepared in accordance with EN ISO 1873-2.

35

DSC analysis, melting temperature (T_m) crystallization temperature (T_c)

DSC parameters are measured with a TA Instrument Q2000 differential scanning calorimetry (DSC) on 5 to 7 mg samples. DSC is run according to ISO 11357 / part 3 / method C2 in a heat /

cool / heat cycle with a scan rate of 10 °C/min in the temperature range of -30 to +225 °C.

Crystallization temperature and heat of crystallization (H_c) are determined from the cooling step, while melting temperature and heat of fusion (H_f) are determined from the second heating step.

- 5 **Charpy impact test:** The Charpy notched impact strength (NIS) was measured according to ISO 179 1eA at +23 °C, using injection moulded bar test specimens of 80x10x4 mm³ prepared in accordance with EN ISO 1873-2

Heat deflection temperature (HDT)

- 10 HDT is measured on injection moulded test specimen as described in EN ISO 1873-2 (80 x 10 x 4 mm³) that are placed in a heating bath, resting horizontally on two supports according to ISO75B. A constant load (0.45 MPa) is applied in the centre of the specimen (three-point bending) and the bath temperature is raised at a constant rate. The temperature of the bath at which the flexural deflection of the loading point has reached a predefined level is the heat
15 deflection temperature of the material.

Haze and Clarity

- 20 Haze and Clarity are determined from 1 mm or 2 mm thick injection moulded plaque samples or on cups (as described below) according to ASTM D1003-A using a hazegard + hazemeter byk-gardner.

Cup testing:

Preparation of 850 ml cups

- 25 Cups are produced by injection moulding using an Engel speed 180 machine with a 35 mm barrier screw (supplied by Engel Austria GmbH). The melt temperature was adjusted to 245 °C and the mould temperature to 10 °C; an injection speed of 770 cm³/s with an injection time of 0.08 s was used, followed by a holding pressure time of 0.1 s with 1300 bar (decreasing to 800 bar) and a cooling time of 1.5 s, giving a standard cycle time of 3.8 s. The dimensions of the cup are as follows: Height 100 mm, diameter top 115 mm, diameter bottom 95 mm, bottom wall
30 thickness 0.44 mm, side-wall thickness 0.40 mm. For the cycle time optimization the machine was run with standard injection parameters first. The machine was run in full automatic mode, reducing the cooling time after a stabilization time of 5 minutes from 1.5 to 0.3 sec. Depending on the material behaviour the cups were then either deformed or could not get de-moulded. Then the cooling time was increased in steps of 0.1 s until the part quality was found to be
35 optically and mechanically satisfactory. The cycle time resulting from this experiment can be found in table 3.

The **Top load** test was performed by compressing cups between two plates attached to a universal testing machine with a test speed of 10 mm/min according to an internal procedure in general agreement with ASTM D642. For testing, the cup is placed upside down (i.e. with the bottom facing the moving plate) into the test setup and compressed to the point of collapse which is noticed by a force drop on the force-deformation curve, for which the maximum force is noted. At least 8 cups are tested to determine an average result.

Drop height

Cups are filled with water. The cups are lifted to a certain height and then dropped down. If they do not collapse, the height is increased. In case of a failure it will be decreased. Generally, the test can be divided into a pre- and a main test phase:

The pre-test phase is used to determine the starting height of the main test phase. 10 cups are needed for this test phase. In this test phase only 1 cup is tested for a selected drop height. The starting height in the pre-test phase is selected according to the material type and previous test results. In case of a cup failure, the drop height will be reduced by 10 cm. If the cup stands the test, the height is increased by 10 cm. If all the 10 cups are tested, the start height for the main test is set to the highest height of the pre-test which led to a non-failure of the cup.

During *the main test*, two cups are tested simultaneously at each height. The procedure of increasing / decreasing the test height is similar to the pre-test phase. The only add-on is, that if one cup stands and one fails at a certain drop height, the test height will stay constant. 20 cups are tested during the main test phase. The drop height is afterwards determined using the formula below:

$$\text{drop height} = \frac{\sum(\text{number of cups @ certain height}) \times \text{height}}{\text{total number of tested cups}}$$

Haze measurement on cups

The measurement is done on the outer wall of the cups produced as described above. The top and bottom of the cups are cut off. The resulting round wall is then split in two, horizontally. Then from this wall six equal samples of app. 60x60 mm² are cut from close to the middle. The specimens are placed into the instrument with their convex side facing the haze port. Then the transparency, haze and clarity are measured for each of the six samples and the haze value is reported as the average of these six parallels.

Comonomer content quantification of poly(propylene-co-ethylene) copolymers

Quantitative ¹³C{¹H} NMR spectra were recorded in the solution-state using a Bruker Advance III 400 NMR spectrometer operating at 400.15 and 100.62 MHz for ¹H and ¹³C respectively. All spectra were recorded using a ¹³C optimised 10 mm extended temperature probe head at 125 °C using nitrogen gas for all pneumatics. Approximately 200 mg of material was dissolved in 3

ml of 1,2-tetrachloroethane-*d*₂ (TCE-*d*₂) along with chromium-(III)-acetylacetonate (Cr(acac)₃) resulting in a 65 mM solution of relaxation agent in solvent {8}. To ensure a homogenous solution, after initial sample preparation in a heat block, the NMR tube was further heated in a rotatory oven for at least 1 hour. Upon insertion into the magnet the tube was spun at 10 Hz.

- 5 This setup was chosen primarily for the high resolution and quantitatively needed for accurate ethylene content quantification. Standard single-pulse excitation was employed without NOE, using an optimised tip angle, 1 s recycle delay and a bi-level WALTZ16 decoupling scheme{3, 4}. A total of 6144 (6k) transients were acquired per spectra.

Quantitative ¹³C{¹H} NMR spectra were processed, integrated and relevant quantitative
10 properties determined from the integrals using proprietary computer programs. All chemical shifts were indirectly referenced to the central methylene group of the ethylene block (EEE) at 30.00 ppm using the chemical shift of the solvent. This approach allowed comparable referencing even when this structural unit was not present. Characteristic signals corresponding to the incorporation of ethylene were observed {7}.

- 15 The comonomer fraction was quantified using the method of Wang et. al. {6} through integration of multiple signals across the whole spectral region in the ¹³C{¹H} spectra. This method was chosen for its robust nature and ability to account for the presence of regio-defects when needed. Integral regions were slightly adjusted to increase applicability across the whole range of encountered comonomer contents.

20 For systems where only isolated ethylene in PPEPP sequences was observed the method of Wang et al. was modified to reduce the influence of non-zero integrals of sites that are known to not be present. This approach reduced the overestimation of ethylene content for such systems and was achieved by of the number of sites used to determine the absolute ethylene content to:

25
$$E = 0.5(S_{\beta\beta} + S_{\beta\gamma} + S_{\beta\delta} + 0.5(S_{\alpha\beta} + S_{\alpha\gamma}))$$

Through the use of this set of sites the corresponding integral equation becomes:

$$E = 0.5(I_H + I_G + 0.5(I_C + I_D))$$

using the same notation used in the article of Wang et al. {6}. Equations used for absolute propylene content were not modified.

- 30 The mole percent comonomer incorporation was calculated from the mole fraction:

$$E [\text{mol}\%] = 100 * fE$$

The weight percent comonomer incorporation was calculated from the mole fraction:

$$E [\text{wt}\%] = 100 * (fE * 28.06) / ((fE * 28.06) + ((1-fE) * 42.08))$$

- 35 Within the term “polypropylene homopolymer” in the meaning of the present inventions, it is understood, that the composition still may comprise the usual additives for utilization with polyolefins, such as pigments (e.g. TiO₂ or carbon black), stabilizers, acid scavengers and/or

UV-stabilisers, lubricants, antistatic agents, further nucleating agents and utilization agents (such as processing aid agents, adhesive promoters, compatibiliser, etc.).

The amount of such additives usually is 10 wt% or less, preferably 5 wt% or less.

5 Material description:

1a) Catalyst preparation

3,4 litre of 2-ethylhexanol and 810 ml of propylene glycol butyl monoether (in a molar ratio 4/1) were added to a 20 l reactor. Then 7,8 litre of a 20 % solution in toluene of BEM (butyl ethyl magnesium) provided by Crompton GmbH were slowly added to the well stirred alcohol mixture.

10 During the addition the temperature was kept at 10 °C. After addition the temperature of the reaction mixture was raised to 60 °C and mixing was continued at this temperature for 30 minutes. Finally after cooling to room temperature the obtained Mg-alkoxide was transferred to storage vessel.

21,2 g of Mg alkoxide prepared above was mixed with 4,0 ml bis(2-ethylhexyl) citraconate for 5
15 min. After mixing the obtained Mg complex was used immediately in the preparation of catalyst component.

19,5 ml titanium tetrachloride was placed in a 300 ml reactor equipped with a mechanical stirrer at 25 °C. Mixing speed was adjusted to 170 rpm. 26,0 of Mg-complex prepared above was added within 30 minutes keeping the temperature at 25 °C. 3,0 ml of Viscoplex 1-254 and 1,0
20 ml of a toluene solution with 2 mg Necadd 447 was added. Then 24,0 ml of heptane was added to form an emulsion. Mixing was continued for 30 minutes at 25 °C. Then the reactor temperature was raised to 90 °C within 30 minutes. The reaction mixture was stirred for further 30 minutes at 90 °C. Afterwards stirring was stopped and the reaction mixture was allowed to settle for 15 minutes at 90 °C.

25 The solid material was washed 5 times: Washings were made at 80 °C under stirring 30 min with 170 rpm. After stirring was stopped the reaction mixture was allowed to settle for 20-30 minutes and followed by siphoning.

Wash 1: Washing was made with a mixture of 100 ml of toluene and 1 ml donor

Wash 2: Washing was made with a mixture of 30 ml of TiCl₄ and 1 ml of donor.

30 Wash 3: Washing was made with 100 ml toluene.

Wash 4: Washing was made with 60 ml of heptane.

Wash 5. Washing was made with 60 ml of heptane under 10 minutes stirring.

Afterwards stirring was stopped and the reaction mixture was allowed to settle for 10 minutes decreasing the temperature to 70 °C with subsequent siphoning, and followed by N₂ sparging
35 for 20 minutes to yield an air sensitive powder.

1b) VCH modification of the catalyst

- 35 ml of mineral oil (Paraffinum Liquidum PL68) was added to a 125 ml stainless steel reactor

followed by 0,82 g of triethyl aluminium (TEAL) and 0,33 g of dicyclopentyl dimethoxy silane (donor D) under inert conditions at room temperature. After 10 minutes 5,0 g of the catalyst prepared in 1a (Ti content 1,4 wt%) was added and after additionally 20 minutes 5,0 g of vinylcyclohexane (VCH) was added.). The temperature was increased to 60 °C during 30 minutes and was kept there for 20 hours. Finally, the temperature was decreased to 20 °C and the concentration of unreacted VCH in the oil/catalyst mixture was analysed and was found to be 120 ppm weight.

For polymerisation the catalyst prepared according to the method of example 1a was modified with VCH in the same way as is described in example 1b, only on a bigger scale. (Ti content of 3.0 wt%). 41 liters of oil, 1.79 kg of TEAL, 0.79 kg of donor D, 5.5 kg of catalyst and 5.55 kg of VCH was used. The concentration of unreacted VCH in the oil/catalyst mixture after the reaction was 150 ppm weight.

All the inventive and comparative example were produced in a Borstar pilot plant with a prepolymerisation reactor, one slurry loop reactor and two gas phase reactors.

The solid catalyst was used in all cases along with triethyl-aluminium (TEAL) as cocatalyst and dicyclo pentyl dimethoxy silane (D-donor) as donor.

The aluminium to donor ratio was 5 mol/mol, the TEAL/Ti-ratio was 90 mol/mol.

Polymerisation conditions are indicated in table 1.

All products were stabilised by melt mixing on a co-rotating twin-screw extruder with 0.2 wt% of Irganox B225 and 0.1 wt% calcium stearate.

CE 1 is HJ120UB, homopolymer, MFR 230/2.16 of 75 g/10 min, Flexural Modulus (determined according to ISO178) of 1500 MPa.

CE2 is HJ325MO, polypropylene homopolymer, MFR 230/2.16 of 50 g/10 min, Flexural Modulus (determined according to ISO178) of 1350 MPa.

CE3 is a non-nucleated, polypropylene homopolymer, MFR 230/2.16 of 59 g/10 min, polymerised in the presence of a catalyst as disclosed according catalyst preparation of step 1a.

CE4 is a nucleated, polypropylene homopolymer, MFR 230/2.16 of 28 g/10 min, polymerised in the presence of a Ziegler-Natta-Catalyst and an internal donor comprising DEHP (di-ethyl-hexyl-phthalate) and 150 ppm Irgaclear XT386 (N-[3,5-bis-(2,2-dimethyl-propionylamino)-phenyl]-2,2-dimethyl-propionamide),

CE5 is a nucleated, polypropylene homopolymer, MFR 230/2.16 of 60 g/10 min, polymerised in the presence of a Ziegler-Natta-Catalyst and an internal donor comprising DEHP (di-ethyl-hexyl-phthalate). CE5 was nucleated via Masterbatch technology by incorporating 2 wt% polypropylene-homopolymer comprising polymeric nucleating agent.

Polymer A is a non-nucleated, polypropylene homopolymer, MFR 230/2.16 of 59 g/10 min, polymerised in the presence of a catalyst as disclosed according catalyst preparation of step 1a.

Polymer B is a non-nucleated, polypropylene homopolymer, MFR 230/2.16 of 8 g/10 min, polymerised in the presence of a catalyst as disclosed according catalyst preparation of step 1a.

- 5 Polymer C is a nucleated polypropylene homopolymer, MFR 230/2.16 of 63 g/10 min, polymerised in the presence of a catalyst as disclosed according catalyst preparation of step 1a and 1b.

- 10 The resulting polymer powders were compounded in a co-rotating twin-screw extruder Coperion ZSK 57 at 220 °C with the below described stabilisers nucleating agents as indicated.

IE1 was produced by compounding Polymer A with 0.2 wt% Millad 3988 (1,3:2,4-di(4-methylbenzylidene) sorbitol).

- 15 IE2 was produced by compounding Polymer B with 150 ppm Irgaclear XT386 (N-[3,5-bis-(2,2-dimethyl-propionylamino)-phenyl]-2,2-dimethyl-propionamide) and Luperox 101 (2,5-di-methyl-2,5 di-(tert-butylperoxy)hexane) for visbreaking the polymer to reach an MFR of 28 g/10 min.

IE3 was produced by compounding Polymer C with 0.2 wt% Millad 3988 (1,3:2,4-di(4-methylbenzylidene) sorbitol).

Table 1 Polymerisation data

		Polymer A	Polymer B	Polymer C
Prepolymerisation				
Temperature	°C	25	30	30
TEAL	g/t C3	250	170	170
Donor	g/t C3	20	20	40
Ethylene feed	kg/h	0	0.33	0.3
Residence time	h	0.33	0.37	0.38
Donor type	n.a.	D	D	D
Loop				
Temperature	°C	70	80	80
H2/C3	mol/kmol	8.8	1.2	10.8
C2/C3	mol/kmol	0.0	1.4	2.2
Split	wt%	100	59	62
Residence time	h	0.52	0.4	0.33
MFR2	g/10 min	59	8	66
XCS	wt%	3.4	3.7	2.7
GPR				
Temperature	°C	not used	80	80
Pressure	kPa		2200	2200
Bed level	cm		90	109
H2/C3	mol/kmol		18.6	91.3
C2/C3	mol/kmol		0.3	8.0
Residence time	h		1.6	2.8
Split	wt%		41	38
XCS	wt%		2.4	2.4
MFR2	g/10 min		8.2	63

Table 2 Polymer characteristics:

		CE1	CE2	CE3	CE4	IE1	IE2
Polymer		HJ120UB	HJ325MO	Polymer A		Polymer A	Polymer B
Internal Donor				Citraconate	DEHP	Citraconate	Citraconate
Nucleation		-	5000 ppm talcum	-	150ppm XT386	2000 ppm DMDBS	150ppm XT386?
MFR230/2.16		75	50	59	28?	60	28
Hf	J/g	98	100	102	108	102	102
Tm	°C	162	164	164	166	166	164
Tc	°C	116	127	120	127	131	126
C2 total (NMR)	Wt%					0	0
Flexural Modulus	MPa	1450	1720	1616	1781	1903	1787
HDT ISO75B	°C	79	94	92	100	109	108
Haze (1mm)	%	-	-	-	48	32	25
Impact	kJ/m ²	1.0	1.5	1.3	2.6	1.0	2.4
Clarity (1mm)	%				94		98

Table 2 above clearly shows, that the inventive polypropylene homopolymer achieves better HDT ISO75B values and even reaches the level, that up to now could only be achieved with 0.5 wt% talcum (CE2)

5 **Table 3**

		CE5	IE3
			Polymer C+ 2000 ppm DMDBS
C2 total (NMR)	wt%	-	0.7
Tc	°C	121	129
Tm1	°C	158	159
Tm2	°C	153	154
Hm1	°C	100	102.7
Hm2	°C	0.78	1.22
Flexural Modulus	MPa	1687	1746
Charpy ISO179/1eA +23 °C	kJ/m ²	1.5	1.5
Haze (1mm)	%	66	39
Haze (2mm)	%	93	69
HDT ISO75B	°C	109	118
Cycle time	Sec	2.6	2.2
Cup testing:Top load	N	350	380
Drop height	m	0.5	0.5
Haze on cups	%	27	16

Table 3 above clearly shows that the inventive polymer has higher stiffness, better top load, higher Heat distortion Temperature and at the same time better optical properties in the sense of lower haze, both on plaques and cups.

Claims

1. Moulded article comprising a polypropylene homopolymer, wherein the polypropylene homopolymer is polymerised in the presence of a Ziegler-Natta catalyst and further characterised in that the polypropylene homopolymer
 - 5 a. comprises 0 – 1.0 wt% of ethylene and/or a C4-C10 α -olefin determined according to ^{13}C -NMR,
 - b. comprises at least one α -nucleating agent
 - c. is free of phthalic acid esters as well as their respective decomposition products
 - d. has a MFR230/2.16 determined according to ISO1133 in the range of 20 - 200 g/10
 - 10 min, and
 - e. a haze of ≤ 45 % (ASTM 1003-D) when measured on 1mm plaques.
2. Moulded article according to claim 1 wherein the Ziegler-Natta-Catalyst comprises
 - a. compounds of a transition metal of Group 4 to 6 of IUPAC,
 - 15 b. a Group 2 metal compound and
 - c. an internal donor, wherein said internal donor is a non-phthalic compound, preferably is a non-phthalic acid ester
 - d. a co-catalyst, and
 - e. optionally an external donor.
 - 20
3. Moulded article according to claims 1 or 2, wherein the at least one α -nucleating agent is either a polymeric nucleating agent and/or a soluble nucleating agent.
4. Moulded article according to any of claim 1 to 3, wherein the polypropylene homopolymer
 - 25 a. comprises 0 – 0.40 wt% of ethylene and/or a C4-C10 α -olefin, and
 - b. has a Heat Distortion Temperature (ISO 75B) of at least 90 °C.
5. Moulded article according to any of claim 1 to 3, wherein the polypropylene homopolymer
 - a. comprises 0 – 0.40 wt% of ethylene and/or a C4-C10 α -olefin, and
 - 30 b. has a haze of ≤ 35 % when measured on 1mm plaques.
6. Moulded article according to any of claim 1 to 3, wherein the polypropylene homopolymer
 - a. comprises ≥ 0.40 – 0.90 wt% of ethylene and/or a C4-C10 α -olefin and
 - b. has a haze of ≤ 42 % when measured on 1mm plaques.
 - 35
7. Moulded article according to any of claim 1 to 3, wherein the polypropylene homopolymer
 - a. comprises more than 0.40 – 0.90 wt% of ethylene and/or a C4-C10 α -olefin and

b. has top load of 360 N or more.

8. Moulded article according to any preceding claim, wherein the moulded article is an injection moulded article.

9. Moulded article according to any preceding claim, wherein the moulded article has a wall thickness of 2 mm or below.

10. Moulded article according to any preceding claim, wherein the moulded article is a container.

11. Method for producing moulded articles with improved Heat Distortion Temperature and/or optical properties such as haze, comprising the steps of

a. polymerising propylene and optionally ethylene in the presence of a Ziegler-Natta catalyst, wherein the Ziegler-Natta-catalyst comprises

- i. compounds of a transition metal of Group 4 to 6 of IUPAC,
- ii. a Group 2 metal compound (MC) and
- iii. an internal donor (ID), wherein said internal donor (ID) is a non-phthalic compound, preferably is a non-phthalic acid ester
- iv. a co-catalyst (Co), and
- v. optionally an external donor (ED)

b. optionally incorporating at least one α -nucleating agent

c. moulding articles comprising said polymer obtained in step a to b).

12. Method according to any claim 12, wherein the α -nucleating agent incorporating in step b) is a polymeric nucleating agent and/or a soluble nucleating agent.

13. Use of the articles according to any of claims 1 to 10 in household applications or packaging applications.

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2016/081635

A. CLASSIFICATION OF SUBJECT MATTER
INV. B65D1/26 C08F110/06 C08K5/00 C08L23/14
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
B65D C08F C08K C08L B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2010/301059 A1 (KAARTO JOHN [US] ET AL) 2 December 2010 (2010-12-02) claims 1-20 paragraphs [0004] - [0013], [0017] - [0022], [0030], [0033] - [0035], [0043] - [0046], [0073], [0102] examples S1,S2; table 3 -----	1-10,13
X	EP 1 801 155 A1 (BOREALIS TECH OY [FI]) 27 June 2007 (2007-06-27) cited in the application claims 1,2,6,7,12-14,20,21 paragraphs [0002], [0010], [0021], [0022], [0053] - [0056], [0064] page 11 - page 12; examples 5,6; table 2 ----- -/-	1-10,13



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

20 March 2017

Date of mailing of the international search report

08/06/2017

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Lippert, Sigrid

INTERNATIONAL SEARCH REPORT

International application No
PCT/EP2016/081635

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 2 719 725 A1 (ABU DHABI POLYMERS COMPANY LTD BOROUGE [AE]; BOREALIS AG [AT]) 16 April 2014 (2014-04-16) claims 1-18 page 17 - page 18; examples C4-C6; tables 1,5 page 14 - page 15; examples Polymer 1, 3 -----	1-10,13
Y	EP 2 610 272 A1 (BOREALIS AG [AT]) 3 July 2013 (2013-07-03) cited in the application claim 1 paragraphs [0016], [0026], [0027] -----	1-10,13
A	WO 2006/065799 A2 (FINA TECHNOLOGY [US]; BURMASTER DOUGLAS [US]; HODGES OWEN [US]; LUMUS) 22 June 2006 (2006-06-22) claims 1-20 paragraphs [0008], [0054] - [0061] -----	1-10,13
A	WO 2007/017360 A1 (BASELL POLIOLEFINE SRL [IT]; CAVALIERI CLAUDIO [IT]; PRADELLA FIORELLA) 15 February 2007 (2007-02-15) the whole document -----	1-10,13

INTERNATIONAL SEARCH REPORT

International application No.
PCT/EP2016/081635

Box No. II Observations where certain claims were found unsearchable (Continuation of item 2 of first sheet)

This international search report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box No. III Observations where unity of invention is lacking (Continuation of item 3 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☐ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fees, this Authority did not invite payment of additional fees.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:
1-10, 13

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest and, where applicable, the payment of a protest fee.
- ☐ The additional search fees were accompanied by the applicant's protest but the applicable protest fee was not paid within the time limit specified in the invitation.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. claims: 1-10, 13

Invention 1 is based on a moulded article comprising a Ziegler-Natta produced polypropylene homopolymer characterized in that it comprises (a) up to 1wt% ethylene and/or C4-C10 alpha-olefin, (b) an alpha-nucleating agent, (c) is free of phthalic acid ester, (d) having a rather high melt flow rate (MFR2 of 20-200 g/10min) and a haze of < 45% (ASTM 1003-D on 1mm plaques).

2. claims: 11, 12

Invention 2 is based on a method for producing moulded articles with improved Heat Distortion Temperature and/or optical properties such as haze, comprising (a) polymerizing propylene and optionally ethylene in the presence of a Ziegler-Natta catalyst comprising (i) compounds of a transition metal of Group 4 to 6 of IUPAC, (ii) a Group 2 metal compound (MC) and (iii) and internal donor (ID) being a non-phthalic compound and (iv) a co-catalyst, and moulding articles comprising said polymer.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2016/081635

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 2010301059	A1	02-12-2010	BR 112012032681 A2 CN 103517924 A EP 2582732 A1 EP 3048120 A1 JP 5802270 B2 JP 2013529700 A KR 20130116859 A MY 158151 A RU 2013102506 A SG 186400 A1 TW 201206685 A US 2010301059 A1 WO 2011163032 A1	29-11-2016 15-01-2014 24-04-2013 27-07-2016 28-10-2015 22-07-2013 24-10-2013 15-09-2016 27-07-2014 30-01-2013 16-02-2012 02-12-2010 29-12-2011
EP 1801155	A1	27-06-2007	AT 451421 T AT 525433 T AU 2006328906 A1 CN 101326237 A CN 101891921 A EA 200870098 A1 EP 1801155 A1 EP 1963424 A1 ES 2336120 T3 ES 2369263 T3 KR 20080086439 A PL 1963424 T3 PT 1963424 E TW 200740908 A US 2009018267 A1 WO 2007071446 A1	15-12-2009 15-10-2011 28-06-2007 17-12-2008 24-11-2010 30-12-2009 27-06-2007 03-09-2008 08-04-2010 28-11-2011 25-09-2008 29-02-2012 04-10-2011 01-11-2007 15-01-2009 28-06-2007
EP 2719725	A1	16-04-2014	AU 2013329910 A1 CN 104797652 A EP 2719725 A1 JP 2015533742 A KR 20150125638 A MA 20150435 A1 NZ 706173 A PH 12015500670 A1 RU 2015111415 A TN 2015000113 A1 WO 2014056559 A1	30-04-2015 22-07-2015 16-04-2014 26-11-2015 09-11-2015 30-11-2015 27-11-2015 18-05-2015 10-12-2016 29-06-2016 17-04-2014
EP 2610272	A1	03-07-2013	EP 2610272 A1 WO 2013098138 A1	03-07-2013 04-07-2013
WO 2006065799	A2	22-06-2006	EP 1824669 A2 TW 200635773 A US 2007202285 A1 US 2012207958 A1 US 2016115282 A1 WO 2006065799 A2	29-08-2007 16-10-2006 30-08-2007 16-08-2012 28-04-2016 22-06-2006
WO 2007017360	A1	15-02-2007	AU 2006278060 A1 BR PI0616556 A2 CA 2618174 A1 CN 101243132 A EP 1913076 A1	15-02-2007 21-06-2011 15-02-2007 13-08-2008 23-04-2008

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2016/081635

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
		JP 5127711 B2	23-01-2013
		JP 2009504822 A	05-02-2009
		KR 20080041647 A	13-05-2008
		TW 200710148 A	16-03-2007
		US 2010160540 A1	24-06-2010
		WO 2007017360 A1	15-02-2007
