



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : C08G 65/336, 18/83</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/37533</p> <p>(43) International Publication Date: 29 June 2000 (29.06.00)</p>
<p>(21) International Application Number: PCT/US99/30486</p> <p>(22) International Filing Date: 20 December 1999 (20.12.99)</p> <p>(30) Priority Data: 09/218,573 22 December 1998 (22.12.98) US</p> <p>(71) Applicant: ADCO PRODUCTS, INC. [US/US]; 4401 Page Avenue, Michigan Center, MI 49254 (US).</p> <p>(72) Inventors: WANG, Xiaobin; Apartment 2, 19 Royal Crest Drive, North Andover, MA 01845 (US). BRIDDELL, Brian, J.; 5901 May King Drive, Jackson, MI 49201 (US). KUBISH, Scott; 129 Tower Drive, Saline, MI 48176 (US).</p> <p>(74) Agents: LUNA, Susan, M. et al.; Killworth, Gottman, Hagan & Schaeff, LLP, Suite 500, One Dayton Centre, One South Main Street, Dayton, OH 45402-2023 (US).</p>		<p>(81) Designated States: AU, CA, JP, MX, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: FAST-CURE SILYLATED POLYMER ADHESIVE</p> <p>(57) Abstract</p> <p>The cure-through rate of one-part silylated polymer adhesive/sealant compositions is improved by the addition of a small but effective amount of an alcohol-free hydrophilic solvent. The composition is particularly suitable for packaging in aluminum or aluminum-lined cartridges.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

FAST-CURE SILYLATED POLYMER ADHESIVE

The invention relates to one-part silylated polymer adhesive/sealant compositions, and more particularly to the use of a hydrophilic solvent to improve the cure-through rate of such adhesive/sealant compositions.

5 Compositions containing vulcanizable silicon terminated organic polymers are well known in the art, and are commonly used as adhesives and/or sealants. For example, U.S. Patent No. 3,632,557, incorporated herein by reference, describes room temperature curable silicon terminated organic polymers made by the reaction of an isocyanate terminated polyurethane prepolymer having urethane
10 linkages and an organic silicon compound. Such polymers are commonly referred to as silylated polymers, and find use as adhesives and sealants, particularly in the automobile industry. Other patents relating to silylated polymers include U.S. Patent Nos. 3,979,344; 4,222,925; 4,889,903; 4,894,426; 4,954,598 and 5,097,053, all incorporated herein by reference.

15 It is often desirable to provide such silylated polymer adhesive/sealant compositions in packages suitable for direct application of the product. A popular, efficient and economical type of package is an aluminum or aluminum-lined cartridge. Unfortunately, it has been discovered that such adhesive/sealant compositions often react with the aluminum, and corrode through the sides of such
20 cartridges. Once the composition corrodes through the cartridge and is exposed to moisture in air, the curing process begins, and the adhesive/sealant solidifies before it can be used.

In using such adhesives and/or sealants, there are two important cure rates which need to be considered. The first is the surface cure rate, generally
25 expressed as the tack-free time, that is, the time until the surface cures to the point of not being tacky. Generally, the application of the composition must be completed before such surface curing is complete. Therefore, the shorter the tack-free time, the less time one has to work with the adhesive/sealant. The second important cure rate is the cure-through rate. This is a measure of the time which it
30 takes for the composition to cure through its thickness. The shorter the cure-through time, the sooner the finished product can be used. Therefore, it is often

desirable to speed up the cure through rate of an adhesive/sealant while maintaining or even increasing the tack free time.

The present inventors made the discovery that methanol, which is commonly used in formulations of such adhesive/sealant compositions, reacts with aluminum when in the presence of the catalysts which normally are also included in such compositions. In an attempt to overcome the corrosion problem, the present inventors tested compositions prepared without methanol. Such compositions were found to be non-reactive with aluminum, and therefore to have a much longer shelf life in aluminum cartridges. Unfortunately, it was also found that the cure-through rate of silylated polymer adhesives and/or sealants without methanol was significantly slower than that of such adhesives/sealants with methanol. Increasing the amount of catalysts and using different catalyst systems did not improve the cure-through rate. In some cases, adding additional catalyst or using alternate catalysts was found to decrease the tack-free time significantly, thus making the adhesive/sealant more difficult to handle, but without improving the cure-through rate. Thus, there is a need for a methanol-free silylated polymer adhesive/sealant composition which is non-corrosive to aluminum with at least as fast a cure-through rate as compositions containing methanol.

In accordance with the present invention, it was discovered that the addition of a small amount of one or more hydrophilic solvents to a one-part silylated polymer based adhesive/sealant composition speeds up the cure-through rate of such compositions. It was further discovered that the elimination of methanol solves the corrosion problem when such compositions are packaged in aluminum containers. Therefore, the present invention provides a silylated polymer-based adhesive/sealant composition comprising a small but effective amount of one or more hydrophilic solvents, which composition is substantially free of methanol and other alcohols. Adhesives and/or sealants made in accordance with the present invention are non-reactive with aluminum and have a faster cure-through rate than such compositions without the solvent. For purposes of this application, an effective amount of such a solvent is that amount which speeds up the cure-through rate of an adhesive/sealant composition as compared to the same

adhesive/sealant composition without the solvent. A suitable method for determining the cure-through rate is set forth below.

In addition to avoiding methanol, it is believed that alcohols other than methanol, such as ethanol or propanol, should also be avoided in such
5 compositions. Such alcohols may undesirably react with other components, particularly the silane components, thus adversely affecting the properties or performance of the adhesive/sealant compositions. Such reactions may also result in the formation of methanol as a byproduct. Therefore, the compositions of the present invention desirably are free of methanol and any other alcohols as well.

10 Another embodiment of the invention is a method of accelerating the cure-through rate of a one-part, moisture-curable silylated polymer-based adhesive/sealant composition comprising adding an effective amount of an alcohol-free hydrophilic solvent to the composition.

A further embodiment of the present invention is a packaged

15 adhesive/sealant composition comprising:

- a) an aluminum or aluminum-lined package; and
- b) a one-part, moisture-curable silylated polymer-based adhesive/sealant composition comprising a moisture-curable silylated polymer and an effective amount of a hydrophilic solvent,

20 wherein the composition is sealed within the package, is substantially free of alcohols and is non-reactive with the aluminum of the package.

Although applicants do not wish to be bound by a particular theory of how the invention works, it is believed that when the hydrophilic solvent evaporates from the adhesive/sealant composition it creates channels for moisture to get into
25 the adhesive/sealant and thereby cure the silylated polymer. If there is no hydrophilic solvent in the composition, then the moisture has more difficulty reaching the interior of the uncured material. As a result, although the tack-free time remains the same or even increases, the cure-through time is significantly diminished.

30 Hydrophilic solvents are those which have an affinity with water. However, because the silylated polymer compositions are cured by exposure to water, the

solvents should be as anhydrous as is reasonably possible. Suitable hydrophilic solvents for use in the present invention should be highly volatile, and include those oxygen and/or nitrogen containing organic solvents whose flash points are less than about 45°C (open cup) and whose evaporation rates are at least 1, with
5 n-butyl acetate defined as having an evaporation rate of 1. However, alcohols should not be used in the solvent because of possible undesirable reactions with aluminum in the packaging or with other components of the composition. Suitable hydrophilic solvents include substituted or unsubstituted esters, ketones and amines, provided they are sufficiently volatile and non-reactive with the other
10 components of the compositions. Among the hydrophilic solvents suitable for use in the present invention are esters such as amyl formate, ethyl acetate, isopropyl acetate, n-propyl acetate, ethyl propionate, isobutyl acetate and n-butyl acetate; ketones such as acetone, methyl ethyl ketone, methyl propyl ketone and methyl isobutyl ketone; amines such as isopropylamine, sec-butylamine, n-amylamine,
15 sec-hexylamine, ethylamine, ethylene diamine, propyl imine, acetonitrile, n-butyronitrile and morpholine; mixture of such solvents and mixtures of them with other anhydrous solvents, especially their azeotropes.

The small amount of hydrophilic solvent used in the composition is not critical, but preferably should be as small as possible. Preferably no more than
20 about 10 percent by weight (wt%) is used, more preferably less than about 6 wt%, and most preferably less than about 3 wt%. To obtain the desired cure-through rate acceleration, preferably a minimum of about 0.1 wt% is used, more preferably at least about 0.5 wt%, and most preferably at least about 1 wt%. Thus, the amount of hydrophilic solvent used is desirably in the range of about 0.1 to about
25 10 wt%, preferably from about 0.5 to about 6 wt%, more preferably from about 1 to about 3 wt%. All percentages herein are by weight unless indicated otherwise.

The following test methods were employed in the examples set forth below. Tack-free time was measured in accordance with ASTM C679-87 (Reapproved 1992) entitled "Standard Test Method for Tack-Free Time of Elastomeric
30 Sealants," incorporated herein by reference. As indicated in the ASTM standard, the test consists of lightly touching a surface of a curing sealant with a polyethylene

film at regular intervals until the sealant does not attach itself to the film and the film appears clean when peeled from the surface.

The cure-through rate of adhesive samples is measured by the following procedure. A sample of the test adhesive is prepared and conditioned to 23°C for at least 6 hours. A polyethylene container is provided which is at least 45 mm in diameter and 10 mm in height, and purged with dry nitrogen. The container is filled with the test adhesive, and the top surface leveled with a spatula. The sample is placed in a 23°C, 50% relative humidity (RH) chamber, in which it cures from the top surface down. After 24 hours, the central thickness of the cured disk-like top portion of the sample is measured.

The materials used in the following examples are all commercially available and/or may be prepared by methods well known in the art, as discussed, for example, in some of the references incorporated by reference above.

EXAMPLE 1

15 Preparation of a Silylated Polyurethane Polymer

A typical silylated polyurethane polymer was prepared for use in testing the present invention. The formulation of the silylated polyurethane polymer was as follows:

TABLE 1

20 Raw Material	Amount, g
PPG-2200 (2000 MW polyether diol from ARCO)	1179.58
TDI-80 (toluene diisocyanate)	123.14
Toluene	96.41
METACURE™ T-1 (dibutyltin diacetate from Air Products)	0.58
25 Acetic Acid	0.29
SILQUEST® A-1110 (γ -aminopropyltrimethoxysilane from OSi specialties)	43.03

All of the raw materials except the A-1110 were charged to a clean and dry reactor. The temperature was raised to 60°C and maintained for about 2 hours. The A-

1110 was not added until the NCO percentage dropped to 0.708. The temperature was then cooled down to 37.8°C. The NCO percentage was reduced to zero in about 15 minutes. This completed the formation of the silylated polyurethane polymer.

5

EXAMPLE 2Preparation of a Silylated Polyether Polymer

A typical silylated polyether polymer was prepared for use in testing the present invention. The formulation of the silylated polyether polymer was as follows:

10

TABLE 2

Raw Material	Amount, g
ACCLAIM™ 12200 (12000 MW polyether diol from ARCO)	1348.27
SILQUEST® Y-5187 (γ -isocyanatopropyltrimethoxysilane from OSi Specialties)	123.14
15 METACURE™ T-1 (dibutyltin diacetate from Air Products)	0.58
Acetic Acid	0.29

All of the raw materials were charged to a clean and dry reactor. The temperature was raised to 60°C and maintained for about 3 hours until all hydroxyl groups were consumed. This completed the formation of the silylated polyether polymer.

20

EXAMPLE 3Silylated Polyurethane Adhesive/Sealant Compositions

This example tests the tack-free times and cure-through rates of adhesive/sealant compositions made with the silylated polyurethane polymer of Example 1 with and without a hydrophilic solvent, in this case n-propyl acetate, in
25 accordance with the present invention. These samples were all prepared without methanol or any other alcohol. Test samples were made as follows:

TABLE 3

Ingredient	Amount, g			
	A	B	C	D
Polymer of Example 1	633.6	633.6	633.6	633.6
5 REGAL® 300R (carbon black from Cabot Corp.)	300.0	300.0	300.0	300.0
POLYCAT® DBU (1,8-diaza-bicyclo (5,4,0) undecene-7 from Air Products)	1.22	2.44	1.22	1.22
METACURE™ T-1	1.22	2.44	1.22	1.22
10 SILQUEST® A-1120, N- <i>beta</i> -(aminoethyl)- <i>gamma</i> -aminopropyltrimethoxysilane from OSi	4.00	4.00	4.00	0.00
SILQUEST® Y-5187	0.00	0.00	0.00	4.00
Toluene	60.00	57.56	30.00	30.00
n-Propyl acetate	0.00	0.00	30.00	30.00

15 Tack-free times and cure-through rates were tested in accordance with the above-described procedures. The results were as follows:

TABLE 4

	A	B	C	D
Tack-free time @23°C/50% RH, min.	15	9	10	27
20 Cure-through rate @23°C/50% RH in 24 h, mm	4.8	4.9	6.0	6.0

Sample A is a comparative example prepared without methanol or any other alcohol, and also without any hydrophilic solvent. Sample B is essentially the same composition, but with twice the dosage of the catalysts (POLYCAT® DBU and METACURE™ T-1). The results in Table 4 show that the additional catalyst
 25 undesirably reduced the tack-free time without any significant effect on the cure-through rate. Sample C, which included hydrophilic solvent in accordance with the

present invention, had the same amount of catalyst as Sample A. Yet, the cure-through rate was significantly improved over the rates of Samples A and B. Sample D is another example using a hydrophilic solvent in accordance with the present invention. In this case, Y-5187 cyanato-silane was used instead of A-1120 amino-silane. The cure-through rate was the same as that of Sample C, although the tack-free time was significantly increased. This shows that compositions can be made in accordance with the present invention which not only increase the cure-through rate, but also increase the tack-free time. That is, while the total cure-through time is shortened, the tack-free time, during which the adhesive/sealant is workable, is increased. This data demonstrates that in comparison to other silanes, amino-silanes, such as SILQUEST® A-1120 or A-1110, shorten tack-free time without improving the total cure-through rate.

EXAMPLE 4

Silylated Polyether Adhesive/Sealant Compositions

Samples of silylated polyether adhesives were formulated as follows:

TABLE 5

Ingredient	Amount, g	
	E	F
Polymer of Example 2	673.6	673.6
REGAL® 300R, carbon black	300.0	300.0
POLYCAT® DBU, catalyst	1.22	1.22
METACURE™ T-1	1.22	1.22
SILQUEST® Y-5187, silane	4.00	4.00
Toluene	20.00	0.00
n-Propyl acetate	0.00	20.00

Tack-free times and cure through rates were tested as in the previous example. The results were as follows:

TABLE 6

	E	F
Tack-free time @23°C/50% RH, min	24	23
Cure-through rate @23°C/50% RH in 24 h, mm	5.9	6.9

In this Example, Sample E was prepared with toluene, which is not a hydrophilic solvent, and Sample F was prepared with n-propyl acetate, which is a hydrophilic solvent in accordance with the present invention. The use of the hydrophilic solvent in Sample F significantly improved the cure-through rate without significantly affecting the tack-free time.

EXAMPLE 5

10

MS Polymer Sealants

Sealant compositions were prepared from Kaneka MS Polymers, which are described by the manufacturer as silyl-terminated polyethers for non-isocyanate and moisture-curable polymer systems. Sample G was prepared in accordance with the manufacturer's recommendations. Sample H is identical to Sample G, except the amount of catalyst (NEOSTANN™ U220 catalyst from Nitto Kasei Co) was doubled. Sample I is the same as Sample G, except 45.9 g of a hydrophilic solvent (n-propyl acetate) was added in accordance with the present invention.

TABLE 7

	Ingredient	Amount, g		
		G	H	I
	S203H, MS polymer from Kaneka Corp.	300.0	300.0	300.0
	S303H, MS polymer from Kaneka Corp.	200.0	200.0	200.0
5	DUP, plasticizer	275.0	260.0	229.0
	Gama-Sperse® CS-11, stearate surface modified calcium carbonate from Georgia Marble Corp.	600.0	600.0	600.0
	TiO ₂	100.0	100.0	100.0
10	TINUVIN® 327, 2-(5-chloro-2H-benzotriazole-2-yl)-4,6-bis (1,1-dimethylethyl)-phenol from Ciba Geigy Co.	10.0	10.0	10.0
	TINUVIN® 770, decanedioic acid, bis(2,2,6,6-tetramethyl-4-piperidinyl)ester from Ciba Geigy Co.	10.0	10.0	10.0
15	SILQUEST® A-171, vinyltrimethoxysilane from OSi	10.0	10.0	10.0
	SILQUEST® A-1120, N-beta-(aminoethyl)-gamma-aminopropyltrimethoxysilane from OSi	15.0	15.0	15.0
	NEOSTANN™ U220 catalyst from Nitto Kasei Co.	10.0	20.0	10.0
	n-Propyl acetate	0.0	0.0	45.9

20 Tack-free times and cure-through rates were tested as in the previous example. The results were as follows:

TABLE 8

	G	H	I
Tack-free time @23°C/50% RH, min.	24	19	23
Cure-through rate @23°C/50% RH in 24 h, mm	3.8	3.8	4.2

25 These results show that doubling the amount of catalyst in Sample H reduced the tack-free time, but had no effect on the cure-through rate. On the

other hand, adding hydrophilic solvent in Sample I increased the cure-through rate about 10% without significantly reducing the tack-free time.

Having thus described a few particular embodiments of the invention, various alterations, modifications, and improvements will readily occur to those
5 skilled in the art. Such alterations, modifications and improvements as are made obvious by this disclosure are intended to be part of this description though not expressly stated herein, and are intended to be within the spirit and scope of the invention. The foregoing description is by way of example only, and not limiting. The invention is limited only as defined in the following claims and equivalents
10 thereto.

CLAIMS

1. An adhesive/sealant composition comprising:
 - a) a moisture-curable silylated polymer; and
 - 5 b) an effective amount of a hydrophilic solvent,wherein said composition is substantially free of alcohols and non-reactive with aluminum.

2. The composition of claim 1 wherein said silylated polymer is selected from the group consisting of silylated polyurethanes, silylated polyethers, and
10 combinations thereof.

3. The composition of claim 1 wherein said hydrophilic solvent is selected from the group consisting of oxygen and/or nitrogen containing organic solvents and mixtures thereof.

4. The composition of claim 3 wherein said hydrophilic solvent has a
15 flash point of less than about 45°C (open cup) and an evaporation rate of at least 1, with n-butyl acetate defined as having an evaporation rate of 1.

5. The composition of claim 4 wherein said hydrophilic solvent comprises one or more solvents selected from the group consisting of esters, ketones, amines, mixtures of such solvents and mixtures of such solvents with
20 other solvents.

6. The composition of claim 5 wherein said hydrophilic solvent comprises one or more esters selected from the group consisting of amyl formate, ethyl acetate, isopropyl acetate, n-propyl acetate, ethyl propionate, isobutyl acetate and n-butyl acetate.

7. The composition of claim 6 wherein said hydrophilic solvent comprises n-propyl acetate.

8. The composition of claim 1 wherein said hydrophilic solvent is present in an amount of about 0.1 to about 10 weight percent, based on the total
5 weight of the composition.

9. The composition of claim 8 wherein said hydrophilic solvent is present in an amount of about 0.5 to about 6 weight percent.

10. The composition of claim 9 wherein said hydrophilic solvent is present in an amount of about 1 to about 3 weight percent.

10 11. A method of accelerating the cure-through rate of a one-part, moisture-curable silylated polymer-based adhesive/sealant composition comprising adding an effective amount of an alcohol-free hydrophilic solvent to said composition.

12. The method of claim 11 wherein said silylated polymer is selected
15 from the group consisting of silylated polyurethanes, silylated polyethers, and combinations thereof.

13. The method of claim 11 wherein said hydrophilic solvent is selected from the group consisting of oxygen and/or nitrogen containing organic solvents and mixtures thereof, and has a flash point of less than about 45°C (open cup) and
20 an evaporation rate of at least 1, with n-butyl acetate defined as having an evaporation rate of 1.

14. The method of claim 13 wherein said hydrophilic solvent comprises one or more solvents selected from the group consisting of esters, ketones, amines, mixtures of such solvents and mixtures of such solvents with other solvents.

15. The method of claim 14 wherein said hydrophilic solvent comprises one or more esters selected from the group consisting of amyl formate, ethyl acetate, isopropyl acetate, n-propyl acetate, ethyl propionate, isobutyl acetate and n-butyl acetate.

5 16. The method of claim 15 wherein said hydrophilic solvent comprises n-propyl acetate.

17. The method of claim 11 wherein said hydrophilic solvent is present in an amount of about 0.1 to about 10 weight percent, based on the total weight of the composition.

10 18. The method of claim 17 wherein said hydrophilic solvent is present in an amount of about 0.5 to about 6 weight percent.

19. The method of claim 18 wherein said hydrophilic solvent is present in an amount of about 1 to about 3 weight percent.

15 20. The adhesive/sealant composition of claim 1 provided in an aluminum or aluminum-lined package, wherein said composition is sealed within said package.

20 21. The adhesive/sealant composition of claim 20 wherein said package is an aluminum or aluminum-lined cartridge suitable for direct application of said composition.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/30486

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 C08G65/336 C08G18/83		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols) IPC 7 C08G C09D C09J		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 94 13723 A (MINNESOTA MINING & MFG) 23 June 1994 (1994-06-23) page 36, line 21 - line 36 page 47, line 6 - line 25; example ALL ---	1-19
X	PATENT ABSTRACTS OF JAPAN vol. 018, no. 291 (C-1208), 3 June 1994 (1994-06-03) & JP 06 057121 A (SEKISUI CHEM CO LTD), 1 March 1994 (1994-03-01) abstract ---	1-3, 8-12, 17-19
X	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 03, 27 February 1998 (1998-02-27) & JP 09 302331 A (SEKISUI CHEM CO LTD), 25 November 1997 (1997-11-25) abstract ---	1-3, 8-12, 17-19
-/--		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.		
<input checked="" type="checkbox"/> Patent family members are listed in annex.		
° Special categories of cited documents :		
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	
"E" earlier document but published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.	
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family	
"P" document published prior to the international filing date but later than the priority date claimed		
Date of the actual completion of the international search <div style="text-align: center; font-weight: bold;">17 March 2000</div>	Date of mailing of the international search report <div style="text-align: center; font-weight: bold;">29/03/2000</div>	
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer <div style="text-align: center; font-weight: bold;">Dury, O</div>	

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/30486

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 018, no. 222 (C-1193), 21 April 1994 (1994-04-21) & JP 06 016920 A (SEKISUI CHEM CO LTD), 25 January 1994 (1994-01-25) abstract -----	1-3, 8-12, 17-19
X	US 4 302 571 A (ARAI MASATOSHI ET AL) 24 November 1981 (1981-11-24) column 8, line 51-61; example ALL -----	1-3, 8-12, 17-21
X	EP 0 228 087 A (TORAY SILICONE CO) 8 July 1987 (1987-07-08) page 4, line 16 - line 18; claims 1-6 -----	1-5, 8-14, 17-19
A	US 4 562 237 A (OKUNO EIICHI ET AL) 31 December 1985 (1985-12-31) -----	1-21

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/30486

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9413723 A	23-06-1994	US 5354808 A	11-10-1994
		AU 682165 B	25-09-1997
		AU 5741394 A	04-07-1994
		DE 69323901 D	15-04-1999
		DE 69323901 T	12-08-1999
		EP 0677072 A	18-10-1995
		ES 2128549 T	16-05-1999
		JP 8504230 T	07-05-1996
		US 5554686 A	10-09-1996
-----	-----	-----	-----
JP 06057121 A	01-03-1994	JP 2809563 B	08-10-1998
-----	-----	-----	-----
JP 09302331 A	25-11-1997	NONE	
-----	-----	-----	-----
JP 06016920 A	25-01-1994	NONE	
-----	-----	-----	-----
US 4302571 A	24-11-1981	JP 55123648 A	24-09-1980
		DE 3009936 A	02-10-1980
-----	-----	-----	-----
EP 0228087 A	08-07-1987	JP 1870236 C	06-09-1994
		JP 5082860 B	22-11-1993
		JP 62153341 A	08-07-1987
		CA 1296832 A	03-03-1992
		DE 3682178 A	28-11-1991
		ES 2004008 A	01-12-1988
		US 4683250 A	28-07-1987
-----	-----	-----	-----
US 4562237 A	31-12-1985	JP 59024771 A	08-02-1984
-----	-----	-----	-----