



(86) Date de dépôt PCT/PCT Filing Date: 2005/03/15
(87) Date publication PCT/PCT Publication Date: 2005/11/03
(85) Entrée phase nationale/National Entry: 2006/10/05
(86) N° demande PCT/PCT Application No.: US 2005/008594
(87) N° publication PCT/PCT Publication No.: 2005/102926
(30) Priorité/Priority: 2004/04/08 (US60/560,532)

(51) Cl.Int./Int.Cl. *C01B 33/00* (2006.01)
(71) Demandeur/Applicant:
DOW CORNING CORPORATION, US
(72) Inventeurs/Inventors:
DOSAJ, VISHU DUTT, US;
KROUPA, MICHAEL GEORGE, US;
MARION, PAUL JACQUES, US
(74) Agent: BERESKIN & PARR

(54) Titre : PROCEDE DE SELECTION D'UN SILICIUM PRESENTANT UN RENDEMENT AMELIORE
(54) Title: METHOD OF SELECTING SILICON HAVING IMPROVED PERFORMANCE

(57) Abrégé/Abstract:
Published without an Abstract

LUBRICANTS FOR METALLURGICAL POWDER COMPOSITIONS

Field of the invention

This invention relates to lubricants for metallurgical powder (PM) compositions. Specifically, the invention concerns iron or iron-based powder compositions including liquid lubricants.

Background of the invention

In industry, the use of metal products manufactured by compacting and sintering metal-powder compositions is becoming increasingly widespread. A number of different products of varying shape and thickness are being produced, and different quality requirements are placed on these products depending on their final use. In order to meet the different requirements the powder metallurgy industry has developed a wide variety of iron and iron-based powder compositions.

One processing technique for producing the parts from these powder compositions is to charge the powder composition into a die cavity and compact the composition under high pressure. The resultant green part is then removed from the die cavity. To avoid excessive wear on the die cavity, lubricants are commonly used during the compaction process. Lubrication is generally accomplished by blending a solid, particular lubricant powder with the iron-based powder (internal lubrication) or by spraying a liquid dispersion or solution of the lubricant onto the die cavity surface (external lubrication). In some cases, both lubrication techniques are utilized.

Lubrication by means of blending a solid lubricant into the iron-based powder composition is widely used and new solid lubricants are developed continuously. These solid lubricants generally have a density of about 1-2 g/cm³, which is very low in comparison with the density of the iron-based powder, which is about 7-8 g/cm³. Additionally, in practice the solid lubricants have to be used in amounts of at least 0.6 % by weight of the powder composition. As a consequence the inclusion of these less dense lubricants in the composition lowers the green density of the compacted part.

Liquid lubricants in combination with iron powders for the preparation of compacted parts are disclosed in the US patent 3 728 110. According to this patent it is necessary to use the lubri-

METHOD OF SELECTING SILICON HAVING IMPROVED PERFORMANCE

FIELD OF THE INVENTION

5 [0001] The invention is directed to a method of selecting individual batches of silicon that are predictive of batches that would be easy to separate from slag, and therefore have low levels of detrimental oxide contamination. This results in improved silicon performance in the Rochow direct process. In particular, the method herein takes into account the interactions of refining temperature, casting temperature, aluminum levels, and calcium levels in silicon, in
0 predicting the slag properties, as well as the ease of slag separation from silicon. This is an improvement on prior solutions that have either considered these factors independently, or relied on the measurement of oxide levels in representative samples of crushed lots.

BACKGROUND OF THE INVENTION

5 [0002] Organohalosilanes, particularly dialkyldichlorosilanes, are important intermediates in the silicone industry. The organohalosilanes are typically hydrolyzed and condensed to form polyorganosiloxanes that can then be processed to form, for example, silicone fluids, elastomers, sealants, adhesives, and resins. The predominant commercial process for preparing these organohalosilane intermediates is one commonly referred to as the “direct
10 process” as originally described by Rochow in US Patent 2,380,995 (August 7, 1945) and US Patent 2,380,996 (August 7, 1945), which are incorporated herein by reference.

[0003] Because of the high volume of organohalosilanes used in the silicone industry, considerable effort has been devoted to optimizing the conversion of the silicon metalloid to the diorganodihalosilane, particularly to dimethyldichlorosilane. It is known in the silicone
15 industry that different lots of chemical grade silicon metalloid react differently in the direct process. To attempt to control the variability of reactivity between lots of chemical grade silicon metalloid in the direct process, manufacturers of organohalosilanes have set strict controls on the acceptable types and levels of contaminants present in the silicon. For example, reference may be had to Volume 376 of the Journal of Organometallic Chemistry,
20 by Michael P. Clarke, Pages 165-222, November 7, 1989, entitled *The Direct Synthesis of Methylchlorosilanes*, which provides a comprehensive review of the direct process for synthesis of methylchlorosilanes and the effects of contaminants on the process.

[0004] US Patent 5,427,952 (June 27, 1995) teaches a method for analyzing chemical grade silicon intended for use in the direct process for the presence of nonmetallic contaminants, including oxides and carbides of calcium, aluminum, and silicon. It is believed that a significant cause of the lot-to-lot variability of chemical grade silicon metalloid in the direct process is the presence of these nonmetallic contaminants. The method involves the separation of the contaminants by an alloying process and subsequent analysis of the contaminants for chemical composition.

[0005] US Patent 5,973,177 (October 26, 1999), hereinafter the '177 patent, teaches a method for analyzing chemical grade silicon metalloid for oxide impurities detrimental to the production of diorganodihalosilanes in the direct process by heating a sample under controlled conditions to a temperature greater than about 2300 °C in the presence of a carbon source such that a reduction product consisting of carbon monoxide and carbon dioxide which forms at above a temperature of about 1900 °C is predictive of chemical grade silicon metalloid performance in the direct process. In particular, the '177 patent teaches that the smaller the amount of reduction product formed above a temperature of about 1900 °C, the greater is the specificity of the chemical grade silicon metalloid for the production yield of diorganodihalosilanes.

[0006] It has been found herein that the amount of detrimental oxide impurities present in chemical grade silicon metalloid can be predicted based on standard elemental analysis of the silicon metalloid and operating conditions of the refining process.

SUMMARY OF THE INVENTION

[0007] The invention relates to a method of selecting silicon metalloid having improved performance in the direct process for making organohalosilanes, in which an organohalide is reacted with silicon metalloid in the presence of a copper catalyst at an elevated temperature. The method is carried out by (A) measuring the temperature of each batch of silicon metalloid during both the refining and the casting of the silicon metalloid; (B) measuring the elemental impurity levels in each batch of the silicon metalloid after refining of the silicon metalloid; (C) predicting the properties of the slag phase produced during refining of the silicon metalloid based on equilibrium calculations using the elemental impurity levels and the measured temperatures of each batch of silicon metalloid; and (D) selecting a silicon metalloid for use in the direct process for making organohalosilanes based upon the predicted

slag properties; such that the slag density, the viscosity, and the melting point of the slag are within acceptable and predetermined ranges for each individual batch.

[0008] In one method, (i) the predicted melting point of the slag is lower than the temperature during refining of the batch of silicon metalloid; (ii) the predicted slag density is at least 0.02 gram per cm³ higher than the density of the batch of silicon metalloid at the casting temperature, alternatively at least 0.04 gram per cm³ higher than the density of the batch of silicon metalloid at the casting temperature; (iii) the predicted slag viscosity is at least 35 poise at the casting temperature, alternatively at least 40 poise at the casting temperature, and alternatively at least 50 poise at the casting temperature.

[0009] These and other features of the invention will become apparent from a consideration of the detailed description.

DETAILED DESCRIPTION OF THE INVENTION

[0010] The method according to the present invention relates to the selection of chemical grade silicon metalloid having improved performance in the direct process for making organohalosilanes. It is generally carried out in four steps. In Step (A), the temperature of a batch of silicon metalloid is measured during both refining and casting. In Step (B), the elemental impurity levels in the batch of silicon metalloid is measured after refining. In Step (C), the properties of the slag phase are predicted based on equilibrium calculations using the elemental impurity levels and measured temperatures for the batch. In Step (D), a silicon metalloid for use in the direct process for making organohalosilanes is selected based upon the predicted slag properties such that the slag density, viscosity, and melting point of the slag are within acceptable and predetermined ranges for the individual batch.

[0011] As used herein, the phrase *chemical grade silicon metalloid or chemical grade silicon* for use in the direct process for making organohalosilanes, is intended to mean any silicon metalloid containing at least about 98 percent but less than 100 percent by weight of silicon metalloid and containing oxides of aluminum, calcium, and silicon as impurities.

[0012] The phrase *direct process* for making organohalosilanes as used herein is intended to mean a process wherein an organohalide is reacted with silicon metalloid in the presence of a copper catalyst at an elevated temperature (e.g., 200 to 700 C) to form a mixture containing various organohalosilanes.

[0013] The term *slag* as used herein, is intended to mean the oxides of aluminum, calcium, and silicon, which are typically separated from chemical grade silicon metalloid during its refining and casting, some of which may remain in the chemical grade silicon metalloid as impurities. The term *detrimental oxide impurities* as used herein, is intended to mean the
5 oxides of aluminum and calcium which remain in the silicon metalloid as impurities.

[0014] The term *silicon metalloid*, as used herein, is synonymous with silicon or silicon metal. The term *batches*, as used herein, is intended to mean individual volumes of molten silicon refined in refining vessels such as refractory lined ladles. The term *lots*, as used
0 herein, is intended to mean groups of batches that are crushed and packaged together. The sizes of lots vary depending on specific customer or supplier needs and shipping methods.

[0015] As noted, equilibrium calculations are used herein to predict the slag composition based on measured silicon impurity levels and temperatures. These calculations are based on equilibrium data which allows slag composition to be related to slag properties such as density, viscosity, and melting point. These calculations and equilibrium data are well known
5 to those skilled in the art.

[0016] Chemical grade silicon metalloid is commonly selected based primarily on independent specification ranges for various impurity levels such as aluminum and calcium. However, it has been determined herein that these commonly used methods of selecting chemical grade silicon alone are insufficient for accurately predicting chemical grade silicon
10 performance in the direct process. It has also been determined herein that interactions between aluminum levels, calcium levels, refining temperature, and casting temperature play strong roles in predicting chemical grade silicon performance in the direct process. In the present invention, these interactions are taken into account in the prediction of slag properties.

[0017] It is believed that the separation effectiveness of chemical grade silicon from slag is strongly influenced by the physical properties of the slag for each batch of refined chemical grade silicon. It should be understood, however, that it is very difficult to measure the physical properties of the slag directly. The method according to the present invention provides one skilled in the art with capability to estimate slag physical properties from easily
15 obtainable measurements and, thereby, predict slag separation for each batch of refined
30 chemical grade silicon. The slag properties of particular interest are viscosity, melting point,

and density relative to the density of molten chemical grade silicon. The slag physical properties for each batch are predicted using equilibrium calculations.

[0018] As noted above, the method according to the invention generally includes four Steps (A), (B), (C), and (D). In Step (A), the refining and casting temperatures of each batch of chemical grade silicon are measured using methods typical in the industry, such as the use of expendable temperature sensors. In step (B), the elemental impurities in each batch of refined chemical grade silicon are measured. These include, for example, the levels of aluminum and calcium which are present. While the sampling method and the analytical method used for measuring the impurity levels is not a critical feature of the present invention, the sample analyzed should be representative of the batch of chemical grade silicon being considered. Accordingly, various sampling methods can be used such as expendable samplers or graphite cup samplers; and various analysis methods can be used such as X-ray fluorescence or plasma emission spectroscopy.

[0019] In step (C), the refining temperature, the casting temperature, and the chemical grade silicon elemental impurity levels (as measured in Steps (A) and (B)) are used to estimate the slag physical properties for each batch of chemical grade silicon. This estimation is accomplished for each batch using equilibrium calculations. The slag properties of particular interest are its melting point, viscosity, and density. In step (D), the predicted slag properties as determined in step (C) are used as the basis for selecting individual batches of chemical grade silicon for use in the direct process for making organohalosilanes, especially organohalosilanes such as dimethyldichlorosilane (CH₃)₂SiCl₂.

[0020] Thus, it has been unexpectedly discovered that the amount of detrimental oxide contaminants can be estimated based on the slag properties predicted for each chemical grade silicon batch, using equilibrium calculations. The estimated amount of detrimental oxide contaminants can then be used to predict the yield of chemical grade silicon for the production of diorganodihalosilanes in the direct process. It has also been unexpectedly discovered (i) that for optimum chemical grade silicon performance, the predicted melting point of the slag should be lower than the temperature during refining of the batch of chemical grade silicon; (ii) that the predicted slag density should be sufficiently different than the density of the batch of chemical grade silicon at the casting temperature; and (iii) that the predicted slag viscosity should be sufficiently large at the casting temperature. It is believed that these features (i) to (iii) are often necessary to allow for effective separation of the

chemical grade silicon from the slag. Examples of this type of data include (i) the predicted melting point of the slag is lower than the temperature during refining of the batch of silicon metalloid; (ii) the predicted slag density is at least 0.02 gram per cm³ higher than the density of the batch of silicon metalloid at the casting temperature, alternatively at least 0.04 gram
5 per cm³ higher than the density of the batch of silicon metalloid at the casting temperature; (iii) the predicted slag viscosity is at least 35 poise at the casting temperature, alternatively at least 40 poise at the casting temperature, and alternatively at least 50 poise at the casting temperature.

[0021] Thus, it is now possible to screen different shipments or lots of chemical grade
0 silicon, and to choose and/or select those lots or shipments having more or less yield during diorganodihalosilane production as may be required by commercial demands. The method herein is especially suited for selecting chemical grade silicon for use in the direct process, where one of the preferred products is dimethyldichlorosilane.

[0022] The method can be used during production of silicon. In this regard, silicon is
5 conventionally produced by the carbothermal reduction of quartz (SiO₂) in an electric arc furnace. The reducing agents are typically coal, charcoal, or coke, and the overall reduction reaction is represented by the equation: $\text{SiO}_2 + 2\text{C} \rightarrow \text{Si} + 2\text{CO}$. During its production, the silicon can be refined by tapping the molten silicon from the furnace into a refining vessel, typically a refractory lined ladle, and subsequently refining it in the ladle. Refining of the
10 silicon is generally conducted on the liquid, i.e., molten silicon, by known oxidation or chlorination techniques. The detrimental oxide levels can be controlled by controlling the refining and casting temperatures and elemental impurity levels in each batch of refined silicon at levels that will result in a slag phase that is easy to separate from the silicon produced, namely that the slag properties, particularly melting point, viscosity, and density
15 are within appropriate ranges. Refining and casting temperatures can be controlled by the addition of solidified silicon or adjusting refining gas flow rates and composition. The refining conditions, such as refining gas flow rates, composition, and refining time, can be adjusted to result in elemental impurity levels in each batch of refined silicon that are within the target ranges.

[0023] The following examples are set forth in order to illustrate the invention in more
20 detail. These examples are not intended to limit the scope of the claims herein.

EXAMPLES

[0024] A number of lots of chemical grade silicon (CGS) were evaluated by the method according to the invention, and the results were correlated with the amount of detrimental oxide contaminants. For each batch of CGS within a specific lot, the slag properties at the time of production were predicted using the present method. The slag properties of each batch in a given lot were then used to calculate the percentage of silicon within acceptable ranges of slag properties for that lot. The slag properties that were evaluated were (i) the predicted slag melting point relative to the refining temperature for each chemical grade silicon batch, (ii) the predicted slag density relative to the chemical grade silicon density at the casting temperature for each batch of chemical grade silicon, and (iii) the predicted slag viscosity at the casting temperature for each batch of chemical grade silicon. The content of the detrimental oxide contaminants was measured for each lot according to the method described in the '177 patent, i.e., carrying out Steps A and B, which is considered incorporated herein by reference.

[0025] The results are summarized in the following Tables 1-4, and illustrate the correlation between the predicted slag properties of each batch of chemical grade silicon and the measured amount of the detrimental oxide contaminants. In particular, the results with respect to predicted slag melting point are summarized in Table 1, and illustrate the correlation between the predicted slag melting point and the amount of detrimental oxide contaminants in the chemical grade silicon.

Table 1 - Correlation of Predicted Slag Melting Point With Detrimental Oxide Contaminants in Chemical Grade Silicon

Lots	Percentage of silicon in lots outside of acceptable range.	Weight % Oxygen
A1	0.2	0.088
A2	15.1	0.111

[0026] The results with respect to the predicted slag density are summarized in Table 2, and illustrate the correlation between the predicted slag density and the amount of detrimental oxide contaminants in the silicon.

Table 2 - Correlation of Predicted Slag Density With Detrimental Oxide Contaminants in Chemical Grade Silicon

Lots	Percentage of Silicon in Lots Outside of Acceptable Range	Weight % Oxygen
B1	0.0	0.113
B2	2.5	0.139

5 [0027] The results with respect to the predicted viscosity are summarized in Table 3, and illustrate the correlation between the predicted slag viscosity and the amount of detrimental oxide contaminants in the silicon.

0 *Table 3 - Correlation of the Predicted Slag Viscosity With Detrimental Oxide Contaminants in Chemical Grade Silicon*

Lots	Percentage of Silicon in Lots Outside of Acceptable Range	Weight % Oxygen
C1	19.9	0.1097
C2	41.2	0.1416

5 [0028] The results with respect to the combined impact of slag melting point, slag density, and the slag viscosity are summarized in Table 4, and illustrate the correlation between the predicted slag properties and the amount of detrimental oxide contaminants in the silicon.

Table 4 Correlation of Predicted Slag Melting Point, Density, and Viscosity With Detrimental Oxide Contaminants in Chemical Grade Silicon

Lots	Percentage of Silicon in Lots Outside of Acceptable Range for Slag Melting Point	Percentage of Silicon in Lots Outside of Acceptable Range for Slag Density	Percentage of Silicon in Lots Outside of Acceptable Range for Slag Viscosity	Weight % Oxygen
D1	0.3	0.0	3.7	0.080
D2	3.4	6.7	37.4	0.153

10 [0029] Other variations may be made in compounds, compositions, and methods described herein without departing from the essential features of the invention. The embodiments of the invention specifically illustrated herein are exemplary only and not intended as limitations on their scope except as defined in the appended claims.

WE CLAIM:

1. A method of selecting chemical grade silicon metalloid having improved performance in
5 the direct process for making organohalosilanes, in which an organohalide is reacted with
silicon metalloid in the presence of a copper catalyst at an elevated temperature, the method
comprising:
(A) measuring the temperature of a batch of silicon metalloid during both the refining and the
casting of the silicon metalloid; (B) measuring the elemental impurity levels in the batch of
0 the silicon metalloid; (C) predicting the properties of slag produced during refining of the
silicon metalloid based on equilibrium calculations using the elemental impurity levels and
the measured temperatures of the batch of silicon metalloid; and (D) selecting a chemical
grade silicon metalloid for use in the direct process for making organohalosilanes based upon
the predicted slag properties; such that the slag density, the viscosity, and the melting point of
5 the slag are within acceptable and predetermined ranges for the batch.
2. A method according to Claim 1 in which the organohalosilanes include
dimethyldichlorosilane and the chemical grade silicon metalloid is selected to favor the
production yield of dimethyldichlorosilane.
10
3. A method according to Claim 1 in which the predicted melting point of the slag is lower
than the temperature during refining of the batch of chemical grade silicon.
4. A method according to Claim 1 in which the predicted slag density is at least 0.02 gram per
25 cm^3 higher than the density of the batch of chemical grade silicon at the casting temperature.
5. A method according to Claim 1 in which the predicted slag density is at least 0.04 gram per
 cm^3 higher than the density of the batch of chemical grade silicon at the casting temperature.
- 30 6. A method according to Claim 1 in which the predicted slag viscosity is at least 35 poise at
the casting temperature.

7. A method according to Claim 1 in which the predicted slag viscosity is at least 40 poise at the casting temperature.

5 8. A method according to Claim 1 in which the predicted slag viscosity is at least 50 poise at the casting temperature.

9. A method according to Claim 1 in which (i) the predicted melting point of the slag is lower than the temperature during refining of the batch of chemical grade silicon; (ii) the predicted slag density is at least 0.02 gram per cm³ higher than the density of the batch of chemical
0 grade silicon at the casting temperature; and (iii) the predicted slag viscosity is at least 35 poise at the casting temperature.

10. A method of production of silicon, in which quartz (SiO₂) is carbothermally reduced in an electric arc furnace, refined, and cast, the method comprising
5 (A) controlling the temperature of silicon during both the refining and the casting of the silicon; (B) controlling the elemental impurity levels in the silicon after refining of the silicon;
(C) predicting the properties of slag produced during refining of the silicon based on equilibrium calculations, using the elemental impurity levels and the measured temperature of
0 the silicon; and (D) selecting the silicon for use in the direct process based upon the predicted slag properties; such that the slag density, the slag viscosity, and the melting point of the slag are within acceptable and predetermined ranges.

11. A method according to Claim 10 in which the predicted melting point of the slag is lower
5 than the temperature during refining of the batch of chemical grade silicon.

12. A method according to Claim 10 in which the predicted slag density is more than 0.02 gram per cm³ higher than the density of the batch of chemical grade silicon at the casting temperature.

0

13. A method according to Claim 10 in which the predicted slag density is more than 0.04 gram per cm³ higher than the density of the batch of chemical grade silicon at the casting temperature.
- 5 14. A method according to Claim 10 in which the predicted slag viscosity is at least 35 poise at the casting temperature.
15. A method according to Claim 10 in which the predicted slag viscosity is at least 40 poise at the casting temperature.
- 10 16. A method according to Claim 10 in which the predicted slag viscosity is at least 50 poise at the casting temperature.
- 5 17. A method according to Claim 10 in which (i) the predicted melting point of the slag is lower than the temperature during refining of the silicon; (ii) the predicted slag density is at least 0.02 gram per cm³ higher than the density of silicon at the casting temperature; and (iii) the predicted slag viscosity is at least 35 poise at the casting temperature.