


INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C02F 1/28, 1/76	A1	(11) International Publication Number: WO 94/16998 (43) International Publication Date: 4 August 1994 (04.08.94)
(21) International Application Number: PCT/US94/00522 (22) International Filing Date: 20 January 1994 (20.01.94) (30) Priority Data: 08/007,146 21 January 1993 (21.01.93) US (71) Applicant: CALGON CARBON CORPORATION [US/US]; 500 Calgon Carbon Drive, Pittsburgh, PA 15205 (US). (72) Inventors: CARRUBBA, Robert, V.; 2217 Ben Franklin Drive, Pittsburgh, PA 15237 (US). HAYDEN, Richard, A.; 348 Lee Avenue, Pittsburgh, PA 15237 (US). MATVIYA, Thomas, M.; 1000 Westpointe Drive, Pittsburgh, PA 15205 (US). (74) Agent: WETTACH, Thomas, C.; Cindrich & Titus, Four Gateway Center, 20th floor, Pittsburgh, PA 15222 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: METHOD FOR REMOVING CHLORAMINE WITH CATALYTIC CARBON

**(57) Abstract**

An improved process is provided for the removal of chloramines from gas or liquid media by contacting said media with a catalytically-active carbonaceous char. The improvement is provided by the use of a carbonaceous char capable of rapidly decomposing hydrogen peroxide in aqueous solutions.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

TITLE**METHOD FOR REMOVING CHLORAMINE WITH CATALYTIC CARBON****FIELD OF THE INVENTION**

5 The present invention relates to the use of a catalytically active carbonaceous char for the removal of chloramines from gas or liquid streams.

BACKGROUND OF THE INVENTION

Chloramines in low concentrations arise from the disinfection of drinking water sources. To improve the taste and odor of the water and to remove the inherently toxic chloramines, the water is typically contacted with activated carbon. The ability of carbonaceous materials, such as activated carbon, to remove chloramines from aqueous streams is generally well known. It is also known that improvements in monochloramine removal can be achieved by reducing the mean particle diameter of the carbon and increasing the empty bed contact time. In some applications, such as in kidney dialysis units, high rates of monochloramine removal are particularly important. Although parameters such as contact time and mean particle diameter are known to affect chloramine removal efficiencies, removal performance is not well understood nor particularly effective.

Accordingly, it is the object of the present invention to provide a method of enhanced chloramine removal. It is a further object of the invention to provide a carbonaceous char which is intrinsically catalytically active for chloramine removal apart from factors such as contact time, mean particle diameter, and the like which are known to affect chloramine removal.

20

SUMMARY OF THE INVENTION

Generally, the present invention comprises a method for removing chloramines from aqueous media by contacting said media with a catalytically-active carbonaceous char which is characterized by its ability

to rapidly decompose hydrogen peroxide in aqueous solutions. Prior art carbon materials which have been used for this application in the past do not rapidly decompose hydrogen peroxide in aqueous solutions. The carbonaceous chars used in the present invention may be prepared from carbon materials which have been contacted or otherwise exposed to nitrogen-containing compounds at temperatures above 700 C and are characterized by an ability to rapidly decompose hydrogen peroxide in aqueous solutions.

The carbonaceous feedstocks from which such carbons are produced may be either nitrogen-poor naturally-occurring materials such as coals or nitrogen-rich processed feedstocks such polyacrylonitrile. The nitrogen-rich feedstocks are carbonized or carbonized and oxidized prior to activation at high temperatures with a gasifying agent such as steam or carbon dioxide. The nitrogen-poor feedstocks may be processed as low-temperature carbonized chars or as high-temperature carbonized chars such as activated carbons. Either carbon may be oxidized prior to, during, or after carbonization. However, all nitrogen-poor chars must be contacted or otherwise exposed to nitrogen-containing compounds such as ammonia, urea or the like at high temperatures prior to, during, or after calcination and/or activation at high temperatures with a gasifying agent such as steam or carbon dioxide. Additionally, it is essential that the final products in all cases described above be cooled to temperatures below 400 C, preferably 200 C, in an oxygen-free or otherwise inert atmosphere.

The catalytically-active carbonaceous chars of the present invention are distinguished from prior art carbons by their ability to rapidly decompose hydrogen peroxide in aqueous solutions. When tested under nearly equivalent conditions of contact time, mean particle diameter, pore volume, pore size distribution, and the like, these catalytically-active carbonaceous chars remove chloramines much more effectively than prior art carbon materials which have been used for this application in the past. Other advantages of the present invention will become apparent from a perusal of the detailed description of the presently preferred embodiments.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a diagrammatic view of a representative apparatus for measuring the catalytic activity of carbonaceous char.

PRESENTLY PREFERRED EMBODIMENTS

Six samples of carbonaceous chars were selected to illustrate the present invention. These chars were all sized to approximately less than 4 and greater than 6 mesh size (U.S. Standard Series Sieves). These chars were selected such that their Apparent Densities (Test Method Number TM-7, Calgon Carbon Corporation, Pittsburgh PA) and Carbon Tetrachloride Numbers (Test Method Number TM-6, Calgon Carbon Corporation, Pittsburgh PA) were nearly equivalent, which indicates that their pore volumes were also nearly equivalent. Although the pore volumes of these six samples were nearly equivalent, their abilities to catalytically decompose hydrogen peroxide in aqueous solutions were very different. These differences were quantified by use of the t-3/4 test method set forth in U.S. Patent Application Serial No. (Atty. Docket No. 92-335; filed January 21, 1993 by the assignee of the present invention and incorporated herein by reference).

This test measures the time required for the catalytically-active carbonaceous char to decompose three fourths of the available hydrogen peroxide, and this time is referred to as the t-3/4 time. In particular, the test measures the elapsed time required for 0.250 grams of carbon to decompose 75% of a standard amount of aqueous hydrogen peroxide (0.42 moles H_2O_2) as indicated by the temperature rise of the system. The time required for decomposition is determined by measuring the temperature of the reaction mixture using an accelerating rate calorimetric method. The test results are set forth in units of minutes. With reference to Figure 1, an apparatus 10 is shown which is useful in conducting the tests of the present invention. Apparatus 10 includes a Dewar 11 (Catalog Number 10-195A, Fisher Scientific, Pittsburgh PA, or equivalent) positioned on a magnetic stirrer 12 (Model PC-351, Corning Hot Plate Stirrer, Corning Scientific Products, Corning, New York, or Model 18425 Nuova II Stir Plate, Thermolyne Corporation, Dubuque Iowa, or equivalent) and containing therein a magnetic stir bar 13. A beveled, tightly fitting, closed-cell styrofoam cap 14 is positioned in the top of Dewar 11 and includes a funnel 15, a vent 16 and an opening 17 therethrough and into Dewar 11. Through opening 17 is positioned thermocouple 18 which is electrically connected to ice point compensator 21 and strip chart recorder 22. In practice, the carbonaceous char to be tested is first pulverized such that greater than 90% of the material would pass through a 325 mesh U.S. Standard Series sieve. The styrofoam cap 14 of dewar 11 is removed and a 0.250 gram portion of this pulverized material is placed therein. Deionized water (100 mL) is then added to the Dewar. The addition of this water is performed in such a manner that any pulverized carbonaceous char clinging to the sides of Dewar 11 is carried into the main body of the water in the bottom. Next, a 50 mL aliquot of aqueous buffer

solution is added to the Dewar. This buffer solution is 0.50 molar in K_2HPO_4 and 0.50 molar in KH_2PO_4 . At this point magnetic stir bar 13 is placed into the Dewar and the magnetic stirrer is energized. Stirring speed is increased until a vortex greater than about 1/2" deep is formed in the mixture and the optimum stirring speed is achieved. The optimum stirring speed is selected such that additional increases in stirring speed do not significantly affect the peroxide decomposition time. Once identified, this optimum stirring speed can be used for all subsequent char samples. If stir bar 13 decouples from the magnetic field before the optimum stirring speed is achieved, it is replaced with a bar which couples more strongly with the magnetic field of the stirrer (12). Optionally, Dewar 11 can be replaced with an equivalent unit that, due to manufacturing variances, positions the stir bar farther into the magnetic field of the stirrer 12. If the stir bar still does not adequately couple with the magnetic field of the stirrer 12, the Dewar can be shortened by removing some of the bottom portion of the outside metal casing. Styrofoam cap 14 is now replaced, and thermocouple 18 (Type K or J, 1/16" diameter, Inconel sheathed, ungrounded or equivalent) is inserted through styrofoam cap 14 and into the mixture such that a measurement representative of the mixture temperature can be obtained, and the thermocouple ice point compensator 21 (Model MCJ-J or MCJ-K, Omega Engineering, Inc., Stamford, CT or equivalent) and strip chart recorder 22 are energized.

The strip chart recorder tracing is monitored until the system is seen to come to thermal equilibrium at ambient temperature. Once thermal equilibrium is achieved, 50 mL of an aqueous hydrogen peroxide solution (0.42 moles H_2O_2 per 50 mL) is added, as rapidly as possible, to the Dewar through the funnel 15 in the styrofoam cap. Care is taken to ensure that the hydrogen peroxide solution is at ambient temperature prior to the addition. As the hydrogen peroxide solution is added to the Dewar, the strip chart recorder tracing is marked to indicate the time of addition. The strip chart recorder tracing is then monitored until the tracing indicates that a constant temperature above ambient has been reached. Using the materials and procedures described, this constant temperature is typically about 40 C greater than ambient temperature. At this point, the styrofoam cap is removed from the Dewar and the action of the stir bar is observed.

If the stir bar is no longer mixing the solution in the desired manner the entire procedure is repeated. If adequate mixing is observed, the elapsed time required for the recorder tracing to reach 75% of its maximum, constant, deflection is determined. This value represents the time required for the catalytically active carbonaceous char to decompose three-fourths of the available hydrogen peroxide and is referred to as the $t_{3/4}$ time. This value is reported in units of minutes. The $t_{3/4}$ time determined for each of the six carbon samples are listed in Table 1 along with the Carbon Tetrachloride Number and Apparent Density of

each sample. The lower the t-3/4 time, the higher is the level of catalytic activity. Typical values of the t-3/4 time for commercial activated carbons are in excess of 30 minutes.

5 The ability of each of the carbonaceous chars to catalytically decompose chloramine in aqueous solution was determined in the following manner. The carbon to be tested is first pulverized such that greater than 90% of the material would pass through a 325 mesh U.S. Standard Series sieve. A stock monochloramine solution is then prepared by combining equal volumes of a 1.5 g/L NH_4Cl solution and a 1.25 g/L Na_2CO_3 solution containing 12.5 mL/L of Chlorox household bleach. This monochloramine solution contains approximately 350 ppm NH_2Cl as Cl_2 . If the assay of this stock solution shows the monochloramine concentration to be low, it may be increased if desired by the addition of small portions of Chlorox and NH_4Cl . A 200 mL aliquot of the stock monochloramine solution is then placed into a 250 mL Erlenmeyer screw top flask.

15 A 0.200 g portion of the pulverized char is next added to the flask. The flask is immediately capped and swirled to thoroughly wet the pulverized char. The capped flask is immediately placed in a covered shaker bath which is maintained at ambient temperature. The flask is agitated in the bath for a period of time such that an elapsed carbon-solution contact time of 75 minutes, as measured from the initial addition of the pulverized carbon char to the solution, is obtained. At the end of this elapsed time period the flask is removed from the shaker bath, and the mixture immediately vacuum filtered through a 0.45 micron filter pad.

20 The monochloramine concentration of the filtrate is then determined using a modified version of a ferrous ammonium sulfate titration described elsewhere (STANDARD METHODS FOR THE EXAMINATION OF WATER AND WASTEWATER, 16th Edition, 1985, pages 306 to 309, American Public Health Association, 1015 Fifteenth Street NW, Washington, DC 20005). The modification to this procedure consisted solely of the substitution of DPD Reagent Powder Pillows For Total Chlorine (Catalog Number 14076-99, HACH Company, P.O. Box 389, Loveland CO 80539) for the DPD indicator solution
25 specified in the procedure. To establish the initial concentration of the stock chloramine solution, the procedure is repeated without the addition of a pulverized char to the flask. Using this procedure, the extent to which each of the six carbonaceous chars catalytically decomposed monochloramine was determined. For these determinations, the stock solution monochloramine concentration was 300 ppm. The percent of chloramine decomposed by each of the carbonaceous chars is given in Table 1 below.

5 Table 1 clearly shows that the extent to which a carbonaceous char catalytically decomposes hydrogen peroxide corresponds to that for the decomposition of chloramines. It has been found that carbonaceous chars having t-3/4 times of less than about 15 minutes provide significantly enhanced removal of chloramine. It is also apparent, as the Apparent Densities and Carbon Tetrachloride Numbers of these chars are nearly equivalent, that the observed effect is not significantly attributable to differences in pore volumes.

While presently preferred embodiments of the invention have been described in detail, the invention may be otherwise embodied within the scope of the appended claims.

TABLE 1
COMPARISON OF CHLORAMINE REMOVAL AND t-3/4 TIME

SAMPLE NUMBER	APPARENT DENSITY (g/cc)	CARBON TETRACHLORIDE NUMBER (%)	t-3/4 TIME (minutes)	CHLORAMINE REMOVED FROM SOLUTION (%)
1	0.483	54.8	2.4	75
2	0.480	60.4	4.6	48
3	0.503	54.0	9.4	40
4	0.499	58.3	23.4	35
5	0.511	54.8	54.4	35
6	0.497	60.4	80.2	33

WHAT IS CLAIMED IS:

1. The process for the removal of chloramines from solutions or streams which comprises contacting said solutions or streams with a catalytically-active carbonaceous char having a $t_{-3/4}$ time less than about 15 minutes.

2. A process as set forth in Claim 1 wherein said carbonaceous char has a $t_{-3/4}$ time of less than about 5 minutes.

3. The process of Claim 1 wherein the solutions or streams are aqueous.

4. The process of Claim 1 wherein said catalytically-active carbonaceous char is granular, pellets, shaped, or powdered.

5. The process of Claim 1 wherein said catalytically-active carbonaceous char is derived from any carbon-containing material.

6. The process of Claim 1 wherein said catalytically-active carbonaceous char is activated carbon[s].

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 94/00522

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 C02F1/28 C02F1/76

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 5 C02F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 022 368 (KERRIDGE) 14 January 1981 see claims 1,2 ---	1,3-6
A	DATABASE WPI Section Ch, Week 9008, Derwent Publications Ltd., London, GB; Class D22, AN 90-057644 & SU,A,1 500 666 (KAZA POTATO VEG RES) 15 August 1989 see abstract ---	1
A	DATABASE WPI Section Ch, Week 7915, Derwent Publications Ltd., London, GB; Class D15, AN 79-28489B & JP,A,54 028 446 (NIPPON JUTAKU KODAN ET AL.) 3 March 1979 see abstract -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

5 April 1994

Date of mailing of the international search report

02.05.94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Kaspers, H

Information on patent family members

PCT/US 94/00522

Form PCT/ISA/210 (patent family annex) (July 1992)