

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
24 August 2006 (24.08.2006)

PCT

(10) International Publication Number
WO 2006/086996 A1

(51) International Patent Classification:

H01L 21/311 (2006.01) *H01L 21/768* (2006.01)
H01L 21/3105 (2006.01)

(21) International Application Number:

PCT/EP2005/001510

(22) International Filing Date:

15 February 2005 (15.02.2005)

(25) Filing Language:

English

(26) Publication Language:

English

(71) Applicant (for all designated States except US):
FREESCALE SEMICONDUCTOR, INC. [US/US];
6501 William Cannon Dr., Austin, TX 78735 (US).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **FARKAS, Janos**
[US/FR]; 689 Chemin Du Patel, Saint Ismier, F-38330
Isere (FR).

(74) Agent: **WHARMBY, Martin, A.**; Impetus IP Ltd, Grove
House, Lutyens Close, Chineham Court, Basingstoke,
Hampshire RG24 8AG (GB).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- with amended claims

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **WAFER CLEANING AFTER VIA-ETCHING**



(57) Abstract: When a semiconductor wafer bears porous dielectric materials it is still possible to perform post-via-etch cleaning of the wafer using aqueous cleaning fluids if, before and/or simultaneously with application of the aqueous cleaning fluid(s), a water-soluble organosilane or like passivation material is used to form a passivation layer on the porous dielectric material.

WO 2006/086996 A1

Wafer cleaning after via-etching

The present invention relates to the processing of semiconductor wafers and the like, and more particularly to a technique for cleaning wafers
5 after dry etching of vias or trench-like structures.

As features sizes in integrated circuits become progressively smaller, it has become increasingly important to reduce the resistance-capacitance delay (RC delay) attributable to the interconnects used in the circuit. In order
10 to reduce this RC delay, it has been proposed that advanced interconnects should have a reduced dielectric constant (k), notably, that these interconnects should be made of low-k materials. As a first step, carbonated silicon dioxide (SiOC) films had been introduced in the 90-120 nm technology nodes. Currently the k-value is being further improved by introducing pores
15 in these carbonated silicon dioxide films.

Incidentally, in the present document the expression "carbonated silicon dioxide films" and the general formula "SiOC" are used to designate silicon dioxide films that have been formed or treated so as to have carbon
20 therein (e.g. by using CH_3SiH_3 in place of the SiH_4 that is often used as a precursor in the formation of a silicon dioxide layer). In other documents such films are sometimes referred to as carbon-doped silicon dioxide films.

These materials are being developed by several vendors, using
25 chemical vapour deposition or spin-on coating techniques. Several vendors are currently developing CVD deposited films using a porogen approach. With this technology the porogens build into a film and are degassed during the post-treatment, leaving pores in the dielectric films. Applied Materials (Black Diamond IIx; III), Novellus systems (ELK Coral), Trikon (Orion); ASM
30 are amongst the companies working on this approach. Suppliers of materials in the field of spin-on porous dielectrics include Dow Chemicals (SiLK), Rhom and Haas (Zirkon) and JSR.

- 2 -

Any silicon oxide-containing material will have a substantial population of surface hydroxyl (silanol) groups on the surface, which are highly polarized and therefore have a high affinity to water uptake. These sites are generated by the break up of four and six member bulk siloxane (Si-O-Si) bridges at the surface of the material. These siloxane structures at the material surface have an uncompensated electric potential and so can be considered to be "strained". They will react with moisture to form surface hydroxyl groups. If the material is porous, the surface hydroxyls and the adsorbed water molecule will propagate to the bulk of the material. This will results in increased dielectric constant values and reduced reliability of the film.

A comparable effect occurs for other materials, such as metal oxides, present on the surface of a wafer. The metal ion - oxide bonds located at the surface of the material have an uncompensated electric potential. This leads to a tendency to react with moisture so as to form surface hydroxyl groups. Once again, if the material is porous the surface hydroxyls and adsorbed water molecule will propagate to the bulk of the material and lead to an unwanted increase in dielectric constant.

As mentioned above, carbonated silicon oxide is often used as a porous dielectric material. The carbon-rich surface has a reduced number of strained oxide bonds. Thus, there is a reduced population of surface hydroxyls at the surface of the material.

For carbon-containing porous dielectrics, the sensitivity to water uptake is significantly higher after a dry etch process. The oxidizing plasma reduces the carbon content at the surface of the material and therefore increases the population of surface hydroxyls. As it can be expected, the change in the dielectric constant of these porous materials increases after the dry etch step and there is a need to "restore" the k value of the film. One common technique is to apply a supercritical CO₂ treatment with Hexamethyldisilazane (HMDS).

- 3 -

For the reasons described above, it is important to prevent water uptake if porous dielectric materials are used to form interconnects. Moreover, it has been observed that absorption of water by a porous dielectric could lead to corrosion of Ta-based barriers.

5

Some potential counter-measures to combat the take-up of water by such porous dielectric materials during manufacture and use of a semiconductor integrated circuit include the above-described "dielectric restoration", and "pore sealing". Pore sealing involves prevention of access
10 to the pores in the porous material, for example by modifying the surface of the porous material (e.g. using an organosilane treatment), or by depositing a thin dielectric film on the surface of the porous dielectric layer. The latter has a disadvantage of increasing the k value of the layer.

15 Now, when a semiconductor integrated circuit is manufactured it is necessary to etch vias or trench-like structures in one or more layers provided on the circuit substrate (wafer). When the vias or trench-like structures are etched, polymer material tends to build up in the via/trench. In addition metallic species (e.g. copper) could be sputtered onto the sidewalls.
20 This organic residues are formed due to the interaction of hydrocarbon etchant gases in the plasma with the substrate material. Thus, it is necessary to perform a cleaning step in order to remove the residual polymer and metallic species, before proceeding to the next stages in the manufacturing process. Traditionally, cleaning to remove such residual polymer would
25 involve the application of aqueous solutions, such as dilute hydrofluoric acid (HF), or organic acids/bases. However, such an approach is not suitable in the case where porous material is present at the surface of the wafer to be cleaned.

30 If the conventional approach were to be adopted for post-via-etch cleaning of a wafer bearing a porous interconnect layer, the porous dielectric material would adsorb water from the aqueous cleaning fluids. This problem

- 4 -

is particularly acute in the case where the dielectric layer has undergone plasma damage during the via/trench-etching process. Besides the negative effect on the dielectric layer's dielectric constant, the adsorbed water can also cause problems during subsequent stages in the manufacture of the circuit, notably degassing and reliability problems.

In some cases, a pore sealing treatment has been applied to the porous dielectric layer after vias have been etched therein. However it has been found that, after cleaning such pore-sealed dielectric layers using conventional water-containing cleaning fluids, there has still been undesirable water adsorption by the dielectric layer.

In view of the above-mentioned problems, an alternative approach has been proposed for post-via-etch cleaning of a wafer bearing a porous dielectric material. The alternative approach involves applying supercritical carbon dioxide (CO_2) to the etched surface. However, this approach has the disadvantage that it requires investment in new equipment which is at a more experimental stage in development than the cleaning equipment already in widespread use in the semiconductor manufacturing industry.

The present invention provides a method of cleaning a substrate bearing a porous dielectric material and etched vias or trench-like structures, as described in the accompanying claims.

A preferred embodiment of the invention will now be described, by way of example, with reference to the drawings, of which:

Fig.1 is a diagram schematically illustrating the main steps in the cleaning method according to the preferred embodiment of the present invention, in which:

Fig.1A illustrates a trench containing residual polymer and metallic contamination to be removed,

- 5 -

Fig.1B shows a passivation layer applied to certain surface regions of the trench, and

Fig.1C illustrates the trench after cleaning; and

Fig.2 is a diagram illustrating steric shielding on the surface of a porous dielectric material in the vicinity of an etched via/trench-like structure, in which:

Fig.2A is a graph representing an absorption spectrum of the porous dielectric material after the surface thereof has been treated using trimethyl dimethyl aminosilane, and

Fig.2B illustrates how methyl groups from the trimethyl dimethyl aminosilane can prevent access to remaining silanol groups on the porous dielectric surface.

The cleaning method of the preferred embodiment of the present invention will now be described with reference to Figs.1 and 2.

In the following description it shall be assumed that the cleaning method is being applied to a semiconductor substrate which has on its surface a porous SiOC layer through which a via has been etched. However, it is to be understood that the present invention is not limited to use on wafers bearing porous SiOC layers, but can be used for wafers bearing other porous dielectrics that are prone to have surface hydroxyls.

The cleaning process aims to remove residual polymer from the via, as well as removing metallic species (e.g. copper) which may have sputtered onto the via side walls during the earlier etch process. Fig.1A illustrates a via, 1, in which residual polymer, 2, has built up. The via's side walls are defined by a porous SiOC layer 3, and the bottom of the via 1 is defined by the surface of the layer (e.g. copper) underlying the porous layer 3.

The preferred embodiments of the present invention allow traditional aqueous cleaning fluids to be used for removing the polymer and/or metallic

- 6 -

species that have built up in the etched vias, trenches or the like during manufacture of the semiconductor integrated circuit. However, porous dielectric materials (e.g. SiOC) on the substrate are protected from contact with the water in the aqueous cleaning fluids because of the application of a
5 passivating material to the surface substantially at the same time as the cleaning fluids are applied.

According to the preferred embodiment of the present invention, the passivating material is applied to the surface and reacts with the surface
10 hydroxyls. This attaches one or more shielding groups present in the passivating material to the surface of the porous dielectric. The gaps between the attached shielding groups are too small to allow water molecules to reach the porous material's surface. Thus the attached groups provide steric shielding.

15

A wide variety of materials may be used to constitute the passivating material. The important features are that the passivating material:

- should include a functional group which reacts with surface hydroxyls,
- 20 - should include at least one, preferably at least two organic shielding groups, and
- after the reaction with the surface should form at least one, preferably at least two shielding layers above the surface


25

It is also advantageous if the passivating material is water-soluble and the functional group(s) thereof has a sufficiently-fast reaction speed with surface hydroxyls, as explained below. The passivating material may include at least one functional group which may be hydrolysed in water.

30

In preferred embodiments of the invention, the passivating material is an organosilane and can be represented using the formula:

- 7 -



where:

Si is a silicon atom;

X_1 is a first functional group reacting with the surface hydroxyl sites of the
 5 porous material;

Y is either:

- X_2 , a further functional group reacting with the surface hydroxyl sites of the porous material,
- H (i.e. hydrogen), or
- 10 - R_1 an organic apolar group or branch;

Z is either:

- X_3 , a further functional group reacting with the surface hydroxyl sites of the porous material,
- H (i.e. hydrogen), or
- 15 - R_2 an organic apolar group or branch;

R is a carbon-containing, organic apolar group or branch.

In a case where the silicon is bonded to two functional groups, X_1 and X_2 , or X_1 and X_3 , these two functional groups could be the same or different from
 20 each other. In a case where the silicon is bonded to three functional groups, X_1 , X_2 and X_3 , these three functional groups could all be different, could all be the same, or two out of three could be the same.

Similarly, in a case where the silicon is bonded to two organic apolar groups,
 25 R and R_1 , or R and R_2 , these two organic groups could be the same or different from each other. In a case where the silicon is bonded to three organic apolar groups, R, R_1 and R_2 , these three organic groups could all be different, could all be the same, or two out of three could be the same.

- 8 -

It is preferable for each of Y and Z to be a functional group or an organic apolar group. However, it is permissible for Y and/or Z to be H.


5 It is the organic apolar groups and/or branches of the molecule which will provide the steric shielding of the surface from the hydroxyl groups and water molecules.

10 The number of organic apolar groups/branches in the molecule depends on how many functional groups (X_1 , or X_1 and X_2/X_3 , or X_1 , X_2 and X_3) are attached to the silicon atom. It should be noted that the organic apolar groups/branches can form multiple shielding layers depending on the selection of those groups/branches as illustrated below.

15 Some examples are given below illustrating the impact of the organic apolar groups/branches on the formation of the shielding layers.

Example 1: R, Y and Z are methyl groups

20 In the case where the silicon atom is connected to one functional group, X_1 , and three methyl groups (i.e. $Y = Z = R = CH_3$) the general structure of the passivating material will be:




, where Me stands for a methyl group.


25 Such a passivating material produces a single shielding layer on the porous material as shown in Fig.2B.

Example 2: R is an iso-propyl group (Y and Z are methyl groups)

In the case where the silicon atom is connected to one functional group, X_1 , two methyl groups (i.e. $Y = Z = \text{CH}_3$) and an iso-propyl group (i.e. $R = \text{iso-propyl group}$), a second shielding layer forms on the porous material, above the one formed by the two methyl groups (Y and Z).


10 Example 3: R is a tert-butyl group (Y and Z are methyl groups)

In the case where the silicon atom is connected to one functional group, X_1 , two methyl groups (i.e. $Y = Z = \text{CH}_3$) and a tert-butyl group (i.e. $R = \text{tert-butyl group}$), once again there is a second shielding layer besides the one formed by the two methyl groups (Y and Z).



Example 4: R is a 3,3-dimethylbutyl group (Y and Z are methyl groups)


In the case where the silicon atom is connected to one functional group, X_1 , two methyl groups (i.e. $Y = Z = \text{CH}_3$) and a 3,3-dimethylbutyl group (i.e. $R = t\text{-BuCH}_2\text{CH}_2$ group, where $\text{Bu} = \text{butyl}$), once again a second shielding layer forms on the porous material, above the one formed by the two methyl groups (Y and Z). However, in this case, the spacing between the first and second shielding layers is greater than that which applies in the second and third examples.



20 The Functional Group(s)

The functional group (or groups) X_i in the shielding material is selected such that it will react with hydroxyl groups at the surface of the porous dielectric layer so as to attach one or more shielding layers in the passivating material to that surface. More particularly, the X functional group reacts by the elimination of the surface hydroxyl.


For example, in the case where the porous dielectric is formed of SiOC , a potential passivating material is a trimethyl dimethyl aminosilane:



- 11 -

In the case of this trimethyl amino compound, there is one functional group X_1 and it is the amine group, the other three methyl groups connected to the silicon will form a first shielding layer on the porous material.

- 5 In the trimethyl dimethyl aminosilane, the amino functional group reacts with a surface silanol in the porous SiOC dielectric so that an NMe_2H molecule is eliminated and an Si-O-Si bond links the porous material's surface to the passivating material, as follows:



10

- The shielding effect achieved using the trimethyl dimethyl aminosilane is illustrated in Fig.2. Fig.2A shows an absorption spectrum of an SiOC layer that has had its surface treated with trimethyl dimethyl aminosilane. As seen in Fig.2A, a significant absorption peak at wave number 3751, which could be expected to appear if significant quantities of silanols were present, does not appear in the absorption spectrum. The peak visible at wave number 2965 indicates the presence of methyl groups on the surface of the porous dielectric. Fig.2B illustrates how the shielding methyl groups which become attached to the porous dielectric layer physically prevent access to those silanols which still remain on the surface of the dielectric layer.
- 15
- 20

- In the passivating materials according to the preferred embodiments of the present invention, the functional group(s) X_i could be, for example Cl, Br, I, acryloxy-, alkoxy-, acetamide, acetate-, allyl-, amine-, cyanide, epoxy- ; imidazole, mercapto-, methanesulfonate-, sulfonate-, a mono-, bi- or tri-functional amino group (e.g. trifluoroacetamide, and urea groups), etc.
- 25

- 12 -

The strength of the bond to the porous dielectric and the speed of the reaction with the surface hydroxyls will be driven by the X_i functional group(s) and the presence or lack of the silicon groups in the passivating material. Organo-silanes form a stronger bond to the surface than non-silicon-containing hydrocarbon chains and so provide a more stable protection for the surface. Accordingly, the preferred embodiments of the invention use organosilanes as the passivating material. However, certain non-silicon-containing materials can also be used as the passivating material, for example, organic amines.

10

When the passivating material includes more than one functional group, X_i , and the passivating material is applied in a gas phase, it is the functional group which reacts most rapidly which will tend to react with the hydroxyls on the surface of the porous material. When such a passivating material is applied in a liquid phase the reaction scenario is complicated by the fact that certain functional groups hydrolyse. However, there are known water-soluble silanes which have more than one functional group and are stable in water; such materials can satisfactorily functionalize a hydrophilic surface.

20

The hydrocarbon part of the passivating material molecule will be able to shield the dielectric material from water penetration. In the above example, methyl groups from the trimethyl dimethyl aminosilane serve to form a first shielding layer shielding the surface of the porous dielectric from water.

25

The length of the hydrocarbon chain, R , as well as the number and type of the hydrocarbon groups R_1 , R_2 , will determine the shielding efficiency from water penetration.

30

In the preferred embodiments of the invention, the passivating material includes groups for forming at least two shielding layers at the surface porous

dielectric material. The shielding group(s) form a first shielding layer close to the porous dielectric material's surface. The second shielding group(s) form a second shielding layer at a greater distance away from the surface of the porous dielectric.

5

Any additional shielding groups in the passivating material form additional shielding layers at greater and greater distances away from the surface of the porous dielectric.

10 Previous studies in other fields have shown that properly chosen organic layers could be efficient to sterically shield non-porous dielectric surfaces from precursors (such as metalorganic compounds), see J. Farkas et al., J. Electrochem. Soc. 141, 3547 (1994). With porous materials it could be expected that the size of the shielding groups R should be proportional to
15 the size of pores.

The effect of R on steric shielding by organosilanes has been studied in the field of HPLC column treatment, see the above-mentioned paper by J. Farkas et al, and in the field of fiber optic protection and selective depositions
20 see K. Szabo et al, Helv. Chim. Acta. vol. 67 p.2128, 1984. The Farkas et al paper showed that an organic layer with about 25 Angstroms thickness can be very efficient for steric shielding of a surface from water penetration, even at elevated temperatures. In the case of using passivating materials for steric shielding of a porous dielectric surface, the length of the hydrocarbon
25 chain can be easily adjusted to optimize the efficiency of steric shielding to the pore size of the dielectric.

According to the preferred embodiments of the invention, the organic apolar group(s) attached to the silicon atom are selected from: methyl, ethyl,
30 propyl, butyl, phenyl, pentafluorophenyl, hexyl, and allyl.

- 14 -

In the preferred embodiment of the present invention illustrated in Fig.1, after the via-etching step the passivating material, e.g. an organosilane, is applied to the surface of the substrate in a preliminary-treatment step. At locations where there is no polymer build up, the applied
5 organosilane reacts with the adsorbed water, or with the silanol-covered SiOC surface layer 3, to form a passivation layer 5 including at least one shielding layer on the SiOC layer 3. Fig.1B shows the passivation layer 5 covering the SiOC surface layer 3. The applied organosilane does not interact with the residual polymer 2 and, thus, does not impede its removal
10 later on.

Any convenient technique can be used for applying the passivating material to the wafer in the preliminary treatment step. For example, the porous material can be subjected to a surface treatment with organosilanes,
15 to seal the pores therein, in the vapour phase or liquid phase. The benefit of this preliminary step is that the porous surface is already pre-treated before it gets to the aqueous cleaning phase.

If the preliminary treatment of the porous dielectric with the passivating
20 material is performed with an organosilane in the liquid phase, the organosilane will often be highly-diluted in water, with some addition of alcohols (to enhance solubility). If the preliminary treatment of the porous dielectric with the passivating material is performed with an organosilane in the vapour phase, the organosilane could be used with a carrier gas, such as
25 N₂ or Ar, if necessary. The preferred temperature for the preliminary treatment in the liquid phase is between 25-80 °C and the process time is 30s to 10 min. In the vapour phase the process temperature can be higher, e.g. 150°C. Moreover, the temperature may be limited by the stability of the silane being used (some are stable at temperatures over 300°C but most are
30 only stable at lower temperatures).

- 15 -

In the cleaning method according to the preferred embodiment of the invention, by formation of the passivation layer 5 it is possible to protect the majority of the porous SiOC surface from water adsorption and penetration. Thus, it could be envisaged to use conventional aqueous cleaning fluids for
5 removal of the residual polymer 2 (and residual metallic species) from the trench 1.

However, after the preliminary treatment step the passivation layer 5 does not cover the entirety of the SiOC surface layer 3. There are locations
10 on the SiOC surface 3 where it bears residual polymer 2. The present inventor has realized that, at the time when a water-containing cleaning fluid removes the residual polymer 2, the freshly-exposed portions of the SiOC surface layer 3 are then liable to absorb water.

15 According to the preferred embodiments of the invention, the chemicals used for cleaning the via/trench 1 are mixed with more of the above-described passivating material. Thus, if the reaction speed of the functional group(s) X_i in the passivating material is sufficiently fast, as soon as the polymer is removed from a particular portion of the trench by the
20 cleaning fluid, the silanols on the surface of the underlying porous SiOC will react with the passivating material and be covered by the protective organic monolayer before water can be adsorbed. It will be seen that, for this purpose, it is important for the reaction speed of the functional group(s) X_i with the surface silanols (or other surface hydroxyls) to be sufficiently fast for
25 the surface silanols to become shielded before significant quantities of water have been adsorbed from the water-containing cleaning fluid(s).

If the passivating material is a water-soluble organosilane, it can be mixed with the cleaning fluid(s) ahead of application thereof to the wafer.
30 However, if the passivating material consists of an organosilane which is traditionally considered not to be water-soluble, notably because of its short pot life (shelf life) when mixed with water, it can be still be used in certain

- 16 -

embodiments of the present invention. More particularly, if the organosilane has a short pot life when mixed with water, mixing of the organosilane and the cleaning fluid(s) can be accomplished at, or in the immediate vicinity of, the cleaning tool (i.e. just before application to the wafer).

5

In general, there is a wider selection of organosilanes possible for the preliminary treatment step than for the cleaning step, since the passivating material used in the preliminary treatment step does not require compatibility with aqueous media.

10

Process conditions for one example of a typical cleaning step according to the preferred embodiments of the present invention are:

- applied cleaning mixture = a water-soluble organosilane mixed with an organic acid (or highly diluted aqueous HF), with optional
15 chelating agent and/or surfactant.
- process temperature = 25-80 °C, and
- process time = 30s to 10 min

As shown in Fig.1C, after the residual polymer 2 (and metallic
20 residues) has been removed, the via 1 is clean and the sidewalls thereof are covered by the passivation layer 5. The pores in the porous dielectric layer 3 are sealed by the passivation layer 5.

As indicated above, if desired, during the cleaning process of the
25 present invention a complexing or chelating agent may be used, in order to remove metallic species. These reagents should be added into the passivating material/cleaning fluid mix, so as to be able to be processed in a common series of steps. Common complexing agents include ethylenediamine tetraacetic acid (EDTA) and its derivatives and organic
30 acids.

- 17 -

Similarly, surfactants can be included in the mix of cleaning chemicals. A wide variety of surfactants can be used. It can be advantageous to use as a surfactant block co-polymers built from blocks of polyethyleneoxide and polypropyleneoxide. These two groups are efficiently
5 absorbing on both hydrophobic and hydrophilic surfaces, and the length and ratio of each group present in the block co-polymer can easily be tailored to the application.

The cleaning method according to the preferred embodiment of the
10 invention enables porous dielectric materials to be cleaned without needing to resort to the use of new equipment. More particularly, it is a simple matter to modify existing post-via-etch "wet" cleaning equipment so that it can implement the cleaning method of the present invention. This is much cheaper than implementing a method using supercritical CO₂.

15 Moreover, the cleaning method according to the preferred embodiment of the invention both enables the porous dielectric material to be protected from aqueous cleaning fluids and seals the pores in the dielectric material, avoiding the need for a separate pore-sealing or dielectric-
20 restoration step. By inhibiting the uptake of water by the porous dielectric material, the cleaning method of the preferred embodiment of the present invention improves reliability of the finished product and increases the yield of the overall manufacturing process.

25 By passivating the surface (notably etched side walls) of a porous dielectric, the cleaning method according to the preferred embodiment of the present invention helps to reduce delamination later, as well as avoiding a potential increase in dielectric constant.

30 Although the present invention has been described above with reference to certain particular preferred embodiments, it is to be understood that the invention is not limited by reference to the specific details of those

preferred embodiments. More specifically, the person skilled in the art will readily appreciate that modifications and developments can be made in the preferred embodiments without departing from the scope of the invention as defined in the accompanying claims.

5

For example, although the preferred embodiment of the cleaning method according to the present invention has been described in terms of cleaning via or trench-like structures etched in layers on a substrate including a layer of porous SiOC, the inventive method is applicable more generally to
10 the post-via-etch cleaning of wafers bearing other porous materials that are prone to surface hydroxyl formation.


Similarly, although the above description of the preferred embodiment of the method according to the invention referred to use of aqueous HF or
15 organic acids for cleaning residual polymer from a via, it is to be understood that any other convenient cleaning fluid comprising water can be used.

Furthermore, although the preferred embodiment of the invention was discussed above in terms of cleaning residual polymer (and residual metallic
20 species) from a via, it is to be understood that the invention is applicable in general to the cleaning of etched structures (vias, trenches, etc.).

Moreover, in the cleaning method according to the present invention it is not essential to include a preliminary treatment step of the porous dielectric
25 with a passivating material. Even if there is no preliminary treatment step, the porous dielectric can be protected from absorbing water during the post-via-etch-cleaning, by mixing passivating material with the cleaning fluid(s) applied to the semiconductor wafer.

CLAIMS:

1. A method of cleaning a semiconductor substrate having at least one region of porous dielectric material at the surface thereof, said porous dielectric material being prone to formation of hydroxyls at the surface thereof in the presence of moisture, the method comprising the steps of:
 - applying one or more cleaning fluids to the substrate, at least one of the applied cleaning fluids comprising water; and
 - during the application of said one or more cleaning fluids to the substrate, applying to the substrate a passivating material adapted to react with hydroxyls on the surface of the porous dielectric material whereby to form at least one shielding layer on said surface of the porous dielectric material, said at least one shielding layer serving to shield the porous dielectric material from water.
2. The cleaning method of claim 1, wherein said passivating material is mixed with the cleaning fluid(s) applied to the substrate.
3. The cleaning method of claim 1 or 2, wherein a further passivating material is applied to the substrate in a preliminary treatment step preceding the application of said one or more cleaning fluids to the substrate, said further passivating material being the same as, or different from, the passivating material applied to the substrate during the step of applying cleaning fluid(s) to the substrate.
4. The cleaning method of claim 1, 2 or 3, wherein the passivating material is an organosilane according to the general formula:



where:

- 20 -

Si is a silicon atom;

X₁ is a first functional group reacting with the surface hydroxyl sites of the porous material;

Y is either:

- 5 - X₂, a further functional group reacting with the surface hydroxyl sites of the porous material,
 - H (i.e. hydrogen), or
 - R₁ an organic apolar group or branch;

Z is either:

- 10 - X₃, a further functional group reacting with the surface hydroxyl sites of the porous material,
 - H (i.e. hydrogen), or
 - R₂ an organic apolar group or branch;

R is a carbon-containing, organic apolar group or branch.

15

5. The cleaning method of claim 4, wherein the passivating material is an organosilane including shielding groups for forming at least two shielding layers.

20 6. The cleaning method of claim 5, wherein said organosilane is water-soluble.

7. The cleaning method of claim 5, wherein said organosilane has a short pot life when mixed with water, and comprising the step of mixing the
25 organosilane with the cleaning fluid(s) substantially at the point of application of the cleaning fluid(s) to the substrate.

8. The cleaning method of any one of claims 4 to 7, wherein the passivating material includes:

30 at least one functional group selected from: Cl, Br, I, acryloxy-, alkoxy-, acetamide, acetate-, allyl-, amine-, cyanide, epoxy- ; imidazole, mercapto-, methanesulfonate-, sulfonate-, trifluoroacetamide, and urea groups;

and at least one organic apolar group selected from: methyl, ethyl, propyl, butyl, phenyl, pentafluorophenyl, hexyl, and allyl.


9. The cleaning method of any previous claim, wherein:
5 the semiconductor substrate has at least one structure etched therein;
at least one region of the porous dielectric material is exposed in the vicinity of an etched structure; and
the one or more cleaning fluids are adapted to remove residual polymer from etched structure(s).
- 10
10. The method of any previous claim, wherein the porous dielectric material comprises SiOC.
11. The cleaning method of any previous claim, and comprising the step
15 of applying a complexing or chelating agent to the substrate, whereby to remove metallic species therefrom, during the step of applying one or more cleaning fluids to the substrate.
12. The cleaning method of any previous claim, and comprising the step
20 of applying a surfactant to the substrate during the step of applying one or more cleaning fluids to the substrate.

AMENDED CLAIMS

[received by the International Bureau on 20 December 2005 (20.12.2005);
original claim 1 amended, claim9 cancelled, claims 10-12 renumbered]

CLAIMS:

1. A method of post-etch cleaning a semiconductor substrate having at least one structure etched therein and a region of porous dielectric material, said porous dielectric material being prone to formation of hydroxyls at the surface thereof in the presence of moisture, the method comprising the steps of:
 - applying to the substrate one or more cleaning fluids adapted to remove post-etch residues, at least one of the applied cleaning fluids comprising water; and
 - applying to the substrate a passivating material adapted to react with hydroxyls on the surface of the porous dielectric material whereby to form at least one shielding layer on said surface of the porous dielectric material, said at least one shielding layer serving to shield the porous dielectric material from water;
 - wherein the passivating material is applied to the substrate during the application of said one or more cleaning fluids to the substrate.
2. The cleaning method of claim 1, wherein said passivating material is mixed with the cleaning fluid(s) applied to the substrate.
3. The cleaning method of claim 1 or 2, wherein a further passivating material is applied to the substrate in a preliminary treatment step preceding the application of said one or more cleaning fluids to the substrate, said further passivating material being the same as, or different from, the passivating material applied to the substrate during the step of applying cleaning fluid(s) to the substrate.
4. The cleaning method of claim 1, 2 or 3, wherein the passivating material is an organosilane according to the general formula:








where:

and at least one organic apolar group selected from: methyl, ethyl, propyl, butyl, phenyl, pentafluorophenyl, hexyl, and allyl.

9. The method of any previous claim, wherein the porous dielectric
5 material comprises SiOC.

10. The cleaning method of any previous claim, and comprising the step
of applying a complexing or chelating agent to the substrate, whereby to
remove metallic species therefrom, during the step of applying one or more
10 cleaning fluids to the substrate.

11. The cleaning method of any previous claim, and comprising the step
of applying a surfactant to the substrate during the step of applying one or
more cleaning fluids to the substrate.
15

*FIG. 1A**FIG. 1B**FIG. 1C**FIG. 2B*

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2005/001510

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01L21/311 H01L21/3105 H01L21/768

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, INSPEC

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 02/01621 A (HONEYWELL INTERNATIONAL, INC; HACKER, NIGEL, P; THOMAS, MICHAEL; DRAGE) 3 January 2002 (2002-01-03) page 5, line 16 - page 7; examples 1,3-5,10	1-12
X	REIDY R F ET AL: "Supercritical silylation of ashed Si-O-C low-k films to limit changes in critical dimensions" ADVANCED METALLIZATION CONFERENCE 2003 (AMC 2003) MATER. RES. SOC WARRENDALE, PA, USA, 2004, pages 513-517, XP008053840 pages 513,514	1,2,4, 8-12
X	US 2004/023515 A1 (GRACIAS DAVID H ET AL) 5 February 2004 (2004-02-05) pages 2,3	1,2,9,10
	----- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

13 October 2005

Date of mailing of the international search report

20/10/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Szarowski, A

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2005/001510

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2003/198895 A1 (TOMA DOREL IOAN ET AL) 23 October 2003 (2003-10-23) paragraphs '0026! - '0028! paragraphs '0061! - '0064! -----	1-12
A	US 2004/020601 A1 (ZHAO JUN ET AL) 5 February 2004 (2004-02-05) paragraphs '0203!, '0204! -----	1-12

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP2005/001510

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 0201621	A	03-01-2002	AU 6699801 A CA 2413592 A1 CN 1502122 A EP 1292973 A2 JP 2004511896 T	08-01-2002 03-01-2002 02-06-2004 19-03-2003 15-04-2004
US 2004023515	A1	05-02-2004	NONE	
US 2003198895	A1	23-10-2003	US 2005191865 A1	01-09-2005
US 2004020601	A1	05-02-2004	EP 1124252 A2 JP 2002033314 A TW 490765 B	16-08-2001 31-01-2002 11-06-2002