(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau

(43) International Publication Date
8 November 2007 (08.11.2007)

PCT

(10) International Publication Number
WO 2007/127414 A2

(51) International Patent Classification:
C08F 4/44 (2006.01) *B01J 31/00* (2006.01)

(21) International Application Number:
PCT/US2007/010316

(22) International Filing Date: 27 April 2007 (27.04.2007)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
11/413,791 28 April 2006 (28.04.2006) US
11/540,181 29 September 2006 (29.09.2006) US

(71) Applicant *(for all designated States except US)*: **FINA TECHNOLOGY, INC.** [US/US]; P.O. Box 674412, Houston, TX 77267-4412 (US).

(72) Inventors; and
(75) Inventors/Applicants *(for US only)*: **ABBAS, Razavi** [US/BE]; Domaine De La Brisee 35, B-7000 Mons (BE). **MARIN, Vladimir** [RU/US]; 8803 Bexar Drive, Houston, TX 77064 (US). **LOPEZ, Margarito** [US/US]; 1615 Buckingham Drive, Pasadena, TX 77504 (US).

(74) Agents: **ALEXANDER, David, J.** et al.; Fina Technology, Inc., P.O. Box 674412, Houston, TX 77267-4412 (US).

(81) Designated States *(unless otherwise indicated, for every kind of national protection available)*: AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States *(unless otherwise indicated, for every kind of regional protection available)*: ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:
— *as to the identity of the inventor (Rule 4.17(i))*

Published:
— *without international search report and to be republished upon receipt of that report*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) **Title:** PROCESS FOR COPOLYMER PRODUCTION USING FLUORINATED TRANSITION METAL CATALYSTS

(57) **Abstract:** Copolymers and methods of forming copolymers are described herein. The methods generally include providing a transition metal compound represented by the formula $[L]_mM[A]_n$, wherein L is a bulky ligand including bis-indenyl, A is a leaving group, M is a transition metal and m and n are such that the total ligand valency corresponds to the transition metal valency and providing a support material having a bonding sequence selected from Si-O-Al-F, F-Si-O-Al, F-Si-O-Al-F and combinations thereof. The methods further include contacting the transition metal compound with the support material to form an active supported catalyst system, wherein the contact of the transition metal compound with the support material occurs in proximity to contact with monomer and contacting the active supported catalyst system with a plurality of monomers to form an olefin copolymer.

WO 2007/127414 A2

COS-1086 PCT Patent Application (as filed).doc

PROCESS FOR COPOLYMER PRODUCTION USING FLUORINATED TRANSITION METAL CATALYSTS

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This application claims the benefit of U.S. Patent Application Serial No. 11/540,181, filed September 29, 2006, which is a continuation-in-part of U.S. Patent Application Serial No. 11/413,791, filed April 28, 2006.

FIELD

[0002] Embodiments of the present invention generally relate to polyolefin copolymerization with supported catalyst compositions.

BACKGROUND

[0003] Many methods of forming olefin polymers include contacting olefin monomers with transition metal catalyst systems, such as metallocene catalyst systems to form polyolefins. While it is widely recognized that the transition metal catalyst systems are capable of producing polymers having desirable properties, the transition metal catalysts generally do not experience commercially viable activities.

[0004] Therefore, a need exists to produce transition metal catalyst systems having enhanced activity.

SUMMARY

[0005] Embodiments of the invention generally include copolymers and methods of forming copolymers. The methods generally include providing a transition metal compound represented by the formula $[L]_mM[A]_n$, wherein L is a bulky ligand including bis-indenyl, A is a leaving group, M is a transition metal and m and n are such that the total ligand valency corresponds to the transition metal valency and providing a support material having a bonding sequence selected from Si-O-Al-F, F-Si-O-Al, F-Si-O-Al-F and combinations thereof. The methods further include contacting the transition metal compound with the support material to form an active supported catalyst system, wherein the contact of the transition metal compound with the support material occurs in proximity to contact with monomer and contacting the

COS-1086 PCT Patent Application (as filed).doc

active supported catalyst system with a plurality of monomers to form an olefin copolymer.

DETAILED DESCRIPTION

Introduction and Definitions

[0006] A detailed description will now be provided. Each of the appended claims defines a separate invention, which for infringement purposes is recognized as including equivalents to the various elements or limitations specified in the claims. Depending on the context, all references below to the "invention" may in some cases refer to certain specific embodiments only. In other cases it will be recognized that references to the "invention" will refer to subject matter recited in one or more, but not necessarily all, of the claims. Each of the inventions will now be described in greater detail below, including specific embodiments, versions and examples, but the inventions are not limited to these embodiments, versions or examples, which are included to enable a person having ordinary skill in the art to make and use the inventions when the information in this patent is combined with available information and technology.

[0007] Various terms as used herein are shown below. To the extent a term used in a claim is not defined below, it should be given the broadest definition persons in the pertinent art have given that term as reflected in printed publications and issued patents. Further, unless otherwise specified, all compounds described herein may be substituted or unsubstituted and the listing of compounds includes derivatives thereof.

[0008] As used herein, the term "*fluorinated support*" refers to a support that includes fluorine or fluoride molecules (*e.g.*, incorporated therein or on the support surface.)

[0009] The term "*activity*" refers to the weight of product produced per weight of the catalyst used in a process per hour of reaction at a standard set of conditions (*e.g.*, grams product/gram catalyst/hr).

[0010] The term "*olefin*" refers to a hydrocarbon with a carbon-carbon double bond.

COS-1086 PCT Patent Application (as filed).doc

[0011] The term *"substituted"* refers to an atom, radical or group replacing hydrogen in a chemical compound.

[0012] The term *"tacticity"* refers to the arrangement of pendant groups in a polymer. For example, a polymer is "atactic" when its pendant groups are arranged in a random fashion on both sides of the chain of the polymer. In contrast, a polymer is "isotactic" when all of its pendant groups are arranged on the same side of the chain and "syndiotactic" when its pendant groups alternate on opposite sides of the chain.

[0013] The term *"C_s symmetry"* refers to a catalyst wherein the entire catalyst is symmetric with respect to a bisecting mirror plane passing through a bridging group and atoms bonded to the bridging group. The term "C_2 symmetry" refers to a catalyst wherein the ligand has an axis of C_2 symmetry passing through the bridging group.

[0014] The term *"bonding sequence"* refers to an elements sequence, wherein each element is connected to another by sigma bonds, dative bonds, ionic bonds or combinations thereof.

[0015] The term *"heterogeneous"* refers to processes wherein the catalyst system is in a different phase than one or more reactants in the process.

[0016] As used herein, *"room temperature"* means that a temperature difference of a few degrees does not matter to the phenomenon under investigation, such as a preparation method. In some environments, room temperature may include a temperature of from about 21°C to about 28°C (68°F to 72°F), for example. However, room temperature measurements generally do not include close monitoring of the temperature of the process and therefore such a recitation does not intend to bind the embodiments described herein to any predetermine temperature range.

[0017] Embodiments of the invention generally include methods of forming polyolefins. The methods generally include introducing a support composition and a transition metal compound, described in greater detail below, to a reaction zone. In one or more embodiments, the support composition has a bonding sequence selected from Si-O-Al-F, F-Si-O-Al or F-Si-O-Al-F, for example.

[0018] One or more embodiments further include identifying desired polymer properties and selecting a support material capable of producing the desired polymer properties.

COS-1086 PCT Patent Application (as filed).doc

Catalyst Systems

[0019] The support composition as used herein is an aluminum containing support material. For example, the support material may include an inorganic support composition. For example, the support material may include talc, inorganic oxides, clays and clay minerals, ion-exchanged layered compounds, diatomaceous earth compounds, zeolites or a resinous support material, such as a polyolefin, for example. Specific inorganic oxides include silica, alumina, magnesia, titania and zirconia, for example.

[0020] In one or more embodiments, the support composition is an aluminum containing silica support material. In one or more embodiments, the support composition is formed of spherical particles.

[0021] The aluminum containing silica support materials may have an average particle/pore size of from about 5 microns to 100 microns, or from about 15 microns to about 30 microns, or from about 10 microns to 100 microns or from about 10 microns to about 30 microns, a surface area of from 50 m^2/g to 1,000 m^2/g, or from about 80 m^2/g to about 800 m^2/g, or from 100 m^2/g to 400 m^2/g, or from about 200 m^2/g to about 300 m^2/g or from about 150 m^2/g to about 300 m^2/g and a pore volume of from about 0.1 cc/g to about 5 cc/g, or from about 0.5 cc/g to about 3.5 cc/g, or from about 0.5 cc/g to about 2.0 cc/g or from about 1.0 cc/g to about 1.5 cc/g, for example.

[0022] The aluminum containing silica support materials may further have an effective number or reactive hydroxyl groups, *e.g.*, a number that is sufficient for binding the fluorinating agent to the support material. For example, the number of reactive hydroxyl groups may be in excess of the number needed to bind the fluorinating agent to the support material. For example, the support material may include from about 0.1 mmol OH^-/g Si to about 5.0 mmol OH^-/g Si or from about 0.5 mmol OH^-/g Si to about 4.0 mmol OH^-/g Si.

[0023] The aluminum containing silica support materials are generally commercially available materials, such as P10 silica alumina that is commercially available from Fuji Silysia Chemical LTD, for example (*e.g.*, silica alumina having a surface area of 296 m^2/g and a pore volume of 1.4 ml/g.)

COS-1086 PCT Patent Application (as filed).doc

[0024] The aluminum containing silica support materials may further have an alumina content of from about 0.5 wt.% to about 95 wt%, of from about 0.1 wt.% to about 20 wt.%, or from about 0.1 wt.% to about 50 wt.%, or from about 1 wt.% to about 25 wt.% or from about 2 wt.% to about 8 wt.%, for example. The aluminum containing silica support materials may further have a silica to aluminum molar ratio of from about 0.01:1 to about 1000:1 or from about 10:1 to about 100:1, for example.

[0025] Alternatively, the aluminum containing silica support materials may be formed by contacting a silica support material with a first aluminum containing compound. Such contact may occur at a reaction temperature of from about room temperature to about 150°C, for example. The formation may further include calcining at a calcining temperature of from about 150°C to about 600°C, or from about 200°C to about 600°C or from about 35°C to about 500°C, for example. In one embodiment, the calcining occurs in the presence of an oxygen containing compound, for example.

[0026] In one or more embodiments, the support composition is prepared by a cogel method (*e.g.*, a gel including both silica and alumina.) As used herein, the term "cogel method" refers to a preparation process including mixing a solution including the first aluminum containing compound into a gel of silica (*e.g.*, $Al_2(SO_4) + H_2SO_4 + Na_2O\text{-}SiO_2$.)

[0027] The first aluminum containing compound may include an organic aluminum containing compound. The organic aluminum containing compound may be represented by the formula AlR_3, wherein each R is independently selected from alkyls, aryls and combinations thereof. The organic aluminum compound may include methyl alumoxane (MAO) or modified methyl alumoxane (MMAO), for example or, in a specific embodiment, triethyl aluminum (TEAl) or triisobutyl aluminum (TIBAl), for example.

[0028] The support composition is fluorinated by methods known to one skilled in the art. For example, the support composition may be contacted with a fluorinating agent to form the fluorinated support. The fluorination process may include contacting the support composition with the fluorine containing compound at a first temperature of from about 100°C to about 200°C or from about 125°C to about 175°C for a first time of from about 1 hour to about 10 hours or from about 1 hour to about 5 hours, for example and then raising the temperature to a second temperature of from

about 250°C to about 550°C or from about 400°C to about 500°C for a second time of from about 1 hour to about 10 hours or from about 1 hour to about 5 hours, for example.

[0029] As described herein, the "support composition" may be impregnated with aluminum prior to contact with the fluorinating agent, after contact with the fluorinating agent or simultaneously as contact with the fluorinating agent. In one embodiment, the fluorinated support composition is formed by simultaneously forming SiO_2 and Al_2O_3 and then contacting the SiO_2 and Al_2O_3 with the fluorinating agent. In another embodiment, the fluorinated support composition is formed by contacting an aluminum containing silica support material with the fluorinating agent. In yet another embodiment, the fluorinated support composition is formed by contacting a silica support material with the fluorinating agent and then contacting the fluorided support with the first aluminum containing compound.

[0030] The fluorinating agent generally includes any fluorinating agent which can form fluorinated supports. Suitable fluorinating agents include, but are not limited to, hydrofluoric acid (HF), ammonium fluoride (NH_4F), ammonium bifluoride (NH_4HF_2), ammonium fluoroborate (NH_4BF_4), ammonium silicofluoride ($(NH_4)_2SiF_6$), ammonium fluorophosphates (NH_4PF_6), $(NH_4)_2TaF_7$, NH_4NbF_4, $(NH_4)_2GeF_6$, $(NH_4)_2SmF_6$, $(NH_4)_2TiF_6$, $(NH_4)ZrF_6$, MoF_6, ReF_6, SO_2ClF, F_2, SiF_4, SF_6, ClF_3, ClF_5, BrF_5, IF_7, NF_3, HF, BF_3, NHF_2 and combinations thereof, for example. In one or more embodiments, the fluorinating agent is an ammonium fluoride including a metalloid or nonmetal (*e.g.*, $(NH_4)_2PF_6$, $(NH_4)_2BF_4$, $(NH_4)_2SiF_6$).

[0031] In one or more embodiments, the molar ratio of fluorine to the first aluminum containing compound ($F:Al^{(1)}$) is generally from about 0.5:1 to 6:1, or from about 0.5:1 to about 4:1 or from about 2.5:1 to about 3.5:1, for example.

[0032] Embodiments of the invention generally include contacting the fluorinated support with a transition metal compound to form a supported catalyst composition. The contact includes in situ activation/heterogenization of the transition metal compound. The term "in situ activation/heterogenization" refers to activation/formation of the catalyst at the point of contact between the support material and the transition metal compound. Such contact may occur in a reaction zone, either prior to, simultaneous with or after the introduction of one or more olefin monomers thereto.

COS-1086 PCT Patent Application (as filed).doc

[0033] Alternatively, the transition metal compound and the fluorinated support may be pre-contacted (contacted prior to entrance to a reaction zone) at a reaction temperature of from about -60°C to about 120°C or from about -45°C to about 100°C or at a reaction temperature below about 90°C, *e.g.*, from about 0°C to about 50°C, or from about 20°C to about 30°C or at room temperature, for example, for a time of from about 10 minutes to about 5 hours or from about 30 minutes to about 120 minutes, for example.

[0034] In addition, and depending on the desired degree of substitution, the weight ratio of fluorine to transition metal (F:M) is from about 1 equivalent to about 20 equivalents or from about 1 to about 5 equivalents, for example. In one embodiment, the supported catalyst composition includes from about 0.1 wt.% to about 5 wt.% or from about 0.5 wt.% to about 2.5 wt.% transition metal compound.

[0035] In one or more embodiments, the transition metal compound includes a metallocene catalyst, a late transition metal catalyst, a post metallocene catalyst or combinations thereof. Late transition metal catalysts may be characterized generally as transition metal catalysts including late transition metals, such as nickel, iron or palladium, for example. Post metallocene catalyst may be characterized generally as transition metal catalysts including Group IV, V or VI metals, for example.

[0036] Metallocene catalysts may be characterized generally as coordination compounds incorporating one or more cyclopentadienyl (Cp) groups (which may be substituted or unsubstituted, each substitution being the same or different) coordinated with a transition metal through π bonding.

[0037] The substituent groups on Cp may be linear, branched or cyclic hydrocarbyl radicals, for example. The cyclic hydrocarbyl radicals may further form other contiguous ring structures, including indenyl, azulenyl and fluorenyl groups, for example. These contiguous ring structures may also be substituted or unsubstituted by hydrocarbyl radicals, such as C_1 to C_{20} hydrocarbyl radicals, for example.

[0038] A specific, non-limiting, example of a metallocene catalyst is a bulky ligand metallocene compound generally represented by the formula:

$$[L]_mM[A]_n;$$

wherein L is a bulky ligand, A is a leaving group, M is a transition metal and m and n are such that the total ligand valency corresponds to the transition metal valency. For example, m may be from 1 to 4 and n may be from 1 to 3.

COS-1086 PCT Patent Application (as filed).doc

[0039] The metal atom "M" of the metallocene catalyst compound, as described throughout the specification and claims, may be selected from Groups 3 through 12 atoms and lanthanide Group atoms, or from Groups 3 through 10 atoms or from Sc, Ti, Zr, Hf, V, Nb, Ta, Mn, Re, Fe, Ru, Os, Co, Rh, Ir and Ni. The oxidation state of the metal atom "M" may range from 0 to +7 or is +1, +2, +3, +4 or +5, for example.

[0040] The bulky ligand generally includes a cyclopentadienyl group (Cp) or a derivative thereof. The Cp ligand(s) form at least one chemical bond with the metal atom M to form the "metallocene catalyst." The Cp ligands are distinct from the leaving groups bound to the catalyst compound in that they are not highly susceptible to substitution/abstraction reactions.

[0041] Cp ligands may include ring(s) or ring system(s) including atoms selected from group 13 to 16 atoms, such as carbon, nitrogen, oxygen, silicon, sulfur, phosphorous, germanium, boron, aluminum and combinations thereof, wherein carbon makes up at least 50% of the ring members. Non-limiting examples of the ring or ring systems include cyclopentadienyl, cyclopentaphenanthreneyl, indenyl, benzindenyl, fluorenyl, tetrahydroindenyl, octahydrofluorenyl, cyclooctatetraenyl, cyclopentacyclododecene, phenanthrindenyl, 3,4-benzofluorenyl, 9-phenylfluorenyl, 8-H-cyclopent[a]acenaphthylenyl, 7-H-dibenzofluorenyl, indeno[1,2-9]anthrene, thiophenoindenyl, thiophenofluorenyl, hydrogenated versions thereof (*e.g.*, 4,5,6,7-tetrahydroindenyl or "H_4Ind"), substituted versions thereof and heterocyclic versions thereof, for example.

[0042] Cp substituent groups may include hydrogen radicals, alkyls (*e.g.*, methyl, ethyl, propyl, butyl, pentyl, hexyl, luoromethyl, fluroethyl, difluroethyl, iodopropyl, bromohexyl, benzyl, phenyl, methylphenyl, tert-butylphenyl, chlorobenzyl, dimethylphosphine and methylphenylphosphine), alkenyls (*e.g.*, 3-butenyl, 2-propenyl and 5-hexenyl), alkynyls, cycloalkyls (*e.g.*, cyclopentyl and cyclohexyl), aryls (*e.g.*, trimethylsilyl, trimethylgermyl, methyldiethylsilyl, acyls, aroyls, tris(trifluoromethyl)silyl, methylbis(difluoromethyl)silyl and bromomethyldimethylgermyl), alkoxys (*e.g.*, methoxy, ethoxy, propoxy and phenoxy), aryloxys, alkylthiols, dialkylamines (*e.g.*, dimethylamine and diphenylamine), alkylamidos, alkoxycarbonyls, aryloxycarbonyls, carbomoyls, alkyl- and dialkyl-carbamoyls, acyloxys, acylaminos, aroylaminos, organometalloid radicals (*e.g.*, dimethylboron), Group 15 and Group 16 radicals (*e.g.*, methylsulfide and

ethylsulfide) and combinations thereof, for example. In one embodiment, at least two substituent groups, two adjacent substituent groups in one embodiment, are joined to form a ring structure.

[0043] Each leaving group "A" is independently selected and may include any ionic leaving group, such as halogens (*e.g.*, chloride and fluoride), hydrides, C_1 to C_{12} alkyls (*e.g.*, methyl, ethyl, propyl, phenyl, cyclobutyl, cyclohexyl, heptyl, tolyl, trifluoromethyl, methylphenyl, dimethylphenyl and trimethylphenyl), C_2 to C_{12} alkenyls (*e.g.*, C_2 to C_6 fluoroalkenyls), C_6 to C_{12} aryls (*e.g.*, C_7 to C_{20} alkylaryls), C_1 to C_{12} alkoxys (*e.g.*, phenoxy, methyoxy, ethyoxy, propoxy and benzoxy), C_6 to C_{16} aryloxys, C_7 to C_{18} alkylaryloxys and C_1 to C_{12} heteroatom-containing hydrocarbons and substituted derivatives thereof, for example.

[0044] Other non-limiting examples of leaving groups include amines, phosphines, ethers, carboxylates (*e.g.*, C_1 to C_6 alkylcarboxylates, C_6 to C_{12} arylcarboxylates and C_7 to C_{18} alkylarylcarboxylates), dienes, alkenes (*e.g.*, tetramethylene, pentamethylene, methylidene), hydrocarbon radicals having from 1 to 20 carbon atoms (*e.g.*, pentafluorophenyl) and combinations thereof, for example. In one embodiment, two or more leaving groups form a part of a fused ring or ring system.

[0045] In a specific embodiment, L and A may be bridged to one another to form a bridged metallocene catalyst. A bridged metallocene catalyst, for example, may be described by the general formula:

$$XCp^ACp^BMA_n;$$

wherein X is a structural bridge, Cp^A and Cp^B each denote a cyclopentadienyl group, each being the same or different and which may be either substituted or unsubstituted, M is a transition metal and A is an alkyl, hydrocarbyl or halogen group and n is an integer between 0 and 4, and either 1 or 2 in a particular embodiment.

[0046] Non-limiting examples of bridging groups "X" include divalent hydrocarbon groups containing at least one Group 13 to 16 atom, such as, but not limited to, at least one of a carbon, oxygen, nitrogen, silicon, aluminum, boron, germanium, tin and combinations thereof; wherein the heteroatom may also be a C_1 to C_{12} alkyl or aryl group substituted to satisfy a neutral valency. The bridging group may also contain substituent groups as defined above including halogen radicals and iron. More particular non-limiting examples of bridging group are represented by C_1

to C_6 alkylenes, substituted C_1 to C_6 alkylenes, oxygen, sulfur, $R_2C=$, $R_2Si=$, --$Si(R)_2Si(R_2)$--, $R_2Ge=$ or $RP=$ (wherein "=" represents two chemical bonds), where R is independently selected from hydrides, hydrocarbyls, halocarbyls, hydrocarbyl-substituted organometalloids, halocarbyl-substituted organometalloids, disubstituted boron atoms, disubstituted Group 15 atoms, substituted Group 16 atoms and halogen radicals, for example. In one embodiment, the bridged metallocene catalyst component has two or more bridging groups.

[0047] Other non-limiting examples of bridging groups include methylene, ethylene, ethylidene, propylidene, isopropylidene, diphenylmethylene, 1,2-dimethylethylene, 1,2-diphenylethylene, 1,1,2,2-tetramethylethylene, dimethylsilyl, diethylsilyl, methyl-ethylsilyl, trifluoromethylbutylsilyl, bis(trifluoromethyl)silyl, di(n-butyl)silyl, di(n-propyl)silyl, di(i-propyl)silyl, di(n-hexyl)silyl, dicyclohexylsilyl, diphenylsilyl, cyclohexylphenylsilyl, t-butylcyclohexylsilyl, di(t-butylphenyl)silyl, di(p-tolyl)silyl and the corresponding moieties, wherein the Si atom is replaced by a Ge or a C atom; dimethylsilyl, diethylsilyl, dimethylgermyl and/or diethylgermyl.

[0048] In another embodiment, the bridging group may also be cyclic and include 4 to 10 ring members or 5 to 7 ring members, for example. The ring members may be selected from the elements mentioned above and/or from one or more of boron, carbon, silicon, germanium, nitrogen and oxygen, for example. Non-limiting examples of ring structures which may be present as or part of the bridging moiety are cyclobutylidene, cyclopentylidene, cyclohexylidene, cycloheptylidene, cyclooctylidene, for example. The cyclic bridging groups may be saturated or unsaturated and/or carry one or more substituents and/or be fused to one or more other ring structures. The one or more Cp groups which the above cyclic bridging moieties may optionally be fused to may be saturated or unsaturated. Moreover, these ring structures may themselves be fused, such as, for example, in the case of a naphthyl group.

[0049] In one embodiment, the metallocene catalyst includes CpFlu Type catalysts (*e.g.*, a metallocene catalyst wherein the ligand includes a Cp fluorenyl ligand structure) represented by the following formula:

$$X(CpR^1{}_nR^2{}_m)(FlR^3{}_p);$$

wherein Cp is a cyclopentadienyl group, Fl is a fluorenyl group, X is a structural bridge between Cp and Fl, R^1 is a substituent on the Cp, n is 1 or 2, R^2 is a substituent

on the Cp at a position which is ortho to the bridge, m is 1 or 2, each R^3 is the same or different and is a hydrocarbyl group having from 1 to 20 carbon atoms with at least one R^3 being substituted in the para position on the fluorenyl group and at least one other R^3 being substituted at an opposed para position on the fluorenyl group and p is 2 or 4.

[0050] In yet another aspect, the metallocene catalyst includes bridged mono-ligand metallocene compounds (*e.g.*, mono cyclopentadienyl catalyst components). In this embodiment, the metallocene catalyst is a bridged "half-sandwich" metallocene catalyst. In yet another aspect of the invention, the at least one metallocene catalyst component is an unbridged "half sandwich" metallocene. (*See*, U.S. Pat. No. 6,069,213, U.S. Pat. No. 5,026,798, U.S. Pat. No. 5,703,187, U.S. Pat. No. 5,747,406, U.S. Pat. No. 5,026,798 and U.S. Pat. No. 6,069,213, which are incorporated by reference herein.)

[0051] Non-limiting examples of metallocene catalyst components consistent with the description herein include, for example cyclopentadienylzirconiumA_n; indenylzirconiumA_n; (1-methylindenyl)zirconiumA_n; (2-methylindenyl)zirconiumA_n, (1-propylindenyl)zirconiumA_n; (2-propylindenyl)zirconiumA_n; (1-butylindenyl)zirconiumA_n; (2-butylindenyl)zirconiumA_n; methylcyclopentadienylzirconiumA_n; tetrahydroindenylzirconiumA_n; pentamethylcyclopentadienylzirconiumA_n; cyclopentadienylzirconiumA_n; pentamethylcyclopentadienyltitaniumA_n; tetramethylcyclopentyltitaniumA_n; (1,2,4-trimethylcyclopentadienyl)zirconiumA_n; dimethylsilyl(1,2,3,4-tetramethylcyclopentadienyl)(cyclopentadienyl)zirconiumA_n; dimethylsilyl(1,2,3,4-tetramethylcyclopentadienyl)(1,2,3-trimethylcyclopentadienyl)zirconiumA_n; dimethylsilyl(1,2,3,4-tetramethylcyclopentadienyl)(1,2-dimethylcyclopentadienyl)zirconiumA_n; dimethylsilyl(1,2,3,4-tetramethylcyclopentadienyl)(2-methylcyclopentadienyl)zirconiumA_n; dimethylsilylcyclopentadienylindenylzirconiumA_n; dimethylsilyl(2-methylindenyl)(fluorenyl)zirconiumA_n; diphenylsilyl(1,2,3,4-tetramethylcyclopentadienyl)(3-propylcyclopentadienyl)zirconiumA_n; dimethylsilyl (1,2,3,4-tetramethylcyclopentadienyl) (3-t-butylcyclopentadienyl)zirconiumA_n; dimethylgermyl(1,2-dimethylcyclopentadienyl)(3-isopropylcyclopentadienyl)zirconiumA_n; dimethylsilyl(1,2,3,4-

tetramethylcyclopentadienyl)(3-methylcyclopentadienyl)zirconiumA_n; diphenylmethylidene(cyclopentadienyl)(9-fluorenyl)zirconiumA_n; diphenylmethylidenecyclopentadienylindenylzirconiumA_n; isopropylidenebiscyclopentadienylzirconiumA_n; isopropylidene(cyclopentadienyl)(9-fluorenyl)zirconiumA_n; isopropylidene(3-methylcyclopentadienyl)(9-fluorenyl)zirconiumA_n; ethylenebis(9-fluorenyl)zirconiumA_n; ethylenebis(1-indenyl)zirconiumA_n; ethylenebis(1-indenyl)zirconiumA_n; ethylenebis(2-methyl-1-indenyl)zirconiumA_n; ethylenebis(2-methyl-4,5,6,7-tetrahydro-1-indenyl)zirconiumA_n; ethylenebis(2-propyl-4,5,6,7-tetrahydro-1-indenyl)zirconiumA_n; ethylenebis(2-isopropyl-4,5,6,7-tetrahydro-1-indenyl)zirconiumA_n; ethylenebis(2-butyl-4,5,6,7-tetrahydro-1-indenyl)zirconiumA_n; ethylenebis(2-isobutyl-4,5,6,7-tetrahydro-1-indenyl)zirconiumA_n; dimethylsilyl(4,5,6,7-tetrahydro-1-indenyl)zirconiumA_n; diphenyl(4,5,6,7-tetrahydro-1-indenyl)zirconiumA_n; ethylenebis(4,5,6,7-tetrahydro-1-indenyl)zirconiumA_n; dimethylsilylbis(cyclopentadienyl)zirconiumA_n; dimethylsilylbis(9-fluorenyl)zirconiumA_n; dimethylsilylbis(1-indenyl)zirconiumA_n; dimethylsilylbis(2-methylindenyl)zirconiumA_n; dimethylsilylbis(2-propylindenyl)zirconiumA_n; dimethylsilylbis(2-butylindenyl)zirconiumA_n; diphenylsilylbis(2-methylindenyl)zirconiumA_n; diphenylsilylbis(2-propylindenyl)zirconiumA_n; diphenylsilylbis(2-butylindenyl)zirconiumA_n; dimethylgermylbis(2-methylindenyl)zirconiumA_n; dimethylsilylbistetrahydroindenylzirconiumA_n; dimethylsilylbistetramethylcyclopentadienylzirconiumA_n; dimethylsilyl(cyclopentadienyl)(9-fluorenyl)zirconiumA_n; diphenylsilyl(cyclopentadienyl)(9-fluorenyl)zirconiumA_n; diphenylsilylbisindenylzirconiumA_n; cyclotrimethylenesilyltetramethylcyclopentadienylcyclopentadienylzirconiumA_n; cyclotetramethylenesilyltetramethylcyclopentadienylcyclopentadienylzirconiumA_n; cyclotrimethylenesilyl(tetramethylcyclopentadienyl)(2-methylindenyl)zirconiumA_n; cyclotrimethylenesilyl(tetramethylcyclopentadienyl)(3-methylcyclopentadienyl)zirconiumA_n; cyclotrimethylenesilylbis(2-methylindenyl)zirconiumA_n; cyclotrimethylenesilyl(tetramethylcyclopentadienyl)(2,3,5-trimethylclopentadienyl)zirconiumA_n;

COS-1086 PCT Patent Application (as filed).doc

cyclotrimethylenesilylbis(tetramethylcyclopentadienyl)zirconiumA_n;
dimethylsilyl(tetramethylcyclopentadieneyl)(N-tertbutylamido)titaniumA_n;
biscyclopentadienylchromiumA_n; biscyclopentadienylzirconiumA_n; bis(n-butylcyclopentadienyl)zirconiumA_n; bis(n-dodecyclcyclopentadienyl)zirconiumA_n;
bisethylcyclopentadienylzirconiumA_n; bisisobutylcyclopentadienylzirconiumA_n;
bisisopropylcyclopentadienylzirconiumA_n; bismethylcyclopentadienylzirconiumA_n;
bisnoxtylcyclopentadienylzirconiumA_n; bis(n-pentylcyclopentadienyl)zirconiumA_n;
bis(n-propylcyclopentadienyl)zirconiumA_n;
bistrimethylsilylcyclopentadienylzirconiumA_n; bis(1,3-bis(trimethylsilyl)cyclopentadienyl)zirconiumA_n; bis(1-ethyl-2-methylcyclopentadienyl)zirconiumA_n; bis(1-ethyl-3-methylcyclopentadienyl)zirconiumA_n; bispentamethylcyclopentadienylzirconiumA_n;
bispentamethylcyclopentadienylzirconiumA_n; bis(1-propyl-3-methylcyclopentadienyl)zirconiumA_n; bis(1-n-butyl-3-methylcyclopentadienyl)zirconiumA_n; bis(1-isobutyl-3-methylcyclopentadienyl)zirconiumA_n; bis(1-propyl-3-butylcyclopentadienyl)zirconiumA_n; bis(1,3-n-butylcyclopentadienyl)zirconiumA_n;
bis(4,7-dimethylindenyl)zirconiumA_n; bisindenylzirconiumA_n; bis(2-methylindenyl)zirconiumA_n; cyclopentadienylindenylzirconiumA_n; bis(n-propylcyclopentadienyl)hafniumA_n; bis(n-butylcyclopentadienyl)hafniumA_n; bis(n-pentylcyclopentadienyl)hafniumA_n; (n-propylcyclopentadienyl)(n-butylcyclopentadienyl)hafniumA_n; bis[(2-trimethylsilylethyl)cyclopentadienyl]hafniumA_n;
bis(trimethylsilylcyclopentadienyl)hafniumA_n; bis(2-n-propylindenyl)hafniumA_n;
bis(2-n-butylindenyl)hafniumA_n; dimethylsilylbis(n-propylcyclopentadienyl)hafniumA_n; dimethylsilylbis(n-butylcyclopentadienyl)hafniumA_n; bis(9-n-propylfluorenyl)hafniumA_n; bis(9-n-butylfluorenyl)hafniumA_n; (9-n-propylfluorenyl)(2-n-propylindenyl)hafniumA_n;
bis(1-n-propyl-2-methylcyclopentadienyl)hafniumA_n; (n-propylcyclopentadienyl)(1-n-propyl-3-n-butylcyclopentadienyl)hafniumA_n;
dimethylsilyltetramethylcyclopentadienylcyclopropylamidotitaniumA_n;
dimethylsilyltetramethyleyclopentadienylcyclobutylamidotitaniumA_n;
dimethylsilyltetramethyleyclopentadienylcyclopentylamidotitaniumA_n;

COS-1086 PCT Patent Application (as filed).doc

dimethylsilyltetramethylcyclopentadienylcyclohexylamidotitaniumA_n;
dimethylsilyltetramethylcyclopentadienylcycloheptylamidotitaniumA_n;
dimethylsilyltetramethylcyclopentadienylcyclooctylamidotitaniumA_n;
dimethylsilyltetramethylcyclopentadienylcyclononylamidotitaniumA_n;
dimethylsilyltetramethylcyclopentadienylcyclodecylamidotitaniumA_n;
dimethylsilyltetramethylcyclopentadienylcycloundecylamidotitaniumA_n;
dimethylsilyltetramethylcyclopentadienylcyclododecylamidotitaniumA_n;
dimethylsilyltetramethylcyclopentadienyl(sec-butylamido)titaniumA_n;
dimethylsilyl(tetramethylcyclopentadienyl)(n-octylamido)titaniumA_n;
dimethylsilyl(tetramethylcyclopentadienyl)(n-decylamido)titaniumA_n;
dimethylsilyl(tetramethylcyclopentadienyl)(n-octadecylamido)titaniumA_n;
dimethylsilylbis(cyclopentadienyl)zirconiumA_n;
dimethylsilylbis(tetramethylcyclopentadienyl)zirconiumA_n;
dimethylsilylbis(methylcyclopentadienyl)zirconiumA_n;
dimethylsilylbis(dimethylcyclopentadienyl)zirconiumA_n; dimethylsilyl(2,4-dimethylcyclopentadienyl) (3',5'-dimethylcyclopentadienyl)zirconiumA_n;
dimethylsilyl(2,3,5-trimethylcyclopentadienyl)(2',4',5'-dimethylcyclopentadienyl)zirconiumA_n; dimethylsilylbis(t-butylcyclopentadienyl)zirconiumA_n;
dimethylsilylbis(trimethylsilylcyclopentadienyl)zirconiumA_n; dimethylsilylbis(2-trimethylsilyl-4-t-butylcyclopentadienyl)zirconiumA_n; dimethylsilylbis(4,5,6,7-tetrahydro-indenyl)zirconiumA_n; dimethylsilylbis(indenyl)zirconiumA_n;
dimethylsilylbis(2-methylindenyl)zirconiumA_n; dimethylsilylbis(2,4-dimethylindenyl)zirconiumA_n; dimethylsilylbis(2,4,7-trimethylindenyl)zirconiumA_n;
dimethylsilylbis(2-methyl-4-phenylindenyl)zirconiumA_n; dimethylsilylbis(2-ethyl-4-phenylindenyl)zirconiumA_n; dimethylsilylbis(benz[e]indenyl)zirconiumA_n;
dimethylsilylbis(2-methylbenz[e]indenyl)zirconiumA_n;
dimethylsilylbis(benz[f]indenyl)zirconiumA_n; dimethylsilylbis(2-methylbenz[f]indenyl)zirconiumA_n; dimethylsilylbis(3-methylbenz[f]indenyl)zirconiumA_n;
dimethylsilylbis(cyclopenta[cd]indenyl)zirconiumA_n;
dimethylsilylbis(cyclopentadienyl)zirconiumA_n;
dimethylsilylbis(tetramethylcyclopentadienyl)zirconiumA_n;

COS-1086 PCT Patent Application (as filed).doc

dimethylsilylbis(methylcyclopentadienyl)zirconiumA_n;
dimethylsilylbis(dimethylcyclopentadienyl)zirconiumA_n;
isopropylidene(cyclopentadienyl-fluorenyl)zirconiumA_n;
isopropylidene(cyclopentadienyl-indenyl)zirconiumA_n;
isopropylidene(cyclopentadienyl-2,7-di-t-butylfluorenyl)zirconiumA_n;
isopropylidene(cyclopentadienyl-3-methylfluorenyl)zirconiumA_n;
isoropylidene(cyclopentadienyl-4-methylfluorenyl)zirconiumA_n;
isopropylidene(cyclopentadienyl-octahydrofluorenyl)zirconiumA_n;
isopropylidene(methylcyclopentadienyl- fluorenyl)zirconiumA_n;
isopropylidene(dimethylcyclopentadienylfluorenyl)zirconiumA_n;
isopropylidene(tetramethylcyclopentadienyl-fluorenyl)zirconiumA_n;
diphenylmethylene(cyclopentadienyl-fluorenyl)zirconiumA_n;
diphenylmethylene(cyclopentadienyl-indenyl)zirconiumA_n;
diphenylmethylene(cyclopentadienyl-2,7-di-t-butylfluorenyl)zirconiumA_n;
diphenylmethylene(cyclopentadienyl-3-methylfluorenyl)zirconiumA_n;
diphenylmethylene(cyclopentadienyl-4-methylfluorenyl)zirconiumA_n;
diphenylmethylene(cyclopentadienyloctahydrofluorenyl)zirconiumA_n;
diphenylmethylene(methylcyclopentadienyl-fluorenyl)zirconiumA_n;
diphenylmethylene(dimethylcyclopentadienyl-fluorenyl)zirconiumA_n;
diphenylmethylene(tetramethylcyclopentadienyl-fluorenyl)zirconiumA_n;
cyclohexylidene(cyclopentadienyl-fluorenyl)zirconiumA_n;
cyclohexylidene(cyclopentadienylindenyl)zirconiumA_n;
cyclohexylidene(cyclopentadienyl-2,7-di-t-butylfluorenyl)zirconiumA_n;
cyclohexylidene(cyclopentadienyl-3-methylfluorenyl)zirconiumA_n;
cyclohexylidene(cyclopentadienyl-4-methylfluorenyl)zirconiumA_n;
cyclohexylidene(cyclopentadienyloctahydrofluorenyl)zirconiumA_n;
cyclohexylidene(methylcyclopentadienylfluorenyl)zirconiumA_n;
cyclohexylidene(dimethylcyclopentadienyl-fluorenyl)zirconiumA_n;
cyclohexylidene(tetramethylcyclopentadienylfluorenyl)zirconiumA_n;
dimethylsilyl(cyclopentadienyl-fluorenyl)zirconiumA_n;
dimethylsilyl(cyclopentadienyl-indenyl)zirconiumA_n; dimethylsilyl(cyclopentdienyl-2,7-di-t-butylfluorenyl)zirconiumA_n; dimethylsilyl(cyclopentadienyl-3-methylfluorenyl)zirconiumA_n; dimethylsilyl(cyclopentadienyl-4-

COS-1086 PCT Patent Application (as filed).doc

methylfluorenyl)zirconiumA_n; dimethylsilyl(cyclopentadienyl-octahydrofluorenyl)zirconiumA_n; dimethylsilyl(methylcyclopentanedienyl-fluorenyl)zirconiumA_n;

dimethylsilyl(dimethylcyclopentadienylfluorenyl)zirconiumA_n;

dimethylsilyl(tetramethylcyclopentadienylfluorenyl)zirconiumA_n;

isopropylidene(cyclopentadienyl-fluorenyl)zirconiumA_n;

isopropylidene(cyclopentadienyl-indenyl)zirconiumA_n;

isopropylidene(cyclopentadienyl-2,7-di-t-butylfluorenyl)zirconiumA_n;

cyclohexylidene(cyclopentadienylfluorenyl)zirconiumA_n;

cyclohexylidene(cyclopentadienyl-2,7-di-t-butylfluorenyl)zirconiumA_n;

dimethylsilyl(cyclopentadienylfluorenyl)zirconiumA_n;

methylphenylsilyltetramethylcyclopentadienylcyclopropylamidotitaniumA_n;

methylphenylsilyltetramethylcyclopentadienylcyclobutylamidotitaniumA_n;

methylphenylsilyltetramethylcyclopentadienylcyclopentylamidotitaniumA_n;

methylphenylsilyltetramethylcyclopentadienylcyclohexylamidotitaniumA_n;

methylphenylsilyltetramethylcyclopentadienylcycloheptylamidotitaniumA_n;

methylphenylsilyltetramethylcyclopentadienylcyclooctylamidotitaniumA_n;

methylphenylsilyltetramethylcyclopentadienylcyclononylamidotitaniumA_n;

methylphenylsilyltetramethylcyclopentadienylcyclodecylamidotitaniumA_n;

methylphenylsilyltetramethylcyclopentadienylcycloundecylamidotitaniumA_n;

methylphenylsilyltetramethylcyclopentadienylcyclododecylamidotitaniumA_n;

methylphenylsilyl(tetramethylcyclopentadienyl)(sec-butylamido)titaniumA_n;

methylphenylsilyl(tetramethylcyclopentadienyl)(n-octylamido)titaniumA_n;

methylphenylsilyl(tetramethylcyclopentadienyl)(n-decylamido)titaniumA_n;

methylphenylsilyl(tetramethylcyclopentadienyl)(n-octadecylamido)titaniumA_n;

diphenylsilyltetramethylcyclopentadienylcyclopropylamidotitaniumA_n;

diphenylsilyltetramethylcyclopentadienylcyclobutylamidotitaniumA_n;

diphenylsilyltetramethylcyclopentadienylcyclopentylamidotitaniumA_n;

diphenylsilyltetramethylcyclopentadienylcyclohexylamidotitaniumA_n;

diphenylsilyltetramethylcyclopentadienylcycloheptylamidotitaniumA_n;

diphenylsilyltetramethylcyclopentadienylcyclooctylamidotitaniumA_n;

diphenylsilyltetramethylcyclopentadienylcyclononylamidotitaniumA_n;

diphenylsilyltetramethylcyclopentadienylcyclodecylamidotitaniumA_n;

diphenylsilyltetramethylcyclopentadienylcycloundecylamidotitaniumA_n;
diphenylsilyltetramethylcyclopentadienylcyclododecylamidotitaniumA_n;
diphenylsilyl(tetramethylcyclopentadienyl)(sec-butylamido)titaniumA_n;
diphenylsilyl(tetramethylcyclopentadienyl)(n-octylamido)titaniumA_n;
diphenylsilyl(tetramethylcyclopentadienyl)(n-decylamido)titaniumA_n; and
diphenylsilyl(tetramethylcyclopentadienyl)(n-octadecylamido)titaniumA_n.

[0052] In one or more embodiments, the transition metal compound includes cyclopentadienyl, indenyl, fluorenyl, tetrahydroindenyl, CpFlu, alkyls, aryls, amides or combinations thereof. In one or more embodiments, the transition metal compound includes a transition metal dichloride, dimethyl or hydride. In one or more embodiments, the transition metal compound may have C_1, C_s or C_2 symmetry, for example. In one specific embodiment, the transition metal compound includes rac-dimethylsilanylbis(2-methyl-4-phenyl-1-indenyl)zirconium dichloride.

[0053] One or more embodiments may further include contacting the fluorinated support with a plurality of catalyst compounds (*e.g.*, a bimetallic catalyst.) As used herein, the term "bimetallic catalyst" means any composition, mixture or system that includes at least two different catalyst compounds, each having a different metal group. Each catalyst compound may reside on a single support particle so that the bimetallic catalyst is a supported bimetallic catalyst. However, the term bimetallic catalyst also broadly includes a system or mixture in which one of the catalysts resides on one collection of support particles and another catalyst resides on another collection of support particles. The plurality of catalyst components may include any catalyst component known to one skilled in the art, so long as at least one of those catalyst components includes a transition metal compound as described herein.

[0054] As demonstrated in the examples that follow, contacting the fluorinated support with the transition metal ligand via the methods described herein unexpectedly results in a supported catalyst composition that is active without alkylation processes (*e.g.*, contact of the catalyst component with an organometallic compound, such as MAO.) Further, the embodiments of the invention provide processes that exhibit increased activity over processes utilizing MAO based catalyst systems.

[0055] The absence of substances, such as MAO, generally results in lower polymer production costs as alumoxanes are expensive compounds. Further,

alumoxanes are generally unstable compounds that are generally stored in cold storage. However, embodiments of the present invention unexpectedly result in a catalyst composition that may be stored at room temperature for periods of time (*e.g.*, up to 2 months) and then used directly in polymerization reactions. Such storage ability further results in improved catalyst variability as a large batch of support material may be prepared and contacted with a variety of transition metal compounds (which may be formed in small amounts and optimized based on the polymer to be formed.)

[0056] In addition, it is contemplated that polymerizations absent alumoxane activators result in minimal leaching/fouling in comparison with alumoxane based systems. However, embodiments of the invention generally provide processes wherein alumoxanes may be included without detriment.

[0057] Optionally, the fluorinated support and/or the transition metal compound may be contacted with a second aluminum containing compound prior to contact with one another. In one embodiment, the fluorinated support is contacted with the second aluminum containing compound prior to contact with the transition metal compound. Alternatively, the fluorinated support may be contacted with the transition metal compound in the presence of the second aluminum containing compound.

[0058] For example, the contact may occur by contacting the fluorinated support with the second aluminum containing compound at a reaction temperature of from about 0°C to about 150°C or from about 20°C to about 100°C for a time of from about 10 minutes hour to about 5 hours or from about 30 minutes to about 120 minutes, for example.

[0059] The second aluminum containing compound may include an organic aluminum compound. The organic aluminum compound may include TEAl, TIBAl, MAO or MMAO, for example. In one embodiment, the organic aluminum compound may be represented by the formula AlR_3, wherein each R is independently selected from alkyls, aryls or combinations thereof.

[0060] In one embodiment, the weight ratio of the silica to the second aluminum containing compound (SiO_2:$Al^{(2)}$) is generally from about 0.01:1 to about 10:1 or from about 0.05:1 to about 8:1, for example

[0061] While it has been observed that contacting the fluorinated support with the second aluminum containing compound results in a catalyst having increased activity,

it is contemplated that the second aluminum containing compound may contact the transition metal compound. When the second aluminum containing compound contacts the transition metal compound, the weight ratio of the second aluminum containing compound to transition metal ($Al^{(2)}$:M) is from about 0.1:1 to about 5000:1 or from about 1:1 to about 1000:1, for example.

[0062] Optionally, the fluorinated support may be contacted with one or more scavenging compounds prior to or during polymerization. The term "scavenging compounds" is meant to include those compounds effective for removing impurities (*e.g.*, polar impurities) from the subsequent polymerization reaction environment. Impurities may be inadvertently introduced with any of the polymerization reaction components, particularly with solvent, monomer and catalyst feed, and adversely affect catalyst activity and stability. Such impurities may result in decreasing, or even elimination, of catalytic activity, for example. The polar impurities or catalyst poisons may include water, oxygen and metal impurities, for example.

[0063] The scavenging compound may include an excess of the first or second aluminum compounds described above, or may be additional known organometallic compounds, such as Group 13 organometallic compounds. For example, the scavenging compounds may include triethyl aluminum (TMA), triisobutyl aluminum (TIBAl), methylalumoxane (MAO), isobutyl aluminoxane and tri-n-octyl aluminum. In one specific embodiment, the scavenging compound is TIBAl.

[0064] In one embodiment, the amount of scavenging compound is minimized during polymerization to that amount effective to enhance activity and avoided altogether if the feeds and polymerization medium may be sufficiently free of impurities. In another embodiment, the process doesn't include any scavenging compound, such as embodiments employing second aluminum compounds, for example.

Polymerization Processes

[0065] As indicated elsewhere herein, catalyst systems are used to form polyolefin compositions. Once the catalyst system is prepared, as described above and/or as known to one skilled in the art, a variety of processes may be carried out using that composition. The equipment, process conditions, reactants, additives and other materials used in polymerization processes will vary in a given process,

depending on the desired composition and properties of the polymer being formed. Such processes may include solution phase, gas phase, slurry phase, bulk phase, high pressure processes or combinations thereof, for example. (*See*, U.S. Patent No. 5,525,678, U.S. Patent No. 6,420,580, U.S. Patent No. 6,380,328, U.S. Patent No. 6,359,072, U.S. Patent No. 6,346,586, U.S. Patent No. 6,340,730, U.S. Patent No. 6,339,134, U.S. Patent No. 6,300,436, U.S. Patent No. 6,274,684, U.S. Patent No. 6,271,323, U.S. Patent No. 6,248,845, U.S. Patent No. 6,245,868, U.S. Patent No. 6,245,705, U.S. Patent No. 6,242,545, U.S. Patent No. 6,211,105, U.S. Patent No. 6,207,606, U.S. Patent No. 6,180,735 and U.S. Patent No. 6,147,173, which are incorporated by reference herein.)

[0066] In certain embodiments, the processes described above generally include polymerizing olefin monomers to form polymers. The olefin monomers may include C_2 to C_{30} olefin monomers, or C_2 to C_{12} olefin monomers (*e.g.*, ethylene, propylene, butene, pentene, methylpentene, hexene, octene and decene), for example. Other monomers include ethylenically unsaturated monomers, C_4 to C_{18} diolefins, conjugated or nonconjugated dienes, polyenes, vinyl monomers and cyclic olefins, for example. Non-limiting examples of other monomers may include norbornene, nobornadiene, isobutylene, isoprene, vinylbenzocyclobutane, sytrene, alkyl substituted styrene, ethylidene norbornene, dicyclopentadiene and cyclopentene, for example. The formed polymer may include homopolymers, copolymers or terpolymers, for example.

[0067] Examples of solution processes are described in U.S. Patent No. 4,271,060, U.S. Patent No. 5,001,205, U.S. Patent No. 5,236,998 and U.S. Patent No. 5,589,555, which are incorporated by reference herein.

[0068] One example of a gas phase polymerization process includes a continuous cycle system, wherein a cycling gas stream (otherwise known as a recycle stream or fluidizing medium) is heated in a reactor by heat of polymerization. The heat is removed from the cycling gas stream in another part of the cycle by a cooling system external to the reactor. The cycling gas stream containing one or more monomers may be continuously cycled through a fluidized bed in the presence of a catalyst under reactive conditions. The cycling gas stream is generally withdrawn from the fluidized bed and recycled back into the reactor. Simultaneously, polymer product may be

withdrawn from the reactor and fresh monomer may be added to replace the polymerized monomer. The reactor pressure in a gas phase process may vary from about 100 psig to about 500 psig, or from about 200 psig to about 400 psig or from about 250 psig to about 350 psig, for example. The reactor temperature in a gas phase process may vary from about 30°C to about 120°C, or from about 60°C to about 115°C, or from about 70°C to about 110°C or from about 70°C to about 95°C, for example. (*See*, for example, U.S. Patent No. 4,543,399, U.S. Patent No. 4,588,790, U.S. Patent No. 5,028,670, U.S. Patent No. 5,317,036, U.S. Patent No. 5,352,749, U.S. Patent No. 5,405,922, U.S. Patent No. 5,436,304, U.S. Patent No. 5,456,471, U.S. Patent No. 5,462,999, U.S. Patent No. 5,616,661, U.S. Patent No. 5,627,242, U.S. Patent No. 5,665,818, U.S. Patent No. 5,677,375 and U.S. Patent No. 5,668,228, which are incorporated by reference herein.) In one embodiment, the polymerization process is a gas phase process and the transition metal compound used to form the supported catalyst composition is CpFlu.

[0069] Slurry phase processes generally include forming a suspension of solid, particulate polymer in a liquid polymerization medium, to which monomers and optionally hydrogen, along with catalyst, are added. The suspension (which may include diluents) may be intermittently or continuously removed from the reactor where the volatile components can be separated from the polymer and recycled, optionally after a distillation, to the reactor. The liquefied diluent employed in the polymerization medium may include a C_3 to C_7 alkane (*e.g.*, hexane or isobutane), for example. The medium employed is generally liquid under the conditions of polymerization and relatively inert. A bulk phase process is similar to that of a slurry process. However, a process may be a bulk process, a slurry process or a bulk slurry process, for example.

[0070] In a specific embodiment, a slurry process or a bulk process may be carried out continuously in one or more loop reactors. The catalyst, as slurry or as a dry free flowing powder, may be injected regularly to the reactor loop, which can itself be filled with circulating slurry of growing polymer particles in a diluent, for example. Optionally, hydrogen may be added to the process, such as for molecular weight control of the resultant polymer. The loop reactor may be maintained at a pressure of from about 27 bar to about 45 bar and a temperature of from about 38°C

to about 121°C, for example. Reaction heat may be removed through the loop wall via any method known to one skilled in the art, such as via a double-jacketed pipe.

[0071] Alternatively, other types of polymerization processes may be used, such stirred reactors in series, parallel or combinations thereof, for example. Upon removal from the reactor, the polymer may be passed to a polymer recovery system for further processing, such as addition of additives and/or extrusion, for example.

[0072] In one embodiment, the polymerization process includes contacting the supported catalyst composition with a bulk olefin monomer prior to contact with the olefin monomer in the gas phase.

Polymer Product

[0073] The polymers (and blends thereof) formed via the processes described herein may include, but are not limited to, linear low density polyethylene, elastomers, plastomers, high density polyethylenes, low density polyethylenes, medium density polyethylenes, polypropylene (*e.g.*, syndiotactic, atactic and isotactic), polypropylene copolymers, random ethylene-propylene copolymers and impact copolymers, for example.

[0074] In one embodiment, the polymer includes copolymers. The copolymers generally include a first polymer and a second polymer. In one or more embodiments, the copolymers include a third polymer.

[0075] For example, the first polymer may include polypropylene, while the second polymer may be represented by the formula CH_2=CHR, wherein R is selected from hydrogen, C_2 to $C2_0$ alkyls, C_6 to C_{30} aryls and combinations thereof. In one specific embodiment, the second polymer is polyethylene. The third polymer may include C_2 to C_{30} alkyls, such as C_6 to C_{30} styrenic olefins, for example.

[0076] In one embodiment, the copolymer includes from about 0.5 wt.% to about 70 wt.%, or from about 0.5 wt.% to about 50 wt.%, or from about 0.5 wt.% to about 10 wt.% or from about 2 wt.% to about 7 wt.% polyethylene, for example.

[0077] In one embodiment, the polymer includes a bimodal molecular weight distribution. The bimodal molecular weight distribution polymer may be formed by a supported catalyst composition including a plurality of transition metal compounds.

COS-1086 PCT Patent Application (as filed).doc

[0078] In one or more embodiments, the copolymer has a melt flow index (MFI) of from about 1 g/10 min to about 1000 g/10 min, or from about 5 g/10 min. to about 500 g.10 min., or from about 10 g/10 min. to about 250 g/10 min. or from about to about 4 g/10 min. to about 150 g/10 min., for example. In particular, the copolymers have an MFI that increases with an increase in the polyethylene content of the copolymer.

[0079] In one or more embodiments, the copolymer has a melting point of from about 90°C to about 160°C, or from about 110°C to about 155°C or from about 130°C to about 150°C, for example. Further, it has been observed that in one or more embodiments, the copolymers described herein do not exhibit a melt temperature peak.

Product Application

[0080] The polymers and blends thereof are useful in applications known to one skilled in the art, such as forming operations (*e.g.*, film, sheet, pipe and fiber extrusion and co-extrusion as well as blow molding, injection molding and rotary molding). Films include blown or cast films formed by co-extrusion or by lamination useful as shrink film, cling film, stretch film, sealing films, oriented films, snack packaging, heavy duty bags, grocery sacks, baked and frozen food packaging, medical packaging, industrial liners, and membranes, for example, in food-contact and non-food contact application. Fibers include melt spinning, solution spinning and melt blown fiber operations for use in woven or non-woven form to make filters, diaper fabrics, medical garments and geotextiles, for example. Extruded articles include medical tubing, wire and cable coatings, geomembranes and pond liners, for example. Molded articles include single and multi-layered constructions in the form of bottles, tanks, large hollow articles, rigid food containers and toys, for example.

[0081] While the foregoing is directed to embodiments of the present invention, other and further embodiments of the invention may be devised without departing from the basic scope thereof and the scope thereof is determined by the claims that follow.

Examples

[0082] In the following examples, samples of copolymers were prepared.

COS-1086 PCT Patent Application (as filed).doc

[0083] As used in the examples, **metallocene type "M1"** refers to rac-dimethylsilanylbis(2-methyl-4-phenyl-1-indenyl)zirconium dichloride.

[0084] As used in the examples, **metallocene type "M2"** refers to rac-dimethylsilanylbis(2-methyl-4,5-benzo-1indenyl)zirconium dichloride.

[0085] As used in the examples, **metallocene type "M3"** refers to diphenylmethylidene(cyclopentadienyl)(9-fluorenyl)zirconium dichloride.

[0086] As used in the examples, **silica alumina** refers to silica alumina that was obtained from Fuji Sylisia Chemical LTD (Silica-Alumina 205 20 μm), such silica having a surface area of 260 m^2/g, a pore volume of 1.30 mL/g, an aluminum content of 4.8 wt.%, an average particle size of 20.5 μm and a pH of 6.5.

[0087] As used in the examples, **Support Type B** refers to silica obtained from Fuji Sylisia Chemical LTD (grade: Cariact P-10, 20 μm), such silica having a surface area of 281 m^2/g, a pore volume of 1.41 mL/g, an average particle size of 20.5 μm and a pH of 6.3, which was treated with methyl alumoxane (0.7g per 1g of silica).

[0088] As used in the examples, **Support Type A1** was prepared by dry mixing silica alumina with 6 wt.% $(NH_4)_2SiF_6$ and then transferring the mixture into a quartz tube having a glass-fritted disc. The quartz tube was then inserted into a tube furnace and equipped with an inverted glass fritted funnel on the top opening of the tube. The mixture was then fluidized with nitrogen (0.4 SLPM). Upon fluidization, the tube was heated from room temperature to an average reaction temperature of 450°C over a period of 6 hours.

[0089] As used in the examples, **Support Type A2** was prepared by mixing silica alumina with 6 wt.% $NH_4F.HF$ in water, drying in a rotavap and then transferring the mixture into a muffle furnace. The muffle furnace was then heated from room temperature to an average reaction temperature of 400°C over a period of 3 hours.

[0090] As used in the examples, Support Type A3 was prepared by mixing silica alumina with 8 wt.% $NH_4F.HF$, drying in a rotavap and then transferring the mixture into a muffle furnace. The muffle furnace was then heated from room temperature to an average reaction temperature of 400°C over a period of 3 hours.

[0091] The preparations of the supported catalyst systems were achieved by mixing a support material (A1, A2, A3 or B) with from 5 to 10 mg of one or more metallocene compounds (M1, M2 and/or M3) and from 2 to 4 g of triisobutyl

aluminum (25% solution in hexane) for 30 min at room temperature. The preparation then included adding 4 g. of mineral oil to the mixture to form a catalyst slurry.

[0092] *Ethylene/Propylene Polymerizations*: Each catalyst slurry was then contacted with ethylene and/or propylene monomer to form polymer. The polymerization conditions and results of each polymerization follow in Tables 1 and 2.

TABLE 1

Run #	Support Type	Metallocene Type	Cat. (mg)	Cocat/Cat wt. ratio	Ethylene (wt.% in feed)	H_2 (ppm)	Activity (g/g/h)	MFI (g/10 min.)
1	A1	M1	19.7	NA	0	119	8292	4.0
2	A1	M1	20.1	NA	2	119	11934	4.4
3	A1	M1	9.9	NA	2	116	8348	95.0
4	A1	M1	10.0	NA	3	115	16903	17.0
5	A1	M1	9.9	NA	5	113	34378	8.9
6 (comp)	B	M1	10.2	0.49	2	116	8392	66.9
7 (comp)	B	M1	9.9	0.5	3	115	8192	61.7
8 (comp)	B	M1	10.0	0.5	5	113	8025	61.4
9	A2	M1	20.1	NA	0	119	7409	16.0
10	A1	M1	10.2	NA	0	119	6664	9.1
11	A2	M1	7.0	NA	0	59	5735	1.6
12	A2	M1	7.1	NA	2	58	10632	4.6
13	A2	M1	7.0	NA	3	58	12350	4.2
14	A1	M2	20	NA	0	10	3321	FAST
15	A1	M2	20	NA	2	10	4274	>150
16	A2	M1+M3	NR	NA	0	119	4751	13.0
17	A2	M1+M3	NR	NA	2	119	6607	5.4
18	A2	M1	10	NA	0	42	10396	16.5
19	A2	M1	10	NA	1	42	15173	7.3
20	A2	M1	10	NA	2	42	17460	6.2
21	A3	M1	10	NA	0	10 mmol	10320	17
22	A3	M1	7	NA	2	10 mmol	18888	18
23	A3	M1	7	NA	5	10 mmol	38028	7

**MFI refers to melt flow index and is measured via ASTM-D-1238-E, Runs 1-17, 21-23 in 6X parallel reactor, Runs 18-20 in 2L reactor, Runs 1-17, 21-23 170 g. propylene, Runs 18-20 700 g propylene), 67°C, Runs1-22 over 30 minutes, Run 23 over 20 minutes)*

TABLE 2

Run #	T_r (°C)	ΔH_r (J/g)	T_m (°C)	ΔH_m (J/g)	Mw	Mw/Mn	Mz/Mw
1	108.5	97.0	150.1	102.2	394172	8.1	3.4
2	99.2	83.9	141.3	94.4	488946	8.6	2.8
3	98.3	81.6	140.0	81.8	NR	NR	NR
4	93.3	75.4	135.5	75.3	NR	NR	NR
5	83.5	59.6	127.9	58.5	NR	NR	NR
6	99.0	78.0	140.2	79.3	NR	NR	NR
7	94.3	72.4	135.9	75.5	NR	NR	NR
8	83.8	61.1	131.0	59.6	NR	NR	NR
9	106.0	91.0	150.2	98.5	230521	4.8	2.3
10	NR	NR	NR	NR	NR	NR	NR
11	NR	NR	NR	NR	NR	NR	NR
12	NR	NR	NR	NR	NR	NR	NR
13	NR	NR	NR	NR	NR	NR	NR
14	NR	NR	NR	NR	NR	NR	NR
15	NR	NR	NR	NR	NR	NR	NR
16	108.3	83.2	150.3	93.0	276433	5.5	2.4

COS-1086 PCT Patent Application (as filed).doc

17	99.9	77.9	141.4	88.4	420871	6.3	3.5
18	107.6	95.4	151.5	116.8	NR	NR	NR
19	101.1	90.1	143.4	113.7	NR	NR	NR
20	95.0	76.7	136.7	93.7	NR	NR	NR
21	109.2	94.6	150.7	111.3	NR	NR	NR
22	99.6	84.3	140.6	104.1	NR	NR	NR
23	83.9	64.2	125.1	90.8	NR	NR	NR

**Tr refers to recrystallization temperature, ΔHr refers to heat of recrystallization, Tm refers to melting point, ΔHm refers to heat of melt, Mw refers to weight average molecular weight, Mn refers to number average molecular weight and Mz refers to z average molecular weight, NR means not recorded, NA means not applicable*

[0093] Unexpectedly, it was observed that the activity of the Fl-Al-Si supported catalyst systems increased with an increasing ethylene content (in contrast to an essentially unchanged activity with the MAO based systems). In addition, a decrease in the polymer melt flow was observed with the Fl-Al-Si supported catalyst systems. Further, a slight increase in the polymer ethylene incorporation was observed with the Fl-Al-Si supported catalyst systems over the MAO based systems.

[0094] *Propylene/1-Hexene Polymerizations*: Each catalyst slurry was then contacted with propylene and/or 1-hexene monomer to form polymer. The polymerization conditions and results of each polymerization follow in Tables 3 and 4.

TABLE 3

Run #	Support Type	Metallocene Type	Cat. (mg)	Cocat/Cat wt. ratio	1-Hexene (wt.% in feed)	H_2 (ppm)	Activity (g/g/h)	MFI (g/10 min.)
24	A3	M1	10(1wt.%)		0	10 mmol	11634	6.6
25	A3	M1	10(1wt.%)		0	10 mmol	10320	17.1
26	A3	M1	10(1wt.%)		2	10 mmol	8782	
27	A3	M1	10(1wt.%)		3	10 mmol	5595	19.9
28	A3	M1	10(1wt.%)		4	10 mmol	4704	34.9

**MFI refers to melt flow index and is measured via ASTM-D-1238-E, 6X parallel reactor, 170 g. propylene, 67°C, 30 minutes, TIBAL:Support=1:1 by wt.*

TABLE 4

Run #	T_r (°C)	ΔH_r (J/g)	T_m (°C)	ΔH_m (J/g)	Mw	Mw/Mn	Mz/Mw
24	107.8	94.4	150.9	114.1	313277	3.5	2.2
25	109.2	94.6	150.7	111.3	207249	4.6	2.1
26	98.6	82.5	138.4	94.9	212221	3.7	2.0
27	94.9	82.1	135.6	107.0	181861	3.8	2.0
28	90.2	76.6	130.7	100.2	161261	3.3	1.9

**Tr refers to recrystallization temperature, ΔHr refers to heat of recrystallization, Tm refers to melting point, ΔHm refers to heat of melt, Mw refers to weight average molecular weight, Mn refers to number average molecular weight and Mz refers to z average molecular weight, NR means not recorded, NA means not applicable*

COS-1086 PCT Patent Application (as filed).doc

[0095] A decrease in the activity of the Fl-Al-Si supported catalyst systems was observed with an increasing 1-hexene content. In addition, an increase in the polymer melt flow was observed with an increasing 1-hexene content.

[0096] *Propylene/Ethylene/1-Hexene Polymerizations*: Each catalyst slurry was then contacted with propylene, ethylene and/or 1-hexene monomer to form polymer. The polymerization conditions and results of each polymerization follow in Tables 5 and 6.

TABLE 5

Run #	Support Type	Metallocene Type	Cat. (mg)	Ethylene (wt.% in feed)	1-Hexene (wt.% in feed)	H_2 (mmol)	Activity (g/g/h)	MFI (g/10 min.)
29	A3	M1	10(1wt.%)	0	0	10	10320	17.1
30	A3	M1	10(1wt.%)	0	3	10	5595	19.9
31	A3	M1	10(1wt.%)	0	4	10	4704	34.9
32	A3	M1	10(1wt.%)	1	3	10	16334	31
33	A3	M1	10(1wt.%)	1	5	10	16888	17
34	A3	M1	10(1wt.%)	2	3	10	5974	33.3
35	A3	M1	10(1wt.%)	2	5	10	20210	26
36	A3	M1	10(1wt.%)	3	3	10	9136	17
37	A3	M1	10(1wt.%)	3	5	10	16183	27

**MFI refers to melt flow index and is measured via ASTM-D-1238-E, 6X parallel reactor, 170 g. propylene, 67°C, 30 minutes, TIBAL:Support=1:1 by wt.*

TABLE 6

Run #	T_r (°C)	ΔH_r (J/g)	T_m (°C)	ΔH_m (J/g)	Mw	Mw/Mn	Mz/Mw
29	109.2	94.6	150.7	111.3	207249	4.6	2.1
30	94.9	82.1	135.6	107.0	181861	3.8	2.0
31	90.2	76.6	130.7	100.2	161261	3.3	1.9
32	88.0	-68.1	134.3	66.6	201567	3.7	2.0
33	74.8	-62.9	123.7	60.4	187627	3	1.9
34	84.5	73.5	126.7	88.0	160585	3.5	2.0
35	73.5	-55.7	120.7	62.3	176025	3.1	1.9
36	76.5	-64.2	122.0	58.1	194615	3.2	2.0
37	73.8	-55.0	118.0	60.6	162713	2.9	1.9

**Tr refers to recrystallization temperature, ΔHr refers to heat of recrystallization, Tm refers to melting point, ΔHm refers to heat of melt, Mw refers to weight average molecular weight, Mn refers to number average molecular weight and Mz refers to z average molecular weight, NR means not recorded, NA means not applicable*

[0097] A decrease in the polymer melt flow was observed with and increase in the 1-hexene content and/or the ethylene content.

[0098] *Propylene/Ethylene/Styrene Polymerizations*: Each catalyst slurry was then contacted with propylene, ethylene and/or strene monomer to form polymer. The polymerization conditions and results of each polymerization follow in Tables 7 and 8.

COS-1086 PCT Patent Application (as filed).doc

TABLE 7

Run #	Support Type	Metallocene Type	Cat. (mg)	Ethylene (wt.% in feed)	Styrene (wt.% in feed)	H_2 (mmol)	Activity (g/g/h)
38	A3	M1	10	0	0	10	4110
39	A3	M1	10	0	1.9	10	1063
40	A3	M1	10	1.0	2.0	10	992

**MFI refers to melt flow index and is measured via ASTM-D-1238-E, 2L reactor, 360 g. propylene, 67°C, 30 minutes*

TABLE 6

Run #	T_r (°C)	ΔH_r (J/g)	T_m (°C)	ΔH_m (J/g)	Mw	Mw/Mn
38	108.3	97.8	149.8	115.9	482449	6.5
39	112.3	106.8	143.8	116.7	10663	1.9
40	108.3	105.5	139.8	116.5	11715	1.9

**Tr refers to recrystallization temperature, ΔHr refers to heat of recrystallization, Tm refers to melting point, ΔHm refers to heat of melt, Mw refers to weight average molecular weight, Mn refers to number average molecular weight and Mz refers to z average molecular weight, NR means not recorded, NA means not applicable*

COS-1086 PCT Patent Application (as filed).doc

CLAIMS

What is claimed is:

1. A method of forming copolymers comprising:

providing a transition metal compound represented by the formula $[L]_mM[A]_n$, wherein L is a bulky ligand comprising bis-indenyl, A is a leaving group, M is a transition metal and m and n are such that the total ligand valency corresponds to the transition metal valency;

providing a support material comprising a bonding sequence selected from Si-O-Al-F, F-Si-O-Al, F-Si-O-Al-F and combinations thereof;

contacting the transition metal compound with the support material to form an active supported catalyst system, wherein the contact of the transition metal compound with the support material occurs in proximity to contact with monomer; and

contacting the active supported catalyst system with a plurality of monomers to form an copolymer.

2. The method of claim 1, wherein the transition metal compound is represented by the formula $XCp^ACp^BMA_n$, wherein X is a structural bridge, Cp^A and Cp^B each denote a cyclopentadienyl group, each being the same or different, at least one comprising a bis-indenyl and which may be either substituted or unsubstituted, M is a transition metal and A is an alkyl, hydrocarbyl or halogen group and n is an integer between 0 and 4.

3. The method of claim 1 further comprising contacting the plurality of monomers with a second transition metal compound.

4. The method of claim 3, wherein the second transition metal compound is selected from dimethylsilylbis(2-methyl-4-phenyl-indenyl)zirconium dichloride, dimethylsilylbis(2-methyl-indenyl)zirconium dichloride, dimethylsilylbis(2-methyl-4,5-benzo-indenyl)zirconium dichloride, diphenylmethylene(fluorenyl)(cyclopentadienyl)zirconium dichloride, dimethylmethylene(2,7-di-tert-butyl-fluorenyl)(cyclopentadienyl)zirconium dichloride,

diphenylmethylene(3,6-di-tert-butyl-fluorenyl)(cyclopentadienyl)zirconium dichloride and combinations thereof.

5. The method of claim 3, wherein the second transition metal compound comprises a symmetry that is different that the transition metal compound.

6. The method of claim 1, wherein the plurality of monomers comprise propylene and at least one monomer represented by the formula CH_2=CHR, wherein R is selected from hydrogen, C_2 to C_{20} alkyls, C_6 to C_{30} aryls and combinations thereof.

7. The method of claim 6, wherein the at least one monomer comprises ethylene.

8. The method of claim 6, wherein the at least one monomer comprises ethylene and an alpha olefin represented by the formula CH_2=CHR, wherein R is selected from C_2 to C_{20} alkyls.

9. The method of claim 1, wherein the plurality of monomers comprise a first olefin monomer comprising propylene, a second olefin monomer represented by the formula CH_2=CHR, wherein R is selected from hydrogen, C_2 to C_{20} alkyls, C_6 to C_{30} aryls and combinations thereof and a third olefin monomer represented by the formula CH_2=CHR, wherein R is a C_2 to C_{20} alkyl.

10. The method of claim 9, wherein the second olefin monomer comprises ethylene and the third olefin monomer comprises a C_6 to C_{30} styrenic olefin.

11. The method of claim 6, wherein the copolymer comprises from about 0.5 wt.% to about 70 wt.% polyethylene.

12. The method of claim 1, wherein the plurality of monomers comprise from about 0.5 wt.% to about 10 wt.% ethylene.

13. The method of claim 1, wherein the copolymer comprises a melt flow index that increases with an increasing amount of polyethylene therein.

14. The method of claim 1, wherein the active supported catalyst system experiences an increase in activity with an increasing amount of ethylene monomer.

15. The method of claim 6, wherein the active supported catalyst system first contacts bulk propylene and then contacts gas phase ethylene.

16. An olefin copolymer formed from the process of claim 1.

17. The copolymer of claim 16 selected from random copolymers, impact copolymers, block copolymers, elastomers, rubbers and combinations thereof.

18. The copolymer of claim 16 comprising from about 0.5 wt.% to about 60 wt.% polyethylene and a melt flow index of from about 1 g/10 min. to about 1000 g/10 min.

19. The copolymer of claim 16 comprising a melting temperature of from about 90°C to about 160°C.

20. The copolymer of claim 16, wherein the copolymer exhibits no melting temperature peak.

21. The method of claim 1, wherein the contact of the transition metal compound with the support material comprises in situ activation/heterogenization of the transition metal compound.

22. The method of claim 1, wherein the contact of the transition metal compound with the support material is carried out in the presence of triisobutyl aluminum.