



(22) **Date de dépôt/Filing Date:** 2004/03/30

(41) **Mise à la disp. pub./Open to Public Insp.:** 2004/09/30

(45) **Date de délivrance/Issue Date:** 2014/11/18

(62) **Demande originale/Original Application:** 2 462 479

(30) **Priorité/Priority:** 2003/03/31 (US10/403195)

(51) **Cl.Int./Int.Cl.** **A61F 2/966** (2013.01)

(72) **Inventeurs/Inventors:**

HOUGHTON, MICHAEL J., US;
MAJERCAK, DAVID C., US


(73) **Propriétaire/Owner:**

CORDIS CORPORATION, US

(74) **Agent:** NORTON ROSE FULBRIGHT CANADA
LLP/S.E.N.C.R.L., S.R.L.

(54) **Titre : DISPOSITIFS MEDICAUX D'ADMINISTRATION ENROBES ET MODIFIES**

(54) **Title: MODIFIED DELIVERY DEVICE FOR COATED MEDICAL DEVICES**



(57) **Abrégé/Abstract:**

Medical devices, and in particular implantable medical devices, may be coated to minimize or substantially eliminate a biological organism's reaction to the introduction of the medical device to the organism. The medical devices may be coated with any number of biocompatible materials. Therapeutic drugs, agents or compounds may be mixed with the biocompatible materials and affixed to at least a portion of the medical device. These therapeutic drugs, agents or compounds may also further reduce a biological organism's reaction to the introduction of the medical device to the organism. In addition, these therapeutic drugs, agents and/or compounds may be utilized to promote healing, including the formation of blood clots. Various materials and coating methodologies may be utilized to maintain the drugs, agents or compounds on the medical device until delivered and positioned. In addition, the devices utilized to deliver the implantable medical devices may be modified to reduce the potential for damaging the implantable medical device during deployment. Medical devices include stents, grafts, anastomotic devices, perivascular wraps, sutures and staples.

ABSTRACT OF THE DISCLOSURE

Medical devices, and in particular implantable medical devices, may be coated to minimize or substantially eliminate a biological organism's reaction to the introduction of the medical device to the organism. The medical devices may be coated with any number of biocompatible materials. Therapeutic drugs, agents or compounds may be mixed with the biocompatible materials and affixed to at least a portion of the medical device. These therapeutic drugs, agents or compounds may also further reduce a biological organism's reaction to the introduction of the medical device to the organism. In addition, these therapeutic drugs, agents and/or compounds may be utilized to promote healing, including the formation of blood clots. Various materials and coating methodologies may be utilized to maintain the drugs, agents or compounds on the medical device until delivered and positioned. In addition, the devices utilized to deliver the implantable medical devices may be modified to reduce the potential for damaging the implantable medical device during deployment. Medical devices include stents, grafts, anastomotic devices, perivascular wraps, sutures and staples.

MODIFIED DELIVERY DEVICE FOR COATED MEDICAL DEVICES

BACKGROUND OF THE INVENTION

5 1. Field of the Invention

10 The present invention relates to the local administration of drug/drug combinations for the prevention and treatment of vascular disease, and more particularly to intraluminal medical devices for the local delivery of drug/drug combinations for the prevention and treatment of vascular disease caused by injury and methods and devices for maintaining the drug/drug combinations on the intraluminal medical devices, as well as preventing damage to the medical device. The present invention also relates to medical devices, including stents, grafts, anastomotic devices, perivascular wraps, sutures and staples having
15 drugs, agents and/or compounds affixed thereto to treat and prevent disease and minimize or substantially eliminate a biological organism's reaction to the introduction of the medical device to the organism. In addition, the drugs, agents and/or compounds may be utilized to promote healing.

20 2. Discussion of the Related Art

 Many individuals suffer from circulatory disease caused by a progressive blockage of the blood vessels that perfuse the heart and other major organs. More severe blockage of blood vessels in such individuals often leads to
25 hypertension, ischemic injury, stroke, or myocardial infarction. Atherosclerotic lesions, which limit or obstruct coronary blood flow, are the major cause of ischemic heart disease. Percutaneous transluminal coronary angioplasty is a medical procedure whose purpose is to increase blood flow through an artery. Percutaneous transluminal coronary angioplasty is the predominant treatment
30 for coronary vessel stenosis. The increasing use of this procedure is attributable to its relatively high success rate and its minimal invasiveness compared with coronary bypass surgery. A limitation associated with percutaneous transluminal coronary angioplasty is the abrupt closure of the

vessel, which may occur immediately after the procedure and restenosis, which occurs gradually following the procedure. Additionally, restenosis is a chronic problem in patients who have undergone saphenous vein bypass grafting. The mechanism of acute occlusion appears to involve several factors and may result from vascular recoil with resultant closure of the artery and/or deposition of blood platelets and fibrin along the damaged length of the newly opened blood vessel.

Restenosis after percutaneous transluminal coronary angioplasty is a more gradual process initiated by vascular injury. Multiple processes, including thrombosis, inflammation, growth factor and cytokine release, cell proliferation, cell migration and extracellular matrix synthesis each contribute to the restenotic process.

While the exact mechanism of restenosis is not completely understood, the general aspects of the restenosis process have been identified. In the normal arterial wall, smooth muscle cells proliferate at a low rate, approximately less than 0.1 percent per day. Smooth muscle cells in the vessel walls exist in a contractile phenotype characterized by eighty to ninety percent of the cell cytoplasmic volume occupied with the contractile apparatus. Endoplasmic reticulum, Golgi, and free ribosomes are few and are located in the perinuclear region. Extracellular matrix surrounds the smooth muscle cells and is rich in heparin-like glycosaminoglycans, which are believed to be responsible for maintaining smooth muscle cells in the contractile phenotypic state (Campbell and Campbell, 1985).

Upon pressure expansion of an intracoronary balloon catheter during angioplasty, smooth muscle cells within the vessel wall become injured, initiating a thrombotic and inflammatory response. Cell derived growth factors such as platelet derived growth factor, basic fibroblast growth factor, epidermal growth factor, thrombin, etc., released from platelets, invading macrophages and/or leukocytes, or directly from the smooth muscle cells provoke a proliferative and migratory response in medial smooth muscle cells. These

cells undergo a change from the contractile phenotype to a synthetic phenotype characterized by only a few contractile filament bundles, extensive rough endoplasmic reticulum, Golgi and free ribosomes. Proliferation/migration usually begins within one to two days' post-injury and peaks several days thereafter (Campbell and Campbell, 1987; Clowes and Schwartz, 1985).

Daughter cells migrate to the intimal layer of arterial smooth muscle and continue to proliferate and secrete significant amounts of extracellular matrix proteins. Proliferation, migration and extracellular matrix synthesis continue until the damaged endothelial layer is repaired at which time proliferation slows within the intima, usually within seven to fourteen days post-injury. The newly formed tissue is called neointima. The further vascular narrowing that occurs over the next three to six months is due primarily to negative or constrictive remodeling.

Simultaneous with local proliferation and migration, inflammatory cells adhere to the site of vascular injury. Within three to seven days post-injury, inflammatory cells have migrated to the deeper layers of the vessel wall. In animal models employing either balloon injury or stent implantation, inflammatory cells may persist at the site of vascular injury for at least thirty days (Tanaka et al., 1993; Edelman et al., 1998). Inflammatory cells therefore are present and may contribute to both the acute and chronic phases of restenosis.

Numerous agents have been examined for presumed anti-proliferative actions in restenosis and have shown some activity in experimental animal models. Some of the agents which have been shown to successfully reduce the extent of intimal hyperplasia in animal models include: heparin and heparin fragments (Clowes, A.W. and Karnovsky M., *Nature* 265: 25-26, 1977; Guyton, J.R. et al., *Circ. Res.*, 46: 625-634, 1980; Clowes, A.W. and Clowes, M.M., *Lab. Invest.* 52: 611-616, 1985; Clowes, A.W. and Clowes, M.M., *Circ. Res.* 58: 839-845, 1986; Majesky et al., *Circ. Res.* 61: 296-300, 1987; Snow et al., *Am. J. Pathol.* 137: 313-330, 1990; Okada, T. et al., *Neurosurgery* 25: 92-98, 1989),

colchicine (Currier, J.W. et al., *Circ.* 80: 11-66, 1989), taxol (Sollot, S.J. et al., *J. Clin. Invest.* 95: 1869-1876, 1995), angiotensin converting enzyme (ACE) inhibitors (Powell, J.S. et al., *Science*, 245: 186-188, 1989), angiopeptin (Lundergan, C.F. et al. *Am. J. Cardiol.* 17(Suppl. B):132B-136B, 1991),
 5 cyclosporin A (Jonasson, L. et al., *Proc. Natl., Acad. Sci.*, 85: 2303, 1988), goat-anti-rabbit PDGF antibody (Ferns, G.A.A., et al., *Science* 253: 1129-1132, 1991), terbinafine (Nemecek, G.M. et al., *J. Pharmacol. Exp. Thera.* 248: 1167-1174, 1989), trapidil (Liu, M.W. et al., *Circ.* 81: 1089-1093, 1990), tranilast (Fukuyama, J. et al., *Eur. J. Pharmacol.* 318: 327-332, 1996), interferon-
 10 gamma (Hansson, G.K. and Holm, J., *Circ.* 84: 1266-1272, 1991), rapamycin (Marx, S.O. et al., *Circ. Res.* 76: 412-417, 1995), steroids (Colburn, M.D. et al., *J. Vasc. Surg.* 15: 510-518, 1992), see also Berk, B.C. et al., *J. Am. Coll. Cardiol.* 17: 111B-117B, 1991), ionizing radiation (Weinberger, J. et al., *Int. J. Rad. Onc. Biol. Phys.* 36: 767-775, 1996), fusion toxins (Farb, A. et al., *Circ. Res.* 80: 542-550, 1997) antisense oligionucleotides (Simons, M. et al., *Nature* 359: 67-70, 1992) and gene vectors (Chang, M.W. et al., *J. Clin. Invest.* 96: 2260-2268, 1995). Anti-proliferative action on smooth muscle cells *in vitro* has been demonstrated for many of these agents, including heparin and heparin conjugates, taxol, tranilast, colchicine, ACE inhibitors, fusion toxins, antisense
 15 oligionucleotides, rapamycin and ionizing radiation. Thus, agents with diverse mechanisms of smooth muscle cell inhibition may have therapeutic utility in reducing intimal hyperplasia.

However, in contrast to animal models, attempts in human angioplasty
 25 patients to prevent restenosis by systemic pharmacologic means have thus far been unsuccessful. Neither aspirin-dipyridamole, ticlopidine, anti-coagulant therapy (acute heparin, chronic warfarin, hirudin or hirulog), thromboxane receptor antagonism nor steroids have been effective in preventing restenosis, although platelet inhibitors have been effective in preventing acute reocclusion
 30 after angioplasty (Mak and Topol, 1997; Lang et al., 1991; Popma et al., 1991). The platelet GP II_b/III_a receptor, antagonist, Reopro® is still under study but Reopro® has not shown definitive results for the reduction in restenosis following angioplasty and stenting. Other agents, which have also been

unsuccessful in the prevention of restenosis, include the calcium channel antagonists, prostacyclin mimetics, angiotensin converting enzyme inhibitors, serotonin receptor antagonists, and anti-proliferative agents. These agents must be given systemically, however, and attainment of a therapeutically effective dose may not be possible; anti-proliferative (or anti-restenosis) concentrations may exceed the known toxic concentrations of these agents so that levels sufficient to produce smooth muscle inhibition may not be reached (Mak and Topol, 1997; Lang et al., 1991; Popma et al., 1991).

Additional clinical trials in which the effectiveness for preventing restenosis utilizing dietary fish oil supplements or cholesterol lowering agents has been examined showing either conflicting or negative results so that no pharmacological agents are as yet clinically available to prevent post-angioplasty restenosis (Mak and Topol, 1997; Franklin and Faxon, 1993; Serruys, P.W. et al., 1993). Recent observations suggest that the antilipid/antioxidant agent, probucol, may be useful in preventing restenosis but this work requires confirmation (Tardif et al., 1997; Yokoi, et al., 1997). Probucol is presently not approved for use in the United States and a thirty-day pretreatment period would preclude its use in emergency angioplasty. Additionally, the application of ionizing radiation has shown significant promise in reducing or preventing restenosis after angioplasty in patients with stents (Teirstein et al., 1997). Currently, however, the most effective treatments for restenosis are repeat angioplasty, atherectomy or coronary artery bypass grafting, because no therapeutic agents currently have Food and Drug Administration approval for use for the prevention of post-angioplasty restenosis.

Unlike systemic pharmacologic therapy, stents have proven useful in significantly reducing restenosis. Typically, stents are balloon-expandable slotted metal tubes (usually, but not limited to, stainless steel), which, when expanded within the lumen of an angioplastied coronary artery, provide structural support through rigid scaffolding to the arterial wall. This support is helpful in maintaining vessel lumen patency. In two randomized clinical trials,

stents increased angiographic success after percutaneous transluminal coronary angioplasty, by increasing minimal lumen diameter and reducing, but not eliminating, the incidence of restenosis at six months (Serruys et al., 1994; Fischman et al., 1994).

5

Additionally, the heparin coating of stents appears to have the added benefit of producing a reduction in sub-acute thrombosis after stent implantation (Serruys et al., 1996). Thus, sustained mechanical expansion of a stenosed coronary artery with a stent has been shown to provide some
10 measure of restenosis prevention, and the coating of stents with heparin has demonstrated both the feasibility and the clinical usefulness of delivering drugs locally, at the site of injured tissue.

As stated above, the use of heparin coated stents demonstrates the
15 feasibility and clinical usefulness of local drug delivery; however, the manner in which the particular drug or drug combination is affixed to the local delivery device will play a role in the efficacy of this type of treatment. For example, the processes and materials utilized to affix the drug/drug combinations to the local delivery device should not interfere with the operations of the drug/drug
20 combinations. In addition, the processes and materials utilized should be biocompatible and maintain the drug/drug combinations on the local device through delivery and over a given period of time. For example, removal of the drug/drug combination during delivery of the local delivery device may potentially cause failure of the device.

25

Accordingly, there exists a need for drug/drug combinations and associated local delivery devices for the prevention and treatment of vascular injury causing intimal thickening which is either biologically induced, for example, atherosclerosis, or mechanically induced, for example, through
30 percutaneous transluminal coronary angioplasty. In addition, there exists a need for maintaining the drug/drug combinations on the local delivery device through delivery and positioning as well as ensuring that the drug/drug combination is released in therapeutic dosages over a given period of time.

A variety of stent coatings and compositions have been proposed for the prevention and treatment of injury causing intimal thickening. The coatings may be capable themselves of reducing the stimulus the stent provides to the injured lumen wall, thus reducing the tendency towards thrombosis or restenosis. Alternately, the coating may deliver a pharmaceutical/therapeutic agent or drug to the lumen that reduces smooth muscle tissue proliferation or restenosis. The mechanism for delivery of the agent is through diffusion of the agent through either a bulk polymer or through pores that are created in the polymer structure, or by erosion of a biodegradable coating.

Both bioabsorbable and biostable compositions have been reported as coatings for stents. They generally have been polymeric coatings that either encapsulate a pharmaceutical/therapeutic agent or drug, e.g. rapamycin, taxol etc., or bind such an agent to the surface, e.g. heparin-coated stents. These coatings are applied to the stent in a number of ways, including, though not limited to, dip, spray, or spin coating processes.

One class of biostable materials that has been reported as coatings for stents is polyfluoro homopolymers. Polytetrafluoroethylene (PTFE) homopolymers have been used as implants for many years. These homopolymers are not soluble in any solvent at reasonable temperatures and therefore are difficult to coat onto small medical devices while maintaining important features of the devices (e.g. slots in stents).

Stents with coatings made from polyvinylidene fluoride homopolymers and containing pharmaceutical/therapeutic agents or drugs for release have been suggested. However, like most crystalline polyfluoro homopolymers, they are difficult to apply as high quality films onto surfaces without subjecting them to relatively high temperatures that correspond to the melting temperature of the polymer.

It would be advantageous to develop coatings for implantable medical devices that will reduce thrombosis, restenosis, or other adverse reactions, that may include, but do not require, the use of pharmaceutical or therapeutic agents or drugs to achieve such affects, and that possess physical and mechanical properties effective for use in such devices even when such coated devices are subjected to relatively low maximum temperatures. It would also be advantageous to develop implantable medical devices in combination with various drugs, agents and/or compounds which treat disease and minimize or substantially eliminate a living organisms' reaction to the implantation of the medical device. In certain circumstances, it may be advantageous to develop implantable medical devices in combination with various drugs, agents and/or compounds which promote wound healing.

It would also be advantageous to develop delivery devices that provide for the delivery of the coated implantable medical devices without adversely affecting the coating or the medical device itself. In addition, such delivery devices should provide the physician with a means for easily and accurately positioning the medical device in the target area.

SUMMARY OF THE INVENTION

The drug/drug combination therapies, drug/drug combination carriers and associated local delivery devices of the present invention provide a means for overcoming the difficulties associated with the methods and devices currently in use, as briefly described above. In addition, the delivery devices and methods for maintaining the drug/drug combination therapies, drug/drug combination carriers on the local delivery device ensure that the drug/drug combination therapies reach the target site.

In accordance with one aspect, the present invention is directed to a self-expanding stent delivery system. The self-expanding stent delivery system comprises a substantially tubular shaft and a substantially tubular sheath. The substantially tubular shaft includes a proximal end, a distal end, a guidewire

lumen extending between the proximal and distal ends, and a stent bed region proximate the distal end upon which the self-expanding stent is positioned. The stent bed region includes a textured surface for preventing longitudinal movement of the stent along the shaft. The substantially tubular sheath
5 defines an interior volume and is coaxially positioned over the tubular shaft and the stent.

In accordance with another aspect, the present invention is directed to a delivery system for coated medical devices. The delivery system for coated
10 medical devices comprises a substantially tubular shaft and a substantially tubular sheath. The substantially tubular shaft has a proximal end, a distal end, a guidewire lumen extending between the proximal and distal ends, and a stent bed region proximate the distal end upon which a coated, self-expanding stent is positioned. The stent bed region includes a textured surface for
15 preventing longitudinal movement of the coated, self-expanding stent along the shaft. The substantially tubular sheath defining an interior volume and is coaxially positioned over the tubular shaft and the coated, self-expanding stent.

The medical devices, drug coatings, delivery devices and methods for
20 maintaining the drug coatings or vehicles thereon of the present invention utilizes a combination of materials to treat disease, and reactions by living organisms due to the implantation of medical devices for the treatment of disease or other conditions. The local delivery of drugs, agents or compounds generally substantially reduces the potential toxicity of the drugs, agents or
25 compounds when compared to systemic delivery while increasing their efficacy.

Drugs, agents or compounds may be affixed to any number of medical devices to treat various diseases. The drugs, agents or compounds may also be affixed to minimize or substantially eliminate the biological organism's
30 reaction to the introduction of the medical device utilized to treat a separate condition. For example, stents may be introduced to open coronary arteries or other body lumens such as biliary ducts. The introduction of these stents cause a smooth muscle cell proliferation effect as well as inflammation.

Accordingly, the stents may be coated with drugs, agents or compounds to combat these reactions. Anastomosis devices, routinely utilized in certain types of surgery, may also cause a smooth muscle cell proliferation effect as well as inflammation. Stent-grafts and systems utilizing stent-grafts, for
5 example, aneurysm bypass systems may be coated with drugs, agents and/or compounds which prevent adverse affects caused by the introduction of these devices as well as to promote healing and incorporation. Therefore, the devices may also be coated with drugs, agents and/or compounds to combat these reactions. In addition, devices such as aneurysm bypass systems may
10 be coated with drugs, agents and/or compounds that promote would healing, thereby reducing the risk of endoleaks or other similar phenomena.

The drugs, agents or compounds will vary depending upon the type of medical device, the reaction to the introduction of the medical device and/or
15 the disease sought to be treated. The type of coating or vehicle utilized to immobilize the drugs, agents or compounds to the medical device may also vary depending on a number of factors, including the type of medical device, the type of drug, agent or compound and the rate of release thereof.

20 In order to be effective, the drugs, agents or compounds should preferably remain on the medical devices during delivery and implantation. Accordingly, various coating techniques for creating strong bonds between the drugs, agents or compounds may be utilized. In addition, various materials may be utilized as surface modifications to prevent the drugs, agents or
25 compounds from coming off prematurely.

Alternately, the delivery devices for the coated implantable medical device may be modified to minimize the potential risk of damage to the coating or the device itself. For example, various modifications to stent delivery
30 devices may be made in order to reduce the frictional forces associated with deploying self-expanding stents. Specifically, the delivery devices may be coated with various substances or incorporate features for reducing the forces acting upon specific areas of the coated stent.

The self-expanding stent delivery system of the present invention comprises a sheath coated with a layer of pyrolytic carbon or similar substance. The layer of pyrolytic carbon may be affixed to the inner lumen of the sheath in the region of the stent or along the entire length of the sheath. 5 The pyrolytic carbon is hard enough to prevent the self-expanding stent from becoming embedded in the softer polymeric sheath. In addition, pyrolytic carbon is a lubricious material. These two properties reduce the change of damage to the stent during deployment, reduce the forces required for stent deployment, thereby making it easier for the physician to accomplish 10 placement, and provide for more accurate stent deployment.

The pyrolytic carbon may be directly affixed to the inner lumen of the sheath or to a substrate which is then affixed to the inner lumen of the sheath. 15 A variety of known techniques may be utilized in the manufacturing process. Pyrolytic carbon is biocompatible and is currently utilized in a number of implantable medical devices. The pyrolytic carbon layer is sufficiently thick to provide the above-described features and thin enough to maintain the overall profile and flexibility of the delivery system.

20 The lubricious nature of the pyrolytic carbon is particularly advantageous with drug coated stents. The drug coatings and polymer containing drugs, agents or compounds should preferably remain on the stent for best results. A lubricious coating on the sheath substantially reduces the risk of the drug or 25 polymer from rubbing off during delivery.

The self-expanding stent delivery system of the present invention may also comprise a modified shaft. The modified shaft may include a plurality of elements which protrude from the shaft in the gaps between the stent 30 elements. These elements may significantly reduce the forces acting upon the stent during deployment by preventing or substantially reducing the compression of the stent. Without the plurality of elements, the stent may move and compress against a stop on the inner shaft of the delivery system.

Compression of the stent leads to higher deployment forces. Accordingly, a shaft comprising a plurality of elements eliminates or substantially reduces longitudinal movement of the stent, thereby eliminating or substantially reducing compression. In addition, the protruding elements distribute the total force acting upon the stent over the plurality of elements so that there is less localized stress on the stent and any coating thereon.

In one aspect, there is provided, a self-expanding stent delivery system comprising:

a substantially tubular shaft having a proximal end, a distal end, a guidewire lumen extending between the proximal and distal ends, and a stent bed region proximate the distal end upon which the self-expanding stent is positioned, the stent bed region including a textured surface for preventing longitudinal movement of the stent along the shaft;

a substantially tubular sheath defining an interior volume and coaxially positioned over the tubular shaft and the stent,

wherein the textured surface comprises one or more raised elements protruding from the substantially tubular shaft and arranged in a pattern corresponding to gaps between the elements comprising the self-expanding stent; wherein the height of the one or more raised elements is greater than the difference in radius between the outside radius of the shaft and the inside radius of the sheath minus the wall thickness of the stent and less than the difference between the inside radius of the sheath and the outside radius of the shaft.

In one aspect, there is provided a delivery system for coated medical devices comprising:

a substantially tubular shaft having a proximal end configured for increased flexibility, a distal end, a guidewire lumen extending between the

proximal and distal ends, a tapered distal tip at the distal end of the shaft and a stop mounted to the shaft proximal to the distal tip and a stent bed region positioned between the stop and the distal tip upon which a coated, self-expanding stent is positioned, the self-expanding stent comprising a tubular member having a plurality of adjacent hoops, including a plurality of longitudinal struts and a plurality of loops, and a plurality of bridges connecting adjacent hoops, the stent bed region including a textured surface comprising one or more raised elements protruding from the substantially tubular shaft and arranged in a pattern corresponding to the gaps between the plurality of bridges comprising the self-expanding stent for preventing longitudinal movement of the coated, self-expanding stent along the shaft; and

a substantially tubular sheath defining an interior volume and coaxially positioned over the tubular shaft and the coated, self-expanding stent, the substantially tubular sheath having a distal end and a proximal end, the distal end having an increased diameter in the distal end proximate the stent bed region relative to the diameter of the proximal end, the substantially tubular sheath also comprising a composite structure having an inner layer formed from a low coefficient of friction material, an outer layer and a wire reinforcement layer between the inner layer and the outer layer, the height of the one or more raised elements is greater than the difference in radius between the outside radius of the shaft and the inside radius of the sheath minus the wall thickness of the stent and less than the difference between the inside radius of the sheath and the outside radius of the shaft, the stop comprising a radio-opaque material and configured to make contact with the self-expanding stent and no frictional contact with the substantially tubular sheath.

In one aspect, there is provided a delivery system for a self-expanding stent, the delivery system comprising:

a self-expanding stent;

a substantially tubular shaft having a proximal end, a distal end, a guidewire lumen extending between the proximal and distal ends, and a stent bed region proximate the distal end upon which the self-expanding stent is positioned, the stent bed region including a textured surface for preventing longitudinal movement of the stent along the shaft; and

a substantially tubular sheath defining an interior volume and coaxially positioned over the tubular shaft and the stent;

wherein the textured surface comprises a plurality of raised elements protruding from the substantially tubular shaft,

wherein the plurality of raised elements are arranged in a pattern such that they correspond to, and fill, the gaps between some but not every one of the elements comprising the self-expanding stent and wherein the plurality of raised elements are distributed along the entire length of the stent.

BRIEF DESCRIPTION OF THE DRAWINGS

The foregoing and other features and advantages of the invention will be apparent from the following, more particular description of preferred embodiments of the invention, as illustrated in the accompanying drawings.

Figure 1 is a view along the length of a stent (ends not shown) prior to expansion showing the exterior surface of the stent and the characteristic banding pattern.

Figure 2 is a perspective view along the length of the stent of Figure 1 having reservoirs in accordance with the present invention.

Figure 3 indicates the fraction of drug released as a function of time from coatings of the present invention over which no topcoat has been disposed.

Figure 4 indicates the fraction of drug released as a function of time from coatings of the present invention including a topcoat disposed thereon.

Figure 5 indicates the fraction of drug released as a function of time from coatings of the present invention over which no topcoat has been disposed.

Figure 6 indicates *in vivo* stent release kinetics of rapamycin from poly(VDF/HFP).

Figure 7 is a cross-sectional view of a band of the stent of Figure 1 having drug coatings thereon in accordance with a first exemplary embodiment of the invention.

5

Figure 8 is a cross-sectional view of a band of the stent of Figure 1 having drug coatings thereon in accordance with a second exemplary embodiment of the invention.

10

Figure 9 is a cross-sectional view of a band of the stent of Figure 1 having drug coatings thereon in accordance with a third exemplary embodiment of the present invention.

15

Figures 10-13 illustrate an exemplary one-piece embodiment of an anastomosis device having a fastening flange and attached staple members in accordance with the present invention.

20

Figure 14 is a side view of an apparatus for joining anatomical structures together, according to an exemplary embodiment of the invention.

Figure 15 is a cross-sectional view showing a needle portion of the Figure 14 apparatus passing through edges of anatomical structures, according to an exemplary embodiment of the invention.

25

Figure 16 is a cross-sectional view showing the Figure 14 apparatus pulled through an anastomosis, according to an exemplary embodiment of the invention.

30

Figure 17 is a cross-sectional view showing a staple of the Figure 14 apparatus being placed into proximity with the anatomical structures, according to an exemplary embodiment of the invention.

Figure 18 is a cross-sectional view showing a staple of the Figure 14 apparatus being engaged on both sides of the anastomosis, according to an exemplary embodiment of the invention.

5 Figure 19 is a cross-sectional view showing a staple after it has been crimped to join the anatomical structures, according to an exemplary embodiment of the invention.

10 Figure 20 is a cross-sectional view of a balloon having a lubricious coating affixed thereto in accordance with the present invention.

15 Figure 21 is a cross-sectional view of a band of the stent in Figure 1 having a lubricious coating affixed thereto in accordance with the present invention.

20 Figure 22 is a partial cross-sectional view of a self-expanding stent in a delivery device having a lubricious coating in accordance with the present invention.

25 Figure 23 is a cross-sectional view of a band of the stent in Figure 1 having a modified polymer coating in accordance with the present invention.

30 Figure 24 is a side elevation of an exemplary stent-graft in accordance with the present invention.

35 Figure 25 is a fragmentary cross-sectional view of another alternate exemplary embodiment of a stent-graft in accordance with the present invention.

40 Figure 26 is a fragmentary cross-sectional view of another alternate exemplary embodiment of a stent-graft in accordance with the present invention.

Figure 27 is an elevation view of a fully deployed aortic repair system in accordance with the present invention.

Figure 28 is a perspective view of a stent for a first prosthesis, shown for clarity in an expanded state, in accordance with the present invention.

Figure 29 is a perspective view of a first prosthesis having a stent covered by a gasket material in accordance with the present invention.

Figure 30 is a diagrammatic representation of an uncoated surgical staple in accordance with the present invention.

Figure 31 is a diagrammatic representation of a surgical staple having a multiplicity of through-holes in accordance with the present invention.

Figure 32 is a diagrammatic representation of a surgical staple having a coating on the outer surface thereof in accordance with the present invention.

Figure 33 is a diagrammatic representation of a section of suture material having a coating thereon in accordance with the present invention.

Figure 34 is a diagrammatic representation of a section of suture material having a coating impregnated into the surface thereof in accordance with the present invention.

Figure 35 is a simplified elevational view of a stent delivery apparatus made in accordance with the present invention.

Figure 36 is a view similar to that of Figure 35 but showing an enlarged view of the distal end of the apparatus having a section cut away to show the stent loaded therein.

Figure 37 is a simplified elevational view of the distal end of the inner shaft made in accordance with the present invention.

Figure 38 is a cross-sectional view of Figure 37 taken along lines 38-38.

5

Figure 39 through 43 are partial cross-sectional views of the apparatus of the present invention sequentially showing the deployment of the self-expanding stent within the vasculature.

10

Figure 44 is a simplified elevational view of a shaft for a stent delivery apparatus made in accordance with the present invention.

Figure 45 is a partial cross-sectional view of the shaft and sheath of the stent delivery apparatus in accordance with the present invention.

15

Figure 46 is a partial cross-sectional view of the shaft and modified sheath of the stent delivery system in accordance with the present invention.

Figure 47 is a partial cross-sectional view of the shaft and modified sheath of the stent delivery system in accordance with the present invention.

20

Figure 48 is a partial cross-sectional view of a modified shaft of the stent delivery system in accordance with the present invention.

25 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The drug/drug combinations and delivery devices of the present invention may be utilized to effectively prevent and treat vascular disease, and in particular, vascular disease caused by injury. Various medical treatment devices utilized in the treatment of vascular disease may ultimately induce further complications. For example, balloon angioplasty is a procedure utilized to increase blood flow through an artery and is the predominant treatment for coronary vessel stenosis. However, as stated above, the procedure typically

30

causes a certain degree of damage to the vessel wall, thereby potentially exacerbating the problem at a point later in time. Although other procedures and diseases may cause similar injury, exemplary embodiments of the present invention will be described with respect to the treatment of restenosis and related complications following percutaneous transluminal coronary angioplasty and other similar arterial/venous procedures, including the joining of arteries, veins and other fluid carrying conduits. In addition, various methods and devices will be described for the effective delivery of the coated medical devices.

10

While exemplary embodiments of the invention will be described with respect to the treatment of restenosis and related complications following percutaneous transluminal coronary angioplasty, it is important to note that the local delivery of drug/drug combinations may be utilized to treat a wide variety of conditions utilizing any number of medical devices, or to enhance the function and/or life of the device. For example, intraocular lenses, placed to restore vision after cataract surgery is often compromised by the formation of a secondary cataract. The latter is often a result of cellular overgrowth on the lens surface and can be potentially minimized by combining a drug or drugs with the device. Other medical devices which often fail due to tissue in-growth or accumulation of proteinaceous material in, on and around the device, such as shunts for hydrocephalus, dialysis grafts, colostomy bag attachment devices, ear drainage tubes, leads for pace makers and implantable defibrillators can also benefit from the device-drug combination approach. Devices which serve to improve the structure and function of tissue or organ may also show benefits when combined with the appropriate agent or agents. For example, improved osteointegration of orthopedic devices to enhance stabilization of the implanted device could potentially be achieved by combining it with agents such as bone-morphogenic protein. Similarly other surgical devices, sutures, staples, anastomosis devices, vertebral disks, bone pins, suture anchors, hemostatic barriers, clamps, screws, plates, clips, vascular implants, tissue adhesives and sealants, tissue scaffolds, various types of dressings, bone substitutes, intraluminal devices, and vascular supports could

30

also provide enhanced patient benefit using this drug-device combination approach. Perivascular wraps may be particularly advantageous, alone or in combination with other medical devices. The perivascular wraps may supply additional drugs to a treatment site. Essentially, any type of medical device
 5 may be coated in some fashion with a drug or drug combination which enhances treatment over use of the singular use of the device or pharmaceutical agent.

In addition to various medical devices, the coatings on these devices
 10 may be used to deliver therapeutic and pharmaceutic agents including: antiproliferative/antimitotic agents including natural products such as vinca alkaloids (i.e. vinblastine, vincristine, and vinorelbine), paclitaxel, epidipodophyllotoxins (i.e. etoposide, teniposide), antibiotics (dactinomycin (actinomycin D) daunorubicin, doxorubicin and idarubicin), anthracyclines,
 15 mitoxantrone, bleomycins, plicamycin (mithramycin) and mitomycin, enzymes (L-asparaginase which systemically metabolizes L-asparagine and deprives cells which do not have the capacity to synthesize their own asparagine); antiplatelet agents such as G(GP) II_b/III_a inhibitors and vitronectin receptor antagonists; antiproliferative/antimitotic alkylating agents such as nitrogen
 20 mustards (mechlorethamine, cyclophosphamide and analogs, melphalan, chlorambucil), ethylenimines and methylmelamines (hexamethylmelamine and thiotepa), alkyl sulfonates-busulfan, nirtosoureas (carmustine (BCNU) and analogs, streptozocin), trazenes – dacarbazine (DTIC); antiproliferative/antimitotic antimetabolites such as folic acid analogs
 25 (methotrexate), pyrimidine analogs (fluorouracil, floxuridine, and cytarabine), purine analogs and related inhibitors (mercaptopurine, thioguanine, pentostatin and 2-chlorodeoxyadenosine {cladribine}); platinum coordination complexes (cisplatin, carboplatin), procarbazine, hydroxyurea, mitotane, aminoglutethimide; hormones (i.e. estrogen); anticoagulants (heparin, synthetic
 30 heparin salts and other inhibitors of thrombin); fibrinolytic agents (such as tissue plasminogen activator, streptokinase and urokinase), aspirin, dipyridamole, ticlopidine, clopidogrel, abciximab; antimigratory; antisecretory (breveldin); anti-inflammatory: such as adrenocortical steroids (cortisol,

cortisone, fludrocortisone, prednisone, prednisolone, 6 α -methylprednisolone, triamcinolone, betamethasone, and dexamethasone), non-steroidal agents (salicylic acid derivatives i.e. aspirin; para-aminophenol derivatives i.e. acetaminophen; indole and indene acetic acids (indomethacin, sulindac, and etodalac), heteroaryl acetic acids (tolmetin, diclofenac, and ketorolac), 5 arylpropionic acids (ibuprofen and derivatives), anthranilic acids (mefenamic acid, and meclofenamic acid), enolic acids (piroxicam, tenoxicam, phenylbutazone, and oxyphenthatrazone), nabumetone, gold compounds (auranofin, aurothioglucose, gold sodium thiomalate); immunosuppressives: 10 (cyclosporine, tacrolimus (FK-506), sirolimus (rapamycin), azathioprine, mycophenolate mofetil); angiogenic agents: vascular endothelial growth factor (VEGF), fibroblast growth factor (FGF); angiotensin receptor blockers; nitric oxide donors; anti-sense oligonucleotides and combinations thereof; cell cycle inhibitors, mTOR inhibitors, and growth factor receptor signal transduction 15 kinase inhibitors; retinoids; cyclin/CDK inhibitors; HMG co-enzyme reductase inhibitors (statins); and protease inhibitors.

As stated previously, the implantation of a coronary stent in conjunction with balloon angioplasty is highly effective in treating acute vessel closure and 20 may reduce the risk of restenosis. Intravascular ultrasound studies (Mintz et al., 1996) suggest that coronary stenting effectively prevents vessel constriction and that most of the late luminal loss after stent implantation is due to plaque growth, probably related to neointimal hyperplasia. The late luminal loss after coronary stenting is almost two times higher than that observed after 25 conventional balloon angioplasty. Thus, inasmuch as stents prevent at least a portion of the restenosis process, a combination of drugs, agents or compounds which prevents smooth muscle cell proliferation, reduces inflammation and reduces coagulation or prevents smooth muscle cell proliferation by multiple mechanisms, reduces inflammation and reduces 30 coagulation combined with a stent may provide the most efficacious treatment for post-angioplasty restenosis. The systemic use of drugs, agents or compounds in combination with the local delivery of the same or different drug/drug combinations may also provide a beneficial treatment option.

The local delivery of drug/drug combinations from a stent has the following advantages; namely, the prevention of vessel recoil and remodeling through the scaffolding action of the stent and the prevention of multiple components of neointimal hyperplasia or restenosis as well as a reduction in inflammation and thrombosis. This local administration of drugs, agents or compounds to stented coronary arteries may also have additional therapeutic benefit. For example, higher tissue concentrations of the drugs, agents or compounds may be achieved utilizing local delivery, rather than systemic administration. In addition, reduced systemic toxicity may be achieved utilizing local delivery rather than systemic administration while maintaining higher tissue concentrations. Also in utilizing local delivery from a stent rather than systemic administration, a single procedure may suffice with better patient compliance. An additional benefit of combination drug, agent, and/or compound therapy may be to reduce the dose of each of the therapeutic drugs, agents or compounds, thereby limiting their toxicity, while still achieving a reduction in restenosis, inflammation and thrombosis. Local stent-based therapy is therefore a means of improving the therapeutic ratio (efficacy/toxicity) of anti-restenosis, anti-inflammatory, anti-thrombotic drugs, agents or compounds.

There are a multiplicity of different stents that may be utilized following percutaneous transluminal coronary angioplasty. Although any number of stents may be utilized in accordance with the present invention, for simplicity, a limited number of stents will be described in exemplary embodiments of the present invention. The skilled artisan will recognize that any number of stents may be utilized in connection with the present invention. In addition, as stated above, other medical devices may be utilized.

A stent is commonly used as a tubular structure left inside the lumen of a duct to relieve an obstruction. Commonly, stents are inserted into the lumen in a non-expanded form and are then expanded autonomously, or with the aid of a second device *in situ*. A typical method of expansion occurs through the

use of a catheter-mounted angioplasty balloon which is inflated within the stenosed vessel or body passageway in order to shear and disrupt the obstructions associated with the wall components of the vessel and to obtain an enlarged lumen.

5

Figure 1 illustrates an exemplary stent 100 which may be utilized in accordance with an exemplary embodiment of the present invention. The expandable cylindrical stent 100 comprises a fenestrated structure for placement in a blood vessel, duct or lumen to hold the vessel, duct or lumen open, more particularly for protecting a segment of artery from restenosis after angioplasty. The stent 100 may be expanded circumferentially and maintained in an expanded configuration, that is circumferentially or radially rigid. The stent 100 is axially flexible and when flexed at a bend, the stent 100 avoids any externally protruding component parts.

15

The stent 100 generally comprises first and second ends with an intermediate section therebetween. The stent 100 has a longitudinal axis and comprises a plurality of longitudinally disposed bands 102, wherein each band 102 defines a generally continuous wave along a line segment parallel to the longitudinal axis. A plurality of circumferentially arranged links 104 maintain the bands 102 in a substantially tubular structure. Essentially, each longitudinally disposed band 102 is connected at a plurality of periodic locations, by a short circumferentially arranged link 104 to an adjacent band 102. The wave associated with each of the bands 102 has approximately the same fundamental spatial frequency in the intermediate section, and the bands 102 are so disposed that the wave associated with them are generally aligned so as to be generally in phase with one another. As illustrated in the figure, each longitudinally arranged band 102 undulates through approximately two cycles before there is a link to an adjacent band 102.

25
30

The stent 100 may be fabricated utilizing any number of methods. For example, the stent 100 may be fabricated from a hollow or formed stainless steel tube that may be machined using lasers, electric discharge milling,

chemical etching or other means. The stent 100 is inserted into the body and placed at the desired site in an unexpanded form. In one exemplary embodiment, expansion may be effected in a blood vessel by a balloon catheter, where the final diameter of the stent 100 is a function of the diameter of the balloon catheter used.

It should be appreciated that a stent 100 in accordance with the present invention may be embodied in a shape-memory material, including, for example, an appropriate alloy of nickel and titanium or stainless steel. Structures formed from stainless steel may be made self-expanding by configuring the stainless steel in a predetermined manner, for example, by twisting it into a braided configuration. In this embodiment after the stent 100 has been formed it may be compressed so as to occupy a space sufficiently small as to permit its insertion in a blood vessel or other tissue by insertion means, wherein the insertion means include a suitable catheter, or flexible rod. On emerging from the catheter, the stent 100 may be configured to expand into the desired configuration where the expansion is automatic or triggered by a change in pressure, temperature or electrical stimulation.

Figure 2 illustrates an exemplary embodiment of the present invention utilizing the stent 100 illustrated in Figure 1. As illustrated, the stent 100 may be modified to comprise one or more reservoirs 106. Each of the reservoirs 106 may be opened or closed as desired. These reservoirs 106 may be specifically designed to hold the drug/drug combinations to be delivered. Regardless of the design of the stent 100, it is preferable to have the drug/drug combination dosage applied with enough specificity and a sufficient concentration to provide an effective dosage in the lesion area. In this regard, the reservoir size in the bands 102 is preferably sized to adequately apply the drug/drug combination dosage at the desired location and in the desired amount.

In an alternate exemplary embodiment, the entire inner and outer surface of the stent 100 may be coated with drug/drug combinations in

therapeutic dosage amounts. A detailed description of a drug for treating restenosis, as well as exemplary coating techniques, is described below. It is, however, important to note that the coating techniques may vary depending on the drug/drug combinations. Also, the coating techniques may vary depending
5 on the material comprising the stent or other intraluminal medical device.

Rapamycin is a macrocyclic triene antibiotic produced by *Streptomyces hygroscopicus* as disclosed in U.S. Patent No. 3,929,992. It has been found that rapamycin among other things inhibits the proliferation of vascular smooth
10 muscle cells *in vivo*. Accordingly, rapamycin may be utilized in treating intimal smooth muscle cell hyperplasia, restenosis, and vascular occlusion in a mammal, particularly following either biologically or mechanically mediated vascular injury, or under conditions that would predispose a mammal to suffering such a vascular injury. Rapamycin functions to inhibit smooth muscle
15 cell proliferation and does not interfere with the re-endothelialization of the vessel walls.

Rapamycin reduces vascular hyperplasia by antagonizing smooth muscle proliferation in response to mitogenic signals that are released during
20 an angioplasty induced injury. Inhibition of growth factor and cytokine mediated smooth muscle proliferation at the late G1 phase of the cell cycle is believed to be the dominant mechanism of action of rapamycin. However, rapamycin is also known to prevent T-cell proliferation and differentiation when administered systemically. This is the basis for its immunosuppressive activity
25 and its ability to prevent graft rejection.

As used herein, rapamycin includes rapamycin and all analogs, derivatives and congeners that bind to FKBP12, and other immunophilins and possesses the same pharmacologic properties as rapamycin including
30 inhibition of TOR.

Although the anti-proliferative effects of rapamycin may be achieved through systemic use, superior results may be achieved through the local

delivery of the compound. Essentially, rapamycin works in the tissues, which are in proximity to the compound, and has diminished effect as the distance from the delivery device increases. In order to take advantage of this effect, one would want the rapamycin in direct contact with the lumen walls.

5 Accordingly, in a preferred embodiment, the rapamycin is incorporated onto the surface of the stent or portions thereof. Essentially, the rapamycin is preferably incorporated into the stent 100, illustrated in Figure 1, where the stent 100 makes contact with the lumen wall.

10 Rapamycin may be incorporated onto or affixed to the stent in a number of ways. In the exemplary embodiment, the rapamycin is directly incorporated into a polymeric matrix and sprayed onto the outer surface of the stent. The rapamycin elutes from the polymeric matrix over time and enters the surrounding tissue. The rapamycin preferably remains on the stent for at least
15 three days up to approximately six months, and more preferably between seven and thirty days.

Any number of non-erodible polymers may be utilized in conjunction with rapamycin. In one exemplary embodiment, the rapamycin or other therapeutic
20 agent may be incorporated into a film-forming polyfluoro copolymer comprising an amount of a first moiety selected from the group consisting of polymerized vinylidene fluoride and polymerized tetrafluoroethylene, and an amount of a second moiety other than the first moiety and which is copolymerized with the first moiety, thereby producing the polyfluoro copolymer, the second moiety
25 being capable of providing toughness or elastomeric properties to the polyfluoro copolymer, wherein the relative amounts of the first moiety and the second moiety are effective to provide the coating and film produced therefrom with properties effective for use in treating implantable medical devices.

30 The present invention provides polymeric coatings comprising a polyfluoro copolymer and implantable medical devices, for example, stents coated with a film of the polymeric coating in amounts effective to reduce thrombosis and/or restenosis when such stents are used in, for example,

angioplasty procedures. As used herein, polyfluoro copolymers means those copolymers comprising an amount of a first moiety selected from the group consisting of polymerized vinylidene fluoride and polymerized tetrafluoroethylene, and an amount of a second moiety other than the first moiety and which is copolymerized with the first moiety to produce the polyfluoro copolymer, the second moiety being capable of providing toughness or elastomeric properties to the polyfluoro copolymer, wherein the relative amounts of the first moiety and the second moiety are effective to provide coatings and film made from such polyfluoro copolymers with properties effective for use in coating implantable medical devices.

The coatings may comprise pharmaceutical or therapeutic agents for reducing restenosis, inflammation, and/or thrombosis, and stents coated with such coatings may provide sustained release of the agents. Films prepared from certain polyfluoro copolymer coatings of the present invention provide the physical and mechanical properties required of conventional coated medical devices, even where maximum temperature, to which the device coatings and films are exposed, are limited to relatively low temperatures. This is particularly important when using the coating/film to deliver pharmaceutical/therapeutic agents or drugs that are heat sensitive, or when applying the coating onto temperature-sensitive devices such as catheters. When maximum exposure temperature is not an issue, for example, where heat-stable agents such as itraconazole are incorporated into the coatings, higher melting thermoplastic polyfluoro copolymers may be used and, if very high elongation and adhesion is required, elastomers may be used. If desired or required, the polyfluoro elastomers may be crosslinked by standard methods described in, e.g., Modern Fluoropolymers, (J. Shires ed.), John Wiley & Sons, New York, 1997, pp. 77-87.

The present invention comprises polyfluoro copolymers that provide improved biocompatible coatings or vehicles for medical devices. These coatings provide inert biocompatible surfaces to be in contact with body tissue of a mammal, for example, a human, sufficient to reduce restenosis, or

thrombosis, or other undesirable reactions. While many reported coatings made from polyfluoro homopolymers are insoluble and/or require high heat, for example, greater than about one hundred twenty-five degrees centigrade, to obtain films with adequate physical and mechanical properties for use on implantable devices, for example, stents, or are not particularly tough or elastomeric, films prepared from the polyfluoro copolymers of the present invention provide adequate adhesion, toughness or elasticity, and resistance to cracking when formed on medical devices. In certain exemplary embodiments, this is the case even where the devices are subjected to relatively low maximum temperatures.

The polyfluoro copolymers used for coatings according to the present invention are preferably film-forming polymers that have molecular weight high enough so as not to be waxy or tacky. The polymers and films formed therefrom should preferably adhere to the stent and not be readily deformable after deposition on the stent as to be able to be displaced by hemodynamic stresses. The polymer molecular weight should preferably be high enough to provide sufficient toughness so that films comprising the polymers will not be rubbed off during handling or deployment of the stent. In certain exemplary embodiments the coating will not crack where expansion of the stent or other medical devices occurs.

Coatings of the present invention comprise polyfluoro copolymers, as defined hereinabove. The second moiety polymerized with the first moiety to prepare the polyfluoro copolymer may be selected from those polymerized, biocompatible monomers that would provide biocompatible polymers acceptable for implantation in a mammal, while maintaining sufficient elastomeric film properties for use on medical devices claimed herein. Such monomers include, without limitation, hexafluoropropylene (HFP), tetrafluoroethylene (TFE), vinylidene fluoride, 1-hydropentafluoropropylene, perfluoro(methyl vinyl ether), chlorotrifluoroethylene (CTFE), pentafluoropropene, trifluoroethylene, hexafluoroacetone and hexafluoroisobutylene.

Polyfluoro copolymers used in the present invention typically comprise vinylidene fluoride copolymerized with hexafluoropropylene, in the weight ratio in the range of from about fifty to about ninety-two weight percent vinylidene fluoride to about fifty to about eight weight percent HFP. Preferably, polyfluoro copolymers used in the present invention comprise from about fifty to about eighty-five weight percent vinylidene fluoride copolymerized with from about fifty to about fifteen weight percent HFP. More preferably, the polyfluoro copolymers will comprise from about fifty-five to about seventy weight percent vinylidene fluoride copolymerized with from about forty-five to about thirty weight percent HFP. Even more preferably, polyfluoro copolymers comprise from about fifty-five to about sixty-five weight percent vinylidene fluoride copolymerized with from about forty-five to about thirty-five weight percent HFP. Such polyfluoro copolymers are soluble, in varying degrees, in solvents such as dimethylacetamide (DMAc), tetrahydrofuran, dimethyl formamide, dimethyl sulfoxide and n-methyl pyrrolidone. Some are soluble in methylethylketone (MEK), acetone, methanol and other solvents commonly used in applying coatings to conventional implantable medical devices.

Conventional polyfluoro homopolymers are crystalline and difficult to apply as high quality films onto metal surfaces without exposing the coatings to relatively high temperatures that correspond to the melting temperature (T_m) of the polymer. The elevated temperature serves to provide films prepared from such PVDF homopolymer coatings that exhibit sufficient adhesion of the film to the device, while preferably maintaining sufficient flexibility to resist film cracking upon expansion/contraction of the coated medical device. Certain films and coatings according to the present invention provide these same physical and mechanical properties, or essentially the same properties, even when the maximum temperatures to which the coatings and films are exposed is less than about a maximum predetermined temperature. This is particularly important when the coatings/films comprise pharmaceutical or therapeutic agents or drugs that are heat sensitive, for example, subject to chemical or physical degradation or other heat-induced negative affects, or when coating

heat sensitive substrates of medical devices, for example, subject to heat-induced compositional or structural degradation.

Depending on the particular device upon which the coatings and films of the present invention are to be applied and the particular use/result required of the device, polyfluoro copolymers used to prepare such devices may be crystalline, semi-crystalline or amorphous.

Where devices have no restrictions or limitations with respect to exposure of same to elevated temperatures, crystalline polyfluoro copolymers may be employed. Crystalline polyfluoro copolymers tend to resist the tendency to flow under applied stress or gravity when exposed to temperatures above their glass transition (T_g) temperatures. Crystalline polyfluoro copolymers provide tougher coatings and films than their fully amorphous counterparts. In addition, crystalline polymers are more lubricious and more easily handled through crimping and transfer processes used to mount self-expanding stents, for example, nitinol stents.

Semi-crystalline and amorphous polyfluoro copolymers are advantageous where exposure to elevated temperatures is an issue, for example, where heat-sensitive pharmaceutical or therapeutic agents are incorporated into the coatings and films, or where device design, structure and/or use preclude exposure to such elevated temperatures. Semi-crystalline polyfluoro copolymer elastomers comprising relatively high levels, for example, from about thirty to about forty-five weight percent of the second moiety, for example, HFP, copolymerized with the first moiety, for example, VDF, have the advantage of reduced coefficient of friction and self-blocking relative to amorphous polyfluoro copolymer elastomers. Such characteristics may be of significant value when processing, packaging and delivering medical devices coated with such polyfluoro copolymers. In addition, such polyfluoro copolymer elastomers comprising such relatively high content of the second moiety serves to control the solubility of certain agents, for example, rapamycin, in the polymer and therefore controls permeability of the agent through the matrix.

Polyfluoro copolymers utilized in the present inventions may be prepared by various known polymerization methods. For example, high pressure, free-radical, semi-continuous emulsion polymerization techniques
5 such as those disclosed in Fluoroelastomers-dependence of relaxation phenomena on compositions, POLYMER 30, 2180, 1989, by Ajroldi, et al., may be employed to prepare amorphous polyfluoro copolymers, some of which may be elastomers. In addition, free-radical batch emulsion polymerization techniques disclosed herein may be used to obtain polymers that are semi-
10 crystalline, even where relatively high levels of the second moiety are included.

As described above, stents may comprise a wide variety of materials and a wide variety of geometrics. Stents may be made of biocompatible materials, including biostable and bioabsorbable materials. Suitable
15 biocompatible metals include, but are not limited to, stainless steel, tantalum, titanium alloys (including nitinol), and cobalt alloys (including cobalt-chromium nickel alloys). Suitable nonmetallic biocompatible materials include, but are not limited to, polyamides, polyolefins (i.e. polypropylene, polyethylene etc.), nonabsorbable polyesters (i.e. polyethylene terephthalate), and bioabsorbable
20 aliphatic polyesters (i.e. homopolymers and copolymers of lactic acid, glycolic acid, lactide, glycolide, para-dioxanone, trimethylene carbonate, ϵ -caprolactone, and blends thereof).

The film-forming biocompatible polymer coatings generally are applied
25 to the stent in order to reduce local turbulence in blood flow through the stent, as well as adverse tissue reactions. The coatings and films formed therefrom also may be used to administer a pharmaceutically active material to the site of the stent placement. Generally, the amount of polymer coating to be applied to the stent will vary depending on, among other possible parameters, the
30 particular polyfluoro copolymer used to prepare the coating, the stent design and the desired effect of the coating. Generally, the coated stent will comprise from about 0.1 to about fifteen weight percent of the coating, preferably from about 0.4 to about ten weight percent. The polyfluoro copolymer coatings may

be applied in one or more coating steps, depending on the amount of polyfluoro copolymer to be applied. Different polyfluoro copolymers may be used for different layers in the stent coating. In fact, in certain exemplary embodiments, it is highly advantageous to use a diluted first coating solution comprising a polyfluoro copolymer as a primer to promote adhesion of a subsequent polyfluoro copolymer coating layer that may include pharmaceutically active materials. The individual coatings may be prepared from different polyfluoro copolymers.

10 Additionally, a top coating may be applied to delay release of the pharmaceutical agent, or they could be used as the matrix for the delivery of a different pharmaceutically active material. Layering of coatings may be used to stage release of the drug or to control release of different agents placed in different layers.

15 Blends of polyfluoro copolymers may also be used to control the release rate of different agents or to provide a desirable balance of coating properties, i.e. elasticity, toughness, etc., and drug delivery characteristics, for example, release profile. Polyfluoro copolymers with different solubilities in solvents may be used to build up different polymer layers that may be used to deliver different drugs or to control the release profile of a drug. For example, polyfluoro copolymers comprising 85.5/14.5 (wt/wt) of poly(vinylidene fluoride/HFP) and 60.6/39.4 (wt/wt) of poly(vinylidene fluoride/HFP) are both soluble in DMAc. However, only the 60.6/39.4 PVDF polyfluoro copolymer is soluble in methanol. So, a first layer of the 85.5/14.5 PVDF polyfluoro copolymer comprising a drug could be over coated with a topcoat of the 60.6/39.4 PVDF polyfluoro copolymer made with the methanol solvent. The top coating may be used to delay the drug delivery of the drug contained in the first layer. Alternately, the second layer could comprise a different drug to provide for sequential drug delivery. Multiple layers of different drugs could be provided by alternating layers of first one polyfluoro copolymer, then the other. As will be readily appreciated by those skilled in the art, numerous layering approaches may be used to provide the desired drug delivery.

Coatings may be formulated by mixing one or more therapeutic agents with the coating polyfluoro copolymers in a coating mixture. The therapeutic agent may be present as a liquid, a finely divided solid, or any other appropriate physical form. Optionally, the coating mixture may include one or more additives, for example, nontoxic auxiliary substances such as diluents, carriers, excipients, stabilizers or the like. Other suitable additives may be formulated with the polymer and pharmaceutically active agent or compound. For example, a hydrophilic polymer may be added to a biocompatible hydrophobic coating to modify the release profile, or a hydrophobic polymer may be added to a hydrophilic coating to modify the release profile. One example would be adding a hydrophilic polymer selected from the group consisting of polyethylene oxide, polyvinyl pyrrolidone, polyethylene glycol, carboxymethyl cellulose, and hydroxymethyl cellulose to a polyfluoro copolymer coating to modify the release profile. Appropriate relative amounts may be determined by monitoring the *in vitro* and/or *in vivo* release profiles for the therapeutic agents.

The best conditions for the coating application are when the polyfluoro copolymer and pharmaceutical agent have a common solvent. This provides a wet coating that is a true solution. Less desirable, yet still usable, are coatings that contain the pharmaceutical agent as a solid dispersion in a solution of the polymer in solvent. Under the dispersion conditions, care must be taken to ensure that the particle size of the dispersed pharmaceutical powder, both the primary powder size and its aggregates and agglomerates, is small enough not to cause an irregular coating surface or to clog the slots of the stent that need to remain essentially free of coating. In cases where a dispersion is applied to the stent and the smoothness of the coating film surface requires improvement, or to be ensured that all particles of the drug are fully encapsulated in the polymer, or in cases where the release rate of the drug is to be slowed, a clear (polyfluoro copolymer only) topcoat of the same polyfluoro copolymer used to provide sustained release of the drug or another polyfluoro copolymer that further restricts the diffusion of the drug out of the coating may be applied. The topcoat may be applied by dip coating with mandrel to clear the slots. This

method is disclosed in United States Patent No. 6,153,252. Other methods for applying the topcoat include spin coating and spray coating. Dip coating of the topcoat can be problematic if the drug is very soluble in the coating solvent, which swells the polyfluoro copolymer, and the clear coating solution acts as a zero concentration sink and redissolves previously deposited drug. The time spent in the dip bath may need to be limited so that the drug is not extracted out into the drug-free bath. Drying should be rapid so that the previously deposited drug does not completely diffuse into the topcoat.

10 The amount of therapeutic agent will be dependent upon the particular drug employed and medical condition being treated. Typically, the amount of drug represents about 0.001 percent to about seventy percent of the total coating weight, more typically about 0.001 percent to about sixty percent of the total coating weight. It is possible that the drug may represent as little as 0.0001
15 percent to the total coating weight.

 The quantity and type of polyfluoro copolymers employed in the coating film comprising the pharmaceutical agent will vary depending on the release profile desired and the amount of drug employed. The product may contain blends of
20 the same or different polyfluoro copolymers having different molecular weights to provide the desired release profile or consistency to a given formulation.

 Polyfluoro copolymers may release dispersed drug by diffusion. This can result in prolonged delivery (over, say approximately one to two-thousand hours, preferably two to eight-hundred hours) of effective amounts ($0.001 \mu\text{g}/\text{cm}^2\text{-min}$ to $1000 \mu\text{g}/\text{cm}^2\text{-min}$) of the drug. The dosage may be tailored to the subject being treated, the severity of the affliction, the judgment of the prescribing physician, and the like.

30 Individual formulations of drugs and polyfluoro copolymers may be tested in appropriate *in vitro* and *in vivo* models to achieve the desired drug release profiles. For example, a drug could be formulated with a polyfluoro copolymer, or blend of polyfluoro copolymers, coated onto a stent and placed in an agitated or

circulating fluid system, for example, twenty-five percent ethanol in water.

Samples of the circulating fluid could be taken to determine the release profile (such as by HPLC, UV analysis or use of radiotagged molecules). The release

of a pharmaceutical compound from a stent coating into the interior wall of a

5 lumen could be modeled in appropriate animal system. The drug release profile could then be monitored by appropriate means such as, by taking samples at specific times and assaying the samples for drug concentration (using HPLC to detect drug concentration). Thrombus formation can be modeled in animal models using the In-platelet imaging methods described by Hanson and Harker,
10 Proc. Natl. Acad. Sci. USA 85:3184-3188 (1988). Following this or similar procedures, those skilled in the art will be able to formulate a variety of stent coating formulations.

While not a requirement of the present invention, the coatings and films
15 may be crosslinked once applied to the medical devices. Crosslinking may be affected by any of the known crosslinking mechanisms, such as chemical, heat or light. In addition, crosslinking initiators and promoters may be used where applicable and appropriate. In those exemplary embodiments utilizing crosslinked films comprising pharmaceutical agents, curing may affect the rate at
20 which the drug diffuses from the coating. Crosslinked polyfluoro copolymers films and coatings of the present invention also may be used without drug to modify the surface of implantable medical devices.

EXAMPLES

25

Example 1:

A PVDF homopolymer (Solef® 1008 from Solvay Advanced Polymers, Houston, TX, T_m about 175°C) and polyfluoro copolymers of poly(vinylidene fluoride/HFP), 92/8 and 91/9 weight percent
30 vinylidene fluoride/HFP as determined by F¹⁹ NMR, respectively (eg: Solef® 11010 and 11008, Solvay Advanced Polymers, Houston, TX, T_m about 159 degrees C and 160 degrees C, respectively) were examined as potential coatings for stents. These polymers are soluble in solvents such as, but not

limited to, DMAc, N,N-dimethylformamide (DMF), dimethyl sulfoxide (DMSO), N-methylpyrrolidone (NMP), tetrahydrofuran (THF) and acetone. Polymer coatings were prepared by dissolving the polymers in acetone, at five weight percent as a primer, or by dissolving the polymer in 50/50 DMAc/acetone, at thirty weight percent as a topcoat. Coatings that were applied to the stents by dipping and dried at 60 degrees C in air for several hours, followed by 60 degrees C for three hours in a <100 mm Hg vacuum, resulted in white foamy films. As applied, these films adhered poorly to the stent and flaked off, indicating they were too brittle. When stents coated in this manner were heated above 175 degrees C, i.e. above the melting temperature of the polymer, a clear, adherent film was formed. Since coatings require high temperatures, for example, above the melting temperature of the polymer, to achieve high quality films. As mentioned above, the high temperature heat treatment is unacceptable for the majority of drug compounds due to their thermal sensitivity.

Example 2:

A polyfluoro copolymer (Solef® 21508) comprising 85.5 weight percent vinylidene fluoride copolymerized with 14.5 weight percent HFP, as determined by F^{19} NMR, was evaluated. This copolymer is less crystalline than the polyfluoro homopolymer and copolymers described in Example 1. It also has a lower melting point reported to be about 133 degrees C. Once again, a coating comprising about twenty weight percent of the polyfluoro copolymer was applied from a polymer solution in 50/50 DMAc/MEK. After drying (in air) at 60 degrees C for several hours, followed by 60 degrees C for three hours in a <100 mtorr Hg vacuum, clear adherent films were obtained. This eliminated the need for a high temperature heat treatment to achieve high quality films. Coatings were smoother and more adherent than those of Example 1. Some coated stents that underwent expansion show some degree of adhesion loss and "tenting" as the film pulls away from the metal. Where necessary, modification of coatings containing such copolymers may be made, e.g. by addition of plasticizers or the like to the coating compositions. Films prepared from such coatings may be used to coat stents or other medical devices,

particularly where those devices are not susceptible to expansion to the degree of the stents.

The coating process above was repeated, this time with a coating
5 comprising the 85.5/14.6 (wt/wt) (vinylidene fluoride/HFP) and about thirty
weight percent of rapamycin (Wyeth-Ayerst Laboratories, Philadelphia, PA),
based on total weight of coating solids. Clear films that would occasionally
crack or peel upon expansion of the coated stents resulted. It is believed that
inclusion of plasticizers and the like in the coating composition will result in
10 coatings and films for use on stents and other medical devices that are not
susceptible to such cracking and peeling.

Example 3:

Polyfluoro copolymers of still higher HFP content were then examined.
15 This series of polymers were not semicrystalline, but rather are marketed as
elastomers. One such copolymer is Fluorel™ FC2261Q (from Dyneon, a 3M-
Hoechst Enterprise, Oakdale, MN), a 60.6/39.4 (wt/wt) copolymer of
vinylidene fluoride/HFP. Although this copolymer has a T_g well below room
temperature (T_g about minus twenty degrees C) it is not tacky at room
20 temperature or even at sixty degrees C. This polymer has no detectable
crystallinity when measured by Differential Scanning Calorimetry (DSC) or by
wide angle X-ray diffraction. Films formed on stents as described above were
non-tacky, clear, and expanded without incident when the stents were
expanded.

25

The coating process above was repeated, this time with coatings
comprising the 60.6/39.4 (wt/wt) (vinylidene fluoride/HFP) and about nine, thirty
and fifty weight percent of rapamycin (Wyeth-Ayerst Laboratories, Philadelphia,
PA), based on total weight of coating solids, respectively. Coatings comprising
30 about nine and thirty weight percent rapamycin provided white, adherent, tough
films that expanded without incident on the stent. Inclusion of fifty percent
drug, in the same manner, resulted in some loss of adhesion upon expansion.

Changes in the comonomer composition of the polyfluoro copolymer also can affect the nature of the solid state coating, once dried. For example, the semicrystalline copolymer, Solef® 21508, containing 85.5 percent vinylidene fluoride polymerized with 14.5 percent by weight HFP forms

5 homogeneous solutions with about 30 percent rapamycin (drug weight divided by total solids weight, for example, drug plus copolymer) in DMAc and 50/50 DMAc/MEK. When the film is dried (60 degrees C/16 hours followed by 60 degrees C/3 hours in vacuum of 100 mm Hg) a clear coating, indicating a solid solution of the drug in the polymer, is obtained. Conversely, when an

10 amorphous copolymer, Fluorel™ FC2261Q, of PDVF/HFP at 60.6/39.5 (wt/wt) forms a similar thirty percent solution of rapamycin in DMAc/MEK and is similarly dried, a white film, indicating phase separation of the drug and the polymer, is obtained. This second drug containing film is much slower to release the drug into an *in vitro* test solution of twenty-five percent ethanol in water than is the

15 former clear film of crystalline Solef® 21508. X-ray analysis of both films indicates that the drug is present in a non-crystalline form. Poor or very low solubility of the drug in the high HFP containing copolymer results in slow permeation of the drug through the thin coating film. Permeability is the product of diffusion rate of the diffusing species (in this case the drug) through the film

20 (the copolymer) and the solubility of the drug in the film.

Example 4: In vitro release results of rapamycin from coating.

Figure 3 is a plot of data for the 85.5/14.5 vinylidene fluoride/HFP polyfluoro copolymer, indicating fraction of drug released as a function of time,

25 with no topcoat. Figure 4 is a plot of data for the same polyfluoro copolymer over which a topcoat has been disposed, indicating that most effect on release rate is with a clear topcoat. As shown therein, TC150 refers to a device comprising one hundred fifty micrograms of topcoat, TC235 refers to two hundred thirty-five micrograms of topcoat, etc. The stents before topcoating

30 had an average of seven hundred fifty micrograms of coating containing thirty percent rapamycin. Figure 5 is a plot for the 60.6/39.4 vinylidene fluoride/HFP polyfluoro copolymer, indicating fraction of drug released as a function of time,

showing significant control of release rate from the coating without the use of a topcoat. Release is controlled by loading of drug in the film.

Example 5: *In vivo* stent release kinetics of rapamycin from poly(VDF/HFP).

5 Nine New Zealand white rabbits (2.5-3.0 kg) on a normal diet were given aspirin twenty-four hours prior to surgery, again just prior to surgery and for the remainder of the study. At the time of surgery, animals were premedicated with Acepromazine (0.1-0.2 mg/kg) and anesthetized with a Ketamine/Xylazine mixture (40 mg/kg and 5 mg/kg, respectively). Animals were given a single
10 intraprocedural dose of heparin (150 IU/kg, i.v.)

Arteriotomy of the right common carotid artery was performed and a 5 F catheter introducer (Cordis, Inc.) placed in the vessel and anchored with ligatures. Iodine contrast agent was injected to visualize the right common
15 carotid artery, brachiocephalic trunk and aortic arch. A steerable guide wire (0.014 inch/180 cm, Cordis, Inc.) was inserted *via* the introducer and advanced sequentially into each iliac artery to a location where the artery possesses a diameter closest to 2 mm using the angiographic mapping done previously. Two stents coated with a film made of poly(VDF/HFP):(60.6/39.4) with thirty
20 percent rapamycin were deployed in each animal where feasible, one in each iliac artery, using 3.0 mm balloon and inflation to 8-10 ATM for thirty seconds followed after a one minute interval by a second inflation to 8-10 ATM for thirty seconds. Follow-up angiographs visualizing both iliac arteries are obtained to confirm correct deployment position of the stent.

25

At the end of procedure, the carotid artery was ligated and the skin is closed with 3/0 vicryl suture using a one layered interrupted closure. Animals were given butorolpanol (0.4 mg/kg, s.c.) and gentamycin (4 mg/kg, i.m.). Following recovery, the animals were returned to their cages and allowed free
30 access to food and water.

Due to early deaths and surgical difficulties, two animals were not used in this analysis. Stented vessels were removed from the remaining seven

animals at the following time points: one vessel (one animal) at ten minutes post implant; six vessels (three animals) between forty minutes and two hours post-implant (average, 1.2 hours); two vessels (two animals) at three days post implant; and two vessels (one animal) at seven days post-implant. In one
5 animal at two hours, the stent was retrieved from the aorta rather than the iliac artery. Upon removal, arteries were carefully trimmed at both the proximal and distal ends of the stent. Vessels were then carefully dissected free of the stent, flushed to remove any residual blood, and both stent and vessel frozen immediately, wrapped separately in foil, labeled and kept frozen at minus
10 eighty degrees C. When all samples had been collected, vessels and stents were frozen, transported and subsequently analyzed for rapamycin in tissue and results are illustrated in Figure 4.

Example 6: Purifying the polymer.

15 The Fluorel™ FC2261Q copolymer was dissolved in MEK at about ten weight percent and was washed in a 50/50 mixture of ethanol/water at a 14:1 of ethanol/water to MEK solution ratio. The polymer precipitated out and was separated from the solvent phase by centrifugation. The polymer again was dissolved in MEK and the washing procedure repeated. The polymer was dried
20 after each washing step at sixty degrees C in a vacuum oven (<200 mtorr) over night.

Example 7: *In vivo* testing of coated stents in porcine coronary arteries.

CrossFlex® stents (available from Cordis, a Johnson & Johnson
25 Company) were coated with the "as received" Fluorel™ FC2261Q PVDF copolymer and with the purified polyfluoro copolymer of Example 6, using the dip and wipe approach. The coated stents were sterilized using ethylene oxide and a standard cycle. The coated stents and bare metal stents (controls) were implanted in porcine coronary arteries, where they remained for twenty-eight
30 days.

Angiography was performed on the pigs at implantation and at twenty-eight days. Angiography indicated that the control uncoated stent exhibited about

twenty-one percent restenosis. The polyfluoro copolymer "as received" exhibited about twenty-six percent restenosis (equivalent to the control) and the washed copolymer exhibited about 12.5 percent restenosis.

5 Histology results reported neointimal area at twenty-eight days to be 2.89 ± 0.2 , 3.57 ± 0.4 and 2.75 ± 0.3 , respectively, for the bare metal control, the unpurified copolymer and the purified copolymer.

10 Since rapamycin acts by entering the surrounding tissue, it is preferably only affixed to the surface of the stent making contact with one tissue. Typically, only the outer surface of the stent makes contact with the tissue. Accordingly, in one exemplary embodiment, only the outer surface of the stent is coated with rapamycin.

15 The circulatory system, under normal conditions, has to be self-sealing, otherwise continued blood loss from an injury would be life threatening. Typically, all but the most catastrophic bleeding is rapidly stopped through a process known as hemostasis. Hemostasis occurs through a progression of steps. At high rates of flow, hemostasis is a combination of events involving
20 platelet aggregation and fibrin formation. Platelet aggregation leads to a reduction in the blood flow due to the formation of a cellular plug while a cascade of biochemical steps leads to the formation of a fibrin clot.

Fibrin clots, as stated above, form in response to injury. There are
25 certain circumstances where blood clotting or clotting in a specific area may pose a health risk. For example, during percutaneous transluminal coronary angioplasty, the endothelial cells of the arterial walls are typically injured, thereby exposing the sub-endothelial cells. Platelets adhere to these exposed cells. The aggregating platelets and the damaged tissue initiate further
30 biochemical process resulting in blood coagulation. Platelet and fibrin blood clots may prevent the normal flow of blood to critical areas. Accordingly, there is a need to control blood clotting in various medical procedures. Compounds that do not allow blood to clot are called anti-coagulants. Essentially, an anti-

coagulant is an inhibitor of thrombin formation or function. These compounds include drugs such as heparin and hirudin. As used herein, heparin includes all direct or indirect inhibitors of thrombin or Factor Xa.

5 In addition to being an effective anti-coagulant, heparin has also been demonstrated to inhibit smooth muscle cell growth *in vivo*. Thus, heparin may be effectively utilized in conjunction with rapamycin in the treatment of vascular disease. Essentially, the combination of rapamycin and heparin may inhibit smooth muscle cell growth via two different mechanisms in addition to the
10 heparin acting as an anti-coagulant.

Because of its multifunctional chemistry, heparin may be immobilized or affixed to a stent in a number of ways. For example, heparin may be immobilized onto a variety of surfaces by various methods, including the
15 photolink methods set forth in U.S. Patent Nos. 3,959,078 and 4,722,906 to Guire et al. and U.S. Patent Nos. 5,229,172; 5,308,641; 5,350,800 and 5,415,938 to Cahalan et al. Heparinized surfaces have also been achieved by controlled release from a polymer matrix, for example, silicone rubber, as set forth in U.S. Patent Nos. 5,837,313; 6,099,562 and 6,120,536 to Ding et al.

20 Unlike rapamycin, heparin acts on circulating proteins in the blood and heparin need only make contact with blood to be effective. Accordingly, if used in conjunction with a medical device, such as a stent, it would preferably be only on the side that comes into contact with the blood. For example, if
25 heparin were to be administered via a stent, it would only have to be on the inner surface of the stent to be effective.

In an exemplary embodiment of the invention, a stent may be utilized in combination with rapamycin and heparin to treat vascular disease. In this
30 exemplary embodiment, the heparin is immobilized to the inner surface of the stent so that it is in contact with the blood and the rapamycin is immobilized to the outer surface of the stent so that it is in contact with the surrounding tissue. Figure 7 illustrates a cross-section of a band 102 of the stent 100 illustrated in

Figure 1. As illustrated, the band 102 is coated with heparin 108 on its inner surface 110 and with rapamycin 112 on its outer surface 114.

In an alternate exemplary embodiment, the stent may comprise a
 5 heparin layer immobilized on its inner surface, and rapamycin and heparin on
 its outer surface. Utilizing current coating techniques, heparin tends to form a
 stronger bond with the surface it is immobilized to than does rapamycin.
 Accordingly, it may be possible to first immobilize the rapamycin to the outer
 surface of the stent and then immobilize a layer of heparin to the rapamycin
 10 layer. In this embodiment, the rapamycin may be more securely affixed to the
 stent while still effectively eluting from its polymeric matrix, through the heparin
 and into the surrounding tissue. Figure 8 illustrates a cross-section of a band
 102 of the stent 100 illustrated in Figure 1. As illustrated, the band 102 is
 coated with heparin 108 on its inner surface 110 and with rapamycin 112 and
 15 heparin 108 on its outer surface 114.

There are a number of possible ways to immobilize, i.e., entrapment or
 covalent linkage with an erodible bond, the heparin layer to the rapamycin
 layer. For example, heparin may be introduced into the top layer of the
 20 polymeric matrix. In other embodiments, different forms of heparin may be
 directly immobilized onto the top coat of the polymeric matrix, for example, as
 illustrated in Figure 9. As illustrated, a hydrophobic heparin layer 116 may be
 immobilized onto the top coat layer 118 of the rapamycin layer 112. A
 hydrophobic form of heparin is utilized because rapamycin and heparin
 25 coatings represent incompatible coating application technologies. Rapamycin
 is an organic solvent-based coating and heparin, in its native form, is a water-
 based coating.

As stated above, a rapamycin coating may be applied to stents by a dip,
 30 spray or spin coating method, and/or any combination of these methods.
 Various polymers may be utilized. For example, as described above,
 poly(ethylene-co-vinyl acetate) and polybutyl methacrylate blends may be
 utilized. Other polymers may also be utilized, but not limited to, for example,

polyvinylidene fluoride-co-hexafluoropropylene and polyethylbutyl methacrylate-co-hexyl methacrylate. Also as described above, barrier or top coatings may also be applied to modulate the dissolution of rapamycin from the polymer matrix. In the exemplary embodiment described above, a thin layer of
5 heparin is applied to the surface of the polymeric matrix. Because these polymer systems are hydrophobic and incompatible with the hydrophilic heparin, appropriate surface modifications may be required.

The application of heparin to the surface of the polymeric matrix may be
10 performed in various ways and utilizing various biocompatible materials. For example, in one embodiment, in water or alcoholic solutions, polyethylene imine may be applied on the stents, with care not to degrade the rapamycin (e.g., pH < 7, low temperature), followed by the application of sodium
15 heparinate in aqueous or alcoholic solutions. As an extension of this surface modification, covalent heparin may be linked on polyethylene imine using amide-type chemistry (using a carbodiimide activator, e.g. EDC) or reductive amination chemistry (using CBAS-heparin and sodium cyanoborohydride for coupling). In another exemplary embodiment, heparin may be photolinked on
20 the surface, if it is appropriately grafted with photo initiator moieties. Upon application of this modified heparin formulation on the covalent stent surface, light exposure causes cross-linking and immobilization of the heparin on the coating surface. In yet another exemplary embodiment, heparin may be
25 complexed with hydrophobic quaternary ammonium salts, rendering the molecule soluble in organic solvents (e.g. benzalkonium heparinate, troidodecylmethylammonium heparinate). Such a formulation of heparin may be compatible with the hydrophobic rapamycin coating, and may be applied directly on the coating surface, or in the rapamycin/hydrophobic polymer formulation.

30 It is important to note that the stent, as described above, may be formed from any number of materials, including various metals, polymeric materials and ceramic materials. Accordingly, various technologies may be utilized to immobilize the various drugs, agent, compound combinations thereon.

Specifically, in addition to the polymeric matrices described above biopolymers may be utilized. Biopolymers may be generally classified as natural polymers, while the above-described polymers may be described as synthetic polymers. Exemplary biopolymers, which may be utilized include, agarose, alginate, gelatin, collagen and elastin. In addition, the drugs, agents or compounds may be utilized in conjunction with other percutaneously delivered medical devices such as grafts and profusion balloons.

In addition to utilizing an anti-proliferative and anti-coagulant, anti-inflammatories may also be utilized in combination therewith. One example of such a combination would be the addition of an anti-inflammatory corticosteroid such as dexamethasone with an anti-proliferative, such as rapamycin, cladribine, vincristine, taxol, or a nitric oxide donor and an anti-coagulant, such as heparin. Such combination therapies might result in a better therapeutic effect, i.e., less proliferation as well as less inflammation, a stimulus for proliferation, than would occur with either agent alone. The delivery of a stent comprising an anti-proliferative, anti-coagulant, and an anti-inflammatory to an injured vessel would provide the added therapeutic benefit of limiting the degree of local smooth muscle cell proliferation, reducing a stimulus for proliferation, i.e., inflammation and reducing the effects of coagulation thus enhancing the restenosis-limiting action of the stent.

In other exemplary embodiments of the inventions, growth factor inhibitor or cytokine signal transduction inhibitor, such as the ras inhibitor, R115777, or P38 kinase inhibitor, RWJ67657, or a tyrosine kinase inhibitor, such as tyrphostin, might be combined with an anti-proliferative agent such as taxol, vincristine or rapamycin so that proliferation of smooth muscle cells could be inhibited by different mechanisms. Alternatively, an anti-proliferative agent such as taxol, vincristine or rapamycin could be combined with an inhibitor of extracellular matrix synthesis such as halofuginone. In the above cases, agents acting by different mechanisms could act synergistically to reduce smooth muscle cell proliferation and vascular hyperplasia. This invention is also intended to cover other combinations of two or more such drug agents.

As mentioned above, such drugs, agents or compounds could be administered systemically, delivered locally via drug delivery catheter, or formulated for delivery from the surface of a stent, or given as a combination of systemic and local therapy.

5

In addition to anti-proliferatives, anti-inflammatories and anti-coagulants, other drugs, agents or compounds may be utilized in conjunction with the medical devices. For example, immunosuppressants may be utilized alone or in combination with these other drugs, agents or compounds. Also gene therapy delivery mechanisms such as modified genes (nucleic acids including recombinant DNA) in viral vectors and non-viral gene vectors such as plasmids may also be introduced locally via a medical device. In addition, the present invention may be utilized with cell based therapy.

10

In addition to all of the drugs, agents, compounds and modified genes described above, chemical agents that are not ordinarily therapeutically or biologically active may also be utilized in conjunction with the present invention. These chemical agents, commonly referred to as pro-drugs, are agents that become biologically active upon their introduction into the living organism by one or more mechanisms. These mechanisms include the addition of compounds supplied by the organism or the cleavage of compounds from the agents caused by another agent supplied by the organism. Typically, pro-drugs are more absorbable by the organism. In addition, pro-drugs may also provide some additional measure of time release.

15

The coatings and drugs, agents or compounds described above may be utilized in combination with any number of medical devices, and in particular, with implantable medical devices such as stents and stent-grafts. Other devices such as vena cava filters and anastomosis devices may be used with coatings having drugs, agents or compounds therein. The exemplary stent illustrated in Figures 1 and 2 is a balloon expandable stent. Balloon expandable stents may be utilized in any number of vessels or conduits, and are particularly well suited for use in coronary arteries. Self-expanding stents,

20

25

on the other hand, are particularly well suited for use in vessels where crush recovery is a critical factor, for example, in the carotid artery. Accordingly, it is important to note that any of the drugs, agents or compounds, as well as the coatings described above, may be utilized in combination with self-expanding
5 stents which are known in the art.

Anastomosis is the surgical joining of biological tissues, specifically the joining of tubular organs to create an intercommunication between them. Vascular surgery often involves creating an anastomosis between blood
10 vessels or between a blood vessel and a vascular graft to create or restore a blood flow path to essential tissues. Coronary artery bypass graft surgery (CABG) is a surgical procedure to restore blood flow to ischemic heart muscle whose blood supply has been compromised by occlusion or stenosis of one or more of the coronary arteries. One method for performing CABG surgery
15 involves harvesting a saphenous vein or other venous or arterial conduit from elsewhere in the body, or using an artificial conduit, such as one made of Dacron® or Goretex® tubing, and connecting this conduit as a bypass graft from a viable artery, such as the aorta, to the coronary artery downstream of the blockage or narrowing. It is preferable to utilize natural grafts rather than
20 synthetic grafts. A graft with both the proximal and distal ends of the graft detached is known as a "free graft." A second method involves rerouting a less essential artery, such as the internal mammary artery, from its native location so that it may be connected to the coronary artery downstream of the blockage. The proximal end of the graft vessel remains attached in its native position.
25 This type of graft is known as a "pedicled graft." In the first case, the bypass graft must be attached to the native arteries by an end-to-side anastomosis at both the proximal and distal ends of the graft. In the second technique at least one end-to-side anastomosis must be made at the distal end of the artery used for the bypass. In the description of the exemplary embodiment given below
30 reference will be made to the anastomoses on a free graft as the proximal anastomosis and the distal anastomosis. A proximal anastomosis is an anastomosis on the end of the graft vessel connected to a source of blood, for example, the aorta and a distal anastomosis is an anastomosis on the end of

the graft vessel connected to the destination of the blood flowing through it, for example, a coronary artery. The anastomoses will also sometimes be called the first anastomosis or second anastomosis, which refers to the order in which the anastomoses are performed regardless of whether the anastomosis is on
5 the proximal or distal end of the graft.

At present, essentially all vascular anastomoses are performed by conventional hand suturing. Suturing the anastomoses is a time-consuming and difficult task, requiring much skill and practice on the part of the surgeon. It
10 is important that each anastomosis provide a smooth, open flow path for the blood and that the attachment be completely free of leaks. A completely leak-free seal is not always achieved on the very first try. Consequently, there is a frequent need for resuturing of the anastomosis to close any leaks that are detected.

15

The time consuming nature of hand sutured anastomoses is of special concern in CABG surgery for several reasons. Firstly, the patient is required to be supported on cardiopulmonary bypass (CPB) for most of the surgical procedure, the heart must be isolated from the systemic circulation (i.e. "cross-clamped"), and the heart must usually be stopped, typically by infusion of cold
20 cardioplegia solution, so that the anastomosis site on the heart is still and blood-free during the suturing of the anastomosis. Cardiopulmonary bypass, circulatory isolation and cardiac arrest are inherently very traumatic, and it has been found that the frequency of certain post-surgical complications varies
25 directly with the duration for which the heart is under cardioplegic arrest (frequently referred to as the "crossclamp time"). Secondly, because of the high cost of cardiac operating room time, any prolongation of the surgical procedure can significantly increase the cost of the bypass operation to the hospital and to the patient. Thus, it is desirable to reduce the duration of the
30 crossclamp time and of the entire surgery by expediting the anastomosis procedure without reducing the quality or effectiveness of the anastomoses.

The already high degree of manual skill required for conventional manually sutured anastomoses is even more elevated for closed-chest or port-access thoracoscopic bypass surgery, a newly developed surgical procedure designed to reduce the morbidity of CABG surgery as compared to the standard open-chest CABG procedure. In the closed-chest procedure, surgical access to the heart is made through narrow access ports made in the intercostal spaces of the patient's chest, and the procedure is performed under thoracoscopic observation. Because the patient's chest is not opened, the suturing of the anastomoses must be performed at some distance, using elongated instruments positioned through the access ports for approximating the tissues and for holding and manipulating the needles and sutures used to make the anastomoses. This requires even greater manual skill than the already difficult procedure of suturing anastomoses during open-chest CABG surgery.

In order to reduce the difficulty of creating the vascular anastomoses during either open or closed-chest CABG surgery, it would be desirable to provide a rapid means for making a reliable end-to-side anastomosis between a bypass graft or artery and the aorta or the native vessels of the heart. A first approach to expediting and improving anastomosis procedures has been through stapling technology. Stapling technology has been successfully employed in many different areas of surgery for making tissue attachments faster and more reliably. The greatest progress in stapling technology has been in the area of gastrointestinal surgery. Various surgical stapling instruments have been developed for end-to-end, side-to-side, and end-to-side anastomoses of hollow or tubular organs, such as the bowel. These instruments, unfortunately, are not easily adaptable for use in creating vascular anastomoses. This is partially due to the difficulty in miniaturizing the instruments to make them suitable for smaller organs such as blood vessels. Possibly even more important is the necessity of providing a smooth, open flow path for the blood. Known gastrointestinal stapling instruments for end-to-side or end-to-end anastomosis of tubular organs are designed to create an inverted anastomosis, that is, one where the tissue folds inward into the lumen

of the organ that is being attached. This is acceptable in gastrointestinal surgery, where it is most important to approximate the outer layers of the intestinal tract (the serosa). This is the tissue which grows together to form a strong, permanent connection. However, in vascular surgery this geometry is unacceptable for several reasons. Firstly, the inverted vessel walls would cause a disruption in the blood flow. This could cause decreased flow and ischemia downstream of the disruption, or, worse yet, the flow disruption or eddies created could become a locus for thrombosis which could shed emboli or occlude the vessel at the anastomosis site. Secondly, unlike the intestinal tract, the outer surfaces of the blood vessels (the adventitia) will not grow together when approximated. The sutures, staples, or other joining device may therefore be needed permanently to maintain the structural integrity of the vascular anastomosis. Thirdly, to establish a permanent, nonthrombogenic vessel, the innermost layer (the endothelium) should grow together for a continuous, uninterrupted lining of the entire vessel. Thus, it would be preferable to have a stapling instrument that would create vascular anastomoses that are everted, that is folded outward, or which create direct edge-to-edge coaptation without inversion.

At least one stapling instrument has been applied to performing vascular anastomoses during CABG surgery. This device, first adapted for use in CABG surgery by Dr. Vasilii I. Kolesov and later refined by Dr. Evgenii V. Kolesov (U.S. Patent No. 4,350,160), was used to create an end-to-end anastomosis between the internal mammary artery (IMA) or a vein graft and one of the coronary arteries, primarily the left anterior descending coronary artery (LAD). Because the device could only perform end-to-end anastomoses, the coronary artery first had to be severed and dissected from the surrounding myocardium, and the exposed end everted for attachment. This technique limited the indications of the device to cases where the coronary artery was totally occluded, and therefore there was no loss of blood flow by completely severing the coronary artery downstream of the blockage to make the anastomosis. Consequently, this device is not applicable where the coronary artery is only partially occluded and is not at all applicable to making the proximal side-to-

end anastomosis between a bypass graft and the aorta.

One attempt to provide a vascular stapling device for end-to-side vascular anastomoses is described in U.S. Patent No. 5,234,447, issued to Kaster et al. for a Side-to-end Vascular Anastomotic Staple Apparatus. Kaster et al. provide a ring-shaped staple with staple legs extending from the proximal and distal ends of the ring to join two blood vessels together in an end-to-side anastomosis. However, Kaster et al. does not provide a complete system for quickly and automatically performing an anastomosis. The method of applying the anastomosis staple disclosed by Kaster et al. involves a great deal of manual manipulation of the staple, using hand operated tools to individually deform the distal tines of the staple after the graft has been attached and before it is inserted into the opening made in the aortic wall. One of the more difficult maneuvers in applying the Kaster et al. staple involves carefully everting the graft vessel over the sharpened ends of the staple legs, then piercing the evened edge of the vessel with the staple legs. Experimental attempts to apply this technique have proven to be very problematic because of difficulty in manipulating the graft vessel and the potential for damage to the graft vessel wall. For speed, reliability and convenience, it is preferable to avoid the need for complex maneuvers while performing the anastomosis. Further bending operations must then be performed on the staple legs. Once the distal tines of the staple have been deformed, it may be difficult to insert the staple through the aortotomy opening. Another disadvantage of the Kaster et al. device is that the distal tines of the staple pierce the wall of the graft vessel at the point where it is evened over the staple. Piercing the wall of the graft vessel potentially invites leaking of the anastomosis and may compromise the structural integrity of the graft vessel wall, serving as a locus for a dissection or even a tear which could lead to catastrophic failure. Because the Kaster et al. staple legs only apply pressure to the anastomosis at selected points, there is a potential for leaks between the staple legs. The distal tines of the staple are also exposed to the blood flow path at the anastomotic site where it is most critical to avoid the potential for thrombosis. There is also the potential that exposure of the medial layers of the graft vessel where the staple pierces the

5 wall could be a site for the onset of intimal hyperplasia, which would compromise the long-term patency of the graft as described above. Because of these potential drawbacks, it is desirable to make the attachment to the graft vessel as atraumatic to the vessel wall as possible and to eliminate as much as possible the exposure of any foreign materials or any vessel layers other than a smooth uninterrupted intimal layer within the anastomosis site or within the graft vessel lumen.

A second approach to expediting and improving anastomosis procedures is through the use of anastomotic fittings for joining blood vessels together. One attempt to provide a vascular anastomotic fitting device for end-to-side vascular anastomoses is described in U.S. Patent No. 4,366,819, issued to Kaster for an Anastomotic Fitting. This device is a four-part anastomotic fitting having a tubular member over which the graft vessel is evened, a ring flange which engages the aortic wall from within the aortic lumen, and a fixation ring and a locking ring which engage the exterior of the aortic wall. Another similar Anastomotic Fitting is described in U.S. Patent No. 4,368,736, also issued to Kaster. This device is a tubular fitting with a flanged distal end that fastens to the aortic wall with an attachment ring, and a proximal end with a graft fixation collar for attaching to the graft vessel. These devices have a number of drawbacks. Firstly, the anastomotic fittings described expose the foreign material of the anastomotic device to the blood flow path within the arteries. This is undesirable because foreign materials within the blood flow path can have a tendency to cause hemolysis, platelet deposition and thrombosis. Immune responses to foreign material, such as rejection of the foreign material or auto-immune responses triggered by the presence of foreign material, tend to be stronger when the material is exposed to the bloodstream. As such, it is preferable that as much as possible of the interior surfaces of an anastomotic fitting that will be exposed to the blood flow path be covered with vascular tissue, either from the target vessel or from the graft vessel, so that a smooth, continuous, hemocompatible endothelial layer will be presented to the bloodstream. The anastomotic fitting described by Kaster in the '819 patent also has the potential drawback that the spikes that hold the

graft vessel onto the anastomotic fitting are very close to the blood flow path, potentially causing trauma to the blood vessel that could lead to leaks in the anastomosis or compromise of the mechanical integrity of the vessels.

Consequently, it is desirable to provide an anastomosis fitting that is as
5 atraumatic to the graft vessel as possible. Any sharp features such as attachment spikes should be placed as far away from the blood flow path and the anastomosis site as possible so that there is no compromise of the anastomosis seal or the structural integrity of the vessels.

10 Another device, the 3M-Unilink device for end-to-end anastomosis (U.S. Patent Nos. 4,624,257; 4,917,090; 4,917,091) is designed for use in microsurgery, such as for reattaching vessels severed in accidents. This device provides an anastomosis clamp that has two eversion rings which are locked
15 together by a series of impaling spikes on their opposing faces. However, this device is awkward for use in end-to-side anastomosis and tends to deform the target vessel; therefore it is not currently used in CABG surgery. Due to the delicate process needed to insert the vessels into the device, it would also be unsuitable for port-access surgery.

20 In order to solve these and other problems, it is desirable to provide an anastomosis device which performs an end-to-side anastomosis between blood vessels or other hollow organs and vessels. It is also desirable to provide an anastomosis device which minimizes the trauma to the blood vessels while performing the anastomosis, which minimizes the amount of foreign materials
25 exposed to the blood flow path within the blood vessels and which avoids leakage problems, and which promotes rapid endothelialization and healing. It is also desirable that the invention provide a complete system for quickly and automatically performing an anastomosis with a minimal amount of manual manipulation.

30

Anastomosis devices may be utilized to join biological tissues, and more particularly, joining tubular organs to create a fluid channel. The connections between the tubular organs or vessels may be made side to side, end to end

and/or end to side. Typically, there is a graft vessel and a target vessel. The target vessel may be an artery, vein or any other conduit or fluid carrying vessel, for example, coronary arteries. The graft vessel may comprise a

5 Anastomosis devices may comprise any suitable biocompatible materials, for example, metals, polymers and elastomers. In addition, there are a wide variety of designs and configurations for anastomosis devices depending on the type of connection to be made. Similarly to stents, anastomosis devices cause some injury to the target vessel, thereby provoking a response from the
10 body. Therefore, as in the case with stents, there is the potential for smooth muscle cell proliferation which can lead to blocked connections. Accordingly, there is a need to minimize or substantially eliminate smooth muscle cell proliferation and inflammation at the anastomotic site. Rapamycin and/or other drugs, agents or compounds may be utilized in a manner analogous to stents
15 as described above. In other words, at least a portion of the anastomosis device may be coated with rapamycin or other drug, agent or compound.

Figures 10-13 illustrate an exemplary anastomosis device 200 for an end to side anastomosis. The exemplary anastomosis device 200 comprises a
20 fastening flange 202 and attached staple members 204. As stated above, the anastomosis device may comprise any suitable biocompatible material. Preferably, the anastomosis device 200 comprises a deformable biocompatible metal, such as a stainless steel alloy, a titanium alloy or a cobalt alloy. Also as stated above, a surface coating or surface coating comprising a drug, agent or
25 compound may be utilized to improve the biocompatibility or other material characteristics of the device as well as to reduce or substantially eliminate the body's response to its placement therein.

In the exemplary embodiment, the fastening flange 202 resides on the
30 interior surface 206 of the target vessel wall 208 when the anastomosis is completed. In order to substantially reduce the risk of hemolysis, thrombogenesis or foreign body reactions, the total mass of the fastening

flange 202 is preferably as small as possible to reduce the amount of foreign material within the target vessel lumen 210.

The fastening flange 202 is in the form of a wire ring with an internal
5 diameter, which when fully expanded, is slightly greater than the outside
diameter of the graft vessel wall 214 and of the opening 216 made in the target
vessel wall 208. Initially, the wire ring of the fastening flange 202 has a rippled
wave-like shape to reduce the diameter of the ring so that it will easily fit
through the opening 216 in the target vessel wall 208. The plurality of staple
10 members 204 extend substantially perpendicular from the wire ring in the
proximal direction. In the illustrative exemplary embodiment, there are nine
staple members 204 attached to the wire ring fastening flange 202. Other
variations of the anastomosis device 200 might typically have from four to
twelve staple members 204 depending on the size of the vessels to be joined
15 and the security of attachment required in the particular application. The staple
members 204 may be integrally formed with the wire ring fastening flange 202
or the staple members 204 may be attached to the fastening flange 202 by
welding, brazing or any other suitable joining method. The proximal ends 218
of the staple members 204 are sharpened to easily pierce the target vessel
20 wall 208 and the graft vessel wall 214. Preferably, the proximal ends 218 of
the staple members 204 have barbs 220 to improve the security of the
attachment when the anastomosis device 200 is deployed. The anastomosis
device 200 is prepared for use by mounting the device onto the distal end of an
application instrument 222. The fastening flange 202 is mounted on an anvil
25 224 attached to the distal end of the elongated shaft 226 of the application
instrument 222. The staple members 204 are compressed inward against a
conical holder 228 attached to the instrument 222 proximal to the anvil 224.
The staple members 204 are secured in this position by a cap 230 which is
slidably mounted on the elongated shaft 226. The cap 230 moves distally to
30 cover the sharpened, barbed proximal ends 218 of the staple members 204
and to hold them against the conical holder 228. The application instrument
222 is then inserted through the lumen 232 of the graft vessel 214. This may
be done by inserting the application instrument 222 through the graft vessel

lumen 232 from the proximal to the distal end of the graft vessel 214, or it may be done by backloading the elongated shaft 226 of the application instrument 222 into the graft vessel lumen 232 from the distal end to the proximal end, whichever is most convenient in the case. The anvil 224 and conical holder 228 on the distal end of the application instrument 222 with the anastomosis device 200 attached is extended through the opening 216 into the lumen 210 of the target vessel.

Next, the distal end 234 of the graft vessel wall 214 is everted against the exterior surface 236 of the target vessel wall 208 with the graft vessel lumen 232 centered over the opening 216 in the target vessel wall 208. The cap 230 is withdrawn from the proximal ends 218 of the staple members 204, allowing the staple members 204 to spring outward to their expanded position. The application instrument 222 is then drawn in the proximal direction so that the staple members pierce the target vessel wall 208 surrounding the opening 216 and the everted distal end 234 of the graft vessel 214.

The application instrument 222 has an annular staple former 238 which surrounds the outside of the graft vessel 214. Slight pressure on the everted graft vessel wall from the annular staple former 238 during the piercing step assists in piercing the staple members 204 through the graft vessel wall 214. Care should be taken not to apply too much pressure with the annular staple former 238 at this point in the process because the staple members 204 could be prematurely deformed before they have fully traversed the vessel walls. If desired, an annular surface made of a softer material, such as an elastomer, can be provided on the application instrument 222 to back up the vessel walls as the staple members 204 pierce through them.

Once the staple members 204 have fully traversed the target vessel wall 208 and the graft vessel wall 214, the staple former 238 is brought down with greater force while supporting the fastening flange 202 with the anvil 224. The staple members 204 are deformed outward so that the sharpened, barbed ends 218 pierce back through the everted distal end 234 and into the target

vessel wall 208 to form a permanent attachment. To complete the anastomosis, the anvil 224 is withdrawn through the graft vessel lumen 232. As the anvil 224 passes through the wire ring fastening flange 202, it straightens out the wave-like ripples so that the wire ring flange 202 assumes its full expanded diameter. Alternately, the wire ring fastening flange 202 may be made of a resilient material so that the flange 202 may be compressed and held in a rippled or folded position until it is released within the target vessel lumen 210, whereupon it will resume its full expanded diameter. Another alternate construction would be to move the anastomosis device of a shape-memory alloy so that the fastening flange may be compressed and inserted through the opening in the target vessel, whereupon it would be returned to its full expanded diameter by heating the device 200 to a temperature above the shape-memory transition temperature.

15 In the above-described exemplary embodiment, the staple members 204 and/or the wire ring fastening flange 202 may be coated with any of the above-described agents, drugs or compounds such as rapamycin to prevent or substantially reduce smooth muscle wall proliferation.

20 Figure 14 illustrates an alternate exemplary embodiment of an anastomosis device. Figure 14 is a side view of an apparatus for joining at least two anatomical structures, according to another exemplary embodiment of the present invention. Apparatus 300 includes a suture 302 having a first end 304 and a second end 306, the suture 302 being constructed for passage through anatomical structures in a manner to be described subsequently. Suture 302 may be formed from a wide variety of materials, for example, monofilament materials having minimal memory, including polypropylene or polyamide. Any appropriate diameter size may be used, for example, through 8-0. Other suture types and sizes are also possible, of course, and are equally contemplated by the present invention.

A needle 308 preferably is curved and is disposed at the first end 304 of the suture 302. A sharp tip 310 of needle 308 enables easy penetration of

various anatomical structures and enables the needle 308 and the suture 302 to readily pass therethrough. The needle 308 may be attached to the suture 302 in various ways, for example, by swedging, preferably substantially matching the outer diameter of the needle 308 and the suture 302 as closely as possible.

Apparatus 300 also includes a holding device 312 disposed at the second end 306 of the suture 302. The holding device 312 includes first and second limbs 314, 316, according to the illustrated exemplary embodiment, and preferably is of greater stiffness than the suture 302. The first limb 314 may be connected to suture 302 in a number of ways, for example, by swedging, preferably substantially matching the outside diameter of the suture 302 and the holding device 312 as closely as possible. The holding device 312 includes a staple structure comprising a bendable material that preferably is soft and malleable enough to crimp and hold its crimped position on the outside of an anastomosis. Such materials may include titanium or stainless steel. The holding device 312 may be referred to as a staple, according to the illustrated embodiment, and the suture 302 and the needle 308 a delivery system for staple 312.

20

Figure 14 illustrates one of the many possible initial configurations of holding device 312, i.e. the configuration the holding device 312 is in upon initial passage through the anatomical structures and/or at a point in time beforehand. As will be described, the holding device 312 is movable from the initial configuration to a holding configuration, in which holding device 312 holds the anatomical structures together. According to the illustrated exemplary embodiments, the holding device 312 assumes the holding configuration when it is bent or crimped, as shown in Figure 19 (further described below).

30

The holding device 312 preferably is substantially V-shaped or substantially U-shaped, as illustrated, but may assume a wide variety of shapes to suit particular surgical situations and/or surgeon preference. For example, one of limbs 314, 316 may be straight and the other curved, or limbs

314, 316 may be collinear. The holding device 312 preferably is as smooth and round in cross-section as the needle 308. Further, the diameters of the needle 308, the suture 302, and the holding device 312 preferably are substantially identical, especially the needle 308 and the holding device 312, to avoid
5 creating holes in the anatomical structures that are larger than the diameter of the staple 312. Such holes likely would cause bleeding and/or leakage.

A method of using apparatus 300 is illustrated in Figures 15-19. First, as illustrated in Figure 15, the needle 308 passes through anatomical structures
10 318, 320, which are, for example, vascular structures. Specifically, according to the illustrated exemplary embodiment, the needle 308 passes through the edges 322, 324 of vascular structures 318, 320. Then, as shown in Figure 16, the needle 308 pulls suture 302 into and through both structures 318, 320. The staple 312 then is pulled into desired proximity with structures 318, 320, as
15 shown in Figures 17-19, such that it is engaged on both sides of the illustrated anastomosis and associated lumen 326. According to one exemplary embodiment, traction is placed on suture 302 to hook staple 312 into position.

As illustrated in Figure 19 and as referenced earlier, the staple 312 then
20 is moved from its initial configuration to a holding or crimped configuration 328, in which anatomical structures 318, 320 are joined together to effect an anastomosis between them. The staple 312 creates a substantially three hundred sixty -degree loop at the edge of the anastomosis, with crimped portion 330 outside lumen 321. A wide variety of tools and/or mechanisms may
25 be used to crimp the staple 312 into its holding configuration, for example, in the manner of closure of a vascular clip. The same tool, or an alternative tool, may then be used to separate the staple 312 from the suture 302, for example, by cutting.

30 Thus, the staple 312 holds vascular structures 318, 320 together from inside the vascular structures, as well as from outside, unlike the many prior art staples that secure opposed structures only externally. This achieves a number of advantages, as described above. Not only does a better approximation

result, but crimping a staple is simpler than tying one or more knots and is also less likely traumatic on tissue. Staple closure with a single crimp provides less tension on an anastomosis, for example, than a knot requiring several throws. Embodiments of the invention are especially advantageous in minimally
5 invasive surgical situations, as knot-tying with, for example, a knot pusher in a minimally invasive setting through a small port is particularly tedious and can require up to four or five throws to prevent slippage. Crimping a staple through the port, as with embodiments of the invention, is far simpler and eliminates much of the difficulty.

10

According to one exemplary embodiment, the surgeon achieves a precise approximation of the vascular or other structures with preferably a limited number of staples or other holding devices, and then completes the anastomosis with biologic glue or laser techniques. The holding devices, for
15 example, two or more in number, may be used to orient or line up the structures initially and thus used as a "pilot" for guiding the completion of the anastomosis.

In the above described exemplary embodiment, the holding device 312
20 may be coated with any of the above-described drugs, agents or compounds such as rapamycin to prevent or substantially reduce smooth muscle cell proliferation.

As described above, various drugs, agents or compounds may be locally
25 delivered via medical devices. For example, rapamycin and heparin may be delivered by a stent to reduce restenosis, inflammation, and coagulation. Various techniques for immobilizing the drugs, agents or compounds are discussed above, however, maintaining the drugs, agents or compounds on the medical devices during delivery and positioning is critical to the success of
30 the procedure or treatment. For example, removal of the drug, agent or compound coating during delivery of the stent can potentially cause failure of the device. For a self-expanding stent, the retraction of the restraining sheath may cause the drugs, agents or compounds to rub off the stent. For a balloon

expandable stent, the expansion of the balloon may cause the drugs, agents or compounds to simply delaminate from the stent through contact with the balloon or via expansion. Therefore, prevention of this potential problem is important to have a successful therapeutic medical device, such as a stent.

5

There are a number of approaches that may be utilized to substantially reduce the above-described concern. In one exemplary embodiment, a lubricant or mold release agent may be utilized. The lubricant or mold release agent may comprise any suitable biocompatible lubricious coating. An exemplary lubricious coating may comprise silicone. In this exemplary embodiment, a solution of the silicone base coating may be introduced onto the balloon surface, onto the polymeric matrix, and/or onto the inner surface of the sheath of a self-expanding stent delivery apparatus and allowed to air cure. Alternately, the silicone based coating may be incorporated into the polymeric matrix. It is important to note, however, that any number of lubricious materials may be utilized, with the basic requirements being that the material be biocompatible, that the material not interfere with the actions/effectiveness of the drugs, agents or compounds and that the material not interfere with the materials utilized to immobilize the drugs, agents or compounds on the medical device. It is also important to note that one or more, or all of the above-described approaches may be utilized in combination.

15
20

Referring now to Figure 20, there is illustrated a balloon 400 of a balloon catheter that may be utilized to expand a stent *in situ*. As illustrated, the balloon 400 comprises a lubricious coating 402. The lubricious coating 402 functions to minimize or substantially eliminate the adhesion between the balloon 400 and the coating on the medical device. In the exemplary embodiment described above, the lubricious coating 402 would minimize or substantially eliminate the adhesion between the balloon 400 and the heparin or rapamycin coating. The lubricious coating 402 may be attached to and maintained on the balloon 400 in any number of ways including but not limited to dipping, spraying, brushing or spin coating of the coating material from a solution or suspension followed by curing or solvent removal step as needed.

25
30

Materials such as synthetic waxes, e.g. diethyleneglycol monostearate, hydrogenated castor oil, oleic acid, stearic acid, zinc stearate, calcium stearate, ethylenebis (stearamide), natural products such as paraffin wax, spermaceti
 5 wax, carnuba wax, sodium alginate, ascorbic acid and flour, fluorinated compounds such as perfluoroalkanes, perfluorofatty acids and alcohol, synthetic polymers such as silicones e.g. polydimethylsiloxane, polytetrafluoroethylene, polyfluoroethers, polyalkylglycol e.g. polyethylene glycol waxes, and inorganic materials such as talc, kaolin, mica, and silica may
 10 be used to prepare these coatings. Vapor deposition polymerization e.g. parylene-C deposition, or RF-plasma polymerization of perfluoroalkenes and perfluoroalkanes can also be used to prepare these lubricious coatings.

Figure 21 illustrates a cross-section of a band 102 of the stent 100
 15 illustrated in Figure 1. In this exemplary embodiment, the lubricious coating 500 is immobilized onto the outer surface of the polymeric coating. As described above, the drugs, agents or compounds may be incorporated into a polymeric matrix. The stent band 102 illustrated in Figure 21 comprises a base coat 502 comprising a polymer and rapamycin and a top coat 504 or diffusion
 20 layer 504 also comprising a polymer. The lubricious coating 500 is affixed to the top coat 502 by any suitable means, including but not limited to spraying, brushing, dipping or spin coating of the coating material from a solution or suspension with or without the polymers used to create the top coat, followed by curing or solvent removal step as needed. Vapor deposition polymerization
 25 and RF-plasma polymerization may also be used to affix those lubricious coating materials that lend themselves to this deposition method, to the top coating. In an alternate exemplary embodiment, the lubricious coating may be directly incorporated into the polymeric matrix.

30 If a self-expanding stent is utilized, the lubricious coating may be affixed to the inner surface of the restraining sheath. Figure 22 illustrates a partial cross-sectional view of self-expanding stent 200 within the lumen of a delivery apparatus sheath 14. As illustrated, a lubricious coating 600 is affixed to the

inner surfaces of the sheath 14. Accordingly, upon deployment of the stent 200, the lubricious coating 600 preferably minimizes or substantially eliminates the adhesion between the sheath 14 and the drug, agent or compound coated stent 200.

5

In an alternate approach, physical and/or chemical cross-linking methods may be applied to improve the bond strength between the polymeric coating containing the drugs, agents or compounds and the surface of the medical device or between the polymeric coating containing the drugs, agents or compounds and a primer. Alternately, other primers applied by either traditional coating methods such as dip, spray or spin coating, or by RF-plasma polymerization may also be used to improve bond strength. For example, as shown in Figure 23, the bond strength can be improved by first depositing a primer layer 700 such as vapor polymerized parylene-C on the device surface, and then placing a secondary layer 702 which comprises a polymer that is similar in chemical composition to the one or more of the polymers that make up the drug-containing matrix 704, e.g., polyethylene-co-vinyl acetate or polybutyl methacrylate but has been modified to contain cross-linking moieties. This secondary layer 702 is then cross-linked to the primer after exposure to ultra-violet light. It should be noted that anyone familiar with the art would recognize that a similar outcome could be achieved using cross-linking agents that are activated by heat with or without the presence of an activating agent. The drug-containing matrix 704 is then layered onto the secondary layer 702 using a solvent that swells, in part or wholly, the secondary layer 702. This promotes the entrainment of polymer chains from the matrix into the secondary layer 702 and conversely from the secondary layer 702 into the drug-containing matrix 704. Upon removal of the solvent from the coated layers, an interpenetrating or interlocking network of the polymer chains is formed between the layers thereby increasing the adhesion strength between them. A top coat 706 is used as described above.

30

A related difficulty occurs in medical devices such as stents. In the drug-coated stents crimped state, some struts come into contact with each

other and when the stent is expanded, the motion causes the polymeric coating comprising the drugs, agents or compounds to stick and stretch. This action may potentially cause the coating to separate from the stent in certain areas. The predominant mechanism of the coating self-adhesion is believed to be due to mechanical forces. When the polymer comes in contact with itself, its chains can tangle causing the mechanical bond, similar to Velcro®. Certain polymers do not bond with each other, for example, fluoropolymers. For other polymers, however, powders may be utilized. In other words, a powder may be applied to the one or more polymers incorporating the drugs, agents or other compounds on the surfaces of the medical device to reduce the mechanical bond. Any suitable biocompatible material which does not interfere with the drugs, agents, compounds or materials utilized to immobilize the drugs, agents or compounds onto the medical device may be utilized. For example, a dusting with a water soluble powder may reduce the tackiness of the coatings surface and this will prevent the polymer from sticking to itself thereby reducing the potential for delamination. The powder should be water-soluble so that it does not present an emboli risk. The powder may comprise an anti-oxidant, such as vitamin C, or it may comprise an anti-coagulant, such as aspirin or heparin. An advantage of utilizing an anti-oxidant may be in the fact that the anti-oxidant may preserve the other drugs, agents or compounds over longer periods of time.

It is important to note that crystalline polymers are generally not sticky or tacky. Accordingly, if crystalline polymers are utilized rather than amorphous polymers, then additional materials may not be necessary. It is also important to note that polymeric coatings without drugs, agents and/or compounds may improve the operating characteristics of the medical device. For example, the mechanical properties of the medical device may be improved by a polymeric coating, with or without drugs, agents and/or compounds. A coated stent may have improved flexibility and increased durability. In addition, the polymeric coating may substantially reduce or eliminate galvanic corrosion between the different metals comprising the medical device. The same holds true for anastomosis devices.

As stated above, for a self-expanding stent, the retraction of the restraining sheath may cause the drugs, agents or compounds to rub off the stent. Accordingly, in an alternate exemplary embodiment, the stent delivery device may be modified to reduce the potential of rubbing off the coating. This is especially important for long stents, for example, long rapamycin coated stents. In addition, there is also the potential of damaging the stent itself when the delivery sheath is retracted during stent deployment. Accordingly, the stent delivery device may be modified to substantially reduce the forces acting on certain areas of the stent by distributing the forces to more areas of the stent. The stent and stent delivery system described herein are intended to be merely illustrative in nature and those skilled in the art will recognize that the designs disclosed may be incorporated into any number of stents and stent delivery systems.

Figures 35 and 36 illustrate an exemplary self-expanding stent delivery apparatus 5010 in accordance with the present invention. Apparatus 5010 comprises inner and outer coaxial tubes. The inner tube is called the shaft 5012 and the outer tube is called the sheath 5014. A self-expanding stent 7000 is located within the sheath 5014, wherein the stent 7000 makes frictional contact with the sheath 5014 and the shaft 5012 is disposed coaxially within a lumen of the stent 7000.

Shaft 5012 has proximal and distal ends 5016 and 5018 respectively. The proximal end 5016 of the shaft 5012 has a Luer guidewire hub 5020 attached thereto. As seen best from Figure 44, the proximal end 5016 of the shaft 5012 is preferably a ground stainless steel hypotube. In one exemplary embodiment, the hypotube is stainless steel and has a 0.042 inch outside diameter at its proximal end and then tapers to a 0.036 inch outside diameter at its distal end. The inside diameter of the hypotube is 0.032 inch throughout its length. The tapered outside diameter is utilized to gradually change the stiffness of the hypotube along its length. This change in the hypotube stiffness allows for a more rigid proximal end or handle end that is needed

during stent deployment. If the proximal end is not stiff enough, the hypotube section extending beyond the Tuohy Borst valve described below could buckle as the deployment forces are transmitted. The distal end of the hypotube is more flexible allowing for better track-ability in tortuous vessels. The distal end
5 of the hypotube also needs to be flexible to minimize the transition between the hypotube and the coil section described below.

As will be described in greater detail below, shaft 5012 has a body portion 5022, wherein at least a section thereof is made from a flexible coiled
10 member 5024, looking very much like a compressed or closed coil spring. Shaft 5012 also includes a distal portion 5026, distal to body portion 5022, which is preferably made from a coextrusion of high-density polyethylene and Nylon®. The two portions 5022 and 5026 are joined together by any number of means known to those of ordinary skill in the art including heat fusing,
15 adhesive bonding, chemical bonding or mechanical attachment.

As best seen from Figure 37, the distal portion 5026 of the shaft 5012 has a distal tip 5028 attached thereto. Distal tip 5028 may be made from any number of suitable materials known in the art including polyamide,
20 polyurethane, polytetrafluoroethylene, and polyethylene including multi-layer or single layer construction. The distal tip 5028 has a proximal end 5030 whose diameter is substantially the same as the outer diameter of the sheath 5014 which is immediately adjacent thereto. The distal tip 5028 tapers to a smaller diameter from its proximal end 5030 to its distal end 5032, wherein the distal
25 end 5032 of the distal tip 5028 has a diameter smaller than the inner diameter of the sheath 5014.

The stent delivery apparatus 5010 glides over a guide wire 8000 (shown in Figure 35) during navigation to the stent deployment site. As used herein,
30 guidewire may also refer to similar guiding devices which have a distal protection apparatus incorporated herein. One preferred distal protection device is disclosed in published PCT Application 98/33443, having an international filing date of February 3, 1998. As discussed above, if the distal

tip 5028 is too stiff it will overpower the guide wire path and push the guide wire 8000 against the lumen wall and in some very tortuous settings the stent delivery apparatus 5010 could prolapse the wire. Overpowering of the wire and pushing of the apparatus against the lumen wall can prevent the device from reaching the target area because the guide wire will no longer be directing the device. Also, as the apparatus is advanced and pushed against the lumen wall, debris from the lesion can be dislodged and travel upstream causing complications to distal vessel lumens. The distal tip 5028 is designed with an extremely flexible leading edge and a gradual transition to a less flexible portion. The distal tip 5028 may be hollow and may be made of any number of suitable materials, including 40D Nylon®. Its flexibility may be changed by gradually increasing the thickness of its cross-sectional diameter, whereby the diameter is thinnest at its distal end, and is thickest at its proximal end. That is, the cross-sectional diameter and wall thickness of the distal tip 5028 increases as you move in the proximal direction. This gives the distal end 5032 of the distal tip 5028 the ability to be directed by the guidewire prior to the larger diameter and thicker wall thickness, less flexible portion, of the distal tip 5028 overpowering the guidewire. Over-powering the wire, as stated above, is when the apparatus, due to its stiffness, dictates the direction of the device instead of following the wire.

The guidewire lumen 5034 has a diameter that is matched to hug the recommended size guide wire so that there is a slight frictional engagement between the guidewire 8000 and the guidewire lumen 5034 of distal tip 5028. The distal tip 5028 has a rounded section 5036 between its distal portion 5032 and its proximal portion 5030. This helps prevent the sheath 5014 from slipping distally over the distal tip 5028, and thereby exposing the squared edges of the sheath 5014 to the vessel, which could cause damage thereto. This improves the device's "pushability." As the distal tip 5028 encounters resistance it does not allow the sheath 5014 to ride over it thereby exposing the sheath's 5014 square cut edge. Instead the sheath 5014 contacts the rounded section 5036 of the distal tip 5028 and thus transmits the forces applied to the distal tip 5028. The distal tip 5028 also has a proximally tapered section 5038

which helps guide the distal tip 5028 through the deployed stent 7000 without providing a sharp edge that could grab or hang up on a stent strut end or other irregularity in the lumen inner diameter.

5 Attached to distal portion 5026 of shaft 5012 is a stop 5040, which is proximal to the distal tip 5028 and stent 7000. Stop 5040 may be made from any number of suitable materials known in the art, including stainless steel, and is even more preferably made from a highly radio-opaque material such as platinum, gold tantalum, or radio-opaque filled polymer. The stop 5040 may be
10 attached to shaft 5012 by any suitable means, including mechanical or adhesive bonding, or by any other means known to those skilled in the art. Preferably, the diameter of stop 5040 is large enough to make sufficient contact with the loaded stent 7000 without making frictional contact with the sheath 5014. As will be explained subsequently, the stop 5040 helps to "push"
15 the stent 7000 or maintain its relative position during deployment, by preventing the stent 7000 from migrating proximally within the sheath 5014 during retraction of the sheath 5014 for stent deployment. The radio-opaque stop 5040 also aides in positioning the stent 7000 within the target lesion area during deployment within a vessel, as is described below.

20

A stent bed 5042 is defined as being that portion of the shaft 5012 between the distal tip 5028 and the stop 5040 (Figure 36). The stent bed 5042 and the stent 7000 are coaxial so that the distal portion 5026 of the shaft 5012 comprising the stent bed 5042 is located within the lumen of stent 7000. The
25 stent bed 5042 makes minimal contact with the stent 7000 because of the space which exists between the shaft 5012 and the sheath 5014. As the stent 7000 is subjected to temperatures at the austenite phase transformation it attempts to recover to its programmed shape by moving outwardly in a radial direction within the sheath 5014. The sheath 5014 constrains the stent 7000
30 as will be explained in detail subsequently. Distal to the distal end of the loaded stent 7000 attached to the shaft 5012 is a radio-opaque marker 5044 which may be made of platinum, iridium coated platinum, gold tantalum,

stainless steel, radio-opaque filled polymer or any other suitable material known in the art.

As seen from Figures 36, 37 and 44, the body portion 5022 of the shaft 5012 is made from a flexible coiled member 5024, similar to a closed coil or compressed spring. During deployment of the stent 7000, the transmission of compressive forces from the stop 5040 to the Luer guidewire hub 5020 is an important factor in deployment accuracy. A more compressive shaft 5012 results in a less accurate deployment because the compression of the shaft 5012 is not taken into account when visualizing the stent 7000 under fluoroscopic imaging. However, a less compressive shaft 5012 usually means less flexibility, which would reduce the ability of the apparatus 5010 to navigate through tortuous vessels. A coiled assembly allows both flexibility and resistance to compression. When the apparatus 5010 is being navigated through the arteries, the shaft 5012 is not in compression and therefore the coiled member 5024 is free to bend with the delivery path. As one deploys the stent 7000, tension is applied to the sheath 5014 as the sheath 5014 is retracted over the encapsulated stent 7000. Because the stent 7000 is self-expanding it is in contact with the sheath 5014 and the forces are transferred along the stent 7000 and to the stop 5040 of the shaft 5012. This results in the shaft 5012 being under compressive forces. When this happens, the flexible coiled member 5024, no gaps between the coil members, transfers the compressive force from one coil to the next.

The flexible coiled member 5024 further includes a covering 5046 that fits over the flexible coiled member 5024 to help resist buckling of the coiled member 5024 in both bending and compressive modes. The covering 5046 is an extruded polymer tube and is preferably a soft material that can elongate slightly to accommodate bending of the flexible coiled member 5024, but does not allow the coils to ride over each other. Covering 5046 may be made from any number of suitable materials including coextrusions of Nylon® and high-density polyethylene, polyurethane, polyamide, polytetrafluoroethylene, etc. The extrusion is also attached to the stop 5040. Flexible coiled member 5024

may be made of any number of materials known in the art including stainless steel, Nitinol, and rigid polymers. In one exemplary embodiment, flexible coiled member 5024 is made from a .003 inch thick by .010 inch wide stainless steel ribbon wire. The wire may be round, or more preferably flat to reduce the profile of the flexible coiled member 5024.

Sheath 5014 is preferably a polymeric catheter and has a proximal end 5048 terminating at a sheath hub 5050 (Figure 35). Sheath 5014 also has a distal end 5052 which terminates at the proximal end 5030 of distal tip 5028 of the shaft 5012, when the stent 7000 is in an un-deployed position as shown in Figure 36. The distal end 5052 of sheath 5014 includes a radio-opaque marker band 5054 disposed along its outer surface (Figure 35). As will be explained below, the stent 7000 is fully deployed when the marker band 5054 is proximal to radio-opaque stop 5040, thus indicating to the physician that it is now safe to remove the delivery apparatus 5010 from the body.

As detailed in Figure 36, the distal end 5052 of sheath 5014 includes an enlarged section 5056. Enlarged section 5056 has larger inside and outside diameters than the inside and outside diameters of the sheath 5014 proximal to enlarged section 5056. Enlarged section 5056 houses the pre-loaded stent 7000, the stop 5040 and the stent bed 5042. The outer sheath 5014 tapers proximally at the proximal end of enlarged section 5056 to a smaller size diameter. This design is more fully set forth in co-pending U.S. Application Serial No. 09/243,750 filed on February 3, 1999, which is hereby incorporated herein by reference. One particular advantage to the reduction in the size of the outer diameter of sheath 5014 proximal to enlarged section 5056 is in an increase in the clearance between the delivery apparatus 5010 and the guiding catheter or sheath that the delivery apparatus 5010 is placed through. Using fluoroscopy, the physician will view an image of the target site within the vessel, before and after deployment of the stent, by injecting a radio-opaque solution through the guiding catheter or sheath with the delivery apparatus 5010 placed within the guiding catheter. Because the clearance between the sheath 5014, and the guiding catheter is increased by tapering or reducing the

outer diameter of the sheath 5014 proximal to enlarged section 5056, higher injection rates may be achieved, resulting in better images of the target site for the physician. The tapering of sheath 5014 provides for higher injection rates of radio-opaque fluid, both before and after deployment of the stent.

5

A problem encountered with earlier self-expanding stent delivery systems is that of the stent becoming embedded within the sheath in which it is disposed. Referring to Figure 45, there is illustrated a sheath construction which may be effectively utilized to substantially prevent the stent from becoming embedded in the sheath as well as provide other benefits as described in detail below. As illustrated, the sheath 5014 comprises a composite structure of at least two layers and preferably three layers. The outer layer 5060 may be formed from any suitable biocompatible material. Preferably, the outer layer 5060 is formed from a lubricious material for ease of insertion and removal of the sheath 5014. In a preferred embodiment, the outer layer 5060 comprises a polymeric material such as Nylon®. The inner layer 5062 may also be formed from any suitable biocompatible material. For example, the inner layer 5062 may be formed from any number of polymers including polyethylene, polyamide or polytetrafluoroethylene. In a preferred embodiment, the inner layer 5062 comprises polytetrafluoroethylene. Polytetrafluoroethylene is also a lubricious material which makes stent delivery easier, thereby preventing damage to the stent 7000. The inner layer 5062 may also be coated with another material to increase the lubricity thereof for facilitating stent deployment. Any number of suitable biocompatible materials may be utilized. In an exemplary embodiment, silicone based coatings may be utilized. Essentially, a solution of the silicone based coating may be injected through the apparatus and allowed to cure at room temperature. The amount of silicone based coating utilized should be minimized to prevent transference of the coating to the stent 7000. Sandwiched between the outer and inner layers 5060 and 5062, respectively, is a wire reinforcement layer 5064. The wire reinforcement layer 5064 may take on any number of configurations. In the exemplary embodiment, the wire reinforcement layer 5064 comprises a simple under and over weave or braiding pattern. The wire used to form the

10

15

20

25

30

wire reinforcement layer 5064 may comprise any suitable material and any suitable cross-sectional shape. In the illustrated exemplary embodiment, the wire forming the wire reinforcement layer 5064 comprises stainless steel and has a substantially circular cross-section. In order to function for its intended purpose, as described in detail below, the wire has a diameter of 0.002 inches.

The three layers 5060, 5062, and 5064 comprising the sheath 5014 collectively enhance stent deployment. The outer layer 5060 facilitates insertion and removal of the entire apparatus 5010. The inner layer 5062 and the wire reinforcement layer 5064 function to prevent the stent 7000 from becoming embedded in the sheath 5014. Self-expanding stents such as the stent 7000 of the present invention tend to expand to their programmed diameter at a given temperature. As the stent attempts to undergo expansion, it exerts a radially outward directed force and may become embedded in the sheath 5014 restraining it from expanding. Accordingly, the wire reinforcing layer 5064 provides radial or hoop strength to the inner layer 5062 thereby creating sufficient resistance to the outwardly directed radial force of the stent 7000 within the sheath 5014. The inner layer 5062, also as discussed above, provides a lower coefficient of friction surface to reduce the forces required to deploy the stent 7000 (typically in the range from about five to eight pounds). The wire reinforcement layer 5064 also provides tensile strength to the sheath 5014. In other words, the wire reinforcement layer 5064 provides the sheath 5014 with better pushability, i.e., the ability to transmit a force applied by the physician at a proximal location on the sheath 5014 to the distal tip 5028, which aids in navigation across tight stenotic lesions within the vasculature. Wire reinforcement layer 5064 also provides the sheath 5014 with better resistance to elongation and necking as a result of tensile loading during sheath retraction for stent deployment.

The sheath 5014 may comprise all three layers along its entire length or only in certain sections, for example, along the length of the stent 7000. In a preferred embodiment, the sheath 5014 comprises all three layers along its entire length.

Prior art self-expanding stent delivery systems did not utilize wire reinforcement layers. Because the size of typical self-expanding stents is relatively large, as compared to balloon expandable coronary stents, the diameter or profile of the delivery devices therefor had to be large as well. However, it is always advantageous to have delivery systems which are as small as possible. This is desirable so that the devices can reach into smaller vessels and so that less trauma is caused to the patient. However, as stated above, the advantages of a thin reinforcing layer in a stent delivery apparatus outweighs the disadvantages of slightly increased profile.

In order to minimize the impact of the wire reinforcement layer on the profile of the apparatus 5010, the configuration of the wire reinforcement layer 5064 may be modified. For example, this may be accomplished in a number of ways, including changing the pitch of the braid, changing the shape of the wire, changing the wire diameter and/or changing the number of wires utilized. In a preferred embodiment, the wire utilized to form the wire reinforcement layer comprises a substantially rectangular cross-section as illustrated in Figure 46. In utilizing a substantially rectangular cross-section wire, the strength features of the reinforcement layer 5064 may be maintained with a significant reduction in the profile of the delivery apparatus. In this preferred embodiment, the rectangular cross-section wire has a width of 0.003 inches and a height of 0.001 inches. Accordingly, braiding the wire in a similar manner to Figure 45, results in a fifty percent decrease in the thickness of the wire reinforcement layer 5064 while maintaining the same beneficial characteristics as the 0.002 round wire. The flat wire may comprise any suitable material, and preferably comprises stainless steel.

In another alternate exemplary embodiment, the sheath of the delivery system may comprise an inner layer or coating on its inner surface which substantially prevents the stent from becoming embedded therein while increasing the lubricity thereof. This inner layer or coating may be utilized with the sheaths illustrated in Figures 45 and 46 or as an alternative means to

decrease the stent deployment forces. Given the thinness of the coating, as described in more detail below, the overall profile of the delivery system will be minimally impacted if at all. In addition to increasing the strength of the sheath and making it more lubricious, the coating is extremely biocompatible which is
5 important since it does make contact with blood, albeit at least temporarily.

Essentially, in the exemplary embodiment, a hard and lubricious coating is applied to or affixed to the inner surface of the sheath of the self-expanding delivery system. The coating provides a number of advantages over currently
10 utilized self-expanding stent delivery systems. For example, the coating provides a hard surface against which the stent exerts a radially outward directed force. As described above, self-expanding stents have a constant outward force of expansion when loaded into the delivery system. This constant and relatively high radially outward directed force can force the
15 polymeric materials that comprise the sheath of the delivery system to creep and allow the stent to become embedded into the polymer surface. As stent platforms are developed with larger diameter stents and subsequently higher radially outward directed forces, the occurrence of this phenomenon will increase. Consequently, embedding increases the force required to deploy the
20 stent because it causes mechanical resistance to the movement of the stent inside the delivery system, thereby preventing accurate deployment and causing potential damage to the stent. In addition, the coating is lubricious, i.e. it has a low coefficient of friction. A lubricious coating, as stated above, functions to further reduce the force required to deploy the stent, thereby
25 increasing the facility by which the stents are delivered and deployed by physicians. This is especially important with respect to newer larger diameter stent designs and/or drug/polymer coated stent designs that have either increased radial forces, increased profile or increased overall diameter. A lubricious coating is particularly advantageous with respect to drug/polymer
30 coated stents. Accordingly, the coating functions to prevent the stent from embedding in the sheath of the delivery system prior to deployment and reducing the friction between the sheath and the stent, both of which will reduce the deployment forces.

Various drugs, agents or compounds may be locally delivered via medical devices such as stents. For example, rapamycin and/or heparin may be delivered by a stent to reduce restenosis, inflammation and coagulation.

5 Various techniques for immobilizing the drugs, agents or compounds onto the stent are known; however, maintaining the drugs, agents or compounds on the stent during delivery and positioning is critical to the success of the procedure or treatment. For example, removal of the drug, agent or compound during delivery of the stent can potentially cause failure of the device. For a self-

10 expanding stent, the retraction of the restraining sheath may cause the drugs, agents or compounds to rub off the stent. Therefore, prevention of this potential problem is important to have successful therapeutic medical devices such as stents.

15 Figure 47 illustrates a partial cross-sectional view of the shaft and modified sheath of the stent delivery system in accordance with an exemplary embodiment of the present invention. As shown, a coating or layer of material 5070 is affixed or otherwise attached to the inner circumference of the sheath 5014. As stated above, the coating or layer of material 5070 comprises a hard

20 and lubricious substance. In a preferred embodiment, the coating 5070 comprises pyrolytic carbon. Pyrolytic carbon is a well-known substance that is utilized in a wide variety of implantable medical prostheses and is most commonly utilized in cardiac valves, as it combines high strength with excellent tissue and blood compatibility.

25

Pyrolytic carbon's usefulness in the implantable medical device area is a result of its unique combination of physical and chemical characteristics, including chemical inertness, isotrophy, low weight, compactness and elasticity. Pyrolytic carbon belongs to a specific family of turbostratic carbons which are

30 similar to the structure of graphite. In graphite, the carbon atoms are covalently bonded in planar hexagonal arrays that are stacked in layers with relatively weak interlayer bonding. In turbostratic carbons, the stacking sequence is disordered and distortions may exist within each of the layers.

These structural distortions in the layers are responsible for the superior ductility and durability of pyrolytic carbon. Essentially, the microstructure of pyrolytic carbon makes the material durable, strong and wear resistant. In addition, pyrolytic carbon is highly thromboresistant and has inherent cellular
5 biocompatibility with blood and soft tissue.

The pyrolytic carbon layer 5070 may be deposited along the entire length of the sheath 5014 or only in proximity to the stent bed 5042, illustrated in Figures 36 and 37. In a preferred embodiment, the pyrolytic carbon layer
10 5070 is affixed to the sheath 5014 in the region of the stent bed 5042. The pyrolytic carbon layer 5070 may be deposited or affixed to the inner circumference utilizing any number of known techniques that are compatible or usable with the polymeric materials comprising the sheath 5014. The thickness of the pyrolytic carbon layer 5070 is selected such that it prevents or
15 substantially reduces the possibility of the stent becoming embedded in the sheath 5014 without decreasing the flexibility of the sheath 5014 or increasing the profile of the self-expanding stent delivery system. As described above, it is important that the sheath be both flexible and pushable to navigate tortuous pathways within the body. In addition, it is always desirable to reduce the
20 profile of percutaneously delivered devices.

As stated above, pyrolytic carbon surfaces are recognized as biocompatible, especially with respect to blood contact applications. This is, however, only a minor benefit in terms of stent delivery applications because
25 the location of the pyrolytic carbon layer 5070 within the sheath 5014 is only minimally exposed to blood and is only within the body for a duration sufficient to deliver a stent.

The pyrolytic carbon layer 5070 may be affixed to the lumen of the
30 sheath in any number of ways as mentioned above. In one exemplary embodiment, the pyrolytic carbon layer 5070 may be directly affixed to the lumen of the sheath 5014. In another exemplary embodiment, the pyrolytic carbon layer 5070 may be indirectly applied to the lumen of the sheath 5014 by

first applying it to a variety of substrates, also utilizing any number of known techniques. Regardless of whether the pyrolytic carbon layer 5070 is deposited directly onto the sheath 5014 or first onto a substrate, any number of known techniques may be utilized, for example, chemical vapor deposition. In
5 chemical vapor deposition, the carbon material is deposited from gaseous hydrocarbon compounds on suitable underlying substrates, e.g. carbon materials, metals, ceramics as well as other materials, at temperatures ranging from about 1000K to about 2500K. At these temperatures, one can understand the need to possibly utilize substrates. Any suitable biocompatible,
10 durable and flexible substrate may be utilized and then affixed to the lumen of the sheath 5014 utilizing well-known techniques such as adhesives. As stated above, profile and flexibility are important design characteristics; accordingly, the type of substrate material chosen and/or its thickness should be considered. It is important to note that a wide range of microstructures, e.g.
15 isotropic, lamellar, substrate-nucleated and a varied content of remaining hydrogen can occur in pyrolytic carbons, depending on the deposition conditions, including temperature, type, concentration and flow rates of the source gas and surface area of the underlying substrate.

20 Other techniques which may be utilized to affix the pyrolytic carbon layer 5070 directly onto the sheath 5014 or onto a substrate include pulsed laser ablation deposition, radio frequency plasma modification, physical vapor deposition as well as other known techniques. In addition to pyrolytic carbon, other materials that might be beneficial in providing similar properties include
25 diamond-like carbon coatings, silane/silicon glass like surfaces and thin ceramic coatings such as alumina, hydroxyapatite and titania.

In an alternate exemplary embodiment, the pyrolytic carbon coating may be applied with a controlled finite porosity as briefly described above. This
30 controlled finite porosity provides two distinct advantages. First, the porosity may serve to reduce the contact surface area if the stent with the pyrolytic carbon coating 5070, thereby reducing the friction between the stent and the inner lumen of the sheath 5014. Second, lubricious materials such as

biocompatible oils, waxes and powders could be infused or impregnated within the porous surface of the coating thereby providing a reservoir of lubricious material further reducing the frictional coefficient.

5 Figures 35 and 36 show the stent 7000 as being in its fully un-deployed position. This is the position the stent is in when the apparatus 5010 is inserted into the vasculature and its distal end is navigated to a target site. Stent 7000 is disposed around the stent bed 5042 and at the distal end 5052 of sheath 5014. The distal tip 5028 of the shaft 5012 is distal to the distal end
10 5052 of the sheath 5014. The stent 7000 is in a compressed state and makes frictional contact with the inner surface of the sheath 5014.

When being inserted into a patient, sheath 5014 and shaft 5012 are locked together at their proximal ends by a Tuohy Borst valve 5058. This
15 prevents any sliding movement between the shaft 5012 and sheath 5014, which could result in a premature deployment or partial deployment of the stent 7000. When the stent 100 reaches its target site and is ready for deployment, the Tuohy Borst valve 5058 is opened so that the sheath 5014 and shaft 5012 are no longer locked together.

20 The method under which delivery apparatus 5010 deploys stent 7000 may best be described by referring to Figures 39-43. In Figure 39, the delivery apparatus 5010 has been inserted into a vessel 9000 so that the stent bed 5042 is at a target diseased site. Once the physician determines that the
25 radio-opaque marker band 5054 and stop 5040 on shaft 5012 indicating the ends of stent 7000 are sufficiently placed about the target disease site, the physician would open Tuohy Borst valve 5058. The physician would then grasp the Luer guidewire hub 5020 of shaft 5012 so as to hold shaft 5012 in a fixed position. Thereafter, the physician would grasp the Tuohy Borst valve
30 5058, attached proximally to sheath 5014, and slide it proximal, relative to the shaft 5012 as shown in Figures 40 and 41. Stop 5040 prevents the stent 7000 from sliding back with sheath 5014, so that as the sheath 5014 is moved back, the stent 7000 is effectively "pushed" out of the distal end 5052 of the sheath

5014, or held in position relative to the target site. Stent 7000 should be deployed in a distal to proximal direction to minimize the potential for creating emboli with the diseased vessel 9000. Stent deployment is complete when the radio-opaque band 5054 on the sheath 5014 is proximal to radio-opaque stop 5040, as shown in Figure 42. The apparatus 5010 can now be withdrawn through stent 7000 and removed from the patient.

Figures 36 and 43 show a preferred embodiment of a stent 7000, which may be used in conjunction with the present invention. Stent 7000 is shown in its unexpanded compressed state, before it is deployed, in Figure 36. Stent 7000 is preferably made from a superelastic alloy such as Nitinol. Most preferably, the stent 7000 is made from an alloy comprising from about 50.5 percent (as used herein these percentages refer to atomic percentages) Ni to about 60 percent Ni, and most preferably about 55 percent Ni, with the remainder of the alloy Ti. Preferably, the stent 7000 is such that it is superelastic at body temperature, and preferably has an Af in the range from about twenty-one degrees C to about thirty-seven degrees C. The superelastic design of the stent makes it crush recoverable which, as discussed above, can be used as a stent or frame for any number of vascular devices for different applications.

Stent 7000 is a tubular member having front and back open ends a longitudinal axis extending there between. The tubular member has a first smaller diameter, Figure 30, for insertion into a patient and navigation through the vessels, and a second larger diameter for deployment into the target area of a vessel. The tubular member is made from a plurality of adjacent hoops 7002 extending between the front and back ends. The hoops 7002 include a plurality of longitudinal struts 7004 and a plurality of loops 7006 connecting adjacent struts, wherein adjacent struts are connected at opposite ends so as to form a substantially S or Z shape pattern. Stent 7000 further includes a plurality of curved bridges 7008, which connect adjacent hoops 7002. Bridges 7008 connect adjacent struts together at bridge to loop connection points which are offset from the center of a loop.

The above described geometry helps to better distribute strain throughout the stent, prevents metal to metal contact when the stent is bent, and minimizes the opening size between the features, struts, loops and bridges. The number of and nature of the design of the struts, loops and bridges are important factors when determining the working properties and fatigue life properties of the stent. Preferably, each hoop has between twenty-four to thirty-six or more struts. Preferably the stent has a ratio of number of struts per hoop to strut length (in inches) which is greater than two hundred. The length of a strut is measured in its compressed state parallel to the longitudinal axis of the stent.

In trying to minimize the maximum strain experienced by features, the stent utilizes structural geometries which distribute strain to areas of the stent which are less susceptible to failure than others. For example, one vulnerable area of the stent is the inside radius of the connecting loops. The connecting loops undergo the most deformation of all the stent features. The inside radius of the loop would normally be the area with the highest level of strain on the stent. This area is also critical in that it is usually the smallest radius on the stent. Stress concentrations are generally controlled or minimized by maintaining the largest radii possible. Similarly, we want to minimize local strain concentrations on the bridge and bridge to loop connection points. One way to accomplish this is to utilize the largest possible radii while maintaining feature widths, which are consistent with applied forces. Another consideration is to minimize the maximum open area of the stent. Efficient utilization of the original tube from which the stent is cut increases stent strength and it's ability to trap embolic material.

As set forth above, stents coated with combinations of polymers and drugs, agents and/or compounds may potentially increase the forces acting on the stent during stent deployment. This increase in forces may in turn damage the stent. For example, as described above, during deployment, the stent is

forced against a stop to overcome the force of sliding the outer sheath back.
 With a longer stent, e.g. greater than
 200 mm, the forces exerted on the end of the stent during sheath retraction
 may be excessive and could potentially cause damage to the end of the stent
 5 or to other sections of the stent. Accordingly, a stent delivery device which
 distributes the forces over a greater area of the stent would be beneficial.

Figure 48 illustrates a modified shaft 5012 of the stent delivery section.
 In this exemplary embodiment, the shaft 5012 comprises a plurality of raised
 10 sections 5200. The raised sections 5200 may comprise any suitable size and
 geometry and may be formed in any suitable manner. The raised sections
 5200 may comprise any suitable material, including the material forming the
 shaft 5012. The number of raised sections 5200 may also be varied.
 Essentially, the raised sections 5200 may occupy the open spaces between
 15 the stent 7000 elements. All of the spaces may be filled or select spaces may
 be filled. In other words, the pattern and number of raised sections 5200 is
 preferably determined by the stent design. In the illustrated embodiment, the
 raised sections or protrusions 5200 are arranged such that they occupy the
 spaces formed between adjacent loops 7006 on adjacent hoops 7002 and
 20 between the bridges 7008.

The raised sections 5200 may be formed in any number of ways. For
 example, the raised sections 5200 may be formed using a heated clamshell
 mold or a waffle iron heated die approach. Either method allows for the low
 25 cost mass production of inner shafts comprising protrusions.

The size, shape and pattern of the raised sections 5200 may be
 modified to accommodate any stent design. The height of each of the raised
 sections 5200 is preferably large enough to compensate for the slight gap that
 30 exists between the inner shaft 5012 and the outer sheath 5014. The height, H ,
 of the raised sections or protrusions 5200 on the shaft 5012 should preferably
 be, at a minimum, greater than the difference in radius between the outside
 diameter of the shaft 5012, $IM(r)$,

and the inside diameter of the sheath 5014, OM(r), minus the wall thickness of the device or stent 7000, WT. The equation representing this relationship is given by

5
$$H > (OM(r) - IM(r)) - WT.$$

For example, if the shaft 5012 has an outside diameter of 0.08 inches, the sheath 5014 has an inside diameter of 0.1 inches, and the wall thickness of the stent 7000 is 0.008 inches, then the height of the raised sections or protrusions
10 5200 is

$$H > \left(\frac{0.100}{2} - \frac{0.080}{2} \right) - 0.008, \text{ or}$$

15
$$H > 0.002 \text{ inches.}$$

It is important to note that the height of the raised sections 5200 should preferably be less than the difference between the radius of the sheath and the radius of the shaft unless the protrusions 5200 are compressible.

20

Although each raised section 5200 is small, the number of raised sections 5200 may be large and each of the raised sections 5200 apply a small amount of force to different parts of the stent 7002, thereby distributing the force to deploy the stent 7000 and preventing damage to the stent 7000 particularly at its proximal end. The raised sections 5200 also protect the stent
25 7000 during loading of the stent 7000 into the delivery system. Essentially, the same forces that act on the stent 7000 during deployment act on the stent 7000 during loading. The longitudinal flexibility of the stent necessitates that as little force as possible is placed on the stent as it is released or deployed to
30 ensure repeatable foreshortening and accurate placement. Essentially, it is preferable that longitudinal movement of the stent 7000 be eliminated or substantially reduced during deployment thereby eliminating or substantially reducing compression of the stent. Without the raised sections 5200, as the stent 7000 is being deployed, the compressive forces will compress the

delivery system as well as the stent 7000. This compressive energy will be released upon deployment, reducing the chances of accurate placement of the stent 7000 and contributing to the possibility of stent "jumping." With the raised sections 5200, the stent 7000 is less likely to move, thereby eliminating or
5 substantially reducing compression.

In an alternate exemplary embodiment, once the stent is positioned on the shaft of the delivery device, the stent may be heated and externally pressurized to make a mirror-like imprint in the inner shaft of the delivery
10 system. The imprint provides a three-dimensional surface which allows the stent to maintain its position as the sheath is retracted. The three-dimensional imprint may be made using heat alone, pressure alone or with a separate device.

15 Any of the above-described medical devices may be utilized for the local delivery of drugs, agents and/or compounds to other areas, not immediately around the device itself. In order to avoid the potential complications associated with systemic drug delivery, the medical devices of the present invention may be utilized to deliver therapeutic agents to areas adjacent to the
20 medical device. For example, a rapamycin coated stent may deliver the rapamycin to the tissues surrounding the stent as well as areas upstream of the stent and downstream of the stent. The degree of tissue penetration depends on a number of factors, including the drug, agent or compound, the concentrations of the drug and the release rate of the agent. The same holds
25 true for coated anastomosis devices.

The drug, agent and/or compound/carrier or vehicle compositions described above may be formulated in a number of ways. For example, they may be formulated utilizing additional components or constituents, including a
30 variety of excipient agents and/or formulary components to affect manufacturability, coating integrity, sterilizability, drug stability, and drug release rate. Within exemplary embodiments of the present invention, excipient agents and/or formulary components may be added to achieve both

fast-release and sustained-release drug elution profiles. Such excipient agents may include salts and/or inorganic compounds such as acids/bases or buffer components, anti-oxidants, surfactants, polypeptides, proteins, carbohydrates including sucrose, glucose or dextrose, chelating agents such as EDTA, glutathione or other excipients or agents.

It is important to note that any of the above-described medical devices may be coated with coatings that comprise drugs, agents or compounds or simply with coatings that contain no drugs, agents or compounds. In addition, the entire medical device may be coated or only a portion of the device may be coated. The coating may be uniform or non-uniform. The coating may be discontinuous.

As described above, any number of drugs, agents and/or compounds may be locally delivered via any number of medical devices. For example, stents and anastomosis devices may incorporate coatings comprising drugs, agents and/or compounds to treat various disease states and reactions by the body as described in detail above. Other devices which may be coated with or otherwise incorporate therapeutic dosages of drugs, agents and/or compounds include stent-grafts, which are briefly described above, and devices utilizing stent-grafts, such as devices for treating abdominal aortic aneurysms as well as other aneurysms, e.g. thoracic aorta aneurysms.

Stent-grafts, as the name implies, comprise a stent and a graft material attached thereto. Figure 24 illustrates an exemplary stent-graft 800. The stent-graft 800 may comprise any type of stent and any type of graft material as described in detail subsequently. In the illustrated exemplary embodiment, the stent 802 is a self-expanding device. A typical self-expanding stent comprises an expandable lattice or network of interconnected struts. In preferred embodiments of the invention, the lattice is fabricated, e.g. laser cut, from an integral tube of material.

In accordance with the present invention, the stent may be variously configured. For example, the stent may be configured with struts or the like that form repeating geometric shapes. One skilled in the art will readily recognize that a stent may be configured or adapted to include certain features
5 and/or to perform a certain function(s), and that alternate designs may be used to promote that feature or function.

In the exemplary embodiment of the invention illustrated in Figure 24, the matrix or struts of stent 802 may be configured into at least two hoops 804,
10 each hoop 804 comprising a number of struts 806 formed into a diamond shape, having approximately nine diamonds. The stent 802 may further include a zigzag shaped ring 808 for connecting adjacent hoops to one another. The zigzag shaped rings 808 may be formed from a number of alternating struts 810, wherein each ring has fifty-four struts.

15

An inner or outer surface of the stent 802 may be covered by or support a graft material. Graft material 812 may be made from any number of materials known to those skilled in the art, including woven or other configurations of polyester, Dacron®, Teflon®, polyurethane porous
20 polyurethane, silicone, polyethylene, terephthalate, expanded polytetrafluoroethylene (ePTFE) and blends of various materials.

The graft material 812 may be variously configured, preferably to achieve predetermined mechanical properties. For example, the graft material
25 may incorporate a single or multiple weaving and/or pleating patterns, or may be pleated or unpleated. For example, the graft material may be configured into a plain weave, a satin weave, include longitudinal pleats, interrupted pleats, annular or helical pleats, radially oriented pleats, or combinations thereof. Alternately, the graft material may be knitted or braided. In the
30 embodiments of the invention in which the graft material is pleated, the pleats may be continuous or discontinuous. Also, the pleats may be oriented longitudinally, circumferentially, or combinations thereof.

As illustrated in Figure 24, the graft material 812 may include a plurality of longitudinal pleats 814 extending along its surface, generally parallel to the longitudinal axis of the stent-graft 800. The pleats 814 allow the stent-graft 800 to collapse around its center, much as it would be when it is delivered into a patient. This provides a relatively low profile delivery system, and provides for a controlled and consistent deployment therefrom. It is believed that this configuration minimizes wrinkling and other geometric irregularities. Upon subsequent expansion, the stent-graft 800 assumes its natural cylindrical shape, and the pleats 814 uniformly and symmetrically open.

In addition, the pleats 814 help facilitate stent-graft manufacture, in that they indicate the direction parallel to the longitudinal axis, allowing stent to graft attachment along these lines, and thereby inhibiting accidental twisting of the graft relative to the stent after attachment. The force required to push the stent-graft 800 out of the delivery system may also be reduced, in that only the pleated edges of the graft make frictional contact with the inner surface of the delivery system. One further advantage of the pleats 814 is that blood tends to coagulate generally uniformly in the troughs of the pleats 814, discouraging asymmetric or large clot formation on the graft surface, thereby reducing embolus risk.

As shown in Figure 24, the graft material 812 may also include one or more, and preferably a plurality of, radially oriented pleat interruptions 816. The pleat interruptions 816 are typically substantially circular and are oriented perpendicular to longitudinal axis. Pleat interruptions 816 allow the graft and stent to bend better at selective points. This design provides for a graft material that has good crimpability and improved kink resistance.

The foregoing graft materials may be braided, knitted or woven, and may be warp or weft knitted. If the material is warp knitted, it may be provided with a velour, or towel like surface; which is believed to speed the formation of blood clots, thereby promoting the integration of a stent-graft or stent-graft component into the surrounding cellular structure.

A graft material may be attached to a stent or to another graft material by any number of structures or methods known to those skilled in the art, including adhesives, such as polyurethane glue; a plurality of conventional
5 sutures of polyvinylidene fluoride, polypropylene, Dacron®, or any other suitable material; ultrasonic welding; mechanical interference fit; and staples.

The stent 802 and/or graft material 812 may be coated with any of the above-described drugs, agents and/or compounds. In one exemplary
10 embodiment, rapamycin may be affixed to at least a portion of the graft material 812 utilizing any of the materials and processes described above. In another exemplary embodiment, rapamycin may be affixed to at least a portion of the graft material 812 and heparin or other antithrombotics may be affixed to at least a portion of the stent 802. With this configuration, the rapamycin
15 coated graft material 812 may be utilized to minimize or substantially eliminate smooth muscle cell hyperproliferation and the heparin coated stent may substantially reduce the chance of thrombosis.

The particular polymer(s) utilized depends on the particular material
20 upon which it is affixed. In addition, the particular drug, agent and/or compound may also affect the selection of polymer(s). As set forth above, rapamycin may be affixed to at least a portion of the graft material 812 utilizing the polymer(s) and processes described above. In another alternate exemplary embodiment, the rapamycin or any other drug, agent and/or
25 compound may be directly impregnated into the graft material 812 utilizing any number of known techniques.

In yet another alternate exemplary embodiment, the stent-graft may be formed from two stents with the graft material sandwiched therebetween.
30 Figure 25 is a simple illustration of a stent-graft 900 formed from an inner stent 902, an outer stent 904 and graft material 906 sandwiched therebetween. The stents 902, 904 and graft material 906 may be formed from the same materials as described above. As before, the inner stent 902 may be coated with an

antithrombotic or anticoagulant such as heparin while the outer stent 904 may be coated with an antiproliferative such as rapamycin. Alternately, the graft material 906 may be coated with any of the above described drugs, agents and/or compounds, as well as combinations thereof, or all three elements may be coated with the same or different drugs, agents and/or compounds.

In yet another alternate exemplary embodiment, the stent-graft design may be modified to include a graft cuff. As illustrated in Figure 26, the graft material 906 may be folded around the outer stent 904 to form cuffs 908. In this exemplary embodiment, the cuffs 908 may be loaded with various drugs, agents and/or compounds, including rapamycin and heparin. The drugs, agents and/or compounds may be affixed to the cuffs 908 utilizing the methods and materials described above or through other means. For example, the drugs, agents and/or compounds may be trapped in the cuffs 908 with the graft material 906 acting as the diffusion barrier through which the drug, agent and/or compound elutes. The particular material selected as well as its physical characteristics would determine the elution rate. Alternately, the graft material 906 forming the cuffs 908 may be coated with one or more polymers to control the elution rate as described above.

20

Stent-grafts may be utilized to treat aneurysms. An aneurysm is an abnormal dilation of a layer or layers of an arterial wall, usually caused by a systemic collagen synthetic or structural defect. An abdominal aortic aneurysm is an aneurysm in the abdominal portion of the aorta, usually located in or near one or both of the two iliac arteries or near the renal arteries. The aneurysm often arises in the infrarenal portion of the diseased aorta, for example, below the kidneys. A thoracic aortic aneurysm is an aneurysm in the thoracic portion of the aorta. When left untreated, the aneurysm may rupture, usually causing rapid fatal hemorrhaging.

30

Aneurysms may be classified or typed by their position as well as by the number of aneurysms in a cluster. Typically, abdominal aortic aneurysms may be classified into five types. A Type I aneurysm is a single dilation located

between the renal arteries and the iliac arteries. Typically, in a Type 1 aneurysm, the aorta is healthy between the renal arteries and the aneurysm and between the aneurysm and the iliac arteries.

5 A Type II A aneurysm is a single dilation located between the renal arteries and the iliac arteries. In a Type II A aneurysm, the aorta is healthy between the renal arteries and the aneurysm, but not healthy between the aneurysm and the iliac arteries. In other words, the dilation extends to the aortic bifurcation. A Type II B aneurysm comprises three dilations. One
10 dilation is located between the renal arteries and the iliac arteries. Like a Type II A aneurysm, the aorta is healthy between the aneurysm and the renal arteries, but not healthy between the aneurysm and the iliac arteries. The other two dilations are located in the iliac arteries between the aortic bifurcation and the bifurcations between the external iliacs and the internal iliacs. The iliac
15 arteries are healthy between the iliac bifurcation and the aneurysms. A Type II C aneurysm also comprises three dilations. However, in a Type II C aneurysm, the dilations in the iliac arteries extend to the iliac bifurcation.

 A Type III aneurysm is a single dilation located between the renal
20 arteries and the iliac arteries. In a Type III aneurysm, the aorta is not healthy between the renal arteries and the aneurysm. In other words, the dilation extends to the renal arteries.

 A ruptured abdominal aortic aneurysm is presently the thirteenth leading
25 cause of death in the United States. The routine management of abdominal aortic aneurysms has been surgical bypass, with the placement of a graft in the involved or dilated segment. Although resection with a synthetic graft via transperitoneal or retroperitoneal approach has been the standard treatment, it is associated with significant risk. For example, complications include
30 perioperative myocardial ischemia, renal failure, erectile impotence, intestinal ischemia, infection, lower limb ischemia, spinal cord injury with paralysis, aorta-enteric fistula, and death. Surgical treatment of abdominal aortic aneurysms is associated with an overall mortality rate of five percent in asymptomatic

patients, sixteen to nineteen percent in symptomatic patients, and is as high as fifty percent in patients with ruptured abdominal aortic aneurysms.

Disadvantages associated with conventional surgery, in addition to the
5 high mortality rate, include an extended recovery period associated with the
large surgical incision and the opening of the abdominal cavity, difficulties in
suturing the graft to the aorta, the loss of the existing thrombosis to support
and reinforce the graft, the unsuitability of the surgery for many patients having
abdominal aortic aneurysms, and the problems associated with performing the
10 surgery on an emergency basis after the aneurysm has ruptured. Further, the
typical recovery period is from one to two weeks in the hospital, and a
convalescence period at home from two to three months or more, if
complications ensue. Since many patients having abdominal aortic aneurysms
have other chronic illnesses, such as heart, lung, liver and/or kidney disease,
15 coupled with the fact that many of these patients are older, they are less than
ideal candidates for surgery.

The occurrence of aneurysms is not confined to the abdominal region.
While abdominal aortic aneurysms are generally the most common, aneurysms
20 in other regions of the aorta or one of its branches are possible. For example,
aneurysms may occur in the thoracic aorta. As is the case with abdominal
aortic aneurysms, the widely accepted approach to treating an aneurysm in the
thoracic aorta is surgical repair, involving replacing the aneurysmal segment
with a prosthetic device. This surgery, as described above, is a major
25 undertaking, with associated high risks and with significant mortality and
morbidity.

Over the past five years, there has been a great deal of research
directed at developing less invasive, percutaneous, e.g., catheter directed,
30 techniques for the treatment of aneurysms, specifically abdominal aortic
aneurysms. This has been facilitated by the development of vascular stents,
which can and have been used in conjunction with standard or thin-wall graft
material in order to create a stent-graft or endograft. The potential advantages

of less invasive treatments have included reduced surgical morbidity and mortality along with shorter hospital and intensive care unit stays.

Stent-grafts or endoprotheses are now FDA approved and commercially available. The delivery procedure typically involves advanced angiographic techniques performed through vascular accesses gained via surgical cutdown of a remote artery, such as the common femoral or brachial arteries. Over a guidewire, the appropriate size introducer will be placed. The catheter and guidewire are passed through the aneurysm, and, with the appropriate size introducer housing a stent-graft, the stent-graft will be advanced along the guidewire to the appropriate position. Typical deployment of the stent-graft device requires withdrawal of an outer sheath while maintaining the position of the stent-graft with an inner-stabilizing device. Most stent-grafts are self-expanding; however, an additional angioplasty procedure, e.g., balloon angioplasty, may be required to secure the position of the stent-graft. Following the placement of the stent-graft, standard angiographic views may be obtained.

Due to the large diameter of the above-described devices, typically greater than twenty French ($3F = 1mm$), arteriotomy closure requires surgical repair. Some procedures may require additional surgical techniques, such as hypogastric artery embolization, vessel ligation, or surgical bypass, in order to adequately treat the aneurysm or to maintain flow to both lower extremities. Likewise, some procedures will require additional, advanced catheter directed techniques, such as angioplasty, stent placement, and embolization, in order to successfully exclude the aneurysm and efficiently manage leaks.

While the above-described endoprotheses represent a significant improvement over conventional surgical techniques, there is a need to improve the endoprotheses, their method of use and their applicability to varied biological conditions. Accordingly, in order to provide a safe and effective alternate means for treating aneurysms, including abdominal aortic aneurysms and thoracic aortic aneurysms, a number of difficulties associated with

currently known endoprostheses and their delivery systems must be overcome. One concern with the use of endoprostheses is the prevention of endo-leaks and the disruption of the normal fluid dynamics of the vasculature. Devices using any technology should preferably be simple to position and reposition as necessary, should preferably provide an acute fluid tight seal, and should preferably be anchored to prevent migration without interfering with normal blood flow in both the aneurysmal vessel as well as branching vessels. In addition, devices using the technology should preferably be able to be anchored, sealed, and maintained in bifurcated vessels, tortuous vessels, highly angulated vessels, partially diseased vessels, calcified vessels, odd shaped vessels, short vessels, and long vessels. In order to accomplish this, the endoprostheses should preferably be extendable and re-configurable while maintaining acute and long term fluid tight seals and anchoring positions.

The endoprostheses should also preferably be able to be delivered percutaneously utilizing catheters, guidewires and other devices which substantially eliminate the need for open surgical intervention. Accordingly, the diameter of the endoprostheses in the catheter is an important factor. This is especially true for aneurysms in the larger vessels, such as the thoracic aorta.

As stated above, one or more stent-grafts may be utilized to treat aneurysms. These stent-grafts or endoprostheses may comprise any number of materials and configurations. Figure 27 illustrates an exemplary system for treating abdominal aortic aneurysms. The system 1000 includes a first prosthesis 1002 and two second prostheses 1004 and 1006, which in combination, bypass an aneurysm 1008. In the illustrated exemplary embodiment, a proximal portion of the system 1000 may be positioned in a section 1010 of an artery upstream of the aneurysm 1008, and a distal portion of the system 1000 may be positioned in a downstream section of the artery or a different artery such as iliacs 1012 and 1014.

A prosthesis used in a system in accordance with the present invention typically includes a support, stent or lattice of interconnected struts defining an

interior space or lumen having an open proximal end and an open distal end. The lattice also defines an interior surface and an exterior surface. The interior and/or exterior surfaces of the lattice, or a portion of the lattice, may be covered by or support at least one gasket material or graft material.

5

In preferred embodiments of the invention, a prosthesis is moveable between an expanded or inflated position and an unexpanded or deflated position, and any position therebetween. In some exemplary embodiments of the invention, it may be desirable to provide a prosthesis that moves only from
10 fully collapsed to fully expanded. In other exemplary embodiments of the invention, it may be desirable to expand the prosthesis, then collapse or partially collapse the prosthesis. Such capability is beneficial to the surgeon to properly position or re-position the prosthesis. In accordance with the present invention, the prosthesis may be self-expanding, or may be expandable using
15 an inflatable device, such as a balloon or the like.

Referring back to Figure 27, the system 1000 is deployed in the infrarenal neck 1010 of the abdominal aorta, upstream of where the artery splits into first and second common iliac arteries 1012, 1014. Figure 27 shows
20 the first prosthesis or stent gasket 1002 positioned in the infrarenal neck 1010; two second prostheses, 1004, 1006, the proximal ends of which matingly engage a proximal portion of stent gasket 1002, and the distal ends of which extend into a common iliac artery 1012 or 1014. As illustrated, the body of each second prosthesis forms a conduit or fluid flow path that passes through
25 the location of the aneurysm 1008. In preferred embodiments of the invention, the components of the system 1000 define a fluid flow path that bypasses the section of the artery where the aneurysm is located.

The first prosthesis includes a support matrix or stent that supports a
30 sealing material or foam, at least a portion of which is positioned across a biological fluid flow path, e.g., across a blood flow path. In preferred embodiments of the invention, the first prosthesis, the stent, and the sealing material are radially expandable, and define a hollow space between a

proximal portion of the prosthesis and a distal portion of the prosthesis. The first prosthesis may also include one or more structures for positioning and anchoring the prosthesis in the artery, and one or more structures for engaging and fixing at least one second prosthesis in place, e.g., a bypass prosthesis.

5

The support matrix or stent of the first prosthesis may be formed of a wide variety of materials, may be configured in a wide variety of shapes, and their shapes and uses are well known in the art. Exemplary prior art stents are disclosed in U.S. Patents 4,733,665 (Palmaz); U.S. Patent 4,739,762 (Palmaz);
10 and U.S. Patent 4,776,337 (Palmaz).

In preferred embodiments of the invention, the stent of the first prosthesis is a collapsible, flexible, and self-expanding lattice or matrix formed from a metal or metal alloy, such as nitinol or stainless steel. Structures
15 formed from stainless steel may be made self-expanding by configuring the stainless steel in a predetermined manner, for example, by twisting it into a braided configuration. More preferably, the stent is a tubular frame that supports a sealing material. The term tubular, as used herein, refers to any shape having a sidewall or sidewalls defining a hollow space or lumen
20 extending therebetween; the cross-sectional shape may be generally cylindrical, elliptic, oval, rectangular, triangular, or any other shape. Furthermore, the shape may change or be deformable as a consequence of various forces that may press against the stent or prosthesis.

25 The sealing material or gasket member supported by the stent may be formed of a wide variety of materials, may be configured in a wide variety of shapes, and their shapes and uses are well known in the art. Exemplary materials for use with this aspect of the invention are disclosed in U.S. Patent 4,739,762 (Palmaz) and U.S. Patent 4,776,337 (Palmaz).

The sealing material or gasket member may comprise any suitable material. Exemplary materials preferably comprise a biodurable and biocompatible material, including but are not limited to, open cell foam materials and closed cell foam materials. Exemplary materials include
5 polyurethane, polyethylene, polytetrafluoroethylene; and other various polymer materials, preferably woven or knitted, that provide a flexible structure, such as Dacron®. Highly compressible foams are particularly preferred, preferably to keep the crimped profile low for better delivery. The sealing material or foam is preferably substantially impervious to blood when in a compressed state.

10

The sealing material may cover one or more surfaces of the stent i.e., may be located along an interior or exterior wall, or both, and preferably extends across the proximal end or a proximal portion of the stent. The sealing material helps impede any blood trying to flow around the first prosthesis, e.g.,
15 between the first prosthesis and the arterial wall, and around one or more bypass prostheses after they have been deployed within the lumen of the first prosthesis (described in more detail below).

In preferred embodiments of the invention, the sealing material
20 stretches or covers a portion of the proximal end of the stent and along at least a portion of the outside wall of the stent.

In some embodiments of the invention, it may be desirable for the portion of the sealing material covering the proximal portion of the stent to
25 include one or more holes, apertures, points, slits, sleeves, flaps, weakened spots, guides, or the like for positioning a guidewire, for positioning a system component, such as a second prosthesis, and/or for engaging, preferably matingly engaging, one or more system components, such as a second prosthesis. For example, a sealing material configured as a cover or the like,
30 and having a hole, may partially occlude the stent lumen.

These openings may be variously configured, primarily to conform to its use. These structures promote proper side by side placement of one or more,

preferably multiple, prostheses within the first prosthesis, and, in some embodiments of the invention, the sealing material may be configured or adapted to assist in maintaining a certain shape of the fully deployed system or component. Further, these openings may exist prior to deployment of the prosthesis, or may be formed in the prosthesis as part of a deployment procedure. The various functions of the openings will be evident from the description below. In exemplary embodiments of the invention, the sealing material is a foam cover that has a single hole.

10 The sealing material may be attached to the stent by any of a variety of connectors, including a plurality of conventional sutures of polyvinylidene fluoride, polypropylene, Dacron®, or any other suitable material and attached thereto. Other methods of attaching the sealing material to the stent include adhesives, ultrasonic welding, mechanical interference fit and staples.

15 One or more markers may be optionally disposed in or on the stent between the proximal end and the distal end. Preferably, two or more markers are sized and/or positioned to identify a location on the prosthesis, or to identify the position of the prosthesis, or a portion thereof, in relation to an anatomical feature or another system component.

20 First prosthesis is typically deployed in an arterial passageway upstream of an aneurysm, and functions to open and/or expand the artery, to properly position and anchor the various components of the system, and, in combination with other components, seal the system or portions thereof from fluid leaks. For example, the sealing prosthesis may be deployed within the infrarenal neck, between an abdominal aortic aneurysm and the renal arteries of a patient, to assist in repairing an abdominal aortic aneurysm.

30 Figures 27-29 show an exemplary sealing prosthesis of the present invention. Sealing prosthesis 1002 includes a cylindrical or oval self-expanding lattice, support, or stent 1016, typically made from a plurality of interconnected struts 1018. Stent 1016 defines an interior space or lumen 1020 having two

open ends, a proximal end 1022 and a distal end 1024. One or more markers 1026 may be optionally disposed in or on the stent between the proximal end 1022 and the distal end 1024.

5 Stent 1016 may further include at least two but preferably eight (as shown in Figure 28) spaced apart longitudinal legs 1028. Preferably, there is a leg extending from each apex 1030 of diamonds formed by struts 1018. At least one leg, but preferably each leg, includes a flange 1032 adjacent its distal end which allows for the stent 1016 to be retrievable into its delivery apparatus
10 after partial or nearly full deployment thereof so that it can be turned, or otherwise repositioned for proper alignment.

Figure 29 shows the sealing material 1034 covering the proximal end 1022 of stent gasket 1002. In the exemplary embodiment shown in Figure 29;
15 sealing prosthesis 1002 includes a sealing material 1034 having a first opening or hole 1036 and a second opening or slit 1038. The gasket material covers at least a portion of the interior or exterior of the stent, and most preferably covers substantially all of the exterior of the stent. For example, gasket material 1034 may be configured to cover stent 1016 from the proximal end 1022 to the distal
20 end 1024, but preferably not covering longitudinal legs 1028.

The sealing material 1034 helps impede any blood trying to flow around bypass prostheses 1004 and 1006 after they have been deployed (as shown in Figure 27) and from flowing around the stent gasket 1002 itself. For this
25 embodiment, sealing material 1034 is a compressible member or gasket located along the exterior of the stent 1016 and at least a portion of the interior of the stent 1016.

The second prostheses 1004 and 1006 may comprise stent-grafts such
30 as described with respect to Figure 24 and may be coated with any of the drugs, agents and/or compounds as described above. In other words, the stent and/or the graft material may be coated with any of the above-described drugs, agents and/or compounds utilizing any of the above-described polymers

and processes. The stent gasket 1002 may also be coated with any of the above-described drugs, agents and/or compounds. In other words, the stent and/or sealing material may be coated with any of the above-described drugs, agents and/or compounds utilizing any of the above-described polymers and processes. In particular, rapamycin and heparin may be of importance to prevent smooth muscle cell hyperproliferation and thrombosis. Other drugs, agents and/or compounds may be utilized as well. For example drugs, agents and/or compounds which promote re-endothelialization may be utilized to facilitate incorporation of the prosthesis into the living organism. Also, embolic material may be incorporated into the stent-graft to reduce the likelihood of endo leaks.

It is important to note that the above-described system for repairing abdominal aortic aneurysms is one example of such a system. Any number of aneurysmal repair systems comprising stent-grafts may be coated with the appropriate drugs, agents and/or compounds as well as combinations thereof. For example, thoracic aorta aneurysms may be repaired in a similar manner. Regardless of the type of aneurysm or its position within the living organism, the components comprising the repair system may be coated with the appropriate drug, agent and/or compound as described above with respect to stent-grafts.

A difficulty associated with the treatment of aneurysms, specifically abdominal aortic aneurysms, is endoleaks. An endoleak is generally defined as the persistence of blood flow outside of the lumen of the stent-graft, but within the aneurysmal sac or adjacent vascular segment being treated with the stent-graft. Essentially, endoleaks are caused by one of two primary mechanisms, wherein each mechanism has a number of possible modalities. The first mechanism involves the incomplete sealing or exclusion of the aneurysmal sac or vessel segment. The second mechanism involves retrograde flow. In this type of endoleak, blood-flow into the aneurysmal sac is reversed due to retrograde flow from patent collateral vessels, particularly the lumbar arteries or the inferior mesenteric artery. This type of endoleak may

occur even when a complete seal has been achieved around the stent-grafts. It is also possible that an endoleak may develop due to stent-graft failure, for example, a tear in the graft fabric.

5 Endoleaks may be classified by type. A type I endoleak is a perigraft leak at the proximal or distal attachment sites of the stent-grafts. Essentially, this type of endoleak occurs when a persistent perigraft channel of blood flow develops due to an ineffective or inadequate seal at the ends of the stent-graft. There are a number of possible causes of a type I endoleak, including
10 improper sizing of the stent-graft, migration of the stent-graft, incomplete stent-graft expansion and an irregular shape of the arterial lumen. A type II endoleak is persistent collateral blood flow into the aneurysmal sac from a patent branch of the aorta. Essentially, the pressure in the aneurysmal sac is lower than the collateral branches, thereby causing a retrograde blood flow.
15 Sources of type II endoleaks include the accessory renal arteries, the testicular arteries, the lumbar arteries, the middle sacral artery, the inferior mesenteric artery and the spinal artery. A type III endoleak may be caused by a structural failure of the abdominal aortic aneurysm repair system or its components, for example, the stent-grafts. A type III endoleak may also be caused by a
20 junction failure in systems employing modular components. Sources of type III endoleaks include tears, rips or holes in the fabric of the stent-graft, improper sizing of the modular components and limited overlap of the modular components. A type IV endoleak is blood flow through the graft material itself. The blood flow through the pores of the graft material or through small holes in
25 the fabric caused by the staples or sutures attaching the graft material to the stent. Blood flow through the pores typically occurs with highly porous graft fabrics. A type V endoleak or endotension is a persistent or recurrent pressurization of the aneurysmal sac without any radiologically detectable endoleak. Possible causes of a type V endoleak include pressure transmission
30 by thrombus, highly porous graft material, or the adjacent aortic lumen.

There are a number of possible treatment options for each type of endoleak described above. The particular treatment option depends mainly

upon the cause of endoleak and the options are not always successful. The present invention is directed to a modification of existing endovascular abdominal aortic aneurysm repair systems or devices, such as the exemplary devices described herein, that is intended to eliminate or substantially reduce the incidence of endoleaks.

The modification comprises coating at least a portion of the various components comprising an abdominal aortic aneurysm repair system with drugs, agents and/or compounds which promote wound healing as described below. For example, portions of the exemplary system 1000, illustrated in Figure 27, may be coated with one or more drugs, agents and/or compounds that induce or promote the wound healing process, thereby reducing or substantially reducing the risk of endoleaks. It may be particularly advantageous to coat the ends of the two second prostheses 1004 and 1006 and the entire first prosthesis 1002, as these are the most likely regions for endoleaks. However, coating the entire stent-graft, i.e. graft material and stent, may prove beneficial depending upon the type of endoleak. Since it is not always possible to stop endoleaks utilizing currently available methods, the use of wound healing agents, delivered locally, in accordance with the present invention may serve to effectively stop or prevent acute and chronic endoleaks. It is important to note that the present invention may be utilized in combination with any abdominal aortic aneurysm repair system, or with any other type of graft component where leakage is a potential problem. The present invention may be utilized in conjunction with type I, III, IV and V endoleaks.

25

Normal wound healing essentially occurs in three stages or phases, which have a certain degree of overlap. The first phase is cellular migration and inflammation. This phase lasts for several days. The second phase is the proliferation of fibroblasts for two to four weeks with new collagen synthesis. The third phase is remodeling of the scar and typically lasts from one month to a year. This third phase includes collagen cross linking and active collagen turnover.

30

As stated above, there are certain drugs, agents and/or compounds that may be delivered locally to the repair site, via the repair system, that promotes wound healing which in turn may eliminate or substantially reduce the incidence of endoleaks. For example, increased collagen production early in wound healing leads to greater wound strength. Accordingly, collagen may be combined with the repair system to increase wound strength and promote platelet aggregation and fibrin formation. In addition, certain growth factors may be combined with the repair system to promote platelet aggregation and fibrin formation as well as to increase wound strength.

Platelet-derived Growth Factor induces mitoses and is the major mitogen in serum for growth in connective tissue. Platelet Factor 4 is a platelet released protein that promotes blood clotting by neutralizing heparin. Platelet-derived Growth Factor and Platelet Factor 4 are important in inflammation and repair. They are active for human monocytes, neutrophils, smooth muscle cells, fibroblasts and inflammation cells. Transforming Growth Factor- β is a part of a complex family of polypeptide hormones or biological factors that are produced by the body to control growth, division and maturation of blood cells by the bone marrow. Transforming Growth Factor- β is found in tissues and platelets, and is known to stimulate total protein, collagen and DNA content in wound chambers implanted *in vivo*. Transforming Growth Factor- β in combination with collagen has been shown to be extremely effective in wound healing.

A series of reactions take place in the body whenever a blood clot begins to form. A major initiator of these reactions is an enzyme system called the Tissue Factor/VIIa complex. Accordingly, Tissue Factor/VIIa may be utilized to promote blood clot formation and thus enhance wound healing. Other agents which are known to initiate thrombus formation include thrombin, fibrin, plasminogen-activator initiator, adenosine diphosphate and collagen.

The use of these drugs, agents and/or compounds in conjunction with the various components of the repair system may be used to eliminate or

substantially reduce the incidence of endoleaks through the formation of blood clots and wound healing.

5 The stent and/or graft material comprising the components of the system 1000 may be coated with any of the above-described drugs, agents and/or compounds. The above-described drugs, agents and/or compounds may be affixed to a portion of the components or to all of the components utilizing any of the materials and processes described above. For example, the drugs, agents and/or compounds may be incorporated into a polymeric matrix
10 or affixed directly to various portions of the components of the system.

The particular polymer(s) utilized depends on the particular material upon which it is affixed. In addition, the particular drug, agent and/or compound may also affect the selection of polymer(s).

15

As described above, other implantable medical devices that may be coated with various drugs, agents and/or compounds include surgical staples and sutures. These medical devices may be coated with any of the above-described drugs, agents and/or compounds to treat various conditions and/or
20 to minimize or substantially eliminate the organisms' reaction to the implantation of the device.

Figure 30 illustrates an uncoated or bare surgical staple 3000. The staple 3000 may be formed from any suitable biocompatible material having
25 the requisite strength requirements for a given application. Generally, surgical staples comprise stainless steel. Figure 31 illustrates an exemplary embodiment of a surgical staple 3000 comprising a multiplicity of through-holes 3002, which preferably contain one or more drugs, agents and/or compounds as described above. The one or more drugs, agents and/or compounds may
30 be injected into the through-holes 3002 with or without a polymeric mixture. For example, in one exemplary embodiment, the through-holes 3002 may be sized such that the one or more drugs, agents and/or compounds may be injected directly therein and elute at a specific rate based upon the size of the

through-holes 3002. In another exemplary embodiment, the one or more drugs, agents and/or compounds may be mixed with the appropriate polymer, which controls the elution rate, and injected into or loaded into the through-holes 3002. In yet another alternate exemplary embodiment, the one or more drugs, agents and/or compounds may be injected into or loaded into the
5 through-holes 3002 and then covered with a polymer to control the elution rate.

Figure 32 illustrates an exemplary embodiment of a surgical staple 3000 comprising a coating 3006 covering substantially the entire surface thereof. In
10 this embodiment, the one or more drugs, agents and/or compounds may be directly affixed to the staple 3000 utilizing any number of known techniques including spraying or dipping, or the one or more drugs, agents and/or compounds may be mixed with or incorporated into a polymeric matrix and then affixed to the staple 3000. Alternately, the one or more drugs, agents
15 and/or compounds may be directly affixed to the surface of the staple 3000 and then a diffusion barrier may be applied over the layer of one or more drugs, agents and/or compounds.

Although any number of drugs, agents and/or compounds may be used in conjunction with the surgical staple 3000 to treat a variety of conditions
20 and/or to minimize or substantially eliminate the organisms' reaction to the implantation of the staple 3000, in a preferred embodiment, the surgical staple 3000 is coated with an anti-proliferative. The advantage of such a device is that the anti-proliferative coating would function as a prophylactic defense against neo-intimal hyperplasia. As described above, neo-intimal hyperplasia
25 often happens at the site of what the body perceives to be injuries, for example, anastomatic sites, either tissue to tissue or tissue to implant, which are often sites of hyperplastic events. By utilizing a staple that comprises an anti-proliferative agent, the incidence of neo-intimal hyperplasia may be substantially reduced or eliminated.

30

Rapamycin is a known anti-proliferative that may be utilized on or in the surgical staple 3000 and may be incorporated into any of the above-described polymeric materials. An additional benefit of utilizing rapamycin is its action as

an anti-inflammatory. The dual action not only functions to reduce neo-intimal hyperplasia but inflammation as well.

5 In yet another alternate exemplary embodiment, the surgical staple 3000 may be fabricated from a material, such as a polymeric material, which incorporates the one or more drugs, agents, and/or compounds. Regardless of the particular embodiment, the elution rate of the one or more drugs, agents and/or compounds may be controlled as described above.

10 Referring now to Figure 33, there is illustrated a section of suture material 4000. The suture 4000 may comprise any suitable material commonly utilized in the fabrication of both absorbable or non-absorbable sutures. As illustrated, the suture 4000 comprises a coating 4002 of one or more drugs, agents and/or compounds. As in the coating on the surgical staple 3000, the
15 one or more drugs, agents and/or compounds may be applied directly to the suture 4000 or it may be mixed or incorporated into a polymeric matrix and then affixed to the suture 4000. Also as described above, the one or more drugs, agents and/or compounds may be affixed to the suture 4000 and then a diffusion barrier or top coating may be affixed to the one or more drugs, agents
20 and/or compounds to control the elution or release rate.

Figure 34 illustrates a section of suture material 4000 impregnated with one or more drugs, agents and/or compounds 4004. The one or more drugs, agents, and/or compounds may be directly impregnated into the suture
25 material 4000, incorporated into a polymeric matrix and then impregnated into the suture material 4000. Alternately, the one or more drugs, agents and/or compounds may be impregnated into the suture material 4000 and then covered with a polymeric material.

30 In yet another alternate exemplary embodiment, the suture 4000 may be formed from a material, for example, a polymeric material that incorporates the one or more drugs, agents and/or compounds. For example, the one or more

drugs, agents, and/or compounds may be mixed within the polymer matrix and then extruded and/or formed by a dip method to form the suture material.

5 The particular polymer(s) utilized depend on the particular material upon which it is affixed. In addition, the particular drug, agent, and/or compound may also affect the selection of polymers. Rapamycin may be utilized with poly(vinylidene fluoride)/hexafluoropropylene.

10 Although shown and described is what is believed to be the most practical and preferred embodiments, it is apparent that departures from specific designs and methods described and shown will suggest themselves to those skilled in the art and may be used without departing from the spirit and scope of the invention. The present invention is not restricted to the particular constructions described and illustrated, but should be constructed to cohere
15 with all modifications that may fall within the scope of the appended claims.

WHAT IS CLAIMED IS:

1. A delivery system for a self-expanding stent, the delivery system comprising:

a self-expanding stent;

a substantially tubular shaft having a proximal end, a distal end, a guidewire lumen extending between the proximal and distal ends, and a stent bed region proximate the distal end upon which the self-expanding stent is positioned, the stent bed region including a textured surface for preventing longitudinal movement of the stent along the shaft; and

a substantially tubular sheath defining an interior volume and coaxially positioned over the tubular shaft and the stent;

wherein the textured surface comprises a plurality of raised elements protruding from the substantially tubular shaft,

wherein the plurality of raised elements are arranged in a pattern such that they correspond to, and fill, the gaps between some but not every one of the elements comprising the self-expanding stent and wherein the plurality of raised elements are distributed along the entire length of the stent

2. A delivery system for coated medical devices comprising a stent delivery system according to claim 1, wherein the self-expanding stent is a coated, self-expanding stent.

3. The self-expanding stent delivery system according to Claim 1 or 2, wherein the height of the plurality of raised elements is greater than the difference in radius between the outside diameter of the shaft and the inside diameter of the sheath minus the wall thickness of the stent.

4. The self-expanding stent delivery system according to claim 1 or 2, wherein the self-expanding stent comprises a plurality of adjacent hoops, the hoops comprising a plurality of longitudinal struts and a plurality of loops

connecting adjacent struts, the self-expanding stent further comprising a plurality of bridges which connect adjacent hoops;

and wherein the one or more raised elements are arranged such that they occupy the spaces formed between adjacent loops on adjacent hoops and between the bridges.

1/25

FIG. 1




FIG. 2





FIG. 3

FIG. 4

Release in 25% Aq. Ethanol for
21508 + Rapamycin w/ top coat









FIG. 5



5/25

FIG. 6

6/25

FIG. 7**FIG. 8****FIG. 9**

7/25

FIG. 10**FIG. 11**

8/25

FIG. 12











FIG. 13



9/25

FIG. 14**FIG. 15****FIG. 16**

10/25

FIG. 17**FIG. 18****FIG. 19**

11/25

FIG. 20




FIG. 21





FIG. 22



12/25



FIG. 23

FIG. 24



14/25

FIG. 25







FIG. 26



15/25



17/25

FIG. 29

18/25

FIG. 30




FIG. 31





FIG. 32



19/25

FIG. 33





FIG. 34



20/25

FIG. 35





FIG. 36



21/25

FIG. 37











FIG. 38





22/25

FIG. 39**FIG. 40****FIG. 41****FIG. 42****FIG. 43**


23/25



24/25

FIG. 45**FIG. 46**

25/25

FIG. 47**FIG. 48**