



(86) Date de dépôt PCT/PCT Filing Date: 2013/11/22
(87) Date publication PCT/PCT Publication Date: 2014/05/30
(45) Date de délivrance/Issue Date: 2017/03/21
(85) Entrée phase nationale/National Entry: 2015/05/01
(86) N° demande PCT/PCT Application No.: KR 2013/010696
(87) N° publication PCT/PCT Publication No.: 2014/081246
(30) Priorités/Priorities: 2012/11/22 (KR10-2012-0133245);
2012/11/22 (KR10-2012-0133244);
2012/11/27 (KR10-2012-0135518)


(51) Cl.Int./Int.Cl. *B23K 35/24* (2006.01),
C22C 30/00 (2006.01), *C22C 38/40* (2006.01),
C22C 38/58 (2006.01)

(72) Inventeurs/Inventors:
HAN, IL-WOOK, KR;
KIM, JEONG-KIL, KR;
LEE, BONG-KEUN, KR;
LEE, HONG-KIL, KR

(73) Propriétaire/Owner:
POSCO, KR

(74) Agent: ROBIC

(54) Titre : JOINT SOUDE D'ACIER A TENUE AUX TEMPERATURES EXTREMEMENT BASSES, ET MATIERES DE SOUDURE POUR SA PREPARATION
(54) Title: WELDED JOINT OF EXTREMELY LOW-TEMPERATURE STEEL, AND WELDING MATERIALS FOR PREPARING SAME



(57) Abrégé/Abstract:

According to the present invention, provided are a welded joint of extremely low-temperature steel and flux cored, submerged, and gas metal arc welding materials which can be used to prepare the welded joint, wherein the welded joint of extremely low-temperature steel has outstanding impact toughness in extremely low-temperature conditions and excellent yield strength at room temperature.

(12) 특허협력조약에 의하여 공개된 국제출원

(19) 세계지식재산권기구
국제사무국(43) 국제공개일
2014 년 5 월 30 일 (30.05.2014)(10) 국제공개번호
WO 2014/081246 A1

(51) 국제특허분류:

C22C 38/00 (2006.01) C22C 38/58 (2006.01)
C22C 38/50 (2006.01) B23K 35/24 (2006.01)

(21) 국제출원번호:

PCT/KR2013/010696

(22) 국제출원일:

2013 년 11 월 22 일 (22.11.2013)

(25) 출원언어:

한국어

(26) 공개언어:

한국어

(30) 우선권정보:

10-2012-0133244 2012 년 11 월 22 일 (22.11.2012) KR
10-2012-0133245 2012 년 11 월 22 일 (22.11.2012) KR
10-2012-0135518 2012 년 11 월 27 일 (27.11.2012) KR

(71) 출원인: 주식회사 포스코 (POSCO) [KR/KR]; 790-300
경상북도 포항시 남구 동해안로 6261 (괴동동),
Gyeongsangbuk-do 790-300 (KR).

(72) 발명자: 한일옥 (HAN, Il-Wook); 790-360 경상북도 포
항시 남구 동촌동 5 번지 포항제철소내, Kyung-sang-
book-do (KR). 김정길 (KIM, Jeong-Kil); 790-360 경
상북도 포항시 남구 동촌동 5 번지 포항제철소내, Kyung-
sangbook-do (KR). 이봉근 (LEE, Bong-Keun); 790-360
경상북도 포항시 남구 동촌동 5 번지 포항제철소내,
Kyung-sangbook-do (KR). 이홍길 (LEE, Hong-Kil); 790-
360 경상북도 포항시 남구 동촌동 5 번지 포항제철소
내, Kyung-sangbook-do (KR).

(74) 대리인: 특허법인 씨앤에스 (C&S PATENT AND
LAW OFFICE); 135-971 서울시 강남구 언주로 30 길
13 대림아크로텔 7 층, Seoul (KR).

(81) 지정국 (별도의 표시가 없는 한, 가능한 모든 종류의
국내 권리의 보호를 위하여): AE, AG, AL, AM, AO,
AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,
CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO,
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,
HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KZ, LA,
LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK,
MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA,
PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD,
SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR,
TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) 지정국 (별도의 표시가 없는 한, 가능한 모든 종류의
역내 권리의 보호를 위하여): ARIPO (BW, GH, GM,
KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG,
ZM, ZW), 유라시아 (AM, AZ, BY, KG, KZ, RU, TJ,
TM), 유럽 (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC,
MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR),
OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM,
ML, MR, NE, SN, TD, TG).


공개:

— 국제조사보고서와 함께 (조약 제 21 조(3))

[다음 쪽 계속]

(54) Title: WELDED JOINT OF EXTREMELY LOW-TEMPERATURE STEEL, AND WELDING MATERIALS FOR PREPAR-
ING SAME

(54) 발명의 명칭 : 극저온강의 용접이음부 및 이를 제조하기 위한 용접 재료



(57) Abstract: According to the present invention, provided are a welded joint of extremely low-temperature steel and flux cored, submerged, and gas metal arc welding materials which can be used to prepare the welded joint, wherein the welded joint of extremely low-temperature steel has outstanding impact toughness in extremely low-temperature conditions and excellent yield strength at room temperature.

(57) 요약서: 본 발명에 따르면, 극저온 환경에서 충격인성이 우수하고, 상온 항복강도가 뛰어난 극저온강의 용접이음부를 제공할 수 있고, 이를 제조할 수 있는 플럭스코어드, 서브머지드 및 가스메탈 아크 용접재료를 제공할 수 있다.

WO 2014/081246 A1



-
- 청구범위 보정 기한 만료 전의 공개이며, 보정서를
접수하는 경우 그에 관하여 별도 공개함 (규칙
48.2(h))

【DESCRIPTION】**【Invention Title】**

WELDED JOINT OF EXTREMELY LOW-TEMPERATURE STEEL, AND
WELDING MATERIALS FOR PREPARING SAME

【Technical Field】

The present disclosure relates to a welded joint of extremely low temperature steel and a welding material for forming the welded joint. More particularly, the present disclosure relates to flux cored, submerged, and gas metal arc welding materials and welded joints formed of the materials.

【Background Art】

Recently, demand for liquefied natural gas (LNG) has markedly increased, and thus, there is increasing demand for transportation equipment and storage tanks for transporting and storing extremely low temperature LNG. Tanks for transporting and storing LNG should have sufficient impact resistance at LNG temperatures equal to or lower than -162°C . Typical materials having a high degree of impact resistance at extremely low temperatures are aluminum (Al), 9% nickel (Ni) steel, and stainless steel (hereinafter referred to as "STS").

However, aluminum (Al) has a low degree of tensile strength, and thus relatively thick aluminum plates have to

be used. In addition, aluminum (Al) has poor weldability.

9% Ni steel requires relatively expensive welding materials such as Inconel 625 (nickel: 50 wt% or more, Cr: 20 wt% or more), and the yield strength of welded joint of 9% Ni steel is low. STS is relatively expensive and has a low degree of thermal strain, and the quality of STS is not guaranteed at extremely low temperatures.

Therefore, it is necessary to develop a technique for forming high manganese (Mn) welded joints for use in extremely low temperature environments by using a material guaranteeing weldability and which is relatively inexpensive, as compared to nickel (Ni) used as an austenite stabilizing element.

Particularly, a welded joint having a degree of impact toughness of 27 J or greater is necessary for maintaining the stability of a structure at an extremely low temperature of -196°C or lower, and a welded joint having a room temperature yield strength of 360 MPa or greater is necessary for manufacturing a structure at room temperature. To this end, in the related art, materials containing large amounts of relatively expensive nickel (Ni) and chromium (Cr) (Ni: 50 wt% or more, and Cr: 20 wt% or more) are used to form welded joints. Therefore, there is a need for a welding material containing low amounts of

relatively expensive elements and a welded joint formed of the welding material.

【Disclosure】

【Technical Problem】

An aspect of the present disclosure may provide a welded joint having a high degree of low temperature impact toughness and a high degree of yield strength, the welded joint maintaining an austenite phase having a high degree of toughness even at extremely low temperatures and not exhibiting high temperature cracking during a welding process.

An aspect of the present disclosure may also provide a welding material for forming the welded joint.

However, aspects of the present disclosure are not limited thereto. Additional aspects will be set forth in part in the description which follows, and will be apparent from the description to those of ordinary skill in the related art.

【Technical Solution】

According to an aspect of the present disclosure, a welded joint of extremely low temperature steel may include, by wt%, carbon (C): 0.05% to 1.30%, silicon (Si): 0.2% to 1.8%, manganese (Mn): 0.4% to 23%, chromium (Cr): 0.01% or more to less than 12%, nickel (Ni): 23% to 49%, at least one selected from molybdenum (Mo), cobalt (Co), and tungsten (W): 0.01% to 10%, aluminum (Al):

0.2% or less, and excluding 0%, titanium (Ti): 0.9% or less, and excluding 0%, at least one selected from niobium (Nb) and vanadium (V): 0.9% or less, and excluding 0%, at least one selected from sulfur (S) and phosphorus (P): 0.035% or less, and excluding 0%, and the balance of iron (Fe) and inevitable impurities.

According to another aspect of the present disclosure, a flux cored arc welding material may include a core and an outer sheath surrounding the core, wherein the flux cored arc welding material may include, by wt%, carbon (C): 0.05% to 1.30%, silicon (Si): 0.2% to 1.8%, manganese (Mn): 0.5% to 25%, at least one selected from phosphorus (P) and sulfur (S): less than 0.031%, nickel (Ni): 25% to 50%, aluminum (Al): 1.5% or less, TiO_2 : 3.5% to 15%, at least one selected from potassium (K), sodium (Na), and lithium (Li): 0.01% to 1.3%, titanium (Ti): 2.4% or less, at least one selected from molybdenum (Mo), tungsten (W), and cobalt (Co): 0.001% to 10%, and the balance of iron (Fe) and inevitable impurities,

wherein the outer sheath may include, by wt%, nickel (Ni): 35% to 46%, other impurities: 0.05% or less, and the balance of iron (Fe).

According to another aspect of the present disclosure, a submerged and gas metal arc welding material may include

a core and an outer sheath surrounding the core, wherein the submerged and gas metal arc welding material may include, by wt%, carbon (C): 0.05% to 1.20%, silicon (Si): 0.3% to 1.2%, manganese (Mn): 3% to 25%, at least one selected from phosphorus (P) and sulfur (S): 0.03% or less, nickel (Ni): 25% to 50%, aluminum (Al): 1.5% or less, and the balance of iron (Fe) and inevitable impurities,

wherein the outer sheath may include, by wt%, nickel (Ni): 35% to 46%, other impurities: 0.05% or less, and the balance of iron (Fe).

【Advantageous Effects】

The present disclosure provides a welded joint having a high degree of impact toughness at extremely low temperatures and a high degree of yield strength at room temperature. In addition, the present disclosure provides a welding material for forming the welded joint by a flux cored arc welding (FCAW) method, a submerged arc welding (SAW) method, or a gas metal arc welding (GMAW) method. The welding material contains low amounts of relatively expensive alloying elements and thus may be economically used.

【Description of Drawings】

FIG. 1 is a cross-sectional view illustrating a welding material according to an exemplary embodiment of

the present disclosure.

FIG. 2 is a cross-sectional view illustrating a welding material according to an exemplary embodiment of the present disclosure.

FIG. 3 is a cross-sectional view illustrating a welding material according to an exemplary embodiment of the present disclosure.

【Best Mode】

Generally, extremely low temperature high manganese (Mn) steel having a high Mn content is used as a substitute for 9% nickel (Ni) steel and stainless steel STS 304 used for the manufacturing of liquefied natural gas (LNG) storage tanks. It is known that extremely low temperature high Mn steel has a stable austenite structure even at extremely low temperatures and thus does not require additional processes such as a heat treatment process, and does not exhibit toughness deterioration in a heat-affected zone (HAZ) during welding.

A welded joint of extremely low temperature steel of the present disclosure may be formed by welding extremely low temperature high Mn steel (which is used in extremely low temperature applications such as marine structures, energy facilities, shipbuilding facilities, and pressure containers) by a submerged arc welding (SAW) method, a flux

cored arc welding (FCAW) method, or a gas metal arc welding (GMAW) method. The welded joint of the present disclosure is designed to have a high degree of low temperature impact toughness. That is, the present disclosure provides a welded joint formed by a SAW method, a FCAW method, or a GMAW method and having a high degree of low temperature impact toughness and a high degree of room temperature yield strength. For this, components of the welded joint are adjusted so that the welded joint may maintain an austenite phase having a high degree of toughness even in extremely low temperature environments and may not be cracked at high temperatures during welding.

In addition, the present disclosure provides flux cored, submerged, and gas metal arc welding materials. The welding materials may be used to weld extremely low temperature high Mn steel to a different material and may have a high degree of low temperature impact toughness. That is, components of the welding materials are adjusted so that the welding materials may maintain an austenite phase having a high degree of toughness in extremely low temperature environments and may not crack at high temperatures during a welding process. That is, the welding materials have a high degree of low temperature impact toughness and allow all position welding.

First, the welded joint of extremely low temperature steel of the present disclosure will be described in detail.

According to an exemplary embodiment of the present disclosure, the welded joint includes, by wt%, carbon (C): 0.05% to 1.30%, silicon (Si): 0.2% to 1.8%, manganese (Mn): 0.4% to 23%, chromium (Cr): 0.01% to 12%, nickel (Ni): 23% to 49%, at least one selected from molybdenum (Mo), cobalt (Co), and tungsten (W): 0.01% to 10%, aluminum (Al): 0.2% or less, titanium (Ti): 0.9% or less, at least one selected from niobium (Nb) and vanadium (V): 0.9% or less, at least one selected from sulfur (S) and phosphorus (P): 0.035% or less, and the balance of iron (Fe) and inevitable impurities.

The numerical ranges of the contents of the components are set due to the reasons provided below. In the following description, the content of each component is given in wt% unless otherwise specified.

Carbon (C): 0.05% to 1.30%

Carbon (C) is known as a potent element stabilizing austenite, thereby guaranteeing the strength of a metal welding workpiece and the impact toughness of the metal welding workpiece at extremely low temperatures. In

addition, carbon (C) is an interstitial element increasing the yield strength of a metal. If the content of carbon (C) is less than 0.05%, the strength of the welded joint is decreased. In this case, the content of a substitute alloying element may be increased. On the contrary, if the content of carbon (C) is greater than 1.30%, carbon (C) combines with alloying elements manganese (Mn) or chromium (Cr) to form carbides such as MC or $M_{23}C_6$, thereby decreasing the low temperature impact toughness of the welded joint and causing the formation of cracks in the welded joint.

Silicon (Si): 0.2% to 1.8%

If the content of silicon (Si) is less than 0.2%, a metal welding workpiece may not be sufficiently deoxidized, and the fluidity of the metal welding workpiece may be decreased when the metal welding workpiece is melted. On the contrary, if the content of silicon (Si) is greater than 1.8%, segregation may occur in the metal welding workpiece, causing cracks in the welded joint.

Manganese (Mn): 0.4% to 23%

Manganese (Mn) is a main element inducing the formation of austenite which is a stable phase at low

temperature. manganese (Mn) is relatively inexpensive, as compared to nickel (Ni). If the content of manganese (Mn) is less than 0.4%, austenite is not sufficiently formed, thereby markedly lowering the toughness of the welded joint at extremely low temperatures. In contrast, if the content of manganese (Mn) is greater than 23%, problems such as excessive segregation, cracking at high temperatures, and the generation of harmful fumes may occur.

Chromium (Cr): 0.01% to 12%

Chromium (Cr) is a ferrite stabilizing element. In addition, if a certain amount of chromium (Cr) is added, the content of an austenite stabilizing element may be reduced. Furthermore, chromium (Cr) functions as an element improving corrosion resistance and strength. Although chromium (Cr) is added in a small amount of 0.01 wt% or more, the effect of increasing strength and corrosion resistance is obtained. However, if the content of chromium (Cr) is greater than 12%, Cr-based carbides are excessively formed, causing a decrease in the extremely low temperature toughness of the welded joint.

Nickel (Ni): 23% to 49%

Although nickel (Ni) is necessary as an austenite

stabilizing element, since nickel (Ni) is highly expensive, it may be preferable that the content of nickel (Ni) be within the range of 23% to 49%. Although nickel (Ni) increases the extremely low temperature impact toughness of the welded joint, nickel (Ni) decreases the room temperature yield strength of the welded joint. Therefore, the content of nickel (Ni) is properly adjusted to be within the range of 23% to 49%.

At least one selected from molybdenum (Mo), cobalt (Co), and tungsten (W): 0.01% to 10%

Even when molybdenum (Mo), cobalt (Co), and tungsten (W) are added in a small amount of 0.01% or more, the yield strength and tensile strength of a base metal are improved. However, if the total content of one or more of molybdenum (Mo), cobalt (Co), and tungsten (W) is greater than 10%, the formation of carbides thereof is facilitated, thereby decreasing the extremely low temperature toughness of the welded joint.

Aluminum (Al): 0.2% or less

Aluminum (Al) reduces strength and increases stacking fault energy (SFE), thereby guaranteeing low temperature toughness of the welded joint. However, if the content of

aluminum (Al) is greater than 0.2%, oxides are excessively formed, and thus the extremely low temperature impact toughness of the welded joint is lowered.

Titanium (Ti): 0.9% or less

Titanium (Ti) increases the yield strength and tensile strength of the welded joint. However, if the content of titanium (Ti) is greater than 0.9%, cracks may be formed in the welded joint.

At least one selected from niobium (Nb) and vanadium (V): 0.9% or less

Niobium (Nb) and vanadium (V) are elements increasing the room temperature strength of the welded joint. However, if the total content of one or more of niobium (Nb) and vanadium (V) is greater than 0.9%, cracks may be formed in the welded joint. Therefore, the content thereof may be preferably 0.9 wt% or less.

At least one selected from sulfur (S) and phosphorus (P): 0.035% or less

Sulfur (S) and phosphorus (P) are typical elements causing high temperature cracking. Therefore, it is necessary to adjust the contents of sulfur (S) and

phosphorus (P) to be low. Although sulfur (S) and phosphorus (P) are inevitably included, it is necessary to control the total content of sulfur (S) and phosphorus (P) to be 0.035% or less.

In addition to the above-described essential components, the welded joint of the present disclosure may further include at least one selected from nitrogen (N): 0.001 wt% to 0.6 wt% and boron (B): 0.0001 wt% to 0.008 wt%.

Nitrogen (N): 0.001% to 0.6%

Nitrogen (N) increases the strength of the welded joint and has the same characteristics as those of carbon (C). If the content of nitrogen (N) is greater than 0.6%, voids may be formed in the welded joint. Therefore, it is necessary to maintain the content of nitrogen (N) at 0.6% or less. Moreover, if the content of nitrogen (N) in the welded joint is 0.75% or more, nitrides are excessively formed, and thus the impact toughness of the welded joint is lowered.

Boron (B): 0.0001% to 0.008%

Boron (B) is an interstitial strength enhancing element, and even though boron (B) is added to the welded joint in small amounts, the yield strength and tensile

strength of the welded joint may be increased. However, if boron (B) is added in large amounts, the welded joint may crack. Therefore, the content of boron (B) is adjusted to be 0.008% or less.

In the present disclosure, the other component of the welded joint is iron (Fe). However, impurities in raw materials or manufacturing environments may be inevitably included in the welded joint, and such impurities may not be removed. Such impurities are well-known to those of ordinary skill in manufacturing industries, and thus descriptions thereof will not be given in the present disclosure.

The welded joint of the present disclosure includes the above-described components, and at least one selected from molybdenum (Mo), cobalt (Co), and tungsten (W) (hereinafter also referred to as "Mo+W+Co"), at least one selected from niobium (Nb) and vanadium (V) (hereinafter also referred to as "Nb+V"), and nickel (Ni), chromium (Cr), aluminum (Al), and titanium (Ti) included in the welded joint may satisfy the following formulas.

$$\begin{aligned} & \text{(Formula 1) } 1.5\text{Ni} - 8\text{Cr} - 2.5(\text{Mo+W+Co}) - 20\text{Al} - 29\text{Ti} \\ & - 55(\text{Nb+V}) \geq 0 \end{aligned}$$

If Formula 1 is satisfied, the impact toughness of the welded joint may be 27 J or greater at an extremely low

temperature of -196°C .

Furthermore, in the welded joint of the present disclosure including the above-described components, C, Mn, Cr, Ni, Mo+Co+W, Ti, and Nb+V may satisfy Formula 2 below.

$$\text{(Formula 2)} \quad 98.5\text{C} - 1.08\text{Mn} + 9.73\text{Cr} - 1.52\text{Ni} + 10.3(\text{Mo}+\text{W}+\text{Co}) + 122\text{Ti} + 34.7(\text{Nb}+\text{V}) \geq 0$$

If Formula 2 is satisfied, the yield strength of the welded joint may be 360 MPa or greater at room temperature.

Furthermore, in the welded joint of the present disclosure including the above-described components, Si, Al, and Ti may satisfy Formula 3 below.

$$\text{(Formula 3)} \quad \text{Si}+\text{Al}+\text{Ti} \leq 2.0$$

If $\text{Si}+\text{Al}+\text{Ti} > 2.0$, cracks may be formed in the welded joint. Therefore, the welded joint is controlled to satisfy Formula 3.

In other words, according to technical effects of the present disclosure, the welded joint has an impact toughness of 27 J or greater at an extremely low temperature of -196°C and a yield strength of 360 MPa at room temperature.

Next, a flux cored arc welding material of the present disclosure for forming a welded joint will be described in detail.

The flux cored arc welding material of the present disclosure is a composite welding wire having a dual structure formed by a core and an outer sheath. The core includes an alloy and flux powder, and the outer sheath covers the outer surface of the core.

In detail, the outer sheath covering the core has a single structure formed of an iron (Fe)-based strip containing nickel (Ni) in an amount of 35 wt% to 46 wt%.

The flux cored arc welding material for FCAW of the present disclosure includes, by wt%, carbon (C): 0.05% to 1.30%, silicon (Si): 0.2% to 1.8%, manganese (Mn): 0.5% to 25%, at least one selected from phosphorus (P) and sulfur (S): less than 0.031%, nickel (Ni): 25% to 50%, aluminum (Al): 1.5% or less, TiO_2 : 3.5% to 15%, at least one selected from potassium (K), sodium (Na), and lithium (Li): 0.01% to 1.3%, titanium (Ti): 2.4% or less, at least one selected from molybdenum (Mo), tungsten (W), and cobalt (Co): 0.001% to 10%, and the balance of iron (Fe) and inevitable impurities.

The numerical ranges of the contents of the components are set due to the reasons provided below.

Carbon (C): 0.05 wt% to 1.30 wt%

Carbon (C) is known as a potent element stabilizing

austenite, thereby guaranteeing the strength of a metal welding workpiece and the impact toughness of the metal welding workpiece at extremely low temperatures. Thus, carbon (C) is an essential element of the welding material of the present disclosure. However, since the welding wire receives a sufficient amount of carbon (C) from flux even though the welding wire has a low carbon content, it is sufficient that the lower limit of the carbon content is 0.05 wt%. However, if the content of carbon (C) is less than 0.05 wt%, austenite is not formed at extremely low temperatures, thereby causing a decrease in toughness. In contrast, if the content of carbon (C) is greater than 1.30 wt%, carbon dioxide gas may be generated to cause defects in a welded joint during welding, and carbon (C) may combine with alloying elements such as manganese (Mn) and chromium (Cr) to form carbides such as MC and $M_{23}C_6$ that lower the impact toughness of the welded joint. Therefore, it may be preferable that the content of carbon (C) be within the range of 0.05 wt% to 1.30 wt%.

Silicon (Si): 0.2 wt% to 1.8 wt%

If the content of silicon (Si) is less than 0.2 wt%, a metal welding workpiece may not be sufficiently deoxidized, and the fluidity of the metal welding workpiece

may be lowered when the metal welding workpiece is melted. In contrast, if the content of silicon (Si) is greater than 1.8 wt%, segregation may occur in the metal welding workpiece, causing a decrease in low temperature impact toughness and worsening welding crack susceptibility. Therefore, it may be preferable that the content of silicon (Si) be within the range of 0.3 wt% to 1.8 wt%.

Manganese (Mn): 0.5 wt% to 25 wt%

Manganese (Mn) is a main element inducing the formation of austenite which is a stable phase at low temperature. Thus, manganese (Mn) is an essential element in the welding material of the present disclosure. Manganese (Mn) is relatively inexpensive, as compared to nickel (Ni). If the content of manganese (Mn) is less than 0.5%, austenite is not sufficiently formed, thereby markedly lowering the toughness of a welded joint at extremely low temperatures. In contrast, if the content of manganese (Mn) is greater than 23%, problems such as excessive segregation, cracking at high temperatures, and the generation of harmful fumes may occur. Therefore, it may be preferable that the content of manganese (Mn) be within the range of 0.5 wt% to 25 wt%.

At least one selected from sulfur (P) and phosphorus (S): 0.031 wt% or less

Sulfur (P) and phosphorus (S) segregate in a finally solidified portion after welding. Sulfur (P) and phosphorus (S) form a compound having a low melting point, and due to welding stress, cracks may be formed in a portion where the compound is formed. Therefore, it may be preferable that the total content of sulfur (P) and phosphorus (S) be 0.031 wt% or less.

Nickel (Ni): 25 wt% to 50 wt%

In the present disclosure, nickel (Ni) is an essential element stabilizing austenite. Preferably, the content of nickel (Ni) is adjusted to be 25 wt% or more for guaranteeing extremely low temperature toughness, but is adjusted to be 50 wt% or less in consideration of manufacturing costs. That is, it may be preferable that the content of nickel (Ni) be within the range of 25 wt% to 50 wt%.

Aluminum (Al): 1.5 wt% or less

Aluminum (Al) reduces strength and increases stacking fault energy (SFE), thereby guaranteeing the low temperature toughness of the welding material. However, if

the content of aluminum (Al) is greater than 1.5 wt%, TiO_2 formed in a welded joint may be reduced to form $\text{Ti}(\text{C},\text{N})$, and thus the extremely low temperature impact toughness of the welded joint may be greatly reduced. Therefore, it may be preferable that the content of aluminum (Al) be 1.5 wt% or less.

TiO_2 (titanium dioxide): 3.5 wt% to 15 wt%

TiO_2 is a slag forming agent that solidifies before a melted metal welding workpiece solidifies and thus prevents the melted metal welding workpiece from flowing downward, thereby enabling all position welding. For obtaining this effect in the present disclosure, preferably, TiO_2 is added in an amount of 3.5 wt% or more. However, if the content of TiO_2 is greater than 15 wt%, the content of oxides in a metal welding workpiece is steeply increased, and thus the extremely low temperature impact toughness of the metal welding workpiece is decreased. Therefore, it may be preferable that the content of TiO_2 be within the range of 3.5 wt% to 15 wt%.

At least one selected from potassium (K), sodium (Na), and lithium (Li): 0.01 wt% to 1.3 wt%

During welding, these alkali metals may facilitate

the creation of arcs by lowering the ionization potential of arcs and may function to stably maintain arcs. These effects may be obtained when the alkali metals are added in amounts of 0.01 wt% or more. However, if the total content of the alkali metals is greater than 1.3 wt%, fumes may be excessively generated due to a high vapor pressure. In the present disclosure, at least one selected from potassium (K), sodium (Na), and lithium (Li) is added, and the effect of the alkali metals has no relationship with the content ratio of the alkali metals.

Titanium (Ti): 2.4 wt% or less

Preferably, the welding wire of the present disclosure may have a titanium (Ti) content of 2.4 wt% or less. Titanium (Ti) is a powerful deoxidizer capable of removing oxides from a metal welding workpiece. However, if titanium (Ti) is added in excessive amounts, the content of Ti(C,N) may increase, and thus the extremely low temperature impact toughness of the welding material may be extremely decreased. Therefore, it may be preferable that the content of aluminum (Al) be 2.4 wt% or less.

At least one selected from molybdenum (Mo), tungsten (W), and cobalt (Co): 0.001 wt% to 10 wt%

Molybdenum (Mo), tungsten (W), and cobalt (Co) are elements increasing the strength of a base metal. In the present disclosure, preferably, the total content of Mo, W, and Co is 0.001 wt% or more. However, if the total content of Mo, W, and Co is greater than 10%, carbides are excessively formed, decreasing the extremely low temperature toughness of the welding material. Therefore, it may be preferable that the total content of one or more of Mo, W, and Co be within the range of 0.001 wt% to 10 wt%.

In addition to the above-described essential components, the welding material of the present disclosure may further include, by wt%, one or more of chromium (Cr): 0.001% to 10%, at least one selected from niobium (Nb) and vanadium (V): 0.001% to 1.2%, at least one selected from SiO₂, ZrO₂, and Al₂O₃: 0.01% to 7.0%, at least one selected from fluorine (F) and calcium (Ca): 0.01% to 1.0%, and nitrogen (N): 0.01% to 0.5%. In this case, the welding material of the present disclosure may provide improved effects.

Chromium (Cr): 0.001 wt% to 10 wt%

Chromium (Cr) is an element stabilizing ferrite and improving strength and corrosion characteristics. To guarantee these effects, it may be preferable that that

content of chromium (Cr) be 0.001 wt%. However, if the content of chromium (Cr) is greater than 10 wt%, chromium-based carbides are excessively formed, decreasing the extremely low temperature toughness of the welding material. Therefore, it may be preferable that the content of chromium (Cr) be within the range of 0.001 wt% to 10 wt%.

At least one selected from niobium (Nb) and vanadium (V): 0.001 wt% to 1.2 wt%

Niobium (Nb) and vanadium (V) are elements increasing the strength of a base metal. In the present disclosure, preferably, the total content of niobium (Nb) and vanadium (V) is 0.001 wt% or more. However, if the total content of niobium (Nb) and vanadium (V) is greater than 1.2%, carbides are excessively formed, thereby decreasing the extremely low temperature toughness of the welding material. Therefore, it may be preferable that the total content of one or more of niobium (Nb) and vanadium (V) be within the range of 0.001 wt% to 1.2 wt%.

At least one selected from SiO₂ (silicon dioxide), ZrO₂ (zirconium dioxide), and Al₂O₃ (aluminum oxide): 0.01 wt% to 7.0 wt%

If the total content of one or more of SiO₂, ZrO₂, and

Al_2O_3 is less than 0.01 wt%, slag coating, striping of slag, and arc stability are negatively affected, and thus it may be difficult to perform an all position welding process and properly form welding beads. In contrast, if the total content of one or more of SiO_2 , ZrO_2 , and Al_2O_3 is greater than 7.0 wt%, the amount of melted slag may be rapidly increased, and the viscosity of the slag may also be increased, thereby negatively affecting an all position welding process and the formation of welding beads. In addition, the transfer of components such as silicon (Si) and aluminum (Al) to a deposited metal is increased, thereby decreasing impact toughness. Therefore, it may be preferable that the total content of one or more of SiO_2 , ZrO_2 , and Al_2O_3 be within the range of 0.01 wt% to 7.0 wt%.

At least one selected from fluorine (F) and calcium (Ca): 0.01 wt% to 1.0 wt%

Among alkali metal based and alkaline earth metal based fluorine compounds, fluorine (F) and calcium (Ca) may be additionally added to the welding wire of the present disclosure to improve the properties of the welding wire. If a fluorine compound is added to the welding wire in an amount of 0.01 wt% or more, fluorine (F) is present in a high-temperature arc and reacts with hydrogen

(dehydrogenation reaction), thereby effectively reducing diffusion hydrogen. However, if the content of the fluorine compound is greater than 1.0 wt%, fumes are excessively generated because of a high vapor pressure, and the viscosity of slag in a molten pool is excessively decreased to result in unstable welding beads when rutile type slag containing TiO_2 as a main component is used during welding. Therefore, it may be preferable that the total content of fluorine (F) and calcium (Ca) be within the range of 0.01 wt% to 1.0 wt%.

Nitrogen (N): 0.01 wt% to 0.5 wt%

In addition, if nitrogen (N) is additionally added to the welding wire of the present disclosure, the properties of the welding wire may be improved. Nitrogen (N) results in the same effects as carbon (C). In the present disclosure, preferably, the content of nitrogen (N) may be adjusted to be 0.01 wt% or more. However, if the content of nitrogen (N) is greater than 0.5 wt%, nitrides may be excessively formed to result in a decrease in impact toughness. Therefore, it may be preferable that the content of nitrogen (N) be within the range of 0.01 wt% to 0.5 wt%.

In the present disclosure, the other component of the

welding material is iron (Fe). However, impurities in raw materials or manufacturing environments may be inevitably included in the welding material, and such impurities may not be removed. Such impurities are well-known to those of ordinary skill in manufacturing industries, and thus descriptions thereof will not be given in the present disclosure.

The outer sheath of the welding material includes, by wt%, Ni: 35% to 46%, other impurities: 0.05% or less, and the balance of iron (Fe). That is, the outer sheath is formed of high nickel (Ni) steel to increase the content of nickel (Ni) in a welded joint during a welding process. The contents of nickel (Ni) and other impurities in the outer sheath are adjusted to be within the above-mentioned ranges to guarantee toughness at extremely low temperatures and decrease defects such as cracks during welding.

The welding material may have a diameter of about 0.9 mm to about 1.6 mm, and when the density of the outer sheath and the density of the core, the weight fraction of the outer sheath in the welding material may preferably be within the range of 50% to 90%.

As shown in FIG. 1, the outer sheath may have a single layer structure surrounding the core containing an alloy.

Next, a submerged and gas metal arc welding material of the present disclosure for forming a welded joint will be described in detail.

The submerged and gas metal arc welding material of the present disclosure includes, by wt%, carbon (C): 0.05% to 1.20%, silicon (Si): 0.3% to 1.2%, manganese (Mn): 3% to 15%, at least one selected from phosphorus (P) and sulfur (S): 0.03% or less, nickel (Ni): 25% to 50%, aluminum (Al): 1.5% or less, and the balance of iron (Fe) and inevitable impurities.

The numerical ranges of the contents of the components are set due to the reasons provided below.

Carbon (C): 0.05 wt% to 1.20 wt%

Carbon (C) is known as a potent element stabilizing austenite, thereby guaranteeing the strength of a metal welding workpiece and the impact toughness of the metal workpiece at extremely low temperatures. Thus, carbon (C) is an essential element of the welding material of the present disclosure. However, since a welding wire (the welding material) receives a sufficient amount of carbon (C) from flux even though the welding wire has a low carbon content, it is sufficient that the lower limit of the

carbon content is 0.05 wt% or less. However, if the content of carbon (C) is less than 0.05 wt%, austenite is not formed at extremely low temperatures, thereby causing a decrease in toughness. In contrast, if the content of carbon (C) is greater than 1.20 wt%, carbon dioxide gas may be generated to cause defects in a welded joint during welding, and carbon (C) may combine with alloying elements such as manganese (Mn) and chromium (Cr) to form carbides such as MC and $M_{23}C_6$ that lower the impact toughness of the welded joint. Therefore, it may be preferable that the content of carbon (C) be within the range of 0.05 wt% to 1.20 wt%.

Silicon (Si): 0.30 wt% to 1.2 wt%

If the content of silicon (Si) is less than 0.30 wt%, a metal welding workpiece may not be sufficiently deoxidized, and the fluidity of the metal welding workpiece may be lowered when the metal welding workpiece is melted. In contrast, if the content of silicon (Si) is greater than 1.2 wt%, segregation may occur in the metal welding workpiece, causing a decrease in low temperature impact toughness and worsening welding crack susceptibility. Therefore, it may be preferable that the content of silicon (Si) be within the range of 0.30 wt% to 1.2 wt%.

Manganese (Mn): 3 wt% to 15 wt%

Manganese (Mn) is a main element inducing the formation of austenite which is a stable phase at low temperature. Thus, manganese (Mn) is an essential element in the welding material of the present disclosure. Manganese (Mn) is relatively inexpensive, as compared to nickel (Ni). If the content of manganese (Mn) is less than 3%, austenite is not sufficiently formed, thereby markedly lowering toughness at extremely low temperatures. However, if the content of manganese (Mn) is greater than 15 wt%, segregation may occur excessively, and thus high temperature cracking may occur. Therefore, it may be preferable that the content of manganese (Mn) be within the range of 3 wt% to 15 wt%.

At least one selected from sulfur (P) and phosphorus (S): 0.03% or less

Sulfur (P) and phosphorus (S) segregate in a finally solidified portion after welding. Sulfur (P) and phosphorus (S) form a compound having a low melting point, and due to welding stress, cracks may be formed in a portion in which the compound is formed. Therefore, it may be preferable that the total content of sulfur (P) and

phosphorus (S) be 0.03 wt% or less.

Nickel (Ni): 25 wt% to 50 wt%

In the present disclosure, nickel (Ni) is an essential element stabilizing austenite. Preferably, the content of nickel (Ni) is adjusted to be 25 wt% or more for guaranteeing extremely low temperature toughness, but is adjusted to be 50 wt% or less in consideration of manufacturing costs. That is, it may be preferable that the content of nickel (Ni) be within the range of 25 wt% to 50 wt%.

Aluminum (Al): 1.5 wt% or less

Aluminum (Al) reduces strength and increases stacking fault energy (SFE), thereby guaranteeing the low temperature toughness of the welding material. However, if the content of aluminum (Al) is greater than 1.5 wt%, when a welding process is performed using flux including TiO_2 , TiO_2 formed in a welded joint may be reduced to form Ti(C,N) . In this case, the extremely low temperature impact toughness of the welded joint may be greatly reduced. Therefore, it may be preferable that the content of aluminum (Al) be 1.5 wt% or less.

In addition to the above-described essential

components, the welding material of the present disclosure may further include, by wt%, one or more selected from the group consisting of chromium (Cr): 0.001% to 6%, at least one selected from molybdenum (Mo), tungsten (W), and cobalt (Co): 0.001% to 6%, at least one selected from niobium (Nb) and vanadium (V): 0.001% to 1.5%, and nitrogen (N): 0.01% to 0.5%. In this case, the welding material of the present disclosure may provide improved effects.

Chromium (Cr): 0.001 wt% to 6 wt%

Chromium (Cr) is an element stabilizing ferrite and improving strength and corrosion characteristics. To guarantee these effects, it may be preferable that the content of chromium (Cr) be 0.001 wt%. However, if the content of chromium (Cr) is greater than 6%, chromium-based carbides are excessively formed, decreasing the extremely low temperature toughness of the welding material. Therefore, it may be preferable that the content of chromium (Cr) be within the range of 0.001 wt% to 6 wt%.

At least one selected from molybdenum (Mo), tungsten (W), and cobalt (Co): 0.001 wt% to 6 wt%

Molybdenum (Mo), tungsten (W), and cobalt (Co) are elements increasing the strength of a base metal. In the

present disclosure, preferably, the total content of Mo, W, and Co is 0.001% or more. However, if the total content of Mo, W, and Co is greater than 6%, carbides are excessively formed, thereby decreasing the extremely low temperature toughness of the welding material. Therefore, it may be preferable that the total content of one or more of Mo, W, and Co be within the range of 0.001 wt% to 6 wt%.

At least one selected from niobium (Nb) and vanadium (V): 0.001 wt% to 1.5 wt%

Niobium (Nb) and vanadium (V) are elements increasing the strength of a base metal. In the present disclosure, preferably, the total content of niobium (Nb) and vanadium (V) is 0.001 wt% or more. However, if the total content of niobium (Nb) and vanadium (V) is greater than 1.5%, carbides are excessively formed, thereby decreasing the extremely low temperature toughness of the welding material. Therefore, it may be preferable that the total content of one or more of niobium (Nb) and vanadium (V) be within the range of 0.001 wt% to 1.5 wt%.

Nitrogen (N): 0.01 wt% to 0.5 wt%

In addition, if nitrogen (N) is additionally added to the welding wire (welding material) of the present

disclosure, the properties of the welding wire may be improved. Nitrogen (N) results in the same effects as carbon (C). In the present disclosure, preferably, the content of nitrogen (N) may be adjusted to be 0.01 wt% or more. However, if the content of nitrogen (N) is greater than 0.5 wt%, nitrides may be excessively formed to result in a decrease in impact toughness. Therefore, it may be preferable that the content of nitrogen (N) be within the range of 0.01 wt% to 0.5 wt%.

In the present disclosure, the other component of the welding material is iron (Fe). However, impurities in raw materials or manufacturing environments may be inevitably included in the welding material, and such impurities may not be removed. Such impurities are well-known to those of ordinary skill in manufacturing industries, and thus descriptions thereof will not be given in the present disclosure.

An outer sheath of the welding material includes, by wt%, Ni: 35% to 46%, other impurities: 0.05% or less, and the balance of iron (Fe). That is, the outer sheath is formed of high nickel (Ni) steel to increase the content of nickel (Ni) in a welded joint during a welding process. The contents of nickel (Ni) and other impurities in the outer sheath are adjusted to be within the above-mentioned

ranges to guarantee toughness at extremely low temperatures and decrease defects such as cracks during welding.

The welding material may have a diameter of about 0.9 mm to about 6.0 mm, and when the density of the outer sheath and the density of a core of the welding material, the weight fraction of the outer sheath in the welding material may be preferably within the range of 50% to 90%.

As shown in FIG. 1, the outer sheath may have a single layer structure surrounding the core containing an alloy.

An additional outer sheath may be disposed between the core and the outer sheath (refer to FIG. 2) or around the outer sheath (refer to FIG. 3) to form a dual outer sheath structure. The additional outer sheath includes, by wt%, carbon (C): 0.025% or less, manganese (Mn): 0.025% or less, and the balance of iron (Fe) and inevitable impurities.

That is, the additional outer sheath is formed of low carbon steel to increase the depth of welding and enhance the strength of the welding wire (welding material) to make it easy to move the welding wire in a straight line during welding. If the content of carbon (C) or manganese (Mn) is outside the above-mentioned range, it may be difficult to perform a drawing process when the welding material is

manufactured.

Although the additional outer sheath is added as described above, the composition of the entire welding material is not varied. That is, the welding material includes, by wt%, carbon (C): 0.05% to 1.20%, silicon (Si): 0.3% to 1.2%, manganese (Mn): 3% to 15%, at least one selected from phosphorus (P) and sulfur (S): 0.03% or less, nickel (Ni): 25% to 50%, aluminum (Al): 1.5% or less, and the balance of iron (Fe) and inevitable impurities. However, if necessary, the welding material may further include one or more selected from the group consisting of chromium (Cr): 0.001% to 6%, at least one selected from molybdenum (Mo), tungsten (W), and cobalt (Co): 0.001% to 6%, at least one selected from niobium (Nb) and vanadium (V): 0.001% to 1.5%, and nitrogen (N): 0.01% to 0.5%.

The welding material including the additional outer sheath may have a diameter of about 0.9 mm to about 6.0 mm, and the weight fraction of the entire outer sheath including the additional outer sheath may be preferably 50% to 90% of the total weight of the welding material when the density difference between the entire outer sheath and the core is considered. Since the core includes essential elements, the weight fraction of the core in the entire welding wire may be 10% to 50%. Therefore, although the

welding material has a dual outer sheath structure, the weight fraction of the entire outer sheath is 50% to 90% of the total weight of the welding material as in the case in which the welding material has a single outer sheath structure.

Reference numerals used in the accompanying drawing are as follows.

11: CORE, 12: OUTER SHEATH (HAVING A HIGH NI CONTENT)

21: CORE, 22: ADDITIONAL OUTER SHEATH (FORMED OF LOW CARBON STEEL), 23: OUTER SHEATH (HAVING A HIGH NI CONTENT)

31: CORE, 32: ADDITIONAL OUTER SHEATH (FORMED OF LOW CARBON STEEL), 33: OUTER SHEATH (HAVING A HIGH NI CONTENT)

【Mode for Invention】

Hereinafter, the present disclosure will be described more specifically through examples. However, the examples are for illustrative purposes only and are not intended to limit the scope of the present invention.

【Example 1】

Welded joints having compositions shown in Tables 1 and 2 were formed by different welding methods. In Tables 1 and 2, the content of each component is given in wt%.

A submerged arc welding (SAW) method, a flux cored arc welding (FCAW) method, and a gas metal arc welding (GMAW) method (or a MCW method) were used.

In the SAW method, welding was performed using Flux AB (commercial flux) at a heat input rate of 2.4 KJ to 3.0 KJ/mm.

In the FCAW method, welding was performed at a heat input rate of 1.7 KJ/mm under conditions of 100% CO₂.

In the GMAW (or MCW) method, welding was performed at a heat input rate of 1.7 KJ/mm under conditions of 80% Ar + 20% CO₂.

Thereafter, the presence of cracks or voids in the welded joints were observed, and the impact toughness of each welded joint at -196°C and the yield strength of each welded joint at room temperature were measured. Results of the observation or measurement are shown in Tables 1 and 2. In Tables 1 and 2, impact toughness values (CVN@-196°C) are given in joules (J), and yield strength values are given in MPa. In addition, components written using the symbol "+" indicate that at least one selected from the components is included in the welded joints.

[Table 1]

NO.	WM	C	Si	Mn	P+S	Cr	Ni	Mo+W+Co	Al	Ti	Nb+V	B	N	F1	F2	F3	Cracks Voids	CVM _{195C}	YS
C S 1-1	MCV	0.02	0.74	0.55	0.014	0.012	23.8	0.024	0.009	0.007	0.021	0.0005	0.0097	34.006	-32.8533	0.756	X	109	313
C S 1-2	FCAV	0.05	0.21	0.62	0.011	0.007	29.8	0.02	0.009	0.041	0.02	0.0001	0.0123	42.125	-35.0705	0.26	X	103	295
C S 1-3	FCAV	0.03	1.1	0.53	0.009	0.02	33.8	0.02	0.01	0.038	0.023	0.0002	0.0168	47.923	-43.1587	1.148	X	87	279
C S 1-4	FCAV	0.05	0.61	0.49	0.006	0.022	41.8	0.023	0.02	0.036	0.02	0.0002	0.022	59.9225	-53.6032	0.666	X	94	257
C S 1-5	MCV	0.06	0.76	1.71	0.029	0.024	51.6	0.024	0.015	0.032	0.022	0.0002	0.0195	74.71	-69.2207	0.807	X	98	244
C S 1-6	MCV	0.42	0.51	15.2	0.01	0.016	24.3	0.022	0.011	0.011	0.01	0.0006	0.0105	35.178	-9.91072	0.532	X	112	342
C S 1-7	FCAV	0.01	0.59	4.41	0.01	0.01	32.8	0.011	0.015	0.029	0.93	0.0003	0.031	-3.1985	-17.6142	0.634	X	19	348
C S 1-8	FCAV	0.41	0.58	0.88	0.013	0.014	33.6	0.013	0.013	0.058	0.039	0.0002	0.0322	46.1685	-2.93798	0.651	X	72	323
C S 1-9	FCAV	0.66	1.86	7.91	0.017	0.014	26.2	0.022	0.12	0.057	0.017	0.0006	0.0142	34.145	24.54992	2.037	0 (Cracks)	36	426
C S 1-10	FCAV	0.48	0.54	12.4	0.038	0.042	34.9	1.33	0.015	0.083	0.021	0.0004	0.0107	44.827	5.80236	0.638	0 (Cracks)	51	373
C S 1-11	MCV	0.81	0.31	4.05	0.01	0.015	28.5	10.6	0.022	0.01	1.76	0.0003	0.711	-81.4	203.709	0.342	0 (Voids)	20	558
C S 1-12	FCAV	0.92	0.69	6.27	0.015	12.4	31.2	1.77	0.1	0.286	0.03	0.0004	0.0062	-68.189	208.8004	1.056	X	19	573
C S 1-13	FCAV	0.73	0.51	8.54	0.02	4.55	32.5	12.49	0.11	0.161	0.023	0.001	0.0237	-27.009	206.6404	0.781	X	23	497
C S 1-14	FCAV	0.89	0.92	33.1	0.014	0.012	39.6	2.04	0.797	1.215	0.063	0.0226	0.0217	-0.436	163.2699	2.932	0 (C&V)	15	494
C S 1-15	FCAV	1.32	0.39	8.2	0.013	0.016	42.5	1.31	1.23	0.74	0.13	0.0005	0.0105	7.137	165.0037	2.36	0 (Cracks)	31	546

(Note) CS: Comparative Sample, WM: Welding Method, F1: Formula 1, F2: Formula 2, F3: Formula 3, YS: Yield Strength, and C&V: Cracks and Voids

[Table 2]

NO.	WM	C	Si	Mn	P+S	Cr	Ni	Mo+W+Co	Al	Ti	Nb+V	B	N	F1	F2	F3	Cracks Voids	CVN _{100°C}	YS
IS 1-1	FCAW	0.72	0.38	7.76	0.012	0.011	25.8	0.018	0.031	0.061	0.025	0.0002	0.011	34.803	31.92513	0.472	X	91	362
IS 1-2	FCAW	0.45	0.41	22.7	0.008	0.013	25.1	4.23	0.011	0.038	0.037	0.008	0.0119	23.614	31.27239	0.459	X	77	385
IS 1-3	SAW	0.75	0.33	14.7	0.014	0.011	23.4	1.13	0.19	0.321	0.018	0.0002	0.0041	18.088	73.96363	0.841	X	39	445
IS 1-4	FCAW	0.43	0.41	16.4	0.01	0.012	32.6	9.02	0.013	0.454	0.026	0.0002	0.004	11.398	124.404	0.877	X	41	523
IS 1-5	FCAW	0.23	0.95	4.66	0.008	0.012	32.8	0.034	0.02	0.028	0.86	0.0003	0.0112	0.507	1.49116	0.998	X	42	376
IS 1-6	SAW	0.35	0.4	5.62	0.029	5.47	33.7	0.48	0.022	0.053	0.02	0.0002	0.0134	2.513	42.5085	0.475	X	39	439
IS 1-7	SAW	0.45	0.49	10.4	0.01	0.013	32.8	3.93	0.02	0.181	0.023	0.0003	0.0116	32.357	46.72259	0.691	X	65	436
IS 1-8	SAW	0.08	0.55	4.26	0.008	0.02	43.8	5.92	0.011	0.661	0.028	0.0002	0.008	29.811	79.4874	1.222	X	64	461
IS 1-9	FCAW	0.45	0.44	4.79	0.02	0.016	31.2	2.04	0.019	0.083	0.022	0.0003	0.1239	37.575	23.78488	0.542	X	53	448
IS 1-10	FCAW	0.47	0.63	5.34	0.008	0.02	37.1	0.06	0.026	0.092	0.12	0.001	0.0144	45.552	0.3364	0.748	X	41	391
IS 1-11	FCAW	0.41	0.45	4.51	0.01	0.015	30.7	1.46	0.016	0.064	0.012	0.0005	0.2096	39.444	12.25855	0.53	X	77	498
IS 1-12	FCAW	0.05	0.73	6.16	0.01	3.89	48.3	7.62	0.057	0.033	0.014	0.0006	0.0217	19.413	45.7037	0.82	X	44	470
IS 1-13	FCAW	0.82	0.24	4.63	0.012	0.25	46	0.56	0.006	0.86	0.714	0.0005	0.0149	1.27	143.7459	1.106	X	33	521
IS 1-14	FCAW	0.4	0.50	0.51	0.01	3.0	24.3	4.2	0.01	0.01	0.01	0.0001	0.0102	0.91	75.9302	0.52	X	34	510

(Note) IS: Inventive Sample, WM: Welding Method, F1: Formula 1, F2: Formula 2, F3: Formula 3, and YS: Yield Strength

Referring to Tables 1 and 2, inventive samples satisfying alloying component contents and formulas of the present disclosure did not have cracks or voids, and the impact toughness values of the inventive samples were 27 J or greater at an extremely low temperature of -196°C and the yield strength values of the inventive samples were 360 MPa or greater at room temperature.

However, comparative samples were inferior to the inventive samples in at least one of the evaluation items: the presence of cracks or voids, impact toughness, and yield strength.

[Example 2]

Flux cored arc welding materials having compositions shown in Table 3 were prepared. In Table 3, the content of each component is given in wt%.

Inventive samples and comparative samples having the same outer sheath structure and composition but different welding material compositions were prepared. The outer sheath of each welding material includes, by wt%, nickel

(Ni): 35% to 46%, other impurities: 0.05% or less, and the balance of iron (Fe).

A FCAW process was performed using each welding material.

In the FCAW process, welding was performed at a heat input rate of 1.7 KJ/mm under conditions of 100% CO₂. A FCAW wire having a diameter of 1.2 mm was used.

Thereafter, weldability, the presence of cracks or voids in welded joints, impact toughness at -196°C, and yield strength at room temperature were observed or measured, and results of the observation or measurement are shown in Table 1. In Table 3, impact toughness values (CVN) are given in joules (J), and yield strength values are given in MPa. In addition, components written using the symbol "+" indicate that at least one selected from the components is included in the samples.

[Table 3]

NO.	C	Si	Mn	P+S	Cr	Ni	Mo+W+Co	Al	Ti	Nb+V	N	TiO ₂	SiO ₂ +ZrO ₂ +Al ₂ O ₃	K+Na+Li	F+Ca	Weld-ability.	Cracks Voids	CVN _{196°C}	YS
CS 2-1	0.08	0.4	1	0.021	-	31	-	-	-	-	-	4.5	-	0.1	-	Good	X	103	285
CS 2-2	0.05	2.2	0.9	0.018	-	35	-	-	-	-	-	4.5	-	0.1	-	Good	X	87	279
CS 2-3	0.05	2.2	0.9	0.018	-	35	-	-	-	-	-	6.5	-	0.1	1.2	Poor	-	-	-
CS 2-4	0.05	0.9	0.9	0.017	-	43	-	-	-	-	-	8.0	-	0.1	0.1	Good	X	94	257
CS 2-5	0.02	0.9	5	0.021	-	34	-	-	-	1.5	-	8.7	2	0.1	0.1	Good	X	19	348
CS 2-6	0.51	0.9	0.9	0.022	-	35	-	-	-	-	-	9	2	1	-	Good	X	72	323
CS 2-7	0.51	0.9	0.9	0.022	-	35	-	-	-	-	-	3.2	4	1.6	0.2	Poor	-	-	-
CS 2-8	0.8	2.5	9	0.027	-	28	-	-	-	-	-	5	4	1	0.5	Good	O (Cracks)	36	426
CS 2-9	0.6	0.9	14	0.049	-	37	2	-	-	-	-	5	6	0.5	0.5	Good	O (Cracks)	51	373
CS 2-10	1.2	0.9	8	0.024	14	34	2	-	-	-	-	5	6	0.5	0.5	Good	X	19	573
CS 2-11	1.2	0.9	8	0.024	14	34	2	-	-	-	-	7	8	0.1	0.5	Poor	-	-	-
CS 2-12	0.8	0.8	10	0.031	5	35	15	-	0.5	-	-	7	1	0.1	-	Good	X	23	497
CS 2-13	0.9	1.3	35	0.025	-	40	5	1.5	2.5	-	0.7	10	1	0.1	0.2	Good	O (Cracks, Voids)	15	494
CS 2-14	1.5	0.7	10	0.021	-	45	1.5	2.5	1.5	0.3	-	13	1	0.1	0.2	Good	O (Cracks)	31	546
IS 2-1	0.8	0.7	9	0.022	-	28	-	-	-	-	-	4.5	-	0.1	0.1	Good	X	91	362
IS 2-2	0.6	0.7	25	0.019	-	27	5	-	-	-	-	6.5	-	0.1	-	Good	X	77	385
IS 2-3	0.6	0.9	20	0.023	-	34	10	1.5	1	-	-	8	1	0.3	-	Good	X	41	523
IS 2-4	0.3	1.8	6	0.018	-	35	-	-	-	0.3	-	9	1	0.1	0.4	Good	X	42	376
IS 2-5	0.5	0.8	6	0.031	-	34	3	-	-	-	0.2	10	-	1.3	0.4	Good	X	53	448
IS 2-6	0.6	0.9	8	0.019	-	39	-	-	-	0.5	-	5	2	0.5	0.7	Good	X	41	391
IS 2-7	0.6	0.9	6	0.023	-	32	2	1	-	-	0.5	13	-	0.2	0.7	Good	X	77	498
IS 2-8	0.06	1.1	9	0.021	5	50	4	-	-	-	-	12	5	0.1	1	Good	X	44	470
IS 2-9	1.3	0.3	3	0.024	-	48	1	-	2.4	1.2	-	7.5	7	0.1	-	Good	X	33	521
IS 2-10	0.05	0.5	9	0.018	10	25	3	-	-	-	-	4.5	2	0.4	-	Good	X	87	371
IS 2-11	0.08	0.5	0.5	0.021	-	31	5	-	-	-	-	14	-	0.1	-	Good	X	98	373
IS 2-12	0.08	0.5	2	0.021	-	31	5	-	-	-	-	8	-	0.1	-	Good	X	76	382

(Note) CS: Comparative Sample, IS: Inventive Sample, and
YS: Yield Strength

Referring to Table 1, the inventive samples having alloying components according to the present disclosure had good weldability and did not have cracks or voids, and the impact toughness values of the inventive samples were 27 J or greater at an extremely low temperature of -196°C and the yield strength values of the inventive samples were 360 MPa or greater at room temperature.

However, the comparative samples were inferior to the inventive samples in at least one of the evaluation items: weldability, the presence of cracks or voids, impact toughness, and yield strength. The comparative samples were determined as not being suitable as a welding material.

[Example 3]

Submerged and gas metal arc welding materials having compositions shown in Table 4 were prepared. In Table 4, the content of each component is given in wt%.

Inventive samples and comparative samples having the same outer sheath structure and composition but different welding material compositions were prepared.

Comparative samples 3-1, 3-3, and 3-4, Inventive samples 3-1, 3-3, 3-4, 3-5, 3-6, 3-7, and 3-9 each had a single outer sheath structure formed by a high Ni steel

outer sheath. The high Ni steel outer sheath had, by wt%, nickel (Ni): 35% to 46%, other impurities: 0.05% or less, and the balance of iron (Fe). Comparative sample 3-2 and Inventive samples 3-2 and 3-8 each had a dual outer sheath structure formed by a high Ni steel outer sheath and a low carbon steel outer sheath. The high Ni steel outer sheath had, by wt%, nickel (Ni): 35% to 46%, other impurities: 0.05% or less, and the balance of iron (Fe). The low carbon steel outer sheath had, by wt%, carbon (C): 0.025% or less, manganese (Mn): 0.025% or less, and the balance of iron (Fe) and inevitable impurities.

SAW and GMAW processes were performed using each welding material.

In the SAW process, welding was performed at a heat input rate of 2.4 KJ/mm to 3.0 KJ/mm. A SAW wire having a diameter of 4.0 mm was used.

In the GMAW process, welding was performed at a heat input rate of 1.7 KJ/mm under conditions of 80% Ar + 20% CO₂. A GMAW wire having a diameter of 1.2 mm was used.

Thereafter, the presence of cracks or voids in welded joints, impact toughness at -196°C, and yield strength were observed or measured, and results of the observation or measurement are shown in Table 4. In table 4, impact toughness values (CVN) are given in joules (J), and yield

strength values are given in MPa. In addition, components written using the symbol "+" indicate that at least one selected from the components is included in the samples.

[Table 4]

NO.	C	Si	Mn	P+S	Cr	Ni	Mo+W+Co	Al	Nb+V	N	Cracks Voids	CVN _{10-19°C} (SI/FTL)	Yield strength (SI/FTL)
CS 3-1	0.02	0.7	0.5	0.016	-	23	-	-	-	-	X	109/121	313/323
CS 3-2	0.05	0.7	2	0.03	-	51	-	-	-	-	X	98/112	244/264
CS 3-3	0.5	0.6	15	0.01	-	24	-	-	-	-	X	112/124	342/352
CS 3-4	0.8	0.25	5	0.01	-	28	12	-	1.8	0.7	0 (Voids)	20/21	558/582
IS 3-1	0.35	0.5	7	0.03	5.5	33	0.5	-	-	-	X	39/45	439/451
IS 3-2	0.9	0.7	3	0.01	-	35	-	-	-	-	X	63/73	378/394
IS 3-3	0.05	1.2	8	0.01	2	39	5	-	0.5	0.5	X	32/46	452/472
IS 3-4	0.3	0.5	6	0.01	3	43	-	-	-	-	X	83/94	392/403
IS 3-5	0.7	0.3	6	0.015	-	25	-	-	-	-	X	89/94	382/402
IS 3-6	0.5	0.49	11	0.01	-	35	4	-	-	0.01	X	65/73	436/442
IS 3-7	1.2	0.6	10	0.03	-	35	-	1.5	-	-	X	33/36	453/487
IS 3-8	0.1	0.55	5	0.01	-	45	6	-	1.5	-	X	64/71	461/471
IS 3-9	0.8	0.33	15	0.015	-	25	1.5	0.2	-	-	X	39/43	445/465

(Note) CS: Comparative Sample, and IS: Inventive Sample

Referring to Table 4, the inventive samples having alloying components according to the present disclosure had good weldability and did not have cracks or voids, and the impact toughness values of the inventive samples were 27 J or greater at an extremely low temperature of -196°C and the yield strength values of the inventive samples were 360 MPa or greater at room temperature.

However, the comparative samples were inferior to the inventive sample in at least one selected of the evaluation items: the presence of cracks or voids, impact toughness, and yield strength. The comparative samples were determined as not being suitable as a welding material.

【CLAIMS】**【Claim 1】**

A welded joint of extremely low temperature steel, the welded joint comprising, by wt%, carbon (C): 0.05% to 1.30%, silicon (Si): 0.2% to 1.8%, manganese (Mn): 0.4% to 23%, chromium (Cr): 0.01% or more to less than 12%, nickel (Ni): 23% to 49%, at least one selected from molybdenum (Mo), cobalt (Co), and tungsten (W): 0.01% to 10%, aluminum (Al): 0.2% or less, and excluding 0%, titanium (Ti): 0.9% or less, and excluding 0%, at least one selected from niobium (Nb) and vanadium (V): 0.9% or less, and excluding 0%, at least one selected from sulfur (S) and phosphorus (P): 0.035% or less, and excluding 0%, and the balance of iron (Fe) and inevitable impurities.

【Claim 2】

The welded joint of claim 1, further comprising, by wt%, one or more of nitrogen (N): 0.001% to 0.6% and boron (B): 0.0001% to 0.008%.

【Claim 3】

The welded joint of claim 1 or 2, wherein the at least

one selected from molybdenum (Mo), cobalt (Co), and tungsten (W) (expressed as "Mo+W+Co"), the at least one selected from niobium (Nb) and vanadium (V) (expressed as "Nb+V"), and the nickel (Ni), chromium (Cr), aluminum (Al), and titanium (Ti) satisfy Formula 1 below:

$$\begin{aligned} & \text{(Formula 1)} \quad 1.5\text{Ni} - 8\text{Cr} - 2.5(\text{Mo}+\text{W}+\text{Co}) - 20\text{Al} - 29\text{Ti} - \\ & 55(\text{Nb}+\text{V}) \geq 0 \end{aligned}$$

【Claim 4】

The welded joint of claim 1 or 2, wherein the at least one selected from molybdenum (Mo), cobalt (Co), and tungsten (W) (expressed as "Mo+W+Co"), the at least one selected from niobium (Nb) and vanadium (V) (expressed as "Nb+V"), and the nickel (Ni), chromium (Cr), aluminum (Al), and titanium (Ti) satisfy Formula 2 below:

$$\begin{aligned} & \text{(Formula 2)} \quad 98.5\text{C} - 1.08\text{Mn} + 9.73\text{Cr} - 1.52\text{Ni} + \\ & 10.3(\text{Mo}+\text{W}+\text{Co}) + 122\text{Ti} + 34.7(\text{Nb}+\text{V}) \geq 0 \end{aligned}$$

【Claim 5】

The welded joint of claim 1 or 2, wherein the silicon (Si), aluminum (Al), and titanium (Ti) satisfy Formula 3 below:

$$\text{(Formula 3)} \quad \text{Si}+\text{Al}+\text{Ti} \leq 2.0$$

【Claim 6】


The welded joint of claim 1 or 2, wherein the welded joint has an impact toughness of 27 J or greater at an extremely low temperature of -196°C.

【Claim 7】


The welded joint of claim 1 or 2, wherein the welded joint has a yield strength of 360 MPa or greater at room temperature.

【DRAWINGS】

【Figure 1】



【Figure 2】



【Figure 3】

