



(86) Date de dépôt PCT/PCT Filing Date: 2005/04/28
(87) Date publication PCT/PCT Publication Date: 2005/12/01
(45) Date de délivrance/Issue Date: 2012/08/21
(85) Entrée phase nationale/National Entry: 2006/11/09
(86) N° demande PCT/PCT Application No.: EP 2005/004534
(87) N° publication PCT/PCT Publication No.: 2005/113152
(30) Priorité/Priority: 2004/05/10 (DE10 2004 022 925.2)


(51) Cl.Int./Int.Cl. *B03D 1/008* (2006.01),
B03D 1/01 (2006.01), *C07D 215/26* (2006.01)

(72) Inventeurs/Inventors:
HESSE, HEINRICH, DE;
RAU, TOBIAS, DE;
BUCH, WOLFGANG, DE;
GOMEZ, JAIME, CL;
ARENDS, MIGUEL ANGEL, CL;
ERNSTORFER, NORBERT, CL

(73) Propriétaire/Owner:
CLARIANT PRODUKTE (DEUTSCHLAND) GMBH, DE

(74) Agent: FETHERSTONHAUGH & CO.

(54) Titre : COLLECTEUR POUR MINERAIS SULFURES
(54) Title: COLLECTOR FOR SULFIDIC ORES



(1)

(57) Abrégé/Abstract:

The invention relates to a flotation reagent for sulfidic ores, containing at least one compound of formula (I), wherein R², R³, R⁴, R⁵, R⁶ and R⁷, independent of one another, represent hydrogen or groups containing 1 to 15 carbon atoms or groups containing oxygen or nitrogen, and at least another compound serving as collector and containing at least one sulfur atom that is directly bound to a carbon or phosphorus atom, wherein said carbon or phosphorus atom is directly bound to at least another sulfur atom or to an oxygen atom.

(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES
PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG(19) Weltorganisation für geistiges Eigentum
Internationales Büro(43) Internationales Veröffentlichungsdatum
1. Dezember 2005 (01.12.2005)

PCT

(10) Internationale Veröffentlichungsnummer
WO 2005/113152 A1(51) Internationale Patentklassifikation⁷: **B03D 1/008**,
1/01, C07D 215/26(74) **Anwalt: MIKULECKY, Klaus**; Clariant GmbH, Am
Unisys-Park 1, 65843 Sulzbach (DE).

(21) Internationales Aktenzeichen: PCT/EP2005/004534


(22) Internationales Anmeldedatum:
28. April 2005 (28.04.2005)

(25) Einreichungssprache: Deutsch

(26) Veröffentlichungssprache: Deutsch

(30) Angaben zur Priorität:
10 2004 022 925.2 10. Mai 2004 (10.05.2004) DE(71) **Anmelder (für alle Bestimmungsstaaten mit Ausnahme von
US): CLARIANT GMBH** [DE/DE]; Brüningstrasse 50,
65929 Frankfurt am Main (DE).(72) **Erfinder; und**(75) **Erfinder/Anmelder (nur für US): HESSE, Heinrich**
[DE/DE]; Mainzer Landstrasse 84, 65795 Hattersheim
(DE). **RAU, Tobias** [DE/DE]; An der Hechtsheimer Höhe
4c, 55130 Mainz (DE). **BUCH, Wolfgang** [DE/DE];
Merziger Weg 28, 60529 Frankfurt am Main (DE).
GOMEZ, Jaime [CL/CL]; Santa Elena 221 Maipu, San-
tiago de Chile (CL). **ARENDs, Miguel Angel** [CL/CL];
Los Juncos 272 Las Condes, Santiago de Chile (CL).
ERNSTORFER, Norbert [DE/CL]; Benito Perez Galdos
2093 Reina, Santiago de Chile (CL).(81) **Bestimmungsstaaten (soweit nicht anders angegeben, für
jede verfügbare nationale Schutzrechtsart):** AE, AG, AL,
AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH,
CN, CO, CR, CU, CZ, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA,
MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM,
PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY,
TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU,
ZA, ZM, ZW.(84) **Bestimmungsstaaten (soweit nicht anders angegeben, für
jede verfügbare regionale Schutzrechtsart):** ARIPO (BW,
GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG,
ZM, ZW), eurasisches (AM, AZ, BY, KG, KZ, MD, RU,
TJ, TM), europäisches (AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL,
PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI,
CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).**Veröffentlicht:**

— mit internationalem Recherchenbericht

*Zur Erklärung der Zweibuchstaben-Codes und der anderen Ab-
kürzungen wird auf die Erklärungen ("Guidance Notes on Co-
des and Abbreviations") am Anfang jeder regulären Ausgabe der
PCT-Gazette verwiesen.*(54) **Title:** COLLECTOR FOR SULFIDIC ORES(54) **Bezeichnung:** SAMMLER FÜR SULFIDISCHE ERZE

(I)

(57) **Abstract:** The invention relates to a flotation reagent for sulfidic ores, containing at least one compound of formula (I), wherein R², R³, R⁴, R⁵, R⁶ and R⁷, independent of one another, represent hydrogen or groups containing 1 to 15 carbon atoms or groups containing oxygen or nitrogen, and at least another compound serving as collector and containing at least one sulfur atom that is directly bound to a carbon or phosphorus atom, wherein said carbon or phosphorus atom is directly bound to at least another sulfur atom or to an oxygen atom.(57) **Zusammenfassung:** Gegenstand der Erfindung ist ein Flotationsreagenz für sulfidische Erze, enthaltend mindestens eine Verbindung der Formel (I), worin R², R³, R⁴, R⁵, R⁶ und R⁷ unabhängig voneinander Wasserstoff oder Gruppen enthaltend 1 bis 15 Kohlenstoffatome oder Gruppen enthaltend Sauerstoff oder Stickstoff sind, und mindestens eine weitere, als Sammler dienende Verbindung, welche wenigstens ein Schwefelatom enthält, das direkt an ein Kohlenstoff- oder Phosphoratom gebunden ist, und wobei dieses Kohlenstoff oder Phosphoratom an wenigstens ein weiteres Schwefelatom oder an ein Sauerstoffatom direkt gebunden ist.

WO 2005/113152 A1

29374-470

1

Collector for sulfidic ores

- 10 The present invention relates to the use of collectors in the dressing of sulfidic ores by flotation.

In the production by flotation of sulfidic ores, in particular copper ores or molybdenum ores, use is made commercially of various collector types,
15 such as dithiophosphates, xanthates, xanthogen formates, and thionocarbamates (Schubert: Aufbereitung fester mineralischer Rohstoffe [Dressing of solid mineral raw materials], volume II, 1977, pp. 296 ff.) and also their mixtures in combination with frothers. The flotation process separates, for example, copper and molybdenum sulfides from gangue
20 minerals.

Collectors cause wetting of the surface of the mineral of value which leads to hydrophobization of the mineral particles. Injecting air into the aqueous flotation pulp produces air bubbles to which the hydrophobized mineral
25 particles adhere and are discharged by these to the surface of the flotation pulp. The suspended mineral of value, termed concentrate, is skimmed off, while gangue minerals remain in the pulp.

Frothers are added to modify the foam formation. Commercially
30 conventional frothers include, for example, alcohols, polypropylene glycols, and also their ethers and MIBC (methyl isobutyl carbinol).

US-4 699 711 discloses a method for the flotation of sulfide minerals using preferably short-chain alkyl-substituted thionocarbamates.
35

WO-02/38277 discloses the use of mixtures of thionocarbamates and mercaptobenzothiazoles as collectors for the flotation of sulfidic ores, in particular copper ore which is associated with molybdenum and gold.

GB-A-798 769 and US-A-4 178 235 describe the flotation of niobium minerals using 8-quinolinol and 5-hydroxyquinolin, respectively. GB-A-826 827 describes, in addition to 8-quinolinol, alkyl-substituted 8-quinolinol derivatives for the flotation of niobium minerals.

5

8-Quinolinol has a high affinity to metal ions and forms complexes with these, termed oxinates. 8-Quinolinol is therefore also used as precipitation reagent for various metal ions.

10 GB-A 887 469 describes a method for recovering 8-quinolinol after use.

When pyrite-containing ores are dressed by flotation at pHs below 10 using commercially conventional sulfidic collectors such as dialkyl dithiophosphates, xanthates, dialkyl xanthoformates or dialkyl thionocarbamates, concentrates having relatively high pyrite concentrations are obtained. In this case the dialkyl thionocarbamates are even considered as very selective in relation to pyrite in comparison with xanthates and dithiophosphates.

20 This high pyrite fraction, has an adverse consequence in the subsequent further processing of the concentrate. Firstly, the efficacy of the reduction process is decreased, and high amounts of sulfur oxides are formed which pollute the environment, or their disposal gives rise to high costs.

25 To decrease the pyrite fraction in the concentrate, and increase the content of mineral of value, lime is added to the flotation pulp which, depending on the amount, raises the pH of the flotation pulp to above 10. The amounts of added lime vary, depending on pyrite content, between 0 and several kg per tonne of ore feed. The lime thus substantially contributes to the reagent costs of the flotation process. A reduction in the amount of lime and decrease in pH to below 10 would therefore not only contribute to reducing the sulfur oxide emissions to the environment, but also would be accompanied by a saving in reagent costs.


30
35 It was an object of the present invention to find an improved collector type for sulfidic ores which yields better flotation results than collectors of the prior art. It is additionally an object of the invention to reduce the required amounts of pH modifiers, in particular lime, which is used for pH elevation and for lowering pyrite.

29374-470

3

Surprisingly, it has been found that using 8-hydroxyquinolinol derivatives in combination with conventional collectors in the flotation of sulfidic ores causes a marked improvement in the flotation results. In particular, by
5 combining 8-quinolinol with conventional collectors, a marked improvement in the flotation of pyrite-containing copper ores was achieved. Especially in combination with thionocarbamates, a marked improvement in the flotation of copper ore using 8-quinolinol was established.

10 The invention thus relates to a flotation reagent for sulfidic ores, which flotation reagent comprises at least one compound of the formula (I)




15 where R^2 , R^3 , R^4 , R^5 , R^6 and R^7 , independently of one another are hydrogen or groups comprising 1 to 15 carbon atoms, or groups comprising oxygen or nitrogen, and at least one further compound acting as collector for sulfidic ores.

29374-470

3a

According to one aspect of the present invention, there is provided a flotation reagent for sulfidic ores, which flotation reagent comprises a compound of the formula (1)



where R^2 , R^3 , R^4 , R^5 , R^6 and R^7 , independently of one another are hydrogen or groups comprising 1 to 15 carbon atoms, or groups comprising oxygen or nitrogen, and at least one further compound acting as a collector for sulfidic ores which comprises at least one sulfur atom which is directly bound to a carbon or phosphorus atom, and this carbon or phosphorus atom being directly bound to at least one further sulfur atom or a nitrogen atom or an oxygen atom, the mixing ratio of the compounds of the formula 1 to the further collectors being 0.1:99.9 to 20:80.

Preferably, the collector for sulfidic ores is a compound which comprises at least one sulfur atom which is directly bound to a carbon or phosphorus atom, and this carbon or phosphorous atom being directly bound to at least one further sulfur atom or to a nitrogen atom, or to an oxygen atom.

The invention further relates to the use of the inventive flotation reagent for the flotation of sulfidic ores.

According to another aspect of the present invention, there is provided a use of the flotation reagent described herein, in amounts of 0.001 to 1.0 kg per tonne of crude ore for the flotation of sulfidic ores and metals.

The invention further relates to a method for the flotation of sulfidic ores by bringing the inventive flotation reagent into contact with the sulfidic ores.

The invention further relates to the use of compounds of the formula 1 as additive to collectors for sulfidic ores.



Using the inventive flotation reagent, in the flotation of metal sulfides, improved results in selectivity and yield can be achieved compared with standard collectors. The properties of the further collector which are
 5 already selective in relation to pyrite can be further significantly improved by using compounds of the formula (I). In particular, ores which have a high pyrite fraction and are customarily flotated at a pH above 10 can be flotated even at pHs of 7 to 10, for example at pH 8.5 to 9.0. In this case the co-
 10 flotated pyrite fraction in the resultant concentrate is markedly lower than using currently available collectors at the same pH, or the mineral value content is higher.

The sulfidic ores are preferably copper-containing ores which have pyrite fractions up to 90% by weight.



15 It is possible to flotote all metal sulfides and metals (apart from Fe), with Cu, Mo, Pb, Zn, Co, Au, Ag, Pt and Ni being particularly preferred. Particularly good results are observed in the dressing of Cu and Mo. The inventive flotation reagent can be used in a wide pH range, for example 2
 20 to 12, preferably 5 to 12, and is added to the aqueous pulp at a concentration preferably between 0.001 and 1.0 kg/tonne of crude ore.

The compounds of the formula (1), in a preferred embodiment, are those where R^2 , R^3 , R^4 , R^5 , R^6 and R^7 independently of one another are H or C_1 -
 25 to C_4 -alkyl, in particular all H.

The further collectors, in preferred embodiments, are those compounds which structural units of the formulae




5




where the free valencies are saturated by organic radicals or sulfur atoms.


- 5 In particularly preferred embodiments, the further collectors are dithiophosphates of the formula (6)



- 10 or xanthates of the formula (7)




or xanthogen formates of the formula (8)




15

or thionocarbamates of the formula 9

6



or mercaptobenzothiazoles of the formula 10



5

where

R^8 and R^9 independently of one another are hydrocarbon radicals having 1 to 10 carbon atoms, in particular C_1 - to C_{10} -alkyl, C_1 - to C_{10} -alkenyl, C_1 - to C_5 -alkyl, C_1 - to C_5 -alkenyl, phenyl, benzyl or naphthyl, and

10 M^+ is a cation, in particular a metal ion or an ammonium ion.

The mixing ratio of the compounds of the formula 1 to the further collectors which are represented by the formulae 2 to 10 is preferably 0.1:99.9 to 20:80, in particular 1:99 to 10:90. In a preferred embodiment, the inventive
15 flotation reagent comprises between 0.1 and 20% by weight of 8-quinolinol.

Using the inventive flotation reagent, a significant improvement of yield and selectivity are achieved compared with the collectors of the prior art. Examples 1 to 6 clearly show that the yield of copper and molybdenum is
20 higher than using the corresponding standard reagent.

By using the inventive reagent together with a thionocarbamate, at pHs between 8.5 and 10.5, copper concentrates having 5 to 9% higher copper concentrations are obtained than using a conventional thionocarbamate.
25 The copper yield is also significantly improved between 0.9 and 2.4 percentage points.

Examples:

30 The table below shows the flotation results of the inventive collector compared with the standard reagent. Laboratory flotation experiments were carried out on a Chilean copper ore. As standard reagent (comparative

examples 4 to 6), use was made of an ethylthio, O-isopropylthiono carbamate and a dosage of 14 g/t of crude ore feed. A commercially conventional frother (MIBC) was added at a dosage of 15 g/t of ore feed. The invention is shown in the examples (examples 1 to 3). It corresponds to the 94.4% strength ethylthio-, O-isopropoylthionocarbamate at an addition of 5.6% 8-quinolinol. The resultant values for the copper content and the yield are means in each case of three individual flotations.

Table 1: Efficacy of the inventive collectors compared with the prior art

Example	pH	Content of Cu, %	Yield of Cu, %
1	8.5	10.8	93.4
2	9.5	11.1	92.8
3	10.5	11.2	92.2
4 (C)	8.5	9.9	91.0
5 (C)	9.5	10.3	91.6
6 (C)	10.5	10.7	91.3


The results show a generally increased percentage yield and also a higher content of Cu due to the inventive flotation reagent.

29374-470

8




CLAIMS:

1. A flotation reagent for sulfidic ores, which flotation reagent comprises a compound of the formula (1)



- 5 where R^2 , R^3 , R^4 , R^5 , R^6 and R^7 , independently of one another are hydrogen or groups comprising 1 to 15 carbon atoms, or groups comprising oxygen or nitrogen, and at least one further compound acting as a collector for sulfidic ores which comprises at least one sulfur atom which is directly bound to a carbon or phosphorus atom, and this carbon or phosphorus atom being directly bound to at least one further
- 10 sulfur atom or a nitrogen atom or an oxygen atom, the mixing ratio of the compounds of the formula 1 to the further collectors being 0.1:99.9 to 20:80.

2. The flotation reagent as claimed in claim 1, wherein the further collector is selected from compounds which comprise structural units of the formulae




29374-470

9

where the freevalencies are saturated by organic radicals or sulfur atoms.


3. The flotation reagent as claimed in claim 2, wherein the further collector is selected from dithiophosphates of the formula 6




5 or xanthates of the formula (7)



or xanthogen formates of the formula 8




or thionocarbamates of the formula 9



10

or mercaptobenzothiazoles of the formula 10



where


R^8 and R^9 independently of one another are hydrocarbon radicals having 1 to 10 carbon atoms, in particular C_1 to C_{10} -alkyl, C_1 - to C_{10} -alkenyl, C_1 - to C_5 -alkyl, C_1 - to C_5 -alkenyl, phenyl, benzyl or naphthyl, and

29374-470


10

M^+ is a cation.

4. The flotation reagent as claimed in claim 3, wherein M^+ is a metal ion or an ammonium ion.
5. The flotation reagent as claimed in claim 1, comprising 8-quinolinol.
- 5 6. A use of the flotation reagent as claimed in any one of claims 1 to 5, in amounts of 0.001 to 1.0 kg per tonne of crude ore for the flotation of sulfidic ores and metals.
7. The use as claimed in claim 6, wherein the sulfidic ore is copper sulfide, nickel sulfide, zinc sulfide, lead sulfide or molybdenum sulfide.
- 10 8. The use as claimed in claim 5 or 6 in the flotation of sulfidic ores, wherein the sulfidic ore comprises between 0 and 90% pyrite.
9. The use as claimed in any one of claims 6 to 8 for the flotation of copper ores.
10. The use as claimed in any one of claims 6 to 9 in a pH range of 7 to 10.
- 15 11. A use of a compound of the formula 1



where R^2 , R^3 , R^4 , R^5 , R^6 and R^7 independently of one another are hydrogen or groups comprising 1 to 15 carbon atoms or groups comprising oxygen or nitrogen, as additive for collectors for sulfidic ores.



(1)