

(19) DANMARK



(10) DK/EP 3384903 T3

(12)

Oversættelse af
europæisk patentskrift

Patent- og
Varemærkestyrelsen

(51) Int.Cl.: **A 61 K 9/50 (2006.01)**
A 61 P 27/02 (2006.01) **A 61 K 38/17 (2006.01)**
A 61 K 9/16 (2006.01) **A 61 K 39/00 (2006.01)**

(45) Oversættelsen bekendtgjort den: **2020-07-20**

(80) Dato for Den Europæiske Patentmyndigheds
bekendtgørelse om meddelelse af patentet: **2020-05-27**

(86) Europæisk ansøgning nr.: **18173299.1**

(86) Europæisk indleveringsdag: **2012-11-18**

(87) Den europæiske ansøgnings publiceringsdag: **2018-10-10**

(30) Prioritet: **2011-11-18 US 201161561525 P**

(62) Stamansøgningsnr: **12795967.4**

(84) Designerede stater: **AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR**

(73) Patenthaver: **Regeneron Pharmaceuticals, Inc., 777 Old Saw Mill River Road, Tarrytown, NY 10591-6707, USA**

(72) Opfinder: **CHEN, Hunter, 777 Old Saw Mill River Road, Tarrytown, NY New York 10591, USA**
WALSH, Scott, 777 Old Saw Mill River Road, Tarrytown, NY New York 10591, USA

(74) Fuldmægtig i Danmark: **Zacco Denmark A/S, Arne Jacobsens Allé 15, 2300 København S, Danmark**

(54) Benævnelse: **Mikropartikelholdigt terapeutisk protein coatet med biologisk nedbrydelig polymer til medicinsk anvendelse**

(56) Fremdragne publikationer:
WO-A2-03/092665
US-A1- 2008 305 115
US-A1- 2011 104 151
KIM B S ET AL: "BSA-FITC-loaded microcapsules for in vivo delivery", BIOMATERIALS, ELSEVIER SCIENCE PUBLISHERS BV., BARKING, GB, vol. 30, no. 5, 22 November 2008 (2008-11-22), - February 2009 (2009-02), pages 902-909, XP025801484, ISSN: 0142-9612, DOI: 10.1016/J.BIOMATERIALS.2008.10.030 [retrieved on 2008-11-22]

DK/EP 3384903 T3

DESCRIPTION

FIELD

[0001] The invention relates to the manufacture, composition, and use of an extended release protein therapeutic. Specifically, the invention relates to the manufacture, composition, and use of a plurality of polymer coated protein microspheres for the extended and uniform release of protein in an aqueous-based or physiological environment over time. In particular, the present invention relates to an extended release formulation.

BACKGROUND

[0002] The extended release of a therapeutic protein administered toward a biological target, such as e.g., the retina or a tumor, or administered parenterally is desirable for the treatment of many different conditions, including cancers, cardiovascular diseases, vascular conditions, orthopedic disorders, dental disorders, wounds, autoimmune diseases, gastrointestinal disorders, and ocular diseases. Biocompatible and biodegradable polymers for the controlled and extended delivery of drugs have been in use for decades. As the polymer degrades over time, the therapeutic drug is slowly released.

[0003] In the case of intraocular therapeutics, there is a significant unmet medical need for extended release formulations to deliver protein therapeutics effectively over time with as few intraocular injections as possible. In the case of other diseases, such as cancer, diseases of inflammation, and other diseases, there is a need for improved implantable extended release formulations containing protein therapeutics.

[0004] Applicants have discovered and herein disclose and claim methods of manufacturing and using microparticles containing a biodegradable polymer and a therapeutic protein, which is capable of releasing a therapeutically effective amount of the therapeutic protein uniformly over an extended period of time.

[0005] The following documents are also referred to:

- US 2011/104151 which is concerned with microparticle compositions and methods for treating age-related macular degeneration;
- US 2008/305115 which is concerned with reduced-mass, long-acting dosage forms;
- WO 03/092665 which is concerned with ocular delivery systems and uses thereof; and
- Kim et al (2009) *Biomaterials* 30(5): 902-909 which is concerned with BSA_FITC-loaded microcapsules for *in vivo* delivery.

SUMMARY

[0006] The present invention provides an extended release pharmaceutical formulation for use in the vitreous for the treatment of vascular eye disorders, the pharmaceutical formulation comprising microparticles having a diameter of from 2 microns to 70 microns, the microparticles having a protein particle core within a polymer cortex, the protein particle containing less than 3% water by weight, wherein the microparticles release the protein in a physiological aqueous environment at about 37°C at a rate of from about 0.01 mg/week to about 0.30 mg/week over at least 60 days.

[0007] Also disclosed is a microparticle comprising a protein coated with a polymer. In one instance, the microparticle has a diameter of from about 2 microns to about 70 microns. In one instance, the microparticle has a diameter of about 15 microns.

[0008] In one instance, the protein is an antigen-binding protein. In one instance, the protein comprises an Fc domain. In one instance, the protein comprises a receptor domain. In one instance, the protein is an antibody. In another instance, the protein is a receptor-Fc-fusion protein. In another instance, the protein is a trap-type protein, which comprises a cognate-receptor fragment and an Fc domain. In one particular instance, the protein is a VEGF-Trap protein. In one instance, the VEGF-Trap protein comprises an amino acid sequence set forth in SEQ ID NO:1.

[0009] In one instance, the polymer is a biodegradable polymer. In some instances, the polymer is selected from the group consisting of polylactic acid (PLA), polyglycolic acid (PGA), polylactic-polyglycolic copolymer (PLGA), poly-D,L-lactide-co-glycolide (PLGA), PLGA-ethylene oxide fumarate, PLGA-alpha-tocopheryl succinate esterified to polyethylene glycol 1000 (PLGA-TGPS), polyanhydride poly[1,6-bis(p-carboxyphenoxy)hexane] (pCPH), poly(hydroxbutyric acid-cohydroxyvaleric acid) (PHB-PVA), polyethylene glycol-poly (lactic acid) copolymer (PEG-PLA), poly- ϵ -caprolactone (PCL), poly-alkyl-cyano-acrylate (PAC), poly(ethyl)cyanoacrylate (PEC), polyisobutyl cyanoacrylate, poly-*N*-(2-hydroxypropyl)methacrylamide (poly(HPMA)), poly- β -R-hydroxy butyrate (PHB), poly- β -R-hydroxy alcanoate (PHA), poly- β -R-malic acid, phospholipid-cholesterol polymers, 2-dioleoyl-sn-glycero-3-phosphatidylcholine/ polyethyleneglycol-distearoylphosphatidylethanolamine (DOPC/PEG-DSPE)/Cholesterol, polysaccharides, cellulose, ethyl cellulose, methyl cellulose, alginates, dextran and dextran hydrogel polymers, amylose, inulin, pectin and guar gum, chitosan, chitin, heparin, hyaluronic acid, cyclodextrin (CD)-based polyrotaxanes and polypseudorotaxanes, polyaspartates, polyglutamates, polylysine, leucine-glutamate copolymers, polybutylene succinate (PBS), gelatin, collagens, fibrins, fibroin, polyorthoesters, polyorthoester-polyamidine copolymer, polyorthoester-diamine copolymers, polyorthoesters incorporating latent acids, poly(ethylene glycol)/poly(butylene terephthalate) copolymer, and combinations and copolymers thereof. In one embodiment, the polymer is poly- ϵ -caprolactone (PCL) or a derivative or copolymer thereof. In one embodiment, the polymer is PLGA or a

derivative or copolymer thereof. In one embodiment, the polymer is ethyl cellulose or a derivative or copolymer thereof. In one embodiment, the polymer is polyorthoester or a derivative or copolymer thereof.

[0010] In one instance, the microparticle comprises a micronized protein core of less than ten microns and a polymer cortex. In one instance, the micronized protein core is at least 50% coated with polymer, which means that no more than 50% of the surface of the micronized protein core is exposed. In one embodiment, at least 60%, at least 70%, at least 80%, at least 90%, at least 95%, at least 99%, or 100% of the surface of the micronized protein core is coated with polymer.

[0011] In one instance, the microparticle of greater than 10 microns in size comprises (a) a micronized protein core of less than 10 microns, wherein the protein is any one or more of an antibody or antibody fragment, a receptor or soluble fragment thereof, a soluble T-cell receptor fragment, a soluble MHC fragment, a receptor-Fc-fusion protein, a trap-type protein, and a VEGF-Trap protein; and (b) a polymer coat, wherein the polymer is any one or more of a biocompatible polymer, a biodegradable polymer, a bio-erodible polymer, polylactic acid (PLA), polyglycolic acid (PGA), polylactic-polyglycolic copolymer (PLGA), poly-D,L-lactide-co-glycolide (PLGA), PLGA-ethylene oxide fumarate, PLGA-alpha-tocopheryl succinate esterified to polyethylene glycol 1000 (PLGA-TGPS), polyanhydride poly[1,6-bis(p-carboxyphenoxy)hexane] (pCPH), poly(hydroxybutyric acid-cohydroxyvaleric acid) (PHB-PVA), polyethylene glycol-poly (lactic acid) copolymer (PEG-PLA), poly- ϵ -caprolactone (PCL), poly-alkyl-cyano-acrylate (PAC), poly(ethyl)cyanoacrylate (PEC), polyisobutyl cyanoacrylate, poly-*N*-(2-hydroxypropyl)methacrylamide (poly(HPMA)), poly- β -R-hydroxy butyrate (PHB), poly- β -R-hydroxy alkanoate (PHA), poly- β -R-malic acid, phospholipid-cholesterol polymers, 2-dioleoyl-sn-glycero-3-phosphatidylcholine/ polyethyleneglycol-distearoylphosphatidylethanolamine (DOPC/PEG-DSPE)/Cholesterol, polysaccharides, cellulose, ethyl cellulose, methyl cellulose, alginates, dextran and dextran hydrogel polymers, amylose, inulin, pectin and guar gum, chitosan, chitin, heparin, hyaluronic acid, cyclodextrin (CD)-based polyrotaxanes and polypseudorotaxanes, polyaspartates, polyglutamates, polylysine, leucine-glutamate copolymers, polybutylene succinate (PBS), gelatin, collagens, fibrins, fibroin, polyorthoesters, polyorthoester-polyamidine copolymer, polyorthoester-diamine copolymers, polyorthoesters incorporating latent acids, poly(ethylene glycol)/poly(butylene terephthalate) copolymer, and combinations and copolymers thereof.

[0012] In one instance, the microparticle of an average diameter of about 15 microns to about 30 microns comprises (a) a micronized protein core of about 10 to about 12 microns, wherein the protein is a VEGF-Trap protein; and (b) a polymer coat, wherein the polymer is any one or more of PCL, PLGA, ethyl cellulose and polyorthoester, and copolymers or derivatives thereof.

[0013] Also disclosed is a plurality of microparticles, which range in size from about two microns to about 70 microns, and which comprise a micronized protein core of about two microns to about 30 microns, and a polymer cortex.

[0014] In one instance, the protein is an antigen-binding protein. In some instances, the antigen-binding protein is any one or more of an antibody or antibody fragment, a receptor or soluble fragment thereof, a soluble T-cell receptor fragment, a soluble MHC fragment, a receptor-Fc-fusion protein, a trap-type protein, and a VEGF-Trap protein. In one instance, the protein comprises an Fc domain. In one instance, the protein is an antibody. In another instance, the protein is a receptor-Fc-fusion protein. In another instance, the protein is a trap-type protein, which comprises a cognate-receptor fragment and an Fc domain. In one particular instance, the protein is a VEGF-Trap protein. In a specific instance, the VEGF-Trap protein comprises the amino acid sequence set forth in SEQ ID NO:1.

[0015] In one instance, the polymer is a biocompatible polymer. In one instance, the polymer is a bioerodible polymer. In one instance, the polymer is a biodegradable polymer. In some instances, the polymer is selected from the group consisting of polylactic acid (PLA), polyglycolic acid (PGA), polylactic-polyglycolic copolymer (PLGA), poly-D,L-lactide-co-glycolide (PLGA), PLGA-ethylene oxide fumarate, PLGA-alpha-tocopheryl succinate esterified to polyethylene glycol 1000 (PLGA-TGPS), polyanhydride poly[1,6-bis(p-carboxyphenoxy)hexane] (pCPH), poly(hydroxybutyric acid-cohydroxyvaleric acid) (PHB-PVA), polyethylene glycol-poly (lactic acid) copolymer (PEG-PLA), poly- ϵ -caprolactone (PCL), poly-alkyl-cyano-acrylate (PAC), poly(ethyl)cyanoacrylate (PEC), polyisobutyl cyanoacrylate, poly-N-(2-hydroxypropyl)methacrylamide (poly(HPMA)), poly- β -R-hydroxy butyrate (PHB), poly- β -R-hydroxy alkanoate (PHA), poly- β -R-malic acid, phospholipid-cholesterol polymers, 2-dioleoyl-sn-glycero-3-phosphatidylcholine/ polyethyleneglycol-distearoylphosphatidylethanolamine (DOPC/PEG-DSPE)/Cholesterol, polysaccharides, cellulose, ethyl cellulose, methyl cellulose, alginates, dextran and dextran hydrogel polymers, amylose, inulin, pectin and guar gum, chitosan, chitin, heparin, hyaluronic acid, cyclodextrin (CD)-based polyrotaxanes and polypseudorotaxanes, polyaspartates, polyglutamates, polylysine, leucine-glutamate copolymers, polybutylene succinate (PBS), gelatin, collagens, fibrins, fibroin, polyorthoesters, polyorthoester-polyamidine copolymer, polyorthoester-diamine copolymers, polyorthoesters incorporating latent acids, poly(ethylene glycol)/poly(butylene terephthalate) copolymer, and combinations and copolymers thereof. In one instance, the polymer is poly- ϵ -caprolactone (PCL) or a derivative or copolymer thereof. In one instance, the polymer is PLGA or a derivative or copolymer thereof. In one instance, the polymer is ethyl cellulose or a derivative or copolymer thereof. In one instance, the polymer is a polyorthoester incorporating a latent acid.

[0016] In one instance, the micronized protein core of most microparticles of the plurality of microparticles is at least 50% coated with polymer, which means that no more than 50% of the surface of the micronized protein core is exposed. In one instance, at least 60%, at least 70%, at least 80%, at least 90%, at least 95%, at least 99%, or 100% of the surface of the micronized protein core is coated with polymer.

[0017] In one instance, the plurality of microparticles, which range in size from about two microns to about 70 microns, comprise (a) a micronized protein core of from about two microns to about 30 microns, wherein the protein is any one or more of an antibody or

antibody fragment, a receptor or soluble fragment thereof, a soluble T-cell receptor fragment, a soluble MHC fragment, a receptor-Fc-fusion protein, a trap-type protein, and a VEGF-Trap protein; and (b) a polymer cortex, wherein the polymer is any one or more of a biocompatible polymer, a biodegradable polymer, a bio-erodible polymer, polylactic acid (PLA), polyglycolic acid (PGA), polylactic-polyglycolic copolymer (PLGA), poly-D,L-lactide-co-glycolide (PLGA), PLGA-ethylene oxide fumarate, PLGA-alpha-tocopheryl succinate esterified to polyethylene glycol 1000 (PLGA-TGPS), poly- ϵ -caprolactone (PCL), poly-alkyl-cyano-acrylate (polyanhydride poly[1,6-bis(p-carboxyphenoxy)hexane] (pCPH), poly(hydroxybutyric acid-cohydroxyvaleric acid) (PHB-PVA), polyethylene glycol-poly (lactic acid) copolymer (PEG-PLA), poly(ethyl)cyanoacrylate (PEC), polyisobutyl cyanoacrylate, poly-*N*-(2-hydroxypropyl)methacrylamide (poly(HPMA)), poly- β -R-hydroxy butyrate (PHB), poly- β -R-hydroxy alkanoate (PHA), poly- β -R-malic acid, phospholipid-cholesterol polymers, 2-dioleoyl-sn-glycero-3-phosphatidylcholine/ polyethyleneglycol-distearoylphosphatidylethanolamine (DOPC/PEG-DSPE)/Cholesterol, polysaccharides, cellulose, ethyl cellulose, methyl cellulose, alginates, dextran and dextran hydrogel polymers, amylose, inulin, pectin and guar gum, chitosan, chitin, heparin, hyaluronic acid, cyclodextrin (CD)-based polyrotaxanes and polypseudorotaxanes, polyaspartates, polyglutamates, polylucine, leucine-glutamate copolymers, polybutylene succinate (PBS), gelatin, collagens, fibrins, fibroin, polyorthoesters, polyorthoester-polyamidine copolymer, polyorthoester-diamine copolymers, polyorthoesters incorporating latent acids, poly(ethylene glycol)/poly(butylene terephthalate) copolymer, and combinations and copolymers thereof.

[0018] In one instance, the plurality of microparticles, which range in size from about two microns to about 70 microns, with a median size of from about 15 microns to about 30 microns, comprise (a) a micronized protein core of from about two microns to about 30 microns, with a median size of about 10 microns to about 12 microns, wherein the protein is a VEGF-Trap protein; and (b) a polymer cortex, wherein the polymer is any one or more of PLA, PCL, PLGA, ethyl cellulose and polyorthoester, and copolymers or derivatives thereof.

[0019] Also disclosed is a method of manufacturing a microparticle, which comprises a protein core and a polymer cortex. In one instance, the manufactured microparticle has a diameter of about two microns to about 70 microns, or a median diameter of about 15 microns to about 30 microns. In one instance, the method of manufacturing the microparticle comprises (1) obtaining a protein particle; (2) suspending the protein particle in a solution comprising the polymer and a solvent; and (3) removing the solvent, wherein a microparticle is formed comprising the protein core coated with the polymer cortex.

[0020] In one instance, the protein particle of step (1) is a micronized protein particle, which is obtained by spray drying a solution comprising the protein. In some instances, the protein solution is spray dried via dual-nozzle sonication, single-nozzle sonication, or electrospray. In some instances, the resultant micronized protein particle, which forms the core of the manufactured microparticle, has a diameter of from about two microns to about 30 microns, with a median diameter of about 10 microns to about 12 microns.

[0021] In some instances, the protein which forms the core is an antigen-binding protein. In some instances, the antigen-binding protein is any one or more of an antibody (e.g., IgG) or antibody fragment, a receptor or soluble fragment thereof, a soluble T-cell receptor fragment, a soluble MHC fragment, a receptor-Fc-fusion protein, a trap-type protein, and a VEGF-Trap protein. In a specific instance, the protein is a VEGF-Trap comprising the amino acid sequence set forth in SEQ ID NO:1.

[0022] In one instance, the solvent is removed at step (3) by creating a dispersion of the protein-polymer-solvent mixture of step (2) and allowing the solvent to evaporate from the droplets created by the dispersion. In one instance, the dispersion is created by spray-drying, which may be performed by dual-nozzle sonication, single-nozzle sonication, or electrospray. In one instance, the solvent is removed from the droplets by applying heat or air, or by chemical extraction.

[0023] In one instance, the polymer is biodegradable, bioerodible, and/or biocompatible. In some instances, the polymer is any one or more of polylactic acid (PLA), polyglycolic acid (PGA), polylactic-polyglycolic copolymer (PLGA), poly-D,L-lactide-co-glycolide (PLGA), PLGA-ethylene oxide fumarate, PLGA-alpha-tocopheryl succinate esterified to polyethylene glycol 1000 (PLGA-TGPS), polyanhydride poly[1,6-bis(p-carboxyphenoxy)hexane] (pCPH), poly(hydroxybutyric acid-cohydroxyvaleric acid) (PHB-PVA), polyethylene glycol-poly (lactic acid) copolymer (PEG-PLA), poly- ϵ -caprolactone (PCL), poly-alkyl-cyano-acrylate (PAC), poly(ethyl)cyanoacrylate (PEC), polyisobutyl cyanoacrylate, poly-N-(2-hydroxypropyl)methacrylamide (poly(HPMA)), poly- β -R-hydroxy butyrate (PHB), poly- β -R-hydroxy alkanoate (PHA), poly- β -R-malic acid, phospholipid-cholesterol polymers, 2-dioleoyl-sn-glycero-3-phosphatidylcholine/ polyethyleneglycol-distearoylphosphatidylethanolamine (DOPC/PEG-DSPE)/Cholesterol, polysaccharides, cellulose, ethyl cellulose, methyl cellulose, alginates, dextran and dextran hydrogel polymers, amylose, inulin, pectin and guar gum, chitosan, chitin, heparin, hyaluronic acid, cyclodextrin (CD)-based polyrotaxanes and polypseudorotaxanes, polyaspartates, polyglutamates, polylucine, leucine-glutamate copolymers, polybutylene succinate (PBS), gelatin, collagens, fibrins, fibroin, polyorthoesters, polyorthoester-polyamidine copolymer, polyorthoester-diamine copolymers, polyorthoesters incorporating latent acids, poly(ethylene glycol)/poly(butylene terephthalate) copolymer, and combinations and copolymers thereof. In one instance, the polymer is poly- ϵ -caprolactone (PCL) or a derivative or copolymer thereof. In one instance, the polymer is PLGA or a derivative or copolymer thereof. In one instance, the polymer is ethyl cellulose or a derivative or copolymer thereof. In one instance, the polymer is polyorthoester, or a derivative thereof, which contains acid labile elements. In another instance, the polymer is PLA.

[0024] Also disclosed is a method of manufacturing a microparticle comprising the steps of (1) forming a micronized protein particle having a diameter of from about two microns to about 30 microns, with a median diameter of from about 10 microns to 12 microns, by spray-drying a solution containing a protein, wherein the protein is an antigen-binding protein. In some instances, the antigen-binding protein is any one or more of an antibody or antibody fragment, a receptor or soluble fragment thereof, a soluble T-cell receptor fragment, a soluble MHC

fragment, a receptor-Fc-fusion protein, a trap-type protein, and a VEGF-Trap protein (e.g., one having the sequence of SEQ ID NO:1); (2) suspending the micronized protein particle in a solution comprising the polymer and a solvent, wherein the polymer is any one or more of a biodegradable polymer, a bioerodible polymer, a biocompatible polymer, polylactic acid (PLA), polyglycolic acid (PGA), polylactic-polyglycolic copolymer (PLGA), poly-D,L-lactide-co-glycolide (PLGA), PLGA-ethylene oxide fumarate, PLGA-alpha-tocopheryl succinate esterified to polyethylene glycol 1000 (PLGA-TGPS), polyanhydride poly[1,6-bis(p-carboxyphenoxy)hexane] (pCPH), poly(hydroxbutyric acid-cohydroxyvaleric acid) (PHB-PVA), polyethylene glycol-poly (lactic acid) copolymer (PEG-PLA), poly- ϵ -caprolactone (PCL), poly-alkyl-cyano-acrylate (PAC), poly(ethyl)cyanoacrylate (PEC), polyisobutyl cyanoacrylate, poly-N-(2-hydroxypropyl)methacrylamide (poly(HPMA)), poly- β -R-hydroxy butyrate (PHB), poly- β -R-hydroxy alkanoate (PHA), poly- β -R-malic acid, phospholipid-cholesterol polymers, 2-dioleoyl-sn-glycero-3-phosphatidylcholine/ polyethyleneglycol-distearoylphosphatidylethanolamine (DOPC/PEG-DSPE)/Cholesterol, polysaccharides, cellulose, ethyl cellulose, methyl cellulose, alginates, dextran and dextran hydrogel polymers, amylose, inulin, pectin and guar gum, chitosan, chitin, heparin, hyaluronic acid, cyclodextrin (CD)-based polyrotaxanes and polypseudorotaxanes, polyaspartates, polyglutamates, polylucine, leucine-glutamate copolymers, polybutylene succinate (PBS), gelatin, collagens, fibrins, fibroin, polyorthoesters, polyorthoester-polyamidine copolymer, polyorthoester-diamine copolymers, polyorthoesters incorporating latent acids, poly(ethylene glycol)/poly(butylene terephthalate) copolymer, and combinations and copolymers thereof; and (3) removing the solvent by spray-drying micronized protein particle-polymer-solvent suspension and driving off the solvent by applying heat or air, or by extracting the solvent, wherein a microparticle is formed having a diameter of about two microns to about 70 microns, with a median diameter of from about 15 microns to about 30 microns, and comprising a protein core and a polymer cortex.

[0025] In some instances, the spray-drying of step (1) or step (3) is performed via dual-nozzle sonication, single-nozzle sonication, or electrospray.

[0026] In one instance, the method of manufacturing the microparticle comprises the steps of (1) forming a micronized VEGF-Trap particle having a diameter of from about 10 microns to 12 microns by spray-drying a solution containing a VEGF Trap protein; (2) suspending the micronized VEGF Trap particle in a solution comprising polyorthoester incorporating a latent acid and a compatible solvent, or ethylcellulose and a compatible solvent; and (3) removing the solvent by (a) spray-drying the micronized VEGF Trap particle-polyorthoester-latent acid-solvent suspension or the micronized VEGF Trap particle-ethyl cellulose-solvent suspension and (b) driving off the solvent by applying heat or air, or by extracting the solvent, wherein a microparticle is formed having a diameter of about 15 microns to about 30 microns, and comprising a VEGF-Trap core and a polymer cortex of polyorthoester, and copolymers or derivatives thereof.

[0027] In one aspect, the invention provides an extended release formulation of a therapeutic protein for the release or delivery of a steady level of the therapeutic protein over time. In particular, the present invention provides an extended release pharmaceutical formulation for

use in the vitreous for the treatment of vascular eye disorders, the pharmaceutical formulation comprising microparticles having a diameter of from 2 microns to 70 microns, the microparticles having a protein particle core within a polymer cortex, the protein particle containing less than 3% water by weight, wherein the microparticles release the protein in a physiological aqueous environment at about 37°C at a rate of from about 0.01 mg/week to about 0.30 mg/week over at least 60 days. The extended release formulation comprises a plurality of microparticles, which range in size from about two microns to about 70 microns, each of which may comprise a micronized protein core of about two microns to about 30 microns, and a polymer cortex.

[0028] In one embodiment, the therapeutic protein is an antigen-binding protein. In some embodiments, the antigen-binding protein is any one or more of an antibody (e.g., IgG) or antibody fragment, a receptor or soluble fragment thereof, a soluble T-cell receptor fragment, a soluble MHC fragment, a receptor-Fc-fusion protein, a trap-type protein, and a VEGF-Trap protein (e.g., one of which has a primary structure of SEQ ID NO:1). In one embodiment, the therapeutic protein comprises an Fc domain. In one embodiment, the protein is an antibody. In another embodiment, the protein is an IgG. In another embodiment, the therapeutic protein is a receptor-Fc-fusion protein. In another embodiment, the therapeutic protein is a trap-type protein, which comprises a cognate-receptor fragment and an Fc domain. In one particular embodiment, the therapeutic protein is a VEGF-Trap protein. In yet another embodiment, the VEGF-Trap comprises the amino acid sequence set forth in SEQ ID NO:1.

[0029] In one embodiment, the polymer cortex comprises a biocompatible polymer. In one embodiment, the polymer cortex comprises a bioerodible polymer. In one embodiment, the polymer cortex comprises a biodegradable polymer. In some embodiments, the polymer cortex comprises a polymer selected from the group consisting of polylactic acid (PLA), polyglycolic acid (PGA), polylactic-polyglycolic copolymer (PLGA), poly-D,L-lactide-co-glycolide (PLGA), PLGA-ethylene oxide fumarate, PLGA-alpha-tocopheryl succinate esterified to polyethylene glycol 1000 (PLGA-TGPS), polyanhydride poly[1,6-bis(p-carboxyphenoxy)hexane] (pCPH), poly(hydroxbutyric acid-cohydroxyvaleric acid) (PHB-PVA), polyethylene glycol-poly (lactic acid) copolymer (PEG-PLA), poly- ϵ -caprolactone (PCL), poly-alkyl-cyano-acrylate (PAC), poly(ethyl)cyanoacrylate (PEC), polyisobutyl cyanoacrylate, poly-*N*-(2-hydroxypropyl)methacrylamide (poly(HPMA)), poly- β -R-hydroxy butyrate (PHB), poly- β -R-hydroxy alcanoate (PHA), poly- β -R-malic acid, phospholipid-cholesterol polymers, 2-dioleoyl-sn-glycero-3-phosphatidylcholine/ polyethyleneglycol-distearoylphosphatidylethanolamine (DOPC/PEG-DSPE)/Cholesterol, polysaccharides, cellulose, ethyl cellulose, methyl cellulose, alginates, dextran and dextran hydrogel polymers, amylose, inulin, pectin and guar gum, chitosan, chitin, heparin, hyaluronic acid, cyclodextrin (CD)-based polyrotaxanes and polypseudo-rotaxanes, polyaspartates, polyglutamates, polylysine, leucine-glutamate copolymers, polybutylene succinate (PBS), gelatin, collagens, fibrins, fibroin, polyorthoesters, polyorthoester-polyamidine copolymer, polyorthoester-diamine copolymers, polyorthoesters incorporating latent acids, poly(ethylene glycol)/poly(butylene terephthalate) copolymer, and combinations and copolymers thereof. In one embodiment, the polymer is poly- ϵ -caprolactone (PCL) or a derivative or copolymer thereof. In one embodiment, the polymer cortex comprises

a PLGA. In one embodiment, the polymer cortex comprises an ethyl cellulose. In one embodiment, the polymer cortex comprises any one or more of PLA, PLGA, ethyl cellulose, and polyorthoester, and copolymers or derivatives thereof.

[0030] In one embodiment, plurality of microparticles comprises a collection of microparticles having a range of thicknesses of the polymer cortex, such that individual microparticles of the collection of microparticles degrades at a different rate, which allows for a uniform rate of release of the therapeutic protein.

[0031] In one embodiment, the plurality of microparticles comprises a mixture of uncoated micronized protein particles and microparticles having a range of thicknesses of the polymer cortex, which allows for the release of therapeutic protein at periodic intervals based on cortex thickness.

[0032] In one embodiment, the plurality of microparticles comprises a mixture of microparticles having polymer cortices of varying levels of hydrophobicity to control the timing or duration of degradation and subsequent release. In one embodiment, the microparticles each comprise an inner polymer layer and an outer polymer layer, wherein the outer polymer layer limits the hydration of the inner polymer layer to control release of the therapeutic protein.

[0033] The therapeutic protein is released from the plurality of microparticles at a rate of from about 0.01 mg/week to about 0.30 mg/week for a duration of at least 60 days, when the microparticles are in an aqueous environment. In one embodiment, the aqueous environment is in vitro buffer. In one embodiment, the aqueous environment is in vivo. In one embodiment, the aqueous environment is ex vivo. In one embodiment, the aqueous environment is a vitreous humor.

[0034] In one embodiment, the extended release formulation comprises a plurality of microparticles, which range in size from about two microns to about 70 microns and which comprise (a) a core of micronized therapeutic protein of from about two microns to about 30 microns, wherein the therapeutic protein is an antigen-binding protein, which in some cases can be any one or more of an antibody or antibody fragment, a receptor or soluble fragment thereof, a soluble T-cell receptor fragment, a soluble MHC fragment, a receptor-Fc-fusion protein, a trap-type protein, and a VEGF-Trap protein; and (b) a polymer cortex of a range of thicknesses, wherein the polymer is any one or more of a biocompatible polymer, a biodegradable polymer, a bio-erodible polymer, polylactic acid (PLA), polyglycolic acid (PGA), polylactic-polyglycolic copolymer (PLGA), poly-D,L-lactide-co-glycolide (PLGA), PLGA-ethylene oxide fumarate, PLGA-alpha-tocopheryl succinate esterified to polyethylene glycol 1000 (PLGA-TGPS), polyanhydride poly[1,6-bis(p-carboxyphenoxy)hexane] (pCPH), poly(hydroxbutyric acid-cohydroxyvaleric acid) (PHB-PVA), polyethylene glycol-poly (lactic acid) copolymer (PEG-PLA), poly- ϵ -caprolactone (PCL), poly-alkyl-cyano-acrylate (PAC), poly(ethyl)cyanoacrylate (PEC), polyisobutyl cyanoacrylate, poly-*N*-(2-hydroxypropyl)methacrylamide (poly(HPMA)), poly- β -R-hydroxy butyrate (PHB), poly- β -R-hydroxy alkanoate (PHA), poly- β -R-malic acid, phospholipid-cholesterol polymers, 2-dioleoyl-

sn-glycero-3-phosphatidylcholine/ polyethyleneglycol-distearoylphosphatidylethanolamine (DOPC/PEG-DSPE)/Cholesterol, polysaccharides, cellulose, ethyl cellulose, methyl cellulose, alginates, dextran and dextran hydrogel polymers, amylose, inulin, pectin and guar gum, chitosan, chitin, heparin, hyaluronic acid, cyclodextrin (CD)-based polyrotaxanes and polypseudorotaxanes, polyaspartates, polyglutamates, polyLucine, leucine-glutamate copolymers, polybutylene succinate (PBS), gelatin, collagens, fibrins, fibroin, polyorthoesters, polyorthoester-polyamidine copolymer, polyorthoester-diamine copolymers, polyorthoesters incorporating latent acids, poly(ethylene glycol)/poly(butylene terephthalate) copolymer, and combinations and copolymers thereof, wherein the microparticles release or deliver a steady level of the therapeutic protein at a rate of from about 0.01 mg/week to about 0.30 mg/week for at least 60 days.

[0035] In one embodiment, the extended release formulation comprises a plurality of microparticles, which range in size from about two microns to about 70 microns, with a median size of from about 15 microns to about 30 microns, and which comprise (a) a micronized protein core of from about two microns to about 30 microns, with a median size of about 10 microns to about 12 microns, wherein the protein is a VEGF-Trap protein; and (b) a polymer cortex of a range of thicknesses, wherein the polymer is any one or more of PLGA, ethyl cellulose, and polyorthoester, and copolymers or derivatives thereof, such that in an aqueous environment the microparticles release or deliver a steady level of VEGF Trap at a rate of about 0.06 ± 0.02 mg/week for at least 60 days.

[0036] Also disclosed is a method for modulating the release of a protein. In one instance, the method comprises the step of making a plurality of microparticles as described in the previous aspect, followed by the step of placing the microparticles into a solvent. The solvent in some embodiments is aqueous. The solvent can be *in vitro*, such as in a phosphate buffered solution. The solvent can be *in vivo*, such as e.g. vitreous humour.

DRAWINGS

[0037]

Figure 1 depicts the relative amount (% volume) of protein particles without a polymer cortex of a given diameter (ECD (μm)) in a population of protein particles manufactured from 50 mg/mL of VEGF Trap protein, 25 mg/mL of VEGF Trap protein, and 25 mg/mL of VEGF Trap protein plus 0.1% polysorbate 80.

Figure 2 depicts the relative amount (% volume determined by MFI) of microparticles of a given diameter (ECD (μm)) in a population of microparticles manufactured from 50 mg/mL of VEGF Trap protein plus 50 mg/mL POE, 250 mg/mL POE, and 50 mg/mL EC.

Figure 3 depicts the amount of VEGF Trap protein in milligrams released from microparticles manufactured from 50 mg/mL POE, 250 mg/mL POE, or 50 mg/mL EC over approximately 60 days.

DETAILED DESCRIPTION

[0038] The micro particle and protein core particle of the subject invention are roughly spherical in shape. Some microparticles and protein cores will approach sphericity, while others will be more irregular in shape. Thus, as used herein, the term "diameter" means each and any of the following: (a) the diameter of a sphere which circumscribes the microparticle or protein core, (b) the diameter of the largest sphere that fits within the confines of the microparticle or the protein core, (c) any measure between the circumscribed sphere of (a) and the confined sphere of (b), including the mean between the two, (d) the length of the longest axis of the microparticle or protein core, (e) the length of the shortest axis of the microparticle or protein core, (f) any measure between the length of the long axis (d) and the length of the short axis (e), including the mean between the two, and/or (g) equivalent circular diameter ("ECD"), as determined by micro-flow imaging (MFI), nanoparticle tracking analysis (NTA), or light obscuration methods such as dynamic light scattering (DLS). See generally Sharma et al., Micro-flow imaging: flow microscopy applied to subvisible particulate analysis in protein formulations, *AAPS J.* 2010 Sep; 12(3): 455-64. Diameter is generally expressed in micrometers (μm or micron). Diameter can be determined by optical measurement

[0039] "Micronized protein particle" or "protein particle" means a particle containing multiple molecules of protein with low, very low, or close to zero amounts of water (e.g., <3% water by weight). As used herein, the micronized protein particle is generally spherical in shape and has an ECD ranging from 2 microns to about 35 microns. The micronized protein particle is not limited to any particular protein entity, and is suited to the preparation and delivery of a therapeutic protein. Common therapeutic proteins include *inter alia* antigen-binding proteins, such as e.g., soluble receptor fragments, antibodies (including IgGs) and derivatives or fragments of antibodies, other Fc containing proteins, including Fc fusion proteins, and receptor-Fc fusion proteins, including the trap-type proteins (Huang, C., *Curr. Opin. Biotechnol.* 20: 692-99 (2009)) such as e.g. VEGF-Trap.

[0040] The micronized protein particle of the invention can be made by any method known in the art for making micron-sized protein particles. For example, the protein particle may be made by *inter alia* spray-drying (*infra*), lyophilization, jet milling, hanging drop crystallization (Ruth et al., *Acta Crystallographica D56*: 524-28 (2000)), gradual precipitation (US 7,998,477 (2011)), lyophilization of a protein-PEG (polyethylene glycol) aqueous mixture (Morita et al., *Pharma. Res.* 17: 1367-73 (2000)), supercritical fluid precipitation (US 6,063,910 (2000)), or high pressure carbon dioxide induced particle formation (Bustami et al., *Pharma. Res.* 17: 1360-66 (2000)).

[0041] As used herein, the term "protein" refers to a molecule comprising two or more amino acid residues joined to each other by peptide bonds. Peptides, polypeptides and proteins are

also inclusive of modifications including, but not limited to, glycosylation, lipid attachment, sulfation, gamma-carboxylation of glutamic acid residues, hydroxylation and ADP-ribosylation. Polypeptides can be of scientific or commercial interest, including protein-based drugs. Polypeptides include, among other things, antibodies and chimeric or fusion proteins. Polypeptides are produced by recombinant animal cell lines using cell culture methods.

[0042] An "antibody" is intended to refer to immunoglobulin molecules consisting of four polypeptide chains, two heavy (H) chains and two light (L) chains inter-connected by disulfide bonds. Each heavy chain has a heavy chain variable region (HCVR or VH) and a heavy chain constant region. The heavy chain constant region contains three domains, CH1, CH2 and CH3. Each light chain has of a light chain variable region and a light chain constant region. The light chain constant region consists of one domain (CL). The VH and VL regions can be further subdivided into regions of hypervariability, termed complementarity determining regions (CDR), interspersed with regions that are more conserved, termed framework regions (FR). Each VH and VL is composed of three CDRs and four FRs, arranged from amino-terminus to carboxy-terminus in the following order: FR1, CDR1, FR2, CDR2, FR3, CDR3, FR4. The term "antibody" includes reference to both glycosylated and non-glycosylated immunoglobulins of any isotype or subclass. The term "antibody" is inclusive of, but not limited to, those that are prepared, expressed, created or isolated by recombinant means, such as antibodies isolated from a host cell transfected to express the antibody. An IgG comprises a subset of antibodies.

[0043] "Fc fusion proteins" comprise part or all of two or more proteins, one of which is an Fc portion of an immunoglobulin molecule, that are not fused in their natural state. Preparation of fusion proteins comprising certain heterologous polypeptides fused to various portions of antibody-derived polypeptides (including the Fc domain) has been described, e.g., by Ashkenazi et al., Proc. Natl. Acad. Sci. USA 88: 10535, 1991; Byrn et al., Nature 344:677, 1990; and Hollenbaugh et al., "Construction of Immunoglobulin Fusion Proteins", in Current Protocols in Immunology, Suppl. 4, pages 10.19.1 - 10.19.11, 1992. "Receptor Fc fusion proteins" comprise one or more of one or more extracellular domain(s) of a receptor coupled to an Fc moiety, which in some embodiments comprises a hinge region followed by a CH2 and CH3 domain of an immunoglobulin. In some embodiments, the Fc-fusion protein contains two or more distinct receptor chains that bind to a single or more than one ligand(s). For example, an Fc-fusion protein is a trap, such as for example an IL-1 trap (e.g., Rilonacept, which contains the IL-1RAcP ligand binding region fused to the IL-1R1 extracellular region fused to Fc of hIgG1; see U.S. Pat. No. 6,927,004), or a VEGF Trap (e.g., Aflibercept, which contains the Ig domain 2 of the VEGF receptor Flt1 fused to the Ig domain 3 of the VEGF receptor Flk1 fused to Fc of hIgG1; e.g., SEQ ID NO:1; see U.S. Pat. Nos. 7,087,411 and 7,279,159).

[0044] As used herein, the term "polymer" refers to a macromolecule comprising repeating monomers connected by covalent chemical bonds. Polymers used in the practice of this invention are biocompatible and biodegradable. A biocompatible and biodegradable polymer can be natural or synthetic. Natural polymers include polynucleotides, polypeptides, such as naturally occurring proteins, recombinant proteins, gelatin, collagens, fibrins, fibroin, polyaspartates, polyglutamates, polyleucine, leucine-glutamate co-polymers; and

polysaccharides, such as cellulose alginates, dextran and dextran hydrogel polymers, amylose, inulin, pectin and guar gum, chitosan, chitin, heparin, and hyaluronic acid. Synthetic biocompatible or biodegradable polymers include polylactic acid (PLA), polyglycolic acid (PGA), polylactic-polyglycolic copolymer (PLGA), poly-D,L-lactide-co-glycolide (PLGA), PLGA-ethylene oxide fumarate, PLGA-alpha-tocopheryl succinate esterified to polyethylene glycol 1000 (PLGA-TGPS), polyanhydride poly[1,6-bis(p-carboxyphenoxy)hexane] (pCPH), poly(hydroxybutyric acid-cohydroxyvaleric acid) (PHB-PVA), polyethylene glycol-poly (lactic acid) copolymer (PEG-PLA), poly- ϵ -caprolactone (PCL), poly-alkyl-cyano-acrylate (PAC), poly(ethyl)cyanoacrylate (PEC), polyisobutyl cyanoacrylate, poly-*N*-(2-hydroxypropyl)methacrylamide (poly(HPMA)), poly- β -R-hydroxy butyrate (PHB), poly- β -R-hydroxy alkanoate (PHA), poly- β -R-malic acid, phospholipid-cholesterol polymers, 2-dioleoyl-sn-glycero-3-phosphatidylcholine/ polyethyleneglycol-distearoylphosphatidylethanolamine (DOPC/PEG-DSPE)/Cholesterol, ethyl cellulose, cyclodextrin (CD)-based polyrotaxanes and polypseudorotaxanes, polybutylene succinate (PBS), polyorthoesters, polyorthoester-polyamidine copolymers, polyorthoester-diamine copolymers, polyorthoesters incorporating latent acids to control rates of degradation, and *inter alia* poly(ethylene glycol)/poly(butylene terephthalate) copolymers.

[0045] Ethyl cellulose (EC) is a well-known and readily available biomaterial used in the pharmaceutical and food sciences. It is a cellulose derivative in which some of the glucose hydroxyl groups are replaced with ethyl ether. See Martinac et al., *J. Microencapsulation*, 22(5): 549-561 (2005) and references therein, which describe methods of using ethyl cellulose as biocompatible polymers in the manufacture of microspheres. See also US 4,210,529 (1980) and references therein for a detailed description of ethyl cellulose and methods of making derivatives of ethyl cellulose.

[0046] Poly-D,L-lactide-co-glycolide (PLGA) is also a well-known Food and Drug Administration (FDA) approved biocompatible and biodegradable polymer used in tissue engineering and pharmaceutical delivery systems. PLGA is a polyester comprising glycolic acid and lactic acid monomers. For a description of the synthesis of PLGA and manufacture of PLGA nanoparticles, see Astete and Sabliov, *Biomater. Sci. Polym. Ed.*, 17(3): 247-89 (2006) and references therein.

[0047] Poly- ϵ -caprolactone (PCL) is another biocompatible and biodegradable polymer approved by the FDA for use in humans as a drug delivery device. PCL is a polyester of ϵ -caprolactone, which hydrolyses rapidly in the body to form a non-toxic or low toxicity hydroxycarboxylic acid. For a description of the manufacture of PCL, see Labet and Thielemans, *Chemical Society Reviews* 38: 3484-3504 (2009) and references therein. For a description of the manufacture and use of PCL-based microspheres and nanospheres as delivery systems, see Sinha et al., *Int. J. Pharm.*, 278(1): 1-23 (2004) and references therein.

[0048] Polyorthoester (POE) is a bioerodible polymer designed for drug delivery. It is generally a polymer of a ketene acetal, preferably a cyclic diketene acetal, such as e.g., 3,9-dimethylene-2,4,8,10-tetraoxa spiro[5.5]-undecane, which is polymerized via glycol

condensation to form the orthoester linkages. A description of polyorthoester sysnthesis and various types can be found e.g. in US 4,304,767. Polyorthoesters can be modified to control their drug release profile and degradation rates by swapping in or out various hydrophobic diols and polyols, such as e.g., replacing a hexanetriol with a decanetriol.; as well as adding latent acids, such as e.g., octanedioic acid or the like, to the backbone to increase pH sensitivity. Other modifications to the polyorthoester include the integration of an amine to increase functionality. The formation, description, and use of polyorthoesters are described in US 5,968,543; US 4,764,364; Heller and Barr, Biomacromolecules, 5(5): 1625-32 (2004); and Heller, Adv. Drug. Deliv. Rev., 57: 2053-62 (2005).

[0049] As used herein, the phrase "spray-dry" means a method of producing a dry powder comprising micron-sized particles from a slurry or suspension by using a spray-dryer. Spray dryers employ an atomizer or spray nozzle to disperse the suspension or slurry into a controlled drop size spray. Drop sizes from 10 to 500 μm can be generated by spray-drying. As the solvent (water or organic solvent) dries, the protein substance dries into a micron-sized particle, forming a powder-like substance; or in the case of a protein-polymer suspension, during drying, the polymer hardened shell around the protein load.

[0050] The microparticles of the invention comprise a protein core surrounded by a polymer cortex or coat. Briefly, a micronized protein particle is formed, which is then dispersed in a polymer solution (polymer dissolved in solvent) to form a protein-polymer suspension. The protein-polymer suspension is then dispersed into micronized (atomized) droplets, and the solvent is driven-off to form the microparticle.

[0051] In one embodiment, the micronized protein particle is formed by making a solution of the protein and then subjecting that protein solution to dispersion and heat to form a dry powder comprising the protein. One method to form the micronized protein particles is by spray-drying. In one embodiment, the protein is a therapeutic protein that is formulated to include buffers, stabilizers and other pharmaceutically acceptable excipients to make a pharmaceutical formulation of the therapeutic protein. Exemplary pharmaceutical formulations are described in US 7,365,165, US 7,572,893, US 7,608,261, US 7,655,758, US 7,807,164, US 2010-0279933, US 2011-0171241, and PCT/US11/54856.

[0052] The amount of therapeutic protein contained within the pharmaceutical formulations of the present invention may vary depending on the specific properties desired of the formulations, as well as the particular circumstances and purposes for which the formulations are intended to be used. In certain embodiments, the pharmaceutical formulations may contain about 1 mg/mL to about 500 mg/mL of protein; about 5 mg/mL to about 400 mg/mL of protein; about 5 mg/mL to about 200 mg/mL of protein; about 25 mg/mL to about 180 mg/mL of protein; about 25 mg/mL to about 150 mg/mL of protein; or about 50 mg/mL to about 180 mg/mL of protein. For example, the formulations of the present invention may comprise about 1 mg/mL; about 2 mg/mL; about 5 mg/mL; about 10 mg/mL; about 15 mg/mL; about 20 mg/mL; about 25 mg/mL; about 30 mg/mL; about 35 mg/mL; about 40 mg/mL; about 45 mg/mL; about 50 mg/mL; about 55 mg/mL; about 60 mg/mL; about 65 mg/mL; about 70

mg/mL; about 75 mg/mL; about 80 mg/mL; about 85 mg/mL; about 86 mg/mL; about 87 mg/mL; about 88 mg/mL; about 89 mg/mL; about 90 mg/mL; about 95 mg/mL; about 100 mg/mL; about 105 mg/mL; about 110 mg/mL; about 115 mg/mL; about 120 mg/mL; about 125 mg/mL; about 130 mg/mL; about 131 mg/mL; about 132 mg/mL; about 133 mg/mL; about 134 mg/mL; about 135 mg/mL; about 140 mg/mL; about 145 mg/mL; about 150 mg/mL; about 155 mg/mL; about 160 mg/mL; about 165 mg/mL; about 170 mg/mL; about 175 mg/mL; about 180 mg/mL; about 185 mg/mL; about 190 mg/mL; about 195 mg/mL; about 200 mg/mL; about 205 mg/mL; about 210 mg/mL; about 215 mg/mL; about 220 mg/mL; about 225 mg/mL; about 230 mg/mL; about 235 mg/mL; about 240 mg/mL; about 245 mg/mL; about 250 mg/mL; about 255 mg/mL; about 260 mg/mL; about 265 mg/mL; about 270 mg/mL; about 275 mg/mL; about 280 mg/mL; about 285 mg/mL; about 200 mg/mL; about 200 mg/mL; or about 300 mg/mL of therapeutic protein.

[0053] The pharmaceutical formulations of the present invention comprise one or more excipients. The term "excipient," as used herein, means any non-therapeutic agent added to the formulation to provide a desired consistency, viscosity or stabilizing effect.

[0054] The pharmaceutical formulations of the present invention may also comprise one or more carbohydrate, e.g., one or more sugar. The sugar can be a reducing sugar or a non-reducing sugar. "Reducing sugars" include, e.g., sugars with a ketone or aldehyde group and contain a reactive hemiacetal group, which allows the sugar to act as a reducing agent. Specific examples of reducing sugars include fructose, glucose, glyceraldehyde, lactose, arabinose, mannose, xylose, ribose, rhamnose, galactose and maltose. Non-reducing sugars can comprise an anomeric carbon that is an acetal and is not substantially reactive with amino acids or polypeptides to initiate a Maillard reaction. Specific examples of non-reducing sugars include sucrose, trehalose, sorbose, sucralose, melezitose and raffinose. Sugar acids include, for example, saccharic acids, gluconate and other polyhydroxy sugars and salts thereof.

[0055] The amount of sugar contained within the pharmaceutical formulations of the present invention will vary depending on the specific circumstances and intended purposes for which the formulations are used. In certain embodiments, the formulations may contain about 0.1% to about 20% sugar; about 0.5% to about 20% sugar; about 1% to about 20% sugar; about 2% to about 15% sugar; about 3% to about 10% sugar; about 4% to about 10% sugar; or about 5% to about 10% sugar. For example, the pharmaceutical formulations of the present invention may comprise about 0.5%; about 1.0%; about 1.5%; about 2.0%; about 2.5%; about 3.0%; about 3.5%; about 4.0%; about 4.5%; about 5.0%; about 5.5%; about 6.0%; 6.5%; about 7.0%; about 7.5%; about 8.0%; about 8.5%; about 9.0%; about 9.5%; about 10.0%; about 10.5%; about 11.0%; about 11.5%; about 12.0%; about 12.5%; about 13.0%; about 13.5%; about 14.0%; about 14.5%; about 15.0%; about 15.5%; about 16.0%; 16.5%; about 17.0%; about 17.5%; about 18.0%; about 18.5%; about 19.0%; about 19.5%; or about 20.0% sugar (e.g., sucrose).

[0056] The pharmaceutical formulations of the present invention may also comprise one or more surfactant. As used herein, the term "surfactant" means a substance which reduces the

surface tension of a fluid in which it is dissolved and/or reduces the interfacial tension between oil and water. Surfactants can be ionic or non-ionic. Exemplary non-ionic surfactants that can be included in the formulations of the present invention include, e.g., alkyl poly(ethylene oxide), alkyl polyglucosides (e.g., octyl glucoside and decyl maltoside), fatty alcohols such as cetyl alcohol and oleyl alcohol, cocamide MEA, cocamide DEA, and cocamide TEA. Specific non-ionic surfactants that can be included in the formulations of the present invention include, e.g., polysorbates such as polysorbate 20, polysorbate 28, polysorbate 40, polysorbate 60, polysorbate 65, polysorbate 80, polysorbate 81, and polysorbate 85; poloxamers such as poloxamer 188, poloxamer 407; polyethylene-polypropylene glycol; or polyethylene glycol (PEG). Polysorbate 20 is also known as TWEEN 20, sorbitan monolaurate and polyoxyethylenesorbitan monolaurate.

[0057] The amount of surfactant contained within the pharmaceutical formulations of the present invention may vary depending on the specific properties desired of the formulations, as well as the particular circumstances and purposes for which the formulations are intended to be used. In certain embodiments, the formulations may contain about 0.05% to about 5% surfactant; or about 0.1% to about 0.2% surfactant. For example, the formulations of the present invention may comprise about 0.05%; about 0.06%; about 0.07%; about 0.08%; about 0.09%; about 0.10%; about 0.11%; about 0.12%; about 0.13%; about 0.14%; about 0.15%; about 0.16%; about 0.17%; about 0.18%; about 0.19%; about 0.20%; about 0.21%; about 0.22%; about 0.23%; about 0.24%; about 0.25%; about 0.26%; about 0.27%; about 0.28%; about 0.29%; or about 0.30% surfactant (e.g., polysorbate 20).

[0058] The pharmaceutical formulations of the present invention may also comprise one or more buffers. In some embodiments, the buffer has a buffering range that overlaps fully or in part the range of pH 5.5 - 7.4. In one embodiment, the buffer has a pKa of about 6.0 ± 0.5 . In certain embodiments, the buffer comprises a phosphate buffer. In certain embodiments, the phosphate is present at a concentration of 5 mM \pm 0.75 mM to 15 mM \pm 2.25 mM; 6 mM \pm 0.9 mM to 14 mM \pm 2.1 mM; 7 mM \pm 1.05 mM to 13 mM \pm 1.95 mM; 8 mM \pm 1.2 mM to 12 mM \pm 1.8 mM; 9 mM \pm 1.35 mM to 11 mM \pm 1.65 mM; 10 mM \pm 1.5 mM; or about 10 mM. In certain embodiments, the buffer system comprises histidine at 10 mM \pm 1.5 mM, at a pH of 6.0 ± 0.5 .

[0059] The pharmaceutical formulations of the present invention may have a pH of from about 5.0 to about 8.0. For example, the formulations of the present invention may have a pH of about 5.0; about 5.2; about 5.4; about 5.6; about 5.8; about 6.0; about 6.2; about 6.4; about 6.6; about 6.8; about 7.0; about 7.2; about 7.4; about 7.6; about 7.8; or about 8.0.

[0060] In one particular embodiment, the therapeutic protein is a VEGF Trap protein. Pharmaceutical formulations for the formation of micronized VEGF Trap protein particles may contain from about 10 mg/mL to about 100 mg/mL VEGF Trap protein, about 10 mg/mL, about 15 mg/mL, about 20 mg/mL, about 25 mg/mL, about 30 mg/mL, about 35 mg/mL, about 40 mg/mL, about 45 mg/mL, about 50 mg/mL, about 55 mg/mL, about 60 mg/mL, about 65 mg/mL, about 70 mg/mL, about 75 mg/mL, about 80 mg/mL, about 85 mg/mL, about 90 mg/mL, about 95 mg/mL, or about 100 mg/mL VEGF Trap protein. Solutions may contain one

or more buffers of from about 5 mM to about 50 mM. In one embodiment, the buffer is about 10 mM phosphate at a pH of about 6 ± 0.5. Solutions may also contain sucrose at a concentration of from about 1% to about 10%. In one embodiment, the solution contains sucrose at about 2% w/w.

[0061] In some embodiments, the therapeutic protein solution contains VEGF Trap protein at about 25 mg/mL or about 50 mg/mL in 10 mM phosphate, pH 6.2, 2% sucrose, and optionally 0.1% polysorbate.

[0062] The therapeutic protein formulation is then subjected to dispersion and drying to form micronized protein particles. One method of making the micronized protein particles is to subject the protein solution to spray-drying. Spray-drying is generally known in the art and may be performed on equipment such as e.g., a BÜCHI Mini Spray Dryer B-290 (Buchi Labortechnik AG, Flawil, CH). In one particular embodiment, the protein solution (e.g., but not limited to any one of the VEGF Trap formulations described above) is pumped into the spray dryer at a rate of about 2 mL/min to about 15 mL/min, or about 7 mL/min. The inlet temperature of the spray dryer is set at a temperature above the boiling point of water, such as e.g., at about 130°C. The outlet temperature at a temperature below the boiling point of water and above ambient temperature, such as e.g., 55°C. In one specific embodiment, a protein solution (e.g., VEGF Trap solution or IgG solution) is pumped into a BÜCHI Mini Spray Dryer B-290 at about 7 mL/min, with an inlet temperature of about 130°C and an outlet temperature of about 55°C, with the aspirator set at 33 m³/h and the spray gas at 530 L/h.

[0063] The resulting micronized protein particles range in size from about 1 µm to about 100 µm in diameter, depending upon the particular formulation and concentration of protein and excipients. In some embodiments, the micronized protein particles have a diameter of from about 1 µm to about 100 µm, from about 1 µm to about 40 µm, from about 2 µm to about 15 µm, from about 2.5 µm to about 13 µm, from about 3 µm to about 10 µm, about 5 µm, about 6 µm, about 7 µm, about 8 µm, about 9 µm, about 10 µm, about 11 µm, or about 12 µm.

[0064] The micronized protein particles are then coated with a biocompatible and biodegradable polymer. This can be accomplished by suspending the micronized protein particles in a polymer solution. A polymer solution is essentially a polymer dissolved in a solvent. For example, the biocompatible and biodegradable polymer may be dissolved in *inter alia* methylene chloride, tetrahydrofuran, ethyl acetate, or some other useful solvent. Ethyl acetate is widely known as a safe solvent and is often used in the preparation of drugs, implants and foodstuffs.

[0065] In some embodiments, the polymer can be ethyl cellulose ("EC"), poly(lactic acid) ("PLA"), polyorthoester ("POE"), poly-D,L-lactide-co-glycolide ("PLGA"), or poly-ε-caprolactone ("PCL"). The polymer can be dissolved in the solvent (e.g., ethyl acetate) at a concentration of from about 10 mg/mL to about 300 mg/mL, from about 15 mg/mL to about 295 mg/mL, from about 20 mg/mL to about 290 mg/mL, from about 25 mg/mL to about 280 mg/mL, from about 30 mg/mL to about 270 mg/mL, from about 35 mg/mL to about 265 mg/mL, from about 40

mg/mL to about 260 mg/mL, from about 45 mg/mL to about 260 mg/mL, from about 50 mg/mL to about 255 mg/mL, from about 55 mg/mL to about 250 mg/mL, about 20 mg/mL, about 25 mg/mL, about 30 mg/mL, about 35 mg/mL, about 40 mg/mL, about 45 mg/mL, about 50 mg/mL, about 75 mg/mL, about 100 mg/mL, about 125 mg/mL, about 150 mg/mL, about 175 mg/mL, about 200 mg/mL, about 225 mg/mL, or about 250 mg/mL.

[0066] The micronized protein particles are added to the polymer solution at about 10 mg/mL to about 100 mg/mL, about 15 mg/mL to about 95 mg/mL, about 20 mg/mL to about 90 mg/mL, about 25 mg/mL to about 85 mg/mL, about 30 mg/mL to about 80 mg/mL, about 35 mg/mL to about 75 mg/mL, about 40 mg/mL to about 70 mg/mL, about 45 mg/mL to about 65 mg/mL, about 50 mg/mL to about 60 mg/mL, at about 25 mg/mL, at about 30 mg/mL, at about 35 mg/mL, at about 40 mg/mL, at about 45 mg/mL, or at about 50 mg/mL. The particles are mixed to form a slurry or suspension, which is then subjected to dispersion and drying to form the polymer coated protein particle (*i.e.*, microparticle).

[0067] In one embodiment, the protein particle-polymer solution suspension is subjected to the spray-drying, which is performed in a manner similar to the method for manufacturing the micronized protein particles, but with a reduced intake temperature to protect against igniting the organic solvent or polymer. Briefly, the protein particle-polymer solution suspension is pumped into the spray dryer at a rate of about 5 mL/min to about 20 mL/min, or about 12.5 mL/min. The suspension was pumped at 12.5 mL/min into the spray dryer with an aspirator air and spray gas flow rate of about 530 L/h and 35 m³/h (mm), respectively. The inlet temperature was set at 90° and the outlet temperature was set at about 54°C. The inlet temperature of the spray dryer is set at a temperature above the flash point of the solvent, such as *e.g.*, at about 90°C. The outlet temperature at a temperature below the intake temperature and above ambient temperature, such as *e.g.*, about 54°C. In one particular embodiment, a suspension containing about 50 mg/mL of protein particle (*e.g.*, VEGF Trap) in about 50 mg/mL to about 250 mg/mL polymer/ethyl acetate solution is pumped into a BÜCHI Mini Spray Dryer B-290 at about 12.5 mL/min, with an inlet temperature of about 90°C and an outlet temperature of about 54°C, with the aspirator set at about 35 m³/h and the spray gas at about 530 L/h.

[0068] The resulting microparticles, which contain a protein particle core within a polymer cortex, have a range of diameters of from about 2 µm to about 70 µm, about 5 µm to about 65 µm, about 10 µm to about 60 µm, about 15 µm to about 55 µm, about 20 µm to about 50 µm, about 15 µm, about 20 µm, about 25 µm, or about 30 µm. The size variation in large part reflects the thickness of the polymer cortex, although the diameter of the protein core could contribute to size variation to some extent. Manipulating the starting concentration of the polymer solution, and/or the polymer itself can control the diameter of the microparticle. For example, those microparticles which were manufactured using 50 mg/mL polymer have a median size of about 15 µm to 20 µm, whereas those microparticles which were manufactured using 250 mg/mL polymer had a median size of about 30 µm.

[0069] The microparticles in the formulation of the invention are useful in the time-release or

extended release of protein therapeutics. For example, it is envisioned that the VEGF Trap microparticles are useful in the extended release of VEGF Trap therapeutic protein in, for example, the vitreous for the treatment of vascular eye disorders, or subcutaneous implantation for the extended release of VEGF Trap to treat cancer or other disorders.

[0070] The microparticles in the formulation of the instant invention release protein in a physiological aqueous environment at about 37°C at a relatively constant rate over an extended period of time, to at least 60 days. In general, those microparticles manufactured with a higher concentration of polymer (e.g., 250 mg/mL) tended to show a relatively linear protein release profile; whereas those microparticles manufactured with a lower concentration of polymer (e.g., 50 mg/mL) tended to show an initial burst followed by an onset of a delayed burst release. Furthermore, microparticles formed from a higher concentration of polymer showed a slower rate of release of protein than those formed from a lower concentration of particles. The quality of protein released from the microparticles over time was consistent with the quality of the starting protein material. Little to no protein degradation occurred.

EXAMPLES

[0071] The following examples are put forth so as to provide those of ordinary skill in the art with a complete disclosure and description of how to make and use the methods and compositions of the invention. Efforts have been made to ensure accuracy with respect to numbers used (e.g., amounts, sizes, etc.) but some experimental errors and deviations should be accounted for.

[0072] In the following examples, VEGF-Trap protein ("VGT"), which is a dimer of the polypeptide comprising the amino acid sequence SEQ ID NO:1, serves as an exemplar receptor-Fc-fusion protein.

EXAMPLE 1: MICRONIZED PROTEINS

[0073] Solutions containing 25 mg/mL VEGF Trap protein ("VGT"), 25 mg/mL VGT plus 0.1% polysorbate 80, and 50 mg/mL VGT in 10 mM phosphate, 2% sucrose, pH 6.2 were each independently atomized in a spray dry micronizer (BÜCHI Mini Spray Dryer B-290, Buchi Labortechnik AG, Flawil, CH) to form droplets containing VEGF Trap. Heat was applied to evaporate the water from the droplets, resulting in a powder containing VEGF Trap. The inlet temperature was set at 130°C and outlet temperature at about 55°C. The aspirator was set at 33 m³/h and spray gas at 530 L/h. The VGT solution was pumped at about 7 mL/min.

[0074] The size of the resultant VGT particles was measured by micro-flow imaging (MFI) and dynamic light imaging (DLS). Figure 1 depicts the particle size distribution as determined by MFI for the VGT particles derived from each of the 25 mg/mL VGT, 25 mg/mL VGT plus 0.1%

polysorbate 80, and 50 mg/mL VGT concentrations. For all concentrations, the equivalent circular diameter (ECD) of VGT particles ranged from about 1 μm to about 39 μm , with the majority of particles ranging in size of from about 2 μm to about 14 μm . For the 25 mg/mL VGT solution, the particles clustered in the range of about 2.5 μm to about 8.8 μm , with a mode of about 6 μm . For the 25 mg/mL VGT plus 0.1% polysorbate 80 solution, the particles clustered in the range of about 2.5 μm to about 9.7 μm , with a mode of about 6 μm . For the 50 mg/mL VGT solution, the particles clustered in the range of about 2.7 μm to about 12.8 μm , with a mode of about 7 μm . Median diameters for each formulation, as determined by both MFI and DLS methods, are described in Table 1.

[0075] VGT particles were reconstituted in water for injection and examined via size exclusion, *i.e.*, size exclusion - ultra performance liquid chromatography (SE-UPLC) to determine protein purity. No change in purity was noted after micronization relative to starting material (see Table 3).

Table 1: Median protein particle sizes (μm) as determined by MFI and DLS

Formulation	Median size by MFI (μm)	Median size by DLS (μm)
50mg/mL VEGF Trap	7	7.6
25mg/mL VEGF Trap	6	5.9
25mg/mL VEGF Trap, 0.1% polysorbate 80	6	7.1

EXAMPLE 2: MICRONIZED PROTEIN SUSPENSIONS IN ORGANIC POLYMER SOLUTIONS

[0076] Various polymers were used or are contemplated for use in the manufacture of the polymer cortex of the microparticles. Those polymers include *inter alia* ethyl cellulose ("EC"), polyorthoester ("POE"), poly-D,L-lactide-co-glycolide ("PLGA"), and poly- ϵ -caprolactone ("PCL").

Ethyl cellulose coating

[0077] Micronized VEGF Trap particles were suspended in a solution of 50 mg/mL ethyl cellulose in ethyl acetate at a concentration of about 50 mg/mL VGT; herein designated "VGT-50-EC suspension".

[0078] Micronized VEGF Trap particles were suspended in a solution of 100 mg/mL ethyl cellulose in ethyl acetate at a concentration of about 50 mg/mL VGT; herein designated "VGT-100-EC suspension".

[0079] Micronized VEGF Trap particles are suspended in a solution of 250 mg/mL ethyl

cellulose in ethyl acetate at a concentration of about 50 mg/mL VGT; herein designated "VGT-250-EC suspension".

Polyorthoester coating

[0080] Micronized VEGF Trap particles were suspended in a solution of 50 mg/mL polyorthoester containing about 5% latent acid in ethyl acetate at a concentration of about 50 mg/mL VGT; herein designated "VGT-50-POE suspension".

[0081] Micronized VEGF Trap particles were suspended in a solution of 250 mg/mL polyorthoester containing about 5% latent acid in ethyl acetate at a concentration of about 50 mg/mL VGT; herein designated "VGT-250-POE suspension".

Poly-D,L-lactide-co-glycolide coating

[0082] Micronized VEGF Trap particles were suspended in a solution of 50 mg/mL PLGA in ethyl acetate at a concentration of about 50 mg/mL VGT; herein designated "VGT-50-PLGA suspension".

[0083] Micronized VEGF Trap particles were suspended in a solution of 200 mg/mL PLGA in ethyl acetate at a concentration of about 50 mg/mL VGT; herein designated "VGT-200-PLGA suspension".

[0084] Micronized VEGF Trap particles were suspended in a solution of 250 mg/mL PLGA in ethyl acetate at a concentration of about 50 mg/mL VGT; herein designated "VGT-250-PLGA suspension".

Poly- ϵ -caprolactone coating

[0085] Micronized VEGF Trap particles are suspended in a solution of 50 mg/mL PCL in ethyl acetate at a concentration of about 50 mg/mL VGT; herein designated "VGT-50-PCL suspension".

[0086] Micronized VEGF Trap particles are suspended in a solution of 250 mg/mL PCL in ethyl acetate at a concentration of about 50 mg/mL VGT; herein designated "VGT-250-PCL suspension".

[0087] PCL has a low Tg and may not be suitable for heat-drying as described below, but can be used for solvent extraction in an aqueous bath with polyvinyl alcohol (PVA), for example.

EXAMPLE 3: DISPERSION OF PROTEIN-POLYMER FINE DROPLETS AND SOLVENT REMOVAL

[0088] Each VGT polymer suspension, which was made according to Example 2 (*supra*), was subjected to spray drying using a BÜCHI Mini Spray Dryer B-290 (Buchi Labortechnik AG, Flawil, CH). Briefly, each suspension was atomized to form microdroplets, which were subsequently heat dried to remove the solvent and form the polymer-coated protein microparticles. The suspension was pumped at 12.5 mL/min into the spray dryer with an aspirator air and spray gas flow rate of about 530 L/h and 35 m³/h, respectively. The inlet temperature was set at 90° and the outlet temperature was set at about 54°C.

EXAMPLE 4: CHARACTERIZATION OF PROTEIN-POLYMER MICROPARTICLES

[0089] Spray dried polymer coated protein particles manufactured according to the exemplified process generate a plurality of microparticles having a range of equivalent circular diameters of from about 2.5 µm to about 65 µm (Figure 2). The size variation in large part reflects the thickness of the polymer cortex, although the diameter of the protein core could contribute to size variation to some extent.

[0090] The diameter of the microparticle correlates with the starting concentration of the polymer solution (Table 2, Figure 2). Those microparticles which were manufactured using 50 mg/mL polymer had a median size of about 17 µm ± 2.8 µm. Those microparticles which were manufactured using 250 mg/mL polymer had a median size of about 29 µm.

EXAMPLE 5: PROTEIN STABILITY POST SPRAY DRY

[0091] The stability of the VEGF-Trap protein was assessed using quantitative size exclusion chromatography (SE-UPLC), which allows for the quantification of smaller degradation products and larger aggregation products relative to the intact monomer. The results are described in Table 3. Essentially, the protein remained stable throughout the spray drying and spray coating processes.

[0092] The average ratio of protein to polymer by weight was also determined for the manufactured microparticles. A collection of microparticles manufactured with varying polymers and polymer concentration was extracted and subjected to quantitative reverse phase chromatography (RP-HPLC). The results are presented in Table 3. The data may be interpreted to support the theory that a higher starting concentration of polymer yields a thicker polymer cortex on the microparticle.

Table 2: Equivalent circular diameter values

Material	Range (μm)	Median (μm)	Mode (μm)
VEGF-Trap ("VGT") (50 mg/mL)	2.5 - 29.4	10 - 12	8.3
VGT (50 mg/mL) + POE (50 mg/mL)	2.5 - 64.5	15	9.4
VGT (50 mg/mL) + POE (250 mg/mL)	2.5 - 49.4	29	28.5
VGT (50 mg/mL) + EC (50 mg/mL)	2.5 - 49.6	19	16.5

Table 3: Protein stability and loading

Material	VGT starting material	VGT Extracted from Coated Polymers ¹	
		% Native ²	% w/w VGT/polymer ³
VGT starting material	97.7	-	-
Reconstituted VGT	97.6	-	-
VGT (50 mg/mL) + POE (50 mg/mL)	-	96.3	14.6
VGT (50 mg/mL) + POE (250 mg/mL)	-	97.7	1.8
VGT (50 mg/mL) + EC (50 mg/mL)	-	97.1	6.1

¹Based on extracted VEGF Trap after 1 hour reconstitution to remove uncoated VEGF Trap.
²Average of percent native by SE-UPLC (n=4).
³Average of percent weight to weight loading of VGT to polymer by RP-HPLC (n=4).

EXAMPLE 6: PROTEIN RELEASE FROM MICROPARTICLES

[0093] The release of protein from microparticles was determined by suspending various batches of microparticles in buffer (10 mM phosphate, 0.03% polysorbate 20, pH 7.0) and measuring the amount and quality of protein released into solution over time while incubated at 37°C. At 1-2 week intervals, the microparticles were pelleted by mild centrifugation and 80% of the supernatant containing released protein was collected for subsequent analysis. An equivalent amount of fresh buffer was replaced and the microparticles were resuspended by mild vortexing and returned to the 37°C incubation chamber. Protein amount and quality in the supernatant was assessed by size exclusion chromatography.

[0094] In general, those microparticles manufactured with a higher concentration of polymer (e.g., 250 mg/mL) tended to show a relatively linear protein release profile; whereas those microparticles manufactured with a lower concentration of polymer (e.g., 50 mg/mL) tended to

show an initial burst followed by an onset of a delayed burst release. The data showing the extended release of protein, which remained stable, for up to about 60 days is depicted in Figure 3 (release data). Table 4 summarizes the linear rate-of-release data.

Table 4: Protein release dynamics

Material	VEGF Trap protein release (mg VGT/week)
VGT (50 mg/mL) + POE (50 mg/mL)	0.14 ± 0.16
VGT (50 mg/mL) + POE (250 mg/mL)	0.06 ± 0.02
VGT (50 mg/mL) + EC (50 mg/mL)	0.031 ± 0.02

EXAMPLE 7: PARTICLE SIZE CAN BE MANIPULATED BY POLYMER CONCENTRATION AND SPRAY GAS FLOW

[0095] Particle size distributions were controlled by polymer concentration and atomization spray gas flow. Increased polymer concentration shifted the distribution towards larger particles (200 mg/mL PLGA at 45 mm spray gas flow v. 100 mg/mL PLGA at 45 mm spray gas flow; see Table 5). Similarly, a lower atomization spray gas flow resulted in larger droplets and thus, larger particles (100 mg/mL PLGA at 25 mm spray gas flow v. 100 mg/mL PLGA at 45 mm spray gas flow; see Table 5).

Table 5: Particle Size (all metrics are approximate)

[PLGA] (mg/mL)	Gas Flow Rate (m ³ /h)	Particle size range (microns)	Mode of particle size (microns)	Percent total volume of particles with 15 micron particle size
Protein alone	NA	2.5-25	3.5	1.5%
100	25	2.5-40	9.4	3.7%
100	45	2.5-30	9.4	3.7%
200	45	2.5-30	10.2-15.4	5.4%

EXAMPLE 8: PARTICLE SIZE AND PROTEIN RELEASE ACROSS VARIOUS POLYMERS

[0096] VEGF Trap or IgG was spray coated with low molecular weight (202S) poly(lactic acid) (PLA-LMW), high molecular weight (203S) poly(lactic acid) (PLA-HMW), polyanhydride poly[1,6-bis(p-carboxyphenoxy)hexane] (pCPH), poly(hydroxbutyric acid-cohydroxyvaleric acid) (PHB-PVA), PEG-poly(lactic acid) block copolymer (PEG-PLA), and poly-D,L-lactide-co-glycolide (PLGA). 25 mg/mL of spray-dried protein was combined with 50-100 mg/mL polymer. In vitro release assays were performed in 10 mM phosphate buffer, pH7.2 at 37°C. The results are depicted in Table 6.

Table 6: Polymer dependent particle size and protein release (all metrics are approximate)

Polymer	Protein	Relative number of particles at 15 microns	Time to 100% protein release
PLA-LMW	VEGF Trap	0.8×10^2	3 days
PLA-HMW	VEGF Trap	0.8×10^2	3 days
pCPH	VEGF Trap	1×10^2	3 days
PHB-PVA	VEGF Trap	5×10^2	1 days
PEG-PLA	VEGF Trap	0.6×10^2	6 hours
PLGA	IgG	1×10^2	8 days

EXAMPLE 9: PROTEIN STABILITY IN VARIOUS POLYMERS

[0097] VEGF Trap and IgG were extracted from their respective polymer coats and measured for purity by SE-UPLC. The results are summarized in Table 7. The proteins generally were compatible with the spray coating process for the polymers tested. Protein remained stable for at least 14 days for those polymers that continued to release protein.

Table 7

Protein	Polymer	% Purity by Size Exclusion Chromatography			
		After spray coating	1 day in vitro release (IVR)	3 days IVR	14 days IVR
VEGF Trap	POE (AP141)	97.7	98.3	98.2	96.7
VEGF Trap	PLA-LMW	97.0	97.4	92.8	-
VEGF Trap	PLA-HMW	93.9	97.3	95.4	-
VEGF Trap	PEG-PLA	89.9	91.2	-	-
VEGF Trap	pCPH	89.2	94.2	84.8	-
VEGF Trap	PHB-PVA	97.4	96.2	-	-
VEGF Trap	PLGA	96.6	97.8	-	93.6
IgG	PLGA	99.2	98.0	-	92.0

SEQUENCE LISTING

[0098]

<110> Regeneron Pharmaceuticals, Inc.

<120> Polymer Protein Microparticles

<130> 1110A

<140> Not available

<141> 2012-11-18

<150> US 61/561,525

<151> 2011-11-18

<160> 1

<170> PatentIn version 3.5

<210> 1

<211> 415

<212> PRT

<213> Artificial Sequence

<220>

<223> synthetic

<400> 1

Ile	Ile	His	Met	Thr	Glu	Gly	Arg	Glu	Leu	Val	Ile	Pro	Cys	Arg	Val
1					5				10					15	

Thr	Ser	Pro	Asn	Ile	Thr	Val	Thr	Leu	Lys	Lys	Phe	Pro	Leu	Asp	Thr
					20			25					30		

Leu	Ile	Pro	Asp	Gly	Lys	Arg	Ile	Ile	Trp	Asp	Ser	Arg	Lys	Gly	Phe
					35			40				45			

Ile	Ile	Ser	Asn	Ala	Thr	Tyr	Lys	Glu	Ile	Gly	Leu	Leu	Thr	Cys	Glu
					50			55				60			

Ala	Thr	Val	Asn	Gly	His	Leu	Tyr	Lys	Thr	Asn	Tyr	Leu	Thr	His	Arg
					65			70		75			80		

Gln	Thr	Asn	Thr	Ile	Ile	Asp	Val	Val	Leu	Ser	Pro	Ser	His	Gly	Ile
						85			90				95		

Glu	Leu	Ser	Val	Gly	Glu	Lys	Leu	Val	Leu	Asn	Cys	Thr	Ala	Arg	Thr
					100			105				110			

Glu Leu Asn Val Gly Ile Asp Phe Asn Trp Glu Tyr Pro Ser Ser Lys
115 120 125

His Gln His Lys Lys Leu Val Asn Arg Asp Leu Lys Thr Gln Ser Gly
130 135 140

Ser Glu Met Lys Lys Phe Leu Ser Thr Leu Thr Ile Asp Gly Val Thr
145 150 155 160

Arg Ser Asp Gln Gly Leu Tyr Thr Cys Ala Ala Ser Ser Gly Leu Met
165 170 175

Thr Lys Lys Asn Ser Thr Phe Val Arg Val His Glu Lys Asp Lys Thr
180 185 190

His Thr Cys Pro Pro Cys Pro Ala Pro Glu Leu Leu Gly Gly Pro Ser
195 200 205

Val Phe Leu Phe Pro Pro Lys Pro Lys Asp Thr Leu Met Ile Ser Arg
210 215 220

Thr Pro Glu Val Thr Cys Val Val Val Asp Val Ser His Glu Asp Pro
225 230 235 240

Glu Val Lys Phe Asn Trp Tyr Val Asp Gly Val Glu Val His Asn Ala
245 250 255

Lys Thr Lys Pro Arg Glu Glu Gln Tyr Asn Ser Thr Tyr Arg Val Val
260 265 270

Ser Val Leu Thr Val Leu His Gln Asp Trp Leu Asn Gly Lys Glu Tyr
275 280 285

Lys Cys Lys Val Ser Asn Lys Ala Leu Pro Ala Pro Ile Glu Lys Thr
290 295 300

Ile Ser Lys Ala Lys Gly Gln Pro Arg Glu Pro Gln Val Tyr Thr Leu
305 310 315 320

Pro Pro Ser Arg Asp Glu Leu Thr Lys Asn Gln Val Ser Leu Thr Cys
325 330 335

Leu Val Lys Gly Phe Tyr Pro Ser Asp Ile Ala Val Glu Trp Glu Ser
340 345 350

Asn Gly Gln Pro Glu Asn Asn Tyr Lys Thr Thr Pro Pro Val Leu Asp
355 360 365

Ser Asp Gly Ser Phe Phe Leu Tyr Ser Lys Leu Thr Val Asp Lys Ser
370 375 380

Arg Trp Gln Gln Gly Asn Val Phe Ser Cys Ser Val Met His Glu Ala
385 390 395 400

Leu His Asn His Tyr Thr Gln Lys Ser Leu Ser Leu Ser Pro Gly
405 410 415

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US2011104151A [0005]
- US2008305115A [0005]
- WO03092665A [0005]
- US7998477B [0040]
- US6063910A [0040]
- US6927004B [0043]
- US7087411B [0043]
- US7279159B [0043]
- US4210529A [0045]
- US4304767A [0048]
- US5968543A [0048]
- US4764364A [0048]
- US7365165B [0051]
- US7572893B [0051]
- US7608261B [0051]
- US7655758B [0051]
- US7807164B [0051]
- US20100279933A [0051]
- US20110171241A [0051]
- US1154856W [0051]
- US61561525B [0098]

Non-patent literature cited in the description

- **KIM et al.** *Biomaterials*, 2009, vol. 30, 5902-909 [0005]
- **SHARMA et al.** *Micro-flow imaging: flow microscopy applied to subvisible particulate*

analysis in protein formulations AAPS J., 2010, vol. 12, 3455-64 [0038]

- HUANG, C. Curr. Opin. Biotechnol., 2009, vol. 20, 692-99 [0039]
- RUTH et al. Acta Crystallographica, 2000, vol. D56, 524-28 [0040]
- MORITA et al. Pharma. Res., 2000, vol. 17, 1367-73 [0040]
- BUSTAMI et al. Pharma. Res., 2000, vol. 17, 1360-66 [0040]
- ASHKENAZI et al. Proc. Natl. Acad. Sci. USA, 1991, vol. 88, 10535- [0043]
- BYRN et al. Nature, 1990, vol. 344, 677- [0043]
- HOLLENBAUGH et al. Construction of Immunoglobulin Fusion Proteins Current Protocols in Immunology, 1992, vol. 4, 10.19.1-10.19.11 [0043]
- MARTINAC et al. J. Microencapsulation, 2005, vol. 22, 5549-561 [0045]
- ASTETESABLIOV Biomater. Sci. Polym. Ed., 2006, vol. 17, 3247-89 [0046]
- LABETTHIELEMANS Chemical Society Reviews, 2009, vol. 38, 3484-3504 [0047]
- SINHA et al. Int. J. Pharm., 2004, vol. 278, 11-23 [0047]
- HELLERBARR Biomacromolecules, 2004, vol. 5, 51625-32 [0048]
- HELLER Adv. Drug. Deliv. Rev., 2005, vol. 57, 2053-62 [0048]

PATENTKRAV

1. Farmaceutisk formulering med forlænget frigivelse til anvendelse i glaslegemet til behandling af vaskulære øjenlidelser, hvilken farmaceutisk formulering omfatter mikropartikler med en diameter på fra 2 mikron til 70 mikron, 5 hvilke mikropartikler har en proteinpartikelkerne inde i en polymerskal, hvor proteinpartiklen indeholder mindre end 3 % vand efter vægt, hvor mikropartiklerne frigiver proteinet i et fysiologisk vandigt miljø ved ca. 37 °C ved en rate på ca. 0,01 mg/uge til ca. 0,30 mg/uge over mindst 60 dage.
2. Farmaceutisk formulering med forlænget frigivelse til anvendelse ifølge 10 krav 1, hvor polymerskallen omfatter polyorthoester (POE) og den stabile frigivelsesrate er fra 0,01 mg/uge til 0,30 mg/uge.
3. Farmaceutisk formulering med forlænget frigivelse til anvendelsen ifølge et hvilket som helst af de foregående krav, hvor proteinet:
 - (a) er et antigenbindingsprotein;
 - 15 (b) omfatter et Fc-domæne;
 - (c) er et antistof eller et receptor-Fc-fusionsprotein; og/eller
 - (d) er et antistoffragment.
4. Farmaceutisk formulering med forlænget frigivelse til anvendelse ifølge krav 3, hvor:
 - 20 (a) proteinet er en receptor-Fc-fusion, der er en VEGF-Trap; eller
 - (b) et antistof, der er et humant monoklonalt antistof.
5. Farmaceutisk formulering med forlænget frigivelse til anvendelsen ifølge et hvilket som helst af de foregående krav, hvor polymeren er en biologisk nedbrydelig polymer.
- 25 6. Farmaceutisk formulering med forlænget frigivelse til anvendelsen ifølge et hvilket som helst af de foregående krav, hvor polymeren er udvalgt fra gruppen bestående af poly(mælkesyre) (PLA), polyanhydrid poly[1,6-bis(p-carboxyphenoxy)hexan] (pCPH), poly(hydroxysmørtsyre-cohydroxyvalerianesyre) (PHB-PVA), polyethylenglycol-poly(mælkesyre)copolymer (PEG-PLA), poly-D,L-

lactid-co-glycolid (PLGA), polyorthoester (POE), ethylcellulose (EC) og poly- ϵ -caprolacton (PCL).

7. Farmaceutisk formulering med forlænget frigivelse til anvendelse ifølge krav 2, hvor polymeren er POE ved 50 mg/ml, proteinet er VEGF-Trap ved 50 mg/ml, det gennemsnitlige forhold mellem protein og polymer er 14,6 efter vægt, partiklens modalstørrelse er 9,4 mikron, mindst 96,3 % af proteinet bevarer dets native konformation bestemt ved størrelseseksklusionskromatografi, og proteinet frigives fra polymerskallen ved en rate på $0,14 \pm 0,16$ mg/uge.

8. Farmaceutisk formulering med forlænget frigivelse til anvendelse ifølge krav 2, hvor polymeren er POE ved 250 mg/ml, proteinet er VEGF-Trap ved 50 mg/ml, det gennemsnitlige forhold mellem protein og polymer er 1,8 efter vægt, partiklens modalstørrelse er 28,5 mikron, mindst 97,7 % af proteinet bevarer dets native konformation bestemt ved størrelseseksklusionskromatografi, og proteinet frigives fra polymerskallen ved en rate på $0,06 \pm 0,02$ mg/uge.

9. Farmaceutisk formulering med forlænget frigivelse til anvendelse ifølge krav 2, hvor polymeren er EC ved 50 mg/ml, proteinet er VEGF-Trap ved 50 mg/ml, det gennemsnitlige forhold mellem protein og polymer er 6,1 efter vægt, partiklens modalstørrelse er 16,5 mikron, mindst 97,1 % af proteinet bevarer dets native konformation bestemt ved størrelseseksklusionskromatografi, og proteinet frigives fra polymerskallen ved en rate på $0,031 \pm 0,02$ mg/uge.

10. Farmaceutisk formulering med forlænget frigivelse til anvendelse ifølge krav 2, hvor polymeren er PLGA, proteinet er IgG, og mindst 92 % af proteinet bevarer dets native konformation efter 14 dage bestemt ved størrelseseksklusionskromatografi.

11. Farmaceutisk formulering med forlænget frigivelse til anvendelse ifølge krav 2, hvor polymeren er POE (AP141), proteinet er VEGF-Trap og mindst 96,7 % af proteinet bevarer dets native konformation efter 14 dage bestemt ved størrelseseksklusionskromatografi.

12. Farmaceutisk formulering med forlænget frigivelse til anvendelse ifølge et hvilket som helst af de foregående krav til anvendelse i en fremgangsmåde til behandling af en øjensygdom.

13. Fremgangsmåde til fremstilling af en farmaceutisk formulering med
5 forlænget frigivelse til anvendelse ifølge krav 1 omfattende trinnene med (a) opnåelse af en proteinkerne ved spraytørring af en opløsning indeholdende proteinet; (b) suspension af proteinpartiklen i en opløsning omfattende en polymer og et opløsningsmiddel; og (c) fjernelse af opløsningsmidlet ved fordampning.

14. Fremgangsmåde ifølge krav 13, hvor proteinet er et antistof eller et
10 receptor-Fc-fusionsprotein.

DRAWINGS

FIGURE 1




FIGURE 2




FIGURE 3

