



(11) **EP 2 118 181 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
30.03.2011 Bulletin 2011/13

(51) Int Cl.:
C08J 7/04 ^(2006.01) **F16C 33/18** ^(2006.01)
C08J 5/04 ^(2006.01) **C08J 5/16** ^(2006.01)

(21) Application number: **08709393.6**

(86) International application number:
PCT/GB2008/000499

(22) Date of filing: **13.02.2008**

(87) International publication number:
WO 2008/099173 (21.08.2008 Gazette 2008/34)

(54) **BEARING COMPONENTS AND PROCESSES FOR DEPOSITING ADDITIVES, ESPECIALLY FLUOROPOLYMERS, ON CELLULOSE**

LAGERBAUTEILE UND VERFAHREN ZUR ABSCHIEDUNG VON ADDITIVEN, INSBESONDERE FLUORPOLYMEREN, AUF CELLULOSE

COMPOSANTS POUR PALIERS ET PROCÉDÉS DE DÉPÔT D'ADDITIFS, ET NOTAMMENT DE FLUOROPOLYMÈRES, SUR DE LA CELLULOSE

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HR HU IE IS IT LI LT LU LV MC MT NL NO PL PT
RO SE SI SK TR**

(30) Priority: **13.02.2007 GB 0702795**

(43) Date of publication of application:
18.11.2009 Bulletin 2009/47

(73) Proprietor: **Whitford Ltd.**
Manor Park
Runcorn
WA7 1ST (GB)

(72) Inventors:
• **MELVILLE, Andrew, J.**
Cheshire (GB)
• **TOPPING, David, J.**
Merseyside (GB)
• **WILLIS, David, P**
Downingtown, Pennsylvania 19335 (US)

(74) Representative: **Barrett, Jennifer Catherine et al**
Kilburn & Strode LLP
20 Red Lion Street
London WC1R 4PJ (GB)

(56) References cited:
WO-A-98/58986 DE-A1- 10 324 232
JP-A- 2006 312 688 US-A- 3 560 065

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 2 118 181 B1

Description

Technical Field

[0001] The present invention relates to bearing components, especially flexible bearing components, having a bearing surface and comprising cellulose and a fluoropolymer and to methods for applying an additive, for example a hydrophobic fluoropolymer, to cellulose.

Background Art

[0002] Cellulose is a readily available substance which can be used to manufacture a range of articles. There are a number of advantages to using cellulose when manufacturing articles, which include its relatively low cost, and the fact that it is environmentally friendly.

[0003] Fluoropolymers are well-known and can be used to modify materials, in particular the surface properties of manufactured articles. For example, it is common to apply fluoropolymers such as polytetrafluoroethylene (PTFE) to metal articles to obtain low surface-energy coatings imparting a lubricated and water-repellent character to the surface of the article, e.g. these coatings can be used to produce "non-stick" cookware or low friction bearings. However, it is difficult to apply some additives, including fluoropolymers, to cellulose-based articles, because cellulose degrades at the temperatures commonly required to process them.

[0004] Bearings are well known that include a bearing surface provided by a flexible sheet or tube, which is usually made of materials impregnated with a lubricant, such as wax, PTFE or oil. The sheet or tube is placed between the moving parts of the bearing and allows these parts to move relative to each other. This design is often used in bearings that are not subject to large forces, e.g. in the joints or support arms of car tailgates, air-cylinders rotary valves and actuators. If the bearing surface has deteriorated or become worn, the sheet or tube may be replaced.

[0005] It is known from GB-1144048 that aqueous N-methylmorpholine N-oxide (NMMO) and other cyclic amine oxides will dissolve cellulose when mixed with water and this property is exploited in the spinning of cellulose yarn (see for example US-4246221). The use of aqueous NMMO in industrial processes has a number of advantages. NMMO has low toxicity and when it is used as a solvent it is possible to recycle it around the process streams. 50% solutions of NMMO in water are commercially available from the Huntsman Corporation of 10003 Woodloch Drive, The Woodlands, TX77380, USA.

[0006] Figure 1 is a phase diagram of water/NMMO/cellulose at standard temperature and pressure. The shaded region indicates the concentrations at which an aqueous solution of NMMO dissolves cellulose. Outside the shaded area, cellulose exists as a solid. Within the shaded area, cellulose can also exist as a solid if present in excess, e.g. >12wt% cellulose.

[0007] The aim of the present invention is to provide

bearing components comprising cellulose and a fluoropolymer and methods by which certain additives such as fluoropolymers can be applied to solid cellulose.

Disclosure of the Invention

[0008] According to the present invention, there is provided a bearing component, especially a flexible bearing component, having a bearing surface, the bearing component comprising a mat comprising cellulose fibres and a fluoropolymer, wherein at least some of the fluoropolymer is located at the bearing surface and is adhered to the cellulose. Optionally, the fluoropolymer is coated on, or incorporated into the surface of, individual fibres of the mat.

[0009] The surface fluoropolymer may be in the form of a coat on the surface of the mat forming the bearing surface. Alternatively, the fluoropolymer may be incorporated into the cellulose mat so that some of the fluoropolymer is present at the bearing surface. The fluoropolymer may be present across the whole of the bearing surface or it may be discontinuous. This may be achieved by the method of applying a fluoropolymer to cellulose, as described below.

[0010] The mat may include materials other than cellulose fibres, for example reinforcing fibres made of other material, cellulose in a non-fibre form, e.g. powdered cellulose, as well as fillers, pigments, co-resins, dispersing agents and other additives used in paper-making art.

[0011] The component may be incorporated into any suitable known bearing to provide the bearing surface

[0012] The bearing component may be any particular shape or size, depending on the practical application.. The cellulose mat on which the bearing surface is formed may be flexible, stiff or rigid, e.g. it could be paper or cellulose board, depending on its application. An advantage of making a bearing component using a mat of cellulose fibres, e.g. paper, as a substrate, is that the cost of the bearing component is relatively low. Also, the bearing component according to the invention may be used for repairing worn bearing surfaces, either temporarily or permanently, and can easily be cut to size as required.

[0013] The bearing component according to the invention is useable at high temperatures, up to around 220°C.

[0014] Also according to the present invention, there is provided a method of applying a fluoropolymer to a mat comprising cellulose fibres, which method comprises the following steps:

- (a) applying a dispersion of the fluoropolymer on a surface of the mat of cellulose fibres, and
- (b) pressing the mat of cellulose fibres, e.g. by calendering it, such that the fluoropolymer is coated onto, and adheres to, the surface of the cellulose mat.

[0015] The fluoropolymer may be PTFE, fluoroethylene-propylene (FEP), perfluoroalkoxy resin (PFA), perfluoromethyl vinyl ether (MFA), polyvinylidene fluoride

(PVDF), ethylene tetrafluoroethylene (ETFE), ethylene chlorotrifluoroethylene (ECTFE), or tetrafluoroethylene-hexafluoropropylene-vinylidene fluoride (THV) or may be a mixture of these or other fluoropolymers.

[0016] The fluoropolymer may be in an aqueous dispersion and may be in the form of particles that typically have a particle size in the range of 50nm to 10 μ m; the and the typical thickness of the cellulose fibres in the mat is 5 to 20 μ m but larger or thinner fibres can also be used.

[0017] Step (a) may be carried out by means of directly applying the suspension to the cellulose fibre mat at a controlled rate, e.g. by spraying or using an application roller or doctor blade.

[0018] Step (b) is preferably carried out at a temperature of 150 to 250°C at a pressure of 1,000 to 2,000 lb/sq in (6.9 - 13.8 MPa)

[0019] Steps (a) and (b) can take place successively on a continuous production line.

[0020] The invention also extends to cellulose products to which a fluoropolymer has been applied by the above method according to the invention.

[0021] According to another aspect of the present invention, there is provided a further method of applying an additive, e.g. a fluoropolymer, to cellulose, which comprises the following steps:

(a) bringing solid cellulose, a solvent capable of dissolving cellulose and a dispersion of the additive into contact with each other, such that a surface layer of the solid cellulose is dissolved in the solvent; the solvent may be a mixture of water and another liquid, e.g. NMMO,

(b) contacting the dissolved cellulose with the additive, e.g. allowing to diffuse into contact with the dissolved cellulose, and

(c) altering the composition, quantity or temperature of the solvent such that the solubility of cellulose in the solvent is reduced and at least a portion of the dissolved cellulose comes out of solution, whereby the additive that has contacted the dissolved cellulose is incorporated into, or adheres to, the resulting solid cellulose.

[0022] In one embodiment of this aspect of the present invention, the additive is hydrophobic, e.g. a fluoropolymer. However, the invention can be used to add any additive that is insoluble in the solvent and is especially useful to add water-insoluble additives to cellulose. For example, the additive may be a fluoropolymer, including but not limited to PTFE or the other fluoropolymers mentioned above or a mixture of these or other fluoropolymers. The contact time, i.e. the duration of method steps (a) and (b), may be of the order of 10 minutes, but may be shorter or longer depending on the particular conditions. The additive may be combined with the solvent before carrying out the step (a) or it may be added once the solvent is in contact with the cellulose. Preferably, the additive is in the form of a micropowder or dispersion

grade particles, dispersed in a medium such as water. The additive particles may be round, rod-shaped or plate-like, or the additive may be fibrous.

[0023] The solvent may be a mixture of two liquids, e.g. water and another liquid; the mixture may be such that the solubility of cellulose in the mixture is dependent on the relative amounts of the two liquids in the mixture, for example the solvent may be capable of dissolving cellulose only within a restricted compositional range of the solvent mixture. This allows the cellulose to be brought out of solution in step (c) by altering the relative amounts of the two liquids. The alteration can for example be achieved by heating the mixture whereby the liquid with the lower boiling point will evaporate more rapidly than the other, thereby increasing the concentration of the latter in the solvent.

[0024] The solvent may be a mixture of water and a cyclic amine oxide, such as those disclosed in GB-1144048 and US-4246221. Of these, NMMO is preferred since it is commercially available.

[0025] One embodiment of this aspect of the present invention deserves special mention, namely the embodiment in which the solvent is a multi-component system (i.e. containing at least two components) and cellulose is soluble in the system only when the relative amounts of the components lie within restricted ranges; this will be described with reference to a water/NMMO solvent system, which is given by way of example only and it should again be borne in mind that other solvents can be used instead: In step (a) of the method, a water/NMMO mixture is brought into contact with cellulose and the amounts of water/NMMO are adjusted (if necessary) so that the mixture lies in the shaded area of the phase diagram of Figure 1, in which a surface layer of the cellulose dissolves in the solvent mixture. It is believed that the shaded area of Figure 1 corresponds to the area where NMMO monohydrate exists. The additive, which may be added to the water/NMMO mixture before or after contact with the cellulose, can then diffuse into contact with the cellulose solution. In step (c), the amounts of water and NMMO are adjusted to take the water/NMMO mixture out of the shaded area of the phase diagram in Figure 1, which causes the previously dissolved cellulose to come out of solution and fixes the additive within the cellulose. The adjustment of the amounts of water and NMMO in the solvent may be achieved by:

(i) heating the water/NMMO mixture, e.g. to a temperature of 80-100°C. Since water is more volatile than NMMO, water will be preferentially evaporated and the concentration of NMMO in the mixture will increase until the water/NMMO mixture falls outside the shaded area of Figure 1.

(ii) driving off both water and NMMO so that the amount of solvent is insufficient to dissolve the cellulose or

(iii) adding either NMMO or water. Possibility (iii) has the disadvantages of increasing the amounts of in-

redients used, causing difficulties with mixing and control of the process, and hindering the step of separating the cellulose from the water/NMMO.

[0026] When it is not possible to cause the cellulose to come out of solution by altering the relative amounts of the components in a multi-component solvent system, e.g. if a simple one-component solvent is used, option (ii) will generally be available to cause at least a portion of the dissolved cellulose to come out of solution.

[0027] When the solvent is NMMO, the amounts of water and NMMO in step (a) will generally be about 16 to 21 % water and 79 to 84% NMMO in order to dissolve cellulose, assuming that, apart from cellulose, no other materials are present. However, if there are other materials present, these proportions may be different.

[0028] It is possible to use the method on solid cellulose in any form, for example either on cellulose which has already been formed into a product such as paper, or on loose cellulose fibres. In this way it may be possible to modify the surface of cellulose fibres which may subsequently be incorporated into new paper products.

[0029] This method of the present invention may be performed on paper and other ready-formed cellulose products. An advantage of performing the method on cellulose already formed into paper is that it is possible to provide the additive in chosen discrete regions, surfaces and areas of the paper, whereby part of the paper is treated by the method while others are not. For example, if the additive is only required on the surface of a non-absorbent paper and not throughout the thickness of the paper, the selective application of the solvent and additive only to the surface of the paper means that only the cellulose at the surface incorporates the additive, which prevents waste of the additive materials used. At the same time, it allows the bulk properties of the paper, such as strength and density, to be retained. As a further example, it is possible to provide the additive to only one side of a piece of paper using the method of the present invention so that the two sides have different properties.

[0030] After the additive has been incorporated into the cellulose, any remaining solvent may be removed from the solidified cellulose by washing with water; in the case of NMMO this is readily achieved since it is hygroscopic and is readily diluted by water. Generally excess cold water will be used to remove the remaining solvent mixed in with the cellulose. The washing process is preferably such that the concentration of the solvent at the surface of the cellulose does not give rise to a solvent mixture that will dissolve a substantial amount of cellulose, or does so only fleetingly.

[0031] The process stream containing the solvent, e.g. NMMO, can be recovered and recycled for repeated use in the method of the present invention.

[0032] After washing is completed, the cellulose may be dried to remove water and residual solvent, resulting in cellulose or a cellulose-containing article, e.g. paper, having the additive, e.g. fluoropolymer, incorporated into

the surface of the solid cellulose. If the product is a paper, it may then be processed further, for example by calendering to smooth and compress the paper, or by other standard paper processing procedures.

[0033] The invention also extends to products comprising solid cellulose to which an additive has been applied by this method according to the invention.

[0034] In one embodiment of this method according to the invention, an aqueous solution of NMMO is contacted with solid cellulose in the form of paper, in the presence of an aqueous dispersion of fluoropolymer particles. The concentration of NMMO in the solution is increased by evaporation of water, to approach the concentration at which cellulose is dissolved (i.e. the shaded area of Figure 1). The surface layer of the solid cellulose in contact with the mixture then dissolves and the fluoropolymer diffuses throughout the liquid phase. Further water is then driven off so that at least some of the dissolved cellulose comes out of solution; the NMMO is then washed off and the paper is dried.

[0035] In the various aspects of the present invention where an additive, e.g. a fluoropolymer, is present on the surface of a cellulose substrate, the thickness of the additive layer may generally be of the order of 0.1 to 100 μm , e.g. 1 to 50 μm , whether the layer has been calendered or not.

Brief Description of the Drawings

[0036] The invention may be carried into practice in various ways and some embodiments will now be described by way of example, with reference to the accompanying drawings, in which:

Figure 1 is a phase diagram of water/NMMO/cellulose at standard temperature and pressure.

Figures 2 and 3 are scanning electron micrographs of paper before and after calendering (respectively); Figures 4 and 5 are scanning electron micrographs of PTFE coated on paper before and after calendering (respectively); and

Figure 6 is a scanning electron micrograph of PTFE coated on paper using deposition from NMMO; the micrograph is taken after calendering

Modes of Putting the invention into Operation

Example 1

[0037] An initial mixture of water and NMMO was combined with an aqueous dispersion of fluoropolymer particles, in the following proportions, where all percentages are expressed by weight:

- 35% of a dispersion of PTFE particles (Dyneon 5035 PTFE dispersion, particle size 200 nm)
- 55% of a commercially available NMMO solution in

water containing 55%NMMO

- 10% de-ionised water.

[0038] A batch of 223g of this mixture composition was made up.

[0039] The mixture was placed in a rotary evaporator to remove water from the mixture. The pressure in the flask was lowered and a water bath was used to heat the mixture to 88°C. The rotary speed was 100 revolutions/min. The water was removed slowly to avoid foam generation. 123g of water was removed. The concentration of NMMO in the resulting mixture was in the shaded area of Figure 1 and was capable of dissolving solid cellulose, and the viscosity of the mixture was suitable for easy application to paper.

[0040] The concentrated mixture was applied to the surface of dense, brown paper using an applicator bar. The concentrated mixture may be at room temperature or at an elevated temperature. The coated paper was then dried in an oven at 100°C for 10 minutes to remove further water, which causes at least some of the dissolved cellulose to solidify, i.e. come out of solution. Remaining NMMO was then washed away under a running tap for approximately 5 minutes. The paper was re-dried using a photodryer to avoid the paper shrinking or creasing, with the photodryer set at 100-120°C for a further 10 minutes. The dried paper was then calendered.

[0041] The coated paper produced contains PTFE particles, concentrated near the paper surface.

Example 2

[0042] A 50% solution of NMMO in water was placed in a rotary evaporator and 18.9% of the water was removed, leaving a solution containing 55% NMMO. The resulting solution was then combined with a dispersion of fluoropolymer particles in the following proportions:

- 77% NMMO solution (containing 55% NMMO)
- 23% of a PTFE particle dispersion having the same composition as that used in Example 1.

[0043] The concentration of the NMMO solution before incorporation of the fluoropolymer dispersion reduces foaming during evaporation in the rotary drier, as compared to the concentration of the NMMO solution in the presence of the fluoropolymer described in Example 1.

[0044] The mixture of these components was applied to the paper surface in the same way as in Example 1, but the concentration of NMMO in the mixture was too low to dissolve the cellulose since it is about at point X in the phase diagram of Figure 1. During a first drying step, which was conducted in an oven at 100°C, water was driven off and the concentration of NMMO was increased until eventually it was sufficient to dissolve the cellulose in the paper, e.g. it had a concentration of approximately point Y in Figure 1. This was in contrast to

the method of Example 1 where the concentration of NMMO was adjusted to one capable of dissolving cellulose before application to the paper.

[0045] The drying was continued until the amount of water driven off was below the shaded area in Figure 1, e.g. to point Z, where the dissolved cellulose had come out of solution. The paper was then washed, re-dried and calendered as described in Example 1.

[0046] As in Example 1, the coated paper produced contains PTFE particles, concentrated near the paper surface. A scanning electron micrograph (SEM) of the PTFE coated paper after calendering is shown in Figure 6.

Example 31

[0047] A length of dense, brown paper was fed through a calendering apparatus having a pair of flat calendering rollers. Immediately prior to passing between the calendering rollers, an aqueous dispersion of the PTFE was applied at room temperature to the surface of paper using an applicator bar to provide a layer of PTFE suspension approximately 6µm thick. The aqueous dispersion had the following composition:

- 35% of a dispersion containing 60% PTFE particles (Dyneon 5035 PTFE dispersion, particle size 200 nm)
- 65% de-ionised water.

[0048] After the paper was coated, it was passed through the calendering rollers where it was subject to a pressure of 1,000 to 2,000 lb/sq in (6.9 - 13.8 MPa) at a temperature of 150 to 250°C. During the calendering step, the deposited PTFE is caused to flow over the surface of the paper and in this way is coated onto, and adheres to, the surface of the paper.

[0049] Figures 2 and 3 are SEMs of the paper before and after calendering (respectively); Figures 4 and 5 are scanning electron micrographs of the PTFE-coated paper taken before and after calendering (respectively). As can be seen the calendered PTFE is flat and uniform.

[0050] The paper can be cut into discs using an industrial cutter or cut and rolled into cylinders to provide flexible bearing component; the PTFE surface provides an excellent bearing surface. In an emergency, where a bearing surface has failed, the sheet could be cut to shape, e.g. even using a pair of scissors, and inserted into the bearing to provide a temporary bearing surface that can be used for a time, possibly until a replacement spare part is obtained.

Example 4

[0051] The calendered PTFE coated paper made by the NMMO process of Example 2 and shown in Figure 6 was tested by cutting out a disc-shaped piece and adhering it onto a correspondingly shaped aluminium alloy

disc so that the PTFE faced outwardly; the disc carrying the PTFE paper was pressed against a further aluminium alloy disc and rotated at controlled speeds. During a series of tests, the coated paper was pressed against the plate with a pressure of 1MPa and rotated at speeds varying from 20 to 200 rpm. The PTFE surface of the paper was not worn in these tests and just appeared slightly polished.

[0052] The pressure velocity (PV) level of the PTFE paper was measured at 200rpm and was found to be 0.29 MPa.m/sec, which is well above the PV limit of many plastic bearings. The PV Level of typical plastic bearings materials is as follows:

nylon:	0.13
polycarbonate:	0.11
unfilled PTFE:	0.04
unfilled acetal:	0.11
phenolic resins:	0.18

Claims

1. A bearing component having a bearing surface, **characterised in that** the bearing component comprises a mat comprising cellulose fibres and a fluoropolymer, and wherein at least some of the fluoropolymer is located at the bearing surface and is adhered to the cellulose.
2. A bearing component according to claim 1, wherein at least some of the fluoropolymer is in the form of a coat on the cellulose fibres at the surface of the bearing component, and/or wherein at least some of the fluoropolymer is incorporated into the cellulose fibres at the surface of the bearing component.
3. A bearing component according to any preceding claim, wherein the fluoropolymer is selected from PTFE, FEP, PFA, MFA, PVDF, ETFE, ECTFE, THV or a mixture thereof.
4. A bearing component according to any preceding claim, wherein the bearing surface is planar or tubular.
5. Use of a bearing component according to any preceding claim, to provide a bearing surface in a bearing.
6. A method of applying a fluoropolymer, e.g. PTFE, FEP, PFA, MFA, PVDF, ETFE, ECTFE, THV, or a mixture thereof, to a mat comprising cellulose fibres, **characterised in that** the method comprises the steps of:

(a) applying a dispersion of the fluoropolymer

on a surface of the mat of cellulose fibres, wherein the dispersion of the fluoropolymer is optionally an aqueous dispersion, and
(b) pressing the mat of cellulose fibres, e.g. by calendering it, such that the fluoropolymer is coated onto, and adheres to, the said surface of the cellulose mat.

7. A method according to claim 6, wherein step (b) is carried out at a temperature in the range of 150 to 250°C, and/or at a pressure in the range of 1,000 to 2,000 lb/sq in (6.9 - 13.8 MPa).
8. A method of applying an additive, e.g. a fluoropolymer, to cellulose, **characterised in that** the method comprises the steps of:
 - (a) bringing solid cellulose, a solvent capable of dissolving cellulose and a dispersion of the additive into contact with each other, such that a surface layer of the solid cellulose is dissolved in the solvent;
 - (b) contacting the dissolved cellulose with the additive;
 - (c) altering the composition, quantity or temperature of the solvent such that the solubility of cellulose in the solvent is reduced and at least a portion of the dissolved cellulose comes out of solution, whereby the additive is incorporated into, or adheres to, the cellulose; and
 - (d) optionally removing the solvent from the solid cellulose by washing following step (c).
9. A method according to claim 8, further comprising the step of combining the additive with the solvent before step (a).
10. A method according to claim 8, wherein
 - the solvent is a mixture of at least two components, e.g. water and another liquid,
 - the mixture is chosen such that solubility of cellulose in the mixture is dependent on the relative amounts of the components in the mixture and
 - step (c) comprises altering the relative amounts of the components such that the solubility of cellulose in the mixture is reduced as compared to the solubility in step (a).
11. A method according to claim 10, wherein the mixture of the components that is initially contacted with the solid cellulose is such that it can dissolve a surface layer of the solid cellulose.
12. A method according to claim 10, wherein the proportions of components required to dissolve a surface layer of the solid cellulose are obtained by:

applying a mixture of the components to the solid cellulose and
drying the mixture to selectively remove one component to obtain a mixture of components capable of dissolving cellulose.

13. A method according to any one of claims 10 to 12, wherein the step of altering the relative amounts of components so that at least a portion of the cellulose comes out of solution is carried out by:

drying the mixture to selectively drive off one component and increase the concentration of the other component in the mixture.

14. A method according to any one of claims 10 to 13, wherein the solvent comprises water and a cyclic amine oxide, e.g. N-methylmorpholine N-oxide.

15. A method according to claim 14, wherein the mixture in step (a) contains 67 to 87% N-methylmorpholine N-oxide

16. A method according to any of claims 8 to 15, wherein; the additive is in the form of a dispersion of additive particles in a medium, and/or the additive is hydrophobic, and optionally is a fluoropolymer, e.g. PTFE, FEP, PFA, MFA, PVDF, ETFE, ECTFE, THV or a mixture thereof.

17. A method according to any of claims 8 to 16, wherein the solid cellulose is in a form selected from the group of paper, cellulose fibres and particles, such cellulose fibres and particles optionally being in an aqueous suspension.

Patentansprüche

1. Lagerbauteil mit einer Lagerlauffläche, **dadurch gekennzeichnet, dass** das Lagerbauteil ein Vlies umfasst, das Cellulosefasern und ein Fluorpolymer umfasst, und wobei wenigstens ein Teil des Fluorpolymers an der Lauffläche des Lagers angeordnet und an die Cellulose angeheftet ist.
2. Lagerbauteil nach Anspruch 1, wobei wenigstens ein Teil des Fluorpolymers in Form einer Beschichtung auf den Cellulosefasern an der Lauffläche des Lagerbauteils vorliegt und/oder wobei wenigstens ein Teil des Fluorpolymers in die Cellulosefasern auf der Lauffläche des Lagerbauteils integriert ist.
3. Lagerbauteil nach einem der vorhergehenden Ansprüche, wobei das Fluorpolymer ausgewählt ist aus PTFE, FEP, PFA, MFA, PVDF, ETFE, ECTFE, THV oder einem Gemisch davon.

4. Lagerbauteil nach einem der vorhergehenden Ansprüche, wobei die Lauffläche des Lagers ebenflächig oder röhrenförmig ist.

5. Verwendung eines Lagerbauteils nach einem der vorhergehenden Ansprüche, um eine Lauffläche in einem Lager bereitzustellen.

6. Verfahren zum Aufbringen eines Fluorpolymers, z. B. von PTFE, FEP, PFA, MFA, PVDF, ETFE, ECTFE, THV oder einem Gemisch davon, auf ein Vlies, das Cellulosefasern umfasst, **dadurch gekennzeichnet, dass** das Verfahren die folgenden Schritte umfasst:

(a) Aufbringen einer Dispersion des Fluorpolymers auf eine Oberfläche des Vlieses aus Cellulosefasern, wobei die Dispersion des Fluorpolymers wahlweise eine wässrige Dispersion ist, und

(b) Pressen des Vlieses aus Cellulosefasern, z. B. durch Kalandrieren, so dass das Fluorpolymer auf die Oberfläche des Cellulosevlieses geschichtet wird und an dieser haftet.

7. Verfahren nach Anspruch 6, wobei Schritt (b) bei einer Temperatur in einem Bereich zwischen 150 und 250°C und/oder bei einem Druck in einem Bereich zwischen 6,9 und 13,8 MPa (1.000 bis 2.000 lb/inch²) durchgeführt wird.

8. Verfahren zum Aufbringen eines Additivs, z. B. eines Fluorpolymers, auf Cellulose, **dadurch gekennzeichnet, dass** das Verfahren die folgenden Schritte umfasst:

(a) Inkontaktbringen von fester Cellulose mit einem Lösungsmittel, das zum Auflösen von Cellulose in der Lage ist, und mit einer Dispersion des Additivs, so dass eine Oberflächenschicht der festen Cellulose in dem Lösungsmittel aufgelöst wird;

(b) Inkontaktbringen der aufgelösten Cellulose mit dem Additiv;

(c) Verändern von Zusammensetzung, Menge oder Temperatur des Lösungsmittels, so dass die Löslichkeit der Cellulose in dem Lösungsmittel reduziert ist und wenigstens ein Teil der aufgelösten Cellulose aus der Lösung austritt, wodurch das Additiv in die Cellulose integriert oder an diese angeheftet wird; und

(d) wahlweise Entfernen des Lösungsmittels von der festen Cellulose durch einen Waschschritt im Anschluss an Schritt (c).

9. Verfahren nach Anspruch 8, des Weiteren umfassend den Schritt des Kombinierens des Additivs mit dem Lösungsmittel vor Schritt (a).

10. Verfahren nach Anspruch 8, wobei

- das Lösungsmittel ein Gemisch aus wenigstens zwei Komponenten ist, z. B. aus Wasser und einer weiteren Flüssigkeit,
- das Gemisch so ausgewählt ist, dass die Löslichkeit der Cellulose in dem Gemisch von den relativen Mengen der Komponenten in dem Gemisch abhängt, und
- Schritt (c) die Veränderung der relativen Mengen der Komponenten umfasst, so dass die Löslichkeit der Cellulose in dem Gemisch im Vergleich zu der Löslichkeit in Schritt (a) reduziert ist.

11. Verfahren nach Anspruch 10, wobei das Gemisch der Komponenten, das zu Beginn mit der festen Cellulose in Kontakt gebracht wird, so beschaffen ist, dass es zum Auflösen einer Oberflächenschicht der festen Cellulose in der Lage ist.

12. Verfahren nach Anspruch 10, wobei die Proportionen der Komponenten, die zum Auflösen einer Oberflächenschicht der festen Cellulose erforderlich sind, erhalten werden durch:

Aufbringen des Gemischs der Komponenten auf die feste Cellulose und
Trocknen des Gemischs zur selektiven Entfernung einer Komponente, um ein Gemisch aus Komponenten zu erhalten, das zum Auflösen von Cellulose in der Lage ist.

13. Verfahren nach einem der Ansprüche 10 bis 12, wobei der Schritt der Veränderung der relativen Mengen der Komponenten, so dass wenigstens ein Teil der Cellulose aus der Lösung austritt, durchgeführt wird mittels:

Trocknens des Gemischs zur selektiven Entfernung einer Komponente und Erhöhen der Konzentration der anderen Komponente in dem Gemisch.

14. Verfahren nach einem der Ansprüche 10 bis 13, wobei das Lösungsmittel Wasser und ein zyklisches Aminoxid, z. B. N-Methylmorpholin-N-oxid, umfasst.

15. Verfahren nach Anspruch 14, wobei das Gemisch in Schritt (a) 67 bis 87% N-Methylmorpholin-N-oxid enthält.

16. Verfahren nach einem der Ansprüche 8 bis 15, wobei; das Additiv in Form einer Dispersion von Partikeln des Additivs in einem Medium vorliegt, und/oder das Additiv hydrophob ist und wahlweise ein Fluoropolymer, z. B. PTFE, FEP, PFA, MFA, PVDF, ETFE,

ECTFE, THV oder eine Mischung davon, ist.

17. Verfahren nach einem der Ansprüche 8 bis 16, wobei die feste Cellulose in einer Form ausgewählt aus Papier, Cellulosefasern und Cellulosepartikeln vorliegt, wobei solche Cellulosefasern und Cellulosepartikel wahlweise in einer wässrigen Suspension vorliegen.

Revendications

1. Composant de support possédant une surface portante, **caractérisé en ce que** le composant de support comprend un mat comprenant des fibres celluloses et un polymère fluoré, et dans lequel au moins une partie du polymère fluoré est située sur la surface portante et adhère à la cellulose.

2. Composant de support selon la revendication 1, dans lequel au moins une partie du polymère fluoré est sous la forme d'un revêtement sur les fibres celluloses au niveau de la surface du composant de support et/ou dans lequel au moins une partie du polymère fluoré est incorporée dans les fibres celluloses au niveau de la surface du composant de support.

3. Composant de support selon l'une quelconque des revendications précédentes, dans lequel le polymère fluoré est choisi parmi un PTFE, un FEP, un PFA, un MFA, un PVDF, un ETFE, un ECTFE, un THV ou leurs mélanges.

4. Composant de support selon l'une quelconque des revendications précédentes, dans lequel la surface portante est plane ou tubulaire.

5. Utilisation d'un composant de support selon l'une quelconque des revendications précédentes, pour fournir une surface portante à un support.

6. Procédé d'application d'un polymère fluoré, par exemple un PTFE, un FEP, un PFA, un MFA, un PVDF, un ETFE, un ECTFE, un THV ou leurs mélanges, sur un mat comprenant des fibres celluloses, **caractérisé en ce que** le procédé comprend les étapes suivantes :

- (a) l'application d'une dispersion du polymère fluoré sur une surface du mat de fibres celluloses, la dispersion du polymère fluoré étant facultativement une dispersion aqueuse, et
- (b) la mise sous pression du mat de fibres celluloses, par exemple par calandrage, de manière à ce que le polymère fluoré recouvre ladite surface du mat de cellulose et y adhère.

7. Procédé selon la revendication 6, dans laquelle l'étape (b) est menée à une température située dans la plage allant de 150°C à 250°C et/ou à une pression située dans la plage allant de 1000 lb/sd in à 2000 lb/sd in (6,9 MPa à 13,8 MPa). 5
8. Procédé d'application d'un additif, par exemple un polymère fluoré, sur de la cellulose, **caractérisé en ce que** le procédé comprend les étapes suivantes : 10
- (a) la mise en contact d'une cellulose solide, d'un solvant capable de dissoudre la cellulose et d'une dispersion de l'additif les uns avec les autres, de manière à ce qu'une couche superficielle de la cellulose solide soit dissoute dans le solvant ; 15
 - (b) la mise en contact de la cellulose dissoute avec l'additif ; 20
 - (c) la modification de la composition, de la quantité ou de la température du solvant de manière à ce que la solubilité de la cellulose dans le solvant soit réduite et qu'au moins une partie de la cellulose dissoute précipite dans la solution, moyennant quoi l'additif est incorporé dans la cellulose ou y adhère ; et 25
 - (d) facultativement, l'élimination du solvant de la cellulose solide par lavage après l'étape (c).
9. Procédé selon la revendication 8, comprenant en outre l'étape consistant à combiner l'additif avec le solvant avant l'étape (a). 30
10. Procédé selon la revendication 8, dans lequel 35
- le solvant est un mélange contenant au moins deux composants, par exemple de l'eau et un autre liquide, 40
 - le mélange est choisi de manière à ce que la solubilité de la cellulose dans le mélange dépende des quantités relatives des composants du mélange et 45
 - l'étape (c) comprend la modification des quantités relatives des composants de manière à ce que la solubilité de la cellulose dans le mélange soit réduite par rapport à la solubilité dans l'étape (a).
11. Procédé selon la revendication 10, dans lequel le mélange de composants qui est initialement mis en contact avec la cellulose solide est tel qu'il peut dissoudre une couche superficielle de la cellulose solide. 50
12. Procédé selon la revendication 10, dans lequel les proportions de composants nécessaires pour dissoudre une couche superficielle de la cellulose solide sont obtenues : 55
- par l'application d'un mélange des composants sur la cellulose solide et
par le séchage du mélange pour éliminer sélectivement un composant afin d'obtenir un mélange de composants capable de dissoudre la cellulose.
13. Procédé selon l'une quelconque des revendications 10 à 12, dans lequel l'étape consistant à modifier les quantités relatives des composants pour qu'au moins une partie de la cellulose précipite dans la solution est réalisée :

par le séchage du mélange pour chasser sélectivement un composant et augmenter la concentration de l'autre composant dans le mélange.
14. Procédé selon l'une quelconque des revendications 10 à 13, dans lequel le solvant comprend de l'eau et un oxyde d'amine cyclique, par exemple le N-oxyde de N-méthylmorpholine.
15. Procédé selon la revendication 14, dans lequel le mélange dans l'étape (a) contient 67% à 87% de N-oxyde de N-méthylmorpholine.
16. Procédé selon l'une quelconque des revendications 8 à 15, dans lequel :

l'additif est sous la forme d'une dispersion de particules d'additif dans un milieu, et/ou l'additif est hydrophobe et est facultativement un polymère fluoré, par exemple un PTFE, un FEP, un PFA, un MFA, un PVDF, un ETFE, un ECTFE, un THV ou leurs mélanges
17. Procédé selon l'une quelconque des revendications 8 à 16, dans lequel la cellulose solide est sous une forme choisie dans le groupe comprenant le papier, les fibres cellulosiques et les particules cellulosiques, ces fibres et particules cellulosiques étant facultativement en suspension aqueuse.




Figure 1




Figure 2




Figure 3



Figure 4



Figure 5




Figure 6

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- GB 1144048 A [0005] [0024]
- US 4246221 A [0005] [0024]