




(86) Date de dépôt PCT/PCT Filing Date: 2016/08/31
(87) Date publication PCT/PCT Publication Date: 2017/03/09
(45) Date de délivrance/Issue Date: 2020/10/27
(85) Entrée phase nationale/National Entry: 2018/02/26
(86) N° demande PCT/PCT Application No.: US 2016/049561
(87) N° publication PCT/PCT Publication No.: 2017/040569
(30) Priorité/Priority: 2015/08/31 (US62/211,953)

(51) Cl.Int./Int.Cl. *A61L 27/18* (2006.01),
C07C 265/14 (2006.01), *C07F 7/08* (2006.01)
(72) Inventeurs/Inventors:
CLOWER, DOTTIE M., US;
BECKMAN, ERIC J., US;
PICONE, BRADD N., US
(73) Propriétaire/Owner:
COHERA MEDICAL, INC., US
(74) Agent: SMART & BIGGAR LLP

(54) Titre : ADHESIF DE REPARATION DE MENISQUE
(54) Title: MENISCAL REPAIR ADHESIVE



(57) Abrégé/Abstract:

A composition that includes (a) a prepolymer having at least one free isocyanate group that is capable of bonding to tissue and that cures in vivo upon exposure to water to form a polymer having a compressive modulus between 1.9 and 14.4 MPa and a tensile modulus between 5.0 and 30, and (b) an oil that is miscible in the prepolymer, the oil being selected from the group consisting of silicone oils, mineral oil, vegetable oils, and combinations thereof. The composition retains its integrity when delivered in an aqueous medium.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(10) International Publication Number
WO 2017/040569 A1

(43) International Publication Date
9 March 2017 (09.03.2017)

(51) International Patent Classification:

A61L 27/18 (2006.01) *C07C 265/14* (2006.01)
C07F 7/08 (2006.01)

(21) International Application Number:

PCT/US2016/049561

(22) International Filing Date:

31 August 2016 (31.08.2016)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/211,953 31 August 2015 (31.08.2015) US

(71) Applicant: **COHERA MEDICAL, INC.** [US/US]; 227 Fayetteville Street, Suite 900, Raleigh, North Carolina 27601 (US).

(72) Inventors: **CLOWER, Dottie M.**; 625 Cascade Road, Pittsburgh, Pennsylvania 15221 (US). **BECKMAN, Eric J.**; 213 Tenth Street, Aspinwall, Pennsylvania 15215 (US). **PICONE, Bradd N.**; 3 Susquehanna Street, Pittsburgh, Pennsylvania 15210 (US).

(74) Agent: **WHELAN, Dorothy P.**; Fish & Richardson P.C., P.O. Box 1022, Minneapolis, Minnesota 55440-1022 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,

BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- with international search report (Art. 21(3))

(54) Title: MENISCAL REPAIR ADHESIVE

(57) Abstract: A composition that includes (a) a prepolymer having at least one free isocyanate group that is capable of bonding to tissue and that cures *in vivo* upon exposure to water to form a polymer having a compressive modulus between 1.9 and 14.4 MPa and a tensile modulus between 5.0 and 30, and (b) an oil that is miscible in the prepolymer, the oil being selected from the group consisting of silicone oils, mineral oil, vegetable oils, and combinations thereof. The composition retains its integrity when delivered in an aqueous medium.



WO 2017/040569 A1

Meniscal Repair Adhesive

CLAIM OF PRIORITY

This application claims priority to U.S. Provisional Application Serial No. 62/211,953, filed on August 31, 2015.

TECHNICAL FIELD

5 This invention relates to repairing tissue defects and injuries such as meniscal tears.

BACKGROUND

 A meniscus is a C-shaped piece of cartilage located at the edge of the knee between the femur and tibia. Each knee has two menisci: one on the outer edge of the knee (lateral meniscus) and one on the inner edge of the knee (medial meniscus). A
10 meniscal tear is a common injury that often occurs when the knee is twisted. As people age, the meniscus can also become worn and susceptible to tearing. Meniscal tears are typically treated through either open or arthroscopic surgery. In either case, the area typically is flooded with saline during the surgery.


15

SUMMARY

 In one aspect, there is described a composition that includes (a) a prepolymer having at least one free isocyanate group that is capable of bonding to tissue and that cures *in vivo* upon exposure to water to form a polymer having a compressive modulus between 1.9 and 14.4 MPa and a tensile modulus between 5.0 and 30, and (b) an oil that
20 is miscible in the prepolymer, the oil being selected from the group consisting of silicone oils, mineral oil, vegetable oils, and combinations thereof. The composition retains its integrity when delivered in an aqueous medium.

 In certain embodiments, the prepolymer may include urethane linkages, urea linkages, or a combination thereof. Examples of suitable oils include silicone oils such as
25 polydimethylsiloxane, simethicone, and combinations thereof.


In certain embodiments, the prepolymer is a siloxane prepolymer. An example of a suitable siloxane prepolymer has the formula:



5

In this formula, n is 1 to 10; x and y, independently, are 2 to 10; R¹, R², R³, R⁵, and R⁶,
 10 independently, are selected from the group consisting of hydroxyl groups; straight
 chain, branched, or cyclic C₁-C₆ alkyl groups that may be substituted with one or
 more isocyanate groups; straight chain, branched, or cyclic C₁-C₆ fluorinated alkyl
 groups that may be substituted with one or more isocyanate groups; and combinations
 thereof; R⁴ is selected from the group consisting of -NCO, -SH, -OH, R⁷N⁺X⁻; R⁷ is a
 15 straight chain, branched, or cyclic C₁-C₆ alkyl group; and X is selected from the
 group consisting of F, Cl, Br, and I, with the proviso that at least one of R¹, R², R³, R⁴,
 R⁵, and R⁶ includes an isocyanate group.

Another example of a suitable siloxane prepolymer has the following formula:




In this formula, R^1 and R^2 , independently, are selected from the group consisting of hydroxyl groups; straight chain, branched, or cyclic C_1 - C_6 alkyl groups that may be substituted with one or more isocyanate groups; straight chain, branched, or cyclic C_1 - C_6 fluorinated alkyl groups that may be substituted with one or more isocyanate groups; and combinations thereof.

In certain embodiments, the prepolymer can include the reaction product of a polyisocyanate, an active hydrogen component selected from the group consisting of polyols, polyamines, polythiols, polycarboxylic acids, and combinations thereof, and, optionally, an ionic salt or amino acid component having an average hydroxyl or amino

functionality, or combination thereof, of at least 1. Examples of suitable ionic salts components include ammoniates, halides, sulfonates, phosphonates, carboxylates, and combinations thereof. The composition may include at least two different prepolymers.


As used herein, the term “component” refers to single compounds, and to blends
5 of different compounds.

Representative examples of suitable prepolymers having the following structures:



10

and



15

The composition may be used to repair a variety of tissues, including meniscal tissue, tendons, cartilage, and the like. For example, the composition may be used to repair a meniscal defect such as a tear by delivering the composition to a knee joint in an aqueous environment in the area of a meniscal defect, and allowing the composition to cure in the presence of water present in the knee joint. Because the composition retains its integrity even when immersed in an aqueous environment such as the saline environment typically encountered during surgery, it remains intact and in place following delivery to the desired area of the knee joint as it cures and bonds to the meniscal tissue.

The details of one or more embodiments of the invention are set forth in the description below. Other features, objects, and advantages of the invention will be apparent from the description and from the claims.

DETAILED DESCRIPTION

The compositions include (a) a prepolymer having at least one free isocyanate group that is capable of bonding to tissue and that cures *in vivo* upon exposure to water to form a polymer having a compressive modulus between 1.9 and 14.4 MPa and a tensile modulus between 5.0 and 30, and (b) an oil that is miscible in the prepolymer, the oil being selected from the group consisting of silicone oils, mineral oil, vegetable oils, and combinations thereof. The composition retains its integrity when delivered in an aqueous medium.

Because the compositions retain their integrity even when delivered in an aqueous environment, e.g., a saline solution, they remain intact and in place following delivery to the desired area of the tissue during surgery as the prepolymer cures and bonds to the tissue. In addition, the cured compositions are capable of withstanding the tensile, shear, and compressive forces to which they are exposed, e.g., within the knee joint. The specific cure times, viscosities, and mechanical properties can be tailored as necessary for individual applications.

Because the prepolymer includes at least one isocyanate group, it can bond to tissue, e.g., meniscal tissue, by reacting with surface groups on the tissue. In some cases,

the release of controlled amounts of gas can create a scaffold-like structure and/or a textured surface that facilitates potential cell attachment and tissue regrowth through the cured polymer.

The oil in the composition contributes to the ability of the composition to retain its integrity when delivered in an aqueous environment. The oil may also perform the function of a defoaming agent.

In some embodiments, the compositions include siloxane prepolymers having the formula recited in the Summary of the Invention. Such prepolymers may be prepared e.g., by reacting alkoxy silanes and isocyanate-functional organosilanes.

Suitable alkoxy silane reactants have the formula: $(R^1R^2R^3)\text{-Si-CH}_2\text{-Z}$ where (i) Z is an -OH , -SH , -NCO , or -NHR^4 group. R^4 is a hydrogen, an alkyl group (e.g., a $\text{C}_1\text{-C}_6$ alkyl group), or an aryl group (e.g., having at least one ring such as a phenyl group). Each R^1 , R^2 , and R^3 , independently, is H, an alkoxy group (e.g., a $\text{C}_1\text{-C}_6$ alkoxy group), an alkyl group (e.g., a $\text{C}_1\text{-C}_6$ alkyl group), a heteroalkyl group other than an alkoxy group (e.g., an alkyl amido or amido group), an aryl group (e.g., a phenyl group), or a heteroaryl group (e.g., a pyrrolyl, furyl, or pyridinyl group), with the proviso that at least two of R^1 , R^2 , and R^3 are alkoxy groups. The alkyl groups may be straight chain, branched, or cyclic alkyl groups.

Suitable isocyanate-functional organosilane reactants have at least one free isocyanate group and at least one terminal silane group having the formula: $(R^5R^6R^7)\text{-Si-}$ where each R^5 , R^6 , and R^7 , independently, is H, an alkoxy group (e.g., a $\text{C}_1\text{-C}_6$ alkoxy group), an alkyl group (e.g., a $\text{C}_1\text{-C}_6$ alkyl group), a heteroalkyl group other than an alkoxy group (e.g., an alkyl amido or amido group), an aryl group (e.g., a phenyl group), or a heteroaryl group (e.g., a pyrrolyl, furyl, or pyridinyl group).

In some embodiments, the compositions include prepolymers prepared by reacting a polyisocyanate and an active hydrogen component. Examples of suitable active hydrogen components include hydroxyl-functional components, amine-functional components, thiol-functional components, carboxylic acid-functional components, and combinations thereof. In some embodiments, some or all of the functional groups may be primary groups.

One class of suitable active hydrogen components includes multi-functional alcohols selected from glycerol, di-glycerol, erythritol, pentaerythritol, xylitol, arabitol, fucitol, ribitol, sorbitol, mannitol, and combinations thereof. Also suitable are hydroxyalkyl derivatives and esters of any of these alcohols such as ethoxylated pentaerythritol.

Another class of suitable active hydrogen components includes hydroxyalkyl derivatives of C₃-C₁₀ carboxylic or dicarboxylic acids (e.g., dimethylol propionic acid, dimethylol butyric acid, and combinations thereof), and hydroxyalkyl derivatives of C₃-C₁₀ hydrocarbons (e.g., trimethylol propane).

The active hydrogen component can also be a hydroxalkyl amine (e.g., triethanolamine), a di-, tri-, or tetraalkylene glycol, or combination thereof. Also suitable are hydroxyl-functional compounds selected from saccharides (e.g., glucose, fructose, sucrose, or lactose), oligosaccharides, polysaccharides, esters thereof, and combinations thereof.

The active hydrogen component can also be a polyamine or polyetheramine, e.g., Jeffamine.

An ionic salt or amino acid may also be included as a reactant in preparing the prepolymer. Suitable ionic salt reactants include one or more hydroxyl and/or amino functional groups. Consequently, they are able to react with isocyanate-functional components in the reaction mixture, and thereby become covalently incorporated in the prepolymer. Examples of suitable salts include ammoniates, halides, sulfonates, phosphonates, carboxylates, and combinations thereof. Specific examples include ammonium halides (e.g., ethyl triethanol ammonium chloride), choline halides (e.g., choline chloride), and combinations thereof. Examples of suitable amino acids include lysine, l-arginine, and combinations thereof.

The composition may further include a catalyst. Examples of suitable catalysts include tertiary amines (e.g., aliphatic tertiary amines), organometallic compounds (e.g., bismuth salts and zirconium chelates), platinum, and palladium. Specific examples include 1,4-diazabicyclo[2.2.2]octane ("DABCO"), 2,2'-dimorpholine diethyl ether ("DMDEE"), dibutyltin dilaurate ("DBTDL"), bismuth 2-ethylhexanoate, bismuth

neodecanoate, and combinations thereof. The amount of catalyst is selected based upon the particular reactants.

The composition may also include rheology-modifying agents such as a solvent and/or a non-volatile diluent. Examples of suitable solvents include dimethylsulfoxide (DMSO), dimethylformamide (DMF), tetrahydrofuran (THF), glyme, and combinations thereof. Examples of suitable non-volatile diluents include dimethylsulfoxide (DMSO), propylene carbonate, diglyme, polyethylene glycol diacetates, polyethylene glycol dicarbonates, dimethylisobutylate, ethyl pyruvate, triacetin, triethylene glycol and combinations thereof. A single reagent can perform multiple roles. Thus, for example, DMSO can function as both a solvent and a non-volatile diluent. The amount of the rheology modifying agent is selected based upon the constituents of the composition and the particular application for which it is being used.

The composition may also include antioxidants (e.g., BHT and BHA), water scavengers (e.g., acyl and aryl halides, and anhydrides), Bronsted acids, protonic acids (e.g., sulfuric or hydrochloric acid), and the like. The acids may also function as catalysts.


The composition may also include a colorant to help a surgeon visualize the composition during application to the meniscal tissue. An example of a suitable colorant is beta-carotene.

A number of embodiments of the invention have been described. Nevertheless, it will be understood that various modifications may be made without departing from the spirit and scope of the invention. Accordingly, other embodiments are within the scope of the following claims.

CLAIMS:

1. A composition comprising:

- (a) a siloxane prepolymer having at least one free isocyanate group that is capable of bonding to tissue and that cures in vivo upon exposure to water to form a polymer having a compressive modulus between 1.9 and 14.4 MPa and a tensile modulus between 5.0 and 30 MPa, the siloxane prepolymer having the formula:




- where n is 1 to 10; x and y, independently, are 2 to 10, R1, R2, R3, R5, and R6, independently, are selected from the group consisting of hydroxyl groups; straight chain, branched, or cyclic C1-C6 alkyl groups that may be substituted with one or more isocyanate groups; straight chain, branched, or cyclic C1-C6 fluorinated alkyl groups that may be substituted with one or more isocyanate groups; and combinations thereof; R4 is selected from the group consisting of -NCO, -SH, -OH, R7N+X-; R7 is a straight chain, branched, or cyclic C1-C6 alkyl group; and X is selected from the group consisting of F, Cl, Br, and I, with the proviso that at least one of R1, R2, R3, R4, R5 and R6 includes an isocyanate group; and

(b) an oil that is miscible in the siloxane prepolymer, the oil being selected from the group consisting of silicone oils, mineral oil, vegetable oils, and combinations thereof, wherein the composition retains its integrity when delivered in an aqueous medium.

2. A composition comprising:

(a) a siloxane prepolymer having at least one free isocyanate group that is capable of bonding to tissue and that cures in vivo upon exposure to water to form a polymer having a compressive modulus between 1.9 and 14.4 MPa and a tensile modulus between 5.0 and 30 MPa, the siloxane prepolymer having the formula:



5

where R1 and R2, independently, are selected from the group consisting of hydroxyl groups; straight chain, branched, or cyclic C1-C6 alkyl groups that may be substituted with one or more isocyanate groups; straight chain, branched, or cyclic C1-C6 fluorinated alkyl groups that may be substituted with one or more isocyanate groups; and combinations thereof, and

10

(b) an oil that is miscible in the siloxane prepolymer, the oil being selected from the group consisting of silicone oil, mineral oil, vegetable oils, and combinations thereof, wherein the composition retains its integrity when delivered in an aqueous medium.

15

3. The composition according to claim 1 or 2 wherein the siloxane prepolymer comprises linkages selected from the group consisting of urea linkages, urethane linkages, and combinations thereof.

4. The composition according to claim 1 or 2, wherein the siloxane prepolymer comprises the reaction product of a polyisocyanate and an active hydrogen component selected from the group consisting of polyols, polythiols, polycarboxylic acids, and combinations thereof.

5

5. The composition according to claim 1 or 2 wherein siloxane prepolymer comprises the reaction product of (a) a polyisocyanate, (b) an active hydrogen component selected from the group consisting of polyols, polyamines, polythiols, polycarboxylic acids, and combinations thereof, and (c) an ionic salt or amino acid component having an average hydroxyl or amino functionality, or combination thereof, of at least 1.


10

6. The composition according to claim 5, wherein the ionic salt component is selected from the group consisting of ammoniates, halides, sulfonates, phosphonates, carboxylates, and combinations thereof.

15

7. A composition comprising:

(a) a prepolymer selected from the group of compounds having the formulae:



20

and combinations thereof; and

(b) an oil that is miscible in the prepolymer, the oil being selected from the group consisting of silicone oils, mineral oil, vegetable oils, and combinations thereof, wherein the composition retains its integrity when delivered in an aqueous medium.

5 8. The composition according to claim 1, 2 or 7 wherein the composition comprises at least two different prepolymers.

9. The composition according to claim 1, 2, or 7, wherein the oil comprises a silicone oil.

10 10. The composition according to claim 9, wherein the oil is selected from the group consisting of polydimethylsiloxane, simethicone, and combinations thereof

11. The composition according to claim 1, 2, or 7 wherein the tissue is selected from the group consisting of meniscal tissue, cartilage, tendons, and combinations thereof.

15

12. Use of the composition according to claim 1, 2 or 7 for repairing a defect in meniscal tissue wherein the composition is for delivery to the knee joint in an aqueous environment in the area of the meniscal defect, and wherein the composition cures and bonds to the meniscal tissue.

20

13. The composition according to claim 1, 2, or 7, wherein the tissue is meniscal tissue.

