

(12) **United States Patent**
Miller et al.

(10) **Patent No.:** **US 11,873,428 B2**
(45) **Date of Patent:** ***Jan. 16, 2024**

(54) **THERMOSETTING ADHESIVE FILMS**

(71) Applicant: **Zephyros, Inc.**, Romeo, MI (US)

(72) Inventors: **Ira Miller**, Molsheim (FR); **Michael Czaplicki**, Romeo, MI (US); **Michel Awkal**, Molsheim (FR)

(73) Assignee: **Zephyros, Inc.**, Romeo, MI (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 630 days.

This patent is subject to a terminal disclaimer.

(21) Appl. No.: **16/682,516**

(22) Filed: **Nov. 13, 2019**

(65) **Prior Publication Data**

US 2020/0079977 A1 Mar. 12, 2020
US 2023/0392045 A9 Dec. 7, 2023

Related U.S. Application Data

(63) Continuation of application No. 14/907,164, filed as application No. PCT/IB2014/063427 on Jul. 25, 2014, now Pat. No. 10,577,523.

(30) **Foreign Application Priority Data**

Jul. 26, 2013 (GB) 1313328
Feb. 24, 2014 (GB) 1403160
Feb. 24, 2014 (GB) 1403163

(51) **Int. Cl.**
C09J 7/35 (2018.01)
C09J 5/00 (2006.01)

(Continued)

(52) **U.S. Cl.**

CPC **C09J 7/10** (2018.01); **C08J 5/128** (2013.01); **C09J 5/00** (2013.01); **C09J 5/06** (2013.01);

(Continued)

(58) **Field of Classification Search**

CPC C09J 7/10; C09J 5/00; C09J 5/06; C09J 7/21; C09J 7/35; C09J 163/00;

(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,649,714 A 3/1972 Wangness
3,707,583 A 12/1972 McKown
(Continued)

FOREIGN PATENT DOCUMENTS

CA 2425414 A1 4/2002
CN 1929990 A 3/2007
(Continued)

OTHER PUBLICATIONS

European First Communication dated Oct. 30, 2019, Application No. 14750801.4.

(Continued)


Primary Examiner — John D Freeman

(74) *Attorney, Agent, or Firm* — The Dobrusin Law Firm, P.C.

(57) **ABSTRACT**

Flexible films of thermosetting adhesive materials which are non-tacky to the touch are storage stable at room temperature and can be cured at elevated temperature with a short cure time and can be cured to produce a tough flexible adhesive layer including bonding to oily surfaces, the materials are particularly useful in bonding together dissimilar substrates.

20 Claims, 1 Drawing Sheet



(51)	Int. Cl.		5,266,133 A	11/1993	Hanley et al.
	<i>C08J 5/12</i>	(2006.01)	5,274,006 A	12/1993	Kagoshima et al.
	<i>C09J 163/00</i>	(2006.01)	5,275,853 A	1/1994	Silvis et al.
	<i>C09J 7/10</i>	(2018.01)	5,290,857 A	3/1994	Ashida et al.
	<i>C09J 5/06</i>	(2006.01)	5,331,062 A	7/1994	Sorathia et al.
	<i>C09J 7/21</i>	(2018.01)	5,342,873 A	8/1994	Merz et al.
	<i>C09J 171/00</i>	(2006.01)	5,344,208 A	9/1994	Bien et al.
			5,382,606 A	1/1995	Butikofner
(52)	U.S. Cl.		5,401,814 A	3/1995	Schomaker et al.
	CPC . <i>C09J 7/21</i>	(2018.01); <i>C09J 7/35</i>	5,464,924 A	11/1995	Silvis et al.
		(2018.01); <i>C08J 2363/00</i>	5,470,886 A	11/1995	Makhlouf et al.
		(2013.01); <i>C08J 2367/00</i>	5,475,039 A	12/1995	Butikofner
		(2013.01); <i>C08J 2463/00</i>	5,506,025 A	4/1996	Otto et al.
		(2013.01); <i>C09J 163/00</i>	5,575,526 A	11/1996	Wycech
		(2013.01); <i>C09J 171/00</i>	5,648,401 A	7/1997	Czaplicki et al.
		(2013.01); <i>C09J 2301/122</i>	5,649,400 A	7/1997	Norimichi
		(2020.08); <i>C09J 2301/124</i>	5,708,042 A	1/1998	Hasegawa
		(2020.08); <i>C09J 2301/414</i>	5,712,317 A	1/1998	Makhlouf et al.
		(2020.08); <i>C09J 2451/00</i>	5,725,272 A	3/1998	Jones
		(2013.01); <i>C09J 2461/00</i>	5,755,486 A	5/1998	Wycech
		(2013.01); <i>C09J 2463/00</i>	5,763,529 A	6/1998	Lucas
		(2013.01); <i>C09J 2467/006</i>	5,766,719 A	6/1998	Rimkus
		(2013.01); <i>C09J 2477/006</i>	5,783,272 A	7/1998	Wong
		(2013.01); <i>Y10T 428/1476</i>	5,834,078 A	11/1998	Cavitt et al.
		(2015.01); <i>Y10T 428/31515</i>	5,884,960 A	3/1999	Wycech
(58)	Field of Classification Search		5,894,071 A	4/1999	Merz et al.
	CPC	<i>C09J 171/00</i> ; <i>C09J 2301/122</i> ; <i>C09J</i>	5,911,932 A	6/1999	Dyksterhouse
		<i>2301/124</i> ; <i>C09J 2301/414</i> ; <i>C09J 2451/00</i> ;	5,931,474 A	8/1999	Chang et al.
		<i>C09J 2461/00</i> ; <i>C09J 2463/00</i> ; <i>C09J</i>	5,932,680 A	8/1999	Heider
		<i>2463/006</i> ; <i>C09J 2467/006</i> ; <i>C09J 2471/00</i> ;	5,948,508 A	9/1999	Pastore et al.
		<i>C09J 2477/006</i> ; <i>C09J 2479/086</i> ; <i>C09J</i>	5,962,093 A	10/1999	White et al.
		<i>2400/263</i> ; <i>C08J 5/128</i> ; <i>C08J 2363/00</i> ;	5,964,979 A	10/1999	George et al.
		<i>C08J 2367/00</i> ; <i>C08J 2463/00</i> ; <i>Y10T</i>	5,965,256 A	10/1999	Barrera
		<i>428/1476</i> ; <i>Y10T 428/31515</i>	5,985,435 A	11/1999	Czaplicki et al.
			5,994,422 A	11/1999	Born et al.
	See application file for complete search history.		5,997,077 A	12/1999	Siebels et al.
			6,004,425 A	12/1999	Born et al.
			6,006,484 A	12/1999	Geissbuehler
(56)	References Cited		6,030,701 A	2/2000	Johnson et al.
	U.S. PATENT DOCUMENTS		6,033,300 A	3/2000	Schneider
			6,040,350 A	3/2000	Fukui
			6,057,382 A	5/2000	Karim et al.
			6,068,922 A	5/2000	Vercesi et al.
			6,077,884 A	6/2000	Hess et al.
			6,093,358 A	7/2000	Schiewe et al.
			6,096,791 A	8/2000	Born et al.
			6,103,341 A	8/2000	Barz et al.
			6,103,784 A	8/2000	Hilbom et al.
			6,111,015 A	8/2000	Eldin et al.
			6,131,897 A	10/2000	Barz et al.
			6,133,335 A	10/2000	Mahoney et al.
			6,135,541 A	10/2000	Geise et al.
			6,136,398 A	10/2000	Willett et al.
			6,136,944 A	10/2000	Stewart et al.
			6,146,565 A	11/2000	Keller
			6,150,428 A	11/2000	Hanley et al.
			6,153,302 A	11/2000	Karim et al.
			6,162,504 A	12/2000	Hubert et al.
			6,174,932 B1	1/2001	Paehl et al.
			6,180,715 B1	1/2001	Schmidt
			6,218,442 B1	4/2001	Hilbom et al.
			6,228,449 B1	5/2001	Meyer
			6,232,433 B1	5/2001	Narayan
			6,235,842 B1	5/2001	Kuwano et al.
			6,263,635 B1	7/2001	Czaplicki
			6,270,600 B1	8/2001	Wycech
			6,277,898 B1	8/2001	Paehl et al.
			6,281,260 B1	8/2001	Hanley et al.
			6,287,669 B1	9/2001	George et al.
			6,296,298 B1	10/2001	Barz
			6,303,672 B1	10/2001	Papalos et al.
			6,311,452 B1	11/2001	Barz et al.
			6,312,668 B2	11/2001	Mitra et al.
			6,319,964 B1	11/2001	Blank et al.
			6,348,513 B1	2/2002	Hilbom et al.
			6,350,791 B1	2/2002	Feichtmeier et al.
			6,358,584 B1	3/2002	Czaplicki
			6,368,438 B1	4/2002	Chang et al.
			6,376,564 B1	4/2002	Harrison

(56)		References Cited					
		U.S. PATENT DOCUMENTS					
6,382,635	B1	5/2002	Fitzgerald	6,890,964	B2	5/2005	Czaplicki et al.
6,383,610	B1	5/2002	Barz et al.	6,894,082	B2	5/2005	Brantl et al.
6,388,043	B1	5/2002	Langer et al.	6,911,109	B2	6/2005	Giroux et al.
6,392,929	B1	5/2002	Kim et al.	6,920,693	B2	7/2005	Hankins et al.
6,403,222	B1	6/2002	Harrison	6,955,593	B2	10/2005	Lewis et al.
6,416,611	B1	7/2002	Roberts et al.	6,991,237	B2	1/2006	Kassa et al.
6,419,305	B1	7/2002	Larsen	7,008,680	B2	3/2006	Everaerts et al.
6,429,244	B1	8/2002	Rinka et al.	7,025,409	B2	4/2006	Riley et al.
6,432,475	B1	8/2002	Yamamoto et al.	7,071,263	B2	7/2006	Cheng et al.
6,437,055	B1	8/2002	Arity et al.	7,084,209	B2	8/2006	Everaerts et al.
6,440,257	B1	8/2002	Zhou et al.	7,084,210	B2	8/2006	Eagle
6,441,075	B2	8/2002	Hirata et al.	7,094,843	B2	8/2006	Meyer
6,441,081	B1	8/2002	Sadatashi et al.	7,114,763	B2	10/2006	Riley et al.
H2047	H	9/2002	Harrison et al.	7,119,149	B2	10/2006	Ferguson et al.
6,444,149	B1	9/2002	Valentinsson	7,125,461	B2	10/2006	Czaplicki et al.
6,444,713	B1	9/2002	Paehl et al.	7,169,467	B2	1/2007	Wilson
6,448,338	B1	9/2002	Born et al.	7,199,165	B2	4/2007	Kassa et al.
6,451,231	B1	9/2002	Harrison et al.	7,288,604	B2	10/2007	Kuntimaddi et al.
6,451,876	B1	9/2002	Koshy	7,297,740	B2	11/2007	Dyksterhouse
6,455,146	B1	9/2002	Fitzgerald	7,392,929	B1	7/2008	Finerman et al.
6,455,476	B1	9/2002	Imai et al.	7,438,782	B2	10/2008	Sheasley et al.
6,455,634	B1	9/2002	Khandpur et al.	7,467,452	B2	12/2008	Lande et al.
6,467,834	B1	10/2002	Barz et al.	7,494,179	B2	2/2009	Deachin
6,471,285	B1	10/2002	Czaplicki et al.	7,503,620	B2	3/2009	Brennecke et al.
6,479,560	B2	11/2002	Freitag et al.	7,735,906	B2	6/2010	Takahashi et al.
6,482,486	B1	11/2002	Czaplicki et al.	7,892,396	B2	2/2011	Sheasley
6,486,256	B1	11/2002	Tarbutton et al.	7,926,179	B2	4/2011	Gray et al.
6,489,400	B2	12/2002	Khandpur et al.	8,105,460	B2	1/2012	Sheasley
6,506,494	B2	1/2003	Brandys et al.	8,163,116	B2	4/2012	Riley
6,546,693	B2	4/2003	Wycech	10,577,522	B2*	3/2020	Awkal C09J 5/06
6,548,593	B2	4/2003	Merz et al.	10,577,523	B2*	3/2020	Miller C08J 5/128
6,561,571	B1	5/2003	Brennecke	2002/0013389	A1	1/2002	Taylor et al.
6,573,309	B1	6/2003	Reitenbach et al.	2002/0076566	A1*	6/2002	Brandys C08G 59/188
6,586,089	B2	7/2003	Golden				428/458
6,589,621	B1	7/2003	Beckerdite et al.	2002/0123575	A1	9/2002	Kato et al.
6,593,380	B2	7/2003	Gehlsen et al.	2002/0164450	A1	11/2002	Lupini et al.
6,607,831	B2	8/2003	Ho et al.	2002/0182955	A1	12/2002	Weglewski et al.
6,617,366	B2	9/2003	Sueda et al.	2002/0192387	A1	12/2002	Agarwal et al.
6,620,501	B1	9/2003	Kassa et al.	2003/0045620	A1	3/2003	Carlson et al.
6,634,698	B2	10/2003	Kleino	2003/0050352	A1	3/2003	Guenther et al.
6,668,457	B1	12/2003	Czaplicki	2003/0090129	A1	5/2003	Riley et al.
6,682,818	B2	1/2004	Czaplicki et al.	2003/0119987	A1	6/2003	Eadara et al.
6,692,347	B1	2/2004	Schneider	2003/0144416	A1	7/2003	Tarbutton et al.
6,706,772	B2	3/2004	Czaplicki et al.	2003/0183317	A1	10/2003	Czaplicki et al.
6,706,802	B2	3/2004	Carlson et al.	2003/0186049	A1	10/2003	Czaplicki et al.
6,722,720	B2	4/2004	Donick et al.	2004/0033324	A1	2/2004	Meyer
6,730,713	B2	5/2004	Czaplicki	2004/0048078	A1	3/2004	Czaplicki et al.
6,734,263	B2	5/2004	Eadara et al.	2004/0076831	A1	4/2004	Hable et al.
6,740,067	B2	5/2004	Leise et al.	2004/0079478	A1	4/2004	Merz
6,740,379	B1	5/2004	Congard et al.	2004/0180193	A1	9/2004	Oda et al.
6,740,399	B1	5/2004	George et al.	2004/0181013	A1	9/2004	Schenkel
6,753,379	B1	6/2004	Kawate et al.	2004/0191523	A1	9/2004	Kye
6,774,171	B2	8/2004	Kassa et al.	2004/0197545	A1	10/2004	Gehlsen et al.
6,776,869	B1	8/2004	Schenkel	2004/0204551	A1	10/2004	Czaplicki et al.
6,777,079	B2	8/2004	Zhou et al.	2004/0212220	A1	10/2004	Riley et al.
6,787,065	B1	9/2004	Schapiro et al.	2004/0221953	A1	11/2004	Czaplicki et al.
6,787,579	B2	9/2004	Czaplicki et al.	2004/0229000	A1	11/2004	Khandpur et al.
6,787,593	B2	9/2004	Bell et al.	2004/0266898	A1	12/2004	Kassa et al.
6,787,605	B2	9/2004	Clough et al.	2004/0266899	A1	12/2004	Muenz et al.
6,787,606	B1	9/2004	Chen	2005/0016677	A1	1/2005	Carlson et al.
6,790,597	B2	9/2004	Dershem et al.	2005/0017543	A1	1/2005	Riely et al.
6,790,906	B2	9/2004	Chaignon et al.	2005/0020703	A1	1/2005	Czaplicki et al.
6,793,274	B2	9/2004	Riley et al.	2005/0081383	A1	4/2005	Kosal et al.
6,797,371	B1	9/2004	Gehlsen et al.	2005/0103422	A1	5/2005	Kawaguchi
6,800,157	B2	10/2004	Tarbutton et al.	2005/0119372	A1	6/2005	Czaplicki et al.
6,800,680	B2	10/2004	Stark et al.	2005/0129895	A1	6/2005	Nakamura
6,805,768	B2	10/2004	Agarwal et al.	2005/0154089	A1	7/2005	Taylor et al.
6,806,320	B2	10/2004	Everaerts et al.	2005/0159511	A1	7/2005	Kramer
6,811,864	B2	11/2004	Czaplicki et al.	2005/0159531	A1	7/2005	Ferng et al.
6,820,923	B1	11/2004	Bock	2005/0172486	A1	8/2005	Carlson et al.
6,824,451	B2	11/2004	Hollatz et al.	2005/0198907	A1	9/2005	McKnight et al.
6,838,509	B2	1/2005	Shimo et al.	2005/0221046	A1	10/2005	Finerman et al.
6,846,559	B2	1/2005	Czalicki et al.	2005/0230027	A1	10/2005	Kassa et al.
6,884,854	B2	4/2005	Schoenfeld et al.	2005/0241756	A1	11/2005	Harthcock et al.
6,887,914	B2	5/2005	Czalicki et al.	2005/0279567	A1	12/2005	Ito
				2006/0021697	A1	2/2006	Riley
				2006/0057333	A1	3/2006	Brahim
				2006/0090343	A1	5/2006	Riley et al.
				2006/0155045	A1	7/2006	Tsuno et al.

(56) References Cited			EP	0947529	B1	8/2004
U.S. PATENT DOCUMENTS			EP	1185595	A2	8/2004
2006/0171269	A1	8/2006	EP	1252217	B1	8/2004
2006/0188726	A1	8/2006	EP	1449868	A1	8/2004
2006/0252860	A1	11/2006	EP	1658319	B1	8/2004
2007/0045042	A1	3/2007	EP	1023413	B1	9/2004
2007/0087848	A1	4/2007	EP	1155082	B1	9/2004
2007/0088138	A1	4/2007	EP	1305376	B1	9/2004
2007/0090360	A1	4/2007	EP	1155053	B1	10/2004
2007/0090560	A1	4/2007	EP	1163308	B1	10/2004
2007/0095475	A1	5/2007	EP	1471105	A2	10/2004
2007/0101679	A1	5/2007	EP	1001893	B1	11/2004
2007/0116961	A1	5/2007	EP	1115770	B1	11/2004
2007/0117874	A1	5/2007	EP	1187888	B1	11/2004
2007/0122510	A1	5/2007	EP	1591224	A1	2/2005
2007/0134058	A1	6/2007	EP	1574537	A1	9/2005
2007/0138683	A1	6/2007	EP	1123348	B1	12/2005
2007/0191556	A1	8/2007	EP	1602702	A1	12/2005
2007/0264438	A1	11/2007	EP	1458594	B1	3/2006
2007/0281523	A1	12/2007	EP	1666228	A2	6/2006
2007/0284036	A1	12/2007	EP	1506265	B1	7/2006
2008/0014053	A1	1/2008	EP	1578838	B1	8/2006
2008/0029200	A1	2/2008	EP	1609831	B1	8/2006
2008/0060742	A1	3/2008	EP	1453925	B1	10/2006
2008/0105992	A1	5/2008	EP	1900787		3/2008
2008/0241576	A1	10/2008	EP	2182025	A1	5/2010
2008/0257094	A1	10/2008	GB	903146	A	8/1962
2008/0257485	A1	10/2008	JP	S52-5056	B1	1/1977
2008/0262188	A1	10/2008	JP	56-004432	A	1/1981
2008/0269420	A1	10/2008	JP	56/118816	A	9/1981
2008/0299317	A1	12/2008	JP	57-117542	A	7/1982
2008/0308212	A1	12/2008	JP	60-096681	A	5/1985
2008/0311405	A1	12/2008	JP	62-062882	A	3/1987
2009/0085379	A1	4/2009	JP	3/247446	A	11/1991
2009/0131557	A1	5/2009	JP	04-059819	A	2/1992
2009/0269547	A1	10/2009	JP	05-65391		3/1993
2009/0280330	A1	11/2009	JP	06-166852		6/1994
2010/0025147	A1	2/2010	JP	09-176616	A	7/1997
2011/0098382	A1	4/2011	JP	09-249730	A	9/1997
2011/0215632	A1	9/2011	JP	09-316169	A	12/1997
2012/0111488	A1	5/2012	JP	10-045031	A	2/1998
2012/0186721	A1	7/2012	JP	11-106544	A	4/1999
2012/0205029	A1	8/2012	JP	2001-62833	A	3/2001
2013/0056153	A1	3/2013	JP	2001191949	A	7/2001
2013/0133771	A1	5/2013	JP	2002-362412	A	12/2002
2013/0206333	A1	8/2013	JP	2004315688	A	11/2004
			JP	2005187508	A	7/2005
			JP	2006-520848		9/2014
			WO	1994/029358		12/1994
			WO	1995/033785	A1	12/1995
			WO	1997/002967	A1	1/1997
			WO	1997/011122		3/1997
DE	3639266	A1	WO	1997/012929	A1	4/1997
DE	3838655	A1	WO	1997/019124	A1	5/1997
DE	19919783	A1	WO	1998/036944	A1	8/1998
EP	0227002	A1	WO	1998/045382		10/1998
EP	0360214	A2	WO	1998/052997	A1	11/1998
EP	0383498	A2	WO	1998/053008	A1	11/1998
EP	0432923		WO	1999/002578	A1	1/1999
EP	0442178	A1	WO	2000/002968		1/2000
EP	0622833	A1	WO	2000/003894	A1	1/2000
EP	0710696	A2	WO	2000/012571	A1	3/2000
EP	0730999	A1	WO	2000/012595	A1	3/2000
EP	0819723	A1	WO	2000/013876	A1	3/2000
EP	0893332	A1	WO	2000/020483	A2	4/2000
EP	1022320	A1	WO	2000/027920	A1	5/2000
EP	1055699	A1	WO	2000/037242	A1	6/2000
EP	1072647	A2	WO	2000/037554	A1	6/2000
EP	1031496	B1	WO	2000/039232	A1	7/2000
EP	1182087	A2	WO	2000/040629	A1	7/2000
EP	0973840	B1	WO	2000/052086	A2	9/2000
EP	0703931	B1	WO	2001/019667	A1	3/2001
EP	1362683	A2	WO	2001/057130	A1	8/2001
EP	1240266	B1	WO	2001/071225	A1	9/2001
EP	0851894	B1	WO	2001/088033	A1	11/2001
EP	1272587	B1	WO	2002/070620	A1	9/2002
EP	1155084	B1	WO	2002/088214	A1	11/2002
EP	1431325	A1	WO	2003/011954	A1	2/2003
EP	1075498	B1	WO	2003/040251	A1	5/2003
EP	0820491	B1	WO			

(56)

References Cited

FOREIGN PATENT DOCUMENTS

WO	2003/051676	A1	6/2003
WO	2003/054069	A1	7/2003
WO	2003/058340	A1	7/2003
WO	2003/059997	A1	7/2003
WO	2003/072677	A1	9/2003
WO	2003/078163	A1	9/2003
WO	2003/095575	A1	11/2003
WO	2004/050740	A1	6/2004
WO	2004/055092	A1	7/2004
WO	2004/060956	A1	7/2004
WO	2004/060984	A1	7/2004
WO	2004/062869	A2	7/2004
WO	2004/065485	A1	8/2004
WO	2004/076507	A2	9/2004
WO	2004/078853	A2	9/2004
WO	2004/085510	A1	10/2004
WO	2004/085564	A1	10/2004
WO	2004/099312	A1	11/2004
WO	2005/002950	A2	1/2005
WO	2005/007720	A1	1/2005
WO	2005/019285	A1	3/2005
WO	2005/044630	A1	5/2005
WO	2005/047393	A1	5/2005
WO	2005/090431	A1	9/2005
WO	2005/090455	A1	9/2005
WO	2005/095484	A1	10/2005
WO	2005/105405	A1	11/2005
WO	2005/108456	A1	11/2005
WO	2005/113627	A1	12/2005
WO	2006/0743	94 A2	7/2006
WO	2006/128722		12/2006
WO	2006/131190	A1	12/2006
WO	2007/025007		3/2007
WO	2007/050658	A1	5/2007
WO	2008/014053	A2	1/2008
WO	2008/157129	A1	12/2008
WO	2009/016106	A1	2/2009
WO	2009/098141	A1	8/2009
WO	2009/124709	A1	10/2009
WO	2010/000371		1/2010
WO	2010/011705	A1	1/2010
WO	2011/012997	A2	2/2011
WO	2011/025873	A1	3/2011
WO	2011/109699	A1	9/2011
WO	2011/117398	A1	9/2011
WO	2011/117402	A1	9/2011
WO	2012/110230	A1	8/2012
WO	2013/068819	A2	5/2013

OTHER PUBLICATIONS

International Preliminary Report on Patentability dated Oct. 12, 2010; for Corresponding PCT Application No. PCT/EP2009/002546 filed Apr. 7, 2009.

PCT Written Opinion of the International Searching Authority dated Nov. 21, 2014 (Appl. No. PCT/IB2014/063427).

International Search Report dated Jul. 14, 2009; for Corresponding PCT Application No. PCT/EP2009/002546 filed Apr. 7, 2009.

Corresponding PCT Application No. PCT/EP2009/002546 filed Apr. 7, 2009; Published as WO 2009/124709 A1 on Oct. 15, 2009. Search Report dated Oct. 15, 2008; for Corresponding Application No. GB0806434.7 filed Apr. 9, 2008.

Corresponding No. GB0806434.7 filed Apr. 9, 2008; Published as WO 2009/124709 A1 on Oct. 15, 2009.

The Epoxy Book Published by System Three Resins, Inc. Seattle, Washington (2000).

"Epoxy Resins" Second Edition Encyclopedia of Polymer Science and Engineering, vol. 6, pp. 322-382 (1985).

Born et al. "Structural Bonding in Automotive Applications" (Apr. 2004).

Dvorko. "One-Part Epoxy Compounds and Derived Foam Plastics", published Apr. 13, 2004.

Zalobsky et al., "Recommendations on Selection and Use of Cavity Reinforcement Materials" Proceedings of the 1999 Noise and Vibration Conference.

Weber et al., "Characterizing the In Vehicle Performance of Expandable Sealants Used As Acoustic Baffles", Proceedings of the 1999 Noise and Vibrations Conference.

Weber et al., "Requirements for Improved Performance of Specialty Sealing and Bonding Materials for Automotive Applications", SAE 2000 World Congress, Mar. 6-9, 2000.

Liu et al., "Validation of Epoxy Foam for Structural and Crash Application", 2004 SAE World Congress, Mar. 8-11, 2004.

Schulenburg et al., "Structural Adhesives—Improvements in Vehicle Crash Performance", 2004 SAE World Congress, Mar. 8-11, 2004.

Casey et al., "Expandable Epoxy Foam: A Systematic Approach to Improve Vehicle Performance", 2004 SAE World Congress, Mar. 8-11, 2004.

Lilley et al., Vehicle Acoustic Solutions. (May 5-8, 2003).

Related U.S. Appl. No. 11/188,679, filed Jul. 25, 2005; Issued as U.S. Pat. No. 6,392,929 on Jul. 1, 2008.

Related U.S. Appl. No. 11/189,190, filed Jul. 26, 2005; Published as US 2006/0021697 A1 on Feb. 2, 2006.

Related U.S. Appl. No. 11/254,129, filed Oct. 19, 2005; Published as US 2006/0090343 A1 on May 4, 2006.

Related U.S. Appl. No. 11/339,431, filed Jan. 25, 2006; Issued as U.S. Pat. No. 7,467,452 on Dec. 23, 2008.

Related U.S. Appl. No. 11/390,658, filed Mar. 28, 2006; Issued as U.S. Pat. No. 7,494,179 on Feb. 24, 2009.

Related U.S. Appl. No. 11/391,884, filed Mar. 29, 2006; Published as US 2007-0122510 A1 on May 31, 2007.

Related U.S. Appl. No. 11/339,535, filed Mar. 30, 2006; Published as US 2006-0171269 A1 on Aug. 3, 2006.

Related Patent Application No. 11/393,431, filed Mar. 30, 2006; Published as US 2007-0134058 A1 on Jun. 14, 2007.

Related U.S. Appl. No. 11/401,207, filed Apr. 10, 2006; Published as US 2007-0087848 A1 on Apr. 19, 2007.

Related Patent Application No. 11/381,769, filed May 5, 2006; Issued as U.S. Pat. No. 7,503,620 on Mar. 17, 2009.

Related U.S. Appl. No. 11/422,705, filed Jun. 7, 2006; Issued as U.S. Pat. No. 7,438,782 on Oct. 21, 2008.

Related U.S. Appl. No. 10/597,610, filed Aug. 1, 2006; Published as US 2008-0241576 A1 on Oct. 2, 2008.

Related U.S. Appl. No. 11/461,557, filed Aug. 1, 2006; Issued as U.S. Pat. No. 7,926,179 on Apr. 19, 2011.

Related U.S. Appl. No. 11/467,185, filed Aug. 10, 2006; Published as US 2007-0045042 A1 on Mar. 1, 2007.

Related Patent Application No. 10/867,835, filed Jun. 15, 2004; Issued as U.S. Pat. No. 7,199,165 on Apr. 3, 2007.

Related Patent Application No. PCT/US04/20112, filed Jun. 23, 2004; Published as WO 2005/002950 on Jan. 13, 2005.

Related Patent Application No. US 2011/027166 filed Mar. 4, 2011; Published as WO 2011/109699 on Sep. 9, 2011.

Related U.S. Appl. No. 13/387,192, filed Apr. 4, 2012; Published as US 2012-0186721 A1 on Jul. 26, 2012.

Related Patent Application No. 11/551,035, filed Oct. 19, 2006; Published as US 2007-0090560 A1 on Apr. 26, 2007.

Korean Office Action dated Aug. 20, 2015; Application No. 10-2010-7025154.

European Office Action dated Sep. 24, 2014 for Application No. 09729501.8.

European Office Action dated Oct. 4, 2012 for Application No. 09729501.8.

Japanese Office Action dated Jul. 23, 2014; Application No. 2011-503370.

Notice of Opposition dated Apr. 23, 2015; European Patent No. EP2553034.

Opposition dated Apr. 23, 2015; European Patent No. 2553034.

Notice of Opposition dated Mar. 31, 2015; European Patent No. EP2553035.

Opposition dated Apr. 9, 2015; European Patent No. EP2553035. Mechanical Properties of Epoxy—Polyurethane Polymer Blends Dated Dec. 3, 2006; Kh.R.AL Rawi; Um-Salama Science Journal; vol. 3.

(56)


References Cited

OTHER PUBLICATIONS

Shape Memory Epoxy: A Systematic Study of their Performance; 2009; Ingrid A. Rousseau; vol. 7289.
Army Research Laboratory; Interpenetrating Polymer Network (IPN) Adhesives for Electron Beam Cure; James M. Sands; Sep. 2000.
Synthesis and Properties of Polyurethane Acrylate/Epoxy Resin Interpenetrating Polymer Networks; Chinese Journal of Polymer Science; vol. 6, No. 3; 1988.
R.E. Touhsaent, D.A. Thomas, and L.H. Sperling: "Epoxy/Acrylic Simultaneous Interpenetrating Networks" J. Polymer Sci.: Symposium, Nr. 46, 1974, Seiten 175-190.
International Preliminary Report on Patentability dated Oct. 2, 2012; Application No. PCT/EP2011/054642.
International Search Report dated May 30, 2011; Application No. PCT/EP2011/054642.
International Preliminary Report on Patentability dated Oct. 15, 2015; Application No. PCT/EP2011/054647.
International Search Report dated May 30, 2011; Application No. PCT/EP2011/054647.
PCT International Preliminary Report on Patentability dated Feb. 7, 2013; Application No. PCT/EP2011/003736.
PCT International Search Report & the Written Opinion dated Jun. 6, 2012; Application No. PCT/EP2011/003736.
European Communication dated Mar. 12, 2013; Application No. 11746457.8-1302.

Chinese Office Action dated Jan. 12, 2015; Application No. 201180029998.2.
Copending U.S. Appl. No. 12/936,777, filed Dec. 3, 2010 (Published as WO2009124709) .
Copending U.S. Appl. No. 12/136,333, filed Jun. 10, 2008.
International Preliminary Report on Patentability dated Nov. 22, 2012 for PCT/EP2011/002293.
International Search Report & Written Opinion dated Jun. 6, 2012 for PCT/EP2011/002293.
UK Search Report dated May 6, 2011 for Application No. GB1007793.1.
International Preliminary Report on Patentability for PCT/US2008/066413, dated Mar. 19, 2010.
Chinese Second Office Action dated Feb. 9, 2018; Application No. 201480052851.9.
Chinese Office Action dated Dec. 5, 2016; Application No. CN201480052850.4.
Chinese Office Action dated Feb. 9, 2018, Application No. 201480052851.9.
Chinese Decision of Rejection dated Feb. 11, 2019, Application No. 201480052851.9.
Chinese Decision of Rejection dated Jan. 31, 2019, Application No. 201480052850.4.
India Examination Report dated Dec. 23, 2019, Application No. 201637002780.
India Examination Report dated Dec. 18, 2019, Application No. 201637002781.

* cited by examiner



THERMOSETTING ADHESIVE FILMS

FIELD

The present invention relates to adhesive films and in one embodiment to adhesive films that are non-tacky to the touch at room temperature. Additionally the films are storage stable at room temperature and can be heat activated to produce a strong bond between two substrates. The adhesive films are particularly useful in the production of an adhesive bond between two dissimilar substrates and/or in the bonding to oily surfaces which traditionally have been difficult to bond to.

BACKGROUND

The adhesive films when cured should not be brittle and should provide fracture toughness which means that a flaw in the film is protected against propagation and it is also desirable that the cured films have an elongation to break to allow them to help absorb impact. Thermosetting adhesive compositions are well known and many are based on epoxy resins and various methods have been proposed to improve the toughness of the adhesive bond formed and to control the glass transition temperature and accordingly reduce the brittleness of the cured adhesive. The adhesives are often used in highly automated processes such as in the production of components for automobiles, aerospace vehicles such as aircraft and rockets and in the construction and furniture industries. One desirable property is that the adhesive can be cured over a relatively short period of time and at temperatures conventionally used in the production of such components. In this way the curing of the adhesive will not unduly delay the component production process.

It has also been proposed that the adhesives may be in the form of films. The known films based on epoxy resins that can be used as an adhesive do not have the combined properties of being non-tacky to the touch at room temperature and storage stable at room temperature being flexible and protected against the propagation of flaws. Additionally, some have an unpleasant odour and do not have the requisite cure time and cure temperature.

Additionally, it is desirable that the adhesives can be applied and cured in any location. Prior thermosetting adhesives tend to be thin liquids during the curing process which means they can flow during cure if used in a vertical or inclined position and may not remain in the desired location. For example when used to bond vertical or inclined surfaces. Accordingly on one embodiment the invention provides a thermosetting curable adhesive which has thixotropic properties during the curing of the adhesive at the preferred curing temperature.

To be non-tacky to the touch at room temperature is beneficial in that the films may be reeled and unreel without sticking to each other. Within this patent application a film is considered to be non-tacky to the touch if it does not need a force more than 2 N to pull out a 25 mm diameter stainless steel plate applied on its surface. Although in certain instances it may be useful for the film to have a tacky surface.

Storage stability at room temperature is also important in that if the film is storage stable at room temperature it is not necessary to provide costly refrigeration facilities for storage and transport of the film. By storage stable at room temperature we mean that the uncured adhesive does not lose more than 10%, preferably not more than 5%, of its mechanical performances after three months of storage at

room temperature (23° C.). Many earlier films need to be stored at 0° C. or below. The films of this invention can therefore be stored, transported and cut at ambient temperature. Additionally if they are used with a release liner, the liner can be easily removed at room temperature.

It is also desirable that the films can be produced by extrusion.

Another important quality of the film is that it can be cured to adhere to oily surfaces such as metals with oil on their surfaces. The film is considered to adhere to oily surfaces if upon curing the film will adhere to a metal surface provided with a layer of 3 g/m² of corrosion preventive oil like Anticorit® and Ferrocoat®. The shear strength of this assembly should not be reduced by more than 15%, preferably no more than 10%, of the shear strength of a similar assemblies made without the oil.

A difficulty when thermosetting adhesive films are used to bond dissimilar substrates is that the substrates may have different coefficients of thermal expansion and accordingly the surfaces of the substrates may move relative to each other, albeit by small amounts, during the heating to cure the adhesive. Hereagain a short cure time of the adhesive and a low coefficient of thermal expansion are beneficial in that it reduces the time available for thermal expansion of the substrates and thus reduces the relative positional changes of the substrates. Additionally the thermosetting adhesive film should have sufficient flexibility during the cure process to allow for a degree of movement between the substrates.

SUMMARY

The invention provides an adhesive film which satisfies these requirements and which has an overall desirable combination of properties.

The invention therefore seeks to provide a thermosetting adhesive film which is

- i) preferably non-tacky to the touch at room temperature
- ii) is flexible prior to cure
- iii) is storage stable at room temperature
- iv) can be cured in no more than 45 minutes preferably 15 minutes at a temperature no higher than 220° C. preferably no higher than 190° C. preferably 130° C. to 190° C.
- v) preferably forms an adhesive bond with oily surfaces
- vi) has enhanced protection against the propagation of flaws and
- vii) preferably is thixotropic during the heat curing of the adhesive film especially in the temperature range 130° C. to 220° C.

There may be prior films that have one or more comparable properties but the films of this invention provide improved combined overall properties.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a perspective view illustrating a manufacturing process in accordance with the present teachings.

DETAILED DESCRIPTION

In a preferred embodiment the adhesive film is epoxy resin based.

Additionally we have found that through use of a preferred formulation to produce the films of this invention films having improved uniformity of thickness can be obtained which allows more precise predictions and control of the properties of the final bond.

3

It is preferred that the film be produced by extrusion.

The films may be foamable and they preferably have the following properties. An unfoamed film

Density (uncured): 1.1 to 1.5 preferably 1.3±0.1 kg/dm³

Thickness (uncured): 0.3 to 2 mm

Cure Temperature: 130° C. to 210° C. preferably 130° C. to 190° C.

Expansion during curing: <5%

Typical Lap Shear Resistance: >30 MPa

Cure Conditions: 30 min at 165° C.

Samples: 1.8 mm G10/10 HD galvanized steel, 0.3 mm bondline, 25×12.5 mm overlap

Test Speed: 10 mm/min

Average T Peel resistance greater than 7 Nmm

Young Modulus: >2200 MPa

Elongation to break: 1 to 4%

Storage stability at room temperature at least 3 months

Good adhesion to oily surfaces, as shown by loses of less than 20% of its mechanical properties when compared to adhesion to a non-oily surface.

A Foamed Film

Density (uncured): 1.1 to 1.5 preferably 1.3±0.1 kg/dm³

Thickness (uncured): 0.3 to 2 mm

Cure Temperature: 130° C. to 210° C. preferably 130° C. to 190° C.

Expansion During Curing: 5 to 140% preferably 50% for 2 mm film thickness (increase slightly with thickness)

Typical Lap Shear Resistance: >20 MPa

Cure Conditions: 30 min at 165° C.

Samples: 1.8 mm G10/10 HD galvanized steel, 0.3 mm bondline, 25×12.5 mm overlap

Test Speed: 10 mm/min

Average T Peel resistance greater than 7 Nmm

Young Modulus: >750 MPa

Elongation to break: 12 to 20%

Storage stability at room temperature at least 3 months

Good adhesion to oily surfaces, as shown by loses of less than 20% of its mechanical properties when compared to adhesion to a non-oily surface.

T Peel resistance is measured according to NFEN ISO 113394 with a substrate of 0.7 mm G 10/10 galvanised steel and a bond line of 25×100×0.3 mm.

The adhesive film preferably has an uncured thickness between 0.2 and 3.0 mm.

PCT Publication WO 2011/025873 relates to thermosetting adhesive compositions which can be provided as films. However, the thermosetting materials are pre-reacted which means that the films will not have the desired flexibility prior to exposure in the thermosetting environment and are difficult to employ in irregular shaped environments. Additionally the adhesive film cannot be produced by extrusion and the adhesives of WO 2011/025873 are shown to have an undesirably long cure time of about 90 minutes at 165° C. The films also have poor storage stability at room temperature and need to be stored under refrigerated conditions

The formulations employed to produce the adhesive films of the present invention will depend upon the use to which the adhesive film is to be put.

A preferred formulation from which the adhesive film of the invention may be produced comprises

- i) a phenoxy resin
- ii) an elastomer/epoxy resin adduct
- iii) a core shell material and
- iv) a curing agent

preferably the formulation additionally contains an epoxy resin.


4

It is important that the films of this invention are not brittle and also that they have fracture toughness which is the ability to resist propagation of a flaw once one exists within the film. We have found that the use of a phenoxy resin improves the flexibility of the film and reduces the brittleness compared to films based solely upon epoxy resins. We have also found that the use of the elastomer epoxy adduct and the core/shell material provide fracture toughness as well as contributing to the flexibility of the film.

We prefer to use a formulation that contains at least 15 wt % of a phenoxy resin, preferably from 15 to 40 wt % of a phenoxy resin. We prefer that the formulation contain at least 5 wt % of an elastomer epoxy resin adduct preferably from 5 to 40 wt %. Additionally the preferred formulation contains at least 5 wt % of a core shell polymer, preferably from 5 to 25 wt %. The percentages being of the entire formulation including other ingredients that may be present.

The phenoxy resins are high molecular weight materials which typically have a melting point around 150° C. or higher. As one important use of the films of this invention is in the production of adhesive bonds by the curing of the films at temperatures experienced in the automobile e-coat process, it is preferred to formulate the formulation from which the film is made at temperatures below the melting point of the phenoxy resin. Accordingly it is preferred that the phenoxy resin be provided to the formulating activity as a solution. We have found that a liquid epoxy resin is a particularly good solvent for the phenoxy resin.

Preferred phenoxy resins are high molecular weight thermoplastic condensation products of bisphenol A and epichlorohydrin and their derivatives. Typically the phenoxy resins that may be employed are of the formula



where n is typically from 30 to 100 preferably from 50 to 90. Modified phenoxy resins may also be used. Examples of phenoxy resins that may be used are the products marketed by Inchem Corp. Examples of suitable materials are the PKHB, PKHC, PKHH, PKHJ, PKHP-pellets and powder. Alternatively phenoxy/polyester hybrids and epoxy/phenoxy hybrids may be used. In order to enhance the production of the structural adhesive the phenoxy resin may be supplied to the other components as a solution. While any solvent may be used it is particularly preferred to use a liquid epoxy resin as the solvent as this can also contribute to the adhesive properties upon activation.

Typical other ingredients which may be used in the formulation include epoxy resins, hardeners (curing agents) for the epoxy resins, tougheners for the epoxy resin system and flexibilizers. The films are preferably produced by extrusion and it is therefore preferred to include a reactive diluent in the formulation which aids extrusion and increases the flexibility of the uncured adhesive film, the use of a reactive diluent can also enable extrusion of the adhesive composition to form the film and can increase the ability of the adhesive formulation to impregnate fibrous layers which may be used as a support for the adhesive film as is discussed later. Mono-functional epoxy resins are particularly useful as reactive diluents.

In one embodiment the invention therefore provides the use of reactive diluent such as a mono-functional epoxy

resin in a thermosetting adhesive film to increase the flexibility of the uncured adhesive film.

The thermosetting adhesive films of this invention may contain epoxy resins and may contain other components according to the adhesive performance that is required.

Examples of other components which may be included in the formulations from which the films are made are

- i. rubbers and elastomers optionally modified with epoxy resins to provide increased toughness to the cured adhesive, preferably including a core shell rubber material
- ii. curing agents for epoxy resins optionally together with curing agent accelerators
- iii. optionally foaming agents if the adhesive is required to be a foamable material.

The preferred thermosetting adhesive compositions therefore contain a phenoxy resin, an epoxy resin in combination with elastomers and/or thermoplastics which are preferably core-shell particles and can be thermally cured with curing agents such as amine curing agents to provide thermosetting adhesive compositions having high toughness and high temperature shear properties upon cure combined with a non-tacky surface at room temperature and good storage stability at room temperature. In addition to the unexpected increase in higher temperature properties with improved toughness, these cured films are also characterized by high glass transition temperatures, high Young's modulus, a desirable elongation to break and low water absorption making these compositions suitable for demanding environments that require high performance, such as for the aerospace and automotive industries.

Core-Shell Particles

Particles having a core-shell structure are a preferred component of the compositions used to produce the films of the present invention. Such particles generally have a core comprised of a polymeric material having elastomeric or rubbery properties (i.e., a glass transition temperature less than about 0° C., e.g., less than about -30° C.) surrounded by a shell comprised of a non-elastomeric polymeric material (i.e., a thermoplastic or thermoset/crosslinked polymer having a glass transition temperature greater than room temperatures, e.g., greater than about 50° C.). For example, the core may be comprised of, for example, a diene homopolymer or copolymer (for example, a homopolymer of butadiene or isoprene, a copolymer of butadiene or isoprene with one or more ethylenically unsaturated monomers such as vinyl aromatic monomers, (meth)acrylonitrile, (meth)acrylates, or the like) while the shell may be comprised of a polymer or copolymer of one or more monomers such as (meth)acrylates (e.g., methyl methacrylate), vinyl aromatic monomers (e.g., styrene), vinyl cyanides (e.g., acrylonitrile), unsaturated acids and anhydrides (e.g., acrylic acid), (meth)acrylamides, and the like having a suitably high glass transition temperature. The polymer or copolymer used in the shell may have acid groups that are crosslinked ionically through metal carboxylate formation (e.g., by forming salts of divalent metal cations). The shell polymer or copolymer could also be covalently crosslinked through the use of monomers having two or more double bonds per molecule. Other elastomeric polymers may also be suitably be used for the core, including polybutylacrylate or polysiloxane elastomer (e.g., polydimethylsiloxane, particularly crosslinked polydimethylsiloxane). The particle may be comprised of more than two layers (e.g., a central core of one elastomeric material may be surrounded by a second core of a different elastomeric material or the core may be surrounded by two shells of different composition or the particle may have the

structure soft core, hard shell, soft shell, hard shell). Either the core or the shell or both the core and the shell may be crosslinked (e.g., ionically or covalently), as described, for example, in U.S. Pat. No. 5,686,509. The shell may be grafted onto the core. The polymer comprising the shell may bear one or more different types of functional groups (e.g., epoxy groups, carboxylic acid groups) that are capable of interacting with other components of the compositions of the present invention. In other embodiments, though, the shell is free of functional groups capable of reacting with other components present in the composition. Typically, the core will comprise from about 50 to about 95 percent by weight of the particles while the shell will comprise from about 5 to about 50 percent by weight of the particles.

Preferably, the elastomeric particles are relatively small in size. For example, the average particle size may be from about 30 nm to about 120 nm. In certain embodiments of the invention, the particles have an average diameter of less than about 80 nm. In other embodiments, the average particle size is less than about 100 nm. For example, the core-shell particles may have an average diameter within the range of from 50 to about 100 nm.

Elastomeric particles having a core-shell structure are available from several commercial sources. The following core-shell particles are suitable for use in the present invention, for example: the core-shell particles available in powder form from Wacker Chemie under the tradename GENIOPERL, including GENIOPERL P22, P23, P52 and P53, which are described by the supplier as having crosslinked polysiloxane cores, epoxy-functionalized polymethylmethacrylate shells, polysiloxane content of about 65 weight percent, softening points as measured by DSC/DMTA of about 120° C., and a primary particle size of about 100 nm, the core-shell rubber particles available from Dow under the tradename PARALOID, in particular the PARALOID EXL 2600/3600 series of products, which are grafted polymers containing a polybutadiene core upon which is grafted a styrene/methylmethacrylate copolymer and having an average particle size of ca. 0.1 to about 0.3 microns; the core-shell rubber particles sold under the tradename DEGALAN by Evonik Röhm GmbH or Röhm America, Inc. (e.g., DEGALAN 4899F, which is reported to have a glass transition temperature of about 95° C.); the core-shell rubber particles sold by Nippon Zeon under the tradename F351; and the core-shell rubber particles sold by Galata Chemicals under the tradename BLENDX.

Elastomeric particles having a core-shell structure may be prepared as a masterbatch where the particles are dispersed in one or more epoxy resins such as a diglycidyl ether of bisphenol A. For example, the particles typically are prepared as aqueous dispersions or emulsions. Such dispersions or emulsions may be combined with the desired epoxy resin or mixture of epoxy resins and the water and other volatile substances removed by distillation or the like. One method of preparing such masterbatches is described in more detail in European Patent Application EP 1632533. For example, an aqueous latex of rubber particles may be brought into contact with an organic medium having partial solubility in water and then with another organic medium having lower partial solubility in water than the first organic medium to separate the water and to provide a dispersion of the rubber particles in the second organic medium. This dispersion may then be mixed with the desired epoxy resin(s) and volatile substances removed by distillation or the like to provide the masterbatch. Other methods for preparing masterbatches of elastomeric particles having a core-shell structure stably dispersed in an epoxy resin matrix are described in U.S. Pat.

Nos. 4,778,851 and 6,111,015. Preferably, the particles are stably dispersed in the epoxy resin matrix, i.e., the core-shell particles remain as separated individual particles with little or no agglomeration of the particles or precipitation (settling) of the particles from the masterbatch as the masterbatch is aged by standing at room temperature. The shell of the elastomeric particles may advantageously be functionalized to improve the stability of the masterbatch, although in another embodiment the shell is non-functionalized (i.e., does not contain any functional groups that react with any of the other components of the adhesive composition (such as the epoxy resin or curing agent) when that composition is cured). Particularly suitable dispersions of particles having a core-shell structure in an epoxy resin matrix are available from Kaneka Corporation, and include, for example, KANE ACE MX 120®.

Assuming that the total amount of the epoxy resin and rubber particles in a masterbatch is 100% by weight, the content of the core-shell particles may be, for example, 0.5 to 80% by weight, preferably 1 to 70% by weight, more preferably 3 to 60% by weight, still more preferably 20 to 40% by weight. In one embodiment, the weight percentage of the epoxy resin containing, or predispersed with, nano core-shell particles is from 40% to 50% of the total weight of the composition.

The use of these core shell rubbers provides toughness to the cured adhesive film, irrespective of the temperature or temperatures used to cure the formulation. Many of the core-shell rubber structures available from Kaneka in the form of phase separated particles dispersed in epoxy resin are believed to have a core made from a copolymer of (meth)acrylate-butadiene-styrene, where butadiene is the primary component of the copolymer in the core. Other commercially available masterbatches of core-shell rubber particles dispersed in epoxy resins include GENIOPERL M23A (a dispersion of 30 wt % core-shell particles in an aromatic epoxy resin based on bisphenol A diglycidyl ether; the core-shell particles have an average diameter of ca. 100 nm and contain a crosslinked silicone elastomer core onto which an epoxy-functional acrylate copolymer has been grafted; the silicone elastomer core represents about 65 wt % of the core-shell particle), available from Wacker Chemie GmbH.

Typically, the composition from which the films are made may contain from 5 to 30 wt %, preferably 5 to 25 wt %, more preferably from 8 to 20 wt %, elastomeric particles having a core-shell structure. Combinations of different core-shell particles may advantageously be used in the present invention. The core-shell particles may differ, for example, in particle size, the glass transition temperatures of their respective cores and/or shells, the compositions of the polymers used in their respective cores and/or shells, the functionalization of their respective shells, and so forth.

Toughening Agents

Toughening agents are preferably included in the compositions used to prepare the films of this invention. Suitable toughening agents may be selected from a wide variety of substances, but generally speaking such materials are polymeric or oligomeric in character, and may have functional groups such as epoxy groups, carboxylic acid groups, amino groups and/or hydroxyl groups capable of reacting with the other components of the compositions, the composition is cured by heating.

The epoxy-based prepolymers obtained by reacting one or more amine-terminated polymers such as amine-terminated polyethers and amino silane-terminated polymers with one or more epoxy resins represent a particularly preferred class

of toughening agents. The epoxy resins useful for such purpose may be selected from among the epoxy resins described hereinabove, with particular preference being given to the diglycidyl ethers of polyphenols such as bisphenol A and bisphenol F (for example, having epoxy equivalent weights of from about 150 to about 1000). Mixtures of solid and liquid epoxy resins may be suitably employed.

The preparation of such epoxy-based prepolymers from amine-terminated polyethers is well known in the art and is described, for example, in U.S. Pat. Nos. 5,084,532 and 6,015,865. Generally speaking, it will often be desirable to adjust the ratio of amine-terminated polyether epoxy resin being reacted such that there is an excess of epoxy groups relative to amine groups such that the latter functional groups are completely reacted (i.e., the epoxy-based prepolymer contains essentially no free amine groups). Mixtures of di- and trifunctional amine-terminated polyethers may be used. Amine-terminated polyethers containing both oxyethylene and oxypropylene repeating units (e.g., copolymers of ethylene oxide and propylene oxide, with the copolymers having a block, capped or random structure) may also be utilized as the amino-terminated polyether. Preferably, the amino-terminated polyether contains at least two amine groups per molecule. Preferably, the amine groups are primary amine groups.

When reacting the epoxy resins with the amine-terminated polyether, an excess of epoxy groups over the amino groups is preferably used so that the latter react completely with epoxide groups. Typically, there is a 1.5 to 10-fold excess, for example a 3.5-fold excess of epoxy groups over the active hydrogen equivalents (AHEW) of the amine-terminated polyether. In preparing the composition according to the present invention, the epoxy-based prepolymer component preferably is initially prepared in a first stage. To this end, preferably, the epoxy resins are reacted with the amine-terminated polyether in the desired ratio. The reaction preferably is carried out at high temperature, preferably at 90° to 130° C., for example at approximately 120° C., for a duration of, e.g., three hours.

Other suitable toughening agents include amorphous polysulfones, i.e., those polymers that contain predominately ether and sulfone groups interspersed between arylene residues. Such polysulfones, sometimes called polyethersulfones, may be prepared by the processes taught in U.S. Pat. No. 4,175,175, and particularly U.S. Pat. No. 3,647,751, for example.

Polysulfones containing ether and alkylene groups in addition to sulfone groups are predominately amorphous, and are suitable candidates for the practice of the subject invention. Such polysulfones (polyethersulfones) have glass transition temperatures T_g of greater than 150° C., preferably greater than 175° C., and most preferably in excess of 190° C. The T_g of a preferred KM 180 amine terminated polyether sulfone (manufactured by Cytec Industries Inc., Woodland Park N.J.) is approximately 200° C.

Other tougheners or impact modifiers known in the epoxy adhesive art may be used in addition to the aforementioned prereacts derived by reaction of amine-terminated polymers or amino silane-terminated polymers with epoxy resins. Generally speaking, such tougheners and impact modifiers are characterized by having glass transition temperatures ranging from -30° C. to 300° C. Examples of such tougheners and impact modifiers include, but are not limited to: reaction products of epoxy-reactive copolymers of butadiene (especially epoxy-reactive copolymers of butadiene with relatively polar comonomers such as (meth)acryloni-

trile, (meth)acrylic acid, or alkyl acrylates, e.g., carboxyl-terminated butadiene-nitrile rubbers. Other examples include polyimides such as Matrimid 9725 supplied by Huntsman, Polyetherimides such as Ultem supplied by Sabic and others.

Mixtures of different auxiliary impact modifiers/toughening agents may be used. The amount of auxiliary impact modifier/toughening agent in the curable compositions of the present invention may vary substantially but typically is from about 0.1 to about 20 wt %, e.g. from about 5 to about 15 wt %. In one embodiment, it is contemplated that the toughening agent is present from about 10% to about 15% by weight of the total.

In another embodiment, the thermosetting adhesive compositions include a toughening agent chosen from carboxy-terminated acrylonitrile-butadiene copolymer, polyamides, polyimides, and amido-amides. The carboxy-terminated acrylonitrile-butadiene copolymer can include, for example, NIPOL 1472 from Zeon, whereas the polyamide can include, for example, polyamide. Suitable polyimides are known to those of ordinary skill in the art and include, for example, those described in detail in U.S. Pat. No. 5,605,745. Particularly preferred are those polyimides which, because of the asymmetry of the dianhydride or diamine, particularly the latter, possess a lesser degree of crystallinity or are wholly amorphous. Polyimides based on BTDA and AATI are preferred. Such polyimides are available commercially under the trademark MATRIMID® 5218 from Huntsman and have an inherent viscosity of >0.62 dl/g when measured at 0.5 wt % concentration in N-methylpyrrolidone at 25° C. The molecular weight of these most preferred polyimides is greater than 20,000 Daltons, preferably greater than 50,000 Daltons, and most preferably in the range of about 100,000 Daltons.

Epoxy Elastomer Adduct

An epoxy elastomer adduct is preferably included in the formulation to impart flexibility to the structural adhesive film and also enhance the ability to initiate plastic deformation. Various epoxy/elastomer adducts may be employed. The epoxy/elastomer hybrid or adduct may be included in an amount of up to about 50% by weight of the structural adhesive. The epoxy elastomer adduct is approximately at least 5%, more typically at least 7% and even more typically at least 10% by weight of the formulation and more preferably about 12% to 40% by weight of the adduct based on the structural adhesive. The elastomer-containing adduct may be a combination of two or more particular adducts and the adducts may be solid adducts, semi-solids, at a temperature of 23° C. or may also be combinations thereof. A solid adduct is preferred in one preferred embodiment the adduct is composed of substantially entirely (i.e., at least 70%, 80%, 90% or more) of one or more adducts that are solid at a temperature of 23° C. We have found unexpectedly that when the adduct is used in the films of this invention together with a core/shell polymer desirable adhesive performance can be achieved over a wide range of temperatures the adduct imparts high temperature stability to the adhesive since there is little undesirable lowering of the T_g of the cured adhesive.

The adduct itself generally includes about 1:5 to 5:1 parts of epoxy to elastomer, and more preferably about 1:3 to 3:1 parts of epoxy to elastomer. More typically, the adduct includes at least about 10%, more typically at least about 20% and even more typically at least about 40% elastomer and also typically includes not greater than about 60%, although higher or lower percentages are possible. The elastomer compound suitable for the adduct may be a

thermosetting elastomer, although not required. Exemplary elastomers include, without limitation, natural rubber, styrene-butadiene rubber, polyisoprene, polyisobutylene, polybutadiene, isoprene-butadiene copolymer, neoprene, nitrile rubber (e.g., a butyl nitrile, such as carboxy-terminated butyl nitrile), butyl rubber, polysulfide elastomer, acrylic elastomer, acrylonitrile elastomers, silicone rubber, polysiloxanes, polyester rubber, diisocyanate-linked condensation elastomer, EPDM (ethylene-propylene diene rubbers), chlorosulphonated polyethylene, fluorinated hydrocarbons and the like. In one embodiment, recycled tire rubber is employed. Examples of additional or alternative epoxy/elastomer or other adducts suitable for use in the present invention are disclosed in United States Patent Publication 2004/0204551.

The elastomer-containing adduct is included to modify structural properties of the adhesive film such as strength, toughness, stiffness, flexural modulus, and the like. Additionally, the elastomer-containing adduct may be selected to render the activatable material more compatible with coatings such as water-borne paint or primer system or other conventional coatings.

Curing Agents

By the term curing agent is meant a reactive component capable of either reacting with the phenoxy resin, or the epoxy functional group or polymerizing the epoxy functional group. The films of this invention are to be cured at elevated temperature, and they also contain one or more curing agents (hardeners) capable of accomplishing cross-linking or curing of certain of the adhesive components when the adhesive is heated to a temperature well in excess of room temperature.

There may be used as thermally-activatable or latent hardeners for the adhesive compositions of the present invention, for example, guanidines, substituted guanidines, substituted ureas, melamine resins, guanamine derivatives, blocked amines, aromatic amines and/or mixtures thereof. The hardeners may be involved stoichiometrically in the hardening reaction; they may, however, also be catalytically active. Examples of substituted guanidines are methylguanidine, dimethylguanidine, trimethylguanidine, tetramethylguanidine, methylisobiguanidine, dimethylisobiguanidine, tetramethylisobiguanidine, hexamethylisobiguanidine, heptamethylisobiguanidine and, more especially, cyanoguanidine (dicyandiamide). Representatives of suitable guanamine derivatives which may be mentioned are alkylated benzoguanamine resins, benzoguanamine resins or methoxymethylethoxymethylbenzoguanamine. For single-component, thermosetting adhesives, the selection criterion is, of course, the low solubility of those substances at room temperature in the resin system, so that solid, finely ground hardeners are preferred; dicyandiamide is especially suitable. Good storage stability at room temperature of the composition is thereby ensured. The amount of curing agent utilized will depend upon a number of factors, including whether the curing agent acts as a catalyst or participates directly in crosslinking of the composition, the concentration of epoxy groups and other reactive groups in the composition, the desired curing rate and so forth. Typically, the composition contains from about 0.5 to about 1 equivalents of curing agent per one equivalent of epoxy molecule.

Generally, such curing agents have relatively low molecular weights and reactive functionalities which are phenolic hydroxyl, amine, amide, or anhydride. Preferable curing agents are the monomeric and oligomeric amine functional polyarylenes wherein between the arylene groups are simple covalent bridges such as in the diaminodiphenyls, or con-

necting groups selected from the group consisting of alkylene of from 1-8 carbon atoms, ether, sulfone, ketone, carbonate, carboxylate, carboxamide and the like.

In one embodiment, the amine curing agent is a mixture of dicyandiamide (DICY) and bisurea and the composition is cured at 120° C. In another embodiment, the amine curing agent is a diaminodiphenylsulfone (DDS) and the curing temperature is 180° C. In certain embodiments, the curing agent is a combination of DICY and DDS.

Optionally curing agent accelerators may also be included. The amounts of curing agents and curing agent accelerators used can vary widely depending upon the type of structure desired, the desired properties of the structural adhesive and in the embodiment when the material is expandable the desired amount of expansion of the activatable material and the desired rate of expansion. Exemplary ranges for the curing agents or curing agent accelerators present in the structural adhesive range from about 0.001% by weight to about 7% by weight.

Epoxy Resins

The thermosetting resin formulations used to make the films of the invention usually contain epoxy resins. The epoxy resins that can be employed for the present invention are curable epoxy resins having a plurality of epoxy groups per molecule. In general, a large number of glycidyl ethers having at least about two epoxy groups per molecule are suitable as epoxy resins for the compositions used in this invention. The polyepoxides may be saturated, unsaturated, cyclic or acyclic, aliphatic, alicyclic, aromatic or heterocyclic polyepoxide compounds. Examples of suitable polyepoxides include the polyglycidyl ethers, which are prepared by reaction of epichlorohydrin or epibromohydrin with a polyphenol in the presence of alkali. Suitable polyphenols therefore are, for example, resorcinol, pyrocatechol, hydroquinone, bisphenol A (bis(4-hydroxyphenyl)-2,2-propane), bisphenol F (bis(4-hydroxyphenyl)methane), bisphenol S, bis(4-hydroxyphenyl)-1,1-isobutane, fluorene 4,4'-dihydroxybenzophenone, bis(4-hydroxyphenyl)-1,1-ethane, bisphenol Z (4,4'-Cyclohexylidenebisphenol), and 1,5-hydroxynaphthalene. In one embodiment, the epoxy resin includes EPON 828. Other suitable polyphenols as the basis for the polyglycidyl ethers are the known condensation products of phenol and formaldehyde or acetaldehyde of the novolac resin-type.

Other polyepoxides that are in principle suitable are the polyglycidyl ethers of polyalcohols, aminophenols or aromatic diamines. Particular preference is given to the liquid epoxy resins derived by reaction of bisphenol A or bisphenol F and epichlorohydrin. The bisphenol based epoxy resins that are liquid at room temperature generally have epoxy equivalent weights of from 150 to about 200. The epoxy resins that are solid at room temperature may also or alternatively be used and are likewise obtainable from polyphenols and epichlorohydrin and have melting point of from 45 to 130° C., preferably from 50 to 80° C. Typically, the composition may contain from about 25 to about 90 wt % (e.g., 25, 30, 35, 40, 45, 50, 55 wt %) of epoxy resin (unless otherwise stated, all concentrations set forth herein are expressed in terms of the weight percent of the component in question based on the adhesive composition as a whole).

Epoxy resins vary in reactivity and molecular weight and the epoxy resin used should be chosen to provide adhesive strength and also the desired viscosity during cure to prevent sag and flow. Mixtures of liquid and solid epoxy resins may be used.

As mentioned previously, the epoxy resins are not used alone, but are combined with suitable curing agents, catalysts, rheology control agents, tackifiers, fillers, elastomeric toughening agents, reactive diluents, soluble thermoplastics and other additives according to the properties required of the film.

The compositions used to produce the films of this invention may contain other ingredients such as one or more of the following

- i) polymers;
- ii) blowing agents;
- iii) fillers;
- iv) flow control materials;
- v) nano particles;
- vi) pigments;
- vii) flame retardants;
- viii) fibres;
- ix) moisture scavengers.

Other Additives

The compositions from which the films are made may contain known fillers such as the various ground or precipitated chalks, quartz powder, alumina, metallic aluminium powder, aluminium oxide, zinc oxide, calcium oxide, silver flakes, dolomite, graphite, granite, carbon fibres, glass fibres, textile fibres, polymeric fibres, titanium dioxide, fused silica, nano and hydrophobic grade silica (e.g., TS720), sand, carbon black, calcium oxide, calcium magnesium carbonates, barite and, especially, silicate-like fillers of the aluminium magnesium calcium silicate type, for example wollastonite and chlorite. Typically, the compositions used to produce the films of the present invention may contain from about 0.5 to about 40 wt % of fillers.

In another embodiment, the composition additionally contains one or more platy fillers such as mica, talc or clay (e.g., kaolin). The adhesive films of the present invention may also contain other common adjuvants and additives, such as plasticizers, non-reactive diluents, flow auxiliaries, coupling agents (e.g., silanes), adhesion promoters, wetting agents, tackifiers, flame retardants, thixotropic and/or rheology control agents (e.g., fumed silica, mixed mineral thixotropes), ageing and/or corrosion inhibitors, stabilizers and/or colouring pigments. Thixotropic agents such as silica or aramid fibre are particularly preferred as providing control of the viscosity of the adhesive formulation as it is heated to and held at the curing temperature. Depending on the requirements made of the adhesive application with respect to its processing properties, its flexibility, the required rigidifying action and the adhesive bond to the substrates, the relative proportions of the individual components may vary within comparatively wide limits.

For some end uses it may also be desirable to include dyes, pigments, stabilizers, thixotropic agents, and the like. These and other additives may be included in the thermosetting adhesive compositions described herein as needed and at levels commonly practiced in the composite art. Upon curing, the thermosetting adhesive compositions, inclusive of any such additives, will form a substantially single, continuous rigid phase.

Polymer or Copolymer

Depending upon the use to which the adhesive film is to be put, it may include one or more additional polymers or copolymers which may or may not contain functional groups, which can include a variety of different polymers, such as thermoplastics, elastomers, plastomers and combinations thereof or the like. For example, and without limitation, polymers that might be appropriately incorporated into the structural adhesive include halogenated polymers,

polycarbonates, polyketones, urethanes, polyesters, silanes, sulfones, allyls, olefins, styrenes, acrylates, methacrylates, epoxies, silicones, phenolics, rubbers, polyphenylene oxides, terphthalates, acetates (e.g., EVA), acrylates, methacrylates (e.g., ethylene methyl acrylate polymer) or mixtures thereof. Other potential polymeric materials may be or may include, without limitation, polyolefin (e.g., polyethylene, polypropylene) polystyrene, polyacrylate, poly(ethylene oxide), poly(ethyleneimine), polyester, polyurethane, polysiloxane, polyether, polyphosphazine, polyamide, polyimide, polyisobutylene, polyacrylonitrile, polyvinyl chloride, poly(methyl methacrylate), polyvinyl acetate, poly(vinylidene chloride), polytetrafluoroethylene, polyisoprene, polyacrylamide, polyacrylic acid, polymethacrylate.

When used, these polymers can comprise a small portion or a more substantial portion of the material. When used, the one or more additional polymers preferably comprises about 0.1% to about 50%, more preferably about 1% to about 20% and even more preferably about 2% to about 10% by weight of the activatable material.

In certain embodiments, it may be desirable to include one or more thermoplastic polyethers and/or thermoplastic epoxy resins. When included, the one or more thermoplastic polyethers preferably comprise between about 1% and about 90% by weight of the formulation, more preferably between about 3% and about 60% by weight of the formulation and even more preferably between about 4% and about 25% by weight of the formulation. As with the other materials, however, more or less thermoplastic polyether may be employed depending upon the intended use of the film.

The thermoplastic polyethers typically include pendant hydroxyl moieties. The thermoplastic polyethers may also include aromatic ether/amine repeating units in their backbones. The thermoplastic polyethers preferably have a melt index between about 5 and about 100, more preferably between about 25 and about 75 and even more preferably between about 40 and about 60 grams per 10 minutes for samples weighing 2.16 Kg at a temperature of about 190° C. Of course, the thermoplastic polyethers may have higher or lower melt indices depending upon their intended application. Preferred thermoplastic polyethers include, without limitation, polyetheramines, poly(amino ethers), copolymers of monoethanolamine and diglycidyl ether, combinations thereof or the like.

Preferably, the thermoplastic polyethers are formed by reacting an amine with an average functionality of 2 or less (e.g., a difunctional amine) with a glycidyl ether (e.g., a diglycidyl ether). As used herein, the term difunctional amine refers to an amine with an average of two reactive groups (e.g., reactive hydrogens).

According to one embodiment, the thermoplastic polyether is formed by reacting a primary amine, a bis (secondary) diamine, a cyclic diamine, a combination thereof or the like (e.g., monoethanolamine) with a diglycidyl ether or by reacting an amine with an epoxy-functionalized poly(alkylene oxide) to form a poly(amino ether). According to another embodiment, the thermoplastic polyether is prepared by reacting a difunctional amine with a diglycidyl ether or diepoxy-functionalized poly(alkylene oxide) under conditions sufficient to cause the amine moieties to react with the epoxy moieties to form a polymer backbone having amine linkages, ether linkages and pendant hydroxyl moieties. Optionally, the polymer may be treated with a monofunctional nucleophile which may or may not be a primary or secondary amine.

Additionally, it is contemplated that amines (e.g., cyclic amines) with one reactive group (e.g., one reactive hydrogen) may be employed for forming the thermoplastic polyether. Advantageously, such amines may assist in controlling the molecular weight of the thermoplastic ether formed.

Examples of preferred thermoplastic polyethers and their methods of formation are disclosed in U.S. Pat. Nos. 5,275,853; 5,464,924 and 5,962,093. Advantageously, the thermoplastic polyethers can provide the structural adhesive with various desirable characteristics such as desirable physical and chemical properties for a wide variety of applications as is further described herein.

Although not required, the formulation may include one or more ethylene polymers or copolymers such as ethylene acryllate copolymers, ethylene vinyl acetate copolymers. Ethylene methacrylate and ethylene vinyl acetate are two preferred ethylene copolymers.

It may also be desirable to include a reactive polyethylene resin that is modified with one or more reactive groups such as glycidyl methacrylate or maleic anhydride. Examples of such polyethylene resins are sold under the tradename LOTADER® (e.g., LOTADER AX 8900) and are commercially available from Arkema Group.

Blowing Agent

The invention envisages both non-expandable and expandable thermosetting adhesive films. If the film is expandable one or more blowing agents may be added for producing inert gasses that form, as desired, an open and/or closed cellular structure within the film. The material expansion can help to improve sealing capability, acoustic damping and particularly adhesion bonding to a substrate.

The blowing agent may include one or more nitrogen containing groups such as amides, amines and the like. Examples of suitable blowing agents include azodicarbonamide, di nitrosopentamethylenetetramine, azodicarbonamide, dinitrosopentamethylenetetramine, 4,4,oxy-bis-(benzenesulphonylhydrazide), trihydrazinotriazine and N,N-dimethyl-N,Ni-dinitrosoterephthalamide. An accelerator for the blowing agents may also be provided. Various accelerators may be used to increase the rate at which the blowing agents form inert gasses. One preferred blowing agent accelerator is a metal salt, or is an oxide, e.g. a metal oxide, such as zinc oxide. Other preferred accelerators include modified and unmodified thiazoles or imidazoles (ureas).

Another class of blowing agents are physical blowing agents such as Expancel products marketed by Akzo-Nobel. These blowing agents consist of a polymeric particle with a volatile liquid in the centre. As the temperature is increased, the polymer shell softens and the gas inside the particle causes the polymer particle to expand. In this way, a foamed product is produced.

The amounts of blowing agents and blowing agent accelerators that are used can vary widely depending upon the type of cellular structure desired, the desired amount of expansion of the structural adhesive, the desired rate of expansion and the like. Exemplary ranges for the amounts of blowing agents and blowing agent accelerators in the activatable material range from about 0.001% by weight to about 5% by weight and are preferably in the structural adhesive in fractions of weight percentages.

Where the film is expandable the material may expand to at least 5% greater than its unfoamed size, at least 50% greater, at least 200% greater. It is also typically preferred that the volumetric expansion is such that the expanded volume is less than 400%, more typically less than 300%.

even more typically less than 200% and possibly less than 100% relative to the original unexpanded volume.

Filler

The formulations from which the films of this invention are made may also include one or more fillers, including but not limited to particulate materials (e.g., powder), beads, microspheres such as Zeospheres available from 3M, or the like. Preferably the filler includes a material that is generally non-reactive with the other components present in the structural adhesive however, the surfaces may be treated to improve adhesion or compatibility with the adhesive matrix. While the fillers may generally be present to take up space at a relatively low weight and cost, it is contemplated that the fillers may also impart properties such as strength and impact resistance to the cured films.

Examples of fillers that may be used include silica, diatomaceous earth, glass, clay (e.g., including nanoclay), talc, pigments, colorants, glass beads or bubbles, glass, carbon or ceramic fibres, polyamide or aramid fibres (e.g., Kevlar), antioxidants, and the like. Such fillers, particularly clays, can assist the formulation in levelling itself during flow of the material. The clays that may be used as fillers may include clays from the kaolinite, illite, chloritem, smectite or sepiolite groups, which may be calcined. Examples of suitable fillers include, without limitation, talc, vermiculite, pyrophyllite, sauconite, saponite, nontronite, montmorillonite or mixtures thereof. The clays may also include minor amounts of other ingredients such as carbonates, feldspars, micas and quartz. The fillers may also include ammonium chlorides such as dimethyl ammonium chloride and dimethyl benzyl ammonium chloride. Titanium dioxide might also be employed.

In one preferred embodiment, one or more mineral or stone type fillers such as calcium carbonate, sodium carbonate or the like may be used as fillers. In another preferred embodiment, silicate minerals such as mica may be used as fillers.

When employed, the fillers range from 10% or less to 70% or greater by weight of the formulation. According to some embodiments, the formulation may include from about 0% to about 3% by weight, and more preferably slightly less than 1% by weight clays or similar fillers. Powdered (e.g. about 0.01 to about 50, and more preferably about 1 to 25 micron mean particle diameter) mineral type filler can comprise between about 5% and 70% by weight, more preferably about 10% to about 50% by weight.

Other Components and Additives

Other additives, agents or performance modifiers may also be included as desired, including but not limited to an antioxidant, a UV resistant agent, a flame retardant, a heat stabilizer, a colorant, a processing aid, a lubricant, a reinforcement (e.g., chopped or continuous glass, ceramic, aramid, or carbon fibre, particulates or the like). Liquid polysulfides particularly epoxidized may be used to improve the environmental exposure of the adhesive such as exposure to humidity and salt water.

When determining appropriate components for the thermosetting adhesive film, it may be important to form the material such that it will only activate (e.g., flow, foam or otherwise change states) at appropriate times or temperatures. For instance the material should not be reactive at room temperature in an assembly environment. More typically, the adhesive film becomes activated at higher processing temperatures. As an example, temperatures such as those encountered in an automobile assembly plant may be appropriate, especially when the adhesive film is processed along with the other components at elevated temperatures or at higher applied energy levels, e.g., during painting preparation steps. Temperatures encountered in many coating operations (e.g., in a paint and/or e-coat curing oven), for instance, range up to about 250° C. or higher typically 130° C. to 190° C.

The following sets out the preferred amounts of the preferred components that may be employed in the films of this invention and the performance that they provide.

From 15 to 40 wt %	Phenoxy Resin	Provides flexibility and strength to the cured adhesive
From 15 to 30 wt %	Low molecular weight di-functional bisphenol A epoxy resin	Two functions: increases flexibility of the uncured film and its ease of impregnation with a fleece (when employed) increases Young modulus of cured adhesive
From 15 to 40 wt %	Nitrile rubber modified bisphenol F epoxy resin	Two functions: gives moderate Young modulus of cured adhesive increases toughness of cured adhesive
From 0.1 to -0.6 wt % (optional)	Mono-functional epoxy resin (reactive diluent)	Two functions: increases flexibility of the uncured film and its ease of impregnation with a fleece (when employed) may increase toughness of the cured adhesive
From 30 to 40 wt %	Butadiene rubber core shell impact modifier	Increases toughness of the cured adhesive
From 0.5 to 2 wt %	Methylene diphenyl bis (dimethyl urea)	Latent accelerator for the dicyandiamide cure of epoxy resins
From 13 to 6 wt %	Dicyandiamide	Curing agent for epoxy resins
Optionally from 0.2 to 1 wt %	Azobiscarboxamide	Foaming agent

The films of this invention are suitable for bonding together two or more substrates chosen from composites, metal, or honeycomb structures. The films are preferably non-tacky to the touch at room temperature and have good storage stability at room temperature. They are also suitable for bonding to oily surfaces such as the oily metal surfaces that may be encountered in automobile manufacture.

The adhesive films of this invention therefore have improved handleability and improved storage stability. Additionally the adhesive film is readily usable and cured at the temperatures experienced in the automobile anti-corrosion coating bake ovens in that they will retain adhesion to vertical and inclined surfaces at the cure temperature for the desired cure time which is no longer than the time to which the vehicle frame coated with the anticorrosion coating is exposed to the bake temperature, typically 20 to 40 minutes.

In one embodiment, the thermosetting adhesive film has a density of from 1.1 to 1.5. Such films can be supported by a carrier such as a fibrous carrier or fleece such as a woven or knit mat, or a random mat, derived from glass, polyester, polyamide, or other suitable polymeric materials or carbon or aramid fibres. The films of this invention can also be formed by coating or extrusion to produce unsupported films. The adhesive films of the present invention may be produced by extruding the formulations previously described at temperatures below that at which there is any significant activation of the epoxy curing agent such as at temperatures from 70 to 120° C. The formulation may be extruded as a film which for many uses becomes non-tacky to the touch when cooled to room temperature.

In certain instances however it would be useful if the films can be removably adhered to the substrate at temperatures below the activation temperature of the adhesive to retain the film in place prior to activation. This would be particularly useful where the film is to be used with vertical, inclined or contoured components such as the vertical A, B or C pillars of vehicle frames. This would enable a piece of film to be placed manually or robotically in the desired location and retained in that location and would also allow the piece of film to be moved if necessary. The invention therefore further provides tapes comprising a film of this invention provided with a tacky surface. Unlike some thermosetting adhesive tapes the tapes of this invention are storage stable, can be reeled and unreeled, cut easily and do not have an undesirable odour.

In a further embodiment the present invention therefore provides a thermosetting adhesive film of the invention provided with a tacky coating. Thermosetting adhesive films with a tacky surface are known for example, epoxy polyacrylate adhesive tapes are known in which the polyacrylate functions to provide tackiness to the film. However these films have an undesirable odour, additionally for certain applications they do not result in an adequately strong bond. The tack coating is preferably provided in an amount of 2 to 10 grams per square metre of the adhesive film.

We have now found that if a thermosetting adhesive film of the present invention is coated with a liquid, tacky resin that can be cured by the curative employed with the resin used in the film, the adhesive film can have sufficient tack to adhere to vertical and contoured surfaces prior to curing. Because the curing agent or curing agents employed with the resin have been selected so that there is no activation at ambient temperature whereby the film is storage stable the coating material will also not be activated and will remain tacky during any storage, transportation and application of the coated adhesive film. Furthermore the coated films can be stored for long periods of time, for example up to several

months, at ambient temperature without significant loss of any of the mechanical properties of the bond when the adhesive is finally cured.

The present invention therefore provides an adhesive film or tape comprising a layer of a thermosetting film according to this invention containing one or more curing agents coated with a layer of a second tacky resin that is capable of being cured by at least one of the curing agents within the first curable resin.

The second tacky resin is preferably free of curing agent.

The second tacky resin may be applied to the adhesive film at any stage in the film manufacturing process. It may be applied at the point of manufacture of the adhesive film in which case it is desirable to provide a release layer on top of the coating layer to enable reeling and unreeling, transportation and storage of the film. Alternatively the coating may be applied at the point of use of the adhesive film.

As mentioned the second tacky thermosetting resin of the coating may be a polyester resin, a polyurethane or an epoxy resin of the types previously discussed. Epoxy resin being preferred. The second thermosetting resin should be such that it imparts a tacky surface to the adhesive film at ambient temperature and is preferably provides a liquid surface film at ambient temperature. It is preferably a liquid resin having a viscosity at 25° C. of 1000 to 20,000 MPas so that it can be applied to and retained by the surface of the film based on the first thermosetting resin formulation. Alternatively although not preferred it can be applied as a solution and solvent removed to provide the desired tacky surface. Any suitable coating technique may be used. It is preferred that the coating be made by using the tackifying material at from 1 to 10 grams per square metre of the film.

The adhesive films of this invention are suitable for bonding together two or more substrates made from materials chosen from composites, metal, or honeycomb structures. The films have good storage stability at room temperature. They are also suitable for bonding to oily surfaces such as the oily metal surfaces that may be encountered in automobile manufacture. We have also found that they are useful for bonding together heavy structures which may be porous, and may have uneven or roughly profiled surfaces. They are also useful in bonding together substrates derived from materials with different coefficients of thermal expansion.

The adhesive films of this invention may be provided with a fibrous porous support such as a fibrous layer or fleece. Fibrous materials embedded in a matrix of the thermosetting resin such as epoxy resins are well known and are commercially available as what are sometimes known as prepregs. The prepregs are used in the manufacture of articles usually by the laying up of several prepregs in a stack and curing the stack in a mould to produce a finished article such as an automobile or aircraft component, wind turbine blade or sporting goods. In this technology the resin is cured to bond several prepregs together. The present invention is however concerned with the use of a thermosetting adhesive film to bond together substrates other than layers of the fibrous support and is particularly concerned with the use of an adhesive comprising a thermosetting resin supported on a fibrous material for the bonding together of substrates derived from different materials in particular the bonding together of metal such as steel and/or aluminium to fibre reinforced composites such as glass fibre, carbon fibre or aramid filled epoxy or polyester resins. Accordingly the thermosetting resin performs a different function from that performed in a prepreg.

The structural adhesives films of this invention may be used to improve the stiffness of automobiles so reducing the likelihood of vehicle roll over, improving vehicle ride characteristics and increasing vehicle durability and fatigue life.

In the embodiment in which the adhesive film is provided with a support such as a fibrous layer or fleece made, for example, from glass fibre, carbon fibre or aramid the fibrous layer or fleece not only supports the adhesive but can improve the properties of the cured adhesive. The fibres within the fibrous layer or fleece may be unidirectional or multidirectional depending upon the direction in which the strength is required. The adhesive formulation can be adapted to have a viscosity at its deposition temperature such as the extrusion temperature that it can readily impregnate such a fibrous fleece upon contact therewith extrusion, perhaps with the provision of a roller to press the viscous adhesive formulation into the interstices of the fleece.

The film of the invention may be used in a structure comprising a fibrous support such as a fleece and an uncured adhesive film of the invention. The uncured film may be on one or both sides of the fibrous fleece and may also impregnate the interstices of the fibrous fleece. Such a structure may be produced by a process in which thermosetting adhesive formulation which may be epoxy based is extruded at a temperature in the range 70 to 120° C. as a film onto a moving fibrous fleece. It is preferred that the formulation contain a phenoxy resin, a core/shell polymer, an epoxy modified elastomer and a curing agent as previously described.

The adhesive films of the present invention may be used in various articles of manufacture for adding structural integrity to portions or members of articles. Examples of such articles of manufacture include, without limitation, household or industrial appliances, furniture, storage containers, buildings, structures or the like. In preferred embodiments, the adhesive film is used for bonding portions of an automotive vehicle or aircraft such as body or frame members (e.g., a vehicle frame rail) of the automotive vehicle.

The present invention therefore provides a film that can be cured to produce a structural adhesive. The film is solid and can be dry to the touch and is storage stable at room temperature. The film can be activated to develop adhesive properties at an elevated temperature.

The cured adhesive film has a good elongation at breaking, good Lap Shear, good T Peel and good performance in the Wedge Impact Test over the range of temperatures and environmental conditions to which the film may be subjected flexibility, and protection against the propagation of flaws. Other desirable properties include good adhesion durability under various types of exposure conditions such as high humidity, salt water and high and low temperatures such as from sub-zero conditions experienced by aircraft to the high temperatures experienced by land vehicles in extreme climates with maintenance of the physical properties over time. In certain applications a high elastic modulus, a high Tg, high strain to failure and other physical properties may be desired.

The preferred thickness of the thermosetting adhesive films of the present invention will be selected according to the use to which the film is to be put. However films of thickness from 0.3 mm to 2 mm are preferred. The films of this invention are useful in many applications where strong bonds are required. In particular they are useful in bonding together substrates having different coefficients of thermal expansion. One particular use is in the bonding of metals such as steel and aluminium which have high coefficients of expansion to fibre reinforced resins such as glass, carbon or

aramid fibre filled epoxy or poly urethane based resins which have low coefficients of thermal expansion. Additionally the films may be used to obtain a satisfactory bond when one or more of the surfaces is an oily surface.

The invention therefore provides a cured adhesive film derived from a thermosetting adhesive film of the present invention which may incorporate a fibrous layer or fleece as herein before described. In a further embodiment the invention provides a laminar structure comprising a metal substrate and a fibre reinforced resin substrate bonded together by an adhesive film of the present invention.

The cured composition provided by the present invention is capable of exhibiting high peel and shear strengths in the temperature range of -55° C. to +120° C. In the cured state, these adhesives display performance necessary for many end-use applications especially in the manufacture of aircraft structures and high end automobiles. The toughness of the resin matrix may be adjusted, for example, by varying functionality of epoxy resins (di- or tri or tetrafunctional) leading to change in the crosslink density.

The invention is illustrated by reference to the following examples.

EXAMPLE 1

An adhesive film was prepared by blending the following materials.

Component	%
CTBN modified epoxy resin (1600 g/Eq)	6.00%
Epoxy resin (900 g/Eq)	5.00%
Micronized grade of dicyandiamide (<50 micrometers)	5.00%
Aromatic substituted urea (latent accelerator for the dicyandiamide cure of epoxy resins)	0.60%
Calcium oxide (<70 micrometers)	5.00%
Calcium carbonate (<70 micrometers)	18.40%
Epoxy resin (200 g/Eq)	16.00%
Methacrylate-butadiene-styrene (MBS) Coreshell impact modifier: cross-linked poly (butadiene/styrene) core with a grafted polymethyl methacrylate shell	16.00%
Epoxy Phenol Novolac Resin	8.00%
Phenoxy Resin	15.00%
Silica (<50 nanometers: 40%) reinforced bisphenol F based epoxy resin	5.00%

The formulation was extruded from a twin-screw then calendared to make a film as illustrated in FIG. 1 hereto.

The temperatures in the different extruder zones were:

Zone 1	30
Zone 2	60
Zone 3	85
Zone 4	110
Zone 5	100
Zone 6	100
Zone 7	90
Zone 8	80
Zone 9	80
Zone 10	80
Zone 11	80

The temperature of the calendar cylinder is between 80 and 90° C.

The calendared film had a thickness between 0.3 and 2 mm.

The adhesive film was used to bond two steel plates. The curing conditions was heating at 165° C. for 20 minutes.

Lap shear strength: 30 MPa/Coheasive failure

EXAMPLE 2 TAPE MANUFACTURING

A tacky film (a tape) was made by applying a liquid epoxy resin on at least one of the two surfaces of the Adhesive Film of Example 1.

The liquid resin used for the tacky coat can be a Bisphenol-A based epoxy resin or a Bisphenol-F based epoxy resin. The liquid resin can also be: the same than then liquid resin used in the formula of the Adhesive film.

Different from the liquid resin used in the formula of the Adhesive film.

Example 2A: the liquid resin is a Bisphenol-A based epoxy resin and is the same as the liquid resin used in the formula of the Adhesive film.

Example 2B: the liquid resin is a Bisphenol-A based epoxy resin and is different from the liquid resin used in the formula of the Adhesive film.

The mechanical performances of bonded assemblies using the Adhesive Films of Examples or the Adhesive Tapes of Examples 2A and 2B are almost the same. The Adhesive Tapes have a slightly higher lap shear strength and a slightly lower peel strength.

The manufacture of films according to the present invention is illustrated by reference to the accompanying drawing II in which FIG. 1 shows the manufacturing line comprising an extruder (1) to which the first thermosetting resin system (2) is fed. The first thermosetting resin system is extended at about 80° C. and passes into a calendaring system (3) where it is calendared by passage through pressure rollers (4) to the required thickness.

Optionally, the calendared extrudate may then pass to a laminate system where it is laminated to a fibrous layer (5) provided from reels (6). As a further option the laminate may then be passed to a coating system where it is coated with a second tacky thermosetting resin (7) supplied from tanks (8) from which it passes to a cutting system (9) where a release liner (10) can be provided on the tacky surface and the film or tape can be cut by a knife (11) into sections (12) of the desired length.

When the film is to be used without a supporting fibrous layer and without a tacky layer it may pass directly to the cutting station. Similarly if a laminate with a fibrous layer is required without a tacky layer the laminate may pass directly to the cutting station after lamination.

The invention claimed is:

1. An article comprising: a curable thermosetting epoxy resin based adhesive film which is flexible prior to cure and storage stable at room temperature, the adhesive film being derived from a mixture of:

- (a) an elastomer/epoxy resin adduct;
- (b) a core shell material; and
- (c) a curing agent;

wherein the adhesive film is configured to form an adhesive bond with a metal surface having a layer of about 3 g/m² of a corrosion preventive oil; and

wherein a tacky coating free of a curing agent is applied to the adhesive film, and the tacky coating is configured to be cured by the curing agent of the adhesive film.

2. The article according to claim 1, wherein the adhesive film is cured in no more than 45 minutes at a temperature no higher than 190° C.

3. The article according to claim 1, wherein a shear strength of the adhesive film when bonded with the metal

surface having a layer of about 3 g/m² of the corrosion preventive oil is 90% or more of a shear strength of the adhesive film when bonded to a similar surface free of oil.

4. The article according to claim 2, wherein the adhesive film is cured at a temperature in the range of 130° C. to 190° C.

5. The article according to claim 1, wherein the adhesive film is foamable and the adhesive film expands to a size at least 50% greater than a size of the adhesive film in an unfoamed state.

6. The article according to claim 1, wherein the adhesive film has an uncured thickness between 0.2 and 3.0 mm.

7. The article according to claim 1, wherein the adhesive film contains 5 to 40 wt % of the elastomer/epoxy resin adduct, and 5 to 25 wt % of the core shell material.

8. The article according to claim 7, wherein the adhesive film contains 0.5 to 40 wt % of one or more fillers.

9. The article according to claim 7, wherein the adhesive film contains 0.001 to 7 wt % of the curing agent, and the curing agent includes a curing agent accelerator.

10. The article according to claim 1, wherein the article is supported by a carrier.

11. The article according to claim 10, wherein the carrier is a fibrous carrier or fleece selected from: a woven mat, a knit mat, or a random mat; and wherein the fibrous carrier or fleece is derived from: glass, polyester, polyimide, carbon, or aramid fibres.

12. The article according to claim 11, wherein the adhesive film is located on opposing sides of the fibrous carrier prior to curing, and the tacky coating of the adhesive film is a bisphenol-A or bisphenol-F based epoxy resin.

13. The article according to claim 11, wherein the fibers within the fibrous layer or fleece are unidirectional.

14. The article according to claim 10, wherein the adhesive film at least partially impregnates the carrier.

15. The article according to claim 1, wherein the adhesive film is thixotropic during a curing of the adhesive film.

16. The article according to claim 1, wherein the elastomer/epoxy resin adduct is 40% to 60% elastomer.

17. The article according to claim 1, wherein the article includes a release liner disposed on the adhesive film so that the article is adapted for reeling and unreeling at room temperature.

18. The article according to claim 1, wherein the adhesive film contains at least one mono-functional epoxy resin.

19. A process for the manufacture of the article of claim 1, comprising:

- (a) extruding the adhesive film at a temperature in the range of 70° C. to 120° C.;
- (b) calendaring the adhesive film to a thickness of 0.3 to 2 mm;
- (c) applying the tacky coating to the adhesive film to form the article; and
- (d) cutting the article into sections of a desired length.

20. The process according to claim 19, wherein the extruding is completed by a twin-screw having a plurality of extruder zones and the plurality of extruder zones vary in temperature; and wherein the calendaring is completed at a temperature in the range of 80° C. to 90° C.