



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>6</sup> : <b>B41M 5/00</b></p>	<p><b>A1</b></p>	<p>(11) International Publication Number: <b>WO 98/43822</b> (43) International Publication Date: 8 October 1998 (08.10.98)</p>
<p>(21) International Application Number: PCT/US98/05017 (22) International Filing Date: 13 March 1998 (13.03.98) (30) Priority Data: 60/043,040 31 March 1997 (31.03.97) US 60/043,203 8 April 1997 (08.04.97) US 09/027,515 20 February 1998 (20.02.98) US (71) Applicant: KIMBERLY-CLARK WORLDWIDE, INC. [US/US]; 401 North Lake Street, Neenah, WI 54956 (US). (72) Inventor: KRONZER, Francis, Joseph; 3204 Lexington Farm Drive, Alpharetta, GA 30201 (US). (74) Agents: MAYCOCK, William, E. et al.; Kimberly-Clark Worldwide, Inc., 401 North Lake Street, Neenah, WI 54956 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, -CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p><b>Published</b> <i>With international search report.</i></p>
<p>(54) Title: THERMAL DYE DIFFUSION COATING AND SUBSTRATE</p>		
<p>(57) Abstract</p> <p>A coating suitable for receiving an image by dye diffusion printing which includes a thermoplastic polymer having a glass transition temperature of at least about 30 °C and a powdered plasticizer having a melting point of at least about 80 °C. The thermoplastic polymer may have a glass transition temperature of at least about 40 °C. For example, the thermoplastic polymer may be a vinyl chloride-acrylate copolymer. The plasticizer may be an aromatic carboxylic acid ester, such as cyclohexane dimethanol dibenzoate. The average particle size of the powdered plasticizer may be no greater than about 20 micrometers. The weight ratio of the thermoplastic polymer to the plasticizer typically is in a range of from about 80:20 to about 40:60. Finally, the coating includes a release agent. The release agent may be present in a range of from about 0.5 to about 10 percent by weight, based on the weight of dry coating. The present invention also provides a coated substrate suitable for receiving an image by dye diffusion printing and a coating composition which is an aqueous dispersion of a thermoplastic polymer having a glass transition temperature of at least about 30 °C, a powdered plasticizer having a melting point of at least about 80 °C, and a release agent.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

<b>AL</b>	Albania	<b>ES</b>	Spain	<b>LS</b>	Lesotho	<b>SI</b>	Slovenia
<b>AM</b>	Armenia	<b>FI</b>	Finland	<b>LT</b>	Lithuania	<b>SK</b>	Slovakia
<b>AT</b>	Austria	<b>FR</b>	France	<b>LU</b>	Luxembourg	<b>SN</b>	Senegal
<b>AU</b>	Australia	<b>GA</b>	Gabon	<b>LV</b>	Latvia	<b>SZ</b>	Swaziland
<b>AZ</b>	Azerbaijan	<b>GB</b>	United Kingdom	<b>MC</b>	Monaco	<b>TD</b>	Chad
<b>BA</b>	Bosnia and Herzegovina	<b>GE</b>	Georgia	<b>MD</b>	Republic of Moldova	<b>TG</b>	Togo
<b>BB</b>	Barbados	<b>GH</b>	Ghana	<b>MG</b>	Madagascar	<b>TJ</b>	Tajikistan
<b>BE</b>	Belgium	<b>GN</b>	Guinea	<b>MK</b>	The former Yugoslav Republic of Macedonia	<b>TM</b>	Turkmenistan
<b>BF</b>	Burkina Faso	<b>GR</b>	Greece	<b>ML</b>	Mali	<b>TR</b>	Turkey
<b>BG</b>	Bulgaria	<b>HU</b>	Hungary	<b>MN</b>	Mongolia	<b>TT</b>	Trinidad and Tobago
<b>BJ</b>	Benin	<b>IE</b>	Ireland	<b>MR</b>	Mauritania	<b>UA</b>	Ukraine
<b>BR</b>	Brazil	<b>IL</b>	Israel	<b>MW</b>	Malawi	<b>UG</b>	Uganda
<b>BY</b>	Belarus	<b>IS</b>	Iceland	<b>MX</b>	Mexico	<b>US</b>	United States of America
<b>CA</b>	Canada	<b>IT</b>	Italy	<b>NE</b>	Niger	<b>UZ</b>	Uzbekistan
<b>CF</b>	Central African Republic	<b>JP</b>	Japan	<b>NL</b>	Netherlands	<b>VN</b>	Viet Nam
<b>CG</b>	Congo	<b>KE</b>	Kenya	<b>NO</b>	Norway	<b>YU</b>	Yugoslavia
<b>CH</b>	Switzerland	<b>KG</b>	Kyrgyzstan	<b>NZ</b>	New Zealand	<b>ZW</b>	Zimbabwe
<b>CI</b>	Côte d'Ivoire	<b>KP</b>	Democratic People's Republic of Korea	<b>PL</b>	Poland		
<b>CM</b>	Cameroon	<b>KR</b>	Republic of Korea	<b>PT</b>	Portugal		
<b>CN</b>	China	<b>KZ</b>	Kazakstan	<b>RO</b>	Romania		
<b>CU</b>	Cuba	<b>LC</b>	Saint Lucia	<b>RU</b>	Russian Federation		
<b>CZ</b>	Czech Republic	<b>LI</b>	Liechtenstein	<b>SD</b>	Sudan		
<b>DE</b>	Germany	<b>LK</b>	Sri Lanka	<b>SE</b>	Sweden		
<b>DK</b>	Denmark	<b>LR</b>	Liberia	<b>SG</b>	Singapore		
<b>EE</b>	Estonia						

## THERMAL DYE DIFFUSION COATING AND SUBSTRATE

### Background of the Invention

The present invention relates to thermal dye diffusion printing.

Thermal dye diffusion printing is a non-impact electronic printing process which is capable of giving near photographic quality prints. An image is formed by using a thermal head to transfer dye from a color ribbon into a surface of a receiver. The head consists of a line of individually addressable heated elements which are fed appropriate electrical pulses to generate the quantity of heat required to provide the amount of dye transfer needed to reproduce the corresponding pixel in the image. The surface temperature of the thermal head typically is 350°C and the duration of the heating pulse typically is up to 10 milliseconds. The depth of shade is governed by the length of the heating pulse and a full color image is built up in the normal way by transfer of the primary colors on top of each other.

In general, both the ribbon and the receiver have very smooth surfaces. The active layer of the ribbon consists of a solid solution of dye in a binder. The receiver typically consists of a polymer coating on a paper or other supporting material; the coating is designed to be receptive to the dye and to release smoothly from the ribbon, or dye layer, after printing.

The receiver is supported on a platen roller and the thermal head is pressed against the surface of the ribbon. The two media are held together under a pressure of between 10 and 100 atmospheres. As the surfaces are very smooth, there is no air gap between the media in the region where the thermal head is applying maximum pressure. Dye is transferred by phase transfer and diffusion; the dye which is dissolved in the dye layer partitions into the receiver coating by a molecular diffusion process. Once dye is in the receiver coating, it is free to continue diffusing further into the coating as long as the thermal head temperature remains sufficiently high. At all stages, the dye molecules are surrounded by a polymer matrix; transfer occurs from one polymer phase to another without sublimation taking place.

Because the dyes are always constrained by polymer molecules, the dye diffusion process is very well controlled. The build up of color is well defined and sideways diffusion cannot occur, as is possible in the air gap of a sublimation process.

While films have the requisite degree of smoothness, the accumulation of a static charge on the film may occur during the printing process which leads to the attraction of dust particles on the surfaces of the film. The presence of dust on a receiver coating prevents intimate contact over the entire area of the thermal printing head which results in imperfections in the printed image. While papers generally do not suffer from static charge build up, image quality may be reduced. In addition, transfer of the printed image to another substrate may be adversely affected by the use of a paper carrier or support for the receiver coating. Accordingly, there is a need for improved thermal dye diffusion substrates, particularly for substrates intended to be used as a heat transfer material.

### Summary of the Invention

The present invention addresses some of the difficulties and problems discussed above by providing a coating suitable for receiving an image by dye diffusion printing. The coating includes a thermoplastic polymer having a glass transition temperature of at least about 30°C. For example, the thermoplastic polymer may have a glass transition temperature of at least about 40°C. As another example, the thermoplastic polymer may be a vinyl chloride-acrylate copolymer.

The coating also includes a powdered plasticizer having a melting point of at least about 80°C. For example, the plasticizer may be an aromatic carboxylic acid ester. As another example, the plasticizer may be cyclohexane dimethanol dibenzoate. As a further example, the average particle size of the powdered plasticizer may be no greater than about 20 micrometers. The weight ratio of the thermoplastic polymer to the plasticizer typically is in a range of from about 80:20 to about 40:60. For example, the weight ratio of the thermoplastic polymer to the plasticizer may be from about 70:30 to about 50:50.

Finally, the coating includes a release agent. The release agent may be present in a range of from about 0.5 to about 10 percent by weight, based on the dry weight of the coating

The present invention also provides a coated substrate suitable for receiving an image by dye diffusion printing. The coated substrate includes a flexible first layer which has first and second surfaces and is selected from the group consisting of films, fibrous sheet-like materials, and combinations thereof. For example, the first

layer may be a film. As another example, the first layer may be a fibrous sheet-like material.

The present invention further provides a coated substrate suitable for receiving an image by dye diffusion printing which includes a flexible first layer as just described; a second layer overlaying the first surface of the first layer, which second layer comprises a first thermoplastic polymer having a glass transition temperature of at least about 30°C and a first powdered plasticizer having a melting point of at least about 80°C; and a third layer overlaying the second layer, which third layer includes a second thermoplastic polymer having a glass transition temperature of at least about 30°C, a second powdered plasticizer having a melting point of at least about 80°C, and a release agent.

The first layer has a basis weight of from about 50 to about 200 grams per square meter. For example, the first layer may be a film. As a further example, the first layer may be a fibrous sheet-like material. The second layer has a basis weight of from about 0.5 to about 10 grams per square meter, and the third layer has a basis weight of from about 0.5 to about 10 grams per square meter.

The weight ratio of first thermoplastic polymer to first plasticizer is in a range of from about 80:20 to about 40:60 and the weight ratio of second thermoplastic polymer to second plasticizer is in a range of from about 80:20 to about 40:60. The release agent is present in the third layer in a range of from about 0.5 to about 10 percent by weight, based on the weight of the third layer coating.

By way of illustration only, the first thermoplastic polymer may have a glass transition temperature of at least about 40°C. For example, the first thermoplastic polymer may be a vinyl chloride-acrylate copolymer. Similarly, the second thermoplastic polymer may have a glass transition temperature of at least about 40°C and may be a vinyl chloride-acrylate copolymer. The first powdered plasticizer may be an aromatic carboxylic acid ester, such as cyclohexane dimethanol dibenzoate. The average particle size of the first powdered plasticizer may be, for example, no greater than about 20 micrometers. In like manner, the second powdered plasticizer may be an aromatic carboxylic acid ester, such as cyclohexane dimethanol dibenzoate and may have an average particle size no greater than about 20 micrometers.

Finally, the present invention provides a coating composition which is an aqueous dispersion of a thermoplastic polymer having a glass transition temperature of at least about 30°C, a powdered plasticizer having a melting point of at least about 80°C, and a release agent. The weight ratio of thermoplastic polymer to powdered

plasticizer is in a range of from about 80:20 to about 40:60, on a dry weight basis, and the release agent is present in a range of from about 0.5 to about 10 percent by weight, on a dry weight basis, based on the weight of the solids content. The aqueous dispersion contains from about 10 to about 50 percent by weight solids.

By way of example, the thermoplastic polymer may have a glass transition temperature of at least about 40°C. As another example, the thermoplastic polymer may be a vinyl chloride-acrylate copolymer. As a further example, the powdered plasticizer may be an aromatic carboxylic acid ester, such as cyclohexane dimethanol dibenzoate. As a further example, the average particle size of the powdered plasticizer may be no greater than about 20 micrometers.

### Detailed Description of the Invention

As used herein, the term "fibrous sheet-like material" is meant to include any fibrous material which typically is prepared by air laying or wet laying relatively short fibers to form a nonwoven web or sheet. Thus, the term includes nonwoven webs prepared from a papermaking furnish. Such furnish may include, by way of illustration, only cellulose fibers, a mixture of cellulosic fibers and noncellulosic fibers, or only noncellulosic fibers. When the furnish contains only cellulosic fibers or a mixture of cellulosic fibers and noncellulosic fibers, the resulting web is referred to herein as a "cellulosic nonwoven web." Noncellulosic fibers include, by way of illustration only, glass wool and fibers prepared from thermosetting and thermoplastic polymers, as is well known to those having ordinary skill in the art. Of course, the cellulosic nonwoven web also may contain additives and other materials, such as fillers, e.g., clay and titanium dioxide, as is well known in the papermaking art. Desirably, the fibrous sheet-like material will be composed of synthetic thermoplastic fibers, examples of which materials are the Kimdura<sup>®</sup> synthetic papers manufactured by Oji-Yuka Paper Company of Japan. Such materials have desirably smooth surfaces and handle more like paper than films. In addition, such synthetic papers are readily available and more pliable and exhibit a reduced tendency for static build-up which attracts dust. Dust on the coating causes print voids since dye diffusion ribbon printers require intimate contact between the substrate and the ribbon for proper dye transfer.

In general, the term "cellulosic fibers" is meant to include cellulosic fibers from any source. Sources of cellulosic fibers include, by way of illustration only, woods, such as

softwoods and hardwoods; straws and grasses, such as rice, esparto, wheat, rye, and sabai; bamboos; jute; flax; kenaf; cannabis; linen; ramie; abaca; sisal; and cotton and cotton linters. Softwoods and hardwoods are the more commonly used sources of cellulosic fibers. In addition, the cellulosic fibers may be obtained by any of the commonly used pulping processes, such as mechanical, chemimechanical, semichemical, and chemical processes. For example, softwood and hardwood Kraft pulps are desirable for toughness and tear strength, but other pulps, such as recycled fibers, sulfite pulp, and the like may be used, depending upon the application.

The phrase "weight ratio of the thermoplastic polymer to the plasticizer" refers to the parts by weight of thermoplastic polymer and plasticizer per 100 parts by weight of both components, separated by a colon, such as 80:20 or 40:60. The weight ratio also may be expressed as a fraction, e.g., 80/20 or 40/60. Thus, the ratio 80:20 (or 80/20) is equivalent to 4 parts by weight of thermoplastic polymer for each part by weight of plasticizer.

The term "thermoplastic polymer having a glass transition temperature of at least about 30°C" is intended to include any thermoplastic polymer which meets the stated glass transition temperature requirement. Examples of such thermoplastic polymers include, by way of illustration only, poly(acrylonitrile); poly(methacrylonitrile); poly(vinyl chloride); poly(acrylic acid); poly(methacrylic acid); a poly(acrylate), such as poly(4-biphenyl acrylate), poly(2-*t*-butylphenyl acrylate), poly[3-chloro-2,2-bis(chloromethyl)propyl acrylate], poly(4-chlorophenyl acrylate), poly(pentachlorophenyl acrylate), poly(2-ethoxycarbonylphenyl acrylate), poly(2-heptyl acrylate), poly(hexadecyl acrylate), poly(3-methoxycarbonylphenyl acrylate), poly(4-methoxyphenyl acrylate), poly(3,5-dimethyladamantyl acrylate), poly(3-dimethylaminophenyl acrylate), poly(2-naphthyl acrylate), poly(phenyl acrylate), poly(*o*-tolyl acrylate), poly(methyl methacrylate), poly(benzyl methacrylate), poly(2-bromoethyl methacrylate), poly(2-*t*-butylaminoethyl methacrylate), poly(*sec*-butyl methacrylate), atactic and syndiotactic poly(*t*-butyl methacrylate), poly(2-chloroethyl methacrylate), poly(cyclohexyl methacrylate), poly(*t*-butylcyclohexyl methacrylate), atactic and syndiotactic poly(ethyl methacrylate), poly(2-hydroxyethyl methacrylate), atactic and syndiotactic poly(isopropyl methacrylate), poly(ethyl chloroacrylate), and poly(ethyl fluoromethacrylate); a poly(acrylamide), such as poly(acrylamide), poly(*N*-butylacrylamide), poly(*N-sec*-butylacrylamide), poly(*N-t*-butylacrylamide), poly(*N,N*-dibutylacrylamide), poly(isodecylacrylamide), poly(isohexylacrylamide), poly(isononylacrylamide), poly(isooctylacrylamide), poly(*N*-isopropylacrylamide), poly(*N,N*-diiso-

propylacrylamide), poly(N,N-dimethylacrylamide), poly[N-(1-methylbutyl)acrylamide], poly(N-methyl-N-phenylacrylamide), poly(morpholylacrylamide), poly(N-octylacrylamide), and poly(4-ethoxycarbonylphenylmethacrylamide); a poly(styrene), such as poly(styrene), poly(4-acetylstyrene), poly(5-bromo-2-methoxystyrene), poly(4-butoxycarbonylstyrene), poly(3-chlorostyrene), poly(2-ethylstyrene), poly(4-methoxystyrene), and poly(3-methylstyrene); a poly(ester), such as poly(ethylene terephthalate), and poly(trimethylene terephthalate); a poly(substituted ethylene), such as poly(*t*-butylethylene), atactic and isotactic poly(cyclohexylethylene), poly(2-cyclohexylethylene), poly[(cyclohexylmethyl)ethylene], poly(cyclopentylethylene), poly[(cyclopentylmethyl)ethylene], poly-(hexyldecylethylene), poly(isobutylethylene), atactic and isotactic poly(isopropyl-ethylene), poly(3,3-dimethylbutylethylene), poly(1,1,2-trimethyltrimethylene), poly(4,4-dimethylpentylethylene), poly(neopentylethylene), poly(*t*-butoxyethylene), poly(cyclohexyloxyethylene), poly(2-methoxypropylene), poly(benzoylethylene), poly(1,2-difluoroethylene), poly(3-chlorobenzoyloxyethylene); a poly(phenylene), such as poly(2-methyl-1,4-phenyleneethylene), and poly(2-chloro-1,4-phenyleneethylene); a poly(oxide), such as poly(oxy-*t*-butylethylene), poly(oxy-1,4-phenylene), and poly(oxyphenylethylene); a poly(amide), such as poly(iminopentamethyleneiminoadipoyl) (or nylon 5,6), poly(imino-1-oxo-hexamethylene) (or nylon 6), poly(iminoadipoyliminohexamethylene) or (nylon 6,6), and poly(iminohexamethyleneiminododecanedioyl) (or nylon 6,12).

As used herein, the term "acrylate" is meant to include any ester of acrylic acid or a substituted acrylic acid, such as methacrylic acid. For example, the acrylate may be one which is particularly well suited for use in the preparation of a copolymer in which one component is vinyl chloride. The term also is meant to include a single acrylate or two or more acrylates. In an analogous manner, the term "poly(acrylic acid)" is meant to include polymers of acrylic acid or a substituted acrylic acid, such as methacrylic acid.

In accordance with the present invention, there is provided a coating suitable for receiving an image by dye diffusion printing. The coating includes a thermoplastic polymer having a glass transition temperature of at least about 30°C. For example, the thermoplastic polymer may have a glass transition temperature of at least about 40°C. As another example, the thermoplastic polymer may be a vinyl chloride-acrylate copolymer.

The coating also includes a powdered plasticizer having a melting point of at least about 80°C. In general, the plasticizer may be any plasticizer which is



appropriate for the thermoplastic polymer. By way of example, when the thermoplastic polymer is a vinyl chloride-acrylate copolymer, the plasticizer may be an aromatic carboxylic acid ester. As a further example, the plasticizer may be a benzoate. As another example, the plasticizer may be cyclohexane dimethanol dibenzoate.

Desirably, the average particle size of the powdered plasticizer will be no greater than about 20 micrometers. This allows the powdered plasticizer to be readily dispersed in an aqueous medium, such as an aqueous dispersion of the thermoplastic polymer. For example, the average particle size of the powdered plasticizer may be no greater than about 15 micrometers.

The weight ratio of the thermoplastic polymer to the plasticizer typically is in a range of from about 80:20 to about 60:40. For example, the weight ratio of the thermoplastic polymer to the plasticizer may be from about 70:30 to about 50:50.

Finally, the coating includes a release agent. The release agent may be present in a range of from about 0.5 to about 10 percent by weight, based on the total weight of the coating.

The present invention also provides a coated substrate suitable for receiving an image by dye diffusion printing. The coated substrate includes a flexible first layer which has first and second surfaces and is selected from the group consisting of films, fibrous sheet-like materials, and combinations thereof. For example, the first layer may be a film. As another example, the first layer may be a fibrous sheet-like material.

The present invention further provides a coated substrate suitable for receiving an image by dye diffusion printing which includes a flexible first layer as just described; a second layer overlaying the first surface of the first layer, which second layer comprises a first thermoplastic polymer having a glass transition temperature of at least about 30°C and a first powdered plasticizer having a melting point of at least about 80°C; and a third layer overlaying the second layer, which third layer includes a second thermoplastic polymer having a glass transition temperature of at least about 30°C, a second powdered plasticizer having a melting point of at least about 80°C, and a release agent.

The first layer has a basis weight of from about 50 to about 200 grams per square meter. For example, the first layer may be a film. As a further example, the first layer may be a fibrous sheet-like material. The second layer has a basis weight of

from about 0.5 to about 10 grams per square meter, and the third layer has a basis weight of from about 0.5 to about 10 grams per square meter.

The weight ratio of first thermoplastic polymer to first plasticizer is in a range of from about 80:20 to about 40:60 and the weight ratio of second thermoplastic polymer to second plasticizer is in a range of from about 80:20 to about 40:60. The release agent is present in the third layer in a range of from about 0.5 to about 10 percent by weight, based on the weight of the third layer.

By way of illustration only, the first thermoplastic polymer may have a glass transition temperature of at least about 40°C. For example, the first thermoplastic polymer may be a vinyl chloride-acrylate copolymer. Similarly, the second thermoplastic polymer may have a glass transition temperature of at least about 40°C and may be a vinyl chloride-acrylate copolymer. The first powdered plasticizer may be an aromatic carboxylic acid ester, such as cyclohexane dimethanol dibenzoate. The average particle size of the first powdered plasticizer may be, for example, no greater than about 20 micrometers. In like manner, the second powdered plasticizer may be an aromatic carboxylic acid ester, such as cyclohexane dimethanol dibenzoate and may have an average particle size no greater than about 20 micrometers.

Finally, the present invention provides a coating composition which is an aqueous dispersion of a thermoplastic polymer having a glass transition temperature of at least about 30°C, a powdered plasticizer having a melting point of at least about 80°C, and a release agent. The weight ratio of thermoplastic polymer to powdered plasticizer is in a range of from about 80:20 to about 40:60, on a dry weight basis, and the release agent is present in a range of from about 0.5 to about 10 percent by weight, on a dry weight basis, based on the weight of coating solids. The aqueous dispersion contains from about 10 to about 50 percent by weight solids.

By way of example, the thermoplastic polymer may have a glass transition temperature of at least about 40°C. As another example, the thermoplastic polymer may be a vinyl chloride-acrylate copolymer. As a further example, the powdered plasticizer may be an aromatic carboxylic acid ester, such as cyclohexane dimethanol dibenzoate. As a further example, the average particle size of the powdered plasticizer may be no greater than about 20 micrometers.

The present invention is further described by the examples which follow. Such examples, however, are not to be construed as limiting in any way either the spirit or the scope of the present invention.

## Examples

The substrates employed in the examples were Kimdura<sup>®</sup> FPG-150 synthetic paper from Oji-Yuka Paper Company, a 4-mil, white opaque polyester film (Grade 339/380 from Imperial Chemical Industries of Great Britain), and another synthetic paper, Kimdura<sup>®</sup> QBZ180. These are referred to hereinafter as Substrates 1, 2 and 3, respectively (or S-1, S-2, and S-3).

Several different coating compositions also were utilized. These are identified below.

### Coating Composition 1 (C-1)

This coating composition was a 50/50 blend on a dry weight basis of Vycar<sup>®</sup> 352 and Benzoflex<sup>®</sup> 352. Vycar<sup>®</sup> 352 is a 56 percent total solids latex dispersion of a vinyl chloride-acrylate copolymer having a glass transition temperature of 69°C (B. F. Goodrich Company, Cleveland OH). Benzoflex<sup>®</sup> 352 is cyclohexane dimethanol dibenzoate from Velsicol Chemical Corp. (). The flake form of the material was ground to an average particle size of 10 micrometers. In this form it dispersed easily in water containing 3 parts on a dry weight basis of a polyethoxylated octylphenol, Triton X-100 (Rohm and Haas Company, Philadelphia, PA) per 100 parts of the Benzoflex<sup>®</sup> 352; the resulting dispersion contained 33 percent solids.

### Coating Composition 2 (C-2)

Coating Composition 2 was a 46.5/46.5/7 blend on a dry weight basis of Vycar<sup>®</sup> 352, Benzoflex<sup>®</sup> 352, and Dow Corning 190 silicone, a release agent.

### Coating Composition 3 (C-3)

Coating Composition 3 was a 62/31/7 blend on a dry weight basis of Vycar<sup>®</sup> 352, Benzoflex<sup>®</sup> 352, and Dow Corning 190 silicone.

### Coating Composition 4 (C-4)

This coating composition consisted of Michem<sup>®</sup> Prime 4983.

### Coating Composition 5 (C-5)

This coating composition was a 100/50/25/10/5 blend of Vycar<sup>®</sup> 352, Kronitex<sup>®</sup> 100, Michem<sup>®</sup> Prime 4983, calcium stearate (Nopcote<sup>®</sup> C-104, Henkle Corporation, Ambler, PA)), and Xama<sup>®</sup> 7. Kronitex<sup>®</sup> 100 is an aryl phosphate liquid plasticizer (FMC Corporation). Xama<sup>®</sup> 7 is a multifunctional aziridine crosslinker (Sancor Industries, Leomaster, MA).

A substrate was coated with one or more coatings, by means of a Meyer rod, with drying between coats as necessary. The resulting materials are summarized in Table 1.

**Table 1**  
**Summary of Dye Diffusion Substrates**

Ex.	Substrate	1st Coating		2nd Coating		3rd Coating	
		Code	Wt. <sup>a</sup>	Code	Wt. <sup>a</sup>	Code	Wt. <sup>a</sup>
1	A	C-1	2.0	N/P <sup>b</sup>	N/P	N/P	N/P
2	A	C-2	2.0	N/P	N/P	N/P	N/P
3	A	C-1	2.0	C-2	2.0	N/P	N/P
4	A	C-1	2.0	C-3	2.0	N/P	N/P
5	A	C-1	2.0	C-3	2.8	N/P	N/P
6	A	C-4	6.0	C-1	2.0	C-3	2.8
7	B	C-1	2.0	C-3	2.8	N/P	N/P
8	C	C-5	2.5	N/P	N/P	N/P	N/P
<sup>a</sup> Coating weight in grams per square meter.							
<sup>b</sup> Not present.							

Each substrate was printed with a multicolored test pattern with three or more color gradations in each color. The resulting patterns were cut into approximately 3-inch by 2-inch (about 7.6-cm x about 5-cm) rectangles and taped to laser mugs from RPL. The mug press used was the RPL model. Transfer to the mugs was carried out at 275°F (about 135°C) for three minutes, except for Example 7. The printing and mug transfer results are summarized in Table 2.

**Table 2**  
**Printing and Mug Transfer Results**

Example	Print Test	Transfer Test
1	Dark printing, ribbon sticking	Good transfer, mug sticking; film left on mug
2	Coating removed from substrate (poor adhesion)	
3	Good, dark print	Excellent
4	Very good - slightly grainy	Very good
5	Very good - slightly grainy	Very good
6	Excellent	Fair, lighter than Examples 5 & 9
7	Fair - voids due to dust	Good (204°C, 1 minute)
8	Yellowing in light areas, ribbon smudges in nonprint areas	Poor

The utility of a release agent in a single coating was demonstrated by Examples 1 and 2, even though the coating had not been optimized. Examples 3-5 showed the improved results which may be obtained with two coatings, in which the first coating did not contain a release agent. Three coatings may be employed, if desired, as shown by Example 6; the first coating in this example was a primer, which provides better print quality. The problem caused by static charge accumulation with a film was illustrated by Example 7, although printing and transferring of the printed image were otherwise good.

The excellent mug transfer results at only 135°C were very surprising, as were the very good to excellent dark prints. The results seen with Example 8 were more typical of prior art materials. The transfer material used in that example generally is not suitable for mug transfers because of ink smudging and poor transfer of the image to the mug.

Also surprising was the ease of making water-based coatings using the fine, powdered plasticizer as described in the examples. Liquid plasticizers give problems in making stable coatings and using the coatings made therewith.

While the specification has been described in detail with respect to specific embodiments thereof, it will be appreciated by those skilled in the art, upon attaining an understanding of the foregoing, may readily conceive of alterations to, variations of, and equivalents to these embodiments. Accordingly, the scope of the present invention should be assessed as that of the appended claims and any equivalents thereto.

## WHAT IS CLAIMED IS:

1. A coating suitable for receiving an image by dye diffusion printing comprising:

a thermoplastic polymer having a glass transition temperature of at least about 30°C;

a powdered plasticizer having a melting point of at least about 80°C; and

a release agent;

wherein:

the weight ratio of thermoplastic polymer to powdered plasticizer is in a range of from about 80:20 to about 40:60; and

the release agent is present in a range of from about 0.5 to about 10 percent by weight, based on the weight of the dried coating.

2. The coating of Claim 1, in which the thermoplastic polymer has a glass transition temperature of at least about 40°C.

3. The coating of Claim 2, in which the thermoplastic polymer is a vinyl chloride-acrylate copolymer.

4. The coating of Claim 1, in which the powdered plasticizer is an aromatic carboxylic acid ester.

5. The coating of Claim 4, in which the powdered plasticizer is cyclohexane dimethanol dibenzoate.

6. The coating of Claim 1, in which the average particle size of the powdered plasticizer is no greater than about 20 micrometers.

7. A coated substrate suitable for receiving an image by dye diffusion printing comprising:

a flexible first layer having first and second surfaces and selected from the group consisting of films, fibrous sheet-like materials, and combinations thereof; and

a second layer overlaying the first surface of the first layer, which second layer comprises a thermoplastic polymer having a glass transition temperature of at least

about 30°C, a powdered plasticizer having a melting point of at least about 80°C, and a release agent;

wherein:

the first layer has a basis weight of from about 50 to about 200 grams per square meter;

the second layer has a basis weight of from about 0.5 to about 10 grams per square meter;

the weight ratio of thermoplastic polymer to plasticizer is in a range of from about 80:20 to about 40:60; and

the release agent is present in a range of from about 0.5 to about 10 percent by weight, based on the weight of the second layer.

8. The coated substrate of Claim 7, in which the thermoplastic polymer has a glass transition temperature of at least about 40°C.

9. The coated substrate of Claim 8, in which the thermoplastic polymer is a vinyl chloride-acrylate copolymer.

10. The coating of Claim 7, in which the powdered plasticizer is an aromatic carboxylic acid ester.

11. The coating of Claim 10, in which the powdered plasticizer is cyclohexane dimethanol dibenzoate.

12. The coated substrate of Claim 7, in which the average particle size of the powdered plasticizer is no greater than about 20 micrometers.

13. The coated substrate of Claim 7, in which the first layer is a film.

14. The coated substrate of Claim 7, in which the first layer is a fibrous sheet-like material.

15. A coated substrate suitable for receiving an image by dye diffusion printing comprising:



a flexible first layer having first and second surfaces and selected from the group consisting of films, fibrous sheet-like materials, and combinations thereof;

a second layer overlaying the first surface of the first layer, which second layer comprises a first thermoplastic polymer having a glass transition temperature of at least about 30°C and a first powdered plasticizer having a melting point of at least about 80°C; and

a third layer overlaying the second layer, which third layer comprises a second thermoplastic polymer having a glass transition temperature of at least about 30°C, a second powdered plasticizer having a melting point of at least about 80°C, and a release agent;

wherein:

the first layer has a basis weight of from about 50 to about 200 grams per square meter;

the second layer has a basis weight of from about 0.5 to about 10 grams per square meter;

the third layer has a basis weight of from about 0.5 to about 10 grams per square meter;

the weight ratio of first thermoplastic polymer to first powdered plasticizer is in a range of from about 80:20 to about 40:60;

the weight ratio of second thermoplastic polymer to second powdered plasticizer is in a range of from about 80:20 to about 40:60; and

the release agent is present in the third layer in a range of from about 0.5 to about 10 percent by weight, based on the weight of the third layer.

16. The coated substrate of Claim 15, in which the first thermoplastic polymer has a glass transition temperature of at least about 40°C.

17. The coated substrate of Claim 16, in which the first thermoplastic polymer is a vinyl chloride-acrylate copolymer.

18. The coated substrate of Claim 15, in which the second thermoplastic polymer has a glass transition temperature of at least about 40°C.

19. The coated substrate of Claim 18, in which the second thermoplastic polymer is a vinyl chloride-acrylate copolymer.

20. The coating of Claim 15, in which the first powdered plasticizer is an aromatic carboxylic acid ester.

21. The coating of Claim 20, in which the first powdered plasticizer is cyclohexane dimethanol dibenzoate.

22. The coated substrate of Claim 15, in which the average particle size of the first powdered plasticizer is no greater than about 20 micrometers.

23. The coating of Claim 15, in which the second powdered plasticizer is an aromatic carboxylic acid ester.

24. The coating of Claim 23, in which the second powdered plasticizer is cyclohexane dimethanol dibenzoate.

25. The coated substrate of Claim 15, in which the average particle size of the second powdered plasticizer is no greater than about 20 micrometers.

26. The coated substrate of Claim 15, in which the first layer is a film.

27. The coated substrate of Claim 15, in which the first layer is a fibrous sheet-like material.

28. A coating composition comprising an aqueous dispersion of:  
a thermoplastic polymer having a glass transition temperature of at least about 30°C;

a powdered plasticizer having a melting point of at least about 80°C; and  
a release agent;

wherein:

the weight ratio of thermoplastic polymer to powdered plasticizer is in a range of from about 80:20 to about 40:60;

the release agent is present in a range of from about 0.5 to about 10 percent by weight, based on the weight of dry coating composition; and

the aqueous dispersion contains from about 10 to about 50 percent by weight solids.

29. The coating composition of Claim 28, in which the thermoplastic polymer has a glass transition temperature of at least about 40°C.

30. The coating composition of Claim 29, in which the thermoplastic polymer is a vinyl chloride-acrylate copolymer.

31. The coating composition of Claim 28, in which the powdered plasticizer is an aromatic carboxylic acid ester.

32. The coating composition of Claim 31, in which the powdered plasticizer is cyclohexane dimethanol dibenzoate.

33. The coating composition of Claim 31, in which the average particle size of the powdered plasticizer is no greater than about 20 micrometers.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/05017

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> IPC 6 B41M5/00		
According to International Patent Classification (IPC) or to both national classification and IPC		
<b>B. FIELDS SEARCHED</b>		
Minimum documentation searched (classification system followed by classification symbols) IPC 6 B41M C08K		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 699 800 A (NAT STARCH CHEM INVEST) 6 March 1996 see page 2, line 25 - line 30 see page 3, line 28 - line 29 ---	1,2,5-8, 11,12
X	EP 0 469 564 A (FULLER H B LICENSING FINANC) 5 February 1992 see page 6, line 50 - line 55 see page 7, line 36 - line 38 see table I ---	1,2,5,6
X	US 5 091 454 A (ARENDT WILLIAM D) 25 February 1992 see table I see the whole document ---	1,5,6
--- -/--		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.		
<input checked="" type="checkbox"/> Patent family members are listed in annex.		
° Special categories of cited documents :		
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention	
"E" earlier document but published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone	
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.	
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family	
"P" document published prior to the international filing date but later than the priority date claimed		
Date of the actual completion of the international search  <p style="text-align: center; font-weight: bold;">22 June 1998</p>	Date of mailing of the international search report  <p style="text-align: center; font-weight: bold;">06/07/1998</p>	
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer  <p style="text-align: center; font-weight: bold;">Martins Lopes, L</p>	

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 98/05017

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 242 739 A (KRONZER FRANCES J ET AL) 7 September 1993 see examples see the whole document -----	1-33
A	EP 0 523 511 A (AGFA GEVAERT AG) 20 January 1993 see page 5, line 51 - line 55 see page 5, line 1 - line 8 see the whole document -----	1-33

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/05017

Patent document cited in search report	A	Publication date	Patent family member(s)	Publication date
EP 0699800	A	06-03-1996	CA 2156658	01-03-1996
			JP 8081897	26-03-1996
EP 0469564	A	05-02-1992	WO 9202348	20-02-1992
			AT 145582	15-12-1996
			AU 636237	22-04-1993
			AU 8149891	06-02-1992
			CA 2048151	02-02-1992
			DE 9116662	19-05-1993
			DE 69123301	09-01-1997
			DE 69123301	19-06-1997
			DK 469564	12-05-1997
			EP 0649718	26-04-1995
			ES 2097773	16-04-1997
			FI 913652	02-02-1992
			HU 66670	28-12-1994
			IE 76733	05-11-1997
			JP 2543273	16-10-1996
			JP 4294718	19-10-1992
			LV 10406	20-02-1995
RU 2096277	20-11-1997			
US 5257491	02-11-1993			
US 5091454	A	25-02-1992	US 5026756	25-06-1991
			AU 4221289	05-03-1990
			CA 1335122	04-04-1995
			DE 68914994	01-06-1994
			DE 68914994	06-10-1994
			EP 0427792	22-05-1991
			JP 2605156	30-04-1997
			JP 4501279	05-03-1992
			WO 9001525	22-02-1990
US 5242739	A	07-09-1993	CA 2070730	26-04-1993
EP 0523511	A	20-01-1993	DE 4123919	21-01-1993
			DE 59203729	26-10-1995
			JP 5193276	03-08-1993
			US 5317000	31-05-1994